



US007557391B2

(12) **United States Patent**
Koo et al.

(10) **Patent No.:** **US 7,557,391 B2**
(45) **Date of Patent:** **Jul. 7, 2009**

(54) **ORGANIC LIGHT-EMITTING DISPLAY DEVICE**

(56) **References Cited**

U.S. PATENT DOCUMENTS

(75) Inventors: **Young-Mo Koo**, Suwon-si (KR);
Ok-Keun Song, Suwon-si (KR); **Hye-In Jeong**, Suwon-si (KR); **Tae-Shick Kim**, Suwon-si (KR); **Jae-Goo Lee**, Suwon-si (KR)

2005/0012094 A1* 1/2005 Park 257/40
2006/0204788 A1* 9/2006 Yoshikawa 428/690

* cited by examiner

(73) Assignee: **Samsung Mobile Display Co., Ltd.**, Yongin (KR)

Primary Examiner—Cuong Q Nguyen
Assistant Examiner—Cathy N Lam
(74) *Attorney, Agent, or Firm*—Stein McEwen, LLP

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 163 days.

(57) **ABSTRACT**

An organic light-emitting display device wherein an IR drop across a first electrode can be prevented. The organic light-emitting display device includes a substrate; a plurality of stripe-shaped first electrodes disposed on the substrate and extending in a first direction; a plurality of stripe-shaped first insulators extending in a second direction to cross the stripe-shaped first electrodes; a plurality of stripe-shaped second electrodes disposed between the stripe-shaped first insulators to extend in the same direction as the stripe-shaped first insulators and cross the stripe-shaped first electrodes; an intermediate layer disposed at positions where the stripe-shaped first electrodes and the stripe-shaped second electrodes cross and including an emission layer; and first conductors disposed at positions where the stripe-shaped first electrodes and the stripe-shaped first insulators intersect and between the stripe-shaped first electrodes and the stripe-shaped first insulators.

(21) Appl. No.: **11/755,095**

(22) Filed: **May 30, 2007**

(65) **Prior Publication Data**

US 2007/0295959 A1 Dec. 27, 2007

(30) **Foreign Application Priority Data**

Jun. 7, 2006 (KR) 10-2006-0050868

(51) **Int. Cl.**
H01L 51/50 (2006.01)

(52) **U.S. Cl.** **257/232; 257/79; 257/431; 257/749; 257/E51.001; 257/E51.018**

(58) **Field of Classification Search** **257/79-93, 257/232, 431-432, 749, E51.001, E51.018**
See application file for complete search history.

20 Claims, 3 Drawing Sheets




FIG. 1 (CONVENTIONAL ART)




FIG. 2 (CONVENTIONAL ART)




FIG. 3




FIG. 4




FIG. 5





FIG. 6



ORGANIC LIGHT-EMITTING DISPLAY DEVICE

CROSS-REFERENCE TO RELATED PATENT APPLICATIONS

This application claims the benefit of Korean Patent Application No. 2006-50868, filed Jun. 7, 2006, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

Aspects of the present invention relate to an organic light-emitting display device, and more particularly to an organic light-emitting display device wherein an IR drop (voltage drop) across first electrodes is prevented.

2. Description of the Related Art

Various flat panel display devices including passive matrix organic light-emitting display devices have recently been developed to meet the need for slimmer and larger-screen display devices. An example image display unit **20** of a passive matrix organic light-emitting display device is shown in FIG. 1.

Referring to FIG. 1, the image display unit **20** includes stripe-shaped first electrodes **21** extending in a Y direction, stripe-shaped second electrodes **22** extending in an X direction to cross the stripe-shaped first electrodes **21**, and an intermediate layer **24** disposed between the first electrodes **21** and the second electrodes **22**. As shown in FIG. 1, the intermediate layer **24** is disposed to cover the first electrodes **21**; and, the second electrodes **22** are disposed on the intermediate layer **24**. The intermediate layer **24** includes at least an emission layer in which holes combine with electrons to generate light. The first and second electrodes **21** and **22** intersect to form pixels, which are arranged to emit light and form images. The holes are supplied to the intermediate layer **24** from one of the first electrodes **21** and the second electrodes **22**, and the electrons are supplied to the intermediate layer **24** by the other of the first electrodes **21** and the second electrodes **22**.

As described in connection with FIG. 1, the passive matrix organic light-emitting display device includes stripe-shaped electrodes. Methods of forming stripe-shaped electrodes include a method using deposition on an entire surface and lithography, an ink jet printing method, a deposition method using a mask, and the like. However, the method using deposition on an entire surface and lithography involves complex processes, such as deposition, photoresist coating, patterning, and etching, etc. Furthermore, the intermediate layer **24** may be damaged during the formation of the stripe-shaped second electrodes **22**, which are formed after and on the intermediate layer **24**. In contrast, the ink jet printing method is time consuming when applied to a large area.

To address these and/or other problems, a method using a separator has been suggested. FIG. 2 is a sectional view schematically illustrating a portion of a conventional organic light-emitting display device in which second electrodes **22** are formed to be stripe-shaped using second electrode separators **31**.

Referring to FIG. 2, stripe-shaped first electrodes **21** are formed on a substrate **10** using a conventional method to extend in a first direction, i.e., a Y direction. And, the second electrode separators **31** are formed to extend in a second direction, i.e., an X direction, and to cross the stripe-shaped first electrodes **21**. Next, an intermediate layer **24** is formed to cover the first electrodes **21**. Then, the second electrodes **22** are formed on the entire surface of the intermediate layer **24**.

During application of the intermediate layer **24** and the second electrodes **22**, a portion **24a** of the intermediate layer **24** and a portion **22a** of the second electrodes **22** are formed on the second electrode separators **31**. So, when forming the second electrodes **22** on the entire surface of the intermediate layer **24**, a portion **22a**, which is the same as the material used to form the second electrodes **22**, is also deposited on the upper surface of the second electrode separators **31**. As the portion **22a** of the second electrodes **22** is physically separated from the second electrodes **22** by the height of the second electrode separators **31** and because the portion **22a** does not contact the second electrodes **22**, the second electrodes **22** are accordingly formed to be stripe-shaped. A portion of the intermediate layer **24** can also be formed by deposition and the material forming the intermediate layer **24** can be deposited on the upper surface of the second electrode separators **31** (referring to the portion **24a**).

However, the stripe-shaped first electrodes **21** have a high electrical resistance when they are formed of a transparent material. In particular, the IR drop across the stripe-shaped first electrodes **21** increases as the size of a screen of the organic light-emitting display device and brightness are increased. Thus, organic light-emitting display devices suffer from problems such as increased power consumption and reduced life span.

SUMMARY OF THE INVENTION

Several aspects and example embodiments of the present invention provide an organic light-emitting display device wherein an IR drop (voltage drop) across first electrodes is prevented.

In accordance with an example embodiment of the present invention, there is provided an organic light-emitting display device including: a substrate; first electrodes disposed on the substrate and extending in a first direction; first insulators extending in a second direction to cross the first electrodes; second electrodes disposed between the first insulators to extend in the same direction as the first insulators and cross the first electrodes; an intermediate layer disposed at positions between the first electrodes and the second electrodes where the first and second electrodes cross and including an emission layer; and first conductors disposed at positions where the first electrodes and the first insulators cross and disposed between the first electrodes and the first insulators.

According to an aspect of the present invention, the first conductors can be formed of Cr, Mg, Ag, Mo, MoW or Al. A terminal unit can further be included in edges of the substrate. Terminals of the terminal unit can be formed of the same material as the first conductors. The terminals of the terminal unit can have a multi-layer structure including at least two layers. The terminals of the terminal unit can include a first layer which is formed of the same material as the first electrodes and a second layer which is formed of the same material as the first conductors.

According to an aspect of the present invention, the first insulators can be formed so as to cover the first conductors. Second insulators are disposed between the first electrodes can further be included. The first insulators and the stripe-shaped second insulators can be integrally formed as one body. The first electrodes can be transparent electrodes. The first electrodes can be formed of ITO, IZO, ZnO or In₂O₃. Second conductors can further be included disposed on the first insulators wherein the second conductors are formed of the same material as the second electrodes.

Additional aspects and/or advantages of the invention will be set forth in part in the description which follows and, in part, will be obvious from the description, or may be learned by practice of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects and advantages of the invention will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings of which:

FIG. 1 is a schematic plan view illustrating an image display unit of a conventional organic light-emitting display device;

FIG. 2 is a schematic sectional view illustrating a portion of another conventional organic light-emitting display device;

FIG. 3 is a schematic sectional view illustrating a portion of an organic light-emitting display device according to aspects of the present invention;

FIG. 4 is a schematic plan view illustrating a portion of the organic light-emitting display device of FIG. 3;

FIG. 5 is a schematic plan view illustrating a portion of an organic light-emitting display device according to aspects of the present invention; and

FIG. 6 is a schematic plan view illustrating a portion of an organic light-emitting display device according to aspects of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Reference will now be made in detail to the present embodiments of the present invention, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to the like elements throughout. The embodiments are described below in order to explain the present invention by referring to the figures.

FIG. 3 is a schematic sectional view illustrating a portion of an organic light-emitting display device according to aspects of the present invention, and FIG. 4 is a schematic plan view illustrating the portion of the organic light-emitting display device illustrated in FIG. 3.

Referring to FIGS. 3 and 4, a plurality of first electrodes 121 having a stripe shape or elongated, strip shape and extending in a Y direction are disposed on a substrate 110. The substrate 110 can be formed of a transparent glass material or a plastic material such as acryl, polyimide, polyester, Mylar®, etc.

The first electrodes 121 are formed of a transparent conductive material through which light can be transmitted, such as ITO, IZO, ZnO or In₂O₃.

A plurality of first insulators 131, having a stripe shape or elongated, strip shape, are formed to extend in an X direction and to cross the first electrodes 121. The first insulators 131 can function as second electrode separators (31 of FIGS. 1 and 2) to allow for easy formation of the second electrodes 122 on the surface of an intermediate layer 124. Hereinafter, the first insulators 131 function as the second electrode separators as the first insulators 131 provide the stripe or elongated band shape of the second electrodes 122. FIG. 4 schematically shows a portion of the organic light-emitting display device according to aspects of the present invention including the first electrodes 121 and the first insulators 131 on the substrate 110.

When a conductive material is deposited on the entire surface of the substrate 110 to form second electrodes, a plurality of second electrodes 122 having a stripe shape or elongated, strip shape are formed to cross the first electrodes 121 by the first insulators 131 which separate the second electrodes 122 into long, elongated stripe shapes and act as second electrode separators (31 of FIGS. 1 and 2). Therefore, the second electrodes 122 are formed between the first insulators 131 illustrated in FIG. 4 and extend in the same direction as the first insulators 131, that is, the X direction. When depositing the conductive material on the entire surface of the

substrate 110 to form the second electrodes 122, the conductive material is also deposited on the first insulators 131, which separate the second electrodes 122 into elongated, stripe shapes. Thus, as described in FIG. 3, second conductors 122a, which are formed of the same material as the second electrodes 122, can also be disposed on the second intermediate layer 124a and formed on the first insulators 131. It will be known to those of ordinary skill in the art that deposition of the conductive material on the entire surface of the substrate 110 to form the second electrodes 122 can also be performed using a mask so as to not form the conductive material on the first insulators 131.

The second electrodes 122 can be formed of a transparent conductive material or an opaque conductive material according to necessity. Transparent conductive materials such as ITO, IZO, ZnO or In₂O₃ can be used to form the second electrodes 122. When the second electrodes 122 are formed using an opaque conductive material, the structure can include a reflection membrane, which is formed of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, compounds thereof, etc., and an ITO, ZnO or In₂O₃ layer, which is formed on the reflection membrane.

Pixels or sub-pixels are formed where the first electrodes 121 and the second electrodes 122 intersect. For this, as described in FIG. 3, an intermediate layer 124 is disposed where the first electrodes 121 and the second electrodes 122 intersect, and the intermediate layer 124 includes at least one emission layer. The intermediate layer 124 receives holes and electrons from the first electrodes 121 and the second electrodes 122 which combine to generate light. As such, the intermediate layer 124 is disposed between the first and second electrodes 121 and 122 where the first and second electrodes 121 and 122 intersect.

The intermediate layer 124, which includes at least one emission layer and can be formed of an organic substance or an inorganic substance. The organic substance can be a small-molecular organic substance or a polymeric organic substance.

When using a small-molecular organic substance, the intermediate layer 124 can be a single layer or multi-layer structure including a hole injection layer, a hole transport layer, an emission layer, an electron transport layer, an electron injection layer, etc., where various organic materials such as copper phthalocyanine (CuPc), N,N'-Di(naphthalene-1-yl)-N,N'-diphenyl-benzidine (NPB), tris-8-hydroxyquinoline aluminium (Alq3), etc. can be used. The intermediate layer 124 can be formed using various methods, such as a deposition method.

When the intermediate layer 124 is formed of a polymeric organic substance, the intermediate layer 124 can usually have a structure including a hole transport layer and an emission layer, where PEDOT is used as a hole transport layer and a polymeric organic substance such as poly-phenylenevinylene (PPV) polymers or polyfluorene polymers can be used as an emission layer.

Meanwhile, when the electrical resistance of the first electrodes 121 is high, different electrical signals are applied to each sub-pixel connected to the first electrodes 121, depending upon the position of each sub-pixel. The different electrical signals applied to each sub-pixel are due to the IR drop across the first electrodes 121. As a result, the same electrical signal is not applied to each sub-pixel according to the position thereof. This causes deterioration in image quality, such as uneven brightness. In particular, the IR drop across the first electrodes 121 becomes increasingly problematic as the size and the brightness of the display are increased.

Therefore, in the organic light-emitting display device according to aspects of the present invention, the first conductors 121a, which are disposed where the first electrodes 121 and the first insulators 131 intersect, are included

between the first electrodes **121** and the first insulators **131** so that the IR drop across the first electrodes **121** can be decreased or prevented. The first conductors **121a**, which are formed of a material having low electrical resistance, are disposed in area outside the sub-pixels. As there is no light generated outside of the sub-pixels, the first conductors **121a** do not need to be transparent. The first conductors **121a** allow the organic light-emitting display device to display high-quality images on a large screen and with high brightness.

The first conductors **121a** can be formed of Cr, Mg, Ag, Mo, MoW or Al. However, the first conductors are not limited thereto, and the first conductors **121a** can be formed of other conductive materials having low electrical resistance.

The organic light-emitting display device can include a terminal unit (not shown) in or at the edges of the substrate **110**. One side of the terminal unit is electrically connected to the first electrodes **121** or the second electrodes **122**, and another side of the terminal unit is electrically connected to a printed circuit board (PCB) on which a controller IC, a drive IC, a jumper IC, etc are installed, and thus the terminal unit controls electric signals which are applied to the first electrodes **121** and the second electrodes **122**. The controller IC and the like can be included on the substrate **110** without requiring the PCB.

The terminals of the terminal unit are formed of a conductive material; therefore the first conductors **121a** and the terminals of the terminal unit can be formed in the same process. In such case, the terminals of the terminal unit are formed of the same material as the first conductors **121a**.

Further, the terminals of the terminal unit can have a multi-layer structure including at least two layers, wherein a first layer and the first electrodes **121** can be formed in the same process and a second layer and the first conductors **121a** can be formed in the same process. In such case, the terminals of the terminal unit include a layer which is formed of the same material as the first electrodes **121** and another layer which is formed of the same material as the first conductors **121a**.

Likewise, the first conductors **121a** can be formed at the same time as the terminals of the terminal unit. Accordingly, the performance of the organic light-emitting display device can be improved without additional processes or equipment.

FIG. **5** is a schematic plan view illustrating a portion of an organic light-emitting device according to aspects of the present invention. Like the depiction in FIG. **4**, second electrodes and an intermediate layer are not illustrated in FIG. **5**.

Referring to FIG. **5**, a plurality of second insulators **132** can further be included between first electrodes **121**. The second insulators **132** extend in the same direction, that is, a Y direction, in which the first electrodes **121** extend as illustrated in FIG. **5**. In particular, in the organic light-emitting device illustrated in FIG. **5**, first insulators **131** extending in an X direction and the second insulators **132** extending in the Y direction are integrally formed as one body, but the first and second insulators **131** and **132** are not limited thereto. Further, both the first and second insulators **131** and **132** may be formed to a height extending away from the surface of the substrate **110**, or one or both of the first and second insulators **131** and **132** may be formed as having a stripe or elongated, strip shape.

In the structure as illustrated in FIG. **5**, pixels or sub-pixels are formed at each point of the first electrodes **121** not covered by the first insulators **131** or the second insulators **132**. In this case also, first conductors **121a** can be formed at positions where the first electrodes **121** and the first insulators **131** intersect so that an IR drop across the first electrodes **121** can be prevented. As such, the first electrodes **121** are disposed to extend across a surface of a substrate **110**. The first insulators **131** are disposed on the surface of the substrate **110** and formed to cross the first electrodes **121**. Further, the second insulators **132** are formed between adjacent first electrodes

121 and therefore have an elongated strip shape. The intermediate layer **124** and the second electrodes **122** are formed to cross the first electrodes **121** between the first insulators. As such, the second electrodes **122** have an elongated, stripe shape. Pixels are formed at the intersection of the first and second electrodes **121** and **122** in which neither the first nor the second insulators are formed. Further, the first conductors **121a** are disposed on the first electrodes **121**, covered by the first insulators **131**, and formed between the pixels.

FIG. **6** is a schematic sectional view illustrating a portion of an organic light-emitting display device according to aspects of the present invention. While the organic light-emitting display devices according to aspects of the present invention have a structure in which the first insulators **131** cover the first conductors **121a** as illustrated in FIGS. **3** and **4**, referring to FIG. **6**, the end surfaces of first conductors **121a** may not be covered with first insulators **131** but may be exposed. As such, the first conductors **121a** are formed on the first electrodes **121**, and the first insulators are formed to cross the first electrodes **121** at the first conductors **121a**. And, the first insulators **131** cover, but not entirely, the first conductors **121a**. Further, second conductors **122a**, which are formed of the same material as the second electrodes **122**, can also be disposed on the second intermediate layer **124a** and formed on the first insulators **131**.

However, the organic light-emitting display device is not limited to the above descriptions. For example, the second electrodes **122** of FIG. **3** may also comprise conductors disposed thereon to decrease the resistance and IR drop along the length of the second electrodes and increase display quality of the organic light-emitting display device. Further, the conductors disposed on the second electrodes **122** may be located in non-pixel areas between adjacent pixels along the length of the second electrodes **122**.

Effects of the organic light-emitting display device according to aspects of the present invention are described below.

First, an IR drop across first electrodes can be prevented and thus the performance of the organic light-emitting display device can be largely improved by forming conductors having low electric resistance in outer spaces of each pixel or sub-pixel on the first electrodes.

Second, the performance of the organic light-emitting display device can be largely improved without additional processing by forming the conductors, which prevent an IR drop across the first electrodes, at the same time as forming terminals of a terminal unit and the like.

Although a few embodiments of the present invention have been shown and described, it would be appreciated by those skilled in the art that changes may be made in this embodiment without departing from the principles and spirit of the invention, the scope of which is defined in the claims and their equivalents.

What is claimed is:

1. An organic light-emitting display device comprising:
 - a substrate;
 - first electrodes disposed on the substrate and extending in a first direction;
 - first insulators extending in a second direction to cross the first electrodes;
 - second electrodes disposed between the first insulators to extend in the same direction as the first insulators and to cross the first electrodes;
 - an intermediate layer comprising an emission layer is disposed between the first electrodes and the second electrodes where the first electrodes and the second electrodes cross; and
 - first conductors disposed at positions where the first electrodes and the first insulators cross and disposed between the first electrodes and the first insulators.

7

2. The organic light-emitting display device of claim 1, wherein the first conductors are formed of Cr, Mg, Ag, Mo, MoW or Al.

3. The organic light-emitting display device of claim 1, further comprising:

a terminal unit on edges of the substrate.

4. The organic light-emitting display device of claim 3, wherein terminals of the terminal unit are formed of the same material as the first conductors.

5. The organic light-emitting display device of claim 3, wherein the terminals of the terminal unit have a multi-layer structure comprising at least two layers.

6. The organic light-emitting display device of claim 5, wherein the terminals of the terminal unit comprise a first layer which is formed of the same material as the first electrodes and a second layer which is formed of the same material as the first conductors.

7. The organic light-emitting display device of claim 1, wherein the first insulators are formed so as to cover the first conductors.

8. The organic light-emitting display device of claim 1, further comprising

second insulators disposed between the first electrodes.

9. The organic light-emitting display device of claim 8, wherein the first insulators and the second insulators are integrally formed.

10. The organic light-emitting display device of claim 1, wherein the first electrodes are transparent.

11. The organic light-emitting display device of claim 10, wherein the first electrodes are formed of ITO, IZO, ZnO or In_2O_3 .

12. The organic light-emitting display device of claim 1, further comprising

second conductors disposed on the first insulators,

wherein the second conductors are formed of the same material as the second electrodes.

13. The organic light-emitting display device of claim 1, wherein the first and second electrodes and the first insulators have a stripe shape or an elongated, strip shape.

14. An organic light-emitting display device, comprising: a substrate; first electrodes disposed on the substrate to extend in a first direction;

8

second electrodes disposed on the substrate to extend in a second direction and to cross the first electrodes;

an intermediate layer disposed at least between the first and second electrodes at locations in which the first and second electrodes cross; and

first conductors disposed on the first electrodes at locations in which the first and second electrodes do not cross.

15. The organic light-emitting display device of claim 14, further comprising:

second conductors disposed on the second electrodes at locations in which the first and second electrodes do not cross.

16. The organic light-emitting display device of claim 14, further comprising:

insulators disposed between the first electrodes.

17. The organic light-emitting display device of claim 14, further comprising:

insulators disposed between the second electrodes.

18. An organic light-emitting display device, comprising: a substrate;

first electrodes disposed on the substrate to extend in a first direction;

first insulators disposed to cross the first electrodes in a second direction;

first conductors disposed between the first electrodes and the first insulators in locations in which the first electrodes and the first insulators cross;

an intermediate layer disposed between adjacent first insulators and on the first insulators; and

second electrodes disposed on the intermediate layer.

19. The organic light-emitting display device of claim 18, further comprising:

second insulators disposed between adjacent first electrodes and disposed between the substrate and the intermediate layer or the intermediate layer and the second electrodes.

20. The organic light-emitting display device of claim 18, further comprising:

second conductors disposed on the second electrodes at locations in which the first and second electrodes do not cross.

* * * * *

专利名称(译)	有机发光显示装置		
公开(公告)号	US7557391	公开(公告)日	2009-07-07
申请号	US11/755095	申请日	2007-05-30
申请(专利权)人(译)	三星SDI CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KOO YOUNG MO SONG OK KEUN JEONG HYE IN KIM TAE SHICK LEE JAE GOO		
发明人	KOO, YOUNG-MO SONG, OK-KEUN JEONG, HYE-IN KIM, TAE-SHICK LEE, JAE-GOO		
IPC分类号	H01L51/50		
CPC分类号	H01L51/5212 H01L27/3288 H01L27/3283		
优先权	1020060050868 2006-06-07 KR		
其他公开文献	US20070295959A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光显示装置，其中可以防止跨越第一电极的IR降。有机发光显示装置包括基板；多个条形第一电极，设置在基板上并沿第一方向延伸；多个条形第一绝缘体沿第二方向延伸以与条形第一电极交叉；多个条形第二电极设置在条形第一绝缘体之间，以与条形第一绝缘体相同的方向延伸并与条形第一电极交叉；中间层，设置在条形第一电极和条形第二电极交叉的位置，并包括发光层；第一导体设置在条形第一电极和条形第一绝缘体交叉的位置处，并且设置在条形第一电极和条形第一绝缘体之间。

