



US008288944B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 8,288,944 B2**
(45) **Date of Patent:** **Oct. 16, 2012**

(54) **ORGANIC LIGHT-EMITTING DISPLAY
APPARATUS SEALED WITH A SEALANT
CONTAINING A FILLER**

(75) Inventors: **Jung-Min Lee**, Yongin (KR); **Tae-Wook Kang**, Yongin (KR); **Jang-Hwan Shin**, Yongin (KR); **Jin-Hwan Jeon**, Yongin (KR)

(73) Assignee: **Samsung Display Co., Ltd.**,
Giheung-Gu, Yongin, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 51 days.

(21) Appl. No.: **12/962,877**

(22) Filed: **Dec. 8, 2010**

(65) **Prior Publication Data**

US 2011/0140599 A1 Jun. 16, 2011

(30) **Foreign Application Priority Data**

Dec. 10, 2009 (KR) 10-2009-0122538

(51) **Int. Cl.**

H01L 51/50 (2006.01)

H05B 33/04 (2006.01)

(52) **U.S. Cl.** **313/512; 313/504**

(58) **Field of Classification Search** None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2009/0044496 A1* 2/2009 Botelho et al. 313/512
2009/0058292 A1* 3/2009 Koo et al. 313/512
2010/0270919 A1* 10/2010 Hubert et al. 313/512

FOREIGN PATENT DOCUMENTS

JP 2005322432 11/2005

OTHER PUBLICATIONS

Machine translation of Applicant Cited JP2005-322432A published Nov. 17, 2005.*

Korean Office Action issued by KIPO, dated Feb. 8, 2011, corresponding to Korean Patent Application No. 10-2009-0122538, together with Request for Entry.

* cited by examiner

Primary Examiner — Anh Mai

Assistant Examiner — Britt D Hanley

(74) *Attorney, Agent, or Firm* — Robert E. Bushnell, Esq.

(57) **ABSTRACT**

An organic light-emitting display apparatus including: a substrate; a display unit disposed on the substrate; an encapsulation substrate disposed on the display unit; and a sealant by which the substrate is combined with the encapsulation substrate and which includes a filler, wherein a height of the sealant is greater than a height of the filler.

12 Claims, 5 Drawing Sheets




FIG. 1 (RELATED ART)




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 5





FIG. 6



1

ORGANIC LIGHT-EMITTING DISPLAY APPARATUS SEALED WITH A SEALANT CONTAINING A FILLER

CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of Korean Patent Application No. 10-2009-0122538, filed on Dec. 10, 2009, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein by reference.

BACKGROUND

1. Field

The present disclosure relates to organic light-emitting display apparatuses that are resistant to the permeation of external impurities, such as oxygen and/or water vapor, and have enhanced impact resistance.

2. Description of the Related Art

Currently, thin-film portable flat panel display apparatuses are increasing in popularity. Among flat panel display apparatuses, electroluminescent display apparatuses are regarded as the next-generation of display apparatus, because they are self-emissive, have a wide viewing angle, a high contrast ratio, and a short response time. In addition, organic light-emitting display apparatuses, which include an organic emission layer, have a higher brightness, a lower driving voltage, and a shorter response time than inorganic light-emitting display apparatuses.

FIG. 1 is a cross-sectional view of a conventional organic light-emitting display apparatus. Referring to FIG. 1, a display unit 20 is disposed on a substrate 10, and an encapsulation substrate 30 is disposed over the display unit 20. The substrate 10 is combined with the encapsulation substrate 30, using a sealant 41.

An organic light-emitting device included in a flat panel display apparatus may be degraded by various internal and external factors. Such internal factors include the deterioration of an emission layer, due to oxygen from the indium tin oxide (ITO) of an electrode, and deterioration caused by a reaction between an emission layer and adjacent layers. Such external factors include the permeation of external water vapor, oxygen, and ultra violet rays, and device manufacturing conditions. In particular, external water vapor and oxygen greatly affect the lifetime of an organic light-emitting device. Thus, the packaging of an organic light-emitting device is very important.

However, as illustrated in the conventional organic light-emitting display apparatus of FIG. 1, when the substrate 10 is combined with the encapsulation substrate 30 using the sealant 41, impurities such as external oxygen and/or water vapor permeate through the sealant 41, particularly, through an interface between the sealant 41 and the encapsulation substrate 30, thereby damaging the display unit 20. In addition, the sealant 41 may be easily broken by impacts.

SUMMARY

The present disclosure provides an organic light-emitting display apparatus that is resistant to the permeation of external impurities, such as oxygen and/or water vapor, and has enhanced impact resistance.

According to an aspect of the present invention, there is provided an organic light-emitting display apparatus including: a substrate; a display unit disposed on the substrate; an encapsulation substrate disposed over the display unit; and a

2

sealant to attach the substrate to the encapsulation substrate. The sealant comprises a filler, and the height t_{frit} of the sealant is greater than the height d_{filler} of the filler.

According to various embodiments, a ratio of the height d_{filler} of the filler to the height t_{frit} of the sealant may be 0.75 or less.

According to various embodiments, the ratio of the height t_{frit} of the sealant to the height d_{filler} of the filler may be 0.5 or less.

According to various embodiments, the sealant may include a glass frit.

According to various embodiments, the filler may be disposed at the center of the sealant, equidistant from the substrate and the encapsulation substrate.

According to various embodiments, the filler may be cylindrical.

According to various embodiments, the sealant may be formed along edge portions of the encapsulation substrate.

Additional aspects and/or advantages of the invention will be set forth in part in the description which follows and, in part, will be obvious from the description, or may be learned by practice of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects and advantages of the present invention will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings of which:

FIG. 1 is a cross-sectional view of a conventional organic light-emitting display apparatus;

FIG. 2 is a schematic, partial plan view of an organic light-emitting display apparatus, according to an exemplary embodiment of the present invention;

FIG. 3 is a schematic cross-sectional view of the organic light-emitting display apparatus of FIG. 2;

FIG. 4A illustrates a filler disposed at the center of a sealant;

FIG. 4B illustrates a filler disposed near an encapsulation substrate;

FIG. 4C illustrates a filler disposed near a substrate;

FIG. 4D illustrates portions of fillers having various shapes;

FIG. 5 is a graph showing drop-impact experiment results of six display apparatuses having fillers located as shown in FIGS. 4A, 4B, and FIG. 4C, and the having the shapes illustrated in FIG. 4D; and

FIG. 6 is a partial, schematic cross-sectional view of the organic light-emitting display apparatus of FIG. 2.

DETAILED DESCRIPTION

Reference will now be made in detail to the exemplary embodiments of the present invention, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to the like elements throughout. The exemplary embodiments are described below, in order to explain the aspects of the present invention, by referring to the figures.

Herein, when a first element is referred to as being formed or disposed "on" a second element, the first element can be disposed directly on the second element, or one or more other elements may be disposed therebetween. When a first element is referred to as being formed or disposed "directly on" a second element, no other elements are disposed therebetween. In addition, when a first element is described as being "connected to" a second element, the first element may be

directly connected to the second element, or may be indirectly connected to the second element, via one or more intervening elements.

FIG. 2 is a schematic, partial plan view of an organic light-emitting display apparatus 10, according to an exemplary embodiment of the present invention, and FIG. 3 is a schematic cross-sectional view of the organic light-emitting display apparatus 10. Referring to FIGS. 2 and 3, an encapsulation substrate 300 included in the organic light-emitting display apparatus 10 of FIG. 3 is not shown in FIG. 2.

The apparatus 10 includes a display unit 200 disposed on a substrate 100. The substrate 100 may be formed of a transparent glass material including SiO₂ as a main ingredient. However the substrate 100 is not limited thereto. For example, the substrate 100 may also be formed of a transparent plastic material. The transparent plastic material for may be an insulating organic material such as polyethersulphone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylenenaphthalate (PEN), polyethyleneterephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide, polycarbonate (PC), cellulose tri acetate (TAC), or cellulose acetate propionate (CAP).

If the organic light-emitting display apparatus 10 is a bottom emission organic light-emitting display apparatus, in which an image is displayed through the substrate 100, the substrate 100 may be formed of a transparent material. However, if the organic light-emitting display apparatus 10 is a top emission organic light-emitting display apparatus, in which an image is displayed in a direction opposite to the substrate 100, the substrate 100 need not be formed of a transparent material. In the latter case, the substrate 100 may be formed of a metal. When the substrate 100 is formed of a metal, the substrate 100 may include at least one metal selected from the group consisting of carbon, iron, chromium, manganese, nickel, titanium, molybdenum, stainless steel (SUS), Invar alloy, Inconel alloy, and Kovar alloy. However, the substrate 100 may also include other materials. For example, the substrate 100 may be a metal foil.

Although not illustrated, a buffer layer (not shown) may be further formed on the substrate 100. The buffer layer may planarize the substrate 100 and prevent permeation of impurities.

The substrate 100 is combined with the encapsulation substrate 300, such that the encapsulation substrate 300 is disposed over the display unit 200. The encapsulation substrate 300 may also be a glass substrate or a plastic substrate such as an acrylic substrate. Furthermore, the encapsulation substrate 300 may be a metal substrate.

The substrate 100 is combined with the encapsulation substrate 300 using the sealant 410. The sealant 410 may surround the display unit 200. The sealant 410 may include a glass frit. A filler 411 is included in the sealant 410. The height d_{filler} of the filler 411 may be in a predetermined fraction of the height t_{frit} of the sealant 410. Herein, the heights t_{frit} and d_{filler} are taken in a direction perpendicular to the plane of the substrate 100.

In detail, the sealant 410 may be formed using a glass frit paste. The glass frit paste includes glass powder, the filler 411, and a liquid carrier. The glass powder is prepared by finely milling a glass that consists of four or more compounds. The glass powder is dry-milled, such that a particle diameter of the glass powder is within 20% of the height t_{frit} of the sealant 410, after sintering. In general, the height t_{frit} is in the range of about 3 to 30 μm . Thus, an average particle diameter of the glass powder may be in the range of about 0.6 to about 6 μm .

The substrate 100 and the encapsulation substrate 300 are generally formed of glass having a low coefficient of thermal

expansion (CTE), so as to maintain a constant pattern before and after a thermal process. Accordingly, the glass powder used to prepare the glass frit paste should also have a CTE that is similar to those of the substrate 100 and the encapsulation substrate 300.

The substrate 100 is attached to the encapsulation substrate 300, by locally melting the sealant 410. Thus, the sealant 410 may be a sealant that melts at low temperature and then smoothly flows and forms a strong mechanical bond between the substrate 100 and the encapsulation substrate 300. A sealant having such features generally has a high CTE, and a very low impact resistance, due to having weak intermolecular bonds. That is, even when very small impacts are applied to the sealant, the sealant 410 is very likely to crack.

The filler 411 compensates for the low impact resistance and high CTE of the sealant 410. The filler 410 may be, for example, a ceramic that is added to the glass powder when the glass frit paste is prepared. The filler 411 may be any filler that has a lower CTE than that of the glass powder. For example, the filler 411 may have a negative CTE, so as to have good structural stability and a low CTE. The addition of the filler 411 to the glass powder may improve mechanical properties, such as the Young's modulus, fracture toughness, etc., of the sealant 410.

However, when the filler 411 is too large, the inclusion of the filler 411 in the sealant 410 may otherwise result in breakage of a display apparatus including the same, when the display apparatus is dropped. In particular, stress may be focused on the filler 411, although mechanical strength of the display apparatus may be improved.

In detail, the impact resistance of the organic light-emitting display apparatus 10 was evaluated as follows. A panel was inserted into a test jig and then dropped onto a stone surface, from a height of 1.5 m or more. As a result, among defective panels, about 80% cracked at an interface of the sealant 410 and the substrate 100, or at an interface of the sealant 410 and the encapsulation substrate 300. In such cases, the sealant 410 was completely broken and the substrate 100 and the encapsulation substrate 300 also cracked. In regard to the panels in which cracks occurred at the interface of the sealant 410 and the substrate 100, or at the interface of the sealant 410 and the encapsulation substrate 300, cracks mostly originated from the larger fillers 411. That is, when impacts are applied to a panel by dropping, stress focuses more on the filler 411, as the height of the filler 411 is increased. In addition, cracks occur at the interface of the sealant 410 and the substrate 100, or the interface of the sealant 410 and the encapsulation substrate 300.

To solve these and/or other problems, the height, location, and/or shape of filler 411 may be appropriately set. Thus, the organic light-emitting display apparatus 10 may have an enhanced impact resistance. The structure of the filler 411 in the organic light-emitting display apparatus 10 will now be described in further detail.

FIG. 4A illustrates the filler 411 disposed at the center of the sealant 410, according to an exemplary embodiment of the present invention. FIG. 4B illustrates the filler 411 disposed in an upper portion of the sealant 410, that is, near the encapsulation substrate 300, according to an exemplary embodiment of the present invention. FIG. 4C illustrates the filler 411 disposed in a lower portion of the sealant 410, that is, near the substrate 200, according to an embodiment of the present invention. FIG. 4D illustrates sectional views of corner portions of fillers 411a and 411b, which are disposed at corners of a display device. In particular, the filler 411a has rounded corner portions (curved edges), such that the filler 411a is partially cylindrical, i.e., forms a rectangle with

rounded corners. The filler **411b** has cubic corner portions, such that the filler **411b** is rectangular.

FIG. 5 is a graph showing the results of six drop-impact experiments, wherein the filler locations of FIGS. 4A, 4B, and FIG. 4C and the filler shapes illustrated in FIG. 4D were tested. Referring to the graph of FIG. 5, the x-axis represents the sizes (heights) of fillers, and the y-axis represents stress concentration ratios. In this regard, the height of the sealants is maintained at 4 μm .

Referring to FIG. 5, it can be seen that in all six cases, when the height of the filler is more than 3 μm , that is, a ratio of the height d_{filler} of the filler to the height t_{frit} of the sealant is greater than 0.75, the stress concentration ratio significantly increases, meaning that stress is focused on a filler. Thus, the filler is highly likely to crack. That is, only when the ratio of the height d_{filler} of the filler to the height t_{frit} of the sealant is 0.75 or less, the stress concentration ratio is reduced to a satisfactory level, and thus, the impact resistance of the organic light-emitting display apparatus **10** may be sufficiently enhanced.

In addition, it can also be seen that when the height of the filler **411** is 2 μm or less, or the ratio of the height d_{filler} of the filler **411** to the height t_{frit} of the sealant **410** is 0.5 or less, in all the six cases, the stress concentration ratio is 2 or less. That is, when the ratio of the height d_{filler} to the height t_{frit} is 0.5 or less, the impact resistance of the organic light-emitting display apparatus **10** is enhanced.

In particular, when a filler is disposed in at upper or lower portion of a sealant, the ratio of the height d_{filler} of the filler to the height t_{frit} of the sealant should be reduced. In other words, as the filler is disposed closer to the center of the sealant, the impact resistance of the organic light-emitting display apparatus is enhanced.

The cylindrical filler **411a** has rounded corners, and thus, has a smaller stress concentration ratio than the rectangular filler **411b**, in all positions in sealant **410**. That is, when the filler **411a** is disposed at the center of a sealant and in the upper and lower portions of the sealant, stress concentration is reduced. That is, when the filler is cylindrical, the impact resistance of the organic light-emitting display apparatus is improved.

As described above, by properly setting the ratio of the height d_{filler} of a filler to the height t_{frit} of a sealant, the location of the filler in the sealant, and the shape of the filler, the impact resistance of an organic light-emitting display apparatus may be substantially enhanced.

FIG. 6 is a partial, schematic cross-sectional view of the organic light-emitting display apparatus **10** FIG. 2, exemplarily illustrating a detailed structure of the display unit **200**. Referring to FIG. 6, a plurality of thin film transistors (TFTs) **220** are formed on the substrate **100**. An organic light-emitting device **230** is formed on each of the TFTs **220**. The organic light-emitting device **230** may include pixel electrodes **231** electrically connected to each TFT **220**, an opposite electrode **235** disposed above the substrate **100**, and intermediate layers **233** interposed between the pixel electrodes **231** and the opposite electrode **235**. The intermediate layers **233** include an emission layer.

Each TFT **220** may include a gate electrode **221**, source electrode and drain electrodes **223**, a semiconductor layer **227**, a gate insulating layer **213**, and an inter-insulating layer **215**. The structure of the TFTs **220** is not limited to the structure illustrated in FIG. 4. For example, each TFT **220** may also be an organic TFT including the semiconductor layer **227** formed of an organic material, or a silicon TFT including the semiconductor layer **227** formed of silicon.

Optionally, a buffer layer **211** formed of silicon oxide or silicon nitride may be formed between the TFT **220** and the substrate **100**.

The pixel electrode **231** and the opposite electrode **235** face each other. The intermediate layers **233** are interposed between the pixel electrode **231** and the opposite electrode **235** and include an organic material layer. The intermediate layers **233** may include an emission layer. The intermediate layer **233** may include a plurality of layers, which will be described later.

The pixel electrode **231** may operate as an anode, and the opposite electrode **235** may operate as a cathode. In another exemplary embodiment, the pixel electrode **231** operates as a cathode, and the opposite electrode **235** operates as an anode.

The pixel electrode **231** may be a transparent electrode or a reflective electrode. If the pixel electrode **231** is a transparent electrode, the pixel electrode **231** may be formed of ITO, IZO, ZnO, or In_2O_3 . If the pixel electrode **231** is a reflective electrode, the pixel electrode **231** may include a reflective film formed of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, or a mixture thereof, and a film formed of ITO, IZO, ZnO, or In_2O_3 .

The opposite electrode **235** may be a transparent electrode or a reflective electrode. If the opposite electrode **235** is a transparent electrode, the opposite electrode **235** may include a film formed of Li, Ca, LiF/Ca, LiF/Al, Al, Mg, or a mixture thereof. The opposite electrode **235** is disposed facing the pixel electrode **231** and the intermediate layer **233**. The opposite electrode **235** may include an auxiliary electrode or bus electrode line formed on the film. The auxiliary electrode or bus electrode line may be formed of a transparent electrode material, such as ITO, IZO, ZnO, or In_2O_3 . If the opposite electrode **235** is a reflective electrode, the opposite electrode **235** may be formed of Li, Ca, LiF/Ca, LiF/Al, Al, Mg, or a mixture thereof.

A pixel-defining layer (PDL) **219** covers edges of each pixel electrode **231** and has a given height outside the pixel electrode **231**. The PDL **219** defines an emission region, and widens a distance between the pixel electrode **231** and the opposite electrode **235**, in a direction toward the edges of the pixel electrode **231**, so as to prevent the formation of a strong electric field at the edges of the pixel electrode **231**. The PDL **219** thereby prevents short-circuits between the pixel electrodes **231** and the opposite electrode **235**.

The intermediate layer **233** is formed between the pixel electrode **231** and the opposite electrode **235**. The structure of the intermediate layer **233** may vary. The intermediate layer **233** may be formed of a low molecular weight organic material or a polymer organic material.

When the intermediate layer **233** is formed of a low molecular weight organic material, the intermediate layer **233** may include an organic emission layer (EML) and at least one layer selected from the group consisting of a hole injection layer (HIL), a hole transport layer (HTL), an emission layer, an electron transport layer (ETL), and an electron injection layer (EIL). Each of the layers may be a single layer or multi-layered. In this regard, an available low molecular weight organic material may be copper phthalocyanine (CuPc), N,N'-Di naphthalene-1-yl-N,N'-diphenyl-benzidine (NPB), or tris-8-hydroxyquinoline aluminum (Alq3). These low molecular weight organic materials may be applied in, for example, a deposition process using masks.

When the intermediate layer **233** is formed of a polymer organic material, the intermediate layer **233** may generally have an HTL and an EML. The HTL may be formed of PEDOT and the EML may be formed of a polymer material selected from poly-phenylenevinyls (PPV) and polyfluorenes.

7

The organic light-emitting device **230** may be electrically connected to the TFTs **220**. In this regard, if a planarization layer **217** covering the TFTs **220** is included, the organic light-emitting device **230** may be disposed on the planarization layer **217**, and the pixel electrode **231** of the organic light-emitting device **230** may be electrically connected to the TFT **220**, through contact holes formed in the planarization layer **217**.

The organic light-emitting device **230** is sealed between the encapsulation substrate **300**, the substrate **100** and the sealant **410**. As described above, the encapsulation substrate **300** may be formed of glass, a plastic material, etc.

An organic light-emitting display apparatuses, according to exemplary embodiments of the present invention, are resistant to the permeation of external impurities such as oxygen and/or water vapor and have enhanced impact resistance.

Although a few exemplary embodiments of the present invention have been shown and described, it would be appreciated by those skilled in the art that changes may be made in these exemplary embodiments, without departing from the principles and spirit of the invention, the scope of which is defined in the claims and their equivalents.

What is claimed is:

1. An organic light-emitting display apparatus comprising:
 - a substrate;
 - a display unit disposed on the substrate;
 - an encapsulation substrate disposed facing the display unit;
 - a sealant disposed between the substrate and the encapsulation substrate; and
 - a sole rectangular shaped filler disposed in the sealant,

8

wherein the height t_{frit} of the sealant is greater than the height d_{filler} of the filler, and the heights t_{frit} and d_{filler} extend in a direction perpendicular to the plane of the substrate.

2. The organic light-emitting display apparatus of claim 1, wherein a ratio of the height d_{filler} of the filler to the height t_{frit} of the sealant is 0.75 or less.

3. The organic light-emitting display apparatus of claim 2, wherein the ratio of the height t_{frit} of the sealant to the height d_{filler} of the filler is 0.5 or less.

4. The organic light-emitting display apparatus of claim 1, wherein the sealant comprises a glass frit.

5. The organic light-emitting display apparatus of claim 1, wherein the filler is disposed at the center of the sealant, equidistant from the substrate and the encapsulation substrate.

6. The organic light-emitting display apparatus of claim 1, wherein the filler is cylindrical.

7. The organic light-emitting display apparatus of claim 1, wherein the sealant is disposed around the display unit.

8. The organic light-emitting display apparatus of claim 1, wherein the filler is generally rectangular.

9. The organic light-emitting display apparatus of claim 8, wherein corners of the filler are rounded.

10. The organic light-emitting display apparatus of claim 1, wherein the filler comprises a ceramic material.

11. The organic light-emitting display apparatus of claim 1, wherein the filler has a lower coefficient of thermal expansion (CTE) than the sealant.

12. The organic light-emitting display apparatus of claim 1, wherein the filler is disposed directly on the substrate or directly on the encapsulation substrate.

* * * * *

专利名称(译)	用含有填料的密封剂密封的有机发光显示装置		
公开(公告)号	US8288944	公开(公告)日	2012-10-16
申请号	US12/962877	申请日	2010-12-08
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星移动显示器有限公司.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE JUNG MIN KANG TAE WOOK SHIN JANG HWAN JEON JIN HWAN		
发明人	LEE, JUNG-MIN KANG, TAE-WOOK SHIN, JANG-HWAN JEON, JIN-HWAN		
IPC分类号	H01L51/50 H05B33/04		
CPC分类号	H01L51/5246 H01L2251/558		
审查员(译)	MAI , ANH		
优先权	1020090122538 2009-12-10 KR		
其他公开文献	US20110140599A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光显示装置，包括：基板；显示单元，设置在基板上；封装基板，设置在显示单元上；基板与封装基板结合并且包括填料的密封剂，其中密封剂的高度大于填料的高度。

