



US007148622B2

(12) **United States Patent**
Lin

(10) **Patent No.:** **US 7,148,622 B2**
(45) **Date of Patent:** **Dec. 12, 2006**

- (54) **ACTIVE-MATRIX ORGANIC ELECTROLUMINESCENT DISPLAY PANEL AND FABRICATING METHOD THEREOF**
- (75) Inventor: **Chiao-Ju Lin**, Taichung (TW)
- (73) Assignee: **Au Optronics Corporation**, Hsinchu (TW)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 226 days.
- (21) Appl. No.: **10/708,368**
- (22) Filed: **Feb. 26, 2004**
- (65) **Prior Publication Data**
US 2004/0195961 A1 Oct. 7, 2004
- (30) **Foreign Application Priority Data**
Apr. 4, 2003 (TW) 92107721 A
- (51) **Int. Cl.**
H05B 33/02 (2006.01)
H05B 33/12 (2006.01)
- (52) **U.S. Cl.** **313/504; 313/505**
- (58) **Field of Classification Search** 313/499-509; 257/79, 81, 83, 86, 40; 438/151, 156, 157, 438/166


See application file for complete search history.




- (56) **References Cited**
U.S. PATENT DOCUMENTS
6,771,328 B1 * 8/2004 Park et al. 349/42
* cited by examiner
Primary Examiner—Allen C. Ho
(74) *Attorney, Agent, or Firm*—Jianq Chyun IP Office

(57) **ABSTRACT**

A method for fabricating an active-matrix organic electroluminescent (OEL) display panel is described. A transparent conductive layer is formed on a substrate as a common anode for all organic light emitting diodes (OLED), and a passivation layer is formed on the transparent conductive layer. Thin film transistors are formed on the passivation layer to serve as an active matrix, and openings are formed in the passivation layer to expose portions of the transparent conductive layer and define pixel regions. An organic function layer is formed in each opening, and a metal electrode layer is formed on each organic function layer, wherein the metal electrode layer is electrically connected with the drain of the corresponding thin film transistor.

15 Claims, 4 Drawing Sheets








FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 3




FIG. 4




FIG. 5

**ACTIVE-MATRIX ORGANIC
ELECTROLUMINESCENT DISPLAY PANEL
AND FABRICATING METHOD THEREOF**

CROSS REFERENCE TO RELATED
APPLICATIONS

This application claims the priority benefit of Taiwan application serial no. 92107721, filed on Apr. 4, 2003.

BACKGROUND OF INVENTION

1. Field of the Invention

The present invention relates to a structure of a display panel and a fabricating method of the same. More particularly, the present invention relates to a structure of an active-matrix organic electroluminescent display panel and a fabricating method of the same.

2. Description of the Related Art

Organic electroluminescent (OEL) displays are light, thin and readily portable like liquid crystal displays (LCD) are, but do not need an additional backlight source, and therefore are getting more and more attention in the market. OEL displays can be divided into active-matrix OEL displays and simple-matrix OEL displays, wherein the active-matrix ones are preferred because they emit light continuously and can be driven by lower voltages.

Among the active-matrix OEL displays, those utilizing a-Si thin film transistors (TFT) can be manufactured at lower cost, and in larger size because of the better uniformity in manufacturing processes. However, due to the low electrical conductivity of a-Si material, only N-type TFTs are formed in an active-matrix OEL display, and the design of circuit interconnection is therefore restricted. In one option, the source of a TFT is connected with the anode of an organic light-emitting diode (OLED). However, when the voltage across the TFT is shifted, the voltage on the gate electrode will affect the voltage on the source to cause an unstable current through the OLED. In another option, the drain of a TFT is connected with the cathode of an OLED, so the current through the OLED is not affected by the voltage on the drain.

The process for fabricating an OEL display element with the second option mentioned above is illustrated in FIG. 1. A TFT **110** consisting of a gate **102**, a gate insulator **104**, a channel layer **106**, a source **108a** and a drain **108b** is formed on a substrate **100**, and a passivation layer **112** is formed over the substrate **100**. Then, a metal electrode layer **116** is formed on the passivation layer **112** as the cathode of an OLED, electrically connecting with the drain **108b** through an opening **114**. An electron transporting layer **118**, an emitting layer **120**, a hole transporting layer **122** and a hole injection layer **124** are sequentially formed on the metal electrode layer **116** to constitute an organic function layer **126** together. Thereafter, a transparent conductive layer **128** is formed on the organic function layer **126** as the anode of the OLED.

However, the OEL display element illustrated in FIG. 1 has some problems described below.

Conventionally, an OLED is formed by sequentially stacking a transparent conductive layer, a hole injection layer, an emitting layer, an electron transporting layer and a metal electrode layer, wherein the electron transporting layer usually includes Tri(8-Quinolinolato-N1O8)Aluminum (Alq3), and the metal electrode layer includes a LiF/Al composite layer. After the electron transporting layer and the metal electrode layer are formed, aluminum is usually

formed on the metal electrode layer with a sputtering process. The sputtering energy is capable of driving lithium atoms from the LiF layer to the electron transporting layer, and the lithium atoms bond with the Alq3 complexes in the electron transporting layer to enhance the efficiency of electron injection.

However, when the structure illustrated in FIG. 1 is adopted in consideration of the advantage of connecting the drain of the TFT and the cathode of the OLED, the metal electrode layer is formed prior to the electron transporting layer. Therefore, lithium atoms are not driven into the electron transporting layer, and the luminescence efficiency of the OEL display panel cannot be enhanced.

SUMMARY OF INVENTION

In view of the foregoing, this invention provides an active-matrix organic electroluminescent display panel and a fabricating method of the same, wherein the cathode of an OLED is connected with the drain of the corresponding TFT to reduce the affection of the gate voltage to the current through the OLED when the voltage across the TFT is shifted.

This invention also intends to dispose/form the metal electrode layer on the organic function layer in an active-matrix OEL display panel and a fabricating method of the same, so that some metal atoms can be driven into the electron transporting layer during the sputtering process for forming the metal electrode layer. Therefore, the efficiency of electron injection in the OLEDs can be enhanced.

Moreover, in the active-matrix OEL display panels of this invention and the fabricating methods of the same, a transparent conductive layer is firstly formed covering the substrate to serve as a common anode for all OLEDs before the TFTs are formed.

A method for fabricating an active-matrix OEL display panel of this invention is described as follows. A transparent conductive layer is formed on a substrate to serve as a common anode for all OLEDs that will be formed later, and a passivation layer is formed on the transparent conductive layer. Gate electrodes are formed on the passivation layer, and a gate insulator is formed covering the gate electrodes. Thereafter, openings are formed in the gate insulator and the passivation layer to expose portions of the transparent conductive layer, wherein each opening defines a pixel region. A channel layer is formed on the gate insulator over each gate electrode, and a source and a drain is formed on each channel layer to complete the fabrication of thin film transistors. An organic function layer is formed in each opening, and a patterned metal electrode layer is formed on each organic function layer to serve as the cathode of the OLED, wherein the metal electrode layer is electrically connected to a corresponding drain.

An active-matrix OEL display panel of this invention includes a substrate, a transparent conductive layer, a passivation layer, thin film transistors, organic function layers and metal electrode layers. The transparent conductive layer is disposed on the substrate to serve as a common anode for all OLEDs, and the passivation layer is disposed on the transparent conductive layer with openings therein exposing portions of the transparent conductive layer. Each opening defines a pixel region, and each TFT including a gate electrode, a source and a drain is disposed on the passivation layer accompanied with an opening, while all TFTs are arranged in a matrix. Each organic function layer is disposed on the transparent conductive layer in an opening, and each metal electrode layer is disposed on an organic function

layer to serve as the cathode of an OLED and to electrically connect with a corresponding drain.

Another active-matrix OEL display panel of this invention includes a substrate, a metal layer, a passivation layer, thin film transistors, transparent conductive layers, organic function layers and metal electrode layers. The metal layer is disposed on the substrate, and the passivation layer is disposed on the metal layer. The metal layer and the passivation layer have openings therein exposing portions of the substrate. Each opening defines a pixel region, and each TFT including a gate electrode, a source and a drain is disposed on the passivation layer accompanied with an opening, while all TFTs are arranged in a matrix. Each transparent conductive layer is disposed on the substrate in an opening, each organic function layer is disposed on a transparent conductive layer, and each metal electrode layer is disposed on an organic function layer to serve as the cathode of an OLED and to electrically connect a corresponding drain. The metal layer and the transparent conductive layer together constitute a common anode for all OLEDs.

In the active-matrix organic electroluminescent display panels of this invention and the fabricating methods of the same, the organic function layer can be formed by sequentially stacking a hole injection layer, a hole transporting layer, an emitting layer and an electron transporting layer. The metal electrode layer can be formed on the electron transporting layer with a sputtering process.

Moreover, another passivation layer can be formed on the TFTs after the TFTs are formed and before the metal electrode layers are formed. The additional passivation layer is capable of preventing a metal electrode layer from electrically connecting the source and the drain of the corresponding TFT when misalignment occurs during the patterning process of the metal electrode layers. Therefore, it is possible to prevent the source and the drain of a TFT from being shorted.

Since the cathode of an OLED is connected with the drain of a TFT in the active-matrix OEL display panels of this invention, the affection of the gate voltage to the current through the OLED can be reduced when the voltage across the TFT is shifted. Therefore, the stability of the current through the OLED can be improved.

Moreover, since an OLED in this invention can be formed by sequentially stacking a transparent conductive layer, a hole injection layer, a hole transporting layer, an emitting layer, an electron transporting layer and a metal electrode layer, some metal atoms can be driven from the metal electrode layer into the electron transporting layer during the sputtering process for forming the metal electrode layer. Therefore, the efficiency of electron injection in the OLED can be enhanced, and the luminescence efficiency of the OEL display panel can be improved.

In addition, this invention provides a new type of common anode, which consists of transparent conductive layers on the pixel regions of the substrate and a metal layer on the non-pixel region of the substrate. Therefore, the OEL display panel can make bottom light emission, and the electrical conductivity between the OLEDs can be enhanced because the metal layer has a low resistance.

It is to be understood that both the foregoing general description and the following detailed description are exemplary, and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF DRAWINGS

The accompanying drawings are included to provide a further understanding of the invention, and are incorporated in and constitute a part of this specification. The drawings illustrate embodiments of the invention and, together with the description, serve to explain the principles of the invention.

FIG. 1 illustrates a cross-sectional view of a conventional active-matrix OEL display element.

FIGS. 2A–2F illustrate a process flow of fabricating an active-matrix OEL display panel according to a preferred embodiment of this invention in a cross-sectional view.

FIG. 3 illustrates a cross-sectional view of an active-matrix OEL display element according to another preferred embodiment of this invention.

FIG. 4 illustrates a cross-sectional view of an active-matrix OEL display element according to still another preferred embodiment of this invention.

FIG. 5 illustrates a cross-sectional view of an active-matrix OEL display element according to still another preferred embodiment of this invention.

DETAILED DESCRIPTION

FIGS. 2A–2F illustrate a process flow of fabricating an active-matrix OEL display panel according to a preferred embodiment of this invention in a cross-sectional view. Though an OEL display panel has many OEL display elements thereon arranged as a matrix, FIGS. 2A–2F illustrate the fabrication of only one OEL display element for convenience.

Referring to FIG. 2A, a substrate **200**, such as a glass substrate or a plastic substrate, is provided. A transparent conductive layer **228** is formed on the substrate **200** to serve as a common anode. The transparent conductive layer **228** includes a material such as indium tin oxide (ITO) or indium zinc oxide (IZO), and is formed with a sputtering process, for example. A blanket passivation layer **230**, which includes a material such as silicon nitride, is formed on the transparent conductive layer **228** with plasma-enhanced chemical vapor deposition (PECVD), for example. The passivation layer **230** is formed to isolate the transparent conductive layer **228** from subsequent layers.

Referring to FIG. 2B, a gate electrode **202**, which is constituted of a metallic material like chromium (Cr), tungsten (W), tantalum (Ta), titanium (Ti), molybdenum (Mo), aluminum (Al) or an alloy, is formed on the passivation layer **230**. The steps for forming the gate electrode **202** include, for example, forming a metal layer (not shown) all over the passivation layer **230** and patterning the metal layer. Then, a blanket gate insulator **204** is formed covering the gate electrode **202** and the passivation layer **230**. The gate insulator **204** includes a dielectric material such as silicon nitride, and is formed with PECVD, for example.

Referring to FIG. 2C, an opening **232** is formed in the gate insulator **204** and the passivation layer **230** to expose a portion of the transparent conductive layer **228** and define a pixel region. Thereafter, a channel layer **206** is formed on the gate insulator **204** over the gate electrode **202**, and an ohmic contact layer (not shown) may be further formed on the channel layer **206**. The material of the channel layer **206** is, for example, amorphous silicon (a-Si), and the ohmic contact layer includes a conductive material such as n⁺-doped a-Si.

Referring to FIG. 2D, a source **208a** and a drain **208b** are formed on the channel layer **206**, and a portion of the

exposed channel layer **206** is removed. The gate electrode **202**, the gate insulator **204**, the channel layer **206**, the source **208a** and the drain **208b** together constitute a thin film transistor **210**.

Referring to FIG. 2E, an organic function layer **226** is formed in the opening **232** by, for example, sequentially stacking a hole injection layer **224**, a hole transporting layer **222**, an emitting layer **220** and an electron transporting layer **218**. The material of the hole transporting layer **222** is, for example, an aromatic amino compound, the material of the emitting layer **220** is, for example, a luminescent material of metal complex type or fluorescent pigment type, and the electron transporting layer **218** includes an electron transporting material such as Alq₃.

Referring to FIG. 2F, a patterned metal electrode layer **216** is formed on the organic function layer **226**. The metal electrode layer **216** is, for example, an LiF/Al composite layer, and is formed by, for example, depositing a LiF layer (not shown) with sputtering or evaporation, depositing aluminum (Al) on the LiF layer with a sputtering process, and then patterning the Al/LiF composite layer with a mask such as a shadow mask. The metal electrode layer **216** serves as a cathode of the OLED, and is electrically connected to the drain **208b**.

It is noted that during the sputtering process for depositing aluminum, the sputtering energy is capable of driving some metal (Li) atoms from the metal electrode layer **216** into the electron transporting layer **218**. The metal (Li) atoms bond with the material (such as Alq₃) of the electron transporting layer **218** to enhance the efficiency of electron injection, so that the luminescence efficiency of the OEL display panel can be improved.

Refer to FIG. 2F for further understanding the structure of the OEL display panel of this invention, wherein only one OEL display element is illustrated for convenience. The OEL display element includes a substrate **200**, a transparent conductive layer **228**, a passivation layer **230**, a TFT **210**, an organic function layer **226** and a metal electrode layer **216**.

The transparent conductive layer **228** is disposed on the substrate **200** as the anode of the OLED, and includes a transparent conductive material such as ITO or IZO. The passivation layer **230** is disposed on the transparent conductive layer **228** with an opening **232** therein exposing a portion of the transparent conductive layer **228** to define a pixel region. The TFT **210** is disposed on the passivation layer **230** beside the opening **232**, including at least a gate electrode **202**, a gate insulator **204**, a channel layer **206**, a source **208a** and a drain **208b**, and the organic function layer **226** is disposed on the transparent conductive layer **228** in the opening **232**. The metal electrode layer **216** is disposed on the organic function layer **226** as the cathode of the OLED, and is electrically connected to the drain **208b**. The metal electrode layer **216** is, for example, a LiF/Al composite layer.

It is noted that the transparent conductive layer **228** covering the substrate **200** before the TFT **210** is formed can serve as a common anode for all OLEDs on the substrate **200**. Moreover, the cathode of the OLED is electrically connected to the drain **208b** of the TFT **210** in this embodiment, so the affection of a gate voltage shift to the current through the OLED can be reduced to maintain the stability of the current through the OLED.

The other preferred embodiments of this invention are described as follows. FIG. 3 illustrates a cross-sectional view of an active-matrix OEL display element according to another preferred embodiment of this invention. The OEL display element includes a substrate **200**, a metal layer **236**,

a passivation layer **230**, a transparent conductive layer **228**, a TFT **210**, an organic function layer **226** and a metal electrode layer **216**.

The metal layer **236** is disposed on the substrate **200** as a part of the common anode for all OLEDs, and is composed of a low-resistance metallic material, for example. The metal layer **236** has an opening **238** therein, in which a transparent conductive layer **228** is disposed. The metal layer **236** and all transparent conductive layers **228** together constitute a common anode of the display panel. The passivation layer **230** is disposed on the transparent conductive layers **228** and the metal layer **236**, and has an opening **232** therein exposing most of the transparent conductive layer **228**. The TFT **210** is disposed on the passivation layer **230**, including a gate electrode **202**, a gate insulator **204**, a channel layer **206**, and a pair of source **208a** and drain **208b** that are stacked sequentially. The organic function layer **226** and the metal electrode layer **216** are sequentially stacked on the transparent conductive layer **228** in the opening **232**, wherein the metal electrode layer **216** is electrically connected to the drain **208b**.

It is noted that the common anode consists of the transparent conductive layers **228** on the pixel regions of the substrate **200** and the metal layer **236** on the non-pixel region of the substrate **200**. Therefore, the OEL display element can make bottom light emission, and the electrical conductivity between the OEL display elements can be enhanced.

Furthermore, as illustrated in FIGS. 4-5, another passivation layer **234** may be formed covering the TFT **210** after the TFT **210** is formed and before the metal electrode layer **216** is defined in the fabricating process of the OEL display panel of this invention. Thus, the passivation layer **234** is situated between the TFT **210** and the metal layer to be patterned into the metal electrode layer **216**, and is therefore capable of preventing the metal electrode layer **216** from electrically connecting the source **208a** and the drain **208b** when misalignment occurs during the definition of the metal electrode layer **216**. Consequently, it is possible to prevent the source **208a** and the drain **208b** of the TFT **210** from being shorted.

Though the above-mentioned preferred embodiments of this invention is explained with bottom-gate TFTs, this invention is not restricted to use bottom-gate TFTs. The bottom-gate TFTs may be replaced by top-gate TFTs fabricated based on a low-temperature polysilicon (LTPS) process.

Since the cathode of an OLED is connected with the drain of a TFT in the active-matrix OEL display panels in this invention, the affection of the gate voltage to the current through the OLED can be reduced when the voltage across the TFT is shifted. Therefore, the stability of the current through the OLED can be improved.

Moreover, since an OLED in this invention can be formed by sequentially stacking a transparent conductive layer, a hole injection layer, a hole transporting layer, an emitting layer, an electron transporting layer and a metal electrode layer, some metal atoms can be driven from the metal electrode layer into the electron transporting layer during the sputtering process for forming the metal electrode layer. Therefore, the efficiency of electron injection in the OLED can be enhanced, and the luminescence efficiency of the OEL display panel can be improved.

In addition, this invention provides a new structure of common anode, which consists of transparent conductive layers on the pixel regions of the substrate and a metal layer on the non-pixel region of the substrate. Therefore, the OEL

display panel can make bottom light emission, and the electrical conductivity between the OLEDs can be enhanced because the metal layer has a low resistance.

It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present invention without departing from the scope or spirit of the invention. In view of the foregoing, it is intended that the present invention covers modifications and variations of this invention provided they fall within the scope of the following claims and their equivalents.

The invention claimed is:

1. An active-matrix organic electroluminescent (OEL) display panel, comprising:

a substrate;

a transparent conductive layer on the substrate;

a first passivation layer on the transparent conductive layer, having a plurality of openings therein exposing portions of the transparent conductive layer, wherein each opening defines a pixel region;

a plurality of thin film transistors arranged as a matrix, wherein the thin film transistors are disposed on the first passivation layer;

a plurality of organic function layers disposed on the transparent conductive layer in the openings; and

a plurality of metal electrode layers disposed on the organic function layers and electrically connected to the corresponding thin film transistors.

2. The active-matrix OEL display panel of claim 1, wherein each organic function layer comprises a hole injection layer, a hole transporting layer, an emitting layer and an electron transporting layer that are stacked sequentially.

3. The active-matrix OEL display panel of claim 1, further comprising a second passivation layer disposed on each thin film transistor.

4. The active-matrix OEL display panel of claim 1, wherein the transparent conductive layer includes indium tin oxide (ITO) or indium zinc oxide (IZO).

5. The active-matrix OEL, display panel of claim 1, wherein each metal electrode layer includes a LiF/Al composite layer.

6. An active-matrix organic electroluminescent (OEL) display panel, comprising:

a substrate;

a metal layer on the substrate, having a plurality of opening therein exposing portions of the substrate;

a first passivation layer on the metal layer, having a plurality of openings therein aligned with the openings in the metal layer;

a plurality of thin film transistors arranged as a matrix, wherein the thin film transistors are disposed on the first passivation layer;

a plurality of transparent conductive layers disposed on the substrate in the openings;

a plurality of organic function layers disposed on the transparent conductive layers in the openings; and

a plurality of metal electrode layers disposed on the organic function layers and electrically connected to the corresponding thin film transistors.

7. The active-matrix OEL display panel of claim 6, wherein each organic function layer comprises a hole injection layer, a hole transporting layer, an emitting layer and an electron transporting layer.

8. The active-matrix OEL display panel of claim 6, further comprising a second passivation layer on the thin film transistors.

9. The active-matrix OEL display panel of claim 6, wherein the transparent conductive layer contains indium tin oxide (ITO) or indium zinc oxide (IZO).

10. The active-matrix OEL display panel of claim 6, wherein the metal electrode layer includes a LiF/Al composite layer.

11. An active-matrix organic electroluminescent (OEL) display panel, comprising:

a substrate;

a conductive layer disposed on the substrate;

a first passivation layer disposed on a portion of the conductive layer, wherein the first passivation layer has a plurality of openings therein exposing portions of the conductive layer, and each opening defines a pixel region;

a plurality of thin film transistors arranged as a matrix, wherein the thin film transistors are disposed on the first passivation layer;

a plurality of organic function layers disposed on the conductive layer in the openings; and

a plurality of electrode layers disposed on the organic function layers and electrically connected to the corresponding thin film transistors.

12. The active-matrix OEL display panel of claim 11, wherein each organic function layer comprises a hole injection layer, a hole transporting layer, an emitting layer and an electron transporting layer that are stacked sequentially.

13. The active-matrix OEL display panel of claim 11, further comprising a second passivation layer disposed on each thin film transistor.

14. The active-matrix OEL display panel of claim 11, wherein the conductive layer includes indium tin oxide (ITO) or indium zinc oxide (IZO).

15. The active-matrix OEL display panel of claim 11, wherein each electrode layer includes a LiF/Al composite layer.

* * * * *

专利名称(译)	有源矩阵有机电致发光显示面板及其制造方法		
公开(公告)号	US7148622	公开(公告)日	2006-12-12
申请号	US10/708368	申请日	2004-02-26
[标]申请(专利权)人(译)	林巧JU		
申请(专利权)人(译)	林巧-JU		
当前申请(专利权)人(译)	友达光电股份有限公司		
[标]发明人	LIN CHIAO JU		
发明人	LIN, CHIAO-JU		
IPC分类号	H05B33/02 H05B33/12 G02F1/13 G09F9/30 H01L27/32 H01L51/52 H05B33/00		
CPC分类号	H01L27/3248 H01L51/5212		
审查员(译)	HO, ALLEN C.		
优先权	092107721 2003-04-04 TW		
其他公开文献	US20040195961A1		
外部链接	Espacenet USPTO		

摘要(译)

描述了一种制造有源矩阵有机电致发光(OEL)显示板的方法。在基板上形成透明导电层作为所有有机发光二极管(OLED)的公共阳极,并且在透明导电层上形成钝化层。在钝化层上形成薄膜晶体管以用作有源矩阵,并且在钝化层中形成开口以暴露透明导电层的部分并限定像素区域。在每个开口中形成有机功能层,并且在每个有机功能层上形成金属电极层,其中金属电极层与相应的薄膜晶体管的漏极电连接。

