



US007701134B2

(12) **United States Patent**
Yamazaki et al.

(10) **Patent No.:** **US 7,701,134 B2**
(45) **Date of Patent:** **Apr. 20, 2010**

(54) **ACTIVE MATRIX DISPLAY DEVICE WITH
IMPROVED OPERATING PERFORMANCE**

4,530,750 A 7/1985 Aisenberg et al.

(75) Inventors: **Shunpei Yamazaki**, Tokyo (JP); **Jun
Koyama**, Kanagawa (JP); **Kunitaka
Yamamoto**, Kanagawa (JP); **Toshimitsu
Konuma**, Kanagawa (JP)

(Continued)

FOREIGN PATENT DOCUMENTS

(73) Assignee: **Semiconductor Energy Laboratory
Co., Ltd.**, Kanagawa-Ken (JP)

CN 2291695 9/1998

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(Continued)

OTHER PUBLICATIONS

(21) Appl. No.: **11/074,687**

(22) Filed: **Mar. 9, 2005**

Baldo et al., "Highly Efficient Phosphorescent Emission From
Organic Electroluminescent Devices", Letters to Nature, vol. 395,
pp. 151-154, Sep. 10, 1998.

(65) **Prior Publication Data**

US 2005/0161672 A1 Jul. 28, 2005

(Continued)

Related U.S. Application Data

(62) Division of application No. 09/578,895, filed on May
26, 2000.

Primary Examiner—Sikha Roy

(74) Attorney, Agent, or Firm—Nixon Peabody, LLP; Jeffrey
L. Costellia

(30) **Foreign Application Priority Data**

Jun. 4, 1999 (JP) 11-158787

(51) **Int. Cl.**

H05B 33/04 (2006.01)

H05B 33/26 (2006.01)

H01L 31/12 (2006.01)

(52) **U.S. Cl.** **313/506**; 313/512; 313/504;
257/72; 257/79; 257/81; 257/359; 345/76

(58) **Field of Classification Search** None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,040,073 A 8/1977 Luo

4,356,429 A 10/1982 Tang


4,357,557 A 11/1982 Inohara et al.

(57) **ABSTRACT**

An object of the present invention is to provide an EL display
device having a high operation performance and reliability.

The switching TFT **201** formed within a pixel has a multi-gate
structure, which is a structure which imposes an importance
on reduction of OFF current value. Further, the current control
TFT **202** has a channel width wider than that of the
switching TFT to make a structure appropriate for flowing
electric current. Moreover, the LDD region **33** of the current
control TFT **202** is formed so as to overlap a portion of the
gate electrode **35** to make a structure which imposes importance
on prevention of hot carrier injection and reduction of
OFF current value.

42 Claims, 23 Drawing Sheets



U.S. PATENT DOCUMENTS					
4,539,507 A	9/1985	VanSlyke et al.	5,811,177 A	9/1998	Shi et al.
4,586,790 A	5/1986	Umeda et al.	5,824,374 A	10/1998	Bradley
4,602,192 A	7/1986	Nomura et al.	5,839,456 A	11/1998	Han
4,720,432 A	1/1988	VanSlyke et al.	5,853,905 A	12/1998	So et al.
4,769,292 A	9/1988	Tang et al.	5,856,689 A	1/1999	Suzawa
4,885,211 A	12/1989	Tang et al.	5,859,627 A	1/1999	Hoshiya et al.
4,950,950 A	8/1990	Perry et al.	5,882,761 A	3/1999	Kawami et al.
4,975,338 A	12/1990	Kageyama et al.	5,889,459 A	3/1999	Hattori et al.
5,003,221 A	3/1991	Shimizu	5,895,935 A	4/1999	Yamazaki et al.
5,047,687 A	9/1991	VanSlyke	5,897,328 A	4/1999	Yamauchi et al.
5,059,861 A	10/1991	Littman et al.	5,903,249 A	5/1999	Koyama et al.
5,059,862 A	10/1991	VanSlyke et al.	5,904,514 A	5/1999	Konuma et al.
5,061,617 A	10/1991	Maskasky	5,909,081 A	6/1999	Eida et al.
5,072,263 A	12/1991	Watanabe et al.	5,923,962 A	7/1999	Ohtani et al.
5,073,446 A	12/1991	Scozzafava et al.	5,929,487 A	7/1999	Fukada et al.
5,107,175 A	4/1992	Hirano et al.	5,943,107 A	8/1999	Kadota et al.
5,124,204 A	6/1992	Yamashita et al.	5,952,708 A	9/1999	Yamazaki
5,151,629 A	9/1992	VanSlyke	5,952,778 A	9/1999	Haskal et al.
5,151,632 A	9/1992	Troxell	5,962,962 A	10/1999	Fujita et al.
5,189,405 A	2/1993	Yamashita et al.	5,990,542 A	11/1999	Yamazaki
5,190,794 A	3/1993	Yoshino et al.	5,990,615 A	11/1999	Sakaguchi et al.
5,206,749 A	4/1993	Zavracky et al.	6,011,607 A	1/2000	Yamazaki et al.
5,217,700 A	6/1993	Kurihara et al.	6,013,930 A	1/2000	Yamazaki et al.
5,247,190 A	9/1993	Friend et al.	6,028,325 A	2/2000	Yamazaki
5,270,267 A	12/1993	Ouellet	6,034,748 A	3/2000	Furuta
5,294,869 A	3/1994	Tang et al.	6,046,547 A	4/2000	Nishio et al.
5,294,870 A	3/1994	Tang et al.	6,049,167 A	4/2000	Onitsuka et al.
5,317,236 A	5/1994	Zavracky et al.	6,057,647 A	5/2000	Kurosawa et al.
5,323,042 A	6/1994	Matsumoto	6,084,248 A	7/2000	Inoue
5,338,364 A	8/1994	Kurihara et al.	6,097,459 A	8/2000	Shimada et al.
5,399,502 A	3/1995	Friend et al.	6,100,954 A	8/2000	Kim et al.
5,412,240 A	5/1995	Inoue et al.	6,111,270 A	8/2000	Xu et al.
5,412,493 A *	5/1995	Kunii et al. 349/43	6,114,183 A	9/2000	Hamada et al.
5,438,241 A	8/1995	Zavracky et al.	6,114,715 A *	9/2000	Hamada 257/72
5,482,896 A	1/1996	Tang	6,115,090 A	9/2000	Yamazaki
5,496,597 A	3/1996	Soininen et al.	6,128,060 A	10/2000	Shimada et al.
5,503,731 A	4/1996	Konuma et al.	6,146,225 A	11/2000	Sheats et al.
5,518,940 A	5/1996	Hodate et al.	6,147,451 A	11/2000	Shibata et al.
5,528,056 A	6/1996	Shimada et al.	6,150,187 A	11/2000	Zyung et al.
5,530,269 A	6/1996	Tang	6,150,668 A	11/2000	Bao et al.
5,552,668 A	9/1996	Hirose et al.	6,160,272 A	12/2000	Arai et al.
5,583,347 A	12/1996	Misawa et al.	6,165,543 A	12/2000	Otsuki et al.
5,610,738 A	3/1997	Sasano et al.	6,165,824 A	12/2000	Takano et al.
5,619,044 A	4/1997	Makita et al.	6,166,397 A	12/2000	Yamazaki et al.
5,640,067 A	6/1997	Yamauchi et al.	6,169,293 B1	1/2001	Yamazaki
5,641,991 A	6/1997	Sakoh	6,184,559 B1	2/2001	Hayakawa et al.
5,642,213 A	6/1997	Mase et al.	6,194,837 B1 *	2/2001	Ozawa 315/169.1
5,643,826 A	7/1997	Ohtani et al.	6,195,142 B1	2/2001	Gyotoku et al.
5,654,811 A	8/1997	Spitzer et al.	6,198,217 B1	3/2001	Suzuki et al.
5,661,371 A	8/1997	Salerno et al.	6,198,220 B1	3/2001	Jones et al.
5,670,792 A	9/1997	Utsugi et al.	6,198,225 B1	3/2001	Kano et al.
5,674,304 A	10/1997	Fukada et al.	6,204,534 B1	3/2001	Adan
5,677,600 A	10/1997	Takahashi et al.	6,204,535 B1	3/2001	Yamazaki et al.
5,680,165 A	10/1997	Takizawa et al.	6,218,219 B1	4/2001	Yamazaki et al.
5,680,185 A	10/1997	Kobayashi et al.	6,236,064 B1	5/2001	Mase et al.
5,684,365 A	11/1997	Tang et al.	6,239,470 B1	5/2001	Yamazaki
5,686,360 A	11/1997	Harvey, III et al.	6,246,179 B1	6/2001	Yamada
5,688,551 A	11/1997	Littman et al.	6,246,384 B1	6/2001	Sano
5,693,956 A	12/1997	Shi et al.	6,251,712 B1	6/2001	Tanaka et al.
5,703,382 A *	12/1997	Hack et al. 257/72	6,255,705 B1	7/2001	Zhang et al.
5,708,484 A	1/1998	Someya et al.	6,268,071 B1	7/2001	Yasukawa et al.
5,712,495 A	1/1998	Suzawa	6,268,631 B1	7/2001	Fukada et al.
5,712,652 A	1/1998	Sato et al.	6,268,695 B1	7/2001	Affinito
5,729,308 A	3/1998	Yamazaki et al.	6,268,842 B1	7/2001	Yamazaki et al.
5,747,830 A	5/1998	Okita	6,274,887 B1	8/2001	Yamazaki et al.
5,747,930 A	5/1998	Utsugi	6,278,132 B1	8/2001	Yamazaki et al.
5,748,165 A	5/1998	Kubota et al.	6,283,578 B1	9/2001	Popall et al.
5,757,126 A	5/1998	Harvey, III et al.	6,285,039 B1 *	9/2001	Kobori et al. 257/40
5,771,562 A	6/1998	Harvey, III et al.	6,295,054 B1	9/2001	McNight
5,790,213 A	8/1998	Sasaki et al.	6,307,322 B1	10/2001	Dawson et al.
5,798,746 A	8/1998	Koyama	6,316,810 B1	11/2001	Yamazaki et al.
			6,329,672 B1	12/2001	Lyu et al.
			6,337,492 B1	1/2002	Jones et al.

6,355,942 B1	3/2002	Yamazaki et al.	2004/0065902 A1	4/2004	Yamazaki et al.
6,359,606 B1	3/2002	Yudasaka	2004/0141139 A1	7/2004	Yamazaki et al.
6,362,030 B1	3/2002	Nagayama et al.	2004/0150591 A1	8/2004	Ozawa et al.
6,369,495 B2	4/2002	Codama et al.	2004/0196220 A1	10/2004	Kimura et al.
6,373,453 B1	4/2002	Yudasaka	2005/0073242 A1	4/2005	Yamauchi et al.
6,384,528 B1	5/2002	Friend et al.	2005/0156174 A1	7/2005	Murakami et al.
6,384,818 B1	5/2002	Yamazaki et al.	2005/0197031 A1	9/2005	Yamazaki et al.
6,392,340 B2	5/2002	Yoneda et al.	2006/0097256 A1	5/2006	Yamazaki et al.
6,407,431 B2	6/2002	Yamazaki et al.	2006/0192205 A1	8/2006	Yamazaki et al.
6,413,645 B1	7/2002	Graff et al.	2007/0012921 A1	1/2007	Yamazaki
6,417,898 B1	7/2002	Izumi	2008/0036699 A1	2/2008	Yudasaka
6,426,517 B2 *	7/2002	Hayakawa et al. 257/72			
6,429,059 B2	8/2002	Yamazaki et al.			
6,441,399 B1	8/2002	Koyama et al.			
6,441,468 B1	8/2002	Yamazaki	EP	0709718	5/1996
6,445,059 B1	9/2002	Yamazaki	EP	0 717 445	6/1996
6,447,867 B1	9/2002	Kominami et al.	EP	0 776 147	5/1997
6,448,580 B1	9/2002	Arai et al.	EP	0 781 075	6/1997
6,462,722 B1	10/2002	Kimura et al.	EP	859539 A2	8/1998
6,512,504 B1	1/2003	Yamauchi et al.	EP	0 895 219 A1	2/1999
6,522,315 B2	2/2003	Ozawa et al.	EP	0 917 127 A1	5/1999
6,529,178 B1	3/2003	Kimura	EP	0 940 796 A1	9/1999
6,531,713 B1	3/2003	Yamazaki	EP	0942407 A1	9/1999
6,542,137 B2	4/2003	Kimura et al.	EP	961525 A1	12/1999
6,573,564 B2	6/2003	Yamazaki et al.	EP	0 999 595 A2	5/2000
6,580,214 B2	6/2003	Yoneda et al.	EP	1 001 467 A2	5/2000
6,605,826 B2	8/2003	Yamazaki et al.	EP	1 033 755 A2	9/2000
6,617,644 B1	9/2003	Yamazaki et al.	EP	1 049 176 A2	11/2000
6,636,194 B2	10/2003	Ishii	EP	1052701 A2	11/2000
6,642,989 B2	11/2003	Umehara et al.	EP	1 255 240 A1	11/2002
6,674,136 B1	1/2004	Ohtani	EP	1 336 953 A2	8/2003
6,703,643 B2	3/2004	Yamazaki et al.	EP	1 337 131 A2	8/2003
6,730,966 B2 *	5/2004	Koyama 257/350	EP	1 359 789 A1	11/2003
6,737,176 B1	5/2004	Otsuki et al.	EP	1 363 265 A2	11/2003
6,758,538 B2 *	7/2004	Fujita et al. 313/506	EP	1 524 696 A2	4/2005
6,770,502 B2	8/2004	Cok et al.	JP	62-090 260	4/1987
6,770,936 B2	8/2004	Inoue et al.	JP	63-131494	6/1988
6,777,763 B1 *	8/2004	Zhang et al. 257/408	JP	04-350627	12/1992
6,794,675 B1	9/2004	Suzuki et al.	JP	05-036475	2/1993
6,839,045 B2	1/2005	Ozawa et al.	JP	05-080712	4/1993
6,853,083 B1	2/2005	Yamauchi et al.	JP	05-095115	4/1993
6,862,011 B2	3/2005	Kimura et al.	JP	05-116 297	5/1993
6,863,961 B2	3/2005	Miyashita et al.	JP	06-102530	4/1994
6,940,214 B1	9/2005	Komiya et al.	JP	06-186578	7/1994
6,965,195 B2	11/2005	Yamazaki et al.	JP	06-265940	9/1994
6,977,394 B2	12/2005	Yamazaki et al.	JP	07-014678	1/1995
6,992,435 B2	1/2006	Yamauchi et al.	JP	07-130 652	5/1995
7,083,866 B2	8/2006	Otsuki et al.	JP	07-169567	7/1995
7,112,462 B2	9/2006	Arai et al.	JP	08-078 159	3/1996
7,113,154 B1	9/2006	Inukai	JP	08-075908	3/1996
7,126,161 B2	10/2006	Yamazaki	JP	10-092576	4/1996
7,288,420 B1	10/2007	Yamazaki et al.	JP	08-220560	8/1996
7,476,900 B2	1/2009	Yamauchi et al.	JP	08-241 048	9/1996
2001/0000627 A1	5/2001	Hayakawa et al.	JP	08-290 647	11/1996
2001/0019859 A1	9/2001	Yamazaki et al.	JP	08-330 602	12/1996
2001/0049163 A1	12/2001	Yamazaki et al.	JP	08-330600	12/1996
2002/0024493 A1	2/2002	Ozawa et al.	JP	09-045930	2/1997
2002/0056844 A1	5/2002	Yamazaki et al.	JP	09-148 066	6/1997
2002/0075207 A1	6/2002	Yudasaka	JP	09-166788	6/1997
2002/0089497 A1	7/2002	Yudasaka	JP	09-293879	11/1997
2002/0097213 A1	7/2002	Ozawa et al.	JP	10-012 377	1/1998
2002/0125817 A1	9/2002	Yamazaki et al.	JP	10-012377	1/1998
2002/0130363 A1	9/2002	Yamazaki et al.	JP	10-041067	2/1998
2002/0185967 A1	12/2002	Friend	JP	10-082994	3/1998
2002/0196206 A1	12/2002	Kimura et al.	JP	10-092 576	4/1998
2003/0054186 A1 *	3/2003	Miyashita et al. 428/500	JP	10-125463	5/1998
2003/0071771 A1	4/2003	Kimura	JP	H10-125463	5/1998
2003/0098827 A1	5/2003	Ozawa	JP	10-189 252	7/1998
2003/0132900 A1	7/2003	Yamauchi et al.	JP	10-189998	7/1998
2003/0151582 A1	8/2003	Ishii	JP	10-233283	9/1998
2003/0155573 A1	8/2003	Yamazaki et al.	JP	10-254383	9/1998
2003/0206144 A1	11/2003	Yudasaka	JP	10-270 363	10/1998
2003/0231273 A1	12/2003	Kimura et al.	JP	10-275682	10/1998

FOREIGN PATENT DOCUMENTS

JP	10-319872	12/1998
JP	11-026156	1/1999
JP	11-054268	2/1999
JP	11-065487	3/1999
JP	11-097705	4/1999
JP	11-103067	4/1999
JP	11-112001	4/1999
JP	11-272235	10/1999
JP	2000-077191	3/2000
JP	2000-148046	5/2000
JP	2000-223279	8/2000
JP	2000-340 798	12/2000
JP	2001-35659	2/2001
JP	2002-149112	5/2002
WO	WO98/13811	4/1998
WO	WO 98/36405	8/1998
WO	WO 98/36406	8/1998
WO	WO 98/36407	8/1998
WO	WO 99/02277	1/1999
WO	WO99/12394	3/1999

OTHER PUBLICATIONS

Baldo et al., "Very High Efficiency Green Organic Light—Emitting Devices Based on Electrophosphorescence", *Applied Physics Letters*, vol. 75, No. 1, pp. 4-6 Jul. 5, 1999.

Kido et al., "White-Light-Emitting Organic Electroluminescent Device Using Lanthanide Complexes", *Japanese Journal of Applied Physics*, vol. 35, Part 2, No. 3B, pp. L394-L396, Mar. 15, 1996.

Tsutsui et al., "Electroluminescence in Organic Thin Films", *Photochemical Processes in Organized Molecular Systems*, pp. 437-450, 1991.

Tsutsui et al., "High Quantum Efficiency in Organic Light—Emitting Devices With Iridium-Complex as a Triplet Emissive Center", *Japanese Journal of Applied Physics*, vol. 38, Part 2, No. 12B, pp. L1502-L1504, Dec. 15, 1999.

Specification & Drawings of U.S. Appl. No. 09/432,662.

Specification & Drawings of U.S. Appl. No. 09/580,485.

Specification & Drawings of U.S. Appl. No. 09/587,369.

Choi, K. et al., "Gate-Overlapped Lightly Doped Drain Poly-Si Thin-Film Transistors for Large Area-AMLCD", *IEEE Transactions on Electron Devices*, Jun. 1998, vol. 45, No. 6, pp. 1272-1279.

European Search Report (Application No. 00112035.1-2203 PCT; EP 4211), dated: Sep. 19, 2005.

Yamazaki, Shunpei et al. U.S. Appl. No. 11/258,933, filed Oct. 27, 2005 "Electro-Optical Device and Electronic Device" (specification, claims, drawings and filing receipt).

Application No. 05010071.8; Sep. 13, 2005, European Search Report.

Specification, U.S. Appl. No. 11/407,145, filed Apr. 20, 2006, Yamazaki et al.

Office Action of Application No. 00 112 035.1 dated Apr. 6, 2006 from European Patent Office.

Tsutsui, et al. "Electroluminescence in Organic Thin Films", *Photochemical Processes in Organized Molecular Systems*, pp. 437-450, 1991.

Office Action issued in counterpart European Application No. 05010071.8-1235 dated May 14, 2007.

Search Report issued in counterpart European Patent Application No. 06015168.5-1235 dated Mar. 28, 2007.

Pending Claims (as of Dec. 27, 2007) of U.S. Appl. No. 10/678,299, filed Oct. 6, 2003; Inventors: Shunpei Yamazaki et al.

Pending Claims (as of Dec. 27, 2007) of U.S. Appl. No. 11/258,933, filed Oct. 27, 2005; Inventors: Shunpei Yamazaki et al.

Pending Claims (as of Dec. 27, 2007) of U.S. Appl. No. 11/407,145, filed Apr. 20, 2006; Inventors: Shunpei Yamazaki et al.

Allowed Claims (as of Dec. 27, 2007) for U.S. Appl. No. 11/078,521, filed Mar. 14, 2005; Inventors: Shunpei Yamazaki et al.

European Search Report (Application No. 00112035.1-2203 PCT; EP4211), dated: Sep. 19, 2005.

*Search Report (Application No. 00113676.3; EP4226) Dated Apr. 11, 2006.

Schenk H et al., "Polymers for Light Emitting Diodes," *Eurodisplay '99: Proceedings of the 19TH IDRC (International Display Research Conference Proceedings)*, Sep. 6, 1999, pp. 33-37.

Shimoda.T et al., "Multicolor Pixel Patterning of Light-Emitting Polymers by Ink-Jet Printing," *SID Digest '99 : SID International Symposium Digest of Technical Papers*, 1999, vol. XXX, pp. 376-379.

Kimura.M et al., "TFT-LEPD With Image Uniformity by Area Ratio Gray Scale," *Eurodisplay '99: Late-News Papers of the 19TH IDRC (International Display Research Conference)*, Sep. 6, 1999, pp. 71-74.

Shimoda.T et al., "Technology for Active Matrix Light Emitting Polymer Displays," *IEDM 99: Technical Digest of International Electron Devices Meeting*, 1999, pp. 107-110.

Pending Claims (U.S. Appl. No. 10/678,299; US4211D1 (U06688)) Dated Dec. 18, 2008.

Pending Claims (U.S. Appl. No. 11/258,933; US4211D3 (U09005)) Dated Jan. 11, 2008.

Office Action (U.S. Appl. No. 09/578,895; US4211) Dated Oct. 15, 2008.

Office Action (U.S. Appl. No. 10/678,299; US4211D1) Dated Jul. 16, 2008.

Office Action (U.S. Appl. No. 10/678,299; US4211D1) Dated Dec. 24, 2008.

Pending Claims U.S. Appl. No. 10/678,299, Dated May 7, 2009.

* cited by examiner

Fig. 1




Fig. 2A





Fig. 2B






Fig. 3A




Fig. 3B




Fig. 3C




Fig. 3D




Fig. 3E




Fig. 4A




Fig. 4B




Fig. 4C




Fig. 4D




Fig. 5A




Fig. 5B




Fig. 5C


60
b6
b7C


Fig. 7


Fig. 8


Fig. 9

Fig. 10




Fig. 11




Fig. 12A




Fig. 12B




Fig. 13




Fig. 14




Fig. 15A




Fig. 15B




Fig. 16A




Fig. 16B




Fig. 16C




Fig. 16D




Fig. 16E




Fig. 16F




Fig. 17A




Fig. 17B




Fig. 18A




Fig. 18B




Fig. 18C





Fig. 19



Fig. 20A**Fig. 20B**



Fig. 21A**Fig. 21B**




Fig. 22A**Fig. 22B**

Fig. 23



ACTIVE MATRIX DISPLAY DEVICE WITH IMPROVED OPERATING PERFORMANCE

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an electro-optical device, typically an EL (electroluminescence) display device formed by a semiconductor element (an element using a semiconductor thin film) made on a substrate, and to electronic equipment (an electronic device) having the electro-optical device as a display (also referred to as a display portion).

2. Description of the Related Art

Techniques of forming a TFT on a substrate have been widely progressing in recent years, and developments of applications to an active matrix type display device are advancing. In particular, a TFT using a polysilicon film has a higher electric field effect mobility (also referred to as mobility) than a TFT using a conventional amorphous silicon film, and high speed operation is therefore possible. As a result, it becomes possible to perform pixel control, conventionally performed by a driver circuit external to the substrate, by a driver circuit formed on the same substrate as the pixel.

This type of active matrix display device has been in the spotlight because of the many advantage which can be obtained by incorporating various circuits and elements on the same substrate in this type of active matrix display device, such as reduced manufacturing cost, small size, increased yield, and higher throughput.

Switching elements are formed by a TFT for each of the pixels in the active matrix display device, current control is performed by driver elements using the switching elements, and an EL layer (electroluminescence layer) is made to emit light. A typical pixel structure at this time is disclosed in, for example, in FIG. 1 of U.S. Pat. No. 5,684,365 (Japanese Patent Application Laid-open No. Hei 8-234683).

As shown in FIG. 1 of the U.S. Patent, a drain of a switching element (T1) is connected to a gate electrode of a current control element (T2), and is also connected in parallel to a capacitor (Cs). The gate voltage of the current control element (T2) is maintained by the electric charge stored in the capacitor (Cs).

Conversely, when the switching element (T1) is non-selected, the electric charge leaks through the switching element (T1) if the capacitor (Cs) is not connected (the flow of current at this point is referred to as off current), and the voltage applied to the gate electrode of the current control element (T2) becomes unable to be maintained. This is a problem which cannot be avoided because the switching element (T1) is formed by a transistor. However, the capacitor (Cs) is formed within the pixel, and therefore this becomes a factor in reducing the effective luminescence surface area (effective image display area) of the pixel.

Further, it is necessary for a large current to flow in the current control element (T2) in order to luminesce the EL layer. In other words, the performance required of the TFT becomes entirely different in the switching element and the current control element. In this type of case, it is difficult to ensure the performance required by all of the circuits and element with only one TFT structure.

SUMMARY OF THE INVENTION

In view of the above conventional technique, an object of the present invention is to provide an electro-optical device having good operation performance and high reliability, and in particular, to provide an EL display device. Another object

of the present invention is to increase the quality of electronic equipment (an electronic device) having the electro-optical device as a display by increasing the image quality of the electro-optical device.

In order to achieve the above objects, the present invention assigns TFTs having an optimal structure in view of the performance required by elements contained in each pixel of the EL display device. In other words, TFTs having different structures exist within the same pixel.

Specifically, an element which places the most importance on sufficiently lowering the value of the off current (such as a switching element) is given a TFT structure in which the importance is more on reducing the off current value rather than on high speed operation. An element which places the greatest importance on current flow (such as a current control element) is given a TFT structure in which the importance is more on current flow, and on controlling deterioration due to hot carrier injection, which becomes a conspicuous problem at the same time, rather than on reducing the value of the off current.

It becomes possible to raise the operating performance of the EL display device, and to increase its reliability, with the present invention by performing proper use of TFTs on the same substrate, as above. Note that the concepts of the present invention are not limited to a pixel portion, and that the present invention is characterized by the point of being able to optimize the TFT structure contained in the pixel portion and in a driver circuit portion for driving the pixel portion.

BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings:

FIG. 1 is a diagram showing the cross sectional structure of the pixel portion of an EL display device;

FIGS. 2A and 2B are diagrams showing the top view and the composition, respectively, of the pixel portion of an EL display device;

FIGS. 3A to 3E are diagrams showing manufacturing processes of an active matrix type EL display device;

FIGS. 4A to 4D are diagrams showing manufacturing processes of an active matrix type EL display device;

FIGS. 5A to 5C are diagrams showing manufacturing processes of an active matrix type EL display device;

FIG. 6 is a diagram showing an external view of an EL module;

FIG. 7 is a diagram showing the circuit block structure of an EL display device;

FIG. 8 is an enlarged diagram of the pixel portion of an EL display device;

FIG. 9 is a diagram showing the element structure of a sampling circuit of an EL display device;

FIG. 10 is a diagram showing the composition of the pixel portion of an EL display device;

FIG. 11 is a diagram showing the cross sectional structure of an EL display device;

FIGS. 12A and 12B are diagrams showing the top view and the composition, respectively, of the pixel portion of an EL display device;

FIG. 13 is a diagram showing the cross sectional structure of the pixel portion of an EL display device;

FIG. 14 is a diagram showing the cross sectional structure of the pixel portion of an EL display device;

FIGS. 15A and 15B are diagrams showing the top view and the composition, respectively, of the pixel portion of an EL display device;

FIGS. 16A to 16F are diagrams showing specific examples of electronic equipment;

FIGS. 17A and 17B are diagrams showing external views of an EL module;

FIGS. 18A to 18C are diagrams showing manufacturing processes of a contact structure;

FIG. 19 is a diagram showing the laminate structure of an EL layer;

FIGS. 20A and 20B are diagrams showing specific examples of electronic equipment;

FIGS. 21A and 21B are diagrams showing the circuit composition of the pixel portion of an EL display device;

FIGS. 22A and 22B are diagrams showing the circuit composition of the pixel portion of an EL display device; and

FIG. 23 is a diagram showing the cross sectional structure of the pixel portion of an EL display device.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Embodiment Mode

FIGS. 1 to 2B are used in explaining the preferred embodiments of the present invention. Shown in FIG. 1 is a cross sectional diagram of a pixel of an EL display device of the present invention, in FIG. 2A is its top view, and in FIG. 2B is a circuit composition. In practice, a pixel portion (image display portion) is formed with a multiple number of this type of pixel arranged in a matrix state.

Note that the cross sectional diagram of FIG. 1 shows a cross section cut along the line A-A' in the top view shown in FIG. 2A. Common symbols are used in FIG. 1 and in FIGS. 2A and 2B, and therefore the three figures may be referenced as appropriate. Furthermore, two pixels are shown in the top view of FIG. 2A, and both have the same structure.

Reference numeral 11 denotes a substrate, and reference numeral 12 denotes a base film in FIG. 1. A glass substrate, a glass ceramic substrate, a quartz substrate, a silicon substrate, a ceramic substrate, a metallic substrate, or a plastic substrate (including a plastic film) can be used as the substrate 11.

Further, the base film 12 is especially effective for cases in which a substrate containing mobile ions, or a substrate having conductivity, is used, but need not be formed for a quartz substrate. An insulating film containing silicon may be formed as the base film 12. Note that the term "insulating film containing silicon" indicates, specifically, an insulating film that contains silicon, oxygen, and nitrogen in predetermined ratios such as a silicon oxide film, a silicon nitride film, or a silicon oxynitride film (denoted by SiO_xN_y).

Two TFTs are formed within the pixel here. Reference numeral 201 denotes a TFT functioning as a switching element (hereafter referred to as a switching TFT), and reference numeral 202 denotes a TFT functioning as a current control element for controlling the amount of current flowing to an EL element (hereafter referred to as a current control TFT), and both are formed by an n-channel TFT.

The field effect mobility of the n-channel TFT is larger than the field effect mobility of a p-channel TFT, and therefore the operation speed is fast and electric current can flow easily. Further, even with the same amount of current flow, the n-channel TFT can be made smaller. The effective surface area of the display portion therefore becomes larger when using the n-channel TFT as a current control TFT, and this is preferable.

The p-channel TFT has the advantages that hot carrier injection essentially does not become a problem, and that the off current value is low, and there are already reports of examples of using the p-channel TFT as a switching TFT and as a current control TFT. However, by using a structure in

which the position of an LDD region differs, the problems of hot carrier injection and the off current value in the n-channel TFT are solved by the present invention. The present invention is characterized by the use of n-channel TFTs for all of the TFTs within all of the pixels.

Note that it is not necessary to limit the switching TFT and the current control TFT to n-channel TFTs in the present invention, and that it is possible to use p-channel TFTs for either the switching TFT, the current control TFT, or both.

The switching TFT 201 is formed having: an active layer comprising a source region 13, a drain region 14, LDD regions 15a to 15d, a high concentration impurity region 16, and channel forming regions 17a and 17b; a gate insulating film 18; gate electrodes 19a and 19b, a first interlayer insulating film 20, a source wiring 21, and a drain wiring 22.

As shown in FIG. 2A, the present invention is characterized in that the gate electrodes 19a and 19b become a double gate structure electrically connected by a gate wiring 211 which is formed by a different material (a material having a lower resistance than the gate electrodes 19a and 19b). Of course, not only a double gate structure, but a so-called multi-gate structure (a structure containing an active layer having two or more channel forming regions connected in series), such as a triple gate structure, may also be used. The multi-gate structure is extremely effective in lowering the value of the off current, and by making the switching TFT 201 of the pixel into a multi-gate structure with the present invention, a low off current value can be realized for the switching TFT.

The active layer is formed by a semiconductor film containing a crystal structure. In other words, a single crystal semiconductor film may be used, and a polycrystalline semiconductor film or a microcrystalline semiconductor film may also be used. Further, the gate insulating film 18 may be formed by an insulating film containing silicon. Additionally, a conducting film can be used for all of the gate electrodes, the source wiring, and the drain wiring.

In addition, the LDD regions 15a to 15d in the switching TFT 201 are formed so as not to overlay with the gate electrodes 19a and 19b by interposing the gate insulating film 18. This structure is extremely effective in reducing the off current value.

Note that the formation of an offset region (a region that comprises a semiconductor layer having the same composition as the channel forming regions, and to which a gate voltage is not applied) between the channel forming regions and the LDD regions is more preferable for reducing the off current value. Further, when a multi-gate structure having two or more gate electrodes is used, the high concentration impurity region formed between the channel forming regions is effective in lowering the value of the off current.

By thus using the multi-gate structure TFT as the switching TFT 201, as above, a switching element having a sufficiently low off current value is realized by the present invention. The gate voltage of the current control element can therefore be maintained for a sufficient amount of time (for a period from one selection until the next selection) without forming a capacitor (Cs), such as the one stated in the conventional example.

Namely, it becomes possible to eliminate the capacitor which causes a reduction in the effective luminescence surface area, and it becomes possible to increase the effective luminescence surface area. This means that the image quality of the EL display device can be made brighter.

Next, the current control TFT 202 is formed having: an active layer comprising a source region 31, a drain region 32, an LDD region 33, and a channel forming region 34; a gate insulating film 18; a gate electrode 35; the first interlayer

insulating film 20; a source wiring 36; and a drain wiring 37. Note that the gate electrode 35 has a single gate structure, but a multi-gate structure may also be used.

As shown in FIGS. 2A and 2B, the drain of the switching TFT 201 is electrically connected to the gate of the current control TFT 202. Specifically, the gate electrode 35 of the current control TFT 202 is electrically connected to the drain region 14 of the switching TFT 201 through the drain wiring (also referred to as a connection wiring) 22. Further, the source wiring 36 is connected to an electric current supply wiring 212.

A characteristic of the current control TFT 202 is that its channel width is larger than the channel width of the switching TFT 201. Namely, as shown in FIG. 8, when the channel length of the switching TFT is taken as L1 and its channel width as W1, and the channel length of the current control TFT is taken as L2 and its channel width as W2, a relational expression is reached in which $W2/L2 \geq 5 \times W1/L1$ (preferably $W2/L2 \leq 10 \times W1/L1$). Consequently, it is possible for more current to easily flow in the current control TFT than in the switching TFT.

Note that the channel length L1 of the multi-gate structure switching TFT is the sum of each of the channel lengths of the two or more channel forming regions formed. A double gate structure is formed in the case of FIG. 8, and therefore the sum of the channel lengths L1a and L1b, respectively, of the two channel-forming regions becomes the channel length L1 of the switching TFT.

The channel lengths L1 and L2, and the channel widths W1 and W2 are not specifically limited to a range of values with the present invention, but it is preferable that W1 be from 0.1 to 5 μm (typically between 1 and 3 μm), and that W2 be from 0.5 to 30 μm (typically between 2 and 10 μm). It is preferable that L1 be from 0.2 to 18 μm (typically between 2 and 15 μm), and that L2 be from 0.1 to 50 μm (typically between 1 and 20 μm) at this time.

Note that it is preferable to set the channel length L in the current control TFT on the long side in order to prevent excessive current flow. Preferably, $W2/L2 \geq 3$ (more preferably $W2/L2 \geq 5$). It is also preferable that the current flow per pixel is from 0.5 to 2 μA (better between 1 and 1.5 μA).

By setting the numerical values within this range, all standards, from an EL display device having a VGA class number of pixels (640×480) to an EL display device having a high vision class number of pixels (1920×1080) can be included.

Furthermore, the length (width) of the LDD region formed in the switching TFT 201 is set from 0.5 to 3.5 μm , typically between 2.0 and 2.5 μm .

The EL display device shown in FIG. 1 is characterized in that the LDD region 33 is formed between the drain region 32 and the channel forming region 34 in the current control TFT 202. In addition, the LDD region 33 has both a region which overlaps, and a region which does not overlap the gate electrode 35 by interposing a gate insulating film 18.

The current control TFT 202 supplies a current for making the EL element 203 luminesce, and at the same time controls the amount supplied and makes gray scale display possible. It is therefore necessary that there is no deterioration when the current flows, and that steps are taken against deterioration due to hot carrier injection. Furthermore, when black is displayed, the current control TFT 202 is set in the off state, but if the off current value is high, then a clean black color display becomes impossible, and this invites problems such as a reduction in contrast. It is therefore necessary to suppress the value of the off current.

Regarding deterioration due to hot carrier injection, it is known that a structure in which the LDD region overlaps the

gate electrode is extremely effective. However, if the entire LDD region is made to overlap the gate electrode, then the value of the off current rises, and therefore the applicant of the present invention resolves both the hot carrier and off current value countermeasures at the same time by a novel structure in which an LDD region which does not overlap the gate electrode is formed in series.

The length of the LDD region which overlaps the gate electrode may be made from 0.1 to 3 μm (preferable between 0.3 and 1.5 μm) at this point. If it is too long, then the parasitic capacitance will become larger, and if it is too short, then the effect of preventing hot carrier will become weakened. Further, the length of the LDD region not overlapping the gate electrode may be set from 1.0 to 3.5 μm (preferable between 1.5 and 2.0 μm). If it is too long, then a sufficient current becomes unable to flow, and if it is too short, then the effect of reducing off current value becomes weakened.

A parasitic capacitance is formed in the above structure in the region where the gate electrode and the LDD region overlap, and therefore it is preferable that this region not be formed between the source region 31 and the channel forming region 34. The carrier (electrons in this case) flow direction is always the same for the current control TFT, and therefore it is sufficient to form the LDD region on only the drain region side.

Further, looking from the viewpoint of increasing the amount of current that is able to flow, it is effective to make the film thickness of the active layer (especially the channel forming region) of the current control TFT 202 thick (preferably from 50 to 100 nm, more preferably between 60 and 80 nm). Conversely, looking from the point of view of making the off current value smaller for the switching TFT 201, it is effective to make the film thickness of the active layer (especially the channel forming region) thin (preferably from 20 to 50 nm, more preferably between 25 and 40 nm).

Next, reference numeral 41 denotes a first passivation film, and its film thickness may be set from 10 nm to 1 μm (preferably between 200 and 500 nm). An insulating film containing silicon (in particular, preferably a silicon oxynitride film or a silicon nitride film) can be used as the passivation film material. The passivation film 41 plays the role of protecting the manufactured TFT from contaminant matter and moisture. Alkaline metals such as sodium are contained in an EL layer formed on the final TFT. In other words, the first passivation film 41 works as a protecting layer so that these alkaline metals (mobile ions) do not penetrate into the TFT. Note that alkaline metals and alkaline-earth metals are contained in the term 'alkaline metal' throughout this specification.

Further, by making the passivation film 41 possess a heat radiation effect, it is also effective in preventing thermal degradation of the EL layer. Note that light is emitted from the base 11 side in the FIG. 1 structure of the EL display device, and therefore it is necessary for the passivation film 41 to have light transmitting characteristics.

A chemical compound containing at least one element selected from the group consisting of B (boron), C (carbon), and N (nitrogen), and at least one element selected from the group consisting of Al (aluminum), Si (silicon), and P (phosphorous) can be given as a light transparent material possessing heat radiation qualities. For example, it is possible to use: an aluminum nitride compound, typically aluminum nitride (Al_xN_y); a silicon carbide compound, typically silicon carbide (Si_xC_y); a silicon nitride compound, typically silicon nitride (Si_xN_y); a boron nitride compound, typically boron nitride (B_xN_y); or a boron phosphate compound, typically boron phosphate (B_xP_y). Further, an aluminum oxide compound, typically aluminum oxide (Al_xO_y), has superior light

transparency characteristics, and has a thermal conductivity of $20 \text{ Wm}^{-1}\text{K}^{-1}$, and can be said to be a preferable material. These materials not only possess heat radiation qualities, but also are effective in preventing the penetration of substances such as moisture and alkaline metals. Note that x and y are arbitrary integers for the above transparent materials.

The above chemical compounds can also be combined with another element. For example, it is possible to use nitrated aluminum oxide, denoted by AlN_xO_y , in which nitrogen is added to aluminum oxide. This material also not only possesses heat radiation qualities, but also is effective in preventing the penetration of substances such as moisture and alkaline metals. Note that x and y are arbitrary integers for the above nitrated aluminum oxide.

Furthermore, the materials recorded in Japanese Patent Application Laid-open No. Sho 62-90260 can also be used. Namely, a chemical compound containing Si, Al, N, O, and M can also be used (note that M is a rare-earth element, preferably an element selected from the group consisting of Ce (cesium), Yb (ytterbium), Sm (samarium), Er (erbium), Y (yttrium), La (lanthanum), Gd (gadolinium), Dy (dysprosium), and Nd (neodymium)). These materials not only possess heat radiation qualities, but also are effective in preventing the penetration of substances such as moisture and alkaline metals.

Furthermore, carbon films such as a diamond thin film or amorphous carbons (especially those which have characteristics close to those of diamond; referred to as diamond-like carbon) can also be used. These have very high thermal conductivities, and are extremely effective as radiation layers. Note that if the film thickness becomes larger, there is brown banding and the transmissivity is reduced, and therefore it is preferable to use as thin a film thickness (preferably between 5 and 100 nm) as possible.

Note that the aim of the first passivation film **41** is in protecting the TFT from contaminating matter and from moisture, and therefore it must be made so as to not lose this effect. A thin film made from a material possessing the above radiation effect can be used by itself, but it is effective to laminate this thin film and a thin film having shielding properties against alkaline metals and moisture (typically a silicon nitride film (Si_xN_y) or a silicon oxynitride film (SiO_xN_y)). Note that x and y are arbitrary integers for the above silicon nitride films and silicon oxynitride films.

Reference numeral **42** denotes a color filter, and reference numeral **43** denotes a fluorescent substance (also referred to as a fluorescent pigment layer). Both are a combination of the same color, and contain red (R), green (G), or blue (B). The color filter **42** is formed in order to increase the color purity, and the fluorescent substance **43** is formed in order to perform color transformation.

Note that EL display devices are roughly divided into four types of color displays: a method of forming three types of EL elements corresponding to R, G, and B; a method of combining white color luminescing EL elements with color filters; a method of combining blue or blue-green luminescing EL elements and fluorescent matter (fluorescing color change layer, CCM); and a method of using a transparent electrode as a cathode (opposing electrode) and overlapping EL elements corresponding to R, G, and B.

The structure of FIG. 1 is an example of a case of using a combination of blue luminescing EL elements and a fluorescent substance. A blue color emitting luminescence layer is used as the EL element **203** here, light possessing blue color region wavelength, including ultraviolet light, is formed, and the fluorescent substance **43** is activated by the light, and

made to emit red, green, or blue light. The color purity of the light is increased by the color filter **42**, and this is outputted.

Note that it is possible to implement the present invention without being concerned with the method of luminescence, and that all four of the above methods can be used with the present invention.

Furthermore, after forming the color filter **42** and the fluorescent substance **43**, leveling is performed by a second interlayer insulating film **44**. A resin film is preferable as the second interlayer insulating film **44**, and one such as polyimide, polyamide, acrylic, or BCB (benzocyclobutane) may be used. An inorganic film may, of course, also be used, provided that sufficient leveling is possible.

The leveling of steps due to the TFT by the second interlayer insulating film **44** is extremely important. The EL layer formed afterward is very thin and therefore there are cases in which poor luminescence is caused by the existence of a step. It is therefore preferable to perform leveling before forming a pixel electrode so as to be able to form the EL layer on as level a surface as possible.

Furthermore, it is effective to form an insulating film having a high thermal radiation effect (hereafter referred to as a thermal radiation layer) on the second interlayer insulating film **44**. A film thickness of 5 nm to 1 μm (typically between 20 and 300 nm) is preferable. This type of thermal radiation layer functions so that the heat generated by the EL element is released, so that heat is not stored in the EL element. Further, when formed by a resin film, the second interlayer insulating film **44** is weak with respect to heat, and the thermal radiation layer works so as not to impart bad influence due to the heat generated by the EL element.

It is effective to perform leveling of the TFT by the resin film in manufacturing the EL display device, as stated above, but there has not been a conventional structure which considers the deterioration of the resin film due to heat generated by the EL element. It can therefore be said that the formation of the thermal radiation layer is extremely effective in resolving this point.

Furthermore, provided that a material which is not permeable to moisture, oxygen, or alkaline metals (a material similar to that of the first passivation film **41**) is used as the thermal radiation layer, then it can also function as a protecting layer in order that alkaline metals within the EL layer do not diffuse toward the TFT, at the same time as preventing deterioration of the EL element and the resin film due to heat, as above. In addition, the thermal radiation layer also functions as a protecting layer so that moisture and oxygen do not penetrate into the EL layer from the TFT.

In particular, provided that the thermal radiation effect is desired, a carbon film such as a diamond film or a diamond-like carbon film is preferable, and in order to prevent penetration of substances such as moisture, it is more preferable to use a lamination structure of a carbon film and a silicon nitride film (or a silicon oxynitride film).

A structure in which TFT side and EL element side are segregated by an insulating film which has a high radiation effect and is capable of shielding moisture and alkaline metal, is thus effective.

Reference numeral **45** denotes a pixel electrode (EL element anode) made from a transparent conducting film. After opening a contact hole in the second interlayer insulating film **44** and in the first passivation film **41**, the pixel electrode **45** is formed so as to be connected to the drain wiring **37** of the current control TFT **202**.


An EL layer (an organic material is preferable) **46**, a cathode **47**, and a protecting electrode **48** are formed in order on the pixel electrode **45**. A single layer structure or a lamination

structure can be used as the EL layer 46, but there are many cases in which the lamination structure is used. Various lamination structures have been proposed, combinations of layers such as a luminescence layer, an electron transporting layer, an electron injecting layer, a hole injecting layer, and a hole transporting layer, but any structure may be used for the present invention. Doping of a fluorescent pigment into the EL layer may also be performed, of course. Note that a luminescing element formed by a pixel electrode (anode), an EL layer, and a cathode is referred to as an EL element throughout this specification.

All already known EL materials can be used by the present invention. Organic materials are widely known as such materials, and considering the driver voltage, it is preferable to use an organic material. For example, the materials disclosed in the following U.S. Patents and Japanese patent applications can be used as the organic EL material:

U.S. Pat. No. 4,356,429; U.S. Pat. No. 4,539,507; U.S. Pat. No. 4,720,432; U.S. Pat. No. 4,769,292; U.S. Pat. No. 4,885,211; U.S. Pat. No. 4,950,950; U.S. Pat. No. 5,059,861; U.S. Pat. No. 5,047,687; U.S. Pat. No. 5,073,446; U.S. Pat. No. 5,059,862; U.S. Pat. No. 5,061,617; U.S. Pat. No. 5,151,629; U.S. Pat. No. 5,294,869; U.S. Pat. No. 5,294,870; Japanese Patent Application Laid-open No. Hei 10-189525; Japanese Patent Application Laid-open No. Hei 8-241048; and Japanese Patent Application Laid-open No. Hei 8-78159.


Specifically, an organic material such as the one shown by the following general formula can be used as a hole injecting layer.



[formula 1]

Here, Q is either N or a C—R (carbon chain); M is a metal, a metal oxide, or a metal halide; R is hydrogen, an alkyl, an aralkyl, an aryl, or an alkyl; and T1 and T2 are unsaturated six member rings including substituent such as hydrogen, alkyl, or halogen.

Furthermore, an aromatic tertiary amine can be used as an organic material hole transporting layer, preferably including the tetraaryldiamine shown by the following general formula.




[formula 2]

In formula 2 Are is an arylene group, n is an integer from 1 to 4, and Ar, R7, R8, and R9 are each various chosen aryl groups.

In addition, a metal oxynoid compound can be used as an organic material EL layer, electron transporting layer, or elec-


tron injecting layer. A material such as that shown by the general formula below may be used as the metal oxynoid compound.

[formula 3]




It is possible to substitute R2 through R7, and a metal oxynoid such as the following can also be used.

[formula 4]



In formula 4, R2 through R7 are defined as stated above; L1 through L5 are carbohydrate groups containing from 1 to 12 carbon elements; and both L1 and L2, or both L2 and L3 are formed by benzo-rings. Further, a metal oxynoid such as the following may also be used.

[formula 5]



It is possible to substitute R2 through R6 here. Coordination compounds having organic ligands are thus included as organic EL materials. Note that the above examples are only some examples of organic EL materials which can be used as the EL material of the present invention, and that there is absolutely no need to limit the EL material to these.

Furthermore, when using an ink jet method for forming the EL layer, it is preferable to use a polymer material as the EL material. Polymer materials such as the following can be given as typical polymer materials: polyparaphenylene vinylenes (PPVs); and polyfluorenes. For colorization, it is preferable to use, for example, a cyano-polyphenylene vinylene in a red luminescing material; a polyphenylene vinylene in a green luminescing material; and a polyphenylene vinylene and a polyalkylphenylene in a blue luminescing material. Regarding organic EL materials which can be

used in an ink-jet method, all of the materials recorded in Japanese Patent Application Laid-open No. Hei 10-012377 can be cited.

Furthermore, a material containing a low work coefficient material such as magnesium (Mg), lithium (Li), cesium (Cs), barium (Ba), potassium (K), beryllium (Be), or calcium (Ca) is used as the cathode **47**. Preferably, an electrode made from MgAg (a material made from Mg and Ag at a mixture of Mg:Ag=10:1) may be used. In addition, a MgAgAl electrode, a LiAl electrode, and a LiFAl electrode can be given as other examples. Further, the protecting electrode **48** is an electrode formed in order to be a protecting film against moisture from external to the cathode **47**, and a material containing aluminum (Al) or silver (Ag) is used. The protecting electrode **48** also has a heat radiation effect.

Note that it is desirable to form the EL layer **46** and the cathode **47** in succession, without exposure to the atmosphere. In other words, no matter what type of lamination structure the EL layer and the cathode contain, it is preferable to form everything in a multi-chamber (also referred to as a cluster tool) type deposition device in succession. This is in order to avoid the absorption of moisture when the EL layer is exposed to the atmosphere because if an organic material is used as the EL layer, then it is extremely weak with respect to moisture. In addition, not only the EL layer **46** and the cathode **47**, it is even better to form all the way through the protecting electrode **48** in succession.

The EL layer is extremely weak with respect to heat, and therefore it is preferable to use vacuum evaporation (in particular, an organic molecular beam evaporation method is effective in that it forms a very thin film, on the molecular order level), sputtering, plasma CVD, spin coating, screen printing, or ion plating as the film deposition method. It is also possible to form the EL layer by an ink-jet method. For the ink jet method there is a bubble jet method using cavitation (refer to Japanese Patent Application Laid-open No. Hei 5-116297), and there is a piezo method using a piezo element (refer to Japanese Patent Application Laid-open No. Hei 8-290647), and in view of the fact that organic EL materials are weak with respect to heat, the piezo method is preferable.

Reference numeral **49** denotes a second passivation film, and its film thickness may be set from 10 nm to 1 μ m (preferable between 200 and 500 nm). The object of forming the second passivation film **49** is mainly to protect the EL layer **46** from moisture, but it is also good if the second passivation film **49** is made to possess a heat radiation effect, similar to the first passivation film **41**. The same materials as used for the first passivation film **41** can therefore be used as the formation material of the second passivation film **49**. Note that when an organic material is used as the EL layer **46**, it deteriorates due to bonding with oxygen, and therefore it is preferable to use an insulating film which does not easily emit oxygen.

Further, the EL layer is weak with respect to heat, as stated above, and therefore it is preferable to perform film deposition at a low temperature as possible (preferably in the range from room temperature to 120° C.). It can therefore be said that plasma CVD, sputtering, vacuum evaporation, ion plating, and solution application (spin coating) are desirable film deposition methods.

The EL display device of the present invention has a pixel portion containing a pixel with a structure as stated above, and TFTs having differing structures in response to their function are arranged in the pixel. A switching TFT having a sufficiently low off current value, and a current control TFT which is strong with respect to hot carrier injection can be formed

within the same pixel, and an EL display device having high reliability and which is capable of good image display can thus be formed.

Note that the most important point in the pixel structure of FIG. **1** is that a multi-gate structure TFT is used as the switching TFT, and that it is not necessary to place limits on the structure of FIG. **1** with regard to such things as the placement of LDD regions.

A more detailed explanation of the present invention, having the above constitution, is now performed by the embodiments shown below.

Embodiment 1

The embodiments of the present invention are explained using FIGS. **3A** to **5C**. A method of manufacturing a pixel portion, and TFTs of a driver circuit portion formed in the periphery of the pixel portion, is explained here. Note that in order to simplify the explanation, a CMOS circuit is shown as a basic circuit for the driver circuits.

First, as shown in FIG. **3A**, a base film **301** is formed with a 300 nm thickness on a glass substrate **300**. Silicon oxynitride films are laminated as the base film **301** in embodiment **1**. It is good to set the nitrogen concentration to between 10 and 25 wt % in the film contacting the glass substrate **300**.

Further, it is effective to form a heat radiating layer, made from the same material as that of the first passivation film **41** shown in FIG. **1**, as a portion of the base film **301**. A large electric current flows in a current control TFT, heat is easily generated, and therefore it is effective to form the heat radiating layer as close as possible to the current control TFT.

Next, an amorphous silicon film (not shown in the figures) is formed with a thickness of 50 nm on the base film **301** by a known deposition method. Note that it is not necessary to limit this to the amorphous silicon film, and another film may be formed provided that it is a semiconductor film containing an amorphous structure (including a microcrystalline semiconductor film). In addition, a compound semiconductor film containing an amorphous structure, such as an amorphous silicon germanium film, may also be used. Further, the film thickness may be made from 20 to 100 nm.

The amorphous silicon film is then crystallized by a known method, forming a crystalline silicon film (also referred to as a polycrystalline silicon film or a polysilicon film) **302**. Thermal crystallization using an electric furnace, laser annealing crystallization using a laser, and lamp annealing crystallization using an infrared lamp exist as known crystallization methods. Crystallization is performed in embodiment **1** using light from an excimer laser which uses XeCl gas.

Note that pulse emission type excimer laser light formed into a linear shape is used in embodiment **1**, but a rectangular shape may also be used, and continuous emission argon laser light and continuous emission excimer laser light can also be used.

The crystalline silicon film is used as an active layer of the TFTs in embodiment **1**, but it is also possible to use an amorphous silicon film as the active layer. However, it is necessary for a large current to flow through the current control TFT, and therefore it is more effective to use the crystalline silicon film, through which current easily flows.

Note that it is effective to form the active layer of the switching TFT, in which there is a necessity to reduce the off current, by the amorphous silicon film, and to form the active layer of the current control TFT by the crystalline silicon film. Electric current flows with difficulty in the amorphous silicon film because the carrier mobility is low, and the off current does not easily flow. In other words, the most can be made of

the advantages of both the amorphous silicon film, through which current does not flow easily, and the crystalline silicon film, through which current easily flows.

Next, as shown in FIG. 3B, a protecting film **303** is formed on the crystalline silicon film **302** from a silicon oxide film having a thickness of 130 nm. This thickness may be chosen within the range of 100 to 200 nm (preferably between 130 and 170 nm). Furthermore, other films may also be used providing that they are insulating films containing silicon. The protecting film **303** is formed so that the crystalline silicon film is not directly exposed to plasma during addition of an impurity, and so that it is possible to have delicate concentration control of the impurity.

Resist masks **304a** and **304b** are then formed on the protecting film **303**, and an impurity element which imparts n-type conductivity (hereafter referred to as an n-type impurity element) is added. Note that elements residing in periodic table group **15** are generally used as the n-type impurity element, and typically phosphorous or arsenic can be used. Note that a plasma doping method is used, in which phosphine (PH_3) is plasma activated without separation of mass, and phosphorous is added at a concentration of 1×10^{18} atoms/cm³ in embodiment 1. An ion implantation method, in which separation of mass is performed, may also be used, of course.

The dose amount is regulated so that the n-type impurity element is contained in n-type impurity regions **305** and **306**, thus formed by this process, at a concentration of 2×10^{16} to 5×10^{19} atoms/cm³ (typically between 5×10^{17} and 5×10^{18} atoms/cm³).

Next, as shown in FIG. 3C, the protecting film **303** is removed, and activation of the added periodic table group **15** element is performed. A known technique of activation may be used as the means of activation, and activation is done in embodiment 1 by irradiation of excimer laser light. Both of pulse emission type laser and a continuous emission type laser may be used, and it is not necessary to place any limits on the use of excimer laser light. The goal is the activation of the added impurity element, and it is preferable that irradiation is performed at an energy level at which the crystalline silicon film does not melt. Note that the laser irradiation may also be performed with the protecting film **303** in place.

Activation by heat treatment may also be performed along with activation of the impurity element by laser light. When activation is performed by heat treatment, considering the heat resistance of the substrate, it is good to perform heat treatment on the order of 450 to 550° C.

A boundary portion, (connecting portion) with regions along the edges of the n-type impurity regions **305** and **306**, namely regions along the perimeter into which the n-type impurity element, which exists in the n-type impurity regions **305** and **306**, is not added, is delineated by this process. This means that, at the point when the TFTs are later completed, extremely good connections can be formed between LDD regions and channel forming regions.

Unnecessary portions of the crystalline silicon film are removed next, as shown in FIG. 3D, and island shape semiconductor films (hereafter referred to as active layers) **307** to **310** are formed.

Then, as shown in FIG. 3E, a gate insulating film **311** is formed, covering the active layers **307** to **310**. An insulating film containing silicon and with a thickness of 10 to 200 nm, preferably between 50 and 150 nm, may be used as the gate insulating film **311**. A single layer structure or a lamination structure may be used. A 110 nm thick silicon oxynitride film is used in embodiment 1.

A conducting film with a thickness of 200 to 400 nm is formed next and patterned, forming gate electrodes **312** to

316. Note that in embodiment 1, the gate electrodes and lead wirings electrically connected to the gate electrodes (hereafter referred to as gate wirings) are formed from different materials. Specifically, a material having a lower resistance than that of the gate electrodes is used for the gate wirings. This is because a material which is capable of being micro-processed is used as the gate electrodes, and even if the gate wirings cannot be micro-processed, the material used for the wirings has low resistance. Of course, the gate electrodes and the gate wirings may also be formed from the same material.

Further, the gate wirings may be formed by a single layer conducting film, and when necessary, it is preferable to use a two layer or a three layer lamination film. All known conducting films can be used as the gate electrode material. However, as stated above, it is preferable to use a material which is capable of being micro-processed, specifically, a material which is capable of being patterned to a line width of 2 μm or less.

Typically, a film of a material chosen from among the group consisting of tantalum (Ta), titanium (Ti), molybdenum (Mo), tungsten (W), and chromium (Cr); or a nitrated compound of the above elements (typically a tantalum nitride film, a tungsten nitride film, or a titanium nitride film); or an alloy film of a combination of the above elements (typically a Mo—W alloy or a Mo—Ta alloy); or a silicide film of the above elements (typically a tungsten silicide film or a titanium silicide film); or a silicon film which has been made to possess conductivity can be used. A single layer film or a lamination may be used, of course.

A lamination film made from a 50 nm thick tantalum nitride (Ta₃N₅) film and a 350 nm thick Ta film is used in embodiment 1. It is good to form this film by sputtering. Furthermore, if an inert gas such as Xe or Ne is added as a sputtering gas, then film peeling due to the stress can be prevented.

The gate electrodes **313** and **316** are formed at this time so as to overlap a portion of the n-type impurity regions **305** and **306**, respectively, sandwiching the gate insulating film **311**. This overlapping portion later becomes an LDD region overlapping the gate electrode.

Next, an n-type impurity element (phosphorous is used in embodiment 1) is added in a self-aligning manner with the gate electrodes **312** to **316** as masks, as shown in FIG. 4A. The addition is regulated so that phosphorous is added to impurity regions **317** to **323** thus formed at a concentration of $1/10$ to $1/2$ that of the impurity regions **305** and **306** (typically between $1/4$ and $1/3$). Specifically, a concentration of 1×10^{16} to 5×10^{18} atoms/cm³ (typically 3×10^{17} to 3×10^{18} atoms/cm³) is preferable.

Resist masks **324a** to **324d** are formed next to cover the gate electrodes, as shown in FIG. 4B, and an n-type impurity element (phosphorous is used in embodiment 1) is added, forming impurity regions **325** to **331** containing a high concentration of phosphorous. Ion doping using phosphine (PH_3) is also performed here, and is regulated so that the phosphorous concentration of these regions is from 1×10^{20} to 1×10^{21} atoms/cm³ (typically between 2×10^{20} and 5×10^{20} atoms/cm³).

A source region or a drain region of the n-channel TFT is formed by this process, and in the switching TFT, a portion of the n-type impurity regions **320** to **322** formed by the process of FIG. 4A remains. These remaining regions correspond to the LDD regions **15a** to **15d** of the switching TFT in FIG. 1.

Next, as shown in FIG. 4C, the resist masks **324a** to **324d** are removed, and a new resist mask **332** is formed. A p-type impurity element (boron is used in embodiment 1) is then added, forming impurity regions **333** and **334** containing a

high concentration of boron. Boron is added here to a concentration of 3×10^{20} to 3×10^{21} atoms/cm³ (typically between 5×10^{20} and 1×10^{21} atoms/cm³) by ion doping using diborane (B₂H₆).

Note that phosphorous has already been added to the impurity regions **333** and **334** at a concentration of 1×10^{16} to 5×10^{18} atoms/cm³, but boron is added here at a concentration of at least 3 times that of the phosphorous. Therefore, the n-type impurity regions already formed completely invert to p-type, and function as p-type impurity regions.

Next, after removing the resist mask **332**, the n-type and p-type impurity elements added at various concentrations are activated. Furnace annealing, laser annealing, or lamp annealing may be performed as a means of activation. Heat treatment is performed in embodiment 1 in a nitrogen atmosphere for 4 hours at 550° C. in an electric furnace.

It is important to remove as much of the oxygen in the atmosphere as possible at this time. This is because if any oxygen exists, then the exposed surface of the electrode oxidizes, inviting an increase in resistance, and at the same time it becomes more difficult to later make an ohmic contact. It is therefore preferable that the concentration of oxygen in the atmosphere in the above activation process be 1 ppm or less, desirably 0.1 ppm or less.

After the activation process is completed, a gate wiring **335** with a thickness of 300 nm is formed next. A metallic film having aluminum (Al) or copper (Cu) as its principal constituent (comprising 50 to 100% of the composition) may be used as the material of the gate wiring **335**. As with the gate wiring **211** of FIG. 2, the gate wiring **335** is formed with a placement so that the gate electrodes **314** and **315** of the switching TFTs (corresponding to gate electrodes **19a** and **19b** of FIG. 2) are electrically connected. (See FIG. 4D.)

The wiring resistance of the gate wiring can be made extremely small by using this type of structure, and therefore a pixel display region (pixel portion) having a large surface area can be formed. Namely, the pixel structure of embodiment 1 is extremely effective because an EL display device having a screen size of a 10 inch diagonal or larger (in addition, a 30 inch or larger diagonal) is realized.

A first interlayer insulating film **336** is formed next, as shown in FIG. 5A. A single layer insulating film containing silicon is used as the first interlayer insulating film **336**, but a lamination film may be combined in between. Further, a film thickness of between 400 nm and 1.5 μm may be used. A lamination structure of an 800 nm thick silicon oxide film on a 200 nm thick silicon oxynitride film is used in embodiment 1.

In addition, heat treatment is performed for 1 to 12 hours at 300 to 450° C. in an atmosphere containing between 3 and 100% hydrogen, performing hydrogenation. This process is one of hydrogen termination of dangling bonds in the semiconductor film by hydrogen which is thermally activated. Plasma hydrogenation (using hydrogen activated by a plasma) may also be performed as another means of hydrogenation.

Note that the hydrogenation step may also be inserted during the formation of the first interlayer insulating film **336**. Namely, hydrogen processing may be performed as above after forming the 200 nm thick silicon oxynitride film and then the remaining 800 nm thick silicon oxide film may be formed.

A contact hole is formed next in the first interlayer insulating film **336**, and source wirings **337** to **340**, and drain wirings **341** to **343** are formed. In embodiment 1, a lamination film with a three layer structure of a 100 nm titanium film, a 300 nm aluminum film containing titanium, and a 150 nm tita-

anium film formed successively by sputtering, is used as these wirings. Other conducting films may also be used, of course, and an alloy film containing silver, palladium, and copper may also be used.

A first passivation film **344** is formed next with a thickness of 50 to 500 nm (typically between 200 and 300 nm). A 300 nm thick silicon oxynitride film is used as the first passivation film **344** in embodiment 1. This may also be substituted by a silicon nitride film. It is of course possible to use the same materials as those of the first passivation film **41** of FIG. 1.

Note that it is effective to perform plasma processing using a gas containing hydrogen such as H₂ or NH₃ before the formation of the silicon oxynitride film. Hydrogen activated by this preprocess is supplied to the first interlayer insulating film **336**, and the film quality of the first passivation film **344** is improved by performing heat treatment. At the same time, the hydrogen added to the first interlayer insulating film **336** diffuses to the lower side, and the active layers can be hydrogenated effectively.

Next, as shown in FIG. 5B, a color filter **345** and a fluorescing body **346** are formed. Known materials may be used for these. Furthermore, they may be formed by being patterned separately, or they may be formed in succession and then patterned together. A method such as screen printing, ink jetting, or mask evaporation (a selective forming method using a mask material) may be used as the formation method.

The respective film thickness may be chosen in the range of 0.5 to 5 μm (typically between 1 and 2 μm). In particular, the optimal film thickness of the fluorescing body **346** varies with the material used. In other words, if it is too thin, then the color transformation efficiency becomes poor, and if it is too thick, then the step becomes large and the amount of light transmitted drops. Optimal film thicknesses must therefore be set by taking a balance of both characteristics.

Note that, in embodiment 1, an example of a color changing method in which the light emitted from the EL layer is transformed in color, but if a method of manufacturing individual EL layers which correspond to R, G, and B, is employed, then the color filter and the fluorescing body can be omitted.

A second interlayer insulating film **347** is formed next from an organic resin. Materials such as polyimide, polyamide, acrylic, and BCB (benzocyclobutene) can be used as the organic resin. In particular, the purpose of being a leveling film is strong in the second interlayer insulating film **347**, and therefore acrylic, having superior leveling characteristics, is preferable. An acrylic film is formed in embodiment 1 with a film thickness which can sufficiently level the step between the color filter **345** and the fluorescing body **346**. This thickness is preferably from 1 to 5 μm (more preferably between 2 and 4 μm).

A contact hole for reaching the drain wiring **343** is formed next in the second interlayer insulating film **347** and in the first passivation film **344**, and a pixel electrode **348** is formed. A compound of indium oxide and tin oxide is formed into 110 nm thick in embodiment 1, and patterning is performed, making the pixel electrode. The pixel electrode **348** becomes an anode of the EL element. Note that it is also possible to use other materials: a compound film of indium oxide and zinc oxide, or a zinc oxide film containing gallium oxide.

Note that embodiment 1 becomes a structure in which the pixel electrode **348** is electrically connected to the drain region **331** of the current control TFT, through the drain wiring **343**. This structure has the following advantages.

The pixel electrode **348** becomes directly connected to an organic material such as the EL layer (emitting layer) or a charge transporting layer, and therefore it is possible for the

mobile ions contained in the EL layer to diffuse throughout the pixel electrode. In other words, without connecting the pixel electrode **348** directly to the drain region **331**, a portion of the active layer, the introduction of mobile ions into the active layer due to the drain wiring **343** being interrupted can be prevented in the structure of embodiment 1.

Next, as shown in FIG. **5C**, an EL layer **349**, a cathode (MgAg electrode) **350**, and a protecting electrode **351** are formed in succession without exposure to the atmosphere. It is preferable, at this point, to perform heat treatment of the pixel electrode **348**, completely removing all moisture, before forming the EL layer **349** and the cathode **350**. Note that a known material can be used as the EL layer **349**.


The materials explained in the "embodiment mode" section of this specification can be used as the EL layer **349**. In embodiment 1, an EL layer having a 4 layer structure of a hole injecting layer, a hole transporting layer, an emitting layer, and an electron transporting layer is used, as shown in FIG. **19**, but there are cases in which the electron transporting layer is not formed, and cases in which an electron injecting layer is also formed. Furthermore, there are also cases in which the hole injecting layer is omitted. Several examples of these types of combinations have already been reported, and any of these constitutions may be used.

An amine such as TPD (triphenylamine dielectric) may be used as the hole injecting layer or as the hole transporting layer, and in addition, a hydrazone (typically DEH), a stilbene (typically STB), or a starburst (typically m-MTDATA) can also be used. In particular, a starburst material, which has a high glass transition temperature and is difficult to crystallize, is preferable. Further, polyaniline (PANI), polythiophene (PE-DOT), and copper phthalocyanine (CuPc) may also be used.

BPPC, perylene, and DCM can be used as a red color emitting layer in the emitting layer, and in particular, the Eu complex shown by $\text{Eu}(\text{DBM})_3(\text{Phen})$ (refer to Kido, J., et. al, Appl. Phys., vol. 35, pp. L394-6, 1996 for details) is highly monochromatic, possessing a sharp emission at a wavelength of 620 nm.


Further, typically an Alq_3 (8-hydroxyquinoline aluminum) material in which quinacridone or coumarin is added at a level of several mol % can be used as a green color emitting layer.

The chemical formula is as shown below.



[formula 6]

In addition, typically a distile-arylene amino dielectric, in which amino substituted DSA is added to DSA (distile-arylene dielectric) can be used as a blue color emitting layer. In particular, it is preferable to use the high performance material distilyl-biphenyl (DPVBi). Its chemical formula is as shown below.



[formula 7]

Further, a 300 nm thick silicon nitride film is formed as a second passivation film **352**, and this may also be formed in succession, without exposure to the atmosphere, after formation of the protecting electrode **351**. The same materials as those of the second passivation film **49** of FIG. **1** can also be used, of course, as the second passivation film **352**.

A 4 layer structure made from a hole injecting layer, a hole transporting layer, an emitting layer, and an electron injecting layer is used in embodiment 1, but there are already examples of many combinations already reported, and any of these constitutions may also be used. Furthermore, an MgAg electrode is used as the cathode of the EL element in embodiment 1, but other known materials may also be used.

The protecting electrode **351** is formed in order to prevent deterioration of the MgAg electrode **350**, and a metallic film having aluminum as its principal constituent is typical. Other materials may, of course, also be used. Furthermore, the EL layer **349** and the MgAg electrode **350** are extremely weak with respect to moisture, and therefore it is preferable to perform successive formation up through to the protecting electrode **351** without exposure to the atmosphere, protecting the EL layer from external air.

Note that the film thickness of the EL layer **349** may be from 10 to 400 nm (typically between 60 and 160 nm), and that the thickness of the MgAg electrode **350** may be from 180 to 300 nm (typically between 200 and 250 nm).

The active matrix type EL display device with the structure shown in FIG. **5C** is thus completed. By arranging TFTs with optimal structure in not only the pixel portion, but also in the driver circuit portion, the active matrix type EL display device of embodiment 1 shows extremely high reliability, and the operational characteristics can be raised.

First, a TFT having a structure which reduces hot carrier injection as much as possible without a drop in the operation speed is used as an n-channel TFT **205** of the CMOS circuit forming the driver circuits. Note that the driver circuits referred to here include circuits such as a shift register, a buffer, a level shifter, and a sampling circuit (also referred to as a transfer gate). When digital driving is performed, signal conversion circuits such as a D/A converter circuit are also included.

In the case of embodiment 1, an active layer of the n-channel TFT **205** includes a source region **355**, a drain region **356**, an LDD region **357**, and a channel forming region **358**, as shown in FIG. **5C**, and the LDD region **357** overlaps the gate electrode **313**, sandwiching the gate insulating film **311**.

The formation of the LDD region on the drain side only is in consideration of not lowering the operation speed. Further, it is not necessary to be concerned with the value of the off current in the n-channel TFT **205**, and greater emphasis may be placed on the operation speed. It is therefore preferable that the LDD region **357** completely overlap the gate electrode **313**, reducing resistive components as much as possible. In other words, it is good to eliminate all offset.

Deterioration of a p-channel TFT **206** of the CMOS circuit due to hot carrier injection is almost of no concern, and in particular, therefore, an LDD region is not formed. It is also possible, of course, to take action against hot carriers by forming an LDD region similar to that of the n-channel TFT **205**.

Note that among the driver circuits, the sampling circuit is somewhat special when compared to the other circuits, and a large current flows in the channel forming region in both directions. Namely, the roles of the source region and the drain region change. In addition, it is necessary to suppress the value of the off current as much as possible, and with that in mind, it is preferable to arrange a TFT having functions at an intermediate level between the switching TFT and the current control TFT.

It is preferable, therefore, to arrange a TFT with the structure shown in FIG. 9 as an n-type TFT forming the sampling circuit. As shown in FIG. 9, a portion of LDD regions **901a** and **901b** overlap a gate electrode **903**, sandwiching a gate insulating film **902**. This effect is as stated in the explanation of the current control TFT **202**, and the case of the sampling circuit differs in the point of forming the LDD regions **901a** and **901b** with a shape that sandwiches a channel forming region **904**.

Further, a pixel with the structure shown in FIG. 1 is formed, forming a pixel portion. The structures of a switching TFT and a current control TFT formed within the pixel have already been explained in FIG. 1, and therefore that explanation is omitted here.

Note that, in practice, it is preferable to additionally perform packaging (sealing) after completing up through FIG. 5C by using a housing material such as a highly airtight protecting film (such as a laminar film or an ultraviolet hardened resin film) or a ceramic sealing can, so that there is no exposure to the atmosphere. By making the inside of the housing material an inert environment, and by placing an absorbing agent (for example, barium oxide) within the housing material, the reliability (life) of the EL layer is increased.

Furthermore, after the airtightness is increased by the packaging processing, a connector (a flexible printed circuit, FPC) for connecting between output terminals from elements or circuits formed on the substrate, and external signal terminals, is attached, completing a manufactured product. The EL display device in this state of being able to be shipped is referred to as an EL module throughout this specification.

The constitution of the active matrix type EL display device of embodiment 1 is explained here using the perspective view of FIG. 6. The active matrix type EL display device of embodiment 1 is formed on a glass substrate **601**, and is composed of a pixel portion **602**, a gate side driving circuit **603**, and a source side driving circuit **604**. A switching TFT **605** of the pixel portion is an n-channel TFT, and is placed at the intersection of a gate wiring **606** connected to the gate side driving circuit **603**, and a source wiring **607** of the source side driving circuit **604**. Furthermore, the drain of the switching TFT **605** is electrically connected to the gate of a current control TFT **608**.

In addition, the source of the current control TFT **608** is connected to a current supply line **609**, and an EL element **610** is electrically connected to the drain of the current control TFT **608**. Provided that the current control TFT **608** is an n-channel TFT, it is preferable to connect the cathode of the EL element **610** to the drain of the current control TFT **608** at this point. Further, if the current control TFT **608** is a p-channel TFT, then it is preferable to connect the anode of the EL element **610** to the drain of the current control TFT **608**.

Input wirings (connection wirings) **612** and **613**, and an input wiring **614** which is connected to the current supply line **609**, are then formed in an external input terminal FPC **611** in order to transfer signals to the driver circuits.

Shown in FIG. 7 is one example of the circuit composition of the EL display device shown in FIG. 6. The EL display device of embodiment 1 has a source side driving circuit **701**, a gate side driving circuit (A) **707**, a gate side driving circuit (B) **711**, and a pixel portion **706**. Note that, throughout this specification, driver circuit is a generic term which includes source side processing circuits and gate side processing circuits.

The source side driving circuit **701** is provided with a shift register **702**, a level shifter **703**, a buffer **704**, and a sampling circuit (transfer gate) **705**. In addition, the gate side driving circuit (A) **707** is provided with a shift register **708**, a level shifter **709**, and a buffer **710**. The gate side driving circuit (B) **711** has a similar composition.

The driving voltage is from 5 to 16 V (typically 10 V) for the shifter registers **702** and **708** here, and the structure shown by reference numeral **205** of FIG. 5C is suitable for an n-channel TFT used in a CMOS circuit forming the circuits.

Furthermore, the driving voltage becomes high at between 14 and 16 V for the level shifters **703** and **709**, and for the buffers **704** and **710**, and similar to the shifters, a CMOS circuit containing the n-channel TFT **205** of FIG. 5C is suitable. Note that the use of a multi-gate structure, such as a double gate structure or a triple gate structure for the gate wirings, is effective by increasing the reliability of each circuit.

The driving voltage is between 14 and 16 V for the sampling circuit **705**, but it is necessary to reduce the value of the off current because the source region and the drain region invert, and therefore a CMOS circuit containing the n-channel TFT **208** of FIG. 9 is suitable.

In addition, the driving voltage of the pixel portion **706** is between 14 and 16 V, and a pixel with the structure shown in FIG. 1 is arranged.

Note that the above constitutions can be easily realized by manufacturing TFTs in accordance with the manufacturing processes shown in FIGS. 3A to 5C. Furthermore, only the constitution of the pixel portion and the driver circuits is shown in embodiment 1, but it is also possible to form other logic circuits, in addition to the driving circuits, on the same substrate and in accordance with the manufacturing process of embodiment 1, such as a signal divider circuit, a D/A converter circuit, an op-amp circuit, and a γ compensation circuit. In addition, it is considered that circuits such as a memory portion and a microprocessor can also be formed.

An explanation of the EL module of embodiment 1, containing the housing material, is made using FIGS. 17A and 17B. Note that, when necessary, the symbols used in FIGS. 6 and 7 are cited.

A pixel portion **1701**, a source side driving circuit **1702**, and a gate side driving circuit **1703** are formed on a substrate (including a base film underneath a TFT) **1700**. Various wirings from the respective driver circuits are connected to external equipment, via the FPC **611**, through the input wirings **612** to **614**.

A housing material **1704** is formed at this point enclosing at least the pixel portion, and preferably the driving circuits and the pixel portion. Note that the housing material **1704** is of an irregular shape in which the internal size is larger than the external size of the EL element, or has a sheet shape, and is fixed to the substrate **1700** by an adhesive **1705** so as to form an airtight space jointly with the substrate **1700**. At this point, the EL element is in a state of being completely sealed in the

above airtight space, and is completely cutoff from the external atmosphere. Note that a multiple number of housing materials **1704** may be formed.

It is preferable to use an insulating substance such as a glass or a polymer as the housing material **1704**. The following can be given as examples: amorphous glass (such as borosilicate glass or quartz); crystallized glass; ceramic glass; organic resins (such as acrylic resins, styrene resins, polycarbonate resins, and epoxy resins); and silicone resins. In addition, ceramics may also be used. Furthermore, provided that the adhesive **1705** is an insulating material, it is also possible to use a metallic material such as a stainless alloy.

It is possible to use an adhesive such as an epoxy resin or an acrylate resin as the material of the adhesive **1705**. In addition, a thermally hardened resin or a light hardened resin can also be used as the adhesive. Note that it is necessary to use a material through which, as much as is possible, oxygen and moisture is not transmitted.

In addition, it is preferable to fill an opening **1706** between the housing material and the substrate **1700** with an inert gas (such as argon, helium, or nitrogen). There are no limitations on a gas, and it is also possible to use an inert liquid (such as a liquid fluorinated carbon, typically perfluoroalkane). The materials such as those used by Japanese Patent Application Laid-open No. Hei 8-78519 may be referred to regarding inert liquids. The space may also be filled with a resin.

It is effective to form drying agent in the opening **1706**. Materials such as those recorded in Japanese Patent Application Laid-open No. Hei 9-148066 can be used as the drying agent. Typically, barium oxide may be used. Furthermore, it is effective to form an antioxidizing agent as well, not just a drying agent.

A plural number of isolated pixels having EL elements are formed in the pixel portion, as shown in FIG. **17B**, and all of the pixels have a protecting electrode **1707** as a common electrode. In embodiment 1 it is preferable to form the EL layer, the cathode (MgAg electrode), and the protecting electrode in succession, without exposure to the atmosphere. The EL layer and the cathode are formed using the same mask material, and provided that only the protecting electrode is formed by a separate mask material, then the structure of FIG. **17B** can be realized.

The EL layer and the cathode may be formed only in the pixel portion at this point, and it is not necessary to form them on the driving circuits. There is no problem, of course, with forming them on the driving circuits, but considering the fact that alkaline metals are contained in the EL layer, it is preferable to not form it over the driving circuits.

Note that an input wiring **1709** is connected to the protecting electrode **1707** in a region shown by reference numeral **1708**. The input wiring **1709** is a wiring for providing a preset voltage to the protecting electrode **1707**, and is connected to the FPC **611** through a conducting paste material (typically an anisotropic conducting film) **1710**.

A manufacturing process for realizing a contact structure in the region **1708** is explained here using FIGS. **18A** to **18C**.

First, the state of FIG. **5A** is obtained in accordance with the processes of embodiment 1. At this point the first interlayer insulating film **336** and the gate insulating film **311** are removed from the edges of the substrate (in the region shown by reference numeral **1708** in FIG. **17B**), and the input wiring **1709** is formed on that region. The source wirings and the drain wirings of FIG. **5A** are of course formed at the same time. (See FIG. **18A**.)

Next, when etching the second interlayer insulating film **347** and the first passivation film **344** in FIG. **5B**, a region

shown by reference numeral **1801** is removed, and an open portion **1802** is formed. (See FIG. **18B**.)

The processes of forming the EL element (pixel electrode, EL layer, and cathode formation processes) in the pixel portion are performed in this state. A mask material is used in the region shown in FIGS. **18A** to **18C** at this time so that the EL element is not formed in this region. After forming the cathode **349**, the protecting electrode **350** is formed using a separate mask material. The protecting electrode **350** and the input wiring **1709** are thus electrically connected. Further, the second passivation film **352** is formed, and the state of FIG. **18C** is obtained.

The contact structure of the region shown by reference numeral **1708** in FIG. **17B** is thus realized by the above steps. The input wiring **1709** is then connected to the FPC **611** through the opening between the housing material **1704** and the substrate **1700** (note that this is filled by the adhesive **1705**; in other words, it is necessary for the thickness of the adhesive **1705** to be such that it can sufficiently level the step of the input wiring). Note that an explanation of the input wiring **1709** is made here, but the other input wirings **612** to **614** are also similarly connected to the FPC **611** by passing under the housing material **1704**.

Embodiment 2

In embodiment 2, an example of a pixel constitution is shown in FIG. **10** which differs from the constitution shown in FIG. **2B**.

The two pixels shown in FIG. **2B** are arranged with symmetry around the current supply line in embodiment 2. Namely, as shown in FIG. **10**, by making the current supply line **213** common between the two pixels neighboring the current supply line, the number of wirings needed can be reduced. Note that the structure of the TFTs placed inside the pixels may be left as is.

If this type of constitution is used, then it becomes possible to manufacture a very high definition pixel portion, increasing the image quality.

Note that the constitution of embodiment 2 can easily be realized in accordance with the manufacturing processes of embodiment 1, and that the explanations of embodiment 1 and of FIG. **1** may be referenced regarding points such as the structure of the TFTs.

Embodiment 3

A case of forming a pixel portion having a structure which differs from that of FIG. **1** is explained using FIG. **11** in embodiment 3. Note that processes up through the formation of the second interlayer insulating film **44** may be performed in accordance with embodiment 1. Furthermore, the structures of the switching TFT **201** and the current control TFT **202**, covered by the second interlayer insulating film **44**, are the same as those of FIG. **1**, and their explanation is therefore omitted.

In the case of embodiment 3, a pixel electrode **51**, a cathode **52**, and an EL layer **53** are formed after forming a contact hole in the second interlayer insulating film **44** and the first passivation film **41**. The cathode **52** and the EL layer **53** are formed in succession, without exposure to the atmosphere, by vacuum evaporation in embodiment 3, and at that time a red color emitting EL layer, a green color emitting EL layer, and a blue color emitting layer are formed selectively in separate pixels by using a mask material. Note that while only one pixel is shown in FIG. **11**, pixels with the same structure are formed corresponding to the colors of red, green, and blue,

23

respectively, and that color display can be performed by these pixels. A known material may be employed for each EL layer color.

A 150 nm thick aluminum alloy film (an aluminum film containing 1 wt % of titanium) is formed as the pixel electrode **51** in embodiment 3. Provided that it is a metallic material, any material may be used as the pixel electrode material, but it is preferable to use a material having a high reflectivity. Further, a 230 nm thick MgAg electrode is used as the cathode **52**, and the film thickness of the EL layer **53** is 90 nm (including, from the bottom, a 20 nm electron transporting layer, a 40 nm emitting layer, and a 30 nm hole transporting layer).

An anode **54** made from a transparent conducting film (an ITO film in embodiment 3) is formed next with a thickness of 110 nm. An EL element **209** is thus formed, and if a second passivation film **55** is formed by the same materials as shown in embodiment 1, then a pixel with the structure shown in FIG. **11** is completed.

When using the structure of embodiment 3, the red, green, or blue light generated by each pixel is irradiated in the opposite direction as that of the substrate on which the TFTs are formed. For that reason, almost the entire area inside the pixel, namely the region in which the TFTs are formed, can be used as an effective emitting region. As a result, there is a sharp increase in the effective emitting surface area of the pixel, and the brightness and the contrast ratio (the ratio between light and dark) of the image are increased.

Note that it is possible to freely combine the composition of embodiment 3 with the constitutions of any of embodiments 1 and 2.

Embodiment 4

A case of forming a pixel having a structure which differs from that of FIG. **2** of embodiment 1 is explained in embodiment 4 using FIGS. **12A** and **12B**.

In FIG. **12A**, reference numeral **1201** denotes a switching TFT, which comprises an active layer **56**, a gate electrode **57a**, a gate wiring **57b**, a source wiring **58**, and a drain wiring **59**. Further, reference numeral **1202** denotes a current control TFT, which comprises an active layer **60**, a gate electrode **61**, a source wiring **62**, and a drain wiring **63**. The source wiring **62** of the current control TFT **1202** is connected to a current supply line **64**, and the drain wiring **63** is connected to an EL element **65**. FIG. **12B** shows the circuit composition of this pixel.

The point of difference between FIG. **12A** and FIG. **2A** is the structure of the switching TFT. In embodiment 4 the gate electrode **57a** is formed with a fine line width between 0.1 and 5 μm , and the active layer **56** is formed so as to transverse that portion. The gate wiring **57b** is formed so as to electrically connect the gate electrode **57a** of each pixel. A triple gate structure which does not monopolize much surface area is thus realized.

Other portions are similar to those of FIG. **2A**, and the effective emitting surface area becomes larger because the surface area exclusively used by the switching TFT becomes smaller if the structure of embodiment 4 is employed. In other words, the image brightness is increased. Furthermore, a gate structure in which redundancy is increased in order to reduce the value of the off current can be realized, and therefore the image quality can be increased even further.

Note that, in the constitution of embodiment 4, the current supply line **64** can be made common between neighboring pixels, as in embodiment 2, and that a structure like that of

24

embodiment 3 may also be used. Furthermore, processes of manufacturing may be performed in accordance with those of embodiment 1.

Embodiment 5

Cases in which a top gate type TFT is used are explained in embodiments 1 to 4, and the present invention may also be implemented using a bottom gate type TFT. A case of implementing the present invention by using a reverse stagger type TFT is explained in embodiment 5 using FIG. **13**. Note that, except for the structure of the TFT, the structure is the same as that of FIG. **1**, and therefore the same symbols as those of FIG. **1** are used when necessary.

In FIG. **13**, the similar materials as those of FIG. **1** can be used in the substrate **11** and in the base film **12**. A switching TFT **1301** and a current control TFT **1302** are then formed on the base film **12**.

The switching TFT **1301** comprises: gate electrodes **70a** and **70b**; a gate wiring **71**; a gate insulating film **72**; a source region **73**; a drain region **74**; LDD regions **75a** to **75d**; a high concentration impurity region **76**; channel forming regions **77a** and **77b**; channel protecting films **78a** and **78b**; a first interlayer insulating film **79**; a source wiring **80**; and a drain wiring **81**.

Further, the current control TFT **1302** comprises: a gate electrode **82**; the gate insulating film **72**; a source region **83**; a drain region **84**; an LDD region **85**; a channel forming region **86**; a channel protecting film **87**; a first interlayer insulating film **79**; a source wiring **88**; and a drain wiring **89**. The gate electrode **82** is electrically connected to the drain wiring **81** of the switching TFT **1301** at this point.

Note that the above switching TFT **1301** and the current control TFT **1302** may be formed in accordance with a known method of manufacturing a reverse stagger type TFT. Further, similar materials used in corresponding portions of the top gate type TFTs of embodiment 1 can be used for the materials of each portion (such as wirings, insulating films, and active layers) formed in the above TFTs. Note that the channel protecting films **78a**, **78b**, and **87**, which are not in the constitution of the top gate type TFT, may be formed by an insulating film containing silicon. Furthermore, regarding the formation of impurity regions such as the source regions, the drain regions, and the LDD regions, they may be formed by using a photolithography technique and individually changing the impurity concentration.

When the TFTs are completed, a pixel having an EL element **1303** in which the first passivation film **41**, the insulating film (leveling film) **44**, the second passivation film **49**, the pixel electrode (anode) **46**, the EL layer **47**, the MgAg electrode (cathode) **45**, the aluminum electrode (protecting film) **48**, and the third passivation film **SO** are formed in order, is completed. Embodiment 1 may be referred to with respect to manufacturing processes and materials for the above.

Note that it is possible to freely combine the constitution of embodiment 5 with the constitution of any of embodiments 2 to 4.

Embodiment 6

It is effective to use a material having a high thermal radiating effect, similar to that of the first passivation film **41** and the second passivation film **49**, as the base film formed between the active layer and the substrate in the structures of FIG. **5C** of embodiment 1 or FIG. **1**. In particular, a large amount of current flows in the current control TFT, and therefore heat is easily generated, and deterioration due to self

25

generation of heat can become a problem. Thermal deterioration of the TFT can be prevented by using the base film of embodiment 6, which has a thermal radiating effect, for this type of case.

The effect of protecting from the diffusion of mobile ions from the substrate is also very important, of course, and therefore it is preferable to use a lamination structure of a compound including Si, Al, N, O, and M, and an insulating film containing silicon, similar to the first passivation film 41.

Note that it is possible to freely combine the constitution of embodiment 6 with the constitution of any of embodiments 1 to 5.

Embodiment 7

When the pixel structure shown in embodiment 3 is used, the light emitted from the EL layer is radiated in the direction opposite to the substrate, and therefore it is not necessary to pay attention to the transmissivity of materials, such as the insulating film, which exist between the substrate and the pixel electrode. In other words, materials which have a somewhat low transmissivity can also be used.

It is therefore advantageous to use a carbon film, such as one referred to as a diamond thin film, a diamond-like carbon film, or an amorphous carbon film, as the base film 12 or the first passivation film 41. In other words, because it is not necessary to worry about lowering the transmissivity, the film thickness can be set thick, to between 100 and 500 nm, and it is possible to have a very high thermal radiating effect.

Regarding the use of the above carbon films in the second passivation film 49, note that a reduction in the transmissivity must be avoided, and therefore it is preferable to set the film thickness to between 5 and 100 nm.

Note that, in embodiment 7, it is effective to laminate with another insulating film when a carbon film is used in any of the base film 12, the first passivation film 41 and the second passivation film 49.

In addition, embodiment 7 is effective when the pixel structure shown in embodiment 3 is used, and for other constitutions, it is possible to freely combine the constitution of embodiment 7 with the constitution of any of embodiments 1 to 6.

Embodiment 8

The amount of the off current value in the switching TFT in the pixel of the EL display device is reduced by using a multi-gate structure for the switching TFT, and the present invention is characterized by the elimination of the need for a storage capacitor. This is a device for making good use of the surface area, reserved for the storage capacitor, as an emitting region.

However, even if the storage capacitor is not completely eliminated, an effect of increasing the effective emitting surface area, by the amount that the exclusive surface area is made smaller, can be obtained. In other words, the object of the present invention can be sufficiently achieved by reducing the value of the off current by using a multi-gate structure for the switching TFT, and by only shrinking the exclusive surface area of the storage capacitor.

It is therefore possible to use a pixel structure such as that shown in FIG. 14. Note that, when necessary, the same symbols are used in FIG. 14 as in FIG. 1.

The different point between FIG. 14 and FIG. 1 is the existence of a storage capacitor 1401 connected to the switching TFT. The storage capacitor 1401 is formed by a semiconductor region (lower electrode) extended from the drain

26

region 14 of the switching TFT 201, the gate insulating film 18, and a capacitor electrode (upper electrode) 1403. The capacitor electrode 1403 is formed at the same time as the gate electrodes 19a, 19b, and 35 of the TFT.

A top view is shown in FIG. 15A. The cross sectional diagram taken along the line A-A' in the top view of FIG. 15A corresponds to FIG. 14. As shown in FIG. 15A, the capacitor electrode 1403 is electrically connected to the source region 31 of the current control TFT through a connecting wiring 1404 which is electrically connected to the capacitor electrode 1403. Note that the connection wiring 1404 is formed at the same time as the source wirings 21 and 36, and the drain wirings 22 and 37. Furthermore, FIG. 15B shows the circuit constitution of the top view shown in FIG. 15A.

Note that the constitution of embodiment 8 can be freely combined with the constitution of any of embodiments 1 to 7. In other words, only the storage capacitor is formed within the pixel, no limitations are added with regard to the TFT structure or the EL layer materials.

Embodiment 9

Laser crystallization is used as the means of forming the crystalline silicon film 302 in embodiment 1, and a case of using a different means of crystallization is explained in embodiment 9.

After forming an amorphous silicon film in embodiment 9, crystallization is performed using the technique recorded in Japanese Patent Application Laid-open No. Hei 7-130652. The technique recorded in the above patent application is one of obtaining a crystalline silicon film having good crystallinity by using an element such as nickel as a catalyst for promoting crystallization.

Further, after the crystallization process is completed, a process of removing the catalyst used in the crystallization may be performed. In this case, the catalyst may be gettered using the technique recorded in Japanese Patent Application Laid-open No. Hei 10-270363 or Japanese Patent Application Laid-open No. Hei 8-330602.

In addition, a TFT may be formed using the technique recorded in the specification of Japanese Patent Application Laid-open No. Hei 11-076967 by the applicant of the present invention.

The processes of manufacturing shown in embodiment 1 are one embodiment of the present invention, and provided that the structure of FIG. 1 or of FIG. 5C of embodiment 1 can be realized, then other manufacturing process may also be used without any problems, as above.

Note that it is possible to freely combine the constitution of embodiment 9 with the constitution of any of embodiments 1 to 8.

Embodiment 10

In driving the EL display device of the present invention, analog driving can be performed using an analog signal as an image signal, and digital driving can be performed using a digital signal.

When analog driving is performed, the analog signal is sent to a source wiring of a switching TFT, and the analog signal, which contains gray scale information, becomes the gate voltage of a current control TFT. The current flowing in an EL element is then controlled by the current control TFT, the EL element emitting intensity is controlled, and gray scale display is performed. In this case, it is preferable to operate the current control TFT in a saturation region. In other words, it is preferable to operate the TFT within the conditions of

27

$|V_{ds}| > |V_{gs} - V_{th}|$. Note that V_{ds} is the voltage difference between a source region and a drain region, V_{gs} is the voltage difference between the source region and a gate electrode, and V_{th} is the threshold voltage of the TFT.

On the other hand, when digital driving is performed, it differs from the analog type gray scale display, and gray scale display is performed by time division driving (time ratio gray scale driving) or surface area ratio gray scale driving. Namely, by regulating the length of the emission time or the ratio of emitting surface area, color gray scales can be made to be seen visually as changing. In this case, it is preferable to operate the current control TFT in the linear region. In other words, it is preferable to operate the TFT within the conditions of $|V_{ds}| < |V_{gs} - V_{th}|$.

The EL element has an extremely fast response speed in comparison to a liquid crystal element, and therefore it is possible to have high speed driving. Therefore, the EL element is one which is suitable for time ratio gray scale driving, in which one frame is partitioned into a plural number of subframes and then gray scale display is performed. Furthermore, it has the advantage of the period of one frame being short, and therefore the amount of time for which the gate voltage of the current control TFT is maintained is also short, and a storage capacitor can be made smaller or eliminated.

The present invention is a technique related to the element structure and therefore any method of driving it may thus be used.

Embodiment 11

In embodiment 11, examples of the pixel structure of the EL display device of the present invention are shown in FIGS. 21A and 21B. Note that in embodiment 11, reference numeral 4701 denotes a source wiring of a switching TFT 4702, reference numeral 4703 denotes a gate wiring of the switching TFT 4702, reference numeral 4704 denotes a current control TFT, 4705 denotes an electric current supply line, 4706 denotes a power source control TFT, 4707 denotes a power source control gate wiring, and 4708 denotes an EL element. Japanese Patent Application Laid-open No. Hei 11-341272 may be referred to regarding the operation of the power source control TFT 4706.

Further, in embodiment 11 the power source control TFT 4706 is formed between the current control TFT 4704 and the EL element 4708, but a structure in which the current control TFT 4704 is formed between the power source control TFT 4706 and the EL element 4708 may also be used. In addition, it is preferable for the power source control TFT 4706 to have the same structure as the current control TFT 4704, or for both to be formed in series by the same active layer.

FIG. 21A is an example of a case in which the electric current supply line 4705 is common between two pixels. Namely, this is characterized in that the two pixels are formed having linear symmetry around the electric current supply line 4705. In this case, the number of electric current supply lines can be reduced, and therefore the pixel portion can be made even more high precision.

Furthermore, FIG. 21B is an example of a case in which an electric current supply line 4710 is formed parallel to the gate wiring 4703, and in which a power source control gate wiring 4711 is formed parallel to the source wiring 4701. Note that in FIG. 23B, the structure is formed such that the electric current supply line 4710 and the gate wiring 4703 do not overlap, but provided that both are wirings formed on different layers, then they can be formed to overlap, sandwiching an insulating film. In this case, the exclusive surface area of the electric

28

current supply line 4710 and the gate wiring 4703 can be shared, and the pixel section can be made even more high precision.

Embodiment 12

In embodiment 12, examples of the pixel structure of the EL display device of the present invention are shown in FIGS. 22A and 22B. Note that in embodiment 12, reference numeral 4801 denotes a source wiring of a switching TFT 4802, reference numeral 4803 denotes a gate wiring of the switching TFT 4802, reference numeral 4804 denotes a current control TFT, 4805 denotes an electric current supply line, 4806 denotes an erasure TFT, 4807 denotes an erasure gate wiring, and 4808 denotes an EL element. Japanese Patent Application Laid-open No. Hei 11-338786 may be referred to regarding the operation of the erasure TFT 4806.

The drain of the erasure TFT 4806 is connected to a gate of the current control TFT 4804, and it becomes possible to forcibly change the gate voltage of the current control TFT 4804. Note that an n-channel TFT or a p-channel TFT may be used for the erasure TFT 4806, but it is preferable to make it the same structure as the switching TFT 4802 so that the off current value can be made smaller.

FIG. 22A is an example of a case in which the electric current supply line 4805 is common between two pixels. Namely, this is characterized in that the two pixels are formed having linear symmetry around the electric current supply line 4805. In this case, the number of electric current supply lines can be reduced, and therefore the pixel section can be made even more high precision.

In addition, FIG. 22B is an example of a case in which an electric current supply line 4810 is formed parallel to the gate wiring 4803, and in which an erasure gate wiring 4811 is formed parallel to the source wiring 4801. Note that in FIG. 22B, the structure is formed such that the electric current supply line 4810 and the gate wiring 4803 do not overlap, but provided that both are wirings formed on different layers, then they can be formed to overlap, sandwiching an insulating film. In this case, the exclusive surface area of the electric current supply line 4810 and the gate wiring 4803 can be shared, and the pixel section can be made even more high precision.

Embodiment 13

The EL display device of the present invention may have a structure in which several TFTs are formed within a pixel. In embodiments 11 and 12, examples of forming three TFTs are shown, but from 4 to 6 TFTs may also be formed. It is possible to implement the present invention without placing any limitations on the structure of the pixels of the EL display device.

Embodiment 14

An example of using a p-channel TFT as the current control TFT 202 of FIG. 1 is explained in embodiment 14. Note that other portions are the same as those of FIG. 1, and therefore a detailed explanation of the other portions is omitted.

A cross sectional structure of the pixel of embodiment 14 is shown in FIG. 23. Embodiment 1 may be referred to for a method of manufacturing the p-channel TFT used in embodiment 14. An active layer of the p-channel TFT comprises a source region 2801, a drain region 2802, and a channel forming region 2803, and the source region 2801 is connected to the source wiring 36, and the drain region 2802 is connected to the drain wiring 37.

29

For cases in which the anode of an EL element is connected to the current control TFT, it is preferable to use the p-channel TFT as the current control TFT.

Note that it is possible to implement the constitution of embodiment 14 by freely combining it with the constitution of any of embodiments 1 to 13.


Embodiment 15

By using an EL material in which phosphorescence from a triplet state exciton can be utilized in light emission in embodiment 15, the external emission quantum efficiency can be increased by a great amount. By doing so, it becomes possible to make the EL element into a low power consumption, long life, and low weight EL element.

Reports of utilizing triplet state excitons and increasing the external emission quantum efficiency is shown in the following papers.

Tsutsui, T., Adachi, C., and Saito, S., Photochemical Processes in Organized Molecular Systems, Ed. Honda, K., (Elsevier Sci. Pub., Tokyo, 1991), p. 437.


The molecular formula of the EL material (coumarin pigment) reported in the above paper is shown below.



[formula 8]

Baldo, M. A., O'Brien, D. F., You, Y., Shoustikov, A., Sibley, S., Thompson, M. E., and Forrest, S. R., Nature 395 (1998) p. 151.

The molecular formula of the EL material (Pt complex) reported in the above paper is shown below.



[formula 9]


Baldo, M. A., Lamansky, S., Burrows, P. E., Thompson, M. E., and Forrest, S. R., Appl. Phys. Lett., 75 (1999) p. 4.

Tsutsui, T., Yang, M. J., Yahiro, M., Nakamura, K., Watanabe, T., Tsuji, T., Fukuda, Y., Wakimoto, T., Mayaguchi, S., Jpn. Appl. Phys., 38 (12B) (1999) L1502.

The molecular formula of the EL material (Ir complex) reported in the above paper is shown below.

30

[formula 10]



Provided that the phosphorescence emission from triplet state excitons can be utilized, then in principle it is possible to realize an external emission quantum efficiency which is 3 to 4 times higher than that for cases of using the fluorescence emission from singlet state excitons. Note that it is possible to implement the constitution of embodiment 15 by freely combining it with the constitution of any of embodiments 1 to 13.

Embodiment 16

In embodiment 1 it is preferable to use an organic EL material as an EL layer, but the present invention can also be implemented using an inorganic EL material. However, current inorganic EL materials have an extremely high driving voltage, and therefore a TFT which has voltage resistance characteristics that can withstand the driving voltage must be used in cases of performing analog driving.

Alternatively, if inorganic EL materials having lower driving voltages than conventional inorganic EL materials are developed, then it is possible to apply them to the present invention.

Further, it is possible to freely combine the constitution of embodiment 16 with the constitution of any of embodiments 1 to 14.

Embodiment 17

An active matrix type EL display device (EL module) formed by implementing the present invention has superior visibility in bright locations in comparison to a liquid crystal display device because it is a self-emitting type device. It therefore has a wide range of uses as a direct-view type EL display (indicating a display incorporating an EL module).

Note that a wide viewing angle can be given as one advantage which the EL display has over a liquid crystal display. The EL display of the present invention may therefore be used as a display (display monitor) having a diagonal equal to 30 inches or greater (typically equal to 40 inches or greater) for appreciation of TV broadcasts by large screen.

Further, not only can it be used as an EL display (such as a personal computer monitor, a TV broadcast reception monitor, or an advertisement display monitor), it can be used as a display for various electronic devices.

The following can be given as examples of such electronic devices: a video camera; a digital camera; a goggle type display (head mounted display); a car navigation system; a personal computer; a portable information terminal (such as a mobile computer, a mobile telephone, or an electronic book); and an image playback device using a recording medium (specifically, a device which performs playback of a recording medium and is provided with a display which can display

those images, such as a compact disk (CD), a laser disk (LD), or a digital video disk (DVD)). Examples of these electronic devices are shown in FIGS. 16A to 16F.

FIG. 16A is a personal computer, comprising a main body 2001, a casing 2002, a display portion 2003, and a keyboard 2004. The present invention can be used in the display portion 2003.

FIG. 16B is a video camera, comprising a main body 2101, a display portion 2102, an audio input portion 2103, operation switches 2104, a battery 2105, and an image receiving portion 2106. The present invention can be used in the display portion 2102.

FIG. 16C is a goggle display, comprising a main body 2201, a display portion 2202, and an arm portion 2203. The present invention can be used in the display portion 2202.

FIG. 16D is a mobile computer, comprising a main body 2301, a camera portion 2302, an image receiving portion 2303, operation switches 2304, and a display portion 2305. The present invention can be used in the display portion 2305.

FIG. 16E is an image playback device (specifically, a DVD playback device) provided with a recording medium, comprising a main body 2401, a recording medium (such as a CD, an LD, or a DVD) 2402, operation switches 2403, a display portion (a) 2404, and a display portion (b) 2405. The display portion (a) is mainly used for displaying image information, and the image portion (b) is mainly used for displaying character information, and the present invention can be used in the image portion (a) and in the image portion (b). Note that the present invention can be used as an image playback device provided with a recording medium in devices such as a CD playback device and game equipment.

FIG. 16F is an EL display, containing a casing 2501, a support stand 2502, and a display portion 2503. The present invention can be used in the display portion 2503. The EL display of the present invention is especially advantageous for cases in which the screen is made large, and is favorable for displays having a diagonal greater than or equal to 10 inches (especially one which is greater than or equal to 30 inches).

Furthermore, if the emission luminance of EL materials becomes higher in future, then it will become possible to use the present invention in a front type or a rear type projector.

The above electronic devices are becoming more often used to display information provided through an electronic transmission circuit such as the Internet or CATV (cable television), and in particular, opportunities for displaying animation information are increasing. The response speed of EL materials is extremely high, and therefore EL displays are suitable for performing this type of display.

The emitting portion of the EL display device consumes power, and therefore it is preferable to display information so as to have the emitting portion become as small as possible. Therefore, when using the EL display device in a display portion which mainly displays character information, such as a portable information terminal, in particular, a portable telephone of a car audio system, it is preferable to drive it by setting non-emitting portions as background and forming character information in emitting portions.

FIG. 20A is a portable telephone, comprising a main body 2601, an audio output portion 2602, an audio input portion 2603, a display portion 2604, operation switches 2605, and an antenna 2606. The EL display device of the present invention can be used in the display portion 2604. Note that by displaying white characters in a black background in the display portion 2604, the power consumption of the portable telephone can be reduced.

FIG. 20B is an on-board audio system (car audio system), containing a main body 2701, a display portion 2702, and

operation switches 2703 and 2704. The EL display device of the present invention can be used in the display portion 2702. Furthermore, an on-board audio system is shown in embodiment 17, but a desktop type audio system may also be used. Note that by displaying white characters in a black background in the display portion 2702, the power consumption can be reduced.

The range of applications of the present invention is thus extremely wide, and it is possible to apply the present invention to electronic devices in all fields. Furthermore, the electronic devices of embodiment 17 can be realized by using any constitution of any combination of embodiments 1 to 16.

By using the present invention, it becomes possible to form a pixel in which TFTs, having optimal performance in response to the specifications required by elements, are formed on the same substrate, and the operation performance and reliability of an active matrix type EL display device can be greatly increased.

Furthermore, by using this type of EL display device as a display, it becomes possible to produce applied products (electronic equipment) having good image quality and durability (high reliability).

What is claimed is:

1. A display device comprising:

- a substrate;
- a base film over the substrate;
- a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises
 - a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode,
 - a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,
 - a pixel electrode electrically connected to the second source electrode or the second drain electrode,
 - a light emitting layer comprising an organic material formed over the pixel electrode, and
 - a second electrode over the light emitting layer comprising the organic material;
- a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and
- a housing material opposed to the substrate and adhered to the substrate by an adhesive, thereby forming an airtight space between the substrate and the housing material, wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive, wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor,
- wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series, and
- wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the adhesive.

2. The display device according to claim 1,

wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.

3. The display device according to claim 1,

wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation system, a personal computer, a portable information terminal and an image playback device using a recording medium.

33

4. The display device according to claim 1, wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit.
5. The display device according to claim 1, wherein the first active layer comprises a polycrystalline semiconductor.
6. The display device according to claim 1, wherein the second active layer comprises a polycrystalline semiconductor.
7. A display device comprising:
 - a substrate;
 - a base film over the substrate;
 - a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises
 - a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode,
 - a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,
 - a pixel electrode electrically connected to the second source electrode or the second drain electrode,
 - a light emitting layer comprising an organic material formed over the pixel electrode, and
 - a second electrode over the light emitting layer comprising the organic material;
 - a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and
 - a glass opposed to the substrate and adhered to the substrate by an adhesive, thereby forming an airtight space between the substrate and the glass,
 wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive, wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor, wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series, and wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the adhesive.
8. The display device according to claim 7, wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.
9. The display device according to claim 7, wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation system, a personal computer, a portable information terminal and an image playback device using a recording medium.
10. The display device according to claim 7, wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit.
11. The display device according to claim 7, wherein the first active layer comprises a polycrystalline semiconductor.
12. The display device according to claim 7, wherein the second active layer comprises a polycrystalline semiconductor.
13. A display device comprising:
 - a substrate;
 - a base film over the substrate;
 - a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises

34

- a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode,
 - a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,
 - a pixel electrode electrically connected to the second source electrode or the second drain electrode,
 - a light emitting layer comprising an organic material formed over the pixel electrode, and
 - a second electrode over the light emitting layer comprising the organic material;
- a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and
- a housing material opposed to the substrate and adhered to the substrate by epoxy resin, thereby forming an airtight space between the substrate and the housing material, wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive, wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor, wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series, and wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the epoxy resin.
14. The display device according to claim 13, wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.
15. The display device according to claim 13, wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation system, a personal computer, a portable information terminal and an image playback device using a recording medium.
16. The display device according to claim 13, wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit.
17. The display device according to claim 13, wherein the first active layer comprises a polycrystalline semiconductor.
18. The display device according to claim 13, wherein the second active layer comprises a polycrystalline semiconductor.
19. A display device comprising:
 - a substrate;
 - a base film over the substrate;
 - a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises
 - a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode,
 - a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,
 - a pixel electrode electrically connected to the second source electrode or the second drain electrode,
 - a light emitting layer comprising an organic material formed over the pixel electrode, and
 - a second electrode over the light emitting layer comprising the organic material;
 - a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and

35

a housing material opposed to the substrate and adhered to the substrate by an adhesive, thereby forming an airtight space filled with an inert gas between the substrate and the housing material,

wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive,

wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor,

wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series, and

wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the adhesive.

20. The display device according to claim 19,

wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.

21. The display device according to claim 19,

wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation system, a personal computer, a portable information terminal and an image playback device using a recording medium.

22. The display device according to claim 19,

wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit.

23. The display device according to claim 19,

wherein the first active layer comprises a polycrystalline semiconductor.

24. The display device according to claim 19,

wherein the second active layer comprises a polycrystalline semiconductor.

25. A display device comprising:

a substrate;

a base film over the substrate;

a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises

a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode,

a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,

a pixel electrode electrically connected to the second source electrode or the second drain electrode,

a light emitting layer comprising an organic material formed over the pixel electrode, and

a second electrode over the light emitting layer comprising the organic material,

a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and

a housing material opposed to the substrate and adhered to the substrate by an adhesive, thereby forming an airtight space filled with an inert liquid between the substrate and the housing material,

wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive,

wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor,

wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series, and

36

wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the adhesive.

26. The display device according to claim 25,

wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.

27. The display device according to claim 25,

wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation system, a personal computer, a portable information terminal and an image playback device using a recording medium.

28. The display device according to claim 25,

wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit.

29. The display device according to claim 25,

wherein the first active layer comprises a polycrystalline semiconductor.

30. The display device according to claim 25,

wherein the second active layer comprises a polycrystalline semiconductor.

31. A display device comprising:

a substrate;

a base film over the substrate;

a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises

a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode,

a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,

a pixel electrode electrically connected to the second source electrode or the second drain electrode,

a light emitting layer comprising an organic material formed over the pixel electrode, and

a second electrode over the light emitting layer comprising the organic material;

a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and

a housing material opposed to the substrate and adhered to the substrate by an adhesive, thereby forming an airtight space between the substrate and the housing material,

wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive,

wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor,

wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series,

wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the adhesive, and

wherein drying agent is provided in the airtight space.

32. The display device according to claim 31,

wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.

33. The display device according to claim 31,

wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation

37

system, a personal computer, a portable information terminal and an image playback device using a recording medium.

34. The display device according to claim 31, wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit. 5

35. The display device according to claim 31, wherein the first active layer comprises a polycrystalline semiconductor.

36. The display device according to claim 31, wherein the second active layer comprises a polycrystalline semiconductor. 10

37. A display device comprising:

a substrate;

a base film over the substrate; 15

a plurality of pixel regions over the base film, wherein each of the plurality of pixel regions comprises

a first thin film transistor which has a first active layer, a first source electrode, and a first drain electrode, 20

a second thin film transistor which has a second active layer, a second source electrode, a second drain electrode, and a gate electrode,

an interlayer insulating film over the first thin film transistor and the second thin film transistor, 25

a pixel electrode over the interlayer insulating film electrically connected to the second source electrode or the second drain electrode,

a light emitting layer comprising an organic material formed over the pixel electrode, and 30

a second electrode over the light emitting layer comprising the organic material;

a driving circuit for driving the plurality of pixel regions, the driving circuit comprising a third thin film transistor over the substrate; and

38

a housing material opposed to the substrate and adhered to the substrate by an adhesive, thereby forming an airtight space between the substrate and the housing material, wherein the base film is interposed between the substrate and the adhesive and in contact with the adhesive, wherein one of the first source electrode and the first drain electrode is connected to the gate electrode of the second thin film transistor,

wherein the first thin film transistor has a multi gate structure in which the first active layer has a plurality of channel regions connected in series, and wherein the plurality of pixel regions and at least a part of the driving circuit are located in a region surrounded by the adhesive.

38. The display device according to claim 37,

wherein the second thin film transistor has a multi gate structure in which the second active layer has a plurality of channel regions connected in series.

39. The display device according to claim 37,

wherein the display device is used as a display for one selected from the group consisting of a video camera, a digital camera, a goggle type display, a car navigation system, a personal computer, a portable information terminal and an image playback device using a recording medium.

40. The display device according to claim 37,

wherein the driving circuit comprises a gate side driving circuit and a source side driving circuit.

41. The display device according to claim 37,

wherein the first active layer comprises a polycrystalline semiconductor.

42. The display device according to claim 37,

wherein the second active layer comprises a polycrystalline semiconductor.

* * * * *

专利名称(译)	有源矩阵显示装置，具有改进的操作性能		
公开(公告)号	US7701134	公开(公告)日	2010-04-20
申请号	US11/074687	申请日	2005-03-09
[标]申请(专利权)人(译)	株式会社半导体能源研究所		
申请(专利权)人(译)	半导体能源研究所有限公司.		
当前申请(专利权)人(译)	半导体能源研究所有限公司.		
[标]发明人	YAMAZAKI SHUNPEI KOYAMA JUN YAMAMOTO KUNITAKA KONUMA TOSHIMITSU		
发明人	YAMAZAKI, SHUNPEI KOYAMA, JUN YAMAMOTO, KUNITAKA KONUMA, TOSHIMITSU		
IPC分类号	H05B33/04 H01L31/12 H05B33/26 H01L21/77 H01L27/12 H01L27/32 H01L29/423 H01L29/786 H01L51/52		
CPC分类号	H01L27/1255 H01L27/3262 H01L29/42384 H01L29/78621 H01L29/78627 H01L29/78645 H01L29/78696 H01L51/524 H01L51/5246 H01L51/5259 H01L33/08 H01L27/3244 H01L27/1218 H01L27/322 H01L27/3248 H01L51/5237 H01L51/529 H01L2251/5315 H01L2924/0002 H01L2924/00		
优先权	1999158787 1999-06-04 JP		
其他公开文献	US20050161672A1		
外部链接	Espacenet USPTO		

摘要(译)

本发明的一个目的是提供一种具有高操作性能和可靠性的EL显示器件。形成在像素内的开关TFT201具有多栅极结构，该结构对降低截止电流值具有重要性。此外，电流控制TFT202的沟道宽度比开关TFT的沟道宽度宽，以形成适合于流动电流的结构。此外，电流控制TFT 202的LDD区33形成与栅电极35的一部分重叠，以形成对防止热载流子注入和降低OFF电流值起重要作用的结构。

