



(19) **United States**(12) **Patent Application Publication** (10) **Pub. No.: US 2003/0194580 A1**  
Hamada et al. (43) **Pub. Date: Oct. 16, 2003**(54) **LUMINESCENT MATERIAL FOR LIGHT  
EMITTING DEVICE AND ORGANIC  
ELECTROLUMINESCENT DEVICE**(75) Inventors: **Yuji Hamada**, Ikoma-gun (JP);  
**Noriyuki Matsusue**, Hirakata-City (JP);  
**Kazuki Nishimura**, Hirakata-City (JP)Correspondence Address:  
**FASSE PATENT ATTORNEYS, P.A.**  
**P.O. BOX 726**  
**HAMPDEN, ME 04444-0726 (US)**(73) Assignee: **SANYO ELECTRIC CO., LTD.**,  
Moriguchi-City (JP)(21) Appl. No.: **10/376,099**(22) Filed: **Feb. 26, 2003**(30) **Foreign Application Priority Data**

Feb. 27, 2002 (JP) ..... 51802/2002


**Publication Classification**(51) **Int. Cl.<sup>7</sup>** ..... **H05B 33/14; C09K 11/06**(52) **U.S. Cl.** ..... **428/690; 428/917; 252/301.16;**  
313/504; 257/102; 546/2(57) **ABSTRACT**A luminescent material for light emitting device represented  
by the following general formula (1) or (2).

(1)


-continued



(2)

(wherein  $R_1$ ,  $R_2$  and  $R_3$  are H,  $C_nH_{2n+1}$  ( $n$  is an integer of 1 to 10),  $N(C_nH_{2n+1})_2$  ( $n$  is an integer of 1 to 10),  $COOC_nH_{2n+1}$  ( $n$  is an integer of 1 to 10), F, Cl, Br, I, CN, a phenyl group, a naphthyl group or the like, and D is a ligand represented by the following general formula (17) or (18).)

(17)



(18)

wherein  $R_4$ ,  $R_5$  and  $R_6$  are H,  $C_nH_{2n+1}$  ( $n$  is an integer of 1 to 10),  $N(C_nH_{2n+1})_2$  ( $n$  is an integer of 1 to 10),  $COOC_nH_{2n+1}$  ( $n$  is an integer of 1 to 10), F, Cl, Br, I, CN,  $CF_3$ , a furyl group, a thienyl group, a phenyl group, a naphthyl group or the like.).

**LUMINESCENT MATERIAL FOR LIGHT  
EMITTING DEVICE AND ORGANIC  
ELECTROLUMINESCENT DEVICE**

**BACKGROUND OF THE INVENTION**

[0001] 1. Field of the Invention

[0002] The present invention relates to a luminescent material used for light emitting devices such as organic electroluminescent (EL) devices and electrochemiluminescent (ECL) devices.

[0003] 2. Related Art

[0004] In recent years, semiconductor circuits have had greater density, and hence miniaturization and portability of sophisticated information terminals are enabled. In such circumstances, researches on a display device of low-profile, light weight and low power consumption are actively conducted. For example, a liquid crystal display (LCD) is widely applied to displays of small-sized portable devices and notebook computers, and have developed such that it is even replacement to a cathode ray tube (CRT) display. In addition, as a display device of next generation type that can support moving pictures, organic EL devices attract attention.


[0005] An electrochemiluminescent (ECL) device is also one of such type of devices. Likewise the organic EL device, an ECL device is also a self-luminescent device, and the primary characteristic of the ECL device is that the light emission is obtained from a solution.

[0006] As a luminescent material used for the above-mentioned light emitting device such as organic EL device, those exhibiting high brightness in response to applied voltage and current, or those having high luminous efficiency are requested. As such a luminescent material, materials which emit light from the triplet state, such as Tris (2-phenylpyridine) iridium: Ir(ppy)<sub>3</sub> and the like, are known.

**SUMMARY OF THE INVENTION**


[0007] It is an object of the present invention to provide a novel luminescent material for light emitting device having high luminous efficiency and a light emitting device using the same.

[0008] Luminescent materials for light emitting device according to the present invention are iridium-containing organic metal compounds represented by the following general formulae (1) to (16) as follows:




(1)


-continued




(2)




(3)




(4)



(5)




(6)




(7)

-continued




(8)


-continued




(13)




(9)




(14)




(10)




(15)



(11)




(16)




(12)

[0009] (wherein  $R_1$ ,  $R_2$  and  $R_3$  are H,  $C_nH_{2n+1}$  (n is preferably an integer of 1 to 10, more preferably an integer of 1 to 5),  $N(C_nH_{2n+1})_2$  (n is preferably an integer of 1 to 10, more preferably an integer of 1 to 5),  $COOC_nH_{2n+1}$  (n is preferably an integer of 1 to 10, more preferably an integer of 1 to 5), F, Cl, Br, I, CN, an optionally substituted phenyl group or an optionally substituted naphthyl group, which may be the same or different from each other. D is a ligand represented by the following general formula (17) or (18).)



(17)

-continued



(18)

[0010] (wherein  $R_4$ ,  $R_5$  and  $R_6$  are H,  $C_nH_{2n+1}$  ( $n$  is preferably an integer of 1 to 10, more preferably an integer of 1 to 5),  $N(C_nH_{2n+1})_2$  ( $n$  is preferably an integer of 1 to 10, more preferably an integer of 1 to 5),  $COOC_nH_{2n+1}$  ( $n$  is preferably an integer of 1 to 10, more preferably an integer of 1 to 5), F, Cl, Br, I, CN,  $CF_3$ , a furyl group, a thienyl group, an optionally substituted phenyl group or an optionally substituted naphthyl group, which may be the same or different from each other.)

[0011] The luminescent materials of the present invention are materials which emit light from the triplet state, and hence have high luminous efficiency.

[0012] The luminescent materials represented by the general formulae (1), (3), (5), (7), (9), (11), (13) and (15) can be synthesized by a method described in "Inorg Chem. 1991, 30, pp.1685 to 1687." To be more specific, they can be synthesized by allowing iridium acetylacetonato ( $Ir(acac)_3$ ) to react with a nitrogen containing compound which is to be a ligand.

[0013] The luminescent materials represented by the general formulae (2), (4), (6), (8), (10), (12), (14) and (16) can be synthesized by the method described in "J. Am. Chem. Soc. 2001, 123, pp.4304 to 4312." More specifically, the synthesis can be achieved by causing a nitrogen containing compound which is to be a ligand to react with an iridium chlorate to synthesize a dimer bridged by chlorine, and then causing this dimer to react with a ligand D.

[0014] The luminescent material of the present invention can be used as a luminescent material for organic EL devices and ECL devices and the like. When used as a luminescent material for organic EL device, it may be used as a dopant which is contained in a luminescent layer together with a host. The content when used as a dopant is preferably 0.5% by weight or more, and more preferably in the range of 0.5 to 30% by weight, but not particularly limited thereto.

[0015] An organic EL device of the present invention is characterized by containing the above-mentioned luminescent material of the present invention in a luminescent layer.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0016] The present invention will now be described by way of specific examples, however, it is to be noted that the present invention is not limited to the following examples.

#### (EXAMPLES 1 to 14)


[0017] An anode made of ITO was formed on a glass substrate, and a hole transfer layer, a luminescent layer, a hole preventive layer, an electron transfer layer and a cathode were formed thereon by vacuum deposition, to thereby produce an organic EL device having a device

structure of anode/hole transfer layer/luminescent layer/hole preventive layer/electron transfer layer/cathode.


[0018] As the anode, an ITO film having a film thickness of 1000 Å was formed. As the hole transfer layer, an NPB layer having a thickness of 500 Å was formed. As the luminescent layer, a layer of CBP serving as a host to which 6.5% by weight of dopant was added was formed so as to have a thickness of 100 Å. As the hole preventive layer, a BCP layer having a thickness of 100 Å was formed. As the electron transfer layer, an Alq layer having a thickness of 300 Å was formed. As the cathode, a MgIn layer having a thickness of 2000 Å was formed.

[0019] As the dopant to be contained in the luminescent layer, Compounds 1 to 14 which are the luminescent materials of the present invention and represented by the following general formulae were used.


COMPOUND 1



[0020] Compound 1 has the structure as follows:




COMPOUND 2




-continued

COMPOUND 3




-continued


COMPOUND 8




COMPOUND 4




COMPOUND 9




COMPOUND 5




COMPOUND 10




COMPOUND 6



COMPOUND 11




COMPOUND 7




-continued


COMPOUND 12




COMPOUND 13




COMPOUND 14




[0021] NPB used for the hole transfer layer is N,N'-di(naphthalene-1-yl)-N,N'-diphenyl-benzidine and is a compound having the following structure.




[0022] CBP used for the host of the luminescent layer is 4,4'-bis(carbazole-9-yl)-biphenyl and is a compound having the following structure.



[0023] BCP used for the hole preventive layer is 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline and is a compound having the following structure.




[0024] Alq used for the electron transfer layer is Tris(8-hydroxyquinolato) aluminum, and is a compound having the following structure.



(COMPARATIVE EXAMPLE 1)

[0025] An organic EL device was produced in the same manner as the above-mentioned examples except that as the dopant contained in the luminescent layer, 2,3,7,8,12,13,17,18-octaethyl-21H,23H-porphyrin platinum (II) (PtOEP) which is a conventional luminescent material having the following structure was used.



[0026] [Evaluation of Luminous Characteristics of Organic EL Devices]

[0027] With respect to the organic EL devices of Examples 1 to 14 and Comparative example 1 produced in the manner as described above, a current of 10 mA/cm<sup>2</sup> was applied to electrodes, and maximum brightness, luminous efficiency, emission wavelength and chromaticity coordinates were measured. Results of measurement are shown in Table 1. Herein the concentration of the dopant indicated in Table 1 is 6.5% by weight.

TABLE 1

	Luminescent Layer		Maximum Brightness (cd/m <sup>2</sup> )	Luminous Efficiency (cd/A)	Emission Wavelength (nm)	Chromaticity Coordinates (x, y)
	Host	Dopant (Concentration)				
Ex. 1	CBP	Compound 1 (6.5%)	21,000	10.2	607	0.58, 0.42
Ex. 2	CBP	Compound 2 (6.5%)	22,000	11	606	0.58, 0.42
Ex. 3	CBP	Compound 3 (6.5%)	23,000	12	575	0.51, 0.47
Ex. 4	CBP	Compound 4 (6.5%)	23,100	12	574	0.50, 0.47
Ex. 5	CBP	Compound 5 (6.5%)	16,900	9.4	630	0.63, 0.36
Ex. 6	CBP	Compound 6 (6.5%)	15,900	9.3	629	0.63, 0.36
Ex. 7	CBP	Compound 7 (6.5%)	21,200	10.8	545	0.42, 0.47
Ex. 8	CBP	Compound 8 (6.5%)	22,000	11.1	543	0.42, 0.47
Ex. 9	CBP	Compound 9 (6.5%)	12,000	8	648	0.66, 0.33
Ex. 10	CBP	Compound 10 (6.5%)	17,600	9.6	605	0.58, 0.42
Ex. 11	CBP	Compound 11 (6.5%)	15,000	9.2	492	0.19, 0.28
Ex. 12	CBP	Compound 12 (6.5%)	24,000	10.8	589	0.56, 0.43
Ex. 13	CBP	Compound 13 (6.5%)	15,800	9.2	628	0.63, 0.36
Ex. 14	CBP	Compound 14 (6.5%)	15,300	9.1	603	0.58, 0.42
Comp. Ex. 1	CBP	PtOEP (8%)	1,200	0.8	657	0.68, 0.31

[0028] As is apparent from Table 1, Examples 1 to 14 using the luminescent materials of the present invention are superior in luminous efficiency to Comparative example 1 using the conventional luminescent material. The luminescent materials of the present invention are considered as materials which emit light from the triplet state since they are iridium-containing organic metal compounds and have high luminous efficiency.

(EXAMPLES 15 to 18)

[0029] Organic EL devices were produced in the same manner as Example 1 except that the concentrations of Compound 1 to be contained in the luminescent layer as the dopant were 0.5% by weight, 3% by weight, 15% by weight and 30% by weight, respectively.

[0030] With respect to the organic EL devices thus produced, maximum brightness, luminous efficiency, emission wavelength and chromaticity coordinates were measured. Results of measurement are shown in Table 2. Table 2 also shows the result for Example 1.

TABLE 2


	Luminescent Layer		Maximum Brightness (cd/m <sup>2</sup> )	Luminous Efficiency (cd/A)	Emission Wavelength (nm)	Chromaticity Coordinates (x, y)
	Host	Dopant (Concentration)				
Ex. 1	CBP	Compound 1 (6.5%)	21,000	10.2	607	0.58, 0.42
Ex. 15	CBP	Compound 1 (0.5%)	8,500	10.7	595	0.55, 0.45
Ex. 16	CBP	Compound 1 (3%)	21,500	10.7	602	0.57, 0.43
Ex. 17	CBP	Compound 1 (15%)	17,000	9.6	630	0.65, 0.35
Ex. 18	CBP	Compound 1 (30%)	13,500	10.7	630	0.65, 0.35

[0031] As is apparent from Table 2, high luminous efficiency is achieved when the content of the dopant in the luminescent layer is in the range of 0.5% by weight to 30% by weight.


(EXAMPLES 19 to 21)

[0032] Organic EL devices were produced in the same manner as in Example 1 except that TCPB, TCTA and 1AZM-Hex were used as the host to be contained in the luminescent layer.


[0033] TCPB is 1,3,5-Tris(carbazole-9-yl)-benzene and is a compound having the following structure.



[0034] TCTA is 4,4',4''-Tris (carbazole-9-yl)-triphenylamine and is a compound having the following structure.



[0035] 1AZM-Hex is (N,N'-disalicylidene-1,6-hexanediaminato) zinc (II) and is a compound having the following structure.



[0036] With respect to the organic EL devices thus produced, maximum brightness, luminous efficiency, emission wavelength and chromaticity coordinates were measured. Results of measurement are shown in Table 3.

TABLE 3


	Luminescent Layer		Maximum Brightness (cd/m <sup>2</sup> )	Luminous Efficiency (cd/A)	Emission Wavelength (nm)	Chromaticity Coordinates (x, y)
	Host	Dopant (Concentration)				
Ex. 19	TCPB	Compound 1 (6.5%)	22,000	10.3	630	0.65, 0.35
Ex. 20	TCTA	Compound 1 (6.5%)	20,000	9.9	630	0.65, 0.35
Ex. 21	1AZM-Hex	Compound 1 (6.5%)	21,000	10	630	0.65, 0.35

[0037] As is apparent from Table 3, even when the host to be contained in the luminescent layer was changed, high luminous efficiency is obtained.

(EXAMPLES 22 AND 23)

[0038] In Example 22, an organic EL device was produced in the same manner as Example 1 except that for the hole preventive layer, BALq was used in place of BCP.

[0039] BALq is bis-(2-methyl-8-quinolinolato)-4-(phenylphenolato) aluminum (III) and is a compound having the following structure.



[0040] In Example 23, an organic EL device was produced in the same manner as Example 1 except that as the cathode material, a cathode having a two-layer structure of LiF/Al was used in place of MgIn.

[0041] With respect to the organic EL devices thus produced, maximum brightness, luminous efficiency, emission wavelength and chromaticity coordinates were measured. Results of measurement are shown in Table 4.

[0042] As is apparent from Table 4, high luminous efficiency is obtained in both of the cases that BALq is used as the material for the hole preventive layer and that LiF/Al is used as the cathode material.

[0043] By using the luminescent materials of the present invention, it is possible to improve the luminous efficiency in light emitting devices such as organic EL devices and ECL devices. Therefore, the luminescent materials of the present invention are useful for light emitting devices in appliances that are driven at low voltages such as portable devices.

What is claimed is:

1. A luminescent material for light emitting device represented by any one of the following general formulae (1) to (16):





TABLE 4


	Luminescent Layer		Hole Preventive Layer	Electron Transfer Layer		Maximum Brightness (cd/m <sup>2</sup> )	Luminous Efficiency (cd/A)	Emission Wavelength (nm)	Chromaticity Coordinates (x, y)
	Host	Dopant (Concentration)		Layer	Layer				
Ex. 22	CBP	Compound 2(6.5%)	BALq	Alq	MgIn	23,500	11	602	0.57, 0.43
Ex. 23	CBP	Compound 1(6.5%)	BCP	Alq	LiF/Al	35,000	15	602	0.57, 0.43

-continued




(4)


-continued




(9)




(5)




(10)




(6)




(11)




(7)



(12)






(8)





(13)

-continued



(wherein  $R_1$ ,  $R_2$  and  $R_3$  are H,  $C_nH_{2n+1}$  (n is an integer of 1 to 10),  $N(C_nH_{2n+1})_2$  (n is an integer of 1 to 10),  $COOC_nH_{2n+1}$  (n is an integer of 1 to 10), F, Cl, Br, I, CN, an optionally substituted phenyl group or an optionally substituted naphthyl group, which may be the same or different from each other.)

(14) D is a ligand represented by the following general formula (17) or (18).



(wherein  $R_4$ ,  $R_5$  and  $R_6$  are H,  $C_nH_{2n+1}$  (n is an integer of 1 to 10),  $N(C_nH_{2n+1})_2$  (n is an integer of 1 to 10),  $COOC_nH_{2n+1}$  (n is an integer of 1 to 10), F, Cl, Br, I, CN,  $CF_3$ , a furyl group, a thienyl group, an optionally substituted phenyl group or an optionally substituted naphthyl group, which may be the same or different from each other.)

2. The luminescent material for light emitting device according to claim 1, wherein said luminescent material is a dopant which is contained in a luminescent layer of an organic electroluminescent device together with a host.

3. An organic electroluminescent device comprising a luminescent layer containing the luminescent material according to claim 1.

4. An organic electroluminescent device comprising the luminescent layer according to claim 2.

\* \* \* \* \*

专利名称(译)	用于发光器件和有机电致发光器件的发光材料		
公开(公告)号	<a href="#">US20030194580A1</a>	公开(公告)日	2003-10-16
申请号	US10/376099	申请日	2003-02-26
[标]申请(专利权)人(译)	三洋电机株式会社		
申请(专利权)人(译)	SANYO ELECTRIC CO. , LTD.		
当前申请(专利权)人(译)	SANYO ELECTRIC CO. , LTD.		
[标]发明人	HAMADA YUJI MATSUSUE NORIYUKI NISHIMURA KAZUKI		
发明人	HAMADA, YUJI MATSUSUE, NORIYUKI NISHIMURA, KAZUKI		
IPC分类号	H01L51/50 C07F15/00 C09K11/06 H01L51/00 H01L51/30 H05B33/14		
CPC分类号	C07F15/0033 Y10S428/917 C09K2211/1003 C09K2211/1007 C09K2211/1011 C09K2211/1014 C09K2211/1029 C09K2211/185 H01L51/0059 H01L51/0062 H01L51/0077 H01L51/0081 H01L51/0085 H01L51/5016 C09K11/06		
优先权	2002051802 2002-02-27 JP		
其他公开文献	US7022422		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

由以下通式(1)或(2)表示的发光器件用发光材料。(其中R<sub>1</sub>, R<sub>2</sub>和R<sub>3</sub>为H, C<sub>n</sub>H<sub>2n+1</sub>(n是1到10的整数), N(C<sub>n</sub>H<sub>2n+1</sub>)<sub>2</sub>(n是1到10的整数), COOC<sub>n</sub>H<sub>2n+1</sub>(n是1到10的整数), F, Cl, Br, I, CN, 苯基基团, 萘基等, D是由下式表示的配体下列通式(17)或(18)。)其中R<sub>4</sub>, R<sub>5</sub>和R<sub>6</sub>为H, C<sub>n</sub>H<sub>2n+1</sub>(n是1到10的整数), N(C<sub>n</sub>H<sub>2n+1</sub>)<sub>2</sub>(n是1到10的整数), COOC<sub>n</sub>H<sub>2n+1</sub>(n是1至10的整数), F, Cl, Br, I, CN, CF<sub>3</sub>, 咪唑基, 噻吩基, 苯基, 萘基或类似。)

