



US006835953B2

(12) **United States Patent**  
Cok et al.

(10) **Patent No.:** US 6,835,953 B2  
(45) **Date of Patent:** Dec. 28, 2004

(54) **DESICCANT STRUCTURES FOR OLED DISPLAYS**

(75) Inventors: **Ronald S. Cok**, Rochester, NY (US);  
**Michael L. Boroson**, Rochester, NY  
(US); **Terrence R. O'Toole**, Webster,  
NY (US)

(73) Assignee: **Eastman Kodak Company**, Rochester,  
NY (US)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **10/408,910**

(22) Filed: **Apr. 8, 2003**

(65) **Prior Publication Data**

US 2003/0203551 A1 Oct. 30, 2003

**Related U.S. Application Data**

(62) Division of application No. 10/116,307, filed on Apr. 4,  
2002.

(51) **Int. Cl.**<sup>7</sup> ..... **H01L 31/20**

(52) **U.S. Cl.** ..... **257/59; 257/72; 257/E51.022**

(58) **Field of Search** ..... **257/59, 72, E51.022**

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

3,180,730 A 4/1965 Klupfel et al.  
3,567,450 A 3/1971 Brantly et al.  
3,658,520 A 4/1972 Brantly et al.  
4,081,397 A 3/1978 Booe  
4,356,429 A 10/1982 Tang  
4,539,507 A 9/1985 VanSlyke et al.  
4,720,432 A 1/1988 VanSlyke et al.  
4,768,292 A 9/1988 Manzei  
4,885,211 A 12/1989 Tang et al.  
5,059,861 A 10/1991 Littman et al.  
5,059,862 A 10/1991 VanSlyke et al.  
5,061,569 A 10/1991 VanSlyke et al.  
5,141,671 A 8/1992 Bryan et al.

5,150,006 A 9/1992 VanSlyke et al.  
5,151,629 A 9/1992 VanSlyke  
5,247,190 A 9/1993 Friend et al.  
5,276,380 A 1/1994 Tang  
5,294,870 A 3/1994 Tang et al.  
5,384,357 A \* 1/1995 Levinson et al. .... 524/770  
5,405,709 A 4/1995 Littman et al.  
5,484,922 A 1/1996 Moore et al.  
5,593,788 A 1/1997 Shi et al.  
5,608,287 A 3/1997 Hung et al.  
5,645,948 A 7/1997 Shi et al.  
5,677,572 A 10/1997 Hung et al.  
5,683,823 A 11/1997 Shi et al.  
5,703,436 A 12/1997 Forrest et al.  
5,714,838 A 2/1998 Haight et al.  
5,739,545 A 4/1998 Guha et al.  
5,755,999 A 5/1998 Shi et al.  
5,776,622 A 7/1998 Hung et al.  
5,776,623 A 7/1998 Hung et al.  
5,786,042 A \* 7/1998 Inoue et al. .... 428/1.3  
5,837,391 A 11/1998 Utsugi  
5,851,709 A 12/1998 Grande et al.

(List continued on next page.)

**FOREIGN PATENT DOCUMENTS**

JP 11 054285 2/1999  
JP 11-162634 6/1999  
JP 2000 030871 1/2000  
JP 2001 126862 5/2001  
JP 2001-126864 5/2001  
WO WO 00/36665 6/2000

*Primary Examiner*—David Nelms


*Assistant Examiner*—Tu-Tu Ho

(74) *Attorney, Agent, or Firm*—Andrew J. Anderson;  
Thomas H. Close

(57) **ABSTRACT**

This invention provides a top-emitting OLED display device that includes a substrate; an array of OLED elements disposed on one side of the substrate; and a desiccant material provided in a patterned arrangement over the array of OLED elements on the same side of the substrate such that the desiccant material does not interfere with the light emitted by the OLED elements.

**19 Claims, 9 Drawing Sheets**



# US 6,835,953 B2

Page 2

---

## U.S. PATENT DOCUMENTS

|              |         |                |                 |         |                             |
|--------------|---------|----------------|-----------------|---------|-----------------------------|
| 5,928,802 A  | 7/1999  | Shi et al.     | 6,208,075 B1    | 3/2001  | Hung et al.                 |
| 5,935,720 A  | 8/1999  | Chen et al.    | 6,226,890 B1    | 5/2001  | Boroson et al.              |
| 5,935,721 A  | 8/1999  | Shi et al.     | 6,237,529 B1    | 5/2001  | Spahn                       |
| 5,969,474 A  | 10/1999 | Arai           | 6,268,295 B1    | 7/2001  | Ohta et al.                 |
| 5,981,306 A  | 11/1999 | Burrows et al. | 6,278,236 B1    | 8/2001  | Madathil et al.             |
| 6,020,078 A  | 2/2000  | Chen et al.    | 6,300,042 B1    | 10/2001 | Mancini et al.              |
| 6,066,357 A  | 5/2000  | Tang et al.    | 6,515,310 B2 *  | 2/2003  | Yamazaki et al. .... 257/98 |
| 6,069,443 A  | 5/2000  | Jones et al.   | 2002/0015907 A1 | 2/2002  | Wolk et al.                 |
| 6,137,223 A  | 10/2000 | Hung et al.    | 2002/0024096 A1 | 2/2002  | Yamazaki et al.             |
| 6,140,763 A  | 10/2000 | Hung et al.    | 2003/0038590 A1 | 2/2003  | Silvernail et al.           |
| 6,172,459 B1 | 1/2001  | Hung et al.    |                 |         |                             |

\* cited by examiner




FIG. 1  
(Prior Art)




FIG. 1A  
(Prior Art)




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9

1

## DESICCANT STRUCTURES FOR OLED DISPLAYS

### CROSS REFERENCE TO RELATED APPLICATIONS

This is a divisional of application U.S. Ser. No. 10/116, 307 filed Apr. 4, 2002 by Cok et al., entitled *Desiccant Structures for OLED Displays*.

### FIELD OF THE INVENTION

The present invention relates to organic light emitting diode (OLED) displays, and more particularly, to improving the performance, reliability, and robustness of such displays by preventing moisture from degrading the light-emitting OLED materials and improving the contrast of the display.

### BACKGROUND OF THE INVENTION

Organic light-emitting diode (OLED) display devices require humidity levels below about 1000 parts per million (ppm) to prevent premature degradation of device performance within a specified operating and/or storage life of the device. Control of the environment to this range of humidity levels within a packaged device is typically achieved by encapsulating the device or by sealing the device and a desiccant within a cover. Desiccants such as, for example, metal oxides, alkaline earth metal oxides, sulfates, metal halides, and perchlorates are used to maintain the humidity level below the above level. See for example U.S. Pat. No. 6,226,890 B1 issued May 8, 2001 to Boroson et al. describing desiccant materials for moisture-sensitive electronic devices. The device disclosed in FIG. 2 of Boroson et al. is a so-called bottom emitting OLED device that emits light through a transparent substrate. The desiccant material is located over the organic light emitting materials in an enclosure that is sealed to the back-side of the substrate.

In a so-called top emitting OLED the organic material is also located on a substrate, but the light is emitted from the surface of the substrate through a transparent cover plate that also serves as part of the sealed enclosure. In this arrangement, desiccant materials located in the enclosure over to the organic materials will interfere with the light emitted by the OLED.

There is a need therefore for an improved means to provide desiccation in a top-emitting OLED display device.

### SUMMARY OF THE INVENTION

The need is met by providing a top-emitting OLED display device, that includes a substrate; an array of OLED elements disposed on one side of the substrate; and a desiccant material provided in a patterned arrangement over the array of OLED elements on the same side of the substrate such that the desiccant material does not interfere with the light emitted by the OLED elements.

According to a preferred embodiment of the invention, the patterned arrangement of desiccant material performs the function of a black matrix for increasing the contrast of the display.

### ADVANTAGES

The present invention has the advantage that it increases the lifetime of a top-emitting OLED display device by providing desiccation of the OLED elements. In a preferred embodiment, the contrast of the display is also improved.

### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a partial cross section of a prior art conventional top-emitting OLED display device;

2

FIG. 1A is a cross section view of a typical OLED element known in the art that illustrates some of the various layers that can be used to construct an OLED element;

FIG. 2 is a partial cross section of a display having desiccant material applied to the top layer of the OLED substrate according to a first embodiment of the present invention;

FIG. 3 is a top view of a display shown in FIG. 2;

FIG. 4 is a partial cross section of a display with desiccant material applied to the inside of the display device cover according to a second embodiment of the present invention;

FIG. 5 is a partial cross section of a display with desiccant material used within other layers according to a third embodiment of the present invention;

FIG. 6 is a partial cross section of a display with desiccant material on the top layer, on a cover, and within other layers;

FIG. 7 is a cross section of a display illustrating the desiccant material used around the perimeter of the display device;

FIG. 8 is a partial cross section of a display with desiccant material applied to the top layer of the OLED substrate and a conformal cover; and

FIG. 9 is a partial cross section of a display where the desiccant material is contact printed.

It will be understood that the figures are not to scale since the individual layers are too thin and the thickness differences of various layers too great to permit depiction to scale.

### DETAILED DESCRIPTION OF THE INVENTION

Referring to FIG. 1, a prior art top-emitting OLED display device 10 is shown with a substrate 12, and a thin-film transistor (TFT) active matrix layer 14 comprising an array of TFTs that provides power to OLED elements. A patterned first insulating layer 16 is provided over the TFT active matrix layer, and an array of first electrodes 18 are provided over insulating layer 16 and in electrical contact with the TFT active matrix layer. A patterned second insulating layer 17 is provided over the array of first electrodes 18 such that at least a portion of the each of the first electrodes 18 is exposed.

Over the first electrodes and insulating layers are provided red, green, and blue-emitting organic electroluminescent (EL) elements, 19R, 19G, and 19B, respectively. Herein, the collection of organic EL elements may also be referred to as the organic EL layer. The light-emitting pixel area is generally defined by the area of the first electrode 18 in contact with the organic EL elements. Over the organic EL layer is provided a transparent, common second electrode 30 that has sufficient optical transparency to allow transmission of the generated red, green, and blue light. Each first electrode in combination with its associated organic EL element and second electrode is herein referred to as an OLED element. A typical top-emitting OLED display device comprises an array of OLED elements wherein each OLED element emits red, green or blue. However, monochrome display devices are also known where the array of OLED elements emit the same color light, for example, white.

In operation, the thin-film transistors in TFT layer 14 allow current to flow between the first electrode 18, each of which can be selectively addressed, and the common second electrode 30. Holes and electrons recombine within the organic EL elements to emit light.

Referring to FIG. 2, a first embodiment of the top-emitting OLED device of the present invention includes a

transparent protection layer **32** provided over the second electrode, and further provides a patterned layer of light-absorbing desiccant **40** in contact with the transparent protection layer **32**. A transparent cover **36** is provided over OLED device with a gap maintained between the device and the cover. Attachment of the cover to the device at the edges of the display is not shown in this partial view.

The transparent protection layer **32** is optional and the patterned layer of desiccant can instead be provided in direct contact with the second electrode **30**. When provided, the protection layer **32** may comprise inorganic materials such as SiOx or SiNx, for example, as disclosed in JP 2001126864. Alternatively, the protection layer **32** may comprise organic materials such as polymers, including but not limited to, TEFLON®, polyimides, and polymers disclosed in JP 11-162634. Protection layer **32** may comprise multiple layers of organic or inorganic materials, or combinations thereof. Alternating inorganic and organic layers, for example, as disclosed in U.S. Pat. No. 6,268,295 and WO 00/36665, are useful as protection layer **32**. In all cases, the protection layer **32** should have high optical transparency, preferably greater than 70% transmittance. For convenience, the combination of layers from the substrate through the optional protection layer is referred to herein as the OLED substrate.

The light-absorbing desiccant **40** is provided in a patterned arrangement between the light-emitting pixel areas, designated **24R**, **G**, and **B** of the device such that it does not interfere with the light emitted by the OLED elements **19R**, **G**, and **B**. As previously mentioned, the light-emitting pixel area is generally defined by the area of the first electrode in contact with the organic EL elements. A top view of the result is shown in FIG. 3.

Referring to FIG. 3, the display device **10** has a patterned array of light-emitting pixel areas **24R**, **24G**, and **24B** that emit red, green, and blue light, respectively. The light-absorbing desiccant material **40** is patterned between the pixels or OLED elements so as to allow light to be emitted from the pixels through the cover (not shown in FIG. 3). The light-absorbing desiccant material need not be deposited over the entire available area, and may be deposited on only a portion of the available device area not used by the light emitting pixel areas. The desiccant material need not be deposited in a planar layer, but can be conformable to the surface of the materials deposited over the substrate. The desiccant material may be deposited and patterned using thick film manufacturing techniques such as screen-printing as are known in the art. The light-absorbing desiccant can be deposited much more thickly and heavily than the OLED layers. In general, the more material that is deposited, the better desiccation and light absorption is provided.

The light-absorbing desiccant material **40** may be deposited in a pattern using photolithographic techniques known in the art. For example, light absorbing desiccant material may be coated as a liquid on the entire surface and exposed to radiation through a mask to polymerize portions of the coating. Portions of the material exposed to the radiation are cured and the remainder is washed away. Dry film photolithography may also be used. In addition, patterned thermal transfer can be used, for example, by coating desiccant material **40** onto a donor substrate, placing the donor substrate in contact or close proximity to the OLED substrate, and selectively heating the donor with a laser to cause transfer of the desiccant material to the OLED substrate. The desiccant material **40** may comprise a plurality of thinner layers deposited by sequential deposition of desiccant materials.

As shown in FIG. 7, the cover **36** forms a cavity over the OLED pixel areas **24**. The light absorbing desiccant material **40** can be used as a desiccant seal material **40'** around the perimeter of the device, further improving desiccation. Sealing is done under inert atmosphere conditions, for example, under nitrogen or argon, so that the gap contains little to no water or oxygen. The light-absorbing desiccant materials may, or may not, actually touch the cover **36**. If they do touch, each pixel area becomes an independent cavity. For simplicity, the TFT layers, organic EL layers, second electrode and the optional protection layer are depicted in FIG. 7 as a single combined layer **13**.

Many desiccants may be used in this invention, but currently preferred solid desiccants are selected from the group consisting of alkaline metal oxides, alkaline earth metal oxides, sulfates, metal chlorides, and perchlorates. Preferred binders are moisture-permeable and radiation-curable, i.e., they may be cured by exposure to heat or to electromagnetic radiation such as infra-red, visible, or ultraviolet light. Preferred binders include radiation-curable, commercially available photoresist compositions, or radiation-curable acrylates, methacrylates, cyclized polyisoprenes, polyvinyl cinnamates, epoxies, silicones, and adhesives. The desiccant material may include a moisture absorption rate enhancing or maintaining binder selected from the group consisting of cellulose acetates, epoxies, phenoxies, siloxanes, methacrylates, sulfones, phthalates, and amides.

This invention does not require desiccant material **40** or desiccant seal material **40'** to have light-absorbing properties, and it may instead be transparent or translucent. Providing desiccant material **40** with light-absorbing properties is useful to increase the contrast of the device. A preferred light-absorbing desiccant material in the present invention has a black color. Patterned light-absorbing desiccant material **40** serves as a black matrix for improving contrast by absorbing ambient light. The terms "black" or "black matrix" are not meant to imply perfect light absorption at all wavelengths, but rather, to imply that the matrix appears dark to an observer and has little hue. The present invention provides advantages over the art in this regard in that contrast is enhanced without the loss of light through the use of circular polarizers or other light-absorbing layers as known in the art. Moreover, light-absorbing desiccant materials will also absorb light emitted or being guided through other layers of the display device. This will have the effect of reducing the level of stray light in the device, improving its sharpness.

While black is preferred, other desiccant colors may be used to yield a desired feature. A light absorber may be an additive to the desiccant/binder matrix and can be selected from the group comprising dyes and pigments. Pigments can include, for example, carbon black, graphite, metal oxides, metal sulfides, and metal complexes such as phthalocyanines. Alternatively, one may select a desiccant or a binder that intrinsically possesses light absorbing properties.

In a second embodiment, the light-absorbing desiccant material is applied to the inside of transparent cover **36** rather than the top layer on the OLED substrate. Referring to FIG. 4, the cover may be prepared separately from the OLED substrate. A similar masking technique as described above may be used to deposit patterned desiccant material **40** onto the cover **36**. The cover **36** is aligned with the OLED substrate when the cover is affixed to the substrate to ensure that the light-absorbing desiccant does not occlude the light from the pixels.

Alternatively, the light-absorbing desiccant materials are deposited so that the desiccant materials touch both the top

layer of the substrate and the cover (not shown). If this is done over all of the display, each pixel element will be enclosed separately within a cavity. It is also possible to deposit light-absorbing desiccant material that touches both the substrate and the cover only on the perimeter (not shown) so that a physical barrier to moisture exists around the periphery of the OLED display device but the pixel elements are all exposed to the gap in common.

Referring to FIG. 5, according to a further embodiment, a light-absorbing desiccant **40** is patterned in conjunction with one or more of the layers comprising the organic EL layer such that the patterned desiccant layer is provided between the pixel areas **24**. The desiccant material may comprise all or a portion of one or more layers, i.e. it can comprise the layer, or be located within one of the layers. In this case, the process by which the device is made is conventional; the only difference being is that the material that is used to fill the gaps between pixel areas has desiccating properties.

According to another embodiment, second insulating layer **17** comprises an insulating light-absorbing desiccant. Because the second insulating layer defines the pixel areas by defining the exposed area of the first electrode, the patterned desiccant layer is necessarily provided between the pixel areas. The purpose of the second insulating layer **17** is to smooth the edges of the first electrode **18** and to assist in preventing a short circuit to the second electrode **30**. The desiccant material can be, for example, one of the desiccants described above, or an acrylic binder mixed with one of the desiccants described above. Any polymer used as the second insulating layer can be used as the binder. The desiccant and binder may be deposited and patterned using conventional photolithography, or any means normally used to deposit and pattern the second insulating layer. Similarly, the first insulating layer **16** may also comprise a desiccant material.

As shown in FIG. 6, the various embodiments of the present invention are not mutually exclusive and can be combined in a single device. For example, light-absorbing desiccant material **40** may be patterned on the top layer of the substrate, on the cover, and within other layers. Combining the various embodiments provides further desiccation and contrast enhancement in the display device. As shown in FIG. 6, there are gaps formed between the organic electroluminescent elements **19R**, **G**, **B** and the desiccant material **40** is provided within the gaps.

A second insulating layer is not required in this invention. When it is used, it should be appreciated that it is generally much thicker than the combined thickness of the organic EL elements, second electrode and optional protection layer. When this is the case, a three-dimensional relief pattern is created with the light-emitting pixel areas in recessed regions and the second insulating layers representing the raised areas. This is shown in FIG. 9. The organic EL elements, second electrode, and optional protection layer are shown collectively as combined layer **15** which is deposited in a conformable manner over the structure. When such a relief pattern is present, contact printing of the light-absorbing desiccant **40** can be performed through well-known methods. This is advantageous because it greatly simplifies the desiccant-patterning step.

For example, desiccant **40** may be coated onto a donor sheet, which is placed in physical contact with the OLED substrate. Transfer of the desiccant only takes place at the raised portions because that is where the contact takes place. The OLED substrate surface may be treated with an adhesion promoter to aid transfer. Heat may be used to aid the

transfer of the desiccant from the donor to the OLED substrate. Alternatively, the desiccant material **40** may be roller coated onto the raised areas from a roller surface coated with the desiccant.

While transparent cover **36** is typically glass or plastic sheet, the cover can comprise materials that are deposited in a conformable manner over the surface of the materials deposited over the substrate, i.e., over OLED substrate with patterned desiccant material **40**. The same materials useful as protection layer **32** can be used as the transparent conformable cover **36**. This is illustrated in FIG. 8.

This invention is advantageously practiced with top-emitting OLED active matrix devices. However, it is readily apparent to one skilled in the art that this invention may be used in any top-emitting OLED device including simple matrix or passive matrix devices.

#### OLED Element Architecture

There are numerous configurations of the layers within each OLED element wherein the present invention can be successfully practiced. A typical, non-limiting, structure is shown in FIG. 1A and is comprised of an anode layer **103**, a hole-injecting layer **105**, a hole-transporting layer **107**, a light-emitting layer **109**, an electron-transporting layer **111**, and a cathode layer **113**. These layers are described in detail below. The total combined thickness of the organic layers is preferably less than 500 nm. The first electrode **18** may be either the cathode or anode, and the second electrode **30** is necessarily the opposite. A voltage/current source **250** is required to energize the OLED element and conductive wiring **260** is required to make electrical contact to the anode and cathode. The TFT layers and associated wiring serve these functions.

#### Substrate

Because the OLED elements are not viewed through the substrate, substrate **12** can either be light transmissive or opaque. Substrates for use in this case include, but are not limited to, glass, plastic, semiconductor materials, ceramics, and circuit board materials.

#### Anode

When the anode layer **103** serves as second electrode **30**, the anode should be transparent or substantially transparent to the emission of interest. Common transparent anode materials used in this invention are indium-tin oxide (ITO), indium-zinc oxide (IZO) and tin oxide, but other metal oxides can work including, but not limited to, aluminum- or indium-doped zinc oxide, magnesium-indium oxide, and nickel-tungsten oxide. In addition to these oxides, metal nitrides, such as gallium nitride, and metal selenides, such as zinc selenide, and metal sulfides, such as zinc sulfide, can be used in layer **103**. When anode layer serves the function of the first electrode **18**, the transmissive characteristics of layer **103** are immaterial and any conductive material can be used: transparent, opaque or reflective. Example conductors for this application include, but are not limited to: gold, iridium, molybdenum, palladium, and platinum. Typical anode materials, transmissive or otherwise, have a work function of 4.1 eV or greater. Desired anode materials are commonly deposited by any suitable means such as evaporation, sputtering, chemical vapor deposition, or electrochemical means. Anodes can be patterned using well-known photolithographic processes.

#### Hole-Injecting Layer (HIL)

It is often useful that a hole-injecting layer **105** be provided between anode **103** and hole-transporting layer **107**. The hole-injecting material can serve to improve the film formation property of subsequent organic layers and to facilitate injection of holes into the hole-transporting layer.

Suitable materials for use in the hole-injecting layer include, but are not limited to: porphyrinic compounds as described in U.S. Pat. No. 4,720,432, and plasma-deposited fluorocarbon polymers as described in U.S. Pat. No. 6,208,075. Alternative hole-injecting materials reportedly useful in organic EL devices are described in EP 0 891 121 A1 and EP 1 029 909 A1.

#### Hole-Transporting Layer (HTL)

The hole-transporting layer **107** contains at least one hole-transporting compound such as an aromatic tertiary amine, where the latter is understood to be a compound containing at least one trivalent nitrogen atom that is bonded only to carbon atoms, at least one of which is a member of an aromatic ring. In one form the aromatic tertiary amine can be an arylamine, such as a monoarylamine, diarylamine, triarylamine, or a polymeric arylamine. Exemplary monomeric triarylaminos are illustrated by Klupfel et al. U.S. Pat. No. 3,180,730. Other suitable triarylaminos substituted with one or more vinyl radicals and/or comprising at least one active hydrogen containing group are disclosed by Brantley et al. in U.S. Pat. No. 3,567,450 and U.S. Pat. No. 3,658,520. A more preferred class of aromatic tertiary amines are those which include at least two aromatic tertiary amine moieties as described in U.S. Pat. No. 4,720,432 and U.S. Pat. No. 5,061,569. Illustrative of useful aromatic tertiary amines include, but are not limited to, the following:

1,1-Bis(4-di-p-tolylaminophenyl)cyclohexane  
1,1-Bis(4-di-p-tolylaminophenyl)-4-phenylcyclohexane  
4,4'-Bis(diphenylamino)quadruphenyl  
Bis(4-dimethylamino-2-methylphenyl)-phenylmethane  
N,N,N-Tri(p-tolyl)amine  
4-(di-p-tolylamino)-4'-[4(di-p-tolylamino)-styryl]stilbene  
N,N,N,N'-Tetra-p-tolyl-4,4'-diaminobiphenyl  
N,N,N,N'-Tetraphenyl-4,4'-diaminobiphenyl  
N,N,N,N'-tetra-1-naphthyl-4,4'-diaminobiphenyl  
N,N,N,N'-tetra-2-naphthyl-4,4'-diaminobiphenyl  
N-Phenylcarbazole  
4,4'-Bis[N-(1-naphthyl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(1-naphthyl)-N-(2-naphthyl)amino]biphenyl  
4,4''-Bis[N-(1-naphthyl)-N-phenylamino]p-terphenyl  
4,4'-Bis[N-(2-naphthyl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(3-acenaphthenyl)-N-phenylamino]biphenyl  
1,5-Bis[N-(1-naphthyl)-N-phenylamino]naphthalene  
4,4'-Bis[N-(9-anthryl)-N-phenylamino]biphenyl  
4,4''-Bis[N-(1-anthryl)-N-phenylamino]p-terphenyl  
4,4'-Bis[N-(2-phenanthryl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(8-fluoranthryl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(2-pyrenyl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(2-naphthacenyl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(2-perylenyl)-N-phenylamino]biphenyl  
4,4'-Bis[N-(1-coroneryl)-N-phenylamino]biphenyl  
2,6-Bis(di-p-tolylamino)naphthalene  
2,6-Bis[di-(1-naphthyl)amino]naphthalene  
2,6-Bis[N-(1-naphthyl)-N-(2-naphthyl)amino]naphthalene  
N,N,N,N'-Tetra(2-naphthyl)-4,4''-diamino-p-terphenyl  
4,4'-Bis{N-phenyl-N-[4-(1-naphthyl)-phenyl]amino}biphenyl  
4,4'-Bis[N-phenyl-N-(2-pyrenyl)amino]biphenyl  
2,6-Bis[N,N-di(2-naphthyl)amine]fluorene  
1,5-Bis[N-(1-naphthyl)-N-phenylamino]naphthalene

Another class of useful hole-transporting materials includes polycyclic aromatic compounds as described in EP 1 009 041. In addition, polymeric hole-transporting materials can be used such as poly(N-vinylcarbazole) (PVK), polythiophenes, polypyrrole, polyaniline, and copolymers such as poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) also called PEDOT/PSS.

#### Light-Emitting Layer (LEL)

As more fully described in U.S. Pat. No. 4,769,292 and U.S. Pat. No. 5,935,721, the light-emitting layer (LEL) **109** of the organic EL element comprises a luminescent or fluorescent material where electroluminescence is produced as a result of electron-hole pair recombination in this region. The light-emitting layer can be comprised of a single material, but more commonly consists of a host material doped with a guest compound or compounds where light emission comes primarily from the dopant and can be of any color. The host materials in the light-emitting layer can be an electron-transporting material, as defined below, a hole-transporting material, as defined above, or another material or combination of materials that support hole-electron recombination. The dopant is usually chosen from highly fluorescent dyes, but phosphorescent compounds, e.g., transition metal complexes as described in WO 98/55561, WO 00/18851, WO 00/57676, and WO 00/70655 are also useful. Dopants are typically coated as 0.01 to 10% by weight into the host material. Iridium complexes of phenylpyridine and its derivatives are particularly useful luminescent dopants. Polymeric materials such as polyfluorenes and polyvinylarylenes (e.g., poly(p-phenylenevinylene), PPV) can also be used as the host material. In this case, small molecule dopants can be molecularly dispersed into the polymeric host, or the dopant could be added by copolymerizing a minor constituent into the host polymer.

An important relationship for choosing a dye as a dopant is a comparison of the bandgap potential which is defined as the energy difference between the highest occupied molecular orbital and the lowest unoccupied molecular orbital of the molecule. For efficient energy transfer from the host to the dopant molecule, a necessary condition is that the band gap of the dopant is smaller than that of the host material.

Host and emitting molecules known to be of use include, but are not limited to, those disclosed in U.S. Pat. Nos. 4,768,292, 5,141,671, 5,150,006, 5,151,629, 5,405,709, 5,484,922, 5,593,788, 5,645,948, 5,683,823, 5,755,999, 5,928,802, 5,935,720, 5,935,721, 6,020,078.

Metal complexes of 8-hydroxyquinoline and similar oxine derivatives constitute one class of useful host compounds capable of supporting electroluminescence, and are particularly suitable. Illustrative of useful chelated oxinoid compounds are the following:

CO-1: Aluminum trisoxine [alias, tris(8-quinolinolato) aluminum(III)]  
CO-2: Magnesium bisoxine [alias, bis(8-quinolinolato) magnesium(II)]  
CO-3: Bis[benzo{f}-8-quinolinolato]zinc (II)  
CO-4: Bis(2-methyl-8-quinolinolato)aluminum(III)-μ-oxo-bis(2-methyl-8-quinolinolato) aluminum(III)  
CO-5: Indium trisoxine [alias, tris(8-quinolinolato) indium]  
CO-6: Aluminum tris(5-methyloxine) [alias, tris(5-methyl-8-quinolinolato) aluminum(III)]  
CO-7: Lithium oxine [alias, (8-quinolinolato)lithium(I)]  
CO-8: Gallium oxine [alias, tris(8-quinolinolato)gallium (III)]  
CO-9: Zirconium oxine [alias, tetra(8-quinolinolato) zirconium(IV)]

Other classes of useful host materials include, but are not limited to: derivatives of anthracene, such as 9,10-di-(2-naphthyl)anthracene and derivatives thereof, distyrylarylene derivatives as described in U.S. Pat. No. 5,121,029, and benzazole derivatives, for example, 2,2',2''-(1,3,5-phenylene)tris[1-phenyl-1H-benzimidazole].

Useful fluorescent dopants include, but are not limited to: derivatives of anthracene, tetracene, xanthene, perylene, rubrene, coumarin, rhodamine, quinacridone, dicyanomethylenepyrans compounds, thiopyran compounds, polymethine compounds, pyrilium and thiapyrilium compounds, fluorene derivatives, perfluoranthene derivatives and carbostyryl compounds.

#### Electron-Transporting Layer (ETL)

Preferred thin film-forming materials for use in forming the electron-transporting layer **111** of the organic EL elements of this invention are metal chelated oxinoid compounds, including chelates of oxine itself (also commonly referred to as 8-quinolinol or 8-hydroxyquinoline). Such compounds help to inject and transport electrons, exhibit high levels of performance, and are readily fabricated in the form of thin films. Exemplary oxinoid compounds were listed previously.

Other electron-transporting materials include various butadiene derivatives as disclosed in U.S. Pat. No. 4,356,429 and various heterocyclic optical brighteners as described in U.S. Pat. No. 4,539,507. Benzazoles and triazines are also useful electron-transporting materials.

In some instances, layers **111** and **109** can optionally be collapsed into a single layer that serves the function of supporting both light emission and electron transport. These layers can be collapsed in both small molecule OLEO systems and in polymeric OLED systems. For example, in polymeric systems, it is common to employ a hole-transporting layer such as PEDOT-PSS with a polymeric light-emitting layer such as PPV. In this system, PPV serves the function of supporting both light emission and electron transport.

#### Cathode

The cathode **113** serves as the first electrode **18**, it need not be transparent and can comprise nearly any conductive material. Desirable cathode materials have good film-forming properties to ensure good contact with the underlying organic layer, promote electron injection at low voltage, and have good stability. Useful cathode materials often contain a low work function metal (<4.0 eV) or metal alloy. One preferred cathode material is comprised of a Mg:Ag alloy wherein the percentage of silver is in the range of 1 to 20%, as described in U.S. Pat. No. 4,885,221. Another suitable class of cathode materials includes bilayers comprising a thin electron-injection layer (EIL) and a thicker layer of conductive metal. The EIL is situated between the cathode and the organic layer (e.g., ETL). Here, the EIL preferably includes a low work function metal or metal salt, and if so, the thicker conductor layer does not need to have a low work function. One such cathode is comprised of a thin layer of LiF followed by a thicker layer of Al as described in U.S. Pat. No. 5,677,572. Other useful cathode material sets include, but are not limited to, those disclosed in U.S. Pat. Nos. 5,059,861, 5,059,862, and 6,140,763.

When cathode layer **113** serves as the second electrode **30**, the cathode must be transparent or nearly transparent. For such applications, metals must be thin or one must use transparent conductive oxides, or a combination of these materials. Optically transparent cathodes have been described in more detail in U.S. Pat. Nos. 4,885,211, 5,247,190, JP 3,234,963, U.S. Pat. Nos. 5,703,436, 5,608,287, 5,837,391, 5,677,572, 5,776,622, 5,776,623, 5,714,838, 5,969,474, 5,739,545, 5,981,306, 6,137,223, 6,140,763, 6,172,459, EP 1 076 368, and U.S. Pat. No. 6,278,236. Cathode materials are typically deposited by evaporation, sputtering, or chemical vapor deposition. When needed,

patterning can be achieved through many well known methods including, but not limited to, through-mask deposition, integral shadow masking as described in U.S. Pat. No. 5,276,380 and EP 0 732 868, laser ablation, and selective chemical vapor deposition.

#### Deposition of Organic Layers

The organic materials mentioned above are suitably deposited through a vapor-phase method such as sublimation, but can be deposited from a fluid, for example, from a solvent with an optional binder to improve film formation. If the material is a polymer, solvent deposition is useful but other methods can be used, such as sputtering or thermal transfer from a donor sheet. The material to be deposited by sublimation can be vaporized from a sublimator "boat" often comprised of a tantalum material, e.g., as described in U.S. Pat. No. 6,237,529, or can be first coated onto a donor sheet and then sublimed in closer proximity to the substrate. Layers with a mixture of materials can utilize separate sublimator boats or the materials can be pre-mixed and coated from a single boat or donor sheet. Patterned deposition can be achieved using shadow masks, integral shadow masks (U.S. Pat. No. 5,294,870), spatially-defined thermal dye transfer from a donor sheet (U.S. Pat. Nos. 5,851,709 and 6,066,357) and inkjet method (U.S. Pat. No. 6,066,357). While all organic layers may be patterned, it is most common that only the layer emitting light is patterned, and the other layers may be uniformly deposited over the entire device.

#### Optical Optimization

OLED devices of this invention can employ various well-known optical effects in order to enhance its properties if desired. This includes optimizing layer thicknesses to yield maximum light transmission, providing dielectric mirror structures, replacing reflective electrodes with light-absorbing electrodes, providing anti-glare or anti-reflection coatings over the display, providing a polarizing medium over the display, or providing colored, neutral density, or color conversion filters over the display. Filters, polarizers, and anti-glare or anti-reflection coatings may be specifically provided over the cover or as part of the cover. In another embodiment of this invention, the OLED elements may emit white light and a RGB filter array is provided over the white-emitting OLED elements to provide a full color display device.

The invention has been described in detail with particular reference to certain preferred embodiments thereof, but it will be understood that variations and modifications can be effected within the spirit and scope of the invention.

#### Parts List

- 10** top-emitting OLED device
- 12** substrate
- 13** combined layer
- 14** TFT active matrix layer
- 15** combined layer
- 16** first insulating layer
- 17** second insulating layer
- 18** first electrode
- 19B** blue-emitting organic EL element
- 19G** green-emitting organic EL element
- 19R** red-emitting organic EL element
- 24** pixel area
- 24B** blue-emitting pixel area
- 24G** green-emitting pixel area
- 24R** red-emitting pixel area
- 30** transparent second electrode
- 32** protection layer

36 transparent cover  
 36' transparent conformable cover  
 40 desiccant material  
 40' desiccant seal material  
 103 anode layer  
 105 hole-injecting layer  
 107 hole-transporting layer  
 109 light-emitting layer  
 111 electron-transporting layer  
 113 cathode layer  
 250 voltage/current source  
 260 conductive wiring

What is claimed is:

1. A top-emitting OLED display device comprising:
  - a) a substrate;
  - b) an array of OLED elements disposed over one side of the substrate wherein the light-emitting area of each OLED element defines a light-emitting pixel area; and
  - c) desiccant material provided in a patterned arrangement over the array of OLED elements on the same side of the substrate, such that the desiccant material is provided between the light-emitting pixel areas, and wherein the desiccant material is light absorbing and serves as a black matrix for improving contrast.
2. The display device claimed in claim 1, wherein the organic light emitting elements comprise a plurality of layers including one or more insulating layers and the patterned arrangement of desiccant material comprises one or more of the insulating layers.
3. The display device claimed in claim 1, wherein the desiccant material includes a light absorber selected from the group consisting of dyes and pigments.
4. The display device claimed in claim 1, wherein the desiccant material includes a light absorber selected from the group consisting of carbon black, graphite, metal oxides, and metal sulfides.
5. The display device claimed in claim 1, wherein the desiccant is also provided around the perimeter of the device.
6. The display device claimed in claim 1, wherein the array of OLED elements comprises:
  - a) an array of first electrodes;
  - b) an array of organic electro-luminescent elements deposited over the array of first electrodes;
  - c) a transparent, common second electrode provided over the array of organic electro-luminescent elements; and
  - d) wherein the desiccant is provided in contact with the second electrode.
7. The display device claimed in claim 1, wherein the array of OLED elements comprises:
  - a) an array of first electrodes;
  - b) an array of organic electro-luminescent elements deposited over the array of first electrodes;
  - c) a transparent, common second electrode provided over the array organic electro-luminescent elements; and
  - d) a transparent protection layer provided over the common second electrode;
 wherein the desiccant is provided in contact with the transparent protection layer.
8. The display device claimed in claim 1, wherein the top-emitting OLED display device includes a transparent cover provided over the OLED elements and the patterned arrangement of desiccant material is located on the inside of the transparent cover.
9. The display device claimed in claim 1, wherein the patterned arrangement of desiccant material comprises a plurality of layers.

10. The display device claimed in claim 1, wherein the patterned arrangement of desiccant material is a thick film layer.

11. The display device claimed in claim 1, wherein the desiccant material includes a desiccant selected from the group consisting of alkaline metal oxides, alkaline earth metal oxides, sulfates, metal halides, and perchlorates.

12. The display device claimed in claim 1, wherein the desiccant material includes a moisture absorption rate enhancing or maintaining binder selected from the group consisting of cellulose acetates, epoxies, phenoxies, siloxanes, methacrylates, sulfones, phthalates, and amides.

13. The display device claimed in claim 12, wherein the moisture absorption rate enhancing or maintaining binder is a radiation-curable binder selected from the group consisting of radiation-curable photoresist compositions.

14. The display device claimed in claim 1, wherein the desiccant material includes a moisture-absorption rate-enhancing radiation-curable binder selected from the group consisting of acrylates, methacrylates, cyclized polyisoprenes, polyvinyl cinnamates, epoxies, silicones, and adhesives.

15. The display device claimed in claim 1, wherein the desiccant material is conformable to the surface of the materials deposited over the substrate.

16. The display device claimed in claim 1, further comprising a transparent cover that is conformable to the surface of the materials deposited over the substrate.

17. A top-emitting OLED display device comprising:

- a) a substrate;
- b) an array of thin film transistors provided over the substrate;
- c) a patterned first insulating layer provided over the array of thin film transistors;
- d) an array of first electrodes in electrical contact with the thin film transistors;
- e) a second insulating layer provided over the array of first electrodes, wherein the second insulating layer is patterned to expose at least a portion of the first electrodes, the area of which defines the light-emitting pixel area;
- f) an array of organic electro-luminescent elements deposited over the array of first electrodes;
- g) a transparent, common second electrode provided over the array of organic electro-luminescent elements; and
- h) desiccant material provided in a patterned arrangement over the second electrode, such that the desiccant material is provided between the light-emitting pixel areas, and wherein the desiccant material is light absorbing and serves as a black matrix for improving contrast.

18. A top-emitting OLED display device 17 comprising:

- a) a substrate;
- b) an array of thin film transistors provided over the substrate;
- c) a patterned first insulating layer provided over the array of thin film transistors;
- d) an array of first electrodes in electrical contact with the thin film transistors;
- e) a second insulating layer provided over the array of first electrodes, wherein the second insulating layer is patterned to expose at least a portion of the first electrodes, the area of which defines the light-emitting pixel area;
- f) an array of organic electro-luminescent elements deposited over the array of first electrodes;
- g) a transparent, common second electrode provided over the array of organic electro-luminescent elements; and

## 13

h) desiccant material provided in a patterned arrangement over the second electrode, such that the desiccant material is provided between the light-emitting pixel areas wherein the light-emitting pixel areas are located in recessed areas, the patterned second insulating layer defines raised areas, and the desiccant is applied to the raised areas by contact printing. 5

19. A top-emitting OLED display device comprising:

- a) a substrate;
- b) an array of thin film transistors provided over the substrate; 10
- c) a patterned first insulating layer provided over the array of thin film transistors;

## 14

- d) an array of first electrodes in electrical contact with the thin film transistors;
- e) a second insulating layer provided over the array of first electrodes, wherein the second insulating layer is patterned to expose at least a portion of the first electrodes, the area of which defines a light-emitting pixel area;
- f) an array of organic electro-luminescent elements deposited over the array of first electrodes;
- g) a transparent, common second electrode provided over the array organic electro-luminescent elements; and
- h) wherein the first insulating layer or the second insulating layer or both comprise a desiccant material.

\* \* \* \* \*

|                |                                                                                                    |         |            |
|----------------|----------------------------------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | OLED显示器的干燥剂结构                                                                                      |         |            |
| 公开(公告)号        | <a href="#">US6835953</a>                                                                          | 公开(公告)日 | 2004-12-28 |
| 申请号            | US10/408910                                                                                        | 申请日     | 2003-04-08 |
| [标]申请(专利权)人(译) | 库克群岛RONALD小号<br>BOROSON MICHAEL大号<br>OTOOLE泰伦斯 - [R                                                |         |            |
| 申请(专利权)人(译)    | 库克群岛RONALD S.<br>BOROSON MICHAEL L.<br>O'TOOLE泰伦斯R.                                                |         |            |
| 当前申请(专利权)人(译)  | 全球OLED科技有限责任公司                                                                                     |         |            |
| [标]发明人         | COK RONALD S<br>BOROSON MICHAEL L<br>OTOOLE TERRENCE R                                             |         |            |
| 发明人            | COK, RONALD S.<br>BOROSON, MICHAEL L.<br>O'TOOLE, TERRENCE R.                                      |         |            |
| IPC分类号         | H01L27/32 H01L27/28 H01L51/50 H01L51/52 H05B33/04 H01L51/56 H01L31/20                              |         |            |
| CPC分类号         | H01L27/3211 H01L51/5259 H01L51/5284 H01L51/5237 H01L27/3244 H01L27/3295 H01L51/56<br>H01L2251/5315 |         |            |
| 审查员(译)         | 内尔姆斯, DAVID                                                                                        |         |            |
| 其他公开文献         | US20030203551A1                                                                                    |         |            |
| 外部链接           | <a href="#">Espacenet</a> <a href="#">USPTO</a>                                                    |         |            |

#### 摘要(译)

本发明提供一种顶部发光OLED显示装置，包括基板；OLED元件阵列设置在基板的一侧；以及在基板的同一侧上的OLED元件阵列上方以图案化布置提供的干燥剂材料，使得干燥剂材料不会干扰OLED元件发射的光。

