



US007572668B2

(12) **United States Patent**
Suh et al.

(10) **Patent No.:** **US 7,572,668 B2**
(45) **Date of Patent:** **Aug. 11, 2009**

(54) **METHOD OF PATTERNING AN ORGANIC THIN FILM, AN ORGANIC THIN FILM TRANSISTOR, A METHOD OF MANUFACTURING AN ORGANIC THIN FILM TRANSISTOR, AND AN ORGANIC ELECTROLUMINESCENCE DISPLAY DEVICE HAVING THE ORGANIC THIN FILM TRANSISTOR**

(75) Inventors: **Min-Chul Suh**, Suwon-si (KR);
Jae-Bon Koo, Suwon-si (KR)

(73) Assignee: **Samsung Mobile Display Co., Ltd.**,
Yongin, Gyunggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 483 days.

(21) Appl. No.: **11/378,557**

(22) Filed: **Mar. 16, 2006**

(65) **Prior Publication Data**
US 2006/0216852 A1 Sep. 28, 2006

(30) **Foreign Application Priority Data**
Mar. 24, 2005 (KR) 10-2005-0024564

(51) **Int. Cl.**
H01L 51/40 (2006.01)

(52) **U.S. Cl.** **438/99; 438/106; 438/122; 257/40; 257/53**

(58) **Field of Classification Search** **438/99, 438/106, 122, 124, 125; 257/40, 53, 61**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,459,337 B2* 12/2008 Kang et al. 438/99
2004/0104461 A1* 6/2004 Ishihara et al. 257/679
2005/0116231 A1* 6/2005 Kang et al. 257/72

FOREIGN PATENT DOCUMENTS

JP 2003-092410 3/2003
KR 1020040028010 A 4/2004
KR 1020040084427 A 10/2004

* cited by examiner

Primary Examiner—Phuc T Dang

(74) *Attorney, Agent, or Firm*—Knobbe Martens Olson & Bear, LLP.

(57) **ABSTRACT**

Provided is a method of patterning an organic thin film which can prevent surface damage of an organic semiconductor layer. Also, an organic thin film transistor that can reduce an off-current and can prevent surface damage of the organic semiconductor layer and a method of manufacturing the organic thin film transistor, and an organic electroluminescence display device having the organic thin film transistor are provided. The method of patterning the organic thin film includes forming the organic thin film on a substrate, selectively printing a mask material on a portion of the organic thin film, dry etching an exposed portion of the organic thin film using the mask material, and removing the mask material.

12 Claims, 9 Drawing Sheets




FIG. 1 (PRIOR ART)




FIG. 2 (PRIOR ART)




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 7




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D





FIG. 9



METHOD OF PATTERNING AN ORGANIC THIN FILM, AN ORGANIC THIN FILM TRANSISTOR, A METHOD OF MANUFACTURING AN ORGANIC THIN FILM TRANSISTOR, AND AN ORGANIC ELECTROLUMINESCENCE DISPLAY DEVICE HAVING THE ORGANIC THIN FILM TRANSISTOR

CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of Korean Patent Application No. 10-2005-0024564, filed on Mar. 24, 2005, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present embodiments relate to an organic thin film transistor, and more particularly, to a method of patterning an organic thin film which prevents the surface of an organic semiconductor layer from being damaged. The present embodiments also provide an organic thin film transistor and an organic electroluminescence display device having an organic thin film transistor that can prevent surface damage and can reduce an off-current of an organic semiconductor layer and a method of manufacturing the organic thin film transistor.

2. Description of the Related Art

Studies on organic thin film transistors (OTFTs) for use in next generation display devices have been actively performed. OTFTs use an organic film instead of a silicon film as a semiconductor layer, and are classified into low molecule organic thin film transistors using oligothiophene and pentacene, and polymer organic thin film transistors using polythiophene, according to the material for forming the organic film.

An organic electroluminescence display device that uses an organic thin film transistor as a switching device includes at least two organic thin film transistors, for example, one switching organic thin film transistor and one driving organic thin film transistor, one capacitor, and an organic light emitting diode having an organic film layer interposed between upper and lower electrodes.

Typically, a flexible organic electroluminescence display device uses a flexible substrate that includes a plastic substrate. The organic electroluminescence display device that uses the plastic substrate has to be manufactured in a low temperature process since the plastic substrate has very low thermal stability.

Accordingly, an organic thin film transistor that uses an organic film as a semiconductor layer has been largely considered as an alternative for the switching device of the flexible organic electroluminescence display device since the organic thin film transistor can be manufactured in a low temperature process.

A pentacene thin film transistor that can reduce the thin film deposition time and improve the hole mobility has been disclosed in Korea Patent Laid-Open No. 2004-0028010. A device structure of an organic thin film transistor and a method of manufacturing the organic thin film transistor that can improve the electrical performance of the transistor have been disclosed in Korea Patent Publication No. 2004-0084427. Also, a thin film transistor that can improve carrier mobility and on/off current ratio by forming a channel region

into an organic compound having a radical has been disclosed in Japanese Laid-Open Patent No. 2003-92410.

FIG. 1 is a cross-sectional view of a conventional organic thin film transistor having a top gate structure.

Referring to FIG. 1, a conventional organic thin film transistor 10 includes a gate electrode 12 formed on a substrate 11, a gate insulating film 13 formed on the substrate 11 including the gate electrode 12, source and drain electrodes 14 and 15 formed on the gate insulating film 13, and a semiconductor layer 16 formed on the source and drain electrodes 14 and 15 and the gate insulating film 13.

In the conventional organic thin film transistor 10 having the above structure, the semiconductor layer 16 includes an organic semiconductor layer, and the unpatterned semiconductor layer 16 is formed on the entire surface of the substrate 11. Therefore, there is a problem of a leakage current due to the accumulation of carriers, for example, holes, between the semiconductor layer 16 and the gate insulating film 13.

To solve the above problem, when the organic semiconductor layer is pattern using an ablation method, as depicted in FIG. 2, thermal denaturation or recasting by a laser can occur at edge portions of the patterned semiconductor layer.

SUMMARY OF THE INVENTION

The present embodiments provide a method of patterning an organic thin film, in organic semiconductor layer can be patterned without surface damage of the organic semiconductor layer.

The present embodiments also provide an organic thin film transistor that can reduce an off-current and can prevent the surface of the organic semiconductor layer from being damaged and a method of manufacturing the organic thin film transistor.

Some embodiments relate to a method of patterning an organic thin film, comprising:

- forming the organic thin film on a substrate;
- selectively printing a mask material on a portion of the organic thin film;
- dry etching an exposed portion of the organic thin film using the mask material; and
- removing the mask material.

The present embodiments also provide an organic electroluminescence display device having an organic thin film transistor that can reduce an off-current and can prevent the surface of the organic semiconductor layer from being damaged.

According to an aspect of the present embodiments, there is provided a method of patterning an organic thin film, comprising: forming the organic thin film on a substrate; selectively printing a mask material on a portion of the organic thin film; dry etching an exposed portion of the organic thin film using the mask material; and removing the mask material.

The organic thin film comprises an organic semiconductor layer and at least one organic material selected from the group consisting of pentacene, tetracene, anthracene, naphthalene, alpha-6-thiophene, alpha-4-thiophene, perylene and its derivatives, rubrene and its derivatives, coronene and its derivatives, perylene tetracarboxylic diimide and its derivatives, perylene tetracarboxylic dianhydride and its derivatives, polythiophene and its derivatives, polyparaphenylenevinylene and its derivatives, polyparaphenylene and its derivatives, polyfluorene and its derivatives, polythiophene vinylene and its derivatives, thiophene-heterocyclic aromatic copolymer and its derivatives, oligonaphthalene and its derivatives, alpha-5-thiophenyl oligothiophene and its derivatives, phthalocyanine that does not include a metal and

its derivatives, pyromellitic dianhydride and its derivatives, pyromellitic diimide and its derivatives, perylene tetracarboxylic acid dianhydride and its derivatives, naphthalene tetracarboxylic acid diimide and its derivatives, and naphthalene tetracarboxylic acid dianhydride and its derivatives.

The organic thin film may be dry etched using an O₂ ashing process. The mask material may comprise a low viscosity paraffin wax group or a grease group. The mask material may be removed through a washing process using n-hexane.

According to an aspect of the present embodiments, there is provided a method of manufacturing a thin film transistor, comprising: forming source and drain electrodes on a substrate; forming an organic semiconductor layer on the source and drain electrodes and the substrate; selectively printing a mask material on a portion of the organic semiconductor layer; patterning the organic semiconductor layer by a dry etching method using the mask material; forming a gate insulating film on the substrate; and forming a gate electrode on the gate insulating film.

According to an aspect of the present embodiments, there is provided a method of manufacturing a thin film transistor, comprising: forming a gate electrode on a substrate; forming a gate insulating film on the substrate; forming source and drain electrodes on the gate insulating film; forming an organic semiconductor layer on the substrate; selectively forming a mask material on a portion of the organic semiconductor layer; and patterning the organic semiconductor layer by a dry etching method using the mask material.

According to another aspect of the present embodiments, there is provided an organic thin film transistor manufactured according to the method described above and a flat display device having the organic thin film transistor.

The flat display device may comprise a plurality of pixels arranged in a matrix in rows and columns, each of the pixels having at least one organic thin film transistor, wherein the organic thin film transistor comprises one or more gate electrodes, one or more source electrodes and one or more drain electrodes, and a semiconductor layer, and the semiconductor layer has a box shape, a line shape extended in a row or column directions corresponding to at least the source and drain electrodes and a portion between the source and drain electrodes.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features and advantages of the present embodiments will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings in which:

FIG. 1 is a cross-sectional view of a conventional organic thin film transistor;

FIG. 2 is a SEM (scanning electron microscope) image showing the surface damage of an organic semiconductor layer in a conventional organic thin film transistor when the organic semiconductor layer is patterned using a laser ablation method;

FIGS. 3A through 3D are cross-sectional views for explaining a method of patterning an organic thin film transistor according to an embodiment;

FIG. 4 is a cross-sectional view illustrating an organic thin film transistor according to an embodiment;

FIGS. 5A through 5D are cross-sectional views for explaining a method of manufacturing an organic thin film transistor according to an embodiment;

FIGS. 6A through 6D are plan views illustrating a pattern of an organic semiconductor layer in an organic thin film transistor of an organic electroluminescence display device according to an embodiment;

FIG. 7 is a cross-sectional view illustrating an organic thin film transistor according to another embodiment;

FIGS. 8A through 8D are cross-sectional views for explaining a method of manufacturing an organic thin film transistor according to another embodiment; and

FIG. 9 is a cross-sectional view illustrating an organic electroluminescence display device having an organic thin film transistor according to an embodiment.

DETAILED DESCRIPTION OF THE INVENTION

The present embodiments will now be described more fully with reference to the accompanying drawings in which exemplary embodiments are shown.

FIGS. 3A through 3D are cross-sectional views for demonstrating a method of patterning an organic thin film transistor according to an embodiment.

Referring to FIG. 3A, an organic thin film 33 is formed on a substrate 31. The substrate 31 may include a plastic substrate and the organic thin film 33 may include an organic semiconductor layer.

The substrate 31 includes a plastic film selected from the group consisting of polyethersulphone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylene naphthalate (PEN), polyethylene terephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide, polycarbonate (PC), cellulose triacetate (TAC), and cellulose acetate propionate (CAP).

The organic semiconductor layer 33 includes at least one organic film selected from the group consisting of pentacene, tetracene, anthracene, naphthalene, alpha-6-thiophene, alpha-4-thiophene, perylene and its derivatives, rubrene and its derivatives, coronene and its derivatives, perylene tetracarboxylic diimide and its derivatives, perylene tetracarboxylic dianhydride and its derivatives, polythiophene and its derivatives, polyparaphenylenevinylene and its derivatives, polyparaphenylene and its derivatives, polyfluorene and its derivatives, polythiophene vinylene and its derivatives, thiopheneheterocyclic aromatic copolymer and its derivatives, oligonaphthalene and its derivatives, alpha-5-thiophenyl oligothiophene and its derivatives, phthalocyanine that does not include a metal and its derivatives, pyromellitic dianhydride and its derivatives, pyromellitic diimide and its derivatives, perylene tetracarboxylic acid dianhydride and its derivatives, naphthalene tetracarboxylic acid diimide and its derivatives, and naphthalene tetracarboxylic acid dianhydride and its derivatives.

Referring to FIG. 3B and FIG. 3C, a mask material 35 is selectively printed on the organic thin film 33. The mask material 35 may have a thickness in consideration of the thickness and etching rate of the organic film during a subsequent dry etching process for patterning the organic film. The mask material 35 can be formed of a material group, such as a low viscosity paraffin wax or grease, and can be selectively formed on desired portions of the organic thin film 33.

The organic thin film 33 is patterned by etching exposed portions of the organic thin film 33 using the mask material 35. At this time, the organic thin film 33 is etched by a dry etching method using an O₂ ashing process. Referring to FIG. 3D, an organic thin film pattern 37 is formed by removing the mask material 35 through a cleaning process using n-hexane.

In the present embodiment, the organic semiconductor layer is patterned by a dry etching method using the mask

material, such as wax or grease group, but the present embodiments are not limited thereto. That is, various organic materials can be patterned by the dry etching method using wax or grease group as the mask material.

FIG. 4 is a cross-sectional view illustrating an organic thin film transistor used for a flexible organic electroluminescence display device according to an embodiment. The organic thin film transistor 100 according to an embodiment has a top gate structure.

Referring to FIG. 4, the organic thin film transistor 100 includes source and drain electrodes 121 and 125 formed on a substrate 110. A semiconductor layer 135 is formed on the substrate 110. A portion of the semiconductor layer 135 between the source and drain electrodes 121 and 125 serves as a channel layer. Preferably, the substrate 110 includes a plastic substrate, and the semiconductor layer 135 includes an organic semiconductor layer.

A gate insulating film 140 is formed on the substrate 110 and the semiconductor layer 135. A gate electrode 155 is formed on the gate insulating film 140 corresponding to the channel layer of the semiconductor layer 135 located between the source and drain electrodes 121 and 125.

The substrate 110 includes a plastic film selected from the group consisting of polyethersulphone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylene naphthalate (PEN), polyethylene terephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide, polycarbonate (PC), cellulose triacetate (TAC), and cellulose acetate propionate (CAP).

The gate insulating film 140 can be configured into a single layer or multi-layer films of an organic insulating film or an inorganic insulating film or an organic-inorganic hybrid film. The insulating film 140 includes an inorganic insulating film, such as SiO₂, SiN_x, Al₂O₃, Ta₂O₅, BST (barium strontium titanate), and PZT (lead zirconate titanate), or an organic insulating film, such as BCB (benzo-cyclo-butene), polyimide, parylene, and polyvinylphenol (PVP).

The semiconductor layer 135 includes at least one organic film selected from the group consisting of pentacene, tetracene, anthracene, naphthalene, alpha-6-thiophene, alpha-4-thiophene, perylene and its derivatives, rubrene and its derivatives, coronene and its derivatives, perylene tetracarboxylic diimide and its derivatives, perylene tetracarboxylic dianhydride and its derivatives, polythiophene and its derivatives, polyparaphenylenevinylene and its derivatives, polyparaphenylene and its derivatives, polyfluorene and its derivatives, polythiophene vinylene and its derivatives, thiophene-heterocyclic aromatic copolymer and its derivatives, oligonaphthalene and its derivatives, alpha-5-thiophenyl oligothiophene and its derivatives, phthalocyanine that does not include a metal and its derivatives, pyromellitic dianhydride and its derivatives, pyromellitic diimide and its derivatives, perylene tetracarboxylic acid dianhydride and its derivatives, naphthalene tetracarboxylic acid diimide and its derivatives, and naphthalene tetracarboxylic acid dianhydride and its derivatives.

The semiconductor layer 135 is patterned in a region corresponding at least to a portion between the source and drain electrodes 121 and 125. FIGS. 6A through 6D are plan views illustrating a pattern of a semiconductor layer 135 in an organic thin film transistor of an organic electroluminescence display device according to an embodiment.

FIGS. 6A through 6D show a thin film transistor connected to a gate line 101 and a data line 103 of thin film transistors that constitute one pixel of an organic electroluminescence display device. The present embodiment shows an example of using a thin film transistor for making a pixel, but the present

embodiments are not limited thereto. That is, the present embodiment can be applied to any thin film transistors used for organic electroluminescence display devices.

Referring to FIG. 6A, the semiconductor layer 135 is individually arranged in each pixel region 105 defined by the gate line 101 and the data line 103, and a power supply line (not shown), and has a box pattern corresponding at least to the source and drain electrodes 121 and 125 and a portion between the source and drain electrodes 121 and 125.

At this time, the semiconductor layer 135 is arranged in each of the pixel regions, and can have a separated pattern respectively corresponding to a plurality of thin film transistors arranged in each of the pixel regions or can have a separated pattern corresponding to a plurality of thin film transistors arranged in each of the pixel regions.

As another example, the semiconductor layer 135 can be formed in a box shape by overlapping with the gate line 101 and the data line 103 outside of the corresponding pixel region 105 or can be formed over a neighboring pixel region 105a to be separated from a thin film transistor arranged in the neighboring pixel region 105a.

Referring to FIG. 6B, the semiconductor layer 135 has a line shape extended to correspond to the pixel region arranged in a row direction of a plurality of pixel regions defined by the gate line 101 and the data line 103. The semiconductor layer 135 is formed to separate from the thin film transistors arranged in the pixel regions 105a arranged in the neighboring rows of a plurality of pixel regions.

When a plurality of thin film transistors are arranged in the pixel region arranged in the row direction, the semiconductor layer 135 can have a line shaped pattern, separated to respectively correspond to the plural thin film transistors or can have a line shaped pattern corresponding to the plural thin film transistors.

As another example, the semiconductor layer 135 is formed in a line shape by overlapping with the gate line 101 or is formed in a line pattern formed extending along the gate line 101 over the neighboring pixel region 105a outside of the pixel region 105.

Referring to FIG. 6C, the semiconductor layer 135 has a line shape extended corresponding to the pixel regions arranged in a column direction of a plurality of pixel regions defined by the gate line 101 and the data line 103. The semiconductor layer 135 is formed to separate from the thin film transistors arranged in the pixel regions 105a arranged in the neighboring columns of a plurality of pixel regions.

Also, when a plurality of thin film transistors are arranged in the pixel regions arranged in the column direction, the semiconductor layer 135 can have a line shaped pattern separated to respectively correspond to the plural thin film transistors or can have a line shaped pattern corresponding to the plural thin film transistors.

As another example, the semiconductor layer 135 is formed to overlap with the data line 103 outside of the pixel region 105 or formed in a line pattern formed extending along the data line 103 over the neighboring pixel regions 105a.

Referring to FIG. 6D, the semiconductor layer 135 has a mesh shape extended to correspond to pixel regions arranged in row and column directions of a plurality of pixel regions defined by the gate line 101 and the data line 103. The semiconductor layer 135 is formed along the data line 103 and the gate line 101 on a portion corresponding to the plural pixel regions.

Also, when a plurality of thin film transistors are arranged in the pixel region arranged in a row direction, the semiconductor layer 135 can have a pattern separated to respectively

correspond to the plural thin film transistors or can have a pattern corresponding to the plural thin film transistors.

As another example, the semiconductor layer **135** is formed to overlap with the gate line **101** and/or the data line **103** outside of the pixel region **105** or has a mesh shaped pattern formed extending along the gate line **101** and the data line **103** over the neighboring pixel regions **105a**.

FIGS. **5A** through **5D** are cross-sectional views for explaining a method of manufacturing an organic thin film transistor having a top gate structure according to an embodiment.

Referring to FIG. **5A**, the source and drain electrodes **121** and **125** are formed on the plastic substrate **110**, and an organic semiconductor layer **130** covering the source and drain electrodes **121** and **125** is formed on the entire surface of the substrate **110**. Referring to FIG. **5B** and FIG. **5C**, a mask material **160** is selectively formed on a portion of the organic semiconductor layer **130** corresponding to the source and drain electrodes **121** and **125** and a portion between the source and drain electrodes **121** and **125**. The mask material **160** includes a low viscosity paraffin wax or a grease group.

Referring to FIG. **5C**, the exposed portion of the semiconductor layer **130** is dry etched by an O₂ ashing process using the mask material **160**. The mask material **160** is formed to a thickness in consideration of the etching rate and the thickness of the exposed portion of semiconductor layer **130** since the organic semiconductor layer **130** must be etched except for the portion **135** under the mask material **160**.

Referring to FIG. **5D**, the mask material **160** (not shown) is removed through a cleaning process using n-hexane. Then, the patterned organic semiconductor layer **135** is completed. At this time, the patterned organic semiconductor layer **135** has the same pattern as depicted in FIGS. **6A** through **6D**.

According to one embodiment, the surface damage of the organic semiconductor layer by laser can be prevented and an off-current of the transistor can be reduced by preventing the accumulation of carriers since the semiconductor layer is patterned through the dry etching process and not by a laser ablation method (LAT).

FIG. **7** is a cross-sectional view illustrating an organic thin film transistor used for a flexible organic electroluminescence display device according to another embodiment. The organic thin film transistor **200** according to another embodiment has a bottom gate structure.

Referring to FIG. **7**, a gate electrode **225** is formed on a substrate **210**, and a gate insulating film **230** is formed on the gate electrode **225** and the substrate **210**. Source and drain electrodes **241** and **245** are formed on the gate insulating film **230**, and a semiconductor layer **255** is formed on the gate insulating film **230** corresponding the source and drain electrodes **241** and **245** and a portion between the source and drain electrodes **241** and **245**. The semiconductor layer **255** has various shapes of pattern as depicted in FIGS. **6A** through **6D**.

The substrate **210** can be a plastic substrate, and includes a plastic film selected from the group consisting of polyethersulphone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylene naphthalate (PEN), polyethylene terephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide, polycarbonate (PC), cellulose triacetate (TAC), and cellulose acetate propionate (CAP).

The gate insulating film **230** can be configured into a single layer or multi-layer films of an organic insulating film or an inorganic insulating film or an organic-inorganic hybrid film. The insulating film **230** includes an inorganic insulating film, such as SiO₂, SiNx, Al₂O₃, Ta₂O₅, BST, and PZT, or an organic insulating film, such as BCB, polyimide, parylene, and polyvinylphenol (PVP).

The semiconductor layer **255** includes an organic semiconductor layer, and the semiconductor layer **255** includes at least one organic film selected from the group consisting of pentacene, tetracene, anthracene, naphthalene, alpha-6-thiophene, alpha-4-thiophene, perylene and its derivatives, rubrene and its derivatives, coronene and its derivatives, perylene tetracarboxylic diimide and its derivatives, perylene tetracarboxylic dianhydride and its derivatives, polythiophene and its derivatives, polyparaphenylenevinylene and its derivatives, polyparaphenylene and its derivatives, polyfluorene and its derivatives, polythiophene vinylene and its derivatives, thiophene-heterocyclic aromatic copolymer and its derivatives, oligonaphthalene and its derivatives, alpha-5-thiophenyl oligothiophene and its derivatives, phthalocyanine that does not include a metal and its derivatives, pyromellitic dianhydride and its derivatives, pyromellitic diimide and its derivatives, perylene tetracarboxylic acid dianhydride and its derivatives, naphthalene tetracarboxylic acid diimide and its derivatives, and naphthalene tetracarboxylic acid dianhydride and its derivatives.

FIGS. **8A** through **8D** are cross-sectional views for explaining a method of manufacturing an organic thin film transistor having a bottom gate structure according to another embodiment.

Referring to FIG. **8A**, a gate electrode **225** is formed on a plastic substrate **210**, and a gate insulating film **230** is formed on the gate electrode **225** and the substrate **210**. Referring to FIG. **8B**, source and drain electrodes **241** and **245** are formed on the gate insulating film **230**. An organic semiconductor layer **250** covering the source and drain electrodes **241** and **245** is formed on the gate insulating film **230**.

Referring to FIG. **8C**, a mask material **260** is selectively printed on the organic semiconductor layer **250**. The mask material **260** includes a low viscosity paraffin wax or a grease group, and the mask material **260** is selectively formed on a portion of the organic semiconductor layer that will remain after the organic semiconductor layer is patterned.

Referring to FIG. **8D**, a patterned semiconductor layer **255** is formed by patterning the exposed portion of the organic semiconductor layer **250** of FIG. **8D** by a dry etching using an O₂ ashing process using the mask material **260**. The patterned semiconductor layer **255** is patterned to have the same shape as depicted in FIGS. **6A** through **6D**. A thin film transistor **200** as depicted in FIG. **7** is formed by removing the remained mask material **260** (not shown) through a cleaning process using n-hexane.

FIG. **9** is a cross-sectional view illustrating an organic electroluminescence display device having an organic thin film transistor with a top gate structure according to an embodiment. FIG. **9** is a cross-sectional view of one pixel of the organic electroluminescence display device, which includes an organic electroluminescence diode and a thin film transistor for driving the organic electroluminescence diode of one of the pixels.

Referring to FIG. **9**, an organic electroluminescence display device **300** includes source and drain electrodes **321** and **325** formed on a plastic substrate **310**. A semiconductor layer **330** is formed on the source and drain electrodes **321** and **325** and the plastic substrate **310**. A gate insulating film **340** is formed on the semiconductor layer **330**. The semiconductor layer **330** has a pattern as depicted in FIGS. **6A** through **6D**.

A gate electrode **350** is formed on the gate insulating film **340**, and a protection film **360** having a via hole **365** that exposes a portion of one of the source and drain electrodes **321** and **325**, for example, the drain electrode **325**, is formed on the substrate **310**.

A lower electrode 370 which is connected to the drain electrode 325 of the thin film transistor through the via hole 365 is formed on the protection film 360. The lower electrode 370 is an anode electrode and serves as a pixel electrode. A pixel isolation film 380 having an opening 385 that exposes a portion of the lower electrode 370 is formed.

An organic film layer 390 is formed on the lower electrode 370 exposed by the opening 385 of the pixel isolation film 380, and a cathode electrode 395 is formed on the pixel isolation film 380 and the organic film layer 390. The organic film layer 390 includes at least one organic film layer selected from, for example, a hole injection layer, a hole transport layer, a light emitting layer, an electron injection layer, an electron transport layer, and a hole blocking layer etc.

Even though it is not shown, the organic thin film transistor having the bottom gate structure depicted in FIG. 7 can also be applied to an organic electroluminescence display device.

The present embodiments have been described with regard to an organic electroluminescence display device having an organic thin film transistor as a switching device, but the present embodiments can also be applied to a flat display device, such as a liquid crystal device that uses the organic thin film transistor as the switching device. Accordingly, the off-current of the thin film transistor of the flat display device can be reduced and also the surface damage of an organic semiconductor layer of the flat display device can be prevented.

Also, although the present embodiments have been described in conjunction with in a flexible organic electroluminescence display device having a plastic substrate, for which patterning of the semiconductor layer is performed through a dry etching method using a mask material, such as wax, the present embodiments are not limited thereto. That is, the dry etching method using the mask material can be applied to pattern an organic semiconductor layer on a substrate, such as a metal substrate or a glass substrate or can be applied to form an organic thin film transistor.

The organic thin film transistor and the method of manufacturing the organic thin film transistor according to the present embodiment not only prevents the surface damage of the semiconductor layer but also reduces the off-current of the thin film transistor by preventing the leakage current caused by the accumulation of carriers, since the semiconductor layer is formed through a dry etching process with O₂ ashing using wax as a mask material.

While the present embodiments have been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present embodiments as defined by the following claims.

What is claimed is:

1. A flat display device having an organic thin film transistor formed by the following method:

forming a gate electrode on a substrate;
forming a gate insulating film on the substrate;
forming source and drain electrodes on the gate insulating film;

forming an organic semiconductor layer on the substrate;
selectively forming a mask material on a portion of the organic semiconductor layer; and
patterning the organic semiconductor layer by a dry etching method using the mask material;

wherein the flat display device comprises a plurality of pixels arranged in a matrix shape having rows and columns, each of the pixels having at least one organic thin film transistor, wherein

the organic thin film transistor comprises one or more gate electrodes, one or more source electrodes and one or more drain electrodes, and a semiconductor layer, and the semiconductor layer has a box shape, a line shape extended in a row or column direction, or a mesh shape extended in row and column directions corresponding to at least the source and drain electrodes and a portion between the source and drain electrodes.

2. The flat display device of claim 1, wherein the substrate comprises a plastic substrate.

3. The flat display device of claim 1, wherein the organic semiconductor layer comprises at least one organic material selected from the group consisting of pentacene, tetracene, anthracene, naphthalene, alpha-6-thiophene, alpha-4-thiophene, perylene and its derivatives, rubrene and its derivatives, coronene and its derivatives, perylene tetracarboxylic diimide and its derivatives, perylene tetracarboxylic dianhydride and its derivatives, polythiophene and its derivatives, polyparaphenylenevinylene and its derivatives, polyparaphenylene and its derivatives, polyfluorene and its derivatives, polythiophene vinylene and its derivatives, thiophene-heterocyclic aromatic copolymer and its derivatives, oligonaphthalene and its derivatives, alpha-5-thiophenyl oligothiophene and its derivatives, phthalocyanine that does not include a metal and its derivatives, pyromellitic dianhydride and its derivatives, pyromellitic diimide and its derivatives, perylene tetracarboxylic acid dianhydride and its derivatives, naphthalene tetracarboxylic acid diimide and its derivatives, and naphthalene tetracarboxylic acid dianhydride and its derivatives.

4. The flat display device of claim 1, wherein the organic semiconductor layer is dry etched through an O₂ ashing process.

5. The flat display device of claim 1, wherein the mask material comprises a low viscosity paraffin wax group or a grease group.

6. The flat display device of claim 1, wherein the mask material is removed through a cleaning process using n-hexane.

7. A flat display device having an organic thin film transistor formed by the following method:

forming the organic thin film on a substrate;
selectively printing a mask material on a portion of the organic thin film;

dry etching an exposed portion of the organic thin film using the mask material; and
removing the mask material;

wherein the flat display device comprises a plurality of pixels arranged in a matrix shape having rows and columns, each of the pixels having at least one organic thin film transistor, wherein

the organic thin film transistor comprises one or more gate electrodes, one or more source electrodes and one or more drain electrodes, and a semiconductor layer, and the semiconductor layer has a box shape, a line shape extended in a row or column direction, or a mesh shape extended in row and column directions corresponding to at least the source and drain electrodes and a portion between the source and drain electrodes.

8. The flat display device of claim 7, wherein the organic thin film comprises an organic semiconductor layer.

9. The flat display device of claim 8, wherein the organic thin film comprises at least one organic material selected from the group consisting of pentacene, tetracene, anthracene, naphthalene, alpha-6-thiophene, alpha-4-thiophene, perylene and its derivatives, rubrene and its derivatives, coronene and its derivatives, perylene tetracarboxylic diimide and

11

its derivatives, perylene tetracarboxylic dianhydride and its derivatives, polythiophene and its derivatives, polyparaphenylenevinylene and its derivatives, polyparaphenylene and its derivatives, polyfluorene and its derivatives, polythiophene vinylene and its derivatives, thiophene-heterocyclic aromatic copolymer and its derivatives, oligonaphthalene and its derivatives, alpha-5-thiophenyl oligothiophene and its derivatives, phthalocyanine that does not include a metal and its derivatives, pyromellitic dianhydride and its derivatives, pyromellitic diimide and its derivatives, perylene tetracarboxylic acid dianhydride and its derivatives, naphthalene tet-

12

racarboxylic acid diimide and its derivatives, and naphthalene tetracarboxylic acid dianhydride and its derivatives.

10. The flat display device of claim 7, wherein the organic thin film is dry etched using an O₂ ashing process.

11. The flat display device of claim 7, wherein the mask material comprises a low viscosity paraffin wax group or a grease group.

12. The flat display device of claim 7, wherein the mask material is removed through a cleaning process using n-hexane.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 7,572,668 B2
APPLICATION NO. : 11/378557
DATED : August 11, 2009
INVENTOR(S) : Suh et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:


On the Title Page:

The first or sole Notice should read --

Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 631 days.

Signed and Sealed this

Seventh Day of September, 2010

A handwritten signature in black ink that reads "David J. Kappos". The signature is written in a cursive, slightly slanted style.

David J. Kappos
Director of the United States Patent and Trademark Office

专利名称(译)	图案化有机薄膜的方法，有机薄膜晶体管，制造有机薄膜晶体管的方法，以及具有该有机薄膜晶体管的有机电致发光显示装置		
公开(公告)号	US7572668	公开(公告)日	2009-08-11
申请号	US11/378557	申请日	2006-03-16
[标]申请(专利权)人(译)	SUH MIN CHUL KOO JAE BON		
申请(专利权)人(译)	SUH 闵哲 KOO JAE-BON		
当前申请(专利权)人(译)	三星移动显示器有限公司.		
[标]发明人	SUH MIN CHUL KOO JAE BON		
发明人	SUH, MIN-CHUL KOO, JAE-BON		
IPC分类号	H01L51/40		
CPC分类号	H01L51/0019 H01L51/0017 H01L27/283 H01L27/3244 H01L51/0545 H01L51/0541 Y10T428/31504 B60Y2306/09 B60Y2400/406 B62D33/037		
优先权	1020050024564 2005-03-24 KR		
其他公开文献	US20060216852A1		
外部链接	Espacenet USPTO		

摘要(译)

本发明提供一种图案化有机薄膜的方法，该有机薄膜可以防止有机半导体层的表面损伤。此外，提供了一种可以减小截止电流并且可以防止有机半导体层的表面损伤的有机薄膜晶体管，以及制造该有机薄膜晶体管的方法，以及具有该有机薄膜晶体管的有机电致发光显示装置。图案化有机薄膜的方法包括在基板上形成有机薄膜，在有机薄膜的一部分上选择性地印刷掩模材料，使用掩模材料干燥蚀刻有机薄膜的暴露部分，以及去除有机薄膜。面膜材料。

