



(19) **United States**

(12) **Patent Application Publication**

(10) **Pub. No.: US 2003/0134140 A1**

Li et al.

(43) **Pub. Date:**

Jul. 17, 2003

(54) **DEUTERATED SEMI-CONDUCTING ORGANIC COMPOUNDS USED FOR OPTO-ELECTRONIC DEVICES**

Publication Classification

(51) **Int. Cl.⁷** **B21D 39/00**
(52) **U.S. Cl.** **428/621; 428/690**

(75) **Inventors:** **Xiao-Chang Charles Li**, Union City, CA (US); **Kazunori Ueno**, Kanagawa (JP)

(57) **ABSTRACT**

Correspondence Address:
FITZPATRICK CELLA HARPER & SCINTO
30 ROCKEFELLER PLAZA
NEW YORK, NY 10112 (US)

Organic semiconductors consisting of conjugated chromophores wherein one or more hydrogen atoms are deuterated are disclosed. Methods of preparing such organic semiconductors are described. The organic semiconducting compounds exhibit remarkably high luminescence and good thermal stability. Applications of these materials for optoelectronic devices, such as light-emitting devices and photodiodes, with enhanced performance and lifetime are disclosed. The disclosed materials can be used as emissive layer, charge-transporting layer, or energy transfer (i.e. phosphorescence dopant) material in organic light-emitting devices.


(73) **Assignee:** **Canon Kabushiki Kaisha**

(21) **Appl. No.:** **10/347,681**

(22) **Filed:** **Jan. 22, 2003**

Related U.S. Application Data

(62) Division of application No. 09/732,511, filed on Dec. 7, 2000.






Fig. 1




Fig. 2

UV Spectra of D-PPV Polymer and its Precursor




Fig. 3

UV-Visible and Photoluminescent Spectra of D-PPV




Fig. 4

UV-Visible and Photoluminescent Spectra of Semi-deuterated MEH-PPV




Fig. 5

Electroluminescence Spectrum of Ir(ppy)₃




Fig. 6

Electroluminescence Spectrum of Ir(ppy)₃-d8




Fig. 7




Fig. 8




Fig. 9

DEUTERATED SEMI-CONDUCTING ORGANIC COMPOUNDS USED FOR OPTO-ELECTRONIC DEVICES

TECHNICAL FIELD

[0001] The present invention relates to new semiconducting organic compounds and/or polymers for use in optoelectronic devices that contain completely or partially deuterated conjugated backbones, which can promote luminescence and thermal stability of the materials. More particularly, the present invention relates to the effective modification of the molecular structure of known luminescent materials with conjugated backbones containing hydrogen atoms by replacing one or more of the hydrogen atoms with deuterium atoms. The resulting deuterated material is significantly altered and has greatly improved performance over known luminescent light-emitting materials.

BACKGROUND OF THE INVENTION

[0002] Organic semiconductors have the benefit of low cost processing, easy control of properties by changing chemical structures, and attractive electronic properties. These materials are usually composed of conjugated chromophores linked by saturated or unsaturated linkage units. Many interesting applications have been explored in recent years, such as organic light-emitting devices [C. W. Tang, S. A. Van Slyke, *Appl. Phys. Lett.*, 1987, 51(12), 913; J. H. Burroughes; D. D. C. Bradley; A. R. Brown; R. N. Marks; K. Mackay; R. H. Friend; P. L. Bum and A. B. Holmes, *Nature* 1990, 347, 539. R. H. Friend; R. W. Gymer; A. B. Holmes; J. H. Burroughes; R. N. Marks; C. Taliani; D. D. C. Bradley; D. A. Dossantos; J. L. Bredas; M. Logdlund and W. R. Salaneck, *Nature* 1999, 397, 121.], organic lasers [F. Hide; M. A. Diaz-Garcia; B. J. Schwartz and A. J. Heeger, *Acc. Chem. Res.* 1997, 30, 430.], organic thin-film transistors [F. Gamier, R. Hajlaoui, A. Yassar, P. Srivastava, *Science*, 1994, 265, 1684], and organic photodiodes.

[0003] One application of organic semiconductors is as an active flat-panel display or organic light-emitting device (OLED). Such devices offer many unique features, including a low cost, full color, active display with the possibility of a thinner, lighter, larger and more flexible display module, with wider viewing angles (>160°), compared to conventional flat-panel display devices. All these features imply a strong competitive alternative to replace present LCD displays. Such devices consist of one or several semiconducting organic layer(s) sandwiched between two electrodes. When an electric field is applied, electrons are injected by the cathode into the lowest un-occupied molecular orbital (LUMO) of the adjacent molecules, and holes are injected by the anode into the highest occupied molecular orbital (HOMO). As a result of recombination of electrons and holes, an excited state, called singlet exciton, is formed which returns back to the ground state upon emission of light corresponding to the energy band gap of the emissive material. The selection of emissive materials not only can influence the emission color, but also the light emission efficiency (photons per injected electron) and the light emission brightness and lifetime. In practical display applications, color purity, light-emission efficiency, brightness and lifetime are important parameters.

[0004] There have been various organic semiconductor materials developed in the past a few years [Y. Sato,

Semiconductors & Semimetals, 2000, 64, 209; A. Kraft; A. C. Grimsdale and A. B. Holmes, *Angew. Chem.—Int. Ed. In Engl.* 1998, 37, 402; Li, X. -C., Moratti, S. C.; In *Photonic Polymer Systems: Fundamentals, Methods, and Applications*; Wise, D. L.; Wnek, G. E.; Trantolo, D. J.; Cooper, T. M.; Gresser, J. D.; Eds.; Marcel Dekker, Inc.: New York, Chapter 10, 1998, p. 335]. Many prototypes of OLED display modules have been demonstrated with the use of organic luminescent compounds (small molecular compounds or polymers). However, only limited commercial products of OLEDs have been launched, due both to the difficulty of technological integration and to the overall performance of the present organic semiconducting materials, which include emissive materials and charge transporting materials. Accordingly, there is a need in the art to develop new materials that exhibit combinatory high performance of luminescence, excellent stability, and good lifetime.

[0005] The search for new organic materials used for optoelectronic devices, such as organic light-emitting devices, has been a very active field in recent years. This includes research relating to organic semiconductors and organic polymeric materials that present strong luminescence and good processibility. Most researchers have focused on varying the structure of either the core chromophore and/or polymer backbone, and on modifying linkages for solubility, for charge injection ability, or for other processing functionality. These methods require innovative molecular design, coupled with skillful chemical synthesis, which are time consuming and expensive in order to screen off undesired products.

[0006] It is an object of the present invention to provide a unique and effective manner to chemically modify known and novel optoelectronic materials by replacing protons with deuterium atoms on the conjugated chromophores. It is another object of the invention to provide a method to design and synthesize new luminescent organic materials containing deuterium atoms for their application in optoelectronic devices, such as light-emitting devices. It is further another object of the invention to improve OLED performance with brighter luminance and better thermal stability.

SUMMARY OF THE INVENTION

[0007] The present invention relates to deuterated semiconductor organic compounds used in optoelectronic devices and to processes of preparing such deuterated compounds. In one process within the scope of the present invention, known and novel organic semiconductor compounds are deuterated by replacing one or more hydrogen atoms covalently bonded to carbon atoms with deuterium atoms.

[0008] Deuterium is a non-radiative isotope of hydrogen, which is sometimes called heavy hydrogen due to its doubled atomic mass. The difference between hydrogen and deuterium has fairly small chemical effects; however, there are important physical effects because of the mass difference between the isotopes. The heavier isotope, deuterium, lies lower in the potential well, and hence has a lower zero-point energy and vibration frequency, and smaller vibration amplitude than hydrogen. Because of the asymmetry of the potential well, bond lengths and bond angles involving deuterium are different than those involving hydrogen. The

observed smaller amplitude of the C-D stretching and bending motion, relative to C—H, should be best accounted for with a smaller van der Waals radius for D than for H. The weak vibronic coupling in the deuterated system has been used to theoretically predict higher fluorescence quantum yield [A. L. Burin and M. A. Ratner, *J. Chem. Phys.*, 1998, 109, 6092]. Spectroscopic studies indicate that deuterated phenanthrene has a smaller non-radiative triplet rate constant than its aromatic molecule [S. M. Ramasamy, R. J. Hurtubise, *Appl. Spectroscopy*, 1996, 50(9), 1140].

[0009] Deuterium is also found to act as an apparent electron-donating inductive substituent relative to hydrogen. The isotope effects may be applied in the design of new luminescent materials with enhanced charge-injection ability. Additionally, it is known that the C-D bond is shorter than the C—H as a result of the anharmonicity of the bond stretching potential. [M. L. Allinger and H. L. Flanagan, *J. Computational Chem.* 1983, 4(3), 399]. This means the carbon-deuterium chemical bond is stronger, more stable, and reacts more slowly than the carbon-hydrogen chemical bond, so that the deuterated organic system has better thermal stability, and longer lifetime in optoelectronic devices. Deuterated luminescent material may also have a higher electroluminescent quantum yield as a result of smaller non-radiative triplet rate.

[0010] In the prior art, deuterated hydrocarbon lubricants have better anti-oxidation and improved stability than normal hydrocarbon lubricants [U.S. Pat. No. 4,134,843]. A deuterated polymer has been used for optical fiber with low attenuation optical loss [U.S. Pat. No. RE031,868]. Deuterated pharmaceuticals or drugs can enhance drug's efficacy and activity. [U.S. Pat. No. 4,898,855 and U.S. Pat. No. 5,846,514]. Deuterium-treated semiconductor devices have been disclosed [U.S. Pat. No. 5,872,387], wherein degradation of inorganic semiconductor devices has been reduced by using deuterium passivation; deuterium incorporation at the SiO₂/Si interface has been reported to improve the hot carrier reliability of CMOS transistors. [J. Lee, K. Cheng, et al, *IEEE Electron Device Letters*, 2000, 21(5), 221]. Compared with normal hydrogen treated device, the deuterium treated device has a significant lifetime improvement (90 times).

[0011] The deuterated organic semiconductor materials within the scope of the present invention are preferably luminescent. Luminescence here means either fluorescence (singlet emission) or phosphorescence (triplet emission). The deuterated organic semiconductor materials may possess charge injection (electron injection or hole injection), hole blocking, or exciton blocking properties. As used herein, hole blocking property means that the semiconductor material allows electrons to transport, but not holes. Whenever a material has a low mobility for hole transporting (less than 10⁻⁶ cm²/V-s), or a very high HOMO (highest occupied molecular orbital) level, the material normally possesses hole blocking properties. As used herein, exciton blocking property means that excitons are confined within an emissive layer by using another material layer which does not readily transport excitons (usually non-emissive layer).

[0012] The deuterated organic semiconducting material preferably possesses a strong energy transfer property. As used herein, energy transfer includes a Forster process where a higher energy singlet transfers to a lower energy singlet.

An example is a blue emissive polymer (host) doped with red emissive material (guest) [like tetraphenylporphyrin doped polyfluorene reported by T. Virgili, et al., *Adv. Mater.*, 2000, 12(1), 58]. The doping level is usually from 0.1-15%, but more than 90% energy will transfer into the red emissive material, thus lead to red emission rather than blue emission. As used herein, energy transfer also includes an intersystem transfer where the singlet energy transfers to a triplet, and thus lead to phosphorescence. An example is a yellow emissive polymer doped with rare earth metal complexes to lead to electrophosphorescence [M. D. McGehee, et al., *Adv. Mater.*, 1999, 11(16), 1349; *Appl. Phys. Lett.*, 1999, 75, 4]. This triplet-emission can potentially lead to very high quantum efficiency because the maximal probability of a triplet is 75%.

[0013] The deuterated organic semiconducting materials preferably produce more singlet energy states for light-emission, compared to non-deuterated materials. For most organic fluorescent materials, the maximum singlet production probability under electrical excitation is about 25%. Deuterated materials may exceed that limit for electrophosphorescence because of their slow triplet production rate. Therefore, deuterated materials may efficiently produce more singlets than non-deuterated materials, with a potential singlet production exceeding 25%.

BRIEF DESCRIPTION OF THE DRAWINGS

[0014] FIG. 1 is a cross-section illustration of a typical single layer light emitting device.

[0015] FIG. 2 is a cross-section illustration of a typical triple layer light emitting device.

[0016] FIG. 3 is a graph of the UV spectrum of the sulfonium polymer precursor and the converted conjugated polymer deuterated PPV (D-PPV), showing the band gap changes from 3.42 eV to 2.45 eV.

[0017] FIG. 4 is a graph of the ultraviolet (UV) and visible photoluminescent spectrum of the deuterated polymer D-PPV.

[0018] FIG. 5 is a graph of the ultraviolet (UV) spectra and the photoluminescent spectrum (excited by 400 nm UV light) of semi-deuterated MEH-PPV.

[0019] FIG. 6 is a graph of the electroluminescence spectrum of Ir(ppy)₃ in the device structure of ITO/NPD 40 nm/CBP+11% Ir(ppy)₃ 20 nm/BCP 10 nm/Alq₃ 40 nm/LiF 0.75 nm/Al.

[0020] FIG. 7 is a graph of the electroluminescent spectrum of Ir(ppy)₃-d8 in the device structure of ITO/NPD 40 nm/CBP+11% Ir(ppy)₃-d8 20 nm/BCP 10 nm/Alq₃ 40 nm/LiF 0.75 nm/Al.

[0021] FIG. 8 is a comparison graph of the relationship of external quantum efficiency vs. current density for the device in Example 10 (square) and for the device in Example 11 (circle).

[0022] FIG. 9 is a comparison graph of the relationship of luminance efficiency vs. current density for the device in Example 10 (square) and for the device in Example 11 (circle).


DETAILED DESCRIPTION OF THE INVENTION

[0023] Virtually all organic luminescent materials now marketed contain hydrogen atoms, each of which has a

molecular mass of one. According to the present invention one or more of the hydrogen atoms on a conjugated chromophore or a conjugated polymer are deuterated. The molecular mass becomes higher, and the optical and electronic properties of the conjugated luminescent material are altered and improved. The deuterated organic semiconductor has improved performance, for instance, higher fluorescence yield and more stability than its non-deuterated analogue.

[0024] There are several deuterated structures or structural combinations that may be used to form conjugated chromophores that are useful for opto-electronic applications, with particularly application in light-emitting devices.


[0025] 1. A conjugated chromophore, as used herein, includes a linear conjugated organic compound or a polymer with at least 5 conjugated bonds, wherein protons linked to the conjugated bonds are partially or fully deuterated. Examples of typical backbones of conjugated chromophore compounds for this category can be described as in Scheme 1:




[0026] If partially deuterated, the un-deuterated sites for the compounds or polymers in Scheme 1 may be linked with hydrogen atoms, halogens such as F, Cl, Br, etc; or alkyl, alkoxy, thiol, silyl; aromatic rings such as phenyl and naphthalene; or heteroaromatic rings, such as thiophene, pyridine, and quinoline.

[0027] 2. A conjugated chromophore, as used herein, also includes a cyclic ring, fused cyclic ring, and combinations thereof, that form a conjugated organic compound or a polymer with at least 5 conjugated bonds, wherein protons linked to the conjugated bonds are partially or fully deuterated. Examples of typical backbones of conjugated organic compounds for this category can be described as in Scheme 2, below. The protons linked with aromatic rings of the compounds in Scheme 2 should be partially or fully deuterated. If partially deuterated, the un-deuterated sites may be linked with hydrogen atoms, halogens such as F, Cl, Br, etc.; or alkyl, alkoxy, thiol, silyl; aromatic rings such as phenyl and naphthalene; or heteroaromatic rings, such as thiophene, pyridine, and quinoline.


Scheme 2.
Cyclic and fused ring combinations.



-continued




-continued








[0028] 3. A conjugated chromophore, as used herein, also includes heterocyclic ring, fused heterocyclic ring, and combinations thereof, that form a conjugated organic compound or a polymer with at least 5 conjugated bonds, wherein protons linked to the conjugated bonds are partially or fully deuterated. Examples of typical backbones of conjugated organic compounds for this category can be described as in Scheme 3. The protons linked with the heterocyclic rings of the compounds in Scheme 3 should be partially or fully deuterated. If partially deuterated, the un-deuterated sites may be linked with hydrogen atoms; halogens such as F, Cl, Br, etc.; alkyl, alkoxy, thiol, silyl; aromatic rings such as phenyl and naphthalene; or heteroaromatic rings, such as thiophene, pyridine, and quinoline.

Scheme 3.
Heterocyclic/fused ring heterocyclic combination.





[0029] 4. A conjugated chromophore, as used herein, also includes a metal chelated compound or an organometallic compound with a formula of $C_A M_B$, where C denotes a chromophore selected from category 1, 2 or 3; and M denotes a metal selected from, Li, Na, K, Be, Mg, Ca, Ti, Cr, Mo, Mn, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Zn, Cd, B, Al, Ga, In, Si, N, P; A and B denote the number from 1 to 10, preferentially 1-4. The protons linked with the chromophore material of the compounds in Scheme 4 should be partially or fully deuterated. Examples of this category compounds are presented in Scheme 4. If partially deuterated, the un-deuterated sites may be linked with hydrogen atoms, halogens such as F, Cl, Br, etc.; alkyl, alkoxy, thiol, silyl; aromatic rings such as phenyl and naphthalene; or heteroaromatic rings, such as thiophene, pyridine, and quinoline.



(R: D, H, C₁-C₃₀ alkyl, C₁-C₃₀ alkoxy, C₁-C₃₀ silyl, aryl, heteroaryl; m is 1-4).

[0030] 5. A conjugated chromophore, as used herein, also includes a combination of the compounds disclosed in categories 1, 2, 3 and 4, above, to form a conjugated organic compound or a polymer with at least 5 conjugated bonds wherein protons linked to the conjugated bonds are partially or fully deuterated. A few examples of compounds within this category compounds are presented in Scheme 5. If partially deuterated, the un-deuterated sites may be linked with hydrogen atoms, halogens such as F, Cl, Br, etc.; alkyl, alkoxy, thiol, silyl; aromatic rings such as phenyl and naphthalene; or heteroaromatic rings, such as thiophene, pyridine, and quinoline.

Scheme 5.
Organic semiconductor compounds and polymers with deuterium substituents.



(R: D, H, C₁-C₃₀ alkyl, C₁-C₃₀ alkoxy, phenyl, thienyl, pyridyl, C₁-C₃₀ silyl, aryl, heteroaryl; m is from 1 to 4).

[0031] The present invention is also directed to organic electronic devices containing the foregoing deuterated conjugated semiconducting compounds and polymers. Such devices typically include at least one thin film of the deuterated conjugated compound or polymer coupled to a pair of electrodes. Additional thin films of conjugated semiconducting material can be used. In such cases, one thin film may be configured to promote electron transport and a second thin film may be tuned to promote hole transport. When the organic electronic device is fabricated with a plurality of thin films of conjugated semiconducting compounds or polymers, the thin films are preferably tuned to promote balanced electron and hole transport between the first and second electrodes. Typical organic electronic devices include, but are not limited to, a LED, a thin film transistor, a photovoltaic solar cell, an electrochemical luminescent display device, an electrochromic display device, and an electroluminescent device for active flat-panel display applications.

[0032] FIG. 1 shows the sectional structure of a typical single layer light-emitting device 10. The LED device 10 includes a clear substrate 12 having an anode coating 14. A single layer of deuterated semiconducting luminescent polymer 16 is deposited between the anode 14 and a cathode 18. An electrical potential 20 connects the anode 14 and cathode 18.

[0033] In many cases, a double or a multi-layer LED may be fabricated, in which one or two different charge-transporting layers are used. The charge-transporting layer may be an electron-transporting layer or a hole-transporting layer. Each individual layer may be a polymeric or organic film with a thickness less than 1500 nm, preferably less than 300 nm.

[0034] FIG. 2 shows a section diagram of a typical three-layer LED 30. As shown in FIG. 2, the anode substrate 34, preferably ITO on a clear substrate 32, may be pre-coated with a layer of a hole-transporting material 36 either by spin-coating, or by printing. A typical hole-transporting layer 36 can be selected from, but not limited to, polyaniline, poly(phenylenevinylene), poly(3,4-ethylenedioxythiophene) (PEDOT) (doped with polystyrene sulfonic acid), poly(N-vinyl carbazole) (PVK), or an aromatic amine organic compound or polymer. The thickness of the hole-transporting layer 36 is preferably between 0.5 nm to 500 nm, and more preferably less than 150 nm. A deuterated semiconducting luminescent polymer layer 38 is disposed on the hole-transporting material 36. The solvent used to fabricate the luminescent polymer layer 38 is selected to be compatible hole-transporting layer 36 such that it does not dissolve the hole-transporting layer 36. Depending on the luminescent polymer utilized, the luminescent layer 38 can emit various colors from red, yellow, green, to blue. The thickness of the luminescent layer 38 is preferably between 10 nm to 300 nm, preferably between 50 nm to 200 nm.

[0035] The device 30 may be further coated with a layer of an electron-transporting material 40 either by spin-coating or by printing. A typical electron-transporting layer 46 can be selected from, but is not limited to, poly(aromatic oxadiazole)[X. -C. Li, et al., *J. Chem. Soc. Chem. Commun.*, p. 2211, 1995], organic compounds containing aromatic oxadiazoles, triazoles, quinolines, such as 2-tert-butyl-phenyl-5-biphenyl-1,3,4-oxadiazole (PBD), and Alq3. Evaporation or solution coating may be employed. For solution coating (spin-coating or printing), it is again important to select a suitable solvent for the electron transporting solution or ink that does not corrode or dissolve the luminescent polymer layer 38, hole-transporting layer 44, or anode 42. Luminescent polymers formulated as luminescent ink with cross-linking ability may be used. In a preferred embodiment, the cross-linking process can be accomplished by UV irradiation or moderate thermal treatment (less than 300° C.) of the inked anode substrate after printing.


[0036] The cathode metal 42 can be deposited either by thermal vacuum evaporation, or by sputtering. The presently preferred cathode metals are aluminum, calcium and magnesium. The thickness of the cathode layer 42 is preferably between 0.5 nm to 5000 nm, preferably thicker than 50 nm. An electrical potential 44 connects the anode 34 and cathode 42.

EXAMPLES

[0037] The following examples are given to illustrate various embodiments within the scope of the present invention. These are given by way of example only, and it is to be understood that the following examples are not comprehensive or exhaustive of the many types of embodiments of the present invention that can be prepared in accordance with the present invention.

Example 1

[0038] Green Luminescent Poly(Phenylene Vinylene) With Deuterium via Bromo-Precursor Route:




[0039] Synthesis of deuterated 1,4-bis(bromomethyl)benzene 2: Deuterated Xylene-d10 (1.644 g, 14.14 mmol) and N-bromosuccinimide (NBS) (5.6 g, 28.99 mmol) were dissolved in carbon tetrachloride (15 mL) at room temperature. After being degassed 3 times, the mixture was heated by an IR lamp to reflux using light irradiation. The reaction was carried out for 6 hours, and cooled down to room temperature. After filtration, the solid was washed by dichloromethane (3×30 mL), and the solution portions were collected. Evaporation of the solvents gave oil product that was purified by silica flash column using hexane and the mixture of ethyl acetate/hexane (1:10, v/v) to give white solid 2 (1.87 g, 49%). Rf=0.46 (EtOAc/hexane, 1:3, v/v).

[0040] Synthesis of bromo-precursor deuterated PPV 3: Deuterated 1,4-bisbromomethyl-benzene 2 (0.8 g, 2.941 mmol) was dissolved in anhydrous tetrahydrofuran (7 mL) and degassed. The solution was cooled down to 0° C. using an ice bath. Potassium tert-butoxide (2.94 mL, 1.0 M in THF, 2.94 mmol) was added into the solution dropwise. The addition was finished within 20 minutes, and the light yellow solution was stirred at 0° C. for 4 hours. The solution was poured into methanol (100 mL) to give the precursor polymer precipitate (58%).

[0041] Luminescent thin film of deuterated PPV 4 via bromo-precursor 3: The yellow polymer 3 can be soluble in THF, and a thin polymer film of 3 can be cast on a glass substrate. Green luminescent polymer 4 can be obtained by heat treatment of 3 at 160° C. for 4 hours under nitrogen or under vacuum.

Examples 2

[0042] Green Luminescent Poly(Phenylene Vinylene) With Deuterium Substituents Via Sulfonium-Precursor Route:



[0043] Synthesis of sulfonium monomer 5: Deuterated 1,4-bisbromomethyl-benzene 2 (1.0 g, 3.676 mmol) and tetrahydrothiophene (1.62 g, 18.5 mmol) were dissolved in

anhydrous methanol (12 mL), and the mixture was heated to 50° C. The reaction was carried out under nitrogen for 16 hours. The solvent was evaporated under vacuum to give white slurry that was washed by anhydrous chloroform (1×8 mL). The beige powder was dried under vacuum at 0° C. to yield the sulfonium monomer 5 (1.2 g, 68%).

[0044] Synthesis of sulfonium-precursor deuterated PPV 6: The sulfonium monomer 5 (1.1 g, 2.30 mmol) was dissolved in methanol (8 mL) at 0° C. The mixture was degassed before the addition of sodium hydroxide (5.6 mL, 0.4 N in water, 2.25 mmol). The addition of NaOH was finished within 15 min. After reaction at 0° C. for 2 hours, the colorless solution was dialyzed against degassed water using a dialysis tube (Lancaster) to remove oligomers and inorganic species. The dialysis process was repeated for 2 more times, with final dialysis against methanol. The resulting polymer 6 has a yield of 60%, and it is ready to prepare polymer thin films.

[0045] Luminescent thin film of deuterated PPV 7 via sulfonium-precursor 6: The sulfonium polymer 6 is soluble in water and methanol, and is stable at 0° C. Polymer 6 is normally obtained in the mixture solvent of methanol and water with a concentration of 1% which is ready to cast thin film on glass substrate. Green luminescent polymer 7 can be obtained by heat treatment of 6 at 160° C. for 4 hours under nitrogen or under vacuum.

[0046] When the polymer 6 is converted to 7, its conjugation length is increased which is shown in the UV-Visible spectroscopy. FIG. 3 shows the UV spectral change of this conversion, showing the band gap changes from 3.42 eV to 2.45 eV. After conversion, the polymer 7 fluoresces green with the PL peak located at 550 nm, shown in FIG. 4.


Example 3


[0047] Normal PPV Polymer Synthesis Via Sulfonium Precursor (for Comparison).

[0048] Normal PPV precursor polymer can be obtained by polymerization of the monomer, (Aldrich) following the similar procedure as illustrated in example 2. The normal PPV polymer has very similar optical and electronic properties as D-PPV. Comparative photoluminescence (PL) quantum efficiency measurements showed that the deuterated PPV photoluminescence quantum efficiency compared to that of normal PPV was: DPPV/PPV=1.2, which means that the deuterated PPV has a brighter photoluminescence than normal PPV.

Example 4

[0049] Red Luminescent Partially Deuterated Poly(2-methoxy-5-ethylhexyloxy-phenylene Vinylene) (Partially Deuterated MEH-PPV).





[0050] The synthesis of phenylene 1-(2-ethyl-hexyloxy)-4-methoxy-benzene 9: 4-methoxyphenol (24.8 g, 200 mmol) and sodium hydroxide pellets (8.8 g, 220.0 mmol) were charged into a 500 mL two neck flask equipped with a condenser and a septum. The flask was degassed 3 times before adding anhydrous methanol (150 mL) via an annular tube. The solution became hot while stirring. It was heated to reflux for 20 min, and then cooled down to room temperature. 2-Ethyl-hexyl bromide (39 mL, 220 mmol) was then added by a syringe at room temperature, dropwise (15 min.). The mixture was heated to reflux for 20 hour. The methanol was removed by distillation, and then 150 mL ether was added. Deionized water (100 mL) was added to dissolve inorganic salts. The aqueous phase was washed by

ether (3×50 mL), and the combined portions of ether was washed by brine (2×50 mL), dried over sodium sulfate, and evaporated to remove ether. The obtained oil was fraction distilled to remove the unreacted ethylhexyl bromide, and the final product was collected in the fraction of 130-135° C. (2 mm Hg) as a clear oil (35.8 g, 76%).


[0051] Synthesis of 1,4-bis-chloromethyl-d4-2-(2-ethyl-hexyloxy)-5-methoxy-benzene 10: 1-(2-ethyl-hexyloxy)-4-methoxy-benzene 9 (5.9 g, 24.97 mmol) and paraformaldehyde were charged into a 100 mL two neck flask, and degassed by pumping/nitrogen inlet (3 times). Hydrochloric acid (37%, 11.2 mL, 500 mmol) was added by a syringe. While stirring at room temperature, acetic anhydride was added dropwise to control keep the reaction mixture from becoming too hot. The addition of the acetic anhydride was finished within 30 minutes. The mixture was then heated to 75° C. under nitrogen while stirring. After reaction of 8 hours, the mixture was poured into water (200 mL), and the aqueous phase was extracted with ethyl acetate (3×80 mL). The combined organic phase was washed with brine (2×50 mL), dried over magnesium sulfate. Evaporation of the organic solvent yielded the crude slurry, which was purified by a silica flash column using hexane and ethyl acetate/hexane mixture (10% to 20%) to give the product (45%). Rf=0.66 (EtOAc/hexane, 1/3, v/v).

[0052] Synthesis of poly(2-methoxy-5-ethylhexyloxyphenylene vinylene) with deuterium substituent on vinyl (partially deuterated MEH-PPV) 11: 1,4-bis-chloromethyl-d4-2-(2-5-methoxy-benzene 10 (0.62 g, 1.84 mmol) was charged into a 100 mL two neck flask and degassed by pumping/nitrogen inlet (3 times). Anhydrous tetrahydrofuran (60 mL) was added to dissolve the monomer. Potassium tert-butoxide solution (11.0 mL, 1.0 M in THF, 11.0 mmol) was added dropwise into the stirring solution within 20 min. The colorless solution became red and viscous. The reaction was carried out under nitrogen for 18 hours under dark condition. The viscous solution was poured into methanol (300 mL) to give a red precipitate, which was purified by repeated precipitation (2 times more) from its solution of chloroform into methanol. A red polymer was obtained with a yield of 56%.


[0053] The partially deuterated MEH-PPV had a π - π^* band gap of 2.1 eV as illustrated in FIG. 5. The polymer luminesces red in solution and in thin film states. FIG. 5 shows the photoluminescent spectrum (excited by 400 nm UV light), showing a red luminescent color (located around 620 nm).

Example 5

[0054] Red Luminescent MEH-PPV With Deuterium Atom Substituents on Both Vinyl and on Phenyl:




-continued




[0055] According to the above synthesis scheme, the red luminescent deuterated MEH-PPV 15 is prepared following the similar chemical procedure as described in Example 4. The compound 13 is prepared by the chemistry procedure described in: H. Tsuzuki, et al., *J. Chem. Research*, 1994, 1701-1716.

-continued



Example 6


[0056] Red Luminescent Poly(2,5-dioctyl-phenylene Vinylene) With Deuterium Atom Substituents on Vinyl and on Phenyl:





[0057] By using the deuterated starting compound 16, red luminescent poly(dioctyl-phenylene vinylene) 19 can be prepared according to the above scheme with the similar procedures as described in Example 4.

Example 7

[0058] Blue Luminescent Poly(9,9'-dioctyl-fluorene) With Deuterium Atom Substituents.







[0059] By using the deuterated fluorene 20, blue luminescent poly(9,9-dialkyl fluorene) 23 can be prepared according to the above scheme with the similar procedures as described in E. P. Woo et al., U.S. Pat. No. 5,962,631.

Example 8

[0060] Phosphorescent Dopant Metal Complex With Deuterium Atoms.





[0061] By using the deuterated compound 24, phosphorescent dopant metal complex 28, fac-tris(2-phenylpyridine)iridium Ir(ppy)₃, was prepared according to the above scheme with the similar procedures and application mechanism as described in [M. D. McGehee, et al., *Adv. Mater.* 1999, 11(16), 1349; *Appl. Phys. Lett.*, 1999, 75, 4].

[0062] D-9-2-Phenylpyridine 26 was synthesized according to *Organic Syntheses* Vol. 2, p. 517. The yield of the compound was 21%. D-24-Ir(ppy)₃ 28 was synthesized according to *Inorganic Chemistry*, 1991, 30(8), 1685. The yield of this compound was 19%. These compounds were confirmed by ¹H-NMR, which showed no signals due to protons. Parent peak, 164, of D-9-2-phenylpyridine was observed in MS spectrum, and also D-24-Ir(ppy)₃ showed 678.7 as the parent peak.

Example 9

[0063] Deuterated Alq₃: Green Luminescent Compound Preparation.





[0064] By using the deuterated quinoline 29, green luminescent metal complex 35, deuterated tris-(8-hydroxyquinoline) aluminum, can be prepared according to the above scheme with the similar procedures and application mechanism as described in: [Kuznetsoua, "Complex compounds of

metals with some nitrogen containing ligands", *Zhurnal obshchey khimii*, vol. XLVI (CVIII), No. 3, March 1976, pp. 670-675; Hamada et al., "Organic Electroluminescent Devices with 8-Hydroxyquinoline Derivative-Metal Complexes as an Emitter," *Japanese Journal of Applied Physics*, vol. 32, Part 2, No. 4A, Apr. 1, 1993, pp. L514-L515; Tang et al., "Organic electroluminescent diodes," *Applied Physics Letters*, vol. 51, No. 12, Sep. 21, 1987, pp. 913-915.]

Example 10

[0065] Electroluminescence of Fac-Tris(2-Phenylpyridine)iridium $\text{Ir}(\text{ppy})_3$ (For Comparison).

[0066] A device of ITO/NPD 40 nm/CBP+11% $\text{Ir}(\text{ppy})_3$ 20 nm/BCP 10 nm/Alq3 40 nm/LiF 0.75 nm/Al, where NPD denotes to N,N'-bis(naphthyl)-N,N'-diphenylbenzidine, CBP denotes to carbazole biphenyl, was fabricated following a similar procedure as described in: *Appl. Phys. Lett.*, 75, 4 (1999). Each layer was formed and controlled by vacuum thermal evaporation. The NPD was used as a hole transporting layer; the CBP was used as the host with the phosphorescent dopant, $\text{Ir}(\text{ppy})_3$, as the emissive layer; BCP was used as the exciton blocking layer; Alq3 as electron transporting layer; LiF was used as cathode modification layer; Al was used as the cathode metal. Bright green luminescence (electrophosphorescence) was observed at a voltage of 5 V. The electroluminescence spectrum was shown in FIG. 6.

Example 11

[0067] Electroluminescence of Fac-Tris(2-Phenylpyridine)iridium-d8 $\text{Ir}(\text{ppy})_3\text{-d}_8$.

[0068] A device of ITO/NPD/CBP+11% $\text{Ir}(\text{ppy})_3\text{-d}_8$ 20 nm/BCP 10 nm/Alq3 40 nm/LiF 0.75 nm/Al, was fabricated following a similar procedure as described in Example 10. Bright green luminescence (electrophosphorescence) was observed at a voltage of 5 V. The electroluminescence spectrum was shown in FIG. 7.

[0069] FIG. 8 shows the relationship of quantum efficiency (% photons per electron) vs. current density (mA/cm^2) for the device in Example 10 (square symbols) with the device of Example 11 using deuterium $\text{Ir}(\text{ppy})_3\text{-d}_8$ (circle symbols). From FIG. 8, the device of Example 11 has higher quantum efficiency than the device of Example 10.

[0070] FIG. 9 shows the relationship of luminance efficiency (1 m/W) vs. current density (mA/cm^2) for the device in Example 10 (square symbols) with the device of Example 11 using deuterium $\text{Ir}(\text{ppy})_3\text{-d}_8$ (circle symbols). From FIG. 9, the device of Example 11 has higher luminance efficiency than the device of Example 10.

[0071] It will be appreciated that the present invention provides new organic semiconductor materials that exhibit high luminescence, excellent stability, and good lifetime. This is achieved by chemically modifying known and novel optoelectronic materials by replacing protons with deuterium atoms on the conjugated chromophores. New luminescent organic materials are designed and synthesized containing deuterium atoms for their application in optoelectronic devices, including light-emitting devices. Such OLEDs prepared with deuterated organic semiconductor materials have brighter luminance and better thermal stability compared to non-deuterated organic semiconductor materials.

[0072] The present invention may be embodied in other specific forms without departing from its essential characteristics. The described embodiments are to be considered in all respects only as illustrative and not restrictive. The scope of the invention is, therefore, indicated by the appended claims rather than by the foregoing description.

1. An organic semiconductor comprising a conjugated chromophore selected from a linear conjugated organic compound or a polymer, a cyclic ring, a fused cyclic ring, a heterocyclic ring, a fused heterocyclic ring, a chelate or organometallic material having the formula $C_A M_B$, where C denotes a conjugated chromophore, M denotes a metal selected from, Li, Na, K, Be, Mg, Ca, Ti, Cr, Mo, Mn, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Zn, Cd, B, Al, Ga, In, Si, N, P, and A and B denote a number from 1 to 10, respectively, and combinations thereof, said chromophore having with at least 5 conjugated bonds wherein protons linked to the conjugated bonds are partially or fully deuterated.

2. An organic semiconductor according to claim 1, wherein the conjugated chromophore is partially deuterated, and wherein un-deuterated sites are chemically bound to a moiety selected from hydrogen atoms, halogen atoms, alkyl, alkoxy, thiol, silyl, aromatic rings, or heteroaromatic rings.

3. An organic semiconductor according to claim 1, wherein the organic semiconductor is luminescent.

4. An organic semiconductor according to claim 1, wherein the organic semiconductor possesses charge injection, hole blocking, or exciton blocking properties.

5. An organic semiconductor according to claim 1, wherein the organic semiconductor promotes energy transfer.

6. An organic semiconductor according to claim 1, wherein the organic semiconductor produces greater than 25% singlet excitons for light emission.

7. An organic semiconductor comprising a conjugated chromophore with a linear conjugated organic compound or a polymer with at least 5 conjugated bonds, wherein protons linked to the conjugated bonds are partially or fully deuterated.

8. An organic semiconductor according to claim 7, wherein the conjugated chromophore is partially deuterated, and wherein un-deuterated sites are chemically bound to a moiety selected from hydrogen atoms, halogen atoms, alkyl, alkoxy, thiol, silyl, aromatic rings, or heteroaromatic rings.

9. An organic semiconductor according to claim 7, wherein the organic semiconductor is luminescent.

10. An organic semiconductor according to claim 7, wherein the organic semiconductor possesses charge injection, hole blocking, or exciton blocking properties.

11. An organic semiconductor according to claim 7, wherein the organic semiconductor promotes energy transfer.

12. An organic semiconductor according to claim 7, wherein the organic semiconductor produces greater than 25% singlet excitons for light emission.

13. An organic semiconductor comprising a conjugated chromophore with a cyclic ring, a fused cyclic ring, or a combination thereof, in the form of a conjugated organic compound or a polymer with at least 5 conjugated bonds, wherein protons linked to the conjugated bonds are partially or fully deuterated.

14. An organic semiconductor according to claim 13, wherein the conjugated chromophore is partially deuterated, and wherein un-deuterated sites are chemically bound to a moiety selected from hydrogen atoms, halogen atoms, alkyl, alkoxy, thiol, silyl, aromatic rings, or heteroaromatic rings.

15. An organic semiconductor according to claim 13, wherein the organic semiconductor is luminescent.

16. An organic semiconductor according to claim 13, wherein the organic semiconductor possesses charge injection, hole blocking, or exciton blocking properties.

17. An organic semiconductor according to claim 13, wherein the organic semiconductor promotes energy transfer.

18. An organic semiconductor according to claim 13, wherein the organic semiconductor produces greater than 25% singlet excitons for light emission.

19. An organic semiconductor of the formula $C_A M_B$, where C denotes a conjugated chromophore, wherein protons linked to the conjugated bonds are partially or fully deuterated; M denotes a metal selected from, Li, Na, K, Be, Mg, Ca, Ti, Cr, Mo, Mn, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Zn, Cd, B, Al, Ga, In, Si, N, and P; A and B denote a number from 1 to 10, respectively.

20. An organic semiconductor according to claim 19, wherein A and B denote a number from 1 to 4, respectively.

21. An organic semiconductor according to claim 19, wherein the conjugated chromophore is partially deuterated, and wherein un-deuterated sites are chemically bound to a moiety selected from hydrogen atoms, halogen atoms, alkyl, alkoxy, thiol, silyl, aromatic rings, or heteroaromatic rings.

22. An organic semiconductor according to claim 19, wherein the organic semiconductor is luminescent.

23. An organic semiconductor according to claim 19, wherein the organic semiconductor possesses charge injection, hole blocking, or exciton blocking properties.

24. An organic semiconductor according to claim 19, wherein the organic semiconductor promotes energy transfer.

25. An organic semiconductor according to claim 19, wherein the organic semiconductor produces greater than 25% singlet excitons for light emission.

26. An organic semiconductor according to claim 1, fabricated as an organic luminescent device.

27. An organic semiconductor according to claim 7, fabricated as an organic luminescent device.

28. An organic semiconductor according to claim 13, fabricated as an organic luminescent device.

29. An organic semiconductor according to claim 19, fabricated as an organic luminescent device.

30. An organic luminescent device comprising:

a first electrode surface;

a first thin film of conjugated luminescent polymer comprising an organic semiconductor according to claim 1, wherein the luminescent polymer is electrically coupled to the first electrode surface; and

a second electrode, electrically coupled to the conjugated luminescent polymer.

* * * * *


专利名称(译)	用于光电器件的氘化半导体有机化合物		
公开(公告)号	US20030134140A1	公开(公告)日	2003-07-17
申请号	US10/347681	申请日	2003-01-22
[标]申请(专利权)人(译)	佳能株式会社		
申请(专利权)人(译)	佳能株式会社		
当前申请(专利权)人(译)	佳能株式会社		
[标]发明人	LI XIAO CHANG CHARLES UENO KAZUNORI		
发明人	LI, XIAO-CHANG CHARLES UENO, KAZUNORI		
IPC分类号	H01L51/50 C07F5/06 C07F15/00 C09K11/06 H01L51/00 H01L51/30 B21D39/00		
CPC分类号	H01L51/0035 Y10T428/12535 H01L51/0038 H01L51/0039 H01L51/004 H01L51/0054 H01L51/0058 H01L51/0059 H01L51/006 H01L51/0071 H01L51/0077 H01L51/0078 H01L51/008 H01L51/0081 H01L51/0083 H01L51/0085 H01L51/0089 H01L51/5012 Y10S428/917 H01L51/0036		
其他公开文献	US6677060		
外部链接	Espacenet USPTO		

摘要(译)

公开了由共轭生色团组成的有机半导体，其中一个或多个氢原子是氘代的。描述了制备这种有机半导体的方法。有机半导体化合物显示出非常高的发光性和良好的热稳定性。公开了这些材料在具有增强的性能和寿命的光电器件（例如发光器件和光电二极管）中的应用。所公开的材料可用作有机发光器件中的发光层，电荷输送层或能量转移（即磷光掺杂剂）材料。

Scheme 1.

Linear conjugated organic compounds and polymers



n > 2