



US 20060286404A1

(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2006/0286404 A1**

Wu

(43) **Pub. Date: Dec. 21, 2006**

(54) **LIGHT EMISSION MATERIAL AND ORGANIC ELECTROLUMINESCENT DEVICE USING THE SAME**

(75) Inventor: **Pei-Chi Wu, Kaohsiung (TW)**

Correspondence Address:
BACON & THOMAS, PLLC
625 SLATERS LANE
FOURTH FLOOR
ALEXANDRIA, VA 22314

(73) Assignee: **AU OPTRONICS CORP., Hsin-Chu (TW)**

(21) Appl. No.: **11/251,900**

(22) Filed: **Oct. 18, 2005**

(30) **Foreign Application Priority Data**

Jun. 15, 2005 (TW)..... 94119903

Publication Classification

(51) **Int. Cl.**

H01L 51/54 (2006.01)


H05B 33/14 (2006.01)

C09K 11/06 (2006.01)

(52) **U.S. Cl.** **428/690**; 428/917; 313/504;
313/506; 257/102; 257/E51;
546/2; 546/4; 548/101

(57) **ABSTRACT**

An organic electroluminescent device including a substrate, an anode, a cathode, a hole transport layer, an electron transport layer and an emission layer is provided. The anode and the cathode are disposed on the substrate. The hole transport layer is disposed between the anode and the cathode. The electron transport layer is disposed between the hole transport layer and the cathode. The emission layer is disposed between the hole transport layer and the electron transport layer. The chemical structure of the dopant is represented by formula [I]:



“M” represents a metal atom, m is smaller than or equal to the ligand number of “M”, n is smaller than m. “Y1” is selected from aryl or heteroaryl. “Y2” and “Y3” are respectively selected from nitro-containing heterocyclic ring. “X”, “R1”, “R2” and “R3” are respectively selected from any substituent group or hydrogen. “A” is selected from aryl, heteroaryl or nitro-containing heterocyclic group.

10




FIG. 1




FIG. 2

LIGHT EMISSION MATERIAL AND ORGANIC ELECTROLUMINESCENT DEVICE USING THE SAME

[0001] This application claims the benefit of Taiwan application Serial No. 94119903, filed Jun. 15, 2005, the subject matter of which is incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The invention relates in general to an emission material, and more particularly to a phosphorescent emission material and the organic electroluminescent device using the same.

[0004] 2. Description of the Related Art

[0005] In recent years, organic electroluminescent display has gained a rapid growth, and transition metal complex compounds are widely applied to the emission material. Take the emission layer for example, the emission material is categorized as fluorescent type and phosphorescent type. The luminous efficiency of the phosphorescent type is about three times as higher as that of the fluorescent type. The phosphorescence normally exists in the form of transition metal complex compounds. Due to the heavy-atom effect, intersystem crossing would occur, triplet excitation state is formed, the occurrence of phosphorescence is increased, and the fluorescent intensity is weakened. Therefore, the development of a phosphorescent material with high efficient is critical to increase the luminance efficiency of the entire device.

[0006] The recent development in the phosphorescent material is focused on transition metal complex compound. In prior art and related patents, the central metal of phosphorescent material is focused on transition metal with d^6 configuration such as platinum (Pt), osmium (Os), iridium (Ir), rhenium (Re) and ruthenium (Ru). Iridium metal, having the features of stronger bonding with ligand, long-lived excitation state and higher luminous efficiency, is conventionally used as the central metal of phosphorescent material. In recent years, the development of the blue phosphorescent material is focused on iridium metal complex compound, and iridium (III)bis(4,6-di-fluorophenyl)-pyridinato-N,C2' picolinate (Flrpic) blue phosphorescent material is the most popular one.

[0007] The Flrpic blue phosphorescent material is poor in sublimation, so temperature control during the purification process becomes a critical factor. Moreover, the temperature of the Flrpic blue phosphorescent material during the sublimation and purification process is hard to control, so that the Flrpic blue phosphorescent material is decomposed during the sublimation and purification process, causing the yield rate of the Flrpic blue phosphorescent material to decrease.


[0008] It can be seen from prior art and related patents that the maximum wavelength of emission (λ_{max}) of the Flrpic blue phosphorescent material in solution state is 476,492 (nm), the maximum wavelength of emission of the device using the Flrpic blue phosphorescent material is 475,498 (nm), and the CIE[x, y] value of the device is [0.16, 0.29]. Therefore, the photochromism of the Flrpic blue phosphorescent material and the device using the same is not blue enough.

SUMMARY OF THE INVENTION

[0009] It is therefore the object of the invention to provide an emission material and the organic electroluminescent device using the same. The emission material formed according to iridium and pyridyl-triazole ligand has the features of easy sublimation, quick response and high output rate and is capable of resolving the problems of difficult sublimation, poor heat-stability, and long purification time encountered in the conventional manufacturing process of the Flrpic blue phosphorescent material. With the features of easy sublimation, quick response and high output rate, the emission material synthesized according to the invention requires a shorter purification time than conventional Flrpic blue phosphorescent material.

[0010] Besides, the maximum wavelength of emission (λ_{max}) of the emission material of the invention in resolution is 462,492 (nm), the λ_{max} of the device using the emission material of the invention is 464,488 (nm), and the CIE[x, y] value of device is [0.16, 0.27]. However, the λ_{max} of the Flrpic blue phosphorescent material in solution state is 476,492 (nm), the λ_{max} of the device using Flrpic blue phosphorescent material is 475,498 (nm), and the CIE[x, y] value of device is [0.16, 0.29]. Therefore, the emission material of the invention has a bluer photochromism than the Flrpic blue phosphorescent material does, and the device using the emission material of the invention has a bluer photochromism than the device using Flrpic blue phosphorescent material. It can be seen that the emission material of the invention is ideal for the blue phosphorescent material, applicable to a blue phosphorescent device, and is indeed a big breakthrough in terms of the research and development of the blue phosphorescent material.


[0011] According to an object of the invention, the invention provides an emission material whose chemical structure is represented by formula [I]:



[0012] "M" represents a metal atom whose atomic weight is greater than 40. m is smaller than or equal to the ligand number of "M". n is a positive integral and is smaller than m. "Y1" is selected from aryl or heteroaryl. "Y2" and "Y3" are respectively selected from nitro-containing heterocyclic ring. "X", "R1", "R2" and "R3" are respectively selected from any substituent group or hydrogen. "A" is selected from aryl, heteroaryl or nitro-containing heterocyclic group.

[0013] According to another object of the invention, an organic electroluminescent device (OELD) is provided. The OELD includes a substrate, an anode, a cathode, a hole

transport layer, an electron transport layer and a emission layer. The anode and the cathode disposed on the substrate, the hole transport layer is disposed between the anode and the cathode, and the electron transport layer is disposed between the hole transport layer and the cathode. The emission layer is disposed between the hole transport layer and the electron transport layer, and the emission layer comprises a host and a dopant. The chemical structure of the dopant is represented by the formula [I]:



[0014] "M" represents a metal atom whose atomic weight is greater than 40. m is smaller than or equal to the ligand number of "M". n is a positive integral and is smaller than m. "Y1" is selected from aryl or heteroaryl. "Y2" and "Y3" are respectively selected from nitro-containing heterocyclic ring. "X", "R1", "R2" and "R3" are respectively selected from any substituent group or hydrogen. "A" is selected from aryl, heteroaryl or nitro-containing heterocyclic group.

[0015] Other objects, features, and advantages of the invention will become apparent from the following detailed description of the preferred but non-limiting embodiments. The following description is made with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS


[0016] FIG. 1 is a structural diagram of an OLED according to a second embodiment of the invention; and

[0017] FIG. 2 is a flowchart of the manufacturing method of an OLED according to a third embodiment of the invention.

DETAILED DESCRIPTION OF THE INVENTION

First Embodiment

[0018] The invention provides an emission material having the features of easy sublimation, quick response and high output rate, therefore requires a shorter purification time than conventional Irpic blue phosphorescent material. Compared with the conventional device using the Irpic blue phosphorescent material, the device using the emission material of the invention obtains higher luminous efficiency and lower CIE value and has a bluer photochromism. The emission material of the invention is represented by chemical formula [I]:



[0019] "M" represents a metal atom whose atomic weight is greater than 40. m is smaller than or equal to the ligand number of "M". n is a positive integral and is smaller than m. "Y1" is selected from aryl or heteroaryl. "Y2" and "Y3" are respectively selected from nitro-containing heterocyclic ring. "X", "R1", "R2" and "R3" are respectively selected from any substituent group or hydrogen. "A" is selected from aryl, heteroaryl or nitro-containing heterocyclic group.


[0020] "M" is selected from osmium (Os), ruthenium (Ru), iridium (Ir), platinum (Pt), rhenium (Re), thallium (Tl), palladium (Pd) or rhodium (Rh)

[0021] "A" is selected from pyridine, benzene, naphthalene, anthracene, phenanthrene or biphenyl.


[0022] "X", "R1", "R2" and "R3" are respectively selected from alkyl, alkoxy, haloalkyl, halogen, cyano group or electron-withdrawing group.

[0023] Moreover, the emission material disclosed above can be a blue emission material such as a blue phosphorescent dopant. Besides, the emission material of the embodiment can also be manufactured of phosphorescent material or fluorescent material of other colors.

[0024] In the embodiment, the emission material is formed by iridium (Ir) and pyridyl-triazole ligand I. The iridium (Ir) has six coordinates and can be externally connected to three ligands. When the value of n is 1, the value of m is equal to 2. Therefore, the emission material of the embodiment can be the material whose chemical structures are represented by formulas [II]-[V]:





-continued




[III]

2




[IV]



[V]

[0026] In step (a), at first, 1.0 g and 6.3 mmol of 2,4-Difluorophenyl boronic acid, 0.036 g and 0.16 mmol of acetic acid palladium $[Pd(acetate)_2]$, and 0.168 g and 0.641 mmol of Triphenylphosphane are dispersed in 12 ml of potassium carbonate (K_2CO_3) water solution of 2M mol concentration and in 6 ml of 1,2-Dimethoxyethane solution. Next, 6.33 mmol and 0.6 ml of 2-Bromopyridine are dropwise added into the above resolution, and refluxed for 24 hours. After 24 hours of reaction are completed, the solution is left still for the solution temperature to be reduced to the room temperature. Next, the solvent is drained, and a yellowish brown solid is obtained. The yellow solid is dissolved in approximately 60 ml of water, and then is extracted twice using dichloromethane (Cl_2CH_2) with the unit extraction volume being equal to 50 ml. Next, the organic layer in the extracted solution is obtained, and is then dehydrated using sodium sulfate (Na_2SO_4). A filter plate is used to filter the sodium sulfate and the overdosed and remnant catalyst. Then, a rotary concentrator is used to drain the solvent of the obtained organic layer to obtain a product. Next, the dichloromethane/hexane is used as the solvent according to re-crystallization, then a light yellow crystal product is obtained. The light yellow crystal product is exactly the above chemical compound 1, having an output of 0.43 g (2.25 mmol), and an output rate of 36%.


[0027] Next, proceed to step (b), $[(24dfppy)_2Ir(\mu-Cl)_2Ir(24dfppy)_2]$ dimer ligand is synthesized and is denoted by chemical compound 2 whose synthetic reaction is represented by:



[0025] During the manufacturing process of the emission materials whose chemical structures are represented by formulas [II]~[V], at first, in step a, the (2,4-Difluorophenyl)-pyridine (2,4dfppy) ligand is synthesized and is denoted by chemical compound 1 whose synthetic reaction is represented by:


3

1



[0028] In step (b), at first, 3.0 g and 8.52 mmol of chlorine iridium (IrCl_3) denoted by chemical compound 3 and 3.74 g and 19.6 mmol of the chemical compound 1 are dissolved in a doping solution with the ratio of 2-methoxyethanol to water being 3:1, and refluxed for 24 hours. After 24 hours of reaction are completed, 20 ml of water are added to the above reaction solution, a large amount of solids would be obtained. Next, a product is obtained through ventilation filtering. Then, water and hexane are used to moisten and wash the product for several times, then the product is vacuum dried to obtain an iridium dimer compound. The iridium dimer compound is exactly the above chemical compound 2, having an output of 8.5 g (6.9 mmol), and an output rate of 82%.

[0029] Then, proceed to step (c), hydrazidines precursor is synthesized and is denoted by chemical compound 4 whose synthetic reaction is represented by:




[0030] In step (c), at first, 15 ml and 155.7 mmol of 2-Cyanopyridine and 98%, 30 ml and 622.7 mmol of hydrazine denoted by chemical compound 8 are dissolved in appropriate amount of ethanol (EtOH) solvent, and are doped and refluxed for 2 hours under room temperature. After the reaction is completed, a rotary concentrator is used to drain the solvent. Then, the solvent is extracted using ether for three times. Next, magnesium sulfate is used to dehydrate and dry the solution, the solvent is drained, and a light yellow solid is obtained. Then, ethanol (EtOH) is used for re-crystallization to obtain a light yellow solid. The light yellow solid is exactly the above chemical compound 4, having an output of 16.5 g (121.5 mmol), and an output rate of 78%.

[0031] It is noteworthy that, the above steps (a)~(c) are the same with the steps of synthesizing the above the emission


materials whose chemical structures are represented by formulas [II]~[V]. The subsequent manufacturing steps of the emission material whose chemical structure is represented by formulas [II] are exemplified below.

[0032] After the chemical compound 4 is synthesized, proceed to step (d1), [3-(4-Trifluoromethyl-phenyl)-5-(2-pyridyl)-1,2,4-triazole ligand (CF_3 -Ph-PytzH) is synthesized and is denoted by chemical compound 6 whose synthetic reaction is represented by:



[0033] In step (d1), at first, 1.0 g and 4.80 mmol of 4-Trifluoromethylbenzoyl chloride denoted by chemical compound 7 is dissolved in 10 ml solution of Tetrahydrofuran (THF). Moreover, 0.65 g and 4.80 mmol of the chemical compound 4, and 0.33 g and 2.40 mmol of potassium carbonate are dissolved in 40 ml of Tetrahydrofuran solution. Next, the solution containing the chemical compound 7 and Tetrahydrofuran are dropwise added to the above solution containing the chemical compound 4, potassium carbonate and Tetrahydrofuran, then a precipitate is generated immediately. After 6 hours of reaction, a product is obtained through ventilation filtering. Next, water and hexane are used to moisten and wash the product for several times, then the product is vacuum dried. Then, the product is dissolved in the ethylene, heated and refluxed for 30 minutes then the reaction is terminated. After the solution is cooled down and left still for a period of time, a solid precipitate is generated. Next, ventilation filtering is applied, water and hexane are used to moisten and wash the solid precipitate for several times, and then the washed solid precipitate is vacuum dried to obtain an intermediate product which is drier now. Then, sublimation and purification process is applied to the intermediate product to obtain the above chemical compound 6. The above chemical compound 6 has an output of 1.05 g (3.61 mmol), and an output rate of 74%.

[0034] Then, proceed to step (e1), the chemical compounds 2 and 6 are used to synthesize the emission material whose chemical structure is represented by formulas [II]. As for the synthetic reaction of the formula [II] is represented by:




[0035] In step (e1), at first, 2.5 g and 2.0 mmol of the chemical compound 2, 1.31 g and 4.5 mmol of the chemical compound 6, and overdosed Na₂CO₃ are dissolved in 2-methoxyethanol solution to be refluxed for 16 hours. After 16 hours of reaction are completed, 20 ml of water are added to the above reaction solution, and a solid is generated. Next, ventilation filtering is applied, water and hexane are used to moisten and wash the solid for several times. Then, the obtained product is drained, and sublimation and purification process is applied to obtain the emission material whose chemical structure is represented by formulas [II]. The emission material whose chemical structure is represented by formulas [II] has an output of 1.46 g(1.7 mmol), and an output rate of 85%.


[0036] As for the subsequent manufacturing steps of the emission material whose chemical structure is represented by formulas [III] are exemplified below.

[0037] After the chemical compounds 2 and 4 are synthesized according to corresponding steps (a)~(c)中, proceed to step (d2), [3-(2-fluoro-4-fluoro-phenyl)-5-(2-pyridinyl)-1,2,4-triazole ligand (2F-Ph-PyztH) is synthesized, and is denoted by chemical compound 9. The synthetic reaction of the chemical compound 9 is represented by:

[0038] In step (d2), at first, 1.0 g and 5.7 mmol of the 2,4-Difluoro-benzoyl chloride denoted by chemical compound 10 are dissolved in 10 ml of Tetrahydrofuran solution. Moreover, 0.78 g and 5.7 mmol of the chemical compound 4, and 0.40 g and 2.85 mmol of potassium carbonate are dissolved in the 40 ml of Tetrahydrofuran solution. Next, the solution containing the chemical compound 10 is dropwise added to the above solution containing the chemical compound 4, and a precipitate is generated immediately. After 6 hours of reaction, ventilation filtering is applied to obtain a product. Next, water and hexane are used to moisten and wash the product for several times, and then the product is vacuum dried. Then, the product is dissolved in the ethylene, heated and refluxed for 30 minutes then the reaction is terminated. Next, the product is cooled down and left still for a period of time, then a solid precipitate is generated. Then, ventilation filtering is applied, water and hexane are used to moisten and wash the solid precipitate for several times, and then the washed solid precipitate is vacuum dried to the final product. The final product is exactly the above chemical compound 9 having an output of 1.15 g(4.45 mmol), and an output rate of 78%.

[0039] Then, proceed to step (e2), the chemical compounds 2 and 9 are used to synthesize the emission material whose chemical structure is represented by formulas [III]. The synthetic reaction of the formula [III] is represented by:







[0040] In step (e2), at first, 2.5 g and 2.0 mmol of the chemical compound 2, 1.14 g and 4.4 mmol of the chemical compound 9, and overdosed Na_2CO_3 are dissolved in 2-methoxyethanol solution, and refluxed for 16 hours. After 16 hours of reaction are completed, 20 ml of water are added to the above reaction solution, then a solid is generated. Next, ventilation filtering is applied, and water and hexane are used to moisten and wash the solid for several times. Then, the collected product is drained, then the sublimation and purification process is applied to obtain the emission material whose chemical structure is represented by formulas [III]. The emission material whose chemical structure is represented by formulas [III] has an output of 0.96 g (1.2 mmol), and an output rate of 58%.


[0041] As for the subsequent manufacturing steps of the emission material whose chemical structure is represented by formulas [IV] are exemplified below.


[0042] After the chemical compound 2 and 4 are synthesized according to corresponding steps (a)~(c), proceed to step (d3), [3-(4-Trifluoromethyl-pyridyl)-5-(2-pyridyl)-1,2,4-triazole ligand ($\text{CF}_3\text{-Py-PytzH}$)] is synthesized and is denoted by chemical compound 11. As for the synthetic reaction of the chemical compound 11 is represented by:



[0043] In step (d3), at first, 1.0 g and 4.8 mmol of 6-Trifluoromethyl-nicotinyl chloride denoted by chemical compound 12 are dissolved in 10 ml of Tetrahydrofuran solution. Moreover, 0.65 g and 4.8 mmol of the chemical compound 4, and 0.33 g and 2.40 mmol of potassium carbonate are dissolved in the 40 ml of Tetrahydrofuran solution. Next, the solution containing the chemical compound 12 are added dropwise to the above solution containing the chemical compound 4, then a precipitate is generated immediately. After 6 hours of reaction, ventilation filtering is applied to obtain a product. Next, water and hexane are used to moisten and wash the product for several times, and then the product is vacuum dried. Then, the product is dissolved in the ethylene, heated and refluxed for 30 minutes, then the reaction is terminated. Next, after the product is cooled down and left still for a period of time, a solid precipitate is generated. Then, ventilation filtering is applied, water and hexane are used to moisten and wash the solid precipitate for several times, the washed solid precipitate is vacuum dried to obtain a final product. The product is exactly the above chemical compound 11, having an output of 1.01 g (3.43 mmol), and an output rate of 72%.

[0044] Then, proceed to step (e3), the chemical compound 2 and 11 are used to synthesize the emission material whose chemical structure is represented by formulas [IV]. The synthetic reaction of the formula [IV] is represented by:







[0045] In step (e3), at first, 2.5 g and 2.0 mmol of the chemical compound 2, 1.32 g and 4.5 mmol of the chemical compound 11 and overdosed Na_2CO_3 are dissolved in 2-methoxyethanol solution, and refluxed for 16 hours. After 16 hours of reaction are completed, 20 ml of water are added to the above reaction solution, a solid is generated. Next, ventilation filtering is applied, water and hexane are used to moisten and wash the solid for several times. Then, the collected product is drained, and sublimation and purification process is applied to obtain the emission material whose chemical structure is represented by formulas [IV]. The emission material whose chemical structure is represented by formulas [IV] has an output of 1.12 g (1.3 mmol), and an output rate of 65%.


[0046] As for the subsequent manufacturing steps of the emission material whose chemical structure is represented by formulas [V] are exemplified below.


[0047] After the chemical compounds 2 and 4 are synthesized according to corresponding steps (a)-(c), proceed to step (d4), 3-Cyano-phenyl-5-(2-pyridyl)-1,2,4-triazole ligand (CN-Ph-PytzH) is synthesized and denoted by chemical compound 13. The synthetic reaction of the chemical compound 13 is represented by:



[0048] In step (d4), at first, 1.0 g and 6.0 mmol of 4-Cyano-benzoyl chloride denoted by chemical compound 14 are dissolved in 10 ml of Tetrahydrofuran solution. Moreover, 0.82 g and 6.0 mmol of the chemical compound 4, and 0.41 g and 3.0 mmol of potassium carbonate are dissolved in the 40 ml of Tetrahydrofuran solution. Next, the solution containing the chemical compound 14 is added dropwise to the above solution containing the chemical compound 4, and then a precipitate is generated immediately. After 6 hours of reaction are completed, ventilation filtering is applied to obtain a product. Next, water and hexane are used to moisten and wash the product for several times, then the product is vacuum dried. Then, the product is dissolved in the ethylene, heated and refluxed for 30 minutes, then the reaction is terminated. Next, after the product is cooled down and left still for a period of time, a solid precipitate is generated. Then, ventilation filtering is applied, water and hexane are used to moisten and wash the solid precipitate for several times, then the washed solid precipitate is vacuum dried to obtain a final product. The final product is exactly the above chemical compound 13, having an output of 1.1 g (4.5 mmol), and an output rate of 75%.

[0049] Then, proceed to step (e4), the chemical compounds 2 and 13 are used to synthesize the emission material whose chemical structure is represented by formulas [V]. The synthetic reaction of the formula [V] is represented by:





[0050] In step (e4), at first, 2.5 g and 2.0 mmol of the chemical compound 2, 1.11 g and 4.5 mmol of the chemical compound 13, and overdosed Na_2CO_3 are dissolved in 2-methoxyethanol solution, and refluxed for 16 hours. After 16 hours of reaction are completed, 20 ml of water are added to the above reaction solution, a solid is generated. Next, ventilation filtering is applied, and water and hexane are used to moisten and wash the solid for several times. Then, the collected product is drained, and sublimation and purification process is applied to obtain the emission material whose chemical structure is represented by formulas [V]. The emission material whose chemical structure is represented by formulas [V] has an output of 0.85 g(1.04 mmol), and an output rate of 52%.

[0051] In the present embodiment, a Hitachi F-4500 spectrophotometer is used to observe the photoluminescence spectra (PL) of the above emission materials whose chemical structures are represented by formulas [II]-[V] when in thin film state or solution state. For example, the photoluminescence spectra of the above emission materials whose chemical structures are represented by formulas [II]-[V] when in dichloromethane solution is observed. The λ_{max} (nm) of respective emission material in solution state can be known according to the photoluminescence spectra of respective emission material in solution state. Besides, the λ_{max} (nm) and CIE[x, y] value of respective emission material are recorded in the table below.

emission material	λ_{max} (nm)	CIE[x, y] value
chemical formula [II]	462, 490	0.13, 0.25
chemical formula [III]	468, 492	0.13, 0.32

-continued

emission material	λ_{max} (nm)	CIE[x, y] value
chemical formula [IV]	468, 490	0.14, 0.31
chemical formula [V]	468, 492	0.14, 0.32


[0052] It can be seen from the above table that the λ_{max} of the emission materials whose chemical structures are represented by formulas [II]-[V] when in solution state are respectively within the range of blue photochromism, and the CIE[x, y] values of the emission materials whose chemical structures are represented by formulas [II]-[V] are also within blue region. The emission materials whose chemical structures are represented by formulas [II]-[V] has a bluer photochromism than conventional Flrpic blue phosphorescent material does, and the CIE[x, y] value of the emission material whose chemical structure is represented by formulas [II] has a bluer photochromism than the CIE value of the emission materials whose chemical structures are represented by formulas [III]-[V]. Therefore, the emission materials whose chemical structures are represented by formulas [II]-[V] are ideal for the blue emission material such as the blue phosphorescent the emission material for instance. However, the technology of the embodiment is not limited thereto. For example, the emission materials whose chemical structures are represented by formulas [II]-[V] can also be used as the blue fluorescent the emission material or the emission material of other colors, such as the phosphorescent or the fluorescent emission material of other colors.

[0053] The emission material disclosed in the embodiment has the features of easy sublimation, quick response and high output rate and is capable of resolving the problems of difficult sublimation, poor heat-stability, and long purification time encountered in the conventional manufacturing process of the Flrpic blue phosphorescent material. With the features of easy sublimation, quick response and high output rate, the new emission material of the embodiment purification time requires shorter purification time than the conventional Flrpic blue phosphorescent material does, and is a breakthrough in terms of the research and development of the blue phosphorescent material.

Second Embodiment

[0054] Referring to FIG. 1, a structural diagram of an OLED according to a second embodiment of the invention is shown. In the embodiment, the OLED, including organic light emitting diode (OLED) of small molecules and polymer light emitting diode (PLED), is exemplified by the OLED here. However, the technology disclosed in the embodiment is applicable to the PLED.

[0055] In FIG. 1, the OLED 10 includes a substrate 11, an anode 12, a cathode 13, a hole transport layer 14, an electron transport layer 15 and an emission layer 16. The anode 12 and the cathode 13 are disposed on the substrate 11. The hole transport layer 14 is disposed between the anode 12 and the cathode 13. The electron transport layer 15 is disposed between the hole transport layer 14 and the cathode 13. The emission layer 16 is disposed between the hole transport layer 14 and the electron transport layer 15, and the emission layer 16 includes a host and a dopant. The chemical structure of the dopant is represented by the formula [I]:



[0056] “M” represents a metal atom whose atomic weight is greater than 40. m is smaller than or equal to the ligand number of “M”. n is a positive integral and is smaller than m. “Y1” is selected from aryl or heteroaryl. “Y2” and “Y3” are respectively selected from nitro-containing heterocyclic ring. “X”, “R1”, “R2” and “R3” are respectively selected from any substituent group or hydrogen. “A” is selected from aryl, heteroaryl or nitro-containing heterocyclic group.


[0057] “M” is selected from osmium (Os), ruthenium (Ru), iridium (Ir), platinum (Pt), rhenium (Re), thallium (Tl), palladium (Pd) or rhodium (Rh)

[0058] “A” is selected from pyridine, benzene, naphthalene, anthracene, phenanthrene or biphenyl.



[0059] “X”, “R1”, “R2” and “R3” are respectively selected from alkyl, alkoxy, haloalkyl, halogen, cyano group or electron-withdrawing group.

[0060] Moreover, the emission material disclosed above can be a blue emission material such as a blue phosphorescent dopant. Besides, the emission material of the embodiment can also be manufactured of phosphorescent material or fluorescent material of other colors. In the embodiment, the value of n is 1.

[0061] In the embodiment, the emission material can be formed by iridium (Ir) and pyridyl-triazole ligand I. The iridium (Ir) has six coordinates, and can be externally connected to three ligands. When the value of n is 1, the value of m is equal to 2. Therefore, the emission material of the embodiment can be the material whose chemical structures are represented by formulas [III]–[V]:



-continued



[0062] In the embodiment, the OLED 10 further includes a hole injection layer 17 disposed between the hole transport layer 14 and the anode 12. Besides, the OLED 10 further includes an electron injection layer 18 disposed between the electron transport layer 15 and the cathode 13. Moreover, the OLED 10 further includes a hole blocking layer 19 disposed between the electron transport layer 15 and the emission layer 16.

[0063] The electrical injection effect, brightness, luminous efficiency and photo-electro conversion efficiency of the device are elaborated below. In the embodiment, the sub-

strate **11**, the anode **12**, the cathode **13**, the host and the dopant are respectively exemplified by a glass substrate, indium tin oxide (ITO), a cathode composed of lithium fluoride (LiF) and aluminum (Al), N,N'-dicarbazole-1,3-benzene (mCP), and the emission material whose chemical structure is represented by formulas [IV]. Besides, the change in the electrical injection effect, brightness, luminous efficiency and photo-electro conversion efficiency of the device are observed by changing the doping concentration of the emission material whose chemical structure is represented by formulas [IV] in mCP. When the doping concentration of the emission material whose chemical structure is represented by formulas [IV] in mCP is between 10~12%, the device has a better performance in terms of electrical injection effect, brightness, luminous efficiency and photo-electro conversion efficiency. The device can reach the luminous efficiency as high as 10.7 (cd/A), however, the technology of the embodiment is not limited thereto.

[0064] As for the photochromism of the device using the emission material whose chemical structure is represented by formulas [IV], when the dopant has a larger doping concentration, the CIE[x, y] value of the device grows larger as well, but is still within the blue region. The CIE[x, y] value of device approximately falls within in the range of [0.16, 0.28]. When the doping concentration of the dopant is fixed, the CIE[x, y] value of the device may slightly decrease as the operating voltage of the device increases, but is still within the blue region. The λ_{\max} of the device using the emission material whose chemical structure is represented by formulas [IV] is 464 (nm) and only differs by 4 (nm) with the λ_{\max} 468 (nm) of the emission material whose chemical structure is represented by formulas [IV] when in solution state.

[0065] Therefore, the device has a best performance when the doping concentration of the dopant is about 12%. The doping concentration of the dopant being too high or too low is disadvantageous to the performance of the device.

[0066] Moreover, the emission material whose chemical structure is represented by formula [II] is the dopant, and the doping concentration of the emission material whose chemical structure is represented by formulas [II] in mCP is fixed at 11%. Then the electrical injection effect, brightness, luminous efficiency and photo-electro conversion efficiency of the device are observed by changing the thickness of the electron transport layer. When the thickness of the electron transport layer grows thicker, the electrical injection effect of the device becomes poorer, but the luminous efficiency and photo-electro conversion efficiency become better. The luminous efficiency of the device can reach as high as 9.2 (cd/A). The brightness of the device does not show much difference with respect to the thickness of the electron transport layer. However, the technology of the embodiment is not limited thereto.

[0067] As for the photochromism of the device using the emission material whose chemical structure is represented by formulas [II], the photochromism of the device is blue when the CIE[x, y] value approximately falls within the range of [0.16, 0.27]. However, the CIEy value of the device declines as the operating voltage increases. When the thickness of the electron transport layer becomes thicker, the CIE[x, y] value of device becomes lower, but is still within the blue region. The λ_{\max} of device using the emission material whose chemical structure is represented by formulas [II] is 464 (nm) and only differs by 2 (nm) with the λ_{\max}

462 (nm) of the emission material whose chemical structure is represented by formulas [II] when in solution state.

[0068] According to the above disclosure, the device using the emission materials whose chemical structures are represented by [II]~[V] can be blue devices such as a blue phosphorescent device for instance. However, the technology of the embodiment is not limited thereto. For example, the emission materials whose chemical structures are represented by formulas [II]~[V] can be blue or other colored fluorescent device, such as the phosphorescent or fluorescent device of other colors for instance.

[0069] However, anyone who is skilled in the technology of the embodiment will understand that the technology of the invention is not limited thereto. For example, the anode **12** and the cathode **13** include metal, metal alloy or transparent conductive material. At least one of the anode **12** and the cathode **13** is a transparent or semi-transparent electrode. The above transparent conductive material includes transparent metal oxides such as indium tin oxide (ITO), indium zinc oxide (IZO), cadmium tin oxide (CTO), stannum dioxide (SnO₂) and zinc oxide (ZnO). The above metal and metal alloy include aurum (Au), aluminum (Al), indium (In), magnesium (Mg) and calcium (Ca) and so forth.

[0070] When only the anode **12** is transparent or semi-transparent, the cathode **13** can be a reflective metal, then the OLED **10** is a bottom emission and the substrate **11** is a transparent or semi-transparent the substrate. When only the cathode **13** is transparent or semi-transparent, the anode **12** can be a reflective metal, then the OLED **10** is top emission device and the substrate **11** can be a transparent, semi-transparent or transparent substrate. When the anode **12** and the cathode **13** are both transparent or semi-transparent, the OLED **10** is a dual emission device and the substrate **11** is a transparent or semi-transparent substrate.

[0071] The OLED **10** of the present embodiment can be applied to electronic products such as computer screen, flat TV, monitor screen, vehicle TV, mobile phone, handheld game station, digital camera (DC), digital video (DVD), digital audio device, personal digital assistant (PDA), web pad, notebook, handheld computer, laptop computer, table PC, and so forth.

Third Embodiment

[0072] Referring to FIG. 2 is a flowchart of the manufacturing method of an OLED according to a third embodiment of the invention is shown. Refer to FIG. 1 at the same time. At first, the method begins at step **21**, a substrate **11** is provided. Next, proceed to step **22**, an anode **12** is formed on the substrate **11**. Then, proceed to step **23**, a hole injection layer **17** is formed on the anode **12**. Next, proceed to step **24**, a hole transport layer **14** is formed on the hole injection layer **17**. Then, proceed to step **25**, an emission layer **16** is formed on the hole transport layer **14**. The emission layer **16** has a host and a dopant. The chemical structure of the dopant is represented by formulas [I]. Next, proceed to step **26**, a hole blocking layer **19** is formed on the emission layer **16**. Afterwards, proceed to step **27**, an electron transport layer **15** is formed on the hole blocking layer **19**. Next, proceed to step **28**, an electron injection layer **18** is formed on the electron transport layer **15**. At last, proceed to step **29**, a cathode **13** is formed on the electron injection layer **18**, and the OLED **10** is completed.

[0073] Despite the emission material of the embodiment is exemplified by the dopant, the technology of the embodi-

ment is not limited thereto. For example, the emission material of the embodiment can be used as a host to form an emission layer with other dopants.


[0074] According to the emission material disclosed in the embodiment of the invention and the OLED using the same, the emission material formed by iridium and pyridyl-triazole ligand has the features of easy sublimation, quick response and high output rate and is capable of resolving the problems of difficult sublimation, poor heat-stability, and long purification time encountered in the conventional manufacturing process of the Flrpic blue phosphorescent material. With the features of easy sublimation, quick response and high output rate, the new emission material formed according to the embodiment requires shorter purification time than the conventional Flrpic blue phosphorescent material.

[0075] Besides, the λ_{\max} of the emission material of the embodiment in resolution is 462,492 (nm), the λ_{\max} of the device using the emission material of the embodiment is 464,488 (nm), and the CIE[x, y] value of device is [0.16, 0.27]. However, the λ_{\max} of the Flrpic blue phosphorescent material in solution state is 476,492 (nm), the λ_{\max} the device using the Flrpic blue phosphorescent material, is 475,498 (nm), and the CIE[x, y] value of device is [0.16, 0.29]. It can be seen from the above comparison that the emission material of the embodiment has a bluer photochromism than the Flrpic blue phosphorescent material does, and the device using the emission material of the embodiment has a bluer photochromism than the device using Flrpic blue phosphorescent material. It can be seen that the emission material of the invention is ideal for the blue phosphorescent material, applicable to a blue phosphorescent device, and is indeed a big breakthrough in terms of the research and development of the blue phosphorescent material.

[0076] While the invention has been described by way of example and in terms of a preferred embodiment, it is to be understood that the invention is not limited thereto. On the contrary, it is intended to cover various modifications and similar arrangements and procedures, and the scope of the appended claims therefore should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements and procedures.

What is claimed is:

1. An emission material whose chemical structure is represented by formula [I]:



wherein "M" represents a metal atom whose atomic weight is greater than 40, m is smaller than or equal to the ligand number of "M", n is a positive integral and is smaller than m, "Y1" is selected from aryl or heteroaryl, "Y2" and "Y3" are respectively selected

from nitro-containing heterocyclic ring, "X", "R1", "R2" and "R3" are respectively selected from any substituent group or hydrogen, "A" is selected from aryl, heteroaryl or nitro-containing heterocyclic group.

2. The emission material according to claim 1, wherein "M" is selected from osmium (Os), ruthenium (Ru), iridium (Ir), platinum (Pt), rhenium (Re), thallium (Tl), palladium (Pd) or rhodium (Rh)


3. The emission material according to claim 1, wherein "A" is selected from pyridine, benzene, naphthalene, anthracene, phenanthrene or biphenyl.

4. The emission material according to claim 1, wherein "X", "R1", "R2" and "R3" are respectively selected from alkyl, alkoxy, haloalkyl, halogen, cyano group or electron-withdrawing group.


5. The emission material according to claim 1, wherein the value of n is 1.

6. The emission material according to claim 1, being a blue phosphorescent dopant.


7. The emission material according to claim 1, whose chemical structure is further represented by formula [II]:




8. The emission material according to claim 1, whose chemical structure is further represented by formula [III]:



9. The emission material according to claim 1, whose chemical structure is further represented by formula [IV]:




10. The emission material according to claim 1, whose chemical structure is further represented by formula [V]:



11. An organic electroluminescent device (OELD), comprising:

- a substrate;
- an anode and a cathode, disposed on the substrate;
- a hole transport layer disposed between the anode and the cathode;
- an electron transport layer disposed between the hole transport layer and the cathode; and
- an emission layer disposed between the hole transport layer and the electron transport layer, wherein the emission layer comprises a host and a dopant, and the chemical structure of the dopant is represented by the formula [I]:



wherein, “M” represents a metal atom whose atomic weight is greater than 40, m is smaller than or equal to the ligand number of “M”, n is a positive integral and is smaller than m, “Y1” is selected from aryl or heteroaryl, “Y2” and “Y3” are respectively selected from nitro-containing heterocyclic ring, “X”, “R1”, “R2” and “R3” are respectively selected from any substituent group or hydrogen, “A” is selected from aryl, heteroaryl or nitro-containing heterocyclic group.

12. The OELD according to claim 11, wherein “M” is selected from osmium (Os), ruthenium (Ru), iridium (Ir), platinum (Pt), rhenium (Re), thallium (Tl), palladium (Pd) or rhodium (Rh)


13. The OELD according to claim 11, wherein “A” is selected from pyridine, benzene, naphthalene, anthracene, phenanthrene or biphenyl.

14. The OELD according to claim 11, wherein “X”, “R1”, “R2” and “R3” are respectively selected from alkyl, alkoxy, haloalkyl, halogen, cyano group or electron-withdrawing group.


15. The OELD according to claim 11, wherein the value of n is 1.

16. The OELD according to claim 11, wherein the dopant is a blue phosphorescent dopant.


17. The OELD according to claim 11, wherein the chemical structure of the dopant is represented by formula [II]:



18. The OELD according to claim 11, wherein the chemical structure of the dopant is further represented by formula [III]:




19. The OLED according to claim 11, wherein the chemical structure of the dopant is further represented by formula [IV]:



[IV]

20. The OLED according to claim 11, wherein the chemical structure of the dopant is further represented by formula [V]:



[V]

专利名称(译)	发光材料和使用其的有机电致发光器件		
公开(公告)号	US20060286404A1	公开(公告)日	2006-12-21
申请号	US11/251900	申请日	2005-10-18
[标]申请(专利权)人(译)	友达光电股份有限公司		
申请(专利权)人(译)	友达光电.		
当前申请(专利权)人(译)	友达光电.		
[标]发明人	WU PEI CHI		
发明人	WU, PEI-CHI		
IPC分类号	H01L51/54 H05B33/14 C09K11/06		
CPC分类号	C09K11/06 C09K2211/1007 C09K2211/1029 H05B33/14 C09K2211/185 H01L51/0085 H01L51/5016 C09K2211/1059 Y10S428/917		
优先权	094119903 2005-06-15 TW		
其他公开文献	US7662486		
外部链接	Espacenet USPTO		

摘要(译)

提供一种有机电致发光器件，包括基板，阳极，阴极，空穴传输层，电子传输层和发光层。阳极和阴极设置在基板上。空穴传输层设置在阳极和阴极之间。电子传输层设置在空穴传输层和阴极之间。发光层设置在空穴传输层和电子传输层之间。掺杂剂的化学结构由式[I]表示：“M”表示金属原子，m小于或等于配体数“M”，n小于m。“Y1”选自芳基或杂芳基。“Y2”和“Y3”分别选自含硝基的杂环。“X”，“R 1”，“R 2”和“R 3”分别选自任何取代基或氢。“A”选自芳基，杂芳基或含硝基的杂环基。

