





US 20040013902A1

(19) **United States**(12) **Patent Application Publication**
Chen et al.(10) **Pub. No.: US 2004/0013902 A1**(43) **Pub. Date: Jan. 22, 2004**(54) **RED LIGHT EMITTING MATERIALS**(57) **ABSTRACT**

This invention features a compound having the formula:

(76) Inventors: **Chin-Ti Chen**, Taipei (TW); **Hsiu-Chih Yeh**, Sanchung (TW); **Wei-Ching Wu**, Luhchou (TW); **Li-Hsin Chan**, Yangmei (TW)

(I)

Correspondence Address:
FISH & RICHARDSON PC
225 FRANKLIN ST
BOSTON, MA 02110 (US)X is O or NR₁; and each of Y and Z, independently, is(21) Appl. No.: **10/191,145**(22) Filed: **Jul. 9, 2002****Publication Classification**(51) **Int. Cl.⁷** **H05B 33/14**; C09K 11/06
(52) **U.S. Cl.** **428/690**; 428/917; 313/504;
313/506; 252/301.16; 548/517;
548/548; 549/477in which each of R₁, R₂, R₃, and R₄, independently, is alkyl, cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; Ar₁ is aralkyl, aryl, or heteroaryl; and Ar₂ is cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; or Ar₁ and Ar₂ taken together is heterocyclyl, aralkyl, or heteroaryl. This compound can be used as a red light emitting material in an electro-luminescence device.

RED LIGHT EMITTING MATERIALS

BACKGROUND


[0001] Organic light emitting diodes (OLEDs) are useful in a wide range of lighting applications, as well as high and low resolution display devices. They have been made both with low molecular-weight organic materials and with polymers. For full-color applications, it is necessary to have a set of red, green, and blue OLEDs. Efficient green and blue OLEDs are now available. Yet, there has been a lack of red OLEDs that exhibit both saturated emissions and high, stable luminescence quantum efficiency (Picciolo et al. (2001) *Applied Phys. Lett.* 78: 2378).

[0002] Currently, most red OLEDs contain dopant-containing layers made of red light emitting materials. See, e.g., Chen et al. (1997) *Macromol. Symp.* 125: 1; and Zhang et al. (2001) *Chem. Mater.* 13: 1565; and Picciolo et al. (2001) *Appl. Phys. Lett.* 78: 2378. The red light emitting materials can be polar, such as electron donor-substituted pyran compounds (Tang et al. (1989) *Appl. Phys. Lett.* 65: 3610; Zhang et al. (2001) *Chem. Mater.* 13: 1565; and Chen et al. (2001) *J. Phys. D: Appl. Phys.* 34: 30). They can also be extensively π -conjugated, such as porphyrin compounds (Burrows et al. (1996) *Appl. Phys. Lett.* 69: 2959; Morgado et al. (2001) *J. Mater. Chem.* 11: 278; and Kwong et al. (2000) *Adv. Mater.* 12: 1134). These materials have a tendency towards crystallization, and thus, are either weakly emissive or not emissive in solid state. Further, dopant-containing OLEDs are not favored in mass production.

SUMMARY


[0003] This invention relates to compounds that are useful, among others, as red light emitting materials for red OLEDs.

[0004] In one aspect, this invention features a compound having the formula:




(I)

[0005] X is I or NR₁; and each of Y and Z, independently, is






-continued




[0006] (referred to as Ar₁NR₂R₃; Ar₁NR₄; or Ar₁Ar₂N hereinafter); in which each of R₁, R₂, R₃, and R₄, independently, is alkyl, cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; Ar₁ is aralkyl, aryl, or heteroaryl; and Ar₂ is cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; or Ar₁ and Ar₂ taken together is heterocyclyl, aralkyl, or heteroaryl.

[0007] A subset of the above-described compounds are those in which X is NR₁. Embodiments include compounds in which Y and Z, independently, is Ar₁NR₂R₃. Examples of Ar₁ include, but are not limited to, phenyl, furyl, thiophenyl, fluorenyl, 9,9'-R,R-substituted fluorenyl [each of the Rs, independently, is aryl (e.g., phenyl or 4-tolyl), or C₁-C₆ alkyl], and [9,9']spirobifluorenyl. Representative compounds are:




-continued




[0008] In each of the above structures, the two R_2 's (or the two R_3 's) can be the same or different. The same rule applies to other similar situations. Each of R_2 and R_3 , independently, can be phenyl or naphthyl; and R_1 can be CH_3 . Additional examples of R_2 and R_3 include, but are not limited to, biphenyl, terphenyl, anthracenyl, acenaphthyl, perylenyl, pyrenyl, petacenyl, [9,9']spirobifluorenyl, 9,9'-diarylfuorenyl, 9,9'-dialkylfluorenyl, and 9,9'-alkylarylfluorenyl; in which aryl represents phenyl, naphthyl, anthracenyl, pyrenyl, petacenyl, tolyl, or anisoyl, and alkyl represents methyl, ethyl, propyl, or butyl.

[0009] In other embodiments, each of Y and Z, independently, is Ar_1NR_4 . Ar_1 can be carbazolyl or indolyl. Representative compounds are:




[0010] In still other embodiments, each of Y and Z, independently, is $\text{Ar}_1\text{Ar}_2\text{N}$. Ar_1 and Ar_2 taken together can be pyrido-quinoline. A representative compound is:



[0011] Another set of the compounds of this invention are those in which X is O. In these compounds, each of Y and Z, independently, can be $\text{Ar}_1\text{NR}_2\text{R}_3$ and Ar_1 can be phenyl, furyl, thiophenyl, fluorenyl, 9,9'-R,R-substituted fluorenyl [each of the Rs, independently, is aryl (e.g., phenyl or 4-tolyl), or $\text{C}_1\text{--C}_6$ alkyl], or [9,9']spirobifluorenyl. Each of Y and Z, independently, also can be Ar_1NR_4 or $\text{Ar}_1\text{Ar}_2\text{N}$, and Ar_1 can be carbazolyl or indolyl, or Ar_1 and Ar_2 taken together can be pyrido-quinoline. Representative compounds are:

-continued



[0012] Alkyl, cyclyl, heterocyclyl, aralkyl (e.g., fluorenyl or carbazolyl), aryl (e.g., phenyl), or heteroaryl (e.g., furyl, thiophenyl, or indolyl) mentioned above refers to both substituted and unsubstituted moieties. The term “substituted,” in turn, refers to one or more substituents (which may be the same or different), each replacing a hydrogen atom. Examples of substituents include, but are not limited to, halogen, amino, alkylamino, arylamino, dialkylamino, diarylamino, hydroxyl, mercapto, sulfonyl, cyano, nitro, $C_1\sim C_3$ alkyl, $C_1\sim C_6$ alkenyl, $C_1\sim C_6$ alkoxy, aryl, heteroaryl, aryloxy, cyclyl, or heterocyclyl; wherein alkyl, alkenyl, alkoxy, aryl, and heteroaryl are optionally substituted with $C_1\sim C_6$ alkyl, halogen, amino, alkylamino, arylamino, dialkylamino, diarylamino, hydroxyl, mercapto, cyano, or nitro.

[0013] The term “aralkyl” refers to a moiety in which an alkyl hydrogen atom is replaced by an aryl group. Examples of aralkyl moieties include fluorenyl, carbazolyl, and 9,9'-substituted fluorenyl, such as [9,9']spirobifluorenyl, 9,9'-diarylfuorenyl, 9,9'-dialkylfluorenyl, and 9,9'-alkylarylfluorenyl; in which aryl represents phenyl, naphthyl, anthracenyl, pyrenyl, petacenyl, tolyl, or anisoyl, and alkyl represents methyl, ethyl, propyl, or butyl.


[0014] The term “aryl” refers to a hydrocarbon ring system having at least one aromatic ring. Examples of aryl moieties include, but are not limited to, phenyl, naphthyl, anthracenyl, perylenyl, and pyrenyl.

[0015] The term “heteroaryl” refers to a hydrocarbon ring system having at least one aromatic ring which contains at least one heteroatom such as O, N, or S. Examples of heteroaryl moieties include, but are not limited to, pyridinyl, carbazolyl, and indolyl.

[0016] The terms “cyclyl” and “heterocyclyl” refer to partially and fully saturated mono-, bi-, or tri-cyclic rings having from 4 to 14 ring atoms. A heterocyclyl ring contains one or more heteroatoms. Exemplary cyclyl and heterocyclyl rings are cyclohexane, piperidine, piperazine, morpholine, thiomorpholine, and 1,4-oxazepane.

[0017] The compounds described above include the compounds themselves, as well as their salts, if applicable. The salts, for example, can be formed via interactions between a positively charged substituent (e.g., amino) on a compound and an anion. Suitable anions include, but are not limited to, chloride, bromide, iodide, sulfate, nitrate, phosphate, citrate, methanesulfonate, trifluoroacetate, and acetate. Likewise, a negatively charged substituent (e.g., carboxylate) on a compound can form a salt with a cation. Suitable cations include, but are not limited to, sodium ion, potassium ion, magnesium ion, and ammonium cation such as tetramethylammonium ion. In addition, some of the compounds have one or more asymmetric centers. Such compounds can occur as racemates, tautomers, enantiomers, and diastereomers.

[0018] One exemplary compound of this invention is N-methyl-bis(4-(1-naphthylphenylamino)phenyl)maleimide:




[0019] In another aspect, this invention features a red light emitting electro-luminescence device that is made with one or more of the compounds described above. The device includes an anode layer, a hole transporting layer, a light emitting layer that includes the compounds of this invention, an electron transporting layer, and a cathode layer. The anode, the hole transporting layer, the light emitting layer, the electron transporting layer, and the cathode are disposed in the above order. The hole transporting layer and the light emitting layer can be of the same layer. In other words, a layer, that sandwiches between the anode layer and the electron transporting layer, functions as both a hole transporting layer and a light emitting layer.



[0020] Other features, objects, and advantages of the invention will be apparent from the description and from the claims.

DETAILED DESCRIPTION

[0021] Within the scope of this invention are novel compounds and red light emitting electro-luminescence devices that contain such compounds.

[0022] The compounds of this invention can be prepared by methods well known to a skilled person in the art. For example, shown below is a scheme that depicts a synthetic route. In this scheme, Ar_1 , R_1 , R_2 , and R_3 are as defined in Summary.





[0023] As shown in the above scheme, a compound of this invention can be prepared with a cyanomethyl-bromoaryl compound as a starting material. More specifically, a cyanomethyl-bromoaryl compound is oxidized with iodine and hydrolyzed with an acid, followed by alkylation with a R_1 -halide and reaction with a R_2, R_3 -substituted amine in the presence of palladium to form a desired product. If an asymmetrical compound of this invention is desired, two different cyanomethyl-bromoaryl compounds or two different R_2, R_3 -substituted amines can be used.

[0024] In another example, as shown below, a cyanomethyl-substituted compound can be oxidized with an oxidizing agent, hydrolyzed with an acid, and alkylated with a R_1 -halide to form another compound of this invention. Further hydrolysis in alkali alcoholic solution can generate anhydride derivatives. In this scheme, Ar_1, Ar_2 , and R_1 are as defined in Summary.

[0025] The chemicals used in the above-described synthetic routes may include, for example, solvents, reagents, catalysts, protecting group and deprotecting group reagents. The methods described above may also additionally include steps, either before or after the steps described specifically herein, to add or remove suitable protecting groups in order to ultimately allow synthesis of the compound of this invention. In addition, various synthetic steps may be performed in an alternate sequence or order to give a desired compound. Synthetic chemistry transformations and protecting group methodologies (protection and deprotection) useful in synthesizing applicable the claimed compounds are known in the art and include, for example, those described in R. Larock, *Comprehensive Organic Transformations*, VCH Publishers (1989); T. W. Greene and P. G. M. Wuts,

Protective Groups in Organic Synthesis, 2d. Ed., John Wiley and Sons (1991); L. Fieser and M. Fieser, *Fieser and Fieser's Reagents for Organic Synthesis*, John Wiley and Sons (1994); and L. Paquette, ed., *Encyclopedia of Reagents for Organic Synthesis*, John Wiley and Sons (1995) and subsequent editions thereof.

[0026] A compound of this invention thus synthesized can be further purified by a method such as column chromatography, high pressure liquid chromatography, recrystallization, or sublimation.

[0027] One or more compounds of the invention can be used as a red light emitting material in an electro-luminescence device.

[0028] Typically, an electro-luminescence device is either a two- or a three-layer structured device. A two-layer structured device can include a hole transporting layer and an electron transporting layer, sandwiched between two layers of electrodes. Either the hole transporting layer or the electron transporting layer can function as a luminescent layer, which emits lights (Tang et al., (1989) *J. Appl. Phys.* 65: 3610). Generally, an anode layer, a hole transporting layer, an electron transport layer, and a cathode layer are deposited sequentially in the above order. The anode layer can be formed on a substrate, such as a glass. A three-layer structured device can include a hole transporting layer, a luminescent layer (i.e., light emitting layer), and an electron transporting layer, sandwiched between two layers of electrodes. More specifically, an anode layer, a hole transporting layer, a luminescent layer, an electron transport layer, and a cathode layer are deposited sequentially in the above order. The luminescent layer can be another hole transporting, another electron transporting layer, or a hole blocking layer. Optionally, the electro-luminescence device can include a dopant-containing layer, which can be an electron transporting layer or a luminescent layer.

[0029] Each of the above mentioned layers can be made of various materials, as described in, for example, U.S. Pat. No. 5,698,740. More specifically, a substrate can be made of glass; an anode layer can be a film of a transparent electroconductive material, e.g., indium tin oxide (ITO); a hole transporting layer can be made of 4,4'-bis[N-(1-naphthyl)-N-phenyl-amino]-biphenyl; an optional hole blocking layer can be made of 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP); an electron transporting layer can be made of 1,3,5-tris(N-phenylbenzimidazol-2-yl)benzene (TPBI); and a cathode layer can be made of a metal film, e.g., an alloy of magnesium and silver.

[0030] The fabrication of an electro-luminescence device has been described in, for example, Tang & VanSlyke (1987) *Appl. Phys. Lett.* 51: 913; Tang et al., (1989) *J. Appl. Phys.* 65: 3610, or Kido & Lizumi (1997) *Chem. Lett.* 963. More specifically, each layer may be formed by any film forming method such as vacuum deposition. See U.S. Pat. No. 5,698,740.


[0031] This invention features a device containing a light emitting layer that is made of one of the novel compounds described above. As an example, the device includes an anode layer, a hole transporting/light emitting layer that includes the compounds of this invention; an electron transporting layer; and a cathode layer. The anode, the hole

transporting/light emitting layer, the electron transporting layer, and the cathode are disposed in the above order. Unexpectedly, this device is capable of emitting red light efficiently.

[0032] The specific example below is to be construed as merely illustrative, and not limitative of the remainder of the disclosure in any way whatsoever. Without further elaboration, it is believed that one skilled in the art can, based on the description herein, utilize the present invention to its fullest extent. All publications, including patents, cited herein are hereby incorporated by reference in their entirety.

[0033] Synthesis and Characterization of N-methyl-bis(4-(1-naphthylphenylamino)phenyl)maleimide (NPAMLI)

[0034] NPAMLI was prepared as follows:



[0035] More specifically, 4-bromobenzyl cyanide was oxidized with iodine and hydrolyzed with 3% HCl (aq)/THF to

form bis(4-bromophenyl)maleonitrile (40~50%). See Cook & Linstead (1937) *J. Chem. Soc.* 929. Bis(4-bromophenyl)maleonitrile thus obtained was alkylated with $\text{KotBu}/\text{CH}_3\text{I}$ to afford N-methyl-bis(4-bromophenyl)maleimide (86%). NPAMLI was prepared by palladium catalyzed amination of N-methyl-bis(4-bromophenyl)maleimide (71%), followed by column chromatography and sublimation purification. The synthetic data of the synthesized compounds are listed below:

[0036] Bis(4-bromophenyl)maleimide: ^1H NMR (400 MHz, CDCl_3): δ [ppm] 7.51 (d, 4H, $J=8.7$ Hz), 7.49 (s, 1H), 7.33 (d, 4H, $J=8.7$ Hz). $^{13}\text{C}\{^1\text{H}\}$ NMR (100 MHz, CDCl_3): δ [ppm] 169.4, 136.0, 132.2, 131.3, 126.9, 125.1. FAB-MS: calcd MW, 407.06, $m/e=408$ (M^++1).

[0037] N-Methyl-bis(4-bromophenyl)maleimide: ^1H NMR (400 MHz, CDCl_3): δ [ppm] 7.50 (d, 4H, $J=8.6$ Hz), 7.33 (d, 4H, $J=8.6$ Hz), 3.13 (s, 3H). $^{13}\text{C}\{^1\text{H}\}$ NMR (100 MHz, CDCl_3): δ [ppm] 170.2, 135.5, 132.1, 131.3, 127.2, 124.8, 24.4. FAB-MS: calcd MW, 421.08, $m/e=422$ (M^++1).

[0038] N-Methyl-bis(4-(1-naphthylphenylamino)phenyl)maleimide (NPAMLI): Data of optical, electrochemical, and thermal properties of NPAMLI are summarized in Table 1. ^1H NMR (400 MHz, CDCl_3): δ [ppm] 7.91. (d, 2H, $J=8.2$ Hz), 7.83 (d, 2H, $J=8.3$ Hz), 7.78 (d, 2H, $J=8.5$ Hz), 7.52 (t, 2H, $J=11.9$ Hz), 7.36-7.42 (m, 4H), 7.20-7.25 (m, 6H), 6.94-7.06 (m, 10H), 6.54-6.59 (m, 4H), 3.09 (s, 3H). $^{13}\text{C}\{^1\text{H}\}$ NMR (100 MHz, CDCl_3): δ [ppm] 171.9, 149.9, 147.0, 142.9, 136.1, 133.6, 131.7, 131.4, 129.8, 129.0, 128.1, 127.8, 126.9, 126.8, 124.4, 124.3, 124.0, 121.1, 118.7, 118.7, 24.4. FAB-MS: calcd MW, 697.27, $m/e=697$ (M^+). Anal. Found (calcd) for $\text{C}_{49}\text{H}_{35}\text{N}_3\text{O}_2$: C, 84.21.(84.34), H, 5.04 (5.06), N, 5.99 (6.02).

[0039] Optical, electrochemical, and thermal properties of NPAMLI were also determined. NPAMLI was dissolved in deoxygenated dry dichloromethane, containing 0.1 M tetrabutylammonium perchlorate as electrolyte and a platinum working electrode, as well as a saturated Ag/AgNO_3 reference electrode. Ferrocene was used for potential calibration (all reported potentials are references against ferrocene/ferrocenium, FOC) and (or) reversibility criteria. Nile red ($\Phi_f=0.68$ in 1,4-dioxane) (Sarkar et al. (1994) *Langmuir* 10: 326) was used as the standard for the fluorescence quantum yield determination. Fluorescence and absorption spectra were recorded by fluorescence spectrophotometer (Hitachi F-450) and absorption spectrophotometer (Hewlett-Packard 8453), respectively. Glass transition temperature (T_g) and thermal decomposition temperature (T_d) of NPAMLI were determined by differential scanning calorimetry (DSC) and thermogravimetric analysis (TGA) using a Perkin-Elmer DSC-6 and TGA-7 analyzer systems, respectively. Both thermal analyses were performed with scanning (both heating and cooling) rate at 10 deg/min under nitrogen atmosphere. The temperatures were recorded on the intercept of the slope of thermogram changes (endothermic, exothermic, or weight loss) and the leading baseline as the estimation for on-set T_g and T_d . Redox potentials of NPAMLI were determined by cyclic voltammetry (CV) using Electrochemical Analyzer BAS 100B with scanning rate at 100 mV/s.

[0040] As shown in Table 1, NPAMLI has a fluorescence quantum yield (Φ_f) of 21%, in 1,4-dioxane, which is almost two-folds of that of DCM (i.e., 11%), a commercially available laser dye and red dopant for red OLEDs (Tang et

al. (1989) *Appl. Phys. Lett.* 65: 3610). Further, NPAMLI has a relatively wide full-width at half-maximum (fwhm~94 nm) of emission bands. Due to its long wavelength of emission, nearly half of emission bands (either of PL or EL spectra) locate outside the long wavelength limit of the human vision.

TABLE 1

Optical, electrochemical, and thermal properties of NPAMLI.							
Φ_f (%)	$\lambda_{\text{max}}^{\text{abs}}$ (nm) ^[a]	$\lambda_{\text{max}}^{\text{em}}$ Solution	(nm) ^[a] Solid film	E^{red} (V vs FOC)	E^{oxd} (V vs FOC)	T_g (° C.)	T_d (° C.)
21	501	683	651	-1.68	+0.53	122	419

^[a]Samples were dissolved in chloroform when spectra were recorded. Solid films were prepared by spin-casting from chloroform solution and then vacuum-dried.

[0041] Unexpectedly, NPAMLI showed an amorphous feature. More specifically, it is a fluorophore having a donor (two arylamines) and acceptor (imide), and does not tend to crystallization in solid state. DSC thermograms (>400° C.) of NPAMLI showed that a weak endothermic step-transition was around 120° C., indicating the glass phase transition, and no crystallization or melting was observed. The glass phase of NPAMLI was relatively stable since the endothermic step-transition was still observed even after the sample was repeated heating and cooling. With this amorphous feature, NPAMLI was able to be used as a nondoping red light emitting material with weak or no concentration quenching effect.

[0042] It was also unexpected that NPAMLI was electrochemically stable. Cyclic voltamograms showed NPAMLI's redox process involving one electroreduction and one electrooxidation, both of which were apparently reversible under CV conditions. After quantitation of redox signals on CV, it was concluded that the redox process involved one-electron reduction and two-electron oxidation per molecule of NPAMLI, which indicated that two arylamines are electronically independent and are electrooxidized simultaneously. With this feature, NPAMLI was able to be used as a hole transporting material in addition to a red light emitting material. Further, NPAMLI is thermally robust. Its T_d is about 420° C. estimated by TGA.

[0043] Fabrication of a Device Including NPAMLI as a Red Light Emitting Material and a Hole-Transporting Material

[0044] A trilayer device ITO/NPAMLI/BCP/TPBI/Mg:Ag was fabricated by thermal deposition in a vacuum chamber (ULVAC Cryogenics at a chamber pressure of 10^{-6} Torr-). The substrate was an ITO-coated glass with a sheer resistance of <50 Ω/sq . ITO cleaning included a routine chemical cleaning using detergent and alcohol in sequence, followed by oxygen plasma cleaning. Sequential evaporation of NPAMLI as a hole transporting layer (500 Å) as well as red light emitting layer, BCP as a hole blocking layer (100 Å), and TPBI as an electron transporting layer (400 Å) was performed. A cathode $\text{Mg}_{0.9}\text{Ag}_{0.1}$ alloy was then deposited (50 nm) by co-evaporation and followed by a thick silver capping layer.

[0045] The just-obtained device was tested for current density (I)-voltage (V)-luminance (L) characteristics, EL spectra of the device and PL spectra of NPAMLI, current density dependency of external quantum efficiency, and a CIE (Commission Internationale de l'Eclairage) 1931 color chromaticity diagram of the device. An EL spectrum with an emission maximum of 650 nm was observed, which was almost superimposable on a PL spectrum of NPAMLI. A weak but discernable emission band (around 380 nm) was also observed due to TPBI emission (Tao et al. (2000) *Appl. Phys. Lett.* 77: 933), even though a hole blocking layer of BCP was added to prevent the emission of TPBI. When the EL spectrum was converted into a chromaticity coordinates on a CIE 1931 diagram, an indication of red light emitting from the device was obtained ($x=0.66$, $y=0.32$), which was comparable with ($x=0.64$, $y=0.33$) of National Television System Committee (NTSC) standard red color. This device had the maximum luminance of near 8,000 cd/m² at 15 V; and luminance of more than 300 cd/m² at low current density of 20 mA/cm². It had the maximum external quantum efficiency of 2.4% (corresponding to 1.5 cd/A or 0.9 lm/W) at about 20 mA/cm². The performance of the device is comparable with or better than known red OLEDs, which all include a red dopant-containing layer. As the other red OLEDs, the device showed steady decline in efficiency with increasing current density and barely maintained at 1% of the external quantum efficiency at maximum luminance. See, e.g., Picciolo et al. (2000) *Appl. Phys. Lett.* 78: 2378; and Young et al. (2002) *Appl. Phys. Lett.* 80: 874. Unexpectedly, without using a dopant-containing layer, this device is able to emit red light efficiently, and is easily fabricated.


Other Embodiments

[0046] All of the features disclosed in this specification may be combined in any combination. Each feature disclosed in this specification may be replaced by an alternative feature serving the same, equivalent, or similar purpose. Thus, unless expressly stated otherwise, each feature disclosed is only an example of a generic series of equivalent or similar features.

[0047] From the above description, one skilled in the art can easily ascertain the essential characteristics of the present invention, and without departing from the spirit and scope thereof, can make various changes and modifications of the invention to adapt it to various usages and conditions. Accordingly, other embodiments are also within the scope of the following claims.

What is claimed is:

1. A compound of formula (J):




(I)

wherein

X is O or NR₁; and


each of Y and Z, independently, is



in which each of R₁, R₂, R₃, and R₄, independently, is alkyl, cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; Ar₁ is aralkyl, aryl, or heteroaryl; and Ar₂ is cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; or Ar₁ and Ar₂ taken together is heterocyclyl, aralkyl, or heteroaryl.

2. The compound of claim 1, wherein X is NR₁.

3. The compound of claim 2, wherein each of Y and Z, independently, is



4. The compound of claim 3, wherein Ar₁ is phenyl.

5. The compound of claim 3, wherein Ar₁ is furyl.

6. The compound of claim 3, wherein Ar₁ is thiophenyl.

7. The compound of claim 3, wherein Ar₁ is fluorenyl.

8. The compound of claim 3, wherein Ar₁ is 9,9'-R,R-substituted fluorenyl, in which R is aryl or C₁~C₆ alkyl.

9. The compound of claim 3, wherein Ar₁ is [9,9']spiro-bifluorenyl.

10. The compound of claim 4, wherein one of R₂ and R₃ is phenyl.

11. The compound of claim 10, wherein the other of R₂ and R₃ is naphthyl, and R₁ is CH₃.


12. The compound of claim 2, wherein each of Y and Z, independently, is



13. The compound of claim 12, wherein Ar₁ is carbazolyl.

14. The compound of claim 12, wherein Ar₁ is indolyl.


15. The compound of claim 2, wherein each of Y and Z, independently, is



16. The compound of claim 15, wherein Ar₁ and Ar₂ taken together is pyrido-quinolinyl.

17. The compound of claim 1, wherein X is O.

18. The compound of claim 17, wherein each of Y and Z, independently, is



19. The compound of claim 18, wherein Ar₁ is phenyl.

20. The compound of claim 18, wherein Ar₁ is furyl.

21. The compound of claim 18, wherein Ar₁ is thiophenyl.

22. The compound of claim 18, wherein Ar₁ is fluorenyl.


23. The compound of claim 18, wherein Ar₁ is 9,9'-R,R-substituted fluorenyl, in which R is aryl or C₁-C₆ alkyl.

24. The compound of claim 18, wherein Ar₁ is [9,9']spirobifluorenyl.

25. The compound of claim 19, wherein one of R₂ and R₃ is phenyl.

26. The compound of claim 25, wherein the other of R₂ and R₃ is naphthyl.


27. The compound of claim 17, wherein each of Y and Z, independently, is



28. The compound of claim 27, wherein Ar₁ is carbazolyl.

29. The compound of claim 27, wherein Ar₁ is indolyl.

30. The compound of claim 17, wherein each of Y and Z, independently, is



31. The compound of claim 30, wherein Ar₁ and Ar₂ taken together is pyrido-quinolinyl.

32. A red light emitting electro-luminescence device, comprising:

an anode layer,


a hole transporting layer,

a light emitting layer,

an electron transporting layer, and


a cathode layer,

wherein the anode layer, the hole transporting layer, the light emitting layer, the electron transporting layer, and the cathode layer are disposed in the above order; and the light emitting layer includes a compound of formula (I):



(I)


in which X is O or NR₁; and each of Y and Z, independently, is



each of R₁, R₂, R₃, and R₄, independently, is alkyl, cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; Ar₁ is aralkyl, aryl, or heteroaryl; and Ar₂ is cyclyl, heterocyclyl, aralkyl, aryl, or heteroaryl; or Ar₁ and Ar₂ taken together is heterocyclyl, aralkyl, or heteroaryl.

33. The device of claim 32, wherein X is NR₁.

34. The device of claim 33, wherein each of Y and Z, independently, is



35. The device of claim 34, wherein Ar₁ is phenyl.

36. The device of claim 34, wherein Ar₁ is furyl.

37. The device of claim 34, wherein Ar₁ is thiophenyl.

38. The device of claim 34, wherein Ar₁ is fluorenyl.


39. The device of claim 34, wherein Ar₁ is 9,9'-R,R-substituted fluorenyl, in which R is aryl or C₁-C₆ alkyl.

40. The device of claim 34, wherein Ar₁ is [9,9']spirobifluorenyl.

41. The device of claim 35, wherein one of R₂ and R₃ is phenyl.

42. The device of claim 41, wherein the other of R₂ and R₃ is naphthyl, and R₁ is CH₃.


43. The device of claim 33, wherein each of Y and Z, independently, is



44. The device of claim 43, wherein Ar₁ is carbazolyl.

45. The device of claim 43, wherein Ar₁ is indolyl.


46. The device of claim 33, wherein each of Y and Z, independently, is



47. The device of claim 46, wherein Ar₁ and Ar₂ taken together is pyrido-quinolinyl.

48. The device of claim 32, wherein X is O.

49. The device of claim 48, wherein each of Y and Z, independently, is



50. The device of claim 49, wherein Ar₁ is phenyl.

51. The device of claim 49, wherein Ar₁ is furyl.

52. The device of claim 49, wherein Ar₁ is thiophenyl.

53. The device of claim 49, wherein Ar₁ is fluorenyl.


54. The device of claim 49, wherein Ar₁ is 9,9'-R,R-substituted fluorenyl, in which R is aryl or C₁~C₆ alkyl.

55. The device claim 49, wherein Ar₁ is [9,9']spirobifluorenyl.

56. The device of claim 50, wherein one of R₂ and R₃ is phenyl.

57. The device of claim 56, wherein the other of R₂ and R₃ is naphthyl.


58. The device of claim 48, wherein each of Y and Z, independently, is



59. The device of claim 58, wherein Ar₁ is carbazolyl.

60. The device of claim 58, wherein Ar₁ is indolyl.

61. The device of claim 48, wherein each of Y and Z, independently, is




62. The device of claim 61, wherein Ar₁ and Ar₂ taken together is pyrido-quinolinyl.

* * * * *

专利名称(译)	红光发光材料		
公开(公告)号	US20040013902A1	公开(公告)日	2004-01-22
申请号	US10/191145	申请日	2002-07-09
[标]申请(专利权)人(译)	陈勤TI YEH阿秀CHIH 吴伟CHING 陈李HSIN		
申请(专利权)人(译)	陈金TI YEH修CHIH 吴蔚CHING 陈李鑫		
当前申请(专利权)人(译)	陈金TI YEH修CHIH 吴蔚CHING 陈李鑫		
[标]发明人	CHEN CHIN TI YEH HSIU CHIH WU WEI CHING CHAN LI HSIN		
发明人	CHEN, CHIN-TI YEH, HSIU-CHIH WU, WEI-CHING CHAN, LI-HSIN		
IPC分类号	C09K11/06 H01L51/00 H01L51/30 H01L51/50 H05B33/14		
CPC分类号	C09K11/06 H01L51/0058 H01L51/006 Y10S428/917 H01L51/5012 H05B33/14 H01L51/0072		
其他公开文献	US6884525		
外部链接	Espacenet USPTO		

摘要(译)

本发明的特征在于具有下式的化合物：X为O或NR¹；Y，Z各自独立地为，R¹，R²，R³和R⁴各自独立地为烷基，环基，杂环基，芳烷基，芳基或杂芳基；Ar¹是芳烷基，芳基或杂芳基；Ar²是环基，杂环基，芳烷基，芳基或杂芳基；或Ar¹和Ar²合在一起是杂环基，芳烷基或杂芳基。该化合物可用作电致发光器件中的红色发光材料。



(I)