



US007486016B2

(12) **United States Patent**
Lee

(10) **Patent No.:** **US 7,486,016 B2**
(45) **Date of Patent:** **Feb. 3, 2009**

(54) **ORGANIC ELECTROLUMINESCENT DISPLAY DEVICE**

6,831,407 B2* 12/2004 Cok 313/504
7,038,373 B2* 5/2006 Arnold et al. 313/506
2002/0043928 A1 4/2002 Cho

(75) Inventor: **Kwan-Hee Lee**, Seoul (KR)

(73) Assignee: **Samsung SDI Co., Ltd.**, Suwon-si (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 307 days.

(21) Appl. No.: **10/820,845**

(22) Filed: **Apr. 9, 2004**

(65) **Prior Publication Data**

US 2004/0239238 A1 Dec. 2, 2004

(30) **Foreign Application Priority Data**

May 30, 2003 (KR) 10-2003-0034947

(51) **Int. Cl.**
H05B 33/14 (2006.01)
H01L 51/50 (2006.01)

(52) **U.S. Cl.** **313/506; 313/504; 313/503**

(58) **Field of Classification Search** 313/503-506,
313/512, 498; 428/690

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,758,538 B2* 7/2004 Fujita et al. 313/506

OTHER PUBLICATIONS

Office Action issued on Aug. 3, 2007 by the Chinese Intellectual Property Office for Chinese Patent Application No. 200410045940.9.

* cited by examiner

Primary Examiner—Nimeshkumar D Patel

Assistant Examiner—Anne M Hines

(74) *Attorney, Agent, or Firm*—Stein, McEwen & Bui, LLP

(57) **ABSTRACT**

An organic electroluminescent display device includes an anode electrode formed on a substrate; a buffer pattern formed under the anode electrode having a certain thickness; a pixel define layer for exposing a portion of the anode electrode; an organic thin film layer formed on the anode electrode; and a cathode electrode formed on the substrate. An upper surface of the pixel define layer is at least coplanar with or lower than that of the anode electrode. The thickness of the pixel define layer is at least substantially the same as or less than a sum of thicknesses of the anode electrode and the buffer pattern.

14 Claims, 4 Drawing Sheets




FIG. 1
(PRIOR ART)




FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D





FIG. 3E



ORGANIC ELECTROLUMINESCENT DISPLAY DEVICE

CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of Korean Patent Application No. 2003-34947, filed on May 30, 2003 in the Korean Intellectual Property Office, the disclosure of which is hereby incorporated herein by reference in its entirety.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a flat panel display, more particularly, to an organic electroluminescent display device capable of improving luminance non-uniformity and extending life time by removing a height difference between an anode electrode and a pixel define layer so that a good organic thin film layer is formed, and a fabrication method of the organic electroluminescent display device.

2. Description of the Related Art

FIG. 1 illustrates a cross sectional view of a conventional organic electroluminescent display device. Referring to FIG. 1, anode electrodes **21** are formed on a substrate **20** spaced apart from each other in a certain distance per each pixel, such as R, G and B unit pixels. A pixel define layer **23** is formed on the substrate **20** so that a portion of the anode electrode **21** is exposed to form an opening **22**. The pixel define layer **23** has an organic insulation film, which defines neighboring anode electrodes **21** per each pixel. An R, G or B emitting layer **25** is formed on the opening **22** of the anode electrode **21**. A cathode electrode **27** is formed on the substrate **20** above the layer **25**. Although it is not illustrated on drawing, the emitting layer **25** has at least one layer selected from a hole injection layer, a hole transport layer, a hole barrier layer, an electron injection layer and an electron transport layer.

Important features of the organic electroluminescent display device are a flatness of a conductive material used in the anode electrode **21** and a structure of the pixel define layer **23** having the organic insulation film for determining size of the opening **22** in the anode electrode **21**. Conventionally, the anode electrode **21** is formed by patterning a deposited anode electrode material after depositing an anode electrode material on the substrate **20**. The pixel define layer **23** is subsequently formed by patterning a deposited organic insulation film to expose a portion of the anode electrode **21** after depositing an organic insulation film on the substrate **20**. Therefore, the pixel define layer **23** is formed in such a manner that the pixel define layer **23** has a higher step difference than the anode electrode **21** as shown in FIG. 1.

As described above, the conventional organic electroluminescent display device has problems in that a polymer remains since the pixel define layer **23** is formed by patterning the organic insulation film using a photosensitive photoresist. Furthermore, the conventional organic electroluminescent display device has problems in that a luminance becomes non-uniform and the life time deteriorates since the emitting layer **25** and the cathode electrode **27** are incompletely formed during the process of successively forming the emitting layer **25** and the cathode electrode **27** due to an angle of a part of the pixel define layer **23** having a step difference from the anode electrode **21**. Also, the organic thin film layer deteriorates by outgassing generated from the photoresist. Moreover, the conventional organic electroluminescent display device has had problems due to contact defects generated between the anode electrode **21** and the organic emitting layer

25 since an organic material is not properly transferred at the part of the pixel define layer **23** having the step difference from the anode electrode **21** when the organic emitting layer is formed using a laser induced thermal imaging method.

SUMMARY OF THE INVENTION

An aspect of the invention is to provide an organic electroluminescent display device capable of obtaining uniform luminance and long life time by preventing deterioration of an organic emitting layer and a fabrication method of the organic electroluminescent display device.

It is another aspect to provide an organic electroluminescent display device capable of forming a good organic emitting layer by forming a pixel define layer having a lower step difference than an anode electrode, and a fabrication method of the organic electroluminescent display device.

Additional aspects and/or advantages of the invention will be set forth in part in the description which follows and, in part, will be obvious from the description, or may be learned by practice of the invention.

According to an aspect of the present invention, an organic electroluminescent display device includes a lower electrode formed on a substrate; a pixel define layer for exposing a portion of the lower electrode; an organic thin film layer formed on the lower electrode; and an upper electrode formed on the substrate, wherein the pixel define layer has at least a same or lower step difference above the substrate as a step difference of the lower electrode above the substrate.

According to an aspect of the present invention, the organic electroluminescent display device further comprises a buffer pattern having a certain thickness formed under the lower electrode for smoothing the step difference to be at or above the step difference of the pixel define layer.

According to an aspect of the invention, the buffer pattern comprises an inorganic insulation film including an oxide film or a nitride film, or an organic insulation film including a thermosetting resin or a photosensitive resin, and a thickness of the pixel dividing layer is at least the same as or less than a sum of thicknesses of the lower electrode and the buffer pattern.

According to an aspect of the present invention, the lower electrode comprises a reflective electrode material selected from the group consisting of Al, Al/ITO, Cr, Pt, Au, Ag, Ag/ITO, Al/IZO, Ag/IZO, Pd, Ni and an alloy film thereof, or a transmittive electrode material selected from the group consisting of ITO, IZO and ATO.

According to an aspect of the present invention, an organic electroluminescent display device includes a substrate comprising a plurality of pixel regions; a plurality of lower electrodes formed in the plurality of pixel regions, respectively; a plurality of buffer patterns formed under the plurality of lower electrodes, respectively; a pixel define layer for defining neighboring lower electrodes in the plurality of lower electrodes; organic thin film layers formed on the lower electrodes; and an upper electrode formed on the pixel define layer and the organic thin film layer, wherein the pixel define layer is formed in such a way that an upper surface of the pixel define layer is at least coplanar with or lower than that of the lower electrode by the buffer pattern.

According to an aspect of the present invention, a fabrication method of an organic electroluminescent display device includes forming a buffer pattern for smoothing a step difference on a substrate; forming a lower electrode on the buffer pattern; forming a pixel define layer on the substrate to expose a portion of the pixel electrode; forming an organic thin film layer on the lower electrode; and forming an upper electrode

on the substrate, wherein an upper surface of the pixel define layer is at least coplanar with or lower than that of the lower electrode by the buffer pattern.

According to an aspect of the present invention, the buffer pattern or pixel dividing layer is formed by depositing a thermosetting resin on the substrate and dry etching the thermosetting resin using a photoresist film, or formed by depositing a photosensitive resin on the substrate and patterning the photosensitive resin through an exposure and developing process.

According to an aspect of the present invention, the organic thin film layer is formed using a laser induced thermal imaging or inkjet printing method, and the pixel define layer has a thickness determined by a combined thickness of the buffer pattern and the lower electrodes.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and/or other features and advantages of the present invention will become more apparent to and more readily appreciated by those of ordinary skill in the art by describing in detail embodiments thereof with reference to the accompanying drawings in which:

FIG. 1 is a cross section view illustrating a conventional organic electroluminescent display device;

FIG. 2 is a cross section view illustrating an organic electroluminescent display device according to an embodiment of the present invention; and

FIG. 3A to FIG. 3E are cross sectional views for illustrating a fabrication method of organic electroluminescent display device according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

The present invention will now be described in detail in connection with embodiments with reference to the accompanying drawings. For reference, like reference characters designate corresponding parts throughout several views.

FIG. 2 illustrates a cross sectional view of an organic electroluminescent display device according to an embodiment of the present invention. Referring to FIG. 2, a buffer layer 210 is formed on a transparent insulation substrate 200. A semiconductor layer 220 including source/drain regions 221 and 225 is formed on the buffer layer 210. A gate 240 is formed on a gate insulation film 230. Source/drain electrodes 261 and 265 are formed on an interlayer insulation film 250 and are connected to the source/drain regions 221 and 225 through contact holes 251 and 255. A passivation film 270 is formed above the interlayer insulation film 250 and the source/drain electrodes 261 and 265.

A buffer pattern 280 is formed on the passivation film 270. The buffer pattern 280 smoothes a step difference between an anode electrode 290 above the substrate 200 and a step difference between a pixel define layer 300 and the substrate 200 such that a thickness of the electrode 290 above the substrate 200 is substantially the same as the pixel define layer 300 above the substrate 200. The anode electrode 290 is formed on the buffer pattern 280 in such a way that the anode electrode 290 is connected to one of the source/drain electrodes 281 and 285. For example, the anode electrode 290 is shown connected on the drain electrode 265 through a via hole 275. It is understood that the buffer pattern 280 need not be used in all aspects of the invention.

The pixel define layer 300 defines the anode electrode 290 for each pixel (i.e., R, G and B unit pixels). The pixel define layer 300 is formed on the passivation film 270 between

adjacent anode electrodes 290. According to an aspect of the invention, the pixel define layer 300 is formed in such a way that the pixel define layer 300 has at least the same step difference as the step difference of the anode electrode 290.

According to another aspect of the invention, the pixel define layer 300 has a lower step difference than the step difference of the anode electrode 290. In other words, the upper surface of the anode electrode 290 is substantially coplanar with or is lower than the upper surface of the pixel define layer 300.

An organic thin film layer 310 is formed on the anode electrode 290. A cathode electrode 320 is formed on the thin film layer 310. While not explicitly shown, the organic thin film layer 310 is formed of a R, G, or B emission layer comprising at least one layer selected from a hole injection layer, a hole transport layer, a hole barrier layer, an electron injection layer and an electron transport layer.

In the organic electroluminescent display device according to an embodiment of the present invention, the pixel define layer 300 is formed to have a lower step difference than the step difference of the anode electrode 290, or the pixel define layer 300 has a same step difference as the step difference of the anode electrode 290. Thus, a good organic thin film layer 310 can be formed accordingly due to a superior adhesive force between the organic thin film layer 310 and the anode electrode 290. Therefore, a deterioration of the device due to outgassing from a photoresist film is prevented.

Referring to FIG. 3A to FIG. 3E, a fabrication method of an organic electroluminescent display device of an embodiment of the present invention having the foregoing structure is described as follows. For the sake of simplicity and as the construction of the remaining parts are understood, FIG. 3A to FIG. 3E are limited to an EL device part in the organic electroluminescent display device. Specifically and with reference to FIG. 2, it is understood that the construction of the remaining parts includes forming a buffer layer 210 on a transparent insulation substrate 200 as illustrated in FIG. 2, forming a thin film transistor through an ordinary thin film transistor forming process, and forming a passivation film 270 on the substrate 200 including the thin film transistor.

Referring to FIG. 3A, a buffer material for smoothing a step difference is deposited on the substrate 30 to a thickness of 0.5 to 2.0 μm . The substrate 30 includes the substrate 200, the thin film transistor, and the passivation film 270 shown in FIG. 2. According to aspects of the invention, the buffer material includes an organic insulation film or an inorganic insulation film. Examples of the organic insulation film include a photosensitive material (such as a polyimide based resin, a polyacryl based resin and a polyphenol based resin having superior flatness), or a thermosetting resin such as BCB. Examples of the inorganic insulation film include a nitride film or oxide film. However, it is understood that other suitable materials can be used.

The buffer material is patterned to form a buffer pattern 31. Where the buffer material is a photosensitive material, the buffer pattern 31 is formed by patterning the buffer material through an exposure and developing process. Where the buffer material is a thermosetting resin, the buffer pattern 31 is formed by patterning the buffer material through a dry etching process using a photoresist film. Further, where the buffer material is of the same material as the passivation film 270 of FIG. 2, the buffer pattern 31 can be directly patterned into the passivation film.

Referring to FIG. 3B, an anode electrode material 32 is deposited on a substrate 30 including the buffer pattern 31. According to an aspect of the invention, the anode electrode material 32 is formed to a thickness of 40 to 200 nm. However, it is understood that other thicknesses can be used.

Where the organic electroluminescent display device is a front emission type organic electroluminescent display device, the anode electrode material **32** is a reflective electrode material. Where the organic electroluminescent display device is a rear emission type organic electroluminescent display, the anode electrode material **32** is a transmissive electrode material. In a front emission type structure, the anode electrode **33** may use a single layer of the reflective electrode material, or the anode electrode **33** may use a multilayer in which a bi-layer or triple-layer transparent conductive material is formed on the reflective electrode material. However, it is understood that other materials and constructions can be used.

The reflective electrode material for the anode electrode includes, but is not limited to, Al, Al/ITO, Cr, Pt, Au, Ag, Ag/ITO, Al/IZO, Ag/IZO, Pd, Ni or alloy film thereof. According to an aspect of the invention, the transmissive electrode material for the anode electrode includes, but is not limited to, Indium Tin Oxide (ITO), Indium Zinc Oxide (IZO), or Antimony Tin Oxide (ATO).

Referring to FIG. 3C, adjacent pairs of the anode electrodes **33** are separated from each other and are arranged per pixel. The anode electrodes **33** are formed by etching the anode electrode material **32**. The anode electrode **33** is formed in such a way that the anode electrode **33** has a step difference that is as much as a thickness of the buffer pattern **31**.

Referring to FIG. 3D, an organic insulation film **34**, such as the thermosetting resin or the photosensitive resin, is formed on the substrate **301**. A thickness of the organic insulation film **34** is at least the same as or lower than a sum of the thickness of the buffer pattern **31** and the anode electrodes **33**. As shown, the thickness of the organic insulation film **34** is greater than the sum of the thickness of the buffer pattern **31** and the anode electrodes **33**.

Referring to FIG. 3E, a pixel define layer **35** is formed on the substrate between the anode electrodes **33** by patterning the organic insulation film **34** in the same method as a method for forming the buffer pattern **31**. The pixel define layer **35** has at least the same step difference as or a lower step difference than the anode electrode **33** by the buffer pattern **31** so that the pixel define layer **35** defines neighboring pixels. However, it is understood that, where the thickness of the organic insulation film **34** is less than or equal to the sum of the thickness of the buffer pattern **31** and the anode electrodes **33**, a patterning operation need not be performed.

Subsequently, an organic electroluminescent display device of an embodiment of the present invention is formed by forming an organic thin film layer **310** on the anode electrode **33** using a laser induced thermal imaging method or an inkjet method and forming a cathode electrode **320** on the organic thin film layer **310** as illustrated in FIG. 2.

According to an embodiment of the present invention as described in the above, an organic emission layer having good film quality is formed by forming the anode electrode using the buffer pattern for smoothing a step difference so that the anode electrode has no step difference with the pixel define layer in an organic electroluminescent display device. Therefore, luminance uniformity of device is improved, and the lifetime of the device is extended.

While the invention has been particularly shown and described with reference to embodiments thereof, it will be understood by those skilled in the art that the foregoing and other changes in form and details may be made therein without departing from the spirit and scope of the invention and equivalents thereof.

What is claimed is:

1. An organic electroluminescent display device comprising:
 - a substrate;
 - a lower electrode formed on the substrate, the lower electrode having a substantially planar upper surface at a first step difference above the substrate;
 - a pixel define layer formed on the substrate and covering one portion of the lower electrode while exposing another portion of the lower electrode, the portion of the pixel define layer, which covers the one portion of the lower electrode, having a planar upper surface at a second step difference above the substrate;
 - an organic thin film layer formed on the lower electrode; and
 - an upper electrode formed on the organic thin film layer, wherein the second step difference of the pixel define layer is not greater than the first step difference of the lower electrode.
2. The organic electroluminescent display device according to claim 1, wherein the pixel define layer comprises a thermosetting resin or a photosensitive resin.
3. The organic electroluminescent display device according to claim 1, further comprising a buffer pattern between the lower electrode and the substrate and which has a predetermined thickness sufficient to reduce a difference between the first and second step differences.
4. The organic electroluminescent display device according to claim 3, wherein a thickness of the pixel define layer above the substrate is substantially the same as or less than a sum of thicknesses of the lower electrode and the buffer pattern above the substrate.
5. The organic electroluminescent display device according to claim 3, wherein the buffer pattern includes an inorganic insulation film comprising an oxide film or a nitride film.
6. The organic electroluminescent display device according to claim 3, wherein the buffer pattern comprises an organic insulation film comprising a thermosetting resin or a photosensitive resin.
7. The organic electroluminescent display device according to claim 1, wherein the lower electrode comprises a reflective electrode material, a transmissive electrode material, or a stacked layer of the reflective electrode material and the transmissive electrode material.
8. The organic electroluminescent display device according to claim 7, wherein the lower electrode comprises the reflective electrode material selected from the group consisting of Al, Al/ITO, Cr, Pt, Au, Ag, Ag/ITO, Al/IZO, Ag/IZO, Pd, Ni and an alloy film thereof.
9. The organic electroluminescent display device according to claim 7, wherein the lower electrode comprises the transmissive electrode material selected from the group consisting of ITO, IZO and ATO.
10. The organic electroluminescent display device according to claim 1, wherein the second step difference of the pixel define layer is less than or substantially equal to the first step difference of the lower electrode.
11. An organic electroluminescent display device comprising:
 - a substrate;
 - a lower electrode formed on the substrate, the lower electrode having a substantially planar upper surface at a first step difference above the substrate;
 - a pixel define layer formed on the substrate and covering one portion of the lower electrode while exposing

7

another portion of the lower electrode, the pixel define layer having an upper surface at a second step difference above the substrate;
 an organic thin film layer formed on the lower electrode;
 an upper electrode formed on the organic thin film layer;
 and
 a buffer pattern between the lower electrode and the substrate and which has a predetermined thickness sufficient to reduce a difference between the first and second step differences,
 wherein the second step difference of the pixel define layer is less than or substantially equal to the first step difference of the lower electrode.

8

12. The organic electroluminescent display device according to claim 11, wherein a thickness of the pixel define layer above the substrate is substantially the same as or less than a sum of thicknesses of the lower electrode and the buffer pattern above the substrate.

13. The organic electroluminescent display device according to claim 11, wherein the buffer pattern includes an inorganic insulation film comprising an oxide film or a nitride film.

14. The organic electroluminescent display device according to claim 11, wherein the buffer pattern comprises an organic insulation film comprising a thermosetting resin or a photosensitive resin.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 7,486,016 B2
APPLICATION NO. : 10/820845
DATED : February 3, 2009
INVENTOR(S) : Kwan-Hee Lee et al.


Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 6, line 6, delete “substantially”.

Signed and Sealed this

Twenty-ninth Day of September, 2009

A handwritten signature in black ink that reads "David J. Kappos". The signature is written in a cursive style with a large initial 'D' and 'K'.

David J. Kappos
Director of the United States Patent and Trademark Office

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 7,486,016 B2
APPLICATION NO. : 10/820845
DATED : February 3, 2009
INVENTOR(S) : Kwan-Hee Lee et al.


Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Title Page, Item (73) Assignee, change "Samsung SDI Co., Ltd., Suwon-si (KR)" to
--Samsung Mobile Display Co., Ltd., Suwon-si (KR)--.

Signed and Sealed this

Sixth Day of April, 2010

A handwritten signature in black ink that reads "David J. Kappos". The signature is written in a cursive style with a large initial "D" and "K".

David J. Kappos
Director of the United States Patent and Trademark Office

专利名称(译)	有机电致发光显示装置		
公开(公告)号	US7486016	公开(公告)日	2009-02-03
申请号	US10/820845	申请日	2004-04-09
申请(专利权)人(译)	三星SDI CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE KWAN HEE		
发明人	LEE, KWAN-HEE		
IPC分类号	H05B33/14 H01L51/50 H05B33/10 H01L27/32 H01L51/52 H05B33/00 H05B33/12 H05B33/22 H05B33/26		
CPC分类号	H01L27/3246 H01L27/3283 H01L51/5206 H01L27/3258 H01L51/5218		
优先权	1020030034947 2003-05-30 KR		
其他公开文献	US20040239238A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机电致发光显示装置，包括形成在基板上的阳极；在阳极下形成的具有一定厚度的缓冲图案；像素限定层，用于暴露阳极电极的一部分；在阳极上形成有机薄膜层；以及在基板上形成的阴极电极。像素限定层的上表面至少与阳极电极的上表面共面或低于阳极电极的上表面。像素限定层的厚度至少基本上等于或小于阳极电极和缓冲图案的厚度之和。

