



US007728509B2

(12) **United States Patent**
Bae et al.

(10) **Patent No.:** **US 7,728,509 B2**
(45) **Date of Patent:** **Jun. 1, 2010**

(54) **ORGANIC ELECTROLUMINESCENT
DISPLAY DEVICE AND METHOD OF
FABRICATING THE SAME**

(75) Inventors: **Sung-Joon Bae**, Gyeonggi-do (KR);
Jin-Ook Kim, Seoul (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 790 days.

(21) Appl. No.: **11/024,015**

(22) Filed: **Dec. 29, 2004**

(65) **Prior Publication Data**

US 2005/0162061 A1 Jul. 28, 2005

(30) **Foreign Application Priority Data**

Dec. 30, 2003 (KR) 10-2003-0100668

(51) **Int. Cl.**
H05B 33/14 (2006.01)

(52) **U.S. Cl.** **313/504**; 313/509

(58) **Field of Classification Search** 313/498–512;
315/169.3; 345/36, 45, 76
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,175,345 B1 1/2001 Kuribayashi et al.
6,548,961 B2 4/2003 Barth et al.
7,199,516 B2 4/2007 Seo et al.
2001/0026125 A1* 10/2001 Yamazaki et al. 313/505
2002/0158577 A1 10/2002 Shimoda et al.

2004/0017162 A1* 1/2004 Sato et al. 315/169.3

FOREIGN PATENT DOCUMENTS

CN	1434669	8/2003
JP	2001-177509	4/2001
KR	2002-0047889	6/2002
KR	2003-0017246	3/2003
KR	403291 B *	10/2003
KR	2003-0086167	11/2003
KR	2004-0079476	9/2004
WO	WO-02/078101	10/2002

OTHER PUBLICATIONS

Y.S. Kim, et al. "Fabricating of Three-Dimensional Microstructures
by Soft Molding." *American Institute of Physics*. vol. 79, No. 14, Oct.
2001, pp. 2285-2287.

* cited by examiner

Primary Examiner—Nimeshkumar D Patel

Assistant Examiner—Christopher M Raabe

(74) *Attorney, Agent, or Firm*—Morgan Lewis & Bockius
LLP

(57) **ABSTRACT**

An organic electroluminescent display device comprises a substrate, including a pixel region and a non-pixel region at a boundary of the pixel region; a first electrode on the substrate in the pixel region; a separator over the first electrode, the separator located in the non-pixel region, the separator including a first portion having a first width and a second portion having a second width smaller than the first width, the first portion overlapping edges of the first electrode, and the second portion within the non-pixel region; an organic electroluminescent layer over the separator in the pixel region surrounded by the separator; and a second electrode on an entire surface of the organic electroluminescent layer and the separator.

4 Claims, 14 Drawing Sheets




FIG. 1

Related Art




FIG. 2

Related Art




FIG. 4A

Related Art




FIG. 4B

Related Art




FIG. 5

Related Art




FIG. 6A

Related Art




FIG. 6B

Related Art




FIG. 6C

Related Art




FIG. 6D

Related Art




FIG. 6E

Related Art




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D




FIG. 9




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 10D






FIG. 11





ORGANIC ELECTROLUMINESCENT DISPLAY DEVICE AND METHOD OF FABRICATING THE SAME

The present invention claims the benefit of Korean Patent Application No. 2003-0100668, filed in Korea on Dec. 30, 2003, which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a display device, and more particularly, an organic electroluminescent display device and a method of fabricating the same.

2. Discussion of the Related Art

Generally, an organic electroluminescent display (OLED) device emits light by injecting electrons from a cathode and holes from an anode into an emission layer, combining the electrons with the holes, generating excitons, and transitioning the excitons from an excited state to a ground state. In contrast to a liquid crystal display (LCD) device, an OLED device does not require an additional light source because the OLED device transmits light emitted by the transition of the excitons between states. Accordingly, the OLED device is lighter and smaller than a comparable liquid crystal display (LCD) device. The OLED device has other desirable characteristics, such as low power consumption, superior brightness and a fast response time. Because of these advantageous characteristics, the OLED device is regarded as a promising candidate for use in various next-generation consumer electronic applications, such as cellular phones, car navigation systems (CNS), personal digital assistants (PDA), camcorders and palmtop computers. Moreover, an OLED device is much cheaper to produce than an LCD device because the fabrication process is relatively simpler for the OLED device than the LCD device and has fewer processing steps. There are two different types of OLED devices: passive matrix and active matrix.

FIG. 1 is a cross-sectional view of an organic electroluminescent device according to a related art. Referring to FIG. 1, an OLED device 10 includes a first substrate 12 and a second substrate 28 facing and spaced apart from each other. An array element layer 14 is formed on an inner surface of the first substrate 12. The array element layer 14 includes including a thin film transistor (TFT) T. A first electrode 46, an organic electroluminescent (EL) layer 50, and a second electrode 52 are sequentially formed over the array element layer 14. The organic EL layer 50 may separately display red, green, and blue colors for each pixel region P.

The first substrate 12 and the second substrate 28 are attached with a sealant 26. The OLED device 10 is encapsulated by attaching the first substrate 12 to the second substrate 28. A moisture absorbent desiccant 22 is positioned on the second substrate 28. The moisture absorbent desiccant 22 eliminates moisture and oxygen that may penetrate the encapsulated organic EL layer 50. More particularly, a portion of the second substrate 28 is etched and the moisture absorbent desiccant 22 is placed in the etched portion and affixed by a holding element 25. Although not shown, the organic EL layer may be divided into a plurality of pixel regions by a separator.

FIG. 2 is a plan view of a separator in an organic electroluminescent device according to the related art. Referring to FIG. 2, a first electrode 46 and an organic EL layer 50 (shown in FIG. 1) are located in the pixel region P. A second electrode 52 (shown in FIG. 1) is formed on an entire surface of the first substrate 12. For example, when the first electrode 46 acts as

an anode, it is formed by depositing and patterning a conductive material having a high work-function, such as indium tin oxide (ITO), through a vacuum apparatus, such as a sputtering chamber. In addition, when the organic EL layer 50 is made of a polymeric material, it is formed by a printing process, for example ink-jet printing. On the other hand, when the organic EL layer 50 is made of a monomeric material, it is formed by a deposition process.

A separator SP is required to divide the organic EL layer 50 into a plurality of pixel regions P in an independent emitting type OLED device using a polymeric organic EL material. The separator SP can prevent mixing between different colors of the organic EL layers 50. Although not shown, the buffer layer 48 and the separator SP correspond to portions of the gate, data and power lines.

The organic EL layer 50 includes red, green and blue EL layers (not shown) formed in the pixel regions P in repeating order after forming the separator SP at a boundary of the pixel regions P and a buffer layer 48 on the separator SP. The buffer layer 48 is located at the boundary of the pixel regions P including a portion overlapping edges of the first electrode 46 to prevent any electrical contact between the first electrode 46 and the second electrode 52 (shown in FIG. 1) at the corner of the separator SP. Thus, the buffer layer 48 is larger than the separator SP.

FIG. 3 is a plan view of an array substrate of an organic electroluminescent device for one pixel region according to the related art. In general, an array element layer 14 (shown in FIG. 1) of an OLED device 10 includes a switching thin film transistor T_s , a driving thin film transistor T_D and a storage capacitor C_{ST} . A first substrate 12 is made of a transparent insulating substrate, such as glass and plastic. A gate line GL and a data line DL cross each other are formed on the first substrate 12. The gate line GL and the data line DL define a pixel region. An insulating layer (not shown) is interposed between the gate line GL and the data line DL. A power line PL crosses the gate line GL, in parallel with and spaced apart from the data line DL.

The switching thin film transistor T_s includes a switching gate electrode 26, a switching active layer 16, a switching source electrode 34, and a switching drain electrode 36. Similarly, the driving thin film transistor T_D includes a driving gate electrode 28, a driving active layer 18, a driving source electrode 38, and a driving drain electrode 40. The switching gate electrode 26 is connected to the gate line GL and the switching source electrode 34 is connected to the data line DL. The switching drain electrode 36 is connected to the driving gate electrode 28 via a first contact hole 69 that exposes a portion of the driving gate electrode 28. The driving source electrode 38 is connected to the power line PL via a second contact hole 57 that exposes a portion of the power line PL. Moreover, a first electrode 46 is connected to the driving drain electrode 40 via the third contact hole 59. The power line PL overlaps a first capacitor electrode 20 with the insulating layer interposed therebetween to form the storage capacitor C_{ST} .

Although not shown, the separator SP (shown in FIG. 2), which is formed in a portion corresponding to the data line DL and the power line PL, can divide the organic EL layer emitting a specific light into a plurality of pixel regions. Further, the buffer layer 48 (shown in FIG. 2) is formed between the first electrode 46 and the separator SP and is located in the non-pixel region at a boundary of the pixel region P including the portion overlapping edges of the first electrode 46.

FIGS. 4A, 4B and 5 are cross-sectional views taken along lines IVA-IVA, IVB-IVB and V-V of FIG. 3, respectively. Referring to FIGS. 4A, 4B and 5, a switching thin film tran-

sistor T_S and a driving thin film transistor T_D are formed on a first substrate **12** including a switching region S and a driving region D within a pixel region P, respectively. The switching thin film transistor T_S includes a switching active layer **16**, a switching gate electrode **26**, a switching source electrode **34**, and a switching drain electrode **36**. Similarly, the driving thin film transistor T_D includes a driving active layer **18**, a driving gate electrode **28**, a driving source electrode **38**, and a driving drain electrode **40**.

Specifically, although not shown, the switching gate electrode **26** is connected to the gate line GL and the switching source electrode **34** is connected to the data line DL. The switching drain electrode **36** is connected to the driving gate electrode **28**. The driving source electrode **38** is connected to the power line PL, and the driving drain electrode **40** is connected to a first electrode **46** in the pixel region P. A buffer layer **48** is formed on the first electrode **46** at a boundary of the pixel region P corresponding to the data line DL and the power line PL, as shown in FIG. 5. The buffer layer **48** overlaps edges of the first electrode **46**. A separator SP is formed on the buffer layer **48** within the boundary of the pixel region P. An organic EL layer **50** is formed on the first electrode **46** in the pixel region P surrounded by the separator SP. A second electrode **52** is formed on the entire surface of the organic EL layer **50** and the separator SP. However, at least two mask processes are required to form the buffer layer **48** and the separator SP for the OLED device.

FIGS. 6A to 6E are cross-sectional views of a fabricating process of an organic electroluminescent diode substrate for an organic electroluminescent device according to the related art. Referring to FIG. 6A, a first electrode **46** is formed on a first substrate **12** including a pixel region P. The first electrode **46** is located in the pixel region P. An inorganic material layer **47** is formed by depositing an inorganic material, such as silicon nitride (SiNx), on the entire surface of the first electrode **46** and the first substrate **12**. A photoresist layer **80** is formed by coating photoresist on the inorganic insulating material layer **47**.

Referring to FIG. 6B, a photoresist pattern **82** is formed by patterning the photoresist layer **80** on the inorganic material layer **47** at the boundary of the pixel region P including a portion overlapping edges of the first electrode **46**. Referring to FIG. 6C, a buffer layer **48** is formed by etching a portion of the inorganic material layer **47** (shown in FIG. 6B) uncovered by the photoresist pattern **82** (shown in FIG. 6B). Then, the buffer layer **48** is formed using a first mask process, which includes exposing, developing and etching. An organic layer **90** is formed by coating an organic insulating material on the entire surface of the buffer layer **48** and the first electrode **46**.

Referring to FIG. 6D, a separator SP is formed by patterning the organic material layer **90** (shown in FIG. 6C) through a second mask process similar to the first mask process. The separator SP is located within the boundary of the pixel region P but the buffer layer **48** overlaps the edges of neighboring pixel regions P to prevent the first electrode **46** and a second electrode that will be formed later from electrically contacting each other. Thus, although not shown, a width of the buffer layer **48** is larger than a width of the separator SP. When an organic EL layer is formed by coating a polymeric material, the separator SP should have a height of more than 1 micrometer. Thus, a portion of the organic EL layer near to the separator SP becomes thicker. Accordingly, the separator SP should have a predetermined side gap K with the buffer layer **48** toward the first electrode **46**.

Referring to FIG. 6E, an organic EL layer **50** is formed on the first electrode **46** in the pixel region P surrounded by the separator SP. A second electrode **52** is formed on the entire

surface of the organic EL layer **50** and the separator SP. The second electrode **52** acts as a cathode and comprises a metallic material having a low work-function, such as calcium (Ca), aluminum (Al) and magnesium (Mg) and lithium fluoride/aluminum (LiF/Al). In addition, when the organic EL layer **50** is formed by coating, no mask process is required for forming the organic EL layer **50**.

At least two mask processes are required to form the buffer layer **48** and the separator SP. As a result, several mask processes are required for the entire manufacturing process. The defective fraction increases with the number of mask processes. Moreover, production yield decreases and production cost increases because of processing delay, thus weakening a competitive pricing of the EL device.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to an OLED device and a method of fabricating the same that substantially obviate one or more of the problems due to limitations and disadvantages of the related art.

An object of the present invention is to provide an OLED device that can reduce fabrication processing time and cost.

Another object of the present invention is to provide a method of fabricating an OLED device that can reduce fabrication processing time and cost.

Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, a method of fabricating an organic electroluminescent display device comprises forming a first electrode in a pixel region of a substrate, the substrate including a non-pixel region at a boundary of the pixel region; forming a resin solution layer by coating a resin solution on the first electrode; pressing a mold on the resin solution layer, the mold having a recessed portion alternating with a protruding portion, the recessed portion having the same height as the protruding portion, the recessed portion and the protruding portion facing the resin solution layer, a first width of the recessed portion near to the resin solution layer being larger than a second width of the recessed portion away from the resin solution layer; solidifying the resin solution layer by heating; removing the mold from the solidified resin solution layer forming a separator in the non-pixel region on the substrate, the separator having a first portion having the first width and a second portion having the second width, the first portion overlapping edges of the first electrode, and the second portion within the non-pixel region; forming an organic electroluminescent layer on the first electrode in the pixel region surrounded by the separator; and forming a second electrode on the organic electroluminescent layer and the separator.

In another aspect, a method of fabricating an organic electroluminescent display device comprises forming a first electrode in a pixel region of a substrate, the substrate including a non-pixel region at a boundary of the pixel region; forming a resin solution layer by coating a resin solution on the first electrode; pressing a mold on the resin solution layer, the mold having a recessed portion alternating with a protruding portion, the recessed portion having the same height as the protruding portion, the recessed portion and the protruding

5

portion facing the resin solution layer, the recessed portion and the protruding portion having respective square shapes; solidifying the resin solution layer by sequentially heating at two different temperatures including a first temperature smaller or equal to a boiling point of the resin solution and a second temperature higher than the first temperature; removing the mold from the solidified resin solution layer forming a separator in the non-pixel region on the substrate, the separator having a first portion having a first width and a second portion having a second width smaller than the first width, the first portion overlapping edges of the first electrode, and the second portion within the non-pixel region; forming an organic electroluminescent layer in the pixel region surrounded by the separator; and forming a second electrode on the organic electroluminescent layer and the separator.

In another aspect, a method of fabricating an organic electroluminescent device comprises forming a first electrode on the entire surface of a first substrate including a pixel region and a non-pixel region at a boundary of the pixel region; forming a resin solution layer by coating a resin solution on the entire surface of the first electrode; pressing a mold on the resin solution layer under a predetermined pressure, the mold including a recessed portion alternating with a protruding portion, the recessed portion having the same height as the protruding portion, the recessed portion and the protruding portion of the mold facing the resin solution layer, a width of the recessed portion gradually increasing toward the substrate and a width of the protruding portion gradually decreasing toward the substrate; solidifying the resin solution layer by heating; removing the mold from the solidified resin solution layer forming a separator in the non-pixel region on the substrate, the separator having a first portion having a first width and a second portion having a second width smaller than the first width, the first portion closer to the substrate than the second portion, a cross-sectional of the second portion decreasing gradually from both end sides thereof toward a middle part thereof; and sequentially forming an organic electroluminescent layer and a second electrode on the first electrode, the organic electroluminescent layer and the second electrode divided into a region corresponding to the pixel region by the separator.

In another aspect, an organic electroluminescent display device comprises a substrate, including a pixel region and a non-pixel region at a boundary of the pixel region; a first electrode on the substrate in the pixel region; a separator over the first electrode, the separator located in the non-pixel region, the separator including a first portion having a first width and a second portion having a second width smaller than the first width, the first portion overlapping edges of the first electrode, and the second portion within the non-pixel region; an organic electroluminescent layer over the separator in the pixel region surrounded by the separator; and a second electrode on the entire surface of the organic electroluminescent layer and the separator.

In another aspect, an organic electroluminescent display device comprises a first substrate, including a pixel region and a non-pixel region at a boundary of the pixel region; a first electrode on the entire surface of the first substrate; a separator over the first electrode in the non-pixel region, the separator having a first portion having a first width and a second portion having a second width smaller than the first width, a cross-sectional of the second portion decreasing gradually from both end sides thereof toward a middle part thereof; an organic electroluminescent layer over the separator, the organic electroluminescent layer in the pixel region; and a

6

second electrode on the organic electroluminescent layer, the second electrode corresponding to the organic electroluminescent layer.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention.

FIG. 1 is a cross-sectional view of an organic electroluminescent device according to a related art.

FIG. 2 is a plan view of a separator in an organic electroluminescent device according to the related art.

FIG. 3 is a plan view of an array substrate of an organic electroluminescent device for one pixel region according to the related art.

FIGS. 4A, 4B and 5 are cross-sectional views taken along lines IVA-IVA, IVB-IVB and V-V of FIG. 3, respectively.

FIGS. 6A to 6E are cross-sectional views of a fabricating process of an organic electroluminescent diode substrate for an organic electroluminescent device according to the related art.

FIG. 7A is a cross-sectional view of the formation of a pixel electrode on a substrate in a process of fabricating an organic electroluminescent device according to a first embodiment of the present invention.

FIG. 7B is a cross-sectional view of the molding of a resin layer on a substrate in a process of fabricating an organic electroluminescent device according to the first embodiment of the present invention.

FIG. 7C is a cross-sectional view of the formation of a separator on a substrate in a process of fabricating an organic electroluminescent device according to the first embodiment of the present invention.

FIG. 7D is a cross-sectional view of the formation of an organic electroluminescent layer on a substrate in a process of fabricating an organic electroluminescent device according to the first embodiment of the present invention.

FIG. 8A is a cross-sectional view of the formation of a pixel electrode on a substrate in a process of fabricating an organic electroluminescent device according to a second embodiment of the present invention.

FIG. 8B is a cross-sectional view of the molding of a resin layer on a substrate in a process of fabricating an organic electroluminescent device according to the second embodiment of the present invention.

FIG. 8C is a cross-sectional view of the formation of a separator on a substrate in a process of fabricating an organic electroluminescent device according to the second embodiment of the present invention.

FIG. 8D is a cross-sectional view of the formation of an organic electroluminescent layer on a substrate in a process of fabricating an organic electroluminescent device according to the second embodiment of the present invention.

FIG. 9 is a cross-sectional view of an exemplary dual-panel type organic electroluminescent device according to a third embodiment of the present invention.

FIG. 10A is a cross-sectional view of the formation of a full-color element layer on a substrate in a process of fabricating an organic electroluminescent diode substrate for a

dual-panel type organic electroluminescent device according to the third embodiment of the present invention.

FIG. 10B is a cross-sectional view of the molding of a resin layer on an electrode in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention.

FIG. 10C is a cross-sectional view of the formation of a separator on an electrode in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention.

FIG. 10D is a cross-sectional view of the formation of an organic electroluminescent layer on an electrode in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention.

FIG. 11 is a scanning electron microscopic view of an exemplary separator manufactured in accordance with the third embodiment of the present invention.

FIGS. 12A and 12B are cross-sectional views of an array substrate for a dual-panel type organic electroluminescent device according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

FIG. 7A is a cross-sectional view of the formation of a pixel electrode on a substrate in a process of fabricating an organic electroluminescent device according to a first embodiment of the present invention. Referring to FIG. 7A, a substrate 100 includes a pixel region P, and a non-pixel region NP at a boundary of the pixel region P. A first electrode 102 is formed on the substrate 100. The first electrode 102 is located in the pixel region P. For example, when the first electrode 102 acts as an anode, it is made of a conductive material having a high work-function, such as indium tin oxide (ITO). Then, a resin solution layer 104 is formed on the entire surface of the substrate 100 including the first electrode 102 by coating the entire surface of the substrate 100 and the first electrode 102 with a resin solution. The coating process may be performed by dipping the substrate in the resin solution. Alternatively, the coating process may be performed by dropping the resin solution on the substrate. The resin solution may include a transparent organic material, such as acrylic resin.

FIG. 7B is a cross-sectional view of the molding of a resin layer on a substrate in a process of fabricating an organic electroluminescent device according to the first embodiment of the present invention. Referring to FIG. 7B, a mold M1 is prepared. The mold M1 has a recessed portion RP alternating with a protruding portion PP. The recessed portion RP has the same height H1 as the protruding portion PP. The mold M1 is slightly pressed on the resin solution layer 104, with the recessed portion RP and the protruding portion PP of the mold M1 facing the resin solution layer 104. The recessed portion RP has a first portion having a first width W1 and a second portion having a second width W2. The first portion is closer to the resin solution layer 104 than the second portion. The second width W2 is smaller than the first width W1. A portion of the resin solution layer 104 corresponding to the recessed portion RP of the mold M1 become a separator at a later stage in the manufacturing process.

In an embodiment of the invention, recessed and protruding patterns for the mold M1 maybe formed using a soft

molding method. In this case, the mold M1 is formed by filling an elastomeric in a predetermined mold frame. For example, the elastomeric includes one of polydimethylsiloxane (PDMS), polyurethane and polyimide.

When the mold M1 is slightly pressed against the resin solution layer 104, a portion of the resin solution layer 104 contacting the protruding portion PP of the mold M1 is moved toward the recessed portion RP due to a repulsion between the mold M1 and the resin solution layer 104. Thus, the portion of the resin solution layer 104 contacting the protruding portion PP of the mold M1 fills the inner part of the recessed portion RP of the mold M1. Then, the resin solution layer 104 is solidified by heating it. Heating may be performed at a temperature higher than a boiling point and a transition temperature of the resin solution.

FIG. 7C is a cross-sectional view of the formation of a separator on a substrate in a process of fabricating an organic electroluminescent device according to the first embodiment of the present invention. Referring to FIG. 7C, the mold M1 (shown in FIG. 7B) is removed, leaving the solidified molded resin solution layer on the substrate 100. The solidified molded resin solution layer forms a separator 106 on the substrate 100. The separator 106 has a first portion BB having the first width W1 and a second portion SS having the second width W2. The first portion BB of the separator 106 overlaps edges of the first electrode 102. The second portion SS of the separator 106 is located within the non-pixel region P. The first portion BB acts as a buffer layer and the second portion SS acts as a substantial separator means.

The first width W1 of the first portion BB is larger than the second width W2 of the second portion SS. A side gap K between the first width W1 and the second width W2 is between 2 micrometers and 10 micrometers, a thickness KK of the first portion BB of the separator 106 is less than about 300 nanometers. A side of the second portion SS is perpendicular to a surface of the substrate 100.

FIG. 7D is a cross-sectional view of the formation of an organic electroluminescent layer on a substrate in a process of fabricating an organic electroluminescent device according to the first embodiment of the present invention. Referring to FIG. 7D, at least one organic electroluminescent (EL) layer 108 is formed on the first electrode 102 in the pixel region P surrounded by the separator 106. Forming the organic EL layer 108 includes forming red, green and blue EL layers (not shown) in the pixel regions P in repeating orders. The at least one organic EL layer 108 may be a single layer or may include multiple layers. When the at least one organic EL layer 108 includes multiple layers and the first electrode 102 acts as the anode, the at least one organic EL layer 108 includes a hole transporting layer 108a on the first electrode 102, an emitting layer 108b and an electron transporting layer 108c on a later-formed second electrode.

A second electrode 110 is formed on the entire surface of the organic EL layer 108 and the separator 106. When the second electrode 110 acts as a cathode, it includes a metallic material, such as calcium (Ca), aluminum (Al) and magnesium (Mg) and lithium fluoride/aluminum (LiF/Al). The first electrode 102, the organic EL layer 108 and the second electrode 110 form an organic EL diode D_{EL}.

FIG. 8A is a cross-sectional view of the formation of a pixel electrode on a substrate in a process of fabricating an organic electroluminescent device according to a second embodiment of the present invention. Referring to FIG. 8A, a substrate 200 includes a pixel region P, and a non-pixel region NP at a boundary of the pixel region P. A first electrode 202 is formed on the substrate 200. The first electrode 202 is located in the pixel region P. Then, a resin solution is coated on the entire

surface of the substrate **200** including the first electrode **202** to form a resin solution layer **204**. The resin solution may include a transparent organic material, such as acrylic resin.

FIG. **8B** is a cross-sectional view of the molding of a resin layer on a substrate in a process of fabricating an organic electroluminescent device according to the second embodiment of the present invention. Referring to FIG. **8B**, a mold **M2** is prepared. The mold **M2** has a recessed portion **RP** alternating with a protruding portion **PP**. The recessed portion **RP** has the same height **H2** as the protruding portion **PP**. The recessed portion **RP** and the protruding portion **PP** may each have a square shape. The mold **M2** is slightly pressed on the resin solution layer **204**.

When the mold **M2** is slightly pressed against the resin solution layer **204**, a portion of the resin solution layer **204** contacting the protruding portion **PP** of the mold **M2** is moved toward the recessed portion **RP** due to a repulsion between the mold **M2** and the resin solution layer **204**. Thus, the portion of the resin solution layer **204** contacting the protruding portion **PP** of the mold **M2** fills the inner part of the recessed portion **RP** of the mold **M2**. Then, the resin solution layer **204** is solidified by heating it. Heating may be performed at two different temperatures including a first temperature smaller than or equal to a boiling point of the resin solution of the resin solution layer **204**, and a second temperature higher than the first temperature.

FIG. **8C** is a cross-sectional view of the formation of a separator on a substrate in a process of fabricating an organic electroluminescent device according to the second embodiment of the present invention. Referring to FIG. **8C**, the mold **M2** (shown in FIG. **8B**) is removed, leaving the solidified molded resin solution layer on the substrate **200**. The solidified molded resin solution layer forms a separator **206** on the substrate **200**. The separator **206** has a first portion **BB** having the first width **W1** and a second portion **SS** having the second width **W2**. The first portion **BB** of the separator **206** overlaps edges of the first electrode **202**. The second portion **SS** of the separator **206** is located within the non-pixel region **P**.

The first portion **BB** acts as a buffer layer and the second portion **SS** acts as a substantial separator means. The first width **W1** of the first portion **BB** is larger than the second width **W2** of the second portion **SS**. A side gap **K** between the first width **W1** and the second width **W2** is between 2 micrometers and 10 micrometers, a thickness **KK** of the first portion **BB** of the separator **206** is less than about 300 nanometers.

FIG. **8D** is a cross-sectional view of the formation of an organic electroluminescent layer on a substrate in a process of fabricating an organic electroluminescent device according to the second embodiment of the present invention. Referring to FIG. **8D**, at least one organic electroluminescent (EL) layer **208** is formed on the first electrode **202** in the pixel region **P** surrounded by the separator **206**. Forming the organic EL layer **208** includes forming red, green and blue EL layers (not shown) in the pixel regions **P** in repeating order. The at least one organic EL layer **208** may be a single layer or may include multiple layers. When the at least one organic EL layer **208** includes multiple layers and the first electrode **202** acts as the anode, the at least one organic EL layer **208** includes a hole transporting layer **208a** on the first electrode **202**, an emitting layer **208b** and an electron transporting layer **208c** on a later-formed second electrode.

A second electrode **210** is formed on the entire surface of the organic EL layer **208** and the separator **206**. When the second electrode **210** acts as a cathode, it includes a metallic material, such as calcium (Ca), aluminum (Al) and magnesium (Mg) and lithium fluorine/aluminum (LiF/Al). The first

electrode **202**, the organic EL layer **208** and the second electrode **210** form an organic EL diode **DEL**. Although not shown, an array element layer including a gate line, a data line, a power line and a thin film transistor may be formed between the substrate **200** and the organic EL diode **DEL**.

Hereinafter, a dual-panel type OLED device will be described, in which an array element layer and an organic EL diode are formed on their respective substrates. A method of fabricating a dual-panel type OLED device will also be described, which can reduce processing time and cost by providing a separator that functions as a buffer.

FIG. **9** is a cross-sectional view of an exemplary dual-panel type organic electroluminescent device according to a third embodiment of the present invention. Referring to FIG. **9**, first and second substrates **300** and **400** including a plurality of pixel regions **P** face each other and are spaced apart from each other. A full-color element layer **FE** is formed on the second substrate **400**. Specifically, the full-color element layer **FE** includes a color filter layer **404** on the second substrate **400** in the pixel region **P**, a color changing medium **405** on the color filter layer **404**, a black matrix **402** on the second substrate **400** at a boundary of the color filter layer **404** and the color changing medium **405**, and an overcoat layer **406** covering the entire surface of the black matrix **402**, the color changing medium **405** and the color filter layer **404**. The color filter layer **404** includes red, green and blue sub-color filters (not shown). The color changing medium **405** includes red, green and blue color changing media (not shown) corresponding to the red, green and blue sub-color filters, respectively. The overcoat layer **406** may include an organic insulating material, such as benzocyclobutene (BCB), polyacrylate, polyimide and polyamide.

A first electrode **408** is formed on the overcoat layer **406**. A separator **410** is formed over the first electrode **408** at the boundary of the pixel region **P**. An organic EL layer **412** and a second electrode **414** are formed on the first electrode **408** in the pixel region **P** surrounded by the separator **410**. When the first electrode **408** acts as an anode and the second electrode **414** acts as a cathode, the first electrode **408** may include a conductive material, such as indium tin oxide (ITO), and the second electrode **414** may include a metallic material, such as calcium (Ca), aluminum (Al) and magnesium (Mg), and lithium fluorine/aluminum (LiF/Al). The first electrode **408**, the organic EL layer **412** and the second electrode **414** form an organic EL diode **DEL**.

FIG. **10A** is a cross-sectional view of the formation of a full-color element layer on a substrate in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention. Referring to FIG. **10A**, a second substrate **400** includes a pixel region **P**, and a non-pixel region **NP** at a boundary of the pixel region **P**. A full-color element layer **FE** is formed on the second substrate **400**. The full-color element layer **FE** includes a black matrix **402**, a color filter layer **404** and a color changing medium **405**. The black matrix **402** is located in the non-pixel region **NP** and includes one of a black resin and a chrome based material. An overcoat layer **406** is formed on the entire surface of the full-color element layer **FE**.

FIG. **10B** is a cross-sectional view of the molding of a resin layer on an electrode in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention. Referring to FIG. **10B**, a first electrode **408** is formed on the entire surface of the overcoat layer **406**. When the first electrode **408** acts as an

anode, it includes a conductive material having a high work-function such as indium tin oxide (ITO).

A resin solution is coated on the entire surface of the first electrode **408** to form a resin solution layer **409**. The resin solution layer **409** may include a transparent organic insulating material, such as acrylic resin. Then, a mold **M3** is pressed on the resin solution layer **409** according to a predetermined pressure. The mold **M3** includes a recessed portion **RP** alternating with a protruding portion **PP**. The recessed portion **RP** has the same height **H3** as the protruding portion **PP**. As shown in FIG. **10B**, when the recessed portion **RP** and the protruding portion **PP** of the mold **M3** face the resin solution layer **409**, the width of the recessed portion **RP** gradually decreases toward the second substrate **400** and the width of the protruding portion **PP** gradually increases toward the second substrate **400**.

The resin solution layer **409** is solidified by heating under a predetermined pressure. The heating process may be performed at a temperature higher than a boiling point and a transition temperature of the resin solution layer **409**. For example, the predetermined pressure may be within 1 N/cm² to 100 N/cm². The pressing process is similar to the one described in reference to FIG. **7B**.

FIG. **10C** is a cross-sectional view of the formation of a separator on an electrode in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention. Referring to FIG. **10C**, the mold **M3** (shown in FIG. **10B**) is removed from the second substrate **400** leaving a solidified resin solution layer on the first electrode **408**. The solidified resin solution layer on the first electrode **408** forms a separator **410** on the first electrode **408** in the non-pixel region **NP**.

The separator **410** has a first portion **BB** and a second portion **SS**. The first portion **BB** is closer to the second substrate **400** than the second portion **SS**. A first width **W1** of the first portion **BB** is larger than a second width **W2** of the second portion **SS**. A cross-sectional of the second portion **SS** decreases gradually from both end sides toward a middle part of the cross-sectional. A side gap **K** of a top side of the second portion **SS** and a bottom side of the first portion **BB** may be about 2 micrometers.

FIG. **10D** is a cross-sectional view of the formation of an organic electroluminescent layer on an electrode in a process of fabricating an organic electroluminescent diode substrate for a dual-panel type organic electroluminescent device according to the third embodiment of the present invention. Referring to FIG. **10D**, at least one organic EL layer **412** and a second electrode **414** are sequentially formed on the first electrode **408** in the pixel region **P** surrounded by the separator **410**. The organic EL layer **412** includes red, green and blue EL layers (not shown) in the pixel regions **P** in repeating order.

The at least one organic EL layer **412** may include a single layer or multiple layers. When the at least one organic EL layer **412** includes multiple layers and the first electrode **414** acts as the anode, the at least one organic EL layer **412** includes a hole transporting layer **412a** on the first electrode **414**, an emitting layer **412b** and an electron transporting layer **412c**. When the second electrode **414** acts as a cathode, it may include a metallic material, such as calcium (Ca), aluminum (Al) and magnesium (Mg) and lithium fluoride/aluminum (LiF/Al).

FIG. **11** is a scanning electron microscopic view of an exemplary separator manufactured in accordance with the third embodiment of the present invention. Referring to FIG. **11**, the separator includes a novolac solution dissolved in

ethanol at a concentration of 15% in weight. The resin solution layer is pressed under a pressure of about 10 N/cm² and heating is performed at about 130 degrees Celsius while the resin solution layer is pressed by the mold. Moreover, the first width of the first portion is about 5 micrometers.

FIGS. **12A** and **12B** are cross-sectional views of an array substrate for a dual-panel type organic electroluminescent device according to an embodiment of the present invention. Hereinafter, a method of fabricating an array substrate for a dual-panel type OLED device will be described in reference to FIGS. **12A** and **12B**. Referring to FIGS. **12A** and **12B**, a pixel region **P** on a first substrate **300** includes a switching region **S** and a driving region **D**. A switching thin film transistor **T_S** and a driving thin film transistor **T_D** are formed on the first substrate **300** including the switching region **S** and the driving region **D**, respectively. The switching thin film transistor **T_S** includes a switching gate electrode **302**, a switching active layer **310**, a switching source electrode **318**, and a switching drain electrode **320**. Similarly, the driving thin film transistor **T_D** includes a driving gate electrode **304**, a driving active layer **314**, a driving source electrode **322**, and a driving drain electrode **324**.

The switching gate electrode **302** is connected to a gate line (not shown). The switching source electrode **318** is connected to a data line (not shown). The switching drain electrode **320** is connected to the driving gate electrode **304**. The driving source electrode **322** is connected to a power line **326**. A gate insulating layer **306** is formed between the gate electrodes **302** and **304** and the active layers **310** and **314**.

A first passivation layer **325** is formed between the switching thin film transistor **T_S** and the power line **326**. A first contact hole **327** is provided through the first passivation layer **325**. The first contact hole **327** exposes a portion of the driving source electrode **322**. The power line **326** is connected to the driving source electrode **322** via the first contact hole **327**.

A second passivation layer **328** is formed on the entire surface of the power line **326** and the switching thin film transistor **T_S**. A second contact hole **329** is provided through the first passivation layer **325** and the second passivation layers **328**. The second contact hole **329** exposes a portion of the driving drain electrode **324**.

A connection electrode **350** is formed on the second passivation layer **328**. The connection electrode **350** is connected to the driving drain electrode **324** via the second contact hole **329**. The connection electrode **350** includes an organic pattern **350a** having a predetermined height and a metallic material layer **350b** covering the organic pattern **350a**. Although not shown, the connection electrode **350** electrically connects the organic EL diode and the array element layer by attaching the first and second substrates **300** and **400**. For example, the connection electrode **350** connects the second electrode **400** and the driving thin film transistor **T_D**.

In accordance with embodiments of the present invention, the OLED device may have a high aperture ratio because the OLED device is a top emission type. Undesired effects due to the fabricating process of the organic EL diode can be prevented because the array layers are independently formed on respective substrates. Accordingly, overall production yield increases. A separate buffer layer is not required because the OLED device includes a separator, a second portion of which functions as a buffer layer. The molding of the separator can be performed without any mask process, thereby reducing processing time and cost.

It will be apparent to those skilled in the art that various modifications and variations can be made in the organic electroluminescent display device and fabricating method thereof of the present invention without departing from the spirit or

13

scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An organic electroluminescent display device, comprising:

a substrate, including a pixel region and a non-pixel region at a boundary of the pixel region;

a first electrode on the substrate in the pixel region;

a separator over the first electrode, the separator located in the non-pixel region, the separator including a first portion having a first width and a second portion having a second width smaller than the first width, the first portion overlapping edges of the first electrode, and the second portion within the non-pixel region, wherein sides of the first and second portions form a step shape,

14

the second portion is on the first portion, and the first portion is between the second portion and the first electrode;

an organic electroluminescent layer over the separator in the pixel region surrounded by the separator; and

a second electrode on an entire surface of the organic electroluminescent layer and the separator.

2. The device according to claim 1, wherein a side gap between the first width and the second width is between 2 micrometers to 10 micrometers.

3. The device according to claim 1, wherein a thickness of the first portion of the separator is less than about 300 nanometers.

4. The device according to claim 1, wherein a side of the second portion is perpendicular to a surface of the substrate.

* * * * *

专利名称(译)	有机电致发光显示装置及其制造方法		
公开(公告)号	US7728509	公开(公告)日	2010-06-01
申请号	US11/024015	申请日	2004-12-29
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG.PHILIPS LCD CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	BAE SUNG JOON KIM JIN OOK		
发明人	BAE, SUNG-JOON KIM, JIN-OOK		
IPC分类号	H05B33/14 H05B33/22 B05D5/06 B05D5/12 H01L21/336 H01L27/32 H01L29/786 H01L51/40 H05B33/10		
CPC分类号	H01L27/3246 H01L51/0002 H01L27/3251 H01L27/3211 H01L51/0004		
代理机构(译)	摩根路易斯律师事务所		
优先权	1020030100668 2003-12-30 KR		
其他公开文献	US20050162061A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机电致发光显示装置，包括基板，所述基板包括像素区域和位于所述像素区域边界处的非像素区域；像素区域中的基板上的第一电极；第一电极上方的隔板，位于非像素区域中的隔板，隔板包括具有第一宽度的第一部分和具有小于第一宽度的第二宽度的第二部分，第一部分与第一电极的边缘重叠，以及非像素区域内的第二部分；隔板包围的像素区域中的隔板上方的有机电致发光层；在有机电致发光层和隔板的整个表面上的第二电极。

