



US 20070278950A1

(19) **United States**(12) **Patent Application Publication** (10) **Pub. No.: US 2007/0278950 A1**
Hu et al. (43) **Pub. Date: Dec. 6, 2007**(54) **ORGANIC ELECTROLUMINESCENCE
DEVICE AND ORGANIC
ELECTROLUMINESCENCE PANEL USING
THE SAME**(30) **Foreign Application Priority Data**

Jun. 5, 2006 (TW) 95119834

Publication Classification(75) Inventors: **Min-Chieh Hu**, Shanhua Township
(TW); **Min-Ling Hung**, Kanding
Township (TW)(51) **Int. Cl.**
H05B 33/02 (2006.01)(52) **U.S. Cl.** **313/512**(57) **ABSTRACT**

An organic electroluminescence device (OELD) and a display panel are provided. The OELD comprises a first electrode, a second electrode, an emissive layer and a shielding structure. The second electrode is disposed above the first electrode. The emissive layer is disposed between the first electrode and the second electrode. The shielding structure is disposed above the second electrode. The hardness of the shielding structure is smaller than that of the second electrode.

Correspondence Address:


RABIN & Berdo, PC
1101 14TH STREET, NW, SUITE 500
WASHINGTON, DC 20005(73) Assignee: **AU OPTRONICS CORP.**,
Hsinchu (TW)(21) Appl. No.: **11/525,870**(22) Filed: **Sep. 25, 2006**

FIG. 1(RELATED ART)




FIG. 2




FIG. 3




FIG. 4




FIG. 5

ORGANIC ELECTROLUMINESCENCE DEVICE AND ORGANIC ELECTROLUMINESCENCE PANEL USING THE SAME

[0001] This application claims the benefit of Taiwan Patent Application Serial No. 95119834, filed Jun. 5, 2006, the subject matter of which is incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The invention relates in general to an organic electroluminescence device (OELD) and an organic electroluminescence (OEL) panel using the same, and more particularly to an OELD having a shielding structure on the electrode and an OEL panel using the same. The hardness of the shielding structure is approximately smaller than or equal to the hardness of the electrode.

[0004] 2. Description of the Related Art

[0005] The OEL panel having the advantages of light weight, thinness, high contrast, power saving, high color saturation, and fast response has become a display with great potential. Both the manufacturing process and the structure of an organic electroluminescence device (OELD) are simpler than that of other display devices such as cathode ray tube (CRT) display and liquid crystal display (LCD). Moreover, the OEL panel is self-illuminant, free of view-angle restriction and can be incorporated with flexible substrate. Therefore, the OEL panel is applicable to a large variety of products related to display devices.

[0006] Referring to FIG. 1, a diagram of a conventional OEL panel is shown. As shown in FIG. 1, the OEL panel 1 comprises a substrate 10, a top cover 11 and an OELD 12. The top cover 11 is disposed on the substrate 10. The OELD 12 is disposed on the substrate 10 and positioned between the top cover 11 and the substrate 10. The top cover 11 and the substrate 10 are bonded by a sealant S.

[0007] The OEL panel 1 further comprises an absorbent layer 13. The absorbent layer 13 is disposed on the top cover 11 and positioned between the top cover 11 and the OELD 12. Due to the fragile structure of the OELD 12, if the top cover 11 or the substrate 10 is bent or deformed during the packaging process or back-end process of the OEL panel 1, the OELD 12 would easily be pressed and damaged. Meanwhile, since the absorbent layer 13 is a drying agent, the generated particles P would alight on the surface or the adjacent side of the OELD 12. When the top cover 11 is squeezed or twisted, the particles P would easily scratch or press the OELD 12 if the particles P are squeezed by the top cover 11. Due to the structure design and physical characteristics of the OEL panel, if particle problem occurs to the display panel, the illuminant element would be pressed and damaged easily, affecting the yield rate and reliability of the product.

SUMMARY OF THE INVENTION

[0008] It is therefore an object of the invention to provide an organic electroluminescence device (OELD) and an OEL panel using the same. A shielding structure is formed on the electrode of the OELD. The hardness of the shielding structure is smaller than the hardness of the electrode.

[0009] The invention achieves the above-identified object by providing an organic electroluminescence device (OELD). The OELD comprises a first electrode, a second electrode, an emissive layer and a shielding structure. The second electrode is disposed above the first electrode. The emissive layer is disposed between the first electrode and the second electrode. The shielding structure is disposed on the second electrode. The hardness of the shielding structure is smaller than the hardness of the second electrode.

[0010] The invention achieves the above-identified object by providing an organic electroluminescence (OEL) panel. The OEL panel comprises a substrate, a top cover and an OELD. The top cover is disposed above the substrate. The OELD is disposed on the substrate and positioned between the top cover and the substrate. The OELD comprises a first electrode, a second electrode, an emissive layer and a shielding structure. The second electrode is disposed above the first electrode. The emissive layer is disposed between the first electrode and the second electrode. The shielding structure is disposed on the second electrode. The hardness of the shielding structure is smaller than the hardness of the second electrode.

[0011] Other objects, features, and advantages of the invention will become apparent from the following detailed description of the preferred but non-limiting embodiments. The following description is made with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] FIG. 1 (Related Art) is a diagram of a conventional OEL panel;

[0013] FIG. 2 is a first diagram of an OEL panel according to a first embodiment of the invention;

[0014] FIG. 3 is a second diagram of an OEL panel according to a first embodiment of the invention;

[0015] FIG. 4 is a first diagram of an OEL panel according to a second embodiment of the invention; and

[0016] FIG. 5 is a second diagram of an OEL panel according to a second embodiment of the invention.

DETAILED DESCRIPTION OF THE INVENTION

First Embodiment

[0017] Referring to FIG. 2, a first diagram of an OEL panel according to a first embodiment of the invention is shown. As shown in FIG. 2, the OEL panel 2 mainly comprises a substrate 20, a top cover 21 and an OELD 22. The top cover 21 is disposed on the substrate 20. The OELD 22 is disposed on the substrate 20 and positioned between the top cover 21 and the substrate 20. The OELD 22 comprises a first electrode 24, a second electrode 25, an emissive layer 26 and a shielding structure 27. The second electrode 25 is disposed above the first electrode 24. The emissive layer 26 is disposed between the first electrode 24 and the second electrode 25. The shielding structure 27 is disposed on the second electrode 25 as a buffer layer in order to protect the OELD from being scratched or damaged by particles. The hardness of the shielding structure 27 is smaller than the hardness of the second electrode 25. The yield rate of the OEL panel can be improved.

[0018] A sealant S is filled between the top cover 21 and the substrate 20 and pasted on the top cover 21 for bonding and packaging the top cover 21 and the substrate 20 after the

top cover **21** and the substrate **20** are aligned and matched. The OEL panel **2** further comprises an absorbent layer **23** disposed on the top cover **21** and positioned between the top cover **21** and the OELD **22**. The absorbent layer **23** is formed on the top cover **21** by adhering, pasting, or electroplating.

[0019] The cross-section of the top cover **21** is an inverted U-shaped cross-section such that the absorbent layer **23** is received in the inverted U-shaped recess.

[0020] The first electrode **24** and the second electrode **25** are respectively an anode and a cathode, or a cathode and an anode. Since the shielding structure **27** is disposed on the second electrode **25**, the hardness of the shielding structure **27** is approximately smaller than or equal to the hardness of the second electrode **25** such that the shielding structure **27** is used as a buffer layer to protect the second electrode **25**. Preferably, the Mohs' hardness of the shielding structure **27** is smaller than about 4, and the thickness of the shielding structure **27** approximately ranges between 0.2 μm and 100 μm . Ideally, the thickness of the shielding structure **27** is approximately equal to 3 μm .

[0021] Referring to FIG. 3, a second diagram of an OEL panel according to a first embodiment of the invention is shown. As shown in FIG. 3, the shielding structure **27'** only covers a part of the second electrode **25**. That is, the area covered by the shielding structure **27'** is smaller than the area of the top surface of the second electrode **25**. Besides, the area covered by the shielding structure **27'** can be designed as being equal to or larger than the area of the top surface of the second electrode **25**.

[0022] Similarly, the area covered by the shielding structure **27** can be larger than, equal to or smaller than the area of the bottom surface of the absorbent layer **23** such that the OELD **22** is effectively protected and the particles are prevented from alighting on the top surface of the OELD **22**, lest the particles might press and damage the OELD **22** when the top cover **21** or the substrate **20** is bent, twisted or deformed. Thus, the OELD **22** is still well protected when the particles alight on the OELD **22**.

[0023] The shielding structure **27** can be made from an organic material or an inorganic material. When the second electrode **25** is made from indium tin oxide (ITO), the material of the shielding structure **27** may include aluminum. Since the Mohs' hardness of the ITO is 4 and the Mohs' hardness of aluminum is 3, the shielding structure **27** made from aluminum is capable of effectively protecting the second electrode **25** without scratching the surface of the second electrode **25**. The shielding structure **27** can also be made from copper phthalocyanine (CuPC), 8-tris-hydroquinoline-aluminum (Alq_3) or triphenylamine derivative (TPD).

[0024] The substrate **20** can be an active substrate or a passive substrate. Meanwhile, the material of the substrate **20** may include an organic material or an inorganic material.

[0025] The manufacturing process of the OEL panel **2** is disclosed below. Firstly, the OELD **22** is manufactured on the substrate **20**. The first electrode **24**, the emissive layer **26** and the second electrode **25** are sequentially formed on the substrate **20**. Next, the shielding structure **27** exemplified by an organic thick film is formed on the second electrode **25** as a protection layer. The shielding structure **27** can be made from copper phthalocyanine (CuPC) or 8-tris-hydroquinoline-aluminum (Alq_3). Then, the absorbent layer **23** is disposed on the top cover **21** by adhering, pasting or electroplating and the sealant **S** is pasted around the top cover **21**

such that the top cover **21** is bounded and packaged with the substrate **20**. The manufacturing process of the OEL panel **2** is completed.

[0026] With a shielding structure being disposed on the OELD as a protection layer, when particles are generated inside the OEL panel (for example, particles may come off the drying agent of the absorbent layer), the shielding structure prevents the particles from alighting on the surface of the OELD. When the OEL panel receives an external force (for example, when the OEL panel is squeezed or twisted), the particles are less likely to scratch or damage the surface of the OELD, hence improving the yield rate of the OEL panel.

Second Embodiment

[0027] Referring to FIG. 4, a first diagram of an OEL panel according to a second embodiment of the invention is shown. The OEL panel **3** of the present embodiment of the invention differs with the OEL panel **2** of the first embodiment in the elements of the OELD. As for other similar elements, the same reference numbers are used and are not repeated here. As shown in FIG. 4, the OELD **32** of the OEL panel **3** comprises a first electrode **34**, a second electrode **35**, an emissive layer **36** and a shielding structure **37**. The emissive layer **36** is disposed between the first electrode **34** and the second electrode **35**. The shielding structure **37** is disposed on the second electrode **35**. The hardness of the shielding structure **37** is approximately smaller than or equal to the hardness of the second electrode **35**.

[0028] In practical application, the shielding structure **37** may comprise several shielding layers, wherein the present embodiment of the invention is exemplified by having two shielding layers. In FIG. 4, the shielding structure **37** has a first shielding layer **38** and a second shielding layer **39**. The first shielding layer **38** is positioned between the second shielding layer **39** and the second electrode **35**. Preferably, the first shielding layer **38** completely covers the second electrode **35**, and the second shielding layer **39** completely covers the first shielding layer **38**, such that the first shielding layer **38** is completely enclosed in the second shielding layer **39**.

[0029] Since the first shielding layer **38** is spread over the second electrode **35**, the first shielding layer **38** has complete contact with the second electrode **35** and would not scratch the top surface of the second electrode **35**. Preferably, the Mohs' hardness of the first shielding layer **38** is smaller than about 4.

[0030] The first shielding layer **38** can be made from an organic material or an inorganic material. Examples of the material of first shielding layer **38** include copper phthalocyanine (CuPC), 8-tris-hydroquinoline-aluminum (Alq_3) and triphenylamine derivative (TPD). The second shielding layer **39** can be made from Al_2O_3 or SiNx . Preferably, the thickness of the first shielding layer **38** is equal to about 2 μm but preferably more than about 3 μm . The thickness of the second shielding layer **39** is equal to about 5 μm .

[0031] Referring to FIG. 5, a second diagram of an OEL panel according to a third embodiment of the invention is shown. As shown in FIG. 5, the shielding structure **37'** of the OELD **32'** comprises a first shielding layer **38'** and a second shielding layer **39'**. The second shielding layer **39'** is disposed on the first shielding layer **38'**. The second shielding layer **39'** of FIG. 5 differs with the shielding structure **37** of FIG. 4 in that the second shielding layer **39'** does not

completely cover the first shielding layer 38', that is, the second shielding layer 39' only covers the top surface of the first shielding layer 38'. Preferably, the first shielding layer 38' completely covers the second electrode 35 such that the second electrode 35 is well protected.

[0032] The manufacturing process of the OEL panel 3 is disclosed below. Firstly, the first electrode 34, the emissive layer 36 and the second electrode 35 are sequentially formed on the substrate 20. Next, the first shielding layer 38 is formed on the second electrode 35 of the OELD 32. Examples of the first shielding layer 38 include an organic thick film made from CuPC. Then, the second shielding layer 39 is manufactured on the first shielding layer 38. Examples of the second shielding layer 39 include an aluminum layer. Next, the absorbent layer 23 is disposed on the top cover 21 by adhering, pasting or electroplating, and the sealant S is pasted around the top cover 21 such that the top cover 21 is bounded and packaged with the substrate 20. The manufacturing process of the OEL panel 3 is completed.

[0033] According to the OELD and the OEL panel using the same disclosed in the above embodiments of the invention, a shielding structure is formed on the electrode, such that the shielding structure completely covers the electrode to protect the electrode. Meanwhile, the hardness of the shielding structure is smaller than or equal to the hardness of the electrode of the OELD adjacent to the shielding structure to avoid damaging the electrode. The present embodiment of the invention uses the shielding structure with buffer function to prevent the OELD from being damaged by the particles when the top cover or the substrate is bent or deformed and squeezes the OELD during the packaging process and the back-end process of the OELD.

[0034] While the invention has been described by way of example and in terms of a preferred embodiment, it is to be understood that the invention is not limited thereto. On the contrary, it is intended to cover various modifications and similar arrangements and procedures, and the scope of the appended claims therefore should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements and procedures.

What is claimed is:

1. An organic electroluminescence device (OELD), comprising:

- a first electrode;
- a second electrode disposed on the first electrode;
- an emissive layer disposed between the first electrode and the second electrode; and
- a shielding structure disposed on the second electrode, wherein the hardness of the shielding structure is approximately smaller than or equal to the hardness of the second electrode.

2. The OELD according to claim 1, wherein the first electrode is an anode and the second electrode is a cathode.

3. The OELD according to claim 1, wherein the first electrode is a cathode and the second electrode is an anode.

4. The OELD according to claim 1, wherein the Mohs' hardness of the shielding structure is approximately smaller than 4.

5. The OELD according to claim 1, wherein the thickness of the shielding structure approximately ranges between 0.2 μm and 100 μm .

6. The OELD according to claim 1, wherein the thickness of the shielding structure is approximately equal to 5 μm .

7. The OELD according to claim 1, wherein the shielding structure comprises a first shielding layer and a second shielding layer, and the first shielding layer is positioned between the second shielding layer and the second electrode.

8. The OELD according to claim 7, wherein the Mohs' hardness of the first shielding layer is approximately smaller than 4.

9. The OELD according to claim 7, wherein the first shielding layer is comprised of an organic material or an inorganic material.

10. The OELD according to claim 7, wherein the second electrode is comprised of indium tin oxide (ITO), and the material of the first shielding layer includes aluminum.

11. The OELD according to claim 7, wherein the material of the first shielding layer includes copper phthalocyanine (CuPC), 8-tris-hydroquinoline-aluminum (Alq_3) or triphenylamine derivative (TPD), and the material of the second shielding layer includes aluminum.

12. The OELD according to claim 11, wherein the thickness of the first shielding layer is approximately equal to 2 μm .

13. An organic electroluminescence (OEL) panel, comprising:

- a substrate;
- a top cover disposed on the substrate; and
- an OELD disposed on the substrate and positioned between the top cover and the substrate, the OELD comprising:
 - a first electrode;
 - a second electrode disposed on the first electrode;
 - an emissive layer disposed between the first electrode and the second electrode; and
 - a shielding structure disposed on the second electrode, wherein the hardness of the shielding structure is approximately smaller than the hardness of the second electrode.

14. The OEL panel according to claim 13, further comprising:

- an absorbent layer disposed on the top cover and positioned between the top cover and the shielding structure.

15. The OEL panel according to claim 13, further comprising:

- a sealant disposed between the top cover and the substrate.

16. The OEL panel according to claim 13, wherein the first electrode is an anode and the second electrode is a cathode.

17. The OEL panel according to claim 13, wherein the first electrode is a cathode and the second electrode is an anode.

18. The OEL panel according to claim 13, wherein the Mohs' hardness of the shielding structure is approximately smaller than 4.

19. The OEL panel according to claim 13, wherein the thickness of the shielding structure approximately ranges between 0.2 μm and 100 μm .

20. The OEL panel according to claim 19, wherein the thickness of the shielding structure is approximately equal to 5 μm .

21. The OEL panel according to claim 13, wherein the shielding structure comprises a first shielding layer having a Mohs' hardness approximately smaller than 4 and a second

shielding layer, and the first shielding layer is positioned between the second shielding layer and the second electrode.

22. The OEL panel according to claim **21**, wherein the first shielding layer is comprised of an organic material or an inorganic material.

23. The OEL panel according to claim **21**, wherein the second electrode is comprised of indium tin oxide (ITO), and the material of the first shielding layer includes aluminum.

24. The OEL panel according to claim **21**, wherein the material of the first shielding layer includes copper phthalocyanine (CuPC), 8-tris-hydroquinoline-aluminum (Alq₃) or triphenylamine derivative (TPD), and the material of the second shielding layer includes aluminum.

* * * * *

专利名称(译)	有机电致发光器件和使用其的有机电致发光面板		
公开(公告)号	US20070278950A1	公开(公告)日	2007-12-06
申请号	US11/525870	申请日	2006-09-25
[标]申请(专利权)人(译)	友达光电股份有限公司		
申请(专利权)人(译)	友达光电.		
当前申请(专利权)人(译)	友达光电.		
[标]发明人	HU MIN CHIEH HUNG MIN LING		
发明人	HU, MIN-CHIEH HUNG, MIN-LING		
IPC分类号	H05B33/02		
CPC分类号	H01L51/5237 H01L51/5259 H01L51/5243 H01L51/5253		
优先权	095119834 2006-06-05 TW		
其他公开文献	US7495391		
外部链接	Espacenet USPTO		

摘要(译)

提供有机电致发光器件 (OELD) 和显示面板。OELD包括第一电极，第二电极，发光层和屏蔽结构。第二电极设置在第一电极上方。发光层设置在第一电极和第二电极之间。屏蔽结构设置在第二电极上方。屏蔽结构的硬度小于第二电极的硬度。

