



US 20170194414A1

(19) **United States**(12) **Patent Application Publication**  
**LEE et al.**(10) **Pub. No.: US 2017/0194414 A1**(43) **Pub. Date: Jul. 6, 2017**(54) **ORGANIC LIGHT-EMITTING DIODE  
DISPLAY DEVICE****Publication Classification**(51) **Int. Cl.****H01L 27/32** (2006.01)**H01L 51/00** (2006.01)(52) **U.S. Cl.**CPC ..... **H01L 27/3276** (2013.01); **H01L 27/3246**(2013.01); **H01L 27/3211** (2013.01); **H01L****51/0003** (2013.01); **H01L 51/5012** (2013.01)(71) Applicant: **LG Display Co., Ltd.**, Seoul (KR)(72) Inventors: **A-Ryoung LEE**, Seoul (KR); **Ki-Soub  
YANG**, Gyeonggi-do (KR); **Da-Hye  
SHIM**, Gyeonggi-do (KR)(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)(21) Appl. No.: **15/395,042**(22) Filed: **Dec. 30, 2016**(30) **Foreign Application Priority Data**


Dec. 30, 2015 (KR) ..... 10-2015-0189787

Dec. 1, 2016 (KR) ..... 10-2016-0162704


(57)

**ABSTRACT**


Provided is an organic light-emitting display device. An organic light-emitting display device (OLED) includes: a substrate including at least three pixel regions arranged in a horizontal direction, a first electrode in each pixel region on the substrate, a bank surrounding each pixel region, and a power line in the horizontal portion at a lower side of each pixel region on the substrate, the power line being configured to supply a driving voltage to each pixel region.




**FIG. 1**  
**(Related Art)**



**FIG. 2A**  
**(Related Art)**



**FIG. 2B**  
**(Related Art)**



**FIG. 3**




FIG. 4A




FIG. 4B




FIG. 5






FIG. 6A



**FIG. 6B**






FIG. 8




FIG. 9




FIG. 10




FIG. 11





FIG. 12



## ORGANIC LIGHT-EMITTING DIODE DISPLAY DEVICE

### CROSS-REFERENCE TO RELATED APPLICATION(S)

[0001] This application claims the benefit of Korean Patent Applications No. 10-2015-0189787, filed on Dec. 30, 2015, and No. 10-2016-0162704, filed on Dec. 1, 2016, the entire disclosure of each of which is hereby incorporated by reference herein.

### BACKGROUND

[0002] 1. Technical Field

[0003] The present disclosure relates to an organic light-emitting diode display device (OLED), and more particularly, to an OLED that can improve a uniformity of thickness of an organic light-emitting layer.

[0004] 2. Discussion of the Related Art

[0005] Recently, flat display devices, such as a plasma display panel (PDP), a liquid crystal display device (LCD), and an organic light-emitting diode display device (OLED), have been researched. Among the flat display devices, the OLED is a self-luminescent device and can have a thin profile because the OLED does not need a backlight, such as that used for the LCD.

[0006] Further, compared with the LCD, the OLED has advantages of excellent viewing angle and contrast ratio, low power consumption, operation in low DC voltage, fast response speed, being strong to resist an external impact because of its solid internal components, and wide operating temperature range. Particularly, because processes of manufacturing the OLED are simple, production cost of the OLED can be reduced more than that of the LCD.

[0007] FIG. 1 is a plan view illustrating an OLED according to the related art. FIG. 2A is a cross-sectional view taken along line IIa-IIa of FIG. 1. FIG. 2B is a cross-sectional view taken along line IIb-IIb of FIG. 1.

[0008] With reference to FIGS. 1 to 2B, the related art OLED includes a substrate 11, including first to third pixel regions P1 to P3 arranged in a horizontal direction, a planarization layer 17 on the substrate 11, a first electrode 20 on the planarization layer 17 and located in each of first to third pixel regions P1 to P3, and a bank 50 covering an edge portion of the first electrode 20 and surrounding each of the first to third pixel regions P1 to P3 on the planarization layer 17. The OLED further includes a power line 13 and a data line 15 in a vertical direction at boundary portions B1 and B2 among the first to third pixel regions P1 to P3, and a gate line 14 crossing the power line 13 and the data line 15 and located at a lower side of the first to third pixel regions P1 to P3. A gate insulating layer 12 is on the substrate 11 covering the gate line 14, and the planarization layer 17 is on the gate insulating layer 12 covering the power line 13 and the data line 15.

[0009] When the OLED operates, a driving voltage is supplied to the first to third pixel regions P1 to P3 through one power line 13. Accordingly, the driving voltage drops. Thus, display quality is degraded.

[0010] To prevent the driving voltage drop, a width of the first boundary portion B1 between the first and second pixel regions P1 and P2 is greater than that of the second boundary portion B2 between the second and third pixel regions P2 and P3, the power line 13 is arranged on the gate insulating

layer 12 at the first boundary portion B1, and the data line 15 is arranged on the gate insulating layer at the second boundary portion B2. Accordingly, a width of the power line 13 becomes great in correspondence to the width of the first boundary portion B1. Thus, even for a large-sized OLED, a driving voltage drop is minimized, and degradation of display quality is prevented.

[0011] A width of the bank 50 at the first boundary portion B1 is greater than that of the bank 50 at the second boundary portion B2. Organic light-emitting layers 70a to 70c are formed on respective first pixel electrodes 20. The organic light-emitting layers 70a to 70c are formed using a soluble process method, such as an inject printing method, a nozzle printing method, or the like.

[0012] In detail, with reference to FIGS. 2A and 2B, an organic light-emitting material solution is dropped on the first electrode 20 of each of the first to third pixel regions P1 to P3, then the dropped organic light-emitting material solution is dried. Thus, the organic light-emitting layers 70a to 70c are formed. In this case, the width of the bank 50 at the first boundary portion B1 is greater than that of the bank 50 at the second boundary portion B2.

[0013] Accordingly, for the dropped organic light-emitting material solution in each of the first to third pixel regions P1 to P3, an evaporation environment of solvent molecules of the organic light-emitting material solutions located at respective sides of the first and second pixel regions P1 and P2 with the first boundary portion B1 therebetween is different from an evaporation environment of solvent molecules of the organic light-emitting material solutions located at respective sides of the second and third pixel regions P2 and P3 with the second boundary portion B2.

[0014] In other words, when drying the organic light-emitting material solutions, an evaporation rate of the solvent molecules of the organic light-emitting material solutions located at adjacent sides of the first and second pixel regions P1 and P2 is faster than an evaporation rate of the solvent molecules of the organic light-emitting material solutions located at adjacent sides of the second and third pixel regions P2 and P3.

[0015] Accordingly, after drying the organic light-emitting material solutions, unlike the organic light-emitting layer 70c formed in the third pixel region P3, the organic light-emitting layers 70a and 70b formed in the first and second pixel regions P1 and P2 become thicker where they are closer to the first boundary portion B1. Such non-uniformity of thickness of the organic light-emitting layers 70a to 70c causes degradation of display quality of the OLED and reduction of light emission efficiency and lifetime of the OLED.

### SUMMARY

[0016] Accordingly, the present disclosure is directed to an organic light-emitting display device that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

[0017] An object of the present disclosure is to improve a uniformity of thickness of an organic light-emitting layer and a non-uniformity of brightness.

[0018] Additional features and advantages will be set forth in the description that follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the disclosure will be realized and attained by the structure par-

ticularly pointed out in the written description and claims thereof as well as the appended drawings.

[0019] To achieve these and other advantages and in accordance with the purpose of the present disclosure, as embodied and broadly described, there is provided an organic light-emitting display device (OLED), including: a substrate including at least three pixel regions arranged in a horizontal direction, a first electrode in each pixel region on the substrate, a bank surrounding each pixel region, and a power line in the horizontal portion at a lower side of each pixel region on the substrate, the power line being configured to supply a driving voltage to each pixel region.

[0020] In another aspect, there is provided an organic light-emitting display device (OLED), including: a substrate including: a plurality of gate lines and data lines crossing each other, and at least three pixel regions arranged in a horizontal direction at crossing portions of the gate and data lines, a first electrode in each pixel region on the substrate, a bank surrounding each pixel region, and a power line in parallel with the gate line, the power line being configured to supply a driving voltage to each pixel region.

[0021] In another aspect, there is provided an organic light-emitting display device (OLED), including: a substrate including pixel regions emitting a same color on each column line, a first electrode in each pixel region on the substrate, a bank surrounding each pixel group including neighboring pixel regions on each column line, and an organic light-emitting layer on the first electrode and corresponding to each pixel group.

[0022] In another aspect, there is provided an organic light-emitting display device, including: organic light-emitting display device (OLED), including: a substrate including pixel regions emitting a same color on each column line, a first electrode in each pixel region on the substrate, a bank between neighboring pixel regions on each column line, the bank including: a first part, and second parts at each side of the first part and each having a thickness less than that of the first part, and an organic light-emitting layer on the first electrode and the second parts.

[0023] Other systems, methods, features and advantages will be, or will become, apparent to one with skill in the art upon examination of the following figures and detailed description. It is intended that all such additional systems, methods, features and advantages be included within this description, be within the scope of the present disclosure, and be protected by the following claims. Nothing in this section should be taken as a limitation on those claims. Further aspects and advantages are discussed below in conjunction with the embodiments of the disclosure. It is to be understood that both the foregoing general description and the following detailed description of the present disclosure are examples and explanatory, and are intended to provide further explanation of the disclosure as claimed.

#### BRIEF DESCRIPTION OF THE DRAWINGS

[0024] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate implementations of the invention and together with the description serve to explain the principles of the disclosure.

[0025] FIG. 1 is a plan view illustrating an OLED according to the related art.

[0026] FIG. 2A is a cross-sectional view taken along line IIa-IIa of FIG. 1.

[0027] FIG. 2B is a cross-sectional view taken along line IIb-IIb of FIG. 1.

[0028] FIG. 3 is a plan view illustrating an OLED according to a first embodiment of the present disclosure.

[0029] FIG. 4A is a cross-sectional view taken along line IVa-IVa of FIG. 3.

[0030] FIG. 4B is a cross-sectional view taken along line IVb-IVb of FIG. 3.

[0031] FIG. 5 is a plan view illustrating an OLED according to a second embodiment of the present disclosure.

[0032] FIG. 6A is a cross-sectional view taken along line VIa-VIa of FIG. 5.

[0033] FIG. 6B is a cross-sectional view taken along line VIb-VIb of FIG. 5.

[0034] FIG. 7 is a plan view illustrating an OLED according to a third embodiment of the present disclosure.

[0035] FIG. 8 is a cross-sectional view taken along line VIII-VIII of FIG. 7.

[0036] FIG. 9 is a plan view illustrating an OLED of a comparative example.

[0037] FIG. 10 is a cross-sectional view taken along line X-X of FIG. 9.

[0038] FIG. 11 is a plan view illustrating an OLED according to a fourth embodiment of the present disclosure.

[0039] FIG. 12 is a cross-sectional view taken along line XII-XII of FIG. 11.

[0040] Throughout the drawings and the detailed description, unless otherwise described, the same drawing reference numerals should be understood to refer to the same elements, features, and structures. The relative size and depiction of these elements may be exaggerated for clarity, illustration, and convenience.

#### DETAILED DESCRIPTION

[0041] Reference will now be made in detail to embodiments of the present disclosure, examples of which are illustrated in the accompanying drawings. In the following description, when a detailed description of well-known functions or configurations related to this document is determined to unnecessarily cloud a gist of the invention, the detailed description thereof will be omitted. The progression of processing steps and/or operations described is an example; however, the sequence of steps and/or operations is not limited to that set forth herein and may be changed as is known in the art, with the exception of steps and/or operations necessarily occurring in a certain order. Like reference numerals designate like elements throughout. Names of the respective elements used in the following explanations are selected only for convenience of writing the specification and may be thus different from those used in actual products.

[0042] In the description of embodiments, when a structure is described as being positioned “on or above” or “under or below” another structure, this description should be construed as including a case in which the structures contact each other as well as a case in which a third structure is disposed therebetween.

#### First Embodiment

[0043] FIG. 3 is a plan view illustrating an OLED according to a first embodiment of the present disclosure. FIG. 4A

is a cross-sectional view taken along line IVa-IVa of FIG. 3. FIG. 4B is a cross-sectional view taken along line IVb-IVb of FIG. 3.

[0044] With reference to FIG. 3, the OLED of the first embodiment may include a substrate **101** including first to third pixel regions **P1** to **P3** arranged in a horizontal direction, a first electrode **120** in each of first to third pixel regions **P1** to **P3** on the substrate **101**, and a gate line **114**, a data line **115**, and a power line **113** on the substrate **101**. The substrate **101** may include three or more pixel regions. In one example, a fourth pixel region may be arranged at one side of the first to third pixel regions **P1** to **P3**.

[0045] For example, the gate line **114** may be arranged in the horizontal direction at a lower side of the first to third pixel regions **P1** to **P3**. The data line **115** may cross the gate line **114**, and may be arranged at each of boundary portions **B1** and **B2** among the first to third pixel regions **P1** to **P3**. The power line **113** may be arranged at the lower side of the first to third pixel regions **P1** to **P3**, and may be spaced part from and parallel with the gate line **114**.

[0046] With reference to FIGS. 4A and 4B, the OLED may further include a bank **150** on a planarization layer **117**. The bank **150** may cover an edge portion of the first electrode **120**, and may surround each of the first to third pixel regions **P1** to **P3**. The OLED may further include a gate insulating layer **112** located on the substrate **101** and covering the power line **113** and the gate line **114**, and the planarization layer **117** on the gate insulating layer **112**.

[0047] The data line **115** may be between the gate insulating layer **112** and the planarization layer **117**, and the first electrode **120** is on the planarization layer **117**. The power line **113** and the gate line **114** may be formed at the same layer and of the same material. The first electrode **120** may be formed of a transparent conductive material having a relatively high work function to serve as an anode. The bank **150** may be formed of a hydrophobic material.

[0048] To achieve a large-sized OLED, the plurality of pixel regions **P1** to **P3** may be supplied with a driving voltage through one power line **113**. This may cause the driving voltage drop and degradation of display quality.

[0049] In the OLED of the first embodiment, the power line **113** may be arranged in the horizontal direction at the lower side of the first to third pixel regions **P1** to **P3**, and a driving voltage may be supplied from both ends of the power line **113**. Thus, the driving voltage drop can be prevented. Accordingly, even when achieving the large-sized OLED, the driving voltage drop can be minimized, and degradation of display quality can be prevented.

[0050] Because the driving voltage is supplied from both ends of the power line **113**, a width of the power line **113** can be reduced along with minimizing the driving voltage drop. Thus, reduction of aperture ratio due to the arrangement of the power line **113** can be minimized.

[0051] Organic light-emitting layers **170a** to **170c** may be formed on respective first electrodes **120**. The organic light-emitting layers **170a** to **170c** may be laminated using a soluble process method, such as an inject printing method, a nozzle printing method, or the like.

[0052] For example, an organic light-emitting material solution may be dropped on the first electrode **120** of each of the first to third pixel regions **P1** to **P3**, then the dropped organic light-emitting material solution may be dried. Thus, the organic light-emitting layers **170a** to **170c** may be formed. Because the bank **150** may be hydrophobic, the

bank **150** may function as a partition wall to prevent the organic light-emitting material solutions dropped on the first to third pixel regions **P1** to **P3** from being mixed.

[0053] Further, the data line **115** may be arranged at the boundary portions **B1** and **B2** among the first to third pixel regions **P1** to **P3**, and the power line **113** may be arranged at the lower side of the first to third pixel regions **P1** to **P3**. Thus, a width of the first boundary portion **B1** and a width of the second boundary portion **B2** may be equal to each other, and a width of the bank **150** at the first boundary portion **B1** and a width of the bank **150** at the second boundary portion **B2** may be equal to each other.

[0054] When the widths of the first and second boundary portions **B1** and **B2** are equal to each other, amounts of organic light-emitting material solutions around minor axes of the first to third pixel regions **P1** to **P3** may be equal to each other. Accordingly, in a process of drying the organic light-emitting material solution, evaporation rates of solvent molecules of the organic light-emitting material solutions in the minor axes of the first to third pixel regions **P1** to **P3** may be equal to each other.

[0055] Further, after the drying process, thicknesses of the organic light-emitting layers **170a** to **170c** in the minor axes of the first to third pixel regions **P1** to **P3** may be uniform. Accordingly, degradation of display quality of the OLED can be prevented, and reduction of light emission efficiency and lifetime of the OLED can be prevented.

#### Second Embodiment

[0056] FIG. 5 is a plan view illustrating an OLED according to a second embodiment of the present disclosure. FIG. 6A is a cross-sectional view taken along line VIa-VIa of FIG. 5. FIG. 6B is a cross-sectional view taken along line VIb-VIb of FIG. 5.

[0057] With reference to FIG. 5, the OLED of the second embodiment may include a substrate **201** including first to third pixel regions **P1** to **P3** arranged in a horizontal direction, a first electrode **220** in each of first to third pixel regions **P1** to **P3** on the substrate **201**, and a gate line **214**, a data line **215**, and a power line **213** on the substrate **201**. The substrate **201** may include three or more pixel regions. In one example, a fourth pixel region may be arranged at one side of the first to third pixel regions **P1** to **P3**. Further, the OLED may include an auxiliary electrode **221** located at a boundary portion between pixel regions along a vertical direction and spaced apart from the first electrode **220**.

[0058] For example, the gate line **214** may be arranged in the horizontal direction at a lower side of the first to third pixel regions **P1** to **P3**. The data line **215** may cross the gate line **214**, and may be arranged at each of boundary portions **B1** and **B2** among the first to third pixel regions **P1** to **P3**. The power line **213** may be arranged at the lower side of the first to third pixel regions **P1** to **P3**, and may be spaced part from and parallel with the gate line **214**. The power line **213** may be electrically connected with the auxiliary electrode **221** through a contact hole **CH**.

[0059] With reference to FIGS. 6A and 6B, the OLED may further include a bank **250** on a planarization layer **217**. The bank **250** may cover an edge portion of the first electrode **220**, and may surround each of the first to third pixel regions **P1** to **P3**.

[0060] The OLED may further include a gate insulating layer **212** located on the substrate **201** and covering the power line **213** and the gate line **214**, and the planarization

layer **217** on the gate insulating layer **212**. The data line **215** may be between the gate insulating layer **212** and the planarization layer **217**, and the first electrode **220** and the auxiliary electrode **221** may be on the planarization layer **217**.

[0061] The gate insulating layer **212** and the planarization layer **217** may include a contact hole CH exposing a portion of the power line **213**, and the auxiliary electrode **221** may be connected with the power line **213** through the contact hole CH. The auxiliary electrode may be connected to a driving thin film transistor.

[0062] The power line **213** and the gate line **214** may be formed at the same layer and of the same material. The first electrode **220** and the auxiliary electrode **221** may be formed at the same layer and of the same material. The first electrode **220** may be formed of a transparent conductive material having a relatively high work function to serve as an anode. The bank **250** may be formed of a hydrophobic material.

[0063] To achieve a large-sized OLED, the plurality of pixel regions **P1** to **P3** may be supplied with a driving voltage through one power line **213**. This may cause the driving voltage drop and degradation of display quality.

[0064] In the OLED of the second embodiment, the power line **213** may be arranged in the horizontal direction at the lower side of the first to third pixel regions **P1** to **P3**, and a driving voltage may be supplied from both ends of the power line **213**. Thus, the driving voltage drop can be prevented. Accordingly, even when achieving the large-sized OLED, the driving voltage drop can be minimized, and degradation of display quality can be prevented.

[0065] Because the driving voltage is supplied from both ends of the power line **213**, a width of the power line **213** can be reduced along with minimizing the driving voltage drop. Thus, reduction of aperture ratio due to the arrangement of the power line **213** can be minimized.

[0066] Further, because the power line **213** is electrically connected with the auxiliary electrode **221** through the contact hole CH, a sheet resistance of the power line **213** may be reduced. A width of the power line **213** can be reduced as much as the sheet resistance of the power line is reduced. Thus, reduction of aperture ratio can be further minimized.

[0067] Organic light-emitting layers **270a** to **270c** may be formed on respective first electrodes **220**. The organic light-emitting layers **270a** to **270c** may be laminated using a soluble process method, such as an inject printing method, a nozzle printing method or the like.

[0068] For example, an organic light-emitting material solution may be dropped on the first electrode **220** of each of the first to third pixel regions **P1** to **P3**, then the dropped organic light-emitting material solution may be dried. Thus, the organic light-emitting layers **270a** to **270c** may be formed. Because the bank **250** is hydrophobic, the bank **250** may function as a partition wall to prevent the organic light-emitting material solutions dropped on the first to third pixel regions **P1** to **P3** from being mixed.

[0069] Further, the data line **215** may be arranged at the boundary portions **B1** and **B2** among the first to third pixel regions **P1** to **P3**, and the power line **213** may be arranged at the lower side of the first to third pixel regions **P1** to **P3**. Thus, a width of the first boundary portion **B1** and a width of the second boundary portion **B2** may be equal to each other, and a width of the bank **250** at the first boundary

portion **B1** and a width of the bank **250** at the second boundary portion **B2** may be equal to each other.

[0070] When the widths of the first and second boundary portions **B1** and **B2** are equal to each other, amounts of organic light-emitting material solutions around minor axes of the first to third pixel regions **P1** to **P3** may be equal to each other. Accordingly, in a process of drying the organic light-emitting material solution, evaporation rates of solvent molecules of the organic light-emitting material solutions in the minor axes of the first to third pixel regions **P1** to **P3** may be equal to each other.

[0071] Further, after the drying process, thicknesses of the organic light-emitting layers **270a** to **270c** in the minor axes of the first to third pixel regions **P1** to **P3** may be uniform. Accordingly, degradation of display quality of the OLED can be prevented, and reduction of light emission efficiency and lifetime of the OLED can be prevented.

### Third Embodiment

[0072] FIG. 7 is a plan view illustrating an OLED according to a third embodiment of the present disclosure. FIG. 8 is a cross-sectional view taken along line VIII-VIII of FIG. 7.

[0073] The OLED of the third embodiment is similar to the OLED of the first or second embodiments, except for a structure of pixel regions emitting the same color on each column line. Explanations similar to parts of the first or second embodiment may be omitted. For the purpose of explanation, gate lines, data lines, and power lines, and so on are not shown in FIGS. 7-8.

[0074] In the OLED of this embodiment, pixel regions emitting the same color may be located on each column line. For example, the first pixel regions **P1** on the first column line may emit red, the second pixel regions **P2** on the second column line may emit green, and the third pixel regions **P3** on the third column line may emit blue. Embodiments are not limited thereto. The first pixel region **P1**, the second pixel region **P2**, and the third pixel region **P3** may alternate on each row line. A bank **350** may be formed between the neighboring pixel regions on each row line.

[0075] In this embodiment, regarding the pixel regions on each column line, at least two neighboring pixel regions may form a pixel group as a unit group. In this case, no bank may be formed at a boundary portion between the neighboring pixel regions within each pixel group, and the bank **350** may be formed between at a boundary portion between the neighboring pixel group.

[0076] This is illustrated with the first pixel regions **P1** by way of example. Two neighboring first pixel regions **P1** may form each pixel group PG, and the bank **350** may not be formed between the first pixel regions **P1** within the pixel group PG. However, the bank **350** may be formed between the neighboring first pixel groups PG, e.g., between an outermost first pixel region **P1** of a first pixel group PG1 and an outermost first pixel region **P1** of a second pixel group PG2 neighboring to the outermost first pixel region **P1** of the first pixel group PG1. In other words, on each column line, the bank **350** may be formed for every at least two pixel regions.

[0077] By forming the bank **350** with the pixel group PG including at least two pixel regions on each column line, the bank **350** may surround each pixel group PG. Each of first, second, and third organic light-emitting layers **370a** to **370c**

emitting red, green, and blue, respectively, may be formed corresponding to each pixel group PG. Embodiments are not limited to these examples.

[0078] In one example, the pixel group PG emitting red may be surrounded by portions of the bank 350 which may be located at both sides (e.g., an upper side and a lower side) of the column line and both sides (e.g., a left side and a right side) on the row line, and the first organic light-emitting layer 370a may be formed in the bank 350 surrounding each pixel group PG emitting red. Accordingly, a number of the bank portions (e.g., bank patterns) on the column line can be reduced, and a unit region to form each organic light-emitting layer may correspond to the pixel group PG and may increase in area.

[0079] Thus, the thickness uniformity of the organic light-emitting layer can be improved, and an efficiency of forming the organic light-emitting layer can be improved. This is explained below in comparison with an comparative example of forming a bank at each pixel region.

[0080] FIG. 9 is a plan view illustrating an OLED of a comparative example. FIG. 10 is a cross-sectional view taken along line X-X of FIG. 9.

[0081] In the comparative example, because a bank 450 is formed between neighboring pixel regions on each column line, each of first, second, and third organic light-emitting layers 470a and 470c is formed corresponding to every pixel region. Compared with the third embodiment of the present disclosure, the comparative OLED has more bank patterns on each column line, and a unit region to form each organic light-emitting layer is the pixel region and an area of this unit region is smaller.

[0082] Accordingly, a thickness profile of the organic light-emitting layer is produced every pixel region in the comparative example. In other words, a profile in which a thickness of the organic light-emitting layer near the bank 450 is greater than a thickness of the organic light-emitting layer inside the pixel region is produced at every pixel region in the comparative example.

[0083] In contrast, in the third embodiment, a thickness profile of the organic light-emitting layer is produced at every pixel group that includes a plurality of pixel regions. Thus, compared with the comparative example, the thickness uniformity of the organic light-emitting layer can be greatly improved.

[0084] Further, regarding jetting an organic light-emitting material solution through nozzles 510 of an inkjet head 500, the comparative example conducts the jetting at every pixel region. As such, the nozzles 510 located in correspondence to the pixel regions are used, but the nozzles 510a located between the pixel regions are not used. Thus, a use rate of the nozzles 510 is reduced for the comparative example. Further, a number of the used nozzles 510 is limited in a production facility. Therefore, the solution may not be jetted by a required amount, which may cause a spot defect may happen.

[0085] In contrast, in the third embodiment, the jetting is conducted at every pixel group. Thus, a number of the used nozzles 510 increases, and a number of the unused nozzles 510a is reduced compared with the comparative example. In the FIG. 9 comparative example, it can be seen that there are more unused nozzles 510a than there are in the example of FIG. 7 for the third embodiment. Accordingly, the use rate of the nozzles 510 increases in an embodiment of the present

disclosure, and the solution can be jetted by the required amount. Thus, the spot defect can be prevented according to an embodiment.

[0086] Further, in the third embodiment, to obtain an insulation property between first electrodes 320 of the neighboring pixel regions within the pixel group PG, an insulation pattern 340 may be formed. The insulation pattern 340 may be formed of an inorganic insulating material, for example, silicon oxide or silicon nitride. The insulation pattern 340 may be formed between the neighboring first electrodes 320 covering edge portions of the first electrodes 320. Further, the insulation pattern 340 may be formed between the first electrodes 340 neighboring each other on the row line as well.

[0087] Further, the configuration of the first or second embodiment may be applied to the OLED of the third embodiment. For example, in the third embodiment, a power line may be formed parallel with a gate line in a row direction. Accordingly, a thickness uniformity of the organic light-emitting layer can be maximized.

[0088] Alternatively, the configuration of the related art may be applied to the OLED of the third embodiment. In other words, in the third embodiment, a power line may be formed in a column direction. In this case, because the bank 350 may be formed according to the pixel group PG, the thickness uniformity of the organic light-emitting layer can be improved compared with the related art.

#### Fourth Embodiment

[0089] FIG. 11 is a plan view illustrating an OLED according to a fourth embodiment of the present disclosure. FIG. 12 is a cross-sectional view taken along line XII-XII of FIG. 11.

[0090] The OLED of the fourth embodiment is similar to the OLED of the first, second, or third embodiments, except for a structure of pixel regions emitting the same color on each column line. Explanations similar to parts of the first, second, or third embodiments may be omitted. For the purpose of explanations, gate lines, data lines, and power lines, and so on are not shown in FIGS. 11-12.

[0091] In the OLED of the fourth embodiment, pixel regions emitting the same color may be located on each column line. For example, the first pixel regions P1 on the first column line may emit red, the second pixel regions P2 on the second column line may emit green, and the third pixel regions P3 on the third column line may emit blue. The first pixel region P1, the second pixel region P2, and the third pixel region P3 may alternate on each row line. A bank 450 may be formed between the neighboring pixel regions on each row line.

[0092] In the fourth embodiment, the bank 450 formed between the neighboring pixel regions on each column line may be formed to have a step structure. This is illustrated with the first pixel regions P1 as an example. The bank 450 between the two neighboring first pixel regions P1 may have a first part 551 and second parts 552 at each side, on the column line, of the first part 551. The second part 552 may have a thickness less than that of the first part 551. As such, by the first part 551 being configured to protrude upwardly and the second parts 552 having the lesser thickness, the bank 550 may have the step structure in directions to the first pixel pixels P1 located at both sides thereof.

[0093] When the bank 550 has the step structure, the first organic light-emitting layer 570a of the first pixel region P1

may further extend over the second parts **552** located at both sides of the first pixel region **P1**. Thus, an area to form the first organic light-emitting layer **570a** in the first pixel region **P1** can expand in the column direction.

**[0094]** Accordingly, compared with a case using a bank having no step structure, a unit area to form the organic light-emitting layer increases. Thus, a thickness uniformity of the organic light-emitting layer can be improved.

**[0095]** Further, the configuration of the first or second embodiment may be applied to the OLED of the fourth embodiment. For example, in the fourth embodiment, a power line may be formed parallel with a gate line in a row direction. Accordingly, a thickness uniformity of the organic light-emitting layer can be maximized.

**[0096]** Alternatively, the configuration of the related art may be applied to the OLED of the fourth embodiment. In other words, in the fourth embodiment, a power line may be formed in a column direction. In this case, because the bank **550** is formed to have the step structure, the thickness uniformity of the organic light-emitting layer can be improved compared with the related art.

**[0097]** It will be apparent to those skilled in the art that various modifications and variations may be made in the present disclosure without departing from the spirit or scope of the invention. Thus, it is intended that embodiments of the present disclosure cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An organic light-emitting display device (OLED), comprising:

a substrate including at least three pixel regions arranged in a horizontal direction;  
a first electrode in each pixel region on the substrate;  
a bank surrounding each pixel region; and  
a power line in the horizontal portion at a lower side of each pixel region on the substrate, the power line being configured to supply a driving voltage to each pixel region.

2. The OLED of claim 1, wherein the bank has a same width at boundary portions among the at least three pixel regions.

3. The OLED of claim 1, wherein the driving voltage is supplied from both ends of the power line.

4. The OLED of claim 1, further comprising:  
a gate line in the horizontal direction on the substrate; and  
a data line crossing the gate line,  
wherein the power line and the gate line are at a same layer and are formed of a same material.

5. The OLED of claim 1, further comprising an auxiliary electrode spaced apart from the first electrode and electrically connected with the power line.

6. The OLED of claim 5, further comprising:  
a gate insulating layer on the gate line and the power line; and  
a planarization layer on the gate insulating layer,  
wherein the data line is between the gate insulating layer and the planarization layer, and  
wherein the first electrode is on the planarization layer.

7. The OLED of claim 6, wherein:  
the gate insulating layer and the planarization layer include a contact hole exposing a portion of the power line; and

the power line is connected to the auxiliary electrode through the contact hole.

8. The OLED of claim 1, further comprising an organic light-emitting layer on the first electrode.

9. The OLED of claim 8, wherein the organic light-emitting layer is laminated using a soluble process.

10. An organic light-emitting display device (OLED), comprising:

a substrate including:  
a plurality of gate lines and data lines crossing each other; and  
at least three pixel regions arranged in a horizontal direction at crossing portions of the gate and data lines;  
a first electrode in each pixel region on the substrate;  
a bank surrounding each pixel region; and  
a power line in parallel with the gate line, the power line being configured to supply a driving voltage to each pixel region.

11. The OLED of claim 10, wherein the bank has a same width at boundary portions among the at least three pixel regions.

12. The OLED of claim 10, wherein the driving voltage is supplied from both ends of the power line.

13. The OLED of claim 10, wherein the power line and the gate line are at a same layer and are formed of a same material.

14. The OLED of claim 10, further comprising an auxiliary electrode spaced apart from the first electrode and electrically connected with the power line.

15. The OLED of claim 14, further comprising:  
a gate insulating layer on the gate line and the power line; and  
a planarization layer on the gate insulating layer,  
wherein the data line is between the gate insulating layer and the planarization layer, and  
wherein the first electrode is on the planarization layer.

16. The OLED of claim 15, wherein:  
the gate insulating layer and the planarization layer include a contact hole exposing a portion of the power line; and

the power line is connected to the auxiliary electrode through the contact hole.

17. The OLED of claim 10, further comprising an organic light-emitting layer on the first electrode.

18. The OLED of claim 17, wherein the organic light-emitting layer is laminated using a soluble process.

19. An organic light-emitting display device (OLED), comprising:

a substrate including pixel regions emitting a same color on each column line;  
a first electrode in each pixel region on the substrate;  
a bank surrounding each pixel group including neighboring pixel regions on each column line; and  
an organic light-emitting layer on the first electrode and corresponding to each pixel group.

20. The OLED of claim 19, further comprising:  
a data line in a column direction;  
a gate line in a row direction; and  
a power line in parallel with the gate line.

21. The OLED of claim 20, wherein the bank has a same width at boundary portions among pixel regions emitting different colors on a row line.

**22.** The OLED of claim **20**, further comprising an auxiliary electrode spaced apart from the first electrode and electrically connected with the power line.

**23.** The OLED of claim **19**, further comprising:

a data line in a column direction;

a gate line in a row direction; and

a power line in parallel with the data line.

**24.** The OLED of claim **19**, further comprising an insulation pattern between neighboring pixel regions within each pixel group, the insulation pattern covering edge portions of the neighboring pixel regions within each pixel group.

**25.** The OLED of claim **19**, wherein the organic light-emitting layer is laminated using a soluble process.

**26.** An organic light-emitting display device (OLED), comprising:

a substrate including pixel regions emitting a same color on each column line;

a first electrode in each pixel region on the substrate;

a bank between neighboring pixel regions on each column line, the bank including:

a first part; and

second parts at each side of the first part and each having a thickness less than that of the first part; and an organic light-emitting layer on the first electrode and the second parts.

**27.** The OLED of claim **26**, further comprising:

a data line in a column direction;

a gate line in a row direction; and

a power line parallel with the gate line.

**28.** The OLED of claim **27**, wherein the bank has a same width at boundary portions among pixel regions emitting different colors on a row line.

**29.** The OLED of claim **27**, further comprising an auxiliary electrode spaced apart from the first electrode and electrically connected with the power line.

**30.** The OLED of claim **26**, further comprising:

a data line in a column direction;

a gate line in a row direction; and

a power line parallel with the data line.

**31.** The OLED of claim **26**, wherein the organic light-emitting layer is laminated using a soluble process.

\* \* \* \* \*

|                |                                                                                               |         |            |
|----------------|-----------------------------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | 有机发光二极管显示装置                                                                                   |         |            |
| 公开(公告)号        | <a href="#">US20170194414A1</a>                                                               | 公开(公告)日 | 2017-07-06 |
| 申请号            | US15/395042                                                                                   | 申请日     | 2016-12-30 |
| [标]申请(专利权)人(译) | 乐金显示有限公司                                                                                      |         |            |
| 申请(专利权)人(译)    | LG DISPLAY CO. , LTD.                                                                         |         |            |
| 当前申请(专利权)人(译)  | LG DISPLAY CO. , LTD.                                                                         |         |            |
| [标]发明人         | LEE A RYOUNG<br>YANG KI SOUB<br>SHIM DA HYE                                                   |         |            |
| 发明人            | LEE, A-RYOUNG<br>YANG, KI-SOUB<br>SHIM, DA-HYE                                                |         |            |
| IPC分类号         | H01L27/32 H01L51/00                                                                           |         |            |
| CPC分类号         | H01L27/3276 H01L27/3246 H01L51/5012 H01L51/0003 H01L27/3211 H01L51/0005 H01L27/3288 H01L51/52 |         |            |
| 优先权            | 1020150189787 2015-12-30 KR<br>1020160162704 2016-12-01 KR                                    |         |            |
| 其他公开文献         | US10020356                                                                                    |         |            |
| 外部链接           | <a href="#">Espacenet</a> <a href="#">USPTO</a>                                               |         |            |

#### 摘要(译)

提供一种有机发光显示装置。有机发光显示装置 ( OLED ) 包括：基板，包括沿水平方向布置的至少三个像素区域；基板上的每个像素区域中的第一电极；围绕每个像素区域的堤岸；以及电源线，在基板上的每个像素区域的下侧的水平部分，电源线被配置为向每个像素区域提供驱动电压。

