



US009859346B2

(12) **United States Patent**
Seo et al.

(10) **Patent No.:** **US 9,859,346 B2**
(45) **Date of Patent:** **Jan. 2, 2018**

(54) **ORGANIC LIGHT-EMITTING DIODE
DISPLAY AND METHOD OF
MANUFACTURING THE SAME**

(58) **Field of Classification Search**
CPC H01L 27/32; H01L 51/52; H01L 51/56;
H01L 27/3246; H01L 51/5253
See application file for complete search history.

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si,
Gyeonggi-do (KR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(72) Inventors: **Tae-an Seo**, Yongin-si (KR); **Kihyun Kim**, Yongin-si (KR); **Juchan Park**, Yongin-si (KR); **Younggug Seol**, Yongin-si (KR); **Pilsuk Lee**, Yongin-si (KR); **Jinhwan Choi**, Yongin-si (KR)

2011/0140113 A1 6/2011 Park
2012/0268000 A1 10/2012 Choi et al.
2013/0248867 A1* 9/2013 Kim H01L 51/5253
257/59
2013/0300697 A1 11/2013 Kim et al.
(Continued)

(73) Assignee: **Samsung Display Co., Ltd.**,
Gyeonggi-do (KR)

FOREIGN PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

KR 10-2002-0022287 A 3/2002
KR 10-2011-0067404 A 6/2011
KR 10-2012-0119097 A 10/2012
(Continued)

Primary Examiner — Roy Potter

Assistant Examiner — Paul Patton

(21) Appl. No.: **15/255,632**

(22) Filed: **Sep. 2, 2016**

(74) *Attorney, Agent, or Firm* — Knobbe, Martens, Olson & Bear, LLP

(65) **Prior Publication Data**

US 2017/0077195 A1 Mar. 16, 2017

(30) **Foreign Application Priority Data**

Sep. 15, 2015 (KR) 10-2015-0130596

(51) **Int. Cl.**

H01L 27/32 (2006.01)

H01L 51/52 (2006.01)


(52) **U.S. Cl.**

CPC **H01L 27/3246** (2013.01); **H01L 51/5253** (2013.01); **H01L 51/5256** (2013.01); **H01L 2251/5338** (2013.01)

(57) **ABSTRACT**

An organic light-emitting diode (OLED) display and a method of manufacturing the same are disclosed. In one aspect, the OLED display includes an OLED formed over a substrate, the OLED including a first electrode, a second electrode formed over the first electrode and an intermediate layer interposed between the first and second electrodes. A pixel defining layer is formed over the substrate and adjacent to the OLED, and a protection layer is formed over the second electrode and configured to protect the OLED. A thin-film encapsulating layer is formed over the protection layer and sealing the OLED so as to protect the OLED from the environment, at least a part of the thin-film encapsulating layer contacting the pixel defining layer.

18 Claims, 8 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS


2014/0217373 A1 8/2014 Youn et al.
2014/0232956 A1 8/2014 Kwon et al.

FOREIGN PATENT DOCUMENTS

KR 10-2013-0127050 A 11/2013
KR 10-2014-0039470 A 4/2014
KR 10-2014-0064156 A 5/2014
KR 10-2014-0099164 A 8/2014
KR 10-2014-0103025 A 8/2014
KR 10-2014-0129647 A 11/2014
KR 10-2014-0148176 A 12/2014

* cited by examiner

FIG. 1



2
C
H
E




FIG. 3




FIG. 4




FIG. 5




FIG. 7




FIG. 8





FIG. 9



ORGANIC LIGHT-EMITTING DIODE DISPLAY AND METHOD OF MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of Korean Patent Application No. 10-2015-0130596, filed on Sep. 15, 2015, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

Field

The described technology generally relates to an organic light-emitting diode (OLED) display and a method of manufacturing the same.

Description of the Related Technology

An OLED display includes an OLED having a hole-injecting electrode, an electron-injecting electrode, and an interposed organic light-emitting layer. The OLED emits light as excitons, generated by the combination of holes injected by the hole-injecting electrode and electrons injected by the electron-injecting electrode at the organic light-emitting layer, are transitioned from excited state to ground state.

Since OLED technology requires no separate light source, there are desirable characteristics such as being driven with a low voltage, being lightweight and thin, and having a wide viewing angle, high contrast, and rapid response rate. Therefore, an OLED display is being spotlighted as a next-generation display apparatus.

SUMMARY OF CERTAIN INVENTIVE ASPECTS

One inventive aspect relates to an OLED display and a method of manufacturing the same.

Another aspect is an OLED display that includes a substrate; an OLED, which is formed on the substrate and includes a first electrode, an intermediate layer, and a second electrode; a pixel defining layer, which is formed on the substrate and defines a pixel region including the OLED and emitting light and a non-pixel region; a protection layer, which is formed on the second electrode and protects the OLED; and a thin-film encapsulating layer, which is formed on the protection layer and seals the OLED to protect the OLED from outside, wherein the thin-film encapsulating layer is formed to contact the pixel defining layer at at least a region.

The first electrode may be formed between the pixel defining layers adjacent to each other, the intermediate layer may be formed on the first electrode, and the second electrode and the protection layer may be formed on the intermediate layer and the pixel defining layer.

The protection layer may be formed of a LiF-containing material.

The second electrode and the protection layer may be pattern-formed, such that a first opening is formed at at least portions thereof contacting the pixel defining layer.

The thin-film encapsulating layer may be formed to directly contact the pixel defining layer at the first opening.

The thin-film encapsulating layer may be formed by alternately stacking a plurality of inorganic layers and organic layers.

The thin-film encapsulating layer may include an inorganic layer; and an organic layer, which is formed on the inorganic layer, wherein the inorganic layer contacts the pixel defining layer at the first opening.

A thin-film transistor including an active layer, a gate electrode, a source electrode, and a drain electrode may be formed on the substrate, and the OLED display may further include a gate insulation layer, which is formed between the active layer and the gate electrode; an interlayer insulation layer, which is formed between the gate electrode and the source and drain electrodes; and a via layer, which is formed on the source electrode and the drain electrode.

The substrate may include a bending portion at which a bending occurs, and the interlayer insulation layer and the via layer may be pattern-formed, such that a second opening is formed at the bending portion.

The thin-film encapsulating layer may contact the gate insulation layer at the second opening.

The thin-film encapsulating layer may contact side surfaces of the interlayer insulation layer and the via layer at the second opening.

The thin-film encapsulating layer may include an inorganic layer and an organic layer formed on the inorganic layer, and the inorganic layer may contact the gate insulation layer at the second opening.

Another aspect is a method of manufacturing an OLED display, the method including providing a substrate; forming a thin-film transistor and a via layer on the substrate; forming a pixel defining layer, which defines a pixel region and a non-pixel region, on the via layer; forming an OLED on the via layer; forming a protection layer on the OLED to cover the pixel defining layer; and forming a thin-film encapsulating layer that seals the OLED from the top of the protection layer to protect the OLED from outside, wherein the forming of the OLED includes forming a first electrode between the pixel defining layers adjacent to each other; forming an intermediate layer on the first electrode; and forming a second electrode on the intermediate layer and the first electrode, and, in the forming of the second electrode and in the forming of the protection layer, the second electrode and the protection layer are pattern-formed, such that at least portions thereof contacting the pixel defining layer are removed and a first opening is formed thereat.

The protection layer may be formed of a LiF-containing material.

In the forming of the thin-film encapsulating layer, the thin-film encapsulating layer may be formed to contact the pixel defining layer at the first opening.

The forming of the thin-film encapsulating layer may include forming an inorganic layer on the protection layer; and forming an organic layer on the inorganic layer, and the inorganic layer is formed to contact the pixel defining layer at the first opening.

The substrate may include a bending portion at which a bending occurs, and the method may further include, after the providing of the substrate, forming a gate insulation layer on the substrate, forming an interlayer insulation layer on the gate insulation layer; and forming a via layer on the interlayer insulation layer.

In the forming of the interlayer insulation layer and in the forming of the via layer, the interlayer insulation layer and the via layer may be pattern-formed to be partially removed at the bending portion, such that a second opening is formed at the second electrode and the protection layer.

In the forming of the thin-film encapsulating layer, the thin-film encapsulating layer may be formed to contact the gate insulation layer at the second opening.

In the forming of the thin-film encapsulating layer, the thin-film encapsulating layer may be formed to contact side surfaces of the interlayer insulation layer and the via layer at the second opening.

Another aspect is an organic light-emitting diode (OLED) display comprising: a substrate; an OLED formed over the substrate and comprising a first electrode, a second electrode formed over the first electrode and an intermediate layer interposed between the first and second electrodes; a pixel defining layer formed over the substrate and adjacent to the OLED; a protection layer formed over the second electrode and configured to protect the OLED; and a thin-film encapsulating layer formed over the protection layer and sealing the OLED so as to protect the OLED from the environment, wherein at least a part of the thin-film encapsulating layer contacts the pixel defining layer.

In the above OLED display, the first electrode is formed between adjacent pixel defining layers, wherein the intermediate layer is formed over the first electrode, wherein the second electrode and the protection layer are formed over the intermediate layer and the pixel defining layer.

In the above OLED display, the protection layer is formed of LiF.

In the above OLED display, the second electrode and the protection layer have a first opening formed over the pixel defining layer, the first opening overlaps at least a part of the thin-film encapsulating layer contacts the pixel defining layer.

In the above OLED display, the thin-film encapsulating layer directly contacts the pixel defining layer at the first opening.

In the above OLED display, the thin-film encapsulating layer comprises: an inorganic layer; and an organic layer formed over the inorganic layer, wherein the inorganic layer contacts the pixel defining layer at the first opening.

In the above OLED display, the thin-film encapsulating layer comprises a plurality of inorganic layers and a plurality of organic layers that are alternately stacked.

The above OLED display further comprises: a thin-film transistor (TFT) including an active layer, a gate electrode, a source electrode, and a drain electrode is formed over the substrate; a gate insulation layer formed between the active layer and the gate electrode; an interlayer insulation layer formed between the gate electrode and the source and drain electrodes; and a via layer formed over the source and drain electrodes.

In the above OLED display, the substrate comprises a bending portion configured to bend, wherein the interlayer insulation layer and the via layer have a second opening formed over the bending portion.

In the above OLED display, the thin-film encapsulating layer contacts the gate insulation layer at the second opening.

In the above OLED display, the thin-film encapsulating layer contacts side surfaces of the interlayer insulation layer and the via layer at the second opening.

In the above OLED display, the thin-film encapsulating layer comprises an inorganic layer and an organic layer formed over the inorganic layer, wherein the inorganic layer contacts the gate insulation layer at the second opening.

Another aspect is a method of manufacturing an organic light-emitting diode (OLED) display, the method comprising: providing a substrate; forming a thin-film transistor (TFT) and a via layer over the substrate; forming a pixel defining layer over the via layer; forming an OLED over the via layer; forming a protection layer over the OLED so as to cover the pixel defining layer; and forming a thin-film

encapsulating layer that seals the OLED and the protection layer to protect the OLED from the environment. The forming of the OLED comprises: forming a first electrode between adjacent pixel defining layers; forming an intermediate layer over the first electrode; and forming a second electrode over the intermediate layer and the first electrode, and wherein the second electrode and the protection layer are pattern-formed such that at least portions thereof contacting the pixel defining layer are removed and a first opening is formed therein.

In the above method, the protection layer is formed of LiF.

In the above method, the thin-film encapsulating layer contacts the pixel defining layer at the first opening.

In the above method, the forming of the thin-film encapsulating layer comprises: forming an inorganic layer over the protection layer; and forming an organic layer over the inorganic layer, wherein the inorganic layer contacts the pixel defining layer at the first opening.

In the above method, the substrate comprises a bending portion configured to bend, wherein the method further comprises: after the providing of the substrate, forming a gate insulation layer over the substrate; forming an interlayer insulation layer over the gate insulation layer; and forming a via layer over the interlayer insulation layer.

In the above method, the interlayer insulation layer and the via layer are pattern-formed to be partially removed at the bending portion such that a second opening is formed in the second electrode and the protection layer.

In the above method, the thin-film encapsulating layer contacts the gate insulation layer at the second opening.

In the above method, the thin-film encapsulating layer contacts side surfaces of the interlayer insulation layer and the via layer at the second opening.

Another aspect is an organic light-emitting diode (OLED) display comprising: a substrate; a plurality of OLEDs formed over the substrate; a pixel defining layer interposed between the OLEDs; a thin-film encapsulating layer formed over the pixel defining layer and sealing the OLED so as to protect the OLEDs from the environment, wherein the thin-film encapsulating layer contacts the pixel defining layer through a plurality of openings.

In the above OLED display, the thin-film encapsulating layer includes a first portion formed over the openings and a second portion formed over the OLEDs, wherein the first portion is thicker than the second portion.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic sectional view of an OLED display according to an exemplary embodiment.

FIG. 2 is a detailed sectional view diagram showing the OLED display of FIG. 1.

FIG. 3 is a schematic plan view diagram showing a region for forming a second electrode, a protection layer, and a pixel defining layer of the OLED display of FIG. 2.

FIG. 4 shows a first opening formed in a second electrode and a protection layer according to another exemplary embodiment.

FIG. 5 shows a first opening formed in a second electrode and a protection layer according to another exemplary embodiment.

FIG. 6 is a sectional view of an OLED display according to another exemplary embodiment.

FIG. 7 is a perspective view of an OLED display according to another exemplary embodiment.

FIG. 8 is a detailed schematic sectional view of the OLED display shown in FIG. 7.

FIG. 9 is a detailed schematic sectional view diagram showing the bent OLED display around a bending portion.

DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

Reference will now be made in detail to exemplary embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present exemplary embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the exemplary embodiments are merely described below, by referring to the figures, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

As the present disclosure allows for various changes and numerous embodiments, particular embodiments will be illustrated in the drawings and described in detail in the written description. However, this is not intended to limit the present disclosure to particular modes of practice, and it is to be appreciated that all changes, equivalents, and substitutes that do not depart from the spirit and technical scope of the present disclosure are encompassed in the present disclosure. In the description of the present disclosure, certain detailed explanations of the related art are omitted when it is deemed that they may unnecessarily obscure the essence of the present disclosure.

While such terms as “first,” “second,” etc., may be used to describe various components, such components must not be limited to the above terms. The above terms are used only to distinguish one component from another.

The terms used in the present specification are merely used to describe particular embodiments, and are not intended to limit the present disclosure. An expression used in the singular encompasses the expression of the plural, unless it has a clearly different meaning in the context. In the present specification, it is to be understood that the terms such as “including” or “having,” etc., are intended to indicate the existence of the features, numbers, steps, actions, components, parts, or combinations thereof disclosed in the specification, and are not intended to preclude the possibility that one or more other features, numbers, steps, actions, components, parts, or combinations thereof may exist or may be added.

Hereinafter, the present disclosure will be described in detail by explaining preferred embodiments of the present disclosure with reference to the attached drawings. Like reference numerals in the drawings denote like elements. In this disclosure, the term “substantially” includes the meanings of completely, almost completely or to any significant degree under some applications and in accordance with those skilled in the art. Moreover, “formed, disposed or positioned over” can also mean “formed, disposed or positioned on.” The term “connected” includes an electrical connection.

FIG. 1 is a schematic sectional view of an OLED display according to an exemplary embodiment.

An OLED display according to the present embodiment includes a substrate **100**, a display **200** formed on the substrate **100**, and a thin-film encapsulating layer **300** that seals the display **200**.

The substrate **100** may be formed of various materials. For example, the substrate **100** may be formed of a glass or one of various insulation materials or may be formed of a metal thin-film.

According to a selective embodiment, the substrate **100** is formed of a flexible material. For example, the substrate **100** is formed of an organic material.

According to a selective embodiment, the substrate **100** is formed of at least one of a silicone-based polymer, polyurethane, polyurethane acrylate, an acrylate polymer, and an acrylate terpolymer. Here, the silicon-based polymer may include polydimethylsiloxane (PDMS) and hexamethyldisiloxane (HMDSO), for example.

The OLED display according to the present embodiment may include the flexible substrate **100**, and thus the OLED display may be 2-dimensionally elongated.

According to a selective embodiment, the substrate **100** is formed of a material having a Poisson's ratio of about 0.4 or higher. The Poisson's ratio is the ratio of transverse contraction strain to longitudinal extension strain in the direction of stretching force. By forming the substrate **100** using a material having a Poisson's ratio about 0.4 or higher (that is, by forming the substrate **100** to be highly stretchable), flexibility of the substrate **100** may be improved and the substrate **100** may have a bending portion. Therefore, a display apparatus may easily include a bending portion.

In the OLED display according to the present embodiment, the substrate **100** is formed to be flexible as described above. Therefore, the OLED display according to the present embodiment may be a flat display apparatus or a flexible display apparatus as shown in FIGS. 1A to 1C.

However, flexibility of an OLED display according to an exemplary embodiment is not limited thereto. An OLED display may be entirely bent as shown in FIG. 1B or two opposite ends of an OLED display may be folded as shown in FIG. 1C.

The display **200** is formed on the substrate **100**. The display **200** generates visible rays to be visually recognized by a user. The display **200** may include various devices, e.g., an OLED or a liquid crystal display (LCD) device.

In an OLED display according to an exemplary embodiment, the display **200** may include an OLED. Detailed descriptions of the OLED will be given below.

A thin-film encapsulating layer **300** may be formed on the display **200** for completely sealing the display **200** to protect the display **200** from outside moisture or oxygen.

Since the display **200** is protected by the thin-film encapsulating layer **300** in which a plurality of thin-films are stacked, flexibility of an OLED display may be easily secured as shown in FIGS. 1A to 1C.

According to a selective embodiment, the thin-film encapsulating layer **300** may be formed on the display **200**, where two opposite ends of the thin-film encapsulating layer **300** may closely contact the substrate **100**. Structure and function of the thin-film encapsulating layer **300** will be described below with reference to FIG. 2.

FIG. 2 is a sectional view diagram showing the OLED display **1000** according to an exemplary embodiment in closer detail than FIG. 1.

As shown in FIG. 2, in the OLED display **1000**, a buffer layer **110** may be formed on the substrate **100**. The buffer layer **110** may prevent spreading of impurity ions, prevent permeation of moisture or outside atmosphere, and function as a barrier layer for planarizing a surface and/or a blocking layer.

A thin-film transistor TFT may be formed on the buffer layer **110**. An active layer A of the thin-film transistor TFT

may be formed of polysilicon and may include a channel that is not doped with an impurity and source and drain regions, which are formed next to two opposite ends of the channel layer and are doped with impurities. Here, types of impurities may vary according to type of the thin-film transistor TFT, where an N-type impurity or a P-type impurity may be employed.

After the active layer A is formed, a gate insulation layer **210** may be formed on the active layer A.

The gate insulation layer **210** may include a single layer or multiple layers formed of an inorganic material, e.g., a silicon oxide or a silicon nitride. The gate insulation layer **210** insulates the active layer A from a gate electrode G on the active layer A.

After the gate insulation layer **210** is formed, the gate electrode G may be formed on the gate insulation layer **210**. The gate electrode G may be formed via a photolithography operation and an etching operation.

Materials constituting the gate electrode G may be formed of at least one or more metals of molybdenum (Mo), aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), titanium (Ti), tungsten (W), and copper (Cu).

After the gate electrode G is formed, an interlayer insulation layer **230** may be formed throughout a surface of the substrate **100**.

The interlayer insulation layer **230** may be formed of an inorganic material. For example, the interlayer insulation layer **230** is formed of a metal oxide or a metal nitride. For example, the inorganic material may be formed of silicon oxide (SiO₂), silicon nitride (SiN_x), silicon oxynitride (SiON), aluminum oxide (Al₂O₃), titanium oxide (TiO₂), tantalum oxide (Ta₂O₅), hafnium oxide (HfO₂), or zirconium oxide (ZrO₂).

The interlayer insulation layer **230** may include a single layer or multiple layers formed of an inorganic material, such as a silicon oxide (SiO₂) and/or a silicon nitride (SiN_x). According to some embodiments, the interlayer insulation layer **230** may have a double layer structure including SiO_x/SiN_y or SiN_x/SiO_y.

A source electrode S and a drain electrode D of the thin-film transistor TFT may be arranged on the interlayer insulation layer **230**.

The source electrode S and the drain electrode D may be formed of one or more metals of aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), molybdenum (Mo), titanium (Ti), tungsten (W), and copper (Cu).

A via layer **250** is formed throughout a surface of the substrate **100** to cover the source electrode S and the drain electrode D. The via layer **250** may protect the thin-film transistor TFT.

An OLED may be arranged on the via layer **250**. According to the embodiment shown in FIG. 2, the OLED is connected to the drain electrode D via a via hole.

The OLED may include a first electrode **281**, an intermediate layer **283** including an organic light-emitting layer, and a second electrode **285**.

Holes and electrons injected by the first electrode **281** and the second electrode **285** of the OLED are combined with each other at the organic light-emitting layer of the intermediate layer **283**, thereby emitting light.

The first electrode **281** and the second electrode **285** may be formed of various conductive materials.

According to a selective embodiment, the first electrode **281** and/or the second electrode **285** is formed of a phototransmissive material or a reflective material.

In case of a top emission structure for embodying an image toward the second electrode **285**, the first electrode **281** may be arranged as a reflective electrode. To this end, the first electrode **281** includes a reflective film formed of an alloy containing Al or Ag.

In case of using the first electrode **281** as an anode, the first electrode **281** is formed to include a layer formed of a metal oxide with a high work function (absolute value), such as ITO, IZO, and ZnO. In case of using the first electrode **281** as a cathode, a highly conductive metal with a low work function (absolute value), such as Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, or Ca, is used to form the first electrode **281**. Therefore, in this case, the above-stated reflective layer is not necessary.

The second electrode **285** may be arranged as a phototransmissive electrode. To this end, the second electrode **285** may include a semi-transmissive reflective layer, which is a thin-film formed of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, or Ca, or a phototransmissive metal oxide, such as ITO, IZO, or ZnO.

In case of using the first electrode **281** as an anode, the second electrode **285** is used as a cathode. In case of using the first electrode **281** as a cathode, the second electrode **285** is used as an anode.

The intermediate layer **283** may be formed between the first electrode **281** and the second electrode **285** and may include an organic light-emitting layer.

According to a selective embodiment, the intermediate layer **283** may include an organic light-emitting layer and may further include at least one of common layers including a hole injection layer (HIL), a hole transport layer (HTL), a hole blocking layer (Buffer), an electron transport layer (ETL), and an electron injection layer (EIL). However, the present embodiment is not limited thereto. For example, the intermediate layer **283** may include a light-emitting layer and may further include common layers that perform various other functions.

According to a selective embodiment, common layers including a hole injection layer (HIL) and a hole transport layer (HTL) are formed on the first electrode **281**, and an light-emitting layer is formed on the hole transport layer (HTL).

According to a selective embodiment, a common layer, which is a hole blocking layer (Buffer), may be formed on the light-emitting layer, and common layers including an electron transport layer (ETL) and an electron injection layer (EIL) may be formed on the hole blocking layer (Buffer).

The hole injection layer (HIL) may be formed of a phthalocyanine compound, such as copper phthalocyanine, or a starburst amines of type TCTA, such as m-MTDATA or m-MTDAPB.

The hole transport layer (HTL) may be formed of N,N'-bis (3-methylphenyl)-N, N'-diphenyl-[1,1-biphenyl]-4,4'-diamine (TPD) or N,N'-di (naphthalene-1-yl)-N,N'-diphenyl benzidine (α -NPD).

The electron injection layer (EIL) may be formed of LiF, NaCl, CsF, Li₂O, BaO, or Liq.

The electron transport layer (ETL) may be formed of Alq₃.

The OLED display **1000** according to the present embodiment may further include a pixel defining layer **270** formed at edges of the first electrode **281**. The pixel defining layer **270** may define a pixel region, in which an OLED is arranged and light is emitted, and a non-pixel region.

According to a selective embodiment, the first electrode **281** is deposited between the pixel defining layer **270**, and the intermediate layer **283** is formed on the first electrode **281**.

Furthermore, the second electrode **285** may be formed on the intermediate layer **283** and the pixel defining layer **270**.

A protection layer **290** may be formed on the second electrode **285** and cover and protect the OLED.

According to a selective embodiment, the protection layer **290** is formed of a LiF-containing material.

According to a selective embodiment, the protection layer **290** is a buffer layer for protecting the OLED and is formed of various deposition methods, such as evaporation.

In the OLED display **1000** according to the present embodiment, the protection layer **290** is formed throughout a surface of the substrate **100** to cover the pixel defining layer **270** together with the second electrode **285**.

In the OLED display **1000** according to the present embodiment, first openings **OP1** are formed at at least portions of the second electrode **285** and the protection layer **290** contacting the pixel defining layer **270**.

For example, at least portions of the second electrode **285** and the protection layer **290** covering the pixel defining layer **270** are removed to expose the pixel defining layer **270** arranged therebelow.

According to a selective embodiment, in the OLED display **1000** shown in FIG. 2, portions of the second electrode **285** and the protection layer **290** located on the top surface of the pixel defining layer **270** are removed, thereby forming the first opening **OP1**.

However, locations and numbers of the first opening **OP1** are limited thereto, and the first opening **OP1** may be formed at anywhere at which the second electrode **285** and the protection layer **290** contact the pixel defining layer **270**.

For example, the first opening **OP1** may be formed at anywhere at which the pixel defining layer **270** may be exposed by removing portions of the second electrode **285** and the protection layer **290**.

A thin-film encapsulating layer **300** that seals the OLED to protect the OLED from outside moisture or oxygen may be formed on the OLED and the protection layer **290**.

According to a selective embodiment, the thin-film encapsulating layer **300** has a structure in which a plurality of thin-films are stacked, where an inorganic layer **310** and an organic layer **330** may be alternately stacked.

According to a selective embodiment, as shown in FIG. 2, the thin-film encapsulating layer **300** is formed by sequentially stacking the inorganic layer **310** and the organic layer **330**.

Although the OLED display **1000** according to the present embodiment includes one inorganic layer **310** and one organic layer **330**, a number of the thin-films are not limited thereto, and a larger number of the thin-films are alternately stacked.

In the OLED display **1000** according to the present embodiment, the inorganic layer **310** is formed on the protection layer **290**, and the organic layer **330** is formed on the inorganic layer **310**.

The inorganic layer **310** may impregnably block permeation of oxygen or moisture, whereas the organic layer **330** may absorb stress of the inorganic layer **310** and provide flexibility to the organic layer **330**.

The inorganic layer **310** may include a single layer or stacked layers formed of a metal oxide or a metal nitride. According to a selective embodiment, the inorganic layer **310** is formed of any one of SiN_x , Al_2O_3 , SiO_2 , and TiO_2 .

The organic layer **330** is formed of a polymer. For example, the organic layer **330** includes a single layer or stacked layers formed of any one of polyethylene terephthalate, polyimide, polycarbonate, epoxy, polyethylene, and polyacrylate. For example, the organic layer **330** is formed of polyacrylate. For example, the organic layer **330** is formed of a polymerized monomer composition including a diacrylate monomer and a triacrylate monomer. The monomer composition may further include a monoacrylate-based monomer. Furthermore, the monomer composition may further contain a photoinitiator known in the art, e.g., TPO. However, the present disclosure is not limited thereto.

For example, the OLED may be protected by the inorganic layer **310** and, at the same time, flexibility of the OLED display **1000** may be improved by the organic layer **330**.

At least a portion of the thin-film encapsulating layer **300** of the OLED display **1000** according to the present embodiment may directly contact the exposed portions of the pixel defining layer **270**.

As described above, according to a selective embodiment, at least portions of the second electrode **285** and the protection layer **290** contacting the pixel defining layer **270** are removed to expose the pixel defining layer **270**.

For example, the first opening **OP1** is formed at at least portions of the second electrode **285** and the protection layer **290**, and the pixel defining layer **270** is exposed at the first opening **OP1**. Therefore, the thin-film encapsulating layer **300** may be formed to directly contact the pixel defining layer **270**.

According to a selective embodiment, as the thin-film encapsulating layer **300** includes the inorganic layer **310** and the organic layer **330** formed on the inorganic layer **310**, the thin-film encapsulating layer **300** is formed to directly contact the pixel defining layer **270**.

Therefore, since the inorganic layer **310** is formed to directly contact the pixel defining layer **270**, adhesion between the thin-film encapsulating layer **300** and the display **200** is improved.

If adhesion between the thin-film encapsulating layer **300** and the display **200** is insufficient when the OLED display **1000** is flexible and bent, the thin-film encapsulating layer **300** is exfoliated due to stress.

For example, if the thin-film encapsulating layer **300** is formed to contact the protection layer **290** that is formed to have a small thickness in an evaporation operation, when the OLED display bending occurs the thin-film encapsulating layer **300** is exfoliated due to insufficient adhesion between the thin-film encapsulating layer **300** and the protection layer **290**. As a result, if the thin-film encapsulating layer **300** is exfoliated in a flexible display apparatus, the OLED is not sufficiently protected, and thus reliability of the flexible display apparatus can degrade.

Here, if at least a portion of the thin-film encapsulating layer **300** is directly adhered to the pixel defining layer **270**, which is arranged below the thin-film encapsulating layer **300** and has a certain thickness, adhesion is improved, and thus thin-film encapsulating layer **300** will not be exfoliated.

Although not shown, spacers (not shown) may be further arranged on the pixel defining layer **270**. According to a selective embodiment, spacers may not be formed on all of the pixel defining layers **270** and may be arbitrarily formed on some of the pixel defining layers **270**.

The spacers (not shown) may be arranged to protrude upward from the pixel defining layer **270** and may be arranged to prevent deterioration of display characteristics due to external shocks.

According to a selective embodiment, the spacer may be formed of the same material in a same operation as the pixel defining layer 270. For example, the pixel defining layer 270 and the spacer may be substantially simultaneously or concurrently formed in an exposing operation by adjusting exposure by using a half-tone mask. However, the present disclosure is not limited thereto. The pixel defining layer 270 and the spacer may be sequentially or separately formed and may be independent structures formed of different materials.

According to a selective embodiment, the first opening OP1 is formed at portions of the second electrode 285 and the protection layer 290 contacting the pixel defining layer 270, where the first opening OP1 may be formed at a portion without the spacer.

At portions with the spacers, the spacers are formed on the pixel defining layer 270, and thus the thin-film encapsulating layer 300 is not exfoliated. Therefore, it is not necessary to form the first opening OP1.

Therefore, the first opening OP1 may be formed at at least portions of the second electrode 285 and the protection layer 290 contacting the pixel defining layer 270 from among portions without the spacers.

FIG. 3 is a schematic plan view diagram showing a region for forming the second electrode 285, the protection layer 290, and the pixel defining layer 270 of the OLED display 1000 of FIG. 2. FIGS. 4 and 5 are schematic plan view diagrams showing a second electrode, a protection layer, and a region for forming a pixel defining layer of OLED displays according to other exemplary embodiments.

As shown in FIG. 3, the pixel defining layer 270 may be formed, and the second electrode 285 and the protection layer 290 may be formed on the pixel defining layer 270 to cover the pixel defining layer 270.

According to a selective embodiment, the second electrode 285 and the protection layer 290 may be formed on a same region. Therefore, for convenience of explanation, the second electrode 285 and the protection layer 290 will be shown as a single component.

In the OLED display 1000 according to the present embodiment, the first opening OP1 may be formed at at least portions of the second electrode 285 and the protection layer 290. As described above, the first opening OP1 may be formed at portions of the second electrode 285 and the protection layer 290 contacting the pixel defining layer 270 and may be formed between a pixel region and another pixel region adjacent thereto.

Although FIG. 3 shows the first opening OP1 that is formed in the second electrode 285 and the protection layer 290 in the OLED display 1000 shown in FIG. 2, locations and numbers of the first opening OP1 are not limited thereto.

FIG. 4 shows a first opening OP1 formed in a second electrode 285a and a protection layer 290a according to another exemplary embodiment.

Although an OLED display according to the present embodiment has a diamond-shaped pixel region like the embodiment shown in FIG. 3, the first openings OP1 are not formed between pixel regions adjacent to each other, but are formed at regions adjacent to each pixel region.

For example, according to a selective embodiment, two first openings OP1 are formed at regions adjacent to each pixel region.

In the OLED display according to the embodiment shown in FIG. 4, a thin-film encapsulating layer (300; refer to FIG. 2) also directly contact the exposed pixel defining layer 270 at the first opening OP1, adhesion between the thin-film encapsulating layer 300 and the pixel defining layer 270 is

improved, and thus the thin-film encapsulating layer 300 will not be exfoliated even if the OLED display is bent.

FIG. 5 shows a first opening OP1 formed in a second electrode 285b and a protection layer 290b according to another exemplary embodiment.

An OLED display according to the present embodiment has rectangular pixel regions unlike the embodiments shown in FIGS. 3 and 4. In this case, distances between pixel regions may be reduced compared to a case where pixel regions are formed to have a diamond-like shape.

Therefore, according to a selective embodiment, size of the first opening OP1 formed in the second electrode 285b and the protection layer 290b may be reduced.

For example, the first opening OP1 may be formed between rectangular pixel regions adjacent to each other, where size of the first opening OP1 may be smaller than those in the previous embodiments. However, locations and numbers of the first openings OP1 are not limited thereto, and the first openings OP1 may be formed at anywhere as long as the first openings OP1 are formed in the second electrode 285b and the protection layer 290b and expose the pixel defining layer 270 therebelow.

In the OLED display according to the embodiment shown in FIG. 5, a thin-film encapsulating layer (300; refer to FIG. 2) also directly contact the exposed pixel defining layer 270 at the first opening OP1, adhesion between the thin-film encapsulating layer 300 and the pixel defining layer 270 is improved, and thus the thin-film encapsulating layer 300 will not be exfoliated even if the OLED display is bent.

FIG. 6 is a detailed sectional view of an OLED display 2000 according to another exemplary embodiment. In FIG. 6, reference numerals identical to those shown in FIG. 2 denote same components as those shown in FIG. 2. Therefore, for simplification of explanation, detailed descriptions thereof will be omitted.

Like the OLED display 1000 according to the embodiment shown in FIG. 2, in the OLED display 2000 according to the present embodiment, a buffer layer 110, a semiconductor layer A, a gate insulation layer 210, a gate electrode G, an interlayer insulation layer 230, a source electrode S, a drain electrode D, a via layer 250, and an OLED are sequentially formed on a substrate 100.

According to a selective embodiment, a pixel defining layer 270 for defining a pixel region, in which an OLED is arranged and light is emitted, and a non-pixel region are formed on the via layer 250.

According to a selective embodiment, the OLED includes a first electrode 281, an intermediate layer 283, and a second electrode 285. The first electrode 281 is formed between pixel defining layers 270 adjacent to each other, the intermediate layer 283 may be formed on the first electrode 281, and the second electrode 285 may be pattern-formed on the intermediate layer 283 and the pixel defining layer 270.

A protection layer 290, which is a buffer layer for protecting the OLED, may be formed on the second electrode 285.

According to a selective embodiment, the protection layer 290 may be formed of a LiF-containing material. Furthermore, according to another selective embodiment, the protection layer 290 is patterned on the substrate 100 and pattern-formed to cover the pixel defining layer 270 together with the second electrode 285.

According to a selective embodiment, the first opening OP1 is formed at at least portions of the second electrode 285 and the protection layer 290 contacting the pixel defining layer 270.

13

In the OLED display **2000** according to the present embodiment, the first opening **OP1** is formed at a side surface of the pixel defining layer **270** as shown in FIG. 6.

For example, according to a selective embodiment, portions of the second electrode **285** and the protection layer **290** contacting a side surface of the pixel defining layer **270** are patterned by removing to expose the side surface of the pixel defining layer **270**.

According to a selective embodiment, the second electrode **285** and the protection layer **290** are partially patterned between the top surface of the pixel defining layer **270** and a side surface of the pixel defining layer **270** to include the first opening **OP1** at the side surface of the pixel defining layer **270**.

However, locations and numbers of the first openings **OP1** are not limited thereto, and the first opening **OP1** may be formed at any of portions of the second electrode **285** and the protection layer **290** contacting the pixel defining layer **270**.

After the pixel defining layer **270** and the OLED are formed, a thin-film encapsulating layer **300** may be formed thereon to protect the OLED from outside moisture or oxygen.

The thin-film encapsulating layer **300** may be formed by alternately stacking a plurality of inorganic layers and organic layers. According to a selective embodiment, an inorganic layer **310** may be formed, and an organic layer **330** may be formed on the inorganic layer **310**.

The inorganic layer **310** may be formed on the OLED to contact a portion of the pixel defining layer **270** exposed at the first opening **OP1**.

Since the inorganic layer **310** is formed to directly contact the pixel defining layer **270** at at least a portion, adhesion between the thin-film encapsulating layer **300** and the pixel defining layer **270** may be improved as compared to a case in which the thin-film encapsulating layer **300** is formed to contact the thin protection layer **290** deposited in an evaporation operation.

For example, if the thin-film encapsulating layer **300** is formed to contact the thin protection layer **290** formed in one of various deposition operations (e.g., an evaporation operation), adhesion between the thin-film encapsulating layer **300** and a structure below the thin-film encapsulating layer **300** is insufficient, and thus the thin-film encapsulating layer **300** may be exfoliated when the OLED display **2000** is bent.

As a result, if the thin-film encapsulating layer **300** is exfoliated in a flexible display, the OLED is not sufficiently protected, and thus reliability of the flexibly display apparatus is questioned.

On the contrary, in the OLED display **2000**, the thin-film encapsulating layer **300** is formed to be adhered to at least a portion of the pixel defining layer **270** that is formed to have a certain thickness, the thin-film encapsulating layer **300** will not be exfoliated even if the OLED display **2000** is bent.

FIG. 7 is a perspective view of an OLED display **3000** according to another exemplary embodiment.

Although a mobile phone device is shown as an embodiment of the OLED display **3000** according to the present embodiment, the OLED display **3000** is not limited thereto, and any of various display apparatuses may be applicable as long as a user may recognize a screen.

According to a selective embodiment, the OLED display **3000** is a flexible display apparatus and includes a front surface portion A, which is a front surface to a user, emits light, and displays a screen image, a bending portion B, at

14

which bending occurs, and side surface portions C, which are side surfaces of the display apparatus to the user.

According to a selective embodiment, the front surface portion A is a light-emitting region in which a screen image is displayed, whereas the bending portion B may also be an region in which a screen image is displayed.

According to a selective embodiment, the bending portion B is an region in which no screen image is displayed and a circuit is arranged.

According to a selective embodiment, the side surface portions C are light-emitting regions in which a screen image is displayed. In this case, a display region may expand, and a bending may occur in the display region.

According to a selective embodiment, the side surface portions C are regions that does not emit visible rays that may be recognized by a user, that is, bezel regions in which no screen image is displayed.

FIG. 7 shows a mobile phone device in which a screen image is displayed at all of the front surface portion A, the bending portion B, and the side surface portions C. However, according to a selective embodiment, the bending portion B and/or the side surface portions C may not be light-emitting regions as described above, and the present disclosure is not limited thereto.

FIG. 8 is a detailed schematic sectional view of the OLED display **3000** shown in FIG. 7. In FIG. 8, reference numerals identical to those shown in FIG. 2 denote same components as those shown in FIG. 2. Therefore, for simplification of explanation, detailed descriptions thereof will be omitted.

Like the OLED display **1000** according to the embodiment shown in FIG. 2, in the OLED display **3000** according to the present embodiment, a buffer layer **110**, a semiconductor layer A, a gate insulation layer **210**, a gate electrode G, an interlayer insulation layer **230**, a source electrode S, a drain electrode D, a via layer **250**, and an OLED may be formed on a substrate **100** in the order stated.

In the OLED display **3000**, a second opening **OP2** is formed at the interlayer insulation layer **230** and the via layer **250** corresponding to the bending portion B at which a bending occurs.

For example, the interlayer insulation layer **230** and the via layer **250** are patterned to be removed at the bending portion B.

According to a selective embodiment, a pixel defining layer **270** for defining a pixel region including the OLED and a non-pixel region are formed on the via layer **250**.

According to a selective embodiment, the OLED includes a first electrode **281**, an intermediate layer **283**, and a second electrode **285**, where the first electrode **281** may be formed between the pixel defining layers **270** adjacent to each other, the intermediate layer **283** may be formed on the first electrode **281**, and the second electrode **285** may be formed on the intermediate layer **283** and the pixel defining layer **270**.

A protection layer **290**, which is a buffer layer for protecting the OLED, may be formed on the second electrode **285**.

According to a selective embodiment, the protection layer **290** may be formed of a LiF-containing material. Furthermore, according to another selective embodiment, the protection layer **290** may be patterned on the substrate **100** and pattern-formed to cover the pixel defining layer **270** together with the second electrode **285**.

According to a selective embodiment, the first openings **OP1** are formed at at least portions of the second electrode **285** and the protection layer **290** contacting the pixel defining layer **270**.

For example, at least portions of the second electrode **285** and the protection layer **290** covering the pixel defining layer **270** may be removed to expose the pixel defining layer **270** arranged therebelow.

According to a selective embodiment, in the OLED display **3000** shown in FIG. 7, portions of the second electrode **285** and the protection layer **290** located on the top surface of the pixel defining layer **270** may be removed, thereby forming the first opening **OP1**.

However, locations and numbers of the first opening **OP1** are limited thereto, and the first opening **OP1** may be formed anywhere where the second electrode **285** and the protection layer **290** contact the pixel defining layer **270**. For example, the first opening **OP1** may be formed at anywhere at which the pixel defining layer **270** may be exposed by removing portions of the second electrode **285** and the protection layer **290**.

A thin-film encapsulating layer **300** that seals the OLED to protect the OLED from outside moisture or oxygen may be formed on the OLED and the protection layer **290**. According to a selective embodiment, the thin-film encapsulating layer **300** includes an inorganic layer **310** formed at the bottom and an organic layer **330** formed on the inorganic layer **310**.

According to a selective embodiment, the thin-film encapsulating layer **300** is formed to directly contact the pixel defining layer **270**.

Therefore, since the inorganic layer **310** is formed to directly contact the pixel defining layer **270**, adhesion between the thin-film encapsulating layer **300** and the display **200** is improved.

If adhesion between the thin-film encapsulating layer **300** and the display **200** is insufficient when the OLED display **1000** is flexible and bent, the thin-film encapsulating layer **300** is exfoliated due to stress.

For example, if the thin-film encapsulating layer **300** is formed to contact the protection layer **290** that is formed to have a small thickness in an evaporation operation, when the OLED display bending occurs the thin-film encapsulating layer **300** is exfoliated due to insufficient adhesion between the thin-film encapsulating layer **300** and the protection layer **290**. As a result, if the thin-film encapsulating layer **300** is exfoliated in a flexible display apparatus, the OLED is not sufficiently protected, and thus reliability of the flexible display apparatus can degrade.

Here, if at least a portion of the thin-film encapsulating layer **300** is directly adhered to the pixel defining layer **270**, which is arranged below the thin-film encapsulating layer **300** and has a certain thickness, adhesion between the thin-film encapsulating layer **300** and the pixel defining layer **270** is improved, and thus thin-film encapsulating layer **300** will not be exfoliated.

The thin-film encapsulating layer **300** of the OLED display **3000** according to the present embodiment is directly adhered to the gate insulation layer **210** at the second opening **OP2**.

According to a selective embodiment, the second opening **OP2** is formed at the bending portion B, and the interlayer insulation layer **230** and the via layer **250** are patterned to be removed at the second opening **OP2**. Therefore, at the second opening **OP2**, the thin-film encapsulating layer **300** formed thereon may be formed to directly contact the top surface of the gate insulation layer **210**.

According to a selective embodiment, the inorganic layer **310** included in the thin-film encapsulating layer **300** is formed to contact the top surface of the gate insulation layer **210** at the second opening **OP2**.

Furthermore, according to a selective embodiment, the thin-film encapsulating layer **300** is formed to directly contact side surfaces of the interlayer insulation layer **230** and the via layer **250** at the second opening **OP2**.

According to a selective embodiment, the inorganic layer **310** included in the thin-film encapsulating layer **300** is formed to contact side surfaces of the interlayer insulation layer **230** and the via layer **250** at the second opening **OP2**.

Thickness of the OLED display **3000** may be reduced at the bending portion B. For example, since the gate insulation layer **210** is arranged on the substrate **100** and the thin-film encapsulating layer **300** is formed directly on the gate insulation layer **210**, thickness of the bending portion B of the OLED display **3000** may become smaller than thickness of the remaining portions of the OLED display **3000**.

Therefore, as thickness of the bending portion B at which a bending occurs is reduced, stress may be reduced, and thus flexibility of the OLED display **3000** may be improved.

Furthermore, at the second opening **OP2**, the thin-film encapsulating layer **300** is not formed to have a small thickness in an evaporation operation, but is formed to directly contact the pixel defining layer **270** that is formed to have a certain thickness. Therefore, adhesion of the thin-film encapsulating layer **300** to a structure therebelow may be improved at the bending portion B.

At a region at which a bending occurs, if adhesion between the thin-film encapsulating layer **300** and a structure therebelow is insufficient, the thin-film encapsulating layer **300** may be easily exfoliated. Therefore, in the OLED display **3000**, the thin-film encapsulating layer **300** is directly adhered to the gate insulation layer **210** therebelow at the bending portion B, at which a bending occurs, and thus adhesion between the thin-film encapsulating layer **300** and a structure therebelow may be improved.

However, although FIG. 8 shows that, in the OLED display **3000**, the second opening **OP2** is formed at the interlayer insulation layer **230** and the via layer **250** and the thin-film encapsulating layer **300** is formed directly on the gate insulation layer **210**, the present disclosure is not limited thereto.

For example, according to a selective embodiment, the second opening **OP2** may be formed only at the via layer **250**. In this case, only the via layer **250** is patterned to be removed at the second opening **OP2**, and the thin-film encapsulating layer **300** is formed to be directly adhered to the interlayer insulation layer **230**.

FIG. 9 is a schematic sectional view diagram showing the bent OLED display **3000** around the bending portion B in closer details. In FIG. 9, reference numerals identical to those shown in FIG. 8 denote same components as those shown in FIG. 8. Therefore, for simplification of explanation, detailed descriptions thereof will be omitted.

As shown in FIG. 9, the OLED display **3000** according to the present embodiment may be bent at the bending portion B.

According to a selective embodiment, components formed on the substrate **100** may include the buffer layer **110**, the gate insulation layer **210**, and the thin-film encapsulating layer **300** only, where thickness of the bending portion B may be smaller than those of the portions A and C other than the bending portion B.

Therefore, thickness of a bending portion is reduced, stresses applied to stacked layers when the OLED display **3000** is bent are reduced, and thus flexibility of the OLED display **3000** may be improved. Furthermore, as the second opening **OP2** is formed at the interlayer insulation layer **230** and the via layer **250** at the bending portion B, the thin-film

encapsulating layer **300** is formed to be directly adhered to the gate insulation layer **210**. As a result, even if the OLED display **3000** is bent, the thin-film encapsulating layer **300** may not be exfoliated due to improved adhesion of the thin-film encapsulating layer **300** to a structure therebelow.

Hereinafter, a method of manufacturing the OLED display **1000** according to an exemplary embodiment will be described in detail.

A flexible substrate **100** may be provided, a buffer layer **110** may be provided on the substrate **100**, and a thin-film transistor TFT may be formed on the buffer layer **110**.

A semiconductor layer A is formed of a semiconductor including amorphous silicon or a crystalline silicon. The semiconductor layer A may be deposited using one of various deposition methods on the buffer layer **110**. Here, the crystalline silicon may be formed by crystallizing amorphous silicon. According to a selective embodiment, amorphous silicon may be crystallized by using one of various methods including a rapid thermal annealing (RTA) method, a solid phase crystallization (SPC) method, an excimer laser annealing (ELA) method, a metal-induced crystallization (MIC) method, a metal-induced lateral crystallization (MILC) method, and a sequential lateral solidification (SLS) method. According to a selective embodiment, the semiconductor layer A may be patterned in a photolithography operation.

A gate insulation layer **210** insulates the semiconductor layer A from a gate electrode G to be formed thereto and is formed thoroughly on the buffer layer **110** to cover the semiconductor layer A. The gate insulation layer **210** may be formed of one of various deposition methods including sputtering, chemical vapor deposition (CVD), or plasma-enhanced chemical vapor deposition (PECVD).

Next, the gate electrode G may be formed on the gate insulation layer **210**, such that the gate electrode G to at least partially overlap the semiconductor layer A.

Next, an interlayer insulation layer **230** is formed thoroughly on the substrate to cover the gate electrode G. According to a selective embodiment, the interlayer insulation layer **230** may be formed of one of various deposition methods including sputtering, chemical vapor deposition (CVD), or plasma-enhanced chemical vapor deposition (PECVD).

Next, a source electrode S and a drain electrode D may be formed on the interlayer insulation layer **230**, and a via layer **250** is formed thoroughly on the substrate to cover the source electrode S and the drain electrode D.

A pixel defining layer **270** that defines a pixel region and a non-pixel region may be formed on the via layer **250**, and spacers (not shown) may be formed on portions of the pixel defining layer **270**.

A first electrode **281** may be formed between the pixel defining layers **270**, an intermediate layer **283** may be formed on the first electrode **281**, and a second electrode **285** may be formed on the intermediate layer **283** and the pixel defining layer **270**.

Here, a first opening OP1 at which the second electrode **285** is removed may be formed at a portion of a region in which the second electrode **285** and the pixel defining layer **270** contact each other.

For example, the second electrode **285** may be patterned thoroughly on the substrate, such that a portion of the second electrode **285** is removed at the first opening OP1 to expose the pixel defining layer **270**.

A protection layer **290** for protecting an OLED may be formed on the second electrode **285**. According to a selective

embodiment, the protection layer **290** may be formed of LiF by depositing a LiF thin-film in an evaporation operation.

Here, the protection layer **290** may be formed to cover the pixel defining layer **270** together with the second electrode **285**.

According to a selective embodiment, the first opening OP1 at which the protection layer **290** is removed may be formed at a portion of a region in which the protection layer **290** and the pixel defining layer **270** contact each other.

For example, the protection layer **290** may be patterned on the substrate to expose the pixel defining layer **270** by removing a portion of the protection layer **290** at a same location as that of the first opening OP1 at which a portion of the second electrode **285** is removed.

After the OLED and the protection layer **290** are formed, a thin-film encapsulating layer **300** for sealing the OLED may be formed to protect the OLED from outside moisture or oxygen.

Here, an inorganic layer **310** may be formed, and then an organic layer **330** may be formed on the inorganic layer **310**, where the inorganic layer **310** may be formed to directly contact the pixel defining layer **270** at the first opening OP1.

Therefore, the OLED display **1000** according to the present embodiment is formed, such that the thin-film encapsulating layer **300** directly contacts the pixel defining layer **270** at at least a region. Therefore, adhesion between the thin-film encapsulating layer **300** and the pixel defining layer **270** may be improved.

Hereinafter, a method of manufacturing the OLED display **3000** according to an exemplary embodiment will be described in detail with reference to FIG. 8. For convenience of explanation, descriptions identical to those given above in relation to the method of manufacturing the OLED display **1000** according to the embodiment shown in FIG. 2 will be omitted.

A substrate **100** formed of a flexible material may be provided, a buffer layer **110** may be formed on the substrate **100**, and a thin-film transistor TFT may be formed on the buffer layer **110**.

A semiconductor layer A may be formed on the buffer layer **110**, and a gate insulation layer **210** may be formed to cover the semiconductor layer A. A gate electrode G may be formed on the gate insulation layer **210** to at least partially overlap the semiconductor layer A.

Next, an interlayer insulation layer **230** may be patterned to cover the gate electrode G. According to a selective embodiment, the interlayer insulation layer **230** may be formed of one of various deposition methods including sputtering, chemical vapor deposition (CVD), or plasma-enhanced chemical vapor deposition (PECVD).

Furthermore, according to a selective embodiment, the interlayer insulation layer **230** may be patterned, such that a portion of the interlayer insulation layer **230** is removed at the bending portion B. Therefore, a second opening OP2 may be formed at the bending portion B.

Next, a source electrode S and a drain electrode D may be formed on the interlayer insulation layer **230**, and a via layer **250** may be formed to cover the source electrode S and the drain electrode D.

According to a selective embodiment, the via layer **250** may be deposited, such that a portion of the via layer **250** is removed at the bending portion B. Therefore, the second opening OP2 may be formed at the bending portion B.

For example, portions of the interlayer insulation layer **230** and the via layer **250** are removed at the bending portion B, and thus the second opening OP2 may be formed at

portions of the interlayer insulation layer **230** and the via layer **250** at the bending portion B.

An OLED and a pixel defining layer **270** may be formed on the via layer **250**. A protection layer **290** may be formed on the OLED and the pixel defining layer **270**, where the protection layer **290** may be formed in one of various deposition operations, such as an evaporation operation. According to a selective embodiment, the protection layer **290** may be formed of a LiF-containing material.

After the OLED and the protection layer **290** are formed, a thin-film encapsulating layer **300** that seals the OLED to protect the OLED from outside moisture or oxygen may be formed.

Here, an inorganic layer **310** may be formed, and then an organic layer **330** may be formed on the inorganic layer **310**, where the inorganic layer **310** may be formed to directly contact the gate insulation layer **210** at the second opening OP2.

Therefore, thickness of the bending portion B may be reduced and adhesiveness of the thin-film encapsulating layer **300** may be improved. As a result, concentration of stress at the bending portion B or an exfoliation of the thin-film encapsulating layer **300** in a flexible OLED display may be prevented.

As described above, according to the one or more of the above exemplary embodiments, an exfoliation of a thin-film encapsulating layer of an OLED display due to deterioration of adhesiveness may be prevented.

It should be understood that exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment should typically be considered as available for other similar features or aspects in other exemplary embodiments.

While the inventive technology has been described with reference to the drawings, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims.

What is claimed is:

1. An organic light-emitting diode (OLED) display comprising:

a substrate;

an OLED formed over the substrate and comprising a first electrode, a second electrode formed over the first electrode and an intermediate layer interposed between the first and second electrodes;

a pixel defining layer formed over the substrate and adjacent to the OLED;

a protection layer formed over the second electrode and configured to protect the OLED; and

a thin-film encapsulating layer formed over the protection layer and sealing the OLED so as to protect the OLED from the environment,

wherein the thin-film encapsulating layer comprises an inorganic layer and an organic layer formed over the inorganic layer, and

wherein at least a part of the inorganic layer contacts the pixel defining layer.

2. The OLED display of claim 1, wherein the first electrode is formed between adjacent pixel defining layers, wherein the intermediate layer is formed over the first electrode, and wherein the second electrode and the protection layer are formed over the intermediate layer and the pixel defining layer.

3. The OLED display of claim 1, wherein the protection layer is formed of LiF.

4. The OLED display of claim 2, wherein the second electrode and the protection layer have a first opening formed over the pixel defining layer, the first opening overlaps at least a part of the thin-film encapsulating layer contacts the pixel defining layer.

5. The OLED display of claim 4,

wherein the inorganic layer contacts the pixel defining layer at the first opening.

6. The OLED display of claim 1, wherein the thin-film encapsulating layer further comprises a plurality of inorganic layers and a plurality of organic layers that are alternately stacked.

7. The OLED display of claim 1, further comprising:

a thin-film transistor (TFT) including an active layer, a gate electrode, a source electrode, and a drain electrode is formed over the substrate;

a gate insulation layer formed between the active layer and the gate electrode;

an interlayer insulation layer formed between the gate electrode and the source and drain electrodes; and

a via layer formed over the source and drain electrodes.

8. The OLED display of claim 7, wherein the substrate comprises a bending portion configured to bend, and wherein the interlayer insulation layer and the via layer have a second opening formed over the bending portion.

9. The OLED display of claim 8, wherein the thin-film encapsulating layer contacts the gate insulation layer at the second opening.

10. The OLED display of claim 8, wherein the thin-film encapsulating layer contacts side surfaces of the interlayer insulation layer and the via layer at the second opening.

11. The OLED display of claim 8, wherein the inorganic layer contacts the gate insulation layer at the second opening.

12. A method of manufacturing an organic light-emitting diode (OLED) display, the method comprising:

providing a substrate;

forming a thin-film transistor (TFT) and a via layer over the substrate;

forming a pixel defining layer over the via layer;

forming an OLED over the via layer;

forming a protection layer over the OLED so as to cover the pixel defining layer; and

forming a thin-film encapsulating layer that seals the OLED and the protection layer to protect the OLED from the environment,

wherein the forming of the OLED comprises:

forming a first electrode between adjacent pixel defining layers;

forming an intermediate layer over the first electrode; and

forming a second electrode over the intermediate layer and the first electrode,

wherein the second electrode and the protection layer are pattern-formed such that at least portions thereof contacting the pixel defining layer are removed and a first opening is formed therein,

wherein the forming of the thin-film encapsulating layer comprises:

forming an inorganic layer over the protection layer; and

forming an organic layer over the inorganic layer, and wherein the inorganic layer contacts the pixel defining layer at the first opening.

13. The method of claim 12, wherein the protection layer is formed of LiF.

14. The method of claim **12**, wherein the substrate comprises a bending portion configured to bend, and wherein the method further comprises:

after the providing of the substrate, forming a gate insulation layer over the substrate; 5

forming an interlayer insulation layer over the gate insulation layer; and

forming a via layer over the interlayer insulation layer.

15. The method of claim **14**, wherein the interlayer insulation layer and the via layer are pattern-formed to be partially removed at the bending portion such that a second opening is formed in the second electrode and the protection layer. 10

16. The method of claim **15**, wherein the thin-film encapsulating layer contacts the gate insulation layer at the second opening. 15

17. The method of claim **15**, wherein the thin-film encapsulating layer contacts side surfaces of the interlayer insulation layer and the via layer at the second opening.

18. An organic light-emitting diode (OLED) display comprising: 20

a substrate;

a plurality of OLEDs formed over the substrate;

a pixel defining layer interposed between the OLEDs;

a thin-film encapsulating layer formed over the pixel defining layer and sealing the OLED so as to protect the OLEDs from the environment, 25

wherein the thin-film encapsulating layer comprises an inorganic layer and an organic layer formed over the inorganic layer, and 30

wherein the inorganic layer contacts the pixel defining layer through a plurality of openings.

* * * * *

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	US9859346	公开(公告)日	2018-01-02
申请号	US15/255632	申请日	2016-09-02
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SEO TAEAN KIM KIHYUN PARK JUCHAN SEOL YOUNGGUG LEE PILSUK CHOI JINHWAN		
发明人	SEO, TAEAN KIM, KIHYUN PARK, JUCHAN SEOL, YOUNGGUG LEE, PILSUK CHOI, JINHWAN		
IPC分类号	H01L27/32 H01L51/52		
CPC分类号	H01L27/3246 H01L51/5256 H01L51/5253 H01L2251/5338 H01L51/5225		
审查员(译)	波特, ROY		
助理审查员(译)	巴顿PAUL		
优先权	1020150130596 2015-09-15 KR		
其他公开文献	US20170077195A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种有机发光二极管 (OLED) 显示器及其制造方法。在一个方面，OLED显示器包括形成在衬底上的OLED，OLED包括第一电极，形成在第一电极上的第二电极和插入在第一和第二电极之间的中间层。像素限定层形成在衬底上方并且与OLED相邻，并且保护层形成在第二电极上方并且被配置为保护OLED。在保护层上形成薄膜封装层并密封OLED以保护OLED免受环境影响，薄膜封装层的至少一部分接触像素限定层。

