




US 20150090980A1

(19) **United States**(12) **Patent Application Publication**
LEE et al.(10) **Pub. No.: US 2015/0090980 A1**(43) **Pub. Date: Apr. 2, 2015**(54) **ORGANIC LIGHT-EMITTING DIODE (OLED)
DISPLAY AND METHOD FOR
MANUFACTURING THE SAME***H01L 29/786* (2006.01)*H01L 51/56* (2006.01)(52) **U.S. Cl.**CPC *H01L 27/3262* (2013.01); *H01L 51/56*
(2013.01); *H01L 27/1259* (2013.01); *H01L*
29/78675 (2013.01); *H01L 2227/323* (2013.01)USPC **257/40**; 438/34(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-city
(KR)(72) Inventors: **Wang Woo LEE**, Osan-si (KR); **Moo**
Soon Ko, Seoul (KR); **Min Woo Woo**,
Bucheon-si (KR); **Il Jeong Lee**, Seoul
(KR); **Jeong Ho Lee**, Seoul (KR)(21) Appl. No.: **14/457,862**(22) Filed: **Aug. 12, 2014**(30) **Foreign Application Priority Data**

Sep. 27, 2013 (KR) 10-2013-0115350

Publication Classification(51) **Int. Cl.***H01L 27/32* (2006.01)*H01L 27/12* (2006.01)(57) **ABSTRACT**

An organic light-emitting diode (OLED) display having thin film transistors (TFTs) is disclosed. In one aspect, TFTs of the OLED display include a substrate and a first semiconductor layer formed over the substrate and including first channel, source, and drain regions and a lightly doped region between the first channel region and the first source and drain regions. The OLED display also includes a second semiconductor layer formed over the substrate and including second channel, source, and drain regions. The OLED display further includes first and second gate electrodes formed over the first semiconductor layer and a third gate electrode formed over the second semiconductor layer. The width of the second gate electrode is less than that of the first gate electrode and the lightly doped region overlaps a portion of the first gate electrode and does not overlap the second gate electrode.






FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7





FIG. 8



**ORGANIC LIGHT-EMITTING DIODE (OLED)
DISPLAY AND METHOD FOR
MANUFACTURING THE SAME**

**CROSS-REFERENCE TO RELATED
APPLICATIONS**

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2013-0115350 filed in the Korean Intellectual Property Office on Sep. 27, 2013, the entire contents of which are incorporated herein by reference.

BACKGROUND

[0002] 1. Field

[0003] The described technology generally relates to an organic light-emitting diode (OLED) display having thin film transistors and a manufacturing method thereof.

[0004] 2. Description of the Related Technology

[0005] Active matrix OLED displays include a display panel including a plurality of pixels each including a thin film transistor (TFT) and an OLED. Images can be displayed on the OLED display by controlling the current flowing to each OLED using the corresponding thin film transistor.

SUMMARY OF CERTAIN INVENTIVE ASPECTS

[0006] One inventive aspect is an OLED display having a greater aperture ratio and a favorable characteristics in both on and off states by forming a lightly doped region near a channel region of a gate electrode by using a plurality of gate electrodes having different widths and a manufacturing method thereof.

[0007] Another aspect is an OLED display including a substrate, a first semiconductor layer including a first channel region, a first source region, a first drain region, and a lightly doped region between the first channel region and the first source and drain regions, and a second semiconductor layer including a second channel region and a second source region and second drain region, on the substrate, a gate insulating layer disposed on the first semiconductor layer, the second semiconductor layer, and the substrate, a first gate electrode disposed at a position corresponding to the first semiconductor layer on the gate insulating layer, a first interlayer insulating layer disposed on the first gate electrode and the gate insulating layer, and a second gate electrode disposed at a position corresponding to the first gate electrode on the first interlayer insulating layer and a third gate electrode disposed at a position corresponding to the second semiconductor layer, wherein the second gate electrode is formed with a narrower width than the first gate electrode, and the lightly doped region of the first semiconductor layer overlaps the first gate electrode does not overlap the second gate electrode.

[0008] The first channel region of the first semiconductor layer is formed at a position overlapping all of the first gate electrode and the second gate electrode and the first source region and the first drain region are formed at a position where the first gate electrode and the second gate electrode do not overlap.

[0009] A blocking film may be formed between the substrate and the first semiconductor layer and second semiconductor layer.

[0010] The first semiconductor layer may be doped with an impurity such as boron, gallium, phosphorus, arsenic, or combinations thereof.

[0011] The lightly doped region may be an offset region which includes a small amount of impurities.

[0012] The second channel region of the second semiconductor layer may be positioned overlapping the third gate electrode and the second source and second drain region may be positioned at a position where the third gate electrode is not overlapped.

[0013] The first gate electrode may be formed with a thickness of less than about 1000 Å.

[0014] The OLED display may further include a second interlayer insulating layer disposed on the second gate electrode and the third gate electrode, a data conductor disposed on the second interlayer insulating layer, a passivation layer disposed on the data conductor, a plurality of pixel electrodes and partitions disposed on the passivation layer, an organic light-emitting member disposed on the partition, and a common electrode disposed on the organic light-emitting member, wherein the second interlayer insulating layer and the gate insulating layer may have a plurality of contact holes exposing the source and drain regions to contact the data conductor and the passivation layer may have a plurality of contact holes exposing the data conductor to be connected to the pixel electrodes.

[0015] The first semiconductor layer, the first gate electrode, and the second gate electrode may form a switching thin film transistor connected to the data conductor and the second semiconductor layer and the third gate electrode may form a driving thin film transistor connected to the organic light-emitting member.

[0016] Another aspect is a method of manufacturing an organic light-emitting diode (OLED) display including forming a first semiconductor layer and a second semiconductor layer on a substrate, forming a gate insulating layer on the first semiconductor layer, the second semiconductor layer, and the substrate, forming a first gate electrode on the gate insulating layer corresponding to the first semiconductor layer, forming a first interlayer insulating layer on the first gate electrode and the gate insulating layer, forming a second gate electrode and a third gate electrode on the first interlayer insulating layer corresponding to the first gate electrode and the second semiconductor layer, and adding an impurity element to the first semiconductor layer and the second semiconductor layer to dope the semiconductor layer, wherein the second gate electrode is formed with a narrower width than the first gate electrode, the first semiconductor layer includes a first channel region, a first source region, a first drain region, and a lightly doped region positioned between the first channel region and the first source and drain regions, and the lightly doped region as a portion overlapping the first gate electrode does not overlap the second gate electrode.

[0017] Another aspect is an organic light-emitting diode (OLED) display, comprising: a substrate; a first semiconductor layer formed over the substrate and including a first channel region, a first source region, a first drain region, and a lightly doped region formed between i) the first channel region and ii) the first source and drain regions; a second semiconductor layer formed over the substrate and including a second channel region, a second source region, and second drain region; a gate insulating layer formed over the first and second semiconductor layers and the substrate; a first gate electrode formed over the gate insulating layer wherein the first gate electrode is formed directly above at least a portion of the first semiconductor layer; a first interlayer insulating layer formed over the first gate electrode and the gate insu-

lating layer; a second gate electrode formed over the first interlayer insulating layer wherein the second gate electrode is formed directly above at least a portion of the first gate electrode; and a third gate electrode formed directly above at least a portion of the second semiconductor layer, wherein the width of the second gate electrode is less than that of the first gate electrode, wherein at least a portion of the lightly doped region overlaps the first gate electrode, and wherein the lightly doped region does not overlap the second gate electrode.

[0018] In the above display, the first channel region overlaps i) at least a portion of the first gate electrode and ii) the second gate electrode and wherein the first source and drain regions overlap neither the first gate electrode nor the second gate electrode. The above display further comprises a blocking film formed between i) the substrate and ii) the first and second semiconductor layers. In the above display, the first semiconductor layer is doped with at least one of boron, gallium, phosphorus, or arsenic. In the above display, the lightly doped region comprises an offset region including fewer impurities than each of the first source and drain regions. In the above display, the second channel region is formed directly below the third gate electrode and wherein the second source and drain regions do not overlap the third gate electrode.

[0019] In the above display, the first gate electrode has a thickness of less than about 1000 Å. The above display further comprises: a second interlayer insulating layer formed over the second and third gate electrodes; a plurality of data conductors formed over the second interlayer insulating layer; a passivation layer formed over the data conductors; a plurality of pixel electrodes formed over the passivation layer; a pixel defining layer formed over the passivation layer and at least a portion of the pixel electrodes; an organic light-emitting layer formed over the pixel electrodes; and a common electrode formed over the organic light-emitting layer, wherein the second interlayer insulating layer and the gate insulating layer define a plurality of contact holes, wherein the passivation layer defines a plurality of contact holes, wherein the data conductors pass through the respective contact holes to be electrically connected to the first source and drain regions, the second source and drain regions, and the pixel electrodes. In the above display, the first semiconductor layer and the first and second gate electrodes form a switching thin film transistor electrically connected to the data conductors and wherein the second semiconductor layer and the third gate electrode form a driving thin film transistor electrically connected to the organic light-emitting layer.

[0020] Another aspect is a method of manufacturing an organic light-emitting diode (OLED) display, comprising: forming a first semiconductor layer and a second semiconductor layer over a substrate; forming a gate insulating layer over the first and second semiconductor layers and the substrate; forming a first gate electrode over the gate insulating layer such that the first gate electrode is formed directly above at least a portion of the first semiconductor layer; forming a first interlayer insulating layer over the first gate electrode and the gate insulating layer; forming a second gate electrode over the first interlayer insulating layer such that the second gate electrode is formed directly above at least a portion of the first gate electrode; forming a third gate electrode over the first interlayer insulating layer such that the third gate electrode is formed directly above at least a portion of the second semiconductor layer; and doping the first and second semiconduc-

tor layers, wherein the width of the second gate electrode is less than that of the first gate electrode, wherein the first semiconductor layer includes a first channel region, a first source region, a first drain region, and a lightly doped region between i) the first channel region and ii) the first source and drain regions, wherein the lightly doped region overlaps the first gate electrode and does not overlap the second gate electrode.

[0021] In the above method, the first channel region overlaps i) at least a portion of the first gate electrode and ii) the second gate electrode and wherein the first source and drain regions overlaps neither the first gate electrode nor the second gate electrode. The above method further comprises forming a blocking film over the substrate before forming the first and second semiconductor layers. In the above method the doping comprises doping with at least one of boron, gallium, phosphorus, or arsenic. In the above method, the lightly doped region comprises an offset region including fewer impurities than each of the first source and drain regions. In the above method, the second channel region is formed substantially directly below the third gate electrode and wherein the second source and drain regions do not overlap the third gate electrode.

[0022] In the above method, the first gate electrode has a thickness of less than about 1000 Å. The above method further comprising: forming a second interlayer insulating layer over the second and third gate electrodes; forming a plurality of first contact holes in the second interlayer insulating layer and the gate insulating layer to expose the first source and drain regions and the second source and drain regions; forming a plurality of data conductors over the second interlayer insulating layer and in the first contact holes; forming a passivation layer over the data conductors; forming a plurality of second contact holes in the passivation layer to expose the data conductors; forming a plurality of pixel electrodes over the passivation layer and in the second contact holes; forming a pixel defining layer over the passivation layer and at least a portion of the pixel electrodes; forming an organic light-emitting layer over the pixel electrodes; and forming a common electrode over the organic light-emitting layer. In the above method, the first semiconductor layer and the first and second gate electrodes form a switching thin film transistor electrically connected to the data conductors and wherein the second semiconductor layer and the third gate electrode form a driving thin film transistor electrically connected to the organic light-emitting layer.

[0023] Another aspect is an organic light-emitting diode (OLED) display including a plurality of thin film transistors (TFTs), each TFT comprising: a substrate; a semiconductor layer formed over the substrate and including a first channel region, a source region, a drain region, and a lightly doped region formed between i) the first channel region and ii) the source and drain regions; a first gate electrode formed directly over at least a portion of the semiconductor layer; and a second gate electrode formed directly over at least a portion of the first gate electrode, wherein the width of the second gate electrode is less than that of the first gate electrode, wherein at least a portion of the lightly doped region overlaps the first gate electrode and does not overlap the second gate electrode.

[0024] In the above display, the semiconductor layer further comprises: a second channel region; and an intermediate region, wherein the lightly doped region is further located between i) the intermediate region and ii) the first and second

channel regions, wherein the first gate electrode comprises a pair of first gate electrodes respectively formed directly above the first and second channel regions, and wherein the second gate electrode comprises a pair of second gate electrodes respectively formed directly above the pair of first gate electrodes.

[0025] According to at least one embodiment, the extrinsic region and the lightly doped region of the semiconductor layer of the OLED display may be easily formed and may achieve favorable characteristics in both on and off states, thereby improving the quality of the OLED display.

BRIEF DESCRIPTION OF THE DRAWINGS

[0026] FIG. 1 is a cross-sectional view of the structure of a semiconductor layer of an OLED display according to an exemplary embodiment.

[0027] FIG. 2 is an equivalent circuit diagram of an OLED display according to an exemplary embodiment.

[0028] FIG. 3 is a layout view of an OLED display according to an exemplary embodiment.

[0029] FIG. 4 is a cross-sectional view of the OLED display of FIG. 3 taken along line II-II.

[0030] FIG. 5 is a cross-sectional view of the OLED display of FIG. 3 taken along line III-III.

[0031] FIG. 6 to FIG. 8 are views showing a method of manufacturing an OLED display according to an exemplary embodiment.

DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

[0032] High mobility can be achieved in a thin film transistor by using a semiconductor layer having a crystalline structure as the active layer of the TFT (a crystalline thin film transistor). Functional circuits are commonly integrated on the same substrate in order to display high quality images.

[0033] To form an active matrix OLED display, one to two million crystalline thin film transistors are generally required in the display panel. A number of additional thin film transistors are required to form a functional circuit attached to the display. The stability of the OLED display depends on the uniformity and reliability of each crystalline thin film transistor.

[0034] The described technology will be described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments are shown. As those skilled in the art would realize, the described embodiments may be modified in various different ways, all without departing from the spirit or scope of the described technology.

[0035] In the drawings, the thicknesses of layers, films, panels, regions, etc., may be exaggerated for clarity. Like reference numerals designate like elements throughout the specification. It will be understood that when an element such as a layer, film, region, or substrate is referred to as being "on" another element, it can be directly on the other element or intervening elements may also be present. In contrast, when an element is referred to as being "directly on" another element, there are no intervening elements present.

[0036] An organic light-emitting diode (OLED) display according to an exemplary embodiment will now be described in detail with reference to accompanying drawings.

[0037] FIG. 1 is a cross-sectional view of the structure of a semiconductor layer of an OLED display according to an exemplary embodiment.

[0038] Referring to FIG. 1, the OLED display includes a blocking film 111 formed of a silicon nitride (SiNx) or a silicon oxide (SiOx). The blocking film 111 is formed on an insulation substrate 110 formed of transparent glass or plastic. The blocking film 111 may have a dual-layered structure.

[0039] According to some embodiments, a plurality of pairs of first and second semiconductor islands or semiconductor layers 151a and 151b that are formed of polysilicon are formed on the blocking film 111. The semiconductor islands 151a and 151b respectively include a plurality of extrinsic regions including conductive impurities of an n-type or a p-type and at least one intrinsic region that does not include conductive impurities.

[0040] According to some embodiments, in the first semiconductor island 151a, the extrinsic region includes first source and drain regions 153a and 155a that are doped with an n-type impurity and separated from each other. The intrinsic region includes a channel region 154a positioned between the extrinsic regions 153a and 155a.

[0041] The extrinsic region further includes a lightly doped region 152a positioned between the first channel region 154a and the first source and drain regions 153a and 155a. The lightly doped region may be replaced with an offset region including a relatively low amount of impurities, i.e. the offset region may include fewer impurities than each of the first source and drain regions 153a and 155a.

[0042] The first source and drain regions 153a and 155a may be formed at a region outside the width of a first gate electrode 124a, the lightly doped region 152a is formed at a position corresponding to the difference in width between the first gate electrode 124a and a second gate electrode 125a, and the first channel region 154a is formed at a position corresponding to the width of the second gate electrode 125a.

[0043] The lightly doped drain (LDD) structure smoothes a high electric field near the drain to decrease the off current in the thin film transistor. The lightly doped extrinsic region formed outside of the channel region and is referred to as an LDD region.

[0044] According to some embodiments, in the second semiconductor island 151b, the extrinsic region includes second source and drain regions 153b and 155b that are doped with a p-type impurity and are separated from each other. The intrinsic region includes a second channel region 154b formed between the second source and drain regions 153b and 155b.

[0045] Alternatively, the extrinsic regions 153a and 155a of the first semiconductor island 151a may be doped with p-type impurities and the extrinsic regions 153b and 155b of the second semiconductor island 151b may be doped with n-type impurities. The conductive p-type impurity may be boron (B) or gallium (Ga) and the conductive n-type impurity may be phosphorus (P) or arsenic (As).

[0046] According to some embodiments, a gate insulating layer 140 formed of a silicon nitride or a silicon oxide is formed on the semiconductor islands 151a and 151b and the blocking film 111.

[0047] A plurality of gate lines are formed on the gate insulating layer 140. The gate lines include the first gate electrode 124a positioned corresponding to the channel region 154a and the lightly doped region 152a of the first semiconductor 151a.

[0048] The gate lines transmit gate signals and are substantially extended in the transverse direction. The first gate electrode 124a extends upward from the gate line, thereby inter-

secting the first semiconductor **151a** and overlapping the first channel region **154a**. Each gate line may include an end portion having a large area for contact with another layer or an external driving circuit. When a gate driving circuit or gate driver (not shown) for generating gate signals is formed directly on the substrate **110**, the gate lines may extend and be directly connected to the gate driving circuit.

[0049] A gate conductor including the first gate electrode **124a** may be formed of an aluminum-based metal including aluminum (Al) or aluminum alloys, a silver-based metal including silver (Ag) or silver alloys, a copper-based metal including copper (Cu) or copper alloys, a molybdenum-based metal including molybdenum (Mo) or molybdenum alloys, chromium (Cr), tantalum (Ta), titanium (Ti), etc. However, they may have a multi-layer structure including two conductive layers (not shown) that have different physical properties from each other. One of the conductive layers may be formed using a metal having low resistivity, such as an aluminum-based metal, a silver-based metal, or a copper-based metal, in order to reduce signal delay or voltage drop. Other conductive layers may be formed using a material having good physical, chemical, and electrical contact characteristics particularly with indium tin oxide (ITO) and indium zinc oxide (IZO), such as a molybdenum-based metal, chromium, tantalum, titanium, or the like. Examples of the combination may include a lower chromium film and an upper aluminum (alloy) film, and a lower aluminum (alloy) film and an upper molybdenum (alloy) film. However, the gate conductors may be made of various metals or conductors.

[0050] The thickness of the first gate electrode may be less than about 1000 Å. Such a thickness assists in the formation of the lightly doped region **152a** by partially transmitting the impurity through the first gate electrode **124a** when doping the impurity to the first semiconductor **151a**; however, the impurity is not transmitted through the second gate electrode **125a**.

[0051] A first interlayer insulating layer **160** is formed on the gate conductor including the first gate electrode **124a**. The first interlayer insulating layer **160** is made of an inorganic insulator such as a silicon nitride, a silicon oxide, etc., an organic insulator, or an insulator having a low dielectric constant. In some embodiments, the dielectric constant of the organic insulator and the low dielectric insulator is less than about 4.0, for example a-Si:C:O or a-Si:O:F, which is formed through plasma enhanced chemical vapor deposition (PECVD). The first interlayer insulating layer **160** may be made of an organic insulator having photosensitivity and may provide a flat surface.

[0052] The second gate electrode **125a** is formed on the first interlayer insulating layer **160** to overlap the first gate electrode **124a** and the first channel region **154a**. A third gate electrode **124b** is also formed on the first interlayer insulating layer **160** to overlap the channel region **154b** of the second semiconductor **151b**.

[0053] The second gate electrode **125a** is formed to assist in the formation the lightly doped region **152a** in the first channel region **154a** of the first semiconductor **151a**.

[0054] The second gate electrode **125a** has a narrower width than that of the first gate electrode **124a**. The width of the lightly doped region **152a** corresponds to the difference in width between the first gate electrode **124a** and the second gate electrode **125a**. Accordingly, by controlling the size of a mask of the second gate electrode **125a**, the size of the lightly doped region **152a** may be easily predetermined.

[0055] The third gate electrode **124b** is separated from the gate line and overlaps the second channel region **154b** of the second semiconductor **151b**.

[0056] The second and third gate electrodes **125a** and **124b** may be formed of an aluminum-based metal including aluminum (Al) or aluminum alloys, a silver-based metal including silver (Ag) or silver alloys, a copper-based metal including copper (Cu) or copper alloys, a molybdenum-based metal including molybdenum (Mo) or molybdenum alloys, chromium (Cr), tantalum (Ta), titanium (Ti), etc. However, they may have a multi-layer structure including two conductive layers (not shown) that have different physical properties from each other. One of the conductive layers may be formed using a metal having low resistivity, such as an aluminum-based metal, a silver-based metal, or a copper-based metal, in order to reduce signal delay or voltage drop. Other conductive layers may be formed using a material having good physical, chemical, and electrical contact characteristics particularly with indium tin oxide (ITO) and indium zinc oxide (IZO), such as a molybdenum-based metal, chromium, tantalum, titanium, or the like. Examples of the combination may include a lower chromium film and an upper aluminum (alloy) film, and a lower aluminum (alloy) film and an upper molybdenum (alloy) film. However, they may be made of various metals or conductors.

[0057] A second interlayer insulating layer **161** is formed on the gate conductor including the second gate electrode **125a** and the third gate electrode **124b**. The second interlayer insulating layer **161** is made of an inorganic insulator such as a silicon nitride, a silicon oxide, etc., an organic insulator, or an insulator having a low dielectric constant. In some embodiments, the dielectric constant of the organic insulator and the low dielectric insulator is less than about 4.0, for example a-Si:C:O or a-Si:O:F, which is formed through plasma enhanced chemical vapor deposition (PECVD). The second interlayer insulating layer **161** may be made of an organic insulator having photosensitivity and may provide a flat surface.

[0058] In the OLED display shown in FIG. 1, the first semiconductor **151a**, the first gate electrode **124a**, and the second gate electrode **125a** formed on the first gate electrode **124a** form a switching thin film transistor (TFT) Qs and are connected to a data conductor and the second semiconductor **151b** and the third gate electrode **124b** form a driving thin film transistor (TFT) Qd and are connected to an OLED.

[0059] Next, an OLED display according to an exemplary embodiment will be described with reference to FIG. 2.

[0060] FIG. 2 is an equivalent circuit diagram of an OLED display according to an exemplary embodiment.

[0061] Referring to FIG. 2, the OLED display includes a plurality of signal lines **121**, **171**, and **172** and a plurality of pixels PX that are connected to the signal lines **121**, **171**, and **172** and arranged in a matrix.

[0062] The signal lines includes a plurality of gate lines **121** for transferring gate signals or scanning signals, a plurality of data lines **171** for transferring data signals, and a plurality of driving voltage lines **172** for transferring driving voltages. The gate lines **121** extend in a row direction substantially parallel to each other, while the data lines **171** and the driving voltage lines **172** extend in a column direction substantially parallel to each other.

[0063] Each of the pixels PX includes a switching transistor Qs, a driving transistor Qd, a storage capacitor Cst, and an OLED LD.

[0064] The switching transistor Qs includes a control terminal, an input terminal, and an output terminal. The control terminal is connected to the gate line 121, the input terminal is connected to the data line 171, and the output terminal is connected to the driving transistor Qd. The switching transistor Qs transfers a data signal supplied to the data line 171 to the driving transistor Qd in response to a scanning signal supplied to the gate line 121.

[0065] The driving transistor Qd also includes a control terminal, an input terminal, and an output terminal. The control terminal is connected to the switching transistor Qs, the input terminal is connected to the driving voltage line 172, and the output terminal is connected to the OLED LD. The driving transistor Qd outputs an output current ILD having a magnitude that varies depending on the voltage between the control terminal and the output terminal.

[0066] The capacitor Cst is connected between the control terminal and the input terminal of the driving transistor Qd. The capacitor Cst stores a data signal supplied to the control terminal of the driving transistor Qd and maintains the charged data signal even after the switching transistor Qs is turned off.

[0067] The OLED LD includes an anode connected to the output terminal of the driving transistor Qd and a cathode connected to a common voltage Vss. The OLED LD emits lights with an intensity dependent on the output current ILD of the driving transistor Qd so as to display images.

[0068] According to some embodiments, the switching transistor Qs is an n-channel electric field effect transistor (FET) and the driving transistor Qd is a p-channel electric field effect transistor. However, the channel types of the switching transistor Qs and the driving transistor Qd may be exchanged and the two transistors Qs and Qd may respectively be n-channel and the p-channel electric field effect transistors. Also, the connection relationship of the transistors Qs and Qd, the capacitor Cst, and the OLED LD may be changed.

[0069] Next, the OLED display according to an exemplary embodiment will be described with reference to FIG. 3 to FIG. 5.

[0070] FIG. 3 is a layout view of an OLED display according to an exemplary embodiment, FIG. 4 is a cross-sectional view of the OLED display of FIG. 3 taken along line II-II, and FIG. 5 is a cross-sectional view of the OLED display of FIG. 3 taken along line III-III.

[0071] The OLED display according to an exemplary embodiment includes the blocking film 111 formed of a silicon nitride (SiNx) or a silicon oxide (SiOx). The blocking film 111 is formed on the insulation substrate 110 formed of transparent glass or plastic. The blocking film 111 may have a dual-layered structure.

[0072] According to some embodiments, a plurality of pairs of first and second semiconductor islands 151a and 151b that are formed of polysilicon are formed on the blocking film 111. The semiconductor islands 151a and 151b respectively include a plurality of extrinsic regions including n-type or p-type conductive impurities and at least one intrinsic region that does not include conductive impurities.

[0073] According to some embodiments, in the first semiconductor island 151a, the extrinsic region includes the first source and drain regions 153a and 155a and an intermediate region 1535 that are doped with an n-type impurity and separated from each other. The intrinsic region includes a pair of

first channel regions 154a1 and 154a2 positioned between the extrinsic regions 153a, 1535, and 155a.

[0074] In the first semiconductor 151a, the extrinsic region further includes lightly doped regions 152a1 and 152a2 positioned between the first channel regions 154a1 and 154a2 and the first source and drain regions 153a and 155a. The lightly doped region may be replaced with an offset region which includes including a relatively low amount of impurities.

[0075] The lightly doped drain (LDD) structure smoothes a high electric field near the drain to decrease the off current in the thin film transistor and the lightly doped extrinsic region is formed outside of the channel region and is referred to as an LDD region.

[0076] According to some embodiments, the second semiconductor island 151b, the extrinsic region includes the second source and drain regions 153b and 155b that are doped with a p-type impurity and are separated from each other. The intrinsic region includes the second channel region 154b disposed between the second source and drain regions 153b and 155b and a storage region 157 extending from the second source and drain regions 153b and 155b.

[0077] Alternatively, the extrinsic regions 153a and 155a of the first semiconductor island 151a may be doped with p-type impurities and the extrinsic regions 153b and 155b of the second semiconductor island 151b may be doped with n-type impurities. The conductive p-type impurity may be boron (B) or gallium (Ga) and the conductive impurity of the n-type may be phosphorus (P) or arsenic (As).

[0078] According to some embodiments, the gate insulating layer 140 is formed of a silicon nitride or a silicon oxide and is formed on the semiconductor islands 151a and 151b and the blocking film 111.

[0079] The gate lines 121 including the first gate electrodes 124a are formed on the gate insulating layer 140.

[0080] The gate lines 121 transmit gate signals and are substantially extended in the transverse direction. The first gate electrode 124a is extended upward from the gate line, thereby intersecting the first semiconductor 151a and overlapping the first channel regions 154a1 and 154a2. Each gate line 121 may include an end portion having a large area for contact with another layer or an external driving circuit. When a gate driving circuit (not shown) for generating gate signals is formed directly on the substrate 110, the gate lines 121 may extend and be directly connected to the gate driving circuit.

[0081] A gate conductor including the first gate electrode 124a may be made of an aluminum-based metal including aluminum (Al) or aluminum alloys, a silver-based metal including silver (Ag) or silver alloys, a copper-based metal including copper (Cu) or copper alloys, a molybdenum-based metal including molybdenum (Mo) or molybdenum alloys, chromium (Cr), tantalum (Ta), titanium (Ti), etc. However, they may have a multi-layer structure including two conductive layers (not shown) that have different physical properties from each other. One of the conductive layers may be formed using a metal having low resistivity, such as an aluminum-based metal, a silver-based metal, or a copper-based metal, in order to reduce signal delay or voltage drop. Other conductive layers may be formed using a material having good physical, chemical, and electrical contact characteristics particularly with indium tin oxide (ITO) and indium zinc oxide (IZO), such as a molybdenum-based metal, chromium, tantalum, titanium, or the like. Examples of the combination may include a lower chromium film and an upper aluminum (al-

loy) film, and a lower aluminum (alloy) film and an upper molybdenum (alloy) film. However, the gate conductors may be made of various metals or conductors.

[0082] The first interlayer insulating layer **160** is formed on the gate conductor including the first gate electrode **124a**. The first interlayer insulating layer **160** is made of an inorganic insulator such as a silicon nitride, a silicon oxide, etc., an organic insulator, or an insulator having a low dielectric constant. In some embodiments, the dielectric constant of the organic insulator and the low dielectric insulator is less than about 4.0, for example a-Si:C:O or a-Si:O:F, which is formed through plasma enhanced chemical vapor deposition (PECVD). The first interlayer insulating layer **160** may be formed of an organic insulator having photosensitivity and may provide a flat surface.

[0083] The second gate electrode **125a** is formed on the first interlayer insulating layer **160** to overlap the first gate electrode **124a** and the first channel region **154a**. The third gate electrode **124b** is also formed on the first interlayer insulating layer **160** to overlap the channel region **154b** of the second semiconductor **151b**.

[0084] The second gate electrode **125a** assists in forming the lightly doped region **152a** in the first channel region **154a** of the first semiconductor **151a**.

[0085] The second gate electrode **125a** has a narrower width than that of the first gate electrode **124a**. The width of the lightly doped region **152a** corresponds to the difference in width between the first and second gate electrodes **124a** and **135a**. Accordingly, by controlling the size of the mask of the second gate electrode **125a**, the size of the lightly doped region **152a** may be easily predetermined.

[0086] The third gate electrode **124b** is separated from the gate line and overlaps the second channel region **154b** of the second semiconductor **151b**. The third gate electrode **124b** is extended forming a storage electrode **127** and the storage electrode **127** overlaps the storage region **157** of the second semiconductor **151b**.

[0087] The second and third gate electrodes **125a** and **124b** may be formed of an aluminum-based metal including aluminum (Al) or aluminum alloys, a silver-based metal including silver (Ag) or silver alloys, a copper-based metal including copper (Cu) or copper alloys, a molybdenum-based metal including molybdenum (Mo) or molybdenum alloys, chromium (Cr), tantalum (Ta), titanium (Ti), etc. However, they may have a multi-layer structure including two conductive layers (not shown) that have different physical properties from each other. One of the conductive layers may be formed using a metal having low resistivity, such as an aluminum-based metal, a silver-based metal, or a copper-based metal, in order to reduce signal delay or voltage drop. Other conductive layers may be formed using a material having good physical, chemical, and electrical contact characteristics particularly with indium tin oxide (ITO) and indium zinc oxide (IZO), such as a molybdenum-based metal, chromium, tantalum, titanium, or the like. Examples of the combination may include a lower chromium film and an upper aluminum (alloy) film, and a lower aluminum (alloy) film and an upper molybdenum (alloy) film. However, they may be made of various metals or conductors.

[0088] The second interlayer insulating layer **161** is formed on the gate conductor including the second and third gate electrodes **125a** and **124b**. The second interlayer insulating layer **161** is made of an inorganic insulator such as a silicon nitride, a silicon oxide, etc., an organic insulator, or an insu-

lator having a low dielectric ratio. In some embodiments, the dielectric constant of the organic insulator and the low dielectric insulator is less than about 4.0, for example a-Si:C:O or a-Si:O:F, which is formed through plasma enhanced chemical vapor deposition (PECVD). The second interlayer insulating layer **161** may be made of an organic insulator having photosensitivity and may provide a flat surface.

[0089] The second interlayer insulating layer **161** has a plurality of contact holes **164** exposing the third gate electrode **124b**. Also, the first and second interlayer insulating layers **160** and **161** and the gate insulating layer **140** have a plurality of contact holes **163a**, **163b**, **165a**, and **165b** exposing the source and drain regions **153a**, **153b**, **155a**, and **155b**.

[0090] A plurality of data conductors including a plurality of data lines **171**, a plurality of driving voltage lines **172**, and a plurality of first and second output electrodes **175a** and **175b** are formed on the second interlayer insulating layer **161**.

[0091] The data lines **171** transmit a data signal and extend in the longitudinal direction thereby intersecting the gate lines **121**. Each data line **171** includes a first input electrode **173a** connected to the first source region **153a** through the contact hole **163a** and may include an end portion having a large area for contact with another layer or an external driving circuit. When a data driving circuit or data driver (not shown) for generating data signals is formed directly on the substrate **110**, the data line **171** may extend and be directly connected to the data driving circuit.

[0092] The driving voltage lines **172** transmit a driving voltage and extend in a longitudinal direction, thereby intersecting the gate lines **121**. Each driving voltage line **172** includes a plurality of second input electrodes **173b** connected to the second source region **153b** through the contact hole **163b**. The driving voltage line **172** overlaps the storage electrode **127** and they may be connected to each other.

[0093] The first output electrode **175a** is separated from the data line **171** and the driving voltage line **172**. The first output electrode **175a** is connected to the first drain region **155a** through the contact hole **165a** and to the third gate electrode **124b** through the contact hole **164**.

[0094] The second output electrode **175b** is separated from the data line **171**, the driving voltage line **172**, and the first output electrode **175a**, and is connected to the second drain region **155b** through the contact hole **165b**.

[0095] The data conductors **171**, **172**, **175a**, and **175b** may be made of a refractory metal such as molybdenum, chromium, tantalum, or titanium, or alloys thereof, and have a multi-layered structure including a refractory metal layer (not shown) and a low resistance conductive layer (not shown). The multi-layered structure includes, for example, a dual layer of a chromium or molybdenum (alloy) lower layer and an aluminum (alloy) upper layer, and a triple-layer of a molybdenum (alloy) lower layer, an aluminum (alloy) middle layer, and a molybdenum (alloy) upper layer. However, the data conductors **171**, **172**, **175a**, and **175b** may be made of various other metals or conductors.

[0096] A passivation layer **180** is formed on the data conductors **171**, **172**, **175a**, and **175b**. The passivation layer **180** is made of an inorganic material, an organic material, or a low dielectric constant insulating material.

[0097] The passivation layer **180** has a plurality of contact holes **185** exposing the second output electrode **175b**. The passivation layer **180** may also have a plurality of contact holes (not shown) exposing the end of the data line **171** and the passivation layer **180** and the second interlayer insulating

layer **161** may have a plurality of contact holes (not shown) exposing the end of the gate line **121**.

[0098] A plurality of pixel electrodes **191** are formed on the passivation layer **180**. The pixel electrodes **191** are physically and electrically connected to the second output electrodes **175b** through the contact holes **185** and may be formed of a transparent conductive material such as ITO or IZO, or a reflective conductor such as silver, aluminum, or alloys thereof.

[0099] A plurality of contact assistants (not shown) or connecting members (not shown) may be formed on the passivation layer **180** and may be connected to the exposed ends of the gate lines **121** and the data lines **171**.

[0100] Partitions or a pixel defining layer **361** are formed on the passivation layer **180**. The partitions **361** define a plurality of openings enclosing edges of the pixel electrodes **191** like a bank and are made of an organic insulator or an inorganic insulator. The partitions **361** may be made of a photoresist including black pigments and the partitions **361** function as a light blocking member in this case thereby simplifying the manufacturing process.

[0101] An organic light-emitting member or organic light-emitting layer **370** is formed in openings **365** defined by the partitions **361** on the pixel electrode **191**. According to some embodiments, the organic light-emitting member **370** functions as an emission layer and is formed of an organic material uniquely emitting light of one primary color such as one of three primary colors of red, green, and blue. The OLED display may also display desired images by a spatial combination of the colored light of the primary colors emitted by the organic light-emitting members **370**.

[0102] The organic light-emitting member **370** may have a multilayered structure including auxiliary layers (not illustrated) for improving light emission efficiency of an emitting layer in addition to the emitting layer (not illustrated) emitting light. In the auxiliary layers, an electron transport layer (not illustrated), a hole transport layer (not illustrated) for adjusting the balance of electrons and holes, an electron injecting layer (not illustrated), and a hole injecting layer (not illustrated) for reinforcing injection of the electrons and the holes, are included.

[0103] A common electrode **270** is formed on the organic light-emitting member **370**. The common electrode **270** receives a common voltage V_{ss} and may be formed of reflective metal including calcium (Ca), barium (Ba), magnesium (Mg), aluminum, silver, or the like, or a transparent conductive material such as ITO or IZO.

[0104] In the OLED display, the first semiconductor **151a**, the first gate electrode **124a** connected to the gate line **121**, the second gate electrode **125a** formed on the first gate electrode **124a**, the first input electrode **173a** connected to the data line **171**, and the first output electrode **175a** together form the switching thin film transistor (TFT) Qs. The channel of the switching thin film transistor Qs is formed in the first channel regions **154a1** and **154a2** of the first semiconductor **151a**. The second semiconductor **151b**, the third gate electrode **124b** connected to the first output electrode **175a**, the second input electrode **173b** connected to the driving voltage line **172**, and the second output electrode **175b** connected to the pixel electrode **191** together form the driving thin film transistor (TFT) Qd connected to the organic light-emitting member. The channel of the driving thin film transistor Qd is formed in the channel region **154b** of the second semiconductor **151b**. The pixel electrode **191**, the organic light-emitting

member **370**, and the common electrode **270** form the OLED. The pixel electrode **191** is an anode and the common electrode **270** is a cathode, or alternatively, the pixel electrode **191** is a cathode and the common electrode **270** is an anode. The storage electrode **127**, the driving voltage line **172**, and the storage region **157**, which overlap each other, may form a storage capacitor Cst.

[0105] Such an OLED display emits light upward or downward from the substrate **110** to display an image. An opaque pixel electrode **191** and a transparent common electrode **270** are applied to a top emission OLED display which displays an image in an upper direction of the substrate **110**. A transparent pixel electrode **191** and an opaque common electrode **270** are applied to a bottom emission OLED display which displays an image in a lower direction of the substrate **110**.

[0106] Next, a manufacturing method of a thin film transistor in the OLED display according to an exemplary embodiment will be described with reference to FIG. 6 to FIG. 8.

[0107] FIG. 6 to FIG. 8 are views showing a method of manufacturing an OLED display according to an exemplary embodiment.

[0108] Referring to FIG. 6 and FIG. 7, a blocking film **111** formed of a silicon nitride (SiNx) or a silicon oxide (SiOx) is formed on an insulation substrate **110** formed of transparent glass or plastic. The blocking film **111** may be formed to have a dual-layer structure.

[0109] A plurality of pairs of the first and second semiconductor islands **151a** and **151b** formed of polysilicon are formed on the blocking film **111** and a gate insulating layer **140** formed of a silicon nitride or a silicon oxide is formed covering the first and second semiconductors **151a** and **151b** and the blocking film **111**.

[0110] Next, a conductive layer **124** is formed to form the first gate electrode **124a** and a photoresist mask PR is formed on the first semiconductor layer **151a** at a position to form the first gate electrode **124a** on the conductive layer **124**.

[0111] The conductive layer **124** is etched by using the photoresist mask PR to form the first gate electrode **124a**.

[0112] The thickness of the first gate electrode **124a** is formed to be less than about 1000 Å in order to facilitate the formation of the lightly doped region **152a** by partially transmitting the impurity through the first gate electrode **124a** when doping the impurity to the first semiconductor **151a**. The impurity is not transmitted through the second gate electrode **125a**.

[0113] Next, referring to FIG. 8, the first interlayer insulating layer **160** formed of an inorganic insulator such as a silicon nitride or a silicon oxide, an organic insulator, or a low dielectric insulator is formed on the first gate electrode **124a**.

[0114] The second gate electrode **125a** is formed on the first interlayer insulating layer **160** and positioned over each of the first semiconductor **151a** and the first gate electrode **124a**. A third gate electrode **124b** is formed on the first interlayer insulating layer and positioned over the second semiconductor **151b**.

[0115] At this time, the second gate electrode **125a** is formed to have a narrower width than that of the first gate electrode **124a** so as to be appropriate for forming the lightly doped region **152a** of the first semiconductor **151a** with the desired width. The third gate electrode **124b** is formed with a width corresponding to the width of the channel region of the second semiconductor **151b**.

[0116] According to some embodiments, first doping is then performed on the first semiconductor layer **151a** to add

the impurity element providing the n-type conductivity. The doping is performed by using the first gate electrode **124a** and the second gate electrode **125a** as a mask for the impurity element and is performed to add the impurity element to the region under the first gate electrode **124a**.

[0117] Accordingly, the lightly doped region (LDD region) **152a** overlapping the first gate electrode **124a** and the source and drain regions **153a** and **155a** having a higher impurity concentration than the lightly doped region **152a** may be formed.

[0118] Through the process, the first source and drain regions **153a** and **155a** may be formed outside the width of the first gate electrode **124a**, the lightly doped region **152a** may be formed at the position corresponding to the difference in width between the first and second gate electrodes **124a** and **125a**, and the channel region **154a** may be positioned at the position corresponding to the width of the second gate electrode **125a**.

[0119] Accordingly, control of the width of the lightly doped region **152a** is possible by controlling the width of the second gate electrode **125a**.

[0120] In the OLED display according to the exemplary embodiment shown in FIG. 6 to FIG. 8, the first semiconductor **151a**, the first gate electrode **124a**, and the second gate electrode **125a** formed on the first gate electrode **124a** together form the switching thin film transistor (TFT) Qs. The switching TFT Qs is connected to the data conductor. The second semiconductor **151b** and the third gate electrode **124b** form the driving thin film transistor (TFT) Qd and is connected to the organic light-emitting member.

[0121] As described above, according to an exemplary embodiment, the extrinsic region and the lightly doped region of the semiconductor layer of the OLED display may be easily formed and high quality characteristics may be obtained in the on and off states.

[0122] While the described technology has been described in connection with what is presently considered to be practical exemplary embodiments, it is to be understood that the invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

What is claimed is:

1. An organic light-emitting diode (OLED) display, comprising:

- a substrate;
- a first semiconductor layer formed over the substrate and including a first channel region, a first source region, a first drain region, and a lightly doped region formed between i) the first channel region and ii) the first source and drain regions;
- a second semiconductor layer formed over the substrate and including a second channel region, a second source region, and second drain region;
- a gate insulating layer formed over the first and second semiconductor layers and the substrate;
- a first gate electrode formed over the gate insulating layer wherein the first gate electrode is formed directly above at least a portion of the first semiconductor layer;
- a first interlayer insulating layer formed over the first gate electrode and the gate insulating layer;

- a second gate electrode formed over the first interlayer insulating layer wherein the second gate electrode is formed directly above at least a portion of the first gate electrode; and

- a third gate electrode formed directly above at least a portion of the second semiconductor layer, wherein the width of the second gate electrode is less than that of the first gate electrode, wherein at least a portion of the lightly doped region overlaps the first gate electrode, and wherein the lightly doped region does not overlap the second gate electrode.

2. The OLED display of claim 1, wherein the first channel region overlaps i) at least a portion of the first gate electrode and ii) the second gate electrode and wherein the first source and drain regions overlap neither the first gate electrode nor the second gate electrode.

3. The OLED display of claim 2, further comprising a blocking film formed between i) the substrate and ii) the first and second semiconductor layers.

4. The OLED display of claim 3, wherein the first semiconductor layer is doped with at least one of boron, gallium, phosphorus, or arsenic.

5. The OLED display of claim 2, wherein the lightly doped region comprises an offset region including fewer impurities than each of the first source and drain regions.

6. The OLED display of claim 1, wherein the second channel region is formed directly below the third gate electrode and wherein the second source and drain regions do not overlap the third gate electrode.

7. The OLED display of claim 1, wherein the first gate electrode has a thickness of less than about 1000 Å.

8. The OLED display of claim 2, further comprising:

- a second interlayer insulating layer formed over the second and third gate electrodes;
 - a plurality of data conductors formed over the second interlayer insulating layer;
 - a passivation layer formed over the data conductors;
 - a plurality of pixel electrodes formed over the passivation layer;
 - a pixel defining layer formed over the passivation layer and at least a portion of the pixel electrodes;
 - an organic light-emitting layer formed over the pixel electrodes; and
 - a common electrode formed over the organic light-emitting layer,
- wherein the second interlayer insulating layer and the gate insulating layer define a plurality of contact holes, wherein the passivation layer defines a plurality of contact holes, wherein the data conductors pass through the respective contact holes to be electrically connected to the first source and drain regions, the second source and drain regions, and the pixel electrodes.

9. The OLED display of claim 8, wherein the first semiconductor layer and the first and second gate electrodes form a switching thin film transistor electrically connected to the data conductors and wherein the second semiconductor layer and the third gate electrode form a driving thin film transistor electrically connected to the organic light-emitting layer.

10. A method of manufacturing an organic light-emitting diode (OLED) display, comprising:

- forming a first semiconductor layer and a second semiconductor layer over a substrate;

forming a gate insulating layer over the first and second semiconductor layers and the substrate;
 forming a first gate electrode over the gate insulating layer such that the first gate electrode is formed directly above at least a portion the first semiconductor layer;
 forming a first interlayer insulating layer over the first gate electrode and the gate insulating layer;
 forming a second gate electrode over the first interlayer insulating layer such that the second gate electrode is formed directly above at least a portion of the first gate electrode;

forming a third gate electrode over the first interlayer insulating layer such that the third gate electrode is formed directly above at least a portion of the second semiconductor layer; and

doping the first and second semiconductor layers, wherein the width of the second gate electrode is less than that of the first gate electrode,

wherein the first semiconductor layer includes a first channel region, a first source region, a first drain region, and a lightly doped region between i) the first channel region and ii) the first source and drain regions,

wherein the lightly doped region overlaps the first gate electrode and does not overlap the second gate electrode.

11. The method of claim **10**, wherein the first channel region overlaps i) at least a portion of the first gate electrode and ii) the second gate electrode and wherein the first source and drain regions overlaps neither the first gate electrode nor the second gate electrode.

12. The method of claim **11**, further comprising forming a blocking film over the substrate before forming the first and second semiconductor layers.

13. The method of claim **12**, wherein the doping comprises doping with at least one of boron, gallium, phosphorus, or arsenic.

14. The method of claim **11**, wherein the lightly doped region comprises an offset region including fewer impurities than each of the first source and drain regions.

15. The method of claim **10**, wherein the second channel region is formed substantially directly below the third gate electrode and wherein the second source and drain regions do not overlap the third gate electrode.

16. The method of claim **10**, wherein the first gate electrode has a thickness of less than about 1000 Å.

17. The method of claim **11**, further comprising:

forming a second interlayer insulating layer over the second and third gate electrodes;

forming a plurality of first contact holes in the second interlayer insulating layer and the gate insulating layer to expose the first source and drain regions and the second source and drain regions;

forming a plurality of data conductors over the second interlayer insulating layer and in the first contact holes;
 forming a passivation layer over the data conductors;
 forming a plurality of second contact holes in the passivation layer to expose the data conductors;
 forming a plurality of pixel electrodes over the passivation layer and in the second contact holes;

forming a pixel defining layer over the passivation layer and at least a portion of the pixel electrodes; forming an organic light-emitting layer over the pixel electrodes; and

forming a common electrode over the organic light-emitting layer.

18. The method of claim **17**, wherein the first semiconductor layer and the first and second gate electrodes form a switching thin film transistor electrically connected to the data conductors and wherein the second semiconductor layer and the third gate electrode form a driving thin film transistor electrically connected to the organic light-emitting layer.

19. An organic light-emitting diode (OLED) display including a plurality of thin film transistors (TFTs), each TFT comprising:

a substrate;

a semiconductor layer formed over the substrate and including a first channel region, a source region, a drain region, and a lightly doped region formed between i) the first channel region and ii) the source and drain regions;

a first gate electrode formed directly over at least a portion of the semiconductor layer; and

a second gate electrode formed directly over at least a portion of the first gate electrode, wherein the width of the second gate electrode is less than that of the first gate electrode,

wherein at least a portion of the lightly doped region overlaps the first gate electrode and does not overlap the second gate electrode.

20. The OLED display of claim **19**, wherein the semiconductor layer further comprises:

a second channel region; and

an intermediate region,

wherein the lightly doped region is further located between i) the intermediate region and ii) the first and second channel regions,

wherein the first gate electrode comprises a pair of first gate electrodes respectively formed directly above the first and second channel regions, and

wherein the second gate electrode comprises a pair of second gate electrodes respectively formed directly above the pair of first gate electrodes.

* * * * *

专利名称(译)	有机发光二极管 (OLED) 显示器及其制造方法		
公开(公告)号	US20150090980A1	公开(公告)日	2015-04-02
申请号	US14/457862	申请日	2014-08-12
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE WANG WOO KO MOO SOON WOO MIN WOO LEE II JEONG LEE JEONG HO		
发明人	LEE, WANG WOO KO, MOO SOON WOO, MIN WOO LEE, II JEONG LEE, JEONG HO		
IPC分类号	H01L27/32 H01L27/12 H01L29/786 H01L51/56		
CPC分类号	H01L27/3262 H01L51/56 H01L2227/323 H01L29/78675 H01L27/1259 H01L27/124 H01L27/127 H01L29/78621 H01L29/78645 H01L27/1214 H01L27/1237 H01L29/42384 H01L27/3258 H01L27/3276		
优先权	1020130115350 2013-09-27 KR		
其他公开文献	US9263507		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种具有薄膜晶体管 (TFT) 的有机发光二极管 (OLED) 显示器。在一个方面, OLED显示器的TFT包括衬底和形成在衬底上方的第一半导体层, 第一半导体层包括第一沟道, 源极和漏极区域以及第一沟道区域与第一源极和漏极区域之间的轻掺杂区域。 OLED显示器还包括形成在衬底上方并包括第二沟道, 源极和漏极区域的第二半导体层。 OLED显示器还包括形成在第一半导体层上的第一和第二栅电极以及形成在第二半导体层上的第三栅电极。第二栅电极的宽度小于第一栅电极的宽度, 并且轻掺杂区与第一栅电极的一部分重叠并且不与第二栅电极重叠。

