



US 20160351651A1

(19) **United States**(12) **Patent Application Publication**
JANG et al.(10) **Pub. No.: US 2016/0351651 A1**(43) **Pub. Date: Dec. 1, 2016**(54) **ORGANIC LIGHT EMITTING DISPLAY
DEVICE AND METHOD OF
MANUFACTURING THE SAME**(71) Applicant: **LG DISPLAY CO., LTD.**, SEOUL
(KR)(72) Inventors: **Jin-Hee JANG**, SEOUL (KR); **Se June
KIM**, PAJU-SI (KR); **Joon Suk LEE**,
SEOUL (KR); **So Jung LEE**, PAJU-SI
(KR); **Jong Hyeok IM**, BUSAN (KR);
Jae Sung LEE, SEOUL (KR)(73) Assignee: **LG DISPLAY CO., LTD.**, SEOUL
(KR)(21) Appl. No.: **15/167,456**(22) Filed: **May 27, 2016**(30) **Foreign Application Priority Data**

May 29, 2015 (KR) 10-2015-0076674

Publication Classification(51) **Int. Cl.**
H01L 27/32 (2006.01)
H01L 51/52 (2006.01)(52) **U.S. Cl.**CPC **H01L 27/3276** (2013.01); **H01L 51/5228**
(2013.01); **H01L 51/5215** (2013.01); **H01L**
27/3244 (2013.01); **H01L 2227/323** (2013.01);
H01L 2251/301 (2013.01); **H01L 2224/05166**
(2013.01); **H01L 2224/0518** (2013.01); **H01L**
2224/05647 (2013.01); **H01L 2924/0132**
(2013.01); **H01L 2224/05073** (2013.01)

(57)

ABSTRACT

Discussed are an organic light emitting display device and a method of manufacturing the same. The organic light emitting display device according to an embodiment includes a substrate including an active area and a pad area, a thin film transistor (TFT) in the active area of the substrate, an anode electrode on the TFT, an organic emission layer on the anode electrode, a cathode electrode on the organic emission layer, an auxiliary electrode connected to the cathode electrode and disposed on the same layer as the anode electrode, a signal pad in the pad area of the substrate, and a pad electrode connected to the signal pad to cover a top of the signal pad for preventing the top of the signal pad from being corroded. The TFT includes a gate electrode. The signal pad is disposed on the same layer as the gate electrode.




FIG. 1
RELATED ART




FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 3F




FIG. 3G




FIG. 3H






FIG. 3I





**ORGANIC LIGHT EMITTING DISPLAY
DEVICE AND METHOD OF
MANUFACTURING THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATIONS

[0001] This application claims the priority benefit of the Korean Patent Application No. 10-2015-0076674 filed on May 29, 2015, which is hereby incorporated by reference as if fully set forth herein.

BACKGROUND OF THE INVENTION

[0002] Field of the Invention

[0003] The present invention relates to an organic light emitting display device, and more particularly, to a top emission type organic light emitting display device and a method of manufacturing the same.

[0004] Discussion of the Related Art

[0005] Organic light emitting display devices are self-emitting devices and have low power consumption, a fast response time, high emission efficiency, high luminance, and a wide viewing angle.

[0006] The organic light emitting display devices are classified into a top emission type and a bottom emission type, based on a transmission direction of light emitted from an organic light emitting device. In the bottom emission type, a circuit element is disposed between an emission layer and an image displaying surface, and for this reason, an aperture ratio is lowered. On the other hand, in the top emission type, the circuit element is not disposed between the emission layer and the image displaying surface, and thus, an aperture ratio is enhanced.

[0007] FIG. 1 is a schematic cross-sectional view of a related art top emission type organic light emitting display device.

[0008] As seen in FIG. 1, a thin film transistor (TFT) layer T which includes an active layer 11, a gate insulation layer 12, a gate electrode 13, an interlayer dielectric 14, a source electrode 15, and a drain electrode 16 is formed in an active area AA on a substrate 10, and a passivation layer 20 and a planarization layer 30 are sequentially formed on the TFT layer T.

[0009] An anode electrode 40 and an auxiliary electrode 50 are formed on the planarization layer 30. The auxiliary electrode 50 decreases a resistance of a cathode electrode 80 to be described below.

[0010] A bank 60 is formed on the anode electrode 40 and the auxiliary electrode 50 and defines a pixel area. An organic emission layer 70 is formed in the pixel area defined by the bank 60, and the cathode electrode 80 is formed on the organic emission layer 70.

[0011] In the top emission type, light emitted from the organic emission layer 70 travels through the cathode electrode 80. Therefore, the cathode electrode 80 is formed of a transparent conductive material, and for this reason, a resistance of the cathode electrode 80 increases. In order to decrease the resistance of the cathode electrode 80, the cathode electrode 80 is connected to the auxiliary electrode 50.

[0012] The gate insulation layer 12 and the interlayer dielectric 14 are formed in a pad area PA on the substrate 10, a signal pad 90 is formed on the interlayer dielectric 14, and the passivation layer 20 is formed on the signal pad 90. A

hole is formed in the passivation layer 20, and the signal pad 90 is exposed to the outside through the hole. Since the signal pad 90 should be connected to an external driving circuit, the hole is formed in the passivation layer 20, and the signal pad 90 is exposed to the outside through the hole.

[0013] The related art top emission type organic light emitting display device has at least the following problems.

[0014] Since the signal pad 90 should be connected to the external driving circuit, a top of the signal pad 90 is exposed to the outside. For this reason, the top of the signal pad 90 is corroded, and the corrosion is spread to another area. In order to prevent the top of the signal pad 90 from being corroded, a metal layer which is good in corrosion resistance may be further formed on the top of the signal pad 90, but in this case, a separate process is additionally performed. Also, in order to prevent the top of the signal pad 90 from being corroded without the separate process being additionally performed, an electrode layer which is the same as the anode electrode 40 may be formed on the signal pad 90 through the same process, but in this case, it is unable to prevent corrosion from being made through a side of the electrode layer.

[0015] Moreover, in order to connect the signal pad 90 to the external driving circuit, the hole is formed in the passivation layer 20, and the top of the signal pad 90 is exposed through the hole. However, if the hole is previously formed in the passivation layer 20, an etchant for forming a pattern of the anode electrode 40 flows in through the hole to damage the signal pad 90. In order to prevent the damage, the hole of the passivation layer 20 for exposing the top of the signal pad 90 may be separately performed after a process of forming the pattern of the anode electrode 40 is completed, but in this case, a separate mask process is additionally performed.

SUMMARY OF THE INVENTION

[0016] Accordingly, the present invention is directed to provide a top emission type organic light emitting display device and a method of manufacturing the same that substantially obviate one or more problems due to limitations and disadvantages of the related art.

[0017] An aspect of the present invention is directed to provide a top emission type organic light emitting display device and a method of manufacturing the same, in which the number of additional processes is minimized, and a signal pad is prevented from being corroded.

[0018] In addition to the aforesaid objects of the present invention, other features and advantages of the present invention will be described below, but will be clearly understood by those skilled in the art from descriptions below.

[0019] Additional advantages and features of the invention will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following or may be learned from practice of the invention. The objectives and other advantages of the invention may be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

[0020] To achieve these and other advantages and in accordance with the purpose of the invention, as embodied and broadly described herein, there is provided an organic light emitting display device that includes a substrate includ-

ing an active area and a pad area, a thin film transistor (TFT) in the active area of the substrate, the TFT including a gate electrode, an anode electrode on the TFT, an organic emission layer on the anode electrode, a cathode electrode on the organic emission layer, an auxiliary electrode connected to the cathode electrode and disposed on the same layer as the anode electrode, a signal pad in the pad area of the substrate, the signal pad being disposed on the same layer as the gate electrode, and a pad electrode connected to the signal pad to cover a top of the signal pad for preventing the top of the signal pad from being corroded.

[0021] In another aspect of the present invention, there is provided a method of manufacturing an organic light emitting display device which includes forming a thin film transistor (TFT) in an active area of a substrate and forming a signal pad and a first pad electrode, connected to the signal pad, in a pad area of the substrate, forming a passivation layer on the TFT and the first pad electrode, forming a planarization layer on the passivation layer, removing a certain region of the passivation layer to simultaneously form an area, through which the TFT is exposed to the outside, and an area through which the first pad electrode is exposed to the outside, forming a first anode electrode connected to the TFT, a first auxiliary electrode spaced apart from the first anode electrode, and a second pad electrode that is connected to the first pad electrode and covers the exposed first pad electrode, and forming a second anode electrode, covering a top and a side surface of the first anode electrode, and a second auxiliary electrode covering a top and a side surface of the first auxiliary electrode.

[0022] It is to be understood that both the foregoing general description and the following detailed description of the present invention are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0023] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this application, illustrate embodiments of the invention and together with the description serve to explain the principle of the invention. In the drawings:

[0024] FIG. 1 is a schematic cross-sectional view of a related art organic light emitting display device;

[0025] FIG. 2 is a schematic cross-sectional view of an organic light emitting display device according to an embodiment of the present invention; and

[0026] FIGS. 3A to 3J are process cross-sectional views illustrating a method of manufacturing an organic light emitting display device according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0027] Reference will now be made in detail to the exemplary embodiments of the present invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

[0028] Advantages and features of the present invention, and implementation methods thereof will be clarified through following embodiments described with reference to

the accompanying drawings. The present invention may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the present invention to those skilled in the art. Further, the present invention is only defined by scopes of claims.

[0029] A shape, a size, a ratio, an angle, and a number disclosed in the drawings for describing embodiments of the present invention are merely an example, and thus, the present invention is not limited to the illustrated details. Like reference numerals refer to like elements throughout. In the following description, when the detailed description of the relevant known function or configuration is determined to unnecessarily obscure the important point of the present invention, the detailed description will be omitted. In a case where 'comprise', 'have', and 'include' described in the present specification are used, another part may be added unless 'only~' is used. The terms of a singular form may include plural forms unless referred to the contrary.

[0030] In construing an element, the element is construed as including an error range although there is no explicit description.

[0031] In describing a position relationship, for example, when a position relation between two parts is described as 'on~', 'over~', 'under~', and 'next~', one or more other parts may be disposed between the two parts unless 'just' or 'direct' is used.

[0032] In describing a time relationship, for example, when the temporal order is described as 'after~', 'subsequent~', 'next~', and 'before~', a case which is not continuous may be included unless 'just' or 'direct' is used.

[0033] It will be understood that, although the terms "first", "second", etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another. For example, a first element could be termed a second element, and, similarly, a second element could be termed a first element, without departing from the scope of the present invention.

[0034] Features of various embodiments of the present invention may be partially or overall coupled to or combined with each other, and may be variously inter-operated with each other and driven technically as those skilled in the art can sufficiently understand. The embodiments of the present invention may be carried out independently from each other, or may be carried out together in co-dependent relationship.

[0035] Hereinafter, exemplary embodiments of the present invention will be described in detail with reference to the accompanying drawings.

[0036] FIG. 2 is a cross-sectional view of an organic light emitting display device 100 according to an embodiment of the present invention. All the components of the organic light emitting display device according to all embodiments of the present invention are operatively coupled and configured.

[0037] As seen in FIG. 2, the organic light emitting display device 100 according to an embodiment of the present invention may include an active area AA and a pad area PA which are provided on the substrate 100.

[0038] A thin film transistor (TFT) layer T, a passivation layer 165, a planarization layer 170, a first anode electrode 180, a second anode electrode 200, a first auxiliary electrode

190, a second auxiliary electrode 210, a bank 220, a partition wall 230, an organic emission layer 240, and a cathode electrode 250 may be formed in the active area AA on the substrate 100.

[0039] The TFT layer T may include an active layer 110, a gate insulation layer 120, a gate electrode 130, an interlayer dielectric 140, a source electrode 150, and a drain electrode 160.

[0040] The active layer 110 may be formed on the substrate 100 to overlap the gate electrode 130. The active layer 110 may be formed of a silicon-based semiconductor material, or may be formed of an oxide-based semiconductor material. A light shielding layer may be further formed between the substrate 100 and the active layer 110, and in this case, external light incident through a bottom of the substrate 100 is blocked by the light shielding layer, thereby preventing the active layer 110 from being damaged by the external light.

[0041] The gate insulation layer 120 may be formed on the active layer 110. The gate insulation layer 120 may insulate the active layer 110 from the gate electrode 130. The gate insulation layer 120 may be formed of an inorganic insulating material, for example, silicon oxide (SiO_x), silicon nitride (SiN_x), or a multilayer thereof, but is not limited thereto. The gate insulation layer 120 may extend to the pad area PA.

[0042] The gate electrode 130 may be formed on the gate insulation layer 120. The gate electrode 130 may be formed to overlap the active layer 110 with the gate insulation layer 120 therebetween. The gate electrode 130 may be formed of a single layer or a multilayer including one of molybdenum (Mo), aluminum (Al), chromium (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd), and copper (Cu) or an alloy thereof, but is not limited thereto.

[0043] The gate electrode 130 may include a lower gate electrode 131 and an upper gate electrode 132.

[0044] The lower gate electrode 131 may be formed between the gate insulation layer 120 and the upper gate electrode 132 to enhance an adhesive force between the gate insulation layer 120 and the upper gate electrode 132. Also, the lower gate electrode 131 prevents a bottom of the upper gate electrode 132 from being corroded. Therefore, an oxidation rate of the lower gate electrode 131 may be lower than that of the upper gate electrode 132. That is, the lower gate electrode 131 may be formed of a material which is stronger in corrosion resistance than a material included in the upper gate electrode 132. As described above, the lower gate electrode 131 may be formed of an alloy (MoTi) of Mo and Ti, but is not limited thereto.

[0045] The upper gate electrode 132 may be formed on a top of the lower gate electrode 131 and may be formed of copper (Cu), but is not limited thereto. In order to lower a total resistance of the gate electrode 130, a thickness of the upper gate electrode 132 may be formed thicker than that of the lower gate electrode 131.

[0046] The interlayer dielectric 140 may be formed on the gate electrode 130. The interlayer dielectric 140 may be formed of the same inorganic insulating material as that of the gate insulation layer 120, for example, may be formed of silicon oxide (SiO_x), silicon nitride (SiN_x), or a multilayer thereof, but is not limited thereto. The interlayer dielectric 140 may extend to the pad area PA.

[0047] The source electrode 150 and the drain electrode 160 may be formed to face each other on the interlayer

dielectric 140. A first contact hole CH1 exposing one end region of the active layer 110 and a second contact hole CH2 exposing the other end region of the active layer 110 may be included in the gate insulation layer 120 and the interlayer dielectric 140. The source electrode 150 may be connected to the other end region of the active layer 110 through the second contact hole CH2, and the drain electrode 160 may be connected to the one end region of the active layer 110 through the first contact hole CH1.

[0048] The source electrode 150 may include a lower source electrode 151 and an upper source electrode 152.

[0049] The lower source electrode 151 may be formed between the interlayer dielectric 140 and the upper source electrode 152 to enhance an adhesive force between the interlayer dielectric 140 and the upper source electrode 152. Also, the lower source electrode 151 protects a bottom of the upper source electrode 152, thereby preventing the bottom of the upper source electrode 152 from being corroded. Therefore, an oxidation rate of the lower source electrode 151 may be lower than that of the upper source electrode 152. That is, the lower source electrode 151 may be formed of a material which is stronger in corrosion resistance than a material included in the upper source electrode 152. As described above, the lower source electrode 151 may act as an adhesion enhancement layer or an anti-corrosion layer and may be formed of an alloy (MoTi) of Mo and Ti, but is not limited thereto.

[0050] The upper source electrode 152 may be formed on a top of the lower source electrode 151. The upper source electrode 152 may be formed of Cu which is metal having a low resistance, but is not limited thereto. The upper source electrode 152 may be formed of metal which is relatively lower in resistance than the lower source electrode 151. In order to lower a total resistance of the source electrode 150, a thickness of the upper source electrode 152 may be formed thicker than that of the lower source electrode 151.

[0051] Similarly to the above-described source electrode 150, the drain electrode 160 may include a lower drain electrode 161 and an upper drain electrode 162.

[0052] The lower drain electrode 161 may be formed between the interlayer dielectric 140 and the upper drain electrode 162 to enhance an adhesive force between the interlayer dielectric 140 and the upper drain electrode 162 and prevent a bottom of the upper drain electrode 162 from being corroded. Therefore, an oxidation rate of the lower drain electrode 161 may be lower than that of the upper drain electrode 162. That is, the lower drain electrode 161 may be formed of a material which is stronger in corrosion resistance than a material included in the upper drain electrode 162. As described above, the lower drain electrode 161 may be formed of an alloy (MoTi) of Mo and Ti which is the same as the above-described material of the lower source electrode 151, but is not limited thereto.

[0053] The upper drain electrode 162 may be formed on a top of the lower drain electrode 161 and may be formed of Cu which is the same as the above-described material of the upper source electrode 152, but is not limited thereto. A thickness of the upper drain electrode 162 may be formed thicker than that of the lower drain electrode 161, thereby lowering a total resistance of the drain electrode 160.

[0054] The upper drain electrode 162 may be formed of the same material as that of the upper source electrode 152 to have the same thickness as that of the upper source electrode 152, and the lower drain electrode 161 may be

formed of the same material as that of the lower source electrode **151** to have the same thickness as that of the lower source electrode **151**. In this case, the drain electrode **160** and the source electrode **150** may be simultaneously formed through the same process.

[0055] A structure of the TFT T is not limited to the illustrated structure, and may be variously modified to structures known to those skilled in the art. For example, a top gate structure where the gate electrode **130** is formed on the active layer **110** is illustrated in the drawing, but the TFT T may be formed in a bottom gate structure where the gate electrode **130** is formed under the active layer **110**.

[0056] The passivation layer **165** may be formed on the TFT layer T, and in more detail, may be formed on tops of the source electrode **150** and the drain electrode **160**. The passivation layer **165** protects the TFT layer T. The passivation layer **165** may be formed of an inorganic insulating material (for example, SiOx and SiNx), but is not limited thereto. The passivation layer **165** may extend to the pad area PA.

[0057] The planarization layer **170** may be formed on the passivation layer **165**. The planarization layer **170** may planarize an upper surface of the substrate **100** including the TFT layer T. The planarization layer **170** may be formed of an organic insulating material such as acryl resin, epoxy resin, phenolic resin, polyamide resin, polyimide resin, or the like, but is not limited thereto. The planarization layer **170** may not extend to the pad area PA.

[0058] The first anode electrode **180** and the first auxiliary electrode **190** may be formed on the planarization layer **170**. That is, the first anode electrode **180** and the first auxiliary electrode **190** may be formed on the same layer. A fourth contact hole CH4 exposing the source electrode **150** may be included in the passivation layer **165** and the planarization layer **170**, and the source electrode **150** may be connected to the first anode electrode **180** through the fourth contact hole CH4.

[0059] The first anode electrode **180** may include a first lower anode electrode **181** and a first upper anode electrode **182**.

[0060] The first lower anode electrode **181** may be formed between the planarization layer **170** and the first upper anode electrode **182** to enhance an adhesive force between the planarization layer **170** and the first upper anode electrode **182**. Also, the first lower anode electrode **181** protects a bottom of the first upper anode electrode **182**, thereby preventing the bottom of the first upper anode electrode **182** from being corroded. Therefore, an oxidation rate of the first lower anode electrode **181** may be lower than that of the first upper anode electrode **182**. That is, the first lower anode electrode **181** may be formed of a material which is stronger in corrosion resistance than a material included in the first upper anode electrode **182**. Also, the first lower anode electrode **181** protects a top of the upper source electrode **152**, thereby preventing the top of the upper source electrode **152** from being corroded. Therefore, an oxidation rate of the first lower anode electrode **181** may be lower than that of the upper source electrode **152**. That is, the first lower anode electrode **181** may be formed of a material which is stronger in corrosion resistance than a material included in the upper source electrode **152**. As described above, the first lower anode electrode **181** prevents the top of the upper source electrode **152** from being corroded, and thus, the source electrode **150** may be formed in the above-described two-

layer structure. The first lower anode electrode **181** may act as an adhesion enhancement layer or an anti-corrosion layer and may be formed of an alloy (MoTi) of Mo and Ti, but is not limited thereto.

[0061] The first upper anode electrode **182** may be formed on a top of the first lower anode electrode **181**. The first upper anode electrode **182** may be formed of Cu which is metal having a low resistance, but is not limited thereto. The first upper anode electrode **182** may be formed of metal which is relatively lower in resistance than the first lower anode electrode **181**. In order to lower a total resistance of the first anode electrode **180**, a thickness of the first upper anode electrode **182** may be formed thicker than that of the first lower anode electrode **181**.

[0062] Similarly to the above-described first anode electrode **180**, the first auxiliary electrode **190** may include a first lower auxiliary electrode **191** and a first upper auxiliary electrode **192**.

[0063] The first lower auxiliary electrode **191** may be formed between the planarization layer **170** and the first upper auxiliary electrode **192** to enhance an adhesive force between the planarization layer **170** and the first upper auxiliary electrode **192** and prevent a bottom of the first upper auxiliary electrode **192** from being corroded. Therefore, an oxidation rate of the first lower auxiliary electrode **191** may be lower than that of the first upper auxiliary electrode **192**. That is, the first lower auxiliary electrode **191** may be formed of a material which is stronger in corrosion resistance than a material included in the first upper auxiliary electrode **192**. As described above, the first lower auxiliary electrode **191** may be formed of an alloy (MoTi) of Mo and Ti which is the same as the above-described material of the first lower anode electrode **181**, but is not limited thereto.

[0064] The first upper auxiliary electrode **192** may be formed on a top of the first lower auxiliary electrode **191** and may be formed of Cu which is the same as the above-described material of the first upper anode electrode **182**, but is not limited thereto. A thickness of the first upper auxiliary electrode **192** which is relatively low in resistance may be formed thicker than that of the first lower auxiliary electrode **191** which is relatively high in resistance, thereby lowering a total resistance of the first auxiliary electrode **190**.

[0065] The first upper auxiliary electrode **192** may be formed of the same material as that of the first upper anode electrode **182** to have the same thickness as that of the first upper anode electrode **182**, and the first lower auxiliary electrode **191** may be formed of the same material as that of the first lower anode electrode **181** to have the same thickness as that of the first lower anode electrode **181**. In this case, the first auxiliary electrode **190** and the first anode electrode **180** may be simultaneously formed through the same process.

[0066] The second anode electrode **200** may be formed on a top of the first anode electrode **180**. The second anode electrode **200** may be formed to contact the whole top and a whole side surface of the first anode electrode **180**. That is, a separate insulation layer may not be formed between the second anode electrode **200** and the first anode electrode **180**, and thus, a process of forming an insulation layer and a contact hole may be omitted. The second anode electrode **200** may reflect light, emitted from the organic emission layer **240**, in an up direction and thus may include a material which is good in reflectivity. Also, the second anode elec-

trode 200 may be formed to cover the top and the side surface of the first anode electrode 180, thereby preventing the top and the side surface of the first anode electrode 180 from being corroded.

[0067] The second anode electrode 200 may include a second lower anode electrode 201, a second center anode electrode 202, and a second upper anode electrode 203.

[0068] The second lower anode electrode 201 may be formed between the first anode electrode 180 and the second center anode electrode 202. The second lower anode electrode 201 may be formed to cover the top and the side surface of the first anode electrode 180, thereby preventing the first anode electrode 180 from being corroded. To this end, an oxidation rate of the second lower anode electrode 201 may be lower than that of each of the first lower anode electrode 181 and the first upper anode electrode 182 which configure the first anode electrode 180. That is, the second lower anode electrode 201 may be formed of a material which is stronger in corrosion resistance than a material included in each of the first lower anode electrode 181 and the first upper anode electrode 182. Also, the second lower anode electrode 201 protects a bottom of the second center anode electrode 202, thereby preventing the bottom of the second center anode electrode 202 from being corroded. Therefore, an oxidation rate of the second lower anode electrode 201 may be lower than that of the second center anode electrode 202. That is, the second lower anode electrode 201 may be formed of a material which is stronger in corrosion resistance than a material included in the second center anode electrode 202. The second lower anode electrode 201 may be formed of a transparent conductive material such as indium tin oxide (ITO) or the like, but is not limited thereto.

[0069] The second center anode electrode 202 may be formed between the second lower anode electrode 201 and the second upper anode electrode 203. The second center anode electrode 202 may be formed of a material which is lower in resistance than and better in reflectivity than the second lower anode electrode 201 and the second upper anode electrode 203, and for example, may be formed of silver (Ag) and/or the like. However, the present embodiment is not limited thereto. A thickness of the second center anode electrode 202 which is relatively low in resistance may be formed thicker than that of each of the second lower anode electrode 201 and the second upper anode electrode 203 which are relatively high in resistance, thereby lowering a total resistance of the second anode electrode 200.

[0070] The second upper anode electrode 203 may be formed on a top of the second center anode electrode 202, thereby preventing the top of the second center anode electrode 202 from being corroded. To this end, an oxidation rate of the second upper anode electrode 203 may be lower than that of the second center anode electrode 202. That is, the second upper anode electrode 203 may be formed of a material which is stronger in corrosion resistance than a material included in the second center anode electrode 202. The second upper anode electrode 203 may be formed of a transparent conductive material such as ITO or the like, but is not limited thereto.

[0071] The second auxiliary electrode 210 may be formed on a top of the first auxiliary electrode 190. The second auxiliary electrode 210 may be formed on the same layer as that of the second anode electrode 200. The second auxiliary electrode 210 may be formed to contact the whole top and

a whole side surface of the first auxiliary electrode 190. That is, a separate insulation layer may not be formed between the second auxiliary electrode 210 and the first auxiliary electrode 190, and thus, a process of forming an insulation layer and a contact hole may be omitted. The second auxiliary electrode 210 may lower a resistance of the cathode electrode 250 along with the first auxiliary electrode 190. According to an embodiment of the present invention, in order to lower a resistance of the cathode electrode 250, two auxiliary electrodes (e.g., the first auxiliary electrode 190 and the second auxiliary electrode 210) may be stacked, and thus, the desired resistance characteristics of the auxiliary electrodes are more easily adjusted. Also, the second auxiliary electrode 210 may be formed to cover the top and the side surface of the first auxiliary electrode 190, thereby preventing the top and the side surface of the first auxiliary electrode 190 from being corroded.

[0072] The second auxiliary electrode 210 may include a second lower auxiliary electrode 211, a second center auxiliary electrode 212, and a second upper auxiliary electrode 213.

[0073] The second lower auxiliary electrode 211 may be formed between the first auxiliary electrode 190 and the second center auxiliary electrode 212. The second lower auxiliary electrode 211 may be formed to cover the top and the side surface of the first auxiliary electrode 190, thereby preventing the first auxiliary electrode 190 from being corroded. To this end, an oxidation rate of the second lower auxiliary electrode 211 may be lower than that of each of the first lower auxiliary electrode 191 and the first upper auxiliary electrode 192 which configure the first auxiliary electrode 190. That is, the second lower auxiliary electrode 211 may be formed of a material which is stronger in corrosion resistance than a material included in each of the first lower auxiliary electrode 191 and the first upper auxiliary electrode 192. Also, the second lower auxiliary electrode 211 protects a bottom of the second center auxiliary electrode 212, thereby preventing the bottom of the second center auxiliary electrode 212 from being corroded. Therefore, an oxidation rate of the second lower auxiliary electrode 211 may be lower than that of the second center auxiliary electrode 212. That is, the second lower auxiliary electrode 211 may be formed of a material which is stronger in corrosion resistance than a material included in the second center auxiliary electrode 212. The second lower auxiliary electrode 211 may be formed of a transparent conductive material such as indium tin oxide (ITO) or the like, but is not limited thereto.

[0074] The second center auxiliary electrode 212 may be formed between the second lower auxiliary electrode 211 and the second upper auxiliary electrode 213. The second center auxiliary electrode 212 may be formed of a material which is lower in resistance than and better in reflectivity than the second lower auxiliary electrode 211 and the second upper auxiliary electrode 213, and for example, may be formed of silver (Ag) and/or the like. However, the present embodiment is not limited thereto. A thickness of the second center auxiliary electrode 212 which is relatively low in resistance may be formed thicker than that of each of the second lower auxiliary electrode 211 and the second upper auxiliary electrode 213 which are relatively high in resistance, thereby lowering a total resistance of the second auxiliary electrode 210.

[0075] The second upper auxiliary electrode 213 may be formed on a top of the second center auxiliary electrode 212, thereby preventing the top of the second center auxiliary electrode 212 from being corroded. To this end, an oxidation rate of the second upper auxiliary electrode 213 may be lower than that of the second center auxiliary electrode 212. That is, the second upper auxiliary electrode 213 may be formed of a material which is stronger in corrosion resistance than a material included in the second center auxiliary electrode 212. The second upper auxiliary electrode 213 may be formed of a transparent conductive material such as ITO or the like, but is not limited thereto.

[0076] The second upper auxiliary electrode 213 may be formed of the same material as that of the second upper anode electrode 203 to have the same thickness as that of the second upper anode electrode 203, the second center auxiliary electrode 212 may be formed of the same material as that of the second center anode electrode 202 to have the same thickness as that of the second center anode electrode 202, and the second lower auxiliary electrode 211 may be formed of the same material as that of the second lower anode electrode 201 to have the same thickness as that of the second lower anode electrode 201. In this case, the second auxiliary electrode 210 and the second anode electrode 200 may be simultaneously formed through the same process.

[0077] The bank 220 may be formed on the second anode electrode 200 and the second auxiliary electrode 210.

[0078] The bank 220 may be formed on each of one side and the other side of the second anode electrode 200 to expose a top of the second anode electrode 200. Since the bank 220 is formed to expose the top of the second anode electrode 200, an area where an image is displayed is secured. Also, since the bank 220 is formed on each of the one side and the other side of the second anode electrode 200, a side surface of the second center anode electrode 202 vulnerable to corrosion is prevented from being exposed to the outside, thereby preventing the side surface of the second center anode electrode 202 from being corroded.

[0079] The bank 220 may be formed on each of one side and the other side of the second auxiliary electrode 210 to expose a top of the second auxiliary electrode 210. Since the bank 220 is formed to expose the top of the second auxiliary electrode 210, an electrical connection space between the second auxiliary electrode 210 and the cathode electrode 250 is secured. Also, since the bank 220 is formed on each of the one side and the other side of the second auxiliary electrode 210, a side surface of the second center auxiliary electrode 212 vulnerable to corrosion is prevented from being exposed to the outside, thereby preventing the side surface of the second center auxiliary electrode 212 from being corroded.

[0080] Moreover, the bank 220 may be formed between the second anode electrode 200 and the second auxiliary electrode 210 to insulate the second anode electrode 200 from the second auxiliary electrode 210. The bank 220 may be formed of an organic insulating material such as polyimide resin, acryl resin, benzocyclobutene (BCB), or the like, but is not limited thereto.

[0081] The partition wall 230 may be formed on the second auxiliary electrode 210. The partition wall 230 may be spaced apart from the bank 220 by a certain distance, and the second auxiliary electrode 210 may be electrically connected to the cathode electrode 250 through a separation space between the partition wall 230 and the bank 220. The

second auxiliary electrode 210 may be electrically connected to the cathode electrode 250 without forming the partition wall 230. However, if the partition wall 230 is formed, the organic emission layer 240 is more easily deposition-formed. This will be described below in more detail.

[0082] If the partition wall 230 is not formed, a mask pattern which covers a top of the second auxiliary electrode 210 is needed in depositing the organic emission layer 240, in order for the top of the second auxiliary electrode 210 not to be covered by the organic emission layer 240. However, if the partition wall 230 is formed, a top of the partition wall 230 may act like eaves in depositing the organic emission layer 240, and thus, since the organic emission layer 240 is not deposited under the eaves, the mask pattern which covers the top of the second auxiliary electrode 210 is not needed. That is, with respect to a case where the organic light emitting display device is seen from the front thereof, when the top of the partition wall 230 that acts as eaves is formed to cover a separation space between the partition wall 230 and the bank 220, the organic emission layer 240 cannot penetrate into the separation space between the partition wall 230 and the bank 220, and thus, the second auxiliary electrode 210 may be exposed in the separation space between the partition wall 230 and the bank 220. Particularly, the organic emission layer 240 may be formed by a deposition process such as an evaporation process which is excellent in straightness of a deposited material, and thus, the organic emission layer 240 is not deposited in the separation space between the partition wall 230 and the bank 220 in a process of depositing the organic emission layer 240.

[0083] As described above, a width of the top of the partition wall 230 may be formed greater than that of a bottom of the partition wall 230, in order for the top of the partition wall 230 to act as the eaves. The partition wall 230 may include a lower first partition wall 231 and an upper second partition wall 232. The first partition wall 231 may be formed on a top of the second auxiliary electrode 210 and may be formed of the same material as that of the bank 220 through the same process as that of the bank 220. The second partition wall 232 may be formed on a top of the first partition wall 231. A width of a top of the second partition wall 232 may be formed greater than that of a bottom of the second partition wall 232, and particularly, the top of the second partition wall 232 may be formed to cover the separation space between the partition wall 230 and the bank 220 and may act as eaves.

[0084] The organic emission layer 240 may be formed on the second anode electrode 200. The organic emission layer 240 may include a hole injection layer, a hole transport layer, an emission layer, an electron transport layer, and an electron injection layer. The organic emission layer 240 may be modified to have various structures known to those skilled in the art.

[0085] The organic emission layer 240 may extend to the top of the bank 220. However, the organic emission layer 240 may not extend to the top of the second auxiliary electrode 210 in a state of covering the top of the second auxiliary electrode 210. This is because when the organic emission layer 240 covers the top of the second auxiliary electrode 210, it is difficult to electrically connect the second auxiliary electrode 210 to the cathode electrode 250. As described above, the organic emission layer 240 may be

formed by a deposition process without a mask that covers the top of the second auxiliary electrode 210, and in this case, the organic emission layer 240 may be formed on the top of the partition wall 230.

[0086] The cathode electrode 250 may be formed on the organic emission layer 240. The cathode electrode 250 may be formed on a surface from which light is emitted, and thus may be formed of a transparent conductive material. Since the cathode electrode 250 is formed of a transparent conductive material, a resistance of the cathode electrode 250 is high, and for this reason, in order to lower the resistance of the cathode electrode 250, the cathode electrode 250 may be connected to the second auxiliary electrode 210. That is, the cathode electrode 250 may be connected to the second auxiliary electrode 210 through the separation space between the partition wall 230 and the bank 220. The cathode electrode 250 may be formed by a deposition process such as a sputtering process which is not good in straightness of a deposited material, and thus, the cathode electrode 250 may be deposited in the separation space between the partition wall 230 and the bank 220 in a process of depositing the cathode electrode 250.

[0087] An encapsulation layer may be further formed on the cathode electrode 250 and prevents penetration of water. The encapsulation layer may use various materials known to those skilled in the art. Also, a color filter may be further formed for each pixel and on the cathode electrode 250, and in this case, white light may be emitted from the organic emission layer 240.

[0088] The gate insulation layer 120, the interlayer dielectric 140, a signal pad 300, and a pad electrode 400 may be formed in the pad area PA of the substrate 100.

[0089] The gate insulation layer 120 may be formed on the substrate 100. The interlayer dielectric 140 extend from the active area AA and may be formed all over the pad area PA.

[0090] The signal pad 300 may be formed on the gate insulation layer 120. The signal pad 300 may be formed on the same layer as that of the gate electrode 130 disposed in the active area AA.

[0091] The signal pad 300 may include a lower signal pad 301 and an upper signal pad 302.

[0092] The lower signal pad 301 may be formed between the gate insulation layer 120 and the upper signal pad 302 to enhance an adhesive force between the gate insulation layer 120 and the upper signal pad 302. Also, the lower signal pad 301 prevents a bottom of the upper signal pad 302 from being corroded. Therefore, an oxidation rate of the lower signal pad 301 may be lower than that of the upper signal pad 302. That is, the lower signal pad 301 may be formed of a material which is stronger in corrosion resistance than a material included in the upper signal pad 302. As described above, the lower signal pad 301 may be formed of an alloy (MoTi) of Mo and Ti which is the same as the above-described material of the lower gate electrode 131, but is not limited thereto.

[0093] The upper signal pad 302 may be formed on a top of the lower signal pad 301. The upper signal pad 302 may be formed of Cu which is metal having a low resistance, but is not limited thereto. The upper signal pad 302 may be formed of metal which is relatively lower in resistance than the lower signal pad 301. In order to lower a total resistance of the signal pad 300, a thickness of the upper signal pad 302 may be formed thicker than that of the lower signal pad 301.

[0094] The upper signal pad 302 may be formed of the same material as that of the upper gate electrode 132 to have the same thickness as that of the upper gate electrode 132, and the lower signal pad 301 may be formed of the same material as that of the lower gate electrode 131 to have the same thickness as that of the lower gate electrode 131. In this case, the signal pad 300 and the gate electrode 130 and/or the drain electrode 160 may be simultaneously formed through the same process.

[0095] The interlayer dielectric 140 may be formed on the signal pad 300. The interlayer dielectric 140 may extend from the active area AA. A third contact hole CH3 exposing a portion of the signal pad 300 may be included in the interlayer dielectric 140.

[0096] The interlayer dielectric 140 may be formed to expose a top of the signal pad 300 and cover a side surface of the signal pad 300. Since the interlayer dielectric 140 is formed to expose the top of the signal pad 300, the interlayer dielectric 140 may be connected to the below-described pad electrode 400. Also, the interlayer dielectric 140 may be formed on each of one side and the other side of the signal pad 300, and thus, the side surface of the upper signal pad 302 vulnerable to corrosion is not exposed to the outside, thereby preventing the side surface of the upper signal pad 302 from being corroded.

[0097] The pad electrode 400 may be formed on the interlayer dielectric 140. The pad electrode 400 may be connected to the signal pad 300 through the third contact hole CH3. The pad electrode 400 may be exposed to the outside and connected to an external driver.

[0098] The pad electrode 400 may include a lower pad electrode 401, an upper pad electrode 402, and a cover pad electrode 403.

[0099] The lower pad electrode 401 may be formed to cover a top of the upper signal pad 302 through the third contact hole CH3, thereby preventing the upper signal pad 302 from being corroded. To this end, an oxidation rate of the lower pad electrode 401 may be lower than that of the upper signal pad 302. That is, the lower pad electrode 401 may be formed of a material which is stronger in corrosion resistance than a material included in the upper signal pad 302. As described above, the lower pad electrode 401 prevents the top of the upper signal pad 302 from being corroded, and thus, the signal pad 300 may be formed in the above-described two-layer structure. An oxidation rate of the lower pad electrode 401 may be lower than that of the upper pad electrode 402. The lower pad electrode 401 may be formed of an alloy (MoTi) of Mo and Ti which is the same as the above-described material of the lower source electrode 151 and/or the lower drain electrode 161, but is not limited thereto. The lower pad electrode 401 may be formed of the same material as that of the lower source electrode 151 and/or the lower drain electrode 161 to have the same thickness as that of the lower source electrode 151 and/or the lower drain electrode 161, and in this case, the lower pad electrode 401 and the lower source electrode 151 and/or the lower drain electrode 161 may be pattern-formed through the same mask process.

[0100] The upper pad electrode 402 may be formed between the lower pad electrode 401 and the cover pad electrode 403. The upper pad electrode 402 may be formed of Cu which is metal having a low resistance, but is not limited thereto. The upper pad electrode 402 may be formed of metal which is relatively lower in resistance than the

lower pad electrode **401** and the cover pad electrode **403**. In order to lower a total resistance of the pad electrode **400**, a thickness of the upper pad electrode **402** may be formed thicker than that of each of the lower pad electrode **401** and the cover pad electrode **403**. The upper pad electrode **402** may be formed of the same material as that of the upper source electrode **152** and/or the upper drain electrode **162** to have the same thickness as that of the first upper anode electrode **182** and/or the first upper auxiliary electrode **192**, and in this case, the upper pad electrode **402** and the upper source electrode **152** and/or the upper drain electrode **162** may be pattern-formed through the same mask process.

[0101] The cover pad electrode **403** may be formed on the upper pad electrode **402**. The cover pad electrode **403** may be formed to cover a top and a side surface of the upper pad electrode **402**, thereby preventing the upper pad electrode **402** from being corroded. That is, the cover pad electrode **403** prevents the upper pad electrode **402** from being exposed to the outside. To this end, an oxidation rate of the cover pad electrode **403** may be lower than that of the upper pad electrode **402**. That is, the cover pad electrode **403** may be formed of a material which is stronger in corrosion resistance than a material forming the upper pad electrode **402**.

[0102] The cover pad electrode **403** may cover up to a side surface of the lower pad electrode **401**. In this case, an oxidation rate of the cover pad electrode **403** may be lower than that of the lower pad electrode **401**. That is, the cover pad electrode **403** may be formed of a material which is stronger in corrosion resistance than a material included in the lower pad electrode **401**. The cover pad electrode **403** may be formed of an alloy (MoTi) of Mo and Ti, but is not limited thereto. The cover pad electrode **403** may be formed of the same material as that of the first lower anode electrode **181** and/or the first lower auxiliary electrode **191** to have the same thickness as that of the first lower anode electrode **181** and/or the first lower auxiliary electrode **191**, and in this case, the cover pad electrode **403** and the first lower anode electrode **181** and/or the first lower auxiliary electrode **191** may be pattern-formed through the same mask process.

[0103] FIGS. 3A to 3J are process cross-sectional views illustrating a method of manufacturing an organic light emitting display device according to an embodiment of the present invention and relate to a method of manufacturing the above-described organic light emitting display device of FIG. 2. Thus, like reference numerals refer to like elements, and in a material and a structure of each element, the same or similar descriptions may not be repeated or may be brief.

[0104] First, as seen in FIG. 3A, an active layer **110**, a gate insulation layer **120**, a gate electrode **130**, and a signal pad **300** may be sequentially formed on a substrate **100**.

[0105] To provide a more detailed description, the active layer **110** may be formed on the substrate **100**, the gate insulation layer **120** may be formed on the active layer **110**, the gate electrode **130** may be formed on the gate insulation layer **120**, and the signal pad **300** may be formed.

[0106] Here, the active layer **110** and the gate electrode **130** may be formed in an active area AA, the gate insulation layer **120** may be formed to extend from the active area AA to a pad area PA, and the signal pad **300** may be formed in the pad area AA.

[0107] The gate electrode **130** may be configured with a lower gate electrode **131** and an upper gate electrode **132**, and the signal pad **300** may be configured with a lower

signal pad **301** and an upper signal pad **302**. The gate electrode **130** and the signal pad **300** may be simultaneously formed of the same material by the same patterning process.

[0108] Subsequently, as seen in FIG. 3B, an interlayer dielectric **140** may be formed on the gate electrode **130**, and a first contact hole CH1 and a second contact hole CH2 may be formed in the gate insulation layer **120** and the interlayer dielectric **140**. Subsequently, a third contact hole CH3 may be in a drain electrode connected to one end region of the active layer **110** through the first contact hole CH1, a source electrode **150** connected to the other end region of the active layer **110** through the second contact hole CH2, and the interlayer dielectric **140**, and a first pad electrode **400a** may be formed to be connected to the signal pad **300** through the third contact hole CH3.

[0109] Here, the source electrode **150** and the drain electrode **160** may be formed in the active area AA, and the interlayer dielectric **140** may be formed to extend from the active area AA to the pad area PA, and the first pad electrode **400a** may be formed in the pad area PA. Through such a process, a TFT layer T may be formed in the active area AA.

[0110] The source electrode **150** may include a lower source electrode **151** and an upper source electrode **152**, the drain electrode **160** may include a lower drain electrode **161** and an upper drain electrode **162**, and the first pad electrode **400a** may include a first lower pad electrode **401** and a first upper pad electrode **402**. The source electrode **150**, the drain electrode **160**, and the first pad electrode **400a** may be simultaneously formed of the same material through the same patterning process.

[0111] Subsequently, as seen in FIG. 3C, a passivation layer **165** may be formed on the source electrode **150**, the drain electrode **160**, and the first pad electrode **400a**, and a planarization layer **170** may be formed on the passivation layer **165**. The planarization layer **170** may include a fourth contact hole CH4.

[0112] The passivation layer **165** may be formed to extend from the active area AA to the pad area PA, and the planarization layer **170** may be formed in the active area AA. Since a TFT is not formed in the pad area PA, the necessity to planarize a surface thereof is small, and thus, the planarization layer **170** may not be formed in the pad area PA.

[0113] Subsequently, as seen in FIG. 3D, the fourth contact hole CH4 may be formed in the passivation layer **165**, and by removing a certain region of the passivation layer **165** in the pad area PA, the first pad electrode **400a** may be exposed to the outside. The source electrode **150** may be exposed to the outside through the fourth contact hole CH4 included in the passivation layer **165** and the planarization layer **170**.

[0114] According to an embodiment of the present invention, a process of forming the fourth contact hole CH4 of the passivation layer **165** for exposing the source electrode **150** to the outside and a process of removing a certain region of the passivation layer **165** in the pad area PA for exposing the first pad electrode **400a** to the outside may be simultaneously performed, and thus, by using one mask process, the fourth contact hole CH4 may be formed and the certain region of the passivation layer **165** may be removed, whereby the number of mask processes does not increase. To provide a more detailed description on this, since the first upper pad electrode **402** is vulnerable to corrosion, an etchant should not be brought in contact with the first upper pad electrode **402**. According to an embodiment of the

present invention, the exposed first upper pad electrode **402** may be covered by a second pad electrode **400b** in a process of FIG. 3E to be described below, and thus, the etchant cannot be brought in contact with the first upper pad electrode **402**. For the same reason as this, the process of forming the fourth contact hole CH4 and the process of removing the certain region of the passivation layer **165** may be simultaneously performed.

[0115] Subsequently, as seen in FIG. 3E, a first anode electrode **180** and a first auxiliary electrode **190** may be formed to be spaced apart from each other on the planarization layer **170** in the active area AA, and the second pad electrode **400b** may be formed on the first pad electrode **400a** in the pad area PA.

[0116] The first anode electrode **180** may be formed to be connected to the source electrode **150** through the fourth contact hole CH4, and the second pad electrode **400b** may be formed to cover a top and a side surface of the first pad electrode **400a**.

[0117] The first anode electrode **180** may be configured with a first lower anode electrode **181** and a first upper anode electrode **182**. The first auxiliary electrode **190** may be configured with a first lower auxiliary electrode **191** and a first upper auxiliary electrode **192**. The second pad electrode **400b** may be configured with a second lower pad electrode **403** and a second upper pad electrode **404**.

[0118] The first anode electrode **180**, the first auxiliary electrode **190**, and the second pad electrode **400b** may be simultaneously formed of the same material through the same patterning process.

[0119] Subsequently, as seen in FIG. 3F, a second anode electrode **200** may be formed on the first anode electrode **180** in the active area AA, a second auxiliary electrode **210** may be formed on the first auxiliary electrode **190** in the active area AA, and a third pad electrode **400c** may be formed on the second pad electrode **400b**.

[0120] The second anode electrode **200** may be pattern-formed to cover a top and a side surface of the first anode electrode **180**, and the second auxiliary electrode **210** may be pattern-formed to cover a top and a side surface of the first auxiliary electrode **190**. The third pad electrode **400c** may be pattern-formed to cover a top and a side surface of the second pad electrode **400b**.

[0121] The second anode electrode **200**, the second auxiliary electrode **210**, and the third pad electrode **400c** may be simultaneously formed of the same material through the same patterning process.

[0122] The second anode electrode **200** may include a second lower anode electrode **201**, a second center anode electrode **202**, and a second upper anode electrode **203**. The second auxiliary electrode **210** may include a second lower auxiliary electrode **211**, a second center auxiliary electrode **212**, and a second upper auxiliary electrode **213**. The third pad electrode **400c** may include a third lower pad electrode **405**, a third center pad electrode **406**, and a third upper pad electrode **407**.

[0123] Subsequently, as seen in FIG. 3G, a process of pattern-forming the second anode electrode **200** and the second auxiliary electrode **210** may include an etching process based on an etchant, and in the etching process, the second upper pad electrode **404** and the third pad electrode **400c** which are disposed in the pad area PA may be etched together. That is, in a process of pattern-forming the second anode electrode **200** and the second auxiliary electrode **210**,

by removing the second upper pad electrode **404** and the third pad electrode **400c**, the pad electrode **400** which includes only the first pad electrode **400a** and the second lower pad electrode **403** may be finished.

[0124] A photoresist pattern may be formed on the third pad electrode **400c**, the planarization layer **170**, the second anode electrode **200**, and the second auxiliary electrode **210** through a half-tone mask process, and by ashing the photoresist pattern, a process of removing the third pad electrode **400c** and the second upper pad electrode **404** and a process of pattern-forming the second anode electrode **200** and the second auxiliary electrode **210** may be simultaneously performed without performing a process illustrated in FIG. 3F. In this case, a photoresist pattern formed on the third pad electrode **400c** and the second upper pad electrode **404** may be thin, and a photoresist pattern formed on the second anode electrode **200** and the second auxiliary electrode **210** may be thick, whereby the third pad electrode **400c** and the second upper pad electrode **404** may be removed and the second anode electrode **200** and the second auxiliary electrode **210** may remain. The process of removing the third pad electrode **400c** and the second upper pad electrode **404** is not limited thereto, and various manufacturing methods may be performed.

[0125] Subsequently, as seen in FIG. 3H, a bank **220** may be formed on each of one side and the other side of the second anode electrode **200** to expose a top of the second anode electrode **200**, and moreover, the bank **220** may be formed on each of one side and the other side of the second auxiliary electrode **210** to expose a top of the second auxiliary electrode **210**.

[0126] Moreover, a first partition wall **231** and a second partition wall **232** may be sequentially formed on the exposed top of the second auxiliary electrode **210**. The first partition wall **231** and the bank **220** may be simultaneously formed of the same material through the same patterning process. The partition wall **230** may be disposed to be spaced apart from the bank **220** by a certain distance, and thus, a separation space may be provided between the partition wall **230** and the bank **220**.

[0127] In order for a top of the partition wall **230** to act as eaves, a width of a top of the second partition wall **232** may be adjusted to greater than that of a bottom of the second partition wall **232**. Particularly, with respect to a case where the organic light emitting display device is seen from the front thereof, the top of the second partition wall **232** may cover the separation space between the partition wall **230** and the bank **220**, and thus, in a process of depositing an organic emission layer **240** to be described below, the organic emission layer **240** cannot be deposited in the separation space between the partition wall **230** and the bank **220**.

[0128] Subsequently, as seen in FIG. 3I, the organic emission layer **240** may be formed on the second anode electrode **200**. The organic emission layer **240** may be formed by a deposition process such as an evaporation process which is excellent in straightness of a deposited material, and thus, the organic emission layer **240** is not deposited in the separation space between the partition wall **230** and the bank **220** although the organic emission layer **240** is deposited on the bank **220** and the top of the partition wall **230**. That is, since the top of the partition wall **230** may act like eaves in depositing the organic emission layer **240**, the organic emission layer **240** cannot be deposited in the separation

space between the partition wall **230** and the bank **220** even when the organic emission layer **240** is deposited without a mask pattern covering the top of the second auxiliary electrode **210**.

[0129] Subsequently, as seen in FIG. 3J, a cathode electrode **250** may be formed on the organic emission layer **240**.

[0130] The cathode electrode **250** may be formed to be connected to the second auxiliary electrode **210** through the separation space between the partition wall **230** and the bank **220**. The cathode electrode **250** may be formed by a deposition process such as a sputtering process which is not good in straightness of a deposited material, and thus, the cathode electrode **250** may be deposited in the separation space between the partition wall **230** and the bank **220** in a process of depositing the cathode electrode **250**.

[0131] As described above, according to the embodiments of the present invention, since the pad electrode is formed to cover the top of the signal pad, the signal pad is prevented from being corroded. Accordingly, the signal pad may be formed in the two-layer structure which includes the lower signal pad and the upper signal pad vulnerable to corrosion.

[0132] Moreover, according to the embodiments of the present invention, the contact hole for externally exposing the source electrode and the area for externally exposing the pad electrode may be simultaneously formed, and thus, one mask process is not additionally performed.

[0133] Moreover, according to the embodiments of the present invention, the two auxiliary electrodes (for example, the first auxiliary electrode and the second auxiliary electrode) may be stacked for lowering a resistance of the cathode electrode, and thus, the desired resistance characteristic of the auxiliary electrode is more easily adjusted.

[0134] It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the inventions. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An organic light emitting display device comprising: a substrate including an active area and a pad area; a thin film transistor (TFT) in the active area of the substrate, the TFT including a gate electrode; an anode electrode on the TFT; an organic emission layer on the anode electrode; a cathode electrode on the organic emission layer; an auxiliary electrode connected to the cathode electrode and disposed on the same layer as the anode electrode; a signal pad in the pad area of the substrate, the signal pad being disposed on the same layer as the gate electrode; and a pad electrode connected to the signal pad to cover a top of the signal pad for preventing the top of the signal pad from being corroded.
2. The organic light emitting display device of claim 1, wherein the pad electrode comprises a lower pad electrode, an upper pad electrode, and a cover pad electrode, and the cover pad electrode is provided to cover a top and a side surface of the upper pad electrode.
3. The organic light emitting display device of claim 2, wherein

an oxidation rate of each of the lower pad electrode and the cover pad electrode is lower than an oxidation rate of the upper pad electrode, and

a resistance of the upper pad electrode is lower than a resistance of each of the lower pad electrode and the cover pad electrode.

4. The organic light emitting display device of claim 2, wherein

the TFT comprises a source electrode, the source electrode including a lower source electrode and an upper source electrode, and

the lower pad electrode comprises a material which is the same as a material of the lower source electrode, and the upper pad electrode comprises a material which is the same as a material of the upper source electrode.

5. The organic light emitting display device of claim 2, wherein

the anode electrode comprises a first anode electrode, the first anode electrode including a first lower anode electrode and a first upper anode electrode, and

the cover pad electrode comprises a material which is the same as a material of the first lower anode electrode.

6. The organic light emitting display device of claim 5, wherein the anode electrode further comprises a second anode electrode provided to cover a top and a side surface of the first anode electrode.

7. The organic light emitting display device of claim 6, wherein

the second anode electrode comprises a second lower anode electrode, a second center anode electrode, and a second upper anode electrode, and

an oxidation rate of each of the second lower anode electrode and the second upper anode electrode is lower than an oxidation rate of the second center anode electrode, and

a resistance of the second center anode electrode is lower than a resistance of each of the second lower anode electrode and the second upper anode electrode.

8. The organic light emitting display device of claim 1, wherein

the signal pad comprises a lower signal pad and an upper signal pad on the lower signal pad,

an oxidation rate of the lower signal pad is lower than an oxidation rate of the upper signal pad, and

a resistance of the upper signal pad is lower than a resistance of the lower signal pad.

9. The organic light emitting display device of claim 1, wherein the auxiliary electrode comprises a first auxiliary electrode and a second auxiliary electrode provided to cover a top and a side surface of the first auxiliary electrode.

10. The organic light emitting display device of claim 9, further comprising:

a bank on each of one side and the other side of the second auxiliary electrode; and

a partition wall on the second auxiliary electrode, the partition wall being spaced apart from the bank, wherein the cathode electrode is connected to the second auxiliary electrode through a separation space between the bank and the partition wall.

11. The organic light emitting display device of claim 1, wherein

the TFT comprises a source electrode, the source electrode including a lower source electrode and an upper source electrode, and

- a thickness of the upper source electrode is thicker than that of the lower source electrode.
- 12.** The organic light emitting display device of claim **1**, wherein
- the anode electrode comprises a first anode electrode, the first anode electrode including a first lower anode electrode and a first upper anode electrode, and a thickness of the first upper anode electrode is thicker than that of the first lower anode electrode
- 13.** The organic light emitting display device of claim **9**, wherein
- a thickness of the first upper auxiliary electrode is thicker than that of the first lower auxiliary electrode.
- 14.** The organic light emitting display device of claim **7**, wherein
- a thickness of the second center anode electrode is thicker than that of each of the second lower anode electrode and the second upper anode electrode.
- 15.** The organic light emitting display device of claim **9**, wherein
- the second auxiliary electrode includes a second lower auxiliary electrode, a second center auxiliary electrode, and a second upper auxiliary electrode.
- 16.** The organic light emitting display device of claim **6**, further comprising:
- a bank on each of one side and the other side of the second anode electrode.
- 17.** The organic light emitting display device of claim **10**, wherein
- a width of a top of the partition wall is greater than that of a bottom of the partition wall.
- 18.** The organic light emitting display device of claim **1**, further comprising:
- an interlayer dielectric on the signal pad.
- 19.** The organic light emitting display device of claim **18**, wherein
- the interlayer dielectric is formed to expose a top of the signal pad and cover a side surface of the signal pad.
- 20.** The organic light emitting display device of claim **1**, wherein
- the pad electrode comprises a lower pad electrode, an upper pad electrode, and a cover pad electrode, and a thickness of the upper pad electrode is thicker than that of each of the lower pad electrode and the cover pad electrode.
- 21.** A method of manufacturing an organic light emitting display device, the method comprising:
- forming a thin film transistor (TFT) in an active area of a substrate and forming a signal pad and a first pad electrode, connected to the signal pad, in a pad area of the substrate;
- forming a passivation layer on the TFT and the first pad electrode;
- forming a planarization layer on the passivation layer;
- removing a certain region of the passivation layer to simultaneously form an area, through which the TFT is exposed to the outside, and an area through which the first pad electrode is exposed to the outside;
- forming a first anode electrode connected to the TFT, a first auxiliary electrode spaced apart from the first anode electrode, and a second pad electrode that is connected to the first pad electrode and covers the exposed first pad electrode; and
- forming a second anode electrode, covering a top and a side surface of the first anode electrode, and a second auxiliary electrode covering a top and a side surface of the first auxiliary electrode.
- 22.** The method of claim **21**, wherein
- the TFT comprises a gate electrode and a source electrode, the signal pad is formed simultaneously with the gate electrode, and
- the first pad electrode is formed simultaneously with the source electrode.
- 23.** The method of claim **21**, wherein the forming of the second pad electrode comprises simultaneously removing elements disposed on the second pad electrode by using an etchant in a process of forming the second anode electrode and the second auxiliary electrode.
- 24.** The method of claim **21**, further comprising:
- forming a bank on each of one side and the other side of the second auxiliary electrode and forming a partition wall on a top of the second auxiliary electrode;
- forming an organic emission layer on the second anode electrode not to be deposited in a separation space between the bank and the partition wall; and
- forming a cathode electrode connected to the second auxiliary electrode to be deposited in the separation space between the bank and the partition wall.
- * * * * *

专利名称(译)	有机发光显示装置及其制造方法		
公开(公告)号	US20160351651A1	公开(公告)日	2016-12-01
申请号	US15/167456	申请日	2016-05-27
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	JANG JIN HEE KIM SE JUNE LEE JOON SUK LEE SO JUNG IM JONG HYEOK LEE JAE SUNG		
发明人	JANG, JIN-HEE KIM, SE JUNE LEE, JOON SUK LEE, SO JUNG IM, JONG HYEOK LEE, JAE SUNG		
IPC分类号	H01L27/32 H01L51/52		
CPC分类号	H01L27/3276 H01L51/5228 H01L51/5215 H01L27/3244 H01L2227/323 H01L2224/05073 H01L2224/05166 H01L2224/0518 H01L2224/05647 H01L2924/0132 H01L2251/301 H01L27/3248 H01L51/56 H01L27/3246 H01L51/5218		
优先权	1020150076674 2015-05-29 KR		
其他公开文献	US10109700		
外部链接	Espacenet USPTO		

摘要(译)

讨论了有机发光显示装置及其制造方法。根据实施例的有机发光显示装置包括：基板，包括有源区和焊盘区；基板的有源区中的薄膜晶体管（TFT），TFT上的阳极，有机发光层。阳极电极，有机发光层上的阴极电极，连接到阴极电极并与阳极电极设置在同一层上的辅助电极，基板焊盘区域中的信号焊盘，以及连接到信号的焊盘电极垫覆盖信号垫的顶部，以防止信号垫的顶部被腐蚀。TFT包括栅电极。信号焊盘设置在与栅电极相同的层上。

