



US009620613B2

(12) **United States Patent**  
**Park et al.**

(10) **Patent No.:** **US 9,620,613 B2**  
(45) **Date of Patent:** **Apr. 11, 2017**

(54) **ORGANIC LIGHT EMITTING DISPLAY DEVICES AND METHODS OF MANUFACTURING ORGANIC LIGHT EMITTING DISPLAY DEVICES**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin, Gyeonggi-Do (KR)

(72) Inventors: **Sang-Ho Park**, Suwon-si (KR);  
**Jae-Hyuk Jang**, Seongnam-si (KR);  
**Chang-Ok Kim**, Yongin-si (KR);  
**Joo-Sun Yoon**, Seoul (KR); **Yong-Jae Jang**, Seoul (KR)

(73) Assignee: **Samsung Display Co., Ltd.** (KR)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/721,952**

(22) Filed: **May 26, 2015**

(65) **Prior Publication Data**

US 2016/0020266 A1 Jan. 21, 2016

(30) **Foreign Application Priority Data**

Jul. 18, 2014 (KR) ..... 10-2014-0090714

(51) **Int. Cl.**  
**H01L 27/32** (2006.01)  
**H01L 21/02** (2006.01)  
**H01L 27/12** (2006.01)  
**H01L 29/49** (2006.01)  
**H01L 29/51** (2006.01)

(Continued)

(52) **U.S. Cl.**  
CPC ..... **H01L 29/518** (2013.01); **H01L 27/1259** (2013.01); **H01L 27/326** (2013.01); **H01L 27/3262** (2013.01); **H01L 27/3265** (2013.01); **H01L 29/4908** (2013.01); **H01L 27/3258** (2013.01)

(58) **Field of Classification Search**

CPC ..... H01L 27/326; H01L 27/3262; H01L 27/1214; H01L 29/4908; H01L 27/3265; H01L 27/1255; H01L 27/1259; H01L 27/3258; H01L 29/518

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,928,732 A \* 7/1999 Law ..... C23C 16/308  
257/E21.268  
7,435,992 B2 \* 10/2008 Choi ..... G09G 3/3233  
257/72

(Continued)

FOREIGN PATENT DOCUMENTS

KR 1020120002759 A 1/2012  
KR 1020120129592 A 11/2012  
KR 1020140039840 A 4/2014

*Primary Examiner* — Khiem D Nguyen


*Assistant Examiner* — Pauline Vu

(74) *Attorney, Agent, or Firm* — Innovation Counsel LLP

(57) **ABSTRACT**

An organic light emitting display device includes a substrate, a first transistor disposed on the substrate in the opaque region, a second transistor disposed on the substrate in the opaque region, the second transistor being adjacent to the first transistor along a first direction, and a capacitor disposed on the substrate in the opaque region, the capacitor being adjacent to the first transistor along a second direction different from the first direction. Here, the capacitor may include a first capacitor electrode, a dielectric structure including silicon oxynitride and a second capacitor electrode.

**15 Claims, 10 Drawing Sheets**



# US 9,620,613 B2

Page 2

(51) **Int. Cl.**  
**H01L 49/02** (2006.01)  
**H01L 51/56** (2006.01)

## (56) **References Cited**

### U.S. PATENT DOCUMENTS

2002/0102776 A1\* 8/2002 Yamazaki ..... H01L 27/12  
438/149  
2003/0082889 A1\* 5/2003 Maruyama ..... H01L 27/1214  
438/455  
2003/0111666 A1\* 6/2003 Nishi ..... H01L 51/0051  
257/79  
2003/0111954 A1\* 6/2003 Koo ..... H01L 27/3276  
313/498  
2003/0117059 A1\* 6/2003 Koo ..... H01L 27/3265  
313/422  
2003/0117352 A1\* 6/2003 Kimura ..... G09G 3/3233  
345/87  
2003/0127652 A1\* 7/2003 Park ..... H01L 27/3244  
257/72  
2003/0193284 A1\* 10/2003 Park ..... H01L 27/3244  
313/504  
2004/0012028 A1\* 1/2004 Park ..... H01L 27/3244  
257/88  
2004/0090173 A1\* 5/2004 Park ..... H01L 27/3253  
313/500  
2005/0029593 A1\* 2/2005 Kudo ..... H01L 29/66757  
257/347  
2005/0099369 A1\* 5/2005 Lee ..... H01L 27/3279  
345/76  
2005/0212447 A1\* 9/2005 Oh ..... H01L 27/3246  
315/169.3  
2006/0091399 A1\* 5/2006 Lee ..... H01L 27/12  
257/72  
2007/0024181 A1\* 2/2007 Oh ..... H01L 27/3258  
313/500  
2007/0138478 A1\* 6/2007 Son ..... H01L 27/3276  
257/72  
2007/0159077 A1\* 7/2007 Kim ..... H01L 27/3265  
313/504  
2008/0067932 A1\* 3/2008 Baek ..... H01L 27/3223  
313/509

2009/0047774 A1\* 2/2009 Yamazaki ..... C23C 16/509  
438/479  
2011/0084281 A1\* 4/2011 Koyama ..... G09G 3/3241  
257/59  
2011/0108844 A1\* 5/2011 Kwak ..... G09G 3/3233  
257/71  
2011/0108848 A1\* 5/2011 Lee ..... H01L 27/3262  
257/72  
2011/0147770 A1\* 6/2011 Hwang ..... H01L 27/326  
257/89  
2011/0163664 A1\* 7/2011 Kang ..... H01L 27/3232  
313/504  
2011/0204369 A1\* 8/2011 Ha ..... H01L 51/5228  
257/59  
2011/0241014 A1\* 10/2011 Yoon ..... H01L 27/3276  
257/72  
2011/0303922 A1\* 12/2011 Cho ..... H01L 27/1248  
257/71  
2012/0001191 A1\* 1/2012 Ma ..... G02F 1/136213  
257/71  
2012/0153286 A1\* 6/2012 Yoon ..... B82Y 10/00  
257/59  
2012/0267611 A1\* 10/2012 Chung ..... H01L 27/3211  
257/40  
2012/0292612 A1\* 11/2012 Jeong ..... H01L 27/1225  
257/43  
2012/0326151 A1\* 12/2012 Zhan ..... H01L 27/1255  
257/59  
2013/0175514 A1\* 7/2013 Han ..... H01L 27/3213  
257/40  
2013/0187131 A1\* 7/2013 Chung ..... H01L 27/326  
257/40  
2013/0328022 A1 12/2013 Choi et al.  
2014/0084264 A1\* 3/2014 Lee ..... H01L 27/124  
257/40  
2014/0117323 A1\* 5/2014 Ahn ..... H01L 27/1288  
257/40  
2014/0175396 A1\* 6/2014 Lee ..... H01L 51/56  
257/40  
2014/0239270 A1\* 8/2014 Ko ..... H01L 27/1255  
257/40

\* cited by examiner



FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6










FIG. 9





FIG. 10



1

# ORGANIC LIGHT EMITTING DISPLAY DEVICES AND METHODS OF MANUFACTURING ORGANIC LIGHT EMITTING DISPLAY DEVICES

## CROSS-REFERENCE TO RELATED APPLICATION(S)

This application claims priority under 35 U.S.C. §119 to Korean patent Application No. 10-2014-0090714, filed on Jul. 18, 2014, the disclosure of which is hereby incorporated by reference herein in its entirety.

## BACKGROUND

### 1. Technical Field

Example embodiments relate to organic light emitting display devices and methods of manufacturing organic light emitting display devices. More particularly, example embodiments relate to organic light emitting display devices including at least one capacitor having a dielectric structure containing silicon oxynitride, and methods of manufacturing the organic light emitting display devices.

### 2. Description of the Related Art

Recently, a transparent organic light emitting display device has been rapidly developed. The transparent organic light emitting display device may include a transparent region and an opaque region. In the transparent organic light emitting display device, an image of an object before or after a transparent region of the organic light emitting display device may be recognized when the organic light emitting display device is in an ON state. In an OFF state of the organic light emitting display device, an image may be displayed in a pixel region of the organic light emitting display device.

In the conventional transparent organic light emitting display device, since transistors and capacitors are positioned in the opaque region, an area of the transparent region may not be sufficiently obtained, and the capacitor may not provide a sufficient capacitance for other elements of the organic light emitting display device.

## SUMMARY

Example embodiments provide an organic light emitting display device including a capacitor having a dielectric structure containing silicon oxynitride.

Example embodiments provide a method of manufacturing an organic light emitting display device including a capacitor having a dielectric structure containing silicon oxynitride.

According to one embodiment, there is provided an organic light emitting display device having an opaque region and a transparent region. The organic light emitting display device may include a substrate, a first transistor disposed on the substrate in the opaque region, a second transistor disposed on the substrate in the opaque region, the second transistor being adjacent to the first transistor along a first direction, and a capacitor disposed on the substrate in the opaque region, the capacitor being adjacent to the first transistor along a second direction different from the first direction. Here, the capacitor may include a first capacitor electrode, a dielectric structure including silicon oxynitride and a second capacitor electrode.

In example embodiments, the first transistor may include a first active pattern disposed on the substrate in the opaque region, a first gate insulation layer disposed on the first

2

active pattern, the first gate insulation layer extending into the transparent region, a second gate insulation layer including silicon oxynitride disposed on the first gate insulation layer, the second gate insulation layer extending into the transparent region, a first gate electrode disposed on the second gate insulation layer, a first source electrode contacting the first active pattern, the first source electrode extending along the second direction, and a first drain electrode contacting the first active pattern.

In example embodiments, a dielectric constant of the second gate insulation layer and a refractive index of the second gate insulation layer may be controlled in accordance with a nitrogen content of the second gate insulation layer.

In example embodiments, the first capacitor electrode may be disposed over the first gate insulation layer.

In example embodiments, the dielectric structure may include a portion of the second gate insulation layer.

In example embodiments, the second capacitor electrode may be disposed on the second gate insulation layer, and may be spaced apart from the first gate electrode along the second direction.

In example embodiments, the second capacitor electrode may contact an extended portion of the first source electrode.

In example embodiments, the second transistor may include a second active pattern disposed on the substrate in the opaque region, the first gate insulation layer being disposed on the second active pattern, a second gate electrode disposed on the first gate insulation layer, the second gate insulation layer being disposed on the second gate electrode, and a second source electrode and a second drain electrode contacting the second active pattern.

In example embodiments, the first capacitor electrode may be disposed on the first gate insulation layer, and is spaced apart from the second gate electrode along the second direction.

In example embodiments, the organic light emitting display device may additionally include an insulating interlayer covering the first gate electrode, the insulating interlayer including silicon oxide and a data line disposed on the insulating interlayer, the data line being spaced apart from the first source electrode along the second direction.

In example embodiments, the organic light emitting display device may additionally include an additional capacitor disposed on the capacitor.

In example embodiments, the additional capacitor may additionally include a first additional capacitor electrode positioned at a level same as that of the first gate electrode, an additional dielectric structure disposed on the first additional capacitor electrode, the additional dielectric structure including a portion of the insulating interlayer, and a second additional capacitor electrode disposed on the additional dielectric structure, the second additional capacitor electrode including a portion of the data line.

In example embodiments, the organic light emitting display device may additionally include an insulation layer disposed on the first transistor, the second transistor and the capacitor, the insulation layer having an opening extending to the transparent region, a first electrode disposed on the insulation layer, an organic light emitting structure disposed on the first electrode, and a second electrode disposed on the organic light emitting structure.

According to another embodiment, there is provided a method of manufacturing an organic light emitting display device having an opaque region and a transparent region. In the method, a first transistor may be formed on a substrate in the opaque region. A second transistor may be formed on the substrate in the opaque region. Here, the second tran-

3

sistor may be adjacent to the first transistor along a first direction. A capacitor may be formed on the substrate in the opaque region. Here, the capacitor may be adjacent to the first transistor along a second direction different from the first direction. For example, the capacitor may include a first capacitor electrode, a dielectric structure including silicon oxynitride and a second capacitor electrode.

In the formation of the first transistor according to example embodiments, a first active pattern may be formed on the substrate in the opaque region. A first gate insulation layer covering the first active pattern and extending into the transparent region may be formed. A second gate insulation layer including silicon oxynitride may be formed on the first gate insulation layer. Here, the second gate insulation layer may extend into the transparent region. A first gate electrode may be formed on the second gate insulation layer. A first source electrode contacting the first active pattern and extending along the second direction may be formed. A first drain electrode contacting the first active pattern may be formed. For example, the second gate insulation layer and the dielectric structure may be simultaneously formed, and the first gate electrode and the second capacitor electrode may be simultaneously formed.

In the formation of the second transistor according to example embodiments, a second active pattern may be formed on the substrate in the opaque region. The first gate insulation layer covering the second active pattern may be formed. A second gate electrode may be formed on the first gate insulation layer. The second gate insulation layer covering the second gate electrode may be formed. A second source electrode contacting the second active pattern may be formed. A second drain electrode contacting the second active pattern may be formed. For example, the second gate electrode and the first capacitor electrode may be simultaneously formed.

In the formation of the organic light emitting display device according to example embodiments, an insulating interlayer covering the first gate electrode may be additionally formed using silicon oxide. A data line may be additionally formed on the insulating interlayer. Here, the data line may be spaced apart from the first source electrode along the second direction.

In the formation of the organic light emitting display device according to example embodiments, an additional capacitor including a first additional capacitor electrode located at a level same as that of the first gate electrode, an additional dielectric structure disposed on the first additional capacitor electrode, the additional dielectric structure including a portion of the insulating interlayer, and a second additional capacitor electrode disposed on the additional dielectric structure, the second additional capacitor electrode including a portion of the data line may be additionally formed.

In example embodiments, the first transistor, the second transistor and the capacitor may be simultaneously formed.

In the formation of the organic light emitting display device according to example embodiments, an insulation layer may be additionally formed on the first transistor, the second transistor and the capacitor, the insulation layer having an opening extending to the transparent region. A first electrode may be additionally formed on the insulation layer. An organic light emitting structure may be additionally formed on the first electrode. A second electrode may be additionally formed on the organic light emitting structure.

According to example embodiments, the organic light emitting display device may include the substrate, the first transistor, the second transistor, the at least one capacitor,

4

etc. The dielectric structure of the capacitor may include silicon oxynitride. Here, the dielectric constant and the refractive index of the dielectric structure may be adjusted in accordance with the nitrogen content therein, so that the capacitor may provide a sufficient capacitance for elements of the organic light emitting display device. In addition, when the dielectric structure extends from the opaque region to the transparent region, the transmittance of the transparent region may not be substantially reduced because a difference of refractive indices of adjacent layers may be minimized. Furthermore, the additional capacitor may be provided over the capacitor. In other words, the organic light emitting display device may have the configuration in which a plurality of capacitors is substantially vertically stacked. Thus, an area for the capacitors may be substantially reduced compared to the configuration in which the capacitors are disposed in parallel. As a result, the organic light emitting display device may ensure a more sufficient capacitance while increasing an area of the transparent region.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Illustrative, non-limiting example embodiments will be more clearly understood from the following detailed description taken in conjunction containing the accompanying drawings.

FIG. 1 is a cross sectional view illustrating an organic light emitting display device in accordance with example embodiments.

FIG. 2 is a cross-sectional view illustrating an organic light emitting display device in accordance with some example embodiments.

FIGS. 3, 4, 5, 6, 7, 8, 9 and 10 are cross sectional views illustrating a method of manufacturing an organic light emitting display device in accordance with example embodiments.

#### DETAILED DESCRIPTION OF THE EMBODIMENTS

Hereinafter, organic light emitting display devices and methods of manufacturing organic light emitting display devices in accordance with example embodiments will be explained in detail with reference to the accompanying drawings.

FIG. 1 is a cross sectional view illustrating an organic light emitting display device **100** in accordance with example embodiments.

Referring to FIG. 1, the organic light emitting display device **100** may include a substrate **102**, a first transistor **TR1**, a second transistor **TR2**, a capacitor **CAP**, an organic light emitting structure **140**, etc. The organic light emitting display device **100** may include an opaque region I and a transparent region II. While the organic light emitting display device **100** is in an ON state, an image may be displayed in the opaque region I. Further, while the organic light emitting display device **100** is in an OFF state, an image of an object positioned before and/or after the transparent region II of the organic light emitting display device **100** may be recognized by a user.

As illustrated in FIG. 1, the first transistor **TR1**, the second transistor **TR2**, the capacitor **CAP** and the organic light emitting structure **140** may be disposed in the opaque region I of the substrate **102**. The second transistor **TR2** may be located adjacent to the first transistor **TR1** along a first direction. The capacitor **CAP** may be disposed adjacent to the first transistor **TR1** along a second direction different

from the first direction. For example, the second direction may be perpendicular to the first direction.

The substrate **102** may include a transparent insulation material. For example, the substrate **102** may include a glass substrate, a quartz substrate, a transparent resin substrate, etc. A buffer layer **104** may be disposed on the substrate **102**. As illustrated in FIG. 1, the buffer layer **104** may extend from the opaque region I into the transparent region II. The buffer layer **104** may prevent the diffusion of metal atoms and/or impurities from the substrate **102**. In addition, the buffer layer **104** may improve the surface flatness of the substrate **102** when the surface of the substrate **102** may be relatively irregular. For example, the buffer layer **104** may include a silicon compound such as silicon oxide. When the buffer layer **104** includes silicon oxide, an incident light from an outside to the transparent region II may pass through the buffer layer **104**. Alternatively, the buffer layer **104** may be omitted in accordance with the material of the substrate **102**, the surface condition of the substrate **102**, etc.

The first transistor TR1 may be disposed on the buffer layer **104** in the opaque region I. As described above, when the buffer layer **104** is not provided on the substrate **102**, the first transistor TR1 may be directly positioned on the substrate **102**. The first transistor TR1 may include a first active pattern **106**, a first gate insulation layer **110**, a second gate insulation layer **116**, a first gate electrode **118**, a first source electrode **124**, and a first drain electrode **126**. For example, the first transistor TR1 may function as a driving transistor of the organic light emitting display device **100**.

The second transistor TR2 may be disposed on the buffer layer **104** and may be adjacent to the first transistor TR1. The second transistor TR2 may include a second active pattern **108**, the first gate insulation layer **110**, a second gate electrode **112**, a second source electrode **128**, and a second drain electrode **130**. For example, the second transistor TR2 may serve as a switching transistor of the organic light emitting display device **100**.

The first and the second active patterns **106** and **108** may be positioned on the buffer layer **104** on the opaque region I. The second active pattern **108** may be spaced apart from the first active pattern **106** along the first direction. Each of the first and the second active patterns **106** and **108** may include a material containing silicon or oxide semiconductor.

The first gate insulation layer **110** may cover the first and the second active patterns **106** and **108**, and also may extend into the transparent region II. For example, the first gate insulation layer **110** may include a silicon compound, a metal oxide, etc. In example embodiments, the first gate insulation layer **110** may include silicon oxide. In some example embodiments, the first gate insulation layer **110** may include a material substantially the same as that of the buffer layer **104**. In this case, the first gate insulation layer **110** may have a transmittance substantially the same as that of the buffer layer **104** in the transparent region II.

The second gate electrode **112** may be disposed on the first gate insulation layer **110** so that the second gate electrode **112** may be partially overlapped with the second active pattern **108**. The second gate electrode **112** may metal, alloy, metal nitride, conductive metal oxide, transparent conductive material, etc. These may be used alone or in a combination thereof.

In example embodiments, a first capacitor electrode **114** may be separated from the second gate electrode **112** on the first gate insulation layer **110** along the second direction by a predetermined distance. The first capacitor electrode **114** may include a material substantially the same as that of the

second gate electrode **112**. Alternatively, the first capacitor electrode **114** may include a material different from that of the second gate electrode **112**.

The second gate insulation layer **116** may cover the second gate electrode **112** and the first capacitor electrode **114**, and also may extend into the transparent region II. In example embodiments, the second gate insulation layer **116** may include silicon oxynitride, so that a dielectric constant of the second gate insulation layer **116** and a refractive index of the second gate insulation layer **116** may be controlled in accordance with a nitrogen content of silicon oxynitride included in second gate insulation layer **116**. For example, the nitrogen content of silicon oxynitride in second gate insulation layer **116** may be less than about 25%. The second gate insulation layer **116** may have the dielectric constant less than about 5 and the refractive index less than about 1.7. Additionally, the second gate insulation layer **116** including silicon oxynitride may have a thickness substantially larger than that of the first gate insulation layer **110** including silicon oxide by about 1.2 times. Thus, when the second gate insulation layer **116** includes silicon oxynitride, the capacitor CAP may have a sufficient capacitance without substantially reducing a transmittance of the organic light emitting display device **100** even though the second gate insulation layer **116** is located in the transparent region II.

In example embodiments, threshold voltages of the first and the second transistors TR1 and TR2 may decrease, so that the first and the second transistors TR1 and TR2 may have improved electrical characteristics when the second gate insulation layer **116** includes silicon oxynitride. In addition, when a portion of the second gate insulation layer **116** functions as the dielectric structure of the capacitor CAP, the capacitance of the capacitor CAP may be sufficiently ensured because the capacitance of the second gate insulation layer **116** may be proportional to the dielectric constant of the second gate insulation layer **116**. Further, the transmittance of the organic light emitting display device **100** may not decrease even though the second gate insulation layer **116** extends into the transparent region II because the difference between the adjacent layers may be minimized.

The first gate electrode **118** may be disposed on a portion of the first gate insulation layer **110** and the second gate insulation layer **116** under which the first active pattern **106** is located. The first gate electrode **118** may include a material substantially the same as a material of the second gate electrode **112** and a material of the first capacitor electrode **114**. In some example embodiments, the first gate electrode **118**, the second gate electrode **112**, and the first capacitor electrode **114** may include different materials, respectively.

A second capacitor electrode **120** may be separated from the first gate electrode **118** on the second gate insulation layer **116** along the second direction by a predetermined distance. The second capacitor electrode **120** may extend into a portion of the transparent region II along the second direction. Thus, an additional capacitor (i.e., a second capacitor CAP2; see FIG. 2) may include the second capacitor electrode **120**, an insulating interlayer **122** and the second drain electrode **130**. The additional capacitor will be described below. The second capacitor electrode **120** may include a material substantially the same as that of the first gate electrode **118**. Alternatively, the second capacitor electrode **120** may include a material different from that of the first gate electrode **118**.

The insulating interlayer **122** may cover the first gate electrode **118** and the second capacitor electrode **120**, and

also may extend into the transparent region II. The insulating interlayer 122 may electrically insulate the first gate electrode 118 from the first source and drain electrodes 124 and 126. Additionally, the insulating interlayer 122 may electrically insulate the second gate electrode 112 from the second source and drain electrodes 128 and 130. In example embodiments, the organic light emitting display device 100 including the insulating interlayer 122 may have an improved transmittance compared with that of the conventional organic light emitting display device including an insulating interlayer of silicon nitride. In addition, the insulating interlayer 122 may include a material substantially the same as a material of the buffer layer 104 and a material of the first gate insulation layer 110, so that the insulating interlayer 122, the buffer layer 104 and the first gate insulation layer 110 may have substantially the same transmittance. As a result, an external light may efficiently pass through the insulating interlayer 122, the buffer layer 104 and the first gate insulation layer 110 in the transparent region II. Further, the insulating interlayer 122 may have a thickness substantially larger than that of the second gate insulation layer 116. For example, the insulating interlayer 122 may have an increased thickness substantially larger than those of other insulation layers (i.e., the buffer layer 104 and the first gate insulation layer 110) including silicon oxide by about 1.6 times. Therefore, a coupling effect generated between the first gate electrode 118 and the first source electrode 124, and a coupling effect generated between the first gate electrode 118 and the first drain electrode 126 may be reduced. Additionally, a coupling effect generated between the first source electrode 124 and the first drain electrode 126 may also be decreased.

When a portion of the insulating interlayer 122 belongs to an additional dielectric structure of the additional capacitor (i.e., the second capacitor CAP2), the organic light emitting display device 100 may have an increased capacitance substantially larger than the conventional organic light emitting display device including a capacitor. The capacitance of the capacitor CAP2 as described below may be sufficiently ensured compared with that of the conventional capacitor including the dielectric structure of silicon nitride because the insulating interlayer 122 may have a thickness substantially larger than the second gate insulation layer 116. Some example embodiments in which the dielectric structure of the second capacitor CAP2 includes the portion of the insulating interlayer 122 will be described below.

The first source electrode 124 and the first drain electrode 126 may be disposed on the insulating interlayer 122. The first source electrode 124 and the first drain electrode 126 may pass through a portion of the insulating interlayer 122, a portion of the second gate insulation layer 116, and a portion of the first gate insulating layer 110. Then, the first source electrode 124 and the first drain electrode 126 may contact the first active pattern 106. In example embodiments, since the first source electrode 124 may extend into the transparent region II, an extended portion of the first source electrode 124 in the transparent region II may pass through the insulating interlayer 122 to make contact with the second capacitor electrode 120. The first source electrode 124 and the first drain electrode 126 may include metal, alloy, metal nitride, conductive metal oxide, transparent conductive material, etc. These may be used alone or in a combination thereof.

The second source electrode 128 and the second drain electrode 130 may be disposed on the insulating interlayer 122. The second source electrode 128 and the second drain electrode 130 may pass through a portion of the insulating

interlayer 122, a portion of the second gate insulation layer 116, and a portion of the first gate insulating layer 110. Then, the second source electrode 128 and the second drain electrode 130 may contact the second active pattern 108. The second source electrode 128 may include a material substantially the same as that of the first source electrode 124. Additionally, the second drain electrode 130 may include a material substantially the same as that of the first drain electrode 126.

An insulation layer 134 may be positioned on the insulating interlayer 122 to cover the first source electrode 124, the second source electrode 128, the first drain electrode 126, and the second drain electrode 130. In example embodiments, the insulation layer 134 may have an opening 135b extending to and exposing a portion of the transparent region II. Further, the opening 135b may extend to and expose an extended portion of the insulating interlayer 122 in the transparent region II. As illustrated in FIG. 1, the insulation layer 134 may additionally have a contact hole 135a partially exposing the extended portion of the first source electrode 124 in the transparent region II. For example, the insulation layer 134 may include an organic material or an inorganic material.

A first electrode 136 may be disposed on the insulation layer 134 to make contact with the extended portion of the first source electrode 124 in the transparent region II through the contact hole 135a. The first electrode 136 may include metal, alloy, metal nitride, conductive metal oxide.

A pixel defining layer 138 may be located on the first electrode 136. The pixel defining layer 138 may have an opening partially exposing the first electrode 136. For example, the pixel defining layer 138 may include an organic material or an inorganic material.

The organic light emitting structure 140 may be disposed on the exposed first electrode 136 through the opening of the pixel defining layer 138. The organic light emitting structure 140 may include a light emitting material for generating a red color of light, a green color of light or a blue color of light. Alternatively, the organic light emitting structure 140 may include a plurality of materials for generating a red color of light, a green color of light and/or a blue color of light, thereby finally emitting a white color of light.

A second electrode 142 may be disposed on the pixel defining layer 138 and the organic light emitting structure 140. The second electrode 142 may extend into the transparent region II to make contact with the portion of the insulating interlayer 122 through the opening 135b of the insulation layer 134. The second electrode 142 may include a transparent conductive material. For example, the second electrode 142 may include indium tin oxide, indium zinc oxide, zinc oxide, tin oxide, gallium oxide, indium oxide, etc. Thus, the transmittance of the transparent region II may not be reduced even though the second electrode 142 is positioned in the transparent region II. Alternatively, the second electrode 142 may include a material substantially the same as that of the first electrode 136.

As for the conventional organic light emitting display device, all of the transistors and the capacitors are located on the substrate in the opaque region, so that the transparent region may not have a sufficient area. Thus, the capacitor of the conventional organic light emitting display device may not have a sufficient capacitance. The organic light emitting display device according to example embodiments may include the opaque region I in which the first transistor TR1, the second transistor TR2 and at least one capacitor CAP may be located. The capacitor CAP may include the first capacitor electrode 114, the dielectric structure including



silicon oxynitride (i.e., the portion of the second gate insulation layer **116**), and the second capacitor electrode **120**. Here, the threshold voltages of the first and the second transistors **TR1** and **TR2** may decrease to thereby improve the distribution of electrical characteristics of the first and the second transistors **TR1** and **TR2** when the second gate insulation layer **116** includes silicon oxynitride. Further, when the portion of the second gate insulation layer **116** serves as the dielectric structure of the capacitor **CAP**, the capacitance of the capacitor **CAP** may be sufficiently ensured because the capacitance of the capacitor **CAP** may be substantially proportional to the dielectric constant of the second gate insulation layer **116**. Moreover, the transmittance of the organic light emitting display device **100** may not be reduced even though the second gate insulation layer **116** extends into the transparent region II because the difference of refractive indices of adjacent layers in the transparent region II may be minimized.

FIG. 2 is a cross-sectional view illustrating an organic light emitting display device in accordance with some example embodiments. The organic light emitting display device **200** illustrated in FIG. 2 may have a configuration substantially the same as or similar to the organic light emitting display device **100** described with reference to FIG. 1 except a second additional capacitor **CAP2**. More particularly, the elements **202**, **204**, **206**, **208**, **210**, **212**, **214**, **216**, **218**, **222**, **224**, **226**, **228**, **230**, **232**, **234**, **236**, **238**, **240**, **242**, **235a**, **235b** of the organic light emitting display device **200** illustrated in FIG. 2 may be the same as or similar to the elements **102**, **104**, **106**, **108**, **110**, **112**, **114**, **116**, **118**, **122**, **124**, **126**, **128**, **130**, **132**, **134**, **136**, **138**, **140**, **142**, **135a**, **135b** of the organic light emitting display device **100** illustrated in FIG. 1, respectively.

Referring to FIG. 2, the second additional capacitor **CAP2** may include a first additional capacitor electrode **220**, an additional dielectric structure, and a second additional capacitor electrode. Here, the second additional capacitor electrode may include a portion of a data line **232**.

The first additional capacitor electrode **220** may be located on the second gate insulation layer **216**, and may extend into a portion of the transparent region II along the second direction. Thus, the second additional capacitor **CAP2** may include the first additional capacitor electrode **220**, portions of the insulating interlayer **222**, and the portion of the data line **232**. In other words, the first additional capacitor electrode **220** may serve as a lower electrode of the additional capacitor **CAP2**, and also, as illustrated in FIG. 2, the first additional capacitor electrode **220** may serve as the upper electrode of the capacitor **CAP1**. Therefore, the organic light emitting display device **200** may have the configuration in which the capacitor **CAP1** and the additional capacitor **CAP2** may be substantially vertically stacked. Here, the capacitor **CAP1** and the additional capacitor **CAP2** may share the first capacitor electrode **220**. Thus, the capacitors **CAP1** and **CAP2** may occupy a substantially small area in comparison with the configuration in which the capacitors are disposed in parallel. As a result, the transparent region II of the organic light emitting display device **200** may have a substantially increased area.

As described above, the portion of the insulating interlayer **222** including silicon oxide may serve as the additional dielectric structure of the additional capacitor **CAP2**. For example, the insulating interlayer **222** according to example embodiments may have an increased thickness substantially larger than those of other insulation layers including silicon oxide by about 1.6 times. Accordingly when the additional dielectric structure of the additional capacitor includes the

portion of the insulating interlayer **122**, the organic light emitting display device **200** may have a more increased capacitance compared to the organic light emitting display device that includes one capacitor only. In addition, the insulating interlayer **222** may include a material substantially the same as that of the buffer layer **204** and that of the first gate insulation layer **210**, so that the insulating interlayer **222**, the buffer layer **204** and the first gate insulation layer **210** may have substantially the same transmittance. Therefore, an external light may efficiently pass through the insulating interlayer **222**, the buffer layer **204** and the first gate insulation layer **210** in the transparent region II.

As described above, the insulating interlayer **222** including silicon oxide may have an increased thickness substantially larger than that of other insulating interlayers including silicon oxide by about 1.6 times. Thus, increased thickness of the insulating interlayer **222** may prevent electrostatic discharges generated among the first gate electrode **218**, the first source electrode **224** and the first drain electrode **226**, and among the first source electrode **224** and the first drain electrode **226**. Therefore, the organic light emitting display device **200** may have an improved reliability. As a result, when the portion of the insulating interlayer **222** may serve as the additional dielectric structure of the additional capacitor **CAP2**, the organic light emitting display device **200** may provide a more sufficient capacitance without substantially reducing the transmittance of the organic light emitting display device **200** even through the insulating interlayer **222** extends into the transparent region II.

FIGS. 3 to 10 are cross sectional views illustrating a method of manufacturing an organic light emitting display device in accordance with example embodiments. The method illustrated in FIGS. 3 to 10 may provide an organic light emitting display device having a configuration substantially the same as or similar to that of the organic light emitting display device **100** described with reference to FIG. 1, however, the organic light emitting display device **100** or **200** illustrated in FIG. 1 or FIG. 2 may be manufactured by obviously modifying some processes such as a deposition process, an etching process, etc.

Referring to FIG. 3, a buffer layer **104** may be formed on a substrate **102**. The substrate **102** may be formed using a transparent insulation material. The buffer layer **104** may be formed using silicon oxide, so that a transmittance of a transparent region II may not be reduced even though the buffer layer **104** is formed from an opaque region I into the transparent region II.

A first active pattern **106** and a second active pattern **108** may be formed on the buffer layer **104**. As illustrated in FIG. 3, the first active pattern **106** and the second active pattern **108** may be separated from each other by a predetermined distance in the opaque region I.

Referring to FIG. 4, a first gate insulation layer **110** may be formed on the buffer layer **104** to cover the active pattern **106** and the second active pattern **108**. The first gate insulation layer **110** may extend into the transparent region II. In other words, the first gate insulation layer **110** may be continuously disposed on the buffer layer **104** from the opaque region I to the transparent region II. In example embodiments, the transmittance of the transparent region II may not be reduced even though the first gate insulation layer **110** is disposed into the transparent region II because the first gate insulation layer **110** may be formed using silicon oxide.

A second gate electrode **112** and a first capacitor electrode **114** may be formed on the first gate insulation layer **110**. The second gate electrode **112** and the first capacitor electrode

114 may be positioned in the opaque region I. For example, the second gate electrode 112 may be overlapped over the second active pattern 108 by interposing the first gate insulation layer 110 therebetween. The first capacitor electrode 114 and the second active pattern 108 may be separated from each other by a predetermined distance along a second direction. The second gate electrode 112 may include a material substantially the same as that of the first capacitor electrode 114. For example, each of the second gate electrode 112 and the first capacitor electrode 114 may be formed using metal, alloy, metal nitride, conductive metal oxide, transparent conductive material, etc. In addition, the second gate electrode 112 and the first capacitor electrode 114 may be simultaneously formed by an etching process using one mask. Alternatively, the second gate electrode 112 may include a material different from that of the first capacitor electrode 114.

Referring to FIG. 5, a second gate insulation layer 116 may be formed on the first gate insulation layer 110 to cover the first capacitor electrode 114 and the second gate electrode 112. The second gate insulation layer 116 may be positioned on the first gate insulation layer 110 in the opaque region I and the transparent region II. In example embodiments, the second gate insulation layer 116 may be formed using silicon oxynitride. In this case, a dielectric constant and a refractive index of the second gate insulation layer 116 may be controlled in accordance with a nitrogen content of silicon oxide included in the second gate insulation layer 116, so that the difference of refraction indices of adjacent layers may be minimized even though the second gate insulation layer 116 is formed in the transparent region II. Thus, a capacitance of a capacitor CAP may be sufficiently ensured without substantially reducing a transmittance of the organic light emitting display device 100. Further, the second gate insulation layer 116 may have an increased thickness substantially larger than that of the first gate insulation layer 110 including silicon oxide by about 1.2 times. Accordingly, when a portion of the second gate insulation layer 116 serves as a dielectric structure of the capacitor CAP, the organic light emitting display device 100 may have a sufficient capacitance without substantially decreasing the transmittance of the organic light emitting display device 100.

Referring still to FIG. 5, a first gate electrode 118 may be formed on a portion of the second gate insulation layer 116 under which the first active pattern 106 is located. A second capacitor electrode 120 may be separated from the first gate electrode 118 by a predetermined distance along the second direction. As illustrated in FIG. 5, the first gate electrode 118 and the second capacitor electrode 120 may be positioned in the opaque region I. Each of the first gate electrode 118 and the second capacitor electrode 120 may include metal, alloy, metal nitride, conductive metal oxide, transparent conductive material, etc. In addition, the first gate electrode 118 and the second capacitor electrode 120 may be simultaneously formed by one etching process. As the formation of the second capacitor electrode 120, the capacitor CAP may be provided in the opaque region I. The capacitor CAP may include the first capacitor electrode 114, the dielectric structure including the portion of the second gate insulation layer 116, and the second capacitor electrode 120.

Referring to FIG. 6, an insulating interlayer 122 may be formed on the second gate insulation layer 116 to cover the first gate electrode 118 and the second capacitor electrode 120. The insulating interlayer 122 may extend into the transparent region II to sufficiently cover the first gate electrode 118 and the second capacitor electrode 120. In

example embodiments, the insulating interlayer 122 may be formed using silicon oxide, such that the transmittance of the transparent region II may not be substantially reduced even though the insulating interlayer 122 is positioned in the transparent region II. Further, the insulating interlayer 122 may be formed using silicon oxide, so that the organic light emitting display device 100 may have an increased transmittance larger than that of the conventional organic light emitting display device including the insulating interlayer of silicon nitride. Moreover, the insulating interlayer 122 may have a thickness relatively larger than the second gate insulation layer 116. For example, the insulating interlayer 122 according to example embodiments may have an increased thickness substantially larger than those of other insulation layers of silicon oxide by about 1.6 times. Such insulating interlayer 122 may effectively insulate between a first source electrode 124 and the first gate electrode 118, between a second source electrode 128 and the second gate electrode 112, and between a second drain electrode 130 and the second gate electrode 112. Therefore, the organic light emitting display device 100 may have an enhanced reliability because of the insulating interlayer 122 efficiently insulating the electrodes of the organic light emitting display device 100.

Referring to FIG. 7, the first source electrode 124 and the first drain electrode 126 may be formed on the insulating interlayer 122. The first source electrode 124 and the first drain electrode 126 may contact portions of the first active pattern 106 through contact holes provided through a portion of the insulating interlayer 122 and portions of the first and the second gate insulation layers 110 and 116. Simultaneously, the second source electrode 128 and the second drain electrode 130 may be formed on the insulating interlayer 122. The second source electrode 128 and the second drain electrode 130 may contact portions of the second active pattern 108 through contact holes formed through the insulating interlayer 122 and the first and the second gate insulation layers 110 and 116. In example embodiments, the first source electrode 124 may extend in the opaque region I along the second direction. Thus, the first source electrode 124 may contact the second capacitor electrode 120 through contact holes provided through a portion of the insulating interlayer 122. As illustrated in FIG. 7, a data line 132 may be formed to be spaced apart from the first source electrode 124 by a predetermined distance in the transparent region II. Each of the first and the second source electrodes 124 and 128, the first and the second drain electrodes 126 and 130, and the data line 132 may be formed using metal, alloy, metal nitride, conductive metal oxide, a material having a transmittance, etc.

Referring to FIG. 8, an insulation layer 134 may be formed on the insulating interlayer 122 to cover the first and the second source electrodes 124 and 128, and the first and the second drain electrodes 126 and 130. In example embodiments, the insulation layer 134 may have an opening 135b extending to and partially exposing the insulating interlayer 122 in the transparent region II. Then, a first electrode 136 may be formed on the insulation layer 134. The first electrode 136 may be formed using metal, alloy, metal nitride, conductive metal oxide, transparent conductive material, etc.

Referring to FIG. 9, a pixel defining layer 138 may be formed on the first electrode 136 and the insulation layer 134. The pixel defining layer 138 may include a pixel opening partially exposing the first electrode 136. For example, the pixel defining layer 138 may be formed using an organic material or an inorganic material.

## 13

Referring still to FIG. 9, an organic light emitting structure **140** may be formed on the first electrode **136** exposed by the pixel opening of the pixel defining layer **138**. In example embodiments, the organic light emitting structure **140** may have a multi-layered configuration that includes an organic light emitting layer (EL), a hole injection layer (HIL), a hole transfer layer (HTL), an electron transfer layer (ETL), an electron injection layer (EIL), etc.

Referring to FIG. 10, a second electrode **142** may be formed on the pixel defining layer **138** and the organic light emitting structure **140**. For example, the second electrode **142** may be formed using a material substantially the same as that of the first electrode **136**. Alternatively, the second electrode **142** may be formed using a material different from that of the first electrode **136**.

Example embodiments may be employed in any electronic device including a transparent organic light emitting display device. For example, the transparent organic light emitting display device according to embodiments may be used in a refrigerator for business, a smart window, a transparent tablet, a head-up display device, a wearable display device, etc.

The foregoing is illustrative of example embodiments and is not to be construed as limiting thereof. Although a few example embodiments have been described, those skilled in the art will readily appreciate that many modifications are possible in the example embodiments without materially departing from the novel teachings and advantages of the present inventive concept. Accordingly, all such modifications are intended to be included within the scope of the present inventive concept as defined in the claims. Therefore, it is to be understood that the foregoing is illustrative of various example embodiments and is not to be construed as limited to the specific example embodiments disclosed, and that modifications to the disclosed example embodiments, as well as other example embodiments, are intended to be included within the scope of the appended claims.

What is claimed is:

1. An organic light emitting display device having an opaque region and a transparent region, which comprises:  
 a substrate;  
 a first transistor disposed on the substrate in the opaque region;  
 a second transistor disposed on the substrate in the opaque region, the second transistor being adjacent to the first transistor; and  
 a capacitor disposed on the substrate in the opaque region, the capacitor being adjacent to the first transistor,  
 wherein the capacitor includes a first capacitor electrode, a dielectric structure including silicon oxynitride and a second capacitor electrode,  
 wherein the first transistor comprises:  
 a first active pattern disposed on the substrate in the opaque region;  
 a first gate insulation layer disposed on the first active pattern, the first gate insulation layer extending into the transparent region;  
 a second gate insulation layer including silicon oxynitride disposed on the first gate insulation layer, the second gate insulation layer extending into the transparent region;  
 a first gate electrode disposed on the second gate insulation layer;  
 a first source electrode contacting the first active pattern, the first source electrode extending along a first direction parallel to the substrate; and

## 14

a first drain electrode contacting the first active pattern, wherein the second transistor comprises:

a second active pattern disposed on the substrate in the opaque region;

the first gate insulation layer being disposed on the second active pattern;

a second gate electrode disposed on the first gate insulation layer;

the second gate insulation layer being disposed on the second gate electrode; and

a second source electrode and a second drain electrode contacting the second active pattern.

2. The organic light emitting display device of claim 1, wherein the first capacitor electrode is disposed over the first gate insulation layer.

3. The organic light emitting display device of claim 1, wherein the dielectric structure includes a portion of the second gate insulation layer.

4. The organic light emitting display device of claim 1, wherein the second capacitor electrode is disposed on the second gate insulation layer, and is spaced apart from the first gate electrode along the first direction.

5. The organic light emitting display device of claim 1, wherein the second capacitor electrode contacts an extended portion of the first source electrode.

6. The organic light emitting display device of claim 1, wherein the first capacitor electrode is disposed on the first gate insulation layer, and is spaced apart from the second gate electrode along the first direction.

7. The organic light emitting display device of claim 1, further comprising:

an insulating interlayer covering the first gate electrode, the insulating interlayer including silicon oxide; and

a data line disposed on the insulating interlayer, the data line being spaced apart from the first source electrode along the first direction.

8. The organic light emitting display device of claim 7, further comprising:

an additional capacitor disposed on the capacitor.

9. The organic light emitting display device of claim 8, wherein the additional capacitor comprises:

a first additional capacitor electrode positioned at a level same as that of the first gate electrode;

an additional dielectric structure disposed on the first additional capacitor electrode, the additional dielectric structure including a portion of the insulating interlayer; and

a second additional capacitor electrode disposed on the additional dielectric structure, the second additional capacitor electrode including a portion of the data line.

10. The organic light emitting display device of claim 1, further comprising:

an insulation layer disposed on the first transistor, the second transistor and the capacitor, the insulation layer having an opening extending to the transparent region;

a first electrode disposed on the insulation layer;

an organic light emitting structure disposed on the first electrode; and

a second electrode disposed on the organic light emitting structure.

11. A method of manufacturing an organic light emitting display device including an opaque region and a transparent region, which comprises:

forming a first transistor on a substrate in the opaque region; and

## 15

forming a second transistor on the substrate in the opaque region, the second transistor being adjacent to the first transistor; and  
forming a capacitor on the substrate in the opaque region, the capacitor being adjacent to the first transistor,  
wherein the capacitor includes a first capacitor electrode, 5  
a dielectric structure including silicon oxynitride and a second capacitor electrode, wherein forming the first transistor comprises:  
forming a first active pattern on the substrate in the 10  
opaque region;  
forming a first gate insulation layer covering the first active pattern and extending into the transparent region;  
forming a second gate insulation layer including silicon 15  
oxynitride on the first gate insulation layer, the second gate insulation layer extending into the transparent region;  
forming a first gate electrode on the second gate insulation layer;  
forming a first source electrode contacting the first 20  
active pattern and extending along a first direction parallel to the substrate; and  
forming a first drain electrode contacting the first active 25  
pattern,  
wherein the second gate insulation layer and the dielectric structure are simultaneously formed, and the first gate electrode and the second capacitor electrode are simultaneously formed, wherein forming the second transistor comprises:  
forming a second active pattern on the substrate in the 30  
opaque region;  
forming the first gate insulation layer covering the second active pattern;

## 16

forming a second gate electrode on the first gate insulation layer;  
forming the second gate insulation layer covering the second gate electrode;  
forming a second source electrode contacting the second 5  
active pattern; and  
forming a second drain electrode contacting the second active pattern,  
wherein the second gate electrode and the first capacitor electrode are simultaneously formed.  
12. The method of claim 11, further comprising:  
forming an insulating interlayer covering the first gate 10  
electrode using silicon oxide; and  
forming a data line on the insulating interlayer, the data line being spaced apart from the first source electrode along the first direction.  
13. The method of claim 12, further comprising:  
forming an additional capacitor including a first additional 15  
capacitor electrode located at a level same as that of the first gate electrode, an additional dielectric structure disposed on the first additional capacitor electrode, the additional dielectric structure including a portion of the insulating interlayer, and a second additional capacitor 20  
electrode disposed on the additional dielectric structure, the second additional capacitor electrode including a portion of the data line.  
14. The method of claim 11, wherein the first transistor, the second transistor and the capacitor are simultaneously 25  
formed.  
15. The organic light emitting display device of claim 1, wherein a nitrogen content of the silicon oxynitride in the dielectric structure is less than 25%.

\* \* \* \* \*

|                |                                                                                                              |         |            |
|----------------|--------------------------------------------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | 有机发光显示装置和制造有机发光显示装置的方法                                                                                       |         |            |
| 公开(公告)号        | <a href="#">US9620613</a>                                                                                    | 公开(公告)日 | 2017-04-11 |
| 申请号            | US14/721952                                                                                                  | 申请日     | 2015-05-26 |
| [标]申请(专利权)人(译) | 三星显示有限公司                                                                                                     |         |            |
| 申请(专利权)人(译)    | 三星DISPLAY CO. , LTD.                                                                                         |         |            |
| 当前申请(专利权)人(译)  | 三星DISPLAY CO. , LTD.                                                                                         |         |            |
| [标]发明人         | PARK SANG HO<br>JANG JAE HYUK<br>KIM CHANG OK<br>YOON JOO SUN<br>JANG YONG JAE                               |         |            |
| 发明人            | PARK, SANG-HO<br>JANG, JAE-HYUK<br>KIM, CHANG-OK<br>YOON, JOO-SUN<br>JANG, YONG-JAE                          |         |            |
| IPC分类号         | H01L27/32 H01L21/02 H01L27/12 H01L29/49 H01L29/51 H01L49/02 H01L51/56                                        |         |            |
| CPC分类号         | H01L29/518 H01L27/1259 H01L27/326 H01L27/3262 H01L27/3265 H01L29/4908 H01L27/3258<br>H01L27/1237 H01L27/1255 |         |            |
| 优先权            | 1020140090714 2014-07-18 KR                                                                                  |         |            |
| 其他公开文献         | US20160020266A1                                                                                              |         |            |
| 外部链接           | <a href="#">Espacenet</a> <a href="#">USPTO</a>                                                              |         |            |

#### 摘要(译)

一种有机发光显示装置，包括基板，设置在不透明区域中的基板上的第一晶体管，设置在不透明区域中的基板上的第二晶体管，第二晶体管沿第一方向与第一晶体管相邻，以及电容器设置在不透明区域中的基板上，电容器沿不同于第一方向的第二方向与第一晶体管相邻。这里，电容器可以包括第一电容器电极，包括氮氧化硅的电介质结构和第二电容器电极。

