



US008692459B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 8,692,459 B2**
(45) **Date of Patent:** **Apr. 8, 2014**

(54) **ORGANIC LIGHT-EMITTING DISPLAY APPARATUS AND METHOD OF MANUFACTURING THE ORGANIC LIGHT-EMITTING DISPLAY APPARATUS**

2007/0114523 A1* 5/2007 Oumi et al. 257/40
2009/0128014 A1* 5/2009 Kitazume 313/504
2011/0042694 A1* 2/2011 Oyamada 257/88
2011/0187264 A1* 8/2011 Yasuda et al. 313/504
2012/0080668 A1* 4/2012 Seki 257/40

(75) Inventors: **Dae-Woo Lee**, Yongin (KR); **Soo-Beom Jo**, Yongin (KR); **Jong-Hyun Choi**, Yongin (KR)

FOREIGN PATENT DOCUMENTS

JP 2010238775 A * 10/2010
KR 10-2006-0089214 A 8/2006
KR 10-2007-0063067 A 6/2007
KR 10-2007-0068092 A 6/2007
KR 10-2008-0003314 1/2008

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 72 days.

OTHER PUBLICATIONS

Machine English translation of JP2010238775 to Yasuda et al.*
“Enhanced Fluorescence by surface plasmon coupling of Au nanoparticles in an organic Electroluminescence Diode”, Fujiki et al. Applied Physics Letters, vol. 96, pp. 043307-1-043307-3, 2010.*
Jong-Min Moon et al., Enhancement of Hole Injection Using Ozone Treated Ag Nanodots Dispersed on Indium, etc., Appl. Physics Letters 90, 163516-1, 2007.

* cited by examiner

(21) Appl. No.: **13/306,010**

(22) Filed: **Nov. 29, 2011**

(65) **Prior Publication Data**

US 2013/0009542 A1 Jan. 10, 2013

(30) **Foreign Application Priority Data**

Jul. 4, 2011 (KR) 10-2011-0066122

(51) **Int. Cl.**

H01L 51/50 (2006.01)

G09G 3/10 (2006.01)

(52) **U.S. Cl.**

USPC **313/506**; 313/504; 257/40; 257/89

(58) **Field of Classification Search**

USPC 313/504-512
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS


7,666,247 B2 2/2010 He et al.
7,812,523 B2* 10/2010 Jung et al. 313/506

Primary Examiner — Sikha Roy

(74) Attorney, Agent, or Firm — Lee & Morse, P.C.

(57) **ABSTRACT**

An organic light-emitting display apparatus includes a substrate; a first electrode on the substrate; a particle unit including a plurality of particles that are separate from each other on a top surface of the first electrode; an intermediate layer on the first electrode and the particle unit and including an organic emission layer; and a second electrode on the intermediate layer.



10 Claims, 4 Drawing Sheets

FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E





FIG. 4F



ORGANIC LIGHT-EMITTING DISPLAY APPARATUS AND METHOD OF MANUFACTURING THE ORGANIC LIGHT-EMITTING DISPLAY APPARATUS

CROSS-REFERENCE TO RELATED PATENT APPLICATION

This application claims the benefit of Korean Patent Application No. 10-2011-0066122, filed on Jul. 4, 2011, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

Embodiments relate to an organic light-emitting display apparatus and method of manufacturing the organic light-emitting display apparatus.

2. Description of the Related Art

Recently, display apparatuses are being replaced with portable, thin flat panel display apparatuses. Among the flat panel display apparatuses, organic light-emitting display apparatuses are self-emissive display apparatuses that have wide viewing angles and an excellent contrast ratio, and high response speeds, and thus are regarded as next-generation display apparatuses.

SUMMARY

According to an embodiment, there is provided an organic light-emitting display apparatus, including a substrate, a first electrode on the substrate, a particle unit including a plurality of particles that are separate from each other on a top surface of the first electrode, an intermediate layer on the first electrode and the particle unit, the intermediate layer including an organic emission layer, and a second electrode on the intermediate layer.

A size of the particles of the particle unit may be from about 300 angstroms to about 1000 angstroms.

The particles of the particle unit may include Ag.

The organic light-emitting display apparatus may further include a pixel defining layer (PDL) on the first electrode, the pixel defining layer including an opening that overlaps with the first electrode. The particle unit may further include particles on an inner portion and an outer portion of the opening of the PDL.

The first electrode may include a transmissive conductive material.

The transmissive conductive material may include at least one of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), indium gallium oxide (IGO), and aluminum zinc oxide (AZO).

The second electrode may contact predetermined particles from among the plurality of particles of the particle unit.

The predetermined particles may not correspond to the intermediate layer.

According to an embodiment, there is provided a method of manufacturing an organic light-emitting display apparatus, the method including forming a first electrode on a substrate, forming a particle unit including a plurality of particles that are separate from each other on a top surface of the first electrode, forming an intermediate layer including an organic emission layer on the first electrode and the particle unit, and forming a second electrode on the intermediate layer.

The forming of the particle unit may include forming a conductive layer that includes Ag, and performing a thermal treatment on the conductive layer so as to allow the Ag to agglomerate.

A thickness of the conductive layer may be about 10 angstroms to about 200 angstroms.

The thermal treatment may be performed in a nitrogen atmosphere.

The thermal treatment may be performed at a temperature in a range of about 250 degrees Celsius to about 300 degrees Celsius.

After the forming of the first electrode and before the forming of the particle unit, the method may further include forming a pixel defining layer (PDL) on the first electrode, wherein the PDL includes an opening that overlaps with the first electrode.

The particle unit may be additionally formed on an inner portion and an outer portion of the opening of the PDL.

The forming of the particle unit may include forming a conductive layer including Ag on the first electrode and the PDL, and performing a thermal treatment on the conductive layer so as to allow the Ag to agglomerate.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features and advantages will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings in which:

FIG. 1 is a schematic cross-sectional view illustrating an organic light-emitting display apparatus according to an embodiment;

FIG. 2 is a schematic cross-sectional view illustrating an organic light-emitting display apparatus according to another embodiment;

FIG. 3 is a schematic cross-sectional view illustrating an organic light-emitting display apparatus according to another embodiment; and

FIGS. 4A through 4F are cross-sectional views that sequentially illustrate a method of manufacturing an organic light-emitting display apparatus, according to an embodiment.

DETAILED DESCRIPTION

Hereinafter, the embodiments will be described in detail by explaining exemplary embodiments with reference to the attached drawings.

As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items.

FIG. 1 is a schematic cross-sectional view illustrating an organic light-emitting display apparatus 100 according to an embodiment.

Referring to FIG. 1, the organic light-emitting display apparatus 100 may include a substrate 101, a first electrode 110, a particle unit 120, an intermediate layer 130, and a second electrode 140. The particle unit 120 may include a plurality of particles 121 that are separate from each other.

The substrate 101 may be formed of a transparent glass containing SiO_2 as a main component. The substrate 101 may also be formed of a transparent plastic material that may be at least one insulating organic material selected from polyether-sulfone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylene naphthalate (PEN), polyethylene terephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide, polycarbonate (PC), triacetate cellulose (TAC), and cellulose acetate propionate (CAP).

Also, the substrate **101** may be formed of metal or may have a foil shape.

The first electrode **110** may be disposed on portions of the substrate **101**. The first electrode **110** may be patterned by a photolithography method. Although not illustrated in FIG. **1**, a buffer layer (not shown) may be formed between the substrate **101** and the first electrode **110**. The buffer layer may provide a plane surface on the substrate **101** and may prevent penetration of foreign substances into the substrate **101**. The buffer layer may be formed of SiO₂ and/or SiN_x.

The pattern of the first electrode **110** may be formed as stripe lines that are separate from each other by a predetermined distance. That is, the organic light-emitting display apparatus **100** according to the present embodiment may be a passive matrix (PM) type organic light-emitting display apparatus. An active matrix (AM) type organic light-emitting display apparatus will be described below.

The first electrode **110** may include one of various conductive materials. The first electrode **110** may include a transmissive conductive material. For example, the first electrode **110** may include at least one of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In₂O₃), indium gallium oxide (IGO), and aluminum zinc oxide (AZO).

A pixel defining layer (PDL) **115** may be disposed on the first electrode **110**. The PDL **115** may include an opening **115a**. The opening **115a** may correspond to the first electrode **110**. The PDL **115** may cover a side edge of the first electrode **110**, and the opening **115a** may overlap with a predetermined region of a top surface of the first electrode **110**. The PDL **115** may be formed of by using one of various insulating materials.

The particle unit **120** may be disposed to contact the top surface of the first electrode **110**. The particle unit **120** may include a plurality of particles **121**. Each of the particles **121** may include Ag. The particles **121** may be formed not only on the top surface of the first electrode **110** but also on a top portion of the PDL **115**.

The particles **121** of the particle unit **120** may have a predetermined size from about 300 angstroms to about 1000 angstroms.

In a case where a size of the particle **121** is less than 300 angstroms, visible light that is emitted from the intermediate layer **130** and transmitted toward the particle unit **120** may not be effectively dispersed and reflected such that a luminescent efficiency of the organic light-emitting display apparatus **100** may be poor.

Visible light emitted from the intermediate layer **130** may be dispersed by each of the particles **121** of the particle unit **120**, so that light of the visible light emitted from the intermediate layer **130** and having a specific wavelength may be filtered. Also, the visible light emitted from the intermediate layer **130** may be reflected between the particle unit **120** and the second electrode **140**, so that an optical resonance effect occurs in a space between the particle unit **120** and the second electrode **140**. If the size of the particles **121** is less than 300 angstroms, effective reflection and dispersion may not occur. It is desirable that the size of the particles **121** be equal to or greater than 300 angstroms.

In a case where the size of the particles **121** is greater than 1000 angstroms, the transmittance of the visible light that is emitted from the intermediate layer **130** and transmitted toward the substrate **101** may be decreased. In the case of a bottom emission type organic light emitting display apparatus **100**, in which visible light emitted from the intermediate layer **130** is transmitted toward the substrate **101** by which a user recognizes the visible light, if the size of the particles **121**

is greater than 1000 angstroms, the transmittance of the visible light emitted from the intermediate layer **130** may be decreased by the particles **121**. Thus, it is desirable that the size of the particles **121** be equal to or less than 1000 angstroms.

Here, the term "size of the particles **121**" may refer to a width of each of the particles **121**. For example, in a case where each of the particles **121** has a spherical shape, the size of the particles **121** may be defined as a diameter. In a case where each of the particles **121** is not spherical, a largest width of the particle **121** may be defined as the size of the particle **121**, provided that the size of the particle **121** is measured with respect to a center of the particle **121**.

The intermediate layer **130** may be disposed on the particle unit **120**. The intermediate layer **130** may include an organic emission layer. In more detail, the intermediate layer **130** may be disposed to correspond to the opening **115a** of the PDL **115**. The intermediate layer **130** may be disposed on the particles **121** of the particle unit **120**, and may contact the first electrode **110** via a space between the particles **121** that are separate from each other.

The organic emission layer of the intermediate layer **130** emits visible light and may produce various colors. For example, the organic emission layer may emit visible light of red, green, and blue colors.

The second electrode **140** may be disposed on the intermediate layer **130**. The second electrode **140** may have a stripe pattern that is perpendicular to the pattern of the first electrode **110**. The second electrode **140** may be formed of one or more of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca or a compound thereof.

The second electrode **140** may contact the particles **121** of the particle unit **120**. That is, the second electrode **140** may contact predetermined particles **121** from among the particles **121** that do not correspond to the intermediate layer **130**. Because the second electrode **140** may contact the particles **121** including Ag, it may be possible to prevent an IR drop in the second electrode **140** that may occur when a voltage is applied to the second electrode **140** and when the organic light-emitting display apparatus **100** is large.

Although not illustrated in FIG. **1**, a sealing member (not shown) may be formed on the second electrode **140** so as to face one surface of the substrate **101**. The sealing member may be formed to protect the intermediate layers **130** from water or oxygen from outside. The sealing member may be formed of glass or plastic or may have a structure in which a plurality of organic and inorganic materials is stacked.

The organic light-emitting display apparatus **100** may include the particle unit **120**. A part of visible light which is emitted from the intermediate layers **130** of the organic light-emitting display apparatus **100** and which is transmitted toward the substrate **101** may reach the particle unit **120** and then may be reflected from the particle unit **120**. The visible light that is reflected from the particle unit **120** may be transmitted toward the second electrode **140** and then may be reflected from the second electrode **140**. In this process, the visible light may resonate in a space between the particle unit **120** and the second electrode **140**, and the optical resonance may improve a luminescent efficiency of the organic light-emitting display apparatus **100**. Accordingly, a display quality of the organic light-emitting display apparatus **100** may be improved.

In particular, the luminescent efficiency of the organic light-emitting display apparatus **100** may be further improved in the bottom emission type organic light emitting display apparatus **100** in which visible light emitted from the intermediate layer **130** is transmitted toward the substrate **101** by

which a user recognizes the visible light. The particle unit **120** does not include an extended thin layer, but may include the particles **121** that are separate from each other, so that, after the resonance, visible light is transmitted toward the substrate **101** via a space between the particles **121** and then reaches a user, and thus optical loss may be decreased.

Also, visible light emitted from the intermediate layer **130** may reach the particle unit **120** and then may be dispersed by the particles **121**. Due to the optical dispersion, the luminescent efficiency of the organic light-emitting display apparatus **100** may be improved. In particular, the optical dispersion may induce filtering on a specific wavelength of the visible light. Due to this, a luminescent quality of blue visible light emitted from the intermediate layer **130** may be easily improved, and accordingly, the display quality of the organic light-emitting display apparatus **100** may be improved.

Also, because the second electrode **140** contacts the particles **121**, a voltage drop of the second electrode **140** may be prevented, so that an electrical characteristic and the display quality of the organic light-emitting display apparatus **100** may be improved.

FIG. 2 is a schematic cross-sectional view illustrating an organic light-emitting display apparatus **200** according to another embodiment.

Referring to FIG. 2, the organic light-emitting display apparatus **200** may include a substrate **201**, a thin film transistor (TFT), a first electrode **210**, a particle unit **220**, an intermediate layer **230**, and a second electrode **240**. The TFT may include an active layer **203**, a gate electrode **205**, a source electrode **207**, and a drain electrode **208**.

A configuration of each member will now be described in detail.

A buffer layer **202** may be formed on the substrate **201**. The buffer layer **202** may be formed of SiO₂ or SiN_x. Also, the buffer layer **202** may have a structure in which a plurality of layers is stacked. The buffer layer **202** may provide a plane surface on the substrate **201** and may prevent penetration of water and foreign substances into the substrate **201**.

The active layer **203**, which has a predetermined pattern, may be formed on the buffer layer **202**. The active layer **203** may be formed of an inorganic semiconductor including amorphous silicon or polysilicon, or an organic semiconductor. The active layer **203** may include a source region and a drain region. A gate insulating layer **204** may be formed on the active layer **203**. The gate insulating layer **204** may be formed using various insulating materials.

The gate electrode **205** may be formed on a predetermined region of the gate insulating layer **204**. The gate electrode **205** may be connected to a gate line (not shown) that applies TFT ON/OFF signals to the TFT. The gate electrode **205** may be formed of a metal including Au, Ag, Cu, Ni, Pt, Pd, Al, or Mo, or a metal alloy including an Al:Nd alloy, a Mo:W alloy, or the like, as examples.

An interlayer insulating layer **206** may be formed on the gate electrode **205** and may expose the source and drain regions of the active layer **203**.

The source electrode **207** and the drain electrode **208** may be formed to respectively contact the exposed source and drain regions of the active layer **203**.

A passivation layer **209** may be formed on the interlayer insulating layer **206** to cover the TFT.

The first electrode **210** may be formed on the passivation layer **209**. The passivation layer **209** may be formed to expose the drain electrode **208**, and the first electrode **210** may be connected to the exposed drain electrode **208**.

The first electrode **210** may include at least one of ITO, IZO, ZnO, In₂O₃, IGO, and AZO.

A PDL **215** may be disposed on the first electrode **210**. The PDL **215** may be formed of one of various insulating materials and may include an opening **215a**. The opening **215a** may correspond to the first electrode **210**. The opening **215a** may overlap with a predetermined region of a top surface of the first electrode **210**.

The particle unit **220** may be disposed to contact the top surface of the first electrode **210**. The particle unit **220** may include a plurality of particles **221**. Each of the particles **221** may include Ag. The particles **221** may be formed on the top surface of the first electrode **210** and on a top portion of the PDL **215**.

The particles **221** of the particle unit **220** may have a predetermined size that is from about 300 angstrom to about 1000 angstrom. A detailed description regarding a configuration of each particle **221** may be the same as the previous embodiment, and thus, is not repeated here.

The intermediate layer **230** may be disposed on the particle unit **220**. The intermediate layer **230** may include an organic emission layer. In more detail, the intermediate layer **230** may be disposed to correspond to the opening **215a** of the PDL **215**. The intermediate layer **230** may be disposed on the particles **221** of the particle unit **220**, and contacts the first electrode **210** via a space between the particles **221** that are separate from each other.

The organic emission layer of the intermediate layer **230** emits visible light and may produce various colors. For example, the organic emission layer may emit visible light of red, green, and blue colors.

The second electrode **240** may be disposed on the intermediate layer **230**. The second electrode **240** may not have a specific pattern and may be commonly formed on all subpixels (not shown). The second electrode **240** may be formed of one or more of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, or a compound thereof.

Although not illustrated in FIG. 2, a sealing member (not shown) may be formed on the second electrode **240** so as to face one surface of the substrate **201**. The sealing member may be formed to protect the intermediate layer **230** from water or oxygen from outside. The sealing member may be formed of glass or plastic or may have a structure in which a plurality of organic and inorganic materials is stacked.

FIG. 3 is a schematic cross-sectional view illustrating an organic light-emitting display apparatus **300** according to another embodiment.

Referring to FIG. 3, the organic light-emitting display apparatus **300** may include a substrate **301**, a TFT, a first electrode **310**, an intermediate layer **330**, a second electrode **340**, a particle unit **320**, and a capacitor **318**.

The TFT may include an active layer **303**, a gate electrode **307**, a source electrode **311**, and a drain electrode **312**. The capacitor **318** may include a first capacitor electrode **313** and a second capacitor electrode **317**.

A buffer layer **302** may be formed on the substrate **301**. The active layer **303** may be formed on a portion of the buffer layer **302**. Also, the first capacitor electrode **313** may be formed on a portion of the buffer layer **302**. The first capacitor electrode **313** may be formed of the same material as the active layer **303**.

A gate insulating layer **304** may be formed on the buffer layer **302** so as to cover the active layer **303** and the first capacitor **313**. The gate electrode **307**, the first electrode **310**, and the second capacitor electrode **317** may be formed on portions of the gate insulating layer **304**.

The gate electrode **307** may include a first conductive layer **305** and a second conductive layer **306**. The first conductive layer **305** may include a transmissive conductive material,

and in more detail, the first conductive layer **305** may include at least one of ITO, IZO, ZnO, In₂O₃, IGO, and AZO. The second conductive layer **306** may be formed of a metal including Mo, or a metal alloy including a Mo:W alloy, an Al-based alloy, or the like, as examples.

The first electrode **310** may include a transmissive conductive material and may be formed of the same material as the first conductive layer **305** of the gate electrode **307**. A conductive portion **310a** may be disposed on a predetermined region of the first electrode **310** and may be formed of the same material as the second conductive layer **306** of the gate electrode **307**.

The second capacitor electrode **317** may include a first layer **314** and a second layer **316**. The first layer **314** of the second capacitor electrode **317** may be formed of the same material as the first conductive layer **305** of the gate electrode **307**, and the second layer **316** of the second capacitor electrode **317** may be formed of the same material as the second conductive layer **306** of the gate electrode **307**.

An interlayer insulating layer **308** may be formed on the first electrode **310**, the gate electrode **307**, and the second capacitor electrode **317**. The interlayer insulating layer **308** may include various organic or inorganic insulating materials.

The source electrode **311** and the drain electrode **312** may be formed on the interlayer insulating layer **308**. The source electrode **311** and the drain electrode **312** may be connected to the active layer **303** via the interlayer insulating layer **308** and the gate insulating layer **304**.

Also, one of the source electrode **311** and the drain electrode **312** may be electrically connected to the first electrode **310**. FIG. 3 corresponds to a case in which the drain electrode **312** is electrically connected to the first electrode **310**. The drain electrode **312** may contact the conductive portion **310a**.

A PDL **315** may be formed on the interlayer insulating layer **308** so as to cover the TFT and the capacitor **318**. The PDL **315** may include an opening **315a**. The opening **315a** may overlap with a predetermined region of a top surface of the first electrode **310**.

The particle unit **320** may be disposed to contact the top surface of the first electrode **310**. The particle unit **320** may include a plurality of particles **321**. Each of the particles **321** may include Ag. The particles **321** may be formed on the top surface of the first electrode **310** and on a top portion of the PDL **315**.

The particles **321** of the particle unit **320** may have a predetermined size that is from about 300 angstrom to about 1000 angstrom. A detailed description regarding a configuration of each particle **321** may be the same as the previous embodiment, and thus, is not repeated here.

The intermediate layer **330** may be disposed on the particle unit **320**. The intermediate layer **330** may include an organic emission layer. In more detail, the intermediate layer **330** may be disposed to correspond to the opening **315a** of the PDL **315**. The intermediate layer **330** may be disposed on the particles **321** of the particle unit **320**, and contacts the first electrode **310** via a space between the particles **321** that are separate from each other.

The second electrode **340** may be disposed on the intermediate layer **330**. When a voltage is applied to the intermediate layer **330** via the first electrode **310** and the second electrode **340**, visible light may be emitted from the organic emission layer of the intermediate layer **330**.

A sealing member (not shown) may be disposed on the second electrode **340**. The sealing member may be formed to protect the intermediate layers **330** and other layers from water and oxygen from outside and may be formed of a

transparent material. The sealing member may have a structure in which a glass, a plastic, or a plurality of organic and inorganic materials is stacked.

FIGS. 4A through 4F are cross-sectional views that sequentially illustrate a method of manufacturing an organic light-emitting display apparatus, according to an embodiment.

In particular, the present embodiment corresponds to a method of manufacturing the organic light-emitting display apparatus **100** of FIG. 1. Although not illustrated in FIGS. 4A through 4F, aspects of the method according to the present embodiment may also apply to a method of manufacturing the organic light-emitting display apparatuses **200** and **300** of FIGS. 2 and 3.

Referring to FIG. 4A, the first electrode **110** may be formed on portions of the substrate **101**. The first electrode **110** may be formed by a photolithography method to have a predetermined pattern. Although not illustrated, a buffer layer (not shown) may be formed before the first electrode **110** is formed on the substrate **101**.

The first electrode **110** may be formed of at least one conductive material selected from ITO, IZO, ZnO, In₂O₃, IGO, and AZO.

Referring to FIG. 4B, the PDL **115** may be formed on the first electrode **110**. The PDL **115** may be formed to include the opening **115a**, which has a predetermined pattern. The PDL **115** may include a polymer material.

The opening **115a** may correspond to the first electrode **110**. The PDL **115** may cover a side edge of the first electrode **110**. The opening **115a** may expose a predetermined region of a top surface of the first electrode **110**.

Referring to FIG. 4C, a conductive layer **120a** to form the particle unit **120** may be formed on an exposed surface of the first electrode **110** and a top surface of the PDL **115**. The conductive layer **120a** may be formed on the first electrode **110** and the PDL **115** without using a separate pattern.

The conductive layer **120a** may include Ag, and may have a predetermined thickness. The thickness of the conductive layer **120a** may be about 10 angstroms to about 200 angstroms. When the conductive layer **120a** is formed to have the predetermined thickness, the particles **121** may be formed to have a size in the range of about 300 angstroms to about 1000 angstroms by performing a thermal treatment process.

Referring to FIG. 4D, the thermal treatment process may be performed so that agglomeration occurs in the conductive layer **120a**, and thus, the particles **121** may be formed. The thermal treatment process may be performed by inserting the substrate **101** into a thermal processing chamber **500**. The thermal treatment process may be performed at a temperature in the range of about 250 degrees Celsius to about 300 degrees Celsius. For example, the thermal treatment process may be performed at a temperature of about 250 degrees Celsius. If the thermal treatment process is performed at a temperature less than 250 degrees Celsius, agglomeration may not occur in the conductive layer **120a** such that the particles **121** may not be generated. If the thermal treatment process is performed at a temperature greater than 300 degrees Celsius, the first electrode **110** and the PDL **115** may be damaged or a characteristic of the conductive layer **120a** may be poor.

The thermal treatment process may be performed for a time period between about 50 minutes and about 90 minutes. For example, the thermal treatment process may be performed for one hour.

The thermal treatment process may be performed in a nitrogen atmosphere. When the thermal treatment process is complete, as illustrated in FIG. 4E, the particle unit **120** may be formed.

If the conductive layer **120a** is thermally treated with the aforementioned conditions, agglomeration may occur in the conductive layer **120a** to form the particles **121** that have a predetermined size and are separate from each other.

Referring to FIG. 4F, the intermediate layer **130** and the second electrode **140** may be formed on the first electrode **110**, so that the organic light-emitting display apparatus **100** is finally manufactured.

The intermediate layer **130** may include an organic emission layer. The intermediate layer **130** may be disposed to correspond to the opening **115a** of the PDL **115**. The intermediate layer **130** may be disposed on the particles **121** of the particle unit **120** and may contact the first electrode **110** via a space between the particles **121** that are separate from each other.

The second electrode **140** may be disposed on the intermediate layer **130**. The second electrode **140** may contact the particles **121** of the particle unit **120**. The second electrode **140** may contact predetermined particles **121** from among the particles **121** that do not correspond to the intermediate layer **130**.

Although not illustrated, a sealing member (not shown) may be formed on the second electrode **140** so as to face one surface of the substrate **101**. The sealing member may be formed to protect the intermediate layers **130** from water or oxygen from outside. The sealing member may be formed of glass or plastic or may have a structure in which a plurality of organic and inorganic materials is stacked.

By using the method of manufacturing the organic light-emitting display apparatus **100**, the particle unit **120** that includes the particles **121** may be easily formed on the first electrode **110**. Thus, a luminescent efficiency of the organic light-emitting display apparatus may be easily improved.

By way of summation and review, an organic light-emitting display apparatus may include an intermediate layer between a first electrode and a second electrode. The intermediate layer may include an organic emission layer. When a voltage is applied to the first and second electrodes, the organic emission layer emits visible light.

Visible light emitted from an organic emission layer of an intermediate layer included in a typical organic light-emitting display apparatus may be significantly lost before visible light reaches a user. A luminescent efficiency of the organic light-emitting display apparatus may be poor. Accordingly, it may be difficult to improve a display quality of the typical organic light-emitting display apparatus.

However, according to an organic light-emitting display apparatus and a method of manufacturing the organic light-emitting display apparatus according to the one or more embodiments, a display quality of the organic light-emitting display apparatus may be easily improved.

While embodiments have been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope thereof as defined by the following claims.

What is claimed is:

1. An organic light-emitting display apparatus, comprising:

- a substrate;
- a first electrode on the substrate;
- a pixel defining layer on the substrate and on the first electrode, the pixel defining layer including an opening that exposes the first electrode;

an intermediate layer on the first electrode, the intermediate layer including an organic emission layer;

a second electrode on the intermediate layer and on the pixel defining layer, and

a plurality of particles, the plurality of particles including a first set of particles contacting a top surface of the first electrode and the intermediate layer, a second set of particles contacting a side surface of the pixel defining layer and the intermediate layer, and a third set of particles contacting a top surface of the pixel defining layer, contacting the second electrode, and not contacting the intermediate layer.

2. The organic light-emitting display apparatus as claimed in claim 1, wherein a size of the particles of the plurality of particles is from about 300 angstroms to about 1000 angstroms.

3. The organic light-emitting display apparatus as claimed in claim 1, wherein the particles of the plurality of particles include Ag.

4. The organic light-emitting display apparatus as claimed in claim 1, wherein the first electrode includes a transmissive conductive material.

5. The organic light-emitting display apparatus as claimed in claim 4, wherein the transmissive conductive material includes at least one of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In₂O₃), indium gallium oxide (IGO), and aluminum zinc oxide (AZO).

6. A method of manufacturing an organic light-emitting display apparatus, the method comprising:

- forming a first electrode on a substrate;
- forming a pixel defining layer on the substrate and on the first electrode, the pixel defining layer including an opening that exposes the first electrode,

forming a plurality of particles, the plurality of particles including a first set of particles on a top surface of the first electrode, a second set of particles on a side surface and a third set of particles on a top surface of the pixel defining layer;

forming an intermediate layer including an organic emission layer on the first electrode and the particle unit; and forming a second electrode on the intermediate layer, such that the first set of particles contacts the top surface of the first electrode and the intermediate layer, the second set of particles contacts the side surface of the pixel defining layer and the intermediate layer, and the third set of particles contacts the top surface of the pixel defining layer, contacts the second electrode, and does not contact the intermediate layer.

7. The method as claimed in claim 6, wherein the forming of the plurality of particles includes:

- forming a conductive layer that includes Ag; and
- performing a thermal treatment on the conductive layer so as to allow the Ag to agglomerate.

8. The method as claimed in claim 7, wherein a thickness of the conductive layer is about 10 angstroms to about 200 angstroms.

9. The method as claimed in claim 7, wherein the thermal treatment is performed in a nitrogen atmosphere.

10. The method as claimed in claim 7, wherein the thermal treatment is performed at a temperature in a range of about 250 degrees Celsius to about 300 degrees Celsius.

专利名称(译)	有机发光显示装置和制造有机发光显示装置的方法		
公开(公告)号	US8692459	公开(公告)日	2014-04-08
申请号	US13/306010	申请日	2011-11-29
[标]申请(专利权)人(译)	LEE DAE WOO JO SOO BEOM 崔钟HYUN		
申请(专利权)人(译)	LEE DAE-WOO JO洙BEOM 崔钟铉		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE DAE WOO JO SOO BEOM CHOI JONG HYUN		
发明人	LEE, DAE-WOO JO, SOO-BEOM CHOI, JONG-HYUN		
IPC分类号	H01L51/50 G09G3/10		
CPC分类号	H01L51/5228 H01L51/5265 H01L2251/5369 H01L27/3248 H01L51/5271 H01L27/3246 H01L27/3283		
优先权	1020110066122 2011-07-04 KR		
其他公开文献	US20130009542A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光显示装置，包括基板;基板上的第一电极;粒子单元，包括在第一电极的顶表面上彼此分离的多个粒子;第一电极和颗粒单元上的中间层，包括有机发光层;和中间层上的第二电极。

