



US009780327B2

(12) **United States Patent**
Choi

(10) **Patent No.:** **US 9,780,327 B2**
(45) **Date of Patent:** **Oct. 3, 2017**

(54) **ORGANIC LIGHT EMITTING DISPLAY
DEVICE**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si
(KR)

(72) Inventor: **Ilshin Choi**, Yongin-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-shi
(KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/880,778**

(22) Filed: **Oct. 12, 2015**

(65) **Prior Publication Data**

US 2016/0111679 A1 Apr. 21, 2016

(30) **Foreign Application Priority Data**

Oct. 16, 2014 (KR) 10-2014-0140172

(51) **Int. Cl.**
H01L 51/52 (2006.01)
H01L 27/32 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/5246** (2013.01)

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,617,932 B2* 12/2013 Lee H01L 27/3276
349/190
8,748,756 B2* 6/2014 Kasahara H01L 51/5246
174/524

2001/0051398 A1* 12/2001 Hirakata G02F 1/13454
438/149
2007/0177069 A1* 8/2007 Lee H01L 51/5246
349/56

2007/0279571 A1 12/2007 Koo et al.
(Continued)

FOREIGN PATENT DOCUMENTS

KR 10-2006-0036522 5/2006
KR 10-0688972 3/2007

(Continued)

OTHER PUBLICATIONS

Guo, Chuan Fei, Jianming Zhang, Junjie Miao, Yongtao Fan, and
Qian Liu. "MTMO Grayscale Photomask." Optics Express 18.3
(2010): 2621.*



Primary Examiner — Joseph Schoenholtz

(74) *Attorney, Agent, or Firm* — H.C. Park & Associates,
PLC

(57) **ABSTRACT**

An organic light emitting display device including a first substrate; a second substrate facing the first substrate; a display unit, which is formed on a surface of the first substrate facing the second substrate and includes at least one organic light-emitting element; a first sealing unit, which is disposed between the first substrate and the second substrate to surround the display unit; a second sealing unit, which is disposed between the first substrate and the second substrate along the inner edges of the first sealing unit and includes a plurality of dots disposed apart from one another; and a screen, which is formed on a surface of the second substrate opposite a surface facing the first substrate to cover the second sealing unit.

16 Claims, 6 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

2008/0213482 A1 * 9/2008 Logunov C03C 17/09
427/259
2010/0117067 A1 5/2010 Sin et al.
2010/0148192 A1 * 6/2010 Jung H01L 27/3246
257/88
2011/0008593 A1 * 1/2011 Abbott, Jr. C03C 8/24
428/203
2011/0037095 A1 * 2/2011 Park H01L 51/525
257/100
2011/0291119 A1 12/2011 Ryu et al.
2012/0138979 A1 * 6/2012 Lee H01L 51/5246
257/91
2012/0248950 A1 * 10/2012 Niihori H01L 51/5246
312/223.1
2012/0319092 A1 * 12/2012 Shimomura B32B 37/06
257/40
2013/0313528 A1 * 11/2013 So H01L 51/5246
257/40
2014/0097746 A1 4/2014 Ha
2014/0319998 A1 10/2014 Han
2015/0041772 A1 2/2015 Han
2016/0035996 A1 * 2/2016 Sun H01L 21/77
257/40

FOREIGN PATENT DOCUMENTS

KR 10-2010-0052895 5/2010
KR 10-2011-0048130 5/2011
KR 10-2011-0130926 12/2011
KR 10-2014-0044111 4/2014
KR 10-2014-0128595 11/2014
KR 10-2015-0017988 2/2015

* cited by examiner

FIG. 1




FIG. 2A




FIG. 2B




FIG. 3




FIG. 4




FIG. 5





FIG. 6



1

**ORGANIC LIGHT EMITTING DISPLAY
DEVICE****CROSS-REFERENCE TO RELATED
APPLICATION**

This application claims priority from and the benefit of Korean Patent Application No. 10-2014-0140172, filed on Oct. 16, 2014, which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND**Field**

Exemplary embodiments relate to an organic light emitting display device.

Discussion of the Background

An organic light emitting display device is a self-luminous display device, from which a light is emitted by applying a voltage to an organic layer including an anode, a cathode, and an organic emission layer disposed therebetween to recombine electrons and holes in the organic emission layer. An organic light emitting display device may not only have a smaller volume than a cathode ray tube ("CRT") or a liquid crystal display ("LCD"), but may also feature wide viewing angle, fast response, and low power consumption, thus being spotlighted as a next-generation display device.

In an organic light emitting display device, an organic light-emitting element is disposed at a display area. The organic light-emitting element includes a pixel electrode and a counter electrode, which face each other, and an emission layer interposed between the pixel electrode and the counter electrode. Because such an organic light-emitting element may be easily damaged by various substances, such as moisture or oxygen from the outside, an organic light-emitting element may be sealed to prevent permeation of external impurities. One of the popular methods therefor is sealing edges of a substrate by using a frit material.

However, a sealing portion formed of a frit is vulnerable to external shock, and thus, improved mechanical strength is desirable.

The above information disclosed in this Background section is only for enhancement of understanding of the background of the inventive concept, and, therefore, it may contain information that does not form the prior art that is already known in this country to a person of ordinary skill in the art.

SUMMARY

Exemplary embodiments provide an organic light emitting display device with a sealing portion having improved mechanical strength and an improved outward appearance.

Additional aspects will be set forth in part in the description which follows, and, in part, will be apparent from the disclosure, or may be learned by practice of the inventive concept.

According to exemplary embodiments, an organic light emitting display device includes a first substrate; a second substrate disposed to face the first substrate; a display unit, which is disposed on a surface of the first substrate facing the second substrate and includes at least one organic light-emitting element; a first sealing unit, which is disposed between the first substrate and the second substrate and configured to surround the display unit; a second sealing unit, which is disposed between the first substrate and the

2

second substrate along the inner edges of the first sealing unit and includes a plurality of dots disposed apart from one another; and a screen, which is formed on a surface of the second substrate opposite a surface facing the first substrate to cover the second sealing unit.

According to exemplary embodiments, an organic light emitting display device includes a first substrate; a second substrate disposed to face the first substrate; a display unit, which is formed on a surface of the first substrate facing the second substrate and includes at least one organic light-emitting element; a first sealing unit, which is disposed between the first substrate and the second substrate to surround the display unit; a second sealing unit, which is disposed between the first substrate and the second substrate along the inner edges of the first sealing unit; and a screen, which is formed on a surface of the second substrate opposite a surface facing the first substrate to cover the second sealing unit.

The foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the claimed subject matter.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the inventive concept, and are incorporated in and constitute a part of this specification, illustrate exemplary embodiments of the inventive concept, and, together with the description, serve to explain principles of the inventive concept.

FIG. 1 is a schematic perspective diagram showing attachment between a first substrate, a second substrate, and a screen of an organic light emitting display device according to an embodiment.

FIG. 2A is a schematic plan view of the organic light emitting display device of FIG. 1, and FIG. 2B is a sectional view of the same, taken along a line II-II'.

FIG. 3 is a schematic sectional view of a display unit of the organic light emitting display device of FIG. 1.

FIGS. 4 and 5 are schematic plan views showing other embodiments with dots having different shapes and arrangements from those in the organic light emitting display device of FIG. 1.

FIG. 6 is a schematic plan view of an organic light emitting display device having a second sealing unit having a different shape from that of the organic light emitting display device of FIG. 1.

**DETAILED DESCRIPTION OF THE
ILLUSTRATED EMBODIMENTS**

In the following description, for the purposes of explanation, numerous specific details are set forth in order to provide a thorough understanding of various exemplary embodiments. It is apparent, however, that various exemplary embodiments may be practiced without these specific details or with one or more equivalent arrangements. In other instances, well-known structures and devices are shown in block diagram form in order to avoid unnecessarily obscuring various exemplary embodiments.

In the accompanying figures, the size and relative sizes of layers, films, panels, regions, etc., may be exaggerated for clarity and descriptive purposes. Also, like reference numerals denote like elements.

When an element or layer is referred to as being "on," "connected to," or "coupled to" another element or layer, it

may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being “directly on,” “directly connected to,” or “directly coupled to” another element or layer, there are no intervening elements or layers present. For the purposes of this disclosure, “at least one of X, Y, and Z” and “at least one selected from the group consisting of X, Y, and Z” may be construed as X only, Y only, Z only, or any combination of two or more of X, Y, and Z, such as, for instance, XYZ, 10 XXX, YZ, and ZZ. Like numbers refer to like elements throughout. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

Although the terms first, second, etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer, and/or section from another element, component, region, layer, and/or section. Thus, a first element, component, region, layer, and/or section discussed below could be termed a second element, component, region, layer, and/or section without departing from the teachings of the present disclosure.

Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper,” and the like, may be used herein for descriptive purposes, and, thereby, to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. Furthermore, the apparatus may be otherwise oriented (e.g., rotated 90 degrees or at other orientations), and, as such, the spatially 40 relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments and is not intended to be limiting. As used herein, the singular forms, “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. Moreover, the terms “comprises,” “comprising,” “includes,” and/or “including,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

Various exemplary embodiments are described herein with reference to sectional illustrations that are schematic illustrations of idealized exemplary embodiments and/or intermediate structures. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, exemplary embodiments disclosed herein should not be construed as limited to the particular illustrated shapes of regions, but are to include deviations in shapes that result from, for instance, manufacturing. For example, an implanted region illustrated as a rectangle will, typically, have rounded or curved features and/or a gradient of implant concentration at its edges rather than a binary change from implanted to non-implanted region. Likewise, a buried

region formed by implantation may result in some implantation in the region between the buried region and the surface through which the implantation takes place. Thus, the regions illustrated in the drawings are schematic in nature and their shapes are not intended to illustrate the actual shape of a region of a device and are not intended to be limiting.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure is a part. Terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

First, referring to FIGS. 1, 2A, and 2B, the organic light emitting display device according to an exemplary embodiment may include a first substrate **100**, a second substrate **110** facing the first substrate **100**, a display unit **200** that is formed on the first substrate **100** and includes at least one organic light-emitting element, a first sealing unit **300** that is disposed between the first substrate **100** and the second substrate **110** to surround the display unit **200**, a second 25 sealing unit **400** that includes a plurality of dots disposed apart from one another along inner edges of the first sealing unit **300**, and a screen **600** that is formed on the second substrate **110** to cover the second sealing unit **400**.

Furthermore, the organic light emitting display device according to an exemplary embodiment may further include a non-display unit **210** that is formed on the first substrate **100** along the outer edges of the display unit **200**.

The first substrate **100** may be formed of a SiO₂-based transparent glass material. However, materials for forming the first substrate **100** are not limited thereto, and the first substrate **100** may also be formed of a transparent plastic material. A plastic material for forming the first substrate **100** may be an organic insulation material selected from a group consisting of polyethersulphone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylenenaphthalate (PEN), polyethyleneterephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide (polyimide), polycarbonate (PC), cellulose triacetate (TAC), and cellulose acetate propionate (CAP).

Meanwhile, if the organic light emitting display device is a bottom emission type display device in which an image is formed toward the first substrate **100**, the first substrate **100** is formed using a transparent material. However, if the organic light emitting display device is a top emission type display device in which an image is formed toward the second substrate **110**, the first substrate **100** need not be using a transparent material.

Like the first substrate **100** as described above, the second substrate **110** may be formed of any of various materials and may be formed of at least one from among the above-stated various materials for forming the first substrate **100**.

Selectively, if the second substrate **110** functions as an encapsulating substrate sealed by a frit, the second substrate **110** may be formed of a glass that almost perfectly blocks moisture or oxygen in the air.

If the organic light emitting display device is a top emission type in which an image is formed toward the second substrate **110**, the second substrate **110** is formed using a transparent material. However, it is not necessary to form the first substrate **100** using a transparent material. On the contrary, if the organic light emitting display device is a bottom emission type in which an image is formed toward

the first substrate **100**, the first substrate **100** is formed using a transparent material, but it is not necessary to form the second substrate **110** using a transparent material. In other words, if either the first substrate **100** or the second substrate **110** is not formed of a transparent material, the first substrate **100** or the second substrate **110** may be formed of an opaque material.

The display unit **200** is disposed on the top surface of the first substrate **100**. The term display unit **200** herein refers to an organic light-emitting element and a thin-film transistor (TFT) array for driving the same, that is, a portion for displaying an image and a driving unit for displaying the image.

FIG. 3 is a schematic sectional view of the display unit **200** of the organic light emitting display device of FIG. 1.

The display unit **200** is formed on the first substrate **100** and may include a TFT **200a** and an organic light-emitting element **200b**. Hereinafter, detailed descriptions of the display unit **200** will be given below with reference to FIG. 3.

A buffer layer **212** may be formed on the first substrate **100**. The buffer layer **212** prevents permeation of impurity ions via the first substrate **100** and provides a flat surface on the first substrate **100**, where the buffer layer **212** may be formed of any of various materials suitable for the functions. For example, the buffer layer **212** may contain an inorganic material, such as silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, titanium oxide, or titanium nitride; or an organic material, such as polyimide, polyester, or acryl, where the buffer layer **212** may be formed as a stacked structure including a plurality of the above-stated materials.

An active layer **221** may be formed on the buffer layer **212** using an inorganic semiconductor, e.g., silicon, or an organic semiconductor. The active material **221** includes a source region, a drain region, and a channel region disposed therebetween. For example, if the active material **221** is formed using amorphous silicon, the active material **221** including a source region, a drain region, and a channel region therebetween may be formed by forming an amorphous silicon layer on the first substrate **100**, forming a poly-crystal silicon layer by crystallizing the amorphous silicon layer, patterning the poly-crystal silicon layer, and doping impurities to a source region and a drain region at edges of the poly-crystal silicon layer.

A gate insulation layer **213** is formed on the active material **221**. The gate insulation layer **213** insulates the active material **221** from the gate electrode **222**, and may be formed of an inorganic material, such as SiN_x or SiO_2 .

The gate electrode **222** is formed at a designated region on the gate insulation layer **213**. The gate electrode **222** is connected to a gate line (not shown) for applying ON/OFF signal to a TFT.

The gate electrode **222** may contain Au, Ag, Cu, Ni, Pt, Pd, Al, or Mo, and may contain an alloy, such as Al:Nd or Mo:W. However, the gate electrode **222** may also be formed of various other materials based on design considerations.

An interlayer insulation layer **214** formed on the gate electrode **222** is a layer for insulating the gate electrode **222**, a source electrode **223**, and a drain electrode **224** from one another, and may be formed of an inorganic material, such as SiN_x or SiO_2 .

The source electrode **223** and the drain electrode **224** are formed on the interlayer insulation layer **214**. In detail, the interlayer insulation layer **214** and the gate insulation layer **213** are formed to expose the source region and the drain region of the active material **221**, and the source electrode

223 and the drain electrode **224** are formed to contact the source region and the drain region of the active material **221**, respectively.

Meanwhile, although FIG. 3 shows a top gate type TFT including the active material **221**, the gate electrode **222**, the source electrode **223**, and the drain electrode **224** in the order stated, the gate electrode **222** may alternatively be disposed below the active material **221**.

The TFT **200a** is electrically connected to the organic light-emitting element **200b**, drives the organic light-emitting element **200b**, and is covered and protected by a planarizing layer **215**.

The planarizing layer **215** may be an inorganic insulation layer and/or an organic insulation layer. The inorganic insulation layer may include SiO_2 , SiN_x , SiON , Al_2O_3 , TiO_2 , Ta_2O_5 , HfO_2 , ZrO_2 , BST, or PZT, whereas the organic insulation layer may include a general commercial polymer (PMMA or PS), a polymer derivative containing the phenol-based group, acryl-based polymer, imide-based polymer, arylether-based polymer, amide-based polymer, fluorine-based polymer, p-xylene-based polymer, vinyl alcohol-based polymer, or a blend thereof. Furthermore, the planarizing layer **215** may be formed as a composite stack of an inorganic insulation layer and an organic insulation layer.

The organic light-emitting element **200b** may include a pixel electrode **231**, an intermediate layer **232**, and a counter electrode **233**.

The pixel electrode **231** is formed on the planarizing layer **215** and is electrically connected to the drain electrode **224** via a contact hole **230** formed in the planarizing layer **215**.

The pixel electrode **231** may be a reflective electrode and may include a reflective layer formed of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, or a compound thereof, and a transparent or semi-transparent electrode layer formed on the reflective layer. The transparent or semi-transparent electrode layer may contain at least one selected from a group consisting of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), indium gallium oxide (IGO), and aluminum zinc oxide (AZO).

The counter electrode **233** faces the pixel electrode **231** and may be a transparent or semi-transparent electrode formed of a metal thin-film containing a metal with a small work function, such as Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, or a compound thereof. Furthermore, an auxiliary electrode layer or a bus electrode may be further formed on the metal thin-film using a material for forming a transparent electrode, such as ITO, IZO, ZnO, or In_2O_3 .

Therefore, the source electrode **223** may transmit light emitted by an organic emission layer (not shown) included in the intermediate layer **232**. In other words, light emitted by the organic emission layer may be reflected directly, or by the pixel electrode **231** formed as a reflective electrode, and may be emitted toward the counter electrode **233**.

However, exemplary embodiments of the organic light emitting display device **10** are not limited to the top emission type display device, and may alternatively be configured as a bottom emission type display device, in which a light emitted by an organic emission layer (not shown) is emitted toward the first substrate **100**. In this case, the pixel electrode **231** may be formed as a transparent or semi-transparent electrode, whereas the counter electrode **233** may be formed as a reflective electrode. Furthermore, the organic light emitting display device **10** according to the present exemplary embodiment may be a two-way emission type display device that emits lights in two opposite top and bottom directions.

Meanwhile, a pixel defining layer **216** is formed on the pixel electrode **231** using an insulation material. The pixel defining layer **216** may be formed of one or more organic insulation materials selected from a group consisting of polyimide, polyamide, acrylic resin, benzocyclobutene, and phenolic resin using a method like spin coating. The pixel defining layer **216** exposes a designated region of the pixel electrode **231**, and the intermediate layer **232**, including an organic emission layer, is located at the exposed region.

The organic emission layer (not shown) included in the intermediate layer **232** may be formed of an organic monomer material or an organic polymer material, where the intermediate layer **232** may further include function layers other than the organic emission layer, such as a hole transport layer (HTL), a hole injection layer (HIL), an electron transport layer (ETL), and an electron injection layer (EIL), selectively.

Meanwhile, the non-display unit **210** may be defined on the first substrate **100** as a region excluding the display unit **200**. Here, the non-display unit **210** may be formed to have a frame-like shape along outer edges of the display unit **200** to surround the display unit **200**.

Furthermore, the non-display unit **210** may include a plurality of wirings **501** that are connected to the display unit **200** and extend toward an edge of the first substrate **100**. Furthermore, the first sealing unit **300** may be disposed along edges of the first substrate **100** and the second substrate **110** at the outermost portions of the non-display unit **210**, and the second sealing unit **400** may be disposed on the non-display unit **210** at a gap **500** between the first sealing unit **300** and the display unit **200**.

The first sealing unit **300** seals edges of the space between the first substrate **100** and the second substrate **110**. As described above, although the second substrate **110** blocks most of moisture or oxygen in the air, if there is a space between the second substrate **110** and the first substrate **100**, moisture or oxygen may permeate through the space. Therefore, the gap **500** between the second substrate **110** and the first substrate **100** is sealed by using the first sealing unit **300**. Therefore, the first sealing unit **300** may form a closed curve that perfectly seals edges of the first substrate **100** or the second substrate **110**.

Furthermore, according to an exemplary embodiment, the first sealing unit **300** may be formed of a glass material capable of blocking moisture or air. For example, the first sealing unit **300** may contain frit. Here, the frit may be formed of one or more materials selected from a group consisting of K_2O , Fe_2O_3 , Sb_2O_3 , ZnO , P_2O_5 , V_2O_5 , TiO_2 , Al_2O_3 , B_2O_3 , WO_3 , SnO , and Pb . Furthermore, the frit may be doped with a filler that lowers the thermal expansion coefficient of the frit, such that thermal expansion coefficient of the frit substantially matches that of the first substrate **100** or the second substrate **110**. Here, the filler may be an inversion filler or an additive filler.

The first sealing unit **300** is melted by radiating a laser beam or an infrared ray and re-hardened for complete adherence between the first substrate **100** and the second substrate **110**. Therefore, the organic light-emitting element may be completely sealed and protected from oxygen and moisture.

As described above, because the first sealing unit **300** is formed of a glass material, the first sealing unit **300** is heated at a high temperature for melting the same. Thus, while the first sealing unit **300** is being hardened, the organic light-emitting element **200b** disposed at the display unit **200** may be damaged. To prevent such damage to the organic light-

emitting element **200b**, the first sealing unit **300** is disposed apart from the display unit **200**.

As described above, the frit is a glass material with fragility. Therefore, an auxiliary sealing unit may be formed inside the first sealing unit **300** containing the frit. Therefore, according to an exemplary embodiment, the second sealing unit **400**, which functions as an auxiliary sealing unit, is disposed between the first substrate **100** and the second substrate **110**.

The second sealing unit **400** may be formed between the first substrate **100** and the second substrate **110** along the inner edges of the first sealing unit **300**. Here, the main sealing unit and the auxiliary sealing unit may be disposed apart from each other, thereby preventing shock waves applied to the auxiliary sealing unit from being transmitted to the main sealing unit.

The second sealing unit **400**, which blocks shock waves transmitted toward the first sealing unit **300** containing the frit, may be formed of a resin. In other words, to function as a buffer for sufficient absorption of external shocks, the second sealing unit **400** may contain a material selected from among a poly-silicon-based material, an epoxy-based material, and various other organic materials. Furthermore, by employing a flexible organic material as described above, fragility of the frit of the first sealing unit **300** may be reduced. Particularly, excellent adherence of an epoxy-based resin may prevent the both substrates from being detached from each other, and may provide high reliability with respect to peeling test.

Meanwhile, the second sealing unit **400** may include a plurality of dots disposed to be apart from one another. When the second sealing unit **400** includes the plurality of dots, the volume of a material for forming the entire sealing line may be reduced. Therefore, as compared to a case in which a successive sealing line is formed, an amount of residual gas discharged from a sealing material may be further reduced.

If an amount of residual gas discharged from a sealing material is reduced as described above, permeations of moisture and oxygen into the display unit **200** may be prevented, and adherence at the sealing line may be improved.

The width of the second sealing unit **400** may be to the same as, or up to twice as large as, the width of the first sealing unit **300**. Since mechanical strength of the overall sealing structure is improved, the width of the first sealing unit **300** may be reduced, and thus dead space may be reduced.

Hereinafter, various exemplary embodiments of shapes and arrangements of dots constituting the second sealing unit **400** will be described.

FIGS. 1 and 2A show dots having circular shapes, and a plurality of dots are uniformly disposed.

Meanwhile, FIGS. 4 and 5 are schematic plan views showing other exemplary embodiments with dots having different shapes and arrangements from those in the organic light emitting display device of FIG. 1.

However, the shapes of the dots are not limited thereto. The dots may have a rectangular shape, as shown in FIG. 4, or may have any of various shapes, e.g., a rhombus-like shape, a donut-like shape, etc. Furthermore, dots having such a shape may be disposed to be tilted with respect to edges of the substrate.

As shown in FIG. 5, at least two dots may form a single set **405**, and a plurality of sets **405** may be disposed to be apart from one another. By arranging a plurality of plurality of dots in the form of the sets **405** as described above, a

larger number of discontinuous portions are formed, and thus, residual gas may be discharged more effectively. Furthermore, adherence of the second sealing unit **400** may be further improved.

The dots may be formed via printing, nozzle jetting, or any other suitable method.

Meanwhile, in order to not to expose the second sealing unit **400** to the outside, the screen **600** may be formed on a surface opposite to a surface of the second substrate **110** facing the first substrate **100**.

In case of the second sealing unit **400** formed inside the first sealing unit **300**, since the second substrate **110**, which is the top substrate, is formed of a transparent material, a user may be mistakenly identify the second sealing unit **400** as a foreign substance when the user is looking at the display device. Therefore, the second sealing unit **400** disposed close to a display unit may be considered to be a cosmetic defect. Therefore, to prevent the second sealing unit **400** from being seen from outside, the screen **600** is formed on the top surface of the second substrate **110**.

The screen **600** may include a single metal film or stacked films including a metal film and an inorganic film. In other words, the screen **600** may be a film containing a metal or an opaque film, such as a film included in a touch screen panel.

Selectively, the screen **600** may further include a scattering film for scattering a light incident from outside. The scattering film may include an inorganic film and the light transmittance of the inorganic film may be 60% or lower.

Furthermore, the screen **600** may be formed to have a width greater than or at least equal to that of the second sealing unit **400** to efficiently cover the second sealing unit **400**.

However, the screen **600** may not only cover the second sealing unit **400**, but also narrow viewing angle of a display device. Therefore, the screen **600** may be formed to not to overlap the display unit **200**.

Meanwhile, according to another exemplary embodiment, the second sealing unit **400** may be disposed between the first substrate **100** and the second substrate **110** along the inner edges of the first sealing unit **300** in the form of a single strip, as in the first sealing unit **300**.

FIG. 6 is a schematic plan view of an organic light emitting display device having a second sealing unit having a different shape from that of the organic light emitting display device of FIG. 1.

As shown in FIG. 6, this exemplary embodiment is identical to the organic light emitting display device of FIG. 1, except the organic light emitting display device of FIG. 1 includes a plurality of dots.

As described above, organic light emitting display devices according to exemplary embodiments have double sealing structures, thereby resolving mechanical strength problem of a single sealing structure and preventing an auxiliary sealing unit inside a double sealing structure to be seen by a user as a defect.

As described above, organic light emitting display devices according to the one or more of the above exemplary embodiments may improve mechanical strength of a sealing unit formed of a frit and reduce dead space.

Furthermore, organic light emitting display devices according to the above exemplary embodiments have an improved cosmetic appearance to prevent cosmetic defects.

Although certain exemplary embodiments and implementations have been described herein, other embodiments and modifications will be apparent from this description. Accordingly, the inventive concept is not limited to such

embodiments, but rather to the broader scope of the presented claims and various obvious modifications and equivalent arrangements.

What is claimed is:

1. An organic light emitting display device comprising:
 - a first substrate;
 - a second substrate facing the first substrate;
 - a display unit disposed on a surface of the first substrate facing the second substrate, the display unit comprising at least one organic light-emitting element;
 - a first sealing unit disposed between the first substrate and the second substrate and surrounding the display unit;
 - a second sealing unit disposed between the first substrate and the second substrate along the inner edges of the first sealing unit, the second sealing unit comprising a plurality of discrete areas disposed apart from one another; and

a screen disposed on a surface of the second substrate opposite a surface facing the first substrate, the screen configured to cover the second sealing unit,

wherein:

the screen comprises:

- an opening overlapping a central portion of the display unit; and
 - stacked films comprising a metal film and an inorganic film and overlapping the second sealing unit; and
- transmittance of the inorganic film is 60% or lower.

2. The organic light emitting display device of claim 1, further comprising a non-display unit disposed on the first substrate along outer edges of the display unit, the non-display unit comprising a plurality of wirings extending toward an edge of the first substrate.

3. The organic light emitting display device of claim 2, wherein the second sealing unit is disposed on the non-display unit to at least overlap the plurality of wirings.

4. The organic light emitting display device of claim 1, wherein the width of the second sealing unit is equal to or up to twice as large as the width of the first sealing unit.

5. The organic light emitting display device of claim 1, wherein each of the discrete areas has a circular shape or a polygonal shape.

6. The organic light emitting display device of claim 4, wherein:

- at least two of the discrete areas form one of a plurality of sets; and

the sets are disposed to be apart from one another.

7. The organic light emitting display device of claim 1, wherein the second sealing unit comprises a poly-silicon material, an epoxy material, or at least one other organic material.

8. The organic light emitting display device of claim 1, wherein the first sealing unit comprises a frit.

9. The organic light emitting display device of claim 1, wherein the width of the screen is greater than or at least equal to the width of the second sealing unit.

10. An organic light emitting display device comprising:
 - a first substrate;
 - a second substrate facing the first substrate;
 - a display unit disposed on a surface of the first substrate facing the second substrate, the display unit comprising at least one organic light-emitting element;
 - a first sealing unit disposed between the first substrate and the second substrate and surrounding the display unit;
 - a second sealing unit disposed between the first substrate and the second substrate along the inner edges of the first sealing unit; and

a screen disposed on a surface of the second substrate opposite a surface facing the first substrate, the screen configured to cover the second sealing unit,

wherein:

the screen comprises:

an opening overlapping a central portion of the display unit; and

stacked films comprising a metal film and an inorganic film and overlapping the second sealing unit; and

transmittance of the inorganic film is 60% or lower.

11. The organic light emitting display device of claim **10**, further comprising a non-display unit disposed on the first substrate along the outer edges of the display unit, the non-display unit comprising a plurality of wirings extending toward an edge of the first substrate.

12. The organic light emitting display device of claim **11**, wherein the second sealing unit is disposed on the non-display unit to at least overlap the wirings.

13. The organic light emitting display device of claim **10**, wherein the width of the second sealing unit is equal to or up to twice as large as the width of the first sealing unit.

14. The organic light emitting display device of claim **10**, wherein the second sealing unit comprises one selected from among a poly-silicon material, an epoxy material, and at least one other organic material.

15. The organic light emitting display device of claim **10**, wherein the first sealing unit comprises a frit.

16. The organic light emitting display device of claim **10**, wherein the width of the screen is greater than or at least equal to the width of the second sealing unit.

* * * * *

专利名称(译)	有机发光显示装置		
公开(公告)号	US9780327	公开(公告)日	2017-10-03
申请号	US14/880778	申请日	2015-10-12
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	CHOI ILSHIN		
发明人	CHOI, ILSHIN		
IPC分类号	H01L51/52 H01L27/32		
CPC分类号	H01L51/5246		
优先权	1020140140172 2014-10-16 KR		
其他公开文献	US20160111679A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光显示装置，包括第一基板;面向第一基板的第二基板;显示单元，形成在第一基板的面对第二基板的表面上，并包括至少一个有机发光元件;第一密封单元，设置在第一基板和第二基板之间以包围显示单元;第二密封单元，沿第一密封单元的内边缘设置在第一基板和第二基板之间，并包括多个彼此分开设置的点;屏幕，其形成在第二基板的与面对第一基板的表面相对的表面上，以覆盖第二密封单元。

