



US 20160218165A1

(19) **United States**(12) **Patent Application Publication**
Park et al.(10) **Pub. No.: US 2016/0218165 A1**(43) **Pub. Date: Jul. 28, 2016**(54) **ORGANIC LIGHT-EMITTING DIODE
DISPLAY AND METHOD OF
MANUFACTURING THE SAME**(52) **U.S. CL.**CPC *H01L 27/3276* (2013.01); *H01L 27/3248*
(2013.01); *H01L 25/18* (2013.01); *H01L 51/56*
(2013.01); *H01L 2227/323* (2013.01)(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si
(KR)(72) Inventors: **Kyung Hoon Park**, Suwon-si (KR);
Chun Gi You, Asan-si (KR); **Sun Park**,
Suwon-si (KR)(21) Appl. No.: **14/836,643**(22) Filed: **Aug. 26, 2015**(30) **Foreign Application Priority Data**

Jan. 23, 2015 (KR) 10-2015-0011566

Publication Classification(51) **Int. Cl.***H01L 27/32* (2006.01)*H01L 51/56* (2006.01)*H01L 25/18* (2006.01)(57) **ABSTRACT**

An organic light-emitting diode (OLED) display and a method of manufacturing an OLED display are disclosed. In one aspect, the method includes forming a data electrode layer and patterning the data electrode layer so as to form a source electrode, a drain electrode, and a pad electrode. The method can also include forming a first organic insulating layer over the source, drain and pad electrodes and forming a via hole corresponding to the source electrode or the drain electrode in the first organic insulating layer via a one tone mask. The method can further include forming an OLED including an anode electrically connected to the source electrode or the drain electrode, an organic emission layer, and a cathode, and etching a first portion of the first organic insulating layer formed over the pad electrode and a second portion of the organic emission layer formed over the pad electrode.




FIG. 1




FIG. 2




FIG. 3A




FIG. 3B






FIG. 3C





**ORGANIC LIGHT-EMITTING DIODE
DISPLAY AND METHOD OF
MANUFACTURING THE SAME**

**CROSS-REFERENCE TO RELATED
APPLICATION**

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2015-0011566 filed in the Korean Intellectual Property Office on Jan. 23, 2015, the entire contents of which are incorporated herein by reference.

BACKGROUND

[0002] 1. Field

[0003] The described technology generally relates to an organic light-emitting diode display and a manufacturing method thereof.

[0004] 2. Description of the Related Technology

[0005] Organic light-emitting diode (OLED) displays have favorable characteristics such as wide viewing angles, excellent contrast ratios, and rapid refresh rates compared to liquid crystal displays (LCDs).

[0006] An OLED display panel includes pad electrodes to be connected with an external mounted component such as a driving integrated circuit (IC).

SUMMARY OF CERTAIN INVENTIVE ASPECTS

[0007] One inventive aspect relates to an OLED display including a pad portion which is not corroded without a cladding process and a manufacturing method thereof.

[0008] Another aspect is a manufacturing method of the OLED display including: stacking a data electrode layer; forming a source electrode, a drain electrode, and a pad electrode by patterning the data electrode layer; stacking a first organic insulating layer on the source electrode, the drain electrode, and the pad electrode; forming a via hole corresponding to the source electrode or the drain electrode in the first organic insulating layer by using a one tone mask; forming an OLED of which an anode is electrically connected to the source electrode or the drain electrode and including an organic emission layer and a cathode; and etching a portion of the first organic insulating layer covering the pad electrode and a remaining organic material.

[0009] The forming of the OLED can include: forming the anode; stacking and etching a second organic insulating layer so that the anode is exposed; stacking the organic emission layer on the anode; and stacking the cathode on the organic emission layer and the second organic insulating layer.

[0010] In the forming of the via hole, the portion of the first organic insulating layer covering the pad electrode can be maintained.

[0011] When the organic emission layer is formed, the remaining organic material can be formed on a seal line region and on the portion of the first organic insulating layer covering the pad electrode.

[0012] In the etching, a difference between a height of the first organic insulating layer around the pad electrode and a height of the pad electrode can be 1.5 μm or less.

[0013] In the etching, the first organic insulating layer can be etched so that the height of the first organic insulating layer around the pad electrode is smaller than the height of the pad electrode, and the pad electrode can be projected.

[0014] An etching method used in the etching can be dry etching.

[0015] The dry etching can be plasma etching.

[0016] Another aspect is a method of manufacturing an organic light-emitting diode (OLED) display, comprising: forming a data electrode layer; patterning the data electrode layer so as to form a source electrode, a drain electrode, and a pad electrode; forming a first organic insulating layer over the source, drain and pad electrodes; forming a via hole corresponding to the source electrode or the drain electrode in the first organic insulating layer via a one tone mask; forming an OLED including i) an anode electrically connected to the source electrode or the drain electrode, ii) an organic emission layer and iii) a cathode; and etching a first portion of the first organic insulating layer formed over the pad electrode and a second portion of the organic emission layer formed over the pad electrode.

[0017] In the above method, the forming of the OLED includes: forming the anode; forming a second organic insulating layer; etching a portion of the second organic insulating layer so that the anode is exposed via the etched portion; forming the organic emission layer over the anode; and forming the cathode over the organic emission layer and the second organic insulating layer.

[0018] In the above method, the forming of the via hole includes maintaining the first portion.

[0019] In the above method, the second portion is formed over a seal line region and the first portion.

[0020] In the above method, the difference between the height of the first organic insulating layer around the pad electrode and the height of the pad electrode is about 1.5 μm or less.

[0021] In the above method, the first organic insulating layer is etched such that the height of the first organic insulating layer around the pad electrode is less than the height of the pad electrode.

[0022] In the above method, the etching includes dry etching.

[0023] In the above method, the dry etching includes plasma etching.

[0024] The above method further comprises forming a driving integrated circuit over the pad electrode and the first portion.

[0025] Another aspect is an organic light-emitting diode (OLED) display, comprising: a substrate including a display area and a non-display area surrounding the display area; source and drain electrodes formed over the display area; a pad electrode formed over the non-display area; a first organic insulating layer formed over the source electrode and contacting the drain and pad electrodes; and a via hole corresponding to the source or drain electrode formed in the first organic insulating layer.

[0026] In the above OLED display, the forming of the OLED includes: an anode electrically connected to the source or drain electrode; an organic emission layer formed over the anode; a second organic insulating layer formed over the anode and the first organic insulating layer; and a cathode formed over the organic emission layer and the second organic insulating layer.

[0027] In the above OLED display, the second portion is formed over a seal line region located between the display area and the non-display area.

[0028] In the above OLED display, the difference between the height of the first organic insulating layer around the pad electrode and the height of the pad electrode is about 1.5 μm or less.

[0029] In the above OLED display, the height of the first organic insulating layer around the pad electrode is less than the height of the pad electrode.

[0030] The above OLED display further comprises a driving integrated circuit formed over the pad electrode and a portion of the first organic insulating layer contacting the pad electrode.

[0031] Another aspect is a method of manufacturing an organic light-emitting diode (OLED) display, comprising: forming source, drain and pad electrodes; forming a first organic insulating layer over the source, drain and pad electrodes; forming a via hole corresponding to the source or drain electrode in the first organic insulating layer via a one tone mask; and etching a first portion of the first organic insulating layer formed over the pad electrode and a second portion of the organic emission layer formed over the pad electrode.

[0032] The above method further comprises forming an OLED, wherein the forming of the OLED includes: forming an anode; forming a second organic insulating layer; etching a portion of the second organic insulating layer so the anode is exposed via the etched portion; forming an organic emission layer over the anode; and forming a cathode over the organic emission layer and the second organic insulating layer.

[0033] In the above method, the forming of the via hole includes maintaining the first portion.

[0034] In the above method, the second portion is formed over a seal line region and the first portion.

[0035] In the above method, the difference between the height of the first organic insulating layer around the pad electrode and the height of the pad electrode is about 1.5 μm or less.

[0036] According to at least one of the disclosed embodiments, it is possible to provide an OLED display including a pad portion which does not corrode without a cladding process and a manufacturing method thereof.

BRIEF DESCRIPTION OF THE DRAWINGS

[0037] FIG. 1 is a diagram illustrating a display panel of an OLED display according to an exemplary embodiment of the described technology.

[0038] FIG. 2 is a cross-sectional view of the display panel of FIG. 1 taken along lines A-A', B-B', and C-C'.

[0039] FIGS. 3A, 3B, 3C and 3D are diagrams for describing a manufacturing method of the OLED display of FIG. 1.

DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

[0040] Generally, a pad electrode for an OLED display is formed of a conductive material (Mo/Al/Mo) having low resistance but low resistance to corrosion. A low corrosive metal such as indium tin oxide (ITO) and indium zinc oxide (IZO) is clad on the pad electrode. As a result, in wet, cleaning, and like process steps which are performed after forming the pad electrode, the corrosion can be prevented.

[0041] However, cladding requires use of an additional mask and a resultant increase in manufacturing cost.

[0042] The described technology will be described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments are shown. As those skilled in the art would realize, the described embodiments

can be modified in various different ways, all without departing from the spirit or scope of the described technology.

[0043] In the drawings, the thickness of layers, films, panels, regions, etc., are exaggerated for clarity. Like reference numerals designate like elements throughout the specification. It will be understood that when an element such as a layer, film, region, or substrate is referred to as being "on" another element, it can be directly on the other element or intervening elements can also be present. In contrast, when an element is referred to as being "directly on" another element, there are no intervening elements present. In this disclosure, the term "substantially" includes the meanings of completely, almost completely or to any significant degree under some applications and in accordance with those skilled in the art. Moreover, "formed on" can also mean "formed over." The term "connected" can include an electrical connection.

[0044] FIG. 1 is a diagram illustrating a display panel of an OLED display according to an exemplary embodiment. FIG. 2 is a cross-sectional view of the display panel of FIG. 1 taken along lines A-A', B-B', and C-C'.

[0045] Referring to FIGS. 1 and 2, the display panel includes a first substrate 100, a second substrate 200, a driving IC 300, and a flexible printed circuit (FPC) 400.

[0046] The first substrate 100 is a substrate on which a plurality of OLEDs and corresponding thin film transistors are formed, and can be formed of a plastic material such as glass or polyimide and the like.

[0047] A buffer layer 110 is stacked on the first substrate 100. The buffer layer 110 can be formed of an inorganic material such as silicon oxide (SiO_x) and silicon nitride (SiN_x) and can be a single layer or a multilayer.

[0048] The buffer layer 110 serves to prevent impurity, oxygen, moisture, and the like from permeating the surface. The buffer layer 110 also planarizes the surface.

[0049] The semiconductor layer 120 is stacked on the buffer layer 110. The semiconductor layer 120 can be formed of polycrystalline silicon, and include a channel region, a source region, and a drain region.

[0050] The channel region can be formed of polysilicon on which impurity is not doped, that is, an intrinsic semiconductor, and the source region and the drain region can be formed at both sides of the channel region and impurity semiconductors in which impurities are doped.

[0051] A gate insulating layer 130 is stacked on the semiconductor layer 120. The gate insulating layer 130 can be formed of an inorganic material such as silicon oxide (SiO_x) and silicon nitride (SiN_x) and can be a single layer or a multilayer.

[0052] The gate electrode 140 is formed to correspond to the channel region of the semiconductor layer 120, on the gate insulating layer 130. The gate electrode 140 can be formed of a single or two or more kinds of conductive materials.

[0053] An interlayer insulating layer 150 is stacked on the gate electrode 140. The interlayer insulating layer 150 can be formed of an inorganic material such as silicon oxide (SiO_x) and silicon nitride (SiN_x) and can be configured by a single layer or a multilayer.

[0054] Via holes exposing the source region and the drain region of the semiconductor layer 120, respectively, are formed in the interlayer insulating layer 150 and the gate insulating layer 130.

[0055] On the interlayer insulating layer 150, a source electrode 161 connected to the source region through the via hole

and a drain electrode **162** connected to the drain region through the via hole are formed.

[0056] Further, referring to a cross section taken along line C-C', the pad electrode **163** is formed on the interlayer insulating layer **150**.

[0057] The source electrode **161**, the drain electrode **162**, and the pad electrode **163** can be formed of the same conductive material, and copper (Cu), aluminum (Al), molybdenum (Mo), chromium (Cr), titanium (Ti), and the like or alloys thereof can be formed in a single-layered or multilayered structure.

[0058] A first organic insulating layer **170** is stacked on the source electrode **161** and the drain electrode **162**. The first organic insulating layer **170** is formed around the pad electrode **163**.

[0059] The first organic insulating layer **170** can include a photoresist.

[0060] The first organic insulating layer **170** includes a via hole exposing the drain electrode **162**.

[0061] Depending on whether the thin film transistor is a P type or an N type, a via hole exposing the source electrode **161** rather than the drain electrode **162** can be formed.

[0062] On the first organic insulating layer **170**, an anode **180** of the OLED is formed. On the anode **180**, an organic emission layer **181** and a cathode **182** are sequentially stacked to form the OLED.

[0063] In some embodiments, the anode **180** is formed on the first organic insulating layer **170**, but is not limited thereto.

[0064] For example, the anode **180** is patterned once and formed with the same metal as the source electrode **161** and the drain electrode **162**, and in this case, the anode **180** is formed on the gate insulating layer **130** or on the interlayer insulating layer **150**.

[0065] As another example, the anode **180** is patterned once and formed with the same metal as the gate electrode **140**.

[0066] Further, depending on an applied voltage, the layout of the anode **180** and the cathode **182** can be reversed.

[0067] Accordingly, in the described technology, there is no limitation on a stacking structure for electric connection between the OLED and the thin film transistor.

[0068] The anode **180** can be formed of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), or indium oxide (In_2O_3), or a reflective metal such as lithium (Li), calcium (Ca), lithium fluoride/calcium (LiF/Ca), lithium fluoride/aluminum (LiF/Al), aluminum (Al), silver (Ag), magnesium (Mg), or gold (Au).

[0069] The second organic insulating layer **190** surrounds an edge of the anode **180** and is formed on the first organic insulating layer **170**. The second organic insulating layer **190** is called a pixel defining layer partitioning a light emission area of the OLED.

[0070] The second organic insulating layer **190** can be formed by resin such as polyacrylates or polyimides.

[0071] The organic emission layer **181** is formed on the anode **180** which is the light emission area partitioned by the second organic insulating layer **190**.

[0072] The organic emission layer **181** can include a single layer or a multilayer including one or more of an emission layer, a hole-injection layer (HIL), a hole-transporting layer (HTL), an electron-transporting layer (ETL), and an electron-injection layer (EIL).

[0073] In the case where the organic emission layer **181** includes all the layers, the HIL is positioned on the anode **180**, and the HTL, the emission layer, the ETL, and the EIL can be sequentially stacked thereon.

[0074] The organic emission layer **181** can include red, green and blue organic emission layers respectively emitting red, green and blue light. The red, green and blue organic emission layers are respectively formed in a red pixel, a green pixel, and a blue pixel, thereby implementing a color image.

[0075] Further, in the organic emission layer **181**, all of the red, green and blue organic emission layers are together stacked on the red, green and blue pixels. Red, green and blue color filters are formed for each pixel, thereby implementing a color image. As another example, white organic emission layers emitting white light are formed on the red, green and blue pixels, and red, green and blue color filters are formed for each pixel, thereby implementing the color image. In the case of implementing the color image by using the white organic emission layer and the color filters, it is not required to use a deposition mask for depositing the red, green and blue organic emission layers on respective pixels, that is, the red, green and blue pixels.

[0076] The white organic emission layer can be formed by one organic emission layer, and also includes a configuration formed so as to emit white light by stacking a plurality of organic emission layers. For example, the white organic emission layer includes a configuration which can emit white light by combining at least one yellow organic emission layer and at least one blue organic emission layer, a configuration which can emit white light by combining at least one cyan organic emission layer and at least one red organic emission layer, a configuration which can emit white light by combining at least one magenta organic emission layer and at least one green organic emission layer, and the like.

[0077] The cathode **182** is formed on the second organic insulating layer **190** and the organic emission layer **181**. The cathode **182** can be formed of a transparent conductive material such as ITO, IZO, ZnO, or In_2O_3 , or a reflective metal such as lithium, calcium, lithium fluoride/calcium, lithium fluoride/aluminum, aluminum, silver, magnesium, or gold.

[0078] Referring to a seal line region which is a region of line B-B', a seal line **500** is formed on the interlayer insulating layer **150** to assemble and encapsulate the first substrate **100** and the second substrate **200**.

[0079] In some embodiments, the seal line **500** is formed on the interlayer insulating layer **150**, but can also be formed on the first substrate **100**, on the buffer layer **110**, on the gate insulating layer **130**, or the like. Accordingly, a formation position of the seal line **500** is not limited to the described technology.

[0080] Referring to a pad region which is a region of C-C' line, the driving IC **300** includes a bump **320**, and the bump **320** is electrically connected to the pad electrode **163** through a plurality of conductive balls **310**.

[0081] The conductive balls **310** can be included and coated on an anisotropic conductive film (ACF).

[0082] In FIG. 2, a height of the first organic insulating layer **170** around the pad electrode **163** is formed to be lower than a height of the pad electrode **163**. However, the height of the first organic insulating layer **170** can be formed to be larger than the height of the pad electrode **163**, and in this case, a difference between the height of the first organic insulating layer **170** and the height of the pad electrode **163** can be formed to be smaller than a diameter of the conductive

ball **310**. The difference can vary according to a diameter and a characteristic of the conductive balls **310**, but generally, the difference in height can be about 1.5 μm or less. However, depending on the embodiments, the difference in height can be greater than about 1.5 μm .

[0083] The driving IC **300** can be one of a data driving IC and a gate driving IC, or can include both the data driving IC and the gate driving IC. Further, the driving IC **300** can further include a power supplying unit. The layout position and the configuration of the driving IC **300** illustrated in FIG. 1 are exemplified, and the described technology is not limited thereto.

[0084] A flexible printed circuit (FPC) **400** serves to apply an external signal to a display panel and can be electrically connected to another portion (not illustrated) of the driving IC **300**.

[0085] FIGS. 3A-3D are diagrams for describing a manufacturing method of the OLED display of FIG. 1.

[0086] Referring to FIG. 3A, the thin film transistor and the pad electrode **163** are formed.

[0087] The buffer layer **110** which prevents impurity from permeating the surface and planarizes the surface is formed on the first substrate **100**.

[0088] The semiconductor layer **120** of the thin film transistor is formed on the buffer layer **110**. The semiconductor layer **120** can be formed of polycrystalline silicon and patterned by using a first mask.

[0089] The gate insulating layer **130** is formed on the semiconductor layer **120**. The gate insulating layer **130** can deposit an inorganic insulating layer such as silicon oxide and silicon nitride by a method such as a PECVD method, an APCVD method, and an LPCVD method.

[0090] The gate electrode **140** is formed on the gate insulating layer **130** by using a second mask.

[0091] The gate electrode **140** can include a single layer or a multilayer formed of a transparent material such as ITO, IZO, ZnO, or In_2O_3 or a material such as Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, Mo, Ti, W, MoW, or Al/Cu.

[0092] An n type or p type impurity can be doped according to a kind of thin film transistor by using the gate electrode **140** as a mask. The semiconductor layer **120** covered by the gate electrode **140** becomes a channel region, and an edge portion which is not covered by the gate electrode **140** becomes a source region and a drain region.

[0093] The interlayer insulating layer **150** is formed on the gate electrode **140**. The interlayer insulating layer **150** can be formed by spin-coating one or more organic insulating materials such as polyimide, polyamide, acrylic resin, benzocyclobutene, and phenol resin, (this can be a closed group) and can be formed to be larger than the aforementioned gate insulating layer **130** in thickness to insulate the gate electrode **140** and the source/drain electrodes **161** and **162** of the thin film transistor from each other. Further, the interlayer insulating layer **150** can be formed on an organic insulating material and an inorganic insulating material such as silicon oxide and silicon nitride, and can also be formed by alternating the organic insulating material and the inorganic insulating material.

[0094] In the interlayer insulating layer **150** and the gate insulating layer **130**, via holes corresponding to the source region and the drain region of the semiconductor layer **120** are formed by using a third mask.

[0095] A data electrode layer is deposited on the interlayer insulating layer **150**, and the data electrode layer is patterned

by using a fourth mask to form the source electrode **161**, the drain electrode **162**, and the pad electrode **163**.

[0096] The data electrode layer can be formed of the same material as the gate electrode **140**. The data electrode layer can be formed of a Mo/Al/Mo material.

[0097] As described above, when the data electrode layer is formed of a material having low resistance and high corrosion such as Mo/Al/Mo, in order to prevent corrosion in a wet process and a cleaning process which is a subsequent process, a cladding process was performed in the related art.

[0098] However, in the described technology, the first organic insulating layer **170** serves as a passivation layer of the pad electrode **163** and thus the cladding process is not required. Accordingly, since a separate mask used in the cladding process is not required, manufacturing costs can be reduced.

[0099] Referring to FIG. 3B, the first organic insulating layer **170** is stacked on the source electrode **161**, the drain electrode **162**, and the pad electrode **163**.

[0100] In the first organic insulating layer **170**, a via hole etched by using a fifth mask to expose the drain electrode **162** is formed.

[0101] In this case, the fifth mask uses a general one-tone mask, not a two-tone mask such as a half-tone mask, thereby reducing the manufacturing cost.

[0102] That is, in the existing process, in order to electrically connect the bump **320** and the pad electrode **163**, the height of the first organic insulating layer **170** around the pad electrode **163** is decreased, and in order to prevent a parasitic capacitance, the height of the first organic insulating layer **170** on the thin film transistor needs to be increased, and as a result, the half-tone mask is required as the fifth mask.

[0103] However, in the described technology, in order to serve as the passivation layer of the pad electrode **163**, since the etching of the first organic insulating layer **170** therearound is not required in a current step, the half-tone mask is not required. That is, in the forming of the via hole, the portion of the first organic insulating layer **170** covering the pad electrode **163** is maintained.

[0104] As a result, in the described technology, in a step of FIG. 3B, one of the number of masks is reduced when the cladding process is not performed, and the one-tone mask is used as the fifth mask to reduce the manufacturing cost.

[0105] Referring to FIG. 3C, the anode **180** is deposited and patterned.

[0106] Next, the second organic insulating layer **190** is formed and etched on the first organic insulating layer **170** to expose the anode **180** and partition a light emission region.

[0107] Generally, a step of patterning the second organic insulating layer **190** is called a backplane (BP) process.

[0108] A process after the BP process is called an evaporation (EV) process.

[0109] In the EV process, first, a raw plate where a plurality of display panels is formed together is divided, and chamfering and cleaning processes are performed.

[0110] Thereafter, cleaning before depositing, and plasma treatment for oven and interface processing are performed, and the organic emission layer **181** is deposited.

[0111] The organic emission layer **181** is deposited so that one surface contacts the anode **180** through the patterned second organic insulating layer **190**.

[0112] In this case, when the organic emission layer **181** is deposited, the mask is not separately used, or due to other processes, the remaining organic material **181** having the

same configuration as the organic emission layer **181** can be deposited in the seal line region (B-B' line) and the pad electrode region (C-C').

[0113] Since the remaining organic material **181** becomes a problem to form the seal line **500**, the remaining organic material **181** needs to be removed in order to ensure contact force. The removing process can be performed by dry etching, and will be described in detail in FIG. 3D.

[0114] Referring to FIG. 3D, after the deposition process of the organic emission layer **181**, the cathode **182** is deposited and patterned.

[0115] Next, a plasma etching process for removing the remaining organic material **181** is performed by using a plasma mask. A pixel area **600** which does not need to be etched is covered by a blocking portion **700a** of the plasma mask and opened by an opening **700b** of the plasma mask in the seal line region and the pad electrode region. The pixel area **600** can be a display area and the regions outside the pixel area **600** can be a non-display area of the OLED display.

[0116] In the related art, the remaining organic material **181** of the seal line region and the pad electrode region is removed, but in the described technology, the first organic insulating layer **170** to be etched in the pad electrode region (C-C') is etched together. In this case, the pad electrode **163** can be prevented from being damaged by adjusting etch selectivity.

[0117] In this case, the first organic insulating layer **170** needs to be etched so that the pad electrode **163** is sufficiently exposed. Accordingly, electrical connection of the bump **320** and the pad electrode **163** can be ensured.

[0118] The difference between the height of the first organic insulating layer **170** around the pad electrode **163** and the height of the pad electrode **163** need to be sufficiently smaller than the diameter of the conductive ball **310**, and can be generally about 1.5 μm or less. However, depending on the embodiments, the difference can be greater than about 1.5 μm .

[0119] Alternatively, the height of the first organic insulating layer **170** around the pad electrode **163** is etched to be smaller than the height of the pad electrode **163**, and like FIG. 3D, the pad electrode **163** can have a projected shape.

[0120] The drawings referred to in the above and disclosed description of the described technology only illustrate the described technology, and are intended to describe the described technology, not to restrict the meanings or the scope of the described technology claimed in the claims. Therefore, it will be appreciated by those skilled in the art that various modifications and other equivalent embodiment can be made. Accordingly, the true technical scope of the present should be defined by the technical spirit of the appended claims.

[0121] While the inventive technology has been described in connection with what is presently considered to be practical exemplary embodiments, it is to be understood that the invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

What is claimed is:

1. A method of manufacturing an organic light-emitting diode (OLED) display, comprising:

forming a data electrode layer;

patterning the data electrode layer so as to form a source electrode, a drain electrode, and a pad electrode;

forming a first organic insulating layer over the source, drain and pad electrodes;

forming a via hole corresponding to the source electrode or the drain electrode in the first organic insulating layer via a one tone mask;

forming an OLED including i) an anode electrically connected to the source electrode or the drain electrode, ii) an organic emission layer and iii) a cathode; and

etching a first portion of the first organic insulating layer formed over the pad electrode and a second portion of the organic emission layer formed over the pad electrode.

2. The method of claim 1, wherein the forming of the OLED includes:

forming the anode;

forming a second organic insulating layer;

etching a portion of the second organic insulating layer so that the anode is exposed via the etched portion;

forming the organic emission layer over the anode; and

forming the cathode over the organic emission layer and the second organic insulating layer.

3. The method of claim 1, wherein the forming of the via hole includes maintaining the first portion.

4. The method of claim 3, wherein the second portion is formed over a seal line region and the first portion.

5. The method of claim 4, wherein the difference between the height of the first organic insulating layer around the pad electrode and the height of the pad electrode is about 1.5 μm or less.

6. The method of claim 4, wherein the first organic insulating layer is etched such that the height of the first organic insulating layer around the pad electrode is less than the height of the pad electrode.

7. The method of claim 1, wherein the etching includes dry etching.

8. The method of claim 7, wherein the dry etching includes plasma etching.

9. The method of claim 1, further comprising forming a driving integrated circuit over the pad electrode and the first portion.

10. An organic light-emitting diode (OLED) display, comprising:

a substrate including a display area and a non-display area surrounding the display area;

source and drain electrodes formed over the display area;

a pad electrode formed over the non-display area;

a first organic insulating layer formed over the source electrode and contacting the drain and pad electrodes; and

a via hole corresponding to the source or drain electrode formed in the first organic insulating layer.

11. The OLED display of claim 9, wherein the forming of the OLED includes:

an anode electrically connected to the source or drain electrode;

an organic emission layer formed over the anode;

a second organic insulating layer formed over the anode and the first organic insulating layer; and

a cathode formed over the organic emission layer and the second organic insulating layer.

12. The OLED display of claim 9, wherein the second portion is formed over a seal line region located between the display area and the non-display area.

13. The OLED display of claim **9**, wherein the difference between the height of the first organic insulating layer around the pad electrode and the height of the pad electrode is about 1.5 μm or less.

14. The OLED display of claim **9**, wherein the height of the first organic insulating layer around the pad electrode is less than the height of the pad electrode.

15. The OLED display of claim **9**, further comprising a driving integrated circuit formed over the pad electrode and a portion of the first organic insulating layer contacting the pad electrode.

16. A method of manufacturing an organic light-emitting diode (OLED) display, comprising:

forming source, drain and pad electrodes;

forming a first organic insulating layer over the source, drain and pad electrodes;

forming a via hole corresponding to the source or drain electrode in the first organic insulating layer via a one tone mask; and

etching a first portion of the first organic insulating layer formed over the pad electrode and a second portion of the organic emission layer formed over the pad electrode.

17. The method of claim **16**, further comprising forming an OLED, wherein the forming of the OLED includes:

forming an anode;

forming a second organic insulating layer;

etching a portion of the second organic insulating layer so the anode is exposed via the etched portion;

forming an organic emission layer over the anode; and forming a cathode over the organic emission layer and the second organic insulating layer.

18. The method of claim **16**, wherein the forming of the via hole includes maintaining the first portion.

19. The method of claim **18**, wherein the second portion is formed over a seal line region and the first portion.

20. The method of claim **19**, wherein the difference between the height of the first organic insulating layer around the pad electrode and the height of the pad electrode is about 1.5 μm or less.

* * * * *

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	US20160218165A1	公开(公告)日	2016-07-28
申请号	US14/836643	申请日	2015-08-26
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	PARK KYUNG HOON YOU CHUN GI PARK SUN		
发明人	PARK, KYUNG HOON YOU, CHUN GI PARK, SUN		
IPC分类号	H01L27/32 H01L51/56 H01L25/18		
CPC分类号	H01L27/3276 H01L27/3248 H01L2227/323 H01L51/56 H01L25/18 H01L24/16 H01L24/29 H01L24/32 H01L27/3258 H01L2224/16148 H01L2224/2929 H01L2224/293 H01L2224/32145 H01L2224/73204 H01L2224/81424 H01L2224/81447 H01L2224/81466 H01L2224/81471 H01L2224/8148 H01L2224/81903 H01L2224/83851 H01L2251/558 H01L2924/12044 H01L2924/14 H01L2924/00014 H01L2224/16145 H01L2924/00 H01L29/786		
优先权	1020150011566 2015-01-23 KR		
其他公开文献	US10529790		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种有机发光二极管 (OLED) 显示器和制造OLED显示器的方法。在一个方面, 该方法包括形成数据电极层和图案化数据电极层, 以便形成源电极, 漏电极和焊盘电极。该方法还可以包括在源极, 漏极和焊盘电极上方形成第一有机绝缘层, 以及通过单色调掩模在第一有机绝缘层中形成与源电极或漏电极对应的通孔。该方法还可以包括形成 OLED, 该OLED包括电连接到源电极或漏电极的阳极, 有机发光层和阴极, 以及蚀刻在焊盘电极上形成的第一有机绝缘层的第一部分和第二部分。在焊盘电极上形成有机发光层的一部分。

