



US 20170148865A1

(19) **United States**(12) **Patent Application Publication**
Cho et al.(10) **Pub. No.: US 2017/0148865 A1**(43) **Pub. Date: May 25, 2017**(54) **ORGANIC LIGHT-EMITTING DIODE
DISPLAY AND METHOD OF
MANUFACTURING THE SAME**(52) **U.S. Cl.**
CPC **H01L 27/3279** (2013.01); **H01L 27/3246**
(2013.01); **H01L 2227/323** (2013.01)(71) Applicant: **Samsung Display Co., Ltd., Yongin-si**
(KR)(72) Inventors: **Youngjin Cho, Yongin-si (KR);**
Chulkyu Kang, Yongin-si (KR);
Yongjae Kim, Yongin-si (KR)(21) Appl. No.: **15/360,840**(22) Filed: **Nov. 23, 2016**(30) **Foreign Application Priority Data**

Nov. 23, 2015 (KR) 10-2015-0163974

Publication Classification(51) **Int. Cl.**
H01L 27/32 (2006.01)(57) **ABSTRACT**

An organic light-emitting diode (OLED) display and a method of manufacturing the same are disclosed. In one aspect, the display includes a plurality of pixel electrodes positioned over a substrate and separate from each other, a plurality of auxiliary wirings between the pixel electrodes, a pixel-defining layer over the pixel electrodes except for a central portion of the pixel electrodes and at least a portion of each of the auxiliary wirings, an intermediate layer over the pixel-defining layer and having a plurality of openings formed over the portion of each of the auxiliary wirings, and an opposite electrode positioned over the intermediate layer and facing the pixel electrodes, the opposite electrode electrically contacting the auxiliary wirings via the openings. The auxiliary wirings extend in a first direction and separate from each other by a first distance. The openings are aligned in a diagonal direction crossing the first direction.




FIG. 1




FIG. 3




FIG. 4




FIG. 6




FIG. 7




FIG. 8





FIG. 9



**ORGANIC LIGHT-EMITTING DIODE
DISPLAY AND METHOD OF
MANUFACTURING THE SAME**

**CROSS-REFERENCE TO RELATED
APPLICATION**

[0001] This application claims the benefit of Korean Patent Application No. 10-2015-0163974, filed on Nov. 23, 2015, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

[0002] Field

[0003] The described technology generally relates to an organic light-emitting diode display and a method of manufacturing the same.

[0004] Description of the Related Technology

[0005] In general, an organic light-emitting diode (OLED) display includes a matrix of pixels each having an OLED. The OLED includes a pixel electrode, an opposite electrode facing the pixel electrode, and an intermediate layer between the pixel electrode and the opposite electrode and including an emission layer. In such an OLED display, pixel electrodes have island shapes formed by patterning each pixel, and an opposite electrode is provided as one body with respect to the pixels. In typical OLED displays, a voltage (IR) drop occurs in the opposite electrode, and thus, the pixels have unintended brightness differences relative to each other.

**SUMMARY OF CERTAIN INVENTIVE
ASPECTS**

[0006] One inventive aspect relates to an OLED display that is easy to manufacture and has high emission stability and a method of manufacturing the OLED display that is easy to manufacture and has high emission stability, so as to solve problems including the problem described above. However, this is only an example, and does not pose a limitation on the scope of the inventive concept.

[0007] Another aspect is an OLED display that includes: a plurality of pixel electrodes above a substrate and separate from each other; a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction and separate from each other by a first distance; a pixel-defining layer on the pixel electrodes and exposing at least a portion of the pixel electrodes that includes a central portion of the pixel electrodes and at least a portion of the auxiliary wirings; an intermediate layer on the pixel-defining layer and including a plurality of openings that expose at least a portion of each of the auxiliary wirings and are in a diagonal direction crossing the first direction; and an opposite electrode on the intermediate layer and facing the pixel electrodes, the opposite electrode electrically contacting the auxiliary wirings via the openings.

[0008] In the present embodiment, a portion of the intermediate layer that is adjacent to the openings is transformed by strong heat.

[0009] In the present embodiment, the auxiliary wirings includes a first auxiliary wiring and a second auxiliary wiring separate from the first auxiliary wiring by a second distance, the openings may include a first opening that exposes at least a portion of the first auxiliary wiring and a second opening that exposes at least a portion of the second

auxiliary wiring, and the first opening and the second opening may shift in the diagonal direction.

[0010] In the present embodiment, the second distance is identical to the first distance.

[0011] In the present embodiment, the second distance is n times the first distance.

[0012] In the present embodiment, the openings further include a third opening and a fourth opening that are most adjacent to the first opening and the second opening respectively in a second direction perpendicular to the first direction, and a shape obtained by connecting vertices of the first opening, the second opening, the third opening, and the fourth opening to each other may be a parallelogram.

[0013] In the present embodiment, the apparatus further includes an emission layer between the pixel electrodes and the opposite electrode, the emission layer corresponding to each of the pixel electrodes.

[0014] In the present embodiment, the apparatus further includes a plurality of sub-wirings extending in a second direction perpendicular to the first direction.

[0015] In the present embodiment, the auxiliary wirings and the sub-wirings are electrically connected to each other via contact holes.

[0016] Another aspect is a method of manufacturing an OLED display. The method includes: forming a plurality of pixel electrodes above a substrate, the pixel electrodes being separate from each other; forming a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction and separate from each other by a first distance; forming a pixel-defining layer on the pixel electrodes, the pixel-defining layer exposing at least a portion of the pixel electrodes that includes a central portion of the pixel electrodes and at least a portion of the auxiliary wirings; forming an intermediate layer over the entire surface of the substrate, the intermediate layer covering the pixel-defining layer; forming a plurality of openings in the intermediate layer that expose at least a portion of each of the auxiliary wirings and are in a diagonal direction crossing the first direction; and forming, on the intermediate layer, an opposite electrode that faces the pixel electrodes, the opposite electrode electrically contacting the auxiliary wirings via the openings.

[0017] In the present embodiment, the forming of the openings includes forming the openings by irradiating a laser beam on the intermediate layer.

[0018] In the present embodiment, the forming of the auxiliary wirings includes forming a first auxiliary wiring and forming a second auxiliary wiring separate from the first auxiliary wiring by a second distance, the forming of the openings may include forming a first opening that exposes at least a portion of the first auxiliary wiring and forming a second opening that exposes at least a portion of the second auxiliary wiring, and the first opening and the second opening may shift in the diagonal direction.

[0019] In the present embodiment, the second distance is identical to the first distance.

[0020] In the present embodiment, the second distance is n times the first distance.

[0021] In the present embodiment, the forming of the openings includes forming a third opening that is most adjacent to the first opening in a second direction perpendicular to the first direction and forming a fourth opening that is most adjacent to the second opening in the second direction perpendicular to the first direction, and a shape

obtained by connecting vertices of the first opening, the second opening, the third opening, and the fourth opening to each other may be a parallelogram.

[0022] In the present embodiment, the method further includes forming an emission layer between the pixel electrodes and the opposite electrode, the emission layer corresponding to each of the pixel electrodes.

[0023] These general and specific embodiments may be implemented by using a system, a method, a computer program, or a combination thereof.

[0024] An organic light-emitting diode (OLED) display comprising: a substrate; a plurality of pixel electrodes positioned over the substrate and separate from each other; a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction and separate from each other by a first distance; a pixel-defining layer over the pixel electrodes except for a central portion of the pixel electrodes and at least a portion of each of the auxiliary wirings; an intermediate layer over the pixel-defining layer and having a plurality of openings formed over the portion of each of the auxiliary wirings, wherein the openings are aligned in a diagonal direction crossing the first direction; and an opposite electrode positioned over the intermediate layer and facing the pixel electrodes, the opposite electrode electrically contacting the auxiliary wirings via the openings.

[0025] In the above display, a portion of the intermediate layer that is adjacent to the openings is configured to be transformed by heat.

[0026] In the above display, the auxiliary wirings comprise a first auxiliary wiring and a second auxiliary wiring separate from the first auxiliary wiring by a second distance, wherein the openings comprise a first opening formed over at least a portion of the first auxiliary wiring and a second opening formed over at least a portion of the second auxiliary wiring.

[0027] In the above display, the second distance is the same as the first distance.

[0028] In the above display, the second distance is n times longer than the first distance, and wherein n is a natural number.

[0029] In the above display, the openings further comprise a third opening and a fourth opening that are respectively located closest to the first opening and the second opening in a second direction crossing the first direction, wherein the first to fourth openings have a parallelogram shape.

[0030] The above display further comprises an emission layer between the pixel electrodes and the opposite electrode.

[0031] The above display further comprises a plurality of sub-wirings extending in a second direction crossing the first direction.

[0032] In the above display, the auxiliary wirings and the sub-wirings are electrically connected to each other via a plurality of contact holes.

[0033] Another aspect is a method of manufacturing an organic light-emitting diode (OLED) display, the method comprising: forming a plurality of pixel electrodes over a substrate, the pixel electrodes being separate from each other; forming a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction and separate from each other by a first distance; forming a pixel-defining layer over the pixel electrodes except for a central portion of the pixel electrodes and at

least a portion of each of the auxiliary wirings; forming an intermediate layer over the entire surface of the substrate, the intermediate layer covering the pixel-defining layer; forming a plurality of openings in the intermediate layer that respectively expose at least a portion of each of the auxiliary wirings, wherein the openings are aligned in a diagonal direction crossing the first direction; and forming an opposite electrode that faces the pixel electrodes over the intermediate layer, the opposite electrode electrically contacting the auxiliary wirings via the openings.

[0034] In the above method, the forming of the openings comprises irradiating a laser beam on the intermediate layer.

[0035] In the above method, the forming of the auxiliary wirings comprises forming a first auxiliary wiring and forming a second auxiliary wiring separate from the first auxiliary wiring by a second distance, wherein the forming of the openings comprises forming a first opening that exposes at least a portion of the first auxiliary wiring and forming a second opening that exposes at least a portion of the second auxiliary wiring.

[0036] In the above method, the second distance is to the same as the first distance.

[0037] In the above method, the second distance is n times longer the first distance, and wherein n is a natural number.

[0038] In the above method, the forming of the openings comprises i) forming a third opening that is located closest to the first opening in a second direction crossing the first direction and ii) forming a fourth opening that is located closest to the second opening in the second direction and wherein the first to fourth openings have a parallelogram shape.

[0039] The above method further comprises forming an emission layer between the pixel electrodes and the opposite electrode.

[0040] Another aspect is an organic light-emitting diode (OLED) display comprising: a substrate; a plurality of pixel electrodes formed over the substrate; a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction; an intermediate layer formed over the auxiliary wirings and having a plurality of openings formed therethrough; and an opposite electrode formed over the intermediate layer and electrically connected to the auxiliary wirings via the openings.

[0041] In the above display, the auxiliary wirings include first and second auxiliary wirings adjacent to each other, wherein the openings include first and second openings respectively formed over the first and second auxiliary wirings, and wherein the first and second openings are not aligned in a second direction perpendicular to the first direction.

[0042] In the above display, the auxiliary wirings further include third and fourth auxiliary wirings adjacent to each other, wherein the third and fourth auxiliary wirings are respectively separated from the first and second auxiliary wirings by at least two interposed auxiliary wirings, wherein the openings further include third and fourth openings respectively formed over the third and fourth auxiliary wirings, and wherein the third and fourth openings are not aligned in the second direction.

[0043] The above display further comprises a metal layer interposed between and electrically connecting the auxiliary wirings and the opposite electrode.

BRIEF DESCRIPTION OF THE DRAWINGS

[0044] FIG. 1 is a schematic plan view of an OLED display according to an embodiment.

[0045] FIG. 2 is an enlarged view of part II of FIG. 1.

[0046] FIG. 3 is a schematic cross-sectional view taken along line III-III of FIG. 2.

[0047] FIG. 4 is a schematic plan view of an OLED display according to an embodiment.

[0048] FIG. 5 is an enlarged view of part V of FIG. 4.

[0049] FIGS. 6, 7, 8 and 9 are schematic cross-sectional views of a process of manufacturing an OLED display according to an embodiment.

DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

[0050] As the described technology allows for various changes and numerous embodiments, exemplary embodiments will be illustrated in the drawings and described in detail in the written description. Advantages and features of one or more exemplary embodiments and methods of accomplishing the same may be understood more readily by reference to the following detailed description of the one or more exemplary embodiments and the accompanying drawings. The described technology may, however, be embodied in many different forms and should not be construed as being limited to the one or more exemplary embodiments set forth herein.

[0051] Reference will now be made in detail to exemplary embodiments, examples of which are illustrated in the accompanying drawings. Like reference numerals in the drawings denote like elements, and a repeated description thereof will be omitted. The term “and/or” used herein includes any and all combinations of one or more of the associated listed items.

[0052] While such terms as “first” and “second” may be used to describe various components, such components must not be limited to the above terms. The above terms are used only to distinguish one component from another. The singular forms “a,” “an,” and “the” used herein are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0053] It will be understood that the terms such as “include,” “comprise,” and “have” used herein specify the presence of stated features or components, but do not preclude the presence or addition of one or more other features or components.

[0054] Sizes of components in the drawings may be exaggerated for convenience of explanation. In other words, since sizes and thicknesses of components in the drawings are arbitrarily illustrated for convenience of explanation, exemplary embodiments are not limited thereto.

[0055] The x-axis, the y-axis and the z-axis are not limited to three axes of the rectangular coordinate system and may be interpreted in a broader sense. For example, the x-axis, the y-axis, and the z-axis may be perpendicular to one another or may represent different directions that are not perpendicular to one another.

[0056] When an embodiment may be implemented differently, a specific process order may be performed differently from the described order. For example, two consecutively described processes may be performed substantially at the same time or performed in an order opposite to the described order. In this disclosure, the term “substantially” includes

the meanings of completely, almost completely or to any significant degree under some applications and in accordance with those skilled in the art. Moreover, “formed, disposed or positioned over” can also mean “formed, disposed or positioned on.” The term “connected” includes an electrical connection.

[0057] FIG. 1 is a schematic plan view of an OLED display 1 according to an embodiment. FIG. 2 is an enlarged view of part II of FIG. 1. FIG. 3 is a schematic cross-sectional view taken along line III-III of FIG. 2.

[0058] Referring to FIGS. 1 to 3, the OLED display 1 includes a plurality of pixel electrodes 210 above a substrate 100, a plurality of auxiliary wirings 160a between the pixel electrodes 210, a pixel-defining layer 180 on the pixel electrodes 210, an intermediate layer 221 and 222 including a plurality of openings 230a that expose at least a portion of a plurality of auxiliary wirings 160a1 to 160an, and an opposite electrode 230 electrically contacting the auxiliary wirings 160a1 to 160an via the openings 230a.

[0059] The substrate 100 may be formed of one or more materials, for example, glass, metal, or plastic such as polyethylene terephthalate (PET), polyethylene naphthalate (PEN), or polyimide. The substrate 100 may include a display area DA where a plurality of pixels is arranged and a peripheral area PA surrounding the display area DA.

[0060] The pixel electrodes 210 may be in the display area DA. The pixel electrodes 210 may be directly on the substrate 100, or over the substrate 100 with various layers including a thin film transistor TFT between the substrate 100 and the pixel electrodes 210. The pixel electrodes 210 may be separate from each other and arranged in a certain direction. That is, as illustrated in FIG. 2, the pixel electrodes 210 may be arranged in x and y directions to form a matrix.

[0061] The auxiliary wirings 160a1 to 160an may be between the pixel electrodes 210. The auxiliary wirings 160a1 to 160an are electrically connected to the opposite electrode 230, which will be described below, and thus, decrease an IR drop of the opposite electrode 230. The auxiliary wirings 160a may extend in a first direction (y-axis direction) and may be separate from each other by a first distance d. The auxiliary wirings 160a1 to 160an may be on the same layer as the pixel electrodes 210 or may be on the same layer as one of the electrodes constituting the thin film transistor TFT. In the present embodiment, as illustrated in FIG. 3, the auxiliary wirings 160a may be on the same layer as a source electrode 160s or a drain electrode 160d of the thin film transistor TFT or may be formed of the same material as the source electrode 160s or the drain electrode 160d of the thin film transistor TFT.

[0062] The pixel-defining layer 180 may be on the pixel electrodes 210. The pixel-defining layer 180 may expose at least a portion of the pixel electrodes 210 that includes a central portion of the pixel electrodes 210 and at least a portion of the auxiliary wirings 160a1 to 160an. The pixel-defining layer 180 may include an opening that exposes at least a portion of the pixel electrodes 210 that includes a central portion of the pixel electrodes 210, that is, an opening that corresponds to each sub-pixel, and thus may define a pixel. Also, the pixel-defining layer 180 may increase a distance between an end portion of the pixel electrodes 210 and the opposite electrode 230 that will be

above the pixel electrodes **210** later and thus may prevent an arc or the like from occurring in the end portion of the pixel electrodes **210**.

[0063] The intermediate layer **221** and **222** and an emission layer **223** may be on the pixel-defining layer **180**. The intermediate layer **221** and **222** may have a single-layered or multi-layered structure, and as illustrated in FIG. 3, may be disposed over the entire surface of the substrate **100**. That is, unlike the emission layer **223**, the intermediate layer **221** and **222** may entirely cover the top surface of the pixel-defining layer **180**. The intermediate layer **221** and **222** may include one or more selected from a hole injection layer (HIL), a hole transport layer (HTL), an electron transport layer (ETL), and an electron injection layer (EIL).

[0064] The intermediate layer **221** and **222** may include a first intermediate layer **221** and a second intermediate layer **222**. In this regard, the first intermediate layer **221** may include an opening **221'**, and the second intermediate layer **222** may include an opening **222'**. That is, the openings **230a** illustrated in FIG. 2 may each include the opening **221'** in the first intermediate layer **221** and the opening **222'** in the second intermediate layer **222**.

[0065] The first intermediate layer **221** may have a single-layered or multi-layered structure. For example, when the first intermediate layer **221** is formed of a polymer, the first intermediate layer **221** may include a single HTL, the HTL including poly-(3,4)-ethylene-dihydroxy thiophene (PEDOT) or polyaniline (PANI). When the first intermediate layer **221** is formed of a low molecular material, the first intermediate layer **221** may include an HIL and an HTL.

[0066] The second intermediate layer **222** may be optionally formed. For example, when the first intermediate layer **221** and the emission layer **223** each include a polymer, the second intermediate layer **222** may be omitted. When the first intermediate layer **221** and the emission layer **223** each include a low molecular material, the second intermediate layer **222** may be formed to obtain an OLED having excellent characteristics. In this case, the second intermediate layer **222** may have a single-layered or multi-layered structure and may include an ETL and/or an EIL.

[0067] The intermediate layer **221** and **222** may include the openings **230a** exposing at least a portion of the auxiliary wirings **160a1** to **160an**. The openings **230a** may be in a diagonal direction (direction A) crossing the first direction (y-axis direction) in which the auxiliary wirings **160a1** to **160an** extend. Although it is illustrated in FIG. 2 that the openings **230a** are provided for every five pixel electrodes **210** each in width and length, the disclosure is not limited thereto. A position in which the openings **230a** are repeatedly formed may be changed depending on the size of a display area (active area).

[0068] Referring to FIG. 2 again, the auxiliary wirings **160a1** to **160an** include a first auxiliary wiring **160a1** and a second auxiliary wiring **160a2** adjacent to the first auxiliary wiring **160a1**. The second auxiliary wiring **160a2** may be separate from the first auxiliary wiring **160a1** by a second distance, and in this regard, the second distance may be identical to the first distance *d* or may be *n* times the first distance *d*. That is, when the second distance is identical to the first distance *d*, the second auxiliary wiring **160a2** may be right next to the first auxiliary wiring **160a1**. When the second distance is *n* times the first distance *d*, the second auxiliary wiring **160a2** may not be right next to the first auxiliary wiring **160a1**.

[0069] The openings **230a** may include a first opening **230a1** and a second opening **230a2**. The first opening **230a1** may expose at least a portion of the first auxiliary wiring **160a1**, and the second opening **230a2** may expose at least a portion of the second auxiliary wiring **160a2**. In this regard, the first opening **230a1** and the second opening **230a2** may be shifted in the diagonal direction (direction A). Accordingly, the first opening **230a1** and the second opening **230a2** shifted from the first opening **230a1** by a predetermined distance may be above different auxiliary wirings from each other, and as such a pattern is repeated, current may be prevented from concentrating into a certain auxiliary wiring.

[0070] The openings **230a** may further include a third opening **230a3** and a fourth opening **230a4** in addition to the first opening **230a1** and the second opening **230a2**. The third opening **230a3** may be most adjacent to the first opening **230a1** in a second direction (x-axis direction) perpendicular to the first direction (y-axis direction). Similarly, the fourth opening **230a4** may be most adjacent to the second opening **230a2** in the second direction (x-axis direction) perpendicular to the first direction (y-axis direction). In this regard, a shape obtained by connecting respective vertices of the first opening **230a1**, the second opening **230a2**, the third opening **230a3**, and the fourth opening **230a4** may be a parallelogram. That is, when the first opening **230a1** and the third opening **230a3** are parallel to each other in the second direction (x-axis direction), and the second opening **230a2** and the fourth opening **230a4** are also parallel to each other in the second direction (x-axis direction), the second opening **230a2** is shifted from the first opening **230a1** by a predetermined distance in the diagonal direction (direction A), and the fourth opening **230a4** is shifted from the third opening **230a3** by a predetermined distance in the diagonal direction (direction A).

[0071] When the first opening **230a1** and the second opening **230a2** are not in the diagonal direction (direction A) but consecutively in the first direction (y-axis direction) along a certain auxiliary wiring, for example, the first auxiliary wiring **160a1**, current concentrates into the first auxiliary wiring **160a1**. This degrades the performance of an auxiliary wiring formed to lower the IR drop of the opposite electrode **230**. Accordingly, in the OLED display **1**, when the openings **230a** via which the auxiliary wirings **160a1** to **160an** and the opposite electrode **230** may electrically contact each other are formed, the openings **230a** may be shifted as much as a predetermined distance in the diagonal direction (direction A) and thus may be above different auxiliary wirings from each other. Accordingly, current may be prevented from concentrating into a certain auxiliary wiring.

[0072] Next, a cross-sectional structure of the OLED display **1** will be mainly described in the following with reference to FIG. 3.

[0073] The thin film transistor TFT and a capacitor CAP may be disposed above the substrate **100**, and an OLED electrically connected to the thin film transistor TFT may be placed above the substrate **100**. The thin film transistor TFT includes a semiconductor layer **120** formed of amorphous silicon, polycrystalline silicon, or an organic semiconductor material, a gate electrode **140**, the source electrode **160s**, and the drain electrode **160d**. A general structure of the thin film transistor TFT will now be described.

[0074] A buffer layer **110** formed of silicon oxide, silicon nitride, or the like may be disposed on the substrate **100** to

planarize a surface of the substrate **100** or to prevent impurities or the like from penetrating into the semiconductor layer **120** of the thin film transistor TFT, and the semiconductor layer **120** may be on the buffer layer **110**.

[0075] The gate electrode **140** may be disposed above the semiconductor layer **120**, and according to a signal applied to the gate electrode **140**, the source electrode **160s** and the drain electrode **160d** may be electrically connected to each other. The gate electrode **140** may include a single layer or layers including, for example, one or more materials selected from aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), molybdenum (Mo), titanium (Ti), tungsten (W), and copper (Cu) by taking into account factors such as adhesiveness to an adjacent layer, surface smoothness of a stacked layer, and processability.

[0076] In this regard, in order to secure insulation between the semiconductor layer **120** and the gate electrode **140**, a gate insulation layer **130** including silicon oxide and/or silicon nitride may be between the semiconductor layer **120** and the gate electrode **140**.

[0077] An interlayer insulation layer **150** may be on the gate electrode **140** and may include a single layer or layers formed of a material such as silicon oxide or silicon nitride.

[0078] The source electrode **160s** and the drain electrode **160d** may be on the interlayer insulation layer **150**. The source electrode **160s** and the drain electrode **160d** may each be electrically connected to the semiconductor layer **120** via contact holes in the interlayer insulation layer **150** and the gate insulation layer **130**. The source electrode **160s** and the drain electrode **160d** may include a single layer or layers including, for example, one or more materials selected from aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), molybdenum (Mo), titanium (Ti), tungsten (W), and copper (Cu) by taking into account a factor such as conductivity.

[0079] Although not illustrated, a protective layer (not shown) may be provided to cover the thin film transistor TFT for protection of the thin film transistor TFT having such a structure. The protective layer may be formed of an inorganic material, for example, silicon oxide, silicon nitride, or silicon oxynitride.

[0080] A planarization layer **170** may be disposed above the substrate **100**. When an OLED is above the thin film transistor TFT, the planarization layer **170** substantially planarizes the top surface of the thin film transistor TFT and protects the thin film transistor TFT and various devices. The planarization layer **170** may be formed of, for example, an acrylic organic material or benzocyclobutene (BCB). In this regard, as illustrated in FIG. 3, the buffer layer **110**, the gate insulation layer **130**, the interlayer insulation layer **150**, and the first planarization layer **170** may be over the entire surface of the substrate **100**.

[0081] The pixel-defining layer **180** may be disposed above the thin film transistor TFT. The pixel-defining layer **180** may be on the planarization layer **170** and may have an opening. The pixel-defining layer **180** defines a pixel area above the substrate **100**. The pixel-defining layer **180** may be, for example, an organic insulation layer. The organic insulation layer may include an acrylic polymer such as poly(methyl methacrylate) (PMMA), polystyrene (PS), a polymer derivative containing a phenol group, an imide-

based polymer, an aryl ether-based polymer, an amide-based polymer, a fluorine-based polymer, a p-xylylene-based polymer, a vinyl alcohol-based polymer, and a mixture thereof.

[0082] The OLED may be on the pixel-defining layer **180**. The OLED may include a pixel electrode **210**, the emission layer **223**, and the opposite electrode **230**.

[0083] The pixel electrode **210** may be a (semi)transparent electrode or a reflective electrode. When the pixel electrode **210** is a (semi)transparent electrode, the pixel electrode **210** may be formed of, for example, indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In₂O₃), indium gallium oxide (IGO), or aluminum zinc oxide (AZO). When the pixel electrode **210** is a reflective electrode, the pixel electrode **210** may include a reflective layer formed of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, and a compound thereof, and a layer including ITO, IZO, ZnO, In₂O₃, IGO, or AZO. However, the disclosure is not limited thereto, and the pixel electrode **210** may include various materials. Also, a structure of the pixel electrode **210** may differ, such as a single layer or layers.

[0084] The emission layer **223** may be in the pixel area defined by the pixel-defining layer **180** and may be in the middle of the first intermediate layer **221** and the second intermediate layer **222**. The first intermediate layer **221** may include an HIL and/or an HTL between the emission layer **223** and the pixel electrode **210**, and the second intermediate layer **222** may include an ETL and/or an EIL between the emission layer **223** and the opposite electrode **230**. However, the first and second intermediate layers **221** and **222** are not limited thereto and may have various structures.

[0085] The opposite electrode **230** covering the first and second intermediate layers **221** and **222** as well as the emission layer **223** and facing the pixel electrode **210** may be disposed over the entire surface of the substrate **100**. The opposite electrode **230** may be a (semi)transparent electrode or a reflective electrode.

[0086] When the opposite electrode **230** is a (semi)transparent electrode, the opposite electrode **230** may include a layer including metal having a low work function, that is, Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, and a compound thereof, and a (semi)transparent conductive layer including ITO, IZO, ZnO, In₂O₃, or the like. When the opposite electrode **230** is a reflective electrode, the opposite electrode **230** may include a layer including Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, and a compound thereof. However, a structure and a material of the opposite electrode **230** are not limited thereto and may vary.

[0087] Referring to FIG. 3, an auxiliary wiring **160a** may be on the same layer as the source electrode **160s** and the drain electrode **160d**. In this case, the auxiliary wiring **160a** does not necessarily have to be on the same layer as the source electrode **160s** or the drain electrode **160d**. However, when the auxiliary wiring **160a** is on the same layer as the source electrode **160s** or the drain electrode **160d** relatively thicker than other conductive layers, it may be easy to decrease resistance applied to the auxiliary wiring **160a**.

[0088] The opposite electrode **230** may electrically contact the auxiliary wiring **160a** via an opening **230a**. Referring to FIG. 3, a material layer **210a** may be further disposed between a portion of the opposite electrode **230** that corresponds to the opening **230a** and the auxiliary wiring **160a**. The material layer **210a** may include the same material as the pixel electrode **210** and may be on the same layer as the pixel electrode **210**.

[0089] The opposite electrode **230** may electrically contact the auxiliary wiring **160a** via the opening **230a** in the intermediate layer **221** and **222**. The opening **230a** may be formed by irradiating a laser beam on the intermediate layer **221** and **222**, and accordingly, a portion of the intermediate layer **221** and **222** that is adjacent to the opening **230a** in the intermediate layer **221** and **222** may be transformed by strong heat. For example, after the intermediate layer **221** and **222** is formed over the entire surface of the pixel-defining layer **180**, a laser beam may be irradiated around the auxiliary wiring **160a** having at least a portion exposed by the pixel-defining layer **180**, and thus, the opening **230a** may be formed.

[0090] FIG. 4 is a schematic plan view of an OLED display **2** according to an embodiment. FIG. 5 is an enlarged view of part V of FIG. 4.

[0091] Referring to FIGS. 4 and 5, the OLED display **2** may further include a plurality of sub-wirings **140a** disposed perpendicular to the auxiliary wirings **160a1** to **160an**. The OLED display **2** in the present embodiment is identical to the OLED display **1** of FIGS. 1 to 3 except that the sub-wirings **140a** are additionally provided. Accordingly, the sub-wirings **140a** will be mainly described hereinafter, and repeated descriptions thereof will be omitted.

[0092] The OLED display **2** may include the sub-wirings **140a**. As illustrated in FIG. 5, the sub-wirings **140a** may extend in the second direction (x-axis direction) perpendicular to the first direction (y-axis direction). That is, the sub-wirings **140a** may cross the auxiliary wirings **160a** and thus, may form a mesh shape. The sub-wirings **140a** may be electrically connected to the auxiliary wirings **160a** via contact holes (not shown) in a position where the sub-wirings **140a** cross the auxiliary wirings **160a**. Due to the sub-wirings **140a**, the amount of current passing through the auxiliary wirings **160a** may be easily dispersed. Although not illustrated, the sub-wirings **140a** may be on the same layer as one of the electrodes included in the thin film transistor TFT. For example, in the previous embodiment of FIG. 3, the sub-wirings **140a** may be on the same layer as the gate electrode **140**, and accordingly, the sub-wirings **140a** may be formed of the same material as the gate electrode **140**.

[0093] Although an OLED display according to one or more embodiments has been mainly described above, the disclosure is not limited thereto. For example, a method of manufacturing an OLED display, according to one or more embodiments, is within the scope of the described technology.

[0094] FIGS. 6 to 9 are schematic cross-sectional views of a process of manufacturing an OLED display according to an embodiment. Although a plurality of pixels have to be disposed in the display area DA of the substrate **100** in order to manufacture the OLED display according to an embodiment, the manufacturing process will be described with focus on a cross-sectional structure of one pixel with reference to FIGS. 6 to 9.

[0095] Referring to FIGS. 2 and 6, the pixel electrodes **210** that are separate from each other are disposed above the substrate **100**. Although it is illustrated in FIG. 6 that the pixel electrode **210** is disposed on the planarization layer **170**, the disclosure is not limited thereto.

[0096] Various layers may be disposed before the pixel electrode **210** is disposed. It is illustrated in FIG. 6 that, after the thin film transistor TFT and the capacitor CAP are

disposed above the substrate **100**, and the planarization layer **170** covering the thin film transistor TFT and the capacitor CAP is disposed thereon, the pixel electrode **210** is disposed on the planarization layer **170**.

[0097] In this regard, before the pixel electrodes **210** are disposed, as illustrated in FIG. 2, the auxiliary wirings **160a1** to **160an** may be disposed between the pixel electrodes **210** and be separate from each other by a predetermined distance. The auxiliary wirings **160a1** to **160an** may extend in the first direction (y-axis direction).

[0098] Referring to FIG. 6, the auxiliary wiring **160a** is disposed on the same layer as the source electrode **160s** and the drain electrode **160d** of the thin film transistor TFT and is formed of the same material as the source electrode **160s** and the drain electrode **160d**. However, the disclosure is not limited thereto. Any conductive layer may be used to form the auxiliary wiring **160a**, and the auxiliary wiring **160a** may be disposed on the same layer as the gate electrode **140** or the pixel electrode **210**.

[0099] Referring to FIG. 6 with FIG. 2, the formation of the auxiliary wirings **160a1** to **160an** includes formation of the first auxiliary wiring **160a1** and the second auxiliary wiring **160a2** separate from each other by the second distance.

[0100] After the auxiliary wiring **160a** is disposed, the planarization layer **170** may be disposed on the auxiliary wiring **160a**. In this regard, the planarization layer **170** may expose at least a portion of the auxiliary wiring **160a**, and the exposed at least a portion of the auxiliary wiring **160a** may electrically contact the opposite electrode **230**. The conductive material layer **210a** may be further disposed on the portion of the auxiliary wiring **160a** that is exposed by the planarization layer **170**. The material layer **210a** of FIG. 6 may be disposed on the same layer as the pixel electrode **210**.

[0101] Afterwards, referring to FIG. 6, the pixel-defining layer **180** is disposed on the pixel electrode **210** so as to expose at least a portion of the pixel electrode **210** that includes a central portion of the pixel electrode **210**. In this regard, the pixel-defining layer **180** may expose at least a portion of the material layer **210a**. Although, in the present embodiment, the material layer **210a** is disposed on the auxiliary wiring **160a**, and the pixel-defining layer **180** exposes at least a portion of the material layer **210a**, the disclosure is not limited thereto. The material layer **210a** may not be disposed on the auxiliary wiring **160a**, and in this case, the pixel-defining layer **180** may directly expose at least a portion of the auxiliary wiring **160a**.

[0102] Afterwards, the intermediate layer **221** and **222** and the emission layer **223** may be over the entire surface of the substrate **100** to cover the pixel-defining layer **180**. Although not illustrated, the intermediate layer **221** and **222** may be integrally formed with each other on a plurality of pixels. For example, the first intermediate layer **221** is formed to cover the pixel-defining layer **180** and the pixel electrode **210**, and then, the emission layer **223** may be formed so as to correspond to the pixel electrode **210**. Afterwards, the second intermediate layer **222** may be formed to cover the emission layer **223** and the first intermediate layer **221**.

[0103] For example, the first intermediate layer **221** includes an HIL and/or an HTL, and the second intermediate layer **222** may include an ETL and/or an EIL.

[0104] Afterwards, as illustrated in FIG. 8, a portion of the first intermediate layer **221** that is above the auxiliary wiring

160a and a portion of the second intermediate layer **222** that is above the auxiliary wiring **160a** are removed to form the opening **221'** in the first intermediate layer **221** and the opening **222'** in the second intermediate layer **222**, and thus, at least a portion of the auxiliary wiring **160a** is exposed. For this, as illustrated in FIG. 7, a laser beam may be irradiated on the second intermediate layer **222**, and thus, the opening **221'** and the opening **222'** may be respectively formed in the first intermediate layer **221** and the second intermediate layer **222** simultaneously (or concurrently).

[0105] The openings **230a** formed by using such a method may be, as illustrated in FIG. 2, in the diagonal direction (direction A) crossing the first direction (y-axis direction) in which the auxiliary wirings **160a1** to **160an** extend. The openings **230a** may be shifted as much as a predetermined distance in the diagonal direction (direction A).

[0106] The formation of the openings **230a** may include formation of the first opening **230a1** exposing at least a portion of the first auxiliary wiring **160a1** and the second opening **230a2** exposing at least a portion of the second auxiliary wiring **160a2**. In this case, the second opening **230a2** may be shifted from the first opening **230a1** by a predetermined distance. In this regard, since the first auxiliary wiring **160a1** and the second auxiliary wiring **160a2** are separate from each other by the second distance, the second opening **230a2** may be shifted from the first opening **230a1** by the second distance. In this regard, the second distance may be the same as the first distance d or may be n times the first distance d . That is, when the second distance is the same as the first distance d , the second auxiliary wiring **160a2** may be right next to the first auxiliary wiring **160a1**. When the second distance is n times the first distance d , the second auxiliary wiring **160a2** may not be right next to the first auxiliary wiring **160a1**.

[0107] Referring to FIG. 2, the formation of the openings **230a** may further include formation of the third opening **230a3** and the fourth opening **230a4** in addition to the first opening **230a1** and the second opening **230a2**. The third opening **230a3** may be most adjacent to the first opening **230a1** in the second direction (x-axis direction) perpendicular to the first direction (y-axis direction). Similarly, the fourth opening **230a4** may be most adjacent to the second opening **230a2** in the second direction (x-axis direction) perpendicular to the first direction (y-axis direction). In this regard, a shape obtained by connecting respective vertices of the first opening **230a1**, the second opening **230a2**, the third opening **230a3**, and the fourth opening **230a4** may be a parallelogram. That is, when the first opening **230a1** and the third opening **230a3** are parallel to each other in the second direction (x-axis direction), and the second opening **230a2** and the fourth opening **230a4** are also parallel to each other in the second direction (x-axis direction), the second opening **230a2** is shifted from the first opening **230a1** by a predetermined distance in the diagonal direction (direction A), and the fourth opening **230a4** is shifted from the third opening **230a3** by a predetermined distance in the diagonal direction (direction A).

[0108] When the first opening **230a1** and the second opening **230a2** are not in the diagonal direction (direction A) but consecutively in the first direction (y-axis direction) along a certain auxiliary wiring, for example, the first auxiliary wiring **160a1**, current concentrates into the first auxiliary wiring **160a1**. This degrades the performance of an auxiliary wiring formed to lower the IR drop of the opposite

electrode **230**. Accordingly, in the OLED display **1** according to an embodiment, when the openings **230a** via which the auxiliary wirings **160a1** to **160an** and the opposite electrode **230** may electrically contact each other are formed, the openings **230a** may be shifted as much as a predetermined distance in the diagonal direction (direction A) and thus may be above different auxiliary wirings from each other. Accordingly, current may be prevented from concentrating into a certain auxiliary wiring.

[0109] Next, as illustrated in FIG. 9, the opposite electrode **230** corresponding to the pixel electrode **210** and the auxiliary wiring **160a** is formed so as to electrically contact the auxiliary wiring **160a** via the opening **230a**. The opposite electrode **230** may be formed as one body with respect to the plurality of pixels to cover a display area (active area). In this regard, the display area may refer to any area of the entire OLED display, from which light may be emitted. For example, the display area may refer to all areas except an edge of the OLED display, where a controller or the like is disposed. When there is no dead area over the entire surface of the OLED display, the entire surface of the OLED display may be referred to as the display area. The opposite electrode **230** may contact an electrode power supply line outside of the display area and receive an electrical signal from the electrode power supply line.

[0110] According to at least one of the disclosed embodiments, an OLED display that is easy to manufacture and has high emission stability and a method of manufacturing the OLED display may be provided. However, such an effect does not pose a limitation on the scope of the described technology.

[0111] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0112] While the inventive technology has been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims.

What is claimed is:

1. An organic light-emitting diode (OLED) display comprising:

- a substrate;
- a plurality of pixel electrodes positioned over the substrate and separate from each other;
- a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction and separate from each other by a first distance;
- a pixel-defining layer over the pixel electrodes except for a central portion of the pixel electrodes and at least a portion of each of the auxiliary wirings;
- an intermediate layer over the pixel-defining layer and having a plurality of openings formed over the portion of each of the auxiliary wirings, wherein the openings are aligned in a diagonal direction crossing the first direction; and
- an opposite electrode positioned over the intermediate layer and facing the pixel electrodes, the opposite electrode electrically contacting the auxiliary wirings via the openings.

2. The display of claim 1, wherein a portion of the intermediate layer that is adjacent to the openings is configured to be transformed by heat.

3. The display of claim 1, wherein the auxiliary wirings comprise a first auxiliary wiring and a second auxiliary wiring separate from the first auxiliary wiring by a second distance, and wherein the openings comprise a first opening formed over at least a portion of the first auxiliary wiring and a second opening formed over at least a portion of the second auxiliary wiring.

4. The display of claim 3, wherein the second distance is the same as the first distance.

5. The display of claim 3, wherein the second distance is n times longer than the first distance, and wherein n is a natural number.

6. The display of claim 3, wherein the openings further comprise a third opening and a fourth opening that are respectively located closest to the first opening and the second opening in a second direction crossing the first direction, and wherein the first to fourth openings have a parallelogram shape.

7. The display of claim 1, further comprising an emission layer between the pixel electrodes and the opposite electrode.

8. The display of claim 1, further comprising a plurality of sub-wirings extending in a second direction crossing the first direction.

9. The display of claim 8, wherein the auxiliary wirings and the sub-wirings are electrically connected to each other via a plurality of contact holes.

10. A method of manufacturing an organic light-emitting diode (OLED) display, the method comprising:

forming a plurality of pixel electrodes over a substrate, the pixel electrodes being separate from each other;

forming a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction and separate from each other by a first distance;

forming a pixel-defining layer over the pixel electrodes except for a central portion of the pixel electrodes and at least a portion of each of the auxiliary wirings;

forming an intermediate layer over the entire surface of the substrate, the intermediate layer covering the pixel-defining layer;

forming a plurality of openings in the intermediate layer that respectively expose at least a portion of each of the auxiliary wirings, wherein the openings are aligned in a diagonal direction crossing the first direction; and

forming an opposite electrode that faces the pixel electrodes over the intermediate layer, the opposite electrode electrically contacting the auxiliary wirings via the openings.

11. The method of claim 10, wherein the forming of the openings comprises irradiating a laser beam on the intermediate layer.

12. The method of claim 10, wherein the forming of the auxiliary wirings comprises forming a first auxiliary wiring and forming a second auxiliary wiring separate from the first auxiliary wiring by a second distance, and wherein the forming of the openings comprises forming a first opening that exposes at least a portion of the first auxiliary wiring and forming a second opening that exposes at least a portion of the second auxiliary wiring.

13. The method of claim 12, wherein the second distance is to the same as the first distance.

14. The method of claim 12, wherein the second distance is n times longer the first distance, and wherein n is a natural number.

15. The method of claim 12, wherein the forming of the openings comprises i) forming a third opening that is located closest to the first opening in a second direction crossing the first direction and ii) forming a fourth opening that is located closest to the second opening in the second direction and wherein the first to fourth openings have a parallelogram shape.

16. The method of claim 10, further comprising forming an emission layer between the pixel electrodes and the opposite electrode.

17. An organic light-emitting diode (OLED) display comprising:

a substrate;

a plurality of pixel electrodes formed over the substrate;

a plurality of auxiliary wirings between the pixel electrodes, the auxiliary wirings extending in a first direction;

an intermediate layer formed over the auxiliary wirings and having a plurality of openings formed there-through; and

an opposite electrode formed over the intermediate layer and electrically connected to the auxiliary wirings via the openings.

18. The display of claim 17, wherein the auxiliary wirings include first and second auxiliary wirings adjacent to each other, wherein the openings include first and second openings respectively formed over the first and second auxiliary wirings, and wherein the first and second openings are not aligned in a second direction perpendicular to the first direction.

19. The display of claim 18, wherein the auxiliary wirings further include third and fourth auxiliary wirings adjacent to each other, wherein the third and fourth auxiliary wirings are respectively separated from the first and second auxiliary wirings by at least two interposed auxiliary wirings, wherein the openings further include third and fourth openings respectively formed over the third and fourth auxiliary wirings, and wherein the third and fourth openings are not aligned in the second direction.

20. The display of claim 17, further comprising a metal layer interposed between and electrically connecting the auxiliary wirings and the opposite electrode.

* * * * *

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	US20170148865A1	公开(公告)日	2017-05-25
申请号	US15/360840	申请日	2016-11-23
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	CHO YOUNGJIN KANG CHULKYU KIM YONGJAE		
发明人	CHO, YOUNGJIN KANG, CHULKYU KIM, YONGJAE		
IPC分类号	H01L27/32		
CPC分类号	H01L27/3279 H01L2227/323 H01L27/3246		
优先权	1020150163974 2015-11-23 KR		
其他公开文献	US10297656		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种有机发光二极管 (OLED) 显示器及其制造方法。在一个方面，显示器包括位于基板上并彼此分离的多个像素电极，像素电极之间的多个辅助布线，像素电极上方的像素限定层，除了像素电极的中心部分每个辅助布线的至少一部分，在像素限定层上方的中间层，并且具有在每个辅助布线的部分上形成的多个开口，以及位于中间层上并面向所述辅助布线的相对电极。在像素电极中，相对电极通过开口与辅助布线电接触。辅助配线沿第一方向延伸并且彼此分开第一距离。开口在与第一方向交叉的对角线方向上对齐。

