



US010658438B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 10,658,438 B2**
(45) **Date of Patent:** **May 19, 2020**

(54) **ORGANIC LIGHT-EMITTING DISPLAY APPARATUS COMPRISING SELF-ASSEMBLED LAYER CONTAINING FLUORINE AND METHOD OF MANUFACTURING THE SAME**

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si, Gyeonggi-do (KR)

(72) Inventors: **Jaesik Kim**, Yongin-si (KR); **Yeonhwa Lee**, Yongin-si (KR); **Joongu Lee**, Yongin-si (KR); **Sehoon Jeong**, Yongin-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/907,430**

(22) Filed: **Feb. 28, 2018**

(65) **Prior Publication Data**
US 2018/0261656 A1 Sep. 13, 2018

(30) **Foreign Application Priority Data**
Mar. 13, 2017 (KR) 10-2017-0030982

(51) **Int. Cl.**
H01L 51/56 (2006.01)
H01L 27/32 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 27/3246** (2013.01); **H01L 51/0016** (2013.01); **H01L 51/0023** (2013.01);
(Continued)

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,610,552 B2 8/2003 Fujimori et al.
9,054,341 B2 6/2015 Kim et al.
(Continued)

FOREIGN PATENT DOCUMENTS

JP 2002-170669 A 6/2002
JP 2002-237383 A 8/2002
(Continued)

OTHER PUBLICATIONS

Extended European search report issued by the European Patent Office dated Jul. 12, 2018 in the examination of the European Patent Application No. 18 161 103.9.


Primary Examiner — Daniel Whalen

(74) *Attorney, Agent, or Firm* — Lewis Roca Rothgerber Christie LLP

(57) **ABSTRACT**

An organic light-emitting display apparatus including a substrate, a first first electrode on the substrate, a first organic functional layer on the first first electrode, the first organic functional layer including a first emission layer, a first second electrode on the first organic functional layer, a second first electrode on the substrate, the second first electrode being spaced apart from the first first electrode, a second organic functional layer on the second first electrode, the second organic functional layer including a second emission layer, a second second electrode on the second organic functional layer, and a self-assembled layer between the first organic functional layer and the second organic functional layer, the self-assembled layer containing fluorine.

25 Claims, 40 Drawing Sheets



(51) **Int. Cl.**

H01L 51/00 (2006.01)
H01L 51/52 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/56** (2013.01); **H01L 51/5206**
(2013.01); **H01L 51/5221** (2013.01); **H01L**
2227/323 (2013.01); **H01L 2251/305**
(2013.01); **H01L 2251/308** (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2008/0268280 A1 10/2008 Cho et al.
2010/0289019 A1 11/2010 Katz et al.
2011/0156079 A1 6/2011 Nakatani et al.
2016/0020424 A1* 1/2016 Kim H01L 51/5056
257/40
2017/0025610 A1* 1/2017 Kwon H01L 51/0007
2017/0133443 A1* 5/2017 Nendai H01L 27/3246

FOREIGN PATENT DOCUMENTS

JP WO2010/100922 A1 9/2012
KR 10-0841170 B1 6/2008
KR 10-2010-0065769 A 6/2010
KR 10-2014-0082089 A 7/2014

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5A





FIG. 5B






FIG. 5E




FIG. 5F




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 6F




FIG. 7A




FIG. 7B




FIG. 7C





FIG. 7D






FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 12D




FIG. 12E





FIG. 12F






FIG. 13E




FIG. 13F




FIG. 14A




FIG. 14B




FIG. 14C




FIG. 14D




FIG. 14E




FIG. 14F




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 15D




FIG. 15E




FIG. 16A




FIG. 16B




FIG. 16C




FIG. 16D




FIG. 17A





FIG. 17B






FIG. 17E




FIG. 18A (Related Art)




FIG. 18B (Related Art)




FIG. 18C (Related Art)

FIG. 18E (Related Art)




FIG. 19A (Related Art)




FIG. 19B (Related Art)




FIG. 19C (Related Art)





FIG. 19D (Related Art)






FIG. 20A (Related Art)




FIG. 20B (Related Art)




FIG. 20C (Related Art)




FIG. 20D (Related Art)




FIG. 20E (Related Art)





FIG. 21



1

**ORGANIC LIGHT-EMITTING DISPLAY
APPARATUS COMPRISING
SELF-ASSEMBLED LAYER CONTAINING
FLUORINE AND METHOD OF
MANUFACTURING THE SAME**

**CROSS-REFERENCE TO RELATED
APPLICATION**

Korean Patent Application No. 10-2017-0030982, filed on Mar. 13, 2017, in the Korean Intellectual Property Office, and entitled: "Organic Light-Emitting Display Apparatus and Method of Manufacturing the Same," is incorporated by reference herein in its entirety.

BACKGROUND

1. Field

One or more embodiments relate to an organic light-emitting display apparatus and a method of manufacturing the organic light-emitting display apparatus.

2. Description of the Related Art

An organic light-emitting display apparatus is a self-emitting display apparatus that includes a hole injection electrode, an electron injection electrode, and an organic emission layer formed between the hole injection electrode and the electron injection electrode; and emits light when holes injected from the hole injection electrode and electrons injected from the electron injection electrode recombine in the organic emission layer. The organic light-emitting display apparatus has advantages such as low power consumption, high luminance, and fast response, and thus has received attention as a next-generation display apparatus.

SUMMARY

Embodiments are directed to an organic light-emitting display apparatus including a substrate, a first first electrode on the substrate, a first organic functional layer on the first first electrode, the first organic functional layer including a first emission layer, a first second electrode on the first organic functional layer, a second first electrode on the substrate, the second first electrode being spaced apart from the first first electrode, a second organic functional layer on the second first electrode, the second organic functional layer including a second emission layer, a second second electrode on the second organic functional layer, and a self-assembled layer between the first organic functional layer and the second organic functional layer, the self-assembled layer containing fluorine.

A color of light emitted from the first emission layer may be different from a color of light emitted from the second emission layer.

Each of the first organic functional layer and the second organic functional layer may further include at least one of a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer.

The organic light-emitting display apparatus may further include a pixel-defining layer including an insulating layer and covering an edge of the first first electrode and an edge of the second first electrode.

An edge portion of the first organic functional layer and an edge portion of the second organic functional layer may be on an inclined surface of the pixel-defining layer.

2

The self-assembled layer may be on the pixel-defining layer and may surround the first organic functional layer and the second organic functional layer.

The self-assembled layer may be spaced apart from end portions of the first organic functional layer and the second organic functional layer by a preset gap.

The self-assembled layer may be under the pixel-defining layer and may surround peripheries of the first first electrode and the second first electrode.

The self-assembled layer may overlap end portions of the first first electrode and the second first electrode.

The self-assembled layer may include a fluorocarbon group ($-\text{CF}_3$).

The first first electrode and the second first electrode may include a conductive oxide.

The first first electrode and the second first electrode may include at least one of indium tin oxide, indium zinc oxide, zinc oxide, indium oxide, indium gallium oxide, and aluminum zinc oxide.

The organic light-emitting display apparatus may further include a common electrode integrally formed on the first second electrode and the second second electrode.

Embodiments are also directed to a method of manufacturing an organic light-emitting display apparatus including forming a first first electrode and a second first electrode on a substrate so as to be spaced apart from each other, forming a self-assembled layer containing fluorine on the first first electrode and the second first electrode, sequentially forming a first lift-off layer and a first photoresist on the self-assembled layer, removing a portion of the first lift-off layer and a portion of the first photoresist in an area corresponding to the first first electrode and allowing the self-assembled layer to remain, removing a portion of the self-assembled layer on the first first electrode by performing first plasma heat treatment, and sequentially forming, on the first first electrode, a first organic functional layer and a first second electrode, wherein the first organic functional layer includes a first emission layer, and lifting off a remaining portion of the first lift-off layer.

The first lift-off layer may have a fluorine content ranging from 20 wt % to 60 wt %.

The first organic functional layer and the first second electrode may be formed by a deposition process.

Removing the portion of the first photoresist may include performing a photolithography process.

The first lift-off layer may be etched and removed by using a first solvent containing fluorine.

The self-assembled layer may be formed by a vapor deposition method.

The self-assembled layer may include a hydrolyzable reactive group and a fluorine-containing functional group.

The method may further include sequentially forming a second lift-off layer and a second photoresist after lifting off the remaining portion of the first lift-off layer, removing a portion of the second lift-off layer and a portion of the second photoresist in an area corresponding to the second first electrode and allowing the self-assembled layer to remain removing a portion of the self-assembled layer on the second first electrode by performing second plasma heat treatment, sequentially forming a second organic functional layer and the second second electrode on the second first electrode, wherein the second organic functional layer includes a second emission layer, and lifting off a remaining portion of the second lift-off layer.

The method may further include forming, between the first first electrode and the second first electrode, a pixel-defining layer including an insulating layer.

The self-assembled layer may be formed on the pixel-defining layer.

The self-assembled layer may be formed under the pixel-defining layer.

The method may further include forming a common electrode in an integral form on the first second electrode and the second second electrode.

Embodiments are also directed to a method of manufacturing an organic light-emitting display apparatus, including forming a first first electrode and a second first electrode on a substrate so as to be spaced apart from each other, forming a first self-assembled layer on the first first electrode and the second first electrode, forming a first photoresist on the first self-assembled layer, removing a portion of the first photoresist in an area corresponding to the first first electrode and allowing the first self-assembled layer to remain, removing a portion of the first self-assembled layer on the first first electrode by performing first plasma heat treatment, and sequentially forming a first organic functional layer and a first second electrode on the first first electrode. The first organic functional layer includes a first emission layer, and lifting off a remaining portion of the first photoresist and a remaining portion of the first self-assembled layer.

BRIEF DESCRIPTION OF THE DRAWINGS

Features will become apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

FIG. 1 illustrates a cross-sectional view of an organic light-emitting display apparatus according to an embodiment;

FIG. 2 illustrates a plan view of a portion of the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 1;

FIG. 3 illustrates a cross-sectional view for explaining forming a plurality of anodes on a substrate of the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 1;

FIG. 4 illustrates a cross-sectional view for explaining forming a pixel-defining layer in the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 1;

FIGS. 5A to 5F illustrate cross-sectional views for explaining stages of a first unit process of forming the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 1;

FIGS. 6A to 6F illustrate cross-sectional views for explaining stages of a second unit process of forming the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 1;

FIGS. 7A to 7F illustrate cross-sectional views for explaining stages a third unit process of forming the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 1;

FIG. 8 illustrates a cross-sectional view of an organic light-emitting display apparatus according to an embodiment;

FIG. 9 illustrates a plan view of a portion of the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 8;

FIG. 10 illustrates a cross-sectional view for explaining an operation of forming a plurality of anodes and a self-assembled monolayer on a substrate of the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 8;

FIG. 11 illustrates a cross-sectional view for explaining forming a pixel-defining layer in the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 8;

FIGS. 12A to 12F illustrate cross-sectional views for explaining stages of a first unit process of forming the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 8;

FIGS. 13A to 13F illustrate cross-sectional views for explaining stages of a second unit process of forming the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 8;

FIGS. 14A to 14F illustrate cross-sectional views for explaining a third unit process of forming the organic light-emitting display apparatus according to the embodiment illustrated in FIG. 8;

FIGS. 15A to 15E illustrate cross-sectional views for explaining a first unit process of forming an organic light-emitting display apparatus according to an embodiment;

FIGS. 16A to 16E illustrate cross-sectional views for explaining a second unit process of forming the organic light-emitting display apparatus following the first unit process illustrated in FIGS. 15A to 15E according to an embodiment;

FIGS. 17A to 17E illustrate cross-sectional views for explaining a third unit process of forming the organic light-emitting display apparatus following the second unit process illustrated in FIGS. 16A to 16E according to an embodiment;

FIGS. 18A to 18E illustrate cross-sectional views for explaining a first unit process of forming an organic light-emitting display apparatus according to a comparative example;

FIGS. 19A to 19E illustrate cross-sectional views for explaining a second unit process of the organic light-emitting display apparatus according to the comparative example;

FIGS. 20A to 20E illustrate cross-sectional views for explaining a third unit process of the organic light-emitting display apparatus according to the comparative example; and

FIG. 21 illustrates a diagram illustrating an operation mechanism of a self-assembled monolayer.

DETAILED DESCRIPTION

Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. It will also be understood that when a layer or element is referred to as being “on” another layer or substrate, it can be directly on the other layer or substrate, or intervening layers may also be present. Further, it will be understood that when a layer is referred to as being “under” another layer, it can be directly under, and one or more intervening layers may also be present. In this regard, unless otherwise provided, a description that a layer or element is “under” another layer or element may be interpreted as indicating that the layer or element is closer to the substrate than the other layer or element. In addition, it will also be understood that when a

layer is referred to as being “between” two layers, it can be the only layer between the two layers, or one or more intervening layers may also be present. Like reference numerals refer to like elements throughout.

FIG. 1 illustrates a cross-sectional view of an organic light-emitting display apparatus 1 according to an embodiment, and FIG. 2 illustrates a plan view of a portion of the organic light-emitting display apparatus 1 according to the embodiment.

Referring to FIGS. 1 and 2, in the organic light-emitting display apparatus 1, a plurality of anodes including a first anode 101, a second anode 102, and a third anode 103 may be on a substrate 100 in a spaced apart relationship each other.

First to third organic functional layers 141, 142, and 143 including first to third emission layers may be respectively located on the first to third anodes 101, 102, and 103. First to third auxiliary cathodes 181, 182, and 183 including a conductive material may be respectively located on the first to third organic functional layers 141, 142, and 143. An integrally formed common electrode 180 may be located on the first to third auxiliary cathodes 181, 182, and 183. (The first auxiliary cathode 181, the second auxiliary cathode 182, and the third auxiliary cathode 183 may also be referred to as a first second electrode, a second second electrode and a third second electrode, so as to not be limited as to polarity. For example, in some implementations, electrodes 101, 102, and 103 may be cathodes, and electrodes 180, 181, 182, and 183 may be anodes.)

A pixel-defining layer 110 including an insulating material may cover end portions of the first to third anodes 101, 102, and 103. The pixel-defining layer 110 may prevent electric field concentration at each of the end portions of the first to third anodes 101, 102, and 103.

A self-assembled monolayer 150 may be located on the pixel-defining layer 110. The self-assembled monolayer 150 may surround the first to third organic functional layers 141, 142 and 143. The self-assembled monolayer 150 may be spaced apart from the end portions of the first to third organic functional layers 141, 142, 413 by a predetermined distance D1.

The self-assembled monolayer 150 may include a fluorine-containing functional group and a hydrolyzable reactive group.

The fluorine-containing functional group may include fluorocarbon ($-\text{CF}_3$). The hydrolyzable reactive group may include a silicone compound. For example, the self-assembled monolayer 150 may include FOTS (1H,1H,2H,2H-perfluorodecyltrichlorosilane-perfluoro), FOTS (heptadecafluoro-1,1,2,2,-tetrahydrodecyl)trichlorosilane), FOMMS ($(\text{CF}_3(\text{CF}_2)_5(\text{CH}_2)_2\text{Si}(\text{CH}_3)_2\text{Cl})$), FOMDS ($(\text{CF}_3(\text{CF}_2)_5(\text{CH}_2)_2\text{Si}(\text{CH}_3)\text{Cl}_2)$), FOTES ($(\text{CF}_3(\text{CF}_2)_5(\text{CH}_2)_2\text{Si}(\text{OC}_2\text{HO}_3)_2)$), or the like.

The self-assembled monolayer may include a hydrophobic functional group containing a methyl group ($-\text{CH}_3$). For example, the self-assembled monolayer may include octadecyltrichlorosilane (OTS), dichlorodimethylsilane (DDMS), or the like.

The fluorine-containing functional group may be located at a greater distance from the surfaces of the first to third anodes 101, 102, and 103 and the pixel-defining layer 110 than the hydrolyzable reactive group. The fluorine-containing functional group of the self-assembled monolayer 150 may have a small difference in surface energy with respect to a lift-off layer 121 (see FIG. 5A) containing fluorine, to be described below. Thus, the lift-off layer 121 may be uniformly formed on the self-assembled monolayer 150,

thereby improving patterning precision. In addition, the term “monolayer” used in the self-assembled monolayer is not limited as meaning that the self-assembled monolayer includes a single molecule. Herein, instead of the term “self-assembled monolayer”, the term “self-assembled layer” may be used as having the same meaning as the term “self-assembled monolayer”.

With reference to FIGS. 3 to 7F, a method of manufacturing the organic light-emitting display apparatus 1 and the organic light-emitting display apparatus 1 manufactured by the above method are described in more detail.

FIG. 3 illustrates a cross-sectional view for explaining forming the first to third anodes 101, 102, and 103 on the substrate 100 of the organic light-emitting display apparatus 1. FIG. 4 illustrates a cross-sectional view for explaining forming the pixel-defining layer 110 in the organic light-emitting display apparatus 1. FIGS. 5A to 5F illustrates cross-sectional views for explaining a first unit process of forming the organic light-emitting display apparatus 1. FIGS. 6A to 6F illustrate cross-sectional views for explaining a second unit process of the organic light-emitting display apparatus 1. FIGS. 7A to 7F illustrate cross-sectional views for explaining a third unit process of the organic light-emitting display apparatus 1.

Referring to FIG. 3, a plurality of anodes including the first anode 101, the second anode 102, and the third anode 103 may be formed on the substrate 100. (The first anode 101, the second anode 102, and the third anode 103 may also be referred to as a first first electrode, a second first electrode and a third first electrode, so as to not be limited as to polarity.)

The substrate 100 may include suitable materials. For example, the substrate 100 may include glass or plastic. Examples of the plastic may include materials having excellent heat resistance and excellent durability, such as polyimide, polyethylenenaphthalate, polyethyleneterephthalate, polyarylate, polycarbonate, polyetherimide, and polyethersulfone.

A buffer layer for flattening a top surface of the substrate 100 and preventing penetration of impurities may be further formed on the substrate 100. For example, the buffer layer may be a single layer or a plurality of layers including silicon nitride, silicon oxide, and/or the like.

The first to third anodes 101, 102, and 103 may be hole injection electrodes and may include materials having a high work function. The first to third anodes 101, 102, and 103 may each include a transparent conductive oxide component. For example, the first to third anodes 101, 102, and 103 may include at least one selected from indium tin oxide, indium zinc oxide, zinc oxide, indium oxide, indium gallium oxide, and aluminum zinc oxide. The first to third anodes 101, 102, and 103 may each be a single layer or may be a plurality of layers including a metal and/or an alloy such as silver (Ag), aluminum (Al), magnesium (Mg), lithium (Li), or calcium (Ca).

The first to third anodes 101, 102, and 103 may electrically contact first to third thin-film transistors, respectively, that are located between the substrate 100 and the first to third anodes 101, 102, and 103.

Referring to FIG. 4, the pixel-defining layer 110 surrounding edges of the first anode 101, the second anode 102, and the third anode 103 may be formed on the substrate 100.

End portions of the first to third anodes 101, 102, and 103 may be sharp. Accordingly, when a current is applied after the first to third auxiliary cathodes 181, 182, and 183 are formed, there is a possibility that an electric field could concentrate on the end portions of the first to third anodes

101, **102**, and **103**, and thus an electrical short circuit could occur during operation. However, when the end portions of the first to third anodes **101**, **102**, and **103** are covered by the pixel-defining layer **110**, as illustrated in FIGS. **1** and **4**, an electric field may be prevented from concentrating at the end portions of the first to third anodes **101**, **102**, and **103**.

The pixel-defining layer **110** may be an organic insulating layer including, for example, a general-purpose polymer such as poly(methyl methacrylate) (PMMA) or polystyrene (PS), a polymer derivative having a phenol group, an acryl-based polymer, an imide-based polymer, an arylether-based polymer, an amide-based polymer, a fluorine-based polymer, a p-xylene-based polymer, a vinyl alcohol-based polymer, or a blend thereof.

Referring to FIG. **5A**, a self-assembled monolayer **150**, a first lift-off layer **121**, and a first photoresist **131** are sequentially formed on the substrate **100** on which the first to third anodes **101**, **102**, and **103** are formed.

The self-assembled monolayer **150** may be formed by using a coating method, a printing method, a deposition method, or the like. The self-assembled monolayer **150** may include a fluorine-containing functional group and a hydrolyzable reactive group, as described above. For example, as described above, the self-assembled monolayer **150** may include FOTS (1H,1H,2H,2H-perfluorodecyltrichlorosilane-perfluoro), FDTS (heptadecafluoro-1,1,2,2-tetrahydrodecyl)trichlorosilane), FOMMS ($(CF_3(CF_2)_5(CH_2)_2Si(CH_3)_2Cl)$), FOMDS ($(CF_3(CF_2)_5(CH_2)_2Si(CH_3)Cl_2)$), FOTES ($(CF_3(CF_2)_5(CH_2)_2Si(OC_2H_5)_3)$), or the like.

The first lift-off layer **121** may include a fluoropolymer. The fluoropolymer included in the first lift-off layer **121** may include a polymer having a fluorine content ranging from about 20 wt % to about 60 wt %. For example, the fluoropolymer included in the first lift-off layer **121** may include at least one from among a copolymer of polytetrafluoroethylene, polychlorotrifluoroethylene, polydichlorodifluoroethylene, chlorotrifluoroethylene, and dichlorodifluoroethylene, a copolymer of tetrafluoroethylene and perfluoroalkylvinylether, a copolymer of chlorotrifluoroethylene and perfluoroalkylvinylether, a copolymer of tetrafluoroethylene and perfluoroalkylvinylether, and a copolymer of chlorotrifluoroethylene and perfluoroalkylvinylether.

The first lift-off layer **121** may be formed by using a coating method, a printing method, a deposition method, or the like. When the first lift-off layer **121** is formed by using a coating method or a printing method, curing and polymerization may be performed as desired, and then a process of forming a first photoresist **131** may be performed.

FIG. **21** schematically illustrates a mechanism by which a self-assembled monolayer **150** may operate when the self-assembled monolayer **150** is formed on a first anode **101**.

For example, when a self-assembled monolayer **150** including FOTS is deposited on a first anode **101** including indium tin oxide, a hydrolysis reactive group that includes silicon, of the self-assembled monolayer **150**, may cause a hydrolysis and condensation reaction with a hydroxyl group ($-OH$) of the surface of the first anode **101**. The self-assembled monolayer **150** may be covalently bonded to the surface of the first anode **101**. This covalent bonding may increase adhesion between the surface of the self-assembled monolayer **150** and the surface of the first anode **101**.

When a first lift-off layer **121** including a fluoropolymer is formed on the self-assembled monolayer **150**, a fluorine-containing functional group of the self-assembled monolayer **150**, which is in close contact with the first lift-off layer **121**, may have a small difference in surface energy with

respect to the lift-off layer **121**. Thus, the lift-off layer **121** may be uniformly formed on the self-assembled monolayer **150**.

The first photoresist **131** may be formed on the first lift-off layer **121**. As illustrated in FIG. **5A**, the first photoresist **131** at a position corresponding to the first anode **101** may be exposed through a first photomask **M1** including an area **M11** through which light **L** is transmitted.

Referring to FIG. **5B**, the first photoresist **131** may be developed. The first photoresist **131** may be a positive photoresist or a negative photoresist. In the present embodiment, it is assumed that the first photoresist **131** is a positive photoresist. In the first photoresist **131** that is developed, a first portion **131-1** corresponding to the first anode **101** may be removed and a second portion **131-2** other than the first portion **131-1** may remain.

Referring to FIG. **5C**, the first lift-off layer **121** may be etched by using a pattern of the first portion **131-1** of the first photoresist **131** as an etch mask.

The first lift-off layer **121** may include the fluoropolymer. Accordingly, a solvent that etches the fluoropolymer may be used as an etchant.

A first solvent including fluorine may be used as the etchant. The first solvent may include hydrofluoroether, which is a material that is electrochemically stable due to a low interaction with other materials and is environmentally stable due to a low global warming potential and a low toxicity.

A portion of the first lift-off layer **121** formed at a position corresponding to the first portion **131-1**, that is, above the first anode **101**, may be etched during an etching process. The first lift-off layer **121** may be etched by the first solvent including fluorine to form a first undercut profile **UC1-1** under a boundary surface of the first portion **131-1** of the first photoresist **131**.

The self-assembled monolayer **150** may be well bonded to the top surface of the first anode **101** while the first lift-off layer **121** is etched. For example, as described above, a hydrolysis and condensation reaction may occur between a reactive group including silicon, included in the self-assembled monolayer **150**, and the surface of the first anode **101**. An adhesive strength due to covalent bonding between the self-assembled monolayer **150** and the surface of the first anode **101** may be increased.

In addition, a hydrolysis and condensation reaction may occur between a reactive group including silicon, included in the self-assembled monolayer **150**, and a surface material of the pixel-defining layer **110**, and thus an adhesive strength between the surface of the self-assembled monolayer **150** and the surface of the pixel-defining layer **110** may be increased. The self-assembled monolayer **150** may be well bonded to the top surface of the pixel-defining layer **110** while the first lift-off layer **121** is etched.

Referring to FIG. **5D**, a portion of the self-assembled monolayer **150** on the first anode **101** may be removed by performing first plasma heat treatment on the structure illustrated in FIG. **5C**.

The Si—O bond between the first anode **101** and the self-assembled monolayer **150** shown in FIG. **21** may be cleanly broken by the first plasma heat treatment. In this regard, if the first lift-off layer **121** were to be directly formed on the first anode **101** after the formation of the first anode **101** without forming the self-assembled monolayer **150** and were to be removed in a subsequent process, a residue of the first lift-off layer **121** could remain on the first anode **101**, causing contamination. However, in the present embodiment, the self-assembled monolayer **150** may be

formed between the first anode **101** and the first lift-off layer **121** to prevent a residue of the first lift-off layer **121** from remaining on the first anode **101**, thereby preventing deterioration of the organic-light emitting display apparatus.

Referring to FIG. **5E**, a first organic functional layer **141** including a first emission layer and a first auxiliary cathode **181** may be sequentially formed on the structure illustrated in FIG. **5D**.

The first organic functional layer **141** may further include at least one selected from a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer.

The first organic functional layer **141** may be formed by a vacuum deposition method. In the deposition process, the first lift-off layer **121** and the first photoresist **131** may function as masks. A portion of the first organic functional layer **141** may be formed at a position corresponding to the first portion **131-1**, that is, above the first anode **101**, and the other portion of the first organic functional layer **141** may be formed on a second portion **131-2** of the first photoresist **131**.

Like the first organic functional layer **141**, the first auxiliary cathode **181** may also be formed by using a vacuum deposition method. In the deposition process, the first lift-off layer **121** and the first photoresist **131** may function as masks. A portion of the first auxiliary cathode **181** may be formed to cover a top surface of the first organic functional layer **141**, and the other portion of the first auxiliary cathode **181** may be formed on the first organic functional layer **141** on a second portion **131-2** of the first photoresist **131** other than the first portion **131-1**.

The first auxiliary cathode **181** may include the same material as that of a cathode **180** that is a common electrode to be described below. In some implementations, the first auxiliary cathode **181** may include a material different from that of the cathode **180**. The first auxiliary cathode **181** may function as a barrier for protecting the first organic functional layer **141** from a solvent used in a subsequent lift-off process.

Referring to FIG. **5F**, a lift-off process may be performed on the structure illustrated in FIG. **5E**.

The first lift-off layer **121** may include the fluoropolymer. Accordingly, a second solvent including fluorine may be used in the lift-off process. The first organic functional layer **141** may be formed and then the lift-off process may be performed. Accordingly, the second solvent may include a material having a low reactivity with the first organic functional layer **141**. Like the first solvent, the second solvent may include hydrofluoroether.

When the first lift-off layer **121** formed under the second portion **131-2** (see FIG. **5E**) of the first photoresist **131** is lifted off, portions of the first organic functional layer **141** and the first auxiliary cathode **181** that were formed on the second portion **131-2** of the first photoresist **131** may be removed. Portions of the first organic functional layer **141** and the first auxiliary cathode **181** formed over the first anode **101** may remain as patterns.

The self-assembled monolayer **150** formed on the pixel-defining layer **110** is not removed. As described above, an adhesive strength between the surface of the self-assembled monolayer **150** and the surface of the pixel-defining layer **110** is high due to a hydrolysis and condensation reaction between a reactive group including silicon, included in the self-assembled monolayer **150**, and a surface material of the pixel-defining layer **110**. Accordingly, the self-assembled

monolayer **150** may be well bonded to the top surface of the pixel-defining layer **110** while the first lift-off layer **121** is lifted off.

After the first unit process is performed, a second unit process of forming the second organic functional layer **142**, which may emit light of a different color from that emitted by the first organic functional layer **141**, may be performed on an area where the second anode **102** is located. The second unit process will now be described with reference to FIGS. **6A** to **6F**.

Referring to FIG. **6A**, a second lift-off layer **122** and a second photoresist **132** may be sequentially formed on the structure illustrated in FIG. **5F**.

The second lift-off layer **122** may include a fluoropolymer. The second lift-off layer **122** may include the same material as that of the first lift-off layer **121** and may be formed by using a coating method, a printing method, or a deposition method.

The second photoresist **132** may be formed on the second lift-off layer **122**. The second photoresist **132**, may be exposed through a second photomask **M2** including an area **M21** through which light **L** is transmitted, the area **M21** being at a position corresponding to the second anode **102**.

Referring to FIG. **6B**, the second photoresist **132** may be developed. In the second photoresist **132**, a first portion **132-1** corresponding to the second anode **102** may be removed and a second portion **132-2** other than the first portion **132-1** may remain.

Referring to FIG. **6C**, the second lift-off layer **122** may be etched by using a pattern of the first portion **132-1** of the second photoresist **132** as an etch mask.

The second lift-off layer **122** includes the fluoropolymer. Accordingly, a solvent that etches the fluoropolymer may be used as an etchant. For example, a first solvent including fluorine may be used as the etchant. The first solvent may include hydrofluoroether.

A portion of the second lift-off layer **122** formed at a position corresponding to the first portion **132-1**, that is, above the second anode **102**, may be etched during an etching process. The second lift-off layer **122** may be etched by the first solvent including fluorine to form a second undercut profile **UC2-1** under a boundary surface of the first portion **132-1** of the second photoresist **132**.

The self-assembled monolayer **150** may be well bonded to the top surface of the second anode **102** while the second lift-off layer **122** is etched. In addition, the self-assembled monolayer **150** may be well bonded to the top surface of the pixel-defining layer **110** while the second lift-off layer **122** is etched.

Referring to FIG. **6D**, a portion of the self-assembled monolayer **150** on the second anode **102** may be removed by performing a second plasma heat treatment on the structure illustrated in FIG. **6C**.

An Si—O bond between the second anode **102** and the self-assembled monolayer **150** may be cleanly broken by the second plasma heat treatment. Accordingly, a residue of the second lift-off layer **122** may not remain on the second anode **102**.

Referring to FIG. **6E**, a second organic functional layer **142** including a second emission layer and a second auxiliary cathode **182** may be sequentially formed on the structure illustrated in FIG. **6D**.

The second organic functional layer **142** may further include at least one selected from a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer.

The second organic functional layer **142** may be formed by using a vacuum deposition method. In the deposition process, the second lift-off layer **122** and the second photoresist **132** may function as masks. A portion of the second organic functional layer **142** may be formed at a position corresponding to the first portion **132-1**, that is, above the second anode **102**, and another portion of the second organic functional layer **142** may be formed on the second portion **132-2** of the second photoresist **132**.

Like the second organic functional layer **142**, the second auxiliary cathode **182** may be formed by using a vacuum deposition method. In the deposition process, the second lift-off layer **122** and the second photoresist **132** may function as masks. A portion of the second auxiliary cathode **182** may be formed to cover a top surface of the second organic functional layer **142**, and another portion of the second auxiliary cathode **182** may be formed on the second organic functional layer **142** on the second portion **132-2** of the second photoresist **132**.

The second auxiliary cathode **182** may include the same material as that of the cathode **180** that is a common electrode to be described below. In some implementations, the second auxiliary cathode **182** may include a material different from that of the cathode **180**. The second auxiliary cathode **182** may function as a barrier for protecting the second organic functional layer **142** from a solvent used in a subsequent lift-off process.

Referring to FIG. 6F, a lift-off process may be performed on the structure illustrated in FIG. 6E.

The second lift-off layer **122** includes the fluoropolymer. Accordingly, a second solvent including fluorine may be used in the lift-off process. The second organic functional layer **142** may be formed and then the lift-off process may be performed. Accordingly, the second solvent may include a material having a low reactivity with the second organic functional layer **142**. Like the first solvent, the second solvent may include hydrofluoroether.

When the second lift-off layer **122** formed under the second portion **132-2** (see FIG. 6E) of the second photoresist **132** is lifted off, portions of the second organic functional layer **142** and the second auxiliary cathode **182** that were formed on the second portion **132-2** of the second photoresist **132** may be removed. Portions of the second organic functional layer **142** and the second auxiliary cathode **182** formed over the second anode **102** may remain as patterns.

As described above, an adhesive strength between the self-assembled monolayer **150** and the pixel-defining layer **110** may be sufficient such that the self-assembled monolayer **150** formed on the pixel-defining layer **110** is not removed when the second lift-off layer **122** is lifted off.

After the second unit process is performed, a third unit process of forming the third organic functional layer **143**, which may emit light of a different color from that emitted by the first organic functional layer **141** and the second organic functional layer **142** may be performed on an area where the third anode **103** is located. The third unit process will now be described with reference to FIGS. 7A to 7F.

Referring to FIG. 7A, a third lift-off layer **123** and a third photoresist **133** may be sequentially formed the structure illustrated in FIG. 6F.

The third lift-off layer **123** may include a fluoropolymer. The third lift-off layer **123** may include the same material as that of the first and second lift-off layers **121** and **122** and may be formed by using a coating method, a printing method, or a deposition method.

The third photoresist **133** may be formed on the third lift-off layer **123**. The third photoresist **133** at a position

corresponding to the third anode **103** may be exposed through a third photomask **M3** including an area **M31** through which light **L** is transmitted.

Referring to FIG. 7B, the third photoresist **133** may be developed. In the third photoresist **133**, a first portion **133-1** corresponding to the third anode **103** may be removed and a second portion **133-2** other than the first portion **133-1** may remain.

Referring to FIG. 7C, the third lift-off layer **123** may be etched by using a pattern of the first portion **133-1** of the third photoresist **133** as an etch mask.

The third lift-off layer **123** may include the fluoropolymer. Accordingly, a solvent that etches the fluoropolymer may be used as an etchant. For example, a first solvent including fluorine may be used as the etchant. The first solvent may include hydrofluoroether.

A portion of the third lift-off layer **123** formed at a position corresponding to the first portion **133-1**, that is, above the third anode **103**, may be etched during an etching process. The third lift-off layer **123** may be etched by the first solvent including fluorine to form a third undercut profile **UC3-1** under a boundary surface of the first portion **133-1** of the third photoresist **133**.

The self-assembled monolayer **150** may be well bonded to the top surface of the third anode **103** while the third lift-off layer **123** is etched. In addition, the self-assembled monolayer **150** may be well bonded to the top surface of the pixel-defining layer **110** while the third lift-off layer **123** is etched.

Referring to FIG. 7D, a portion of the self-assembled monolayer **150** on the third anode **103** may be removed by performing third plasma heat treatment on the structure illustrated in FIG. 7C.

An Si—O bond between the third anode **103** and the self-assembled monolayer **150** may be cleanly broken by the third plasma heat treatment. Accordingly, a residue of the third lift-off layer **123** may not remain on the third anode **103**.

Referring to FIG. 7E, a third organic functional layer **143** including a third emission layer and a third auxiliary cathode **183** may be sequentially formed on the structure illustrated in FIG. 7D.

The third organic functional layer **143** may further include at least one selected from a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer.

The third organic functional layer **143** may be formed by using a vacuum deposition method. In the deposition process, the third lift-off layer **123** and the third photoresist **133** may function as masks. A portion of the third organic functional layer **143** is formed at a position corresponding to the first portion **133-1**, that is, above the third anode **103**, and another portion of the third organic functional layer **143** may be formed on the second portion **133-2** of the third photoresist **133**.

Like the third organic functional layer **143**, the third auxiliary cathode **183** may be formed by using a vacuum deposition method. In the deposition process, the third lift-off layer **123** and the third photoresist **133** may function as masks. A portion of the third auxiliary cathode **183** may be formed to cover a top surface of the third organic functional layer **143**, and another portion of the third auxiliary cathode **183** may be formed on the third organic functional layer **143** on the second portion **133-2** of the third photoresist **133**.

The third auxiliary cathode **183** may include the same material as that of the cathode **180** that is a common

13

electrode to be described below. In some implementations, the third auxiliary cathode **183** may include a material different from that of the cathode **180**. The third auxiliary cathode **183** may function as a barrier for protecting the third organic functional layer **143** from a solvent used in a subsequent lift-off process.

Referring to FIG. 7F, a lift-off process is performed on the structure illustrated in FIG. 7E.

The third lift-off layer **123** may include the fluoropolymer. Accordingly, a second solvent including fluorine may be used in the lift-off process. The third organic functional layer **143** may be formed and then the lift-off process is performed. Accordingly, the second solvent may include a material having a low reactivity with the third organic functional layer **143**. Like the first solvent, the second solvent may include hydrofluoroether.

When the third lift-off layer **123** formed under the second portion **133-2** (see FIG. 7E) of the third photoresist **133** is lifted off, portions of the third organic functional layer **143** and the third auxiliary cathode **183** that were formed on the second portion **133-2** of the third photoresist **133** may be removed, and portions of the third organic functional layer **143** and the third auxiliary cathode **183** formed over the third anode **103** may remain as patterns.

As described above, an adhesive strength between the self-assembled monolayer **150** and the pixel-defining layer **110** may be sufficient such that the self-assembled monolayer **150** formed on the pixel-defining layer **110** is not removed when the third lift-off layer **123** is lifted off.

The first, second, and third organic functional layers **141**, **142**, and **143** may emit light of different colors. When the light of different colors emitted from the first to third organic functional layers **141**, **142**, and **143** is mixed, white light may be formed. For example, the first, second, and third organic functional layers **141**, **142**, and **143** may emit red light, green light, and blue light, respectively. For example, the first to third organic functional layers **141**, **142**, and **143** may be elements of sub-pixels constituting a unit pixel of the organic light-emitting display apparatus **1**.

The organic light-emitting display apparatus **1** illustrated in FIG. 1 may represent one unit pixel. Embodiments may also be applied to an organic light-emitting display apparatus including a plurality of unit pixels that are the same as the unit pixel illustrated in FIG. 1. For example, a plurality of first organic functional layers **141**, which emit a first color, may be simultaneously formed as first sub-pixels by using the first unit process. A plurality of second organic functional layers **142**, which emit a second color, may be simultaneously formed as second sub-pixels by using the second unit process. A plurality of third organic functional layers **143**, which emit a third color, may be simultaneously formed as third sub-pixels by using the third unit process. Through the first to third unit processes, full color may be realized.

In the present embodiment, when a self-assembled monolayer is formed between an anode and a lift-off layer without the formation of the lift-off layer directly on the anode, the self-assembled monolayer may prevent a residual film of the lift-off layer from being left on the anode, and thus deterioration of the organic light-emitting display apparatus **1** may be prevented.

Hereinafter, a method of manufacturing an organic light-emitting display apparatus **4** according to a comparative example is described with reference to FIGS. 18A to 20E.

FIGS. 18A to 18E illustrate cross-sectional views for explaining a first unit process of the organic light-emitting display apparatus **4** according to the comparative example.

14

FIGS. 19A to 19E illustrate cross-sectional views for explaining a second unit process of the organic light-emitting display apparatus **4** according to the comparative example. FIGS. 20A to 20E illustrate cross-sectional views for explaining a third unit process of the organic light-emitting display apparatus **4** according to the comparative example.

Referring to FIG. 18A, a first lift-off layer **121** including a fluoropolymer is formed above a substrate **100** on which first to third anodes **101** to **103** and a pixel-defining layer **110** covering end portions of the first to third anodes **101** to **103** are formed, and a first photoresist **131** is formed on the first lift-off layer **121**. The first photoresist **131** at a position corresponding to a first anode **101** is exposed through a first photomask M1 including an area M11 through which light L is transmitted.

Referring to FIG. 18B, the first photoresist **131** is patterned. The first photoresist **131** that is exposed and developed is removed at the first portion **131-1** corresponding to the first anode **101** and remains at a second portion **131-2** other than the first portion **131-1**.

Referring to FIG. 18C, the first lift-off layer **121** is etched by using a pattern of the first photoresist **131** of FIG. 18B as an etch mask and using a first solvent (not shown) including fluorine. During an etching process, a portion of the first lift-off layer **121** formed at a position corresponding to the first portion **131-1**, that is, on the first anode **101**, is etched. The first lift-off layer **121** is etched to form a first undercut profile UC1 under a boundary surface of the first portion **131-1** of the first photoresist **131**. When the first lift-off layer **121** is stripped after the etching process is performed, an undesirable residue of the first lift-off layer **121** may remain on the first anode **101**.

Referring to FIG. 18D, a first organic functional layer **141** and a first auxiliary cathode **181** are sequentially formed on a structure of FIG. 18C.

Referring to FIG. 18E, a first lift-off process is performed such that remaining portions of the first lift-off layer **121** are entirely removed, and as a result, the first organic functional layer **141** and the first auxiliary cathode **181** remain as patterns on the first anode **101**.

After the first unit process is completed, the second unit process is performed on an area at which a second anode **102** is located.

Referring to FIG. 19A, a second lift-off layer **122** and a second photoresist **132** are sequentially formed on a structure of FIG. 18E.

Referring to FIG. 19B, the second photoresist **132** is patterned. The second photoresist **132** that is exposed and developed is patterned to be removed at a first portion **132-1** corresponding to the second anode **102** and remain at a second portion **132-2** other than the first portion **132-1**.

Referring to FIG. 19C, the second lift-off layer **122** is etched by using a pattern of the second photoresist **132** of FIG. 19B as an etch mask and using the first solvent (not shown) including fluorine. During an etching process, a portion of the second lift-off layer **122** formed at a position corresponding to the first portion **132-1**, that is, on the second anode **102**, is etched. The second lift-off layer **122** is etched to form a second undercut profile UC2 under a boundary surface of the first portion **132-1** of the second photoresist **132**. When the second lift-off layer **122** is stripped after the etching process is performed, an undesirable residue of the second lift-off layer **122** may remain on the second anode **102**.

15

Referring to FIG. 19D, a second organic functional layer **142** and an auxiliary cathode **182** are sequentially formed on a structure of FIG. 19C.

Referring to FIG. 19E, a second lift-off process is performed such that remaining portions of the second lift-off layer **122** are entirely removed, and as a result, the second organic functional layer **142** and the second auxiliary cathode **182** remain as patterns on the second anode **102**.

After the second unit process is completed, the third unit process is performed on an area at which a third anode **103** is located.

Referring to FIG. 20A, a third lift-off layer **123** and a third photoresist **133** are sequentially formed on a structure of FIG. 19E.

Referring to FIG. 20B, the third photoresist **132** is patterned. The third photoresist **133** that is exposed and developed is patterned to be removed at a first portion **133-1** corresponding to the third anode **103** and remain at a second portion **133-2** other than the first portion **133-1**.

Referring to FIG. 20C, the third lift-off layer **123** is etched by using a pattern of the third photoresist **133** of FIG. 20B as an etch mask and using the first solvent (not shown) including fluorine. During an etching process, a portion of the third lift-off layer **123** formed at a position corresponding to the first portion **133-1**, that is, on the third anode **103**, is etched. The third lift-off layer **123** is etched to form a third undercut profile UC3 under a boundary surface of the first portion **133-1** of the third photoresist **133**. When the third lift-off layer **123** is stripped after the etching process is performed, an undesirable residue of the third lift-off layer **123** may remain on the third anode **102**.

Referring to FIG. 20D, a third organic functional layer **143** and a third auxiliary cathode **183** are sequentially formed on a structure of FIG. 20C.

Referring to FIG. 20E, a third lift-off process is performed such that remaining portions of the third lift-off layer **123** are entirely removed, and as a result, the third organic functional layer **143** and the third auxiliary cathode **183** remain as patterns on the third anode **103**.

That is, according to the comparative example, when a lift-off layer is formed directly on an anode and then is patterned, it may not be possible to prevent a residual film of the lift-off layer from remaining on the anode.

Hereinafter, with reference to FIGS. 8 to 14F, an organic light-emitting display apparatus **2** according to an embodiment and a method of manufacturing the organic light-emitting display apparatus **2** are disclosed.

FIG. 8 illustrates a cross-sectional view of an organic light-emitting display apparatus **2** according to an embodiment, and FIG. 9 illustrates a plan view of a portion of the organic light-emitting display apparatus **2** according to the embodiment.

Referring to FIGS. 8 and 9, a plurality of anodes including a first anode **101**, a second anode **102**, and a third anode **103** that are spaced apart from each other on a substrate **100** may be provided. First to third organic functional layers **141**, **142**, and **143** including first to third emission layers may be respectively located on the first to third anodes **101**, **102**, and **103**. First to third auxiliary cathodes **181**, **182**, and **183** including a conductive material may be respectively located on the first to third organic functional layers **141**, **142**, and **143**. An integrally formed common electrode **180** may be located on the first to third auxiliary cathodes **181**, **182**, and **183**.

In the organic light-emitting display apparatus **2** according to the embodiment, a self-assembled monolayer **150** may surround the first to third anodes **101**, **102** and **103**, and

16

a pixel-defining layer **110** may be formed on the self-assembled monolayer **150**. For example, portions of the self-assembled monolayer **150** may be under the pixel defining layer. In this embodiment, the self-assembled monolayer **150** may overlap end portions of the first to third anodes **101**, **102**, and **103** by a predetermined thickness D2. Hereinafter, descriptions of this embodiment that are the same as those of the above-described embodiment illustrated in FIG. 1 may be omitted.

Referring to FIG. 10, a plurality of anodes including the first anode **101**, the second anode **102**, and the third anode **103** may be formed on the substrate **100**, and the self-assembled monolayer **150** may be formed over the plurality of anodes.

Referring to FIG. 11, the pixel-defining layer **110** may be formed to surround edges of the first anode **101**, the second anode **102**, and the third anode **103**. In this case, an end portion of the pixel-defining layer **110** may overlap an end portion of the self-assembled monolayer **150**. The self-assembled monolayer **150** may include a fluorine-containing functional group and a hydrolyzable reactive group.

Referring to FIG. 12A, a first lift-off layer **121** and a first photoresist **131** may be sequentially formed on the structure illustrated in FIG. 11.

The first lift-off layer **121** may include a fluoropolymer and may be formed by using a coating method, a printing method, or a deposition method. The first photoresist **131** may be formed on the first lift-off layer **121**. The first photoresist **131** at a position corresponding to the first anode **101** may be exposed through a first photomask M1 including an area M11 through which light L is transmitted.

The fluorine-containing functional group of the self-assembled monolayer **150** that closely contacts the first lift-off layer **121** may have a small difference in surface energy with respect to the first lift-off layer **121**, and thus the first lift-off layer **121** may be uniformly formed on the self-assembled monolayer **150**.

Referring to FIG. 12B, the first photoresist **131** may be developed. In the first photoresist **131** that is developed, a first portion **131-1** corresponding to the first anode **101** may be removed and a second portion **131-2** other than the first portion **131-1** may remain.

Referring to FIG. 12C, the first lift-off layer **121** may be etched by using a pattern of the first portion **131-1** of the first photoresist **131** as an etch mask. During an etching process, a portion of the first lift-off layer **121** formed at a position corresponding to the first portion **131-1**, that is, above the first anode **101**, may be etched. The first lift-off layer **121** may be etched by a first solvent including fluorine to form a first undercut profile UC1-1 under a boundary surface of the first portion **131-1** of the first photoresist **131**.

The self-assembled monolayer **150** may be well bonded to the top surface of the first anode **101** while the first lift-off layer **121** is etched.

Referring to FIG. 12D, a portion of the self-assembled monolayer **150** on the first anode **101** may be removed by performing first plasma heat treatment on the structure illustrated in FIG. 12C.

The Si—O bond between the first anode **101** and the self-assembled monolayer **150** shown in FIG. 21 may be cleanly broken by the first plasma heat treatment.

Referring to FIG. 12E, a first organic functional layer **141** including a first emission layer and a first auxiliary cathode **181** are sequentially formed on the structure illustrated in FIG. 12D. A portion of the first organic functional layer **141** may be formed at a position corresponding to the first portion **131-1**, that is, above the first anode **101**, and another

portion of the first organic functional layer **141** may be formed on the second portion **131-2** of the first photoresist **131**. A portion of the first auxiliary cathode **181** may be formed to cover a top surface of the first organic functional layer **141**, and another portion of the first auxiliary cathode **181** may be formed on the first organic functional layer **141** on the second portion **131-2** of the first photoresist **131** other than the first portion **131-1**.

Referring to FIG. **12F**, a lift-off process may be performed on the structure illustrated in FIG. **12E**. When the first lift-off layer **121** formed under the second portion **131-2** (see FIG. **12E**) of the first photoresist **131** is lifted off, portions of the first organic functional layer **141** and the first auxiliary cathode **181** formed over the second portion **131-2** of the first photoresist **131** may be removed, and portions of the first organic functional layer **141** and the first auxiliary cathode **181** formed over the first anode **101** may remain as patterns.

After the first unit process is performed, a second unit process of forming the second organic functional layer **142** that emits light of a different color from a color of light emitted by the first organic functional layer **141** may be performed on an area where the second anode **102** is located. The second unit process will now be described with reference to FIGS. **13A** to **13F**.

Referring to FIG. **13A**, a second lift-off layer **122** and a second photoresist **132** may be sequentially formed on the structure illustrated in FIG. **12F**. The second photoresist **132** at a position corresponding to the second anode **102** may be exposed through a second photomask **M2** including an area **M21** through which light **L** is transmitted.

The fluorine-containing functional group of the self-assembled monolayer **150** that closely contacts the second lift-off layer **122** may have a small difference in surface energy with respect to the second lift-off layer **122**, and thus the second lift-off layer **122** may be uniformly formed on the self-assembled monolayer **150**.

Referring to FIG. **13B**, the second photoresist **132** may be developed. In the second photoresist **132**, a first portion **132-1** corresponding to the second anode **102** is removed and a second portion **132-2** other than the first portion **132-1** may remain.

Referring to FIG. **13C**, the second lift-off layer **122** may be etched by using a pattern of the first portion **132-1** of the second photoresist **132** as an etch mask. A portion of the second lift-off layer **122** formed at a position corresponding to the first portion **132-1**, that is, above the second anode **102**, may be etched during an etching process. The second lift-off layer **122** may be etched by the first solvent including fluorine to form a second undercut profile **UC2-1** under a boundary surface of the first portion **132-1** of the second photoresist **132**. The self-assembled monolayer **150** may be well bonded to the top surface of the second anode **102** while the second lift-off layer **122** is etched.

Referring to FIG. **13D**, a portion of the self-assembled monolayer **150** on the second anode **102** may be removed by performing a second plasma heat treatment **PT2** on the structure illustrated in FIG. **13C**. An Si—O bond between the second anode **102** and the self-assembled monolayer **150** may be cleanly broken by the second plasma heat treatment.

Referring to FIG. **13E**, a second organic functional layer **142** including a second emission layer and a second auxiliary cathode **182** may be sequentially formed on the structure illustrated in FIG. **13D**. A portion of the second organic functional layer **142** may be formed at a position corresponding to the first portion **132-1**, that is, above the second anode **102**, and the other portion of the second organic

functional layer **142** may be formed on the second portion **132-2** of the second photoresist **132**. A portion of the second auxiliary cathode **182** may be formed to cover a top surface of the second organic functional layer **142**, and the other portion of the second auxiliary cathode **182** may be formed on the second organic functional layer **142** on the second portion **132-2** of the second photoresist **132** other than the first portion **132-1**.

Referring to FIG. **13F**, a lift-off process may be performed on a structure illustrated in FIG. **13E**. When the second lift-off layer **122** formed under the second portion **132-2** of the second photoresist **132** is lifted off, portions of the second organic functional layer **142** and the second auxiliary cathode **182** formed over the second portion **132-2** of the second photoresist **132** may be removed, and portions of the second organic functional layer **142** and the second auxiliary cathode **182** formed over the second anode **102** may remain as patterns.

After the second unit process is performed, a third unit process of forming the third organic functional layer **143** that emits light of a different color from a color of light emitted by the first and second organic functional layers **141** and **142** may be performed on an area where the third anode **103** is located. The third unit process will now be described with reference to FIGS. **14A** to **14F**.

Referring to FIG. **14A**, a third lift-off layer **123** and a third photoresist **133** may be sequentially formed on the structure illustrated in FIG. **13F**. The third photoresist **133** at a position corresponding to the third anode **103** may be exposed through a third photomask **M3** including an area **M31** through which light **L** is transmitted.

The fluorine-containing functional group of the self-assembled monolayer **150** that closely contacts the third lift-off layer **123** may have a small difference in surface energy with respect to the third lift-off layer **123**, and thus the third lift-off layer **123** may be uniformly formed on the self-assembled monolayer **150**.

Referring to FIG. **14B**, the third photoresist **133** may be developed. In the third photoresist **133**, a first portion **133-1** corresponding to the third anode **103** may be removed and a second portion **133-2** other than the first portion **133-1** may remain.

Referring to FIG. **14C**, the third lift-off layer **123** may be etched by using a pattern of the first portion **133-1** of the third photoresist **133** as an etch mask. A portion of the third lift-off layer **123** formed at a position corresponding to the first portion **133-1**, that is, above the third anode **103**, may be etched during an etching process. The third lift-off layer **123** may be etched by the first solvent including fluorine to form a third undercut profile **UC3-1** under a boundary surface of the first portion **133-1** of the third photoresist **133**. The self-assembled monolayer **150** may be well bonded to the top surface of the third anode **103** while the third lift-off layer **123** is etched.

Referring to FIG. **14D**, a portion of the self-assembled monolayer **150** on the third anode **103** may be removed by performing a third plasma heat treatment on a structure illustrated in FIG. **14C**. An Si—O bond between the third anode **103** and the self-assembled monolayer **150** may be cleanly broken by the third plasma heat treatment.

Referring to FIG. **14E**, a third organic functional layer **143** including a third emission layer and a third auxiliary cathode **183** may be sequentially formed on a structure illustrated in FIG. **14D**. A portion of the third organic functional layer **143** may be formed at a position corresponding to the first portion **133-1**, that is, above the third anode **103**, and another portion of the third organic functional layer **143** may be

formed on the second portion **133-2** of the third photoresist **133**. A portion of the third auxiliary cathode **183** may be formed to cover a top surface of the third organic functional layer **143**, and another portion of the third auxiliary cathode **183** may be formed on the third organic functional layer **143** on the second portion **133-2** of the third photoresist **133** other than the first portion **133-1**.

Referring to FIG. **14F**, a lift-off process may be performed on the structure illustrated in FIG. **14E**. When the third lift-off layer **123** formed under the second portion **133-2** of the third photoresist **133** is lifted off, portions of the third organic functional layer **143** and the third auxiliary cathode **183** formed over the second portion **133-2** of the third photoresist **133** may be removed, and portions of the third organic functional layer **143** and the third auxiliary cathode **183** formed over the third anode **103** may remain as patterns.

Hereinafter, a method for manufacturing an organic light-emitting display apparatus **3** according to an embodiment will be briefly described with reference to FIGS. **15A** to **17E**.

The present embodiment differs from the previous embodiments in that a self-assembled monolayer is used as a lift-off layer without independently using the lift-off layer and the self-assembled monolayer.

FIGS. **15A** to **15E** illustrate cross-sectional views for explaining a first unit process of an organic light-emitting display apparatus **3** according to the embodiment.

Referring to FIG. **15A**, first to third anodes **101**, **102**, and **103** may be formed on a substrate **101**, and a pixel defining layer **110** defining a plurality of pixels may be formed to cover end portions of the first to third anodes **101**, **102**, and **103**. After the pixel-defining layer **110** is formed, a first self-assembled monolayer **151** may be formed. A first photoresist **131** may be formed on the first self-assembled monolayer **151**.

The first self-assembled monolayer **151** may include a hydrolyzable reactive group and a fluorine-containing functional group. In the present embodiment, as described above, the first photoresist **131** may be formed on the first self-assembled monolayer **151**. The first photoresist **131** may, but need not, include a fluoropolymer. Accordingly, the first self-assembled monolayer **151** of the present embodiment need not necessarily include a fluorine-containing functional group as in the above-described embodiment. For example, the first self-assembled monolayer **151** may further include octadecyltrichlorosilane (OTS), dichlorodimethylsilane (DDMS), tetraethoxysilane (TEOS), or the like.

The first photoresist **131** at a position corresponding to the first anode **101** may be exposed through a first photomask **M1** including an area **M11** through which light **L** is transmitted. The fluorine-containing functional group of the first self-assembled monolayer **151** that closely contacts the first photoresist **131** may use a material having a small difference in surface energy with respect to a photosensitive material contained in the first photoresist **131**.

Referring to FIG. **15B**, the first photoresist **131** may be developed. In the first photoresist **131** that is developed, a first portion **131-1** corresponding to the first anode **101** may be removed and a second portion **131-2** other than the first portion **131-1** may remain.

Referring to FIG. **15C**, a portion of the first self-assembled monolayer **151** on the first anode **101** may be removed by performing a first plasma heat treatment **PT1** on the structure illustrated in FIG. **15B**. An Si—O bond between the first anode **101** and the first self-assembled monolayer **151** may be cleanly broken by the first plasma heat treatment **PT1**.

Referring to FIG. **15D**, a first organic functional layer **141** including a first emission layer and a first auxiliary cathode **181** may be sequentially formed on the structure illustrated in FIG. **15C**. A portion of the first organic functional layer **141** may be formed at a position corresponding to the first portion **131-1**, that is, above the first anode **101**, and another portion of the first organic functional layer **141** may be formed on the second portion **131-2** of the first photoresist **131**. A portion of the first auxiliary cathode **181** may be formed to cover a top surface of the first organic functional layer **141**, and another portion of the first auxiliary cathode **181** may be formed on the first organic functional layer **141** on the second portion **131-2** of the first photoresist **131** other than the first portion **131-1**.

Referring to FIG. **15E**, a lift-off process may be performed on the structure illustrated in FIG. **15D**. When the first photoresist **131** is lifted off, portions of the first organic functional layer **141** and the first auxiliary cathode **181** formed over the second portion **131-2** of the first photoresist **131** may be removed, and portions of the first organic functional layer **141** and the first auxiliary cathode **181** formed over the first anode **101** may remain as patterns. The first self-assembled monolayer **151** located between the pixel-defining layer **110** and the first photoresist **131** may also be removed.

FIGS. **16A** to **16E** illustrate cross-sectional views for explaining a second unit process of the organic light-emitting display apparatus **3** according to this embodiment.

Referring to FIG. **16A**, a second self-assembled monolayer **152** and a second photoresist **132** may be sequentially formed on the structure illustrated in FIG. **15E**. The second photoresist **132** at a position corresponding to the second anode **102** may be exposed through a second photomask **M2** including an area **M21** through which light **L** is transmitted. A functional group of the second self-assembled monolayer **152** that closely contacts the second photoresist **132** may use a material having a small difference in surface energy with respect to a photosensitive material contained in the second photoresist **132**.

Referring to FIG. **16B**, the second photoresist **132** may be developed. In the second photoresist **132** that is developed, a first portion **132-1** corresponding to the second anode **102** may be removed and a second portion **132-2** other than the first portion **132-1** may remain.

Referring to FIG. **16C**, a portion of the second self-assembled monolayer **152** on the second anode **102** may be removed by performing second plasma heat treatment **PT2** on a structure illustrated in FIG. **16B**. An Si—O bond between the second anode **102** and the second self-assembled monolayer **152** may be cleanly broken by the second plasma heat treatment **PT2**.

Referring to FIG. **16D**, a second organic functional layer **142** including a first emission layer and a second auxiliary cathode **182** may be sequentially formed on the structure illustrated in FIG. **16C**. A portion of the second organic functional layer **142** may be formed at a position corresponding to the first portion **132-1**, that is, above the second anode **102**, and another portion of the second organic functional layer **142** may be formed on the second portion **132-2** of the second photoresist **132**. A portion of the second auxiliary cathode **182** may be formed to cover a top surface of the second organic functional layer **142**, and another portion of the second auxiliary cathode **182** may be formed on the second organic functional layer **142** on the second portion **132-2** of the second photoresist **132** other than the first portion **132-1**.

Referring to FIG. 16E, a lift-off process is performed on the structure illustrated in FIG. 16D. When the second photoresist 132 is lifted off, portions of the second organic functional layer 142 and the second auxiliary cathode 182 formed over the second portion 132-2 of the second photoresist 132 may be removed, and portions of the second organic functional layer 142 and the second auxiliary cathode 182 formed over the second anode 102 may remain as patterns. The second self-assembled monolayer 152 located between the pixel-defining layer 110 and the second photoresist 132 may also be removed.

FIGS. 17A to 17E illustrate cross-sectional views for explaining a third unit process of the organic light-emitting display apparatus 3 according to this embodiment.

The third unit process is similar to the second unit process described with reference to FIGS. 16A to 16E, except that a third self-assembled monolayer 153 is formed and finally removed, and thus, a detailed description of the third unit process will not be repeated.

Although not shown in the drawings, the organic light-emitting display apparatuses described above may further include a sealing member for sealing an organic emission layer. The sealing member may include a glass substrate, a metal foil, a thin film encapsulating layer in which an inorganic layer and an organic layer are mixed, or the like.

By way of summation and review, embodiments provide an organic light-emitting display apparatus with increased resolution and reduced defects and cost. Embodiments further provide a method of manufacturing the organic light-emitting display.

According to one or more embodiments as described above, an emission layer is formed without using a fine metal mask (FMM). Accordingly, a high resolution display panel may be formed.

A self-assembled monolayer may be formed between an anode and a lift-off layer. Accordingly, the self-assembled monolayer may prevent a residue of lift-off layer from remaining on the anode. Thus, quality of an organic light-emitting display apparatuses according to the embodiments may be improved.

Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope thereof as set forth in the following claims.

What is claimed is:

1. An organic light-emitting display apparatus, comprising:

- a substrate;
- a first first electrode on the substrate;
- a first organic functional layer on the first first electrode, the first organic functional layer including a first emission layer;
- a first second electrode on the first organic functional layer;
- a second first electrode on the substrate, the second first electrode being spaced apart from the first first electrode;

a second organic functional layer on the second first electrode, the second organic functional layer including a second emission layer;

a second second electrode on the second organic functional layer; and

a self-assembled layer between the first organic functional layer and the second organic functional layer, the self-assembled layer containing fluorine and a hydrolyzable reactive group.

2. The organic light-emitting display apparatus as claimed in claim 1, wherein a color of light emitted from the first emission layer is different from a color of light emitted from the second emission layer.

3. The organic light-emitting display apparatus as claimed in claim 1, wherein each of the first organic functional layer and the second organic functional layer further includes at least one of a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer.

4. The organic light-emitting display apparatus as claimed in claim 1, further comprising a pixel-defining layer including an insulating layer and covering an edge of the first first electrode and an edge of the second first electrode.

5. The organic light-emitting display apparatus as claimed in claim 4, wherein an edge portion of the first organic functional layer and an edge portion of the second organic functional layer are on an inclined surface of the pixel-defining layer.

6. The organic light-emitting display apparatus as claimed in claim 4, wherein the self-assembled layer is on the pixel-defining layer and surrounds the first organic functional layer and the second organic functional layer.

7. The organic light-emitting display apparatus as claimed in claim 6, wherein the self-assembled layer is spaced apart from end portions of the first organic functional layer and the second organic functional layer by a preset gap.

8. The organic light-emitting display apparatus as claimed in claim 4, wherein the self-assembled layer is under the pixel-defining layer and surrounds peripheries of the first first electrode and the second first electrode.

9. The organic light-emitting display apparatus as claimed in claim 8, wherein the self-assembled layer overlaps end portions of the first first electrode and the second first electrode.

10. The organic light-emitting display apparatus as claimed in claim 1, wherein the self-assembled layer includes a fluorocarbon group ($-\text{CF}_3$).

11. The organic light-emitting display apparatus as claimed in claim 1, wherein the first first electrode and the second first electrode include a conductive oxide.

12. The organic light-emitting display apparatus as claimed in claim 11, wherein the first first electrode and the second first electrode include at least one of indium tin oxide, indium zinc oxide, zinc oxide, indium oxide, indium gallium oxide, and aluminum zinc oxide.

13. The organic light-emitting display apparatus as claimed in claim 1, further comprising a common electrode integrally formed on the first second electrode and the second second electrode.

14. A method of manufacturing an organic light-emitting display apparatus, the method comprising:

- forming a first first electrode and a second first electrode on a substrate so as to be spaced apart from each other;
- forming a self-assembled layer containing fluorine on the first first electrode and the second first electrode;
- sequentially forming a first lift-off layer and a first photoresist on the self-assembled layer;

23

removing a portion of the first lift-off layer and a portion of the first photoresist in an area corresponding to the first first electrode and allowing the self-assembled layer to remain;

removing a portion of the self-assembled layer on the first first electrode by performing first plasma heat treatment; and

sequentially forming, on the first first electrode, a first organic functional layer and a first second electrode, wherein the first organic functional layer includes a first emission layer, and lifting off a remaining portion of the first lift-off layer.

15. The method as claimed in claim 14, wherein the first lift-off layer has a fluorine content ranging from 20 wt % to 60 wt %.

16. The method as claimed in claim 14, wherein the first organic functional layer and the first second electrode are formed by a deposition process.

17. The method as claimed in claim 14, wherein removing the portion of the first photoresist includes performing a photolithography process.

18. The method as claimed in claim 14, wherein the first lift-off layer is etched and removed by using a first solvent containing fluorine.

19. The method as claimed in claim 14, wherein the self-assembled layer is formed by a vapor deposition method.

20. The method as claimed in claim 14, wherein the self-assembled layer includes a hydrolyzable reactive group and a fluorine-containing functional group.

24

21. The method as claimed in claim 14, further comprising:

sequentially forming a second lift-off layer and a second photoresist after lifting off the remaining portion of the first lift-off layer;

removing a portion of the second lift-off layer and a portion of the second photoresist in an area corresponding to the second first electrode and allowing the self-assembled layer to remain;

removing a portion of the self-assembled layer on the second first electrode by performing second plasma heat treatment;

sequentially forming a second organic functional layer and a second second electrode on the second first electrode, wherein the second organic functional layer includes a second emission layer, and

lifting off a remaining portion of the second lift-off layer.

22. The method as claimed in claim 14, further comprising forming, between the first first electrode and the second first electrode, a pixel-defining layer including an insulating layer.

23. The method as claimed in claim 22, wherein the self-assembled layer is formed on the pixel-defining layer.

24. The method as claimed in claim 22, wherein the self-assembled layer is formed under the pixel-defining layer.

25. The method as claimed in claim 21, further comprising forming a common electrode in an integral form on the first second electrode and the second second electrode.

* * * * *

专利名称(译)	包含含氟的自组装层的有机发光显示装置及其制造方法		
公开(公告)号	US10658438	公开(公告)日	2020-05-19
申请号	US15/907430	申请日	2018-02-28
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM JAESIK LEE YEONHWA LEE JOONGU JEONG SEHOON		
发明人	KIM, JAESIK LEE, YEONHWA LEE, JOONGU JEONG, SEHOON		
IPC分类号	H01L51/56 H01L51/00 H01L27/32 H01L51/52		
CPC分类号	H01L51/56 H01L27/3246 H01L51/0023 H01L51/0016 H01L51/5206 H01L2227/323 H01L2251/305 H01L2251/308 H01L51/5221 H01L51/5253		
优先权	1020170030982 2017-03-13 KR		
其他公开文献	US20180261656A1		
外部链接	Espacenet		

摘要(译)

一种有机发光显示装置，包括基板，在基板上的第一第一电极，在第一第一电极上的第一有机功能层，第一有机功能层包括第一发射层，在第一有机功能层上的第一第二电极层，衬底上的第二第一电极，第二第一电极与第一第一电极间隔开，第二第一电极上的第二有机功能层，第二有机功能层包括第二发射层，第二第二电极 第二有机功能层，以及在第一有机功能层和第二有机功能层之间的自组装层，该自组装层包含氟。

