



US008981378B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 8,981,378 B2**
(45) **Date of Patent:** **Mar. 17, 2015**

(54) **MOTHER SUBSTRATE FOR ORGANIC
LIGHT-EMITTING DISPLAY APPARATUS**

USPC 257/48, 32, 72, 99
See application file for complete search history.

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin
(KR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(72) Inventors: **Kwang-Min Kim**, Yongin (KR);
Won-Kyu Kwak, Yongin (KR); **Jin-Tae
Jeong**, Yongin (KR); **Ji-Hyun Ka**,
Yongin (KR)

8,367,444	B2 *	2/2013	Kim et al.	438/34
8,614,591	B2 *	12/2013	Kim et al.	324/762.07
2006/0043508	A1 *	3/2006	Ohta et al.	257/417
2008/0198284	A1 *	8/2008	Oyamada	349/39
2009/0278835	A1	11/2009	Ka	
2010/0052564	A1 *	3/2010	Park et al.	315/291
2011/0080173	A1	4/2011	Kim et al.	
2012/0146085	A1 *	6/2012	Park et al.	257/99

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin
(KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

FOREIGN PATENT DOCUMENTS

JP	09-265110	10/1997
KR	10-2009-0116334	11/2009
KR	10-2011-0037638	4/2011
KR	10-2012-0065521	6/2012

(21) Appl. No.: **14/219,763**

(22) Filed: **Mar. 19, 2014**

* cited by examiner

(65) **Prior Publication Data**

US 2015/0008432 A1 Jan. 8, 2015

Primary Examiner — Yu-Hsi D Sun

Assistant Examiner — Chi-Hua Yang

(30) **Foreign Application Priority Data**

Jul. 5, 2013 (KR) 10-2013-0079034

(74) *Attorney, Agent, or Firm* — H.C. Park & Associates,
PLC

(57) **ABSTRACT**

(51) **Int. Cl.**
H01L 27/14 (2006.01)
H01L 27/12 (2006.01)
H01L 21/66 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 27/124** (2013.01); **H01L 22/32**
(2013.01)
USPC **257/72**; **257/32**

(58) **Field of Classification Search**
CPC H01L 29/04

A mother substrate for an organic light-emitting display apparatus. The mother substrate has a panel area and a peripheral area surrounding the panel area, pixels disposed in a display area of the panel area, pads that are disposed in a non-display area of the panel area and are coupled to the pixels, test wirings disposed in the peripheral area, a local buffer electrically connected to the test wirings, a bridge wiring connecting the local buffer to one of the pads, and a dummy resistance layer having one end in contact with the bridge wiring and another end in contact with one of the test wirings.

20 Claims, 6 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5



MOTHER SUBSTRATE FOR ORGANIC LIGHT-EMITTING DISPLAY APPARATUS

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority from and the benefit of Korean Patent Application No. 10-2013-0079034, filed on Jul. 5, 2013, which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND

1. Field

Exemplary embodiments of the present invention relate to a display apparatus, and more particularly, to a mother substrate for an organic light-emitting display apparatus.

2. Discussion of the Background

In general, organic light-emitting display apparatuses are respectively manufactured in various panel areas included in a mother substrate, and the organic light-emitting display apparatuses are individually separated along cutting lines on the edges of the panel areas when the manufacturing of the organic light-emitting display apparatuses are completed. Tests for applying various test signals and power to the organic light-emitting apparatuses are performed in order to examine the presence of defects before the separation of the individual organic light-emitting apparatuses. Various test signals and a power supply are transmitted to the organic light-emitting display apparatus through test wirings disposed in a peripheral area around the panel area in which the organic light-emitting apparatus is disposed. The test wirings are coupled to pads included in the organic light-emitting display apparatus.

However, because some pads are not directly connected through test wirings and wiring lines but are connected through a circuit unit including a thin film transistor, some pads may be substantially isolated. Thus, the pads may be easily corroded as a result of an etchant used during a patterning process of a pixel electrode disposed on the pads.

The above information disclosed in this Background section is only for enhancement of understanding of the background of the invention and, therefore, it may contain information that does not form the prior art that is already known in this country to a person of ordinary skill in the art.

SUMMARY

Exemplary embodiments of the present invention provide a mother substrate for an organic light-emitting display apparatus having a structure that may prevent the corrosion of the pad during the patterning process of the pixel electrode.

Additional features of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention.

An exemplary embodiment of the present invention provides a mother substrate for an organic light-emitting display apparatus, the mother substrate including: a panel area and a peripheral area surrounding the panel area; pixels disposed in a display area of the panel area; pads disposed in a non-display area of the panel area and coupled to the pixels; test wirings disposed in the peripheral area; a local buffer electrically connected to the test wirings; a bridge wiring connecting the local buffer to one of the pads; and a dummy resistance layer having one end in contact with the bridge wiring and another end in contact with one of the test wirings.

An exemplary embodiment of the present invention provides a mother substrate for an organic light-emitting display apparatus, the mother substrate including: a panel area and a peripheral area surrounding the panel area; pixels disposed in a display area of the panel area; a first pad and a second pad disposed in a non-display area of the panel area and coupled to the pixels; test wirings disposed in the peripheral area; a local buffer electrically connected to the test wirings; a first bridge wiring connecting the local buffer to the first pad; a dummy resistance layer having one end being in contact with the bridge wiring and another end being in contact with one of the test wirings; and a second bridge wiring directly connecting another one of the test wirings to the second pad.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate exemplary embodiments of the invention, and together with the description serve to explain the principles of the invention.

FIG. 1 is a plan view schematically illustrating a mother substrate for an organic light-emitting display apparatus, according to an exemplary embodiment of the present invention.

FIG. 2 is an enlarged plan view of region "II" of FIG. 1.

FIG. 3 is a cross-sectional view schematically illustrating a cross-section taken along line III-III of FIG. 2.

FIG. 4 is an enlarged plan view of region "IV" of FIG. 1.

FIG. 5 is a cross-sectional view schematically illustrating a cross-section taken along line V-V of FIG. 4.

FIG. 6 is a cross-sectional view schematically illustrating a state during a manufacturing process of the mother substrate for an organic light-emitting display apparatus of FIG. 3.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

The invention is described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as limited to the exemplary embodiments set forth herein. Rather, these exemplary embodiments are provided so that this disclosure is thorough, and will fully convey the scope of the invention to those skilled in the art. In the drawings, the size and relative sizes of elements may be exaggerated for clarity. Like reference numerals in the drawings denote like elements.

It will be understood that although the terms "first", "second", etc. may be used herein to describe various components, these components should not be limited by these terms. These components are only used to distinguish one component from another. As used herein, the singular forms "a," "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise.

It will be further understood that the terms "comprises" and/or "comprising" used herein specify the presence of stated features or components, but do not preclude the presence or addition of one or more other features or components. It will be understood that when a layer, region, or component is referred to as being "formed on," another layer, region, or

component, it can be directly or indirectly formed on the other layer, region, or component. That is, for example, intervening layers, regions, or components may be present.

It will be understood that when an element or layer is referred to as being “on”; “connected to”; or “coupled to” another element or layer, it can be directly on; directly connected to; or directly coupled to the other element or layer, or intervening elements or layers may be present. In contrast, when an element or layer is referred to as being “directly on”; “directly connected to”; or “directly coupled to” another element or layer, there are no intervening elements or layers present. It will be understood that for the purposes of this disclosure, “at least one of X, Y, and Z” can be construed as X only, Y only, Z only, or any combination of two or more items X, Y, and Z (e.g., XYZ, XYY, YZ, ZZ).

In the following examples, the x-axis and the y-axis are not limited to two axes of the rectangular coordinate system, and may be interpreted in a broader sense. For example, the x-axis and the y-axis may be perpendicular to each another, or may lie in different directions that are not perpendicular to each another.

As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

FIG. 1 is a plan view schematically illustrating a mother substrate **10** for an organic light-emitting display apparatus, according to an exemplary embodiment of the present invention. The mother substrate **10** includes a panel area CA, in which an organic light-emitting display panel is disposed, and a peripheral area PA that is a “dead area” around the panel area CA. A plurality of matrix-type panel areas CA may be included in the mother substrate **10** for an organic light-emitting display apparatus.

The panel area CA includes a display area DA, in which an image is displayed, and a non-display area NDA, in which an image is not displayed. Pixels are disposed in the display area DA. The pixels include a plurality of thin film transistors (TFTs) and an organic light-emitting device electrically connected to the plurality of TFTs. A driver for controlling the pixels disposed in the display area DA, pads for applying electrical signals transmitted from the outside to the pixels disposed in the display area DA, and wirings for electrically connecting the pads and the pixels may be disposed in the non-display area NDA.

Test wirings **306** are disposed in the peripheral area PA outside the panel area CA of the mother substrate **10** for an organic light-emitting display apparatus, and the test wirings **306** and the pads are electrically connected through a structure.

FIG. 2 is an enlarged plan view of region “II” of FIG. 1. Referring to FIG. 2, for example, a first pad **106a** is electrically coupled to the test wirings **306** through a local buffer LB, a first bridge wiring **106b**, and a dummy resistance layer **102a**. FIG. 3, to be described later, is a cross-sectional view schematically illustrating a cross-section taken along line III-III of FIG. 2.

FIG. 4 is an enlarged plan view of region “IV” of FIG. 1. Referring to FIG. 4, for example, a second pad **206a** is electrically connected to the test wirings **306** through a second bridge wiring **204b**. FIG. 5 is a cross-sectional view schematically illustrating a cross-section taken along line V-V of FIG. 4, and will be described in more detail with reference to FIG. 3 below.

The mother substrate **10** for an organic light-emitting display apparatus disclosed in the present specification is different from a base substrate **100**, and denotes a substrate in which an organic light-emitting display panel is formed in the

panel area CA on the base substrate **100**, and test wirings or the like are formed in the peripheral area PA.

Referring to FIGS. 3 and 5, the base substrate **100** may be formed of various materials, such as a glass material, a metallic material, or a plastic material. A buffer layer **101** formed of silicon oxide or silicon nitride is disposed on the base substrate **100** in order to planarize a surface of the base substrate **100** and/or prevent the penetration of impurities into a semiconductor layer **102**.

The TFT disposed in the display area DA includes the semiconductor layer **102**, a gate electrode **104**, and source/drain electrodes **106s** and **106d**. The semiconductor layer **102** may include amorphous silicon, polysilicon, or an organic semiconductor material. A dummy resistance layer **102a** is disposed in the peripheral area PA, and the dummy resistance layer **102a** is formed of the same material and disposed on the same layer as the semiconductor layer **102** of the TFT disposed in the display area DA.

The gate electrode **104** is disposed adjacent to a channel region of the semiconductor layer **102**, where the source/drain electrodes **106s** and **106d** are in electrical communication with each other according to a signal applied to the gate electrode **104**. The gate electrode **104**, for example, may be formed as a single layer or multiple layers of one or more materials of aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), molybdenum (Mo), titanium (Ti), tungsten (W), and copper (Cu), in consideration of adhesion to adjacent layers, surface flatness of a stacked layer, and processability. A gate dielectric layer **103** formed of silicon oxide and/or silicon nitride may be disposed between the semiconductor layer **102** and the gate electrode **104**, in order to insulate the semiconductor layer **102** and the gate electrode **104**. An interlayer dielectric **105** may be disposed on the gate electrode **104**, and the interlayer dielectric **105** may be formed as a single layer or multiple layers of a material, such as silicon oxide or silicon nitride. The gate dielectric layer **103** and the interlayer dielectric **105** may be formed on the entire base substrate **100** and, for example, may also be disposed on the peripheral area PA in addition to the panel area CA.

The source/drain electrodes **106s** and **106d** are disposed on the interlayer dielectric **105**. The source/drain electrodes **106s** and **106d** are respectively electrically connected to the semiconductor layer **102** through contact holes formed in the interlayer dielectric **105** and the gate dielectric layer **103**. The source/drain electrodes **106s** and **106d**, for example, may be formed as a single layer or multiple layers of one or more materials of Al, Pt, Pd, Ag, Mg, Au, Ni, Nd, Ir, Cr, Li, Ca, Mo, Ti, W, and Cu in consideration of conductivity. For example, in order to protect an easily oxidized aluminum layer (see **126b** of FIG. 6), the source/drain electrodes **106s** and **106d** may have a multilayer structure in which titanium layers (see **116b** and **136b** of FIG. 6) having high corrosion resistance are stacked on and under the aluminum layer (see **126b** of FIG. 6). Pads are disposed in the non-display area NDA of the panel area CA. The pads may have the same stack structure, may be formed of the same material, and may be disposed on the same layer as the source/drain electrodes **106s** and **106d** of the TFT. Also, the test wirings **306** are disposed in the peripheral area PA. The test wirings **306** may also have the same stack structure, may be formed of the same material, and may be disposed on the same layer as the source/drain electrodes **106s** and **106d** of the TFT.

A passivation layer **107** covering the TFT may be disposed in order to protect the TFT and to planarize a top surface thereof on which an OLED is to be formed. The passivation

layer **107**, for example, may be formed of an inorganic material, such as silicon oxide, silicon nitride, or silicon oxynitride, and may be formed of acrylic organic materials or benzocyclobutene (BCB). Although the passivation layer **107** is illustrated as a single layer in FIGS. **3**, **5** and **6**, it may also have a multilayer structure.

An OLED having a pixel electrode **111**, a counter electrode **112**, and an intermediate layer **113** disposed therebetween is disposed on the passivation layer **107** in the display area DA. The intermediate layer **113** includes a light-emitting layer.

An opening exposing one of the source/drain electrodes **106s** and **106d** of the TFT is included in the passivation layer **107**. The pixel electrode **111**, which is electrically connected to the TFT by being in contact with one of the source/drain electrodes **106s** and **106d** through the opening, is disposed on the passivation layer **107**. The pixel electrode **111** may be formed as a (semi) transparent electrode or a reflective electrode. In a case where the pixel electrode **111** is formed as the (semi) transparent electrode, the pixel electrode **111**, for example, may be formed of indium tin oxide (ITO), indium zinc oxide (IZO), ZnO, In₂O₃, indium gallium oxide (IGO), or aluminum zinc oxide (AZO). In a case where the pixel electrode **111** is formed as the reflective electrode, the pixel electrode **111** may have a reflective layer formed of Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, or a compound thereof, and a layer formed of ITO, IZO, ZnO, In₂O₃, IGO, or AZO. However, the present invention is not limited thereto. The pixel electrode **111** may be formed of various other materials, and various modifications may also be possible. For example, the structure thereof may be a single layer or a multilayer structure.

A pixel-defining layer **109** may be disposed on the passivation layer **107**. The pixel-defining layer **109** defines a pixel by having an opening corresponding to each pixel, i.e., an opening at least exposing a center portion of the pixel electrode **111**. Also, the pixel-defining layer **109** operates to prevent the occurrence of arcs at ends of the pixel electrode **111** by increasing the distance between the ends of the pixel electrode **111** and the counter electrode **112** on the pixel electrode **111**. As illustrated in FIG. **3**, the pixel-defining layer **109** may also be disposed as a protective layer **109a** in one or both of the non-display area NDA and the peripheral area PA, in addition to the display area DA. However, the pixel-defining layer **109** need not be disposed in either the non-display area NDA or the peripheral area PA. The pixel-defining layer **109**, for example, may be formed of an organic material, such as polyimide.

The intermediate layer **113** of the OLED may include a low molecular weight material or a polymer material. In a case where the intermediate layer **113** includes a low molecular weight material, the intermediate layer **113** may be formed by stacking a hole injection layer (HIL), a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and an electron injection layer (EIL) in a single or composite structure. Various materials, including copper phthalocyanine (CuP_C), N,N'-di(naphthalene-1-yl)-N,N'-diphenyl-benzidine (NPB), and tris-8-hydroxyquinoline aluminum (Alq₃), may be used as a usable organic material. These layers may be formed by vacuum deposition.

In a case where the intermediate layer **113** includes a polymer material, the intermediate layer **113** may generally have a structure including the HTL and the EML. In this case, poly(ethylenedioxythiophene) (PEDOT) may be used as the HTL, and a polymer material, such as a poly(phenylenevinylene) (PPV) and a polyfluorene, may be used as the EML. The HTL and the EML may be formed by screen printing, inkjet printing, or laser induced thermal imaging (LITI).

However, the intermediate layer **113** is not limited thereto, and the intermediate layer **113** may have various other structures.

The counter electrode **112** is disposed on the display area DA, and the counter electrode **112** may cover the entire display area DA, as illustrated in FIG. **3**. The counter electrode **112** may correspond to the pixel electrodes **111** by being formed in one piece in the OLEDs. The counter electrode **112** may be formed as a (semi) transparent electrode or a reflective electrode. In a case where the counter electrode **112** is formed as the (semi) transparent electrode, the counter electrode **112** may have a layer formed of a low work function metal, such as Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, or a compound thereof, and a (semi) transparent conductive layer, such as an ITO, IZO, ZnO, or In₂O₃ layer. In a case where counter electrode **112** is formed as the reflective electrode, the counter electrode **112** may have a layer formed of Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, or a compound thereof. However, the configuration and material of the counter electrode **112** are not limited thereto, and various modifications may be possible.

The test wirings **306** are disposed between the panel area and extend in one direction. For example, the test wirings **306** are disposed near the panel area CA, in which the pads are disposed, and may be disposed on the interlayer dielectric **105** in the same manner as the source/drain electrodes **106s** and **106d** of the TFT. The test wirings **306** are connected to the pads in a dummy region disposed at edges of the mother substrate **10**, and is configured to receive electrical signals from the outside through the pads in the dummy region. Each of the test wirings **306** transmits a different electrical signal. For example, the test wirings **306** may include a first test wiring **306a**, a second test wiring **306b**, and a third test wiring **306c**. The first test wiring **306a** transmits a first electrical signal, the second test wiring **306b** transmits a second electrical signal, and the third test wiring **306c** transmits a third electrical signal. The second electrical signal may be direct current power. However, the number of the test wirings or the types of the signals transmitted by the test wirings is not limited to descriptions in the present specification.

Because the test wirings **306** have a width greater than those of other wirings in order to prevent a voltage drop as a result of a high line resistance, an area of the mother substrate **10** occupied by the test wirings **306** is wider than an area of the mother substrate **10** occupied by the other wirings. The test wirings **306** may transmit a greater number of carriers (electrons or holes) in comparison to the other wirings as a result of the wider area.

Hereinafter, the present invention will be described with reference to FIGS. **2** and **4** in addition to FIGS. **3** and **5**. The pads respectively receive different electrical signals, wherein the first pad **106a** may be regarded as a pad that mainly receives a clock signal composed of high and low signals. The second pad **206a** may be regarded as a pad that receives direct current power having a preset value or an electrical signal which is not a clock signal.

Although high and low values of the clock signal applied to the first pad **106a** should be distinguished, there is a greater risk that distortion of the clock signal may occur as a result of the IR drop of the test wirings **306**. Therefore, as illustrated in FIG. **2**, the test wirings **306** and the first pad **106a** may be coupled by the local buffer LB.

The local buffer LB amplifies electrical signals and includes a plurality of thin film transistors and a plurality of capacitors. Because the first pad **106a** is connected to the test wirings **306** through the local buffer LB, the first pad **106a** is substantially isolated from the test wirings **306**. Although described later in FIG. **6**, if the dummy resistance layer **102a**

does not exist, galvanic corrosion may occur in the aluminum layer (see **126b** of FIG. 6) of the first pad **106a** as a result of an etchant used during the patterning of the pixel electrode **111** of the TFT.

One end of the dummy resistance layer **102a** is in direct contact with the first bridge wiring **106b** that is directly connected to the first pad **106a**, and the other end thereof is in direct contact with one of the test wirings **306**. Because the first bridge wiring **106b** and the test wirings **306** are all included in the same layer as the source/drain electrodes of the TFT, contact holes are included in the gate dielectric layer **103** and the interlayer dielectric **105** in order for the dummy resistance layer **102a** to be physically in contact with the first bridge wiring **106b** and one of the test wirings **306**. The dummy resistance layer **102a** connects the first pad **106a**, which is substantially isolated by the local buffer LB, to one of the test wirings **306** through the first bridge wiring **106b**. Because the first pad **106a** is not substantially isolated from the test wirings **306** as a result of the dummy resistance layer **102a**, the galvanic corrosion due to the etchant used during the patterning of the pixel electrode **111** of the TFT may be prevented.

As described above, the dummy resistance layer **102a** is formed of the same material and disposed on the same layer as the semiconductor layer **102** of the TFT. The dummy resistance layer **102a**, for example, may be formed of polysilicon. The dummy resistance layer **102a** may have a non-linear shape in plan view. Because the dummy resistance layer **102a** is formed of a semiconductor material and has the non-linear shape, the dummy resistance layer **102a** may exhibit a higher resistance, in comparison to a case where the dummy resistance layer **102a** is formed of a conductive material and has a linear shape. Because the dummy resistance layer **102a** may exhibit a relatively high resistance, the local buffer LB may operate properly and interference to the electrical signal applied to the first pad **106a** through the local buffer LB may be significantly reduced or prevented.

The test wiring, which is in contact with the dummy resistance layer **102a**, may be the second test wiring **306b** that transmits direct current power. The second test wiring **306b** in contact with the dummy resistance layer **102a** may be directly connected to the local buffer LB. For example, the local buffer LB may be directly connected to the test wirings **306**. Since FIG. 2 is an exemplary illustration, the type and number of the test wirings **306** connected to the local buffer LB are not limited.

The first bridge wiring **106b**, which is in contact with the dummy resistance layer **102a**, may be formed of the same material and may be disposed in the same layer as the first pad **106a**. For example, at least a part of the first bridge wiring **106b** may be formed in one piece with the first pad **106a**. Similar to the first pad **106a**, the first bridge wiring **106b** may also include the corrosive aluminum layer (see **126b** of FIG. 6), and the presence of the dummy resistance layer **102a** inhibits corrosion of the first bridge wiring **106b** as well as the first pad **106a** dummy resistance layer.

All parts of the first bridge wiring **106b** may be formed in one piece with the first pad **106a**. However, as illustrated in FIG. 3, the first bridge wiring **106b** may include two or more different conductive layers. According to the exemplary embodiment illustrated in FIGS. 2 and 3, a part of the first bridge wiring **106b** formed in one piece with the first pad **106a** may have a discontinuous portion. The discontinuous portion may be electrically connected to the part of the first bridge wiring **106b** formed in one piece with the first pad **106a** through a connection part **104b** formed in a different layer from that of the first pad **106a** and the first bridge wiring

106b. The connection part **104b** may be disposed on the same layer as the gate electrode **104** of the TFT. The discontinuous portion, i.e., the connection part **104b**, overlaps a cutting line CL for separating the panel area CA from the peripheral area PA. Because the connection part **104b** overlapping the cutting line CL of the first bridge wiring **106b** crossing the cutting line CL is formed on the layer of the gate electrode **104**, which is a layer lower than the layer on which the source/drain electrodes **106s** and **106d** are formed, wear of a blade may be prevented during cutting of the organic light-emitting display panel, thereby facilitating the cutting.

Referring to FIGS. 4 and 5, because the second pad **206a**, unlike the first pad **106a**, receives an electrical signal which is not a clock signal, or direct current power from the test wiring, the second pad **206a** and the test wiring are directly connected through the second bridge wiring **204b**, and not via the local buffer LB. One end of the second bridge wiring **204b** may be in contact with the second pad **206a**, and the other end of the second bridge wiring **204b** may be in contact with one of the test wirings **306**. FIGS. 4 and 5 show that the second test wiring **306b** is in contact with the second bridge wiring **204b**. However, the second bridge wiring **204b** may be in contact with another test wiring.

The second bridge wiring **204b**, similar to the first bridge wiring **106b**, may be formed in one piece with the second pad **206a**. However, as illustrated in FIG. 4, the second bridge wiring **204b** may be included in a layer that is different from the second pad **206a**. According to the exemplary embodiment illustrated in FIGS. 4 and 5, the second bridge wiring **204b** may be disposed in the same layer as the gate electrode **104** of the TFT. A part of the second bridge wiring **204b** overlaps the cutting line CL for separating the panel area CA from the peripheral area PA. Because the second bridge wiring **204b** is formed in the same layer as the gate electrode **104** of the TFT, the wear of the blade may be prevented during the cutting of the organic light-emitting display panel, thereby facilitating the cutting.

FIG. 6 is a cross-sectional view schematically illustrating a state during a manufacturing process of the mother substrate **10** of FIG. 3.

A passivation layer **107** is formed in the display area DA, and an electrode material layer **111a** for the pixel electrode **111** is entirely formed on a top surface of the mother substrate **10** in order to form the pixel electrode **111** of the OLED. In order to pattern the electrode material layer **111a** into the pixel electrode **111**, a photoresist pattern PR is formed where the pixel electrode **111** is to be formed. The electrode material layer **111a** may be wet etched by using the photoresist pattern PR as a mask. The remaining electrode material layer **111a**, excluding the electrode material layer **111a** that is covered with the photoresist pattern PR, is exposed to an etchant for wet etching. The first pad **106a** and the first bridge wiring **106b** are formed in a stack structure having an aluminium layer **126b** that is disposed between upper and lower titanium layers **116b** and **136b**. The end of the aluminium layer **126b** is not covered with the titanium layers **116b** and **136b** at the ends of the first bridge wiring **106b** or the edges of the first pad **106a**. Because the aluminium layer **126b** may lose electrons, galvanic corrosion resulting from an oxidation reaction may be facilitated during a wet etching process of the electrode material layer **111a**.

However, because the dummy resistance layer **102a** electrically connects the test wiring to the first bridge wiring **106b** and the first pad **106a**, the first bridge wiring **106b** and the first pad **106a** may receive carriers (electrons) from the test wiring. Because the received electrons may be provided in the oxidation reaction during the wet etching process, and deple-

tion of the electrons in the aluminium layer **126b** may be relatively reduced, corrosion of the first pad **106a** and the first bridge wiring **106b** may be prevented.

As described above, according to the one or more of the above exemplary embodiments of the present invention, a mother substrate for an organic light-emitting display apparatus having a structure that may prevent the corrosion of the pad during the patterning process of the pixel electrode may be realized. It should be understood that the exemplary embodiments described therein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. A mother substrate for an organic light-emitting display apparatus, the mother substrate comprising:

- a panel area comprising a display area and a non-display area;
- a peripheral area surrounding the panel area;
- pixels disposed in the display area;
- pads disposed in the non-display area and coupled to the pixels;
- test wirings disposed in the peripheral area;
- a local buffer electrically connected to the test wirings;
- a bridge wiring connecting the local buffer to one of the pads; and
- a dummy resistance layer having a first end that contacts the bridge wiring and a second end that contacts one of the test wirings.

2. The mother substrate of claim 1, wherein the dummy resistance layer comprises a semiconductor material.

3. The mother substrate of claim 1, further comprising thin film transistors disposed in the pixels, wherein the dummy resistance layer is disposed in a same layer as a semiconductor layers of the thin film transistors.

4. The mother substrate of claim 1, wherein the dummy resistance layer has a non-linear shape.

5. The mother substrate of claim 1, wherein the one of the test wirings is in contact with the dummy resistance layer and is configured to transmit direct current power.

6. The mother substrate of claim 1, wherein the pads comprise an aluminum layer.

7. The mother substrate of claim 1, wherein the bridge wiring comprises an aluminum layer.

8. The mother substrate of claim 1, wherein the one of the pads that is connected to the bridge wiring and at least one part of the bridge wiring are integrally formed in one piece.

9. The mother substrate of claim 8, wherein:

- the at least one part of the bridge wiring comprises a discontinuous portion; and
- the discontinuous portion is electrically connected to the at least one part of the bridge wiring that is integrally formed in one piece with the one of the pads through a connection part that is formed in a different layer from each other.

10. The mother substrate of claim 9, wherein the at least one part of the bridge wiring that is integrally formed in one

piece with the one of the pads is disposed in a same layer as a layer of source/drain electrodes of a thin film transistor that is included in the pixels, and the connection part is disposed in a same layer as gate electrodes of the thin film transistor.

11. The mother substrate of claim 10, wherein the discontinuous portion overlaps a cutting line separating the panel area from the peripheral area.

12. A mother substrate for an organic light-emitting display apparatus, the mother substrate comprising:

- a panel area comprising a display area and a non-display area;
- a peripheral area surrounding the panel area;
- pixels disposed in the display area;
- a first pad and a second pad disposed in a non-display area of the panel area and are coupled to the pixels;
- test wirings disposed in the peripheral area;
- a local buffer electrically connected to the test wirings;
- a first bridge wiring connecting the local buffer to the first pad;
- a dummy resistance layer having a first end that contacts with the bridge wiring and a second end that contacts one of the test wirings; and
- a second bridge wiring that directly connects another one of the test wirings to the second pad.

13. The mother substrate of claim 12, wherein the dummy resistance layer comprises a semiconductor material.

14. The mother substrate of claim 12, further comprising thin film transistors disposed in the pixels, wherein the dummy resistance layer is disposed in a same layer as a semiconductor layers of the thin film transistors.

15. The mother substrate of claim 12, wherein the dummy resistance layer has a non-linear shape.

16. The mother substrate of claim 12, wherein the one of the test wirings is in contact with the dummy resistance layer and is configured to transmit direct current power.

17. The mother substrate of claim 12, wherein the first pad and the second pad each comprise an aluminum layer.

18. The mother substrate for an organic light-emitting display apparatus of claim 1, wherein the first bridge wiring comprises an aluminum layer.

19. The mother substrate for an organic light-emitting display apparatus of claim 1, wherein the first pad and at least one part of the first bridge wiring are integrally formed in one piece.

20. A substrate for an organic light-emitting display apparatus, the substrate comprising:

- a panel area;
 - a peripheral area surrounding the panel area;
 - pixels disposed in a display area of the panel area;
 - pads disposed in a non-display area of the panel area and coupled to the pixels;
 - test wirings disposed in the peripheral area;
 - a buffer electrically connected to the test wirings;
 - a wiring connecting the local buffer to one of the pads; and
 - a dummy resistance layer having one end in contact with the bridge wiring and another end in contact with one of the test wirings,
- wherein the dummy resistance layer comprises a semiconductor material and has a non-linear shape.

专利名称(译)	用于有机发光显示装置的母基板		
公开(公告)号	US8981378	公开(公告)日	2015-03-17
申请号	US14/219763	申请日	2014-03-19
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM KWANG MIN KWAK WON KYU JEONG JIN TAE KA JI HYUN		
发明人	KIM, KWANG-MIN KWAK, WON-KYU JEONG, JIN-TAE KA, JI-HYUN		
IPC分类号	H01L27/14 H01L21/66 H01L27/12		
CPC分类号	H01L22/32 H01L27/124 H01L27/1255 H01L27/3276 H01L51/0096		
助理审查员(译)	杨, 华驰		
优先权	1020130079034 2013-07-05 KR		
其他公开文献	US20150008432A1		
外部链接	Espacenet USPTO		

摘要(译)

用于有机发光显示装置的母基板。母基板具有面板区域和围绕面板区域的外围区域，设置在面板区域的显示区域中的像素，设置在面板区域的非显示区域中并且耦合到像素的焊盘，测试布线设置在外围区域中的局部缓冲器，电连接到测试配线的局部缓冲器，将局部缓冲器连接到其中一个焊盘的桥接布线，以及一端与桥接线接触并与另一端接触的另一端的虚设电阻层测试接线。

