

(10) **Patent No.:** US 9,041,035 B2
(45) **Date of Patent:** May 26, 2015

- (58) **Field of Classification Search**
CPC H01L 51/5281; H01L 51/5284
See application file for complete search history.

- (56)
- References Cited**

- U.S. PATENT DOCUMENTS

- | | | | | |
|--------------|-----|--------|-------------|--------|
| 2005/0046342 | A1 | 3/2005 | Park et al. | |
| 2006/0175961 | A1 | 8/2006 | Choong | |
| 2011/0024780 | A1* | 2/2011 | Park et al. | 257/98 |
| 2013/0001603 | A1 | 1/2013 | Lim et al. | |

- FOREIGN PATENT DOCUMENTS

- | | | | |
|----|-----------------|---|---------|
| KR | 10-2005-0052291 | A | 6/2005 |
| KR | 10-2010-0131074 | A | 12/2010 |
| KR | 10-2013-0007421 | A | 1/2013 |

- * cited by examiner

- Primary Examiner* — Daniel Luke

- (74) *Attorney, Agent, or Firm* — Knobbe Martens Olson & Bear LLP

- (57) **ABSTRACT**

- In an aspect, an organic light-emitting display apparatus is provided, including: an insulating layer having an inclined structure; a first electrode disposed on the insulating layer; a selective wavelength transparent layer disposed on the first electrode; a pixel defined layer disposed on the insulating layer and the first electrode and defining an emissive region and a non-emissive region; an organic emissive layer disposed on the first electrode; and a second electrode disposed on the organic emissive layer.

20 Claims, 5 Drawing Sheets

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5


30

FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7





FIG. 8



ORGANIC LIGHT-EMITTING DISPLAY APPARATUS

INCORPORATION BY REFERENCE TO RELATED APPLICATIONS

Any and all priority claims identified in the Application Data Sheet, or any correction thereto, are hereby incorporated by reference under 37 CFR 1.57. For example, this application claims priority to and the benefit of Korean Patent Application No. 10-2013-0022451, filed on Feb. 28, 2013, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

This disclosure relates to an organic light-emitting display apparatus, and more particularly, to an organic light-emitting display apparatus having excellent light efficiency and that is capable of reducing reflectivity of external light.

2. Description of the Related Technology

Generally, an organic light-emitting display apparatus is a self-emission display which is formed by using an organic light-emitting diode (OLED) which includes a hole-injecting electrode, an electron-injecting electrode, and an organic light-emitting layer formed therebetween. The organic light-emitting display apparatus emits light when an exciton, generated when a hole injected from the hole-injecting electrode and an electron injected from the electron-injecting electrode are combined, drops from an excitation state to a ground state.

Since the organic light-emitting display apparatus, which is a self-emission display, does not need an additional power source, it may be driven with a low voltage, and may be formed of light films. Additionally, the organic light-emitting display apparatus provides high-quality characteristics such as wide viewing angles, high contrast, and a rapid response. Thus, an organic light-emitting display apparatus receives consideration as a next-generation display apparatus.

SUMMARY

The present disclosure provides an organic light-emitting display apparatus having excellent light efficiency and that is capable of reducing reflectivity of external light.

According to an aspect of the present disclosure, there is provided an organic light-emitting display apparatus including: an insulating layer having an inclined structure; a first electrode disposed on the insulating layer; a selective wavelength transparent layer disposed on the first electrode; a pixel defined layer disposed on the insulating layer and the first electrode and defining an emissive region and a non-emissive region; an organic emissive layer disposed on the first electrode; and a second electrode disposed on the organic emissive layer.

In some embodiments, the first electrode may be provided on a bottom surface and a sidewall of the inclined structure.

In some embodiments, the pixel defined layer may extend on an upper surface of the insulating layer, and the emissive region may include an opening exposing the first electrode.

In some embodiments, the pixel defined layer may cover the selective wavelength transparent layer.

In some embodiments, an N ($N \geq 3$, N is an integer) number of low refractive index layers and an N number of high refractive index layers may be alternately stacked in the selective wavelength transparent layer.

In some embodiments, a difference in a refractive index between the N number of low refractive index layers and the N number of high refractive index layers may be equal to or greater than 0.5.

In some embodiments, a thickness of one of the N number of low refractive index layers may be greater than thicknesses of the other low refractive index layers. In some embodiments, one of the low refractive index layers has a thickness T^1 and each of the other low refractive index layers has a thickness T^2 . In some embodiments, the thickness T^1 is greater than the thicknesses T^2 .

In some embodiments, a thickness of an intermediate layer of the low refractive index layers may be greater than thicknesses of the other low refractive index layers.

In some embodiments, a sidewall of the inclined structure may have a tilt angle in a range from about 20 degrees to about 70 degrees with respect to an extending line of a bottom surface of the inclined structure.

In some embodiments, the inclined structure may have a recess shape, and the first electrode may have a concave shape.

In some embodiments, the first electrode may be disposed on a sidewall of the inclined structure, and reflect light generated in the organic emissive layer.

In some embodiments, the inclined structure may have a protruding shape, and the first electrode may have a convex shape.

In some embodiments, the first electrode may be a transparent electrode, and the second electrode may be a bottom emissive type including a reflective layer.

According to another aspect of the present disclosure, there is provided an organic light-emitting display apparatus including: a substrate; an insulating layer disposed on the substrate and including a recess having an inclined surface; an organic light-emitting diode (OLED) disposed on the insulating layer and including a first electrode, an organic emissive layer, and a second electrode; a pixel defined layer disposed between the first electrode and the second electrode and defining an emissive region and a non-emissive region; and a selective wavelength transparent layer provided on the inclined surface.

In some embodiments, the first electrode may be disposed on the inclined surface.

In some embodiments, the insulating layer may further comprise a plurality of recesses, and the OLED may be disposed in each of the recesses.

In some embodiments, an N ($N \geq 3$, N is an integer) number of low refractive index layers and an N number of high refractive index layers may be alternately stacked in the selective wavelength transparent layer, wherein a thickness of one of the N number of low refractive index layers is different from thicknesses of the other low refractive index layers. In some embodiments, one of the low refractive index layers has a thickness T^3 and each of the other low refractive index layers has a thickness T^4 , and wherein thickness T^3 is different than the thicknesses T^4 .

In some embodiments, the organic light-emitting display apparatus may further include: a thin film transistor connected to the first electrode.

In some embodiments, the organic light-emitting display apparatus may further include: a sealing film covering the OLED.

In some embodiments, the first electrode may include a reflective layer.

According to another aspect of the present disclosure, there is provided an organic light-emitting display apparatus including: a substrate; an insulating layer disposed on the

3

substrate and including a plurality of recesses each having a inclined surface; a plurality of OLEDs disposed on the insulating layer and including a first electrode, an organic emissive layer, and a second electrode; and a pixel defined layer disposed between the first electrode and the second electrode and defining an emissive region and a non-emissive region, wherein the pixel defined layer is a color filter.

In some embodiments, the inclined surface may have a tilt angle in a range from about 20 degrees to about 70 degrees with respect to a parallel line of the substrate.

In some embodiments, the first electrode may be disposed on the inclined surface.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features and advantages of the present disclosure will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings in which:

FIG. 1 is a cross-sectional view of an organic light-emitting display apparatus according to an embodiment of the present invention;

FIG. 2 is a cross-sectional view of an organic light-emitting display apparatus according to another embodiment of the present invention;

FIG. 3 is a schematic cross-sectional view of a region I of FIGS. 1 and 2;

FIGS. 4 and 5 are schematic cross-sectional views of a selective wavelength transparent layer applied to embodiments of the present invention;

FIGS. 6A through 6C are graphs showing a characteristic of the selective wavelength transparent layer of FIG. 5 according to a design change thereof;

FIG. 7 is a schematic cross-sectional view of a region I of FIGS. 1 and 2, according to another embodiment of the present invention; and

FIG. 8 is a schematic cross-sectional view of a region I of FIGS. 1 and 2, according to another embodiment of the present invention.

DETAILED DESCRIPTION

The present disclosure will now be described more fully with reference to the accompanying drawings, in which exemplary embodiments are shown. Like reference numerals in the drawings denote like elements, and thus their description will be omitted. In the drawings, the lengths and sizes of elements are exaggerated for clarity and convenience of description.

This disclosure may be embodied in many different forms and should not be construed as limited to the exemplary embodiments set forth herein. For example, it will be understood that when a layer is referred to as being "on" or "on the top of" another layer, the layer can be directly on another layer or intervening or layers.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used herein, the singular forms "a", "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms "comprises," "comprising," "includes," and/or "including," when used herein, specify the presence of stated steps, operations, and/or elements, but do not preclude the presence or addition of one or more other steps, operations, and/or elements. It will be understood that, although the terms, 'first', 'second', etc. may be used herein to describe various elements, these elements should not be

4

limited by these terms. These terms are only used to distinguish one element from another.

As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items. Expressions such as "at least one of," when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

FIGS. 1 and 2 are cross-sectional views of organic light-emitting display apparatuses 1 and 2, according to embodiments of the present invention.

Referring to FIG. 1, the organic light-emitting display apparatus 1 includes an organic emissive portion 22 provided on a substrate 21 and a sealing substrate 23 that seals the organic emissive portion 22.

In some embodiments, the organic emissive portion 22 may include a plurality of organic light-emitting diodes (OLEDs) that emit one of red, green, blue, and white colors, as described later.

In some embodiments, the sealing substrate 23 may be formed of a transparent material to form an image from the organic emissive portion 22 and to prevent oxygen and moisture from reaching the organic emissive portion 22.

Edges of the substrate 21 and the sealing substrate 23 are coupled to each other by using a sealing member 24 so that an inner space 25 between the substrate 21 and the sealing substrate 23 is sealed. In some embodiments, a moisture absorbent or a filler may be disposed in the inner space 25.

Referring to FIG. 2, the organic light-emitting display apparatus 2 includes the organic emissive portion 22 provided on the substrate 21 and a sealing film 26 that seals the organic emissive portion 22.

The organic light-emitting display apparatus 2 of FIG. 2 is different from the organic light-emitting display apparatus 1 of FIG. 1 in that the organic light-emitting display apparatus 2 includes the sealing film 26 that is a thin film instead of the sealing substrate 23 of FIG. 1. In some embodiments, the sealing film 26 may cover the organic emissive portion 22 to protect the organic emissive portion 22 from external air. For example, the sealing film 26 may have a structure in which an inorganic layer formed of an inorganic substance such as silicon oxide or silicon nitride and an organic layer formed of an organic substance such as epoxy or polyimide are alternately formed.

In some embodiments, the number of inorganic layers or organic layers may be plural.

In some embodiments, the organic layer may be formed of polymer, and be a single layer or multi-layer formed of one selected from the group consisting of polyethylene terephthalate, polyimide, polycarbonate, epoxy, polyethylene, and polyacrylate. In some embodiments, the organic layer may also be formed of polyacrylate, and, more particularly, include a high molecular monomer component including a diacrylate-based monomer and a triacrylate-based monomer. In some embodiments, the monomer component may further include a monoacrylate-based monomer. In some embodiments, the monomer component may further include a well-known photoinitiator such as TPO (2,4,6-Trimethylbenzoyl-diphenyl-phosphineoxide) but it is not limited thereto.

In some embodiments, the inorganic layer may be a single layer or multi-layer including metal oxide or metal nitride. In some embodiments, the inorganic layer may include one selected from the group consisting of SiNx, Al₂O₃, SiO₂, TiO₂, etc.

In some embodiments, an uppermost layer of the sealing film 26 that is exposed to the outside may be an inorganic layer so as to prevent moisture from reaching an OLED.

In some embodiments, the sealing film **26** may include at least one sandwich structure in which at least one organic layer is disposed between at least two inorganic layers. In some embodiments, the sealing film **26** may include at least one sandwich structure in which at least one inorganic layer is disposed between at least two organic layers.

In some embodiments, the sealing film **26** may sequentially include a first inorganic layer, a first organic layer, and a second inorganic layer from an upper portion of the organic emissive portion **22**. In some embodiments, the sealing film **26** may also include the first inorganic layer, the first organic layer, the second inorganic layer, a second organic layer, and a third inorganic layer from the upper portion of the organic emissive portion **22**. In some embodiments, the sealing film **26** may also include the first inorganic layer, the first organic layer, the second inorganic layer, the second organic layer, the third inorganic layer, a third organic layer, and a fourth inorganic layer from the upper portion of the organic emissive portion **22**.

In some embodiments, a halogenized metal layer including LiF may be further disposed between the organic emissive layer **22** and the first inorganic layer. In some embodiments, the halogenized metal layer may prevent the organic emissive layer **22** from being damaged when the first inorganic layer is formed using a sputtering method or plasma deposition method.

In some embodiments, the first organic layer may have a narrower area than that of the second inorganic layer. In some embodiments, the second organic layer may also have a narrower area than that of the third inorganic layer. In some embodiments, the first organic layer may be entirely covered by the second inorganic layer. In some embodiments, the second organic layer may also be entirely covered by the third inorganic layer.

As another example, the sealing film **26** may have a film structure including low melting glass such as tin oxide (SnO). However, this is merely exemplary and the sealing film **26** is not necessarily limited thereto.

FIG. **3** is a schematic cross-sectional view of region I of FIGS. **1** and **2**.

Referring to FIG. **3**, an organic light-emitting display apparatus **100** may include the substrate **21**, a buffer film **211**, a thin film transistor TR, an insulating layer **210** including an inclined structure **209**, an OLED, a pixel defined layer **223**, and a selective wavelength transparent layer **30**.

In some embodiments, the substrate **21** may be formed of transparent glass having silicon dioxide (SiO₂) as a main component. However, the substrate **21** is not necessarily limited thereto, and may be formed of various materials such as ceramic, transparent plastic, metal, and the like.

In some embodiments, the buffer film **211** may function to prevent impurity ions, moisture, or external air from reaching an upper surface of the substrate **21** and planarize a surface of the substrate **21**. In some embodiments, the buffer film **211** may be formed of an inorganic substance such as silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, titanium oxide, or titanium nitride, etc., an organic substance such as polyimide, polyester, acryl, etc., or a stack structure of the inorganic substance and the organic substance. The buffer film **211** is not an indispensable element and may not be provided according to circumstances. In some embodiments, the buffer film **211** may be formed by using diverse deposition methods such as plasma-enhanced chemical vapor deposition (PECVD), atmospheric pressure chemical vapor deposition (APCVD), low pressure CVD (LPCVD), and the like.

The thin film transistor TR includes an active layer **212**, a gate electrode **214**, and source and drain electrodes **216** and **217**. A gate insulating layer **213** for insulating the gate electrode **214** from the active layer **212** is disposed between the gate electrode **214** and the active layer **212**.

In some embodiments, the active layer **212** may be provided on the buffer film **211**. In some embodiments, the active layer **212** may use an inorganic semiconductor or an organic semiconductor such as amorphous silicon or polysilicon. In some embodiments, the active layer **212** may be formed of an oxide semiconductor. For example, the oxide semiconductor may include an oxide of at least one material selected from metal elements in Groups **12** through **14** consisting of zinc (Zn), indium (In), gallium (Ga), stannum (Sn), cadmium (Cd), germanium (Ge), and hafnium (Hf), and a combination thereof.

In some embodiments, the gate insulating layer **213** may be provided on the buffer film **211** to cover the active layer **212**. In some embodiments, the gate electrode **214** may be formed on the gate insulating layer **213**.

In some embodiments, an interlayer insulating layer **215** may be formed on the gate insulating layer **213** to cover the gate electrode **214**. In some embodiments, the source and drain electrodes **216** and **217** may be formed on the interlayer insulating layer **215** to contact the active layer **212** through contact holes.

The above-described structure of the thin film transistor TR is not necessarily limited thereto, and other structures of a thin film transistor TR may be applied. For example, the thin film transistor TR is formed as a top gate structure or may be formed as a bottom gate structure in which the gate electrode **214** is disposed below the active layer **212**.

In some embodiments, a pixel circuit (not shown) including a capacitor and the thin film transistor TR may be formed.

In some embodiments, the insulating layer **210** may include the inclined structure **209**. In some embodiments, the insulating layer **210** may be provided on the interlayer insulating layer **215** to cover the pixel circuit including the thin film transistor TR. In some embodiments, the insulating layer **210** may be composed of a plurality of insulating films.

In some embodiments, the inclined structure **209** includes a planarized bottom surface and a side wall having a tilt angle θ . In some embodiments, the inclined structure **209** may be provided to form a recess having inclined surface in a part of the insulating layer **210**. The tilt angle θ refers to an angle formed by an extending line of a bottom surface and a side wall of the inclined structure **209** and may be adjusted through a process. An upper width of the inclined structure **209** may be greater than a lower width thereof since it has the side wall having the tilt angle θ . In some embodiments, the tilt angle θ may be in a range from about 20 degrees to about 70 degrees with respect to the extending line of the bottom surface.

In some embodiments, the insulating layer **210** may be formed of an inorganic substance and/or an organic substance. For example, the insulating layer **210** may include photoresist, acryl-based polymer, polyimide-based polymer, polyamide-based polymer, siloxane-based polymer, polymer including a photosensitive acryl carboxyl group, novolac resin, alkali soluble resin, silicon oxide, silicon nitride, silicon oxynitride, silicon oxycarbide, silicon carbonitride, aluminum, magnesium, zinc, hafnium, zirconium, titanium, tantalum, aluminum oxide, titanium oxide, tantalum oxide, magnesium oxide, zinc oxide, hafnium oxide, zirconium oxide, etc.

In some embodiments, the insulating layer **210** may include a first insulating layer **218** and a second insulating

layer **219**. In some embodiments, the first insulating layer **218** may be a single-layered or multi-layered insulating film having a planarized top surface. In some embodiments, the second insulating film **219** may be disposed on the first insulating layer **218** and have the inclined structure **209**. In some embodiments, the first insulating layer **218** and the second insulating layer **219** may be formed of a same or similar material. In some embodiments, the first insulating layer **218** and the second insulating layer **219** may be also formed of different materials.

In some embodiments, the OLED may be disposed on the insulating layer **210** and may include a first electrode **221**, an organic emissive layer **220**, and a second electrode **222**. In some embodiments, the pixel defined layer **223** may be disposed on the insulating layer **210** and the first electrode **221** and defines an emissive region and a non-emissive region.

In some embodiments, the organic emissive layer **220** may be formed of a low-molecular weight organic material or a polymer organic material. When the organic emissive layer **220** is formed of a low-molecular weight organic material, a hole injection layer (HIL), a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), an electron injection layer (EIL), etc. may be stacked to form a single or multiple structure. These low-molecular weight organic materials may be formed using a vacuum deposition method. In this regard, the organic emissive layer **220** may be independently formed for each of red R, green G, and blue B pixels. The HIL, the HTL, the ETL, and the EIL may be applied to the RGB pixels as common layers.

Otherwise, when the organic emissive layer **220** is formed of a polymer organic material, only an HIL may be included with respect to an EML in a direction of the first electrode **221**. In some embodiments, the HIL may be formed of poly (3,4-ethylenedioxythiophene) (PEDOT) or polyaniline (PANI) and formed on an upper portion of the first electrode **221** using an inkjet printing method or a spin coating method. In this regard, a polyphenylene vinylene (PPV) or polyfluorene-based polymer organic substance may be used as an organic material, and a color pattern may be formed using a general method such as the inkjet printing method or the spin coating method or a thermal transfer method using laser.

In some embodiments, the HIL may be formed of a phthalocyanine component such as copper phthalocyanine or TCTA, m-MTDATA, m-MTDAPB, etc. that are starburst type amine derivatives.

In some embodiments, the HTL may be formed of N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (TPD), N,N'-di(naphthalene-1-yl)-N'-diphenyl benzidine (α -NPD), etc.

In some embodiments, the EIL may be formed of LiF, NaCl, CsF, Li₂O, BaO, Liq, etc.

In some embodiments, the ETL may be formed of Alq₃.

In some embodiments, the EML may be formed of a host material and a dopant material.

In some embodiments, the host material may use Tris(8-hydroxyquilonato) aluminum (Alq₃), 9,10-di (naphth-2-yl) anthracene (AND), 3-tert-butyl-9,10-di(naphth-2-yl)anthracene (TBADN), 4,4'-bis(2,2-diphenyl-ethene-1-yl)-4,4'-dimethylphenyl (DPVBi), 4,4'-bis(2,2-diphenyl-ethene-1-yl)-4,4'-dimethylphenyl (p-DMDPVB), Tert (9,9'-diarylfluorene)-s (TDAF), 2-(9,9'-spirobifluorene-2-yl)-9,9'-spirobifluorene (BSDF), 2,7-bis(9,9'-spirobifluorene-2-yl)-9,9'-spirobifluorene (TSDF), bis-(9,9'-diarylfluorene)s (BDAF), 4,4'-bis(2,2-diphenyl-ethene-1-yl)-4,4'-di-(tert-butyl)phenyl (p-TDPVBi), 1,3-bis(carbazole-9-yl)benzene (mCP), 1,3,5-tris (carbazole-9-yl)benzene (tCP), 4,4',4"-tris (carbazole-9-yl)triphenylamine (TcTa), 4,4'-bis(carbazole-9-

yl)biphenyl (CBP), 4,4'-bis(9-carbazolyl)-2,2'-dimethylbiphenyl (CBDP), 4,4'-bis(carbazole-9-yl)-9,9-dimethylfluorene (DMFL-CBP), 4,4'-bis(carbazole-9-yl)-9,9-bis(9-phenyl-9H-carbazole)fluorene (FL-4CBP), 4,4'-bis(carbazole-9-yl)-9,9-di-tolyl-fluorene (DPFL-CBP), 9,9-bis(9-phenyl-9H-carbazole)fluorene (FL-2CBP), etc.

In some embodiments, the dopant material may use 4,4'-bis[4-(di-p-tolylamino)styryl]biphenyl (DPAVB), 9,10-di(naph-2-thyl)anthracene (AND), 3-tert-butyl-9,10-di(naph-2-thyl)anthracene (TBADN), etc.

In some embodiments, the first electrode **221** may be disposed on the insulating layer **210**. In some embodiments, the first electrode **221** may be disposed on the side wall of the inclined structure **209** with respect to the bottom surface thereof. In some embodiments, the first electrode **221** may be at an angle that is the same as or similar to the tilt angle θ formed by the side wall of the inclined structure **209** with respect to the extending line of the bottom surface of the inclined structure **209**. In some embodiments, the first electrode **221** may have a concave shape since it is disposed on the side wall of the inclined structure **209**.

In a case where light generated in the organic emissive layer **220** is incident to the first electrode **221** disposed on the side wall of the inclined structure **209**, the incident light may be reflected from the first electrode **221** and discharged to the outside. In this regard, the tilt angle θ may be adjusted in such a way that the light generated in the organic emissive layer **220** may be emitted in a desired direction. Accordingly, an efficiency of the light discharged from the OLED disposed on the inclined structure **209** to the outside may be improved.

In some embodiments, the first electrode **221** may be electrically connected to the drain electrode **217** of the thin film transistor TR via a through hole **208** that passes through the insulating layer **210**. Although the through hole **208** is formed in the bottom surface of the inclined structure **209** in FIG. 3, the present embodiments are not limited thereto. In some embodiments, the through hole **208** may be formed in the side wall of the inclined structure **209** or in an upper surface of the insulating layer **210**.

In some embodiments, the first electrode **221** may function as an anode and the second electrode **222** may function as a cathode. However, the polarities of the first and second electrodes **221** and **222** are not limited thereto and may be switched.

If the first electrode **221** functions as an anode, the first electrode **221** may include indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), or indium oxide (In₂O₃) having a high work function. If the organic light-emitting display device **1** is a top emission type for displaying an image in a direction opposite to the display substrate **21**, the first electrode **221** may further include a reflective layer including metal such as silver (Ag), magnesium (Mg), aluminum (Al), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), ytterbium (Yb), or calcium (Ca), or an alloy thereof. In some embodiments, the first electrode **221** may be formed as a monolayer or a multilayer including the above-mentioned metal or alloy. In some embodiments, the first electrode **221** may include an ITO/Ag/ITO structure as a reflective electrode.

If the second electrode **222** functions as a cathode electrode, the second electrode **222** may be formed of metal such as Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, or Ca. If the organic light-emitting display device **1** is a top emission type, the second electrode **222** should transmit light. In some embodiments, the second electrode **222** may include transparent conductive metal oxide such as ITO, IZO, zinc tin

oxide (ZTO), ZnO, or In_2O_3 . According to another embodiment, the second electrode **222** may be formed as a thin film including at least one selected from the group consisting of Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, and Yb. For example, the second electrode **222** may be formed as a monolayer or a multilayer including Mg:Ag, Ag:Yb, and/or Ag. Unlike the first electrode **221**, the second electrode **222** may be formed to apply a common voltage to all pixels.

In some embodiments, the pixel defining layer **219** defines the pixel regions PA of the OLEDs and the non-pixel region NPA by using a plurality of openings for exposing the first electrode **221**. In the opening of the pixel defining layer **219**, the first electrode **221**, the organic emission layer **220B** or **220R**, and the second electrode **222** may be sequentially stacked and the organic emission layer **220B** or **220R** may emit light. That is, a region where the pixel defining layer **219** is formed substantially corresponds to the non-pixel region NPA, and the openings of the pixel defining layer **219** substantially correspond to the pixel regions PA.

In some embodiments, the pixel defined layer **223** may be disposed on the insulating layer **210** and the first electrode **221** and may define the emissive region and the non-emissive region. In some embodiments, the pixel defined layer **223** may cover the first electrode **221** disposed on the side wall of the inclined structure **209** and extend on the upper surface of the insulating layer **210**. In other words, the pixel defined layer **223** may be disposed between a part of the bottom surface and an upper part of the side wall of the inclined structure **209**. A part of the pixel defined layer **223** is the non-emissive region. In some embodiments, an opening (not shown) pixel defined layer disposed between the pixel defined layers **223** and exposes the first electrode **221** may be the emissive region.

In some embodiments, the organic emissive layer **220** may be disposed on the pixel defined layer **223**. In other words, the organic emissive layer **220** may be disposed on the first electrode **221** of the opening **223a** and extend on the upper portion of the pixel defined layer **223**.

In some embodiments, the pixel defined layer **223** may be formed of an organic material, an inorganic material, etc. For example, the pixel defined layer **223** may include an organic material such as photoresist, polyacryl-based resin, polyimide-based resin, acryl-based polymer, or an inorganic material such as a silicon compound.

A pixel is defined by the opening pixel defined layer between the pixel defined layers **223**, and a single OLED is disposed for each pixel. Each pixel may be a red pixel, a green pixel, a blue pixel, or a white pixel according to a color emitted by the organic emissive layer **220** of the OLED.

In some embodiments, the selective wavelength transparent layer **30** may be provided to reduce reflection by external light while maintaining light efficiency that may be increased by the inclined structure **209**.

In some embodiments, the selective wavelength transparent layer **30** may be provided on the first electrode **221** disposed on the side wall of the inclined structure **209**. In some embodiments, the selective wavelength transparent layer **30** may transmit only light of a wavelength range generated in the organic emissive layer **220** of each pixel and may not transmit light of other wavelength ranges. In other words, a selective wavelength transparent layer **30** that transmits only a red light is provided in a red pixel, a selective wavelength transparent layer **30** that transmits only a green light is provided in a green pixel, and a selective wavelength transparent layer **30** that transmits only a blue light is provided in a blue pixel.

Thus, the light generated in the organic emissive layer **220** of each pixel and traveling to a side surface thereof may transmit through the selective wavelength transparent layer **30** disposed on a inclined surface and then may be reflected from the first electrode **221** and emitted to the outside, whereas most of the light incident from the outside may not transmit through the selective wavelength transparent layer **30** and may become extinct.

For example, the selective wavelength transparent layer **30** that transmits only the red light is provided in the red pixel so that the red light generated in the organic emissive layer **220** may transmit through the selective wavelength transparent layer **30**. Then the light may be reflected from the first electrode **221** disposed on the inclined surface and be emitted to the outside, whereas visible light of the light incident from the outside, except for the red light, may not transmit through the selective wavelength transparent layer **30** and thus may not be reflected from the first electrode **221**.

In some embodiments, the selective wavelength transparent layer **30** may be a red, green, or blue color filter according to each pixel. In some embodiments, the selective wavelength transparent layer **30** may have a structure in which low refractive index layers and high refractive index layers are alternately stacked, as described with reference to FIGS. **4** and **5** below.

FIGS. **4** and **5** are schematic cross-sectional views of the selective wavelength transparent layer **30** applied to embodiments of the present invention.

Referring to FIG. **4**, an $N(N \geq 3, N$ is an integer) number of low refractive index layers **1a, 2a, 3a, . . . , Na** and an N number of high refractive index layers **1b, 2b, 3b, . . . , Nb** may be alternately stacked in the selective wavelength transparent layer **30**. Although the low refractive index layer **1a** is disposed as a lowermost layer of the selective wavelength transparent layer **30**, the present embodiments are not limited thereto, and the high refractive index layer **1b** may be disposed as a lowermost layer of the selective wavelength transparent layer **30**.

A difference in a refractive index n between the low refractive index layers **1a, 2a, 3a, . . . , Na** and the high refractive index layers **1b, 2b, 3b, . . . , Nb** may be equal to or greater than approximately 0.5. A thickness $d1$ of each of the low refractive index layers **1a, 2a, 3a, . . . , Na** and a thickness $d2$ of each of the high refractive index layers **1b, 2b, 3b, . . . , Nb** may be designed such that a light path (nd , n denotes the refractive index, and d denotes a moving distance of light) is $\lambda/4$. In this regard, λ may denote a wavelength of light that may transmit through the selective wavelength transparent layer **30**.

In this regard, a thickness $d3$ of at least one of the low refractive index layers **1a, 2a, 3a, . . . , Na** may be different from the thickness $d1$ of the other layers. For example, the thickness $d3$ of at least one of the low refractive index layers **1a, 2a, 3a, . . . , Na** may be greater than the thickness $d1$ of the other layers. In some embodiments, the low refractive index layer having a different thickness may be disposed in the middle of the selective wavelength transparent layer **30**.

FIG. **5** shows the selective wavelength transparent layer **30** in a case where the low refractive index layers **1a~6a** and the high refractive index layers **1b~6b** are 6 pairs.

Referring to FIG. **5**, the selective wavelength transparent layer **30** has a structure in which the low refractive index layer **1a**, the high refractive index layer **1b**, the low refractive index layer **2a**, the high refractive index layer **2b, . . . ,** the low refractive index layer **6a**, and the high refractive index layer **6b** are stacked.

In some embodiments, the first through sixth low refractive index layers **1a~6a** may have a same or similar refractive

index. The first through sixth high refractive index layers **1b~6b** may have a same or similar refractive index.

In some embodiments, the refractive index of each of the first through sixth low refractive index layers **1a~6a** may be approximately 0.5 times or more smaller than that of each of the first through sixth high refractive index layers **1b~6b**.

In some embodiments, the thickness **d1** of the first, second, third, fifth, and sixth low refractive index layers **1a, 2a, 3a, 5a, and 6a** may be the same or similar. In some embodiments, the thickness **d2** of the first through sixth high refractive index layers **1b~6b** may be the same or similar. In some embodiments, the thickness **d1** may be smaller than the thickness **d2**.

In some embodiments, the fourth low refractive index layer **4a** may have a thickness **d3** that is different from those of the first, second, third, fifth, and sixth low refractive index layers **1a, 2a, 3a, 5a, and 6a**. In some embodiments, the thickness **d3** of the fourth low refractive index layer **4a** may be 1.5 times or more greater than the thickness **d1** of the first, second, third, fifth, and sixth low refractive index layers **1a, 2a, 3a, 5a, and 6a**.

FIGS. **6A** through **6C** are graphs showing a characteristic of the selective wavelength transparent layer **30** of FIG. **5** according to a design change thereof.

Common design parameters with respect to data of FIGS. **6A** through **6C** are as follows:

- 1) Refractive index of the low refractive index layers **1a~6a**: 1.5
- 2) Refractive index of the high refractive index layers **1b~6b**: 2.3
- 3) Thickness **d1** of the first, second, third, fifth, and sixth low refractive index layers **1a, 2a, 3a, 5a, and 6a**: 70 nm
- 4) Thickness **d2** of the high refractive index layers **1b~6b**: 100 nm

The data of FIGS. **6A** through **6C** shows the characteristic of the selective wavelength transparent layer **30** with respect to a change in the thickness **d3** of the fourth low refractive index layer **4a**.

Referring to FIG. **6A**, the thickness **d3** of the fourth low refractive index layer **4a** is 140 nm. In this case, light of a wavelength from about 460 nm to about 470 nm in a visible light range may be transmitted like a region A, which represents a blue light.

Referring to FIG. **6B**, the thickness **d3** of the fourth low refractive index layer **4a** is 220 nm. In this case, light of a wavelength from about 520 nm to about 530 nm in a visible light range may be transmitted like a region B, which represents a green light.

Referring to FIG. **6C**, the thickness **d3** of the fourth low refractive index layer **4a** is 320 nm. In this case, light of a wavelength from about 610 nm to about 620 nm in a visible light range may be transmitted like a region C, which represents a red light.

As described above, the design change of the selective wavelength transparent layer **30** may be made by changing a thickness of one of a plurality of low refractive index layers so as to transmit light of a desired wavelength range.

The above-described design parameter is merely an example, and may be changed in various ways. For example, a difference in a refractive index, the number of low refractive index layers having different thicknesses, a location of a low refractive index layer having a different thickness, etc. may be changed. Also, the selective wavelength transparent layer **30** may be designed by changing a thickness of at least one of high refractive index layer instead of low refractive index layers.

FIG. **7** is a schematic cross-sectional view of region I of FIGS. **1** and **2**, according to another embodiment of the

present invention. The same reference numerals between FIGS. **3** and **7** denote the same elements, and thus repeated descriptions thereof are omitted here for brevity of explanation.

Referring to FIG. **7**, an organic light-emitting display apparatus **200** is different from the organic light-emitting display apparatus **100** of FIG. **3** in that the organic light-emitting display apparatus **200** does not include the selective wavelength transparent layer **30** and instead includes a pixel defined layer **225** functioning as the selective wavelength transparent layer **30**.

In some embodiments, the pixel defined layer **225** may be a color filter. That is, the pixel defined layer **225** may transmit only light of a wavelength range generated in the organic emissive layer **220** of each pixel and may not transmit light of other wavelength ranges. In other words, a pixel defined layer **225** that transmits only a red light is provided in a red pixel, a pixel defined layer **225** that transmits only a green light is provided in a green pixel, and a pixel defined layer **225** that transmits only a blue light is provided in a blue pixel.

Thus, the light generated in the organic emissive layer **220** of each pixel and traveling to a side surface may transmit through the pixel defined layer **225** and then may be reflected from the first electrode **221** and emitted to the outside, whereas most of the light incident from the outside may not transmit through the pixel defined layer **225** and may become extinct.

FIG. **8** is a schematic cross-sectional view of a region I of FIGS. **1** and **2**, according to another embodiment of the present invention. The same reference numerals between FIGS. **3** and **8** denote the same elements, and thus repeated descriptions thereof are omitted here for brevity of explanation.

Referring to FIG. **8**, an organic light-emitting display apparatus **300** is different from the organic light-emitting display apparatus **100** of FIG. **3** in that the organic light-emitting display apparatus **300** has a top emissive structure in which light is emitted in a direction of the substrate **21**.

In some embodiments, the organic light-emitting display apparatus **300** may include an insulating layer **210** having a inclined structure **209** having a protruding shape. Also, an OLED may be provided on a protruding portion of the insulating layer **210**. In this case, the first electrode **221** may be a transparent electrode and have a convex shape. In some embodiments, the second electrode **222** may include a reflective material.

In some embodiments, the selective wavelength transparent layer **30** may be disposed on the first electrode **221** disposed on the sidewall of the inclined structure **209**. In some embodiments, the selective wavelength transparent layer **30** may transmit only light of a wavelength range generated in the organic emissive layer **220** of each pixel and may not transmit light of other wavelength ranges.

Thus, the light generated in the organic emissive layer **220** of each pixel and traveling in a direction of a side surface thereof may be reflected from the second electrode **222** and then emitted toward the substrate **21**, whereas most of the light incident from the outside may not transmit through the selective wavelength transparent layer **30** and may become extinct, and thus an external light reflectivity of the organic light-emitting display apparatus **300** may be reduced.

It should be understood that example embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments. While some example embodiments have

13

been particularly shown and described, it will be understood by one of ordinary skill in the art that variations in form and detail may be made therein without departing from the spirit and scope of the claims.

What is claimed is:

1. An organic light-emitting display apparatus comprising: an insulating layer having a inclined structure; a first electrode disposed on the insulating layer; a selective wavelength transparent layer disposed on and in direct physical contact with the first electrode; a pixel defined layer disposed on the insulating layer and the first electrode and defining an emissive region and a non-emissive region; an organic emissive layer disposed on the first electrode; and a second electrode disposed on the organic emissive layer.
2. The organic light-emitting display apparatus of claim 1, wherein the first electrode is provided on a bottom surface and a sidewall of the inclined structure.
3. The organic light-emitting display apparatus of claim 1, wherein the pixel defined layer extends on an upper surface of the insulating layer, and the emissive region comprises an opening exposing the first electrode.
4. The organic light-emitting display apparatus of claim 1, wherein the pixel defined layer covers the selective wavelength transparent layer.
5. The organic light-emitting display apparatus of claim 1, wherein the selective wavelength transparent layer further comprises an $N(N \geq 3, N$ is an integer) number of low refractive index layers alternately stacked with an N number of high refractive index layers, wherein one of the low refractive index layers has a thickness T^1 and each of the other low refractive index layers has a thickness T^2 .
6. The organic light-emitting display apparatus of claim 5, wherein a difference in a refractive index between the N number of low refractive index layers and the N number of high refractive index layers is equal to or greater than 0.5.
7. The organic light-emitting display apparatus of claim 5, wherein the thickness T^1 is greater than the thicknesses T^2 .
8. The organic light-emitting display apparatus of claim 5, wherein a thickness of an intermediate layer of the low refractive index layers is greater than thicknesses of the other low refractive index layers.
9. The organic light-emitting display apparatus of claim 1, wherein a sidewall of the inclined structure has a tilt angle in a range from about 20 degrees to about 70 degrees with respect to an extending line of a bottom surface of the inclined structure.
10. The organic light-emitting display apparatus of claim 1, wherein the inclined structure has a recess shape, and the first electrode has a concave shape.

14

11. The organic light-emitting display apparatus of claim 1, wherein the first electrode is disposed on a sidewall of the inclined structure, and reflects light generated in the organic emissive layer.

12. The organic light-emitting display apparatus of claim 1, wherein the inclined structure has a protruding shape, and the first electrode has a convex shape.

13. The organic light-emitting display apparatus of claim 1, wherein the first electrode is a transparent electrode, and the second electrode is a bottom emissive type comprising a reflective layer.

14. An organic light-emitting display apparatus comprising:

- a substrate;
 - an insulating layer disposed on the substrate and comprising a recess having an inclined surface;
 - an organic light-emitting diode (OLED) disposed on the insulating layer and comprising a first electrode, an organic emissive layer, and a second electrode;
 - a pixel defined layer disposed between the first electrode and the second electrode and defining an emissive region and a non-emissive region; and
 - a selective wavelength transparent layer provided on the inclined surface between the first electrode and the pixel defined layer.
15. The organic light-emitting display apparatus of claim 14, wherein the first electrode is disposed on the inclined surface.
16. The organic light-emitting display apparatus of claim 14, wherein the insulating layer further comprises a plurality of recesses, and the OLED is disposed in each of the recesses.
17. The organic light-emitting display apparatus of claim 14, wherein an $N(N \geq 3, N$ is an integer) number of low refractive index layers and an N number of high refractive index layers are alternately stacked in the selective wavelength transparent layer,
- wherein one of the low refractive index layers has a thickness T^3 and each of the other low refractive index layers has a thickness T^4 , and wherein thickness T^3 is different than the thicknesses T^4 .
18. The organic light-emitting display apparatus of claim 14, further comprising: a thin film transistor connected to the first electrode.
19. The organic light-emitting display apparatus of claim 14, further comprising a sealing film covering the OLED.
20. The organic light-emitting display apparatus of claim 14, wherein the first electrode comprises a reflective layer.

* * * * *

专利名称(译)	有机发光显示装置		
公开(公告)号	US9041035	公开(公告)日	2015-05-26
申请号	US13/914210	申请日	2013-06-10
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LIM JAE IK KIM JAE KYOUNG		
发明人	LIM, JAE-IK KIM, JAE-KYOUNG		
IPC分类号	H01L51/00 H01L33/00 H01L27/32 H01L51/52		
CPC分类号	H01L51/5281 H01L51/5262 H01L27/3246 H01L27/322 H01L51/5284		
审查员(译)	LUKE , DANIEL		
优先权	1020130022451 2013-02-28 KR		
其他公开文献	US20140239259A1		
外部链接	Espacenet USPTO		

摘要(译)

一方面,提供一种有机发光显示装置,包括:具有倾斜结构的绝缘层;第一电极设置在绝缘层上;选择性波长透明层,设置在第一电极上;像素限定层,设置在绝缘层和第一电极上,并限定发光区域和非发光区域;有机发光层,设置在第一电极上;和设置在有机发光层上的第二电极。

