



(12) **Patent Application Publication**
Yun et al.

(43) **Pub. Date:** Nov. 14, 2019

Dec. 28, 2015 (KR) 10-2015-0187639

Publication Classification

(51) **Int. Cl.**

H01L 27/32 (2006.01)

H01L 51/52 (2006.01)

(52) U.S. Cl.

CPC *H01L 27/322* (2013.01); *H01L 2251/5369*
(2013.01); *H01L 51/5253* (2013.01)

(57) **ABSTRACT**

An organic light-emitting display apparatus includes a substrate; a pixel electrode over the substrate; a pixel-defining layer including an opening that exposes at least a portion of the pixel electrode; an intermediate layer, which is over the portion of the pixel electrode exposed by the opening and includes an organic emission layer; a counter electrode over the intermediate layer; and an encapsulating structure, which is over the counter electrode and includes at least one inorganic layer and at least one organic layer, and the at least one organic layer includes quantum dots and is in the opening.

(21) Appl. No.: 16/520,175

(22) Filed: **Jul. 23, 2019**

Related U.S. Application Data

(63) Continuation of application No. 15/203,735, filed on Jul. 6, 2016.




FIG. 1




FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 3F





FIG. 4



ORGANIC LIGHT-EMITTING DISPLAY APPARATUS AND METHOD OF MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation of U.S. patent application Ser. No. 15/203,735, filed on Jul. 6, 2016, which claims priority to and the benefit of Korean Patent Application No. 10-2015-0187639, filed on Dec. 28, 2015, in the Korean Intellectual Property Office, the disclosure of each of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

[0002] Aspects of one or more embodiments relate to an organic light-emitting display apparatus and a method of manufacturing the same, and more particularly, to an organic light-emitting display apparatus including quantum dots and a method of manufacturing the same.

2. Description of the Related Art

[0003] An organic light-emitting display apparatus is a self-luminescent display apparatus that includes a hole injection electrode, an electron injection electrode, and an organic emission layer therebetween and emits light as excitons, which are generated as holes injected by the hole injection electrode and electrons injected by the electron injection electrode combine in the organic emission layer, and transition from an excited state to a ground state.

[0004] Since an organic light-emitting display apparatus, which is a self-luminescent display apparatus, does not require a separate light source, the organic light-emitting display apparatus may be driven with a low voltage and may be configured into a lightweight and slim apparatus. Furthermore, due to excellent properties including a viewing angle, contrast, and a response speed, an organic light-emitting display apparatus is widely applied to portable apparatuses, such as an MP3 player or a mobile phone, a television (TV), etc.

[0005] Recently, for reduced thickness and/or flexibility of an organic light-emitting display apparatus, a thin-film encapsulation (TFE) including at least one inorganic layer and at least one organic layer is employed to seal an organic light-emitting device.

SUMMARY

[0006] According to an aspect of one or more embodiments, an organic light-emitting display apparatus has enhanced color purity that may be easily manufactured as a flexible display apparatus.

[0007] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0008] According to one or more embodiments, an organic light-emitting display apparatus includes a substrate; a pixel electrode over the substrate; a pixel-defining layer including an opening that exposes at least a portion of the pixel electrode; an intermediate layer, which is over the portion of the pixel electrode exposed by the opening and includes an organic emission layer; a counter electrode over the inter-

mediate layer; and an encapsulating structure, which is over the counter electrode and includes at least one inorganic layer and at least one organic layer, and the at least one organic layer includes quantum dots and is in the opening.

[0009] The thickness of the at least one organic layer including the quantum dots may be less than or equal to about 20 μm .

[0010] According to an embodiment, the at least one inorganic layer may have a thickness less than or equal to about 5 μm and may include at least one of silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y) or aluminum oxide (Al_2O_3).

[0011] According to an embodiment, the pixel electrode may be a reflective electrode that reflects light, and the counter electrode may be a transparent or semi-transparent electrode that at least partially transmits light therethrough.

[0012] According to an embodiment, the organic emission layer may emit blue light.

[0013] According to an embodiment, the quantum dots may absorb at least a part of the blue light and emit yellow light, and at least a part of the blue light may be transmitted through the organic layer including the quantum dots.

[0014] According to an embodiment, the at least one inorganic layer may include a first inorganic layer over the counter electrode and a second inorganic layer over the first inorganic layer, and the at least one organic layer including the quantum dots may include a lower organic layer between the first inorganic layer and the second inorganic layer.

[0015] According to an embodiment, the second inorganic layer may include a first area directly contacting the first inorganic layer, and a second area that is spaced apart from the first inorganic layer by the lower organic layer.

[0016] According to an embodiment, the at least one organic layer including the quantum dots may further include an upper organic layer over the second inorganic layer, and the at least one inorganic layer may further include a third inorganic layer over the upper organic layer.

[0017] According to an embodiment, the pixel electrode may include a first pixel electrode, a second pixel electrode, and a third pixel electrode that are apart from one another, the pixel-defining layer may include a first opening, a second opening, and a third opening that expose at least portions of the first pixel electrode, the second pixel electrode, and the third pixel electrode, respectively, and the intermediate layer may include a first intermediate layer over the first pixel electrode, a second intermediate layer over the second pixel electrode, and a third intermediate layer over the third pixel electrode.

[0018] According to an embodiment, the at least one organic layer including the quantum dots may include a first organic layer that is in the first opening and includes first quantum dots of the quantum dots, a second organic layer that is in the second opening and includes second quantum dots of the quantum dots, and a third organic layer that is in the third opening and includes third quantum dots of the quantum dots.

[0019] According to an embodiment, the first intermediate layer, the second intermediate layer, and the third intermediate layer may emit red light, green light, and blue light, respectively, and the first quantum dots, the second quantum dots, and the third quantum dots may be red quantum dots, green quantum dots, and blue quantum dots, respectively.

[0020] According to an embodiment, all of the first intermediate layer, the second intermediate layer, and the third

intermediate layer may emit white light, and the first quantum dots, the second quantum dots, and the third quantum dots may be red quantum dots, green quantum dots, and blue quantum dots, respectively.

[0021] According to an embodiment, the first organic layer, the second organic layer, and the third organic layer may be separated from one another by the pixel-defining layer.

[0022] According to one or more embodiments, a method of manufacturing an organic light-emitting display apparatus includes forming a pixel electrode disposed over a substrate; forming a pixel-defining layer including an opening that exposes at least a portion of the pixel electrode over the pixel electrode; forming an intermediate layer, which includes an organic emission layer, over the portion of the pixel electrode exposed by the opening; forming a counter electrode over the intermediate layer; and forming an encapsulating structure, which includes at least one inorganic layer and at least one organic layer over the counter electrode, wherein the organic layer includes quantum dots and is in the opening.

[0023] According to an embodiment, the thickness of the at least one organic layer including the quantum dots may be less than or equal to about 20 μm .

[0024] According to an embodiment, the at least one inorganic layer may have a thickness less than or equal to about 5 μm and may include at least one of silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y), and aluminum oxide (Al_2O_3).

[0025] According to an embodiment, the forming of the encapsulating structure may include forming a first inorganic layer of the at least one inorganic layer over the counter electrode; forming an organic layer of the at least one organic layer including the quantum dots over the first inorganic layer; and forming a second inorganic layer of the at least one inorganic layer over the organic layer.

[0026] According to an embodiment, the forming of the organic layer may include forming an organic material having dispersed therein the quantum dots in the opening included in the pixel-defining layer via inkjet-printing; and curing the organic material having dispersed therein the quantum dots.

[0027] According to an embodiment, the forming of the second inorganic layer may include forming the second inorganic layer to include a first area directly contacting the first inorganic layer, and a second area that is spaced apart from the first inorganic layer by the organic layer including the quantum dots.

BRIEF DESCRIPTION OF THE DRAWINGS

[0028] These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings in which:

[0029] FIG. 1 is a schematic sectional view of an organic light-emitting display apparatus according to an embodiment;

[0030] FIG. 2 is a schematic sectional view of an organic light-emitting display apparatus according to another embodiment;

[0031] FIGS. 3A through 3G are sectional diagrams showing a method of manufacturing the organic light-emitting display apparatus of FIG. 2, according to an embodiment; and

[0032] FIG. 4 is a schematic sectional view of an organic light-emitting display apparatus according to another embodiment.

DETAILED DESCRIPTION

[0033] As the inventive concept allows for various changes and numerous embodiments, some particular embodiments will be illustrated in the drawings and described in further detail in the following description. However, this is not intended to limit the inventive concept to particular modes of practice, and it is to be appreciated that all changes, equivalents, and substitutes that do not depart from the spirit and technical scope of the inventive concept are encompassed in the inventive concept. In the description of the inventive concept, certain detailed explanations of the related art are omitted when it is deemed that they may unnecessarily obscure the essence of the inventive concept.

[0034] It will be understood that although the terms “first,” “second,” etc. may be used herein to describe various components, these components should not be limited by these terms. These components are only used to distinguish one component from another.

[0035] As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0036] It will be further understood that the terms “comprises” and/or “comprising” used herein specify the presence of stated features or components, but do not preclude the presence or addition of one or more other features or components.

[0037] It will be understood that when a layer, region, or component is referred to as being “formed on” another layer, region, or component, it can be directly or indirectly formed on the other layer, region, or component. That is, for example, intervening layers, regions, or components may be present.

[0038] Sizes of elements in the drawings may be exaggerated for convenience of explanation. In other words, since sizes and thicknesses of components in the drawings may be arbitrarily illustrated for convenience of explanation, the following embodiments are not limited thereto.

[0039] Reference will now be made in further detail to some embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of” when preceding a list of elements, modify the entire list of elements, and do not modify the individual elements of the list.

[0040] FIG. 1 is a schematic sectional view of an organic light-emitting display apparatus 1 according to an embodiment.

[0041] Referring to FIG. 1, the organic light-emitting display apparatus 1 according to an embodiment includes a flexible substrate 110, a pixel electrode 120 disposed over the flexible substrate 110, an intermediate layer 130, which is disposed over the pixel electrode 120 and includes an

organic emission layer **133**, a counter electrode **140** disposed over the intermediate layer **130**, and an encapsulating structure **150**, which is disposed over the counter electrode **140** and includes at least one inorganic layer **151**, **153**, **155** and at least one organic layer **152**, **154** including quantum dots **152a** and **154a**.

[0042] The flexible substrate **110** may include various materials, such as glass, a metal, or plastic. Here, the flexible substrate **110** may refer to a substrate that may be easily bent, curved, folded, or rolled. The flexible substrate **110** may include ultra-thin glass, a metal, or plastic. For example, if the flexible substrate **110** includes plastic, the flexible substrate **110** may include polyimide (PI), but is not limited thereto.

[0043] An organic light-emitting device OLED is disposed over the flexible substrate **110**, where the organic light-emitting device OLED may include the pixel electrode **120**, the intermediate layer **130**, and the counter electrode **140**.

[0044] The pixel electrode **120** may be a reflective electrode including a reflective layer. According to an embodiment, the reflective layer may include at least one of silver (Ag), magnesium (Mg), aluminum (Al), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), and chromium (Cr), where a transparent or semi-transparent electrode layer including at least one selected from a group consisting of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), indium gallium oxide (IGO), and aluminum zinc oxide (AZO) may be further disposed over the reflective layer. For example, the pixel electrode **120** may include three layers of ITO/Ag/ITO.

[0045] The counter electrode **140** may include various conductive materials and may be a transparent or semi-transparent electrode. According to an embodiment, the counter electrode **140** may include one or more materials selected from among silver (Ag), aluminum (Al), ytterbium (Yb), titanium (Ti), magnesium (Mg), nickel (Ni), lithium (Li), calcium (Ca), copper (Cu), LiF/Ga, LiF/Al, MgAg, and CaAg, where the counter electrode **140** may include a thin film having a thickness from several nm to dozens of nm by using one or more of the above-stated materials to transmit light therethrough.

[0046] The organic light-emitting display apparatus **1** according to an embodiment may be a top-emission type display apparatus in which light is emitted from the intermediate layer **130** toward the encapsulating structure **150**.

[0047] The intermediate layer **130** includes the organic emission layer **133** and may further include a common layer. According to an embodiment, the common layer may include a hole injection layer **131** and a hole transport layer **132** between the pixel electrode **120** and the organic emission layer **133** and may include an electron transport layer **134** and an electron injection layer **135** between the organic emission layer **133** and the counter electrode **140**.

[0048] However, the inventive concept is not limited thereto. The intermediate layer **130** may not include at least some of the above-stated common layers or may further include function layers other than the above-stated common layers.

[0049] According to an embodiment, the organic light-emitting device OLED may emit red light, green light, or blue light according to the type of the organic emission layer

133. However, the inventive concept is not limited thereto, and the organic light-emitting device OLED may emit other light colors or white light.

[0050] In the case the organic light-emitting device OLED emits white light, the organic emission layer **133** included in the organic light-emitting device OLED may have a structure in which different types of organic emission layers are stacked or may be a layer including a combination of different organic materials.

[0051] The encapsulating structure **150** may be disposed over the organic light-emitting device OLED, where the encapsulating structure **150** may include at least one inorganic layer **151**, **153**, **155** and at least one organic layer **152**, **154**. According to an embodiment, the encapsulating structure **150** may include a first inorganic layer **151** disposed over the counter electrode **140**, a lower organic layer **152**, which is disposed over the first inorganic layer **151** and includes quantum dots **152a**, and a second inorganic layer **153** disposed over the lower organic layer **152**. In other words, the lower organic layer **152** may be between the first inorganic layer **151** and the second inorganic layer **153**. An upper organic layer **154** including quantum dots **154a** may be disposed over the second inorganic layer **153**, and a third inorganic layer **155** may be further disposed over the upper organic layer **154**.

[0052] Although FIG. 1 shows a case in which the three inorganic layers **151**, **153**, and **155** and the two organic layers **152** and **154** are disposed, the inventive concept is not limited thereto.

[0053] The encapsulating structure **150** seals the organic light-emitting device OLED to prevent or substantially prevent the organic light-emitting device OLED from being exposed to the outside atmosphere or impurities. Since the encapsulating structure **150** has a very small thickness, the encapsulating structure **150** may be used as an encapsulating structure in a bendable or foldable flexible display apparatus.

[0054] A function layer **170** that enhances characteristics emitted by the organic light-emitting device OLED may be further disposed between the counter electrode **140** and the encapsulating structure **150**, where the function layer **170** may include a capping layer and a cover layer that protects the organic light-emitting device OLED from possible damage during an operation using plasma, for example. According to an embodiment, the capping layer may include an organic material, whereas the cover layer may include LiF.

[0055] According to an embodiment, the inorganic layers **151**, **153**, and **155** may include silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y) or aluminum oxide (Al_2O_3) and may block or reduce permeation of impurities, such as moisture or oxygen, to the organic light-emitting device OLED.

[0056] The organic layers **152** and **154** may include organic materials **152b** and **154b** and the quantum dots **152a** and **154a** that are respectively dispersed in the organic materials **152b** and **154b**. The organic layers **152** and **154** may be used together with the inorganic layers **151**, **153**, and **155** to improve sealing characteristics of the encapsulating structure **150** and to planarize rough surfaces therebelow. The organic materials **152b** and **154b** may include various organic materials, such as epoxy-based resins, acryl-based resins, or polyimide-based resins, and may be inkjet-printable materials.

[0057] According to an embodiment, a thickness t_1 of each of the inorganic layers 151, 153, and 155 may be less than or equal to about 5 μm , whereas a thickness t_2 of each of the organic layers 152 and 154 may be less than or equal to about 20 μm . If the thickness t_1 of each of the inorganic layers 151, 153, and 155 exceeds about 5 μm or the thickness t_2 of each of the organic layers 152 and 154 exceeds about 20 μm , it may be difficult to reduce the thickness of the organic light-emitting display apparatus 1 and/or to manufacture the organic light-emitting display apparatus 1 as a flexible display apparatus.

[0058] Furthermore, the thickness t_1 of each of the inorganic layers 151, 153, and 155 may be greater than about 300 nm, whereas the thickness t_2 of each of the organic layers 152 and 154 may be greater than about 1 μm . If the thickness t_1 of each of the inorganic layers 151, 153, and 155 is less than or equal to about 300 nm, it may be difficult to block permeation of moisture or oxygen to the organic light-emitting device OLED. If the thickness t_2 of each of the organic layers 152 and 154 is less than or equal to about 1 μm , it may be difficult to uniformly disperse the quantum dots 152a and 154a having sizes from several nm to hundreds of nm.

[0059] The quantum dots 152a and 154a are respectively dispersed in the organic materials 152b and 154b. A quantum dot refers to a spherical semiconductor nano-material having a size from several nm to hundreds of nm and may include a core CR including a material having a small band gap and a shell SL that surrounds the core CR. Unlike a material in a bulk state, a quantum dot has discontinuous band gap energy due to the quantum confinement effect. Therefore, a quantum dot may absorb light of a certain wavelength and emit light of a wavelength longer than that of the absorbed light, where the emitted light may have very high color purity with a small full width at half maximum (FWHM). The quantum dot may further include a capping ligand CL for preventing quantum dots from being massed with one another and improving solubility.

[0060] According to an embodiment, the core CR may include a group II-VI semiconductor, a group III-V semiconductor, a group I-III-VI semiconductor, or a group VI-IV semiconductor and may include one of CdSe, CdTe, CdS, ZnSe, ZnO, ZnTe, InP, InAs, GaP, GaInP₂, PbS, TiO, AgI, AgBr, PbSe, In₂S₃, In₂Se₃, Cd₃P₂, Cd₃As₂, InGaN, and InN.

[0061] Intervals between energy bands vary depending on sizes of the quantum dots. Therefore, if same quantum dots with different sizes are used, light of different wavelengths may be emitted. An energy band gap of a quantum dot increases as the size of the quantum dot decreases, and thus the wavelength of light emitted thereby decreases.

[0062] The quantum dots 152a and 154a included in the organic layers 152 and 154 may absorb light of a certain wavelength and emit light of a wavelength longer than that of the absorbed light. According to an embodiment, the quantum dots 152a and 154a may be red quantum dots that emit red light, green quantum dots that emit green light, blue quantum dots that emit blue light, or yellow quantum dots that emit yellow light.

[0063] According to an embodiment, the organic light-emitting device OLED may emit blue light, and the quantum dots 152a and 154a included in the organic layers 152 and 154 of the encapsulating structure 150 may be yellow quantum dots that absorb blue light and emit yellow light. According to another embodiment, the quantum dots 152a

and 154a may be a combination of red quantum dots that absorb blue light and emit red light and green quantum dots that emit green light. In this case, yellow light may be emitted as a combination of red light and green light.

[0064] According to another embodiment, the quantum dots 152a included in the single organic layer 152 may be red quantum dots, whereas the quantum dots 154a included in the other organic layer 154 may be green quantum dots.

[0065] A part of blue light emitted by the organic light-emitting device OLED may not be absorbed by the encapsulating structure 150 and may be transmitted therethrough, whereas the other part of the blue light may be absorbed by the quantum dots 152a and 154a included in the encapsulating structure 150 and transformed to yellow light. As a result, the organic light-emitting display apparatus 1 may emit white light as a combination of the blue light and the yellow light.

[0066] FIG. 2 is a schematic sectional view of an organic light-emitting display apparatus 2 according to another embodiment. Descriptions below of the organic light-emitting display apparatus 2 according to another embodiment will focus on differences between the organic light-emitting display apparatus 2 of FIG. 2 and the organic light-emitting display apparatus 1 previously described.

[0067] Referring to FIG. 2, the organic light-emitting display apparatus 2 according to an embodiment may include a substrate 210, a pixel electrode 220 disposed over the substrate 210, a pixel-defining layer 260 including an opening 260h that exposes at least a portion of the pixel electrode 220, an intermediate layer 230, which is disposed on the portion of pixel electrode 220 exposed by the opening 260h and includes an organic emission layer, a counter electrode 240 disposed over the intermediate layer 230, and an encapsulating structure 250, which is disposed over the counter electrode 240 and includes at least one inorganic layer 251 or 253 and at least one organic layer 252 including quantum dots 252a.

[0068] A pixel circuit that drives an organic light-emitting device OLED and includes at least one thin-film transistor (TFT) may be between the substrate 210 and the organic light-emitting device OLED.

[0069] The TFT may include an active layer 213 disposed over the substrate 210, a gate electrode 215 disposed over at least a portion of the active layer 213, and a source electrode 217S and a drain electrode 217D that are disposed over the gate electrode 215 and are electrically connected to the active layer 213.

[0070] A buffer layer 212 may be between the substrate 210 and the active layer 213, a first insulation layer 214 may be between the active layer 213 and the gate electrode 215, and a second insulation layer 216 may be disposed over the gate electrode 215.

[0071] A third insulation layer 218 may be disposed over the second insulation layer 216 and covers the source electrode 217S and the drain electrode 217D, and the third insulation layer 218 may include a via hole VIA that exposes at least a portion of the drain electrode 217D. The TFT may be electrically connected to the pixel electrode 220 via the via hole VIA.

[0072] According to an embodiment, the pixel electrode 220 may be a reflective electrode, the counter electrode 240 may be a transparent or semi-transparent electrode, and light emitted by the organic emission layer included in the intermediate layer 230 may be transmitted through the counter

electrode **240** and emitted from the organic light-emitting display apparatus **2**. In other words, the organic light-emitting display apparatus **2** may be a top-emission type display apparatus.

[0073] According to an embodiment, the TFT may overlap the pixel electrode **220** in a plan view. In other words, when viewed in a direction perpendicular to the main surfaces of the substrate **210**, the pixel electrode **220** and the TFT may at least partially overlap each other.

[0074] In the top-emission type organic light-emitting display apparatus **2**, since at least a portion of the pixel circuit is between the substrate **210** and the pixel electrode **220**, it is not necessary to secure a separate space for arranging the pixel circuit, and thus an aperture ratio of the organic light-emitting display apparatus **2** may be increased.

[0075] The intermediate layer **230** includes an organic emission layer and may further include a hole injection layer, a hole transport layer, an electron transport layer, and/or an electron injection layer. According to an embodiment, the intermediate layer **230** includes an organic emission layer, and the organic light-emitting device OLED may emit red light, green light, or blue light according to the type of the organic emission layer. However, the inventive concept is not limited thereto, and the organic light-emitting device OLED may emit other light colors or white light.

[0076] The encapsulating structure **250** may be disposed over the organic light-emitting device OLED, where the encapsulating structure **250** may include at least one inorganic layer **251**, **253** and at least one organic layer **252**. According to an embodiment, the encapsulating structure **250** may include a first inorganic layer **251** disposed over the counter electrode **240**, a lower organic layer **252**, which is disposed over the first inorganic layer **251** and includes quantum dots **252a**, and a second inorganic layer **253** disposed over the lower organic layer **252**. Although FIG. **2** shows a case in which two inorganic layers **251** and **253** and one lower organic layer **252** are disposed, the inventive concept is not limited thereto.

[0077] According to an embodiment, the inorganic layers **251** and **253** may include silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y) or aluminum oxide (Al_2O_3) and may block or reduce permeation of impurities, such as moisture or oxygen, to the organic light-emitting device OLED.

[0078] The lower organic layer **252** may include an organic material **252b** and the quantum dots **252a** that are dispersed in the organic material **252b**. The lower organic layer **252** may be used together with the inorganic layers **251** and **253** to improve sealing characteristics of the encapsulating structure **250** and to planarize rough surfaces therebelow. The organic material **252b** may include various organic materials, such as epoxy-based resins, acryl-based resins, or polyimide-based resins, and may be an inkjet-printable material.

[0079] According to an embodiment, a thickness **t1** of each of the inorganic layers **251** and **253** may be less than or equal to about $5\ \mu\text{m}$, whereas a thickness **t2** of the lower organic layer **252** may be less than or equal to about $20\ \mu\text{m}$. If the thickness **t1** of each of the inorganic layers **251** and **253** exceeds about $5\ \mu\text{m}$ or the thickness **t2** of the lower organic layer **252** exceeds about $20\ \mu\text{m}$, it may be difficult to reduce the thickness of the organic light-emitting display apparatus **2** and/or to manufacture the organic light-emitting display apparatus **2** as a flexible display apparatus.

[0080] Furthermore, the thickness **t1** of each of the inorganic layers **251** and **253** may be greater than about $300\ \text{nm}$, whereas the thickness **t2** of the lower organic layer **252** may be greater than about $1\ \mu\text{m}$. If the thickness **t1** of each of the inorganic layers **251** and **253** is less than or equal to about $300\ \text{nm}$, it may be difficult to block permeation of moisture or oxygen to the organic light-emitting device OLED. If the thickness **t2** of the lower organic layer **252** is less than or equal to about $1\ \mu\text{m}$, it may be difficult to uniformly disperse the quantum dots **252a** having sizes from several nm to hundreds of nm.

[0081] The lower organic layer **252** including the quantum dots **252a** may be inside the opening **260h** in the pixel-defining layer **260**. In other words, the lower organic layer **252** may be in an area defined by the pixel-defining layer **260**.

[0082] Therefore, according to an embodiment, the lower organic layer **252** may be only in an area corresponding to the opening **260h**, between the first inorganic layer **251** and the second inorganic layer **253**. The second inorganic layer **253** may include a first area **253a** that directly contacts the first inorganic layer **251** and a second area **253b** that is disposed or spaced apart from the first inorganic layer **251** by the lower organic layer **252**.

[0083] The first area **253a** may correspond to an area in which the pixel-defining layer **260** is disposed, whereas the second area **253b** may correspond to an area above the pixel electrode **220** exposed by the opening **260h** in the pixel-defining layer **260**.

[0084] The quantum dots **252a** included in the lower organic layer **252** may absorb light of a certain wavelength and emit light of a wavelength longer than that of the absorbed light. According to an embodiment, the quantum dots **252a** may be red quantum dots that emit red light, green quantum dots that emit green light, blue quantum dots that emit blue light, or yellow quantum dots that emit yellow light.

[0085] According to an embodiment, the organic light-emitting device OLED may emit blue light, and the quantum dots **252a** included in the lower organic layer **252** of the encapsulating structure **250** may be yellow quantum dots that absorb blue light and emit yellow light or a combination of red quantum dots that absorb blue light and emit red light and green quantum dots that emit green light.

[0086] A part of blue light emitted by the organic light-emitting device OLED may not be absorbed by the encapsulating structure **250** and may be transmitted therethrough, whereas the other part of the blue light may be absorbed by the quantum dots **252a** included in the encapsulating structure **250** and transformed to yellow light. As a result, the organic light-emitting display apparatus **2** may emit white light as a combination of the blue light and the yellow light.

[0087] However, the inventive concept is not limited thereto. The organic light-emitting device OLED included in the organic light-emitting display apparatus **2** may emit light of various colors, and the organic light-emitting display apparatus **2** including the organic light-emitting device OLED and the encapsulating structure **250** may emit light of various colors other than white light, such as red light, green light, blue light, and yellow light.

[0088] FIGS. **3A** through **3G** are sectional diagrams showing (e.g., sequentially showing) a method of manufacturing the organic light-emitting display apparatus **2** of FIG. **2**, according to an embodiment.

[0089] A method of manufacturing an organic light-emitting display apparatus according to an embodiment includes formation of the pixel electrode **220** over the substrate **210**, formation of the pixel-defining layer **260**, which includes the opening **260h** exposing at least a portion of the pixel electrode **220**, over the pixel electrode **220**, formation of the intermediate layer **230** including the organic emission layer over the portion of the pixel electrode **220** exposed by the opening **260h**, formation of the counter electrode **240** over the intermediate layer **230**, and formation of the encapsulating structure **250**, which includes the at least one inorganic layer **251**, **253** and the at least one organic layer **252** including the quantum dots **252a** and disposed inside the opening **260h**, over the counter electrode **240**.

[0090] Referring to FIG. 3A, after the pixel circuit including a switching device, such as the TFT, is formed over the substrate **210**, the pixel electrode **220** electrically connected to the pixel circuit is formed.

[0091] The pixel electrode **220** may be a reflective electrode including a reflective layer. According to an embodiment, the reflective layer may include at least one selected from silver (Ag), magnesium (Mg), aluminum (Al), platinum (Pt), palladium (Pd), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), and chromium (Cr), where a transparent or semi-transparent electrode layer including at least one selected from a group consisting of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), indium gallium oxide (IGO), and aluminum zinc oxide (AZO) may be further disposed over the reflective layer. For example, the pixel electrode **220** may include three layers of ITO/Ag/ITO.

[0092] The pixel electrode **220** may be formed as an island-like structure by forming the metal and the conductive oxide over the substrate **210** and patterning the same.

[0093] Referring to FIG. 3B, the pixel-defining layer **260** including the opening **260h** that exposes at least a portion of the pixel electrode **220** may be formed over the pixel electrode **220**.

[0094] The pixel-defining layer **260** may include an organic material, such as polyimide (PI), where the pixel-defining layer **260** including the opening **260h** that exposes a portion of the pixel electrode **220** may be formed by forming an organic material over the substrate **210** to cover the pixel electrode **220** and patterning the same.

[0095] The portion exposed by the opening **260h** may be the center area of the pixel electrode **220**, whereas the portion covered by the pixel-defining layer **260** may be the edge area of the pixel electrode **220**.

[0096] Referring to FIG. 3C, the intermediate layer **230** including the organic emission layer may be formed over the portion of the pixel electrode **220** exposed by the opening **260h** in the pixel-defining layer **260**. The intermediate layer **230** includes the organic emission layer and may further include at least one of a hole injection layer (HIL), a hole transport layer (HTL), an electron transport layer (ETL), and an electron injection layer (EIL). Although not shown, the HIL, the HTL, the ETL, and the EIL may not only be disposed inside the opening **260h**, but also extend onto the top of the pixel-defining layer **260**.

[0097] The organic emission layer may emit red light, green light, blue light, or white light.

[0098] Referring to FIG. 3D, the counter electrode **240** may be formed over the intermediate layer **230**. The counter electrode **240** may be disposed over the intermediate layer

230 and the pixel-defining layer **260**. The counter electrode **240** may be a transparent or semi-transparent electrode. According to an embodiment, the counter electrode **240** may include one or more materials selected from among silver (Ag), aluminum (Al), ytterbium (Yb), titanium (Ti), magnesium (Mg), nickel (Ni), lithium (Li), calcium (Ca), copper (Cu), LiF/Ga, LiF/Al, MgAg, and CaAg, where the counter electrode **240** may include a thin film having a thickness from several nm to dozens of nm by using one or more of the above-stated materials to transmit light therethrough.

[0099] Referring to FIG. 3E, the first inorganic layer **251** may be formed over the counter electrode **240**. The first inorganic layer **251** may include silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y), or aluminum oxide (Al_2O_3) and may be formed by using a sputtering method or a chemical vapor deposition (CVD) method, for example.

[0100] The thickness **t1** of the first inorganic layer **251** may be less than or equal to about 5 μm .

[0101] Referring to FIG. 3F, the organic material **252b** having dispersed therein the quantum dots **252a** may be formed inside the opening **260h** of the pixel-defining layer **260** over the first inorganic layer **251** via inkjet-printing, for example. The organic material **252b** may include any of various organic materials, such as epoxy-based resins, acrylic-based resins, or polyimide-based resins.

[0102] By ejecting the organic material **252b** having dispersed therein the quantum dots **252a** from a nozzle **10** included in an inkjet printing apparatus, the organic material **252b** may be dropped into an area defined by the pixel-defining layer **260** that functions as a barrier.

[0103] Referring to FIG. 3G, the lower organic layer **252** including the quantum dots **252a** may be formed by coating the organic material **252b** having dispersed therein the quantum dots **252a** over the top surface of the portion of the first inorganic layer **251** inside the opening **260h** and curing the same. The thickness **t2** of the lower organic layer **252** may be less than or equal to about 20 μm .

[0104] Referring back to FIG. 2, by forming the second inorganic layer **253** over the lower organic layer **252**, the encapsulating structure **250** including the first inorganic layer **251**, the lower organic layer **252**, and the second inorganic layer **253** may be formed. The second inorganic layer **253** may include the first area **253a** that directly contacts the first inorganic layer **251** and the second area **253b** that is disposed or spaced apart from the first inorganic layer **251** by the lower organic layer **252**.

[0105] Although not shown, a function layer that enhances characteristics emitted by the organic light-emitting device OLED may be further formed before the first inorganic layer **251** is formed.

[0106] According to the organic light-emitting display apparatus **2** and the method of manufacturing the same as described above, the organic layer **252** including the quantum dots **252a** may be simply formed inside the opening **260h** in the pixel-defining layer **260** to enhance color purity of the organic light-emitting display apparatus **2**, and the lower organic layer **252**, which is a part of the encapsulating structure **250**, may prevent or substantially prevent permeation of moisture or oxygen to the organic light-emitting device OLED, together with the inorganic layers **251** and **253**.

[0107] Color purity of the organic light-emitting display apparatus **2** may be enhanced by introducing the quantum

dots **252a** to the encapsulating structure **250** without adding a separate layer, and thus the organic light-emitting display apparatus **2** may be easily manufactured as a flexible display apparatus.

[0108] FIG. 4 is a schematic sectional view of an organic light-emitting display apparatus **3** according to another embodiment. Descriptions below of the organic light-emitting display apparatus **3** according to another embodiment will focus on differences between the organic light-emitting display apparatus **3** of FIG. 4 and the organic light-emitting display apparatuses **1** and **2** previously described.

[0109] Referring to FIG. 4, the organic light-emitting display apparatus **3** according to another embodiment may include a substrate **310**, pixel electrodes **320r**, **320g**, and **320b** disposed over the substrate **310**, a pixel-defining layer **360** including openings **360hr**, **360hg**, and **360hb** that respectively expose at least portions of the pixel electrodes **320r**, **320g**, and **320b**, intermediate layers **330r**, **330g**, and **330b** that are disposed over respective portions of the pixel electrodes **320r**, **320g**, and **320b** exposed by the openings **360hr**, **360hg**, and **360hb** and include organic emission layers, a counter electrode **340** disposed over the intermediate layers **330r**, **330g**, and **330b**, and an encapsulating structure **350** including at least one inorganic layer **351**, **353** and at least one organic layer **352r**, **352g**, **352b**, where the organic layers **352r**, **352g**, and **352b** include quantum dots **352ra**, **352ga**, and **352ba** and are disposed in the openings **360hr**, **360hg**, and **360hb**, respectively.

[0110] The organic light-emitting display apparatus **3** according to an embodiment may include a plurality of pixels adjacent to one another, where the plurality of pixels may emit light of different colors. Each of the plurality of pixels may include the pixel electrodes **320r**, **320g**, and **320b** and the intermediate layers **330r**, **330g**, and **330b**.

[0111] The pixel electrodes **320r**, **320g**, and **320b** may include a first pixel electrode **320r**, a second pixel electrode **320g**, and a third pixel electrode **320b** that are apart from one another, and the pixel-defining layer **360** may include a first opening **360hr**, a second opening **360hg**, and a third opening **360hb** that expose the first pixel electrode **320r**, the second pixel electrode **320g**, and the third pixel electrode **320b**, respectively.

[0112] The intermediate layers **330r**, **330g**, and **330b** may include a first intermediate layer **330r** disposed over the first pixel electrode **320r**, a second intermediate layer **330g** disposed over the second pixel electrode **320g**, and a third intermediate layer **330b** disposed over the third pixel electrode **320b**. The counter electrode **340** may be disposed over the intermediate layers **330r**, **330g**, and **330b**.

[0113] A pixel circuit that drives the plurality of pixels may be between the substrate **310** and the pixel electrodes **320r**, **320g**, and **320b**. The pixel circuit may include a first thin-film transistor TFT_r, a second thin-film transistor TFT_g, and a third thin-film transistor TFT_b that are electrically connected to the first pixel electrode **320r**, the second pixel electrode **320g**, and the third pixel electrode **320b**, respectively. Each of the plurality of pixels may be turned on or off by the pixel circuit.

[0114] According to an embodiment, the pixel electrodes **320r**, **320g**, and **320b** may be reflective electrodes, the counter electrode **340** may be a transparent or semi-transparent electrode, and light emitted by organic emission layers included in the intermediate layers **330r**, **330g**, and **330b** may be transmitted through the counter electrode **340**

and emitted from the organic light-emitting display apparatus **3**. In other words, the organic light-emitting display apparatus **3** may be a top-emission type display apparatus.

[0115] Each of the intermediate layers **330r**, **330g**, and **330b** includes an organic emission layer and may further include a hole injection layer, a hole transport layer, an electron transport layer, and/or an electron injection layer. The first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** may include a first organic emission layer, a second organic emission layer, and a third organic emission layer, respectively, where a hole injection layer, a hole transport layer, an electron transport layer, and/or an electron injection layer may be included in each of the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b**.

[0116] According to an embodiment, the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** may emit red light, green light, and blue light, respectively. According to another embodiment, all of the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** may emit white light. If all of the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** emit white light, the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** may have a same structure in which different types of organic emission layers are stacked or may include layers including a combination of different organic materials.

[0117] The encapsulating structure **350** may be disposed over the counter electrode **340**, where the encapsulating structure **350** may include the at least one inorganic layer **351**, **353** and the at least one organic layer **352r**, **352g**, **352b**. According to an embodiment, the encapsulating structure **350** may include a first inorganic layer **351** disposed over the counter electrode **340**, the organic layers **352r**, **352g**, and **352b**, which are disposed over the first inorganic layer **351** and respectively includes the quantum dots **352ra**, **352ga**, and **352ba**, and a second inorganic layer **353** disposed over the organic layers **352r**, **352g**, and **352b**.

[0118] According to an embodiment, the inorganic layers **351** and **353** may include silicon nitride (SiN_x), silicon oxide (SiO₂), silicon oxynitride (SiO_xN_y) or aluminum oxide (Al₂O₃) and may block or reduce permeation of impurities, such as moisture or oxygen, to the organic light-emitting device OLED.

[0119] The organic layers **352r**, **352g**, and **352b** may include organic materials **352rb**, **352gb**, and **352bb** and the quantum dots **352ra**, **352ga**, and **352ba** that are respectively dispersed in the organic materials **352rb**, **352gb**, and **352bb**. The organic layers **352r**, **352g**, and **352b** may be used together with the inorganic layers **351** and **353** to improve sealing characteristics of the encapsulating structure **350** and to planarize rough surfaces therebelow. The organic materials **352rb**, **352gb**, and **352bb** may include any of various organic materials, such as epoxy-based resins, acryl-based resins, or polyimide-based resins, and may be inkjet-printable materials.

[0120] According to an embodiment, a thickness t₁ of each of the inorganic layers **351** and **353** may be less than or equal to about 5 μm, whereas a thickness t₂ of each of the organic layers **352r**, **352g**, and **352b** may be less than or equal to about 20 μm. If the thickness t₁ of each of the

inorganic layers **351** and **353** exceeds about 5 μm or the thickness **t2** of each of the organic layers **352r**, **352g**, and **352b** exceeds about 20 μm , it may be difficult to reduce the thickness of the organic light-emitting display apparatus **3** and/or to manufacture the organic light-emitting display apparatus **3** as a flexible display apparatus.

[0121] Furthermore, the thickness **t1** of each of the inorganic layers **351** and **353** may be greater than about 300 nm, whereas the thickness **t2** of each of the organic layers **352r**, **352g**, and **352b** may be greater than about 1 μm . If the thickness **t1** of each of the inorganic layers **351** and **353** is less than or equal to about 300 nm, it may be difficult to block permeation of moisture or oxygen to the organic light-emitting device OLED. If the thickness **t2** of each of the organic layers **352r**, **352g**, and **352b** is less than or equal to about 1 μm , it may be difficult to uniformly disperse the quantum dots **352ra**, **352ga**, and **352ba** having sizes from several nm to hundreds of nm.

[0122] The organic layers **352r**, **352g**, and **352b** including the quantum dots **352ra**, **352ga**, and **352ba** may be inside the openings **360hr**, **360hg**, and **360hb** included in the pixel-defining layer **360**. In other words, the organic layers **352r**, **352g**, and **352b** may be in an area defined by the pixel-defining layer **360**.

[0123] The organic layers **352r**, **352g**, and **352b** may include a first organic layer **352r** that is disposed inside the first opening **360hr** and includes first quantum dots **352ra**, a second organic layer **352g** that is disposed inside the second opening **360hg** and includes second quantum dots **352ga**, and a third organic layer **352b** that is disposed inside the third opening **360hb** and includes third quantum dots **352ba**. The first organic layer **352r**, the second organic layer **352g**, and the third organic layer **352b** may be separated from each other by the pixel-defining layer **360**. The first quantum dots **352ra**, the second quantum dots **352ga**, and the third quantum dots **352ba** may be disposed on a path in which light is transmitted through the counter electrode **340**.

[0124] The first quantum dots **352ra**, the second quantum dots **352ga**, and the third quantum dots **352ba** may be red quantum dots, green quantum dots, and blue quantum dots, respectively. The red quantum dots, the green quantum dots, and the blue quantum dots refer to quantum dots that absorb light of a certain wavelength and emit light of a wavelength corresponding to red, light of a wavelength corresponding to green, and light of a wavelength corresponding to blue, respectively.

[0125] According to an embodiment, the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** may respectively emit red light, green light, and blue light having a certain FWHM, where the first quantum dots **352ra**, the second quantum dots **352ga**, and the third quantum dots **352ba** may at least partially absorb the red light, the green light, and the blue light respectively emitted by the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** and emit red light, green light, and blue light having a relatively small FWHM.

[0126] In other words, a FWHM of light transmitted through the first organic layer **352r**, the second organic layer **352g**, and the third organic layer **352b** may be less than a FWHM of light emitted by the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b**. Accordingly, color purity of the organic light-emitting display apparatus **3** may be enhanced.

[0127] According to another embodiment, the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** may emit white light, and the first quantum dots **352ra**, the second quantum dots **352ga**, and the third quantum dots **352ba** may at least partially absorb the white light emitted by the first intermediate layer **330r**, the second intermediate layer **330g**, and the third intermediate layer **330b** and emit red light, green light, and blue light having a small FWHM.

[0128] The organic layers **352r**, **352g**, and **352b** may be only in areas corresponding to the openings **360hr**, **360hg**, and **360hb** between the first inorganic layer **351** and the second inorganic layer **353**. Therefore, the second inorganic layer **353** may include a first area **353a** that directly contacts the first inorganic layer **351** and a second area **353b** that is disposed or spaced apart from the first inorganic layer **351** by the organic layers **352r**, **352g**, and **352b**.

[0129] The first area **353a** may correspond to an area in which the pixel-defining layer **360** is disposed, whereas the second area **353b** may correspond to areas above the pixel electrodes **320r**, **320g**, and **320b** respectively exposed by the openings **360hr**, **360hg**, and **360hb** included in the pixel-defining layer **360**.

[0130] According to embodiments of the inventive concept, by disposing an encapsulating structure including an organic layer having dispersed therein quantum dots, an organic light-emitting display apparatus with enhanced color purity that may be easily manufactured as a flexible display apparatus, and a method of manufacturing the same may be provided.

[0131] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0132] While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims.

What is claimed is:

1. A display apparatus comprising:

- a substrate;
- a pixel electrode over the substrate;
- a pixel-defining layer comprising an opening that exposes at least a portion of the pixel electrode;
- an intermediate layer, which is over the portion of the pixel electrode exposed by the opening and comprises an organic emission layer;
- a counter electrode over the intermediate layer; and
- an encapsulating structure, which is over the counter electrode and comprises at least one inorganic layer and at least one organic layer,

wherein the at least one inorganic layer comprises a first inorganic layer and a second inorganic layer over the first inorganic layer, the first inorganic layer being in the opening and extending outside the opening,

wherein the at least one organic layer comprises quantum dots and comprises a lower organic layer and an upper organic layer over the lower organic layer, the lower organic layer being arranged between the first inorganic layer and the second inorganic layer, the lower organic layer being in the opening,

and wherein a thickness of the encapsulating structure in the opening is greater than a thickness of the encapsulating structure outside the opening.

2. The display apparatus of claim 1, wherein the thickness of the at least one organic layer comprising the quantum dots is less than or equal to about 20 μm .

3. The display apparatus of claim 1, wherein the at least one inorganic layer has a thickness less than or equal to about 5 μm and comprises at least one of silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y), or aluminum oxide (Al_2O_3).

4. The display apparatus of claim 1, wherein the pixel electrode comprises a reflective electrode that reflects light, and

the counter electrode comprises a transparent or semi-transparent electrode that at least partially transmits light therethrough.

5. The display apparatus of claim 1, wherein the organic emission layer emits blue light.

6. The display apparatus of claim 5, wherein the quantum dots absorb at least a part of the blue light and emit yellow light, and

at least a part of the blue light is transmitted through the at least one organic layer comprising the quantum dots.

7. The display apparatus of claim 1, wherein the second inorganic layer comprises a first area directly contacting the first inorganic layer, and a second area that is spaced apart from the first inorganic layer by the lower organic layer.

8. The display apparatus of claim 1, wherein the at least one inorganic layer further comprises a third inorganic layer over the upper organic layer.

9. The display apparatus of claim 1, wherein the pixel electrode comprises a first pixel electrode, a second pixel electrode, and a third pixel electrode that are apart from one another,

the pixel-defining layer comprises a first opening, a second opening, and a third opening that expose at least portions of the first pixel electrode, the second pixel electrode, and the third pixel electrode, respectively, and

the intermediate layer comprises a first intermediate layer over the first pixel electrode, a second intermediate layer over the second pixel electrode, and a third intermediate layer over the third pixel electrode.

10. The display apparatus of claim 9, wherein the at least one organic layer comprising the quantum dots comprises a first organic layer that is in the first opening and comprises first quantum dots of the quantum dots, a second organic layer that is in the second opening and comprises second quantum dots of the quantum dots, and a third organic layer that is in the third opening and comprises third quantum dots of the quantum dots.

11. The display apparatus of claim 10, wherein the first intermediate layer, the second intermediate layer, and the third intermediate layer emit red light, green light, and blue light, respectively, and

the first quantum dots, the second quantum dots, and the third quantum dots are red quantum dots, green quantum dots, and blue quantum dots, respectively.

12. The display apparatus of claim 10, wherein all of the first intermediate layer, the second intermediate layer, and the third intermediate layer emit white light, and

the first quantum dots, the second quantum dots, and the third quantum dots are red quantum dots, green quantum dots, and blue quantum dots, respectively.

13. The display apparatus of claim 10, wherein the first organic layer, the second organic layer, and the third organic layer are separated from one another by the pixel-defining layer.

14. A method of manufacturing a display apparatus, the method comprising:

forming a pixel electrode over a substrate;

forming a pixel-defining layer over the pixel electrode, the pixel-defining layer comprising an opening that exposes at least a portion of the pixel electrode;

forming an intermediate layer over the portion of the pixel electrode exposed by the opening, the intermediate layer comprising an organic emission layer;

forming a counter electrode over the intermediate layer; and

forming an encapsulating structure over the counter electrode, the encapsulating structure comprising at least one inorganic layer and at least one organic layer, wherein the at least one inorganic layer comprises a first inorganic layer and a second inorganic layer over the first inorganic layer, the first inorganic layer being in the opening and extending outside the opening, and wherein the at least one organic layer comprises quantum dots and comprises a lower organic layer and an upper organic layer over the lower organic layer, the lower organic layer being arranged between the first inorganic layer and the second inorganic layer, the lower organic layer being in the opening such that a thickness of the encapsulating structure in the opening is greater than a thickness of the encapsulating structure outside the opening.

15. The method of claim 14, wherein the thickness of the at least one organic layer comprising the quantum dots is less than or equal to about 20 μm .

16. The method of claim 14, wherein the at least one inorganic layer has a thickness less than or equal to about 5 μm and comprises at least one of silicon nitride (SiN_x), silicon oxide (SiO_2), silicon oxynitride (SiO_xN_y), and aluminum oxide (Al_2O_3).

17. The method of claim 14, wherein the forming of the encapsulating structure further comprises:

forming a third inorganic layer of the at least one inorganic layer over the upper organic layer.

18. The method of claim 17, wherein the forming of the organic layer comprises:

forming an organic material having dispersed therein the quantum dots in the opening included in the pixel-defining layer via inkjet-printing; and

curing the organic material having dispersed therein the quantum dots.

19. The method of claim 14, wherein the forming of the second inorganic layer comprises forming the second inorganic layer to comprise a first area directly contacting the first inorganic layer, and a second area that is spaced apart from the first inorganic layer by the organic layer including the quantum dots.

* * * * *

专利名称(译)	有机发光显示装置及其制造方法		
公开(公告)号	US20190348472A1	公开(公告)日	2019-11-14
申请号	US16/520175	申请日	2019-07-23
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	YUN WONMIN KIM YISU PARK EUNGSEOK LEE BYOUNGDUK CHUNG YUNAH CHO YOONHYEUNG JU YONGCHAN		
发明人	YUN, WONMIN KIM, YISU PARK, EUNGSEOK LEE, BYOUNGDUK CHUNG, YUNAH CHO, YOONHYEUNG JU, YONGCHAN		
IPC分类号	H01L27/32 H01L51/52		
CPC分类号	H01L2251/5369 H01L51/5253 H01L27/322 H01L27/32 H01L51/0097 H01L51/502 H01L51/5237 H01L51/56		
优先权	1020150187639 2015-12-28 KR		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光显示装置，包括：基板；和基板。基板上的像素电极；像素限定层，其包括暴露至少一部分像素电极的开口；中间层，在像素电极的由开口暴露的部分上，并且包括有机发射层；中间层上方的对电极；封装结构，其位于对电极上方并包括至少一个无机层和至少一个有机层，并且至少一个有机层包括量子点并且在开口中。

