



US 20130270524A1

(19) **United States**(12) **Patent Application Publication****Park et al.**(10) **Pub. No.: US 2013/0270524 A1**(43) **Pub. Date: Oct. 17, 2013**

(54) **COMPOUND FOR ORGANIC
LIGHT-EMITTING DIODE AND ORGANIC
LIGHT-EMITTING DIODE INCLUDING THE
SAME**

C07D 401/06 (2006.01)**C07D 209/94** (2006.01)**C07D 251/24** (2006.01)**C07D 307/91** (2006.01)**C07D 403/12** (2006.01)**C07D 405/12** (2006.01)**C07D 471/04** (2006.01)**C07D 401/14** (2006.01)**C07C 211/61** (2006.01)**C07D 333/00** (2006.01)

(71) Applicant: **SAMSUNG DISPLAY CO. LTD.**,
Yongin-si (KR)

(72) Inventors: **Jun-Ha Park**, Yongin-si (KR);
Seok-Hwan Hwang, Yongin-si (KR);
Young-Kook Kim, Yongin-si (KR);
Hye-Jin Jung, Yongin-si (KR);
Eun-Young Lee, Yongin-si (KR); **Jin-O**
Lim, Yongin-si (KR); **Sang-Hyun Han**,
Yongin-si (KR); **Eun-Jae Jeong**,
Yongin-si (KR); **Soo-Yon Kim**,
Yongin-si (KR); **Se-Jin Cho**, Yongin-si
(KR); **Jong-Hyuk Lee**, Yongin-si (KR)

(52) **U.S. Cl.**

USPC **257/40**; 564/427; 558/418; 546/255;
548/442; 548/420; 549/43; 549/460; 546/87;
546/256; 544/180; 257/E51.026

(73) Assignee: **SAMSUNG DISPLAY CO. LTD.**,
Yongin-si (KR)

(57)

ABSTRACT


A compound represented by Formula 1 below may be used in
an organic light emitting diode.

(21) Appl. No.: **13/633,850**(22) Filed: **Oct. 2, 2012**(30) **Foreign Application Priority Data**

Apr. 17, 2012 (KR) 10-2012-0039968

Publication Classification(51) **Int. Cl.****H01L 51/54** (2006.01)**C07C 255/58** (2006.01)

Formula 1



SECOND ELECTRODE

EIL

ETL

EML

HTL

HIL

FIRST ELECTRODE

FIG. 1

SECOND ELECTRODE
EIL
ETL
EML
HTL
HIL
FIRST ELECTRODE

**COMPOUND FOR ORGANIC
LIGHT-EMITTING DIODE AND ORGANIC
LIGHT-EMITTING DIODE INCLUDING THE
SAME**

CROSS-REFERENCE TO RELATED PATENT
APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2012-0039968, filed on Apr. 17, 2012 in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

[0002] 1. Technical Field

[0003] One or more embodiments of the present invention relate to compounds for organic light-emitting devices and to organic light-emitting devices including the compounds.

[0004] 2. Description of the Related Art

[0005] Organic light-emitting diodes (OLEDs) are self-emitting devices having advantages such as wide viewing angles, good contrast, quick response times, high brightness, and good driving voltage. OLEDs can provide multicolored images.

[0006] In general, an OLED has a structure including a substrate, an anode, a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and a cathode, which are sequentially stacked on the substrate. In this regard, the HTL, the EML, and the ETL are organic thin films formed of organic compounds.

[0007] An operating principle of an OLED having the above-described structure is as follows.

[0008] When a voltage is applied between the anode and the cathode, holes injected from the anode move to the EML via the HTL, and electrons injected from the cathode move to the EML via the ETL. The holes and electrons recombine in the EML to generate excitons. When the excitons drop from an excited state to a ground state, light is emitted.


[0009] The most important factor for determining the luminous efficiency of an OLED is the light-emitting material. Fluorescent materials or phosphorescent materials have been used as the light-emitting material, but OLEDs including such light-emitting materials do not exhibit satisfactory efficiency, driving voltage and lifetime.

SUMMARY

[0010] Embodiments of the present invention provide novel compounds for an organic light-emitting diode which have good electrical properties, good charge transporting abilities, good luminous properties and high glass transition temperatures. The compounds are capable of preventing crystallization, and may be used as electron transporting materials suitable for use in fluorescent and phosphorescent devices of all colors, such as red, green, blue, white, and the like. The compounds may also be used as light-emitting materials of green, blue, or white color having higher luminous efficiency and longer lifetimes than those of conventional host materials. The compounds also have appropriate color coordinates.

[0011] Embodiments of the present invention also provide an organic light-emitting diode including the compound described above and having high efficiency, low voltage, high brightness, and long lifetime.

[0012] According to an aspect of the present invention, a compound for an organic light-emitting diode is represented by Formula 1 below:



Formula 1

[0013] In Formula 1, R₁ and R₂ are each independently a halogen, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₃-C₆₀ heteroaryl group, or a substituted or unsubstituted C₆-C₆₀ condensed polycyclic group.

[0014] R₃ is hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₃-C₆₀ heteroaryl group, or a substituted or unsubstituted C₆-C₆₀ condensed polycyclic group.

[0015] Ar₁ and Ar₂ are each independently a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₃-C₆₀ heteroaryl group, or a substituted or unsubstituted C₆-C₆₀ condensed polycyclic group.

[0016] According to another aspect of the present invention, an organic light-emitting diode includes a first electrode; a second electrode; and an organic layer between the first electrode and the second electrode. The organic layer includes the compound of Formula 1.

[0017] According to another aspect of the present invention, a flat panel display device includes the organic light-emitting diode, and a first electrode of the organic light-emitting diode is electrically connected to a source electrode or a drain electrode of a thin film transistor.

BRIEF DESCRIPTION OF THE DRAWINGS


[0018] The above and other features and advantages of the present invention will become more apparent by reference to the following detailed description when considered in conjunction with the attached drawing in which:

[0019] FIG. 1 is a schematic diagram of a structure of an organic light-emitting diode according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

[0020] Hereinafter, exemplary embodiments of the present invention will be described. As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items. Expressions such as "at least one of," when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0021] According to an embodiment of the present invention, a compound is represented by Formula 1 below:



Formula 1

[0022] In Formula 1, R_1 and R_2 are each independently a halogen, a cyano group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_3 - C_{60} heteroaryl group, or a substituted or unsubstituted C_6 - C_{60} condensed polycyclic group.

[0023] R_3 is hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_3 - C_{60} heteroaryl group, or a substituted or unsubstituted C_6 - C_{60} condensed polycyclic group.

[0024] Ar_1 and Ar_2 are each independently a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_3 - C_{60} heteroaryl group, or a substituted or unsubstituted C_6 - C_{60} condensed polycyclic group.

[0025] The compounds of Formula 1 have higher driving voltages and efficiency than conventional hole transporting materials. Thus, an OLED including a compound of Formula 1 exhibits good driving lifetime and increased power efficiency. Therefore, an OLED with low power consumption may be manufactured.

[0026] The compounds of Formula 1 have asymmetrical structures in which one amine group is substituted in a central fused aromatic ring, which leads to a relatively high Tg and an improved hole transporting ability.


[0027] In a symmetric structure in which two amine groups are substituted in the central fused aromatic ring, free rotation of amine bonds increases. Thus, compounds having a symmetric structure have relatively low Tgs as compared to the compounds of Formula 1 having an asymmetric structure. In addition, the symmetric structure increases the electron-donating properties of the amine groups, and thus makes the HOMO (highest occupied molecular orbital) energy level of the molecules unstable, resulting in an increased HOMO energy level. Therefore, when a compound having a symmetric structure is used as a material for forming the hole transport layer (HTL), there is a large difference in the HOMO energy level between the compound with the symmetric structure and a host. Accordingly, compounds having a symmetric structure may be used to form the hole injection layer (HIL) rather than the HTL.

[0028] The substituents of the compound of Formula 1 will now be described in more detail.


[0029] According to one embodiment, in Formula 1, R_1 and R_2 may be each independently a halogen, a cyano group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a substituted or unsubstituted C_6 - C_{30} aryl group, a substituted or unsubstituted C_3 - C_{30} heteroaryl group, or a substituted or unsubstituted C_6 - C_{30} condensed polycyclic group. R_3 may be hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_6 - C_{30} aryl group, a substituted or unsubstituted C_3 - C_{30} heteroaryl group, or a substituted or unsubstituted C_6 - C_{30} condensed polycyclic group.

R_3 may be hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_1 - C_{20} alkyl group, or a moiety represented by any one of Formulae 2a through 2c below.


[0030] According to another embodiment, in Formula 1, R_1 and R_2 may be each independently hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_1 - C_{20} alkyl group, or a moiety represented by any one of Formulae 2a through 2c below.



2a



2b



2c


[0031] In Formulae 2a through 2c, Y_1 , Y_2 , and Y_3 are each independently a linking group represented by $-N=$, $-N(R_{20})-$, or $-C(R_{21})=$.

[0032] Q is a linking group represented by $-C(R_{30})$, $-N(R_{32})-$, $-S-$, or $-O-$.


[0033] Z_1 , Z_2 , R_{20} , R_{21} , R_{30} , R_{31} , and R_{32} are each independently a hydrogen atom, deuterium, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_3 - C_{20} heteroaryl group, a substituted or unsubstituted C_6 - C_{20} condensed polycyclic group, or an amino group that is substituted with a C_6 - C_{20} aryl group or a C_3 - C_{20} heteroaryl group, a halogen, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group.

[0034] Also, p is an integer of 1 to 7, and $*$ denotes a binding site.

[0035] In another embodiment, in Formula 1, R_3 may be hydrogen, deuterium, a halogen, or a moiety represented by any one of Formulae 3a through 3c below.




3a



3b

-continued



3c


[0036] In Formulae 3a through 3c, Y_1 , Y_2 , and Y_3 are each independently a linking group represented by $-N=$, $-N(R_{20})-$, or $-C(R_{21})=$.

[0037] Z_1 , Z_2 , R_{20} , and R_{21} are each independently a hydrogen atom, deuterium, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_3 - C_{20} heteroaryl group, a substituted or unsubstituted C_6 - C_{20} condensed polycyclic group, a halogen, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group.

[0038] Also, p is an integer of 1 to 7, and $*$ denotes a binding site.

[0039] In Formula 1, Ar_1 and Ar_2 may be any one of Formulae 4a through 4g below.

-continued



4g

[0040] In Formulae 4a through 4g, Q_1 and Q_2 are each independently a linking group represented by $-C(R_{30})$, $(R_{31})-$, $-N(R_{32})-$, $-S-$, or $-O-$.

[0041] Z_1 , Z_2 , Z_3 , R_{30} , R_{31} , and R_{32} are each independently a hydrogen atom, deuterium, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_3 - C_{20} heteroaryl group, an amino group that is substituted with a C_6 - C_{20} aryl group or a C_3 - C_{20} heteroaryl group, a substituted or unsubstituted C_6 - C_{20} condensed polycyclic group, a halogen, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group.

[0042] Also, p is an integer of 1 to 9, q is 1 or 2, r is an integer of 1 to 4, and $*$ denotes a binding site.


[0043] In Formula 1, R_1 and R_2 may be linked to each other to form a ring, or Ar_1 and Ar_2 may be linked to each to form a ring.

[0044] Hereinafter, representative groups of the substituents as used herein will be described. The number of carbon atoms that define the substituents is non-limiting, and do not limit the properties of the substituents.


[0045] The unsubstituted C_1 - C_{60} alkyl group is a linear or branched alkyl group. Nonlimiting examples of the unsubstituted C_1 - C_{60} alkyl group include methyl, ethyl, propyl, isobutyl, sec-butyl, pentyl, iso-amyl, hexyl, heptyl, octyl, nonanyl, dodecyl, and the like. To obtain the substituted alkyl group, at least one hydrogen atom of the unsubstituted C_1 - C_{60} alkyl group may be substituted with deuterium, a halogen atom, a hydroxyl group, a nitro group, a cyano group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_2 - C_{10} alkenyl group, a C_2 - C_{10} alkynyl group, a C_6 - C_{16} aryl group, or a C_4 - C_{16} heteroaryl group.

[0046] The unsubstituted C_2 - C_{60} alkenyl group is a group containing at least one carbon-carbon double bond in the center or at a terminal end of the unsubstituted C_2 - C_{60} alkyl group. Nonlimiting examples of the unsubstituted C_2 - C_{60} alkenyl group include ethenyl, propenyl, butenyl, and the like. To obtain the substituted alkenyl group, at least one hydrogen atom of the unsubstituted C_2 - C_{60} alkenyl group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.


[0047] The unsubstituted C_2 - C_{60} alkynyl group is a group containing at least one carbon-carbon triple bond in the center or at a terminal end of the C_2 - C_{60} alkyl group defined above. Nonlimiting examples of the unsubstituted C_2 - C_{60} alkynyl group include acetylene, propylene, phenylacetylene, naphthylacetylene, isopropylacetylene, t-butylacetylene, diphenylacetylene, and the like. To obtain the substituted alkynyl group, at least one hydrogen atom of the unsubstituted C_2 - C_{60}




4a




4b




4c



4d



4e



4f

alkynyl group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.

[0048] The unsubstituted C_3 - C_{60} cycloalkyl group denotes a C_3 - C_{60} ring-type alkyl group. To obtain the substituted cycloalkyl group, at least one hydrogen atom of the unsubstituted C_3 - C_{60} cycloalkyl group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.

[0049] The unsubstituted C_3 - C_{60} alkoxy group has the Formula —OA in which A is the unsubstituted C_1 - C_{60} alkyl group. Nonlimiting examples of the C_1 - C_{60} alkoxy group include methoxy, ethoxy, propoxy, isopropoxy, butoxy, pentoxy, and the like. To obtain the substituted alkoxy group, at least one hydrogen atom of the unsubstituted C_1 - C_{60} alkoxy group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.

[0050] The unsubstituted C_6 - C_{60} aryl group refers to a C_6 - C_{60} carbocyclic aromatic system containing at least one ring. When the aryl group contains at least two rings, the rings may be fused with each other or linked to each other by a single bond. The term “aryl” refers to an aromatic system, including, for example, phenyl, naphthyl, anthracenyl, and the like. To obtain the substituted aryl group, at least one hydrogen atom of the unsubstituted C_6 - C_{60} aryl group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.

[0051] Nonlimiting examples of the unsubstituted C_6 - C_{60} aryl group include a phenyl group, a C_1 - C_{10} alkylphenyl group (e.g., an ethylphenyl group), a halophenyl group (e.g., an o-, m- and p-fluorophenyl group, and a dichlorophenyl group), a cyanophenyl group, a dicyanophenyl group, a trifluoromethoxyphenyl group, a biphenyl group, a halobiphenyl group, a cyanobiphenyl group, a C_1 - C_{10} alkylbiphenyl group, a C_1 - C_{10} alkoxybiphenyl group, an o-, m-, and p-tolyl group, an o-, m- and p-cumenyl group, a mesityl group, a phenoxypheyl group, an (α,α -dimethylbenzene)phenyl group, a (N,N' -dimethyl)aminophenyl group, a (N,N' -diphenyl)aminophenyl group, a pentalenyl group, an indenyl group, a naphthyl group, a halonaphthyl group (e.g., a fluoronaphthyl group), a C_1 - C_{10} alkylnaphthyl group (e.g., a methylnaphthyl group), a C_1 - C_{10} alkoxynaphthyl group (e.g., a methoxynaphthyl group), a cyanonaphthyl group, an anthracenyl group, an azulenyl group, a heptalenyl group, an acenaphthylenyl group, a phenalenyl group, a fluorenyl group, an anthraquinolyl group, a methylanthryl group, a phenanthryl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, an ethyl-chrysenyl group, a picenyl group, a perylenyl group, a chloroperlylenyl group, a pentaphenyl group, a pentacenyl group, a tetraphenylenyl group, a hexaphenyl group, a hexacenyl group, a rubicenyl group, a coronenyl group, a trinaphthylenyl group, a heptaphenyl group, a heptacenyl, a pyranthrenyl group, and an ovalenyl group.

[0052] The unsubstituted C_3 - C_{60} heteroaryl group indicates a group having 1, 2 or 3 hetero atom(s) selected from N, O, P, and S. When the C_3 - C_{60} heteroaryl group contains at least two rings, the rings may be fused with each other or linked to each other by a single bond. Nonlimiting examples of the unsubstituted C_3 - C_{60} heteroaryl group include a pyrazolyl group, an imidazolyl group, an oxazolyl group, a thiazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridinyl group, a pyridazinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, an


indolyl group, a quinolynyl group, an isoquinolynyl group, and a dibenzothiophene group. To obtain the substituted heteroaryl group, at least one hydrogen atom of the unsubstituted C_3 - C_{60} heteroaryl group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.

[0053] The unsubstituted C_6 - C_{60} aryloxy group has the formula —OA₁ in which A₁ is the C_6 - C_{60} aryl group as described above. Nonlimiting examples of the unsubstituted C_6 - C_{60} aryloxy group include a phenoxy group and the like. To obtain the substituted aryloxy group, at least one hydrogen atom of the unsubstituted C_6 - C_{60} aryloxy group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.


[0054] The unsubstituted C_6 - C_{60} arylthio group has the formula —SA₁ in which A₁ is the C_6 - C_{60} aryl group described above. Nonlimiting examples of the unsubstituted C_6 - C_{60} arylthio group include a benzenethio group, a naphthylthio group, or the like. To obtain the substituted arylthio group, at least one hydrogen atom of the unsubstituted C_6 - C_{60} arylthio group may be substituted with the substituents described above with respect to the substituted C_1 - C_{60} alkyl group.

[0055] The unsubstituted C_6 - C_{60} condensed polycyclic group indicates a substituent having at least two rings in which at least one aromatic ring and at least one non-aromatic ring are fused with each other, or a substituent having an unsaturated group but not having a conjugated system in the ring. The unsubstituted C_6 - C_{60} condensed polycyclic group differs from the aryl and heteroaryl groups in that it is overall non-aromatic.

[0056] In some embodiments, the compound of Formula 1 may be one of Compounds 1 through 51 below, but is not limited thereto.




-continued




2


-continued




5




3



6




4




7

-continued




8


-continued




11




9




12



10




13




14

-continued




15


-continued




18




16



19




17



20


-continued

21




-continued

24





25


22




23



26




-continued




27


28



29




-continued




30


31



32




-continued




33


-continued




36




34



37




35




38

-continued


39



40




41




-continued

42




43




-continued


44



45




46




-continued


47




48




49



50



-continued



[0057] According to another embodiment of the present invention, an OLED includes a first electrode; a second electrode; and an organic layer between the first electrode and the second electrode. The organic layer includes the compound of Formula 1 described above.

[0058] The organic layer may include at least one of a hole injection layer (HIL), a hole transport layer (HTL), a functional layer having both hole injection and hole transport abilities (hereinafter, referred to as an “H-functional layer”), a buffer layer, an electron blocking layer (EBL), an emission layer (EML), a hole blocking layer (HBL), an electron transport layer (ETL), an electron injection layer (EIL), and/or a functional layer having both electron transport and electron injection abilities (hereinafter, referred to as “E-functional layer”).

[0059] In some embodiments, the organic layer may be an EML, and the compound of Formula 1 may be used as a fluorescent host, a phosphorescent host, or a fluorescent dopant.

[0060] In one embodiment, the OLED may include an EIL, an ETL, an EML, a HIL, a HTL, or an H-functional layer. The EML may include the compound of Formula 1; and an anthracene-based compound, an arylamine-based compound, or a styryl-based compound.

[0061] In one embodiment, the OLED may include an EIL, an ETL, an EML, a HIL, a HTL, or an H-functional layer. Any one of a red layer, a green layer, a blue layer, or a white layer of the EML may include a phosphorescent compound. The HIL, the HTL, or the H-functional layer may include a charge-generating material. In this regard, the charge-generating material may be a p-dopant. Nonlimiting examples of the p-dopant include quinone derivatives, metal oxides, and cyano-containing compounds.

[0062] In one embodiment, the organic layer may include an ETL, and the ETL may include an electron transporting organic compound and a metal complex. The metal complex may be a Li complex.

[0063] The term “organic layer,” as used herein, refers to a single layer and/or a plurality of layers positioned between the first electrode and the second electrode.

[0064] The organic layer may include an EML including the compound of Formula 1. Alternatively, the organic layer may include at least one of a HIL, a HTL, and/or an H-func-

tional layer, and at least one of the HIL, the HTL, and/or the H-functional layer may include the compound of Formula 1.

[0065] FIG. 1 is a schematic diagram illustrating the structure of an organic light-emitting diode according to an embodiment of the present invention. Hereinafter, a structure and manufacturing method of an OLED will be described in more detail with reference to FIG. 1.

[0066] A substrate (not shown) may be any substrate generally used in OLEDs, and may be, for example, a glass substrate or a transparent plastic substrate having good mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and waterproofness.

[0067] The first electrode may be formed by applying a first electrode material on the substrate by deposition or sputtering. When the first electrode is an anode, the first electrode material may be selected from materials having a high work function so as to facilitate hole injection. The first electrode may be a reflective electrode or a transparent electrode. Non-limiting examples of the first electrode material include indium-tin oxide (ITO), indium-zinc-oxide (IZO), tin oxide (SnO_2), and zinc oxide (ZnO), which are transparent and have high conductivity. Also, when magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) is used as the first electrode material, the first electrode may be formed as a reflective electrode.

[0068] The first electrode may be formed as a single layer or have a multi-layered structure with at least two layers. For example, the first electrode may have a three-layered structure including ITO/Ag/ITO, but is not limited thereto.

[0069] The organic layer is formed on the first electrode.
[0070] The organic layer may include a HIL, a HTL, a buffer layer (not shown), an EML, an ETL, or an EIL.

[0071] The HIL may be formed on the first electrode by using various methods, such as vacuum deposition, spin coating, casting, or LB deposition.


[0072] When the HIL is formed by vacuum deposition, the deposition conditions may vary according to the compound used as the material for forming the HIL, the structure of the desired HIL, and the thermal characteristics. For example, the deposition conditions may be, but are not limited to, a deposition temperature of about 100°C. to about 500°C., a degree of vacuum of about 10⁻⁸ torr to about 10⁻³ torr, and a deposition speed of about 0.01 Å/sec to about 100 Å/sec.

[0073] When the HIL is formed by spin coating, the coating conditions may vary according to the compound used as the material for forming the HIL, the structure of the desired HIL, and the thermal characteristics. For example, the coating conditions may be, but are not limited to, a coating speed of about 2,000 rpm to about 5,000 rpm and a heat treatment temperature for removing the solvent after coating of about 80° C. to about 200° C.


[0074] The material for forming the HIL may be a known hole injection material.

[0075] Nonlimiting examples of the hole injection material include, but are not limited to, N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine (DNTPD), a phthalocyanine compound such as copper phthalocyanine, 4,4',4''-tris(3-methylphenylphenylamino)triphenylamine (m-MTDATA), N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB), TDATA, 2-TNATA, polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/


PSS), polyaniline/camphor sulfonic acid (Pani/CSA), and (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS).



m-MTDATA



TDATA




2-TNATA


[0076] The thickness of the HIL may be about 100 Å to about 10,000 Å. In some embodiments, the thickness of the HIL may be about 100 Å to about 1,000 Å. When the thickness of the HIL is within these ranges, satisfactory hole injection properties may be obtained without a substantial increase in driving voltage.

[0077] Next, the HTL may be formed on the HIL by various methods, such as vacuum deposition, spin coating, casting, or LB deposition. When the HTL is formed by vacuum deposition or spin coating, the deposition or coating conditions may vary according to the compounds used. However, in general, the deposition or coating conditions may be similar or identical to the conditions used for forming the HIL.

[0078] A material for forming the HTL may be the compound of Formula 1 or a known hole transporting material. Nonlimiting examples of the hole transporting material include, but are not limited to, carbazole derivatives such as N-phenylcarbazole and polyvinylcarbazole, N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (TPD), 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), and N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB).





TPD



[0079] The thickness of the HTL may be about 50 Å to about 2,000 Å. In some embodiments, the thickness of the HTL may be about 100 Å to about 1,500 Å. When the thickness of the HTL is within these ranges, satisfactory hole transport properties may be obtained without a substantial increase in driving voltage.

[0080] The H-functional layer may include at least one of the hole injection materials and the hole transporting materials described above. The thickness of the H-functional layer may be about 500 Å to about 10,000 Å. In some embodiments, the thickness of the HTL may be about 100 Å to about 1,000 Å. When the thickness of the H-functional layer is within these ranges, satisfactory hole injection and hole transport properties may be obtained without a substantial increase in driving voltage.

[0081] At least one of the HIL, the HTL, and/or the H-functional layer may include at least one compound represented by Formula 300 below and/or a compound represented by Formula 350 below:



[0082] In Formulae 300 and 350, Ar₁₁, Ar₁₂, Ar₂₁, and Ar₂₂ are each independently a substituted or unsubstituted C₆-C₆₀ arylene group.


[0083] In Formula 300, e and f may be each independently an integer of 0 to 5, for example, 0, 1, or 2. For example, e may be 1 and f may be 0, but e and f are not limited thereto.

[0084] In Formulae 300 and 350, R₅₁ through R₅₈, R₆₁ through R₆₉, R₇₁, and R₇₂ may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, or a substituted or unsubstituted C₆-C₆₀ arylthio group. For example, R₅₁ through R₅₈, R₆₁ through R₆₉, R₇₁, and R₇₂ may be each independently one of hydrogen; deuterium; a halogen atom; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; hydrazine; hydrazone; a carboxyl group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, and the like); a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, and the like); a C₁-C₁₀ alkyl group or a C₁-C₁₀ alkoxy group substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof; a phenyl group; a naphthyl group; an anthryl group; a fluorenyl group; a pyrenyl group; or a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, or a pyrenyl group substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, or a C₁-C₁₀ alkoxy group.

[0085] In Formula 300, R₅₉ may be one of a phenyl group; a naphthyl group; an anthryl group; a biphenyl group; a pyridyl group; or a phenyl group, a naphthyl group, an anthryl group, a biphenyl group or a pyridyl group substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric

acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{20} alkyl group, or a substituted or unsubstituted C_1 - C_{20} alkoxy group.


[0086] In one embodiment, the compound of Formula 300 may be a compound represented by Formula 300A below, but is not limited thereto:




Formula 300A

[0087] In Formula 300A, R_{51} , R_{60} , R_{61} , and R_{59} are the same as defined above.


[0088] For example, at least one of the HIL, the HTL, or the H-functional layer may include at least one of Compounds 301 through 320 below, but is not limited thereto.




301




302




303



304



305




306

-continued


-continued

307




-continued

310





308




311

309




-continued

312




-continued


314



313




315




-continued

316




-continued


318



317




319




-continued

320



[0089] At least one of the HIL, the HTL, and the H-functional layer may further include a charge-generating material so as to increase the conductivity of the layers, in addition to the hole injection material, the hole transporting material and/or the material having hole injection and hole transport abilities.

[0090] The charge-generating material may be, for example, a p-dopant. The p-dopant may be one selected from quinone derivatives, metal oxides, and cyano-containing compounds, but is not limited thereto. Nonlimiting examples of the p-dopant include quinone derivatives such as tetracyanoquinodimethane (TCNQ) and 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4-CTNQ); metal oxides such as tungsten oxide and molybdenum oxide; and cyano-containing compounds such as Compound 200 below and the like.



[0091] When the HIL, the HTL or the H-functional layer further includes the charge-generating material, the charge-

generating material may be homogeneously or inhomogeneously dispersed in these layers.

[0092] The buffer layer may be positioned between the EML and at least one of the HIL, the HTL, or the H-functional layer. The buffer layer may increase efficiency by compensating for an optical resonance distance according to the wavelength of light emitted from the EML. The buffer layer may include a hole injection material and a hole transporting material. Also, the buffer layer may include the same material as one of the materials included in the HIL, the HTL, or the H-functional layer (which are formed below the buffer layer).


[0093] Next, the EML may be formed on the HTL, the H-functional layer, or the buffer layer by vacuum deposition, spin coating, casting, or LB deposition. When the EML is formed by vacuum deposition or spin coating, the deposition or coating conditions may vary according to the compounds used. However, in general, the conditions may be similar or identical to the conditions for forming the HIL.

[0094] The EML may include one of the compounds of Formula 1 according to embodiments of the present invention.


[0095] The EML may further include a host.

[0096] Nonlimiting examples of the host include Alq₃, 4,4'-N,N'-dicarbazole-biphenyl (CBP), poly(n-vinylcarbazole) (PVK), 9,10-di(naphthalene-2-yl)anthracene (ADN), TCTA, 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di(naphth-2-yl) anthracene (TBADN), E3, and distyrylarylene (DSA), dmCBP (refer to the following formula), and Compounds 501 through 509 below.

TPBI




TBADN




-continued


E3




PVK




ADN




CBP



dmCMP




501




-continued


502






503




504



-continued




?



?

-continued




?

? indicates text missing or illegible when filed

[0097] Also, the host may be an anthracene-based compound represented by Formula 400 below.

Formula 400




[0098] In Formula 400, Ar_{111} and Ar_{112} are each a independently substituted or unsubstituted C_6-C_{60} arylene group. Ar_{113} through Ar_{116} are each independently a substituted or unsubstituted C_1-C_{10} alkyl group or a substituted or unsubstituted C_6-C_{60} aryl group. Also, g, h, i, and j may be each independently an integer of 0 to 4.

[0099] For example, in Formula 400, Ar_{111} and Ar_{112} may be each independently one of a phenylene group, a naphthylene group, a phenanthrenylene group, a pyrenylene group; or a phenylene group, a naphthylene group, a phenanthrenylene group, a fluorenyl group, or a pyrenylene group substituted with at least one of a phenyl group, a naphthyl group, or an anthryl group, but are not limited thereto.

[0100] In Formula 400, g, h, i, and j may be each independently 0, 1, or 2.


[0101] In Formula 400, Ar_{113} through Ar_{116} may be each independently one of a C_1-C_{10} alkyl group that is substituted with at least one of a phenyl group, a naphthyl group, or an anthryl group; a phenyl group; a naphthyl group; an anthryl group; a pyrenyl group; a phenanthrenyl group; a fluorenyl group; a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, a phenanthrenyl group or a fluorenyl group substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a

C₁-C₆₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, a phenanthrenyl group, or a fluorenyl group; or




but are not limited thereto.


[0102] For example, the anthracene-based compound of Formula 400 may be one of the following compounds, but is not limited thereto.




-continued




-continued




-continued




-continued




-continued




-continued




-continued



?



?




?

? indicates text missing or illegible when filed

[0103] Also, the host may be an anthracene-based compound represented by Formula 401 below.

Formula 401





[0104] In Formula 401, Ar₁₂₂ through Ar₁₂₅ are the same as defined above in the description of Ar₁₁₃ of Formula 400.

[0105] In Formula 401, Ar₁₂₆ and Ar₁₂₇ may be each independently a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, or a propyl group).



[0106] In Formula 401, k and l may be each independently an integer of 0 to 4. For example, k and l may be each independently 0, 1, or 2.

[0107] For example, the anthracene-based compound of Formula 401 may be one of the following compounds, but is not limited thereto.




[0108] When the OLED is a full-color OLED, the EML may be patterned into a red EML, a green EML, and a blue EML.

[0109] At least one of the red EML, the green EML, or the blue EML may include one of the following dopants (ppy=phenylpyridine).



DPVBi


-continued








DPAVBi





[0110] Examples of a red dopant include, but are not limited to, the following compounds.

-continued




PtOEP


Ir(pq)₂(acac)Ir(2-phq)₃Ir(piq)₃Btp₂Ir(acac)Ir(BT)₂(acac)Ir(flq)₂(acac)



[0111] Examples of a green dopant include, but are not limited to, the following compounds.




-continued




C545T


[0112] The dopant included in the EML may be a Pt-complex as described below, but is not limited thereto.




D1



D2




D3




D4


-continued




D5




D6




D7



D8








D9



D10


-continued



-continued

D11


D16



D12


D13

D17




D18

D14




D19






D15



D20




-continued




-continued

D21




D26

D22




D27

D23




D28

D24



D29


D25




D30

D31


-continued




D32




D33



D34




D35




D36


-continued




D37



D38




D39




D40


-continued




D41




D42



D43




D44




D45


-continued




D46




D47



D48








D49



D50


[0113] Also, the dopant included in the EML may be an Os-complex as described below, but is not limited thereto.

Os(fppz)₂(CO)₂Os(fppz)₂(PPh₂Me)₂Os(bppz)₂(PPh₃)₂Os(fptz)₂(PPh₂Me)₂Os(hptz)₂(PPhMe₂)₂

[0114] When the EML includes a host and a dopant, the amount of the dopant may be generally about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but is not limited thereto.


[0115] The thickness of the EML may be about 100 Å to about 1,000 Å. In some embodiment, the thickness of the EML may be about 200 Å to about 600 Å. When the thickness of the EML is within these ranges, good luminescent properties may be obtained without a substantial increase in driving voltage.

[0116] Next, the ETL is formed on the EML by various methods, such as vacuum deposition, spin coating, or casting. When the ETL is formed by vacuum deposition or spin coating, the deposition or coating conditions may vary according to the compounds used. However, in general, the deposition and coating conditions may be similar or identical to the conditions for forming the HIL. The material for forming the ETL may be a known electron transporting material that stably transports electrons injected from a cathode. Examples of the electron transporting materials may include, but are not limited to, a quinoline derivative such as tris(8-quinolinolate) aluminum (Alq₃), TAZ, Balq, beryllium bis(benzoquinolin-10-olate) (Bebq₂), ADN, Compound 201 below, and Compound 202 below.



Compound 201


TAZ



Compound 202

BAIq

-continued




[0117] The thickness of the ETL may be about 100 Å to about 1,000 Å. In some embodiments, the thickness of the ETL may be about 150 Å to about 500 Å. When the thickness of the ETL is within these ranges, satisfactory electron transport properties may be obtained without a substantial increase in driving voltage.

[0118] The ETL may include a known electron transporting organic compound and a metal-containing material.

[0119] The metal-containing material may include a Li-complex. Examples of the Li-complex may include, but are not limited to, lithium quinolate (LiQ) and Compound 203 below.

Compound 203



[0120] Also, the EIL, which facilitates electron injection from a cathode, may be formed on the ETL, and the material for forming the EIL is not particularly limited.


[0121] The material for forming the EIL may include a known material for forming an EIL, such as LiF, NaCl, CsF, Li₂O, or BaO. The deposition conditions of the EIL may vary according to the compound used. However, in general, the conditions may be similar or identical to the conditions for forming the HIL.

[0122] The thickness of the EIL may be about 1 Å to about 100 Å. In some embodiments, the thickness of the EIL may be about 3 Å to about 90 Å. When the thickness of the EIL is within these ranges, satisfactory electron injection properties may be obtained without a substantial increase in driving voltage.

[0123] The second electrode is formed on these organic layers. The second electrode may be a cathode, which is an electron injection electrode. Here, a metal for forming the second electrode may include a metal having a low work function, such as a metal, an alloy, an electrically conducting compound, or a mixture thereof. In particular, the second electrode may be formed as a thin film of lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag), thus being transparent. In order to obtain a top-emission type OLED, the second electrode may be formed as a transparent electrode using ITO or IZO.

[0124] The OLED has been described with reference to FIG. 1, but is not limited thereto.

[0125] In addition, when the EML includes a phosphorescent dopant, a HBL may be formed between the HTL and the EML or between the H-functional layer and the EML using various methods, such as vacuum deposition, spin coating, casting, or LB deposition in order to prevent triplet excitons or holes from diffusing into the ETL. When the HBL is formed by vacuum deposition or spin coating, the deposition or coating conditions may vary according to the compound used. However, in general, the deposition or coating conditions may be similar or identical to the conditions for forming the HIL. A material for forming the HBL may be a known hole blocking material, such as an oxadiazole derivative, a triazole derivative, or a phenanthroline derivative. For example, the material for forming the HBL may be BCP below.



BCP

[0126] The thickness of the HBL may be about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the HBL is within these ranges, satisfactory hole blocking properties may be obtained without a substantial increase in driving voltage.

[0127] The OLED may be used in various types of flat panel display devices, for example, passive matrix OLEDs and


active matrix OLEDs. In particular, in an active matrix OLED, a first electrode formed on the substrate side, which is a pixel electrode, may be electrically connected to a source electrode or a drain electrode of a thin film transistor. Also, the OLED may be used in a dual-screen flat panel display device.


[0128] The organic layer of the OLED may be formed using a compound of Formula 1 according to an embodiment of the present invention by deposition, or using a compound of Formula 1 according to an embodiment of the present invention prepared in a liquid state using a wet process.

[0129] OLEDs according to embodiments of the present invention will now be described with reference to the following Synthesis Examples and Examples. These Examples are presented for illustrative purposes only and are not intended to limit the scope of the invention.

EXAMPLES

[0130]





Synthesis Example

Intermediate 1

1) Synthesis of
8,9-dihydro-4H-cyclopenta[def]phenanthrene

[0131] 10.0 g (52.6 mmol) of 4H-cyclopenta[def]phenanthrene and 8.40 g of 5% Pd/C were dissolved in 70 ml of EtOH in a Par reactor bottle, and the resultant solution was stirred at room temperature for 24 hours with hydrogen pressure being maintained at 40 psi. After the reaction was completed, the reaction solution was filtered and the solvent was evaporated therefrom to obtain 8.60 g of white target material (yield: 85.0%).

2) Synthesis of
2-bromo-8,9-dihydro-4H-cyclopenta[def]phenanthrene

[0132] 8.5 g (44.2 mmol) of 8,9-dihydro-4H-cyclopenta[def]phenanthrene was dissolved in 80 ml of CCl_4 , and 7.1 g (44.2 mmol) of Br_2 was then slowly added thereto at 0°C . The reaction solution was stirred at room temperature for 4 hours and a 10% Na_2SO_3 solution was added thereto to separate the organic layer. The obtained organic layer was dried with magnesium sulfate, the solvent was evaporated therefrom, and the resultant product was recrystallized with n-hexane. As a result, 9.6 g of the target material was obtained (yield: 80%).

3) Synthesis of Intermediate 1a

[0133] 9.3 g (34.3 mmol) of 2-bromo-8,9-dihydro-4H-cyclopenta[def]phenanthrene and 8.8 g (36.0 mmol) of o-chloranil were dissolved in 70 ml of Xylene, and the mixture was stirred at 110°C for 72 hours. Thereafter, the reaction solution was cooled to room temperature, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 7.48 g of Intermediate 1a (yield: 81%). The obtained compound was confirmed by ^1H NMR and mass spectrometry/fast atom bombardment (MS/FAB).

[0134] $\text{C}_{15}\text{H}_9\text{Br}$: calc. 267.99, found 267.97

[0135] ^1H NMR (CDCl_3 , 400 MHz) δ 7.98 (2H, s), 7.79 (2H, s), 7.73 (2H, s), 6.94 (dd, 1H), 4.28 (2H, s)

4) Synthesis of Intermediate 1

[0136] 7.3 g (27.1 mmol) of Intermediate 1a, 73.2 g (216.8 mmol) of t-BuOK, and 60 ml of HMPA were dissolved in 60 ml of DMSO, and the resultant product was stirred at room temperature for 1 hour. Subsequently, 30.6 g (216.8 mmol) of CH_3I was slowly added to the reaction solution at 0°C ., the resultant was stirred for 30 hours, 40 ml of water was added thereto, and the resulting product was extracted three times with 70 ml of methylene chloride. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 6.3 g of Intermediate 1 (yield: 78%). The obtained compound was confirmed by ^1H NMR and MS/FAB.

[0137] $\text{C}_{17}\text{H}_{13}\text{Br}$: calc. 296.02, found 296.05

[0138] ^1H NMR (CDCl_3 , 400 MHz) δ 7.98 (2H, s), 7.79 (2H, s), 7.73 (2H, s), 6.94 (dd, 1H), 1.93 (m, 6H)

Synthesis Example

Intermediate 2

1) Synthesis of 2,6-dibromo-8,9-dihydro-4H-cyclopenta[def]phenanthrene

[0139] 8.9 g of a target material was obtained (yield: 57%) in the same manner as in 2) of the Synthesis of Intermediate 1, except that the amount of Br_2 used was 14.2 g (88.4 mmol).

2) Synthesis of Intermediate 2a

[0140] 6.8 g of Intermediate 2a was obtained (yield: 80%) in the same manner as in 3) of the Synthesis of Intermediate 1, except that 2,6-dibromo-8,9-dihydro-4H-cyclopenta[def]phenanthrene was used instead of 2-bromo-8,9-dihydro-4H-cyclopenta[def]phenanthrene. The obtained compound was confirmed by ^1H NMR and MS/FAB.

[0141] $C_{15}H_8Br_2$: calc. 345.90. found 345.92

[0142] 1H NMR ($CDCl_3$, 400 MHz) δ 7.98 (2H, s), 7.79 (2H, s), 7.73 (2H, s), 4.28 (2H, s)

3) Synthesis of Intermediate 2

[0143] 5.8 g of Intermediate 2 was obtained (yield: 79%) in the same manner as in 4) of the Synthesis of Intermediate 1, except that Intermediate 2a was used instead of Intermediate 1a. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0144] $C_{15}H_8Br_2$: calc. 345.90. found 345.92

[0145] 1H NMR ($CDCl_3$, 400 MHz) δ 7.98 (2H, s), 7.79 (2H, s), 7.73 (2H, s), 1.93 (s, 6H)

Synthesis Example

Intermediate 3

1) Synthesis of

2-bromo-cyclopenta[def]phenanthren-4-one

[0146] 7.4 g (27.5 mmol) of Intermediate 1a and 310 g of MnO_2 were dissolved in 200 ml of benzene, and the resultant solution was then stirred at 80° C. for 20 hours. The obtained reaction solution was cooled down to room temperature and then filtered to remove MnO_2 therefrom, and the filtrate was washed with 50 ml of $CHCl_3$, 50 ml of THF and 50 ml of MeOH in that order. The resultant filtrate was evaporated to obtain a residue. The residue was recrystallized with acetone to obtain 3.74 g of the target material (yield: 48%).

2) Synthesis of Intermediate 3a

[0147] 3.05 g (13.1 mmol) of 2-bromo biphenyl was dissolved in 50 ml of THF, and 15.4 ml (26.2 mmol) of $t-BuLi$ (1.7M in Pentane) was then slowly added thereto at -78° C. The resultant solution was stirred for 1 hour at -78° C., 3.7 g (13.1 mmol) of 2-bromo-cyclopenta[def]phenanthrene-4-one was slowly added thereto for 30 minutes, and the resultant reaction solution was stirred at -78° C. for 30 minutes and then further stirred at room temperature for 3 hours. Then, 40 ml of water was added to the reaction solution and the resulting reaction solution was extracted three times with 50 ml of ethyl acetate. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 5.44 g of Intermediate 3a (yield: 95%).

3) Synthesis of Intermediate 3

[0148] 5.4 g (12.3 mmol) of Intermediate 3a was dissolved in 50 ml of acetic acid, 3 ml of concentrated hydrochloric acid was then slowly added at 0° C., and the resultant solution was stirred for 2 hours. A white solid obtained during the reaction was filtered and washed with acetic acid and ethanol to obtain 4.70 g of Intermediate 3 (yield: 90%). The obtained compound was confirmed by 1H NMR and MS/FAB.

[0149] $C_{27}H_{15}Br$: calc. 418.04. found 418.05

[0150] 1H NMR ($CDCl_3$, 400 MHz) δ 7.22-7.26 (m, 8H), 7.70 (s, 2H), 7.80 (s, 2H), 8.00 (s, 2H)

Synthesis Example

Intermediate 4

Synthesis of Intermediate 4a

[0151] 3.7 g (13.1 mmol) of 2-bromo-cyclopenta[def]phenanthrene-4-one was dissolved in 50 ml of ether and 20 ml of THF, 4.55 g (13.1 mmol) of (4-(diphenylamino)-phenyl)-magnesium bromide was then slowly added thereto, and the resultant solution was stirred at 80° C. for 3 hours. The reaction solution was cooled down to room temperature, 30 ml of water was added thereto, the pH of the reaction solution was adjusted to 3 to 4 using a 1N HCl solution, and the resultant reaction solution was extracted three times with 50 ml of ethyl acetate. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 4.98 g of Intermediate 4a (yield: 72%).

Synthesis of Intermediate 4

[0152] 4.98 g (9.43 mmol) of Intermediate 4a was dissolved in 50 ml of benzene, 2.52 mL (28.3 mmol) of trifluoromethane sulfonic acid was then slowly added thereto, and the resultant solution was stirred at 80° C. for 2 hours. Then, the reaction solution was cooled down to room temperature, 40 ml of water was added to the reaction solution, and the resulting reaction solution was extracted three times with 50 ml of ethyl acetate. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was recrystallized with ethyl acetate-hexane to obtain 3.9 g of Intermediate 4 (yield: 70%). The obtained compound was confirmed by 1H NMR and MS/FAB.

[0153] $C_{39}H_{26}BrN$: calc. 587.12. found 587.12

[0154] 1H NMR ($CDCl_3$, 400 MHz) δ 7.97 (s, 1H), 7.84 (d, 1H), 7.79-7.78 (m, 2H), 7.63 (d, 1H), 7.51 (d, 1H), 7.41-7.35 (m, 2H), 7.28-7.18 (m, 7H), 7.02-6.98 (m, 2H), 6.88-6.85 (m, 2H), 6.66-6.61 (m, 3H), 6.51-6.48 (m, 4H)

SYNTHESIS EXAMPLES

1) Synthesis of Compound 1

[0155] 4.5 g (15.1 mmol) of Intermediate 1, 6.40 g (16.6 mmol) of bis-biphenyl-4-yl-amine, 0.28 g (0.3 mmol) of $Pd_2(dba)_3$, 0.06 g (0.3 mmol) of $P(tBu)_3$, and 2.18 g (22.7 mmol) of $NaOtBu$ were dissolved in 70 ml of toluene, and the resultant solution was then stirred at 80° C. for 4 hours. Then, the reaction solution was cooled down to room temperature, 40 ml of water was added to the reaction solution, and the resulting reaction solution was extracted three times with 50 ml of ethyl acetate. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 6.10 g of Compound 1 (yield: 75%). The obtained compound was confirmed by 1H NMR and MS/FAB.

[0156] $C_{41}H_{31}N$: calc. 537.25. found 537.23

[0157] 1H NMR ($CDCl_3$, 400 MHz) δ 7.93 (d, 1H), 7.86 (d, 1H), 7.84-7.81 (m, 5H), 7.73-7.64 (m, 9H), 7.62-7.58 (m, 2H), 7.51 (t, 1H), 7.53 (d, 1H), 6.92 (d, 1H), 6.73-6.70 (m, 4H), 1.92 (s, 6H)

2) Synthesis of Compound 4



[0158] 5.45 g of Compound 4 was obtained (yield: 72%) in the same manner as in the Synthesis of Compound 1, except that (9,9-dimethyl-9H-fluorene-2-yl)-phenyl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ^1H NMR and MS/FAB.

[0159] $\text{C}_{38}\text{H}_{31}\text{N}$: calc. 501.25. found 501.25


[0160] ^1H NMR (CDCl_3 , 400 MHz) δ 7.97 (d, 1H), 7.92 (d, 1H), 7.86 (d, 1H), 7.84-7.80 (m, 2H), 7.67 (d, 1H), 7.56-7.49 (m, 2H), 7.43 (d, 1H), 7.34-7.26 (m, 4H), 6.95-6.84 (m, 3H), 6.68 (d, 1H), 6.53-6.50 (m, 2H), 1.93 (s, 6H), 1.63 (s, 6H)

3) Synthesis of Compound 6

[0161]



-continued



6

[0162] 5.5 g (14.6 mmol) of Intermediate 2, 1.78 g (14.6 mmol) of phenylboronic acid, 0.84 g (0.73 mmol) of $\text{Pd}(\text{PPh}_3)_4$, and 6.05 g (43.8 mmol) of K_2CO_3 were dissolved in 60 ml of THF and 40 ml of H_2O , and the resultant solution was then stirred at 80°C . for 24 hours. Then, the reaction solution was cooled down to room temperature, 40 ml of water was added to the reaction solution, and the resulting reaction solution was extracted three times with 50 ml of ethyl acetate. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 3.92 g of Intermediate 5a (yield: 72%). 3.9 g (10.4 mmol) of Intermediate 5a, 3.78 g (10.4 mmol) of biphenyl-4-yl-(9,9-dimethyl-9H-fluorene-2-yl)-amine, 0.19 g (0.21 mmol) of $\text{Pd}_2(\text{dba})_3$, 0.04 g (0.21 mmol) of $\text{P}(\text{tBu})_3$, and 1.50 g (15.6 mmol) of NaOtBu were dissolved in 60 ml of toluene, and the resultant solution was then stirred at 80°C . for 3 hours. Then, the reaction solution was cooled down to room temperature, 30 ml of water was added to the reaction solution, and the resulting reaction solution was extracted three times with 50 ml of ethyl acetate. The obtained organic layer was dried with magnesium sulfate, and the solvent was evaporated therefrom to obtain a residue. The residue was purified with silicagel column chromatography to obtain 5.24 g of Compound 6 (yield: 77%). The obtained compound was confirmed by ^1H NMR and MS/FAB.

[0163] $\text{C}_{50}\text{H}_{39}\text{N}$: calc. 653.31. found 653.32

[0164] ^1H NMR (CDCl_3 , 400 MHz) δ 8.19 (d, 1H), 7.97 (d, 1H), 7.90-7.88 (m, 2H), 7.85-7.79 (m, 3H), 7.73-7.58 (m, 10H), 7.55-7.51 (m, 2H), 7.47 (d, 1H), 7.34-7.30 (m, 2H), 6.94-6.90 (m, 2H), 6.68-6.65 (m, 3H), 1.93 (s, 6H), 1.65 (s, 6H)

4) Synthesis of Compound 7

[0165] 6.54 g of Compound 7 was obtained (yield: 69%) in the same manner as in the Synthesis of Compound 1, except that (9,9-dimethyl-9H-fluorene-2-yl)-(4-naphthalene-1-yl-phenyl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ^1H NMR and MS/FAB.

[0166] $\text{C}_{48}\text{H}_{37}\text{N}$: calc. 627.29. found 627.30

[0167] ^1H NMR (CDCl_3 , 400 MHz) δ 8.03-8.00 (m, 2H), 7.97 (d, 1H), 7.91 (d, 1H), 7.86 (d, 1H), 7.84-7.79 (m, 3H),

7.72-7.63 (m, 5H), 7.57-7.49 (m, 2H), 7.45-7.41 (m, 2H), 7.35-7.32 (m, 2H), 7.17 (t, 1H), 6.97 (d, 1H), 6.93 (d, 1H), 6.70 (d, 1H), 6.56 (m, 2H), 1.92 (s, 6H), 1.63 (s, 6H)

5) Synthesis of Compound 8

[0168] 6.72 g of Compound 8 was obtained (yield: 77%) in the same manner as in the Synthesis of Compound 1, except that biphenyl-3-yl-(9,9-dimethyl-9H-fluorene-2-yl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0169] C₄₄H₃₅N: calc. 577.28. found 577.25

[0170] ¹H NMR (CDCl₃, 400 MHz) δ 7.98 (d, 1H), 7.93 (d, 1H), 7.87 (d, 1H), 7.84-7.77 (m, 4H), 7.68 (d, 1H), 7.66-7.59 (m, 3H), 7.55-7.49 (m, 2H), 7.46-7.42 (m, 2H), 7.34-7.28 (m, 3H), 7.14 (t, 1H), 6.97 (d, 1H), 6.91 (d, 1H), 6.83 (d, 1H), 6.47 (d, 1H), 1.92 (s, 6H), 1.64 (s, 6H)

6) Synthesis of Compound 9

[0171] 6.33 g of Compound 9 was obtained (yield: 67%) in the same manner as in the Synthesis of Compound 1, except that (9,9-diphenyl-9H-fluorene-2-yl)-phenyl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0172] C₄₈H₃₅N: calc. 628.80. found 628.81

[0173] ¹H NMR (CDCl₃, 400 MHz) δ 8.07 (d, 1H), 7.93 (d, 1H), 7.87 (d, 1H), 7.83 (d, 1H), 7.67-7.62 (m, 2H), 7.53 (d, 2H), 7.48 (d, 1H), 7.40-7.27 (m, 13H), 7.00 (d, 1H), 6.93 (d, 1H), 6.85 (t, 1H), 6.78 (d, 1H), 6.74 (d, 1H), 6.48-6.45 (m, 2H), 1.93 (s, 6H)

7) Synthesis of Compound 10

[0174] 6.50 g of Compound 10 was obtained (yield: 69%) in the same manner as in the Synthesis of Compound 1, except that (9,9-spiro-fluorene-2-yl)-phenyl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0175] C₄₈H₃₃N: calc. 623.78. found 623.80

[0176] ¹H NMR (CDCl₃, 400 MHz) δ 8.05 (d, 1H), 7.99 (d, 2H), 7.83 (d, 1H), 7.79 (d, 1H), 7.73 (d, 2H), 7.67-7.61 (m, 4H), 7.53-7.51 (m, 1H), 7.43 (d, 1H), 7.41-7.35 (m, 4H), 7.31-7.26 (m, 2H), 7.01-6.93 (m, 6H), 6.85 (t, 1H), 6.52-6.49 (m, 2H), 1.93 (s, 6H)

8) Synthesis of Compound 16

[0177] 7.51 g of Compound 16 was obtained (yield: 72%) in the same manner as in the Synthesis of Compound 1, except that Intermediate 3 was used instead of Intermediate 1, and (4-fluoro-phenyl)-(9-phenyl-9H-carbazole-3-yl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0178] C₅₁H₃₁FN₂: calc. 690.25. found 690.23

[0179] ¹H NMR (CDCl₃, 400 MHz) δ 8.21 (d, 1H), 8.07 (d, 2H), 7.93 (d, 1H), 7.85 (d, 1H), 7.81 (d, 1H), 7.74-7.69 (m, 5H), 7.66-7.55 (m, 4H), 7.52-7.47 (m, 6H), 7.25-7.19 (m, 2H), 7.11 (d, 1H), 6.91 (d, 2H), 6.85-6.80 (m, 4H), 6.53 (t, 1H)

9) Synthesis of Compound 17

[0180] 7.05 g of Compound 17 was obtained (yield: 69%) in the same manner as in the Synthesis of Compound 1, except that biphenyl-4-yl-(9-naphthalene-1-yl-9H-carbazole-3-yl)-

amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0181] C₅₁H₃₆N₂: calc. 676.29. found 676.30

[0182] ¹H NMR (CDCl₃, 400 MHz) δ 8.23 (d, 1H), 8.06 (d, 1H), 7.91 (d, 1H), 7.84 (d, 1H), 7.78 (d, 1H), 7.72-7.65 (m, 5H), 7.61 (d, 1H), 7.55-7.47 (m, 7H), 7.43-7.25 (m, 7H), 7.16 (d, 1H), 7.05 (d, 1H), 6.98 (d, 1H), 6.81-6.77 (m, 2H), 1.92 (s, 6H)

10) Synthesis of Compound 18

[0183] 6.82 g of Compound 18 was obtained (yield: 63%) in the same manner as in the synthesis of Compound 1, except that (9,9-dimethyl-9H-fluorene-2-yl)-(7-phenyl-7H-benzo[c]carbazole-10-yl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0184] C₅₄H₄₀N₂: calc. 716.32. found 716.33

[0185] ¹H NMR (CDCl₃, 400 MHz) δ 8.28 (d, 1H), 8.15 (d, 1H), 8.07 (d, 1H), 7.91 (d, 1H), 7.85 (d, 1H), 7.80-7.76 (m, 3H), 7.71-7.65 (m, 4H), 7.61-7.56 (m, 5H), 7.49-7.38 (m, 4H), 7.33 (d, 1H), 7.25-7.21 (m, 2H), 7.05-7.00 (m, 2H), 6.94 (d, 1H), 6.86 (d, 1H), 1.93 (s, 6H), 1.63 (s, 6H)

11) Synthesis of Compound 21

[0186] 4.71 g of Compound 21 was obtained (yield: 70%) in the same manner as in the Synthesis of Compound 1, except that Intermediate 4 was used instead of Intermediate 1, and naphthalene-1-yl-phenyl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0187] C₅₅H₃₈N₂: calc. 726.30. found 726.31

[0188] ¹H NMR (CDCl₃, 400 MHz) δ 8.11 (d, 1H), 7.92 (d, 1H), 7.80 (d, 1H), 7.72-7.65 (m, 4H), 7.61 (d, 1H), 7.57 (t, 1H), 7.52-7.46 (m, 4H), 7.42-7.31 (m, 8H), 7.16 (d, 1H), 7.02 (d, 1H), 6.98-6.92 (m, 4H), 6.84-6.81 (m, 2H), 6.68-6.63 (m, 3H), 6.57-6.52 (m, 4H), 6.48-6.45 (m, 2H)

12) Synthesis of Compound 22

[0189] 4.83 g of Compound 22 was obtained (yield: 68%) in the same manner as in the Synthesis of Compound 21, except that (4-(9H-carbazole-9-yl)-phenyl)-magnesium bromide was used instead of (4-(diphenylamino)-phenyl)-magnesium bromide, and biphenyl-4-yl-p-tolyl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0190] C₅₈H₄₀N₂: calc. 764.32. found 764.33

[0191] ¹H NMR (CDCl₃, 400 MHz) δ 8.11 (d, 2H), 7.91 (d, 1H), 7.84-7.82 (m, 2H), 7.78 (d, 1H), 7.73-7.65 (m, 5H), 7.62-7.45 (m, 7H), 7.41-7.38 (m, 3H), 7.35-7.28 (m, 4H), 7.20-7.18 (m, 2H), 7.04 (d, 1H), 6.83-6.79 (m, 4H), 6.67-6.64 (m, 2H), 6.61-6.57 (m, 3H), 2.30 (s, 3H)

13) Synthesis of Compound 24

[0192] 4.65 g of Compound 24 was obtained (yield: 76%) in the same manner as in the Synthesis of Compound 21, except that (4-(9-naphthalene-1-yl-10-phenyl-anthracene))-magnesium bromide was used instead of (4-(diphenylamino)-phenyl)-magnesium bromide, and diphenyl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0193] C₆₃H₄₁N: calc. 811.32. found 811.34

[0194] ¹H NMR (CDCl₃, 400 MHz) δ 7.95-7.91 (m, 3H), 7.82-7.75 (m, 5H), 7.64-7.60 (m, 2H), 7.57-7.54 (m, 2H),

7.47-7.38 (m, 5H), 7.32-7.27 (m, 3H), 7.21-7.13 (m, 8H), 7.08 (t, 1H), 6.97 (d, 1H), 6.86 (t, 2H), 6.79-6.75 (m, 2H), 6.66-6.63 (m, 2H), 6.58 (t, 1H), 6.53-6.50 (m, 4H)

14) Synthesis of Compound 25

[0195] 5.19 g of Compound 25 was obtained (yield: 72%) in the same manner as in the Synthesis of Compound 21, except that (9,9-dimethyl-9H-fluorene-2-yl)-magnesium bromide was used instead of (4-(diphenylamino)-phenyl)-magnesium bromide, and bis-biphenyl-3-yl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0196] C₆₀H₄₃N: calc. 777.34. found 777.34

[0197] ¹H NMR (CDCl₃, 400 MHz) δ 8.02 (d, 1H), 7.89 (d, 1H), 7.82-7.77 (m, 4H), 7.69-7.59 (m, 11H), 7.55-7.51 (m, 2H), 7.46-7.43 (m, 3H), 7.36-7.27 (m, 8H), 7.12 (t, 2H), 6.87 (d, 1H), 6.65 (t, 1H), 6.53-6.50 (m, 2H), 6.35 (d, 1H), 1.52 (s, 6H)

15) Synthesis of Compound 26

[0198] 5.24 g of Compound 26 was obtained (yield: 70%) in the same manner as in the Synthesis of Compound 21, except that (3-dibenzothienyl)-magnesium bromide was used instead of (4-(diphenylamino)-phenyl)-magnesium bromide, and biphenyl-3-yl-(9,9-dimethyl-9H-fluorene-2-yl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0199] C₆₀H₄₁NS: calc. 807.30. found 807.31

[0200] ¹H NMR (CDCl₃, 400 MHz) δ 8.23 (d, 2H), 7.98 (d, 1H), 7.95-7.90 (m, 2H), 7.85-7.78 (m, 3H), 7.76 (d, 1H), 7.71-7.56 (m, 8H), 7.49-7.46 (m, 1H), 7.42-7.29 (m, 1H), 7.22 (d, 1H), 7.18 (t, 1H), 6.99 (d, 1H), 6.86 (d, 1H), 6.64 (t, 1H), 6.47 (d, 1H), 1.62 (s, 6H)

16) Synthesis of Compound 28

[0201] 7.07 g of Compound 28 was obtained (yield: 63%) in the same manner as in the Synthesis of Compound 1, except that (9,9-diphenyl-9H-fluorene-2-yl)-[4-(9-phenyl-9H-carbazole-3-yl)-phenyl]-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0202] C₅₆H₄₂N₂: calc. 742.33. found 742.35

[0203] ¹H NMR (CDCl₃, 400 MHz) δ 8.23 (d, 1H), 8.16-8.14 (m, 1H), 7.87-7.80 (m, 3H), 7.76-7.67 (m, 6H), 7.62-7.57 (m, 5H), 7.51-7.39 (m, 5H), 7.36-7.30 (d, 2H), 7.23-7.19 (m, 2H), 6.98-6.93 (m, 2H), 6.79-6.75 (m, 3H), 1.94 (s, 6H), 1.63 (s, 6H)

17) Synthesis of Compound 29

[0204] 6.25 g of Compound 29 was obtained (yield: 67%) in the same manner as in the Synthesis of Compound 1, except that bis-(9,9-diphenyl-9H-fluorene-2-yl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0205] C₄₇H₃₉N: calc. 617.31. found 617.30

[0206] ¹H NMR (CDCl₃, 400 MHz) δ 7.96 (d, 2H), 7.92 (d, 1H), 7.85 (d, 1H), 7.82 (s, 3H), 7.72 (d, 1H), 7.67-7.60 (m, 3H), 7.52 (d, 1H), 7.37-7.31 (m, 4H), 7.00 (d, 1H), 6.91 (d, 2H), 6.70 (d, 2H), 1.92 (s, 6H), 1.63 (s, 12H)

18) Synthesis of Compound 34

[0207] 6.10 g of Compound 34 was obtained (yield: 63%) in the same manner as in the Synthesis of Compound 1, except that dibenzofuran-2-yl-(9-phenyl-9H-carbazole-3-yl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0208] C₄₇H₃₂N₂O: calc. 640.25. found 640.23

[0209] ¹H NMR (CDCl₃, 400 MHz) δ 8.22 (d, 1H), 7.92 (d, 1H), 7.85-7.82 (m, 2H), 7.75-7.72 (m, 2H), 7.68 (d, 1H), 7.66 (d, 1H), 7.63 (d, 1H), 7.57-7.49 (m, 6H), 7.46-7.37 (m, 3H), 7.35-7.25 (m, 5H), 7.07-7.03 (m, 2H), 6.97 (d, 1H), 1.93 (s, 6H)

19) Synthesis of Compound 35

[0210] 7.22 g of Compound 35 was obtained (yield: 68%) in the same manner as in the Synthesis of Compound 1, except that (4-carbazole-9-yl-phenyl)-[1,1';3',1'']terphenyl-5'-yl-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0211] C₅₃H₃₈N₂: calc. 702.30. found 702.31

[0212] ¹H NMR (CDCl₃, 400 MHz) δ 8.11 (d, 2H), 7.94 (d, 1H), 7.88-7.79 (m, 6H), 7.73-7.69 (m, 2H), 7.65-7.56 (m, 5H), 7.48-7.40 (m, 8H), 7.37 (d, 1H), 7.28-7.23 (m, 2H), 7.03 (d, 2H), 6.99 (d, 1H), 6.89-6.85 (m, 2H), 1.92 (s, 6H)

20) Synthesis of Compound 36

[0213] 7.13 g of Compound 36 was obtained (yield: 66%) in the same manner as in the Synthesis of Compound 1, except that bis-(4-carbazole-9-yl-phenyl)-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0214] C₅₃H₃₇N₃: calc. 715.30. found 715.32

[0215] ¹H NMR (CDCl₃, 400 MHz) δ 8.11 (d, 4H), 7.93 (d, 1H), 7.87 (d, 1H), 7.83 (d, 1H), 7.70 (d, 1H), 7.59-7.49 (m, 13H), 7.43 (d, 1H), 7.37-7.33 (m, 4H), 6.95-6.92 (m, 5H), 1.94 (s, 6H)

21) Synthesis of Compound 37

[0216] 5.31 g of Compound 37 was obtained (yield: 61%) in the same manner as in the Synthesis of Compound 1, except that 3-(4-pyrido[3,2-b]indole-5-yl-phenylamino)-benzonitrile was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0217] C₄₁H₂₈N₁₄: calc. 576.23. found 576.23

[0218] ¹H NMR (CDCl₃, 400 MHz) δ 8.71 (d, 1H), 8.31 (d, 1H), 7.92 (d, 1H), 7.85-7.81 (m, 2H), 7.79-7.73 (m, 2H), 7.58-7.51 (m, 3H), 7.47-7.36 (m, 8H), 7.01-6.93 (m, 3H), 6.63 (d, 1H), 1.92 (s, 6H)

22) Synthesis of Compound 41

[0219] 7.07 g of Compound 41 was obtained (yield: 65%) in the same manner as in the Synthesis of Compound 1, except that N,N-di-[4-(N,N-diphenylamino)-phenyl]amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by ¹H NMR and MS/FAB.

[0220] $C_{53}H_{41}N_3$: calc. 719.33. found 719.34

[0221] 1H NMR ($CDCl_3$, 400 MHz) δ 7.92 (d, 1H), 7.86 (d, 1H), 7.81 (d, 1H), 7.68 (d, 1H), 7.53 (t, 1H), 7.43 (d, 1H), 7.28-7.23 (m, 8H), 7.02 (d, 1H), 6.96-6.87 (m, 12H), 6.58-6.55 (m, 8H), 1.95 (s, 6H)

23) Synthesis of Compound 42

[0222] 8.30 g of Compound 42 was obtained (yield: 62%) in the same manner as in the Synthesis of Compound 1, except that N,N-di-[4-(N,N-diphenylamino)-biphenyl]amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0223] $C_{65}H_{49}N_3$: calc. 871.39. found 871.40

[0224] 1H NMR ($CDCl_3$, 400 MHz) δ 7.94 (d, 1H), 7.86 (d, 1H), 7.83 (d, 1H), 7.70-7.62 (m, 9H), 7.54 (t, 1H), 7.48 (d, 1H), 7.35-7.30 (m, 8H), 7.17-7.13 (m, 4H), 7.02 (d, 1H), 6.96-6.91 (m, 4H), 6.83-6.79 (m, 4H), 6.56-6.52 (m, 8H), 1.92 (s, 6H)

24) Synthesis of Compound 43

[0225] 6.81 g of Compound 43 was obtained (yield: 62%) in the same manner as in the Synthesis of Compound 1, except that N4'-[1,1'-biphenyl]-4-yl-N4,N4-diphenyl-[1,1'-biphenyl]-4,4'-diamine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0226] $C_{53}H_{40}N_2$: calc. 704.32. found 704.33

[0227] 1H NMR ($CDCl_3$, 400 MHz) δ 7.93 (d, 1H), 7.87 (d, 1H), 7.86-7.82 (m, 3H), 7.75-7.71 (m, 2H), 7.70-7.60 (m, 8H), 7.55 (t, 1H), 7.48 (d, 1H), 7.37-7.32 (m, 4H), 7.06-7.02 (m, 2H), 6.93 (d, 1H), 6.89-6.85 (m, 2H), 6.81-6.73 (m, 4H), 6.62-6.58 (m, 4H), 1.95 (s, 6H)

25) Synthesis of Compound 45

[0228] 7.37 g of Compound 45 was obtained (yield: 67%) in the same manner as in the Synthesis of Compound 1, except that N4,N4'-di-1-naphthalenyl-N4-phenyl-[1,1'-biphenyl]-4,4'-diamine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0229] $C_{55}H_{40}N_2$: calc. 728.32. found 728.32

[0230] 1H NMR ($CDCl_3$, 400 MHz) δ 8.16 (d, 1H), 8.11 (d, 1H), 7.87 (d, 2H), 7.75 (d, 1H), 7.68 (d, 1H), 7.63 (d, 1H), 7.52-7.41 (m, 11H), 7.35-7.25 (m, 4H), 7.12-7.07 (m, 2H), 6.97-6.93 (m, 2H), 6.88-6.83 (m, 3H), 6.79-6.75 (t, 1H), 6.66-6.63 (m, 2H), 6.59-6.56 (m, 2H), 1.93 (s, 6H)

26) Synthesis of Compound 47

[0231] 6.63 g of Compound 47 was obtained (yield: 70%) in the same manner as in the Synthesis of Compound 1, except that 4'-(9H-carbazole-9-yl)-N-phenyl-[1,1'-biphenyl]-4-amine was used instead of bis-biphenyl-4-yl-amine. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0232] $C_{47}H_{34}N_2$: calc. 626.27. found 626.28

[0233] 1H NMR ($CDCl_3$, 400 MHz) δ 8.12 (d, 2H), 7.94 (d, 1H), 7.87 (d, 1H), 7.83 (d, 1H), 7.79-7.75 (m, 2H), 7.71-7.65 (m, 5H), 7.61-7.56 (m, 8H), 7.48-7.43 (m, 2H), 7.15-7.10 (m, 2H), 7.04-7.01 (m, 2H), 6.83-6.79 (m, 2H), 1.93 (s, 6H)

27) Synthesis of Compound 48

[0234] 7.48 g of Compound 48 was obtained (yield: 69%) in the same manner as in the Synthesis of Compound 1, except that N,N,N',N'-tetraphenyl-9H-carbazole-3,6-diamine was used instead of bis-biphenyl-4-yl-amine.

[0235] The obtained compound was confirmed by 1H NMR and MS/FAB. $C_{53}H_{39}N_3$: calc. 717.31. found 717.32

[0236] 1H NMR ($CDCl_3$, 400 MHz) δ 8.17 (d, 1H), 7.95 (d, 1H), 7.88 (d, 1H), 7.79 (d, 1H), 7.68 (d, 2H), 7.56-7.52 (m, 3H), 7.41 (d, 1H), 7.25-7.19 (m, 9H), 6.88-6.82 (m, 6H), 6.63-6.60 (m, 8H), 1.95 (s, 6H)

28) Synthesis of Compound 49

[0237] 5.40 g of Compound 49 was obtained (yield: 60%) in the same manner as in the Synthesis of Compound 6, except that B-(4,6-diphenyl-1,3,5-triazine-2-yl)-boronic acid was used instead of phenylboronic acid, and diphenyl-amine was used instead of biphenyl-4-yl-(9,9-dimethyl-9H-fluorene-2-yl)-amine. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0238] $C_{44}H_{32}N_4$: calc. 616.26. found 616.27

[0239] 1H NMR ($CDCl_3$, 400 MHz) δ 9.22 (s, 1H), 8.80-8.77 (m, 5H), 7.83 (d, 1H), 7.65 (t, 4H), 7.56-7.52 (m, 4H), 7.29-7.25 (m, 4H), 7.01-6.95 (m, 3H), 6.62-6.58 (m, 4H), 1.94 (s, 6H)

29) Synthesis of Compound 50

[0240] 4.72 g of Compound 50 was obtained (yield: 63%) in the same manner as in the Synthesis of Compound 6, except that 3-pyridylboronic acid was used instead of phenylboronic acid, and naphthalene-1-yl-phenyl-amine was used instead of biphenyl-4-yl-(9,9-dimethyl-9H-fluorene-2-yl)-amine. The obtained compound was confirmed by 1H NMR and MS/FAB.

[0241] $C_{38}H_{28}N_2$: calc. 512.23. found 512.25


[0242] 1H NMR ($CDCl_3$, 400 MHz) δ 9.03 (d, 1H), 8.69-8.67 (m, 1H), 8.11 (d, 1H), 8.06 (d, 2H), 7.86 (d, 1H), 7.50-7.39 (m, 6H), 7.37-7.34 (m, 3H), 7.15-7.11 (m, 2H), 6.91 (d, 1H), 6.89-6.86 (m, 2H), 6.53-6.50 (m, 2H), 1.93 (s, 6H)

Example 1


[0243] To prepare an anode, a 15 Ω/cm^2 (1200 Å) Corning ITO glass substrate was cut to a size of 50 mm×50 mm×0.7 mm, washed with ultrasonic waves in isopropyl alcohol and pure water for 5 minutes each, and then cleaned with UV and ozone for 30 minutes. The ITO glass substrate was mounted on a vacuum depositor.

[0244] 2-TNATA was vacuum deposited on the ITO glass substrate to form a HIL having a thickness of 600 Å, and Compound 6 was vacuum deposited on the HIL to form a HTL having a thickness of 300 Å.


[0245] Next, 9,10-di-naphthalene-2-yl-anthracene (DNA) as a blue fluorescent host and 4,4'-bis[2-(4-(N,N-diphenylamino)phenyl)vinyl]biphenyl (DPAVB) as a blue fluorescent dopant were co-deposited on the HTL at a weight ratio of 98:2 to form an EML having a thickness of 300 Å.



2-TNATA



DNA



DPAVB

[0246] Subsequently, Alq₃ was deposited on the EML to form an ETL having a thickness of 300 Å, LiF was deposited on the ETL to form an EIL having a thickness of 10 Å, and Al

was deposited on the EIL to form a LiF/Al electrode (cathode) having a thickness of 3,000 Å, thereby completing the manufacture of an OLED.

[0247] The OLED had a driving voltage of 5.63 V at a current density of 50 mA/cm², a brightness of 2760 cd/m², a luminous efficiency of 5.52 cd/A, and a half-lifetime (hr @100 mA/cm²) of 324 hours.

Example 2

[0248] An OLED was manufactured in the same manner as in Example 1, except that Compound 17 was used instead of Compound 6.

[0249] The OLED had a driving voltage of 5.67 V at a current density of 50 mA/cm², a brightness of 2745 cd/m², a luminous efficiency of 5.49 cd/A, and a half-lifetime (hr @100 mA/cm²) of 293 hours.

Example 3

[0250] An OLED was manufactured in the same manner as in Example 1, except that Compound 21 was used instead of Compound 6.

[0251] The OLED had a driving voltage of 5.79 V at a current density of 50 mA/cm², a brightness of 2770 cd/cm², a luminous efficiency of 5.54 cd/A, and a half-lifetime (hr @100 mA/cm²) of 307 hours.

Example 4

[0252] An OLED was manufactured in the same manner as in Example 1, except that Compound 26 was used instead of Compound 6.

[0253] The OLED had a driving voltage of 5.58 V at a current density of 50 mA/cm², a brightness of 2560 cd/cm², a luminous efficiency of 5.12 cd/A, and a half-lifetime (hr @100 mA/cm²) of 297 hours.

Example 5

[0254] An OLED was manufactured in the same manner as in Example 1, except that Compound 35 was used instead of Compound 6.

[0255] The OLED had a driving voltage of 5.82 V at a current density of 50 mA/cm², a brightness of 2780 cd/cm², a luminous efficiency of 5.56 cd/A, and a half-lifetime (hr @100 mA/cm²) of 317 hours.

Example 6

[0256] An OLED was manufactured in the same manner as in Example 1, except that Compound 41 was used instead of Compound 6.

[0257] The OLED had a driving voltage of 5.56 V at a current density of 50 mA/cm², a brightness of 2805 cd/cm², a luminous efficiency of 5.61 cd/A, and a half-lifetime (hr @100 mA/cm²) of 268 hours.

Example 7

[0258] An OLED was manufactured in the same manner as in Example 1, except that Compound 45 was used instead of Compound 6.

[0259] The OLED had a driving voltage of 5.43 V at a current density of 50 mA/cm², a brightness of 2835 cd/cm², a luminous efficiency of 5.67 cd/A, and a half-lifetime (hr @100 mA/cm²) of 356 hours.

Example 8

[0260] An OLED was manufactured in the same manner as in Example 1, except that Compound 48 was used instead of Compound 6.

[0261] The OLED had a driving voltage of 5.62 V at a current density of 50 mA/cm², a brightness of 2670 cd/cm², a luminous efficiency of 5.34 cd/A, and a half-lifetime (hr @100 mA/cm²) of 322 hours.

Example 9


[0262] An OLED was manufactured in the same manner as in Example 1, except that Compound 49 was used instead of Compound 6.

[0263] The OLED had a driving voltage of 5.37 V at a current density of 50 mA/cm², a brightness of 2575 cd/cm², a luminous efficiency of 5.15 cd/A, and a half-lifetime (hr @100 mA/cm²) of 215 hours.

Comparative Example 1

[0264] An OLED was manufactured in the same manner as in Example 1, except that 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB) was used instead of Compound 6.

[0265] The OLED had a driving voltage of 7.35 V at a current density of 50 mA/cm², a brightness of 2065 cd/cm², a luminous efficiency of 4.13 cd/A, and a half-lifetime (hr @100 mA/cm²) of 145 hours.




NPB

Comparative Example 2

[0266] An OLED was manufactured in the same manner as in Example 1, except that Compound 52 (below) was used instead of Compound 6 in the formation of the HTL.


[0267] The OLED had a driving voltage of 6.87 V at a current density of 50 mA/cm², a brightness of 2,340 cd/cm², a luminous efficiency of 4.68 cd/A, and a half-lifetime (hr @100 mA/cm²) of 220 hours.



Comparative Example 3

[0268] An OLED was manufactured in the same manner as in Example 1, except that Compound 53 (below) was used instead of Compound 6 in the formation of the HTL.

[0269] The OLED had a driving voltage of 7.12 V at a current density of 50 mA/cm², a brightness of 2,105 cd/cm², a luminous efficiency of 4.21 cd/A, and a half-lifetime (hr @100 mA/cm²) of 132 hours.



[0270] The characteristics and lifetimes of the OLEDs of Examples 1 to 9 and Comparative Examples 1 to 3 are shown in Table 1 below.

TABLE 1

	Hole transporting material	Driving voltage (V)	Current density (mA/cm ²)	brightness (cd/m ²)	efficiency (cd/A)	Emission color	Half-lifetime (hr @ 100 mA/cm ²)
Example 1	Compound 6	5.63	50	2,760	5.52	blue	324 hr
Example 2	Compound 17	5.67	50	2,745	5.49	blue	293 hr
Example 3	Compound 21	5.79	50	2,770	5.54	blue	307 hr
Example 4	Compound 26	5.58	50	2,560	5.12	blue	297 hr
Example 5	Compound 35	5.82	50	2,780	5.56	blue	317 hr
Example 6	Compound 41	5.56	50	2,805	5.61	blue	268 hr
Example 7	Compound 45	5.43	50	2,835	5.67	blue	356 hr
Example 8	Compound 48	5.62	50	2,670	5.34	blue	322 hr
Example 9	Compound 49	5.37	50	2,575	5.15	blue	215 hr
Comp.	NPB	7.35	50	2,065	4.13	blue	145 hr
Example 1	Comp.						
Example 2	Compound 52	6.87	50	2,340	4.68	blue	220 hr
Example 3	Compound 53	7.12	50	2,105	4.21	blue	132 hr


[0271] From the results shown in Table 1, it was confirmed that when the compound of Formula 1 was used as a hole transporting material, the OLED including the compound of Formula 1 exhibited good current-voltage-luminance (I-V-L) characteristics, i.e., a significantly improved driving voltage and high efficiency, and in particular, exhibited a significantly improved lifetime, as compared to the OLED including NPB.

[0272] As described above, according to the one or more embodiments of the present invention, novel compounds represented by Formula 1 have good luminous properties and charge transporting abilities, and thus, may be suitable for use as hole injection materials or hole transporting materials in fluorescent and phosphorescent devices of all colors, such as red, green, blue, white, and the like. Thus, OLEDs including the compounds of Formula 1 may have high efficiency, low voltage, high brightness, and long lifetimes.

[0273] While the present invention has been illustrated and described with reference to certain exemplary embodiments, it will be understood by those of ordinary skill in the art that various changes may be made to the described embodiments without departing from the spirit and scope of the present invention as defined by the following claims.

What is claimed is:

1. A compound for an organic light-emitting diode represented by Formula 1:



Formula 1

wherein:

R₁ and R₂ are each independently a halogen, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₃-C₆₀ heteroaryl group, or a substituted or unsubstituted

C_6-C_{60} condensed polycyclic group, or R_1 and R_2 optionally combine to form a ring;

R_3 is hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_3-C_{60} heteroaryl group, or a substituted or unsubstituted C_6-C_{60} condensed polycyclic group;


Ar_1 and Ar_2 are each independently a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_3-C_{60} heteroaryl group, or a substituted or unsubstituted C_6-C_{60} condensed polycyclic group, or Ar_1 and Ar_2 optionally combine to form a ring.

2. The compound of claim 1, wherein R_1 and R_2 are each independently a halogen, a cyano group, a substituted or unsubstituted C_1-C_{30} alkyl group, a substituted or unsubstituted C_6-C_{30} aryl group, a substituted or unsubstituted C_3-C_{30} heteroaryl group, or a substituted or unsubstituted C_6-C_{30} condensed polycyclic group;

R_3 is hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_6-C_{30} aryl group, a substituted or unsubstituted C_3-C_{30} heteroaryl group, or a substituted or unsubstituted C_6-C_{30} condensed polycyclic group; and

Ar_1 and Ar_2 are each independently a substituted or unsubstituted C_6-C_{30} aryl group, a substituted or unsubstituted C_3-C_{30} heteroaryl group, or a substituted or unsubstituted C_6-C_{30} condensed polycyclic group.

3. The compound of claim 1, wherein R_1 and R_2 are each independently hydrogen, deuterium, a halogen, a cyano group, a substituted or unsubstituted C_1-C_{20} alkyl group, or a moiety represented by any one of Formulae 2a through 2c:



wherein:

Y_1 , Y_2 , and Y_3 are each independently a linking group represented by $-N=$, $-N(R_{20})-$, or $-C(R_{21})=$;

Q is a linking group represented by $-C(R_{30})(R_{31})-$, $-N(R_{32})-$, $-S-$, or $-O-$;


Z_1 , Z_2 , R_{20} , R_{21} , R_{30} , R_{31} , and R_{32} are each independently a hydrogen atom, deuterium, a substituted or unsubstituted C_1-C_{20} alkyl group, a substituted or unsubstituted C_6-C_{20} aryl group, a substituted or unsubstituted C_3-C_{20} heteroaryl group, a substituted or unsubstituted C_6-C_{20} condensed polycyclic group, an amino group substituted

with a C_6-C_{20} aryl group or a C_3-C_{20} heteroaryl group, a halogen group, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;

p is an integer of 1 to 7; and

* denotes a binding site.

4. The compound of claim 1, wherein R_3 is hydrogen, deuterium, a halogen, or a moiety represented by at least one of Formulae 3a through 3c:



wherein:


Y_1 , Y_2 , and Y_3 are each independently a linking group represented by $-N=$, $-N(R_{20})-$, or $-C(R_{21})=$;

Z_1 , Z_2 , R_{20} , and R_{21} are each independently a hydrogen atom, deuterium, a substituted or unsubstituted C_1-C_{20} alkyl group, a substituted or unsubstituted C_6-C_{20} aryl group, a substituted or unsubstituted C_3-C_{20} heteroaryl group, a substituted or unsubstituted C_6-C_{20} condensed polycyclic group, a halogen, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;





p is an integer of 1 to 7; and

* denotes a binding site.

5. The compound of claim 1, wherein Ar_1 and Ar_2 are each independently a moiety represented by any one of Formulae 4a through 4g:



-continued



wherein:

Q_1 and Q_2 are each independently a linking group represented by $-C(R_{30})(R_{31})-$, $-N(R_{32})-$, $-S-$, or $-O-$;

Z_1 , Z_2 , Z_3 , R_{30} , R_{31} , and R_{32} are each independently a hydrogen atom, deuterium, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_3 - C_{20} heteroaryl group, an amino group substituted with a C_6 - C_{20} aryl group or a C_3 - C_{20} heteroaryl group, a substituted or unsubstituted C_6 - C_{20} condensed polycyclic group, a halogen, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;

p is an integer of 1 to 9;

q is 1 or 2;

r is an integer of 1 to 4; and

$*$ denotes a binding site.

6. The compound of claim 1, wherein R_1 and R_2 combine to form a ring.

7. The compound of claim 1, wherein Ar_1 and Ar_2 combine to form a ring.

8. The compound of claim 1, wherein the compound of Formula 1 is selected from Compounds 1 through 50:

4d

4e




4f

4g

1


2

3




-continued

4




-continued


7




5




8




6



9




-continued




10

-continued




14


11




12




15




13




16




-continued




-continued



18





21




22

19




-continued

23




-continued


26



24





27




28

25




-continued

29




-continued


32




30




33




31




34




-continued




-continued




36




39




37



40




-continued




41


-continued




43



42




44




45


-continued



46




47




48


-continued



49



50



51

9. An organic light-emitting diode comprising:
a first electrode;
a second electrode; and
an organic layer between the first electrode and the second electrode, the organic layer comprising the compound according to claim 1.

10. The organic light-emitting diode of claim 9, wherein the organic layer is an emission layer, and the compound represented by Formula 1 is a fluorescent host or a phosphorescent host.

11. The organic light-emitting diode of claim 9, wherein the organic layer is an emission layer, and the compound represented by Formula 1 is a fluorescent dopant.

12. The organic light-emitting diode of claim 9, wherein the organic layer is a hole injection layer, a hole transport layer, or a functional layer having hole injection and hole transport abilities.

13. The organic light-emitting diode of claim 9, wherein the organic layer is a hole transport layer.

14. The organic light-emitting diode of claim 9, wherein the organic light-emitting diode comprises an emission layer,

a hole injection layer, a hole transport layer, or a functional layer having hole injection and hole transport abilities, wherein the emission layer, the hole injection layer, the hole transport layer, or the functional layer having hole injection and hole transport abilities comprises the compound according to claim 1, and the emission layer comprises an anthracene-based compound, an arylamine-based compound, or a styryl-based compound.

15. The organic light-emitting diode of claim 9, wherein the organic light-emitting diode comprises an emission layer, a hole injection layer, a hole transport layer, or a functional layer having hole injection and hole transport abilities, wherein the hole injection layer, the hole transport layer, or the functional layer having hole injection and hole transport abilities comprises the compound according to claim 1, and any one of a red layer, a green layer, a blue layer, or a white layer of the emission layer comprises a phosphorescent compound.

16. The organic light-emitting diode of claim 15, wherein the hole injection layer, the hole transport layer, or the func-

tional layer having hole injection and hole transport abilities comprises a charge-generating material.

17. The organic light-emitting diode of claim 16, wherein the charge-generating material is a p-dopant, wherein the p-dopant is a quinone derivative, a metal oxide, or a cyano-containing compound.

18. The organic light-emitting diode of claim 9, wherein the organic layer comprises an electron transport layer, wherein the electron transport layer comprises an electron transporting organic compound and a metal complex.

19. The organic light-emitting diode of claim 9, wherein the organic layer is formed using the compound according to claim 1 using a wet process.

20. A flat panel display device comprising the organic light-emitting diode of claim 9, wherein the first electrode of the organic light-emitting diode is electrically connected to a source electrode or a drain electrode of a thin film transistor.

* * * * *

专利名称(译)	用于有机发光二极管的化合物和包括其的有机发光二极管		
公开(公告)号	US20130270524A1	公开(公告)日	2013-10-17
申请号	US13/633850	申请日	2012-10-02
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	SAMSUNG DISPLAY CO.LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	PARK JUN HA HWANG SEOK HWAN KIM YOUNG KOOK JUNG HYE JIN LEE EUN YOUNG LIM JIN O HAN SANG HYUN JEONG EUN JAE KIM SOO YON CHO SE JIN LEE JONG HYUK		
发明人	PARK, JUN-HA HWANG, SEOK-HWAN KIM, YOUNG-KOOK JUNG, HYE-JIN LEE, EUN-YOUNG LIM, JIN-O HAN, SANG-HYUN JEONG, EUN-JAE KIM, SOO-YON CHO, SE-JIN LEE, JONG-HYUK		
IPC分类号	H01L51/54 C07C255/58 C07D401/06 C07D209/94 C07D251/24 C07D307/91 C07D403/12 C07D405/12 C07D471/04 C07D401/14 C07C211/61 C07D333/00		
CPC分类号	C07C211/61 C07B2200/05 C07C255/58 C07C2103/18 C07C2103/24 C07C2103/26 C07C2103/40 C07C2103/50 C07C2103/54 C07C2103/94 C07C2603/18 C07C2603/24 C07C2603/26 C07C2603/40 C07C2603/50 C07C2603/54 C07C2603/94 C07D209/86 C07D209/88 C07D213/38 C07D235/06 C07D251/24 C07D277/66 C07D401/04 C07D401/12 C07D401/14 C07D403/04 C07D403/10 C07D403/12 C07D403/14 C07D413/04 C07D471/04 C07D487/04 C07D491/16 C09K11/06 C09K2211/1007 C09K2211/1011 C09K2211/1014 C09K2211/1029 C09K2211/1088 H01L51/006 H01L51/0061 H01L51/0072 H01L51/5012 H01L51/5056 H05B33/10		
优先权	1020120039968 2012-04-17 KR		
其他公开文献	US9567287		
外部链接	Espacenet USPTO		

摘要(译)

由下面的式1表示的化合物可以用于有机发光二极管中。

SECOND ELECTRODE
EIL
ETL
EML
HTL
HIL
FIRST ELECTRODE