



US 20150001479A1

(19) **United States**(12) **Patent Application Publication****Lee et al.**(10) **Pub. No.: US 2015/0001479 A1**(43) **Pub. Date:****Jan. 1, 2015**(54) **COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE INCLUDING THE
SAME**

includes the compound represented by Formula 1, 2 or 3. A flat display apparatus includes the organic light-emitting device.


(71) Applicant: **SAMSUNG DISPLAY CO., LTD.,**
Yongin-City (KR)(72) Inventors: **Eun-Young Lee**, Yongin-City (KR);
Seok-Hwan Hwang, Yongin-City (KR);
Young-Kook Kim, Yongin-City (KR);
Hye-Jin Jung, Yongin-City (KR);
Jun-Ha Park, Yongin-City (KR);
Jong-Woo Kim, Yongin-City (KR);
Jin-O Lim, Yongin-City (KR);
Sang-Hyun Han, Yongin-City (KR);
Eun-Jae Jeong, Yongin-City (KR);
Soo-Yon Kim, Yongin-City (KR);
Jong-Hyuk Lee, Yongin-City (KR)(73) Assignee: **SAMSUNG DISPLAY CO., LTD.,**
Yongin-City (KR)(21) Appl. No.: **14/072,478**(22) Filed: **Nov. 5, 2013**(30) **Foreign Application Priority Data**

Jul. 1, 2013 (KR) 10-2013-0076597


Publication Classification(51) **Int. Cl.**
H01L 51/00 (2006.01)(52) **U.S. Cl.**
CPC **H01L 51/0073** (2013.01)
USPC **257/40; 549/384**(57) **ABSTRACT**

A compound is represented by Formula 1, 2, or 3, and an organic light-emitting device includes the compound. The organic light-emitting device includes a first electrode, a second electrode, and an organic layer. The organic layer


Formula 1



Formula 2



Formula 3



SECOND ELECTRODE
EIL
ETL
EML
HTL
HIL
FIRST ELECTRODE

FIG. 1

SECOND ELECTRODE
EIL
ETL
EML
HTL
HIL
FIRST ELECTRODE

**COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE INCLUDING THE
SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2013-0076597, filed on Jul. 1, 2013 in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

[0002] 1. Technical Field

[0003] One or more embodiments of the present invention relate to a compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art

[0005] Organic light-emitting devices (OLEDs) are self-emitting devices having advantages such as wide viewing angles, good contrast, quick response speeds, high brightness, and good driving voltage characteristics. Also, OLEDs can provide full color images.

[0006] A typical OLED has a structure including a substrate, and an anode, a hole transport layer, an emission layer, an electron transport layer, and a cathode sequentially stacked on the substrate. The hole transport layer, the emission layer, and the electron transport layer are organic thin films formed of organic compounds.

[0007] A driving principle of an organic light-emitting device having such a structure is as follows. When a voltage is applied between the anode and the cathode, holes injected from the anode pass through the hole transport layer and migrate toward the emission layer, and electrons injected from the cathode pass through the electron transport layer and migrate toward the emission layer. The holes and electrons are recombined with each other in the emission layer to generate excitons. Then, the excitons transition from an excited state to a ground state, thereby generating light.


SUMMARY

[0008] One or more embodiments of the present invention include a material that has good electric characteristics, high charge transporting capabilities, high light-emitting capabilities, a high glass transition temperature, and crystallization-preventing capabilities. The material is suitable for use as a material for a full color (such as red, green, blue, or white) fluorescent or phosphorescent devices. An organic light-emitting device that includes the material has high efficiency, low voltage, high brightness, and a long lifespan.


[0009] Additional aspects will be set forth in part in the description that follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0010] According to one or more embodiments of the present invention, a compound is represented by Formula 1, Formula 2, or Formula 3 below.


Formula 1



Formula 2





Formula 3



[0011] In Formulae 1, 2, and 3:

[0012] R_1^1 to R_1^{16} , R_2^1 to R_2^{18} , and R_3^1 to R_3^{14} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl group, a substituted or unsubstituted C_2 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group; and





at least one of R_1^1 to R_1^{16} , at least one of R_2^1 to R_2^{16} , and at least one of R_3^1 to R_3^{14} may include one or more L. L is, where the definition of R_0 is the same as the definition (above) of R_1^1 to R_1^{16} , R_2^1 to R_2^{18} , and R_3^1 to R_3^{14} .

[0013] According to another aspect of the present invention, an organic light-emitting device includes a first electrode, a second electrode, and an organic layer between the first electrode and the second electrode. The organic layer includes the compound of Formula 1, 2 or 3.

[0014] According to another aspect of the present invention, a flat panel display apparatus includes the organic light-emitting device, and the first electrode of the organic light-emitting device is electrically connected to a source electrode or a drain electrode of a thin film transistor.




BRIEF DESCRIPTION OF THE DRAWINGS

[0015] These and/or other aspects will become apparent and more readily appreciated from the following description of certain embodiments when taken in conjunction with FIG. 1, which is a schematic view of an organic light-emitting device according to an embodiment of the present invention.

DETAILED DESCRIPTION

[0016] Reference will now be made to certain embodiments, examples of which are illustrated in the accompanying drawings. Like reference numerals refer to like elements throughout. It is understood, however, that the disclosed embodiments may be modified in different ways, and therefore should not be construed as limiting the present invention to the described embodiments. Accordingly, the presented embodiments are merely described below, by reference to the FIGURE, to explain certain aspects of the present invention. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.


[0017] According to an aspect of the present invention, a compound is represented by Formula 1, Formula 2, or Formula 3.




[0018] In Formulae 1, 2, and 3:

[0019] R_1^1 - R_1^{16} , R_2^1 - R_2^{18} , and R_3^1 - R_3^{14} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group; and

[0020] at least one of R_1^1 - R_1^{16} , at least one of R_2^1 - R_2^{18} , and at least one of R_3^1 - R_3^{14} may include one or more L. L is





and the definition of R_0 is the same as the definition (above) of R_1^1 - R_1^{16} , R_2^1 - R_2^{18} , and R_3^1 - R_3^{14} .

[0021] Light-emitting devices are self-emission display devices that have wide viewing angles, high contrast ratios, and short response times. Accordingly, light-emitting devices are receiving a lot of attention. Light-emitting devices are categorized into inorganic light-emitting devices (in which the emission layer includes an inorganic compound) and organic light-emitting devices (in which the emission layer includes an organic compound). Also, organic light-emitting devices are capable of displaying full-color images. In general, an organic light-emitting device has an anode/organic emission layer/cathode stacked structure. Additionally, a hole injection layer and/or a hole transport layer and an electron injection layer may be further stacked between the anode and the emission layer or between the emission layer and the cathode. In the latter case, the organic light-emitting device may have an anode/hole transport layer/organic emission layer/cathode structure, or an anode/hole transport layer/organic emission layer/electron transport layer/cathode structure.

[0022] Anthracene derivatives have been used as the material of the organic emission layer. For example, some organic light-emitting devices use a dimer or trimer compound of phenylanthracene. However, devices using this compound include two or three anthracenes linked through a conjugated system, and the organic light-emitting devices therefore have a narrow energy gap and low color purity of blue emission. Also, this compound is highly susceptible to oxidation and thus, impurities may be easily formed, which makes the purification process difficult. These problems may be reduced or overcome by developing an anthracene compound substituted with naphthalene at sites 1 and 9, and a diphenylanthracene compound substituted with an aryl group at the meta position of the phenyl groups. However, organic light-emitting devices using these compounds have low luminescent efficiency.

[0023] Also, organic light-emitting devices have used a naphthalene-substituted mono anthracene derivative. However, the luminescent efficiency of such an OLED is as low as 1 cd/A, and thus, the organic light-emitting device is not practical. Also, organic light-emitting devices have used compounds having a phenylanthracene structure. However, this compound is substituted with an aryl group at the meta position, and therefore, while organic light-emitting devices using this compound may have good heat resistance, they have luminescent efficiency characteristics as low as 2 cd/A.


[0024] A blue emission compound having a central diphenylanthracene structure and a terminal aryl group has been used as blue emission material, and organic light-emitting devices have used such blue emission compounds. However, the luminescent efficiency and brightness of such organic light-emitting devices are not satisfactory. Also, although organic light-emitting devices have used a substituted

pyrene-based compound, the blue color purity of such OLEDs is low, and thus, it is difficult to display deep blue and to achieve a full-color display.


[0025] The compounds represented by Formulae 1, 2, and 3, described above, act as an emission material for an organic light-emitting device. Also, the compounds represented by Formulae 1, 2, and 3 have high glass transition temperatures (T_g) or high melting points, due to the introduction of a hetero ring. Accordingly, the durability under high temperatures, and the heat resistance against Joule's heat (which occurs within an organic layer, between organic layers, or between an organic layer and a metal electrode during emission) increase. An organic light-emitting device manufactured using a compound according to an embodiment of the present invention has high durability during storage and driving.

[0026] According to an embodiment of the present invention, the compound represented by Formula 1 may be represented by one of Formulae 4 to 7 below.


Formula 4



Formula 5




Formula 6



-continued


Formula 7




[0027] In Formulae 4 to 7, R_1^1 to R_1^{16} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group.

[0028] According to an embodiment of the present invention, the compound represented by Formula 2 may be represented by Formula 8 or 9 below.

Formula 8



Formula 9




[0029] In Formulae 8 and 9, R_2^1 to R_2^{18} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl


group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group.

[0030] According to an embodiment of the present invention, the compound represented by Formula 3 may be represented by Formulae 10 or 11 below.

Formula 10



Formula 11



[0031] In Formulae 10 and 11, R_3^1 to R_3^{14} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{80} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group.

[0032] Substituents of the compounds of Formula 1 through Formula 11 will now be described.

[0033] According to an embodiment of the present invention, R_1^1 , R_1^2 , R_1^8 , R_1^9 , R_1^{10} , R_1^{11} , and R_1^{16} of Formula 1, R_2^1 , R_2^2 , R_2^8 , R_2^9 , R_2^{10} , R_2^{11} , R_2^{17} , and R_2^{18} of Formula 2, and R_3^1 , R_3^6 , R_3^7 , R_3^8 , R_3^{13} , and R_3^{14} of Formula 3 may each independently be a hydrogen atom or a deuterium atom.


[0034] According to an embodiment of the present invention, R_1^1 to R_1^{10} , and R_1^{15} of Formulae 4 and 5, and R_1^1 to R_1^4 , R_1^6 to R_1^{11} , and R_1^{15} of Formulae 6 and 7 may each independently be a hydrogen atom or a deuterium atom.

[0035] According to an embodiment of the present invention, R_2^1 to R_2^{10} , R_2^{16} , and R_2^{17} of Formulae 8 and 9 may each independently be a hydrogen atom or a deuterium atom.

[0036] According to an embodiment of the present invention, R_3^1 to R_3^8 , and R_3^{13} of Formulae 10 and 11 may each independently be a hydrogen atom or a deuterium atom.

[0037] According to an embodiment of the present invention, R_1^1 - R_1^{16} , R_2^1 - R_2^{18} , R_3^1 - R_3^{14} , and R_0 of Formulae 1, 2, and 3, R_1^{13} and R_8^{16} of Formulae 4 and 5, R_1^5 and R_1^{16} of

Formulae 6 and 7, R_2^{13} and R_2^{18} of Formulae 8 and 9, and R_3^{11} and R_3^{14} of Formulae 10 and 11 may each independently be a hydrogen atom, a deuterium atom, a cyano group, a trihalomethyl group, or any one of Formulae 2a to 2c below.



[0038] In Formulae 2a through 2c, R_{51} , R_{52} , R_{53} , and Z_1 are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 to C_{20} alkyl group, a substituted or unsubstituted C_6 to C_{20} aryl group, a substituted or unsubstituted C_2 to C_{20} heteroaryl group, a substituted or unsubstituted C_6 to C_{20} condensed polycyclic group, an amino group substituted with a C_6 to C_{20} aryl group or a C_2 to C_{20} heteroaryl group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group. Also, p is an integer of 1 to 5, and * indicates a binding site to one of Formulae 1 through 11.

[0039] Definitions of representative substituents will now be presented. However, it is understood that the number of carbon atoms listed for a particular substituent is not limiting, and therefore does not limit the properties of the substituent. Also, unless defined otherwise, the definitions of the substituents are consistent with the general definitions of those terms, as would be understood by those of ordinary skill in the art.

[0040] As used herein, the unsubstituted C_1 to C_{60} alkyl group may be a linear or branched alkyl group. Non-limiting examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a pentyl group, an iso-amyl group, a hexyl group, a heptyl group, an octyl group, a nonanyl group, and a dodecyl group. The substituted C_1 to C_{60} alkyl group refers to the substitution of at least one hydrogen atom of the alkyl group with a deuterium atom, a halogen atom, a hydroxyl group, a nitro group, a cyano group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group or salt thereof, a sulfonic acid group or salt thereof, a phosphoric acid group or salt thereof, a C_1 to C_{10} alkyl group, a C_1 to C_{10} alkoxy group, a C_2 to C_{10} alkenyl group, a C_2 to C_{10} alkynyl group, a C_6 to C_{16} aryl group, or a C_2 to C_{16} heteroaryl group.

[0041] As used herein, the unsubstituted C_2 to C_{60} alkenyl group refers to an unsubstituted alkyl group having one or more carbon-carbon double bonds at the center or a terminal end. Non-limiting examples thereof include ethenyl, propenyl, and butenyl. The substituted C_2 to C_{60} alkenyl group refers to the substitution of at least one hydrogen atom of the unsubstituted alkenyl group with the substituents described above in connection with the substituted alkyl group.

[0042] As used herein, the unsubstituted C_2 to C_{60} alkynyl group refers to an unsubstituted alkyl group having one or more carbon-carbon triple bonds at the center or terminal end.

Non-limiting examples thereof include acetylene, propylene, phenylacetylene, naphthylacetylene, isopropylacetylene, t-butylacetylene, and diphenylacetylene. The substituted C_2 to C_{60} alkynyl group refers to the substitution of at least one hydrogen atom of the unsubstituted alkynyl group with the substituents described above in connection with the substituted alkyl group.

[0043] As used herein, the unsubstituted C_3 to C_{60} cycloalkyl group refers to a C_3 to C_{60} cyclic alkyl group. The substituted C_3 to C_{60} cycloalkyl group refers to the substitution of at least one hydrogen atom of the cycloalkyl group with the substituents described above in connection with the C_1 to C_{60} alkyl group.

[0044] As used herein, the unsubstituted C_1 to C_{60} alkoxy group refers to a group represented by —OA where A is the unsubstituted C_1 to C_{60} alkyl group. Non-limiting examples thereof include ethoxy, ethoxy, isopropoxy, butoxy, and pentoxy. The substituted C_1 to C_{60} alkoxy group refers to the substitution of at least one hydrogen atom of the unsubstituted alkoxy group with the substituents described above in connection with the alkyl group.

[0045] As used herein, the unsubstituted C_6 to C_{60} aryl group refers to a carbocyclic aromatic system having at least one aromatic ring. When the number of rings is two or more, the rings may be fused to each other or may be linked to each other via, for example, a single bond. The term 'aryl' includes aromatic systems, such as phenyl, naphthyl, or anthracenyl. The substituted C_6 to C_{60} aryl group refers to the substitution of at least one hydrogen atom of the aryl group with the substituents described above in connection with the C_1 to C_{60} alkyl group.

[0046] Non-limiting examples of a substituted or unsubstituted C_6 to C_{60} aryl group include a phenyl group, a C_1 to C_{10} alkylphenyl group (for example, an ethylphenyl group), a biphenyl group, a C_1 to C_{10} alkylbiphenyl group, a C_1 to C_{10} alkoxybiphenyl group, o-, m-, and p-tolyl groups, o-, m- and p-cumenyl groups, a mesityl group, a phenoxyphenyl group, a (α,α -dimethylbenzene)phenyl group, a (N,N'-dimethyl)aminophenyl group, a (N,N'-diphenyl)aminophenyl group, a pentalenyl group, an indenyl group, a naphthyl group, a C_1 to C_{10} alkyl-naphthyl group (for example, methyl-naphthyl group), a C_1 to C_{10} alkoxy-naphthyl group (for example, methoxy-naphthyl group), an anthracenyl group, an azulenenyl group, a heptalenyl group, an acenaphthalenyl group, a phenalenyl group, a fluorenyl group, an anthraquinolenyl group, a methylanthryl group, a phenanthryl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, an ethyl-chrysenyl group, a picenyl group, a perylenyl group, a chloroperilenyl group, a pentaphenyl group, a pentacenyl group, a tetraphenylenyl group, a hexaphenyl group, a hexacenyl group, a rubicenyl group, a coronenyl group, trinaphthalenyl group, a heptaphenyl group, a heptacenyl group, a pyranthrenyl group, and an ovalenyl group.

[0047] As used herein, the unsubstituted C_1 - C_{60} heteroaryl group refers to an aryl group (as defined above) that includes at least one ring hetero atom, such as nitrogen (N), oxygen (O), phosphorous (P), or sulfur (S). When the heteroaryl group has two or more rings, the rings may be fused to each other or may be linked to each other via, for example, a single bond. Non-limiting examples of the unsubstituted C_1 - C_{60} heteroaryl group include a pyrazolyl group, an imidazolyl

group, a oxazolyl group, a thiazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridinyl group, a pyridazinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, an indolyl group, a quinolinyl group, an isoquinolinyl group, and a dibenzothiophenyl group. The substituted C_1 - C_{60} heteroaryl group refers to the substitution of at least one hydrogen atom of the heteroaryl group with the substituents described above in connection with the C_1 to C_{60} alkyl group.


[0048] As used herein, the unsubstituted C_6 to C_{60} aryloxy group refers to a group represented by $-OA_1$, where A_1 is the C_6 to C_{60} aryl group. A non-limiting example of the aryloxy group is a phenoxy group. The substituted C_6 to C_{60} aryloxy group refers to the substitution of at least one hydrogen atom of the aryloxy group with the substituents described above in connection with the C_1 to C_{60} alkyl group.

[0049] As used herein, the C_6 to C_{60} unsubstituted arylthio group refers to a group represented by $-SA_1$, where A_1 is the C_6 to C_{60} aryl group. Non-limiting examples of the arylthio group include a benzenethio group and a naphthylthio group. The substituted arylthio group refers to the substitution of at least one hydrogen atom of the arylthio group with the substituents described above in connection with the C_1 to C_{60} alkyl group.


[0050] As used herein, the unsubstituted C_6 to C_{60} condensed polycyclic group refers to a substituent having two or more rings formed by fusing at least one aromatic ring and/or at least one non-aromatic ring, or to a substituent in which an unsaturated group is present in a ring but that is not a conjugated system. The condensed polycyclic group does not have overall aromaticity, which is how the condensed polycyclic group is distinguished from the aryl group or the heteroaryl group.

[0051] Non-limiting examples of compounds represented by Formula 1, Formula 2, and Formula 3 include Compounds 1-66 below.


-continued




3




4




5




6




1



2




7




8

-continued


9




10




11




12



13




14




-continued


15




16




17




18




19



20




-continued




21


22




23




24




25




26



-continued




27




28


29




30



31




32




-continued


33




34




35




36



37




38




-continued


39




40




41




42



43




44




-continued


45




46




47




48



49




50




-continued


51




52




53




54



55




56




-continued


57




58




59




60



61




62




-continued


63




64



65



66



[0052] An organic light-emitting device according to an embodiment of the present invention includes a first electrode, a second electrode, and an organic layer between the first electrode and the second electrode. The organic layer includes the compound represented by any one of Formulae 1-9, discussed above.

[0053] The organic layer may include at least one of a hole injection layer, a hole transport layer, a functional layer having a hole injection function and a hole transport function (hereinafter referred to as an "H-functional layer"), a buffer layer, an electron blocking layer, an emission layer, a hole blocking layer, an electron transport layer, an electron injection layer, and/or a functional layer having an electron transport function and an electron injection function (hereinafter referred to as an "E-functional layer").

[0054] For example, the organic layer may be an emission layer, an electron injection layer, an electron transport layer, and/or a functional layer having electron injection capability and electron transportation capability. For example, the organic layer may be a blue emission layer or an electron injection layer.

[0055] According to an embodiment of the present invention, the organic layer may further include an electron injection layer, an electron transport layer, a functional layer having electron injection capability and electron transportation

capability, an emission layer, a hole injection layer, a hole transport layer, or a functional layer having hole injection capability and hole transportation capability. The emission layer may include an anthracene-based compound, an arylamine-based compound, or a styryl-based compound.

[0056] According to another embodiment of the present invention, the organic layer may include an electron injection layer, an electron transport layer, a functional layer having electron injection capability and electron transportation capability, an emission layer, a hole injection layer, a hole transport layer, or a functional layer having hole injection capability and hole transportation capability. The emission layer may include a red layer, a green layer, a blue layer, and a white layer, and any one of these layers may include a phosphorescent compound. The hole injection layer, the hole transport layer, or the functional layer having hole injection capability and hole transportation capability may include a charge-generation material. The charge-generation material may be a p-dopant, and the p-dopant may be a quinone derivative, a metal oxide, or a cyano group-containing compound.

[0057] According to another embodiment of the present invention, the organic layer may include an electron transport layer that includes an electron-transportable organic compound and a metal complex. The metal complex may be a Li complex.

[0058] The term “organic layer,” as used herein, refers to a single layer and/or a plurality of layers between the first electrode and the second electrode of an organic light-emitting device.

[0059] The organic layer includes an emission layer, and the emission layer may include the compound represented by Formula 1. The organic layer may include at least one additional layer, such as, for example, a hole injection layer, a hole transport layer, or a H-functional layer. The at least one additional layer (e.g., a hole injection layer, a hole transport layer, or a H-functional layer) may include the compound.

[0060] FIG. 1 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment of the present invention. The structure of an organic light-emitting device according to an embodiment of the present invention, and a method of manufacturing the organic light-emitting device according to an embodiment of the present invention, will be described with reference to FIG. 1.

[0061] A substrate (not shown) of the OLED may be any one of various substrates commonly used in organic light-emitting devices, and may be, for example, a glass substrate or a transparent plastic substrate with mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0062] A first electrode may be formed on the substrate by depositing or sputtering a first electrode material on the substrate. When the first electrode is an anode, the first electrode material may be selected from materials having a high work function to facilitate easy hole injection. The first electrode may be a reflective electrode or a transmission (i.e., transparent) electrode. The first electrode material may be a transparent material with high conductivity, non-limiting examples of which include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), and zinc oxide (ZnO). According to an embodiment of the present invention, the first electrode may be formed as a reflective electrode using magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag).


[0063] The first electrode may be a single- or multi-layered structure. For example, the first electrode may have a three-layered structure, e.g., ITO/Ag/ITO, but the structure of the first electrode is not limited thereto.

[0064] An organic layer is disposed on the first electrode. The organic layer may include a hole injection layer, a hole transport layer, a buffer layer (not shown), an emission layer, an electron transport layer, or an electron injection layer.



[0065] The hole injection layer (HIL) may be formed on the first electrode by various methods, such as vacuum deposition, spin coating, casting, LB deposition, or the like. When the HIL is formed by vacuum deposition, the deposition conditions may vary according to the material that is used to form the HIL, and the desired structural and thermal characteristics of the HIL. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10^{-8} to about 10^{-3} torr, and a deposition rate of about 0.01 to about 100 Å/sec. However, the deposition conditions are not limited thereto.

[0066] When the HIL is formed using spin coating, the coating conditions may vary according to the material used to form the HIL, and the desired structural and thermal properties of the HIL. For example, the coating speed may be about 2000 rpm to about 5000 rpm, and the temperature at which heat treatment is performed to remove solvent after coating may be about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

[0067] The hole injection material may be any suitable hole injection material, non-limiting examples of which include N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine (DNTPD), a phthalocyanine compound such as copper phthalocyanine, 4,4',4''-tris(3-methylphenylphenylamino)triphenylamine (m-MTDATA), N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB), TDATA, 2-TNATA, a polyaniline/dodecylbenzenesulfonic acid (pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (pani/CSA), and (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS).



m-MTDATA





[0068] The thickness of the HIL may be about 100 Å to about 10,000 Å, for example, about 100 Å to about 1000 Å. When the thickness of the HIL is within either of these ranges, the HIL may have satisfactory hole injection characteristics without a substantial increase in a driving voltage.

[0069] Then, a hole transport layer (HTL) may be formed on the HIL by vacuum deposition, spin coating, casting,

Langmuir-Blodgett (LB) deposition, or the like. When the HTL is formed using vacuum deposition or spin coating, the deposition or coating conditions may be similar to those used to form the HIL, though the conditions for deposition and coating may vary according to the material that is used to form the HTL.

[0070] The hole-transportation material may be any suitable hole transport material, non-limiting examples of which include a carbazole derivative, such as N-phenylcarbazole or polyvinylcarbazole, N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (TPD), 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), and N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB).




[0071] The thickness of the HTL may be about 50 Å to about 2,000 Å, for example, about 100 Å to about 1,500 Å. When the thickness of the HTL is within either of these ranges, the HTL may have satisfactory hole transportation properties without a substantial increase in a driving voltage.


[0072] An H-functional layer (i.e., a functional layer having a hole injection capability and a hole transport capability) may include one or more HIL materials and HTL materials. The thickness of the H-functional layer may be about 500 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the thickness of the H-functional layer is within either of these ranges, satisfactory hole injection and transportation properties may be obtained without a substantial increase in driving voltage.

[0073] In addition, at least one of the HIL, the HTL, and the H-functional layer may include at least one of a compound represented by Formula 300 and a compound represented by Formula 350.

Formula 300



Formula 350



[0074] In Formulae 300 and 350, Ar₁₁, Ar₁₂, Ar₂₁, and Ar₂₂ are each independently a substituted or unsubstituted C₅-C₆₀ arylene group.

[0075] e and f in Formula 300 may each independently be an integer of 0 to 5, or 0, 1 or 2. For example, e may be 1 and f may be 0, but e and f are not limited thereto.


[0076] R₅₁ to R₅₈, R₆₁ to R₆₉, and R₇₁ and R₇₂ in Formulae 300 and 350 may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₅-C₆₀ aryl group, a substituted or unsubstituted C₅-C₆₀ aryloxy group, or a substituted or unsubstituted C₅-C₆₀ arylthio group. For example, R₅₁ to R₅₈, R₆₁ to R₆₉, R₇₁ and R₇₂ may each independently be a hydrogen atom; a deuterium atom; a halogen atom; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; a hydrazine group; a hydrazone group; a carboxyl group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid group or a salt thereof; a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl

group, or the like); a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, or the like); a C₁-C₁₀ alkyl group or a C₁-C₁₀ alkoxy group substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, or a phosphoric acid group or a salt thereof; a phenyl group; a naphthyl group; an anthryl group; a fluorenyl group; a pyrenyl group; or a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, or a pyrenyl group substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, or a C₁-C₁₀ alkoxy group. However, R₅₁ to R₅₈, R₆₁ to R₆₉, R₇₁ and R₇₂ are not limited thereto.

[0077] R₅₉ in Formula 300 may be a phenyl group; a naphthyl group; an anthryl group; a biphenyl group; or a pyridyl group; or a phenyl group, a naphthyl group, an anthryl group, a biphenyl group, or a pyridyl group substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₂₀ alkyl group, or a substituted or unsubstituted C₁-C₂₀ alkoxy group.

[0078] According to an embodiment of the present invention, the compound represented by Formula 300 may be represented by Formula 300A, but the chemical structure of the compound is not limited thereto.









Formula 300A



[0079] In Formula 300A, R₅₁, R₆₁, R₆₂, and R₅₉ are described above with respect to Formula 300.


[0080] In some exemplary embodiments, at least one of the HIL, the HTL, and the H-functional layer may include at least one of Compounds 301 to 320 below, but the HIL, HTL and H-functional layer are not limited thereto, and may include other materials.

-continued




-continued

309




-continued


311



310




312




-continued

313




-continued


315



314




316




-continued

317





-continued

319




320

318




[0081] To increase conductivity of the layer, at least one of the HIL, the HTL, and the H-functional layer may further include a charge-generation material in addition to the hole injecting materials, hole transport materials, and/or materials having both hole injection and hole transport capabilities.


[0082] The charge-generation material may be, for example, a p-dopant. The p-dopant may be one of a quinone derivative, a metal oxide, or a cyano group-containing compound, but is not limited thereto. Non-limiting examples of the p-dopant include a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) and 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ), or the like; a metal oxide, such as a tungsten oxide or a molybdenum oxide; and a cyano group-containing compound, such as Compound 200.




Compound 200




TPBI




TBADN



E3



PVK



ADN

[0083] When the HIL, the HTL or the H-functional layer further includes the charge-generation material, the charge-generation material may be homogeneously dispersed or non-homogeneously distributed in the HIL, the HTL, or the H-functional layer.


[0084] A buffer layer may be disposed between the emission layer and at least one of the HIL, the HTL, and the H-functional layer. The buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer. As such, the efficiency of a resulting organic light-emitting device may be improved. The buffer layer may include a hole injection material and a hole transportation material. Also, the buffer layer may include a material that is the same as the material included in the hole injection layer, the hole transport layer, or the H-functional layer beneath the buffer layer.

[0085] Subsequently, an emission layer (EML) may be formed on the hole transport layer, the H-functional layer, or the buffer layer by vacuum deposition, spin coating, casting, LB deposition, etc. If the EML is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those used to form the HIL, although the deposition or coating conditions may vary according to the material that is used to form the EML.


[0086] The EML may include the compound according to an embodiment of the present invention, or various hosts and dopants. The dopant for use in the EML may be a fluorescent dopant or a phosphorescent dopant.

[0087] Non-limiting examples of suitable hosts include Alq₃, 4,4'-N,N'-dicarbazole-biphenyl (CBP), poly(n-vinylcarbazole)(PVK), 9,10-di(naphthalene-2-yl)anthracene (ADN), TCTA, 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di(naphth-2-yl) anthracene (TBADN), E3, distyrylarylene (DSA), dmCBP (see the following chemical structure), Compounds 501 to 509 illustrated below, or the like. However, other materials may also be used as the host.


-continued




CBP




dmCBP



501




502




503


-continued



504




505



506

-continued



507

508


509

unsubstituted C_1 - C_{10} alkyl group, or a substituted or unsubstituted C_5 - C_{60} aryl group. Also, g, h, l, and j are each independently an integer of 0 to 4.

[0090] For example, Ar_{111} and Ar_{112} in Formula 400 may each independently be a phenylene group, a naphthalene group, a phenanthrenyl group, or a pyrenylene group; or a phenylene group, a naphthalene group, a phenanthrenyl group, a fluorenyl group, or a pyrenylene group substituted with at least one of a phenyl group, a naphthyl group, or an anthryl group. However, Ar_{111} and Ar_{112} are not limited thereto.

[0091] g, h, i, and j in Formula 400 may each independently be 0, 1, or 2.


[0092] Ar_{113} to Ar_{116} in Formula 400 may each independently be a C_1 - C_{10} alkyl group substituted with at least one of a phenyl group, a naphthyl group, or an anthryl group; a phenyl group; a naphthyl group; an anthryl group; a pyrenyl group; a phenanthrenyl group; a fluorenyl group; or a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, a phenanthrenyl group, or a fluorenyl group substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxyl group or salt thereof, a sulfonic acid group or salt thereof, a phosphoric acid group or salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, pyrenyl group, a phenanthrenyl group, a fluorenyl group, or




However, Ar_{113} to Ar_{116} are not limited thereto.

[0093] For example, the anthracene-based compound represented by Formula 400 may be one of the following compounds, but is not limited thereto.

[0088] Also, the host may be an anthracene-based compound represented by Formula 400 below.




Formula 400




[0089] In Formula 400, Ar_{111} and Ar_{112} may each independently be a substituted or unsubstituted C_5 - C_{60} arylene group. Ar_{113} to Ar_{116} may each independently be a substituted or


-continued











-continued






-continued




-continued








[0098] For example, the anthracene-based compound represented by Formula 401 may be one of the following compounds, but is not limited thereto.



[0094] Also, the host may be an anthracene-based compound represented by Formula 401 below.


Formula 401




[0095] Ar_{122} to Ar_{125} in Formula 401 are the same as Ar_{113} in Formula 400, and the description of Ar_{113} in Formula 400 is fully incorporated here.

[0096] Ar_{126} and Ar_{127} in Formula 401 may each independently be a C_1 - C_{10} alkyl group (for example, a methyl group, an ethyl group, or a propyl group).

[0097] k and l in Formula 401 may each independently be an integer of 0 to 4. For example, k and l may be 0, 1, or 2.





-continued







[0099] When the organic light-emitting device is a full color organic light-emitting device, the EML may be patterned into a red EML, a green EML, and a blue EML. The red EML, green EML, and blue EML may include the following dopants (ppy=phenylpyridine).






[0100] Non-limiting examples of suitable blue dopants include the following compounds.




(F2ppy)2Ir(tmd)




-continued



DPVBi













DPAVB



TBPe








[0101] Non-limiting examples of suitable red dopants include the following compounds.










[0102] Non-limiting examples of suitable green dopants include the following compounds.






[0103] The dopant in the EML may also be a Pd-complex or a Pt-complex, but the dopant is not limited thereto. Non-limiting examples of suitable Pd-complexes and Pt-complexes include the following compounds.



-continued



-continued



D5

D10

D6

D11

D7

D12


D8

D13


D9

D14


-continued




D15




D16



D17




D18




D19


-continued




D20




D21



D22









D23




D24

-continued




-continued

D25




D31

D26




D32

D27




D33

D28




D34

D29



D35


D30



D36


-continued

D37




-continued


D41




D42




D43




D44




D45




D38




D39




D40




-continued




D46




D47







D48




D49



D50

 $\text{Os}(\text{fppz})_2(\text{CO})_2$  $\text{Os}(\text{fppz})_2(\text{PPh}_2\text{Me})_2$  $\text{Os}(\text{bppz})_2(\text{PPh}_3)_2$  $\text{Os}(\text{fptz})_2(\text{PPh}_2\text{Me})_2$

[0104] The dopant in the EML may also be an Os-complex, but the dopant is not limited thereto. Non-limiting examples of suitable Os-complexes include the following compounds.








[0105] When the EML includes a host and a dopant, the amount of the dopant may be about 0.01 to about 15 parts by weight based on about 100 parts by weight of the host. However, the amount of the dopant is not limited thereto.

[0106] The thickness of the EML may be about 100 Å to about 10,000 Å, for example, about 200 Å to about 600 Å. If the thickness of the EML is within either of these ranges, good luminescent characteristics may be obtained without a substantial increase in driving voltage.

[0107] Next, an electron transport layer (ETL) is formed on the EML by various methods, for example, by vacuum deposition, spin coating, casting, or the like. When the ETL is formed using vacuum deposition or spin coating, the deposition or coating conditions may be similar to those used to form the HIL, though the conditions for deposition or coating may vary according to the material that is used to form the ETL.


[0108] Any material capable of stably transporting electrons injected from an electron injection electrode (cathode) may be used as the material for the ETL. Non-limiting examples of suitable electron transportation materials include a quinoline derivative, such as tris(8-hydroxyquinolino) aluminum (Alq3), TAZ, Balq, beryllium bis(benzoquinolin-10-olate) (Bebq2), ADN, Compound 201, or Compound 202.



[0109] The thickness of the ETL may be about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the ETL is within either of these

ranges, the ETL may have satisfactory electron transportation characteristics without a substantial increase in driving voltage.

[0110] In addition to an electron transporting organic compound, the ETL may further include a metal-containing material. The metal-containing material may include a lithium (Li) complex. Non-limiting examples of the Li complex include lithium quinolate (LiQ) and Compound 203.



Compound 203

[0111] Then, an electron injection layer (EIL), which facilitates injection of electrons from the cathode, may be formed on the ETL. Any suitable electron-injecting material may be used to form the EIL. Non-limiting examples of suitable EIL materials include LiF, NaCl, CsF, Li₂O, and BaO. The deposition conditions of the EIL may be similar to those used to form the HIL, although the deposition conditions may vary according to the material that is used to form the EIL.


[0112] The thickness of the EIL may be about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the EIL is within either of these ranges, the EIL may have satisfactory electron transportation characteristics without a substantial increase in a driving voltage.

[0113] The second electrode may be disposed on the organic layer. The second electrode may be a cathode, which is an electron injection electrode. The second electrode material may be a low work function material, such as a metal, an alloy, an electrically conductive compound, or a mixture thereof. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), etc. may be used to form a thin film transmissive electrode. In some embodiments, a top-emission light-emitting device may be made using indium tin oxide (ITO) or indium zinc oxide (IZO) to form a transmissive electrode.

[0114] Although the organic light-emitting device has been described with reference to FIG. 1, the OLED is not limited thereto.

[0115] Also, when the EML includes a phosphorescent dopant, to prevent diffusion of triplet excitons or holes into the ETL a hole blocking layer (HBL) may be formed between the ETL and the EML or between the E-functional layer and the EML by vacuum deposition, spin coating, casting, LB deposition, etc. When the HBL is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those used to form the HIL, although the deposition or coating conditions may vary according to the material that is used to form the HBL. The hole blocking material may be any suitable hole blocking material, non-limiting examples of which include an oxadiazole derivative, a triaz-

ole derivative, a phenanthroline derivative, etc. For example, BCP (illustrated below) may be used as the hole blocking material.



BCP

[0116] The thickness of the HBL may be about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. If the thickness of the HBL is within either of these ranges, good hole blocking properties may be obtained without a substantial increase in driving voltage.

[0117] An organic light-emitting device according to an embodiment of the present invention may be used in various flat panel display apparatuses, such as passive matrix organic light-emitting display apparatuses or active matrix organic light-emitting display apparatuses. In particular, when the organic light-emitting device is included in an active matrix organic light-emitting display apparatus, the first electrode (disposed on the substrate) functions as a pixel and may be electrically connected to a source electrode or a drain electrode of a thin film transistor. In addition, the organic light-emitting device may be included in a flat panel display apparatus that emits light in opposing directions.

[0118] The organic layer of an organic light-emitting device according to an embodiment of the present invention may be formed by depositing a compound according to an embodiment of the present invention, or by coating a solution including the compound according to an embodiment of the present invention. The latter method is referred to as a wet method.


[0119] Hereinafter, one or more embodiments of the present invention will be described with reference to the following examples. These examples are presented for illustrative purposes only, and do not limit the purpose and scope of the one or more embodiments of the present invention.


EXAMPLES

Synthesis Example 1

Synthesis of Compound 1

[0120]





Synthesis of Intermediate I-1

[0121] 3.13 g (10 mmol) of 2-bromo-1-iodo-4-methoxybenzene, 1.58 g (11 mmol) of 1-naphthol, 0.112 g (0.5 mmol) of palladium acetate, 0.651 g (2.0 mmol) of triphenylphosphine, and 13 g (40 mmol) of cesium carbonate were dissolved in 60 mL of dimethylformamide (DMF), and then, the mixture was stirred at a temperature of 140°C . for 24 hours. The reaction solution was cooled to room temperature, and then, 60 mL of water was added thereto, and an extraction process was performed three times using 60 mL of ethylether. The collected organic layer was dried using magnesium sulfate, and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.64 g (yield 66%) of Intermediate I-1. The obtained compound was identified by MS/FAB. $\text{C}_{17}\text{H}_{12}\text{O}_2$; calc. 248.08. found 248.10

Synthesis of Intermediate I-2

[0122] 1.64 g (6.6 mmol) of Intermediate I-1 was dissolved in 60 mL of methylene chloride (MC), and then, 0.93 mL (9.9 mmol) of BBr_3 was slowly added dropwise thereto at a temperature of -78°C . The reaction solution was heated to room temperature and then stirred for 24 hours at room temperature. When the reaction was completed, 15 mL of MeOH and 30 mL of H_2O were added thereto, and an extraction process

was performed three times using 30 mL of MC. The collected organic layer was dried using magnesium sulfate, and then the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.41 g (yield 91%) of Intermediate I-2. The obtained compound was identified by MS/FAB. $\text{C}_{16}\text{H}_{10}\text{O}_2$; calc. 234.07. found 234.11

Synthesis of Intermediate I-3

[0123] 1.41 g (6.0 mmol) of Intermediate I-2 was dissolved in 20 mL of toluene and 20 mL of 30% potassium phosphate, and then, at a temperature of 0°C ., 2.03 g (7.2 mmol) of trifluoromethanesulfonic acid anhydride was slowly added dropwise thereto. The reaction solution was heated to room temperature, and then stirred for 3 hours. Then, 30 mL of water was added thereto, and an extraction process was performed three times using 30 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.63 g (yield 81%) of Intermediate I-1. The obtained compound was identified by MS/FAB. $\text{C}_{17}\text{H}_9\text{F}_3\text{O}_4\text{S}$; calc. 336.02. found 336.0

Synthesis of Compound 1

[0124] 1.63 g (4.4 mmol) of Intermediate I-3, 1.89 g (4.4 mmol) of Intermediate I-4, 0.25 g (0.22 mmol) of tetrakis (triphenylphosphine)palladium ($\text{Pd}(\text{PPh}_3)_4$), and 1.40 g (6.6 mmol) of potassium phosphate were dissolved in 50 mL of THF solution, and then, at a temperature of 70°C ., the mixture was stirred for 6 hours. The reaction solution was cooled to room temperature, and then, 40 mL of water was added thereto. Then, an extraction process was performed three times using 40 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.95 g (yield 85%) of Compound 1. The obtained compound was identified by MS/FAB. $\text{C}_{40}\text{H}_{24}\text{O}$; calc. 520.18. found 520.21

Synthesis Example 2


Synthesis of Compound 5


[0125] 1.88 g (yield 82%) of Compound 5 was obtained as in the synthesis of Compound 1, except that 2-bromiodobenzene was used instead of 2-bromo-1-iodo-4-methoxybenzene, and 4-methoxy-1-naphthol was used instead of 1-naphthol. The obtained compound was identified by MS/FAB. $\text{C}_{40}\text{H}_{24}\text{O}$; calc. 520.18. found 520.20

Synthesis Example 3

Synthesis of Compound 12

[0126]





Synthesis of Intermediate I-5

[0127] 3.17 g (10 mmol) of 2-bromo-4-chloro-1-iodobenzene, 1.92 g (11 mmol) of 5-methoxy-1-naphthol, 0.112 g (0.5 mmol) of palladium acetate, 0.651 g (2.0 mmol) of triphenylphosphine, and 13 g (40 mmol) of cesium carbonate were dissolved in 60 mL of DMF, and then the mixture was stirred at a temperature of 140° C. for 24 hours. The reaction solution was cooled to room temperature, and then 60 mL of water was added thereto. Then, an extraction process was performed three times using 60 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.64 g (yield 58%) of Intermediate I-5. The obtained compound was identified by MS/FAB. $C_{17}H_{11}ClO_2$: calc. 282.04. found 282.01

Synthesis of Intermediate I-6

[0128] 1.64 g (5.8 mmol) of Intermediate I-5 was dissolved in 60 mL of MC, and then, at a temperature of -78° C., 0.82

mL (8.7 mmol) of BBr_3 was slowly added dropwise thereto. The reaction solution was heated to room temperature and then stirred for 24 hours at room temperature. When the reaction was completed, 15 mL of MeOH and 30 mL of H_2O were added thereto, and then an extraction process was performed three times using 30 mL of MC. The collected organic layer was dried using magnesium sulfate, and then the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.43 g (yield 92%) of Intermediate I-6. The obtained compound was identified by MS/FAB. $C_{16}H_9ClO_2$: calc. 268.03. found 268.01

Synthesis of Intermediate I-7

[0129] 1.43 g (5.3 mmol) of Intermediate I-6 was dissolved in 20 mL of toluene and 20 mL of 30% potassium phosphate, and then, at a temperature of 0° C., 1.79 g (6.4 mmol) of trifluoromethanesulfonic acid anhydride was slowly added dropwise thereto. The reaction solution was heated to room temperature, and then stirred for 3 hours. Then, 30 mL of water was added thereto, and an extraction process was performed three times using 30 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.70 g (yield 80%) of Intermediate I-7. The obtained compound was identified by MS/FAB. $C_{17}H_8ClF_3O_4S$: calc. 399.98. found 400.01

Synthesis of Intermediate I-8

[0130] 1.70 g (4.2 mmol) of Intermediate I-7, 4.7 mg (0.021 mmol) of palladium acetate, 0.39 g (0.92 mmol) of $K_4[Fe(CN)_6] \cdot 3 H_2O$, and 0.58 g (4.2 mmol) of potassium carbonate were dissolved in 20 mL of $H_2O/1,4$ -dioxane (1:1). Then, at a temperature of 140° C., the mixture was stirred for 10 hours. The reaction solution was cooled to room temperature, and then extracted three times with 30 mL of water and 30 mL of diethylether. The collected organic layer was dried using magnesium sulfate, and then the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 0.96 g (yield 82%) of Intermediate I-8. The obtained compound was identified by MS/FAB. $C_{17}H_8ClNO$: calc. 277.03. found 277.01


Synthesis of Compound 12

[0131] 0.96 g (3.4 mmol) of Intermediate I-8, 1.46 g (3.4 mmol) of Intermediate I-4, 0.046 g (0.05 mmol) of $Pd_2(dba)_3$, 0.02 g (0.1 mmol) of $PtBu_3$, and 1.66 g (5.1 mmol) of cesium carbonate were dissolved in 30 mL of a 1,4-dioxane solution. Then, at a temperature of 90° C., the mixture was stirred for 20 hours. The reaction solution was cooled to room temperature, and then 40 mL of water was added thereto. Then, an extraction process was performed three times using 40 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.54 g (yield 83%) of Compound 12. The obtained compound was identified by MS/FAB. $C_{41}H_{23}NO$: calc. 545.18. found 545.20

Synthesis Example 4

Synthesis of Compound 15

[0132]







I-9

[0133] 2.28 g (yield 82%) of Compound 15 was obtained as in the synthesis of Compound 1, except that 1-bromo-2-iodo-4-methoxybenzene was used instead of 2-bromo-1-iodo-4-methoxybenzene, and Intermediate I-9 was used instead of Intermediate I-4. The obtained compound was identified by MS/FAB. $C_{46}H_{28}O$: calc. 596.21, found 596.18

Synthesis Example 5

Synthesis of Compound 59

[0134]



59

Synthesis of Intermediate I-10

[0135] 1.70 g (4.2 mmol) of Intermediate I-5, 19 mg (0.084 mmol) of palladium acetate, 60 mg (0.13 mmol) of Xphos, 0.44 g (1.05 mmol) of $K_4[Fe(CN)_6] \cdot 3H_2O$, and 0.58 g (4.2 mmol) of potassium carbonate were dissolved in 20 mL of $H_2O/1,4$ -dioxane (1:1). Then, at a temperature of 120° C., the mixture was stirred for 10 hours. The reaction solution was cooled to room temperature, and then extracted three times with 30 mL of water and 30 mL of diethylether. The collected organic layer was dried using magnesium sulfate, and then the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 0.99 g (yield 86%) of Intermediate I-10. The obtained compound was identified by MS/FAB. $C_{18}H_{11}NO_2$: calc. 273.08. found 273.11

Synthesis of Intermediate I-11

[0136] 0.99 g (3.6 mmol) of Intermediate I-10 was dissolved in 20 mL of MC, and then, at a temperature of -78° C., 0.51 mL (5.4 mmol) of BBr_3 was slowly added dropwise thereto. The reaction solution was heated to room temperature and then stirred for 24 hours at room temperature. When the reaction was completed, 10 mL of MeOH and 20 mL of H_2O were added thereto, and then an extraction process was performed three times using 20 mL of MC. The collected organic layer was dried using magnesium sulfate, and then the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 0.87 g (yield 93%) of Intermediate I-11. The obtained compound was identified by MS/FAB. $C_{17}H_9NO_2$: calc. 259.06. found 259.10

Synthesis of Intermediate I-12

[0137] 0.87 g (3.3 mmol) of Intermediate I-6 was dissolved in 10 mL of toluene and 10 mL of 30% potassium phosphate, and then, at a temperature of 0° C., 1.09 g (3.9 mmol) of

trifluoromethanesulfonic acid anhydride was slowly added dropwise thereto. The reaction solution was heated to room temperature, and then stirred for 3 hours. Then, 20 mL of water was added thereto, and an extraction process was performed three times using 20 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.06 g (yield 82%) of Intermediate I-12. The obtained compound was identified by MS/FAB. $C_{18}H_8F_3NO_4S$: calc. 391.01. found 391.05

Synthesis of Compound 59

[0138] 1.06 g (2.7 mmol) of Intermediate I-12, 1.37 g (2.7 mmol) of Intermediate I-13, 0.16 g (0.14 mmol) of tetrakis (triphenylphosphine)palladium ($Pd(PPh_3)_4$), and 0.87 g (4.1 mmol) of potassium phosphate were dissolved in 40 mL of a THF solution. Then, at a temperature of 70° C., the mixture was stirred for 6 hours. The reaction solution was cooled to room temperature, and then 30 mL of water was added thereto. Then, an extraction process was performed three times using 30 mL of ethylether. The collected organic layer was dried using magnesium sulfate and the residue obtained by evaporating the solvent was separation-purified by silica gel column chromatography to obtain 1.04 g (yield 82%) of Compound 59. The obtained compound was identified by MS/FAB. $C_{40}H_{24}O$: calc. 621.21. found 621.24

[0139] Additional compounds were synthesized using analogous synthesis methods to those described above, and appropriate intermediate materials. 1H NMR and MS/FAB results of the synthetic compounds are shown in Table 1 below.

[0140] Also, methods for synthesizing compounds other than the compounds shown in Table 1 would be determinable by those of ordinary skill in the art by reference to the synthesis paths and source materials described above.

TABLE 1

Compound	1H NMR ($CDCl_3$, 400 MHz)	MS/FAB	
		found	calc.
1	δ = 8.02-8.00 (dd, 1H), 7.94 (d, 2H), 7.84-7.82 (m, 2H), 7.80 (d, 1H), 7.78 (d, 1H), 7.76 (d, 1H), 7.73-7.69 (m, 2H), 7.60-7.57 (m, 3H), 7.55-7.51 (m, 2H), 7.47-7.44 (m, 1H), 7.38-7.29 (m, 6H), 7.08-7.04 (m, 1H), 7.02-7.00 (dd, 1H)	520.21	520.18
5	δ = 8.12-8.10 (dd, 1H), 8.03-8.01 (dd, 1H), 7.85-7.80 (m, 5H), 7.73-7.69 (m, 2H), 7.64-7.62 (m, 1H), 7.54-7.52 (dd, 1H), 7.46-7.44 (m, 1H), 7.40-7.38 (m, 1H), 7.35-7.30 (m, 6H), 7.25-7.21 (m, 2H), 7.12-7.09 (m, 2H), 7.03-7.01 (m, 1H)	520.20	520.18
7	δ = 8.24-8.22 (m, 1H), 7.91 (t, 2H), 7.84-7.82 (m, 3H), 7.80 (d, 1H), 7.78 (d, 1H), 7.75 (d, 1H), 7.72-7.66 (m, 3H), 7.56-7.53 (m, 2H), 7.46-7.44 (dd, 1H), 7.37-7.26 (m, 7H), 7.02-6.99 (m, 1H), 0.39 (s, 9H)	592.22	592.19
10	δ = 8.21-8.19 (m, 1H), 7.99-7.92 (m, 3H), 7.85-7.82 (m, 2H), 7.81 (d, 1H), 7.79 (d, 1H), 7.77 (d, 1H), 7.72-7.69 (m, 2H), 7.58-7.51 (m, 3H), 7.46-7.44 (dd, 1H), 7.37-7.28 (m, 6H), 7.04-7.01 (m, 1H), 6.99-6.98 (dd, 1H)	601.21	601.24
12	δ = 8.08-8.04 (m, 2H), 7.95-7.90 (m, 2H), 7.84-7.81 (m, 2H), 7.80 (d, 1H), 7.77 (d, 1H), 7.76-7.74 (m, 2H), 7.73-7.69 (m, 3H), 7.55-7.52 (dd, 1H), 7.47-7.45 (dd, 1H), 7.36-7.27 (m, 6H), 7.10-7.08 (dd, 1H), 7.01-6.99 (m, 1H)	545.20	545.18
15	δ = 8.34-8.33 (dd, 1H), 8.19-8.16 (m, 1H), 8.04-8.01 (m, 2H), 7.93-7.91 (d, 1H), 7.83 (d, 1H), 7.81 (d, 1H), 7.71-7.68 (m, 5H), 7.60-7.57 (m, 3H), 7.50-7.45 (m, 3H), 7.40-7.35 (m, 4H), 7.32-7.28 (m, 3H), 7.06-7.01 (m, 3H)	596.23	596.21

TABLE 1-continued


Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		found	calc.
18	δ = 8.18-8.16 (dd, 1H), 8.09-8.08 (dd, 1H), 8.03-8.01 (m, 2H), 7.94-7.92 (d, 1H), 7.84-7.79 (m, 4H), 7.72-67 (m, 3H), 7.65-7.63 (m, 1H), 7.50-7.45 (m, 2H), 7.41-7.31 (m, 7H), 7.25-7.21 (m, 2H), 7.15-7.10 (m, 2H), 7.07-7.03 (m, 2H)	596.25	596.21
21	δ = 8.41-8.39 (m, 1H), 8.30-8.28 (m, 1H), 8.15-8.14 (dd, 1H), 8.08-8.07 (dd, 1H), 7.93-7.91 (m, 1H), 7.85-7.80 (m, 5H), 7.75-7.70 (m, 2H), 7.62 (t, 1H), 7.40-7.24 (m, 10H), 7.13-7.09 (m, 3H), 7.06-7.03 (m, 1H)	597.26	597.21
25	δ = 8.21 (d, 1H), 8.10-8.08 (dd, 1H), 7.88 (d, 1H), 7.82-7.80 (m, 2H), 7.69-7.67 (dd, 1H), 7.65-7.56 (m, 4H), 7.54-7.49 (m, 2H), 7.45-7.43 (m, 1H), 7.35-7.32 (tt, 1H), 7.29-7.21 (m, 3H), 7.11-7.09 (tt, 1H), 7.06-7.01 (m, 4H)	470.20	470.17
26	δ = 8.13-8.11 (dd, 1H), 8.00-7.98 (m, 1H), 7.82-7.80 (m, 1H), 7.70-7.67 (m, 2H), 7.66-7.55 (m, 6H), 7.51-7.48 (m, 2H), 7.44-7.42 (dd, 1H), 7.33-7.21 (m, 3H), 7.12-7.10 (dd, 1H), 7.07-7.03 (m, 3H)	538.19	538.15
28	δ = 8.05-8.01 (m, 1H), 7.97-7.96 (m, 2H), 7.92-7.89 (m, 1H), 7.78-7.76 (m, 1H), 7.70 (s, 2H), 7.63-7.55 (m, 12H), 7.51-7.48 (m, 2H), 7.39-7.38 (m, 1H), 7.31-7.22 (m, 11H), 7.04-7.00 (m, 2H), 6.98-6.96 (m, 1H)	728.23	728.25
31	δ = 8.04-8.01 (m, 3H), 7.97-7.96 (m, 2H), 7.91-7.89 (m, 1H), 7.72-7.68 (m, 2H), 7.65-7.64 (m, 2H), 7.61-7.57 (m, 4H), 7.53-7.45 (m, 4H), 7.41-7.35 (m, 3H), 7.06-7.03 (m, 4H), 7.00-6.97 (m, 1H)	546.18	546.20
38	δ = 8.23-8.20 (m, 2H), 8.05-8.02 (m, 2H), 7.98-7.96 (m, 2H), 7.91-7.89 (m, 1H), 7.73-7.70 (m, 1H), 7.64-7.63 (m, 2H), 7.59-7.55 (m, 3H), 7.53-7.50 (m, 2H), 7.39 (t, 1H), 7.17-7.13 (tt, 1H), 7.06-6.99 (m, 4H)	636.18	636.15
42	δ = 8.34-8.32 (m, 1H), 8.25-8.23 (dd, 1H), 8.13-8.11 (dd, 2H), 8.09-8.08 (m, 1H), 7.94-7.91 (m, 2H), 7.85-7.83 (m, 2H), 7.71 (d, 1H), 7.57-7.53 (m, 1H), 7.47-7.40 (m, 2H), 7.38-7.32 (m, 6H), 7.25-7.23 (m, 1H), 7.16-7.10 (m, 5H), 7.03-7.01 (m, 1H)	570.23	570.20
44	δ = 8.33-8.32 (m, 1H), 8.23-8.21 (m, 1H), 8.14-8.13 (m, 2H), 8.12-8.11 (m, 1H), 8.03-8.01 (dd, 1H), 7.95-7.93 (m, 2H), 7.92-7.91 (m, 2H), 7.66-7.55 (m, 5H), 7.47-7.43 (m, 2H), 7.40-7.36 (m, 1H), 7.33-7.29 (m, 2H), 7.23-7.21 (dd, 1H), 7.16-7.09 (m, 5H)	570.25	570.20
48	δ = 8.31 (d, 1H), 8.21-8.17 (m, 1H), 7.96-7.95 (m, 2H), 7.94-7.93 (m, 2H), 7.81 (d, 1H), 7.80-7.77 (m, 3H), 7.60-7.54 (m, 7H), 7.50-7.46 (m, 3H), 7.41-7.35 (m, 4H), 7.33-7.27 (m, 5H), 7.04-7.02 (m, 1H)	646.27	646.23
53	δ = 8.41-8.39 (m, 1H), 8.26 (d, 1H), 8.13-8.11 (dd, 1H), 8.02-8.00 (dd, 2H), 7.95-7.91 (m, 3H), 7.83-7.80 (m, 3H), 7.70 (d, 1H), 7.57-7.53 (m, 1H), 7.42-7.33 (m, 10H), 7.26-7.23 (m, 2H), 7.13-7.07 (m, 3H), 7.01-6.99 (m, 1H)	647.25	647.22
57	δ = 8.11-8.09 (m, 1H), 8.03-8.01 (m, 1H), 7.97-7.96 (dd, 2H), 7.83 (d, 1H), 7.81 (d, 1H), 7.79-7.77 (m, 2H), 7.69-7.63 (m, 2H), 7.60-7.58 (m, 2H), 7.57-7.56 (m, 2H), 7.54 (d, 1H), 7.50-7.46 (m, 4H), 7.41-7.29 (m, 6H), 7.09-7.05 (m, 2H), 6.99-6.96 (m, 1H)	596.20	596.21
59	δ = 8.09-8.07 (dd, 1H), 8.06-8.04 (dd, 1H), 7.99-7.97 (m, 1H), 7.86-7.84 (m, 1H), 7.83-7.82 (dd, 1H), 7.81-7.80 (dd, 1H), 7.79-7.76 (m, 2H), 7.69-7.63 (m, 4H), 7.58-7.54 (m, 3H), 7.51-7.46 (m, 4H), 7.40-7.26 (m, 6H), 7.06-7.02 (m, 1H), 6.99-6.95 (m, 1H)	621.19	621.21
60	δ = 8.24-8.22 (dd, 1H), 8.05-8.02 (m, 4H), 7.93-7.90 (m, 2H), 7.83 (d, 1H), 7.81 (d, 1H), 7.79-7.76 (m, 3H), 7.71-7.68 (m, 3H), 7.64-7.60 (m, 1H), 7.48-7.45 (m, 2H), 7.41-7.28 (m, 6H), 7.23 (d, 1H), 7.04-6.96 (m, 2H)	621.26	621.21
65	δ = 8.45-8.44 (dd, 1H), 8.32-8.30 (m, 1H), 8.19 (d, 1H), 8.02-7.90 (m, 5H), 7.85-7.82 (m, 5H), 7.80-7.76 (m, 3H), 7.67-7.60 (m, 3H), 7.48-7.32 (m, 10H), 7.09-7.06 (tt, 1H), 7.01-6.99 (dd, 1H)	673.27	673.24

Example 1


[0141] An anode was manufactured as follows: a corning 15 Ω/cm^2 (1200 Å) ITO glass substrate was cut to a size of 50 mm×50 mm×0.7 mm, sonicated with isopropyl alcohol and pure water each for 5 minutes, and then washed by UV irradiation for 30 minutes and ozone. The resultant glass substrate was loaded into a vacuum deposition apparatus.

[0142] 2-TNATA was vacuum deposited on the substrate to form a HIL having a thickness of 600 Å. Then, 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB) was vacuum deposited thereon to form a HTL having a thickness of 300 Å.


[0143] On the HTL, Compound 1 (as a blue fluorescent host) and 4,4'-bis[2-(4-(N,N-diphenylamino)phenyl)vinyl]biphenyl (DPAVBi) were co-deposited at a weight ratio of 98:2 to form an EML having a thickness of 300 Å.



2-TNATA



NPB



DPAVBi

[0144] Subsequently, Alq₃ was deposited on the EML to form an ETL having a thickness of 300 Å, and then LiF, which is a halogenated alkali metal, was deposited on the ETL to form an EIL having a thickness of 10 Å. Al was vacuum deposited to form a cathode having a thickness of 3,000 Å to form a LiF/Al electrode, thereby completing the manufacture of an organic light-emitting device.

[0145] At a current density of 10 mA/cm², the device had a driving voltage of 5.12 V, a luminescence brightness of 3,535 cd/m², a luminescence efficiency of 7.07 cd/A, and a half-lifespan (hr @100 mA/cm²) of 295 hours.

Example 2

[0146] An organic light-emitting device was manufactured as in Example 1, except that Compound 7 was used instead of Compound 1 to form the EML.

[0147] At a current density of 10 mA/cm², the device had a driving voltage of 5.21 V, a luminescence brightness of 3,620 cd/m², a luminescence efficiency of 7.24 cd/A, and a half-lifespan (hr @100 mA/cm²) of 308 hours.

Example 3

[0148] An organic light-emitting device was manufactured in Example 1, except that 9,10-di-naphthalene-2-yl-anthracene (DNA) was used instead of Compound 1 to form the EML, and Compound 12 was used instead of Alq₃ to form the ETL.

[0149] At a current density of 10 mA/cm², the device had a driving voltage of 5.37 V, a luminescence brightness of 3,725 cd/m², a luminescence efficiency of 7.45 cd/A, and a half-lifespan (hr @100 mA/cm²) of 378 hours.

Example 4

[0150] An organic light-emitting device was manufactured as in Example 1, except that Compound 18 was used instead of Compound 1 to form the EML.

[0151] At a current density of 10 mA/cm², the device had a driving voltage of 5.17 V, a luminescence brightness of 3,575 cd/m², a luminescence efficiency of 7.15 cd/A, and a half-lifespan (hr @100 mA/cm²) of 324 hours.

Example 5

[0152] An organic light-emitting device was manufactured as in Example 1, except that Compound 25 was used instead of Compound 1 to form the EML.

[0153] At a current density of 10 mA/cm², the device had a driving voltage of 5.26 V, a luminescence brightness of 3,380 cd/m², a luminescence efficiency of 6.76 cd/A, and a half-lifespan (hr @100 mA/cm²) of 276 hours.

Example 6

[0154] An organic light-emitting device was manufactured as in Example 1, except that Compound 31 was used instead of Compound 1 to form the EML.

[0155] At a current density of 10 mA/cm², the device had a driving voltage of 5.29 V, a luminescence brightness of 3,455 cd/m², a luminescence efficiency of 6.91 cd/A, and a half-lifespan (hr @100 mA/cm²) of 295 hours.

Example 7

[0156] An organic light-emitting device was manufactured as in Example 1, except that Compound 42 was used instead of Compound 1 to form the EML.

[0157] At a current density of 10 mA/cm², the device had a driving voltage of 5.33 V, a luminescence brightness of 3,665 cd/m², a luminescence efficiency of 7.33 cd/A, and a half-lifespan (hr @100 mA/cm²) of 276 hours.

Example 8

[0158] An organic light-emitting device was manufactured as in Example 1, except that Compound 53 was used instead of Compound 1 to form the EML.

[0159] At a current density of 10 mA/cm², the device had a driving voltage of 5.25 V, a luminescence brightness of 3,645 cd/m², a luminescence efficiency of 7.28 cd/A, and a half-lifespan (hr @100 mA/cm²) of 283 hours.


Example 9

[0160] An organic light-emitting device was manufactured as in Example 3, except that Compound 60 was used instead of Compound 12 to form the ETL.

[0161] At a current density of 10 mA/cm², the device had a driving voltage of 5.34 V, a luminescence brightness of 3,790 cd/m², a luminescence efficiency of 7.58 cd/A, and a half-lifespan (hr @100 mA/cm²) of 385 hours.

Comparative Example 1

[0162] An organic light-emitting device was manufactured as in Example 1, except that DNA (depicted below) was used instead of Compound 1 as a blue fluorescent host in the EML.



DNA

[0163] At a current density of 10 mA/cm², the device had a driving voltage of 7.35 V, a luminescence brightness of 2,065 cd/m², a luminescence efficiency of 4.13 cd/A, and a half-lifespan (hr @100 mA/cm²) of 145 hours.

[0164] In Examples 1 through 9, compounds represented by Formulae 1 through 3 were used as host materials for blue EMLs. Compared with DNA, the compounds represented by Formulae 1 through 3 had low driving voltages, high efficiency, and good I-V-L characteristics. In particular, OLEDs using the compounds represented by Formulae 1 through 3 exhibited significant lifespan improvement effects, thereby substantially prolonging lifespan. Representative characteristics and lifespan results were summarized and the results are shown in Table 1.

TABLE 1


	Emission material and Electron transport material	Driving voltage (V)	Current density (mA/cm ²)	Brightness (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr@100 mA/cm ²)
Example 1	Compound 1	5.12	50	3,535	7.07	Blue	295 hr
Example 2	Compound 7	5.21	50	3,620	7.24	Blue	308 hr
Example 3	Compound 12	5.37	50	3,725	7.45	Blue	378 hr
Example 4	Compound 18	5.17	50	3,575	7.15	Blue	324 hr
Example 5	Compound 25	5.26	50	3,380	6.76	Blue	276 hr
Example 6	Compound 31	5.29	50	3,455	6.91	Blue	295 hr
Example 7	Compound 42	5.33	50	3,665	7.33	Blue	276 hr
Example 8	Compound 53	5.23	50	3,640	7.29	Blue	283 hr
Example 9	Compound 60	5.34	50	3,790	7.58	Blue	385 hr
Comparative Example 1	DNA	7.35	50	2,065	4.13	Blue	145 hr

[0165] As described above, according to one or more embodiments of the present invention, compounds represented by Formulae 1 through 3 are suitable for use in a full color device, such as red, green, blue, or white fluorescent or phosphorescent devices. Due to the inclusion of the compound of one of Formulae 1 through 3, the organic light-emitting device has high efficiency, low voltage, high brightness, and a long lifespan.

[0166] It should be understood that the exemplary embodiments described herein are presented for descriptive purposes only, and not for purposes of limitation. Accordingly, descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.


[0167] While one or more embodiments of the present invention have been described, it will be understood by those of ordinary skill in the art that various changes may be made to the described embodiments without departing from the spirit and scope of the present invention as defined by the following claims.

1. A compound represented by Formula 1, Formula 2, or Formula 3:




Formula 1

-continued



Formula 2




Formula 3

Wherein, in Formulae 1, 2, and 3,

R_1^1 to R_1^{16} , R_2^1 to R_2^{18} , and R_3^1 to R_3^{14} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group, or L , provided that at least one of R_1^1 to R_1^{16} , at least one of R_2^1 to R_2^{18} , and at least one of R_3^1 to R_3^{14} is L ,

wherein:

L is




and


R₀ is a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C₁ to C₆₀ alkyl group, a substituted or unsubstituted C₂ to C₆₀ alkenyl group, a substituted or unsubstituted C₃ to C₆₀ cycloalkyl group, a substituted or unsubstituted C₆ to C₆₀ aryl group, a substituted or unsubstituted C₁ to C₆₀ hetero aryl group, or a substituted or unsubstituted C₆ to C₆₀ condensed polycyclic group.

2. The compound of claim 1, wherein the compound represented by Formula 1 is represented by one of Formulae 4 through 7:

Formula 4




Formula 5




-continued

Formula 6



Formula 7




wherein in Formulae 4 to 7,

R₁¹ to R₁¹⁶ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C₁ to C₆₀ alkyl group, a substituted or unsubstituted C₂ to C₆₀ alkenyl group, a substituted or unsubstituted C₃ to C₆₀ cycloalkyl group, a substituted or unsubstituted C₆ to C₆₀ aryl group, a substituted or unsubstituted C₁ to C₆₀ hetero aryl group, or a substituted or unsubstituted C₆ to C₆₀ condensed polycyclic group.


3. The compound of claim 1, wherein the compound represented by Formula 2 is represented by Formula 8 or 9:

Formula 8



-continued

Formula 9




wherein, in Formulae 8 and 9,


R_2^1 to R_2^{18} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to C_{60} aryl group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group.

4. The compound of claim 1, wherein the compound represented by Formula 3 is represented by Formula 10 or 11:

Formula 10



Formula 11



Wherein, in Formulae 10 and 11,

R_3^1 to R_3^{14} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 to C_{60} alkyl group, a substituted or unsubstituted C_2 to C_{60} alkenyl group, a substituted or unsubstituted C_3 to C_{60} cycloalkyl group, a substituted or unsubstituted C_6 to

C_{60} aryl group, a substituted or unsubstituted C_1 to C_{60} hetero aryl group, or a substituted or unsubstituted C_6 to C_{60} condensed polycyclic group.



5. The compound of claim 1, wherein R_1^1 , R_1^2 , R_1^8 , R_1^9 , R_1^{10} , R_1^{11} , and R_1^{16} of Formula 1, R_2^1 , R_2^2 , R_2^8 , R_2^9 , R_2^{10} , R_2^{11} , R_2^{17} , and R_2^{18} of Formula 2, and R_3^1 , R_3^6 , R_3^7 , R_3^8 , R_3^{13} , and R_3^{14} of Formula 3 are each independently a hydrogen atom or a deuterium atom.

6. The compound of claim 2, wherein R_1^1 to R_1^{10} , and R_1^{15} of Formulae 4 and 5, and R_1^1 to R_1^4 , R_1^6 to R_1^{11} , and R_1^{15} of Formulae 6 and 7 are each independently a hydrogen atom or a deuterium atom.

7. The compound of claim 3, wherein R_2^1 to R_2^{10} , R_2^{16} , and R_2^{17} of Formulae 8 and 9 are each independently a hydrogen atom or a deuterium atom.

8. The compound of claim 4, wherein R_3^1 to R_3^8 , and R_3^{13} of Formulae 10 and 11 are each independently a hydrogen atom or a deuterium atom.

9. The compound of claim 1, wherein R_1^1 - R_1^{16} , R_2^1 - R_2^{18} , R_3^1 - R_3^{14} , and R_0 of Formulae 1, 2, and 3 are each independently a hydrogen atom, a deuterium atom, a cyano group, a trihalomethyl group, or any one of Formulae 2a through 2c:




wherein, in Formulae 2a through 2c:

R_{51} , R_{52} , R_{53} , and Z_1 are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 to C_{20} alkyl group, a substituted or unsubstituted C_6 to C_{20} aryl group, a substituted or unsubstituted C_1 to C_{20} heteroaryl group, a substituted or unsubstituted C_6 to C_{20} condensed polycyclic group, an amino group substituted with a C_6 to C_{20} aryl group or a C_2 to C_{20} heteroaryl group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;


p is an integer of 1 to 5; and

* indicates a binding site to Formula 1, 2 or 3.

10. The compound of claim 2, wherein R_1^{13} and R_1^{16} of Formulae 4 and 5 are each independently a hydrogen atom, a deuterium atom, a cyano group, a trihalomethyl group, or any one of Formulae 2a to 2c:




-continued



2c

-continued



2c

wherein, in Formulae 2a through 2c:

R_{51} , R_{52} , R_{53} , and Z_1 are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 to C_{20} alkyl group, a substituted or unsubstituted C_6 to C_{20} aryl group, a substituted or unsubstituted C_1 to C_{20} heteroaryl group, a substituted or unsubstituted C_6 to C_{20} condensed polycyclic group, an amino group substituted with a C_6 to C_{20} aryl group or a C_2 to C_{20} heteroaryl group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;

p is an integer of 1 to 5; and

$*$ indicates a binding.


11. The compound of claim 3, wherein R_1^{15} and R_1^{16} of Formulae 6 and 7 are each independently a hydrogen atom, a deuterium atom, a cyano group, a trihalomethyl group, or any one of Formulae 2a through 2c:



2a



2b



2c


wherein, in Formulae 2a through 2c:

R_{51} , R_{52} , R_{53} , and Z_1 are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 to C_{20} alkyl group, a substituted or unsubstituted C_6 to C_{20} aryl group, a substituted or unsubstituted C_2 to C_{20} heteroaryl group, a substituted or unsubstituted C_6 to C_{20} condensed polycyclic group, an amino group substituted with a C_6 to C_{20} aryl group or a C_1 to C_{20} heteroaryl group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;


p is an integer of 1 to 5; and

$*$ indicates a binding.

12. The compound of claim 4, wherein R_3^{11} and R_3^{14} of Formulae 10 and, 11 are each independently a hydrogen atom, a deuterium atom, a cyano group, a trihalomethyl group, or any one of Formulae 2a through 2c:



2a



2b


wherein, in Formulae 2a through 2c:

R_{51} , R_{52} , R_{53} , and Z_1 are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 to C_{20} alkyl group, a substituted or unsubstituted C_6 to C_{20} aryl group, a substituted or unsubstituted C_2 to C_{20} heteroaryl group, a substituted or unsubstituted C_6 to C_{20} condensed polycyclic group, an amino group substituted with a C_6 to C_{20} aryl group or a C_1 to C_{20} heteroaryl group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;


p is an integer of 1 to 5; and

$*$ indicates a binding.


13. The compound of claim 1, wherein the compound represented by Formula 1 is one of Compounds 1, 7, 12, 18, 25, 31, 42, 53 and 60:



1




7




12

-continued


18




25




31



42




53



-continued

60

**14.** An organic light-emitting device comprising:

a first electrode;

a second electrode; and

an organic layer between the first electrode and the second electrode, and comprising the compound of claim 1.

15. The organic light-emitting device of claim 14, wherein the organic layer is an emission layer, an electron injection layer, an electron transport layer, or a functional layer having electron injection capability and electron transportation capability.**16.** The organic light-emitting device of claim 14, wherein the organic layer comprises:

an emission layer comprising an anthracene-based compound, an arylamine-based compound, or a styryl-based compound, and

an electron injection layer, an electron transport layer, a functional layer having electron injection capability and electron transportation capability, a hole injection layer, a hole transport layer, or a functional layer having hole injection capability and hole transportation capability.

17. The organic light-emitting device of claim 14, wherein the organic layer comprises:

an emission layer comprising a red layer, a green layer, a blue layer, and a white layer, and one of the red layer, the green layer, the blue layer or the white layer comprises a phosphorescent compound, and

an electron injection layer, an electron transport layer, a functional layer having electron injection capability and electron transportation capability, a hole injection layer, a hole transport layer, or a functional layer having hole injection capability and hole transportation capability.

18. The organic light-emitting device of claim 17, wherein the hole injection layer, the hole transport layer, or the functional layer having hole injection capability and hole transport capability comprises a charge-generation material.**19.** The organic light-emitting device of claim 14, wherein the organic layer is formed by a wet process using the compound represented by Formula 1, Formula 2 or Formula 3.**20.** A flat display apparatus comprising the organic light-emitting device of claim 14, wherein the first electrode of the organic light-emitting device is electrically connected to a source electrode or a drain electrode of a thin film transistor.

* * * * *

专利名称(译)	包含相同的复合和有机发光装置		
公开(公告)号	US20150001479A1	公开(公告)日	2015-01-01
申请号	US14/072478	申请日	2013-11-05
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE EUN YOUNG HWANG SEOK HWAN KIM YOUNG KOOK JUNG HYE JIN PARK JUN HA KIM JONG WOO LIM JIN O HAN SANG HYUN JEONG EUN JAE KIM SOO YON LEE JONG HYUK		
发明人	LEE, EUN-YOUNG HWANG, SEOK-HWAN KIM, YOUNG-KOOK JUNG, HYE-JIN PARK, JUN-HA KIM, JONG-WOO LIM, JIN-O HAN, SANG-HYUN JEONG, EUN-JAE KIM, SOO-YON LEE, JONG-HYUK		
IPC分类号	H01L51/00		
CPC分类号	H01L51/0073 C07B59/001 C07B2200/05 C07C13/567 C07C13/62 C07C15/28 C07C15/30 C07C15/38 C07C2103/18 C07C2103/24 C07C2103/26 C07C2103/50 C07D311/78 C07D405/04 C07D405/10 C07F7/0814 C09B1/00 C09B1/005 C09B11/28 C09K11/06 C09K2211/1011 C09K2211/1014 C09K2211/ 1029 C09K2211/1044 C09K2211/1059 C09K2211/1088 H01L51/0058 H01L51/0059 H01L51/006 H01L51/0081 H01L51/5012 H01L51/5072 C07C2603/18 C07C2603/24 C07C2603/26 C07C2603/50		
优先权	1020130076597 2013-07-01 KR		
其他公开文献	US10256416		
外部链接	Espacenet USPTO		

摘要(译)

化合物由式1,2或3表示, 并且有机发光装置包括该化合物。有机发光装置包括第一电极, 第二电极和有机层。有机层包括由式1,2或3表示的化合物。平板显示装置包括有机发光装置。

SECOND ELECTRODE
EIL
ETL
EML
HTL
HIL
FIRST ELECTRODE