



US 20190081111A1

(19) **United States**(12) **Patent Application Publication**
LEE et al.(10) **Pub. No.: US 2019/0081111 A1**(43) **Pub. Date: Mar. 14, 2019**(54) **ORGANIC LIGHT EMITTING DIODE
DISPLAY AND METHOD OF
MANUFACTURING THE SAME****H01L 27/12** (2006.01)**H01L 51/52** (2006.01)(52) **U.S. Cl.**CPC **H01L 27/3206** (2013.01); **H01L 27/3279**
(2013.01); **H01L 51/0023** (2013.01); **H01L**
2227/32 (2013.01); **H01L 27/127** (2013.01);
H01L 51/0002 (2013.01); **H01L 51/5228**
(2013.01); **H01L 27/3276** (2013.01)(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si (KR)(72) Inventors: **SE HO LEE**, Cheonan-Si (KR); **Tae
Hyung Kim**, Seoul (KR); **Je-Hyun
Song**, Seoul (KR)(21) Appl. No.: **16/186,817**(22) Filed: **Nov. 12, 2018****Related U.S. Application Data**(62) Division of application No. 15/711,103, filed on Sep.
21, 2017, now Pat. No. 10,147,769.(30) **Foreign Application Priority Data**

Dec. 7, 2016 (KR) 10-2016-0165997

Publication Classification(51) **Int. Cl.****H01L 27/32** (2006.01)**H01L 51/00** (2006.01)**ABSTRACT**

An organic light emitting diode display according to an exemplary embodiment includes: a substrate; a pixel formed on the substrate and including a pixel area displaying an image and a peripheral area adjacent to the pixel area; an insulating layer at the pixel area and the peripheral area on the substrate; a first electrode at the pixel area on the insulating layer; an organic emission layer on the first electrode and extending to the peripheral area; a second electrode on the organic emission layer and disposed in the pixel area and the peripheral area; an auxiliary electrode in the peripheral area on the substrate and partially exposed by a first opening formed in the insulating layer; and an auxiliary member disposed on the auxiliary electrode and in contact with an upper surface of the auxiliary electrode exposed by the first opening.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10





FIG. 12



ORGANIC LIGHT EMITTING DIODE DISPLAY AND METHOD OF MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application is a Division of U.S. patent application Ser. No. 15/711,103, filed on Sep. 21, 2017, which claims priority to and the benefit of Korean Patent Application No. 10-2016-0165997, filed in the Korean Intellectual Property Office on Dec. 7, 2016, the entire contents of which are incorporated by reference herein in their entirety.

TECHNICAL FIELD

[0002] The present disclosure relates to a display device, and more particularly, to an organic light emitting diode (OLED) display device and a method of manufacturing the OLED display device.

DISCUSSION OF THE RELATED ART

[0003] Currently popular display devices include liquid crystal displays (LCDs), plasma display panels (PDPs), organic light emitting diode (OLED) displays, field effect displays (FEDs), and electrophoretic displays (EPDs).

[0004] Particularly, the organic light emitting diode (OLED) display includes two electrodes and an organic emission layer disposed therebetween. Electrons from one electrode and holes from the other electrode combine within the organic emission layer to thereby form excitons, which release energy in the form of light as they relax.

[0005] The organic light emitting diode (OLED) display accordingly has a self-luminous characteristic, and because the organic light emitting diode (OLED) display does not need a separate light source, unlike a liquid crystal display (LCD), the OLED display can be relatively thin and light weight. Further, the organic light emitting diode (OLED) display exhibits high-quality characteristics such as low power consumption, high luminance, and fast response speed, and thus receives attention as a next generation display device.

[0006] As the organic light emitting diode display is larger, a screen smudge defect may be observed as a result of a voltage drop in the common electrode. To solve the voltage drop problem, the common electrode and a common voltage line are connected to each other in each sub-pixel.

[0007] To connect the common electrode and the common voltage line to each other, the common electrode and the common voltage line are electrically connected to each other by removing a part of an organic emission layer with a laser.

[0008] However, in the process of removing the part of the organic emission layer by using the laser, a metal layer disposed under the organic emission layer may be damaged, and a remaining gas component of the organic layer may be discharged into the damaged metal layer such that the common electrode may be oxidized.

SUMMARY

[0009] The present invention provides an organic light emitting diode display and a manufacturing method for preventing the metal layer positioned under the organic emission layer from being damaged by the laser.

[0010] Also, the present invention provides an organic light emitting diode display and a manufacturing method for

preventing the common electrode from being oxidized due to the discharge of the remaining gas of the organic layer due to the damaged metal layer.

[0011] An organic light emitting diode display according to an exemplary embodiment includes: a substrate; a pixel formed on the substrate and including a pixel area displaying an image and a peripheral area adjacent to the pixel area; an insulating layer formed at the pixel area and the peripheral area on the substrate; a first electrode formed at the pixel area on the insulating layer; an organic emission layer formed on the first electrode and extending to the peripheral area; a second electrode formed on the organic emission layer and disposed in the pixel area and the peripheral area; an auxiliary electrode disposed in the peripheral area on the substrate and partially exposed by a first opening formed in the insulating layer; and an auxiliary member disposed on the auxiliary electrode and in contact with an upper surface of the auxiliary electrode exposed by the first opening.

[0012] The organic emission layer may be disposed on the auxiliary member in the peripheral area, and may have a second opening exposing part of the auxiliary member.

[0013] The second electrode may be in contact with the auxiliary member through the second opening.

[0014] The second opening may have a circular shape.

[0015] The auxiliary member may cover the first opening of the insulating layer.

[0016] The auxiliary member may be in contact with a part of an interior circumference of the first opening.

[0017] The auxiliary member may be formed with the same layer as the first electrode.

[0018] The auxiliary member may be formed by sequentially stacking ITO (indium tin oxide), silver (Ag), and ITO.

[0019] The auxiliary electrode may be a common voltage line transmitting a common voltage.

[0020] The auxiliary electrode may be formed by sequentially stacking molybdenum (Mo), aluminum (Al), and molybdenum (Mo).

[0021] The pixel may include at least one sub-pixel including the pixel area and the peripheral area, and the sub-pixel may be a red sub-pixel.

[0022] A manufacturing method of an organic light emitting diode display according to an exemplary embodiment includes: preparing a substrate; forming a thin film transistor including a semiconductor layer, a gate electrode on the semiconductor layer, and a source electrode and a drain electrode connected to the semiconductor layer on the substrate; forming an auxiliary electrode supplying a common voltage on the substrate; forming an insulating layer on the thin film transistor and the auxiliary electrode and exposing parts of the drain electrode and the auxiliary electrode; forming a first electrode on the insulating layer and in contact with the drain electrode; forming an auxiliary member in contact with the auxiliary electrode through a first opening formed in the insulating layer; forming an organic emission layer on the first electrode and the auxiliary member; removing a part of the organic emission layer to expose a part of the auxiliary member; and forming a second electrode on the organic emission layer.

[0023] The removal of the part of the organic emission layer may be performed by using a laser.

[0024] The removal of the part of the organic emission layer may include forming a second opening by removing the part of the organic emission layer.

[0025] The second opening may have a circular shape.

[0026] The method may further include forming a pixel definition layer having a third opening exposing the part of the auxiliary member and a fourth opening exposing the part of the first electrode.

[0027] The source electrode, the drain electrode, and the auxiliary electrode may be formed with the same layer.

[0028] The first electrode and the auxiliary member may be formed with the same layer.

[0029] The auxiliary member may be in contact with an entire upper surface of the auxiliary electrode exposed by the first opening.

[0030] According to the organic light emitting diode display and the manufacturing method thereof, damage to the metal layer positioned under the organic emission layer by the laser removing the part of the organic emission layer may be prevented.

[0031] Also, oxidization of the common electrode by the remaining gas component of the organic layer may be prevented.

[0032] Further, generation of a dark spot in the organic light emitting diode display due to no emission of the organic emission layer may be prevented.

[0033] In addition, a voltage drop being generated in the organic light emitting diode display such that the luminance becomes non-uniform may be prevented.

BRIEF DESCRIPTION OF THE DRAWINGS

[0034] A more complete appreciation of the present disclosure and many of the attendant aspects thereof will be readily obtained as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings, wherein:

[0035] FIG. 1 is an equivalent circuit diagram illustrating one pixel of an organic light emitting diode display according to an exemplary embodiment of the present invention;

[0036] FIG. 2 is a partial layout view illustrating an organic light emitting diode display according to an exemplary embodiment of the present invention;

[0037] FIG. 3 is a cross-sectional view taken along a line III-III of FIG. 2;

[0038] FIG. 4 and FIG. 5 are views illustrating a comparative example explaining a process in which an auxiliary member of a region A of FIG. 3 is damaged;

[0039] FIG. 6 is a view illustrating an exemplary variation of an organic light emitting diode display of FIG. 3; and

[0040] FIG. 7 to FIG. 12 are views sequentially illustrating a method of manufacturing an organic light emitting diode display according to an exemplary embodiment of the present invention.

DETAILED DESCRIPTION OF THE DRAWINGS

[0041] Exemplary embodiments of the present invention will be described more fully hereinafter with reference to the accompanying drawings. As those skilled in the art would realize, the described embodiments may be modified in various different ways, all without departing from the spirit or scope of the present disclosure. The drawings and description are to be regarded as illustrative in nature. Like reference numerals may designate like elements throughout the specification.

[0042] In the drawings, the thicknesses of layers, films, panels, regions, areas, etc., may be exaggerated for clarity.

It will be understood that when an element such as a layer, film, region, or substrate is referred to as being “on” another element, it can be directly on the other element or intervening elements may also be present.

[0043] Also, the present invention is not limited to the number of thin film transistors (TFT) and capacitors shown in accompanying drawings, and in the organic light emitting diode display, each pixel may be provided with a plurality of transistors and at least one capacitor, and may be formed to have various structures by further forming additional wires or omitting existing wires. As defined herein, the pixel is a minimum unit for displaying an image, and the organic light emitting diode display displays the image through the plurality of pixels. In particular, the pixel may be a minimum unit for displaying any desired color, while the sub-pixel may be a minimum unit for displaying a particular single color.

[0044] An organic light emitting diode display according to an exemplary embodiment of the present invention will be described below with reference to FIG. 1 to FIG. 3.

[0045] The organic light emitting diode display according to an exemplary embodiment of the present invention may be made of a plurality of pixels each including a plurality of sub-pixels. Each sub-pixel can display a primary color such as red, green, blue, etc., and a predetermined color may be realized in one pixel by a combination of a plurality of sub-pixels representing these colors.

[0046] Referring to FIG. 2 and FIG. 3, at least one sub-pixel may include a display area DA emitting light and a peripheral area PA adjacent to the display area DA. According to an exemplary embodiment of the present invention, light is emitted from an organic emission layer 720 disposed between a first electrode 710 and a second electrode 730 in the display area DA, and a common voltage may be transmitted to the second electrode 730 through an auxiliary electrode 310 disposed in the peripheral area PA.

[0047] According to an exemplary embodiment of the present invention, at least one sub-pixel among a plurality of sub-pixels of one pixel may include the peripheral area PA. For example, when the plurality of sub-pixels are respectively a red sub-pixel, a green sub-pixel, and a blue sub-pixel, only the red sub-pixel may include both the display area DA and the peripheral area PA, while the green sub-pixel and the blue sub-pixel may each only include the display area DA. The common voltage supplied through the red sub-pixel may be commonly used in the green sub-pixel and the blue sub-pixel.

[0048] However, the present invention is not limited to this particular arrangement, and the red sub-pixel, the green sub-pixel, and the blue sub-pixel may all include the display area DA and the peripheral area PA. The common voltage is respectively supplied to the red, green, and blue sub-pixels.

[0049] A principal of operation of one sub-pixel of the organic light emitting diode display will be described below with reference to FIG. 1.

[0050] FIG. 1 is an equivalent circuit diagram illustrating one pixel of an organic light emitting diode display according to an exemplary embodiment of the present invention.

[0051] As shown in FIG. 1, in the organic light emitting diode display according to an exemplary embodiment of the present invention, one sub-pixel PX includes a plurality of signal lines 121, 122, 171, and 172; a plurality of transistors

Td, Ts, and Tvth connected to the plurality of signal lines; a plurality of capacitors Cst and Cvth; and an organic light emitting diode OLED.

[0052] The plurality of transistors Td, Ts, and Tvth include a driving transistor Td, a switching transistor Ts, and a compensation transistor Tvth. The plurality of capacitors Cst and Cvth includes a storage capacitor Cst and a compensation capacitor Cvth.

[0053] The signal lines **121**, **122**, **171**, **172** includes a gate line **121** transmitting a scan signal Sn, a compensation control line **122** transmitting a compensation control signal Gc to the compensation transistor Tvth, a data line **171** crossing the gate line **121** and transmitting a data voltage Dm, and a driving voltage line **172** transmitting a driving voltage ELVDD to the driving transistor Td.

[0054] A gate electrode of the driving transistor Td is connected to one terminal of the compensation capacitor Cvth, a source electrode of the driving transistor Td is connected to the driving voltage line **172**, and a drain electrode of the driving transistor Td is electrically connected to an anode of the organic light emitting diode OLED.

[0055] The compensation transistor Tvth includes a gate electrode connected to the compensation control line **122**, a source electrode connected to the drain electrode of the driving transistor Td and the anode of the organic light emitting diode OLED, and a drain electrode connected to one terminal of the compensation capacitor Cvth and the gate electrode of the driving transistor Td. The compensation transistor Tvth is turned on according to the compensation control signal Gc transmitted through the compensation control line **122** such that the gate electrode and the drain electrode of the driving transistor Td are connected to each other, thereby diode-connecting the driving transistor Td.

[0056] A voltage corresponding to a threshold voltage of the driving thin film transistor Td is programmed in the compensation capacitor Cvth when the driving transistor Td is diode-connected.

[0057] The gate electrode of the switching thin film transistor Ts is connected to the gate line **121**, the source electrode of the switching thin film transistor Ts is connected to the data line **171**, and the drain electrode of the switching thin film transistor Ts is connected to the other terminal of the storage capacitor Cst and the other terminal of the compensation capacitor Cvth. The switching thin film transistor Ts is turned on according to the scan signal Sn transmitted through the gate line **121**.

[0058] One terminal of the storage capacitor Cst is connected to the driving voltage line **172**, and a gate-source voltage of the driving transistor Td is determined according to the programmed voltage in the compensation capacitor Cvth and the storage capacitor Cst. The cathode of the organic light emitting diode OLED is connected to a common voltage line **741** transmitting a common voltage ELVSS.

[0059] The organic light emitting diode OLED emits light according to a driving current Id transmitted through the driving transistor Td from the driving voltage line **172**, and the driving current Id flows into the common voltage line **741**.

[0060] The present invention is not limited to the 3-transistor and 2-capacitor structure is described herein, and the number of transistors and capacitors may vary.

[0061] A detailed structure of an organic light emitting diode display according to an exemplary embodiment of the present invention will be described below with reference to FIG. 2 and FIG. 3.

[0062] Referring to FIG. 2 and FIG. 3, a substrate **110** may be formed as an insulating substrate including glass, quartz, ceramic, or a plastic. The substrate **110** may be made of a flexible material.

[0063] Also, a buffer layer **120** is formed on the substrate **110**. The buffer layer **120** may be formed over an entire surface of the substrate **110** throughout the display area DA and the peripheral area PA. The buffer layer **120** may be formed as a single layer of a silicon nitride (SiNx), or as a dual-layer structure in which a silicon nitride (SiNx) and a silicon oxide (SiOx) are stacked. The buffer layer **120** may prevent permeation of undesirable components such as impurities or moisture, and may also planarize the surface of the substrate **110**.

[0064] A switching semiconductor layer and a driving semiconductor layer **135b** may be formed on the buffer layer **120** and may be separated from each other. Hereafter, the driving semiconductor layer will be described.

[0065] The driving semiconductor layer **135b** may be made of a polysilicon or an oxide semiconductor. The oxide semiconductor may include an oxide based on titanium (Ti), hafnium (Hf), zirconium (Zr), aluminum (Al), tantalum (Ta), germanium (Ge), zinc (Zn), gallium (Ga), tin (Sn), (In) such as zinc oxide (ZnO), indium-gallium-zinc oxide (In-GaZnO₄), indium zinc oxide (Zn—In—O), zinc-tin oxide (Zn—Sn—O), indium gallium oxide (In—Ga—O), indium-tin oxide (In—Sn—O), indium-zirconium oxide (In—Zr—O), indium-zirconium-zinc oxide (In—Zr—Zn—O), indium-zirconium-tin oxide (In—Zr—Sn—O), indium-zirconium-gallium oxide (In—Zr—Ga—O), indium-aluminum oxide (In—Al—O), indium-zinc-aluminum oxide (In—Zn—Al—O), indium-tin-aluminum oxide (In—Sn—Al—O), indium-aluminum-gallium oxide (In—Al—Ga—O), indium-tantalum oxide (In—Ta—O), indium-tantalum-zinc oxide (In—Ta—Zn—O), indium-tantalum-tin oxide (In—Ta—Sn—O), indium-tantalum-gallium oxide (In—Ta—Ga—O), indium-germanium oxide (In—Ge—O), indium-germanium-zinc oxide (In—Ge—Zn—O), indium-germanium-tin oxide (In—Ge—Sn—O), indium-germanium-gallium oxide (In—Ge—Ga—O), titanium-indium-zinc oxide (Ti—In—Zn—O), and/or hafnium-indium-zinc oxide (Hf—In—Zn—O) which are complex oxides thereof.

[0066] When the driving semiconductor layer **135b** is made of the oxide semiconductor, to protect the oxide semiconductor that is vulnerable to an external environment such as a high temperature, a separate passivation layer may be added.

[0067] The driving semiconductor layer **135b** includes a channel area in which impurities are not doped, and a source area and a drain area in which impurities are doped at respective sides of the channel area. The impurities used may be selected according to a kind of thin film transistor being used, and may be, for example, N-type impurities or P-type impurities.

[0068] The driving semiconductor layer **135b** is divided into a channel region **1355**, a source region **1356**, and a drain region **1357**. The source region **1356** and the drain region **1357** are respectively formed at opposite sides of the channel region **1355**.

[0069] The channel region **1355** of the driving semiconductor layer **135b** may include polycrystalline silicon in which no impurity is doped (an intrinsic semiconductor).

[0070] The source region **1356** and the drain region **1357** of the driving semiconductor layer **135b** may include polycrystalline silicon in which a conductive impurity is doped (an impurity semiconductor).

[0071] A gate insulating layer **140** is formed on the driving semiconductor layer **135b**. The gate insulating layer **140** may be a single layer or a multilayer including at least one of a silicon nitride and a silicon oxide.

[0072] A driving gate electrode **125b** is formed on the gate insulating layer **140**.

[0073] The driving gate electrode **125b** may be disposed on the driving semiconductor layer **135b**. The driving gate electrode **125b** may at least partially overlap the channel region **1355**.

[0074] An interlayer insulating layer **160** is formed on the driving gate electrode **125b**. The interlayer insulating layer **160** may be made of a silicon nitride or a silicon oxide.

[0075] The interlayer insulating layer **160** and the gate insulating layer **140** have a source contact hole **61** and a drain contact hole **62** respectively exposing the source region **1356** and the drain region **1357**. A driving source electrode **176b** and a driving drain electrode **177b** are formed on the interlayer insulating layer **160**.

[0076] The driving source electrode **176b** is connected to the source region **1356** through the source contact hole **61**. The driving drain electrode **177b** faces the driving source electrode **176b**.

[0077] The driving drain electrode **177b** is connected to the drain region **1357** through the drain contact hole **62**.

[0078] The driving semiconductor layer **135b**, the driving gate electrode **125b**, the driving source electrode **176b**, and the driving drain electrode **177b** form a driving thin film transistor T.

[0079] The driving thin film transistor T corresponds to a switching element. According to an exemplary embodiment of the present invention, the driving thin film transistor 1T may be formed in each sub-pixel of the organic light emitting diode display.

[0080] A planarization layer **180** is formed on the driving source electrode **176b** and the driving drain electrode **177b**. The planarization layer **180** serves to planarize a step and to thereby increase emission efficiency of the organic light emitting element that will be formed thereon.

[0081] The planarization layer **180** may be made of a polyacrylate resin, an epoxy resin, a phenolic resin, a polyamide resin, a polyimide resin, an unsaturated polyester resin, a polyphenylene ether resin, a polyphenylene sulfide resin, and/or benzocyclobutene (BCB).

[0082] As described above, the sub-pixel PX includes the display area DA and the peripheral area PA, and the display area DA may include the first electrode **710**, the organic emission layer **720**, and the second electrode **730** so as to emit light.

[0083] A first electrode, e.g. a pixel electrode **710**, is formed on the planarization layer **180**. The pixel electrode **710** may be formed of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), or indium oxide (In₂O₃), or a reflective metal such as lithium (Li), calcium (Ca), lithium fluoride/calcium (LiF/Ca), lithium fluoride/aluminum (LiF/Al), aluminum (Al), silver (Ag), magnesium (Mg), or gold (Au). For

example, the pixel electrode **710** may be formed by sequentially stacking ITO, Ag, and ITO.

[0084] The pixel electrode **710** is electrically connected to the driving drain electrode **177b** of the thin film transistor T through a contact hole **181** formed in the interlayer insulating layer **160**, thereby constituting the anode of the organic light emitting element **70**.

[0085] A pixel definition layer **350** is formed on the planarization layer **180** and an edge of the pixel electrode **710**. The pixel definition layer **350** has a fourth opening **352** exposing the pixel electrode **710**. The pixel definition layer **350** may also have a third opening **351** exposing a part of an auxiliary member **410**, which is described in greater detail below.

[0086] The pixel definition layer **350** may be made of a resin such as a polyacrylate resin and a polyimide resin, a silica-based inorganic material, or the like.

[0087] An organic emission layer **720** is formed in the fourth opening **352** of the pixel definition layer **350**. The organic emission layer **720** is formed on the first electrode **710** exposed in the display area DA and also extends to the peripheral area PA. As shown in FIG. 3, the organic emission layer **720** is also disposed in the third opening **351** of the pixel definition layer **350**.

[0088] The organic emission layer **720** has a multilayer structure including an emission layer and a hole-injection layer (HIL), a hole-transporting layer (HTL), electron-transporting layer (ETL), and/or an electron-injection layer (EIL).

[0089] When the organic emission layer **720** includes all of the above-mentioned layers, the hole injection layer may be disposed on the pixel electrode **710** to correspond to an anode, and the hole transporting layer, the emission layer, the electron transporting layer, and the electron injection layer may be sequentially stacked thereon.

[0090] The organic emission layer **720** may include a red emitting layer emitting red light, a green emitting layer emitting green light, and a blue emitting layer emitting blue light. The red emitting layer, the green emitting layer, and the blue emitting layer are respectively formed on a red pixel, a green pixel, and a blue pixel to implement a color image.

[0091] A second electrode (common electrode) **730**, is formed on the pixel definition layer **350** and the organic emission layer **720**. The common electrode **730** is formed as a single structure across the plurality of sub-pixels. For example, the common electrode **730** may be formed continuously throughout the red sub-pixel, the green sub-pixel, and the blue sub-pixel.

[0092] In addition, according to an exemplary embodiment of the present invention, the common electrode **730** extends to the peripheral area PA as well as the display area DA. Accordingly, the common electrode **730** may be disposed on the organic emission layer **720** within the peripheral area PA.

[0093] The common electrode **730** may include a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), or indium oxide (In₂O₃), or a reflective metal such as lithium (Li), calcium (Ca), lithium fluoride/calcium (LiF/Ca), lithium fluoride/aluminum (LiF/Al), aluminum (Al), silver (Ag), magnesium (Mg), or gold (Au).

[0094] The common electrode **730** acts as the cathode of the organic light emitting element **70**. As described above,

the pixel electrode **710**, the organic emission layer **720**, and the common electrode **730** form the organic light emitting element **70**.

[0095] In the peripheral area PA of the sub-pixel PX, the auxiliary electrode **310** may be disposed on the interlayer insulating layer **160**. The auxiliary electrode **310** transmits a common voltage ELVSS to the common electrode **730**. The auxiliary electrode **310** may correspond to a common voltage line transmitting the common voltage ELVSS.

[0096] The auxiliary electrode **310** may be exposed by a first opening **182** formed in the planarization layer **180**. A part of an upper surface of the auxiliary electrode **310** may be exposed by the first opening **182**.

[0097] A cross-sectional shape of the first opening **182** may be rectangular.

[0098] Accordingly, the auxiliary electrode **310** may also be exposed with the rectangular shape.

[0099] The auxiliary electrode **310** may be formed of the same layer as the above-described driving source electrode **176b** and driving drain electrode **177b**. For example, the auxiliary electrode **310**, the driving source electrode **176b**, and the driving drain electrode **177b** may be formed by forming and patterning the same metal layer on the interlayer insulating layer **160**.

[0100] The auxiliary electrode **310** may have a multilayer structure in which metal layers includes copper (Cu), copper alloys, aluminum (Al), aluminum alloys, molybdenum (Mo), and molybdenum alloys are stacked. For example, the auxiliary electrode **310** may have a triple-layer structure including titanium/aluminum/titanium (Ti/Al/Ti), molybdenum/aluminum/molybdenum (Mo/Al/Mo), or molybdenum/copper/molybdenum (Mo/Cu/Mo).

[0101] According to an exemplary embodiment of the present invention, an auxiliary member **410** that is in contact with the auxiliary electrode **310** is disposed on the auxiliary electrode **310**. The auxiliary member **410** is in contact with the auxiliary electrode **310**, thereby transmitting the common voltage ELVSS through the auxiliary electrode **310** to the common electrode **730**.

[0102] The auxiliary member **410** is in contact with the entire upper surface of the auxiliary electrode **310** exposed in the first opening **182**. For example, to not expose the planarization layer **180** between the auxiliary electrode **310** and the auxiliary member **410**, the auxiliary member **410** covers the entire upper surface of the auxiliary electrode **310**.

[0103] According to an exemplary embodiment of the present invention, the auxiliary member **410** is only disposed within the first opening **182** of the planarization layer **180**. The auxiliary member **410** is in contact with a part of an interior circumference of the first opening **182**. For example, part of the auxiliary member **410** is not disposed at the upper surface of the planarization layer **180**.

[0104] Referring to FIG. 4 and FIG. 5, if the planarization layer **180** is formed between an auxiliary member **440** and the auxiliary electrode **310**, in the process of forming a second opening **721** in the organic emission layer **720** by using a laser L, the auxiliary member **440** may be damaged.

[0105] For example, when the auxiliary member **440** is made of an first ITO layer **441**, a Ag layer **442**, and a second ITO layer **443**, while the auxiliary member **440** is bent to the side of the planarization layer **180** by the laser L, the first ITO layer **441**, the Ag layer **442**, and the second ITO layer **443** may each be cut (F). Accordingly, while the remaining

gas component in the planarization layer of the organic layer is discharged through the cut region (F), the common electrode **730** may be oxidized. If the common electrode **730** is oxidized, the organic emission layer **720** might not emit light.

[0106] Referring to FIG. 3, according to an exemplary embodiment of the present invention, as the auxiliary member **410** is disposed to be in contact with the exposed entire upper surface of the auxiliary electrode **310**, the auxiliary member **410** may be prevented from being bent in the lower direction and damaged by the laser L. Accordingly, the oxidization of the common electrode **730** is prevented and generation of a dark spot of the organic light emitting diode display due to lack of emission of the organic emission layer **720** may be prevented.

[0107] The auxiliary electrode **310** of the metal material disposed under the auxiliary member **410** serves to support the auxiliary member **410**.

[0108] As the auxiliary member **410** is in contact with the entire upper surface of the auxiliary electrode **310**, a contact area of the auxiliary member **410** and the auxiliary electrode **310** increases such that resistance of the wire to which the common voltage is transmitted may be reduced. Accordingly, in the organic light emitting diode display, the voltage drop (IR-Drop) may be prevented and accordingly, the luminance may remain uniform.

[0109] The auxiliary member **410** may be formed of the same layer as the first electrode **710**. The auxiliary member **410** may be made of a transparent conductive material such as indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), or indium oxide (In₂O₃), or a reflective metal such as lithium (Li), calcium (Ca), lithium fluoride/calcium (LiF/Ca), lithium fluoride/aluminum (LiF/Al), aluminum (Al), silver (Ag), magnesium (Mg), or gold (Au). For example, the auxiliary member **410** may be formed by sequentially stacking ITO, Ag, and ITO.

[0110] In FIG. 4, the auxiliary member **410** is disposed within the first opening **182**, however part of an auxiliary member **440** may be disposed at the upper surface of the planarization layer **180**. As shown in FIG. 6, the auxiliary member **420** fills the first opening **182** of the planarization layer **180**, and a part thereof may be disposed at the upper surface of the planarization layer **180**.

[0111] According to an exemplary embodiment of the present invention, the organic emission layer **720** is disposed on the auxiliary member **410** in the peripheral area PA. In the organic emission layer **720**, a second opening **721** exposing part of the underlying auxiliary member **410** is formed. The second opening **721** of the organic emission layer **720** is formed by the laser L. After the organic emission layer **720** is coated on the auxiliary member **410**, the organic emission layer **720** is irradiated by the laser L in the region where the auxiliary member **410** and the auxiliary electrode **310** are overlapped with each other.

[0112] By the laser L, the second opening **721** is formed in the organic emission layer **720**. The cross-sectional shape of the second opening **721** may be circular.

[0113] A diameter H2 of the second opening **721** may be smaller than a width H1 of the first opening **182**. However, the present invention is not limited to this particular structure, and the diameter H2 of the second opening **721** may be formed to be equal to the width H1 of the first opening **182**. If the diameter H2 of the second opening **721** increases, the contact area of the auxiliary member **410** and the overlying

second electrode 730 may increase. As described above, if the contact area increases, the resistance of the wire transmitting the common voltage may be reduced.

[0114] In the peripheral area PA, a second electrode 730 may be formed on the organic emission layer 720. The second electrode 730 may be in contact with the auxiliary member 410 through the second opening 721. Accordingly, the second electrode 730 may be electrically connected to the auxiliary member 410 and the auxiliary electrode 310. Therefore, the common voltage ELVSS supplied through the auxiliary electrode 310 may be supplied to the second electrode 730 through the auxiliary member 410.

[0115] Hereinafter, a method of manufacturing the organic light emitting diode display according to an exemplary embodiment of the present invention will be described. When describing the manufacturing method of the organic display device according to an exemplary embodiment of the present invention, it may be understood that like elements may be similar to or identical to corresponding elements that were already described, and accordingly, repeated description of these elements may be omitted.

[0116] First, as shown in FIG. 7, a thin film transistor T is formed on a substrate 110. The thin film transistor T may be the switching thin film transistor or the driving thin film transistor.

[0117] The thin film transistor T includes a semiconductor layer 135b, a gate electrode 125b, a source electrode 176b, and a drain electrode 177b. The gate electrode 125b is spaced apart from the semiconductor layer 135b. The source electrode 176b and the drain electrode 177b are disposed above the gate electrode 125b.

[0118] An auxiliary electrode 310 is simultaneously formed with the source electrode 176b and the drain electrode 177b. After coating the metal layer on the interlayer insulating layer 160, a photolithography process is performed on the metal layer to form the auxiliary electrode 310, and to divide the source electrode 176b and the drain electrode 177b.

[0119] Next, a planarization layer 180 is formed on the source electrode 176b and drain electrode 177b, and the auxiliary electrode 310.

[0120] Also, referring to FIG. 8, by the patterning process, a contact hole 181 exposing part of the auxiliary electrode 310 and a first opening 182 exposing part of the drain electrode 177b are formed in the planarization layer 180.

[0121] The cross-sectional shape of the first opening 182 may be rectangular.

[0122] Accordingly, the exposed auxiliary electrode 310 may be exposed with the rectangular shape.

[0123] Next, a first electrode 710 and an auxiliary member 410 are formed on the planarization layer 180, thereby the first electrode 710 is in contact with the drain electrode 177b and the auxiliary member 410 is in contact with the auxiliary electrode 310. The auxiliary member 410 is in contact with the entire upper surface of the auxiliary electrode 310 exposed by the first opening 182.

[0124] The first electrode 710 and the auxiliary member 410 are formed with the same layer. For example, after the same metal layer is formed on the planarization layer 180, the photolithography process is performed on the metal layer to form the first electrode 710 and to divide the auxiliary member 410.

[0125] Next, as shown in FIG. 9, a pixel definition layer 350 is formed on the planarization layer 180. In the pixel

definition layer 350, a third opening 351 exposing part of the auxiliary member 410 and a fourth opening 352 exposing part of the first electrode 710 are formed.

[0126] Next, an organic emission layer 720 is coated on the pixel definition layer 350. Referring to FIG. 10, the organic emission layer 720 is formed in the display area DA and the peripheral area PA. The organic emission layer 720 is disposed inside the third opening 351 and the fourth opening 352 of the pixel definition layer 350 to cover the auxiliary member 410 and the first electrode 710, respectively.

[0127] According to an exemplary embodiment of the present invention, after coating the organic emission layer 720, part of the organic emission layer 720 is removed to expose part of the auxiliary member 410 in the peripheral area PA. If part of the organic emission layer 720 is removed, a second opening 721 is formed in the organic emission layer 720.

[0128] Referring to FIG. 11, part of the organic emission layer 720 is removed by using the laser L to form the second opening 721. After the laser L is positioned at a center part of the region where the auxiliary member 410 and the auxiliary electrode 310 are overlapped, the organic emission layer 720 is irradiated by the laser L. The second opening 721 formed in the organic emission layer 720 may be made with a circular shape by the laser L.

[0129] As described above, as the auxiliary electrode 310 is disposed to be in contact under the auxiliary member 410, the auxiliary member 410 might not be bent down and damaged by the laser L.

[0130] Next, the second electrode 730 is formed on the organic emission layer 720. The second electrode 730 may be in contact with the auxiliary member 410 through the second opening 721. Accordingly, the second electrode 730 may be electrically connected to the auxiliary member 410 and the auxiliary electrode 310. Therefore, the common voltage ELVSS supplied through the auxiliary electrode 310 may be supplied to the second electrode 730 through the auxiliary member 410.

[0131] In the organic light emitting diode display and the method of manufacturing the OLED display, according to an exemplary embodiment of the present invention, in the process of removing part of the organic emission layer 720 by using the laser L, the auxiliary member 410 may be prevented from being damaged by the laser L. Additionally, the common electrode 730 may be prevented from being oxidized as remaining gas component of the organic layer is prevented from being discharged along a gap of a damaged auxiliary member 410.

[0132] While this invention has been described in connection with what is presently considered to be practical exemplary embodiments, it is to be understood that the invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the present disclosure.

What is claimed is:

1. A method for manufacturing an organic light emitting diode display, comprising:

preparing a substrate;

forming a thin film transistor including a semiconductor layer, a gate electrode on the semiconductor layer, and a source electrode and a drain electrode connected to the semiconductor layer on the substrate;

forming an auxiliary electrode supplying a common voltage on the substrate;

forming an insulating layer on the thin film transistor and the auxiliary electrode and exposing parts of the drain electrode and the auxiliary electrode;

forming a first electrode on the insulating layer and in contact with the drain electrode;

forming an auxiliary member in contact with the auxiliary electrode through a first opening formed in the insulating layer;

forming an organic emission layer on the first electrode and the auxiliary member;

removing a part of the organic emission layer to expose a part of the auxiliary member; and

forming a second electrode on the organic emission layer.

2. The method of claim 1, wherein

the removing of the part of the organic emission layer is performed by using a laser.

3. The method of claim 1, wherein

the removing of the part of the organic emission layer includes forming a second opening by removing the part of the organic emission layer.

4. The method of claim 3, wherein

the second opening has a circular shape.

5. The method of claim 1, further comprising

forming a pixel definition layer having a third opening exposing the part of the auxiliary member and a fourth opening exposing the part of the first electrode.

6. The method of claim 1, wherein:

the source electrode, the drain electrode, and the auxiliary electrode are formed with the same layer.

7. The method of claim 1, wherein

the first electrode and the auxiliary member are formed with the same layer.

8. The method of claim 1, wherein

the auxiliary member is in contact with an entire upper surface of the auxiliary electrode exposed by the first opening.

* * * * *

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	US20190081111A1	公开(公告)日	2019-03-14
申请号	US16/186817	申请日	2018-11-12
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE SE HO KIM TAE HYUNG SONG JE HYUN		
发明人	LEE, SE HO KIM, TAE HYUNG SONG, JE-HYUN		
IPC分类号	H01L27/32 H01L51/00 H01L27/12 H01L51/52		
CPC分类号	H01L27/127 H01L51/5228 H01L51/0002 H01L2227/32 H01L27/3276 H01L27/3206 H01L51/0023 H01L27/3279		
优先权	1020160165997 2016-12-07 KR		
其他公开文献	US10446613		
外部链接	Espacenet USPTO		

摘要(译)

根据示例性实施例的有机发光二极管显示器包括：基板；像素形成在基板上并包括显示图像的像素区域和与像素区域相邻的周边区域；像素区域的绝缘层和基板上的外围区域；绝缘层上的像素区域的第一电极；第一电极上的有机发光层并延伸到周边区域；有机发光层上的第二电极，设置在像素区域和周边区域；在基板上的周边区域中的辅助电极，并且由形成在绝缘层中的第一开口部分地暴露；辅助构件设置在辅助电极上并与由第一开口暴露的辅助电极的上表面接触。

