



US009048208B2

(12) **United States Patent**
Kim

(10) **Patent No.:** **US 9,048,208 B2**
(45) **Date of Patent:** **Jun. 2, 2015**

(54) **ORGANIC LIGHT EMITTING DISPLAY AND FABRICATING METHOD THEREOF**

USPC 438/29, 34, 35, 58; 257/40, 88, 99,
257/E51.018, E51.022, E51.024, E27.119
See application file for complete search history.

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin, Gyeonggi-Do (KR)

(56) **References Cited**

(72) Inventor: **Tae-Kyu Kim**, Yongin (KR)

U.S. PATENT DOCUMENTS

(73) Assignee: **SAMSUNG DISPLAY CO., LTD.**,
Yongin, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

8,772,767 B2 *	7/2014	Dobbs et al.	257/40
2008/0036706 A1	2/2008	Kitazawa	
2010/0176383 A1	7/2010	Park et al.	
2012/0091482 A1 *	4/2012	Uchida et al.	257/88
2013/0001532 A1 *	1/2013	Hwang et al.	257/40
2014/0175390 A1 *	6/2014	Kim et al.	257/40
2014/0346453 A1 *	11/2014	Koo et al.	257/40

FOREIGN PATENT DOCUMENTS

(21) Appl. No.: **14/321,033**

KR	10-2008-0013730	2/2008
KR	10-2010-0082940	7/2010
KR	10-2012-0047003 A	5/2012

(22) Filed: **Jul. 1, 2014**

(65) **Prior Publication Data**

US 2015/0008410 A1 Jan. 8, 2015

* cited by examiner

(30) **Foreign Application Priority Data**

Primary Examiner — Dao H Nguyen

(74) *Attorney, Agent, or Firm* — Lee & Morse, P.C.

Jul. 2, 2013 (KR) 10-2013-0077107

(57) **ABSTRACT**

(51) **Int. Cl.**
H01L 51/54 (2006.01)
H01L 27/32 (2006.01)
H01L 51/56 (2006.01)

A method of making a display device includes forming first electrodes of organic light emitting diodes in respective pixel areas on a substrate, forming a first common layer on the first electrodes in the pixel areas, forming emission layers in the pixel areas on the first common layer, forming a second electrode of the organic light emitting diodes on the emission layer, and applying physical pressure to divide the first common layer.

(52) **U.S. Cl.**
CPC **H01L 27/3248** (2013.01); **H01L 51/56**
(2013.01)

(58) **Field of Classification Search**
CPC H01L 27/3248; H01L 51/56

15 Claims, 6 Drawing Sheets





FIG. 1






FIG. 4A




FIG. 4B




FIG. 5




FIG. 6




FIG. 7





FIG. 8



ORGANIC LIGHT EMITTING DISPLAY AND FABRICATING METHOD THEREOF

CROSS-REFERENCE TO RELATED APPLICATION

Korean Patent Application No. 10-2013-0077107, filed on Jul. 2, 2013, and entitled, "Organic Light Emitting Display and Fabricating Method Thereof," is incorporated by reference herein in its entirety.

BACKGROUND

1. Field

One or more embodiments described herein relates to a display device.

2. Description of the Related Art

The performance of displays must increase as information technology evolves. Flat panel displays have been developed in pursuit of this goal. One type of flat panel display, known as an organic light emitting diode (OLED) display, has pixels which output light based on a recombination of electrons and holes in corresponding active layers. Displays of this type have demonstrated relatively fast response speed, low-voltage driving and power consumption, and excellent viewing angle.

SUMMARY

In accordance with one or more embodiments, a method of making a display device includes forming first electrodes of organic light emitting diodes (OLEDs) in respective pixel areas on a substrate, forming a first common layer on the first electrodes in the pixel areas, forming emission layers in the pixel areas on the first common layer, forming a second electrode of the OLEDs on the emission layer, and applying physical pressure to divide the first common layer. Applying the physical pressure may include applying a force to the first common layer in a different direction of a plane including the substrate.

Applying the physical pressure may include placing a panel on a substrate support having a plurality of grooves, the panel including the first electrodes, the first common layer, the emission layers, and the second electrode, and moving at least one of the panel or the substrate support in a second direction intersecting a first direction, while applying a force in the first direction to divide the first common layer. The substrate support may include first and second regions, each having grooves at a predetermined interval, the grooves in adjacent regions alternately positioned to cross each other. The first direction may be perpendicular to the second direction.

The method may include moving the panel onto the second region on the substrate support when at least one region of the panel is positioned in the first region on the substrate support, wherein moving the panel includes applying the force to the panel in the first direction. Each of the first and second regions of the substrate support may include a plurality of grooves having substantially a same interval and width.

Applying the physical pressure may include applying a force to a panel in a first direction while rotating at least one roller in a second direction crossing the first direction, the at least one roller including a plurality of grooves and the panel including the first electrodes, the first common layer, the emission layers, and the second electrode.

Applying the physical pressure may include rotating a plurality of rollers on the first common layer, each of the

rollers having grooves at a predetermined interval and the rollers are rotated so that the grooves of the rollers are alternately positioned.

Applying the physical pressure may include rotating a plurality of rollers on the first common layer, each of the rollers having a plurality of diagonal grooves.

A number k OLEDs may share the first common layer, where $k \geq 2$, and one or more pixels having a number smaller than the k pixels may share the divided first common layer. Pixels in a horizontal or vertical line may share the first common layer, and applying the physical pressure may include dividing the first common layer into at least two first common layers. At least two first common layers may be divided relative to the horizontal and vertical pixel lines.

Forming a second common layer on the emission layer may allow a plurality of pixels to share the second common layer, and the second common layer may be formed between forming the emission layers and forming of the second electrode. The second common layer may be simultaneously divided with the first common layer.

The first electrodes and emission layers may be patterned for corresponding pixels, and the second electrode may be entirely formed on a pixel unit so that all the pixels share the second electrode.

In accordance with another embodiment, an organic light emitting display includes a plurality of pixels, each of the pixels including at least one organic light emitting diode (OLED) which includes: a first electrode and an emission layer in a respective pixel area, a first common layer between the first electrode and emission layer, and a second electrode on the emission layer, a plurality of pixels sharing the first common layer, wherein the first common layer is divided with respect to a horizontal or vertical pixel line.

The first common layer may be disposed to be divided with respect to horizontal and vertical pixel lines. The OLED may include a second common layer between the emission layer and second electrode, and a plurality of pixels may share the second common layer. The second common layer may be divided with respect to a horizontal or vertical pixel line. The first electrode and emission layer may be patterned for a corresponding one of the pixels, and two or more of the pixels may share the second electrode.

BRIEF DESCRIPTION OF THE DRAWINGS

Features will become apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

FIG. 1 illustrates an embodiment of an organic light emitting display;

FIG. 2 illustrates an embodiment of a pixel in the display;

FIG. 3 illustrates a sectional view of the pixel;

FIGS. 4A and 4B illustrate an embodiment of a method for cutting off leakage current in the pixel;

FIG. 5 illustrates divided common layers of an organic light emitting display;

FIG. 6 illustrates an embodiment of a method for dividing a common layer;

FIG. 7 illustrates another embodiment of a method for dividing a common layer; and

FIG. 8 illustrates another embodiment of a method for dividing a common layer.

DETAILED DESCRIPTION

Example embodiments are described more fully hereinafter with reference to the accompanying drawings; however,

they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. It will also be understood that when a layer or element is referred to as being “on” another layer or substrate, it can be directly on the other layer or substrate, or intervening layers may also be present. Further, it will be understood that when a layer is referred to as being “under” another layer, it can be directly under, and one or more intervening layers may also be present. In addition, it will also be understood that when a layer is referred to as being “between” two layers, it can be the only layer between the two layers, or one or more intervening layers may also be present. Like reference numerals refer to like elements throughout.

FIG. 1 illustrates an embodiment of an organic light emitting display. FIG. 2 illustrates an embodiment of a pixel in FIG. 1. Referring to FIG. 1, the organic light emitting display includes a pixel unit 20, a scan driver 30, an emission control driver 40, a data driver 50, and a timing controller 60.

The pixel unit 20 includes a plurality of pixels 10, each including at least one organic light emitting diode. The pixels 10 may be arranged, for example, in a matrix form at intersection portions of scan lines S1 to Sn and data lines D1 to Dm.

As shown in FIG. 2, pixels 10 include a first color pixel 10R, a second color pixel 10G, and a third color pixel 10B. The first color pixel 10R includes a first color OLEDr emitting light of a first color (e.g., red). The second color pixel 10G includes an OLEDg emitting light of a second color (e.g., green). The third color pixel 10B includes an OLEDb emitting light of a third color (e.g., blue). Adjacent first to third color pixels 10R, 10G, and 10B may be considered to form a pixel unit expressing various colors.

Each pixel 10 may also include a pixel circuit 12 to supply driving current to the OLED. An example of the configuration and operation of each pixel 10 will be described with reference to FIG. 2.

Specifically, each pixel 10 includes a pixel circuit 12 coupled to the OLED. The pixels 10 may be classified into first to third color pixels 10R, 10G, and 10B according to the color of light emitted from their OLEDs.

A first electrode (e.g., an anode electrode) of the OLED is coupled to a first pixel power source ELVDD via the pixel circuit 12. A second electrode (e.g., a cathode electrode) of the OLED is coupled to a second pixel power source ELVSS. The OLED emits light with luminance corresponding to driving current from the pixel circuit 12.

Each pixel circuit 12 may include first to third transistors M1, M2, and M3, and a storage capacitor Cst. In other embodiments, the pixels 10 or pixel circuit 12 may have a different structure.

A first electrode of the first transistor M1 is coupled to a data line D. A second electrode of the first transistor M1 is coupled to a first node N1. The first and second electrodes of the first transistor M1 are different electrodes. For example, when the first electrode is a source electrode, the second electrode is a drain electrode, or vice versa. A gate electrode of the first transistor M1 is coupled to a scan line Sn.

The first transistor M1 is turned on when a scan signal having a predetermined voltage (e.g., a low voltage) is supplied from the scan line, to thereby allow the data line D and first node N1 to be coupled to each other. A data signal of a corresponding pixel 10 is supplied to the data line D. Accord-

ingly, the data signal is supplied to first node N1. The charge corresponding to the data signal supplied to the first node N1 is stored in the storage capacitor Cst.

A first electrode of the second transistor M2 is coupled to the first pixel power source ELVDD. A second electrode of the second transistor M2 is coupled to the first electrode of the OLED via the third transistor M3. A gate electrode of the second transistor M2 is coupled to the first node N1. The second transistor M2 controls the amount of driving current supplied to the OLED, based on the voltage at first node N1.

A first electrode of the third transistor M3 is coupled to the second electrode of the second transistor M2. A second electrode of the third transistor M3 is coupled to the first electrode of the OLED. A gate electrode of the third transistor M3 is coupled to an emission control line En. The third transistor M3 is turned off during a non-emission period in which an emission control signal having a predetermined voltage (e.g., a high voltage) is supplied from the emission control line En. When the third transistor M3 is turned off, the driving current is cut off so that it does not flow through the OLED.

The third transistor M3 is turned on during an emission period, e.g., during which supply of the emission control signal is stopped. The emission period may correspond, for example, to a period in which the voltage of the emission control signal is set to a low voltage. During the emission period, driving current is supplied from the second transistor M2 to the OLED.

One electrode of the storage capacitor Cst is coupled to the first pixel power source ELVDD. The other electrode of the storage capacitor Cst is coupled to the first node N1. The storage capacitor Cst charges to a voltage corresponding to the data signal supplied to the first node N1, and stores this voltage, for example, until a data signal of the next frame is supplied.

The pixel 10 may have a relatively simple structure. For example, pixel 10 may include first transistor M1 for supplying a data signal, storage capacitor Cst for storing the data signal, second transistor M2 for supplying driving current to the OLED, and third transistor M3 for controlling the emission period of the pixel 10, as illustrated in FIG. 2. The pixel 10 may have a different structure in other embodiments. For example, pixel circuit 12 may include other circuit devices such as a transistor device for compensating for the threshold voltage of the second transistor M2 and/or a transistor device for initializing the first node N1.

The pixel 10 is selected by the scan signal from the scan line Sn during a scan period of a corresponding horizontal line. When the scan signal is received, a data signal is transferred from the data line D coupled thereto. In this case, the emission period of the pixel 10 is controlled based on the emission control signal from the emission control line En.

When driving current corresponding to the data signal is supplied to the OLED, pixel 10 emits light with a luminance corresponding to the driving current. However, when a black gray scale value is to be displayed in the pixel in a corresponding period, the data signal may cut off current to the OLED. Accordingly, the OLED does not emit light to thereby display the black gray scale value.

Referring again to FIG. 1, the scan driver 30 selects a pixel line (horizontal pixel line) to receive data signals for each horizontal period in one frame, while supplying a scan signal to scan lines S1 to Sn. For example, the scan driver 30 may progressively select scan lines S1 to Sn and supply the progressively shifted scan signals to the scan lines S1 to Sn.

The emission control driver 40 controls the emission of pixels 10 on at least one pixel line, while supplying emission control signals to emission control lines E1 to En. For

example, the emission control driver **40** cuts off driving current flowing through OLED positioned on a corresponding pixel line during a predetermined non-emission period, including a data writing period, of each pixel line. The emission control driver **40** supplies, to emission control lines E, emission control signals which enable driving current to be supplied to the OLED during an emission period of each pixel line.

The data driver **50** generates data signals based on data supplied from the timing controller **60**, and supplies the generated data signals to pixels **10** through the data lines D1 to Dm.

The timing controller **60** controls the scan driver **30**, emission control driver **40**, and data driver **50** based on one or more control signals that may be externally supplied.

In the organic light emitting display configured as described above, when scan signals are supplied from scan driver **30** through scan lines S1 to Sn, pixels **10** receive the data signals from the data driver **50** through corresponding ones of the data lines D1 to Dm. The pixels **10** also receive emission control signals from the emission control driver **40** through corresponding ones of the emission control lines E1 to En.

Then, driving current with an amplitude corresponding to the data signals flow through the OLEDs of respective ones of the pixels during emission periods corresponding to emission control signals, so that pixels **10** emit light with gray scale values corresponding to the data signals.

When a black gray scale is to be displayed in a predetermined pixel **10**, the data signal is supplied to cut off the driving current flowing through the a corresponding OLED during a corresponding period. Accordingly, the OLED does not emit light and thereby implements the black gray scale value.

However, a path along which leakage current can flow between pixels **10** may be formed according to the structure of the pixels **10**. For example, the OLED in each pixel **10** may include a common layer shared by a plurality of pixels **10**, in addition to a first electrode and an emission layer, patterned for each pixel.

In this case, even the pixel **10** receiving a data signal corresponding to a black gray scale value may emit some amount of light. This is because leakage current flows through the common layer due to parasitic resistance in the common layer. Therefore, the OLED of a pixel **10** intended to implement a black gray scale value is weakly turned on. In this case, pixel **10** does not completely express the black gray scale value. Therefore, deterioration of image quality may result. This will be described in detail with reference to FIGS. 3 to 4B.

FIG. 3 illustrates a main-portion sectional view of the pixel in FIG. 2. For illustrative purposes, only the OLED of each pixel **10R**, **10G** or **10B** in FIG. 2 and a transistor T4 coupled to the OLED will be shown in FIG. 3.

Referring to FIG. 3, an OLED including an emission layer **233** of a corresponding color and a transistor Tr (e.g., the third transistor M3 of FIG. 2) coupled to the OLED are formed in the region of each pixel **10R**, **10G**, and **10B**. Transistor Tr is formed on a substrate **200**. A planarization layer **210** is formed on the transistor Tr. Here, the substrate **200** is formed of glass, plastic, silicon, synthetic resin or the like.

The planarization layer **210** may be formed of an insulative material such as a nitride or oxide layer. A via hole **212**, through which transistor Tr and the OLED are electrically coupled to each other, is formed in the planarization layer **210**.

The OLED coupled to transistor Tr through the via hole **212** is formed on the planarization layer **210**. More specifically, the OLED includes a first electrode **231**, a first common layer **232**, an emission layer **233**, a second common layer **234**, and a second electrode **235** sequentially formed on the planarization layer **210**. The first and second common layers **232** and **234** may be selectively provided. In this embodiment, the OLED includes at least one first common layer **232** and/or at least on second common layer **234**.

The first electrode **231** of the OLED may be patterned for each pixel **10R**, **10G**, and **10B**. A pixel defining layer **220** is formed between adjacent pixels **10R**, **10G**, and **10B**, so that the region of each pixel **10R**, **10G**, or **10B** can be defined. The pixel defining layer **220** may be made of, for example, of one or more of an acrylic organic compound or an insulative material such as polyamide or polyimide.

The first common layer **232** is formed on the first electrode **231** of the OLED and pixel defining layer **220**. The first common layer **232** may include a hole injection layer and/or a hole transport layer. The first common layer **232** may be formed so that the plurality of pixels **10R**, **10G**, and **10B** share the first common layer **232** for the purpose of convenience in the fabricating process of the organic light emitting display.

For example, the first common layer **232** may be formed in a stripe shape so that at least pixels for each horizontal or vertical pixel line share a single first common layer **232**. Alternatively, the first common layer **232** may be entirely formed on the pixel unit, so that all pixels **10R**, **10G**, and **10B** in the pixel unit share a single first common layer **232**.

In one embodiment, the first common layer **232** may be commonly formed on the first electrodes of the pixels **10R**, **10G**, and **10B**, which share first common layer **232** and pixel defining layer **220**. The first common layers **232** between adjacent pixels **10R**, **10G**, and **10B** may be integrally coupled on the pixel defining layer **220**.

The emission layer **233** is formed on the first common layer **232**. The emission layer **233** may be patterned for each pixel **10R**, **10G**, or **10B** to overlap first electrode **231**. The second common layer **234** is formed on the emission layer **233**. The second common layer **234** may include an electron transport layer and/or an electron injection layer.

Like the first common layer **232**, the second common layer **234** may be formed so that a plurality of pixels **10R**, **10G**, and **10B** share second common layer **234**. In one embodiment, a plurality of second common layers **234** may be patterned in a stripe shape on the pixel unit. Alternatively, a single second common layer **234** may be entirely formed on the pixel unit.

That is, second common layer **234** may be formed to overlap at least electrode **231** and emission layer **233**. In this case, the second common layer **234** may extend to the region of the pixel defining layer **220**, so that the second common layers **234** between adjacent pixels **10R**, **10G**, and **10B** can be integrally coupled on the pixel defining layer **220**.

The second electrode **235** of the OLED may be formed on the second common layer **234**. For example, the second electrode **235** may be entirely formed on the pixel unit, but this is not necessary. The second electrode **235** may be patterned to have a variety of shapes.

As described above, an OLED is formed in the area of each of pixels **10R**, **10G**, or **10B** on the substrate **200**. The first electrode **231** the emission layer **233** of the OLED is may be patterned in the area of each pixel **10R**, **10G**, or **10B**, and the second electrode **235** of the OLED, for example, may be entirely formed on the pixel unit, so that all the pixels share the second electrode **235**.

In one embodiment, the OLED in each pixel **10R**, **10G**, or **10B** may include at least one of a first common layer **232**

formed between the first electrode **231** and emission layer **233**, or a second common layer **234** formed between the emission layer **233** and second electrode **235**. The first common layer **232** and/or the second common layer **234** may be formed so that a plurality of pixels **10R**, **10G**, and **10B** share the first common layer **232** and/or the second common layer **234**.

One embodiment of a method of fabricating an organic light emitting display including pixels having OLEDs will now be described. In this embodiment, the method includes forming a first electrode **231** in an area of each pixel **10R**, **10G**, and **10B**. A first common layer **232** is formed on the first electrodes **231** of the OLED, so that a plurality of pixels **10R**, **10G**, and **10B** share the first common layer **232**. An emission layer **233** is formed in the area of each pixel **10R**, **10G**, and **10B** on the first common layer **232**. A second electrode **235** of the OLED is formed on the emission layer **233**.

The method may further include forming a pixel defining layer **220** to define the areas of pixels **10R**, **10G**, and **10B**. The pixel defining layer **220** may be formed between formation of the first electrode **231** of the OLED and formation of the first common layer **232**.

The first common layer **232** may be formed on the first electrodes **231** of the OLED, so that k pixels (k is a natural number of 2 or more) share a single common layer **232**. For example, in forming first common layer **232**, the first common layer **232** may be formed on the first electrodes of the OLEDs, so that pixels **10R**, **10G**, and **10B** on one or more horizontal pixel lines and/or one or more vertical pixel lines share a single first common layer **232**. The first common layer **232** may be patterned in a stripe shape on the pixel unit, or may be entirely formed on the pixel unit.

Previously, the second common layer **234** was indicated to be selectively provided with first common layer **232**. In other embodiments, the first common layer **232** may be omitted and only the second common layer **234** may be formed.

When the first common layer **232** and/or second common layer **234** are/is formed so that a plurality of pixels **10R**, **10G** and **10B** share the first common layer **232** and/or the second common layer **234**, the patterning process may be simplified, thereby improving efficiency of the fabricating process of the organic light emitting display.

However, in a case where leakage current flows via the first common layer **232** and/or the second common layer **234** due to parasitic resistance in the first common layer **232** and/or the second common layer **234**, a small amount of light may be generated in one or more of pixels **10R**, **10G**, or **10B** which are intended to implement black gray scale value. Particularly, the second electrode **235** of the OLED is coupled to the second pixel power source ELVSS. Therefore, if leakage current flows in the first common layer **232**, a small amount of light may be generated in the emission layer **233**.

In order to solve this problem, in one embodiment, the first common layer **232** is divided into first common layers, each having a size smaller than that of the first common layer **232**. Dividing the first common layers in this manner is effective to reduce or cut off leakage current. In another embodiment, leakage current may be reduced or cut off by dividing the first common layer **232** and/or the second common layer **234** into first common layers and/or second common layers, each having a size smaller than that of the first common layer **232** and/or the second common layer **234**.

FIGS. **4A** and **4B** illustrate a sectional views that correspond to one embodiment of a method for reducing or cutting off leakage current. For convenience, only OLEDs of three

adjacent pixels are shown. FIG. **5** illustrates a plan view illustrating divided common layers according to this embodiment.

Referring to FIG. **4A**, leakage current may be generated in the first common layer **232** and/or the second common layer **234**, so that a plurality of pixels share the first common layer **232** and/or the second common layer **234**. For example, leakage current I_{leak} may be generated along the first common layer **232** between the pixels due to parasitic resistance of the first common layer **232**.

In this case, the second electrode **235** of OLED **235** is coupled to the second pixel power source ELVSS. Therefore, if the leakage current I_{leak} flows in the first common layer **232**, the OLED in which the driving current from pixel circuit **12** is cut off (i.e., the OLED to implement a black gray scale value by non-emission) may be slightly turned on by leakage current I_{leak} , so that a small amount of light is generated. This increases black luminance, and therefore results in deterioration of image quality.

In order to overcome this problem, in one embodiment, the common layer in which leakage current flows (e.g., the first common layer **232**) is divided by being cut at regions between the pixels, as shown in FIG. **4B**. Accordingly, it is possible to prevent abnormal emission of the OLED caused by leakage current I_{leak} , thereby improving black luminance.

Although FIG. **4B** illustrates that only the first common layer **232** is divided, in other embodiments only the second common layer **234** may be divided, or both the first and second common layers **232** and **234** may be divided, to produce a cut-off effect for the leakage current I_{leak} .

Also, although FIG. **4B** illustrates that the first common layer **232** is divided for each pixel, the first common layer **232** and/or the second common layer **234** may be practically divided in units of a plurality of pixels.

For example, as shown in FIG. **5**, the first common layer **232** and/or the second common layer **234** are/is formed by being patterned in a stripe shape in the horizontal direction on the pixel unit **20**. As a result, pixels **10** on consecutive horizontal pixel lines share a single first common layer **232** and/or a single second common layer **234**. In one embodiment, the first common layer **232** and/or second common layer **234** may be divided by being cut between the pixels **10** (e.g., an upper portion of the pixel defining layer) in the unit of b vertical pixel lines along the vertical direction of the pixel unit **20**.

When the first common layer **232** and/or the second common layer **234** are/is formed by being patterned in a stripe shape in the vertical direction on the pixel unit **20**, pixels **10** positioned on consecutive b vertical pixel lines share a single first common layer **232** and/or a single second common layer **234**. In this case, the first common layer **232** and/or the second common layer **234** may be divided by being cut between the pixels **10** in a unit of horizontal pixel lines in the horizontal direction of pixel unit **20**.

When the first common layer **232** and/or the second common layer **234** are/is entirely formed on the pixel unit **20**, all pixels **10** share a single first common layer **232** and/or a single second common layer **234**. In this case, the first common layer **232** and/or the second common layer **234** may be divided by being cut along the horizontal direction and/or the vertical direction of the pixel unit **20**.

FIG. **5** illustrates the embodiment where the first common layer **232** and/or the second common layer **234** are/is formed on the pixel unit **20**, by being patterned so that pixels on a plurality of horizontal pixel lines and/or a plurality of vertical pixel lines share a single first common layer **232** and/or a single second common layer **234**. In the embodiments, the first common layer **232** and/or second common layer **234** may

be formed on the pixel unit **20** by being patterned so that pixels one horizontal or vertical pixel line share a single first common layer **232** and/or a single second common layer **234**.

In this embodiment, the first common layer **232** and/or the second common layer **234** are/is formed by being patterned so that a plurality of pixels **10**, e.g., k (k is a natural number of 2 or more) pixels **10** share a single first common layer **232** and/or a single second common layer **234**. Then, the first common layer **232** and/or the second common layer **234** are/is divided, so that one or more pixels **10** having a number smaller than that of the k pixels **10** shares a single first common layer **232** and/or a single second common layer **234**.

For example, in the dividing of the first common layer **232** and/or the second common layer **234**, one first common layer **232** and/or one second common layer **234** (commonly formed with respect to pixels **10** in the unit of one or more horizontal pixel lines or one or more vertical pixel lines) may be divided into at least two first common layers **232** and/or at least two second common layers **234**.

The first common layer **232** and/or the second common layer **234** may be divided into at least two first common layers **234** and/or at least two second common layers **234**. The divided layers may be disposed with respect to each of one or more horizontal pixel lines and one or more vertical pixel lines. In this case, the first common layer **232** and/or the second common layer **234** may be divided into at least two, based on each of the horizontal and vertical pixel lines on the pixel unit **20**.

In the present embodiment, after the process of forming the OLED to include the first common layer **232** and/or the second common layer **234** is completed (e.g., after the fabricating process for individual panels is completed), the first common layer **232** and/or the second common layer **234** are/is divided into common layers, each having a size smaller than that patterned in the process of forming the first common layer **232** and/or the second common layer **234**. This may be accomplished, for example, by applying physical pressure to the panel of the organic light emitting display.

That is, the first common layer **232** and/or the second common layer **234** of the OLED may be formed by being patterned, so that a plurality of pixels **10** share a single first common layer **232** and/or a single second common layer **234**. In this case, the first common layer **232** and/or the second common layer **234** may be divided into common layers having a smaller size, which are spaced from one another. This may be accomplished by applying physical pressure to the first common layer **232** and/or the second common layer **234**, after the panel fabricating process including the process of forming the OLED is completed.

For example, the first common layer **232** and/or the second common layer **234** may be divided by applying a force in the vertical direction of a plane on which the substrate is disposed (a plane on which the panel is disposed), after the panel fabricating process is completed.

Accordingly, leakage current is effectively reduced or cut off through the first common layer **232** and/or the second common layer **234**. Accordingly, it is possible to prevent an increase of luminance caused by leakage current, thereby improving image quality of the organic light emitting display.

FIG. 6 illustrates another embodiment of a method of dividing the common layer in the organic light emitting display device. For convenience, it is assumed that organic light emitting diodes formed in a panel include at least one first common layer. However, in a case where the organic light emitting diodes include only a second common layer, the dividing process may divide the second common layer. Also, in a case where the organic light emitting diodes include both

the first and second common layers, the second common layer may be simultaneously divided together with the first common layer.

Referring to FIG. 6, a panel **300** of the organic light emitting display, which is fabricated to include at least organic light emitting diode, is placed on a substrate support **400** having a plurality of grooves **430** formed therein. A first common layer in panel **300** is then divided by applying pressure. This pressure may be transferred to the first common layer of the organic light emitting diodes formed in the panel **300**.

For example, dividing the first common layer may include placing panel **300** on substrate support **400** having a plurality of grooves **430**. The panel **300** is formed to include one or more organic light emitting diodes, each including at least a first electrode, a first common layer, an emission layer, and a second electrode. The first common layer is pressed and divided by moving panel **300** and/or substrate support **400** in a second direction intersecting a first direction, while pressing panel **300** with a force applied in the first direction perpendicular to the panel **300**.

The first direction may be a direction facing top to bottom, like the direction of the arrow shown by a dotted line of FIG. 6. The second direction intersects the first direction and may be, for example, a direction perpendicular to the first direction, i.e., a direction horizontal to the panel **300**.

The force applied to panel **300** may have intensity such that the first common layer is at least partially cut, by pressing the first common layer in the panel **300**. In this case, the intensity of the force may be set to be smaller than one which causes a driving failure due to breakdown of the panel **300**, or one which causes damage of another driving electrode, device, or line.

As described in FIG. 3, the first common layer **232** may be formed to be coupled to areas of a plurality of pixels **10R**, **10G**, and **10B** via an upper portion of the pixel defining layer **220**. In this case, when a pressing force is applied to panel **300** on the substrate support **400** having grooves **430** formed therein as shown in FIG. 6, the first common layer **232** on the pixel defining layer **220** is easily cut. Accordingly, it is possible to easily divide the first common layer **232** in regions between the pixels **10R**, **10G**, and **10B**. In one embodiment, the force pressing the panel **300** may be equally applied to the entire surface of the panel **300**, in order to prevent a large force from being concentrated on only a portion of the panel **300**.

In FIG. 3, the second electrode **235** may be formed of a material having high flexibility, compared with the material of the first common layer **232** which may be easily cut or broken. The second electrode **235** may be entirely formed on the pixel unit.

Thus, the material(s) of the first common layer **232** and/or second electrode **235** may be selected by taking into consideration of the process of dividing the first common layer **232**. Also, the process of dividing the first common layer **232** may be performed by optimizing the force pressing the panel **300** according to the design conditions of the panel **300**. It is therefore possible to easily divide the first common layer **232**, while at the same time preventing a driving failure resulting from disconnection of the second electrode **235**.

The substrate support **400** may be configured to include a plurality of regions (e.g., a first region **410** and a second region **420**), each having a plurality of grooves **430**. The grooves **430** may be formed, for example, at a predetermined interval. For example, each of the first and second regions **410** and **420** may have a plurality of grooves **430** having the same interval and width. The grooves **430** in the first and second

regions **410** and **420** may be alternately disposed. In this case, the first common layer **232** may be more elaborately divided.

When at least one region of the panel **300** is placed in the first region **410** on the substrate support **400**, the panel **300** may be moved onto the second region **420** on the substrate support **400**. This may be accomplished by moving the panel **300** and/or the substrate support **400** in the second direction intersecting the first direction, while applying a force in the first direction perpendicular to the panel **300**.

In the aforementioned method embodiment, the first common layer **232** may be divided by applying physical pressure to the panel **300** after the panel **300** is fabricated. That is, this embodiment may include dividing first common layer **232** while applying physical pressure to first common layer **232**, in addition to forming the organic light emitting diode on the substrate **200** as described with reference FIGS. **2** and **3**.

Dividing the first common layer **232** may be performed, for example, in a state where a sealing process and a scribing process of dividing the panel into individual panels **300** are completed. For example, dividing the first common layer **232** may be performed before, during, or after a process of attaching a polarizing plate on panel **300**.

For example, the first common layer **232** may be divided by applying physical pressure to panel **300** before, during, or after a process of attaching a polarizing plate on the panel **300**. During this process, substrate support **400** having grooves as shown in FIG. **6** may be used as the substrate support having individual panels **300** mounted thereon. In this case, the first common layer **232** can be easily divided without adding a separate complicated fabricating process, thereby simplifying the fabricating process.

FIG. **7** illustrates another embodiment of a method for dividing the common layer in the organic light emitting display device. Referring to FIG. **7**, the first common layer in panel **300** may be divided, without using a grooved substrate support **400** as shown in FIG. **6**, but rather by using a roller **500** having grooves **530** formed therein.

More specifically, in this embodiment, the common layer in the organic light emitting display may be divided by applying a roller **500** with grooves **530** to panel **300**. The panel **300** may include organic light emitting diodes, each including at least a first electrode, a first common layer, an emission layer, and a second electrode. The first common layer in the panel **300** is divided by moving roller **500** and/or panel **300** in a second direction intersecting a first direction, while pressing panel **300** with a force in the first direction perpendicular to panel **300** while rotating the roller **500**.

According to one embodiment, a plurality of rollers **510** and **520** may be used. Each of the rollers **510** and **520** may include grooves **530** spaced at a predetermined interval. The rollers **510** and **520** may be rotated, so that grooves **530** are alternately positioned to cross each other. In this case, the first common layer may be more elaborately divided. Grooves **530** in roller **500** may be formed in a surface which contacts panel **300**. The size and direction of grooves **530** may be variously modified.

FIG. **7** illustrates another embodiment of a method for dividing the common layer in the organic light emitting display device. As shown in FIG. **8**, the first common layer may be divided using one or more rollers **500'** having a plurality of diagonal grooves **530'**. The one or more rollers **500'** are disposed on panel **300**, and the first common layer may be divided by rotating rollers **500'** while pressing panel **300** with the rollers **500'**.

When the first common layer is divided into common layers, each having a size smaller than that patterned in the process of forming the common layer as described above,

leakage current through the first common layer is effectively reduced or cut off. Accordingly, it is possible to prevent an increase in black luminance, thereby improving image quality of the organic light emitting display.

By way of summation and review, in an organic light emitting display, driving current is supplied to an organic light emitting diode corresponding to a data signal. Accordingly, light with a luminance based on the data signal is emitted to express a corresponding gray scale value. When a black gray scale value is to be implemented, the data signal has a value which cuts off the driving current to the organic light emitting diode. As a result, the organic light emitting diode does not emit light.

However, because of leakage current, the pixel which is to express a black gray scale value may emit some level of light. That is, an increase in luminance may occur because the organic light emitting diode is slightly turned on. Therefore, the black gray scale may not be completely expressed. As a result, image quality may deteriorate.

In accordance with one or more of the aforementioned embodiments, an organic light emitting display and fabricating method are provided in which multiple pixels share a common layer. This is accomplished by dividing the common layer into common layers of smaller size, which are spaced apart from each other. The common layer may be divided by applying physical pressure after completion of a panel fabricating process, including one for forming organic light emitting diodes. Accordingly, leakage current is effectively reduced or cut off. Thus, an increase in luminance caused by the leakage current may be prevented and image quality of the organic light emitting display may be improved.

Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:

1. A method of making a display device, the method comprising:

forming first electrodes of organic light emitting diodes (OLEDs) in respective pixel areas on a substrate;
forming a first common layer on the first electrodes in the pixel areas;
forming emission layers in the pixel areas on the first common layer;
forming a second electrode of the OLEDs on the emission layer; and
applying physical pressure to divide the first common layer.

2. The method as claimed in claim **1**, wherein apply the physical pressure includes applying a force to the first common layer in a different direction of a plane including the substrate.

3. The method as claimed in claim **1**, wherein applying the physical pressure includes:

13

placing a panel on a substrate support having a plurality of grooves, the panel including the first electrodes, the first common layer, the emission layers, and the second electrode; and

moving at least one of the panel or the substrate support in a second direction intersecting a first direction, while applying a force in the first direction to divide the first common layer.

4. The method as claimed in claim 3, wherein:

the substrate support includes first and second regions, each having grooves at a predetermined interval, the grooves in adjacent regions alternately positioned to cross each other, and

the method further includes moving the panel onto the second region on the substrate support when at least one region of the panel is positioned in the first region on the substrate support, wherein moving the panel includes applying the force to the panel in the first direction.

5. The method as claimed in claim 4, wherein each of the first and second regions of the substrate support includes a plurality of grooves having substantially a same interval and width.

6. The method as claimed in claim 3, wherein the first direction is perpendicular to the second direction.

7. The method as claimed in claim 1, wherein applying the physical pressure includes:

applying a force to a panel in a first direction while rotating at least one roller in a second direction crossing the first direction, the at least one roller including a plurality of grooves and the panel including the first electrodes, the first common layer, the emission layers, and the second electrode.

8. The method as claimed in claim 7, wherein applying the physical pressure includes rotating a plurality of rollers on the

14

first common layer, each of the rollers having grooves at a predetermined interval and the rollers are rotated so that the grooves of the rollers are alternately positioned.

9. The method as claimed in claim 7, wherein applying the physical pressure includes rotating a plurality of rollers on the first common layer, each of the rollers having a plurality of diagonal grooves.

10. The method as claimed in claim 1, wherein:

k OLEDs share the first common layer, where $k \geq 2$, and one or more pixels having a number smaller than the k pixels share the divided first common layer.

11. The method as claimed in claim 1, wherein:

pixels in a horizontal or vertical line share the first common layer, and

applying the physical pressure divides the first common layer into at least two first common layers.

12. The method as claimed in claim 11, wherein the at least two first common layers are divided relative to the horizontal and vertical pixel lines.

13. The method as claimed in claim 1, further comprising: forming a second common layer on the emission layer to allow a plurality of pixels to share the second common layer, wherein the second common layer is formed between forming the emission layers and forming of the second electrode.

14. The method as claimed in claim 13, wherein the second common layer is simultaneously divided with the first common layer.

15. The method as claimed in claim 1, wherein:

the first electrodes and emission layers are patterned for corresponding pixels, and the second electrode is entirely formed on a pixel unit so that all the pixels share the second electrode.

* * * * *

专利名称(译)	有机发光显示器及其制造方法		
公开(公告)号	US9048208	公开(公告)日	2015-06-02
申请号	US14/321033	申请日	2014-07-01
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM TAE KYU		
发明人	KIM, TAE-KYU		
IPC分类号	H01L51/54 H01L27/32 H01L51/56		
CPC分类号	H01L27/3248 H01L51/56 H01L27/3246 H01L27/3211 H01L27/3276 H01L51/0015 H01L51/5012 H01L51/5056 H01L51/5072 H01L51/5209		
优先权	1020130077107 2013-07-02 KR		
其他公开文献	US20150008410A1		
外部链接	Espacenet USPTO		

摘要(译)

一种制造显示装置的方法，包括：在基板上的各个像素区域中形成有机发光二极管的第一电极，在像素区域中的第一电极上形成第一公共层，在第一公共层上的像素区域中形成发光层，在发光层上形成有机发光二极管的第二电极，并施加物理压力以划分第一公共层。

