



US010249829B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 10,249,829 B2**
(45) **Date of Patent:** ***Apr. 2, 2019**

(54) **COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE INCLUDING
THE SAME**

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si, Gyeonggi-do (KR)

(72) Inventors: **Jungsub Lee**, Yongin-si (KR); **Seulong
Kim**, Yongin-si (KR); **Younsun Kim**,
Yongin-si (KR); **Dongwoo Shin**,
Yongin-si (KR); **Naoyuki Ito**, Yongin-si
(KR); **Jino Lim**, Yongin-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si
(KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 218 days.

This patent is subject to a terminal dis-
claimer.

(21) Appl. No.: **15/179,818**

(22) Filed: **Jun. 10, 2016**

(65) **Prior Publication Data**

US 2017/0148997 A1 May 25, 2017

(30) **Foreign Application Priority Data**

Nov. 24, 2015 (KR) 10-2015-0164832

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07F 9/6509 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **H01L 51/0072** (2013.01); **C07F 9/5765**
(2013.01); **C07F 9/6547** (2013.01);
(Continued)

(58) **Field of Classification Search**

None

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,895,692 A 4/1999 Shirasaki et al.
5,942,615 A * 8/1999 Kobayashi C07D 265/38
430/58.5

(Continued)

FOREIGN PATENT DOCUMENTS

KR 10-0730132 B1 6/2007
KR 10-2011-0088118 A 8/2011

(Continued)

OTHER PUBLICATIONS


U.S. Office Action dated Sep. 13, 2018, issued in U.S. Appl. No.
15/264,369 (8 pages).

Primary Examiner — Devina Pillay

(74) *Attorney, Agent, or Firm* — Lewis Roca Rothgerber
Christie LLP

(57) **ABSTRACT**

An organic light-emitting device including a first electrode;
a second electrode facing the first electrode; and an organic
layer between the first electrode and the second electrode,
the organic layer including an emission layer, wherein the
organic layer includes a compound represented by Formula
1:



Formula 1

When the compound represented by Formula 1 is used as
electron-transporting material, an organic light-emitting
(Continued)

40

220
190
150
110
210

device including this compound may show significantly improved efficiency, driving voltage, high luminance, and long lifespan characteristics.

20 Claims, 2 Drawing Sheets

(51) Int. Cl.

C07F 9/6547 (2006.01)
C07F 9/6533 (2006.01)
C07F 9/576 (2006.01)
C07F 9/6558 (2006.01)
H01L 51/52 (2006.01)
H01L 51/50 (2006.01)

(52) U.S. Cl.

CPC **C07F 9/65335** (2013.01); **C07F 9/65583**
 (2013.01); **C07F 9/650994** (2013.01); **H01L**
51/006 (2013.01); **H01L 51/0071** (2013.01);
H01L 51/0085 (2013.01); **H01L 51/506**
 (2013.01); **H01L 51/5016** (2013.01); **H01L**
51/5076 (2013.01); **H01L 51/5088** (2013.01);
H01L 51/5092 (2013.01); **H01L 51/5096**
 (2013.01); **H01L 51/5206** (2013.01); **H01L**
51/5221 (2013.01); **H01L 2251/308** (2013.01)

(56)

References Cited

U.S. PATENT DOCUMENTS

8,029,919 B2 * 10/2011 Gessner C07D 279/26
 257/40
 8,174,001 B2 5/2012 Kitamura et al.
 8,981,351 B2 3/2015 Hamada et al.

9,029,425 B2 * 5/2015 Eberle C07C 13/62
 514/766
 9,515,266 B2 * 12/2016 Jatsch C07D 495/04
 9,876,180 B2 * 1/2018 Jeong H01L 51/0072
 2006/0192471 A1 8/2006 Inoue et al.
 2006/0231843 A1 10/2006 Qin et al.
 2006/0261731 A1 11/2006 Aziz et al.
 2006/0263631 A1 11/2006 Lee et al.
 2008/0027028 A1 1/2008 Chichak
 2008/0057609 A1 3/2008 Li
 2010/0308714 A1 12/2010 Gessner et al.
 2011/0204295 A1 8/2011 Kuwabara et al.
 2012/0223346 A1 9/2012 Ohsawa et al.
 2012/0235127 A1 9/2012 Takasu et al.
 2013/0320368 A1 12/2013 Seo et al.
 2014/0151664 A1 6/2014 Sato
 2014/0187791 A1 7/2014 Suzuki et al.
 2015/0129852 A1 5/2015 Park et al.
 2015/0287952 A1 10/2015 Yamazaki et al.
 2016/0036007 A1 2/2016 Facchetti
 2016/0311799 A1 10/2016 Low et al.
 2017/0148997 A1 5/2017 Lee
 2017/0170407 A1 6/2017 Park et al.

FOREIGN PATENT DOCUMENTS

KR 10-2011-0113297 A 10/2011
 KR 10-2013-0076842 A 7/2013
 KR 10-2014-0004005 A 1/2014
 KR 10-2014-0020208 A 2/2014
 KR 10-2014-0076521 A 6/2014
 KR 10-2014-0122680 A 10/2014
 KR 10-2015-0012906 A 2/2015
 KR 10-2015-0030616 A 3/2015
 KR 10-2015-0037605 A 4/2015
 KR 10-2015-0071685 A 6/2015
 WO WO 2011/093609 A1 8/2011
 WO WO 2011/126225 A1 10/2011

* cited by examiner

FIG. 1




FIG. 2




FIG. 3





FIG. 4



1

COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to and the benefit of Korean Patent Application No. 10-2015-0164832, filed on Nov. 24, 2015, in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

1. Field

One or more aspects of example embodiments of the present disclosure are related to a compound and an organic light-emitting device including the same.

2. Description of the Related Art

Organic light-emitting devices are self-emission devices that have wide viewing angles, high contrast ratios, short response times, and/or excellent brightness, driving voltage, and/or response speed characteristics, and may produce full-color images.


An example organic light-emitting device may include a first electrode on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode sequentially positioned on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers (such as holes and electrons) may recombine in the emission layer to produce excitons. These excitons may transition from an excited state to the ground state to thereby generate light.

SUMMARY

One or more aspects of example embodiments of the present disclosure are directed toward a compound that is suitable for use as an electron injection material or as an electron transport material, and has high transport capability and/or high material stability, and an organic light-emitting device having high efficiency, low driving voltage, high luminance, and/or long lifespan characteristics due to inclusion of the compound.

Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

One or more example embodiments of the present disclosure provide a compound represented by Formula 1:



Formula 1

In Formula 1,
X and Y may each independently be selected from O, S, CR₁₁R₁₂, and NR₁₃,

2

R₁, R₁₁, R₁₂, and R₁₃ may each independently be selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, a substituted or unsubstituted C₅-C₆₀ carbocyclic group, and a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

at least one selected from X, Y, and R₁ may include —P(Ph)₂=Z,

Z may be selected from O and S, and

at least one substituent of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, the substituted monovalent non-aromatic condensed heteropolycyclic group, the substituted or unsubstituted C₅-C₆₀ carbocyclic group, and the substituted or unsubstituted C₁-C₆₀ heterocyclic group may be selected from the group consisting of:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

3

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

—P(=O)Q₁Q₂ and —P(=S)Q₃Q₄,

wherein Q₁ to Q₄, Q₁₁ to Q₁₇, and Q₂₁ to Q₂₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

According to one or more embodiments of the present disclosure, an organic light-emitting device includes a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer includes the compound represented by Formula 1.

According to one or more embodiments of the present disclosure, a display apparatus includes an organic light-emitting device, wherein the first electrode of the organic light-emitting device is electrically connected to a source electrode or drain electrode of a thin film transistor.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects will become apparent and more readily appreciated from the following description of example embodiments, taken in conjunction with the accompanying drawings, in which:

FIG. 1 is a schematic view of an organic light-emitting device according to an embodiment of the present disclosure;

FIG. 2 is a schematic view of an organic light-emitting device according to another embodiment of the present disclosure;

FIG. 3 is a schematic view of an organic light-emitting device according to another embodiment of the present disclosure; and

4

FIG. 4 is a schematic view of an organic light-emitting device according to another embodiment of the present disclosure.


DETAILED DESCRIPTION

Reference will now be made in more detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout and duplicative descriptions thereof may not be provided. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the drawings, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

In the drawings, the thicknesses of layers, films, panels, regions, etc., may be exaggerated for clarity. It will be understood that when an element such as a layer, film, region, or substrate is referred to as being “on” another element, it can be directly on the other element or intervening element(s) may also be present. In contrast, when an element is referred to as being “directly on” another element, no intervening elements are present.

A compound according to an embodiment of the present disclosure may be represented by Formula 1:

Formula 1



In Formula 1,

X and Y may each independently be selected from O, S, CR₁₁R₁₂, and NR₁₃,

R₁, R₁₁, R₁₂, and R₁₃ may each independently be selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, a substituted or unsubstituted C₅-C₆₀ carbocyclic group, and a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

at least one selected from X, Y, and R₁ may include —P(Ph)₂=Z,

Z may be selected from O and S,

at least one selected from the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group,

5

the substituted C_3 - C_{10} cycloalkyl group, the substituted C_2 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_2 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, the substituted monovalent non-aromatic condensed heteropolycyclic group, the substituted or unsubstituted C_5 - C_{60} carbocyclic group, and the substituted or unsubstituted C_1 - C_{60} heterocyclic group may be selected from the group consisting of:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_2 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q_{11})(Q_{12}), —Si(Q_{13})(Q_{14})(Q_{15}), and —B(Q_{16})(Q_{17});

a C_3 - C_{10} cycloalkyl group, a C_2 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C_3 - C_{10} cycloalkyl group, a C_2 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_2 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q_{21})(Q_{22}), —Si(Q_{23})(Q_{24})(Q_{25}), and —B(Q_{26})(Q_{27}); and

—P(=O) Q_1Q_2 and —P(=S) Q_3Q_4 ,

wherein Q_1 to Q_4 , Q_{11} to Q_{17} , and Q_{21} to Q_{27} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine


6

group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_2 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_2 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.


As used herein, the expression “at least one selected from X, Y, and R_1 may include —P(Ph) $_2$ =Z” may refer to that —P(Ph) $_2$ =Z is connected to X, Y, and/or R_1 as a substituent.

In one or more embodiments, the compound represented by Formula 1 may be one selected from Formulae 2 to 4:


Formula 2



Formula 3



Formula 4



In Formulae 2 to 4,

R_1 , R_2 , and R_3 may each independently be selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

L_1 , L_2 , and L_3 may each independently be selected from a substituted or unsubstituted C_6 - C_{20} arylene group, a substituted or unsubstituted C_1 - C_{20} heteroarylene group, a sub-

7




stituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a may be an integer selected from 0 to 2,

when the number of $L_1(s)$, $L_2(s)$, and $L_3(s)$ is each two or more, a plurality of $L_1(s)$ may be identical to or different from each other, a plurality of $L_2(s)$ may be identical to or different from each other, and a plurality of $L_3(s)$ may be identical to or different from each other, and

Z may be selected from O and S.

In one or more embodiments, R_1 , R_2 , and R_3 may each independently be represented by one selected from Formulae 2a to 2c:



In Formulae 2a to 2c,



Z_1 may be selected from hydrogen, deuterium, a halogen group (e.g., atom), a cyano group, a nitro group, a hydroxyl group, a carboxyl group, $-\text{P}(\text{Ph})_2=\text{O}$, $-\text{P}(\text{Ph})_2=\text{S}$, a substituted or unsubstituted $\text{C}_1\text{-C}_{20}$ alkyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{20}$ aryl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{20}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

when the number of $Z_{1(s)}$ is two or more, a plurality of $Z_1(s)$ may be identical to or different from each other,

p may be an integer selected from 1 to 7, and

* may indicate a binding site.

In one or more embodiments, L_1 , L_2 , and L_3 may each independently be represented by one selected from Formulae 3a and 3b:




In Formulae 3a and 3b, * may indicate a binding site.


In one or more embodiments, the compound represented by Formula 1 may be one selected from Formulae 5 to 10:

8

Formula 5



Formula 6




2a

2b


2c

25

2c



Formula 7



Formula 8

35

40


3a

55

3b

60


65



Formula 9

9

-continued



In Formulae 5 to 10,

R_1 , R_2 , R_{21} , and R_{22} may each independently be selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,




L_1 and L_2 may each independently be selected from a substituted or unsubstituted C_6 - C_{20} arylene group, a substituted or unsubstituted C_1 - C_{20} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a may be an integer selected from 0 to 2,

when the number of $L_1(s)$ and $L_2(s)$ is each two or more, a plurality of $L_1(s)$ may be identical to or different from each other and a plurality of $L_2(s)$ may be identical to or different from each other, and

Z may be selected from O and S.

In one or more embodiments, R_1 , R_2 , R_{21} , and R_{22} may each independently be a substituted or unsubstituted C_1 - C_{10} alkyl group, or may each independently be represented by one selected from Formulae 2a to 2c:



In Formulae 2a to 2c,

Z_1 may be selected from hydrogen, deuterium, a halogen group (e.g., atom), a cyano group, a nitro group, a hydroxyl group, a carboxyl group, $-P(Ph)_2=O$, $-P(Ph)_2=S$, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

10



Formula 10

when the number of $Z_1(s)$ is two or more, a plurality of $Z_1(s)$ may be equal to or different from each other,

p may be an integer selected from 1 to 7, and



* may indicate a binding site.

In one or more embodiments, L_1 and L_2 may each independently be represented by one selected from Formulae 3a and 3b:







In Formulae 3a and 3b, * may indicate a binding site.

In one or more embodiments, the compound represented by Formula 1 may be one selected from Compounds E-1 to E-34, but embodiments of the present disclosure are not limited thereto:






11

-continued

**12**


-continued



13

-continued

E-10




5

10

15

20

E-11




25

30

35

40

E-12



50

55


60

65

14

-continued

E-13



15

20

E-14

25


30

35

40

45

E-15



50





55

60

65

15

-continued

**16**

-continued

E-16

E-20

5

10

15

20

E-17

25

30

E-18

35

40

45







E-19

50

55





60

65



17

-continued

**18**

-continued

E-25

E-29

5

10

15

E-26

20

25

30

E-27

35

40






45

E-28

55


60

65



19

-continued



[Description of FIG. 1]

FIG. 1 is a schematic view of an organic light-emitting device **10** according to an embodiment of the present disclosure. The organic light-emitting device **10** may include a first electrode **110**, an organic layer **150**, and a second electrode **190**.

Hereinafter, the structure of the organic light-emitting device **10** according to an embodiment of the present disclosure and a method of manufacturing the organic light-emitting device **10** will be described in connection with FIG. 1.

[First Electrode **110**]

In FIG. 1, a substrate may be under the first electrode **110** and/or above the second electrode **190**. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and/or water-resistance.

The first electrode **110** may be formed by depositing and/or sputtering a material for forming the first electrode **110** on the substrate. When the first electrode **110** is an anode, the material for the first electrode may be selected from materials with a high work function to thereby facilitate hole injection.

The first electrode **110** may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode **110** is a transmissive electrode, a material for forming a first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), zinc oxide (ZnO), and combinations thereof, but embodiments of the present disclosure are not limited thereto. In one or more embodiments, when the first electrode **110** is a semi-transmissive electrode or a reflective electrode, a material for forming a first electrode may be selected from magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), and combinations thereof, but embodiments of the present disclosure are not limited thereto. As used herein, the terms “combination”, “combination thereof”, and “combinations thereof” may refer to a chemical combination (e.g., an alloy or chemical compound), a mixture, or a laminated structure of components.

The first electrode **110** may have a single-layered structure or a multi-layered structure including two or more layers. For example, the first electrode **110** may have a three-layered structure of ITO/Ag/ITO, but embodiments of the structure of the first electrode **110** are not limited thereto.

20

[Organic Layer **150**]

The organic layer **150** is on the first electrode **110**. The organic layer **150** may include an emission layer.

The organic layer **150** may further include a hole transport region between the first electrode **110** and the emission layer, and an electron transport region between the emission layer and the second electrode **190**.


[Hole Transport Region in Organic Layer **150**]

The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The hole transport region may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).

For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a structure of hole injection layer/hole transport layer, hole injection layer/hole transport layer/emission auxiliary layer, hole injection layer/emission auxiliary layer, hole transport layer/emission auxiliary layer or hole injection layer/hole transport layer/electron blocking layer, wherein layers of each structure are sequentially stacked on the first electrode **110** in each stated order, but embodiments of the structure of the hole transport region are not limited thereto.


The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




m-MTDATA

21


-continued




TDATA




2-TNATA




NPB

 β -NPB**22**


-continued




TPD




Spiro-TPD




Spiro-NPB



methylated NPB




TAPC



HMTDP

24

Formula 201



a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a

In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from the group consisting of:

25

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group and a pyridinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂),

26

wherein Q₃₁ to Q₃₃ may each independently be the same as described above.

In one or more embodiments, in Formula 201, at least one selected from R₂₀₁ to R₂₀₃ may be selected from the group consisting of:

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, in Formula 202, i) R₂₀₁ and R₂₀₂ may be connected (e.g., coupled) via a single bond, and/or ii) R₂₀₃ and R₂₀₄ may be connected (e.g., coupled) via a single bond.


In one or more embodiments, in Formula 202, at least one selected from R₂₀₁ to R₂₀₄ may be selected from the group consisting of:

a carbazolyl group; and

a carbazolyl group substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments of the present disclosure are not limited thereto.

The compound represented by Formula 201 may be represented by Formula 201A:


Formula 201A



For example, the compound represented by Formula 201 may be represented by Formula 201A(1), but embodiments of the present disclosure are not limited thereto:


27

Formula 201A(1)



For example, the compound represented by Formula 201 may be represented by Formula 201A-1, but embodiments of the present disclosure are not limited thereto:

Formula 201A-1




The compound represented by Formula 202 may be represented by Formula 202A:

28

In one or more embodiments, the compound represented by Formula 202 may be represented by Formula 202A-1:

Formula 202A-1



In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,


L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ may each independently be the same as described above,

R₂₁₁ and R₂₁₂ may each independently be the same as described above in connection with R₂₀₃, and

R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.


The hole transport region may include at least one selected from Compounds HT1 to HT39, but embodiments of the present disclosure are not limited thereto:

Formula 202A




29

HT1




30


HT2




HT3



HT4




31

-continued
HT5



32

HT6




HT7

HT8




33

-continued
HT9



34

HT10





HT11

HT12





HT13



HT14





HT16



HT18




HT20




37

-continued
HT21




38


HT22




HT23




HT24



HT25




39


-continued
HT26

40


HT27




HT28




HT29



HT30



HT31





41

42

-continued



HT32

HT33





HT34

HT35




HT36

HT37




43

-continued
HT38

44

HT39



The thickness of the hole transport region may be about 100 Å to about 10,000 Å, and in some embodiments, about 100 Å to about 1,000 Å. When the hole transport region includes at least one selected from a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be about 100 Å to about 9,000 Å, and in some embodiments, about 100 Å to about 1,000 Å; the thickness of the hole transport layer may be about 50 Å to about 2,000 Å, and in some embodiments, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer (e.g., adjusting the optical resonance distance to match the wavelength of light emitted from the emission layer), and the electron blocking layer may block or reduce the flow of electrons from the electron transport region. The emission auxiliary layer and the electron blocking layer may each include the same materials as described above.


[p-dopant]

The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.


The charge-generation material may be, for example, a p-dopant.

The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments of the present disclosure are not limited thereto.


For example, the p-dopant may include at least one selected from a quinone derivative (such as tetracyanoquinodimethane (TCNQ) and/or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ)); a metal oxide (such as a tungsten oxide and/or a molybdenum oxide); 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and a compound represented by Formula 221, but embodiments of the present disclosure are not limited thereto:



<HAT-CN>



<F4-TCNQ>



Formula 221

In Formula 221,

R₂₂₁ to R₂₂₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic

group, provided that at least one selected from R₂₂₁ to R₂₂₃ includes at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, and a C₁-C₂₀ alkyl group substituted with at least one selected from —F, —Cl, —Br, and —I.

[Emission Layer in Organic Layer 150]

When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and/or a blue emission layer, according to a sub pixel. In one or more embodiments, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers may contact each other or may be separated from each other. In one or more embodiments, the emission layer may include two or more materials selected from a red-light emission material, a green-light emission material, and a blue-light emission material, in which the two or more materials may be mixed with each other in a single layer to thereby emit white light.

The emission layer may include a host and a dopant. The dopant may be at least one selected from a phosphorescent dopant and a fluorescent dopant.

The amount of the dopant in the emission layer may be, in general, about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

The thickness of the emission layer may be about 100 Å to about 1,000 Å, and in some embodiments, about 200 Å to about 600 Å. When the thickness of the emission layer is within these ranges, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[Host in Emission Layer]

In one or more embodiments, the host may include a compound represented by Formula 301:



In Formula 301,

Ar₃₀₁ may be selected from a substituted or unsubstituted C₅-C₆₀ carbocyclic group and a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

xb11 may be selected from 1, 2, and 3,

L₃₀₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

xb1 may be an integer selected from 0 to 5,

R₃₀₁ may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a

substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃), —N(Q₃₀₁)(Q₃₀₂), —B(Q₃₀₁)(Q₃₀₂), —C(=O)(Q₃₀₁), —S(=O)₂(Q₃₀₁), and —P(=O)(Q₃₀₁)(Q₃₀₂), and

xb21 may be an integer selected from 1 to 5,

wherein Q₃₀₁ to Q₃₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, in Formula 301,

Ar₃₀₁ may be selected from the group consisting of:


a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group; and

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),


wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.

In Formula 301, when xb11 is two or more, two or more Ar₃₀₁(s) may be connected (e.g., coupled) via a single bond.

In one or more embodiments, the compound represented by Formula 301 may be represented by one selected from Formula 301-1 and 301-2:



Formula 301-1



Formula 301-2

In Formulae 301-1 and 301-2,

A₃₀₁ to A₃₀₄ may each independently be selected from a benzene, a naphthalene, a phenanthrene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a pyridine, a pyrimidine, an indene, a fluorene, a spiro-bifluorene, a benzofluorene, a dibenzofluorene, an indole, a carbazole, a benzocarbazole, a dibenzocarbazole, a furan, a benzofuran, a dibenzofuran, a naphthofuran, a benzonaphthofuran, a dinaphthofuran, a thiophene, a benzothiophene, a dibenzothiophene, a naphthothiophene, a benzonaphthothiophene, and a dinaphthothiophene,

X₃₀₁ may be selected from O, S, and N-[(L₃₀₄)_{xb4}-R₃₀₄],

R₃₁₁ to R₃₁₄ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

xb22 and xb23 may each independently be selected from 0, 1, and 2,

L₃₀₁, xb1, R₃₀₁, and Q₃₁ to Q₃₃ may each independently be the same as described above,

L₃₀₂ to L₃₀₄ may each independently be the same as described above in connection with L₃₀₁,

xb2 to xb4 may each independently be the same as described above in connection with xb1, and

R₃₀₂ to R₃₀₄ may each independently be the same as described above in connection with R₃₀₁.

For example, in Formulae 301, 301-1, and 301-2,

L₃₀₁ to L₃₀₄ may each independently be selected from the group consisting of:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a

nylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a

triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

wherein Q₃₁ to Q₃₃ may each independently be the same as described above.

In one or more embodiments, in Formulae 301, 301-1, and 301-2,

R₃₀₁ to R₃₀₄ may each independently be selected from the group consisting of:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group,







a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

wherein Q₃₁ to Q₃₃ may each independently be the same as described above.

In one or more embodiments, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.

The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55, but embodiments of the present disclosure are not limited thereto:

51




52

-continued

H1

H7

5




10

H2

H8

15




20

H3

H9

25




30

H4

H10

35




40

H5

H11

45




50

55

H6

H12


60



65

53


-continued



H13

5


10



H14 15

20


25



H15 30


35

40



H16 45

50




H17 55

60


65

54


-continued




H18




H19



H20




H21



H22

55

-continued



H23

5


10

15

20

H24

25




30

35

40

H25

45



50

55


60

65


56

-continued


H26



H27




H28




57

-continued

**58**


-continued



59

-continued

H38




5

10

15

H39 20



25


30

35

40

45

H40



50

55


60

65


60

-continued


H41



H42







H43



61

-continued

**62**

-continued

H44

H48

5

10

H45

15

20

25

30

H46

35

40

45


50

55


H47

60


65




H49





H50



H51




H52



H53



63

-continued



[Phosphorescent Dopant in Emission Layer of Organic Layer 150]

The phosphorescent dopant may include an organometallic complex represented by Formula 401:



In Formulae 401 and 402,

M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

L_{401} may be selected from ligands represented by Formula 402,

$xc1$ may be selected from 1, 2, and 3,

when $xc1$ is two or more, two or more $L_{401}(s)$ may be equal to or different from each other,

L_{402} may be an organic ligand,

$xc2$ may be an integer selected from 0 to 4,

64

H54 when $xc2$ is two or more, two or more $L_{402}(s)$ may be equal to or different from each other,

X_{401} to X_{404} may each independently be selected from nitrogen (N) and carbon (C),

5 X_{401} and X_{403} may be connected (e.g., coupled) via a single bond or a double bond,

X_{402} and X_{404} may be connected (e.g., coupled) via a single bond or a double bond,

10 rings A_{401} and A_{402} may each independently be selected from a C_5 - C_{60} carbocyclic group and a C_1 - C_{60} heterocyclic group,

15 X_{405} may be selected from a single bond, $*-O-*'$, $*-S-*'$, $*-C(=O)-*'$, $*-N(Q_{411})-*'$, $*-C(Q_{411})(Q_{412})-*'$, $*-C(Q_{411})=C(Q_{412})-*'$, $*-C(Q_{411})=*'$, and $*=C(Q_{411})=*'$,

H55 Q_{411} and Q_{412} may each independently be selected from hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

20 X_{406} may be selected from a single bond, O, and S,

R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent

25 non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$,

30 Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

$xc11$ and $xc12$ may each independently be an integer selected from 0 to 10, and

35 in Formula 402, * and *' may indicate binding sites to M in Formula 401.

In one or more embodiments, in Formula 402, A_{401} and A_{402} may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) both X_{401} and X_{402} may be nitrogen.

60 In one or more embodiments, in Formula 402, R_{401} and R_{402} may each independently be selected from the group consisting of:

65

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, and a norbornenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

—Si(Q₄₀₁)(Q₄₀₂)(Q₄₀₃), —N(Q₄₀₁)(Q₄₀₂), —B(Q₄₀₁)(Q₄₀₂), —C(=O)(Q₄₀₁), —S(=O)₂(Q₄₀₁), and —P(=O)(Q)(Q₄₀₂),

wherein Q₄₀₁ to Q₄₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.


In one or more embodiments, in Formula 401, when xc1 is two or more, two A₄₀₁ rings within two or more L₄₀₁ ligands may be optionally connected (e.g., coupled) through a linking group X₄₀₇, or two A₄₀₂ rings may be optionally connected (e.g., coupled) through a linking group X₄₀₈ (as in Compounds PD1 to PD4 and PD7). X₄₀₇ and X₄₀₈ may each independently be selected from a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q₄₁₃)—*, *—C(Q₄₁₃)(Q₄₁₄)—*, and *—C(Q₄₁₃)=C(Q₄₁₄)—* (wherein Q₄₁₃ and Q₄₁₄ may each independently be selected from hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group), but embodiments of the present disclosure are not limited thereto.

In Formula 401, L₄₀₂ may be a monovalent, divalent, or trivalent organic ligand. For example, L₄₀₂ may be selected from a halogen atom, a diketone (for example, an acetylacetonate), a carboxylic acid (for example, a picolinate), —C(=O), an isonitrile, —CN, and a phosphorus ligand (for example, a phosphine and/or a phosphite), but embodiments of the present disclosure are not limited thereto.


66

In one or more embodiments, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25, but embodiments of the present disclosure are not limited thereto:


PD1




PD2



PD3









PD4



67

-continued

**68**

-continued

PD5

5

10

PD6

15

20

PD7

25

30

PD8

35

40

PD9

45






50

PD10

55

60

65



PD11

PD12






PD13

PD14

PD15

69

-continued

**70**

-continued

PD16

5

10

PD17

15

PD18

30

35

PD19

40

45





50

PD20

55

60

65



PD21


PD22

PD23

PD24

71


-continued



PD25

[Fluorescent Dopant in Emission Layer]

The fluorescent dopant may include a compound represented by Formula 501:



Formula 501

In Formula 501,

Ar₅₀₁ may be selected from a substituted or unsubstituted C₅-C₆₀ carbocyclic group and a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

L₅₀₁ to L₅₀₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

xd1 to xd3 may each independently be an integer selected from 0 to 3,

R₅₀₁ and R₅₀₂ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

xd4 may be an integer selected from 1 to 6.

In one or more embodiments, in Formula 501,

Ar₅₀₁ may be selected from the group consisting of:

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene

72

group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, in Formula 501,

L₅₀₁ to L₅₀₃ may each independently be selected from the group consisting of:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, and a pyridinylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

In one or more embodiments, in Formula 501,

R₅₀₁ and R₅₀₂ may each independently be selected from the group consisting of:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenan-

73


threnyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, in Formula 501, xd4 may be two, but embodiments of the present disclosure are not limited thereto.

For example, the fluorescent dopant may be or include at least one selected from Compounds FD1 to FD22:




FD1


74

-continued

FD2



FD3



45


50

55

60


65

FD4



75

-continued



76

-continued


FD7

5

10

15


20



FD5

25

FD8




30

35

40


45



FD6

50


FD9



55










60

65



77
-continued


78
-continued



79


-continued

FD19

**80**


-continued

FD21




FD22


FD20




In one or more embodiments, the fluorescent dopant may be or include at least one selected from the compounds illustrated below, but embodiments of the present disclosure are not limited thereto:



DPVBi



DPAVB



[Electron Transport Region in Organic Layer 150]

The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer (ETL), and an electron injection layer, but embodiments of the present disclosure are not limited thereto.

For example, the electron transport region may have a structure of electron transport layer/electron injection layer, a structure of hole blocking layer/electron transport layer/electron injection layer, a structure of electron control layer/electron transport layer/electron injection layer, or a structure of buffer layer/electron transport layer/electron injection layer, wherein layers of each structure are sequentially stacked on an emission layer in each stated order. However, embodiments of the structure of the electron transport layer are not limited thereto.

The electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, and/or an electron transport layer in the electron transport region) may include a metal-free compound containing at least one 7 electron-depleted nitrogen-containing ring.

The term “7 electron-depleted nitrogen-containing ring” as used herein may indicate a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.


For example, the “ π electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed (e.g., fused) with each other, or iii) a heteropolycyclic group in which at least one 5-membered to 7-membered heteromonocyclic group

having at least one $*-N=*$ moiety is condensed with at least one C_5 - C_{60} carbocyclic group.

Non-limiting examples of the π electron-depleted nitrogen-containing ring may include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazole, an imidazopyridine, an imidazopyrimidine, and an azacarbazole, but embodiments of the present disclosure are not limited thereto.

The electron transport region may include the compound represented by Formula 1 according to an embodiment of the present disclosure. In one or more embodiments, the electron transport layer may include the compound represented by Formula 1 according to an embodiment of the present disclosure.

The electron transport region and the electron transport layer may further include other compounds, in addition to the compound represented by Formula 1. For example, the electron transport region may include a compound represented by Formula 601:



Formula 601

In Formula 601,

Ar_{601} may be selected from a substituted or unsubstituted C_5 - C_{60} carbocyclic group and a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

$xe11$ may be selected from 1, 2, and 3,

L_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or

unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

xe1 may be an integer selected from 0 to 5,

R₆₀₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₆₀₁)(Q₆₀₂)(Q₆₀₃), —C(=O)(Q₆₀₁), —S(=O)₂(Q₆₀₁), and —P(=O)(Q₆₀₁)(Q₆₀₂),

Q₆₀₁ to Q₆₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, and

xe21 may be an integer selected from 1 to 5.

In one or more embodiments, at least one selected from the xe11 (e.g., 1 to 3) Ar₆₀₁(s) and the xe21 (e.g., 1 to 5) R₆₀₁(s) may include the π electron-depleted nitrogen-containing ring as described above.

In one or more embodiments, in Formula 601,

ring Ar₆₀₁ may be selected from the group consisting of:

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothi-

azole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),


wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In Formula 601, when xe11 is two or more, two or more Ar₆₀₁(s) may be connected (e.g., coupled) via a single bond.

In one or more embodiments, in Formula 601, Ar₆₀₁ may be an anthracene group.

In one or more embodiments, the compound represented by Formula 601 may be represented by Formula 601-1:

Formula 601-1



In Formula 601-1,

X₆₁₄ may be selected from N and C(R₆₁₄),

X₆₁₅ may be selected from N and C(R₆₁₅),

X₆₁₆ may be selected from N and C(R₆₁₆),

at least one selected from X₆₁₄ to X₆₁₆ may be N,

L₆₁₁ to L₆₁₃ may each independently be the same as described above in connection with L₆₀₁,

xe611 to xe613 may each independently be the same as described above in connection with xe1,

R₆₁₁ to R₆₁₃ may each independently be the same as described above in connection with R₆₀₁, and

R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, in Formulae 601 and 601-1,

L₆₀₁ and L₆₁₁ to L₆₁₃ may each independently be selected from the group consisting of:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolyl group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isox-

azolyene group, a thiadiazolyene group, an oxadiazolyene group, a pyrazinyne group, a pyrimidinyne group, a pyridazinyne group, a triazinyne group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinyne group, a naphthyridinyne group, a quinoxalinyne group, a quinazolinylene group, a cinnolinylene group, a phenanthridinyne group, an acridinyne group, a phenanthrolinyne group, a phenazinyne group, a benzimidazolyne group, an isobenzothiazolyne group, a benzoxazolyne group, an isobenzoxazolyne group, a triazolyne group, a tetrazolyne group, an imidazopyridinyne group, an imidazopyrimidinyne group, and an azacarbazolyne group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenyne group, a fluoranthenyne group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenyne group, a hexacenyne group, a pentacenyne group, a thiophenyne group, a furanylene group, a carbazolyne group, an indolyne group, an isoindolyne group, a benzofuranylene group, a benzothiophenyne group, a dibenzofuranylene group, a dibenzothiophenyne group, a benzocarbazolyne group, a dibenzocarbazolyne group, a dibenzosilolyl group, a pyridinyne group, an imidazolyne group, a pyrazolyne group, a thiazolyne group, an isothiazolyne group, an oxazolyne group, an isoxazolyne group, a thiadiazolyne group, an oxadiazolyne group, a pyrazinyne group, a pyrimidinyne group, a pyridazinyne group, a triazinyne group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinyne group, a naphthyridinyne group, a quinoxalinyne group, a quinazolinylene group, a cinnolinylene group, a phenanthridinyne group, an acridinyne group, a phenanthrolinyne group, a phenazinyne group, a benzimidazolyne group, an isobenzothiazolyne group, a benzoxazolyne group, an isobenzoxazolyne group, a triazolyne group, a tetrazolyne group, an imidazopyridinyne group, an imidazopyrimidinyne group, and an azacarbazolyne group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, in Formulae 601 and 601-1, xe1 and xe611 to xe613 may each independently be selected from 0, 1, and 2.

In one or more embodiments, in Formulae 601 and 601-1, R₆₀₁ and R₆₁₁ to R₆₁₃ may each independently be selected from the group consisting of:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, but embodiments of the present disclosure are not limited thereto.

87

imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzo-

quinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnol-

inyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetra-

azolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

$-S(=O)_2(Q_{601})$ and $-P(=O)(Q_{601})(Q_{602})$,


wherein Q_{601} and Q_{602} may each independently be the same as described above.

The electron transport region may include at least one selected from Compounds ET1 to ET36, but embodiments of the present disclosure are not limited thereto:


88

-continued


ET3




ET1




ET4



ET2




ET5



89

-continued

ET6




5

10

15

20

ET7




25

30

35

40

ET8



50

55


60

65


90

-continued

ET9




ET10



91


-continued

ET11

**92**



-continued

ET14





ET12

ET15






ET13

ET16



93

-continued

**94**

-continued

ET17

ET20

5

10

15

20

ET18

25

30

35

40

45

ET19

50




55

60

65


ET21

ET22



95
-continued

ET23



5


10

15

20


96
-continued

ET26



ET24

25




30

35

40


45

ET27



ET25

50




55

60

65


ET28



97

-continued

ET29

**98**

-continued


ET32

5

10

15

20



25


ET30

30


35

40

45



ET33




ET31

50


55

60

65





ET34




99

-continued





In one or more embodiments, the electron transport region may include at least one compound selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, Balq, (3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ.

Alq₃


100

-continued

ET35



TAZ



NTAZ

The thicknesses of the buffer layer, the hole blocking layer, and the electron control layer may each be about 20 Å to about 1,000 Å, and in some embodiments, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are each within these ranges, the electron blocking layer may have excellent electron blocking characteristics and/or electron control characteristics without a substantial increase in driving voltage.

The thickness of the electron transport layer may be about 100 Å to about 1,000 Å, and in some embodiments, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within these ranges, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.



The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

The metal-containing material may include at least one selected from an alkali metal complex and an alkaline earth metal complex. The alkali metal complex may include a metal ion selected from an Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. The ligands coordinated with the metal ion of the alkali metal complex or the alkaline earth metal complex may each independently be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyl oxazole, a hydroxyphenyl thiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenyl thiadiazole, a hydroxyphenyl pyridine, a hydroxyphenyl benzimi-

101

dazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) and/or ET-D2.



The electron transport region may include an electron injection layer that may facilitate injection of electrons from the second electrode **190**. The electron injection layer may directly contact the second electrode **190**.

The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron injection layer may include a reducing dopant.

The reducing dopant may include at least one selected from an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth metal complex, and a rare earth metal complex.

The alkali metal may be selected from Na, K, Rb, and Cs. In one or more embodiments, the alkali metal may be selected from K, Rb, and Cs. In one or more embodiments, the alkali metal may be selected from Rb and Cs, but embodiments of the present disclosure are not limited thereto.

The alkaline earth metal may be selected from, Ca, Sr, and Ba.

The rare earth metal may be selected from Sc, Y, Ce, Yb, Gd, and Tb.

The alkali metal compound, the alkaline earth metal compound, and the rare earth metal compound may each independently be selected from oxides and halides (for example, fluorides, chlorides, bromides, and/or iodides) of the alkali metal, the alkaline earth metal, and rare earth metal.

The alkali metal compound may be selected from alkali metal oxides (such as Li_2O , Cs_2O , and/or K_2O) and alkali metal halides (such as LiF , NaF , CsF , KF , LiI , NaI , CsI , and KI). In one or more embodiments, the alkali metal com-

102

pound may be selected from LiF , Li_2O , NaF , LiI , NaI , CsI , and KI , but embodiments of the present disclosure are not limited thereto.

The alkaline earth metal compound may be selected from alkaline earth metal compounds (such as BaO , SrO , CaO , $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), and/or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$)). In one or more embodiments, the alkaline earth metal compound may be selected from BaO , SrO , and CaO , but embodiments of the present disclosure are not limited thereto.

The rare-earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one or more embodiments, the rare-earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments of the present disclosure are not limited thereto.

The alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may each include a metal ion selected from an alkali metal, an alkaline earth metal, and a rare earth metal, as described above. The ligands coordinated with the metal ion of the alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may each independently be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyl oxazole, a hydroxyphenyl thiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenyl thiadiazole, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

The electron injection layer may include only the reducing dopant as described above. In one or more embodiments, the electron injection layer may further include, in addition to the reducing dopant, an organic material. When the electron injection layer includes the reducing dopant and an organic material, the reducing dopant may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

The thickness of the electron injection layer may be about 1 Å to about 100 Å, and in some embodiments, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within these ranges, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[Second Electrode **190**]

The second electrode **190** may be on the organic layer **150**. The second electrode **190** may be a cathode, which is an electron injection electrode, and in this regard, a material for the second electrode **190** may be selected from a metal, an alloy, an electrically conductive compound, and mixtures thereof, each having a relatively low work function.

The second electrode **190** may include at least one selected from lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO, but embodiments of the present disclosure are not limited thereto. The second electrode **190** may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

The second electrode **190** may have a single-layered structure, or a multi-layered structure including two or more layers.

According to an embodiment of the present disclosure, the organic light-emitting device may be suitably included in one or more types or kinds of display apparatuses, for example, a passive matrix organic light-emitting display apparatus and an active matrix organic light-emitting display

103

apparatus. For example, when the organic light-emitting device is included in an active matrix organic light-emitting display apparatus, a first electrode on a substrate may be a pixel electrode, and the first electrode may be electrically connected to a source electrode or drain electrode of a thin film transistor **200**. In some embodiments, the organic light-emitting device may be included in a display apparatus that may display images on both sides.

[Description of FIGS. 2 to 4]

An organic light-emitting device **20** according to FIG. 2 may include a first capping layer **210**, a first electrode **110**, an organic layer **150**, and a second electrode **190** sequentially stacked in this stated order. An organic light-emitting device **30** according to FIG. 3 may include a first electrode **110**, an organic layer **150**, a second electrode **190**, and a second capping layer **220** sequentially stacked in this stated order. An organic light-emitting device **40** according to FIG. 4 may include a first capping layer **210**, a first electrode **110**, an organic layer **150**, a second electrode **190**, and a second capping layer **220** sequentially stacked in this stated order.

In FIGS. 2 to 4, the first electrode **110**, the organic layer **150**, and the second electrode **190** may each be understood by referring to the descriptions presented in connection with FIG. 1.

In the organic layer **150** of each of the organic light-emitting devices **20** and **40**, light generated in an emission layer may pass through the first electrode **110** (which may be a semi-transmissive electrode or a transmissive electrode) and the first capping layer **210** toward the outside. In the organic layer **150** of each of the organic light-emitting devices **30** and **40**, light generated in an emission layer may pass through the second electrode **190** (which is a semi-transmissive electrode or a transmissive electrode) and the second capping layer **220** toward the outside.

The first capping layer **210** and the second capping layer **220** may increase the external luminescent efficiency of the device, according to the principle of constructive interference.

The first capping layer **210** and the second capping layer **220** may each independently be a capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.


At least one selected from the first capping layer **210** and the second capping layer **220** may independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrin derivatives, phthalocyanine derivatives, naphthalocyanine derivatives, alkali metal complexes, and alkaline earth metal complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may each optionally be substituted with a substituent containing at least one element selected from oxygen (O), nitrogen (N), sulfur (S), selenium (Se), silicon (Si), fluorine (F), chlorine (Cl), bromine (Br), and iodine (I). In one or more embodiments, at least one selected from the first capping layer **210** and the second capping layer **220** may independently include an amine-based compound.

In one or more embodiments, at least one selected from the first capping layer **210** and the second capping layer **220** may independently include the compound represented by Formula 201 or the compound represented by Formula 202.

In one or more embodiments, at least one selected from the first capping layer **210** and the second capping layer **220** may independently include a compound selected from Com-


104

pounds HT28 to HT33 and Compounds CP1 to CP5, but embodiments of the present disclosure are not limited thereto.



105

-continued



Hereinbefore, the organic light-emitting device according to an embodiment of the present disclosure has been described in connection with FIGS. 1 to 4. However, embodiments of the present disclosure are not limited thereto.

The layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region may be formed in specific regions using one or more methods selected from vacuum deposition, spin coating, casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, and laser-induced thermal imaging.

When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of about 100° C. to about 500° C., at a vacuum degree of about 10⁻⁸ to about 10⁻³ torr, and at a deposition rate of about 0.01 to about 100 Å/sec depending on the compound to be included in each layer, and the intended structure of each layer.

When the layers constituting the hole transport region, the emission layer, and the layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to 200° C., depending on the compound to be included in each layer, and the intended structure of each layer.

[General Definitions of Substituents]

Hereinafter, definitions of substituents of compounds used herein will be presented. The number of carbon atoms used to restrict a substituent is not limited, and does not limit the properties of the substituent. Unless defined otherwise, the definition of the substituent is consistent with the general definition thereof.

The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and non-limiting examples thereof may include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkenylene group” as used herein refers to a divalent group having substantially the same structure as the C₁-C₆₀ alkyl group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond in the body (e.g., middle) or at the terminus of the C₂-C₆₀ alkyl group, and non-limiting examples thereof may include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkenyl group.

106

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the body (e.g., middle) or at the terminus of the C₂-C₆₀ alkyl group, and non-limiting examples thereof may include an ethynyl group and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having substantially the same structure as the C₂-C₆₀ alkynyl group.

The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —O-A₁₀₁ (wherein A₁₀₁ is a C₁-C₆₀ alkyl group), and non-limiting examples thereof may include a methoxy group, an ethoxy group, and an isopropoxy group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkyl group.

The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom in addition to 1 to 10 carbon atoms, and non-limiting examples thereof may include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuran group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkyl group.

The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and does not have aromaticity (e.g., is non-aromatic), and non-limiting examples thereof may include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkenyl group.

The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group may include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-hydrofuran group, and a 2,3-hydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkenyl group.

The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group may include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused (e.g., condensed) to each other.

The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to

a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group may include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be fused (e.g., condensed) to each other.

The term "C₆-C₆₀ aryloxy group" as used herein indicates —O-A₁₀₂ (wherein A₁₀₂ is a C₆-C₆₀ aryl group), and the term "C₆-C₆₀ arylthio group" as used herein indicates —S-A₁₀₃ (wherein A₁₀₃ is a C₆-C₆₀ aryl group).

The term "monovalent non-aromatic condensed polycyclic group" as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) that has two or more rings condensed with each other, only carbon atoms as a ring-forming atom, and non-aromaticity in the entire molecular structure. A non-limiting example of the monovalent non-aromatic condensed polycyclic group may be a fluorenyl group. The term "divalent non-aromatic condensed polycyclic group" as used herein refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed polycyclic group.

The term "monovalent non-aromatic condensed heteropolycyclic group" as used herein refers to a monovalent group that has two or more rings fused (e.g., condensed) to each other, has at least one heteroatom selected from N, O, Si, P, and S in addition to carbon atoms (for example, 1 to 60 carbon atoms) as ring-forming atoms, and has non-aromaticity in the entire molecular structure. A non-limiting example of the monovalent non-aromatic condensed heteropolycyclic group may be a carbazolyl group. The term "divalent non-aromatic condensed heteropolycyclic group" as used herein refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

The term "C₅-C₆₀ carbocyclic group" as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms, in which all the ring-forming atoms are carbon. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring (such as benzene), a monovalent group (such as a phenyl group), or a divalent group (such as a phenylene group). In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

The term "C₁-C₆₀ heterocyclic group" as used herein refers to a group having substantially the same structure as the C₅-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to the carbon atoms (the number of carbon atoms may be 1 to 60).

At least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ aryloxy group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀

cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from the group consisting of:

deuterium (-D), —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂),

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

wherein Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent

109

non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

The term "Ph" as used herein refers to a phenyl group, the term "Me" as used herein refers to a methyl group, the term "Et" as used herein refers to an ethyl group, the term "ter-Bu" or "Bu" as used herein refers to a tert-butyl group, and the term "OMe" as used herein refers to a methoxy group.

The term "biphenyl group" as used herein refers to "a phenyl group substituted with a phenyl group". In other words, a biphenyl group is "a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent".

The "terphenyl group" as used herein refers to "a phenyl group substituted with a biphenyl group". In other words, a terphenyl group is "a substituted phenyl group having a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group as a substituent."


110

The symbols * and *' as used herein, unless defined otherwise, denote a binding site to a neighboring atom in a corresponding formula.


Hereinafter, a compound represented by Formula 1 according to an embodiment of the present disclosure and an organic light-emitting device according to an embodiment of the present disclosure will be described in more detail with reference to Synthesis Examples and Examples. The wording "B was used instead of A" used in describing Synthesis Examples refers to that an identical number of molar equivalents (e.g., amount) of B was used in place of A.

SYNTHESIS EXAMPLES

Compounds were synthesized according to schemes below.



-continued



Synthesis Example 1: Synthesis of Compound E-1

Pd(PPh₃)₄ (0.02 equivalent (eq)), Na₂CO₃ (1.2 eq), and a mixture of toluene, distilled water, and ethanol (5:3:2 (v/v)) based on 0.1 M reagent (1 eq)) were added to a flask containing Int-3 (1 eq) and 3-(diphenylphosphoryl)phenylboronic acid (1.2 eq). The mixed solution was stirred under reflux for 12 hours. The reaction solution was cooled to room temperature, and extraction was performed using methylene chloride (MC), followed by washing using distilled water. The resulting solution was dried using MgSO₄, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-1 (yield: 82%).

High-resolution mass spectrometry (HRMS) for C₄₉H₃₅N₂OP [M]⁺: calc: 698.81, found: 697.

Elemental analysis for C₄₉H₃₅N₂OP calc: C, 84.22; H, 5.05; N, 4.01; O, 2.29; P, 4.43

Synthesis Example 2: Synthesis of Compound E-4

Pd(dba)₃ (0.03 eq), (t-Bu)₃P (0.06 eq), and toluene (based on 0.1 M reagent (1 eq)) were added to a flask containing Int-2 (1 eq) and (4-bromophenyl)diphenylphosphine oxide (1.2 eq). The mixed solution was stirred under reflux for 3 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using MgSO₄, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-4 (yield: 76.1%).

HRMS for C₄₃H₃₁N₂OP [M]⁺: calc: 622.71, found: 621.

Elemental Analysis for C₄₃H₃₁N₂OP calc: C, 82.94; H, 5.02; N, 4.50; O, 2.57; P, 4.97

Synthesis Example 3: Synthesis of Compound E-17

Pd(PPh₃)₄ (0.02 eq), Na₂CO₃ (1.2 eq), and a mixture of toluene, distilled water, and ethanol (5:3:2 (v/v)) based on 0.1 M reagent (1 eq)) were added to a flask containing Int-6 (1 eq) and 3-(diphenylphosphoryl)phenylboronic acid (1.2 eq). The mixed solution was stirred under reflux for 12 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using MgSO₄, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-17 (yield: 81.6%).

HRMS for C₄₃H₃₀NOPS [M]⁺: calc: 639.75, found: 638.
Elemental Analysis for C₄₃H₃₀NOPS calc: C, 80.73; H, 4.73; N, 2.19; O, 2.50; P, 4.84; S, 5.01

Synthesis Example 4: Synthesis of Compound E-19

Pd(dba)₃ (0.03 eq), (t-Bu)₃P (0.06 eq), and toluene (based on 0.1 M reagent (1 eq)) were added to a flask containing Int-5 (1 eq) and (4-bromophenyl)diphenylphosphine oxide (1.2 eq). The mixed solution was stirred under reflux for 3 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using MgSO₄, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-19 (yield: 73.1%).

HRMS for C₃₇H₂₆NOPS [M]⁺: calc: 563.65, found: 562.

Elemental Analysis for C₃₇H₂₆NOPS calc: C, 78.84; H, 4.65; N, 2.49; O, 2.84; P, 5.50; S, 5.69

Synthesis Example 5: Synthesis of Compound E-20

Pd(PPh₃)₄ (0.02 eq), Na₂CO₃ (1.2 eq), and a mixture of toluene, distilled water, and ethanol (5:3:2 (v/v)) based on 0.1 M reagent (1 eq)) were added to a flask containing Int-6 (1 eq) and 3-(diphenylthiophosphoryl)phenylboronic acid (1.2 eq). The mixed solution was stirred under reflux for 12 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using MgSO₄, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-20 (yield: 83%).

HRMS for C₄₃H₃₀NPS₂ [M]⁺: calc: 655.81, found: 654.

Elemental Analysis for C₄₃H₃₀NPS₂ calc: C, 78.75; H, 4.61; N, 2.14; P, 4.72; S, 9.78

Synthesis Example 6: Synthesis of Compound E-23

Pd(PPh₃)₄ (0.02 eq), Na₂CO₃ (1.2 eq), and a mixture of toluene, distilled water, and ethanol (5:3:2 (v/v)) based on 0.1 M reagent (1 eq)) were added to a flask containing Int-9 (1 eq) and 3-(diphenylphosphoryl)phenylboronic acid (1.2 eq). The mixed solution was stirred under reflux for 12 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using MgSO₄, filtered, and the residue obtained by distillation

113

under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-23 (yield: 79.7%).

HRMS for $C_{43}H_{30}NO_2P$ $[M]^+$: calc: 623.69, found: 622.

Elemental Analysis for $C_{43}H_{30}NO_2P$ calc: C, 82.81; H, 4.85; N, 2.25; O, 5.13; P, 4.97

Synthesis Example 7: Synthesis of Compound E-25

$Pd(dba)_3$ (0.03 eq), $(t-Bu)_3P$ (0.06 eq), and toluene (based on 0.1 M reagent (1 eq)) were added to a flask containing Int-8 (1 eq) and (4-bromophenyl)diphenylphosphine oxide (1.2 eq). The mixed solution was stirred under reflux for 3 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using $MgSO_4$, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-25 (yield: 70.9%).

HRMS for $C_{37}H_{26}NO_2P$ $[M]^+$: calc: 547.59, found: 546.

Elemental Analysis for $C_{37}H_{26}NO_2P$ calc: C, 81.16; H, 4.79; N, 2.56; O, 5.84; P, 5.66

Synthesis Example 8: Synthesis of Compound E-26

$Pd(PPh_3)_4$ (0.02 eq), Na_2CO_3 (1.2 eq), and a mixture of toluene, distilled water, and ethanol (5:3:2 (v/v) based on 0.1 M reagent (1 eq)) were added to a flask containing Int-9 (1 eq) and 3-(diphenylthiophosphoryl)phenylboronic acid (1.2 eq). The mixed solution was stirred under reflux for 12 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using $MgSO_4$, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-26 (yield: 79.8%).

HRMS for $C_{43}H_{30}NOPS$ $[M]^+$: calc: 639.75, found: 638.

Elemental Analysis for $C_{43}H_{30}NOPS$ calc: C, 80.73; H, 4.73; N, 2.19; O, 2.50; P, 4.84; S, 5.01

Synthesis Example 9: Synthesis of Compound E-32

$Pd(PPh_3)_4$ (0.02 eq), Na_2CO_3 (1.2 eq), and a mixture of toluene, distilled water, and ethanol (5:3:2 (v/v) based on 0.1 M reagent (1 eq)) were added to a flask containing Int-12 (1 eq) and 3-(diphenylphosphoryl)phenylboronic acid (1.2 eq). The mixed solution was stirred under reflux for 12 hours. The reaction solution was cooled to room temperature, and extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using $MgSO_4$, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-32 (yield: 80.4%).

HRMS for $C_{46}H_{36}NOP$ $[M]^+$: calc: 649.77, found: 648.

Elemental Analysis for $C_{46}H_{36}NOP$ calc: C, 85.03; H, 5.58; N, 2.16; O, 2.46; P, 4.77

Synthesis Example 10: Synthesis of Compound E-34

$Pd(dba)_3$ (0.03 eq), $(t-Bu)_3P$ (0.06 eq), and toluene (based on 0.1 M reagent (1 eq)) were added to a flask containing Int-11 (1 eq) and (4-bromophenyl)diphenylphosphine oxide (1.2 eq). The mixed solution was stirred under reflux for 3

114

hours. The reaction solution was cooled to room temperature, and an extraction was performed using MC, followed by washing using distilled water. The resulting solution was dried using $MgSO_4$, filtered, and the residue obtained by distillation under reduced pressure was separated by column chromatography, thereby completing the preparation of Compound E-34 (yield: 73.6%).

HRMS for $C_{40}H_{32}NOP$ $[M]^+$: calc: 573.68, found: 572.

Elemental Analysis for $C_{40}H_{32}NOP$ calc: C, 83.75; H, 5.62; N, 2.44; O, 2.79; P, 5.40


Example 1

An anode was prepared by cutting an indium tin oxide (ITO)-coated glass substrate (manufactured by Corning company) with an ITO thickness of $15 \Omega/cm^2$ ($500 \text{ \AA}$) to a size of $50 \text{ mm} \times 50 \text{ mm} \times 0.5 \text{ mm}$, ultrasonically cleaning the ITO glass substrate using isopropyl alcohol and pure water for 10 minutes each, exposing to UV irradiation for 10 minutes, and cleaning with ozone. Then, the ITO glass substrate was loaded into a vacuum deposition apparatus.

2-TNATA was vacuum deposited on the ITO glass substrate to form a hole injection layer having a thickness of $600 \text{ \AA}$, and Compound NPB (which is a hole-transporting compound) was vacuum deposited on the hole injection layer to form a hole transport layer having a thickness of $300 \text{ \AA}$.

[bis-(1-phenylisoquinolyl) iridium(III)acetylacetonate] ($Ir(ppy)_3$) (which is a green fluorescent dopant) and CBP were co-deposited on the hole transport layer at a weight ratio of 15:85 to form an emission layer having a thickness of $300 \text{ \AA}$.


Subsequently, Compound E-1 was deposited on the emission layer to form an electron transport layer having a thickness of $300 \text{ \AA}$, and Al was vacuum deposited on the electron transport layer to form an Al electrode (e.g., a negative electrode) having a thickness of $1,200 \text{ \AA}$, thereby completing the manufacture of an organic light-emitting device.




2-TNATA

115

-continued



NPB



CBP

Example 2

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-4 was used instead of Compound E-1 in forming the electron transport layer.

Example 3

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-17 was used instead of Compound E-1 in forming the electron transport layer.

Example 4

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-19 was used instead of Compound E-1 in forming the electron transport layer.

Example 5

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-20 was used instead of Compound E-1 in forming the electron transport layer.

Example 6

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-23 was used instead of Compound E-1 in forming the electron transport layer.

Example 7

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that

116

Compound E-25 was used instead of Compound E-1 in forming the electron transport layer.

Example 8

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-26 was used instead of Compound E-1 in forming the electron transport layer.

Example 9


An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-32 was used instead of Compound E-1 in forming the electron transport layer.

Example 10

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound E-34 was used instead of Compound E-1 in forming the electron transport layer.

Comparative Example 1

An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound Alq₃ was used instead of Compound E-1 in forming the electron transport layer.



The efficiency and lifespan (T₉₅) of each of the organic light-emitting devices of Examples 1 to 10 and the Comparative Example are summarized as shown in Table 1.

TABLE 1

	Compound for forming an electron transport layer	Efficiency (cd/A)	T ₉₅ lifespan (6,000 nits)
Example 1	E-1	46.4	970
Example 2	E-4	49.0	943
Example 3	E-17	49.2	921
Example 4	E-19	42	937
Example 5	E-20	47.9	897
Example 6	E-23	48.8	911
Example 7	E-25	47.9	956
Example 8	E-26	47.7	923
Example 9	E-32	51	942
Example 10	E-34	48	921
Comparative Example	Alq ₃	38.4	789

Compounds having the structure of Formula 1 according to an embodiment of the present disclosure were used as electron-transporting materials, and consequently, all

organic light-emitting devices including these compounds showed significantly improved characteristics, specifically lifespan characteristics, compared to the organic light-emitting device of Comparative Example 1. Accordingly, it was confirmed that the compounds having the structure of Formula 1 according to embodiments of the present disclosure were excellent electron-transporting materials with significant effects on the characteristics of the organic light-emitting devices.

The organic light-emitting devices according to an embodiment of the present disclosure may have high efficiency, low driving voltage, high luminance, and long lifespan characteristics.

It should be understood that the embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as being available for other similar features or aspects in other embodiments.

As used herein, expressions such as “at least one of”, “one of”, and “selected from”, when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. Further, the use of “may” when describing embodiments of the present disclosure refers to “one or more embodiments of the present disclosure”.

In addition, as used herein, the terms “use”, “using”, and “used” may be considered synonymous with the terms “utilize”, “utilizing”, and “utilized”, respectively.


As used herein, the terms “substantially”, “about”, and similar terms are used as terms of approximation and not as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art.

Also, any numerical range recited herein is intended to include all subranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.

While one or more embodiments have been described with reference to the drawings, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims and equivalents thereof.

What is claimed is:

1. A compound represented by Formula 1:



Formula 1

wherein, in Formula 1,

X and Y are each independently selected from O, S, CR₁₁R₁₂, and NR₁₃,

R₁, R₁₁, R₁₂, and R₁₃ are each independently selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₂-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, a substituted or unsubstituted C₅-C₆₀ carbocyclic group, and a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

at least one selected from X, Y, and R₁ comprises —P(Ph)₂=Z,

Z is selected from O and S,

at least one substituent of the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₂-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₂-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, the substituted monovalent non-aromatic condensed heteropolycyclic group, the substituted or unsubstituted C₅-C₆₀ carbocyclic group, and the substituted or unsubstituted C₁-C₆₀ heterocyclic group is selected from the group consisting of:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group; a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

119

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and


—P(=O)Q₁Q₂ and —P(=S)Q₃Q₄,

wherein Q₁ to Q₄, Q₁₁ to Q₁₇, and Q₂₁ to Q₂₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₂-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₂-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

2. The compound of claim 1, wherein:

the compound represented by Formula 1 is one selected from Formulae 2 to 4:


Formula 2




120

-continued

Formula 3



Formula 4



wherein, in Formulae 2 to 4,

R₁, R₂, and R₃ are each independently selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C₆-C₂₀ aryl group, a substituted or unsubstituted C₁-C₂₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

L₁, L₂, and L₃ are each independently selected from a substituted or unsubstituted C₆-C₂₀ arylene group, a substituted or unsubstituted C₁-C₂₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,


a is an integer selected from 0 to 2,

when the number of L₁(s), L₂(s), and L₃(s) is each two or more, a plurality of L₁(s) are equal to or different from each other, a plurality of L₂(s) are equal to or different from each other, and a plurality of L₃(s) are equal to or different from each other, and


Z is selected from O and S.

3. The compound of claim 2, wherein R₁, R₂, and R₃ are each independently represented by one selected from Formulae 2a to 2c:

2a




2b



121

-continued





wherein, in Formulae 2a to 2c, each Z_1 is independently selected from hydrogen, deuterium, a halogen group, a cyano group, a nitro group, a hydroxyl group, a carboxyl group, $-\text{P}(\text{Ph})_2=\text{O}$, $-\text{P}(\text{Ph})_2=\text{S}$, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

when the number of Z_1 (s) is two or more, a plurality of Z_1 (s) are equal to or different from each other, p is an integer selected from 1 to 7, and


* indicates a binding site.

4. The compound of claim 2, wherein L_1 , L_2 , and L_3 are each independently represented by one selected from Formulae 3a and 3b:




wherein, in Formulae 3a and 3b, * indicates a binding site.


5. The compound of claim 1, wherein the compound represented by Formula 1 is one selected from Formulae 5 to 10:




Formula 5




Formula 6




Formula 7



Formula 8



Formula 9



Formula 10

wherein, in Formulae 5 to 10,

R_1 , R_2 , R_{21} , and R_{22} are each independently selected from hydrogen, deuterium, a halogen atom, a nitro group, a cyano group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

L_1 and L_2 are each independently selected from a substituted or unsubstituted C_6 - C_{20} arylene group, a substituted or unsubstituted C_1 - C_{20} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,




123

a is selected from 0, 1, and 2,

when the number of $L_1(s)$ and $L_2(s)$ is each two or more,
a plurality of $L_1(s)$ are equal to or different from each
other, and a plurality of $L_2(s)$ are equal to or different
from each other, and

Z is selected from O and S.

6. The compound of claim 5, wherein R_1 , R_2 , R_{21} , and R_{22}
are each independently a substituted or unsubstituted C_1 - C_{10}
alkyl group, or are each independently represented by one
selected from Formulae 2a to 2c:



wherein, in Formulae 2a to 2c,



each Z_1 is independently selected from hydrogen, deute-
rium, a halogen group, a cyano group, a nitro group, a
hydroxyl group, a carboxyl group, $-P(Ph)_2=O$,
 $-P(Ph)_2=S$, a substituted or unsubstituted C_1 - C_{20} alkyl
group, a substituted or unsubstituted C_6 - C_{20} aryl group,
a substituted or unsubstituted C_1 - C_{20} heteroaryl group,
a substituted or unsubstituted monovalent non-aromatic
condensed polycyclic group, and a substituted or
unsubstituted monovalent non-aromatic condensed het-
eropolycyclic group,

when the number of $Z_1(s)$ is two or more, a plurality of
 $Z_1(s)$ are equal to or different from each other,

p is an integer selected from 1 to 7, and

* indicates a binding site.

7. The compound of claim 5, wherein L_1 and L_2 are each
independently represented by one selected from Formulae
3a and 3b:




wherein, in Formulae 3a and 3b, * indicates a binding site.

8. The compound of claim 1, wherein the compound
represented by Formula 1 is one selected from Compounds
E-1 to E-34:

124


E-1



2a 15

E-2


2b 20



2c 25

30

E-3



35


40

45

E-4

3a 55


3b 60



65

125

-continued




E-5

5

10

15

E-6



20

25


30

E-7

35

40

45




50

E-8

55


60

65


**126**

-continued


E-9



E-10




E-11



127

-continued



E-12

5

10

15


20

E-13

30

35


40



E-14

50

55

**128**

-continued

E-15

5

10

15


20

25

30

35

40




E-16

25

30

35

40




E-17

45

50


55



E-18





60

65



129

-continued

**130**

-continued

E-19

E-23

5

10

15

E-20

20

25

30

E-21

35

40






45

E-22

55





60

65






131

-continued

**132**

-continued



9. An organic light-emitting device comprising:
a first electrode;
a second electrode facing the first electrode; and
an organic layer between the first electrode and the second
electrode, the organic layer comprising an emission
layer,
wherein the organic layer comprises the compound of
claim 1.

10. The organic light-emitting device of claim 9, wherein
the emission layer is a green phosphorescent emission layer.

11. The organic light-emitting device of claim 9, wherein:
the first electrode is an anode,
the second electrode is a cathode, and
the organic layer comprises:

- i) a hole transport region between the first electrode and
the emission layer, the hole transport region comprising
at least one selected from a hole transport layer, a hole
injection layer, and an electron blocking layer, and
- ii) an electron transport region between the emission layer
and the second electrode, the electron transport region
comprising an electron transport layer and at least one
selected from a hole blocking layer and an electron
injection layer.

12. The organic light-emitting device of claim 11, wherein
the electron transport region comprises the compound rep-
resented by Formula 1.


133

13. The organic light-emitting device of claim 11, wherein the electron transport layer comprises the compound represented by Formula 1.


14. The organic light-emitting device of claim 11, wherein the hole transport region comprises a charge-generation material.

15. The organic light-emitting device of claim 14, wherein the charge-generation material is a p-dopant.

16. The organic light-emitting device of claim 15, wherein the charge-generation material is HT-D1 or F4-TCNQ:



<HT-D1>



<F4-TCNQ>


134

17. The organic light-emitting device of claim 11, wherein the electron transport region comprises a metal-containing material.


18. The organic light-emitting device of claim 11, wherein the electron transport region comprises a lithium (Li) complex.

19. The organic light-emitting device of claim 11, wherein the electron transport region comprises ET-D1 and/or ET-D2:

ET-D1



ET-D2



20. A display apparatus comprising the organic light-emitting device of claim 9, wherein the first electrode of the organic light-emitting device is electrically connected to a source electrode or drain electrode of a thin film transistor.

* * * * *

专利名称(译)	包括其的化合物和有机发光装置		
公开(公告)号	US10249829	公开(公告)日	2019-04-02
申请号	US15/179818	申请日	2016-06-10
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE JUNGSUB KIM SEULONG KIM YOUNSUN SHIN DONGWOO ITO NAOYUKI LIM JINO		
发明人	LEE, JUNGSUB KIM, SEULONG KIM, YOUNSUN SHIN, DONGWOO ITO, NAOYUKI LIM, JINO		
IPC分类号	H01L51/00 C07F9/6509 C07F9/6547 C07F9/6533 C07F9/576 C07F9/6558 H01L51/52 H01L51/50		
CPC分类号	H01L51/0072 C07F9/6547 C07F9/65335 C07F9/65583 C07F9/650994 H01L51/006 H01L51/0071 C07F9/5765 H01L2251/308 H01L51/0085 H01L51/506 H01L51/5016 H01L51/5076 H01L51/5088 H01L51/5092 H01L51/5096 H01L51/5206 H01L51/5221 H01L51/5072		
优先权	1020150164832 2015-11-24 KR		
其他公开文献	US20170148997A1		
外部链接	Espacenet		

摘要(译)

一种有机发光装置，包括第一电极;面向第一电极的第二电极;第一电极和第二电极之间的有机层，有机层包括发光层，其中有机层包括由式1表示的化合物：当式1表示的化合物用作电子传输材料时，包含该化合物的有机发光装置可显示出显著改善的效率，驱动电压，高亮度和长寿命特性。

<u>40</u>
220
190
150
110
210