



US010403851B2

(12) United States Patent
Kim et al.**(10) Patent No.: US 10,403,851 B2**
(45) Date of Patent: Sep. 3, 2019**(54) ORGANIC LIGHT EMITTING DIODE
DISPLAY****(71) Applicant: SAMSUNG DISPLAY CO., LTD.,**
Yongin-si, Gyeonggi-do (KR)**(72) Inventors: Dong Chan Kim,** Gunpo-si (KR); **Won
Jong Kim,** Suwon-si (KR); **Eung Do
Kim,** Seoul (KR); **Ji Hye Lee,** Incheon
(KR); **Da Hea Im,** Incheon (KR); **Sang
Hoon Yim,** Suwon-si (KR); **Yoon
Hyeung Cho,** Yongin-si (KR); **Won
Suk Han,** Yongin-si (KR)**(73) Assignee: Samsung Display Co., Ltd.,** Yongin-si
(KR)**(*) Notice:** Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.**(21) Appl. No.: 14/985,285****(22) Filed: Dec. 30, 2015****(65) Prior Publication Data**

US 2016/0329521 A1 Nov. 10, 2016

(30) Foreign Application Priority Data

May 6, 2015 (KR) 10-2015-0063363

(51) Int. Cl.
H01L 51/52 (2006.01)
H01L 27/32 (2006.01)**(52) U.S. Cl.**
CPC **H01L 51/5253** (2013.01); **H01L 27/3244**
(2013.01); **H01L 51/5275** (2013.01)**(58) Field of Classification Search**
CPC H01L 27/3211; H01L 51/0061; H01L
51/5246; H01L 51/5253; H01L 51/5275
See application file for complete search history.**(56) References Cited**

U.S. PATENT DOCUMENTS

5,677,572 A	10/1997	Hung et al.	
7,875,895 B2	1/2011	Kwack et al.	
8,212,269 B2 *	7/2012	Karg	H01L 51/5262 257/98
9,368,757 B2	6/2016	Choi et al.	
2006/0250084 A1 *	11/2006	Cok	H01L 51/5234 313/512
2008/0278067 A1	11/2008	Tyan et al.	
2010/0001301 A1	1/2010	Karg et al.	
2011/0121271 A1	5/2011	Jeon et al.	
2011/0163330 A1 *	7/2011	Kim	H01L 51/5256 257/88
2011/0309739 A1 *	12/2011	Song	H01L 51/5088 313/504
2011/0315314 A1 *	12/2011	Lee	B32B 38/162 156/281
2013/0187141 A1	7/2013	Nakamura et al.	

2014/0103314 A1	4/2014	Satoh et al.	
2014/0138636 A1	5/2014	Song	
2014/0159023 A1 *	6/2014	Matsumoto	H01L 51/0061 257/40
2014/0284566 A1 *	9/2014	Yoo	H01L 51/5012 257/40
2014/0370307 A1	12/2014	Hao et al.	
2016/0329521 A1	11/2016	Kim et al.	
2016/0380235 A1 *	12/2016	Kim	H01L 51/5262 257/40
2017/0207421 A1	7/2017	Matsuzaki et al.	
2018/0039117 A1	2/2018	Ikeda et al.	

FOREIGN PATENT DOCUMENTS

CN	101044642 A	9/2007
CN	102074568 A	5/2011
CN	102157543 A	8/2011
CN	102290531 A	12/2011
CN	102655164 A	9/2012
CN	103534833 A	1/2014
JP	2009-044104 A	2/2009
KR	10-2011-0058126 A	6/2011
KR	10-2014-0008215	1/2014
KR	10-2014-0038656 A	3/2014
KR	10-2014-0064349 A	5/2014
WO	WO 2012/157211	* 11/2012

OTHER PUBLICATIONS

Magnesium Fluoride (MgF₂), Janos Technology, 2017.*
Machine translation of KR 10-2011-0058126, published on Jun. 1, 2011.*
Machine translation of CN 102157543 A, published on Aug. 17, 2011 (Year: 2011).*
U.S. Office Action dated May 21, 2018, issued in U.S. Appl. No. 15/087,808 (10 pages).
U.S. Final Office Action dated Nov. 23, 2018, issued in U. S. Appl. No. 15/087,808 (11 pages).
U.S. Notice of Allowance dated Mar. 13, 2019, issued in U.S. Appl. No. 15/087,808 (9 pages).

* cited by examiner

Primary Examiner — Anca Eoff

(74) Attorney, Agent, or Firm — Lewis Roca Rothgerber
Christie LLP**(57) ABSTRACT**

An organic light emitting diode display includes: a substrate; an organic light emitting element on the substrate; and a capping layer on the organic light emitting element and including a high refraction layer formed of an inorganic material having a refractive index which is equal to or greater than about 1.7 and equal to or less than about 6.0, wherein the inorganic material includes at least one selected from CuI, thallium iodide (TlI), AgI, CdI₂, HgI₂, SnI₂, PbI₂, BiI₃, ZnI₂, MnI₂, FeI₂, CoI₂, NiI₂, aluminum iodide (AlI₃), thorium (IV) iodide (ThI₄), uranium triiodide (UI₃), MgS, MgSe, MgTe, CaS, CaSe, CaTe, SrS, SrSe, SrTe, BaS, BaSe, BaTe, SnS, PbS, CdS, CaS, ZnS, ZnTe, PbTe, CdTe, SnSe, PbSe, CdSe, CuO, Cu₂O, WO₃, MoO₃, SnO₂, Nb₂O₅, Ag₂O, CdO, CoO, Pr₂O₃, Bi₂O₃, Fe₂O₃, AlAs, GaAs, InAs, GaP, InP, AlP, AlSb, GaSb, and InSb.

12 Claims, 6 Drawing Sheets

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6



1

ORGANIC LIGHT EMITTING DIODE DISPLAY

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to and the benefit of Korean Patent Application No. 10-2015-0063363 filed in the Korean Intellectual Property Office on May 6, 2015, the entire contents of which are incorporated herein by reference.

BACKGROUND

1. Field

Embodiments of the present disclosure relate to an organic light emitting diode display.

2. Description of the Related Art

The recent trend toward lightweight and thin personal computers and television sets necessitates lightweight and thin display devices. Flat panel displays (e.g., a liquid crystal display (LCD)) satisfying such requirements are being substituted for conventional cathode ray tubes (CRTs). However, since an LCD is a passive display device, an additional backlight is used as a light source, and LCDs have various problems, such as a slow response time and a narrow viewing angle.

In this regard, an organic light emitting diode (OLED) display has recently been highlighted as a self-emission display device having features of a wide viewing angle, outstanding contrast, and a fast response time.

The OLED display includes organic light emitting diodes for emitting light, and in the organic light emitting diodes, electrons injected from one electrode and holes injected from another electrode are combined with each other in a light emitting layer, thereby generating excitons, and energy is outputted from the excitons to emit light.

Various suitable methods that can improve light efficiency by effectively extracting light that is generated in the organic light emitting layer are necessitated.

The above information disclosed in this Background section is only to enhance the understanding of the background of the present disclosure and therefore it may contain information that does not form the prior art that is already known in this country to a person of ordinary skill in the art.

SUMMARY

Embodiments of the present disclosure have been made in an effort to provide an organic light emitting diode display in which light efficiency is improved.

An exemplary embodiment of the present disclosure provides an organic light emitting diode display including: a substrate; an organic light emitting element disposed on the substrate; and a capping layer disposed on the organic light emitting element and including a high refraction layer formed of an inorganic material with a refractive index which is equal to or greater than about 1.7 and equal to or less than about 6.0, wherein the inorganic material may include at least one selected from CuI, thallium iodide (TlI), AgI, CdI₂, HgI₂, SnI₂, PbI₂, BiI₃, ZnI₂, MnI₂, FeI₂, CoI₂, NiI₂, aluminium iodide (AlI₃), thorium (IV) iodide (ThI₄), uranium triiodide (UI₃), MgS, MgSe, MgTe, CaS, CaSe, CaTe, SrS, SrSe, SrTe, BaS, BaSe, BaTe, SnS, PbS, CdS,

2

CaS, ZnS, ZnTe, PbTe, CdTe, SnSe, PbSe, CdSe, CuO, Cu₂O, WO₃, MoO₃, SnO₂, Nb₂O₅, Ag₂O, CdO, CoO, Pr₂O₃, Bi₂O₃, Fe₂O₃, AlAs, GaAs, InAs, GaP, InP, AlP, AlSb, GaSb, and InSb.

The capping layer may include a low refraction layer formed of an inorganic material with a refractive index which is equal to or greater than about 1.0 and equal to or less than about 1.7.

The low refraction layer may be disposed between the high refraction layer and the organic light emitting element.

The low refraction layer may include an inorganic material including a halogen compound.

The low refraction layer may include at least one selected from MgF₂, LiF, AlF₃, NaF, KF, RbF, CaF₂, SrF₂, and YbF₂.

A refraction layer including the low refraction layer and the high refraction layer may be formed in plural.

The organic light emitting diode display may further include an encapsulation substrate assembled on and sealing the substrate in order to cover the organic light emitting element.

The encapsulation substrate and the organic light emitting element may be spaced apart from each other.

The organic light emitting element may include a first electrode and a second electrode facing each other, and a light emitting layer disposed between the first electrode and the second electrode, wherein the capping layer is disposed directly on the second electrode.


The first electrode may be formed as a reflective layer.

The light emitting layer may include a red light emitting layer, a green light emitting layer, a blue light emitting layer, and an auxiliary layer disposed below the blue light emitting layer.

The organic light emitting diode display may further include a red resonant auxiliary layer disposed below the red light emitting layer and a green resonant auxiliary layer disposed below the green light emitting layer.

The auxiliary layer may include a compound represented by Chemical Formula 1.


Chemical Formula 1



In Chemical Formula 1, A1, A2, and A3 may be an alkyl group, an aryl group, carbazole, dibenzothiophene, dibenzofuran (DBF), and biphenyl, respectively, and a, b, and c may be each independently positive numbers of zero to four, respectively.

3

The auxiliary layer may include a compound represented by Chemical Formula 2.



In Chemical Formula 2, a may be 0 to 3, b and c may be 0 to 3, respectively, X may be selected from O, N, or S, and each X may be the same as the other or different.

According to an exemplary embodiment of the present disclosure, it is possible to improve light efficiency of an organic light emitting diode display by forming a capping layer with an inorganic material that has a high refractive index.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, together with the specification, illustrate embodiments of the subject matter of the present disclosure, and, together with the description, serve to explain principles of embodiments of the subject matter of the present disclosure.

FIG. 1 is a pixel layout view of an organic light emitting diode display according to an exemplary embodiment of the present disclosure.

FIG. 2 is a cross-sectional view of FIG. 1 taken along line II-II.

FIG. 3 is a cross-sectional view of an exemplary embodiment of the organic light emitting diode display of FIG. 2 including a variation of a capping layer.

FIG. 4 is an enlarged cross-sectional view of the circled area A of the organic light emitting element of FIG. 2.

FIG. 5 is a cross-sectional view of a partially modified organic light emitting element of FIG. 4.

FIG. 6 is a cross-sectional view of an exemplary embodiment of the organic light emitting diode display of FIG. 3 in which an air layer is replaced with a filler.

DETAILED DESCRIPTION

Embodiments of the present disclosure will be described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments of the disclosure are shown. As those skilled in the art would realize, the described embodiments may be modified in various different ways, all without departing from the spirit or scope of the present invention. On the contrary, exemplary embodiments introduced herein are provided to make the present disclo-

4

sure thorough and complete and to sufficiently convey the spirit of the present invention to those skilled in the art.

In the drawings, the thickness of layers and regions may be exaggerated for clarity. In addition, when a layer is described to be formed on another layer or on a substrate, this means that the layer may be formed on the other layer or on the substrate (e.g., the layer may be directly on the other layer or substrate), or a third layer may be interposed between the layer and the other layer or the substrate (e.g., the layer may be indirectly on the other layer or substrate). Like reference numerals designate like elements throughout the specification.

FIG. 1 is a pixel layout view of an organic light emitting diode display according to the exemplary embodiment of the present disclosure. FIG. 2 is a cross-sectional view of FIG. 1 taken along line II-II.

Referring to FIGS. 1 and 2, an organic light emitting diode display 101 according to an exemplary embodiment of the present disclosure includes a substrate 110, a driving circuit DC, an organic light emitting element 70, a capping layer 500, and an encapsulation substrate 210. The organic light emitting diode display 101 may further include a buffer layer 120 and a pixel defining layer 190.

The substrate 110 may be made of an inorganic material such as, for example, glass, an organic (e.g., an organic material) such as, for example, polycarbonate, polymethyl methacrylate, polyethylene terephthalate, polyethylene naphthalate, polyamide, polyimide, polyether sulfone, or combinations or mixtures thereof, a silicon wafer, a metal, or the like.

The buffer layer 120 is disposed on the substrate 110. The buffer layer 120 may be formed as one or more various suitable inorganic and organic films. The buffer layer 120 prevents undesired elements, such as impurities or moisture from penetrating the driving circuit DC or the organic light emitting element 70 (or reduces such penetration of the undesired elements), and concurrently or simultaneously flattens the surface thereof. The buffer layer 120 may be formed of a material that performs such function. For example, the buffer layer 120 may be any one of a silicon nitride (e.g., SiNx ; $\frac{1}{2} \leq x \leq 2$, e.g., $x=1.33$) film, a silicon oxide (e.g., SiOy ; $1 \leq y \leq 2$, e.g., $y=2$) film, or a silicon oxynitriding (e.g., SiOxNy ; $1 \leq x \leq 2$ and $1 \leq y \leq 2$) film (a silicon oxynitride film). However, the buffer layer 120 is not a necessary component and may not be provided depending on the type or kind and the process conditions of the substrate 110.

The driving circuit DC is disposed on buffer layer 120. The driving circuit DC includes a plurality of thin film transistors 10 and 20, and drives the organic light emitting element 70. For example, the organic light emitting element 70 emits light according to a driving signal provided by the driving circuit DC, and displays an image.

The organic light emitting element 70 emits light according to the driving signal provided by the driving circuit DC. Further, the organic light emitting element 70 includes a first electrode 710 that is an anode capable of injecting holes, a second electrode 730 that is a cathode capable of injecting electrons, and a light-emitting element layer 720 disposed between the first and second electrodes 710 and 730. For example, the first electrode 710, the light-emitting element layer 720, and the second electrode 730 are sequentially stacked to form the organic light emitting element 70. However, the present disclosure is not limited thereto. For example, the first electrode 710 may be a cathode electrode, and the second may be an anode electrode 730.

The first electrode **710** according to an exemplary embodiment of the present disclosure may be formed as a reflective layer and the second electrode **730** may be formed as a semi-transmissive layer or a transparent conductive layer. Accordingly, light generated from the light-emitting element layer **720** is emitted through the second electrode **730**. For example, the organic light emitting diode display **101** according to an exemplary embodiment of the present disclosure has a front light-emitting type or kind of a cavity structure.

The reflective layer and the semi-transmissive layer are made of at least one metallic material selected from magnesium (Mg), silver (Ag), gold (Au), calcium (Ca), lithium (Li), chromium (Cr), aluminum (Al), and alloys thereof. Whether the layer is the reflective layer or the semi-transmissive layer is determined by the thickness thereof. In general, the semi-transmissive layer has a thickness that is less than about 200 nm (e.g., a thickness greater than 0 to less than about 200 nm). The thinner the semi-transmissive layer, the greater the transmittance of light through the semi-transmissive layer is, and the thicker the semi-transmissive layer, the less the transmittance of light through the semi-transmissive layer is.

The first electrode **710** may further include a transparent conductive layer. For example, the first electrode **710** may have a multi-layered structure including a reflective layer and a transparent conductive layer. The transparent conductive layer of the first electrode **710** is disposed between the reflective layer and the light-emitting element layer **720**. The first electrode **710** may be formed to have a triple-layered structure in which a transparent conductive layer, a reflective layer, and a transparent conductive layer are sequentially stacked. For example, the first electrode **710** may be formed to have a structure in which indium-tin oxide (ITO), silver (Ag), and indium-tin oxide (ITO) are sequentially stacked.

The first electrode **710** may be formed by sputtering or vacuum deposition.

The transparent conductive layer is made of a material such as indium tin oxide (ITO), indium zinc oxide (IZO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), and/or the like. The transparent conductive layer has a relatively high work function. Accordingly, when the first electrode **710** is formed to have the transparent conductive layer, holes are smoothly injected through the first electrode **710**.

The light-emitting element layer **720** is formed as a multi-layer including one or more selected from a light emitting layer, a hole-injection layer (HIL), a hole-transporting layer (HTL), an electron-transporting layer (ETL), and an electron injection layer (EIL). Among the above-mentioned layers, the remaining layers other than the light emitting layer may be omitted if necessary or desired. When the light-emitting element layer **720** includes all of the above-mentioned layers, the hole-injection layer (HIL) is disposed on the first electrode **710** that is an anode electrode, and the hole-transporting layer (HTL), the light emitting layer, the electron-transporting layer (ETL), and the electron injection layer (EIL) are sequentially stacked on the hole-injection layer (HIL). The light-emitting element layer **720** may further include another layer if necessary or desired.

The pixel defining layer **190** includes an opening **1905**. The opening **1905** of the pixel defining layer **190** partially exposes the first electrode **710**. The first electrode **710**, the light-emitting element layer **720**, and the second electrode **730** are sequentially stacked in the opening **1905** of the pixel defining layer **190**. In this case, the second electrode **730** is formed on not only the light-emitting element layer **720** but

also on the pixel defining layer **190**. Layers other than the light emitting layer among the light-emitting element layer **720** may be disposed between the pixel defining film **190** and the second electrode **730**. The organic light emitting element **70** emits light in the light-emitting element layer **720** that is disposed within the opening **1905** of the pixel defining layer **190**. For example, the opening **1905** of the pixel defining layer **190** defines a light emitting area.

The capping layer **500** is formed on the organic light emitting element **70**. The capping layer **500** assists with effectively or suitably emitting light generated in the light-emitting element layer **720** to the outside while protecting the organic light emitting element **70**.

In the present exemplary embodiment, the capping layer **500** includes an inorganic material having a refractive index which is equal to or greater than about 1.7 and equal to or less than about 6.0 (e.g., a refractive index of about 1.7 to about 6.0). In the present exemplary embodiment, an inorganic material forming the capping layer **500** includes at least one selected from copper iodide (CuI), thallium iodide (TlI), silver iodide (AgI), cadmium iodide (CdI_2), mercury iodide (HgI_2), stannum iodide (SnI_2), lead iodide (PbI_2), bismuth iodide (BiI_3), zinc iodide (ZnI_2), manganese iodide (MnI_2), iron iodide (FeI_2), cobalt iodide (CoI_2), nickel iodide (NiI_2), aluminium iodide (AlI_3), thorium (IV) iodide (ThI_4), and uranium triiodide (UI_3), which are transient metal-based iodides. Among the halogen materials, fluoride has low refractive characteristics, and iodide has high refractive characteristics. Accordingly, since the above-mentioned inorganic materials as transient metal-based iodides are a high refractive material, which is capable of thermal evaporation at a temperature of less than about 500 degrees Celsius, a thermal evaporation source for a thermal evaporation process is not necessarily a high temperature system, and thus costs may be reduced. Further, even when a thermal evaporation is performed under the same or substantially the same condition as in a vacuum, deposition may be implemented by a thermal evaporation method at a temperature of less than about 250 degrees Celsius. Since thermal evaporation may be performed at a relatively low temperature, resonance may strongly occur without change of electrical characteristics of the organic light emitting element **70**. Accordingly, when the capping layer **500** is formed of the inorganic material of the transient metal-based iodides such as the CuI or TlI, light efficiency may increase without change of electrical characteristics of the organic light emitting element **70**. Further, since density of the CuI (5.67 g/cm³) and density of the TlI (7.29 g/cm³) are high, the capping layer may be immune to or substantially non-reactive toward oxygen and moisture. The thermal evaporation temperature of the oxide-based or nitride-based material, which are materials having a high refractive index, is relatively higher than that of an organic material.

The capping layer **500** is not limited to the above-mentioned exemplary embodiment, and it may include at least one selected from MgS, MgSe, MgTe, CaS, CaSe, CaTe, SrS, SrSe, SrTe, BaS, BaSe, BaTe, SnS, PbS, CdS, CaS, ZnS, ZnTe, PbTe, CdTe, SnSe, PbSe, CdSe, CuO, Cu_2O , WO_3 , MoO_3 , SnO_2 , Nb_2O_5 , Ag_2O , CdO, CoO, Pr_2O_3 , Bi_2O_3 , Fe_2O_3 , AlAs, GaAs, InAs, GaP, InP, AlP, AlSb, GaSb, and InSb.

The encapsulation substrate **210** is disposed on the capping layer **500**. The encapsulation substrate **210** is an insulating substrate made of glass, quartz, ceramic, plastic, or the like. The encapsulation substrate **210** and the substrate **110** are assembled and sealed together to cover the organic light emitting element **70**. In this case, the encapsulation

substrate **210** and the organic light emitting element **70** are spaced apart from each other. Further, a space between the encapsulation substrate **210** and the substrate **110** is sealed by a sealant.

In addition, an air layer **300** is disposed in a space between the encapsulation substrate **210** and the organic light emitting element **70**. The air layer **300**, in the present exemplary embodiment, may have a refractive index lower than that of the capping layer **500** corresponding to a high refraction layer.

An exemplary variation of the capping layer **500** will now be described with reference to FIG. **3**.

FIG. **3** is a cross-sectional view of an exemplary embodiment having a variation of the capping layer of FIG. **2**.

In the exemplary embodiment of FIG. **3**, an organic light emitting diode **102** includes a capping layer **500** including a multi-layered layer having different refractive indexes. The capping layer **500** increases an extracting ratio of light emitted from the light-emitting element layer **720** of the organic light emitting element **70**, thereby improving light efficiency.

For example, in FIG. **3** the capping layer **500** has a structure in which a low refraction layer **510** and a high refraction layer **520** are alternately stacked. Although one low refraction layer **510** and one high refraction layer **520** are shown in FIG. **3**, the capping layer **500** is not limited thereto, and it may be formed of three or more layers, including one or more low refraction layer **510** and one or more high refraction layer **520**. For example, the capping layer may include a plurality of refraction layer each including the low refraction layer and the high refraction layer.

In the present exemplary embodiment, the low refraction layer **510** may include an inorganic material having a refractive index which is equal to or greater than about 1.0 and equal to or less than about 1.7 (e.g., a refractive index of about 1.0 to about 1.7). An inorganic material used in the low refraction layer **510** may include a Group I element, a Group II element, a lanthanide, or a transition metal based halogen compound. In some embodiments, the low refraction layer **510** may include fluorine of a halogen compound. For example, the low refraction layer **510** may include at least one selected from MgF_2 , LiF , AlF_3 , NaF , KF , RbF , CaF_2 , SrF_2 , and YbF_2 .

The high refraction layer **520** is disposed on the farthest top layer from the organic light emitting element **70**. For example, the high refraction layer **520** is the farthest layer of the capping layer **500** from the organic light emitting element **70**.

The high refraction layer **520** may include an inorganic material having a refractive index which is equal to or greater than about 1.7 and equal to or less than about 6.0 (e.g., a refractive index of about 1.7 to about 6.0).

An inorganic material used in the high refraction layer **520** may, for example, include at least one selected from CuI , thallium iodide (TlI), AgI , CdI_2 , HgI_2 , SnI_2 , PbI_2 , BiI_3 , ZnI_2 , MnI_2 , FeI_2 , CoI_2 , NiI_2 , aluminium iodide (AlI_3), thorium (IV) iodide (ThI_4), and uranium triiodide (UI_3). The high refraction layer **520** is not limited to the above-mentioned exemplary embodiment, and it may include at least one selected from MgS , MgSe , MgTe , CaS , CaSe , CaTe , SrS , SrSe , SrTe , BaS , BaSe , BaTe , SnS , PbS , CdS , CaS , ZnS , ZnTe , PbTe , CdTe , SnSe , PbSe , CdSe , CuO , Cu_2O , WO_3 , MoO_3 , SnO_2 , Nb_2O_5 , Ag_2O , CdO , CoO , Pr_2O_3 , Bi_2O_3 , Fe_2O_3 , AlAs , GaAs , InAs , GaP , InP , AlP , AlSb , GaSb , and InSb .

In the present exemplary embodiment, the low refraction layer **510** has a thickness of about 100 angstroms to about

400 angstroms, and the high refraction layer **520** has a thickness of about 400 angstroms to about 800 angstroms. When the low refraction layer **510** and the high refraction layer **520** respectively have the above-mentioned thicknesses, efficiency of light which is emitted from the light-emitting element layer **720** and passes through the capping layer **500** may increase by at least 90%. However, the thickness of the capping layer **500** according to an exemplary embodiment of the present disclosure is not limited thereto. Accordingly, thickness of the low refraction layer **510** and the high refraction layer **520** may be appropriately or suitably adjusted, if necessary or desired.

Due to a refractive index difference between the low refraction layer **510** and high refraction layer **520** of the capping layer **500** one portion of light emitted from the light-emitting element layer **720** transmits through the capping layer **500**, and the other portion thereof is reflected from (or reflected by) the capping layer **500**. For example, light is reflected from an interface between the low refraction layer **510** and the high refraction layer **520**, or an interface between the high refraction layer **520** and the air layer **300**.

Light reflected from the capping layer **500** is again reflected from the first electrode **710** or the second electrode **730**, and this process is repeated, thereby amplifying the light. Further, reflection of the light may be repeated inside the capping layer **500**, thereby amplifying the light. For example, reflection of the light may be repeated between the interface between the low refraction layer **510** and the high refraction layer **520** and the interface between the high refraction layer **520** and the air layer **300**.

The organic light emitting diode display **102** may effectively or suitably amplify light through such a resonance effect, thereby improving light efficiency.

In some embodiments, since the low refraction layer **510** and the high refraction layer **520** have different refractive indexes, light is reflected from the interface between the low refraction layer **510** and the high refraction layer **520** due to the refractive index between the low refraction layer **510** and the high refraction layer **520**. The air layer **300**, which directly contacts the high refraction layer **520**, may be a low refractive material. In some embodiments, the air layer **300** has a refractive index of about 1.

Therefore, each of the low refraction layer **510** and the high refraction layer **520** has a refractive index of a set or predetermined range based on a refractive index of the air layer **300** and characteristics of a material that is used for manufacturing each of the refraction films **510** and **520**. For example, the refractive index of the high refraction layer **520** may be equal to or greater than about 1.0 and equal to or less than about 6.0 (e.g., a refractive index of about 1.0 to about 6.0) depending on the component of the high refraction layer **520**. The refractive index of the low refraction layer **510** may be equal to or greater than about 1.0 and less than about 1.7 (e.g., a refractive index of about 1.0 to about 1.7) depending on the component of the low refraction layer **510**. In this case, even if the low refraction layer **510** and the high refraction layer **520** are formed of the same or substantially the same material, their refractive indexes may be different from each other depending on a manufacturing method thereof.

The features and contents described with respect to FIG. **2**, as well as the above-described difference, may be applied to the exemplary embodiment of FIG. **3**.

As described with respect to an exemplary embodiment of the present disclosure, compared to the capping layer **500**

formed of an inorganic material, table 1 represents changes of light efficiency of the capping layer **500** formed of an organic material.

TABLE 1

	Single organic layer	Double organic layer	Organic/ Inorganic double layer	Single inorganic layer	Single inorganic layer	Double inorganic layer	Double inorganic layer
Upper layer	Organic material 1	Organic material 2	Organic material 2	CuI	TiI	CuI	TiI
Lower layer	—	BaIq	AlF ₃	—	—	AlF ₃	AlF ₃
Relative efficiency	1.0	1.06	1.08	1.10	1.17	1.13	1.13

Referring to Table 1, when light efficiency is set at about 1.0 in the case where the capping layer **500** is formed as a single organic layer with organic material **1** and the light efficiency is set at about 1.06 in the case where the capping layer **500** is formed as a double organic layer with an organic material **2** and BaIq, a relative light efficiency of the capping layer **500** formed of a measured CuI is improved by about 10%, and when a lower layer of the capping layer is formed of AlF₃ and an upper layer of the capping layer is formed of CuI, a relative light efficiency of the capping layer is improved by about 13%. In this case, the organic material **1** and the organic material **2** may have a refractive index of about 1.88 to about 1.90, and they may be any suitable organic material available for use in a manufactured capping layer with the refractive index.

Structures of the driving circuit DC and the organic light emitting element **70** will now be described in more detail.

Referring to FIGS. **1** and **2**, although an active matrix (AM) type or kind of organic light emitting diode display **101** having a 2Tr-1Cap structure where a pixel is provided with two thin film transistors (TFTs) **10** and **20** and one capacitor **80** is illustrated, the present disclosure is not limited thereto. Accordingly, the organic light emitting diode display **101** may be provided with three or more thin film transistors and two or more storage capacitors in one pixel, and may be configured to have various suitable structures having additional wires. Herein, a pixel represents a base or minimum unit displaying an image and the organic light emitting diode display **101** displays images by using a plurality of pixels.

A switching thin film transistor **10**, a driving thin film transistor **20**, a capacitor **80**, and an organic light emitting diode (OLED) **70** are formed in each pixel. Here, a configuration including the switching thin film transistor **10**, the driving thin film transistor **20**, and the capacitor **80** is referred to as a driving circuit DC. In addition, gate lines **151** disposed in one direction, data lines **171** crossing the gate lines **151**, and common power lines **172** are formed. Although each pixel may be defined by taking the gate lines **151**, the data line **171**, and the common power line **172** as a boundary, the present disclosure is not limited thereto.

The organic light emitting element **70** includes a first electrode **710**, a light-emitting element layer **720** disposed on the first electrode **710**, and a second electrode **730** formed on the light-emitting element layer **720**. Holes and electrodes from the first electrode **710** and the second electrode **730** are injected into the light-emitting element layer **720**. Light is emitted when excitons in which the injected holes and electrons are combined drop from an excited state to a ground state.

The capacitor **80** includes a pair of capacitor plates **158** and **178** disposed with an interlayer insulating layer **160**

interposed therebetween. Here, the interlayer insulating layer **160** becomes (or includes) a dielectric material. The capacitance of the capacitor **80** is determined depending

upon the charges charged in the capacitor **80**, and the voltages of the capacitor plates **158** and **178**.

The switching thin film transistor **10** includes a switching semiconductor layer **131**, a switching gate electrode **152**, a switching source electrode **173**, and a switching drain electrode **174**. The driving thin film transistor **20** includes a driving semiconductor layer **132**, a driving gate electrode **155**, a driving source electrode **176**, and a driving drain electrode **177**. A gate insulating layer **127** may be disposed between the driving semiconductor layer **132** and the driving gate electrode **155**.

The switching thin film transistor **10** is used as a switch to select a pixel to emit light. The switching gate electrode **152** is coupled or connected to the gate line **151**. The switching source electrode **173** is coupled or connected to the data line **171**. The switching drain electrode **174** is spaced apart from the switching source electrode **173** and is coupled or connected to one (**158** in this case) of the capacitor plates **158** and **178**. The switching drain electrode **174** is disposed to be spaced apart from the switching source electrode **173** and is coupled or connected to the capacitive plate **158**.

The driving thin film transistor **20** applies driving power to the pixel electrode **710** for light emission of the light-emitting element layer **720** of the organic light emitting element **70** in the selected pixel. The driving gate electrode **155** is coupled or connected to the capacitor plate **158** that is coupled or connected to the switching drain electrode **174**. The driving source electrode **176** and the capacitor plate **178** are respectively coupled or connected to the common power lines **172**. The driving drain electrode **177** is coupled or connected to the pixel electrode **710** of the organic light emitting element **70** through a contact hole.

With such a structure, the switching thin film transistor **10** is driven by a gate voltage applied to the gate line **151** to transmit a data voltage applied to the data line **171** to the driving thin film transistor **20**. A voltage corresponding to a voltage difference between the common voltage applied to the driving thin film transistor **20** from the common power line **172** and the data voltage transmitted from the switching thin film transistor **10** is stored in the capacitor **80**, and a current corresponding to the voltage stored in the capacitor **80** flows to the organic light emitting element **70** through the driving thin film transistor **20** such that the organic light emitting element **70** emits light.

Hereinafter, an organic light emitting element **70** according to an exemplary embodiment of the present disclosure will be described with reference to FIG. **4**.

FIG. **4** is an enlarged cross-sectional view of the circled area A of the organic light emitting element of FIG. **2**.

Referring to FIGS. **2** and **4**, the organic light emitting element (portion "A" of FIG. **2**) according to an exemplary

embodiment of the present disclosure includes a structure in which the first electrode **710**, a hole transport layer **714**, a light emitting layer **715**, an electron-transporting layer **777**, an electron injection layer **779**, and the second electrode **730** are sequentially stacked.

In the organic light emitting element **70** according to the present exemplary embodiment, the first electrode **710**, as described above, is formed as a reflective layer so as to have a front light-emitting type or kind of structure, and the second electrode **730** corresponding to the common electrode may be formed as a semi-transmissive layer.

The hole transport layer **714** is formed on the first electrode **710**. The hole transport layer **714** may transport holes transmitted from a hole-injection layer formed between the first electrode **710** and the hole transport layer **714**. The hole transport layer **714** may include an organic material. For example, the hole transport layer **714** may include NPD (N,N-dinaphthyl-N,N'-diphenyl benzidine), TPD (N,N'-bis-(3-methylphenyl)-N,N'-bis-(phenyl)-benzidine), s-TAD, and MTDATA (4,4',4''-Tris (N-3-methylphenyl-N-phenyl-amino)-triphenylamine), but the hole transport layer is not limited thereto.

The hole transport layer **714** may be about 15 nm to about 25 nm thick. For example, the hole transport layer **714** may be about 20 nm thick. The hole transfer/injection layers may be formed to be a single layer by transforming the above-described hole transport layer **714** and including a hole injecting material in the hole transport layer **714**.

The light emitting layer **715** is disposed on the hole transport layer **714**. The light emitting layer **715** includes a light emitting material for expressing a set or specific color. For example, the light emitting layer **715** may express basic colors, such as blue, green, or red, or combinations or mixtures thereof.

The light emitting layer **715** may be about 10 nm to about 50 nm thick. The light emitting layer **715** includes a host and a dopant. The light emitting layer **715** may include a material emitting red, green, blue, and white light, and may be made of a phosphorescent or fluorescent material.

The light emitting layer **715** emits red light, it may be made of a phosphorescent material including a host material, which includes CBP (carbazole biphenyl) or mCP (1,3-bis (carbazol-9-yl)), and a dopant, which includes any one or more selected from a group of PIQIr(acac) (bis (1-phenylisoquinoline)acetylacetonate iridium), PQIr(acac) (bis (1-phenylquinoline)acetylacetonate iridium), PQIr(tris (1-phenylquinoline)iridium) and PtOEP(octaethylporphyrin platinum), or it may be made of a fluorescent material including PBD:Eu(DBM)3(Phen) or Perylene, but the light emitting layer is not limited thereto.

When the light emitting layer **715** emits green light, it may be made of a phosphorescent material including a host material, which includes CBP or mCP, and a dopant material, which includes, Ir(ppy)3(fac-tris (2-phenylpyridine) iridium), or it may be made of a fluorescent material including Alq3(tris (8-hydroxyquinolino)aluminum), but the light emitting layer is not limited thereto.

When the light emitting layer **715** emits blue light, it may be made of a phosphorescent material including a host material, which includes CBP or mCP, and a dopant material, which includes (4,6-F2ppy)2Irpic. In some embodiments, the light emitting layer may be made of a fluorescent material including at least one selected from spiro-DPVBi, spiro-6P, distyryl benzene (DSB), distyrylarylene (DSA), PFO-based polymer, and PPV-based polymer, but the fluorescent material is not limited thereto.

The electron-transporting layer **777** is disposed on the light emitting layer **715**. The electron-transporting layer **777** may transmit the electron to the light emitting layer **715** from the second electrode **730**. The electron-transporting layer **777** may prevent the holes injected by the first electrode **710** from moving to the second electrode **730** through the light emitting layer **715** (or may reduce such movement of the holes). For example, the electron-transporting layer **777** functions as a hole blocking layer to help the holes and the electrons bond in the light emitting layer **715**.

The electron-transporting layer **777** may include an organic material. For example, the electron-transporting layer **777** may be made of any one or more selected from a group of Alq3 (tris (8-hydroxyquinolino) aluminum), PBD, TAZ, spiro-PBD, BAlq and SALq, but the electron-transporting layer is not limited thereto.

The electron injection layer **779** is disposed on the electron-transporting layer **777**. The electron injection layer **779** functions to improve the injection of electrons to the electron-transporting layer **777** from the second electrode **730**. The electron injection layer **779** according to the present exemplary embodiment includes a dipole material and a first metal. Here, the dipole material and the first metal are co-deposited to form one layer. The first metal may include at least one selected from Yb, Mg, Li, Na, Ca, Sr, Ba, In, Sn, La, Ce, Pr, Nd, Pm, Eu, Gd, Tb, Dy, Ho, Er, Sm, and Lu.

The dipole material consists of a first component and a second component of different polarities, which are coupled to each other, and the first component may include one selected from an alkali metal, an alkali earth metal, a rare-earth metal, and a transition metal, and the second component may include a halogen. For example, the first component may be an element including at least one selected from Li, Na, K, Rb, Cs, Be, Mg, Ca, Sr, and Ba, and the second component may be an element including at least one selected from F, Cl, Br, and I. Here, the first component is an element that becomes a cation when the dipole material is ionized, and the second component may be an element that becomes an anion.

In the present exemplary embodiment, the thickness of the electron injection layer **779** has a low or minimum value of about 5 angstroms (Å) by considering a process margin and a high or maximum value of about 50 angstroms (Å) by considering the difficulty as a function of the electron injection layer, and thereby a range thereof may be about 5 angstroms (Å) to about 50 angstroms (Å). In some embodiments, however, the thickness of the electron injection layer may be about 10 angstroms (Å) to about 20 angstroms (Å).

The second electrode **730** is disposed on the electron injection layer **779**. The thickness of the second electrode **730** may be about 30 angstroms (Å) to about 300 angstroms (Å). In the present exemplary embodiment, the second electrode **180** is deposited by sputtering.

FIG. 5 is a cross-sectional view of a partially modified organic light emitting element of FIG. 4.


FIG. 5 illustrates an example variation of the light emitting layer **715** of the organic light emitting element described with reference to FIG. 4. For example, in the present exemplary embodiment, the light emitting layer **715** may include a red light emitting layer (R), a green light emitting layer (G), and a blue light emitting layer (B), and an auxiliary layer (BIL) may be disposed below the blue light emitting layer (B) so that efficiency of the blue light emitting layer (B) may be improved.

The red light emitting layer (R) may be about 30 nm to about 50 nm thick, the green light emitting layer (G) may be about 10 nm to about 30 nm thick, and the blue light emitting

13

layer (B) may be about 10 nm to about 30 nm thick. The auxiliary layer (BIL) disposed below the blue light emitting layer (B) may be equal to or less than about 20 nm thick (e.g., the auxiliary layer (BIL) may have a thickness of greater than 0 nm to about 20 nm). The auxiliary layer (BIL) may improve the efficiency of the blue light emitting layer (B) by adjusting hole charge balance. The auxiliary layer (BIL) may include a compound represented by Chemical Formula 1.


Chemical Formula 1



In Chemical Formula 1, A1, A2, and A3 are each independently selected from an alkyl group, an aryl group, carbazole, dibenzothiophene, dibenzofuran (DBF), and biphenyl, and a, b, and c are each positive numbers of zero to four.

As an example of the compounds represented by Chemical Formula 1, the following Chemical Formulas 1-1, 1-2, 1-3, 1-4, 1-5, and 1-6 may be included.


Chemical Formula 1-1




14

-continued


Chemical Formula 1-2



Chemical Formula 1-3




Chemical Formula 1-4




15

-continued


Chemical Formula 1-5



Chemical Formula 1-6



In an exemplary embodiment, the auxiliary layer (BIL) may include a compound represented by Chemical Formula 2.




16

Chemical Formula 2


In Chemical Formula 2, a may be 0 to 3, b and c may respectively be 0 to 3, X may be selected from O, N, or S, and each X may be the same as the other or different.

As an example of the compound represented by Chemical Formula 2, Chemical Formulas 2-1, 2-2, 2-3, 2-4, 2-5, and 2-6 may be included.


Chemical Formula 2-1



Chemical Formula 2-2




Chemical Formula 2-3



17


-continued

Chemical Formula 2-4

**18**


-continued

Chemical Formula 2-6




In an exemplary embodiment, the auxiliary layer (BIL) may include a compound represented by Chemical Formula 3.

Chemical Formula 3




In Chemical Formula 3, A1 may be an alkyl group, an aryl group, carbazole, dibenzothiophene, or dibenzofuran (DBF), L1 and L2 may be




(wherein n is 0 to 3), and DBF coupled or connected to L1 and L2 may be replaced by carbazole or dibenzothiophene.

Hereinafter, a composition method (e.g., synthesis or manufacture) of the auxiliary layer (BIL) according to an exemplary embodiment of the present disclosure will be described. For example, the composition method of the following Chemical formula 1-1 will be described.

Chemical Formula 2-5





COMPOSITION EXAMPLE

Under an argon atmosphere, 6.3 g of 4-dibenzofuran boronic acid, 4.8 mg of 4,4',4''-tribromotriphenylamine, 104 mg of tetrakis(triphenylphosphine)palladium ($\text{Pd}(\text{PPh}_3)_4$), 48 ml of a sodium carbonate (Na_2CO_3) solution (2 M), and 48 ml of toluene were put in a 300 ml 3-neck flask, and reacted at 80° C. for eight hours. The reaction solution was extracted with toluene/water, and dried with anhydrous sodium sulfate. The resultant was condensed under low pressure, and 3.9 g of a yellowish-white powder was obtained through column purification of the obtained crude product.

In FIG. 5, a red resonant auxiliary layer (R') may be disposed below the red light emitting layer (R), and a green resonant auxiliary layer (G') may be disposed below the green light emitting layer (G). The red resonant auxiliary layer (R') and the green resonant auxiliary layer (G') are layers that can adjust a resonant distance for the respective color. In some embodiments, a resonant auxiliary layer may not be separately formed below the blue light emitting layer (B) corresponding to the red light emitting layer (R) or the green light emitting layer (G) and below the auxiliary layer (BIL) so that the resonant auxiliary layer is interposed between the blue light emitting layer (B) and the auxiliary layer (BIL) and the hole transport layer 714.

The features and contents described with respect to FIGS. 1 to 4, as well as the above-described difference, may be applied to an exemplary embodiment of FIG. 5.

FIG. 6 is a cross-sectional view of an exemplary embodiment in which the air layer of FIG. 3 is replaced with a filler.

As shown in FIG. 6, an organic light emitting diode display 103 according to an exemplary embodiment of the present disclosure includes a filler 400 disposed in a space between the organic light emitting element 70 and the encapsulation substrate 210. The filler 400 fills the inside of the organic light emitting diode display 103 instead of the air layer 300 described with respect to FIG. 3.

The filler 400 is made of an organic material, e.g., a polymer having a refractive index of about 1.7 or less. For example, the filler 400 has a refractive index that is lower than the high refraction film 520 of the capping layer 500.

Through such a configuration, the organic light emitting diode display 103 according to the exemplary embodiment of the present disclosure can improve light efficiency through the capping layer 500.

Further, since the filler 400 fills an empty space of the organic light emitting diode display 103, mechanical strength and durability of the organic light emitting diode display 103 may be improved.

As used herein, expressions such as “at least one selected from,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. Further, the use of “may” when describing embodiments of the present invention refers to “one or more embodiments of the present disclosure.”

It will be understood that, although the terms “first,” “second,” “third,” etc., may be used herein to describe various elements, components, regions, layers and/or sections (e.g., a first electrode and a second electrode), these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section described below could be termed a second element, component, region, layer or section, without departing from the spirit and scope of the present invention.

It will be understood that when an element or layer is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it can be directly on, connected to, or coupled to the other element or layer, or one or more intervening elements or layers may be present. In addition, it will also be understood that when an element or layer is referred to as being “between” two elements or layers, it can be the only element or layer between the two elements or layers, or one or more intervening elements or layers may also be present.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the present invention. As used herein, the singular forms “a” and “an” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises,” “comprising,” “includes,” and “including,” when used in this specification, specify the presence of the stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

As used herein, the term “substantially,” “about,” and similar terms are used as terms of approximation and not as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art. As used herein, the terms “use,” “using,” and “used” may be considered synonymous with the terms “utilize,” “utilizing,” and “utilized,” respectively. Also, the term “exemplary” is intended to refer to an example or illustration.

21

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which the present invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and/or the present specification, and should not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

While this disclosure has been described in connection with what is presently considered to be practical exemplary embodiments, it is to be understood that the disclosure is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

Description of some of the symbols

70	organic light emitting element	210	encapsulation substrate
500	capping layer	510	low refraction layer
520	high refraction layer	BIL	auxiliary layer

What is claimed is:

1. An organic light emitting diode display comprising:
a substrate;
an organic light emitting element on the substrate; and
a capping layer on the organic light emitting element and comprising a high refraction layer comprising an inorganic material having a refractive index which is equal to or greater than about 1.7 and equal to or less than about 6.0,

wherein the inorganic material comprises at least one selected from CuI, thallium iodide (TlI), AgI, CdI₂, HgI₂, SnI₂, PbI₂, BiI₃, ZnI₂, MnI₂, FeI₂, CoI₂, NiI₂, aluminium iodide (AlI₃), thorium (IV) iodide (ThI₄), uranium triiodide (UI₃), MgS, MgSe, MgTe, CaS, CaSe, CaTe, SrS, SrSe, SrTe, BaS, BaSe, BaTe, SnS, CdS, CaS, ZnTe, CdTe, SnSe, CdSe, CuO, Cu₂O, Ag₂O, CdO, CoO, Pr₂O₃, Bi₂O₃, Fe₂O₃, AlAs, GaAs, InAs, GaP, InP, AlP, AlSb, GaSb, and InSb,

wherein the capping layer further comprises a low refraction layer formed of an inorganic material having a refractive index which is equal to or greater than about 1.0 and equal to or less than about 1.7, and
wherein the capping layer comprises a plurality of refraction layers each comprising the low refraction layer and the high refraction layer.

2. The organic light emitting diode display of claim 1, wherein:

the low refraction layer is between the high refraction layer and the organic light emitting element.

3. The organic light emitting diode display of claim 2, wherein:

the low refraction layer comprises an inorganic material comprising a halogen compound.

4. The organic light emitting diode display of claim 3, wherein:

the low refraction layer comprises at least one selected from MgF₂, LiF, AlF₃, NaF, KF, RbF, CaF₂, SrF₂, and YbF₂.

5. The organic light emitting diode display of claim 1, further comprising:

an encapsulation substrate on and sealing the substrate to cover the organic light emitting element.

22

6. The organic light emitting diode display of claim 5, wherein:

the encapsulation substrate and the organic light emitting element are spaced apart from each other.

7. The organic light emitting diode display of claim 1, wherein:

the organic light emitting element comprises:

a first electrode and a second electrode facing each other, and

a light emitting layer between the first electrode and the second electrode,

wherein the capping layer is directly on the second electrode.

8. The organic light emitting diode display of claim 7, wherein:

the first electrode comprises a reflective layer.

9. The organic light emitting diode display of claim 8, wherein:

the light emitting layer comprises a red light emitting layer, a green light emitting layer, a blue light emitting layer, and


an auxiliary layer below the blue light emitting layer.

10. The organic light emitting diode display of claim 9, further comprising:

a red resonant auxiliary layer below the red light emitting layer and a green resonant auxiliary layer below the green light emitting layer.

11. The organic light emitting diode display of claim 9, wherein:

the auxiliary layer comprises a compound represented by Chemical Formula 1:



wherein, in Chemical Formula 1, A1, A2, and A3 are each independently selected from an alkyl group, an aryl group, carbazole, dibenzothiophene, dibenzofuran (DBF), and biphenyl, and a, b, and c are each positive numbers of zero to four.


12. The organic light emitting diode display of claim 9, wherein:

the auxiliary layer comprises a compound represented by Chemical Formula 2:

23

24

Chemical Formula 2



wherein, in Chemical Formula 2, a may be 0 to 3, b and c may be 0 to 3, X may be selected from O, N, or S, and each X may be the same as the other or different.

* * * * *

专利名称(译)	有机发光二极管显示器		
公开(公告)号	US10403851	公开(公告)日	2019-09-03
申请号	US14/985285	申请日	2015-12-30
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM DONG CHAN KIM WON JONG KIM EUNG DO LEE JI HYE IM DA HEA YIM SANG HOON CHO YOON HYEUNG HAN WON SUK		
发明人	KIM, DONG CHAN KIM, WON JONG KIM, EUNG DO LEE, JI HYE IM, DA HEA YIM, SANG HOON CHO, YOON HYEUNG HAN, WON SUK		
IPC分类号	H01L51/52 H01L27/32		
CPC分类号	H01L51/5253 H01L51/5275 H01L27/3244		
优先权	1020150063363 2015-05-06 KR		
其他公开文献	US20160329521A1		
外部链接	Espacenet		

摘要(译)

一种有机发光二极管显示器，包括：基板；基板上的有机发光元件；所述有机发光元件上的覆盖层包括由折射率等于或大于约1.7且等于或小于约6.0的无机材料形成的高折射层，其中所述无机材料至少包括选自CuI，碘化铊（TlI），AgI，CdI₂，HgI₂，SnI₂，PbI₂，BiI₃，ZnI₂，MnI中的一种. sub.2，FeI.sub.2，CoI.sub.2，NiI.sub.2，碘化铝（AlI₃），碘化钍（ThI₄），三碘化铀（UI₃），MgS，MgSe，MgTe，CaS，CaSe，CaTe，SrS，SrSe，SrTe，BaS，BaSe，BaTe，SnS，PbS，CdS，CaS，ZnS，ZnTe，PbTe，CdTe，SnSe，PbSe，CdSe，CuO，Cu₂O，WO₃，MoO₃，SnO₂，Nb₂O₅，Ag₂O，CdO，CoO，Pr. sub.sub.3，Bi.sub.2O.sub.3，Fe.sub.2O.sub.3，AlAs，GaAs，InAs，GaP，InP，AlP，AlSb，GaSb和InSb。

Chemical Formula 1

