



US009065068B2

(12) **United States Patent**
Kang et al.

(10) **Patent No.:** **US 9,065,068 B2**
(45) **Date of Patent:** **Jun. 23, 2015**

(54) **ORGANIC LIGHT EMITTING DISPLAY
DEVICE**

(2013.01); **H01L 51/5056** (2013.01); **H01L
51/5072** (2013.01); **H01L 51/56** (2013.01)

(71) Applicant: **LG Display Co., Ltd.**, Seoul (KR)

(58) **Field of Classification Search**

CPC . H01L 27/32; H01L 27/3202; H01L 27/3204;
H01L 27/3209; H01L 27/3225; H01L 51/50;
H01L 51/5287; H01L 2227/32; H01L
2227/326; H01L 2251/5323; H01L 2251/566;
H01L 2924/12044

See application file for complete search history.

(72) Inventors: **Hye-Seung Kang**, Gimpo-si (KR);
Tae-Il Kum, Paju-si (KR); **Young-Kwan
Jung**, Daegu (KR); **Hyung-June Kim**,
Paju-si (KR); **Jung-Soo Park**, Seoul
(KR)

(73) Assignee: **LG DISPLAY CO., LTD.**, Seoul (KR)

(56)

References Cited

U.S. PATENT DOCUMENTS

2013/0240847 A1 * 9/2013 Zakhidov et al. 257/40

* cited by examiner

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

Primary Examiner — Hoai V Pham

(21) Appl. No.: **14/496,287**

(22) Filed: **Sep. 25, 2014**

(74) *Attorney, Agent, or Firm* — McKenna Long & Aldridge
LLP

(65) **Prior Publication Data**

US 2015/0090984 A1 Apr. 2, 2015

(57)

ABSTRACT

Disclosed is an organic light emitting display (OLED) device
that may include first and second electrodes facing each other
on a substrate, at least two light emitting units between the
first and second electrodes, and a charge generation layer
between the at least two light emitting units, the charge ge-
neration layer including an N-type charge generation layer and
a P-type charge generation layer, wherein the N-type charge
generation layer includes at least two hosts and a dopant, and
wherein the at least two hosts have different lowest unoccu-
pied molecular orbital (LUMO) energy levels.

(30) **Foreign Application Priority Data**

Oct. 2, 2013 (KR) 10-2013-0117760

(51) **Int. Cl.**

H01L 51/52 (2006.01)

H01L 51/50 (2006.01)

H01L 27/32 (2006.01)

H01L 51/56 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/52** (2013.01); **H01L 27/32**

20 Claims, 12 Drawing Sheets




FIG. 1




FIG. 2A




FIG. 2B




FIG. 2c




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9A




FIG. 9B




FIG. 10A




FIG. 10B





FIG. 11



ORGANIC LIGHT EMITTING DISPLAY DEVICE

This application claims the benefit of Korean Patent Application No. 10-2013-0117760, filed on Oct. 2, 2013, which is hereby incorporated by reference as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an organic light emitting display (OLED) device with low drive voltage and high luminous efficiency, and a method for manufacturing the same.

2. Discussion of the Related Art

In line with recent developments in information era, there has been rapid advancement in the display field. To meet such development, various flat panel display devices with excellent performance, such as ultra-thin thickness, lightweight and low power consumption, have been developed.

Examples of flat panel display devices include, without limitation, liquid crystal display (LCD) devices, plasma display panel (PDP) devices, field emission display (FED) devices, and organic light emitting display (OLED) devices.

In particular, OLED devices, which are a self-emissive device, have faster response time, higher luminous efficiency, higher luminance and wider viewing angle compared with other flat panel display devices. OLED devices typically include an anode, a hole injection layer, a hole transport layer, an emission layer, an electron transport layer, an electron injection layer, and a cathode.

OLED devices typically have a single light emitting unit structure including a hole injection layer, a hole transport layer, an emission layer, an electron transport layer, and an electron injection layer disposed between first and second electrodes. In recent years, however, OLED devices having a multi-light emitting unit structure including a plurality of light emitting units disposed between first and second electrodes have been developed.

In the conventional multi-light emitting unit structure, a plurality of organic layers are provided between the first and second electrodes, which leads to an increased drive voltage. In addition, OLED device having the conventional multi-light emitting unit structure may not provide luminous efficiency proportional to the number of the light emitting layers as compared with OLED devices having a single light emitting unit structure.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to an organic light emitting display (OLED) device and method for manufacturing the same that substantially obviates one or more problems due to limitations and disadvantages of the related art.

An advantage of the present invention is to provide an OLED device with low drive voltage and high luminous efficiency, and a method for manufacturing the same.

Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. These and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, an organic light emitting display (OLED)

device may, for example, include first and second electrodes facing each other on a substrate, at least two light emitting units between the first and second electrodes, and a charge generation layer between the at least two light emitting units, the charge generation layer including an N-type charge generation layer and a P-type charge generation layer, wherein the N-type charge generation layer includes at least two hosts and a dopant, and wherein the at least two hosts have different lowest unoccupied molecular orbital (LUMO) energy levels.

In another aspect of the present invention, an organic light emitting display (OLED) device may, for example, include first and second electrodes facing each other on a substrate, at least two light emitting units between the first and second electrodes, and a charge generation layer between the light emitting units, the charge generation layer including an N-type charge generation layer and a P-type charge generation layer, wherein one of the at least two light emitting units includes a hole transport layer on the first electrode, an emission layer on the hole transport layer, and an electron transport layer on the emission layer, the N-type charge generation layer including at least two hosts having different LUMO energy levels and a dopant, and the electron transport layer including any one of the at least two hosts in the N-type charge generation layer.

The N-type charge generation layer may have a multi-layer or single-layer structure including first and second hosts and a dopant.

A difference between the LUMO energy level of the first host and the LUMO energy level of the second host may be 0.1 eV or more, and a difference between a highest occupied molecular orbital (HOMO) energy level of the first host and a HOMO energy level of the second host may be 0.1 eV or more.

A ratio of the second host to the first host in the N-type charge generation layer may be 5 to 95% and a doping ratio of the dopant to the sum of the first and second hosts in the N-type charge generation layer may be 1 to 8%.

The dopant may be formed of an alkali metal or an alkali earth metal and have a work function of -2.5 eV to -3.2 eV.

The N-type charge generation layer may have a multi-layer structure including a first N-type charge generation layer formed of the first host and the dopant, a second N-type charge generation layer formed of the second host and the dopant, and a third N-type charge generation layer formed of the first and second hosts and the dopant.

The first to third N-type charge generation layers may each have a thickness of 10 to 500 Å.

The N-type charge generation layer may have a multi-layer structure including a first N-type charge generation layer formed of the first host and the dopant and a second N-type charge generation layer formed of the second host and the dopant.

The first and second N-type charge generation layers may each have a thickness of 10 to 500 Å.

The electron transport layer may have a thickness of 100 to 500 Å.

In yet another aspect of the present invention, a method for manufacturing an organic light emitting display (OLED) device, the method may, for example, including forming a first electrode on a substrate; forming a first light emitting unit on the first electrode; forming a charge generation layer on the first light emitting unit, the charge generation layer including a first host, a second host and a dopant; forming a second light emitting unit on the charge generation layer; and forming a second electrode on the second light emitting unit, wherein LUMO energy levels of the first host and the second host are

different by about 0.1 eV or more, and wherein HOMO energy levels of the first host and the second host are different by about 0.1 eV or more.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention. In the drawings:

FIG. 1 is a perspective view illustrating OLED device according to the first embodiment of the present invention;

FIGS. 2A to 2C are sectional views illustrating various embodiments of an N-type charge generation layer shown in FIG. 1;

FIG. 3 is a view illustrating an electron movement channel between a P-type charge generation layer and an electron transport layer shown in FIGS. 2A to 2C;

FIGS. 4A and 4B are graphs showing characteristics of a second light emitting unit generating a yellow-green light illustrated in FIG. 1 and a comparative example;

FIGS. 5A and 5B are graphs showing characteristics of a first light emitting unit generating a blue light illustrated in FIG. 1 and a comparative example;

FIGS. 6A to 6C are graphs showing characteristics of a white organic light emitting device according to the first embodiment of the present invention and a comparative example;

FIG. 7 is a perspective view illustrating an OLED device according to a second embodiment of the present invention;

FIGS. 8A to 8C are sectional views illustrating various embodiments of an N-type charge generation layer shown in FIG. 7;

FIGS. 9A and 9B are views illustrating an electron movement channel between a P-type charge generation layer and an electron transport layer shown in FIGS. 8A to 8C;

FIGS. 10A and 10B are graphs showing characteristics of an OLED device illustrated in FIG. 7 and a comparative example; and

FIG. 11 is a sectional view illustrating an OLED device having a color filter according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, examples of which are illustrated in the accompanying drawings. The same reference numbers may be used throughout the drawings to refer to the same or like parts.

FIG. 1 is a perspective view illustrating an organic light emitting display (OLED) device according to the first embodiment of the present invention.

Referring to FIG. 1, the OLED device includes first and second electrodes **102** and **104** facing each other on a substrate **101**, first and second light emitting units **110** and **120** formed between the first and second electrodes **102** and **104**, and a charge generation layer **130** provided between the first and second light emitting units **110** and **120**.

At least one of the first and second electrodes **102** and **104** is formed of a semi-transparent electrode. In a case in which the first electrode **102** is a semi-transparent electrode and the second electrode **104** is a reflective electrode, the OLED device is a rear light emitting structure in which light is emitted downward. In a case in which the second electrode **104** is a semi-transparent electrode and the first electrode **102** is a reflective electrode, the OLED device is a front light emitting structure in which light is emitted upward. Alternatively, both the first and second electrodes **102** and **104** may be formed of a transparent electrode such that the OLED device is a double-side light emitting structure in which light is emitted upward and downward.

The semi-transparent electrode is formed of a transparent conductive material, such as indium tin oxide (ITO) or indium zinc oxide (IZO), and an opaque conductive material, such as aluminum (Al), gold (Au), molybdenum (MO), chrome (Cr), copper (Cu), or LiF. The reflective electrode is formed of a reflective metal material, such as aluminum (Al), gold (Au), molybdenum (MO), chrome (Cr), copper (Cu), or LiF, or has a multi-layered structure using the same.

This embodiment will now be described with a case where the first electrode **102** serving as an anode is formed of a semi-transparent electrode and the second electrode **104** serving as a cathode is formed of a reflective electrode by way of example.

The first light emitting unit **110** is formed between the first electrode **102** and an N-type charge generation layer **132**. The first light emitting unit **110** includes a hole injection layer (HIL) **112**, a first hole transport layer (HTL1) **114**, a first emission layer (EML1) **116**, and a first electron transport layer (ETL1) **118** sequentially formed on the first electrode **102**. The first hole transport layer **114** supplies holes from the first electrode **102** to the first emission layer **116**. The first electron transport layer **118** supplies electrons from the N-type charge generation layer **132** to the first emission layer **116**. In the first emission layer **116**, the holes supplied through the first hole transport layer **114** and the electrons supplied through the first electron transport layer **118** are re-coupled to generate light.

The second light emitting unit **120** is formed between the second electrode **104** and a P-type charge generation layer **134**. The second light emitting unit **120** includes a second hole transport layer (HTL2) **124**, a second emission layer (EML2) **126**, a second electron transport layer (ETL2) **128**, and an electron injection layer (EIL) **122** sequentially formed on the P-type charge generation layer **134**. The second hole transport layer **124** supplies holes from the P-type charge generation layer **134** to the second emission layer **126**. The second electron transport layer **128** supplies electrons from the second electrode **104** injected through the electron injection layer **122** to the second emission layer **126**. In the second emission layer **126**, the holes supplied through the second hole transport layer **124** and the electrons supplied through the second electron transport layer **128** are re-coupled to generate light.

The first emission layer **116**, which is an emission layer including a fluorescent or phosphorescent blue dopant and a host, emits a blue light and the second emission layer **126**, which is an emission layer including a fluorescent or phosphorescent yellow-green dopant and a host, emits a yellow-green light to generate a white light. Alternatively, other fluorescent or phosphorescent dopants may be used to generate a white light.

The N-type charge generation layer **132** and the P-type charge generation layer **134** are sequentially stacked to constitute the charge generation layer **130**.

The P-type charge generation layer **134** is formed between the N-type charge generation layer **132** and the second hole transport layer **124** to generate holes and electrons. The holes generated by the P-type charge generation layer **134** are injected into the second hole transport layer **124** of the second light emitting unit **120**. The electrons generated by the P-type charge generation layer **134** are injected into the N-type charge generation layer **132**.

The N-type charge generation layer **132** is formed between the P-type charge generation layer **134** and the first electron transport layer **118** to inject and transport the electrons injected from the P-type charge generation layer **134** into and to the first electron transport layer **118**.

The N-type charge generation layer **132** includes at least two hosts formed of different materials and a dopant. In this embodiment, the N-type charge generation layer **132** includes first and second hosts H1 and H2 formed of different materials and a dopant D by way of example.

The N-type charge generation layer **132** may have a multi-layer structure as illustrated in FIGS. 2A and 2B or a single-layer structure as illustrated in FIG. 2C.

The N-type charge generation layer **132** illustrated in FIG. 2A includes first and second N-type charge generation layers **132a** and **132b**. The first N-type charge generation layer **132a** is formed by mixing the first host H1 and the dopant D on the first electron transport layer **118**. The second N-type charge generation layer **132b** is formed by mixing the second host H2 and the dopant D on the first N-type charge generation layer **132a**. Thicknesses D1 and D2 of the first and second N-type charge generation layers **132a** and **132b** may be in a range of about 10 Å to about 500 Å.

The N-type charge generation layer **132** illustrated in FIG. 2B includes first to third second N-type charge generation layers **132a**, **132b**, and **132c**. The first N-type charge generation layer **132a** is formed by mixing the first host H1 and the dopant D on the first electron transport layer **118**. The second N-type charge generation layer **132b** is formed by mixing the second host H2 and the dopant D on the third N-type charge generation layer **132c**. The third N-type charge generation layer **132c** is formed by mixing the first and second hosts H1 and H2 and the dopant D between the first and second N-type charge generation layers **132a** and **132b**. In the N-type charge generation layer **132**, a thickness D1 of a region in which the first host H1 is formed and a thickness D2 of a region in which the second host H2 is formed may be in a range of about 10 Å to about 500 Å. A thickness D3 of a region in which the first host H1 and the second host H2 are formed in a mixed state, i.e. the third N-type charge generation layer **132c**, may be in a range of about 10 Å to about 500 Å.

The N-type charge generation layer **132** illustrated in FIG. 2C is formed by mixing the first and second hosts H1 and H2 and the dopant D. That is, the N-type charge generation layer **132** has a single-layer structure. The N-type charge generation layer **132** may have a thickness D in a range of about 10 Å to about 500 Å.

In the N-type charge generation layer **132** illustrated in FIGS. 2A to 2C, a ratio of the second host H2 to the first host H1 may be in a range of about 5% to about 95%. In the N-type charge generation layer **132**, a doping ratio of the dopant D to the sum of the first and second hosts H1 and H2 may be in a range of about 1% to about 8%. The dopant D may be formed of an alkali metal or an alkali earth metal, such as Ca, Li, Mg, or Yb, and may have a work function of about -2.5 eV to about -3.2 eV.

As illustrated in FIG. 3, the first and second hosts H1 and H2 have different lowest unoccupied molecular orbital (LUMO) energy levels and different highest occupied

molecular orbital (HOMO) energy levels. For example, the difference between the LUMO energy level (LUMO1) of the first host H1 and the LUMO energy level (LUMO2) of the second host H2 may be about 0.1 eV or more and the difference between the HOMO energy level (HOMO1) of the first host H1 and the HOMO energy level (HOMO2) of the second host H2 may be about 0.1 eV or more.

Because the N-type charge generation layer **132** has at least two hosts as described above, the charge generation layer may have plural energy levels. In particular, at least two hosts and a dopant constituting the N-type charge generation layer **132** are co-deposited to generate a plurality of energy levels. These energy levels are used as movement channels through which electrons generated by the P-type charge generation layer **134** are injected as illustrated in FIG. 3.

In an OLED device according to an embodiment of the present invention, electrons may thus move to the first emission layer **116** faster as compared with the conventional art, an energy barrier between the P-type charge generation layer **134** and the N-type charge generation layer **132** may be reduced or minimized, and a tunneling effect may be maximized. As a result, drive voltage may be lowered. In addition, in this embodiment, an amount of electrons is increased with the increase of the movement channels through which the electrons may be injected. Also, the balance between holes and electrons may be uniform, whereby luminous efficiency may be improved and an occurrence of a roll-off phenomenon may be restrained. In particular, electrons are injected into the first light emitting unit **110**, which is, for example, a blue light emitting unit located under the N-type charge generation layer **132**, through the N-type charge generation layer **132**. As a result, luminous efficiency of the blue light emitted from the first light emitting unit **110** may be improved, thereby increasing luminous efficiency of the white light and reducing power consumption of the OLED device.

FIGS. 4A to 6C and Tables 1 to 3 show characteristics of a white organic light emitting device according to the first embodiment of the present invention. In FIGS. 4A to 6C and Tables 1 to 3, the comparative example includes an N-type charge generation layer formed of Bphen and the example includes an N-type charge generation layer **132** in which one of first and second hosts H1 and H2 is formed of a pyrene derivative having a phenanthroline substituent and the other of the first and second hosts H1 and H2 is formed of Bphen. In this embodiment, materials of the first and second hosts H1 and H2 are merely illustrative for explanation purposes, and the present invention is not limited thereto.

Table 1 shows characteristics of a second light emitting unit generating a yellow-green light of the white organic light emitting device according to the first embodiment of the present invention and a comparative example.

TABLE 1

N-type charge generation layer	10 mA/cm ²		
	Drive voltage (V)	Luminous efficiency (cd/A)	External quantum efficiency EQE (%)
Comparative example	3.7	75.7	22.3
Example	3.5	76.2	22.5

As shown in Table 1 and FIG. 4A, drive voltage to obtain a current density of 10 mA/cm² in the example is 0.2 V lower than that in the comparative example. In addition, luminous efficiency in the example is 0.5 cd/A higher than that in the comparative example as shown in Table 1, and external quan-

tum efficiency in the example is 0.2% higher than that in the comparative example as shown in Table 1 and FIG. 4B. Furthermore, in the example, the peak intensity is at a wavelength of 530 to 570 nm, in which a yellow-green (YG) is emitted, which is similar to that in the comparative example.

Table 2 shows characteristics of a first light emitting unit generating a blue light of the white organic light emitting device according to the first embodiment of the present invention and a comparative example.

TABLE 2

N-type charge generation layer	10 mA/cm ²		
	Drive voltage (V)	Luminous efficiency (cd/A)	External quantum efficiency EQE (%)
Comparative example	4.0	8.1	9.8
Example	4.0	8.3	10.0

As shown in Table 2, drive voltage to obtain a current density of 10 mA/cm² in the example is equal to that in the comparative example. In addition, luminous efficiency in the example is 0.2 cd/A higher than that in the comparative example as shown in Table 2, and external quantum efficiency in the example is 0.2% higher than that in the comparative example as shown in Table 2 and FIG. 5A. Furthermore, in the example, the peak intensity is at a wavelength of 450 to 475 nm, in which a blue (B) light is emitted, which is higher than that in the comparative example, as shown in FIG. 5B.

Table 3 shows characteristics of the white organic light emitting device according to the first embodiment of the present invention and a comparative example.

TABLE 3

N-type charge generation layer	10 mA/cm ²		
	Drive voltage (V)	Luminous efficiency (cd/A)	External quantum efficiency EQE (%)
Comparative example	7.7	77.0	32.6
Example	7.5	79.3	32.9

As shown in Table 3 and FIG. 6A, drive voltage to obtain a current density of 10 mA/cm² in the example is 0.2V lower than that in the comparative example. In addition, luminous efficiency in the example is 2.3 cd/A higher than that in the comparative example as shown in Table 3 and FIG. 6B, and external quantum efficiency in the example is 0.3% higher than that in the comparative example as shown in Table 3. Furthermore, in the example, the peak intensities are at a wavelength of 450 to 475 nm, in which a blue (B) light is emitted, and at a wavelength of 530 to 570 nm, in which a yellow-green (YG) light is emitted, which is higher than that in the comparative example, as shown in FIG. 6C.

FIG. 7 is a perspective view illustrating an OLED device according to a second embodiment of the present invention. The OLED device illustrated in FIG. 7 is substantially identical to what is shown in FIG. 1, except that an N-type charge generation layer and a first electron transport layer include the same host. Thus, a detailed description of the identical elements will be omitted.

Referring to FIG. 7, a first electron transport layer **118** is formed of the same material as any one of a plurality of hosts included in an N-type charge generation layer **132**. As a result, an energy barrier between the first electron transport

layer **118** and the N-type charge generation layer **132** may be reduced or minimized, and thus electrons may be easily injected into the first electron transport layer **118**. The first electron transport layer **118** may have a thickness D_e in a range of about 100 Å to about 500 Å.

The N-type charge generation layer **132** includes at least two hosts formed of different materials and a dopant. In this embodiment, the N-type charge generation layer **132** includes first and second hosts **H1** and **H2** formed of different materials and a dopant **D** by way of example.

The N-type charge generation layer **132** may have a multi-layer structure as illustrated in FIGS. 8A and 8B or a single-layer structure as shown in FIG. 8C.

The N-type charge generation layer **132** illustrated in FIG. 8A includes first and second N-type charge generation layers **132a** and **132b**. The first N-type charge generation layer **132a** is formed by mixing the first host **H1** and the dopant **D** on the first electron transport layer **118** formed of the first host **H1**. The second N-type charge generation layer **132b** is formed by mixing the second host **H2** and the dopant **D** on the first N-type charge generation layer **132a**. Thicknesses **D1** and **D2** of the first and second N-type charge generation layers **132a** and **132b** may be in a range of about 10 Å to about 500 Å.

The N-type charge generation layer **132** illustrated in FIG. 8B includes first to third second N-type charge generation layers **132a**, **132b**, and **132c**. The first N-type charge generation layer **132a** is formed by mixing the first host **H1** and the dopant **D** on the first electron transport layer **118** formed of the first host **H1**. The second N-type charge generation layer **132b** is formed by mixing the second host **H2** and the dopant **D** on the third N-type charge generation layer **132c**. The third N-type charge generation layer **132c** is formed by mixing the first and second hosts **H1** and **H2** and the dopant **D** between the first and second N-type charge generation layers **132a** and **132b**. In the N-type charge generation layer **132**, a thickness **D1** of a region in which the first host **H1** is formed and a thickness **D2** of a region in which the second host **H2** is formed may be in a range of about 10 Å to about 500 Å. A thickness **D3** of a region in which the first host **H1** and the second host **H2** are formed in a mixed state, i.e. the third N-type charge generation layer **132c**, may be in a range of about 10 Å to about 500 Å.

The N-type charge generation layer **132** illustrated in FIG. 8C is formed by mixing the first and second hosts **H1** and **H2** and the dopant **D**. That is, the N-type charge generation layer **132** has a single-layer structure. A doping amount of the first host **H1** of the N-type charge generation layer **132** increases from the upper part to the lower part of the N-type charge generation layer **132**. A doping amount of the second host **H2** of the N-type charge generation layer **132** decreases from the upper part to the lower part of the N-type charge generation layer **132**. The N-type charge generation layer **132** may have a thickness **D** in a range of about 10 Å to 500 Å.

As described above, because the first host **H1** is adjacent to the first electron transport layer **118** in the N-type charge generation layer **132** as illustrated in FIGS. 8A to 8C, electrons may easily move to the first emission layer **116** with a lower energy barrier through the first electron transport layer **118**. In addition, because the second host **H2** is adjacent to the P-type charge generation layer **134** in the N-type charge generation layer **132** as illustrated in FIGS. 8A to 8C, electrons generated by the P-type charge generation layer **134** may be easily injected.

In the N-type charge generation layer **132** illustrated in FIGS. 8A to 8C, a ratio of the second host **H2** to the first host **H1** may be in a range of about 5% to about 95%. In the N-type charge generation layer **132**, a doping ratio of the dopant **D** to

the sum of the first and second hosts H1 and H2 may be in a range of about 1% to about 8%. The dopant D may be formed of an alkali metal or an alkali earth metal, such as Ca, Li, Mg, or Yb, and may have a work function of about -2.5 eV to about -3.2 eV.

As illustrated in FIGS. 9A and 9B, the first and second hosts H1 and H2 have different LUMO energy levels and different HOMO energy levels. For example, the difference between the LUMO energy level (LUMO1) of the first host H1 and the LUMO energy level (LUMO2) of the second host H2 may be about 0.1 eV or more and the difference between the HOMO energy level (HOMO1) of the first host H1 and the HOMO energy level (HOMO2) of the second host H2 may be about 0.1 eV or more.

Because the N-type charge generation layer 132 has at least two hosts as described above, the charge generation layer may have plural energy levels. In particular, at least two hosts and a dopant constituting the N-type charge generation layer 132 are co-deposited to generate a plurality of energy levels. These energy levels are used as movement channels through which electrons generated by the P-type charge generation layer 134 are injected as illustrated in FIGS. 9A and 9B.

In particular, because the first electron transport layer 118 includes the same material as one of the hosts included in the N-type charge generation layer 132 as illustrated in FIGS. 9A and 9B, an energy barrier between the N-type charge generation layer 132 and the electron transport layer 118 may be reduced or minimized such that electrons can be easily injected. As a result, a drive voltage of the OLED device according to an embodiment of the present invention can be lowered. In addition, because the LUMO energy level (LUMO2) of the second host H2 is lower than the LUMO energy level (LUMO1) of the first host H1, electrons may be easily injected from the P-type charge generation layer 134. As a result, the drive voltage can be further lowered, thereby improving luminous efficiency.

FIGS. 10A and 10B, and Table 4, show characteristics of a white organic light emitting device according to the second embodiment of the present invention illustrated in FIG. 7.

In FIGS. 10A and 10B, and Table 4, the comparative example includes a first electron transport layer formed of Alq3 and an N-type charge generation layer formed of Bphen, example 1 includes an N-type charge generation layer 132 having a multi-layer structure as illustrated in FIGS. 8A and 8B and a first electron transport layer 118 formed of the same material as any one of first and second hosts H1 and H2 included in the N-type charge generation layer 132, and example 2 includes an N-type charge generation layer 132 having a single-layer structure as illustrated in FIG. 8C and a first electron transport layer 118 formed of the same material as any one of the hosts included in the N-type charge generation layer 132. In the N-type charge generation layer 132 of examples 1 and 2, one of the first and second hosts H1 and H2 is formed of a pyrene derivative having a phenanthroline substituent and the other of the first and second hosts H1 and H2 is formed of Bphen. In this embodiment, the materials of the first and second hosts H1 and H2 are merely illustrative for understanding of the present invention and, therefore, the present invention is not limited thereto.

Table 4 shows characteristics of a white organic light emitting device according to the second embodiment of the present invention and a comparative example.

TABLE 4

N-type charge generation layer	10 mA/cm ²		
	Drive voltage (V)	Luminous efficiency (cd/A)	External quantum efficiency EQE (%)
Example 1	3.2	69.2	20.5
Example 2	3.2	71.2	21.0
Comparative example	3.4	70.4	20.8

As shown in Table 4 and FIG. 10A, drive voltage to obtain a current density of 10 mA/cm² in examples 1 and 2 is 0.2 V lower than that in the comparative example. In addition, luminous efficiency in example 2 is 0.8 cd/A higher than that in the comparative example as shown in Table 4 and FIG. 10B, and external quantum efficiency in example 2 is 0.2% higher than that in the comparative example as shown in Table 4.

FIG. 11 is a sectional view illustrating an OLED device having a color filter according to an embodiment of the present invention.

An OLED device according to embodiments of the present invention may be applied to a structure that has a drive thin film transistor connected to a first electrode and a plurality of red, green, and blue color filters 150R, 150G, and 150B, as illustrated in FIG. 11. That is, a white light generated through the charge generation layer and the first and second light emitting units 110 and 120 is converted to a red light while passing through a sub-pixel region having the red color filter 150R, a green light while passing through a sub-pixel region having the green color filter 150G, a blue light while passing through a sub-pixel region having the blue color filter 150B, and a white light while passing through a sub-pixel region having no color filter.

In the embodiments described above, a structure having two light emitting units has been described by way of example. However, the present invention is not limited thereto, and one of ordinary skill in the art would understand that three or more light emitting units may be provided in an OLED device according to the present invention.

As is apparent from the above description, an OLED device according to an embodiment of the present invention is configured such that the N-type charge generation layer includes at least two hosts and, therefore, a plurality of energy levels, which are movement channels through which electrons generated by the P-type charge generation layer may be injected, is provided. As a result, electrons may be more easily injected into the emission layer(s) compared with the conventional art, thereby lowering drive voltage. Furthermore, the balance between holes and electrons may be uniform, which may increase luminous efficiency. In addition, the first electron transport layer is formed of the same material as any one of the hosts included in the N-type charge generation layer. As a result, an energy barrier between the N-type charge generation layer and the electron transport layer may be reduced or minimized such that electrons are easily injected, and that the drive voltage may be thus lowered and luminous efficiency may be increased.

It will be apparent to those skilled in the art that various modifications and variation can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

11

What is claimed is:

1. An organic light emitting display (OLED) device comprising:

first and second electrodes facing each other on a substrate;
at least two light emitting units between the first and second electrodes; and

a charge generation layer between the at least two light emitting units, the charge generation layer including an N-type charge generation layer and a P-type charge generation layer,

wherein the N-type charge generation layer comprises at least two hosts and a dopant, and wherein the at least two hosts have different lowest unoccupied molecular orbital (LUMO) energy levels.

2. The OLED device according to claim 1, wherein the N-type charge generation layer has a multi-layer or single-layer structure comprising first and second hosts and the dopant.

3. The OLED device according to claim 2, wherein a difference between the LUMO energy level of the first host and the LUMO energy level of the second host is about 0.1 eV or more, and

a difference between a highest occupied molecular orbital (HOMO) energy level of the first host and a HOMO energy level of the second host is about 0.1 eV or more.

4. The OLED device according to claim 2, wherein a ratio of the second host to the first host in the N-type charge generation layer is about 5% to about 95% and a doping ratio of the dopant to the sum of the first and second hosts in the N-type charge generation layer is about 1% to about 8%.

5. The OLED device according to claim 2, wherein the dopant includes an alkali metal or an alkali earth metal and has a work function of about -2.5 eV to about -3.2 eV.

6. The OLED device according to claim 2, wherein the N-type charge generation layer has a multi-layer structure comprising:

a first N-type charge generation layer including the first host and the dopant;

a second N-type charge generation layer including the second host and the dopant; and

a third N-type charge generation layer including the first and second hosts and the dopant.

7. The OLED device according to claim 6, wherein the first to third N-type charge generation layers each has a thickness of about 10 Å to about 500 Å.

8. The OLED device according to claim 2, wherein the N-type charge generation layer has a multi-layer structure comprising:

a first N-type charge generation layer including the first host and the dopant; and

a second N-type charge generation layer including the second host and the dopant.

9. The OLED device according to claim 8, wherein the first and second N-type charge generation layers each has a thickness of about 10 Å to about 500 Å.

10. An organic light emitting display (OLED) device comprising:

first and second electrodes facing each other on a substrate;
at least two light emitting units formed between the first and second electrodes; and

a charge generation layer formed between the at least two light emitting units, the charge generation layer comprising an N-type charge generation layer and a P-type charge generation layer, wherein

one of the at least two light emitting units comprises:

a hole transport layer on the first electrode;

an emission layer on the hole transport layer; and

12

an electron transport layer on the emission layer,

the N-type charge generation layer on the electron transport layer, the N-type charge generation layer including at least two hosts having different LUMO energy levels and a dopant, and

the electron transport layer including any one of the at least two hosts in the N-type charge generation layer.

11. The OLED device according to claim 10, wherein the N-type charge generation layer has a multi-layer or single-layer structure comprising first and second hosts and a dopant.

12. The OLED device according to claim 11, wherein

a difference between the LUMO energy level of the first host and the LUMO energy level of the second host is about 0.1 eV or more, and

a difference between a HOMO energy level of the first host and a HOMO energy level of the second host is about 0.1 eV or more.

13. The OLED device according to claim 11, wherein a ratio of the second host to the first host in the N-type charge generation layer is about 5% to 95% and a doping ratio of the dopant to the sum of the first and second hosts in the N-type charge generation layer is about 1% to 8%.

14. The OLED device according to claim 11, wherein the dopant includes an alkali metal or an alkali earth metal and has a work function of about -2.5 eV to about -3.2 eV.

15. The OLED device according to claim 11, wherein the N-type charge generation layer has a multi-layer structure comprising:

a first N-type charge generation layer including the first host and the dopant;

a second N-type charge generation layer including the second host and the dopant; and

a third N-type charge generation layer including the first and second hosts and the dopant.

16. The OLED device according to claim 15, wherein the first to third N-type charge generation layers each has a thickness of about 10 Å to about 500 Å.

17. The OLED device according to claim 11, wherein the N-type charge generation layer has a multi-layer structure comprising:

a first N-type charge generation layer including the first host and the dopant; and

a second N-type charge generation layer including the second host and the dopant.

18. The OLED device according to claim 17, wherein the first and second N-type charge generation layers each has a thickness of about 10 Å to about 500 Å.

19. The OLED device according to claim 11, wherein the electron transport layer has a thickness of about 100 Å to about 500 Å.

20. A method for manufacturing an organic light emitting display (OLED) device, the method comprising:

forming a first electrode on a substrate;

forming a first light emitting unit on the first electrode;

forming a charge generation layer on the first light emitting unit, the charge generation layer including a first host, a second host and a dopant;

forming a second light emitting unit on the charge generation layer; and

forming a second electrode on the second light emitting unit,

wherein LUMO energy levels of the first host and the second host are different by about 0.1 eV or more, and wherein HOMO energy levels of the first host and the second host are different by about 0.1 eV or more.

* * * * *

专利名称(译)	有机发光显示装置		
公开(公告)号	US9065068	公开(公告)日	2015-06-23
申请号	US14/496287	申请日	2014-09-25
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	KANG HYE SEUNG KUM TAE IL JUNG YOUNG KWAN KIM HYUNG JUNE PARK JUNG SOO		
发明人	KANG, HYE-SEUNG KUM, TAE-IL JUNG, YOUNG-KWAN KIM, HYUNG-JUNE PARK, JUNG-SOO		
IPC分类号	H01L51/52 H01L51/56 H01L51/50 H01L27/32		
CPC分类号	H01L51/52 H01L27/32 H01L51/5056 H01L51/5072 H01L51/56 H01L51/5004 H01L51/5044 H01L51/5052 H01L51/5076 H01L51/5088 H01L51/5278 H01L2251/5384 H01L2251/552 H01L27/3209 H01L51/5024 H01L51/5048 H01M2/105		
优先权	1020130117760 2013-10-02 KR		
其他公开文献	US20150090984A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种有机发光显示 (OLED) 器件, 其可包括在基板上彼此面对的第一和第二电极, 在第一和第二电极之间的至少两个发光单元, 以及在至少两个发光器件之间的电荷产生层单元, 电荷产生层包括N型电荷产生层和P型电荷产生层, 其中N型电荷产生层包括至少两个主体和掺杂剂, 并且其中至少两个主体具有不同的最低值未占分子轨道 (LUMO) 能级。

