




US 20120326134A1

(19) **United States**(12) **Patent Application Publication**
KIM et al.(10) **Pub. No.: US 2012/0326134 A1**(43) **Pub. Date: Dec. 27, 2012**(54) **HETEROCYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DIODE AND
FLAT DISPLAY DEVICE INCLUDING THE
HETEROCYCLIC COMPOUND**(52) **U.S. CL. 257/40; 546/41; 544/212; 544/180;
544/281; 257/E51.024**(76) **Inventors:** **Young-Kook KIM**, Yongin-City (KR);
Seok-Hwan HWANG, Yongin-City
(KR); **Hye-Jin JUNG**, Yongin-City
(KR); **Jin-O LIM**, Yongin-City (KR);
Sang-Hyun HAN, Yongin-City (KR);
Yoon-Hyun KWAK, Yongin-City (KR);
Sun-Young LEE, Yongin-City (KR);
Hee-Joo KO, Yongin-City (KR);
Jong-Hyuk LEE, Yongin-City (KR);
Sung-Chul KIM, Yongin-City (KR)(57) **ABSTRACT**

A heterocyclic compound, an organic light-emitting diode, and a flat display device, the heterocyclic compound being represented by Formula 1, below:

<Formula 1>

(21) **Appl. No.: 13/311,770**(22) **Filed: Dec. 6, 2011**(30) **Foreign Application Priority Data**

Jun. 22, 2011 (KR) 10-2011-0060806



Publication Classification(51) **Int. Cl.**
H01L 51/54 (2006.01)
C07D 487/04 (2006.01)
C07D 471/04 (2006.01)

FIG. 1



HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DIODE AND FLAT DISPLAY DEVICE INCLUDING THE HETEROCYCLIC COMPOUND

CROSS-REFERENCE TO RELATED PATENT APPLICATION

[0001] This application claims the benefit of Korean Patent Application No. 10-2011-0060806, filed on Jun. 22, 2011, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

[0002] 1. Field

[0003] Embodiments relate to a heterocyclic compound, and an organic light-emitting diode and a flat display device including the heterocyclic compound, and more particularly, to a heterocyclic compound that is suitable for use as a light-emitting material or electron transporting material included in an organic light-emitting diode, an organic light-emitting diode including the heterocyclic compound, and a flat display device including the organic light-emitting diode. The organic light-emitting diode including an organic layer including the heterocyclic compound may have a low driving voltage, high luminescence efficiency, and long lifetime.

[0004] 2. Description of the Related Art

[0005] Organic light emitting diodes are self-emission devices that have a wide viewing angle, a high contrast ratio, a short response time, and excellent brightness, driving voltage, and response speed characteristics, thus enabling the generation of multi-color images.

[0006] In an organic light-emitting diode, an anode may be formed on a substrate, and a hole transport layer, an emission layer, an electron transport layer, and a cathode may be sequentially formed in this stated order on the anode. In this regard, the hole transport layer, the emission layer, and the electron transport layer may be organic films including organic compounds. When a voltage is applied between the anode and the cathode, holes injected from the anode pass the hole transport layer to the emission layer, and electrons injected from the cathode pass the electron transport layer to the emission layer. The holes and electrons, which are carriers, are recombined in the emission layer to generate excitons, which then change from an excited state to a ground state, thereby generating light.

[0007] An emission layer material of an organic light-emitting diode may include anthracene derivatives. An electron transport material may include Alq₃, TBPI, PBD, PF-6P, PyPySPyPy, etc. An organic light-emitting diode may use a 2 or 3 equivalent amount of a compound of phenyl anthracene. However, a device using the 2 or 3 equivalent amount of the compound of phenyl anthracene may have two or three anthracenes covalently linked. Thus, an energy gap may be narrow and color purity of blue light emission may be low. Also, the 2 or 3 equivalent amount of the compound of phenyl anthracene may be oxidized and thus, purification thereof may be difficult. Accordingly, organic light-emitting diodes using either an anthracene compound in which naphthalene is substituted at sites 1 and 9 of an anthracene group or a diphenylanthracene compound in which an aryl group is substituted at an m-site of a phenyl group may be used. However, such organic light-emitting diodes may have low luminescence efficiency. Also, an organic light-emitting device may


use a monoanthracene derivative substituted with a naphthalene. However, such an organic light-emitting diode may not be practical due to its low luminescence efficiency of about 1 cd/A. Also, an organic light-emitting diode may include a compound having the structure of phenyl anthracene. However, the compound may be substituted with an aryl group at an m-site thereof. Thus, the compound may have a luminescence efficiency as low as about 2 cd/A, although its heat resistance is high.

SUMMARY

[0008] The embodiments provide a heterocyclic compound having a novel structure, and an organic light-emitting diode and a flat display device including the heterocyclic compound, wherein the organic light-emitting diode and the flat display device have a low driving voltage, high luminescence efficiency, and long lifetime due to the inclusion of the heterocyclic compound.

[0009] According to an aspect of the present invention, there is provided a heterocyclic compound represented by Formula 1 below:

<Formula 1>



[0010] wherein A₁ is a substituted or unsubstituted fused pyridine cycle,

[0011] R₁ to R₉ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cyclo alkyl group, a substituted or unsubstituted C₃-C₃₀ cyclo alkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, a substituted or unsubstituted C₃-C₃₀ hetero aryl group, and a group represented by N(Q₁)(Q₂) wherein Q₁ and Q₂ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cyclo alkyl group, a substituted or unsubstituted C₃-C₃₀ cyclo alkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsub-

stituted C₆-C₃₀ arylthio group, or a substituted or unsubstituted C₃-C₃₀ hetero aryl group, and

[0012] L₁ and L₂ are each independently a substituted or unsubstituted C₆-C₃₀ arylene group, or a substituted or unsubstituted C₃-C₃₀ heteroarylene group, and a and b are each independently an integer of 0 to 3.

[0013] According to another aspect of the present invention, there is provided an organic light-emitting diode including: a first electrode; a second electrode facing the first electrode; and a first layer interposed between the first electrode and the second electrode, wherein the first layer includes the heterocyclic compound alone or in a mixed form with other materials.


[0014] According to another aspect of the present invention, there is provided a flat display device including: a transistor comprising a source, a drain, a gate, and an active layer; and the organic light-emitting diode, wherein the source or the drain is electrically connected to the first electrode of the organic light-emitting diode.

BRIEF DESCRIPTION OF THE DRAWINGS

[0015] The embodiments will become apparent by describing in detail exemplary embodiments thereof with reference to FIG. 1 which illustrates a schematic view of an organic light-emitting diode according to an embodiment.

DETAILED DESCRIPTION


[0016] An embodiment provides a heterocyclic compound represented by Formula 1:




<Formula 1>

[0017] In Formula 1, A₁ may represent a substituted or unsubstituted fused pyridine cycle. For example, the heterocyclic compound represented by Formula 1 may include a substituted or unsubstituted pyridinated compound that is fused to a back bone thereof. Among hydrogen atoms of the fused pyridine group, one or more hydrogen atoms may be substituted with substituents. Due to the inclusion of the pyridine ring, the heterocyclic compound represented by Formula 1 may have a high glass transition temperature or melting point.


[0018] A₁ may include a group represented by Formulae 2A to 2D below, but is not limited thereto:




<Formula 2A>



<Formula 2B>



<Formula 2C>




<Formula 2D>

[0019] In the above Formulae, R₁₀ may independently be a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cycloalkyl group, a substituted or unsubstituted C₃-C₃₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, or a substituted or unsubstituted C₃-C₃₀ hetero aryl group, and examples thereof are a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a phenyl group, a non-phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, a phenanthridinyl group, a phenanthroline group, an anthryl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chricenyl group, a naphthacenyl group, a pycenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a benzoimidazolyl group, a pyrazolyl group, a pyridinyl group, an imidazopyridinyl group, a pyrazinyl group, a pyrimidinyl group, an imidazopyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, a pyrido indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazoliny group, a carbazolyl group, a phenazinyl group, a puranyl group, a benzopuranyl group, a dibenzopuranyl group, a thiophenyl group, a benzothiophenyl group, a dibenzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl


group, an oxazolyl group, a benzooxazolyl group, an isooxazolyl group, an oxadiazolyl group, a triazolyl group, a triazinyl group, a tetrazolyl group, etc.

[0020] Also, p may be an integer from 1 to 3, and * and *' may each represent a site that is to be fused to the back bond of Formula 1.

[0021] In an implementation, A₁ may be a group represented by Formulae 3A to 3P below:



-continued



[0022] In the above Formulae, * and *' may each represent a site that is to be fused to the back bond of Formula 1.

[0023] R₁ to R₉ in Formula 1 may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cycloalkyl group, a substituted or unsubstituted C₃-C₃₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, a substituted or unsubstituted C₃-C₃₀ hetero aryl group, or a group represented by N(Q₁)(Q₂) wherein Q₁ and Q₂ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a substituted or

unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cycloalkyl group, a substituted or unsubstituted C₃-C₃₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, or a substituted or unsubstituted C₃-C₃₀ hetero aryl group.

[0024] For example, R₁ to R₉ may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted pentyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted non-phenyl group, a substituted or unsubstituted pentalenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted azulenyl group, a substituted or unsubstituted heptalenyl group, a substituted or unsubstituted indacenyl group, a substituted or unsubstituted acenaphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted spiro-fluorenyl group, a substituted or unsubstituted phenalenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted phenanthridinyl group, a substituted or unsubstituted phenanthroline group, a substituted or unsubstituted anthryl group, a substituted or unsubstituted fluoranthenyl group, a substituted or unsubstituted triphenylenyl group, a substituted or unsubstituted perylene group, a substituted or unsubstituted chricenyl group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted pycenyl group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted pentaphenyl group, a substituted or unsubstituted hexacenyl group, a substituted or unsubstituted pyrrolyl group, a substituted or unsubstituted imidazolyl group, a substituted or unsubstituted benzoimidazolyl group, a substituted or unsubstituted pyrazolyl group, a substituted or unsubstituted pyridinyl group, a substituted or unsubstituted imidazopyridinyl group, a substituted or unsubstituted pyrazinyl group, a substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted imidazopyrimidinyl group, a substituted or unsubstituted pyridazinyl group, a substituted or unsubstituted indolyl group, a substituted or unsubstituted isoindolyl group, a substituted or unsubstituted pyrido indolyl group, a substituted or unsubstituted indazolyl group, a substituted or unsubstituted purinyl group, a substituted or unsubstituted quinolinyl group, a substituted or unsubstituted benzoquinolinyl group, a substituted or unsubstituted phthalazinyl group, a substituted or unsubstituted naphthyridinyl group, a substituted or unsubstituted quinoxalinyl group, a substituted or unsubstituted quinazolinyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted phenazinyl group, a substituted or unsubstituted puranyl group, a substituted or unsubstituted benzopuranyl group, a substituted or unsubstituted dibenzopuranyl group, a substituted or unsubstituted thiophenyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted thiazolyl group, a substituted or unsubstituted isothiazolyl group, a substituted or unsubstituted benzothiazolyl group, a substituted or unsubstituted oxazolyl group, a sub-


stituted or unsubstituted benzooxazolyl group, a substituted or unsubstituted isooxazolyl group, a substituted or unsubstituted oxadiazolyl group, a substituted or unsubstituted triazolyl group, a substituted or unsubstituted triazinyl group, a substituted or unsubstituted tetrazolyl group, or a group represented by N(Q₁)(Q₂) wherein Q₁ and Q₂ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted pentyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthryl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted carbazolyl group, or a substituted or unsubstituted pyridinyl group, but are not limited thereto.

[0025] In an implementation, R₁ to R₉ may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted imidazolyl group, a substituted or unsubstituted benzoimidazolyl group, a substituted or unsubstituted pyridinyl group, a substituted or unsubstituted imidazopyridinyl group, a substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted imidazopyrimidinyl group, a substituted or unsubstituted indolyl group, a substituted or unsubstituted pyrido indolyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted puranyl group, a substituted or unsubstituted benzopuranyl group, a substituted or unsubstituted dibenzopuranyl group, a substituted or unsubstituted thiophenyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted oxadiazolyl group, a substituted or unsubstituted triazinyl group, and a group represented by N(Q₁)(Q₂) wherein Q₁ and Q₂ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted carbazolyl group, or a substituted or unsubstituted pyridinyl group.


[0026] R₁ and R₅ in Formula 1, like A₁, may affect characteristics of the heterocyclic compound. R₁ and R₅ in Formula 1 may each be independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted imidazolyl group, a substituted or unsubstituted benzoimidazolyl group, a substituted or unsubstituted pyridinyl group, a substituted or unsubstituted imidazopyridinyl group,

a substituted or unsubstituted pyrimidinyl group, a substituted or unsubstituted imidazopyrimidinyl group, a substituted or unsubstituted indolyl group, a substituted or unsubstituted pyrido indolyl group, a substituted or unsubstituted carbazolyl group, a substituted or unsubstituted puranyl group, a substituted or unsubstituted benzopuranyl group, a substituted or unsubstituted dibenzopuranyl group, a substituted or unsubstituted thiophenyl group, a substituted or unsubstituted benzothiophenyl group, a substituted or unsubstituted dibenzothiophenyl group, a substituted or unsubstituted oxadiazolyl group, a substituted or unsubstituted triazinyl group, or a group represented by $N(Q_1)(Q_2)$ wherein Q_1 and Q_2 are each independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted carbazolyl group, or a substituted or unsubstituted pyridinyl group. In this regard, R_2 , R_3 , R_4 , R_6 , R_7 , R_8 , and R_9 may each be independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, or a substituted or unsubstituted pentyl.


[0027] In an implementation, R_1 and R_5 may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted isobutyl group, and one of the groups represented by Formulae 4A to 4V below, and R_2 , R_3 , R_4 , R_6 , R_7 , R_8 , and R_9 may be hydrogen atoms:




<Formula 4A>



<Formula 4B>




<Formula 4C>




<Formula 4D>


-continued




<Formula 4E>




<Formula 4F>




<Formula 4G>




<Formula 4H>




<Formula 4I>




<Formula 4J>



<Formula 4K>











<Formula 4L>



<Formula 4M>

-continued



<Formula 4N>

<Formula 4O>

<Formula 4P>

<Formula 4Q>

<Formula 4R>


<Formula 4S>

<Formula 4T>

<Formula 4U>

-continued

<Formula 4V>




[0028] In the above Formulae, Z_1 , Z_2 , Z_3 , Z_4 , and Z_5 may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a hydroxy group, a cyano group, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted methoxy group, a substituted or unsubstituted ethoxy group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthryl group, or a substituted or unsubstituted pyridinyl group, q may be an integer of 1 to 5, r and u may each independently be an integer of 1 to 4, s and x may each independently be an integer of 1 to 3, v may be an integer of 1 or 2, and $*$ may represent a binding site.

[0029] L_1 and L_2 in Formula 1 may be divalent linkers, and may each independently be a substituted or unsubstituted C_6 - C_{30} arylene group, or a substituted or unsubstituted C_3 - C_{30} heteroarylene group. a and b may each represent a number of divalent linkers connected in series and may each independently be an integer of 0 to 3.


[0030] In an implementation, L_1 and L_2 may each independently be a substituted or unsubstituted phenylene group, a substituted or unsubstituted naphthylene group, a substituted or unsubstituted anthrylene group, a substituted or unsubstituted phenanthrenylene group, a substituted or unsubstituted pyrenylene group, a substituted or unsubstituted chrysenylene group, a substituted or unsubstituted perylenylene group, a substituted or unsubstituted fluorenylene group, a substituted or unsubstituted spiro-fluorenyl group, a substituted or unsubstituted carbazolylenylene group, a substituted or unsubstituted pyridinylene group, or a substituted or unsubstituted oxadiazolylenylene group.

[0031] In an implementation, L_1 and L_2 may each independently be a group represented by Formulae 5A to 5G below, but are not limited thereto:


<Formula 5A>




<Formula 5B>




-continued




<Formula 5C>




<Formula 5D>



<Formula 5E>



<Formula 5F>




<Formula 5G>

[0032] In the above Formulae, Z_6 , Z_7 , and Z_8 may each independently be a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, or a substituted or unsubstituted phenyl. Also, r' and u' may each independently be an integer of 1 to 4, s' may be an integer of 1 to 3, v' and y' may each independently be an integer of 1 to 2, and $*$ and $*'$ may each represent a binding site that is linked to any one of R_1 and R_5 or any one of a nitrogen atom and a carbon atom of the back bone.


[0033] In the structure of Formula 1, one or more of the divalent linkers L_1 and L_2 may not be present, or L_1 and L_2 both may not be present. If L_1 and L_2 all are not present, a and b in Formula 1 may be 0. For example, a and b in Formula 1 may each independently be 0 or 1.

[0034] The heterocyclic compound represented by Formula 1 may have a high glass transition temperature or melting point due to the introduction of a heterocycle therein. Accordingly, an organic light-emitting diode including the heterocyclic compound represented by Formula 1 may exhibit a resistance against Joule heat generated in an organic layer during light emission, Joule heat that is generated between organic layers, or Joule heat that is generated between an organic layer and a metallic electrode, and thus, may have stronger resistance under high-temperature environments. Also, due to the inclusion of an indole structure in the heterocyclic compound represented by Formula 1, a formed organic light-emitting diode may have high durability during preservation and driving. Also, when R_1 to R_9 include, e.g., fluorene groups, an organic light-emitting diode including the heterocyclic compound represented by Formula 1 may have an improved molecular film state. Accordingly, when the heterocyclic compound represented by Formula 1 is used in an organic light-emitting diode, it may be used with excellent luminescence characteristics and a charge transporting capability as an electron injection material or an electron transporting material, which are suitable for full colors, for example, red, green, blue, and white fluorescent and phosphorescent devices. For example, the heterocyclic compound represented by Formula 1 may be suitable for use as a light-emitting material of green, blue, white fluorescent devices.

[0035] Non-limiting examples of the heterocyclic compound represented by Formula 1 may include compounds represented by Compounds 1 to 112, below:




1




2

-continued




3


-continued




6




4



7




5




8

-continued




9

-continued




12

10





13




14

11




-continued




15


-continued




18




16



19




17



20

-continued

21




-continued

24






22

25


23



-continued




-continued




31


-continued




34




32



35






33





36



-continued






-continued




-continued



-continued




-continued




47


-continued




50




48



51




49




52

-continued




53


-continued




56




54



57




55




58

-continued




59


-continued




62




60



63




61




64

-continued




65


-continued




68



66




67




69

-continued




70


-continued




72



71




73




74

-continued




75


-continued




78




76



79




77




80

-continued




81


-continued




84




82



85




83




86

-continued




87


-continued




90




88



91




89




92

-continued




93


-continued




96




94



97




95




98

-continued




99


-continued




102




100



103




101






104


-continued




-continued




-continued



109




110



111

-continued

112



[0036] The term “substituted” in the term “substituted or unsubstituted A (where A is an arbitrary substituent)” used herein may refer to “a case in which one or more hydrogen atoms of the A are substituted with a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group or a salt derivative thereof, a sulfonic acid group or a salt derivative thereof, a phosphoric acid group or a salt derivative thereof, a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, a C₁-C₃₀ alkoxy group, a C₃-C₃₀ cyclo alkyl group, a C₃-C₃₀ cyclo alkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a C₃-C₃₀ hetero aryl group, a group represented by N(Q₁₀₁)(Q₁₀₂), or a group represented by Si(Q₁₀₃)(Q₁₀₄)(Q₁₀₅) wherein Q₁₀₁ to Q₁₀₅ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a C₁-C₃₀ alkyl group, a C₂-C₃₀ alkenyl group, a C₂-C₃₀ alkynyl group, a C₁-C₃₀ alkoxy group, a C₃-C₃₀ cyclo alkyl group, a C₃-C₃₀ cyclo alkenyl group, a C₆-C₃₀ aryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, or a C₃-C₃₀ hetero aryl group.

[0037] For example, the term “substituted A” may refer to “a case in which one or more hydrogen atoms of the A are substituted with a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a phenyl group, a non-phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, a phenanthridinyl group, a phenanthroline group, an anthryl group, a fluoranteny group, a triphenylenyl group, a pyrenyl group, a chricenyl group, a naphthacenyl group, a pycenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pyrrolyl group, an imidazolyl group, a benzoimidazolyl group, a pyrazolyl group, a pyridinyl group, an imidazopyridinyl group, a pyrazinyl group, a pyrimidinyl group, an imidazopyrimidinyl group, a pyridazinyl group, an indolyl group, an isoindolyl group, a pyrido indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenazinyl group, a puranyl group, a benzopuranyl group, a dibenzopuranyl group, a thiophenyl

group, a benzothiophenyl group, a dibenzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an oxazolyl group, a benzooxazolyl group, an isooxazolyl group, an oxadiazolyl group, a triazolyl group, a triazinyl group, a tetrazolyl group, a group represented by $N(Q_{101})(Q_{102})$, or a group represented by $Si(Q_{103})(Q_{104})(Q_{105})$.

[0038] The unsubstituted C_1 - C_{30} alkyl group may refer to a linear or branched saturated hydrocarbon group of alkane from which one hydrogen atom is deficient. Examples of the unsubstituted C_1 - C_{30} alkyl group may include methyl, ethyl, propyl, isobutyl, sec-butyl, pentyl, iso-amyl, hexyl, etc. A substituent of the substituted C_1 - C_{30} alkyl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0039] The unsubstituted C_2 - C_{30} alkenyl group used herein may refer to a terminal group having at least one carbon-carbon double bond at the center or at a terminal of the substituted or unsubstituted C_2 - C_{30} alkyl group. Non-limiting examples of the unsubstituted C_2 - C_{30} alkenyl group may include an ethenyl group, a propenyl group, a butenyl group, a pentenyl group, a hexenyl group, a heptenyl group, an octenyl group, a propadienyl group, an isoprenyl group, and an allyl group. A substituent of the substituted C_2 - C_{30} alkenyl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0040] The unsubstituted C_2 - C_{30} alkynyl group used herein may refer to a terminal group having at least one carbon-carbon triple bond at the center or at a terminal of the substituted or unsubstituted C_2 - C_{30} alkyl group. Non-limiting examples of the unsubstituted C_2 - C_{30} alkynyl group may include an acetylenyl group, etc. A substituent of the substituted C_2 - C_{30} alkynyl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0041] The unsubstituted C_1 - C_{30} alkoxy group used herein may have a formula represented by $-OY$ where Y is the unsubstituted C_1 - C_{30} alkyl group as defined above. Non-limiting examples of the unsubstituted C_1 - C_{30} alkoxy group may include methoxy, ethoxy, isopropoxy, butoxy, pentoxy, etc. A substituent of the substituted C_1 - C_{30} alkoxy group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0042] The unsubstituted C_3 - C_{30} cycloalkyl group used herein may refer to a cyclic saturated hydrocarbon group. Non-limiting examples of the unsubstituted C_3 - C_{30} cycloalkyl group may include cyclopropyl group, cyclobutyl group, cyclopentyl group, cyclohexyl group, cyclooctyl group, etc. A substituent of the substituted C_1 - C_{30} cycloalkyl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0043] The unsubstituted C_3 - C_{30} cycloalkenyl group used herein may refer to a cyclic unsaturated hydrocarbon group having one or more carbon double bonds that are not an aromatic ring. Non-limiting examples of the unsubstituted C_3 - C_{30} cycloalkenyl group may include a cyclopropenyl group, a cyclobutenyl group, a cyclopentenyl group, a cyclohexenyl group, a cycloheptenyl group, a 1,3-cyclohexadienyl group, a 1,4-cyclohexadienyl group, a 2,4-cycloheptadienyl group, a 1,5-cyclooctadienyl group, etc. A substituent of the substituted C_3 - C_{30} cycloalkenyl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0044] The unsubstituted C_6 - C_{30} aryl group used herein may refer to a monovalent group having a carbocyclic aromatic system in which the number of carbon atoms is 6 to 30, and may be a monocyclic group or a polycyclic group. If the unsubstituted C_6 - C_{30} aryl group is a polycyclic group, two or more rings contained in the unsubstituted C_6 - C_{30} aryl group may be fused. Non-limiting examples of the unsubstituted C_6 - C_{30} aryl group may include a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthryl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, and a hexacenyl group. A substituent of the substituted C_6 - C_{30} aryl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0045] The unsubstituted C_6 - C_{30} aryloxy group used herein may refer to a monovalent group wherein a carbon atom of the C_6 - C_{30} aryl group is attached via an oxygen linker ($-O-$). A substituent of the substituted C_6 - C_{30} aryloxy group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0046] The unsubstituted C_6 - C_{30} arylthio group used herein may refer to a monovalent group wherein a carbon atom of the C_6 - C_{30} aryl group is attached via a sulfur linker ($-S-$). Examples of the unsubstituted C_6 - C_{30} arylthio group may include a phenylthio group, a naphthylthio group, an indenylthio group, and an indenylthio group. A substituent of the substituted C_6 - C_{30} arylthio group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0047] The unsubstituted C_3 - C_{30} hetero aryl group used herein may refer to a monovalent group that has at least one ring having one or more hetero atoms selected from the group of nitrogen (N), oxygen (O), phosphorous (P), and sulfur (S) and that has 3 to 30 carbon atoms, and may be a monocyclic or polycyclic group. If the unsubstituted C_3 - C_{30} hetero aryl group is a polycyclic group, two or more rings contained in the unsubstituted C_3 - C_{30} hetero aryl group may be fused. Examples of the unsubstituted C_3 - C_{30} hetero aryl group may include a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzooxazolyl group, a benzoimidazolyl group, a furanyl group, a benzofuranyl group, a thiophenyl group, a benzothiophenyl group, a thiazolyl group, an isothiazolyl group, a benzothiazolyl group, an isoxazolyl group, an oxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzooxazolyl group, etc. A substituent of the substituted C_3 - C_{30} hetero aryl group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0048] The unsubstituted C_1 - C_{30} alkylene group used herein may be a linear or branched divalent group of alkane from which two hydrogen atoms are deficient. Examples of the unsubstituted C_1 - C_{30} alkylene group may be understood by referring to the examples of the unsubstituted C_1 - C_{30} alkyl

group presented above. A substituent of the substituted C_1 - C_{30} may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0049] The unsubstituted C_6 - C_{30} arylene used herein may refer to a divalent group having a carbocyclic aromatic system having 6 to 30 carbon atoms, and the divalent group may be a monocyclic or polycyclic group. Examples of the unsubstituted C_6 - C_{30} arylene may be understood by referring to the examples of the unsubstituted C_6 - C_{30} aryl group. A substituent of the substituted C_6 - C_{30} arylene may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0050] The unsubstituted C_3 - C_{30} heteroarylene group used herein may refer to a divalent group that has at least one ring having one or more hetero atoms selected from the group consisting of nitrogen (N), oxygen (O), phosphorous (P), and sulfur (S) and that has 3 to 30 carbon atoms, and may be a monocyclic or polycyclic group. If the unsubstituted C_3 - C_{30} hetero aryl group is a polycyclic group, two or more rings contained in the unsubstituted C_3 - C_{30} hetero aryl group may be fused. Examples of the unsubstituted C_3 - C_{30} heteroarylene group may be understood by referring to the examples of the unsubstituted C_3 - C_{30} hetero aryl group. A substituent of the substituted C_3 - C_{30} heteroarylene group may be any one of the substituents presented above where the term "substituted A" is described in detail.

[0051] The heterocyclic compound represented by Formula 1 may be synthesized by using known organic synthesis methods. One of the heterocyclic compound synthesis methods will be described in detail, below.

[0052] The heterocyclic compound represented by Formula 1 may be used in an organic light-emitting diode.

[0053] An embodiment provides an organic light-emitting diode including a first electrode, a second electrode facing the first electrode, and a first layer between the first electrode and the second electrode, wherein the first layer includes the heterocyclic compound represented by Formula 1. In an implementation, the heterocyclic compound represented by Formula 1 may be used alone or may be used in a mixed form with other materials.

[0054] The first layer may include at least one layer selected from the group of a hole injection layer, a hole transport layer, a functional layer having a hole injection function and a hole transportation function, an electron blocking layer, an emission layer, a hole blocking layer, an electron transport layer, an electron injection layer, and a functional layer having an electron transportation function and an electron injection function.

[0055] For example, the organic light-emitting diode may have a structure of first electrode/hole injection layer/hole transport layer/first layer including the heterocyclic compound represented by Formula 1 (e.g., functions as an emission layer)/electron transport layer/electron injection layer/second electrode, but the structure thereof is not limited thereto.

[0056] Layers interposed between the first electrode and the second electrode may include, e.g., at least one layer selected from the group of a hole injection layer, a hole transport layer, an emission layer, a hole blocking layer, an electron transport layer, and an electron injection layer, and at least one of these layers may be formed by using a deposition process or a wet process.

[0057] The term "wet process" used herein may refer to a process in which a material is mixed with a solvent to prepare

a mixture, and the mixture is provided on a substrate, followed by drying and/or heat treating so as to remove at least a portion of the solvent, thereby forming a film including the material on the substrate.

[0058] For example, the first layer may be formed by using a typical vacuum deposition method. Alternatively, a mixture including the heterocyclic compound and a solvent may be provided on a first layer formation region (e.g., on an upper portion of a hole transport layer) by spin coating, spraying, ink-jet printing, dipping, casting, Gravia coating, bar coating, roll coating, wire bar coating, screen coating, flexo coating, offset coating, or laser transferring, and then, the mixture provided on the first layer formation region is dried and/or heat treated to remove at least a portion of the solvent, thereby forming the first layer.

[0059] Alternatively, after a first layer is formed on a base film by using the wet process as described above, the first layer may be transferred to a first layer formation region (for example, an upper portion of the hole transport layer) by using, for example, a laser.

[0060] The first layer may be an emission layer. When the first layer is an emission layer, the emission layer may include at least one selected from the group of a fluorescent host, a phosphorescent host, a fluorescent dopant, and a phosphorescent dopant.

[0061] For example, the first layer may be an emission layer, and the heterocyclic compound of Formula 1 included in the first layer may be used as a fluorescent host or a phosphorescent host. In this regard, the first layer may further include a fluorescent dopant or a phosphorescent dopant. For example, the first layer may be either an emission layer that includes the heterocyclic compound of Formula 1 functioning as a fluorescent host, and a fluorescent dopant, or an emission layer that includes the heterocyclic compound of Formula 1 functioning as a phosphorescent host, and a phosphorescent dopant. Also, the emission layer may include the heterocyclic compound, wherein i) the heterocyclic compound functions as a fluorescent host, ii) the heterocyclic compound functions as a fluorescent dopant, or iii) the heterocyclic compound functions as both a fluorescent host and a fluorescent dopant.

[0062] According to an embodiment, the first layer may be an emission layer, wherein the emission layer includes at least one selected from the group of an anthracene-based compound, an arylamine-based compound, and a styryl-based compound.

[0063] The emission layer may include the heterocyclic compound described above.

[0064] According to an embodiment, the first layer may be an electron transport layer, wherein the electron transport layer may include the heterocyclic compound described above.

[0065] According to an embodiment, the first layer may include an emission layer and an electron transport layer, and each of the emission layer and the electron transport layer may include the heterocyclic compound described above.


[0066] For example, the first layer included in the organic light-emitting diode may be an electron transport layer, an emission layer may be additionally interposed between the first electrode and the second electrode, and the emission layer may include at least one region selected from the group of a red light-emitting region, a green light-emitting region, a blue light-emitting region, and a white light-emitting region, wherein the at least one region selected from the group of the

red light-emitting region, green light-emitting region, the blue light-emitting region, and the white light-emitting region includes a phosphorescent compound. The red light-emitting region, the green light-emitting region, the blue light-emitting region, and the white light-emitting region may be patterned by using known methods so as to embody full color images or white light emission. The phosphorescent compound may be selected from known phosphorescent hosts and phosphorescent dopants.

[0067] The first layer may include an electron transport layer, which may include a metal-containing compound. The metal-containing compound is the same as described above.

[0068] The first layer may include at least one selected from the group of a hole injection layer, a hole transport layer, and a functional layer having a hole injection function and a hole transportation function, wherein the at least one selected from the group of the hole injection layer, the hole transport layer, and the functional layer having a hole injection function and a hole transportation function may further include a charge generation material. The charge generation material may improve conductivity of the first layer.

[0069] The charge generation material may be, for example, a p-dopant. Non-limiting examples of the p-dopant may include quinine derivatives, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4TCNQ); metallic oxides, such as tungsten oxide or molybdenum oxide; and cyano group-containing compounds, such as Compound 300 illustrated below.



[0070] If the at least one selected from the group of the hole injection layer, the hole transport layer, and the functional layer having a hole injection function and a hole transportation function further includes the charge generation material, the charge generation material may be homogeneously or non-homogeneously dispersed in the layers. However, the structure of the charge generation material in the layers is not limited thereto.

[0071] FIG. 1 illustrates a schematic view of an organic light-emitting diode 10 according to an embodiment. Hereinafter, with reference to FIG. 1, the structure of an organic light-emitting diode according to an embodiment, and a method of manufacturing the organic light-emitting diode, according to an embodiment, will be described in detail.

[0072] The organic light-emitting diode 10 may sequentially include a substrate 11, a first electrode 12, a hole injection layer 13, a hole transport layer 14, an emission layer 15, an electron transport layer 16, an electron injection layer 17, and a second electrode 18 in this stated order.

[0073] The substrate 11 may be any one of various substrates that are used in a known organic light-emitting device, and may include a glass substrate or a transparent plastic substrate with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water repellency.

[0074] The first electrode 12 may be formed by providing a first electrode material on a substrate by deposition or sputtering. If the first electrode 12 is an anode, to allow holes to be injected thereinto easily, the first electrode material may be selected from materials having a high work function. Also, the first electrode 12 may be a reflection electrode or a transmission electrode. The first electrode material may be a transparent and highly conductive material, e.g., an indium tin oxide (ITO), or an indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), etc. Alternatively, if magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag) etc. are used as the first electrode material, the first electrode 12 may be formed as a reflection electrode. The first electrode 12 may include two different materials. For example, the first electrode 12 may have a two-layer structure including two different materials. However, the structure of the first electrode 12 is not limited thereto.


[0075] The hole injection layer 13 may be formed on the first electrode 12.

[0076] The hole injection layer 13 may be formed on the first electrode 12 by using various methods, such as vacuum deposition, wet process, laser transferring, etc., as described above.


[0077] When the hole injection layer 13 is formed by vacuum deposition, the deposition conditions may vary according to a material that is used to form the hole injection layer 13, and the structure and thermal characteristics of the hole injection layer 13. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10⁻⁸ to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Å/sec. However, the deposition conditions are not limited thereto.

[0078] When the hole injection layer 13 is formed using spin coating as a wet process, coating conditions may vary according to the material used to form the hole injection layer 13, and the structure and thermal properties of the hole injection layer 13. For example, a coating speed may be from about 2000 rpm to about 5000 rpm, and a temperature at which a heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.


[0079] A hole injection layer material may be any one of known hole injecting materials. Non-limiting examples of the hole injection layer material may include a phthalocyanine compound, such as copper phthalocyanine, m-MTDATA (a structure thereof is illustrated below), TDATA (a structure thereof is illustrated below), 2-TNATA (a structure thereof is illustrated below), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), polyaniline/poly(4-styrenesulfonate) (Pani/PSS), etc.



m-MTDATA



TDATA




2-TNATA

[0080] The hole injection layer **13** may have a thickness of about 100 Å to about 10,000 Å, e.g., a thickness of about 100 Å to about 1,000 Å. When the thickness of the hole injection layer **13** is within these ranges, the hole injection layer **13** may have satisfactory hole injection characteristics without an increase in driving voltage.

[0081] The hole transport layer **14** may be formed on the hole injection layer **13** by, e.g., vacuum deposition, wet process, or laser transferring.

[0082] When the hole transport layer **14** is formed on the hole injection layer **13** by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer **13**, although the deposition or coating conditions may vary according to the material that is used to form the hole transport layer **14**.

[0083] A hole transport layer material may be any one of known hole transport materials. Non limiting examples of the hole transport materials may include TPD (a structure thereof is illustrated below), NPB (a structure thereof is illustrated below), etc.



TPD

NPB


[0084] The hole transport layer **14** may have a thickness of about 50 Å to about 1000 Å, e.g., a thickness of about 100 Å to about 800 Å. When the thickness of the hole transport layer **14** is within the above ranges, the hole transport layer **14** may have satisfactory hole transport characteristics without an increase in driving voltage.

[0085] The emission layer **15** may be formed on the hole transport layer **14** by, e.g., vacuum deposition, wet process, or laser transferring.


[0086] When the emission layer **15** is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer **13**, although the deposition or coating conditions may vary according to the material that is used to form the emission layer **15**.

[0087] The emission layer **15** may be the first layer including the heterocyclic compound represented by Formula 1 described above. The emission layer **15** may further include, in addition to the heterocyclic compound represented by Formula 1, a known phosphorescent host, fluorescent host, phosphorescent dopant, or fluorescent dopant. The heterocyclic compound represented by Formula 1 may function as a phosphorescent host, a fluorescent host, a phosphorescent dopant, or a fluorescent dopant.


[0088] As a known host, 4,4'-N,N'-dicarbazole-biphenyl (CBP), 9,10-di-naphthalene-2-yl-anthracene (ADN, a structure thereof is illustrated below), TPBI (a structure thereof is illustrated below), TBADN (a structure thereof is illustrated below), E3 (a structure thereof is illustrated below), distyryl arylene (DSA), etc. may be used, but the host is not limited thereto.



[0089] As a red dopant, PtOEP (a structure thereof is illustrated below), Ir(piq)₃ (a structure thereof is illustrated below), Btp₂Ir(acac) (a structure thereof is illustrated below), etc. may be used, but the red dopant is not limited thereto.




[0090] Also, as a green dopant, Ir(ppy)₃ (ppy=phenyl pyridine, a structure thereof is illustrated below), Ir(ppy)₂(acac) (a structure thereof is illustrated below), Ir(mppy)₃ (a structure thereof is illustrated below), etc. may be used, but is not limited thereto.



[0091] As a blue dopant, F_2Irpic (a structure thereof is illustrated below), $(F_2ppy)_2Ir(tmd)$ (a structure thereof is illustrated below), $Ir(dfppz)_3$ (a structure thereof is illustrated below), $DPVBi$ (a structure thereof is illustrated below), $DPAVBi$ (a structure thereof is illustrated below), $TBPc$ (2,5,8,11-tetra-tert-butyl perylene (a structure thereof is illustrated below), etc. may be used, but is not limited thereto.

laser transferring, to prevent diffusion of a triple exciton or a hole into the electron transport layer **16**. If the HBL is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer **13**, although the deposition or coating conditions may vary according to the material that is used to form the HBL. As a HBL material, any one of known hole blocking materials may be used. Examples thereof may



[0092] If the emission layer **15** includes a host and a dopant, an amount of the dopant may be from about 0.01 to about 15 parts by weight based on about 100 parts by weight of the host, but is not limited thereto.

[0093] A thickness of the emission layer **15** may be from about 100 Å to about 1000 Å, e.g., about 200 Å to about 600 Å. If the thickness of the emission layer **15** is within these ranges, excellent luminescence characteristics may be obtained without a substantial increase in driving voltage.



[0094] If the emission layer **15** includes a phosphorescent dopant, a hole blocking layer (HBL) (not shown in FIG. 1) may be formed between the electron transport layer **16** and the emission layer **15** by vacuum deposition, wet process, or

include an oxadiazole derivative, a triazole derivative, a phenanthroline derivative, etc.


[0095] A thickness of the HBL may be from about 50 Å to about 1,000 Å, e.g., about 100 Å to about 300 Å. Maintaining the thickness of the HBL within the ranges described above may help ensure that excellent hole blocking characteristics are obtained without a substantial increase in driving voltage.

[0096] Then, the electron transport layer **16** may be formed by using various methods, e.g., vacuum deposition, a wet process, laser transferring, etc., as described above. As an electron transport layer material, the heterocyclic compound represented by Formula 1 described above may be used. Also, known electron transporting materials may instead be used,

and examples thereof may include a quinoline derivative, such as tris(8-quinolinolate)aluminum (Alq_3), TAZ (a structure thereof is illustrated below), BALq (a structure thereof is illustrated below), and beryllium bis(benzoquinolin-10-olate) (Bebq_2), but are not limited thereto.




[0097] The electron transport layer **16** may include an electron transporting organic compound and a metal-containing compound. Non-limiting examples of the electron transporting organic compound may include (9,10-di(naphthalene-2-yl)anthracene (ADN); and anthracene-based compounds, such as Compounds 201 and 202 below.




-continued

<Compound 202>



[0098] The metal-containing compound may include a Li complex. Non-limiting examples of the Li complex may include lithium quinolate (LiQ), Compound 203 below, etc.:

<Compound 203>



[0099] A thickness of the electron transport layer **16** may be from about 100 Å to about 1000 Å, e.g., about 150 Å to about 500 Å. Maintaining the thickness of the electron transport layer **16** within the ranges described above may help ensure that excellent electron transporting characteristics are obtained without a substantial increase in driving voltage. If the electron transport layer **16** is formed by vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the hole injection layer **13**, although the deposition or coating conditions may vary according to the material that is used to form the electron transport layer **16**.

[0100] The electron injection layer **17** may be deposited on the electron transport layer **16** by using a material that facilitates injection of electrons from an anode. As a material for forming the electron injection layer **17**, any suitable electron injection layer material, e.g., LiF, NaCl, CsF, Li_2O , or BaO , may be used. The deposition conditions of the electron injection layer **17** may be similar to those applied to form the hole injection layer **13**, although the deposition or coating conditions may vary according to the material that is used to form the electron injection layer **17**.

[0101] A thickness of the electron injection layer **17** may be from about 1 Å to about 100 Å, e.g., about 3 Å to about 90 Å. Maintaining the thickness of the electron injection layer **17**

within the ranges described above may help ensure that excellent electron injection characteristics are obtained without a substantial increase in driving voltage.

[0102] The second electrode **18** may be formed as a reflection electrode on the electron injection layer **17**. The second electrode **18** may be a cathode as an electron injection electrode, and in this case, a low work function metal, alloy, electrically conductive compound, and a mixture thereof may be used as a second electrode metal. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), etc. may be formed as a thin film for use as a reflection electrode. Also, if the organic light-emitting diode is used in a top-emission light-emitting device, a transmission electrode may be formed using ITO or IZO.


[0103] The organic light-emitting diode may be included in a flat display device including a transistor. Accordingly, an embodiment provides a flat display device including: a transistor (including a source, a drain, a gate, and an active layer, and the organic light-emitting diode described above), wherein the source or the drain is electrically connected to the first electrode of the organic light-emitting diode. The active layer of the transistor may include an amorphous silicon layer, a crystalline silicon layer, an organic semiconductor layer, or an oxide semiconductor layer, but is not limited thereto.

[0104] Hereinafter, an organic light-emitting diode according to an embodiment will be described in detail with reference to Synthesis Examples and Examples regarding Compounds **7**, **24**, **26**, **27**, **30**, **33**, **39**, **40**, **43**, **52**, **58**, **72**, **81**, **107**, **110**, and **111**. The following Examples and Comparative Examples are provided in order to set forth particular details of one or more embodiments. However, it will be understood that the embodiments are not limited to the particular details described. Further, the Comparative Examples are set forth to highlight certain characteristics of certain embodiments, and are not to be construed as either limiting the scope of the invention as exemplified in the Examples or as necessarily being outside the scope of the invention in every respect.




EXAMPLE

Synthesis of Compound **7**

[0105]



-continued



Synthesis Example 1

Synthesis of Intermediate I-1

[0106] 4.93 g (20.0 mmol) of pyrene boric acid, 4.05 g (20.0 mmol) of 2-bromo-3-nitropyridine, 1.15 g (1.0 mmol) of $\text{Pd}(\text{PPh}_3)_4$, and 8.29 g (60.0 mmol) of K_2CO_3 were dis-

solved in 60 ml of a THF/H₂O (2/1) mixed solution, and then the mixture was stirred at a temperature of 70° C. for 5 hours. The solution was cooled to room temperature and then 40 mL of water was added thereto and the resultant solution was extracted three times with 50 mL of ethyl ether. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified to obtain 5.38 g (Yield: 83%) of Intermediate I-1. The formed compound was confirmed by liquid chromatography-mass spectroscopy (LC-MS) and nuclear magnetic resonance (NMR). C₂₁H₁₂N₂O₂: M+ 324.1

[0107] ¹H NMR (CDCl₃, 400 MHz) δ (ppm) 8.61 (dd, 1H), 8.33 (dd, 1H), 8.25 (d, 1H), 8.22 (s, 1H), 8.20 (d, 1H), 8.11-7.97 (m, 6H), 7.34 (dd, 1H)

Synthesis Example 2

Synthesis of Intermediate I-2

[0108] 3.24 g (10.0 mmol) of Intermediate I-1 and 5.77 g (22 mmol) of triphenyl phosphine (PPh₃) were dissolved in 30 ml of 1,2-dichlorobenzene, and then stirred at a temperature of 170° C. for 12 hours. The solution was cooled to room temperature, and then the used solvent was removed therefrom under vacuum conditions and the resultant solution was extracted three times with 50 mL of water and 50 mL of dichloromethane. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography to obtain 2.31 g (Yield: 79%) of Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. C₂₁H₁₂N₂: M+ 292.1

[0109] ¹H NMR (CDCl₃, 400 MHz) δ (ppm) 11.38 (s, 1H), 9.14 (d, 1H), 8.70 (d, 1H), 8.47-8.44 (m, 2H), 8.17 (d, 1H), 8.10 (s, 1H), 8.00 (dt, 2H), 7.90-7.86 (m, 2H), 7.42-7.38 (m, 1H)

Synthesis Example 3





Synthesis of Compound 7

[0110] 2.92 g (10.0 mmol) of Intermediate I-2, 4.83 g (15.0 mmol) of 9-(4-bromophenyl)carbazole, 0.19 g (1.0 mmol) of CuI, 0.05 g (0.2 mmol) of 18-Crown-6, and 4.15 g (30.0 mmol) of K₂CO₃ were dissolved in 30 ml of 1,3-dimethyl-3,4,5,6-tetrahydro-2(1H)-pyrimidinone (DMPU), and then the mixture was stirred at a temperature of 170° C. for 12 hours. The solution was cooled to room temperature, and extracted three times with 50 mL of water and 50 mL of dichloromethane. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography to obtain 4.81 g (Yield: 90%) of Compound 7. The formed compound was confirmed by LC-MS and NMR. C₃₉H₂₃N₃: M+ 533.2


[0111] ¹H NMR (CDCl₃, 400 MHz) δ (ppm) 9.13 (d, 1H), 8.65 (d, 1H), 8.52-8.49 (m, 2H), 8.21 (s, 1H), 8.14-8.05 (m, 4H), 7.98 (d, 1H), 7.90-7.84 (m, 5H), 7.69 (dd, 1H), 7.37-7.33 (m, 4H), 7.26-7.20 (m, 2H), 7.04 (dd, 1H)

Synthesis of Compound 24

[0112]



-continued



24

Synthesis Example 4

Synthesis of Intermediate I-3

[0113] 4.86 g (15.0 mmol) of Intermediate I-1 was dissolved in 100 ml of dichloromethane, and then 1.75 ml (15.0 mmol) of bromine (Br_2) was slowly dropped thereto at a temperature of 0°C . The solution was stirred at room temperature for 12 hours. Then, 60 mL of water and 30 ml of thiosodium sulfate 20% aqueous solution were added to the reaction solution, and the resultant solution was extracted three times with 80 mL of dichloromethane. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography, followed by recrystallization with a dichloromethane/hexane solution, thereby producing 3.39 g (Yield: 59%) of Intermediate I-3. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{21}\text{H}_{11}\text{BrN}_2\text{O}_2$: M^+ 402.0

[0114] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.84 (d, 1H), 8.61 (dd, 1H), 8.35-8.31 (m, 2H), 8.27-8.22 (m, 3H), 8.10 (d, 1H), 7.95 (d, 1H), 7.90 (d, 1H), 7.34 (dd, 1H)

Synthesis Example 5

Synthesis of Intermediate I-4

[0115] 2.78 g (Yield: 75%) of Intermediate I-4 was obtained using Intermediate I-3 and triphenyl phosphine in the same manner as in the method of synthesizing Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{21}\text{H}_{11}\text{BrN}_2$: M^+ 370.0

[0116] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 11.10 (s, 1H), 8.84 (d, 1H), 8.75 (d, 1H), 8.51-8.40 (m, 2H), 8.37 (d, 1H), 8.15 (s, 1H), 8.06 (d, 1H), 7.98 (d, 1H), 7.88 (d, 1H), 7.41-7.38 (m, 1H)

Synthesis Example 6

Synthesis of Intermediate I-5

[0117] 4.11 g (Yield: 92%) of Intermediate I-5 was obtained using Intermediate I-4 and iodobenzene in the same

manner as in the method of synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{27}\text{H}_{15}\text{BrN}_2$: M^+ 446.0

[0118] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.84 (d, 1H), 8.73 (d, 1H), 8.56-8.51 (m, 2H), 8.35 (d, 1H), 8.27 (s, 1H), 8.11 (d, 1H), 7.98 (d, 1H), 7.69 (dd, 1H), 7.65-7.55 (m, 4H), 7.39-7.32 (m, 1H), 7.06-7.02 (m, 1H)

Synthesis Example 7


Synthesis of Compound 24

[0119] 2.24 g (5.0 mmol) of Intermediate I-5, 1.86 g (5.0 mmol) of Intermediate I-6 disclosed in a known reference, 0.29 g (0.25 mmol) of $\text{Pd}(\text{PPh}_3)_4$, and 2.07 g (15.0 mmol) of K_2CO_3 were dissolved in 30 ml of a THF/ H_2O (2/1) mixed solution, and then the mixture was stirred at a temperature of 70°C . for 5 hours. The solution was cooled to room temperature, and then extracted three times with 50 mL of water and 50 mL of diethyl ether. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography to obtain 2.20 g (Yield: 72%) of Compound 24. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{45}\text{H}_{29}\text{N}_3$: M^+ 611.2


[0120] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.71 (d, 1H), 8.52-8.45 (m, 2H), 8.19-8.16 (m, 2H), 8.01 (d, 1H), 7.95-7.88 (m, 2H), 7.70-7.56 (m, 5H), 7.38-7.29 (m, 7H), 7.06-7.01 (m, 1H), 6.84-6.80 (m, 2H), 6.75-6.71 (m, 2H), 6.53-6.50 (m, 4H)

Synthesis of Compounds 26, 27, and 33

[0121]




I-7




I-8

-continued




I-9

26



-continued

33



Synthesis Example 8

Synthesis of Compound 26

[0122] 2.83 g (Yield: 85%) of Compound 26 was obtained using Intermediate I-5 and Intermediate I-7 disclosed in known references in the same manner as in the method of synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{45}H_{26}F_3N_3$: M^+ 665.2

[0123] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.69 (d, 1H), 8.52 (d, 1H), 8.46 (d, 1H), 8.21-8.13 (m, 2H), 7.98-7.76 (m, 3H), 7.68-7.55 (m, 6H), 7.29-7.18 (m, 5H), 7.08-7.04 (m, 1H), 6.89-6.86 (m, 1H), 6.79-6.76 (m, 3H), 6.62-0.60 (m, 2H)

Synthesis Example 9

Synthesis of Compound 27

27 [0124] 2.52 g (Yield: 82%) of Compound 27 was obtained using Intermediate I-5 and Intermediate I-8 disclosed in known references in the same manner as in the method of synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{43}H_{27}N_5$: M^+ 613.2

[0125] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.73 (d, 1H), 8.62-8.55 (m, 2H), 8.33-8.25 (m, 4H), 8.11-7.98 (m, 3H), 7.72 (dd, 1H), 7.68-7.53 (m, 8H), 7.42-7.34 (m, 3H), 7.06-6.98 (m, 3H), 6.90 (dt, 2H)

Synthesis Example 10


Synthesis of Compound 33

[0126] 2.83 g (Yield: 89%) of Compound 33 was obtained using Intermediate I-5 and Intermediate I-9 disclosed in known references in the same manner as in the method of synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{46}H_{28}N_4$: M^+ 636.2

[0127] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.66 (d, 1H), 8.51 (dd, 1H), 8.46 (d, 1H), 8.19-8.14 (m, 4H), 7.99 (d, 1H), 7.89 (d, 1H), 7.74-7.68 (m, 2H), 7.62-7.53 (m, 4H), 7.48-7.21 (m, 11H), 7.16-7.12 (m, 1H), 7.08-7.04 (m, 1H)

Synthesis of Compound 30

[0128]



Synthesis Example 11

Synthesis of Intermediate I-10

[0129] 4.47 g (10.0 mmol) of Intermediate I-5, 2.54 g (10.0 mmol) of bis(pinacolato)diboron, 0.36 g (0.5 mmol) of $\text{PdCl}_2(\text{dppf})_2$, and 2.94 g (30.0 mmol) of KOAc were dissolved in 40 mL of DMSO and then, stirred at a temperature of 80° C. for 6 hours. The solution was cooled to room temperature, and then extracted three times with 50 mL of water and 50 mL of diethyl ether. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography to obtain Intermediate I-10, 3.76 g (Yield: 76%). The formed compound was confirmed by LC-MS and NMR. $\text{C}_{33}\text{H}_{27}\text{BN}_2\text{O}_2$: M^+ 494.2

[0130] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.64 (d, 1H), 8.58 (d, 1H), 8.43-8.37 (m, 2H), 8.29 (d, 1H), 8.27-8.10 (m, 2H), 7.92 (d, 1H), 7.69-7.58 (m, 5H), 7.39-7.32 (m, 1H), 7.11-7.08 (m, 1H), 1.35 (s, 12H)

Synthesis Example 12


Synthesis of Compound 30


[0131] 2.37 g (Yield: 79%) of Compound 30 was obtained using Intermediate I-10 and 2-chloro-4,6-diphenyl-1,3,5-triazine in the same manner as in the method of synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{42}\text{H}_{25}\text{N}_5$: M^+ 599.2

[0132] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.69-8.64 (m, 5H), 8.57-8.49 (m, 2H), 8.39 (d, 1H), 8.25 (d, 1H), 8.18-8.10 (m, 3H), 7.82-7.66 (m, 5H), 7.45-7.32 (m, 7H), 7.10-7.05 (m, 1H)

Synthesis of Compound 39

[0133]





Synthesis Example 15


Synthesis of Compound 39

[0138] 2.12 g (Yield: 85%) of Compound 39 was obtained using Intermediate I-12 and 2-bromo-9,9-dimethyl fluorene in the same manner as the method of synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $C_{37}H_{26}N_2$: M^+ 498.2

[0139] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.03 (d, 1H), 8.67-8.62 (m, 2H), 8.50 (d, 1H), 8.18 (s, 1H), 8.15-7.98 (m, 3H), 7.90-7.81 (m, 2H), 7.71-7.65 (m, 2H), 7.52 (dd, 1H), 7.24-7.21 (m, 1H), 6.97-6.93 (m, 1H), 6.80-6.79 (m, 1H), 6.72-6.70 (m, 1H), 2.54 (s, 3H), 1.86 (s, 6H)

Synthesis of Compound 40

[0140]



Synthesis Example 13

Synthesis of Intermediate I-11

[0134] 5.21 g (Yield: 77%) of Intermediate I-11 was obtained using a pyrene boric acid and 2-bromo-5-methyl-3-nitropyridine in the same manner as the method of synthesizing Intermediate I-1. The formed compound was confirmed by LC-MS and NMR. $C_{22}H_{14}N_2O_2$: M^+ 338.1



[0135] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.46-8.45 (m, 1H), 8.33-8.32 (m, 1H), 8.27 (d, 1H), 8.23 (s, 1H), 8.19 (d, 1H), 8.09-8.02 (m, 5H), 7.98 (d, 1H), 2.43 (s, 3H)



Synthesis Example 14

Synthesis of Intermediate I-12

[0136] 2.42 g (Yield: 79%) of Intermediate I-12 was obtained using Intermediate I-11 and triphenyl phosphine in the same manner as the method of synthesizing Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. $C_{22}H_{14}N_2$: M^+ 306.1

[0137] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 10.97 (s, 1H), 9.13 (d, 1H), 8.70 (d, 1H), 8.58 (d, 1H), 8.45 (d, 1H), 8.17 (d, 1H), 8.08 (s, 1H), 8.02-8.00 (m, 2H), 7.90-7.86 (m, 1H), 7.65 (d, 1H), 2.56 (s, 3H)





Synthesis Example 16

Synthesis of Intermediate I-13

[0141] 10.17 g (25.0 mmol) of 1-bromo-6-iodopyrene, 2.44 g (20.0 mmol) of phenyl boric acid, 1.15 g (1.0 mmol) of

$\text{Pd}(\text{PPh}_3)_4$, and 8.29 g (60.0 mmol) of K_2CO_3 were dissolved in 60 mL of THF/ H_2O (2/1) mixed solution, and then stirred at a temperature of 70° C. for 5 hours. The solution was cooled to room temperature and then, 40 mL of water was added thereto and the resultant solution was extracted three times with 50 mL of ethyl ether. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography to obtain 3.78 g (Yield: 53%) of Intermediate I-13. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{22}\text{H}_{13}\text{Br}$: M^+ 356.0

[0142] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.84 (d, 1H), 8.32 (d, 1H), 7.99-7.89 (m, 4H), 7.78 (d, 1H), 7.54-7.49 (m, 2H), 7.48-7.43 (m, 1H), 7.37-7.33 (m, 2H)

Synthesis Example 17

Synthesis of Intermediate I-14

[0143] 3.57 g (10.0 mmol) of Intermediate I-13 was dissolved in 30 mL of THF and then, 4 mL (2.5M in Hexane, 10.0 mmol) of normal butyl lithium was slowly dropped thereto at a temperature of -78° C. Then, the mixture was stirred at the same temperature for 1 hour and then 4.61 mL (20.0 mmol) of $\text{B}(\text{O}i\text{Pr})_3$ was slowly dropped thereto. After the temperature of a reaction temperature was slowly raised for 3 hours until the temperature reached room temperature, 40 mL of water was added thereto and the resultant solution was extracted three times with 50 mL of ethyl ether. A collected organic layer was dried using magnesium sulfate, and the residual obtained by removing the used solvent therefrom by evaporation was separation purified by silica gel column chromatography to obtain 5.03 g (Yield: 78%) of Intermediate I-14. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{22}\text{H}_{15}\text{BO}_2$: M^+ 322.1

[0144] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.21 (d, 1H), 8.06-8.02 (m, 2H), 7.94-7.77 (m, 5H), 7.55-7.51 (m, 2H), 7.49-7.43 (m, 1H), 7.39-7.33 (m, 4H)

Synthesis Example 18

Synthesis of Intermediate I-15

[0145] 3.36 g (Yield: 81%) of Intermediate I-15 was obtained using Intermediate I-14 and 2-bromo-4-methyl-3-nitropyridine in the same manner as the method for synthesizing Intermediate I-1. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{28}\text{H}_{18}\text{N}_2\text{O}_2$: M^+ 414.1

[0146] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.43 (d, 1H), 8.33-8.28 (m, 2H), 8.15-8.05 (m, 3H), 7.89-7.84 (m, 2H), 7.78 (d, 1H), 7.55-7.51 (m, 2H), 7.47-7.42 (m, 1H), 7.37-7.32 (m, 2H), 7.14-7.11 (m, 1H), 2.41 (s, 3H)

Synthesis Example 19

Synthesis of Intermediate I-16

[0147] 2.98 g (Yield: 78%) of Intermediate I-16 was obtained using Intermediate I-15 and triphenyl phosphine in the same manner as the method for synthesizing Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. $\text{C}_{28}\text{H}_{18}\text{N}_2$: M^+ 382.1

[0148] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 10.61 (s, 1H), 8.75 (d, 1H), 8.54 (d, 1H), 8.38 (d, 1H), 8.13 (d, 1H), 8.05-

8.02 (m, 2H), 7.89 (d, 1H), 7.78 (d, 1H), 7.54-7.50 (m, 2H), 7.47-7.43 (m, 1H), 7.37-7.24 (m, 3H), 2.61 (s, 3H)

Synthesis Example 20



Synthesis of Compound 40

[0149] 2.77 g (Yield: 89%) of Compound 40 was obtained using Intermediate I-16 in the same manner as the method for synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $C_{46}H_{29}N_3$: M^+ 623.2


[0150] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.71 (d, 1H), 8.59 (d, 1H), 8.43 (d, 1H), 8.17 (d, 1H), 8.14 (s, 1H), 8.09 (d, 2H), 7.99 (d, 1H), 7.87-7.77 (m, 5H), 7.55-7.51 (m, 2H), 7.47-7.43 (m, 1H), 7.37-7.31 (m, 6H), 7.26-7.20 (m, 2H), 6.95-6.93 (m, 1H), 2.66 (s, 3H)

Synthesis of Compound 43


[0151]




I-17



I-18




I-19



I-20

I-21



43

Synthesis Example 21

Synthesis of Intermediate I-17

[0152] 2.67 g (Yield: 79%) of Intermediate I-17 was obtained using a pyrene boric acid and 2-bromo-6-methyl-3-nitropyridine in the same manner as the method for synthesizing Intermediate I-1. The formed compound was confirmed by LC-MS and NMR. $C_{22}H_{14}N_2O_2$: M^+ 338.1

[0153] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.55 (d, 1H), 8.27 (d, 1H), 8.20-8.16 (m, 2H), 8.11-8.02 (m, 5H), 7.98 (d, 1H), 7.22 (d, 1H), 2.52 (s, 3H)

Synthesis Example 22

Synthesis of Intermediate I-18

[0154] 12.21 g (Yield: 53%) of Intermediate I-18 was obtained using Intermediate I-17 in the same manner as the method for synthesizing Intermediate I-3. The formed compound was confirmed by LC-MS and NMR. $C_{22}H_{13}BrN_2O_2$: $M+ 416.0$

[0155] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.84 (d, 1H), 8.52 (d, 1H), 8.34 (d, 1H), 8.25-8.20 (m, 3H), 8.06 (d, 1H), 7.94 (d, 1H), 7.90 (d, 1H), 7.22 (d, 1H), 2.52 (s, 3H)

Synthesis Example 23

Synthesis of Intermediate I-19

[0156] 3.16 g (Yield: 82%) of Intermediate I-19 was obtained using Intermediate I-18 in the same manner as the method for synthesizing Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. $C_{22}H_{13}BrN_2$: $M+ 384.0$

[0157] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 11.21 (s, 1H), 8.76 (d, 1H), 8.63 (d, 1H), 8.49 (d, 1H), 8.39 (d, 1H), 8.12 (s, 1H), 8.06 (d, 1H), 7.98 (d, 1H), 7.66 (d, 1H), 7.17 (d, 1H), 2.64 (s, 3H)

Synthesis Example 24

Synthesis of Intermediate I-20

[0158] 4.34 g (Yield: 94%) of Intermediate I-20 was obtained using Intermediate I-19 and iodobenzene in the same manner as the method for synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $C_{28}H_{17}BrN_2$: $M+ 460.1$

[0159] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.82 (d, 1H), 8.73 (d, 1H), 8.53 (d, 1H), 8.35 (d, 1H), 8.25 (d, 1H), 8.11 (d, 1H), 7.86 (d, 1H), 7.81 (d, 1H), 7.63-7.55 (m, 4H), 7.39-7.32 (m, 1H), 7.02 (d, 1H), 2.63 (s, 3H)

Synthesis Example 25


Synthesis of Compound 43

[0160] 2.51 g (Yield: 80%) of Compound 43 was obtained using Intermediate I-20 and known Intermediate I-21 in the same manner as the method for synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{44}H_{29}N_5$: $M+ 627.2$

[0161] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.71 (d, 1H), 8.44 (d, 1H), 8.16-8.13 (m, 6H), 8.00-7.90 (m, 3H), 7.80 (d, 1H), 7.62-7.56 (m, 4H), 7.36-7.27 (m, 3H), 7.02 (d, 1H), 6.72 (dd, 4H), 6.65 (d, 2H), 2.61 (s, 3H)

Synthesis of Compound 52

[0162]



Synthesis Example 26

Synthesis of Intermediate I-22

[0163] 2.50 g (Yield: 77%) of Intermediate I-22 was obtained using a pyrene boric acid and 3-bromo-4-nitropyridine.

dine in the same manner as the method for synthesizing Intermediate I-1. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{12}N_2O_2$: $M+ 324.1$

[0164] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.56 (d, 1H), 8.50 (br-s, 1H), 8.40 (dd, 1H), 8.36 (d, 1H), 8.21 (d, 1H), 8.18 (s, 2H), 8.11-8.02 (m, 4H), 7.98 (d, 1H)

Synthesis Example 27

Synthesis of Intermediate I-23

[0165] 2.48 g (Yield: 85%) of Intermediate I-23 was obtained using Intermediate I-22 and triphenyl phosphine in the same manner as the method for synthesizing Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{12}N_2$: $M+ 292.1$

[0166] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 10.78 (s, 1H), 9.57 (s, 1H), 8.66 (d, 1H), 8.47-8.44 (m, 2H), 8.17 (d, 1H), 8.10 (s, 1H), 8.00 (dt, 2H), 7.90-7.86 (m, 2H), 7.42-7.38 (m, 1H)

Synthesis Example 28



Synthesis of Compound 52

[0167] 2.40 g (Yield: 90%) of Compound 52 was obtained using Intermediate I-23 in the same manner as the method for synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $C_{39}H_{23}N_3$: $M+ 533.2$

[0168] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.42 (s, 1H), 9.13 (d, 1H), 8.91 (d, 1H), 8.46 (d, 1H), 8.25-8.22 (m, 2H), 8.14-8.08 (m, 3H), 8.00-7.96 (m, 2H), 7.90-7.83 (m, 3H), 7.77-7.74 (m, 2H), 7.56 (dd, 1H), 7.37-7.33 (m, 4H), 7.25-7.20 (m, 2H)

Synthesis of Compound 58

[0169]



Synthesis Example 29

Synthesis of Intermediate I-24

[0170] 2.14 g (Yield: 53%) of Intermediate I-24 was obtained using Intermediate I-22 in the same manner as the method for synthesizing Intermediate I-3. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{11}BrN_2O_2$: $M+ 402.2$

[0171] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.85 (d, 1H), 8.58 (dd, 1H), 8.50 (s, 1H), 8.44-8.40 (m, 2H), 8.27-8.22 (m, 3H), 8.18 (d, 1H), 7.96 (d, 1H), 7.90 (d, 1H)

Synthesis Example 30

Synthesis of Intermediate I-25

[0172] 2.93 g (Yield: 79%) of Intermediate I-25 was obtained using Intermediate I-24 and triphenyl phosphine in

the same manner as the method for synthesizing Intermediate I-4. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{11}BrN_2$: $M+ 370.2$

[0173] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 10.65 (s, 1H), 9.58 (s, 1H), 8.97 (d, 1H), 8.84 (d, 1H), 8.57 (d, 1H), 8.46 (d, 1H), 8.37 (d, 1H), 8.15 (s, 1H), 7.97 (dt, 2H), 7.53 (d, 1H)

Synthesis Example 31

Synthesis of Intermediate I-26

[0174] 4.16 g (Yield: 93%) of Intermediate I-26 was obtained using Intermediate I-25 in the same manner as the method for synthesizing Intermediate I-5. The formed compound was confirmed by LC-MS and NMR. $C_{27}H_{15}BrN_2$: $M+ 446.0$

[0175] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.42 (s, 1H), 9.02 (d, 1H), 8.79 (d, 1H), 8.49 (d, 1H), 8.31 (d, 1H), 8.27-8.24 (m, 2H), 8.03-7.97 (m, 2H), 7.58-7.53 (m, 3H), 7.51-7.45 (m, 2H), 7.36-7.32 (m, 1H)

Synthesis Example 32

Synthesis of Compound 58

[0176] 2.21 g (Yield: 79%) of Compound 58 was obtained using Intermediate I-26 and 9,9-dimethyl-2-fluorene boric acid in the same manner as the method for synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{42}H_{28}N_2$: $M+ 560.2$

[0177] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.42 (s, 1H), 8.92 (d, 1H), 8.51 (d, 1H), 8.25 (d, 1H), 8.18 (s, 1H), 8.08 (d, 1H), 7.97 (d, 1H), 7.87 (d, 1H), 7.78 (d, 1H), 7.72 (d, 1H), 7.57-7.48 (m, 6H), 7.36-7.31 (m, 1H), 7.24-7.21 (m, 1H), 7.01-6.89 (m, 4H), 1.81 (s, 6H)

Synthesis of Compound 72

Synthesis Example 33

Synthesis of Compound 72

[0178] 2.30 g (Yield: 75%) of Compound 72 was obtained using Intermediate I-26 and Intermediate I-8 in the same manner as the method for synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{43}H_{27}N_5$: $M+ 613.2$

[0179] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.42 (d, 1H), 8.92 (d, 1H), 8.52 (d, 1H), 8.25-8.21 (m, 3H), 8.12 (s, 1H), 8.09 (d, 1H), 7.99 (d, 1H), 7.94-7.88 (m, 2H), 7.5-7.42 (m, 9H), 7.36-7.32 (m, 3H), 7.01-6.97 (m, 2H), 6.94-6.89 (m, 2H)

Synthesis of Compound 81

Synthesis Example 34

Synthesis of Compound 81





[0180] 2.51 g (Yield: 79%) of Compound 81 was obtained using Intermediate I-26 and Intermediate I-9 in the same manner as the method for synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{46}H_{28}N_4$: $M+ 636.2$

[0181] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.37 (s, 1H), 8.89 (d, 1H), 8.49 (d, 1H), 8.45 (d, 2H), 8.24 (dd, 1H), 8.17 (s,



1H), 8.09 (d, 1H), 7.99 (d, 1H), 7.89 (d, 1H), 7.76 (d, 1H), 7.61-7.43 (m, 11H), 7.37-7.28 (m, 3H), 7.16-7.12 (m, 1H), 6.97-6.93 (m, 2H)

Synthesis of Compound 107

[0182]



-continued



Synthesis Example 35

Synthesis of Intermediate I-27

[0183] 2.59 g (Yield: 80%) of Intermediate I-27 was obtained using a pyrene boric acid and 4-bromo-3-nitropyridine in the same manner as the method for synthesizing Intermediate I-1. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{12}N_2O_2$; M^+ 324.1

[0184] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.05 (d, 1H), 8.54 (d, 1H), 8.27 (d, 1H), 8.17-8.13 (m, 2H), 8.09-7.97 (m, 6H), 7.02 (dd, 1H)

Synthesis Example 36

Synthesis of Intermediate I-28

[0185] 2.02 g (Yield: 50%) of Intermediate I-28 was obtained using Intermediate I-3 in the same manner as the method for synthesizing Intermediate I-3. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{11}BrN_2O_2$; M^+ 402.0

[0186] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.05 (s, 1H), 8.84 (d, 1H), 8.54 (d, 1H), 8.33 (d, 1H), 8.24-8.18 (m, 3H), 8.05 (d, 1H), 7.95-7.89 (m, 2H), 7.04-7.02 (m, 1H)

Synthesis Example 37

Synthesis of Intermediate I-29

[0187] 3.01 g (Yield: 81%) of Intermediate I-29 was obtained using Intermediate I-28 and triphenyl phosphine in the same manner as the method for synthesizing Intermediate I-4. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{11}BrN_2$; M^+ 370.0

[0188] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 11.48 (s, 1H), 8.94 (d, 1H), 8.82 (d, 1H), 8.79 (s, 1H), 8.50 (d, 1H), 8.40-8.38 (m, 2H), 8.19 (s, 1H), 8.09 (d, 1H), 7.99-7.95 (m, 2H)

Synthesis Example 38

Synthesis of Intermediate I-30

[0189] 4.12 g (Yield: 92%) of Intermediate I-30 was obtained using Intermediate I-29 in the same manner as the method for synthesizing Intermediate I-5. The formed compound was confirmed by LC-MS and NMR. $C_{27}H_{15}BrN_2$; M^+ 446.0

[0190] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.98 (d, 1H), 8.84 (d, 1H), 8.76 (s, 1H), 8.47-8.44 (m, 2H), 8.34 (d, 1H), 8.27 (s, 1H), 8.03-7.97 (m, 2H), 7.84 (dd, 1H), 7.62-7.56 (m, 4H), 7.39-7.32 (m, 1H)

Synthesis Example 39


Synthesis of Compound 107

[0191] 2.59 g (Yield: 78%) of Compound 107 was obtained using Intermediate I-30 and Intermediate I-7 in the same manner as the method for synthesizing Compound 24. The formed compound was confirmed by LC-MS and NMR. $C_{45}H_{26}FN_3$; M^+ 665.2

[0192] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.88 (d, 1H), 8.76 (s, 1H), 8.46-8.41 (m, 2H), 8.19 (s, 1H), 8.09 (d, 1H), 7.97 (d, 1H), 7.95-7.81 (m, 3H), 7.64-7.52 (m, 5H), 7.37-7.30 (m, 5H), 6.87-6.84 (m, 1H), 6.72-6.70 (m, 2H), 6.64 (d, 1H), 6.41 (dd, 2H)

Synthesis of Compounds 110 and 111

[0193]



Synthesis Example 40

Synthesis of Intermediate I-31

[0194] 2.66 g (Yield: 91%) of Intermediate I-31 was obtained using Intermediate I-27 in the same manner as the method for synthesizing Intermediate I-2. The formed compound was confirmed by LC-MS and NMR. $C_{21}H_{12}N_2$: M^+ 292.1

[0195] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 11.29 (s, 1H), 9.13 (d, 1H), 8.87 (d, 1H), 8.73 (s, 1H), 8.44-8.39 (m, 2H), 8.18-8.14 (m, 2H), 8.09 (d, 1H), 8.02 (d, 1H), 7.94-7.86 (m, 2H)

Synthesis Example 41

Synthesis of Compound 110

[0196] 1.81 g (Yield: 69%) of Compound 110 was obtained using Intermediate I-31 and 2-chloro-4,6-diphenyl-1,3,5-triazine in the same manner as the method for synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $C_{36}H_{21}N_5$: M^+ 523.2

[0197] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.72 (s, 1H), 9.13 (d, 1H), 9.00 (s, 1H), 8.92 (d, 1H), 8.60-8.57 (m, 4H), 8.45 (d, 1H), 8.37 (d, 1H), 8.14 (d, 1H), 8.00-7.96 (m, 2H), 7.91-7.84 (m, 2H), 7.45-7.37 (m, 6H)

Synthesis Example 42

Synthesis of Compound 111

[0198] 1.85 g (Yield: 83%) of Compound 111 was obtained using Intermediate I-31 and known Intermediate I-32 in the same manner as the method for synthesizing Compound 7. The formed compound was confirmed by LC-MS and NMR. $C_{31}H_{18}N_4$: M^+ 446.2

[0199] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.17 (s, 1H), 9.13 (d, 1H), 8.93 (d, 1H), 8.61-8.58 (m, 3H), 8.44 (d, 1H), 8.37 (d, 1H), 8.13 (d, 1H), 8.00-7.76 (m, 8H), 7.70 (dd, 1H)

Example 1

[0200] As an anode, $15 \Omega/cm^2$ ($1200 \text{ \AA}$) ITO glass substrate manufactured by Corning Co., Ltd was cut to a size of $50 \text{ mm} \times 50 \text{ mm} \times 0.7 \text{ mm}$ and sonicated with isopropyl alcohol and pure water each for 5 minutes, and then ultraviolet rays

were irradiated thereto for 30 minutes, followed by exposure to ozone. Then, the resultant ITO glass substrate was installed in a vacuum deposition device. 2-TNATA was vacuum deposited on the ITO glass substrate to form a hole injection layer having a thickness of 600 Å, and 4,4'-bis[N-(1-naphthyl)-N-phenyl amino]biphenyl (NPB) was vacuum deposited on the hole injection layer to form a hole transport layer having a thickness of 600 Å.

[0201] Compound 7 as a blue fluorescent host and 1,4-bis(2,2-diphenyl vinyl)biphenyl (DPVBi) as a blue fluorescent dopant were co-deposited on the hole transport layer at a weight ratio of 98:2 to form an emission layer having a thickness of 300 Å.

[0202] Subsequently, Alq₃ was vacuum deposited on the emission layer to form an electron transport layer having a thickness of 300 Å. LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å and then, Al was vacuum deposited thereon to form an electrode having a thickness of 3000 Å, thereby forming a structure of LiF/Al electrodes, thereby completing the manufacture of an organic light-emitting diode.

Example 2

[0203] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using Compound 39 instead of Compound 7.

Example 3

[0204] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using Compound 40 instead of Compound 7.

Example 4

[0205] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the electron transport layer was formed using Compound 52 instead of Compound 7.

Example 5

[0206] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using Compound 58 instead of Compound 7.

Example 6

[0207] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using ADN instead of Compound 7 as the blue fluorescent host and Compound 24 instead of DPVBi as the blue fluorescent dopant.

Example 7

[0208] An organic light-emitting diode was manufactured in the same manner as in Example 6, except that the emission layer was formed using Compound 26 instead of Compound 24.

Example 8

[0209] An organic light-emitting diode was manufactured in the same manner as in Example 6, except that the emission layer was formed using Compound 27 instead of Compound 24.

Example 9

[0210] An organic light-emitting diode was manufactured in the same manner as in Example 6, except that the emission layer was formed using Compound 43 instead of Compound 24.

Example 10

[0211] An organic light-emitting diode was manufactured in the same manner as in Example 6, except that the emission layer was formed using Compound 72 instead of Compound 24.

Example 11

[0212] An organic light-emitting diode was manufactured in the same manner as in Example 6, except that the emission layer was formed using Compound 107 instead of Compound 24.

Example 12

[0213] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using ADN instead of Compound 7 as the blue fluorescent host and DPVBi as the blue fluorescent dopant, and the electron transport layer was formed using Compound 30 instead of Alq₃ on the emission layer.

Example 13

[0214] An organic light-emitting diode was manufactured in the same manner as in Example 12, except that the electron transport layer was formed using Compound 33 instead of Compound 30.

Example 14

[0215] An organic light-emitting diode was manufactured in the same manner as in Example 12, except that the electron transport layer was formed using Compound 81 instead of Compound 30.

Example 15

[0216] An organic light-emitting diode was manufactured in the same manner as in Example 12, except that the electron transport layer was formed using Compound 110 instead of Compound 30.

Example 16

[0217] An organic light-emitting diode was manufactured in the same manner as in Example 12, except that the electron transport layer was formed using Compound III instead of Compound 30.

Example 17

[0218] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using Compound 39 instead of Compound

7 as the blue fluorescent host and Compound 26 instead of DPVBi as the blue fluorescent dopant.

Example 18

[0219] An organic light-emitting diode was manufactured in the same manner as in Example 17, except that emission layer was formed using Compound 43 instead of Compound 26.

Example 19

[0220] An organic light-emitting diode was manufactured in the same manner as in Example 17, except that emission layer was formed using Compound 107 instead of Compound 26.

Example 20

[0221] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission

Comparative Example 1

[0223] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that the emission layer was formed using AND instead of Compound 7 as a blue fluorescent host.

Evaluation Example

[0224] Current density, driving voltage, brightness, luminescence efficiency, emission color, and half lifetime (a time for which brightness is decreased in half (50%) at a current density of 100 mA/cm²) of each of the organic light-emitting diodes manufactured according to Examples 1 to 21, and the organic light-emitting diode manufactured according to Comparative Example 1 were measured by using PR650 (Spectroscan) Source Measurement Unit (product of Photo-Research Co., Ltd), and results thereof are shown in Table 1 below.

TABLE 1

	Light-emitting material or electron transporting material	Driving voltage (V)	Current density (mA/cm ²)	Brightness (cd/m ²)	Luminescence efficiency (cd/A)	Emission color	Lifetime (h)
Example 1	Compound 7	6.85	50	2,355	4.71	blue	198
Example 2	Compound 39	6.73	50	2,445	4.89	blue	212
Example 3	Compound 40	6.76	50	2,390	4.78	blue	218
Example 4	Compound 52	6.89	50	2,315	4.63	blue	186
Example 5	Compound 58	6.91	50	2,260	4.52	blue	165
Example 6	Compound 24	7.81	50	2,490	4.98	blue-green	216
Example 7	Compound 26	7.78	50	2,625	5.25	blue	237
Example 8	Compound 27	7.68	50	2,635	5.27	blue	187
Example 9	Compound 43	7.81	50	2,615	5.23	blue	196
Example 10	Compound 72	7.76	50	2,535	5.07	blue	167
Example 11	Compound 107	7.80	50	2,565	5.13	blue	224
Example 12	Compound 30	5.71	50	2,355	4.71	blue	133
Example 13	Compound 33	6.02	50	2,335	4.67	blue	186
Example 14	Compound 81	6.23	50	2,325	4.65	blue	182
Example 15	Compound 110	5.65	50	2,415	4.83	blue	152
Example 16	Compound 111	5.83	50	2,395	4.79	blue	195
Example 17	Compound 39	6.57	50	3,230	6.46	blue	248
Example 18	Compound 26						
	Compound 39	6.62	50	3,135	6.27	blue	219
	Compound 43						
Example 19	Compound 39	6.62	50	3,065	6.13	blue	222
	Compound 107						
Example 20	Compound 39	5.62	50	3,360	6.72	blue	229
	Compound 26						
	Compound 33						
Example 21	Compound 39	5.65	50	3,475	6.95	blue	263
	Compound 26						
	Compound 111						
Comparative Example 1	DPVBi	7.85	50	1,560	3.12	blue	113

layer was formed using Compound 39 instead of Compound 7 as the blue fluorescent host and Compound 26 instead of DPVBi as the blue fluorescent dopant, and the electron transport layer was formed using Compound 33 instead of Alq₃ on the emission layer.

Example 21

[0222] An organic light-emitting diode was manufactured in the same manner as in Example 20, except that the electron transport layer was formed using Compound III instead of Compound 33.

[0225] Referring to Table 1 above, it may be seen that when the heterocyclic compound represented by Formula 1 was used as an emission layer material (host, dopant) or an electron transport layer material of an organic light-emitting diode, the driving voltage of the corresponding organic light-emitting diodes decreased by 1 V or more compared to when ADN, DPVBi, and Alq₃, which are known materials, were used. In addition, efficiency of the organic light-emitting diodes manufactured according to Examples 1 to 21 substantially increased.

[0226] For example, it may be seen that, in comparison with Comparative Example 1, the driving voltages of the organic

light-emitting diodes manufactured according to Examples 1 to 5 in which the heterocyclic compound represented by Formula 1 was used as a host decreased by 1 V, and efficiency and lifetime thereof also improved; efficiencies of the organic light-emitting diodes manufactured according to Examples 6 to 11 in which the heterocyclic compound represented by Formula 1 was used as a dopant increased by 150% or more, and lifetimes thereof also increased; the driving voltages of the organic light-emitting diodes manufactured according to Examples 12 to 16 in which the heterocyclic compound represented by Formula 1 was used as the electron transporting material decreased by 2 V or more. Also, the driving voltages of the organic light-emitting diodes manufactured according to Examples 17 to 21 in which the heterocyclic compound represented by Formula 1 was used as a host or dopant of an emission layer, or as a host or dopant of the emission layer and an electron transporting material decreased by 2 V compared to Comparative Example 1, and efficiency thereof increased by about 200% and lifetime thereof increased by 100% or more.


[0227] From the results described above, it may be seen that a light-emitting diode including the heterocyclic compound represented by Formula 1 device has a low driving voltage, high luminescence efficiency, and long lifetime.

[0228] The heterocyclic compound represented by Formula 1 may have excellent emission characteristics and charge transport characteristics. An organic light-emitting diode including the heterocyclic compound represented by Formula 1 may have a low driving voltage, high luminescence efficiency, and long lifetime, and thus a flat display device including the organic light-emitting diode has an excellent performance.

[0229] While the present invention has been particularly shown, and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form, and details may be made therein without departing from the spirit, and scope of the present invention as defined by the following claims.

What is claimed is:

1. A heterocyclic compound represented by Formula 1 below:



wherein:





A₁ is a substituted or unsubstituted fused pyridine cycle, R₁ to R₉ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group, a substituted or

unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cycloalkyl group, a substituted or unsubstituted C₃-C₃₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, a substituted or unsubstituted C₃-C₃₀ hetero aryl group, or a group represented by N(Q₁)(Q₂), wherein Q₁ and Q₂ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cycloalkyl group, a substituted or unsubstituted C₃-C₃₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, or a substituted or unsubstituted C₃-C₃₀ hetero aryl group,

L₁ and L₂ are each independently a substituted or unsubstituted C₆-C₃₀ arylene group or a substituted or unsubstituted C₃-C₃₀ heteroarylene group, and

a and b are each independently an integer of 0 to 3.

2. The heterocyclic compound as claimed in claim 1, wherein A₁ is a group represented by one of Formulae 2A to 2D, below:



wherein:


R₁₀ is independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, an amino group, a nitro group, a carboxyl group, a substituted or unsubstituted C₁-C₃₀ alkyl group, a substituted or unsubstituted C₂-C₃₀ alkenyl group, a substituted or unsubstituted C₂-C₃₀ alkynyl group, a substituted or unsubstituted C₁-C₃₀ alkoxy group, a substituted or unsubstituted C₃-C₃₀ cycloalkyl group, a substituted or

unsubstituted C₃-C₃₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, or a substituted or unsubstituted C₃-C₃₀ hetero aryl group,


p is an integer from 1 to 3, and

* and *¹ are sites for fusing.


3. The heterocyclic compound as claimed in claim 1, wherein A₁ is a group represented by one of Formulae 3A to 3P, below:




<Formula 3A>




<Formula 3B>




<Formula 3C>




<Formula 3D>




<Formula 3E>



<Formula 3F>




<Formula 3G>




<Formula 3H>


-continued




<Formula 3I>




<Formula 3J>




<Formula 3K>




<Formula 3L>




<Formula 3M>



<Formula 3N>



<Formula 3O>



<Formula 3P>

wherein * and *¹ are sites for fusing.


4. The heterocyclic compound as claimed in claim 1, wherein R₁ to R₉ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, a carboxyl group, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted pentyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted non-phenyl group, a substituted or unsubstituted pentalenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted azulenylyl

R_2 , R_3 , R_4 , R_6 , R_7 , R_8 , and R_9 are each independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, or a substituted or unsubstituted pentyl.


7. The heterocyclic compound as claimed in claim 1, wherein:

R_2 , R_3 , R_4 , R_6 , R_7 , R_8 , and R_9 are hydrogen atoms,


R_1 and R_5 are each independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted isobutyl group, or a group represented by one of Formulae 4A to 4V, below:




<Formula 4A>




<Formula 4B>




<Formula 4C>




<Formula 4D>



<Formula 4E>




<Formula 4F>




<Formula 4G>


-continued




<Formula 4H>




<Formula 4I>




<Formula 4J>




<Formula 4K>




<Formula 4L>




<Formula 4M>



<Formula 4N>




<Formula 4O>




<Formula 4P>


-continued




<Formula 4Q>




<Formula 4R>




<Formula 4S>



<Formula 4T>



<Formula 4U>



<Formula 4V>

Z₁, Z₂, Z₃, Z₄, and Z₅ are each independently a hydrogen atom, a deuterium atom, a halogen atom, a hydroxy group, a cyano group, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, q is an integer of 1 to 5,


r and u are each independently an integer of 1 to 4, s and x are each independently an integer of 1 to 3, v is an integer of 1 or 2, and * represents a binding site.

8. The heterocyclic compound as claimed in claim 1, wherein L₁ and L₂ are each independently a substituted or unsubstituted phenylene group, a substituted or unsubstituted naphthylene group, a substituted or unsubstituted anthrylene


group, a substituted or unsubstituted phenanthrenylene group, a substituted or unsubstituted pyrenylene group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, a substituted or unsubstituted methoxy group, a substituted or unsubstituted ethoxy group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted anthryl group, or a substituted or unsubstituted pyridinyl group, substituted or unsubstituted chrysenylene group, a substituted or unsubstituted perylenylene group, a substituted or unsubstituted fluorenylene group, a substituted or unsubstituted spiro-fluorenyl group, a substituted or unsubstituted carbazolyne group, a substituted or unsubstituted pyridinylene group, or a substituted or unsubstituted oxadiazolylene group.

9. The heterocyclic compound as claimed in claim 1, wherein:


L₁ and L₂ are each independently a group represented by one of Formulae 5A to 5G below:




<Formula 5A>




<Formula 5B>




<Formula 5C>




<Formula 5D>



<Formula 5E>



<Formula 5F>



<Formula 5G>

Z_6 , Z_7 , and Z_8 are each independently a hydrogen atom, a deuterium atom, a halogen atom, a substituted or unsubstituted methyl group, a substituted or unsubstituted ethyl group, a substituted or unsubstituted propyl group, a substituted or unsubstituted butyl group, or a substituted or unsubstituted phenyl,

r' and u' are each independently an integer of 1 to 4,

s' is an integer of 1 to 3,

v' and y' are each independently an integer of 1 to 2,


and * and *' each represent a binding site.

10. The heterocyclic compound as claimed in claim 1, wherein a and b are each independently an integer of 0 or 1.


11. The heterocyclic compound as claimed in claim 1, wherein the heterocyclic compound represented by Formula 1 is represented by one of the following Compounds 7, 24, 26, 27, 30, 33, 39, 40, 43, 52, 58, 72, 81, 107, 110, and 111:

-continued


26




7



27




24




-continued

30




-continued


40




33




43



39



-continued



52

12. An organic light-emitting diode, comprising:
a first electrode;
a second electrode facing the first electrode; and
a first layer between the first electrode and the second electrode, the first layer including the heterocyclic compound as claimed in claim 1 alone or in a mixed form with other materials.

13. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes at least one layer selected from the group of a hole injection layer, a hole transport layer, a functional layer having a hole injection function and a hole transportation function, an electron blocking layer, an emission layer, a hole blocking layer, an electron transport layer, an electron injection layer, and a functional layer having an electron transportation function and an electron injection function.

14. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes an emission layer, the emission layer including at least one selected from the group of a fluorescent host, a phosphorescent host, a fluorescent dopant, and a phosphorescent dopant.

58

15. The organic light-emitting diode as claimed in claim 14, wherein:

- the emission layer includes the heterocyclic compound, and
- i) the fluorescent host includes the heterocyclic compound,
- ii) the fluorescent dopant includes the heterocyclic compound, or
- iii) the fluorescent host and the fluorescent dopant each include the heterocyclic compound.

16. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes an emission layer, the emission layer including at least one selected from the group of an anthracene-based compound, an arylamine-based compound, and a styryl-based compound.

17. The organic light-emitting diode as claimed in claim 16, wherein the emission layer includes the heterocyclic compound.

72

18. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes an electron transport layer, the electron transport layer including the heterocyclic compound.

19. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes an electron transport layer, the electron transport layer including a metal-containing compound.

20. The organic light-emitting diode as claimed in claim 19, wherein the metal-containing compound includes a lithium (Li) complex.

21. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes an emission layer and an electron transport layer, each of the emission layer and the electron transport layer including the heterocyclic compound.

22. The organic light-emitting diode as claimed in claim 12, wherein the first layer includes at least one layer selected from the group of a hole injection layer, a hole transport layer, and a functional layer having a hole injection function and a hole transportation function, the at least one layer selected from the group of the hole injection layer, the hole transport layer, and the functional layer having a hole injection function and a hole transportation function further including a charge generation material.

23. A flat display device, comprising:
a transistor including a source, a drain, a gate, and an active
layer; and
the organic light-emitting diode as claimed in claim **12**,

wherein the source or the drain is electrically connected to
the first electrode of the organic light-emitting diode.

* * * * *

专利名称(译)	杂环化合物和有机发光二极管以及包含该杂环化合物的平板显示装置		
公开(公告)号	US20120326134A1	公开(公告)日	2012-12-27
申请号	US13/311770	申请日	2011-12-06
[标]申请(专利权)人(译)	金荣KOOK HWANG SEOK HWAN JUNG HYE JIN LIM JINØ 韩相HYUN KWAK YOON HYUN LEE YOUNG SUN KO HEE JOO 李钟赫 金圣CHUL		
申请(专利权)人(译)	金荣KOOK HWANG SEOK-HWAN JUNG HYE-JIN LIM JIN-O 韩相铉 KWAK YOON-HYUN LEE SUN-YOUNG KO HEE JOO 李钟赫 金成哲		
当前申请(专利权)人(译)	金荣KOOK HWANG SEOK-HWAN JUNG HYE-JIN LIM JIN-O 韩相铉 KWAK YOON-HYUN LEE SUN-YOUNG KO HEE JOO 李钟赫 金成哲		
[标]发明人	KIM YOUNG KOOK HWANG SEOK HWAN JUNG HYE JIN LIM JIN O HAN SANG HYUN KWAK YOON HYUN LEE SUN YOUNG KO HEE JOO LEE JONG HYUK KIM SUNG CHUL		
发明人	KIM, YOUNG-KOOK HWANG, SEOK-HWAN JUNG, HYE-JIN LIM, JIN-O HAN, SANG-HYUN		

KWAK, YOON-HYUN
LEE, SUN-YOUNG
KO, HEE-JOO
LEE, JONG-HYUK
KIM, SUNG-CHUL

IPC分类号	H01L51/54 C07D487/04 C07D471/04
CPC分类号	C07D471/04 H01L51/0059 H01L51/0061 H01L51/5016 H01L51/0072 H01L51/0081 H01L51/0067
优先权	1020110060806 2011-06-22 KR
其他公开文献	US8623521
外部链接	Espacenet USPTO

摘要(译)

杂环化合物，有机发光二极管和平板显示装置，该杂环化合物由下式1表示：

