



US 20180006270A1

(19) **United States**(12) **Patent Application Publication**
YI et al.(10) **Pub. No.: US 2018/0006270 A1**(43) **Pub. Date: Jan. 4, 2018**(54) **ORGANIC LIGHT EMITTING DIODES
DISPLAYS AND MANUFACTURING
METHOD THEREOF****Publication Classification**(51) **Int. Cl.***H01L 51/52* (2006.01)*H01L 51/00* (2006.01)*H01L 51/56* (2006.01)*H01L 27/32* (2006.01)(52) **U.S. Cl.**CPC *H01L 51/5253* (2013.01); *H01L 51/56*(2013.01); *H01L 51/0097* (2013.01); *H01L**51/5281* (2013.01); *H01L 51/5293* (2013.01);*H01L 27/3244* (2013.01); *H01L 2227/323*(2013.01); *H01L 2251/5338* (2013.01); *H01L**2251/566* (2013.01)(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-Si
(KR)(72) Inventors: **Chung YI**, Yongin-City (KR);
Sang-Hun OH, Yongin-City (KR)(21) Appl. No.: **15/708,259**(22) Filed: **Sep. 19, 2017****Related U.S. Application Data**(63) Continuation of application No. 15/260,093, filed on
Sep. 8, 2016, now Pat. No. 9,806,290, which is a
continuation of application No. 14/106,434, filed on
Dec. 13, 2013, now Pat. No. 9,461,267.**Foreign Application Priority Data**

Jun. 3, 2013 (KR) 10-2013-0063509

(57)

ABSTRACT

A cracks propagation preventing, polarization film attaches to outer edges of a lower inorganic layer of an organic light emitting diodes display where the display is formed on a flexible substrate having the lower inorganic layer blanket formed thereon. The organic light emitting diodes display further includes a display unit positioned on the inorganic layer and including a plurality of organic light emitting diodes configured to display an image, and a thin film encapsulating layer covering the display unit and joining with edges of the inorganic layer extending beyond the display unit.


100

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9





FIG. 10



ORGANIC LIGHT EMITTING DIODES DISPLAYS AND MANUFACTURING METHOD THEREOF

RELATED APPLICATIONS

[0001] This application is a continuation of Ser. No. 15/260,093 filed on Sep. 8, 2016 which is a continuation application of U.S. patent application Ser. No. 14/106,434 filed on Dec. 13, 2013, which claims priority to and the benefit of Korean Patent Application No. 10-2013-0063509 filed in the Korean Intellectual Property Office on Jun. 3, 2013, the entire contents of which application are incorporated herein by reference.

BACKGROUND

1. Field of Disclosure

[0002] The here described technology relates generally to an organic light emitting diodes display (OLED), and more particularly, to an organic light emitting diodes display having a planarization film, and a manufacturing method thereof.

2. Description of Related Technology

[0003] In an organic light emitting diodes display, a pixel circuit and an organic light emitting diode (OLED) are disposed at every pixel area on a substrate, and light emitted from the plurality of organic light emitting diodes is combined to display an image. If the organic light emitting diodes display uses a polymer film as its substrate it may have a bending characteristic. In such a case it includes a flexible thin film encapsulating layer to encapsulate the organic light emitting diodes. The flexible thin film encapsulating layer is susceptible to cracking when exposed to external impacts.

[0004] During mass production fabrication, the pixel circuits, the organic light emitting diodes, and various wirings may be simultaneously formed while forming a plurality of display panels (referred to as unit cells) on a mother substrate, and then the monolithically integrated display panels are separated into individual unit cells by cutting the mother substrate. In this case, each unit cell is divided into a display area in which the pixel circuits and the organic light emitting diodes are positioned, and into a pad area in which pad electrodes are positioned.

[0005] Particularly, in one mass production method of manufacturing the organic light emitting diodes display, the process may include the steps of (1) forming the plurality of unit cells on the mother substrate, (2) forming the thin film encapsulating layer on the display area of each unit cell, (3) attaching a passivation film to an entire upper portion of the mother substrate, (4) separating the mother substrate into the individual unit cells by cutting the mother substrate, (5) removing a portion of the passivation film corresponding to the pad area; (6) performing an examination after removing the portion corresponding to the pad area in the passivation film, (7) removing the passivation film of the unit cells that are determined from the examination to be non-defective product and (8) attaching a polarization film to such non-defective product.

[0006] The aforementioned organic light emitting diodes display has a very complicated manufacturing process, and thus is difficult to mass produce with consistency and

minimized defects. Further, in the process, a partial area of an inorganic layer (a barrier layer, a buffer layer, and the like) formed on the substrate may not be covered with the thin film encapsulating layer and the polarization film and thus it is exposed. When an external impact is applied to the exposed inorganic layer, cracks can easily occur, and the cracks are propagated into the display panel, thereby causing a contagious defect that can spread across the organic light emitting diodes displays of the mother substrate.

[0007] It is to be understood that this background of the technology section is intended to provide useful background for understanding the here disclosed technology and as such, the technology background section may include ideas, concepts or recognitions that were not part of what was known or appreciated by those skilled in the pertinent art prior to corresponding invention dates of subject matter disclosed herein.

SUMMARY

[0008] The described technology has been made in an effort to provide an organic light emitting diodes display capable of simplifying a manufacturing process and preventing a contagiously spread defect by suppressing an occurrence of cracks due to an exposure of an inorganic layer to crack inducing impacts.

[0009] A cracks propagation preventing, polarization film attaches to outer edges of a lower inorganic layer of an organic light emitting diodes display where the display is formed on a flexible substrate having the lower inorganic layer blanket formed thereon. The organic light emitting diodes display further includes a display unit positioned on and within an interior area of the inorganic layer and including a plurality of organic light emitting diodes configured to display an image, and a thin film encapsulating layer covering the display unit and joining with exterior edges of the inorganic layer that extend beyond the display unit.

[0010] More specifically, an exemplary organic light emitting diodes display, includes a flexible substrate, an inorganic layer formed on an entire upper surface of the substrate, a display unit positioned on and in an interior portion of the inorganic layer and including a plurality of organic light emitting diodes to display an image, a thin film encapsulating layer fully covering the display unit and extending to attach to outer edges of the inorganic layer, and a polarization film attached to and fully covering the thin film encapsulating layer and extending to attach to yet further outer edges of the inorganic layer that are at an exterior side of the thin film encapsulating layer.

[0011] A pads area may be positioned at an exterior side of the display unit on the substrate, and the polarization film may be attached on the entire remaining areas over the substrate, except for the pads area which is exposed to allow for electrical testing. The polarization film may include one edge, which is in contact with the pads area, and three edges, which are matched with edges of the substrate. The substrate may be formed of a polymer film, and the inorganic layer may include at least one of a barrier layer and a buffer layer.

[0012] The disclosure provides a method of manufacturing an organic light emitting diodes display, including forming an inorganic layer to fully cover a flexible mother substrate, forming a plurality of spaced apart display units on the inorganic layer so as to form a matrix of unit cells, forming spaced apart thin film encapsulating layers at upper

portions of the corresponding matrix of display units, respectively, attaching a polarization film exposed portions of the inorganic layer so as to also thereby fully cover the plurality of thin film encapsulating layers (while leaving exposed the pads areas so as to allow for electrical testing of the plural pads areas); and separating the plurality of unit cells into individual unit cells by cutting the mother substrate and the polarization film.

[0013] The flexible mother substrate may be formed of a polymer film, and each of the plurality of unit cells may include a pads area at an exterior side of the display unit. The plurality of unit cells may be disposed as rows extending in two directions crossing each other, and each of the plurality of display units and the plurality of pad areas may be disposed in a row in one direction between the two directions.

[0014] The polarization films having the same number as that of the mother substrates may be provided, and may be provided with openings through which the plurality of pads areas is exposed. The polarization films may be provided with slit-shaped openings parallel to the one direction to simultaneously expose the plurality of pad areas positioned in the one direction. One row of pad areas among the plurality of pad areas may be positioned at an exterior side of one side edge of the polarization film.

[0015] In the meantime, the polarization films may be formed in rod shapes parallel to the one direction to cover one row of thin film encapsulating layers positioned in parallel to the one direction among the plurality of thin film encapsulating layers. The one side edge of the polarization film may be in contact with a boundary of the pad area toward the display unit, and an opposite side edge may be positioned at an exterior side of the edge of the thin film encapsulating layer.

[0016] The polarization film in the individual unit cells may be positioned on the thin film encapsulating layer and in contact with the outer edges of the inorganic layer that extend beyond the exterior sides of the thin film encapsulating layer.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] FIG. 1 is a perspective view of an organic light emitting diodes display according to an exemplary embodiment.

[0018] FIG. 2 is a cross-sectional view of the organic light emitting diodes display taken along line A-A of FIG. 1.

[0019] FIG. 3 is an enlarged cross-sectional view of a display unit and a thin film encapsulating layer illustrated in FIG. 2.

[0020] FIG. 4 is a process flowchart illustrating a method of manufacturing the organic light emitting diodes display according to an exemplary embodiment.

[0021] FIGS. 5, 6, and 7 are perspective views illustrating a mother substrate with plural ones of the organic light emitting diodes displays in the second step, the third step, and the fourth step illustrated in FIG. 4, respectively.

[0022] FIG. 8 is a perspective view illustrating a first exemplary variation of a polarization film illustrated in FIG. 7.

[0023] FIG. 9 is a perspective view illustrating a second exemplary variation of the polarization film illustrated in FIG. 7.

[0024] FIG. 10 is a top plan view illustrating the organic light emitting diodes displays in the fifth step illustrated in FIG. 4.

DETAILED DESCRIPTION

[0025] The present disclosure of invention will be described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments are shown. As those skilled in the art would realize in light of this disclosure, the described embodiments may be modified in various different ways, all without departing from the spirit or scope of the present teachings.

[0026] Unless explicitly described to the contrary, the word “comprise” and variations such as “comprises” or “comprising”, will be understood to imply the inclusion of stated elements but not the exclusion of any other elements. Further, it will be understood that when an element such as a layer, film, region, or substrate is referred to as being “on” another element, it can be directly on the other element or intervening elements may also be present. Further, in the specification, the word “on” means positioning on or below the object portion, but does not essentially mean positioning on the upper side of the object portion based on a gravity direction.

[0027] FIG. 1 is a perspective view of an organic light emitting diodes display according to an exemplary embodiment. FIG. 2 is a cross-sectional view of the organic light emitting diodes display taken along line A-A of FIG. 1.

[0028] Referring to FIGS. 1 and 2, an organic light emitting diodes display 100 includes a substrate 10, and a display unit 20, a thin film encapsulating layer 30, and a polarization film 40 which are formed on the substrate 10 substantially in the recited order.

[0029] The substrate 10, which is a flexible film, may be formed of a transparent or opaque polymer film (for example, polyimide). The substrate 10 is subdivided into a display area DA and a pads area PA. The pads area PA is in contact with an edge of one side of the substrate 10, and with wirings extending into the display area DA. The pads area PA is positioned so as to leave a predetermined distance from the edge of the substrate 10 to the remaining areas of the substrate 10, except for the pad area PA.

[0030] The display unit 20 includes a plurality of organic light emitting diodes and a plurality of pixel circuits that are positioned in the display area DA. At least one organic light emitting diode (OLED) and a corresponding pixel circuit are provided for each pixel. The display unit 20 displays an image by combining lights emitted from the plurality of organic light emitting diodes.

[0031] Pad electrodes 11 are connected by way of integrally extending conductors to the respective pixel circuits of the display unit 20. The pad electrodes 11 are positioned in the pads area PA. In one embodiment, the pad electrodes 11 are not only connected to the circuitry under the encapsulating layer 30 but also to external further circuitry such as a chip on film control circuit and/or an external printed circuit board, which are not illustrated. In other words, the pad electrodes 11 receive control and/or data signals from the external further circuitry for use in driving the pixels of the display area 20 (DA). Alternatively or additionally, one or more on-board integrated circuit chips (not illustrated) may be positioned in the pads area PA for serving as scan

line drivers and/or data line drivers that respectively drive plural scan lines and plural data lines provided under the encapsulating layer 30.

[0032] It is to be observed that in the cross sectional view of FIG. 2, the thin film encapsulating layer 30 joins directly at its ends with an underlying inorganic layer 18 so as to thereby fully and protectively encapsulate the display unit 20.

[0033] FIG. 3 is an enlarged cross-sectional view of the display unit 20, the thin film encapsulating layer 30 and the inorganic layer 18 where the inorganic layer is comprised of sublayers 12 and 13 (also referred to herein as layers 12 and 13).

[0034] Referring to FIG. 3, sublayer 12 serves as a barrier layer 12 and sublayer 13 serves as a buffer layer 13. These thin film sublayers, 12 and 13 are deposited on the entire upper surface of the flexible substrate 10 and are configured to flex with the flexible substrate 10. The barrier layer 12 includes a plurality of different and relatively thin inorganic layers, and may be formed in a structure in which, for example, an SiO₂ layer and an SiNx layer are alternately and repeatedly stacked so as to provide flexibility and impermeability to oxygen and/or other corrosive materials (e.g., H₂O). The barrier layer 12 has a substantially smaller moisture transmission rate and a substantially smaller oxygen transmission rate than those of the polymer substrate 10. Thus the barrier layer 12 inhibits or prevents moisture and oxygen that permeates through the flexible polymer substrate 10 from further permeating inwardly so as to damage the pixel circuits and their corresponding organic light emitting diodes 50.

[0035] The buffer layer 13 is also formed of an inorganic layer, and may include, for example, a planarized SiO₂ or SiNx layer. The buffer layer 13 provides a flat dielectric surface for forming thereon the pixel circuit, and it also suppresses moisture and foreign substances from permeating inwardly to attack the pixel circuits and their corresponding organic light emitting diodes 50.

[0036] One or more thin film transistors such as the exemplary TFT 60 and one or more capacitors such as the exemplary Cst 70 are provided as encapsulated between the thin film encapsulating layer 30 and the inorganic layer 18 (comprised of sublayers 12 and 13) for forming a corresponding pixel circuit.

[0037] The thin film transistor 60 includes a semiconductive layer 61, a gate electrode 62, and source/drain electrodes 63 and 64. The semiconductive layer 61 may be formed of one of a polysilicon or of a semiconductive oxide, and it includes a channel area 611 in which an impurity is not heavily doped, and source/drain areas 612 and 613 in which one or more conductivity providing impurities are doped at both sides of the channel area 611. When the semiconductive layer 61 is formed of the semiconductive oxide, a separate passivation layer (not shown) for protecting the semiconductive layer 61 may be added.

[0038] A gate insulating layer 14 is positioned between the semiconductive layer 61 and the gate electrode 62, and an interlayer insulating layer 15 is positioned between the gate electrode 62 and the source/drain electrodes 63 and 64. The gate insulating layer 14 and the interlayer insulating layer 15 may be formed of an organic material or an inorganic material, such as SiO₂ and SiNx.

[0039] The capacitor 70 includes a first plate capacitor 71 formed on the gate insulating layer 14, and a second plate

capacitor 72 formed on the interlayer insulating layer 15. The first plate capacitor 71 may be formed of the same material as that of the gate electrode 62, and the second plate capacitor 72 may be formed of the same material as those of the source/drain electrodes 63 and 64. The second plate capacitor 72 may be connected with the source electrode 63. [0040] The thin film transistor 60 illustrated in FIG. 3 functions as an OLED driving film transistor. Although not shown, and the pixel circuit may further include a switching thin film transistor for selectively coupling a signal on an adjacent data line to the OLED driving transistor 60. In other words, the switching thin film transistor is used as a switching element for selecting a pixel that is desired to be made to emit a certain predetermined magnitude of light, and the driving thin film transistor applies power for making the OLED 50 of the selected pixel emit that predetermined magnitude of light.

[0041] A planarizing layer 16 is positioned on the source/drain electrodes 63 and 64 and the second plate capacitor 72. The planarizing layer 16 is formed of an organic material or an inorganic material, or a complex form of an organic material and an inorganic material. An acryl-based resin, an epoxy resin, a phenol resin, a polyamide-based resin and the like may be used as the organic material. The planarizing layer 16 is provided with a via hole through which a part of the drain electrode 64 communicates to connect with the organic light emitting diode 50 that is formed on the planarizing layer 16.

[0042] The organic light emitting diode (OLED) 50 includes a pixel electrode 51, an organic emission layer 52, and a common electrode 53. The pixel electrode 51 is individually formed at each pixel, and is connected with the drain electrode 64 of the thin film transistor 60 through the via hole. The common electrode 53 is formed of a light-passing material (e.g., ITO) and extends over the entire display area DA. A pixel bordering/defining layer 17 is positioned on the pixel electrode 51. The pixel defining layer 17 is provided with an opening through which the pixel electrode 51 is exposed, and the organic emission layer 52 is formed at the opening to be in contact with the pixel electrode 51. The pixel defining layer 17 may be formed of an opaque material.

[0043] The organic emission layer 52 may be any one of a red emission layer, a green emission layer, and a blue emission layer. On the other hand, the organic emission layer 52 may be a white emission layer, or a stacked layer of the red emission layer, the green emission layer, and the blue emission layer. In a latter case, the organic light emitting diodes display 100 may further include one or more color filters (not illustrated). The color filters may include a red filter corresponding to a red pixel, a green filter corresponding to a green pixel, and a blue filter corresponding to a blue pixel.

[0044] One of the pixel electrode 51 and the common electrode 53 serves as an anode which is a hole injection electrode, and the other serves as a cathode which is an electron injection electrode. Holes injected from the anode and electrons injected from the cathode are combined in the organic emission layer 52 to generate photons and thus light emission is performed when paired combinations (excitons) of combining holes and electrons join and discharge their combined energy.

[0045] At least one of a hole injection layer and a hole transport layer may be positioned between the anode and the

organic emission layer **52**, and at least one of an electron injection layer and an electron transport layer may be positioned between the organic emission layer **52** and the cathode. The hole injection layer, the hole transport layer, the electron transport layer, and the electron injection layer may be formed on the entire display area DA without distinction as to which pixel they belong to.

[0046] The pixel electrode **51** may be a reflective electrode, while the common electrode **53** is a transfective (and thus resonance creating) or a transmissive electrode. The pixel electrode **51** may be a single layer or a multilayer containing at least one of aluminum (Al), gold (Au), silver (Ag), magnesium (Mg), lithium (Li), and calcium (Ca). The common electrode **53** may contain any one of an indium-tin oxide (ITO), an indium-zinc oxide (IZO), a zinc oxide (ZnO), and an indium oxide (In_2O_3).

[0047] Light emitted from the organic emission layer **52** is reflected from the pixel electrode **51**, penetrates the common electrode **53**, and then is discharged to the outside for perception by a user. In a case where the common electrode **53** is the transfective type, some of the light rays are reflected to the pixel electrode **51** from the common electrode **53** again to thereby form a resonant optics structure.

[0048] The thin film encapsulating layer **30** is positioned on the plurality of organic light emitting diodes **50**. The thin film encapsulating layer **30** encapsulates the organic light emitting diodes **50** from an external environment containing moisture and oxygen to suppress deterioration in the organic light emitting diodes **50** due to exposure to moisture and/or oxygen. The thin film encapsulating layer **30** may be formed of a configuration in which a plurality of organic layers and a plurality of inorganic layers are alternately stacked one by one so as to provide flexibility.

[0049] The organic layer of the thin film encapsulating layer **30** is formed of polymer, and may be a single layer or a stacked layer formed of any one of, for example, polyethyleneterephthalate, polyimide, polycarbonate, epoxy, polyethylene, and polyacrylate. The inorganic layer of the thin film encapsulating layer **30** may be a single layer or a stacked layer containing a silicon oxide or a silicon nitride, a metal oxide or a metal nitride. For example, the inorganic layer may contain any one of SiNx , Al_2O_3 , SiO_2 , and TiO_2 .

[0050] Referring to FIGS. 1 to 4, a polarization film **40** is attached on an exterior surface of the thin film encapsulating layer **30**, and suppresses external light reflection which might be induced by nonplanar structures within the display area (DA), thereby improving visibility of the display unit **20**.

[0051] To reiterate, the inorganic layer **18** (see FIGS. 1 and 2) on the substrate **10** is formed on the entire upper surface of the substrate **10** to have the same width as that of the substrate **10**. In this case, the inorganic layer **17** includes at least one of the aforementioned barrier layer **12** and buffer layer **13**. The display unit **20** is disposed to be spaced apart from the edge of the substrate **10** toward an inner side of the substrate **10**. The thin film encapsulating layer **30** is formed to have a larger area than that of the display unit **20** and to thus; in combination with the inorganic layer **18** (i.e. layers **12-13**) encapsulate the display unit **20**. The thin film encapsulating layer **30** is also disposed to be spaced apart from the edge of the substrate **10** toward the inner side of the substrate **10**.

[0052] Additionally, the polarization film **40** is formed on the entire remaining areas of the substrate **10**, except for the

pad area PA. That is, the polarization film **40** is formed to have the same size as those of the remaining areas of the substrate **10**, except for the pad area PA. In other words, three edges except for one edge of the four-edged polarization film **40** (where the one exception is the edge which is in contact with the pad area PA) are matched with the edges of the substrate **10** after the display cell unit is separated from its mother substrate. Accordingly, the inorganic layer **18** at an exterior side of the display unit **20** is covered with the polarization film **40** in the remaining areas of the substrate **10**, except for the pad area PA, so that the inorganic layer **18** is not exposed to scratching or crack-inducing impacts from the outside.

[0053] The polarization film **40** covers and protects the inorganic layer **18** of the exterior side of the display unit **20**, thereby blocking most of the external impact applied to the inorganic layer **18** in a process of manufacturing the organic light emitting diodes display **100** and a process of assembling the organic light emitting diodes display **100** with other components after the manufacturing.

[0054] Accordingly, the polarization film **40** suppresses an occurrence of cracks of the inorganic layer **18**, and even though the cracks occur in the inorganic layer **18** due to the external impact applied from a side surface, the polarization film **40** may block the cracks from being further propagated with the display unit **20** or to further display units of a common mother substrate. As a result, a contractible defect of the organic light emitting diodes display **100** according to the propagation of the cracks to the display unit **20** may be prevented or its spread reduced.

[0055] FIG. 4 is a process flowchart illustrating a method of manufacturing the organic light emitting diodes display according to the exemplary embodiment.

[0056] Referring to FIG. 4, the method of manufacturing the organic light emitting diodes display includes: (1) a first step S10 of forming an inorganic layer on and over the whole surface of a mother substrate, (2) a second step S20 of forming a plurality of display units on the inorganic layer so as to form a plurality of unit cells, and (3) a third step S30 of forming a thin film encapsulating layer at an upper portion of each of the plurality of display units. Further, the method of manufacturing the organic light emitting diodes displays on a mother substrate includes (4) a fourth step S40 of attaching a polarization film on the inorganic layer so as to cover a plurality of thin film encapsulating layers, and (5) a fifth step S50 of separating the plurality of unit cells into individual unit cells by cutting the mother substrate and the polarization film.

[0057] FIG. 5 is a perspective view illustrating the organic light emitting diodes display in the second step illustrated in FIG. 4.

[0058] Referring to FIGS. 1 and 5, the inorganic layer **18** is blanket-formed (e.g., blanket deposited) on an entire upper surface of a mother substrate **110** (e.g., one formed of a base polymer). The inorganic layer includes at least one of the barrier layer **12** and the buffer layer **13**.

[0059] The flexible mother substrate **110** of the first step S10 and the second step S20 is supported by a rigid carrier substrate (not illustrated) to maintain a flat state in a process of forming the inorganic layers **18** and the display units **20**. The carrier substrate may be a glass substrate, and the flexible mother substrate **110** may be formed by a method of spin coating a polymer material on the glass carrier substrate and curing the polymer material. The carrier substrate is

separated from the mother substrate **110** after forming the thin film encapsulating layer **30** or attaching the cracks-suppressing polarization film **40**.

[0060] The mother substrate **110** has a size sufficient for including a predetermined number of plural unit cells **120**, and the plurality of unit cells **120** is positioned in parallel in a first direction (x-axis direction) and a second direction (y-axis direction) crossing the first direction of the mother substrate. Each unit cell **120** includes a respective display area DA and a respective pads area PA. The display units **20** including the plurality of pixel circuits and the plurality of organic light emitting diodes are positioned in the display area DA. The pad electrodes (not illustrated) are connected with the respective pixel circuits and are positioned in the pads area PA.

[0061] One or more integrated circuit chips (e.g., scan lines driving chip and/or data lines driving chip) may be mounted in the pads area PA in the second step S20 or may be mounted in the pads area PA after the fifth step S50. In FIG. 5, a case where the display unit **20** and the pads area PA are adjacent in the first direction (x-axis direction) is illustrated as an example.

[0062] FIG. 6 is a perspective view illustrating the organic light emitting diodes display in the third step illustrated in FIG. 4.

[0063] Referring to FIG. 6, here the thin film encapsulating layer **30** has been formed at the upper portion of each of the plurality of display units **120** in the third step S30. The thin film encapsulating layer **30** is formed by a method in which the plurality of organic layers and the plurality of inorganic layers are alternately and repeatedly stacked one by one, and is formed to have a larger area than that of the respective display unit **120** to cover the edges of the display units **120** and to join with a part of the blanket-formed inorganic layer **18** (see FIG. 2) to thereby individually encapsulate each respective display unit **20** (DA).

[0064] FIG. 7 is a perspective view illustrating the organic light emitting diodes display in the fourth step illustrated in FIG. 4.

[0065] Referring to FIG. 7, here the polarization film **40** has been blanket formed on top of the plurality of thin film encapsulating layers **30** in the fourth step S40. The polarization film **40** is one sheet of polarization film material corresponding to the full extent of the mother substrate **110**. After or during formation, the one sheet of polarization film **40** is provided with openings **41** as illustrated such that the respective plurality of pads areas PA are exposed and the respective display units **120** can be electrically tested. The one sheet of polarization film **40** simultaneously covers the whole of the thin film encapsulating layers **30** formed on the mother substrate **110**, and is in contact with the inorganic layer **18** at the exterior side of the thin film encapsulating layer **30** of each of the respective display units **120**.

[0066] The plurality of pads areas PA are positioned in parallel in the second direction (y-axis direction) based on FIG. 7. The polarization film **40** is provided with the slit-shaped openings **41** parallel to the second direction, to expose the plurality of pad areas PA positioned in the second direction by using one opening **41**. The number of openings **41** may be the same as the number of unit cells **120** positioned on the mother substrate in the first direction (x-axis direction).

[0067] FIG. 8 is a perspective view illustrating a first exemplary variation of the patterning of the polarization film as compared to the one illustrated in FIG. 7.

[0068] Referring to FIG. 8, in the first exemplary variation, a modified polarization film **401** covers the remaining areas of the mother substrate **110**, except for one row of pad areas PA (pad areas positioned at a right-side end (right side in the drawing) of the mother substrate based on FIG. 8) positioned at an outermost side of the mother substrate **110**. That is, the one row of pad areas PA are positioned at an exterior side of an edge of one side of the polarization film **401**. Thus, less material may be used for forming the modified polarization film **401** as compared to the polarization film **400** of FIG. 7 which covers the entire mother substrate.

[0069] The polarization film **401** is provided with openings **41** for the remaining rows of pad areas PA, except for the aforementioned one row of pad areas PA, to expose the pad areas PA. The number of openings **41** of the polarization film **401** in the first exemplary variation is the same as the number subtracted by 1 from the number of unit cells positioned in the first direction (x-axis direction). One sheet of the polarization film **401** of the first exemplary variation also simultaneously covers the whole of the plurality of thin film encapsulating layers **30** formed on the mother substrate **110**, and is in contact with the inorganic layer **18** at the exterior side of the thin film encapsulating layer **30**.

[0070] FIG. 9 is a perspective view illustrating a second exemplary variation of the polarization film as compared to the one **400** illustrated in FIG. 7.

[0071] Referring to FIG. 9, plural polarization films **402** are deposited in rod (rectangular bar) shapes in the second exemplary variation. The plurality of thin film encapsulating layers **30** are positioned in parallel in the second direction (y-axis direction) based on FIG. 9. The rod-shaped polarization films **402** simultaneously each covers one respective row of the thin film encapsulating layers **30** positioned in the second direction. Thus, less material may be used for forming the second modified polarization film **402** as compared to the polarization film **400** of FIG. 7 which covers the entire mother substrate.

[0072] The number of rod-shaped polarization films **402** may be the same as the number of unit cells **120** positioned in the first direction (x-axis direction) on the mother substrate **110**. One side edge of the polarization film **402** is in contact with the boundary of the pads area PA toward the display area DA, and an opposite side edge thereof is positioned at an exterior side of the edge of the thin film encapsulating layer **30**. That is, the polarization film **402** is formed to be larger than the thin film encapsulating layer **30** to be in contact with the inorganic layer **18** on the mother substrate **110**.

[0073] FIG. 10 is a top plan view illustrating the organic light emitting diodes display in the fifth step illustrated in FIG. 4.

[0074] Referring to FIG. 10, the mother substrate **110** in the fifth step S50 is cut (diced) along a first cutting line CL1 to be separated by a rod unit in which the plurality of unit cells **120** is connected in one direction. Then, the mother substrate **110** is cut along a second cutting line CL2 to be separated into individual unit cells. The first cutting line CL1 is parallel to any one direction of the first direction (x-axis

direction) and the second direction (y-axis direction), and the second cutting line CL2 crosses the first cutting line CL1.

[0075] According to the aforementioned method of manufacturing the organic light emitting diodes display 100, after the thin film encapsulating layer 30 is formed, the respective polarization film 40, 401, or 402 is attached instead of a passivation film. In this case, the plurality of thin film encapsulating layers 30 may be simultaneously covered by using one sheet or several sheets of polarization films 40, 401, or 402. The attached polarization film (e.g., 40, 401, or 402) simultaneously suppresses crack formation and reduces perception of artifact lights from internal reflections. Accordingly, it is possible to omit a process of attaching a passivation film and a process of removing the passivation film, and it is possible to simplify a process of attaching the polarization film which has been performed on each of the unit cells 120.

[0076] Further, the polarization film 40, 401, or 402 covers and protects the inorganic layer 18 at the exterior side of the thin film encapsulating layer 30. Accordingly, the organic layer 18 at the exterior side of the thin film encapsulating layer 30 is not exposed to the outside during the entire manufacturing and assembling processes after the polarization film 40, 401, or 402 is attached.

[0077] Accordingly, it is possible to suppress an occurrence of cracks in the inorganic layer 18 due to external impact, and even though the cracks occur in one spot in the inorganic layer 18 due to the external impact applied from the side surface, the cracks is not propagated to the display units 120 of the mother substrate by the polarization film 40, 401, or 402, thereby not causing a contagiously spread defect.

[0078] Whether the organic light emitting diodes display 100 after the fifth step S50 is a non-defective product is determined through an inspection process, and a process of assembling the chip on film and the printed circuit board is performed on the organic light emitting diodes display 100 which is determined as the non-defective product.

[0079] According to the present exemplary embodiment, it is possible to suppress an occurrence of spreading cracks of the inorganic layer, and even though the cracks may occur in one spot the inorganic layer, it is possible to block the cracks from being propagated to the other display units of a shared mother substrate. Accordingly, it is possible to prevent a contractible defect according to the propagation of the cracks to the other display units. Further, it is possible to omit a process of attaching a passivation film and removing the passivation film, and to simplify a process of attaching the polarization film.

[0080] While this disclosure has been described in connection with what is presently considered to be practical exemplary embodiments, it is to be understood that the present disclosure of invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover

various modifications and equivalent arrangements included within the spirit and scope of the present teachings.

What is claimed is:

1. An organic light emitting diodes display, comprising: a substrate; an inorganic layer disposed on the substrate; a display unit disposed on the inorganic layer; a thin film encapsulation layer that covers the display unit; a polarization film that covers the thin film encapsulating layer, wherein a part of edges of the polarization film and a part of edges of the substrate are matched with each other.
2. The organic light emitting diodes display of claim 1, wherein the part of edges of the polarization film and the part of edges of the substrate are matched with each other at opposite edges of the organic light emitting diodes display.
3. The organic light emitting diodes display of claim 2, wherein: a pad area is provided in the substrate, and the part of edges of polarization film and the part of edges of the substrate are further matched with at an edge of the organic light emitting diodes display, which is located opposite to the pad area.
4. The organic light emitting diodes display of claim 1, wherein edges of the polarization film, disposed at opposite edges of the organic light emitting diodes display, and edges of the substrate, disposed at the opposite edges of the organic light emitting diodes display, are matched with each other.
5. The organic light emitting diodes display of claim 1, wherein the match of the part of the edges of the polarization film and the part of the edges of the substrate is realized by cutting.
6. The organic light emitting diodes display of claim 1, wherein a pad area is provided in the substrate and the polarization film does not overlap the pad area.
7. The organic light emitting diodes display of claim 1, wherein the inorganic layer comprises at least two sub-layers.
8. The organic light emitting diodes display of claim 7, wherein the inorganic layer comprises: a barrier layer disposed on the substrate; and a buffer layer disposed on the barrier layer.
9. The organic light emitting diodes display of claim 1, wherein the area of the thin film encapsulation layer is greater than the area of the display unit.
10. The organic light emitting diodes display of claim 1, wherein the substrate is flexible.
11. The organic light emitting diodes display of claim 10, wherein the substrate comprises polyimide.
12. The organic light emitting diodes display of claim 1, wherein the substrate and the polarization film are respectively formed substantially in the shape of a quadrangle.
13. The organic light emitting diodes display of claim 1, wherein the polarization film covers side walls of the thin film encapsulating layer and a portion of the inorganic layer.

* * * * *

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	US20180006270A1	公开(公告)日	2018-01-04
申请号	US15/708259	申请日	2017-09-19
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	YI CHUNG OH SANG HUN		
发明人	YI, CHUNG OH, SANG-HUN		
IPC分类号	H01L51/52 H01L51/00 H01L51/56 H01L27/32		
CPC分类号	H01L51/5293 H01L2251/5338 H01L2251/566 H01L51/0097 H01L2227/323 H01L27/3244 H01L51/5253 H01L51/5281 H01L51/56 H01L27/3232 H01L27/3272 H01L51/5237 H05B45/60		
优先权	1020130063509 2013-06-03 KR		
其他公开文献	US10374193		
外部链接	Espacenet USPTO		

摘要(译)

防止裂纹扩散，偏振膜附着到有机发光二极管的下无机层的外边缘，其中显示器形成在其上形成有下无机层覆盖层的柔性基板上。有机发光二极管显示器还包括：显示单元，位于无机层上并包括多个有机发光二极管，配置为显示图像；以及薄膜封装层，覆盖显示单元并与延伸的无机层的边缘连接超出显示单元。

