



US009991454B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 9,991,454 B2**
(45) **Date of Patent:** **Jun. 5, 2018**

(54) **ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(51) **Int. Cl.**
C09K 11/00 (2006.01)
H01L 51/00 (2006.01)
(Continued)

(71) Applicants: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si, Gyeonggi-do (KR);
INDUSTRY-ACADEMIC COOPERATION FOUNDATION GYEONGSANG NATIONAL UNIVERSITY, Jinju-si,
Gyeongsangnam-do (KR)

(52) **U.S. Cl.**
CPC **H01L 51/0085** (2013.01); **C07D 413/00** (2013.01); **C07D 413/14** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC . C07F 15/0033; H01L 51/0085; C09K 11/06; C09K 2211/185; C09K 2211/1029; C07D 413/00; C07D 413/14
(Continued)

(72) Inventors: **Heeyeon Kim**, Yongin-si (KR); **Soonki Kwon**, Jinju (KR); **Mikyung Kim**, Yongin-si (KR); **Yunhi Kim**, Jinju (KR); **Jihyun Seo**, Yongin-si (KR); **Hyein Jeong**, Yongin-si (KR)

(56) **References Cited**
U.S. PATENT DOCUMENTS

(73) Assignees: **Samsung Display Co., Ltd.**, Yongin-si (KR); **Industry-Academic Cooperation Foundation Gyeomngsang National University**, Jinju-si (KR)

8,734,963 B2* 5/2014 De Cola C07F 15/0033 252/301.16
2010/0141127 A1 6/2010 Xia et al.
(Continued)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 123 days.

FOREIGN PATENT DOCUMENTS

KR 10-2011-0094027 A 8/2011
KR 10-2014-0048797 A 4/2014
KR 10-2014-0104926 A 8/2014

(21) Appl. No.: **14/967,202**

Primary Examiner — Amanda C Walke

(22) Filed: **Dec. 11, 2015**

(74) *Attorney, Agent, or Firm* — Lewis Roca Rothgerber Christie LLP


(65) **Prior Publication Data**
US 2016/0172607 A1 Jun. 16, 2016

(57) **ABSTRACT**

(30) **Foreign Application Priority Data**
Dec. 16, 2014 (KR) 10-2014-0181615


An organic light-emitting device includes a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode,
(Continued)

10



wherein the organic layer includes an emission layer and at least one organometallic compound of Formula 1.

Formula 1



An organic light-emitting device including an organometallic compound of Formula 1 may have low driving voltage, high efficiency, and excellent color purity.

18 Claims, 2 Drawing Sheets

(51) **Int. Cl.**

C07F 15/00 (2006.01)
C09K 11/06 (2006.01)
C09K 11/02 (2006.01)
C07D 413/14 (2006.01)

C07D 413/00 (2006.01)
H01L 51/50 (2006.01)

(52) **U.S. Cl.**

CPC **C07F 15/0033** (2013.01); **C09K 11/025**
 (2013.01); **C09K 11/06** (2013.01); **C09K**
2211/1007 (2013.01); **C09K 2211/1029**
 (2013.01); **C09K 2211/185** (2013.01); **H01L**
51/5016 (2013.01)

(58) **Field of Classification Search**

USPC 257/40; 546/4; 438/99; 428/690
 See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2011/0251391	A1 *	10/2011	Shiu		C07F 15/0033
					546/4
2013/0169148	A1	7/2013	Alleyne et al.		
2014/0103316	A1	4/2014	Kim et al.		
2014/0231755	A1	8/2014	Xia et al.		
2014/0364611	A1 *	12/2014	Mak		C07F 15/0033
					546/4
2015/0115250	A1 *	4/2015	Ma		H01L 51/0085
					257/40
2015/0171349	A1 *	6/2015	Ma		H01L 51/0085
					257/40
2015/0221878	A1 *	8/2015	Rai		H01L 51/0085
					257/40
2015/0249224	A1 *	9/2015	Jung		C07D 405/14
					252/301.16
2015/0307535	A1 *	10/2015	Xia		C07F 15/0033
					544/225
2015/0364702	A1 *	12/2015	Abe		C09K 11/06
					257/40


* cited by examiner

FIG. 1

10

190
150
110

FIG. 2



ORGANOMETALLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to and the benefit of Korean Patent Application No. 10-2014-0181615, filed on Dec. 16, 2014, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

One or more aspects of embodiments of the present invention relate to an organometallic compound and an organic light-emitting device including the organometallic compound.

2. Description of the Related Art

Organic light-emitting devices (OLEDs) are self-emission devices that have wide viewing angles, high contrast ratios, and short response times. In addition, OLEDs exhibit excellent luminance, low driving voltage, and fast response speed characteristics, and can produce full-color images.


The organic light-emitting device may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. The holes and the electrons are then recombined in the emission layer to produce excitons. These excitons change from an excited state to a ground state to thereby generate light.

SUMMARY

One or more aspects of embodiments of the present invention are directed toward an organometallic compound and an organic light-emitting device including the organometallic compound.

Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

According to one or more exemplary embodiments, an organometallic compound is represented by Formula 1:



Formula 1

In Formula 1,

R₁ and R₂ are each independently selected from:

a C₁-C₁₀ alkyl group and a C₅-C₁₀ cycloalkyl group; and

a C₅-C₁₀ cycloalkyl group substituted with at least one

C₁-C₁₀ alkyl group, and

at least one of R₁ and R₂ is selected from:

a C₅-C₁₀ cycloalkyl group; and

a C₅-C₁₀ cycloalkyl group substituted with at least one C₁-C₁₀ alkyl group.

According to one or more exemplary embodiments, an organic light-emitting device includes a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer includes at least one of the organometallic compounds. The organometallic compound may be included in an emission layer of the organic light-emitting device. In the emission layer, the organometallic compound may serve as a phosphorescent dopant, and the emission layer may further include a host.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects will become apparent and more readily appreciated from the following description of the exemplary embodiments, taken in conjunction with the accompanying drawings in which:

FIG. 1 schematically illustrates a structure of an organic light-emitting device according to one or more embodiments of the present invention; and

FIG. 2 shows a UV-vis absorption spectrum and a photoluminescence (PL) spectrum of Compound 1 and Ir(ppy)₃.

DETAILED DESCRIPTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present exemplary embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the exemplary embodiments are merely described below, by referring to the figures, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. Further, the use of “may” when describing embodiments of the present invention refers to one or more embodiments of the present invention.

In addition, as used herein, the terms “use,” “using,” and “used” may be considered synonymous with the terms “utilize,” “utilizing,” and “utilized,” respectively. Also, the term “exemplary” is intended to refer to an example or illustration.


As used herein, the term “substantially,” “about,” and similar terms are used as terms of approximation and not as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art.

Also, any numerical range recited herein is intended to include all subranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited

3

maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein. All such ranges are intended to be inherently described in this specification such that amending to expressly recite any such subranges would comply with the requirements of 35 U.S.C. § 112, first paragraph, and 35 U.S.C. § 132(a).

According to one or more embodiments, an organometallic compound may be represented by Formula 1:



Formula 1

In Formula 1,

R_1 and R_2 are each independently selected from:

a C_1 - C_{10} alkyl group and a C_5 - C_{10} cycloalkyl group; and
a C_5 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{10} alkyl group, and

at least one of R_1 and R_2 is selected from:

a C_5 - C_{10} cycloalkyl group; and
a C_5 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{10} alkyl group.

In some embodiments, in Formula 1, R_1 and R_2 are each independently selected from:

a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and

4

group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group, and

at least one of R_1 and R_2 is selected from:

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group.

In one embodiment, in Formula 1, R_1 and R_2 may be each independently selected from:

a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, and

at least one of R_1 and R_2 may be selected from:

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group.

In some embodiments, in Formula 1, R_1 and R_2 may be each independently selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, and

at least one of R_1 and R_2 may be selected from a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group.

In some embodiments, in Formula 1,

R_1 may be a C_1 - C_{10} alkyl group, and

R_2 may be selected from:

a C_5 - C_{10} cycloalkyl group; and

a C_5 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{10} alkyl group.

5

In some embodiments, in Formula 1,

R₁ may be selected from:

a C₅-C₁₀ cycloalkyl group; and

a C₅-C₁₀ cycloalkyl group substituted with at least one C₁-C₁₀ alkyl group, and

R₂ may be a C₁-C₁₀ alkyl group.

In some embodiments, in Formula 1,

R₁ may be selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group, and

R₂ may be selected from:

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group.

In some embodiments, in Formula 1,

R₁ may be selected from:

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group; and


a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group, and

R₂ may be selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group.

In some embodiments, in Formula 1,

R₁ may be selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, and

R₂ may be selected from groups represented by Formulae 2-1 to 2-6, but embodiments of the present invention are not limited thereto:




Formula 2-1

6

-continued


Formula 2-2



5


10

Formula 2-3



15


Formula 2-4



25

30


Formula 2-5



35

40

Formula 2-6



45

50

In some embodiments, in Formula 1,


R₁ may be selected from groups represented by Formulae 2-1 to 2-6, and

R₂ may be selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, but embodiments of the present invention are not limited thereto.

A photoluminescence (PL) spectrum of the organometallic compound represented by Formula 1 may have a light-emission peak with a maximum light-emitting wavelength within a range of 460 nm to 510 nm.

The organometallic compound represented by Formula 1 may be any one of Compounds 1 to 32, but embodiments of the present invention are not limited thereto:

7



1

8

-continued


5

4

10

15


20



2

25

5




30

35

40


45



3

50


6



55

60


65



9

-continued

7



5

10


15

20

10


-continued

10



8 25

11




30

35


40

45

9



12




50

55


60

65



11


-continued



13


12

-continued




16

14 25




15

25



17

45




65

50

55


60

18



13

-continued



19

14

-continued

5

22

10

15

20

25

30

35

40

45

50

55

60

65

70

75

80

85

90

95

100

105

110

115






120

125

130


135

140



15


-continued




25

16


-continued




28




26



29



27




30

65

17

-continued



In the organometallic compound represented by Formula 1, i) R_1 is substituted at (occupies) a para position of the pyridine ring, ii) R_2 is substituted at (occupies) a meta position in the benzene ring with respect to a carbon bound of the ring to Ir, and iii) at least one of R_1 and R_2 is selected from a C_5 - C_{10} cycloalkyl group; and a C_5 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{10} alkyl group. In other words, the organometallic compound represented by Formula 1 has a substituent selected from a C_5 - C_{10} cycloalkyl group; and a C_5 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{10} alkyl group at a position of at least one of R_1 and R_2 . The C_5 - C_{10} cycloalkyl group and the C_5 - C_{10} cycloalkyl group substituted with at least one C_1 - C_{10} alkyl group are bulky groups having a relatively large number of carbon atoms, and thus may effectively provide electrons to the organometallic compound represented by Formula 1. Accordingly, an organic light-emitting device including the organometallic compound represented by Formula 1 may emit green light with high purity and high efficiency.

The organometallic compound represented by Formula 1 may be synthesized using one or more suitable organic synthesis methods commonly known to those of skill in the

18

art. Non-limiting examples of the synthesis method for the organometallic compound of Formula 1 should be apparent to those skilled in the art from the examples described below.

At least one of the organometallic compounds represented by Formula 1 may be used (utilized) between a pair of electrodes of an organic light-emitting device. For example, the organometallic compound may be included in an emission layer. Here, the organometallic compound included in the emission layer of the organic light-emitting device serves as a phosphorescent dopant, and the emission layer may further include a host.

According to one or more embodiments of the present invention, an organic light-emitting device includes a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer includes at least one organometallic compound represented by Formula 1.

As used herein, the phrase "organic layer includes at least one organometallic compound" may be construed as "organic layer may include one organometallic compound represented by Formula 1 or two or more different organometallic compounds represented by Formula 1".

In some embodiments, an organic layer of an organic light-emitting device may include only Compound 1 as the organometallic compound. In this regard, Compound 1 may be included in an emission layer of the organic light-emitting device. In other embodiments, the organic layer may include Compound 1 and Compound 17 as the organometallic compound. In this regard, Compound 1 and Compound 17 may both be included in the same layer (for example, Compound 1 and Compound 17 may both be included in the emission layer).

The organic layer may include i) a hole-transport region between the first electrode (e.g., an anode) and the emission layer, the hole-transport region including at least one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer; and ii) an electron transport region between the emission layer and the second electrode (e.g., a cathode), the electron transport region including at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer. The emission layer may include the organometallic compound represented by Formula 1.

In some embodiments, the emission layer may include at least one organometallic compound represented by Formula 1. The emission layer including at least one organometallic compound represented by Formula 1 may further include a host. The organometallic compound may serve as a dopant in the emission layer, and the amount of the organometallic compound may be less than the amount of the host.

As used herein, the term "organic layer" refers to a single layer and/or a plurality of layers between the first electrode and the second electrode in an organic light-emitting device. A material included in the "organic layer" is not limited to an organic material.

FIG. 1 is a schematic view of an organic light-emitting device 10 according to one or more embodiments of the present invention. The organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

Hereinafter, a structure and a method of manufacturing an organic light-emitting device according to one or more embodiments will be described with reference to FIG. 1.

Referring to FIG. 1, a substrate may be additionally disposed under the first electrode 110 or on the second electrode 190. The substrate may be a glass substrate or transparent plastic substrate, each with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

The first electrode **110** may be formed by depositing or sputtering a material for forming the first electrode **110** on the substrate. When the first electrode **110** is an anode, the material for the first electrode **110** may be selected from materials with a high work function so as to facilitate hole injection. The first electrode **110** may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for the first electrode **110** may be a transparent and highly conductive material, and non-limiting examples of such material include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), and zinc oxide (ZnO). When the first electrode **110** is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode **110**, at least one selected from magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag) may be used (utilized).

The first electrode **110** may have a single-layer structure, or a multi-layer structure including a plurality of layers. For example, the first electrode **110** may have a triple-layer structure of ITO/Ag/ITO, but embodiments of the present invention are not limited thereto.

The organic layer **150** is positioned on the first electrode **110**. The organic layer **150** may include an emission layer.

The organic layer **150** may further include a hole transport region between the first electrode **110** and the emission layer, and an electron transport region between the emission layer and the second electrode **190**.

The hole transport region may include at least one selected from a hole injection layer (HIL), a hole transport layer (HTL), a buffer layer, and an electron blocking layer (EBL), and the electron transport region may include at least one selected from a hole blocking layer (HBL), an electron transport layer (ETL), and an electron injection layer (EIL), but embodiments of the present invention are not limited thereto.

The hole transport region may have a single-layered structure formed of a single material, a single-layered structure formed of a plurality of different materials, or a multi-layered structure having a plurality of layers formed of a plurality of different materials.

For example, the hole transport region may have a single-layered structure formed of a plurality of different materials, or a structure of hole injection layer/hole transport layer, a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole injection layer/buffer layer, a structure of hole transport layer/buffer layer, or a structure of hole injection layer/hole transport layer/electron blocking layer, wherein the layers of each structure are sequentially stacked from the first electrode **110** in the stated order, but embodiments of the present invention are not limited thereto.

When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode **110** by using one or more suitable methods, such as vacuum deposition, spin coating, casting, a Langmuir-Blodgett (LB) method, inkjet printing, laser printing, and/or laser-induced thermal imaging (LITI).


When the hole injection layer is formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature in a range of about 100° C. to about 500° C., at a vacuum degree in a range of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate in a range of about 0.01 Å/sec to about 100 Å/sec depending on the compound for forming the hole injection layer and the structure of the hole injection layer to be formed.

When the hole injection layer is formed by spin coating, the spin coating may be performed at a coating rate in a range of about 2000 rpm to about 5000 rpm and at a temperature in a range of about 80° C. to 200° C. depending

on the compound for forming the hole injection layer and the structure of the hole injection layer to be formed.


When the hole transport region includes a hole transport layer, the hole transport layer may be formed on the first electrode **110** or the hole injection layer by using one or more suitable methods, such as vacuum deposition, spin coating, casting, an LB method, inkjet printing, laser printing, and/or LITI. When the hole transport layer is formed by vacuum deposition and/or spin coating, conditions for vacuum deposition and coating may be similar to the above-described vacuum deposition and coating conditions for forming the hole injection layer.

The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β-NPB, TPD, spiro-TPD, spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




21



-continued



2-TNATA




NPB

 β -NPB


TPD

22


-continued




Spiro-TPD




Spiro-NPB



methylated NPB




TAPC




HMTPD

Formula 201



Formula 202



xa1 to xa4 may be each independently selected from 0, 1, 2, and 3.

R₂₀₁ to R₂₀₄ may be each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

L₂₀₁ to L₂₀₅ may be each independently selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysenylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolininylenylene group, a carbazolylenylene group, and a triazinylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁–C₂₀ alkyl group, a C₁–C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazoyl group, and a triazinyl group.


xa5 may be 1, 2, or 3, and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and


a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an azulenyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, but embodiments of the present invention are not limited thereto.

The compound represented by Formula 201 may be represented by Formula 201A:

Formula 201A




Formula 201A-1




25

In some embodiments, the compound represented by Formula 202 may be represented by Formula 202A, but embodiments of the present invention are not limited thereto:



In Formulae 201A, 201A-1, and 202A, the descriptions of L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} may be as provided herein, R_{211} and R_{212} may each independently be the same as defined in connection with R_{203} , and R_{213} to R_{216} may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.



The compound represented by Formula 201 and the compound represented by Formula 202 may each independently include Compounds HT1 to HT20, but embodiments of the present invention are not limited thereto:



26

-continued


HT2



27


-continued

HT4

**28**

-continued

HT6




30

35

40

HT5



45


50

55

60

65


HT7



29

-continued

HT8



5


10

15

20

HT9

25




30

35

40

HT10

45




50

55

30

-continued

HT11



5

10

15

20

25

HT12

30

35

40


45

50

55

60

65



HT13

55


60

65

31

-continued

HT14



5


10

15

32


-continued

HT18



HT15 20


HT19



25


30

35



HT16


HT20




40

45

50



HT17



55

60


65

A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1000 Å. When the hole transport region includes a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 9,950 Å, or about 100 Å to about 1000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2000 Å, for example, about 100 Å to about 1500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within any of these ranges, good hole transport characteristics may be obtained without a substantial increase in driving voltage.

The hole transport region may further include, in addition to the materials mentioned above, a charge-generating material to improve conductive properties. The charge-generat-

ing material may be homogeneously or non-homogeneously dispersed throughout the hole transport region.

The charge-generating material may be, for example, a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments of the present invention are not limited thereto. Non-limiting examples of the p-dopant include quinone derivatives such as tetracyanoquinonodimethane (TCNQ) and/or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ); metal oxides such as a tungsten oxide and/or a molybdenum oxide; and Compound HT-D1:




The hole transport region may further include, in addition to the hole injection layer and the hole transport layer, at least one selected from a buffer layer and an electron blocking layer. Since the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, the light-emission efficiency of the resulting organic light-emitting device may be improved. As a material included in the buffer layer, materials that are included in the hole transport region may be used (utilized). In some embodiments, the electron blocking layer prevents or substantially reduces or blocks the injection of electrons from the electron transport region.

An emission layer may be formed on the first electrode 110 or the hole transport region by using one or more suitable methods, such as vacuum deposition, spin coating, casting, an LB method, inkjet printing, laser printing, and/or LITI. When the emission layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the emission layer may be similar to the deposition and coating conditions for the hole injection layer.

When the organic light-emitting device 10 is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. Alternatively, the emission layer may have a stacked structure of a red emission layer, a green emission layer, and a blue emission layer, or may include a red-light emission material, a green-light emission material, and a blue-light emission material, which are mixed with each other in a single layer, to emit white light.

The emission layer may include a host and a dopant. The dopant included in the emission layer may include the organometallic compound represented by Formula 1.

The host may include a compound represented by Formula 301:



Formula 301

In Formula 301,

Ar_{301} may be selected from:

- 10 a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene; and
- 15 a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I,
- 20 a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{301})(Q_{302})(Q_{303}) (where Q_{301} to Q_{303} are each independently selected from a hydrogen, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_6 - C_{60} aryl group, and a C_1 - C_{60} heteroaryl group),

L_{301} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

R_{301} may be selected from:

- a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group;
- a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl

35

group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group,

xb1 may be selected from 0, 1, 2, and 3, and

xb2 may be selected from 1, 2, 3, and 4.

In some embodiments, in Formula 301,

L_{301} may be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group, and a chrysenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group, and a chrysenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group,

R_{301} may be selected from:

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-


36

fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, but embodiments of the present invention are not limited thereto.

In some embodiments, the host may include a compound represented by Formula 301A:


Formula 301A




The descriptions of substituents in Formula 301A may be as provided herein.

The compound represented by Formula 301 may include at least one compound selected from Compounds H1 to H42 below, but embodiments of the present invention are not limited thereto:

H1









H2



37

-continued



38

-continued

H3

5

10

H4

15

20

25

H5

30

35

H6

40

45

H7

50

55

H8

60

65

H9







H10

H11

H12


H13

H14




39

-continued


**40**

-continued



41


-continued



H25


5

10




H26

15



H27


30



H28

40


45



H29

50

55




H30

60


65

42


-continued




H31



H32




H33



H34

43

-continued



H35


44

-continued

5

10

15



H38

H36


20

25

30

35

40



H39

H37


45

50


55

60

65




H40



45

-continued



H41

5


10

15

20

46

-continued





H44

H42 25

30

35


40



H45

In some embodiments, the host may include at least one ⁴⁵ selected from Compounds H43 to H49 below, but is not limited thereto:


H43 50



55

60




65



H46

47

-continued




In some embodiments, the emission layer may further include a compound represented by any one of Formula 50 and Formula 51, in addition to the organometallic compound represented by Formula 1. In some embodiments, the emission layer may include a dopant and a host, wherein the dopant may include the organometallic compound represented by Formula 1, and the host may include the compound represented by Formula 50 or Formula 51:

48


H47

Formula 50



H48

Formula 51



In Formulae 50 and 51,

A_1 may be CR_{11} or N, A_2 may be CR_{12} or N, A_3 may be CR_{13} or N, A_4 may be CR_{14} or N, A_5 may be CR_{15} or N, A_6 may be CR_{16} or N, A_7 may be CR_{17} or N, A_8 may be CR_{18} or N, A_9 may be CR_{19} or N, A_{10} may be CR_{20} or N, A_{11} may be CR_{21} or N, A_{12} may be CR_{22} or N, A_{13} may be CR_{23} or N, A_{14} may be CR_{24} or N, A_{15} may be CR_{25} or N, A_{16} may be CR_{26} or N, A_{17} may be CR_{27} or N, A_{18} may be CR_{28} or N, A_{19} may be CR_{29} or N, A_{20} may be CR_{30} or N, A_{21} may be CR_{31} or N, A_{22} may be CR_{32} or N, A_{23} may be CR_{33} or N, and A_{24} may be CR_{34} or N,

rings B_1 and B_2 may be each independently selected from a benzene, a pyridine, a pyrimidine, a pyrazine, a naphthalene, a quinoline, an isoquinoline, a quinoxaline, a quinazoline, a cinnoline, a fluorene, a carbazole, a dibenzofuran, and a dibenzothiophene,

X may be $-C(R_{40})(R_{41})-$, $-N(R_{42})-$, $-S-$, $-O-$, $-Si(R_{43})(R_{44})-$, $P(R_{45})-$, $-P(=O)(R_{46})-$, or $-B(R_{47})-$;

Ar_1 may be selected from a substituted or unsubstituted C_3-C_{10} cycloalkylene group, a substituted or unsubstituted C_1-C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3-C_{10} cycloalkenylene group, a substituted or unsubstituted C_1-C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6-C_{60} arylene group, a substituted or unsubstituted C_1-C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

R_{11} to R_{36} and R_{40} to R_{47} may be each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an imidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or

unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and B(Q₆)(Q₇), and at least two of R₁₁ to R₂₉ may be linked each other to form a saturated or unsaturated ring.

e and f1 may each independently be an integer selected from 0 to 2,

f2 and f3 may each independently be an integer selected from 0 to 7,

at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and B(Q₁₆)(Q₁₇).

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group,

a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and B(Q₂₆)(Q₂₇); and

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and B(Q₃₆)(Q₃₇),

wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

In some embodiments,

at least one of A₁₅ to A₁₉ in Formula 50 may be N, and at least one of A₂₀ to A₂₄ in Formula 51 may be N,

rings B₁ and B₂ in Formula 51 may be each independently selected from a benzene, a fluorene, a dibenzofuran, and a dibenzothiophene,

in Formulae 50 and 51, Ar₁ may be each independently selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenenylene group, a spiro-fluorenenylene group, a benzofluorenenylene group, a dibenzofluorenenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylenylene group, a thiophenylene group, a furanylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylenylene group, an indolylenylene group, an indazolylenylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylenylene group, a benzofuranylene group, a

benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

a phenylene group, a pentalenyne group, an indenylene group, a naphthylene group, an azulenyne group, a heptalenylene group, an indacenyne group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenyne group, a phenanthrenylene group, an anthracenyne group, a fluoranthenyne group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenyne group, a picenylene group, a perylenylene group, a pentaphenyne group, a hexacenyne group, a pentacenyne group, a rubicenyne group, a coronenyne group, an ovalenyne group, a pyrrolylene group, a thiophenyne group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinyne group, a pyrazinyne group, a pyrimidinyne group, a pyridazinyne group, an isoindolyne group, a purinyne group, an indolinyne group, an indazolyne group, a purinyne group, a benzoquinolinyne group, a phthalazinyne group, a naphthyridinyne group, a quinoxalinyne group, a quinazolinylene group, a cinnolinyne group, a carbazolyne group, a phenanthridinyne group, an acridinyne group, a phenanthrolinyne group, a phenazinyne group, a benzoimidazolyne group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolyne group, a tetrazolyne group, an oxadiazolyne group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolyne group, a dibenzocarbazolyne group, a thiadiazolyne group, an imidazopyridinyne group, and an imidazopyrimidinyne group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyne group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyne group, a pentacenyne group, a rubicenyne group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofura-

a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group,

R_{11} to R_{36} and R_{40} to R_{47} may be each independently selected from:

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyne group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyne group, a pentacenyne group, a rubicenyne group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyne group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyne group, a pentacenyne group, a rubicenyne group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofura-

53


nyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_{33})(Q_{34})(Q_{35}),

where Q_{33} to Q_{35} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, but embodiments of the present invention are not limited thereto.


In some embodiments, the emission layer may include the organometallic compound represented by Formula 1, and

54


the emission layer may further include a compound represented by one of the formulae below, in addition to the organometallic compound represented by Formula 1, but embodiments of the present invention are not limited thereto:




79



80







81






82

55

-continued




**56**

-continued







57

-continued






58

-continued



59

-continued



60

-continued

97

100

5

10

15

20

25

98

35

40

45

50

99




55

60

65





101

102




61

-continued



62

-continued



103

107

5

10

15

20

104 25

In the emission layer, a concentration of the organometallic compound represented by Formula 1 may be in a range of about 1 wt % to about 30 wt % based on 100 wt % of the emission layer. When the concentration of the organometallic compound is within this range, an organic light-emitting device may effectively emit light without a substantial exciton quenching.

A thickness of the emission layer may be in a range of about 100 Å to about 1000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, good light-emission characteristics may be obtained without a substantial increase in driving voltage.

Then, an electron transport region may be positioned on the emission layer.

The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer, but embodiments of the present invention are not limited thereto.

105

For example, the electron transport region may have a structure of electron transport layer/electron injection layer or a structure of hole blocking layer/electron transport layer/electron injection layer, wherein the layers of each structure are sequentially stacked from the emission layer in the stated order, but embodiments of the present invention are not limited thereto.

In some embodiments, the organic layer **150** of the organic light-emitting device may include an electron transport region between the emission layer and the second electrode **190**.

106

When the electron transport region includes a hole blocking layer, the hole blocking layer may be formed on the emission layer by using one or more suitable methods, such as vacuum deposition, spin coating, casting, an LB method, inkjet printing, laser printing, and/or LITI. When the hole blocking layer is formed by vacuum deposition and/or spin coating, deposition and coating conditions for the hole blocking layer may be similar to the deposition and coating conditions for the hole injection layer.

The hole blocking layer may include, for example, at least one selected from BCP and Bphen, but embodiments of the present invention are not limited thereto:

64



The electron transport layer may be formed on the emission layer or the hole blocking layer by using one or more suitable methods, such as vacuum deposition, spin coating, casting, an LB method, inkjet printing, laser printing, and/or LITI. When the electron transport layer is formed by using vacuum deposition and/or spin coating, vacuum deposition and coating conditions for the electron transport layer may be similar to the vacuum deposition and coating conditions for the hole injection layer.

The electron transport layer may include at least one selected from compounds represented by Formula 601 and compounds represented by Formula 602:



In Formula 601,

Ar₆₀₁ may be selected from:

a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene; and

a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazono group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃) (where Q₃₀₁ to Q₃₀₃ are each independently

selected from a hydrogen, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₆-C₆₀ aryl group, and a C₁-C₆₀ heteroaryl group),

the description of L_{501} may be the same as the description

5 provided in connection with L₂₀₁,

E₆₀₁ may be selected from:

a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthroli-
n-1-yl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and


25 a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an
30 indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthroli-
35 nyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a diben-
40 zothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an
45 amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl
50 group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spirofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl
55 group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl
60 group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl
65 group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenan-

65

thridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuran-
 yl group, a benzothiophenyl group, an isobenzothiazolyl
 group, a benzoxazolyl group, an isobenzoxazolyl group, a
 triazolyl group, a tetrazolyl group, an oxadiazolyl group, a
 triazinyl group, a dibenzofuranyl group, a dibenzothiophe-
 nyl group, a benzocarbazolyl group, a dibenzocarbazolyl
 group, an imidazopyridinyl group, and an imidazopyrimidi-
 nyl group,

xe1 is selected from 0, 1, 2, and 3, and

xe2 is selected from 1, 2, 3, and 4.



Formula 602

In Formula 602,

X₆₁₁ may be N or C-(L₆₁₁)_{xe611}-R₆₁₁, X₆₁₂ may be N or
 C-(L₆₁₂)_{xe612}-R₆₁₂, X₆₁₃ may be N or C-(L₆₁₃)_{xe613}-R₆₁₃, at
 least one of X₆₁₁ to X₆₁₃ may be N,

L₆₁₁ to L₆₁₆ may be each independently the same as
 defined in connection with L₁ provided herein,

R₆₁₁ to R₆₁₆ may be each independently selected from:

a phenyl group, a naphthyl group, a fluorenyl group, a
 spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-
 fluorenyl group, a phenanthrenyl group, an anthracenyl
 group, a pyrenyl group, a chrysenyl group, a pyridinyl
 group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl
 group, a quinolinyl group, an isoquinolinyl group, a qui-
 noxalinyl group, a quinazolinyl group, a carbazolyl group,
 and a triazinyl group; and


a phenyl group, a naphthyl group, a fluorenyl group, a
 spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-
 fluorenyl group, a phenanthrenyl group, an anthracenyl
 group, a pyrenyl group, a chrysenyl group, a pyridinyl
 group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl
 group, a quinolinyl group, an isoquinolinyl group, a qui-
 noxalinyl group, a quinazolinyl group, carbazolyl, and a
 triazinyl group, each substituted with at least one selected
 from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group,
 a cyano group, a nitro group, an amino group, an amidino
 group, a hydrazine group, a hydrazone group, a carboxylic
 acid group or a salt thereof, a sulfonic acid group or a salt
 thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀
 alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a
 naphthyl group, an azulenyl group, a fluorenyl group, a
 spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-
 fluorenyl group, a phenanthrenyl group, an anthracenyl
 group, a pyrenyl group, a chrysenyl group, a pyridinyl
 group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl
 group, a quinolinyl group, an isoquinolinyl group, a qui-
 noxalinyl group, a quinazolinyl group, a carbazolyl group,
 and a triazinyl group, and

xe611 to xe616 may be each independently selected from
 0, 1, 2, and 3.


The compound represented by Formula 601 and the
 compound represented by Formula 602 may be each inde-
 pendently selected from Compounds ET1 to ET15:

66


ET1




ET2








ET3



67
-continued




68
-continued



69

-continued



ET10

5

10

15

20

ET11

30

35

40


45

ET12

50

55

60

**70**

-continued

ET13

5

10

15

20

ET14

25

30

35

40




45

ET15

50





55

60



65 In some embodiments, the electron transport layer may include at least one of BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ:

71




A thickness of the electron transport layer may be in a range of about 100 Å to about 1000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within this range, good electron transport characteristics may be obtained without a substantial increase in driving voltage.

The electron transport layer may further include a metal-containing material, in addition to the materials described above.


The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2:

72

ET-D1



ET-D2



20

The electron transport region may include an electron injection layer that is capable of facilitating electron injection from the second electrode **190**.

The electron injection layer may be formed on the electron transport layer by using one or more suitable methods, such as vacuum deposition, spin coating, casting, an LB method, inkjet printing, laser printing, and/or LITI. When the electron injection layer is formed by vacuum deposition and/or spin coating, vacuum deposition and coating conditions for the electron injection layer may be similar to the vacuum deposition and coating conditions for the hole injection layer.

The electron injection layer may include at least one selected from: LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within this range, good electron injection characteristics may be obtained without a substantial increase in driving voltage.

The second electrode **190** is positioned on the organic layer **150**. The second electrode **190** may be a cathode (that is, an electron injection electrode), and in this regard, a material for forming the second electrode **190** may be a material having a low work function, for example, a metal, an alloy, an electrically conductive compound, or a mixture thereof. Non-limiting examples of the material for forming the second electrode **190** include lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag). In some embodiments, the material for forming the second electrode **190** may be ITO or IZO. The second electrode **190** may be a semi-transmissive electrode or a transmissive electrode.

Hereinbefore, an organic light-emitting device has been described with reference to FIG. 1, but embodiments of the present invention are not limited thereto.

As used herein, a C₁-C₆₀ alkyl group refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms in the main carbon chain, and non-limiting examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. As used herein, a C₁-C₆₀ alkylene group refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

As used herein, a C_1 - C_{60} alkoxy group refers to a monovalent group represented by $-OA_{101}$ (where A_{101} is the C_1 - C_{60} alkyl group), and non-limiting examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

As used herein, a C_2 - C_{60} alkenyl group refers to a group including at least one carbon-carbon double bond at one or more positions along a carbon chain of the C_2 - C_{60} alkyl group (e.g., in the middle or at either end of the C_2 - C_{60} alkyl group), and non-limiting examples thereof include an ethenyl group, a propenyl group, and a butenyl group. As used herein, a C_2 - C_{60} alkenylene group refers to a divalent group having the same structure as the C_2 - C_{60} alkenyl group.

As used herein, a C_2 - C_{60} alkynyl group refers to a group including at least one carbon-carbon triple bond at one or more positions along a carbon chain of the C_2 - C_{60} alkyl group (e.g., in the middle or at either end of the C_2 - C_{60} alkyl group), and non-limiting examples thereof include an ethynyl group and a propynyl group. As used herein, a C_2 - C_{60} alkynylene group refers to a divalent group having the same structure as the C_2 - C_{60} alkynyl group.

As used herein, a C_3 - C_{10} cycloalkyl group refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms as ring-forming atoms, and non-limiting examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. As used herein, a C_3 - C_{10} cycloalkylene group refers to a divalent group having the same structure as the C_3 - C_{10} cycloalkyl group.

As used herein, a C_1 - C_{10} heterocycloalkyl group refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms as the remaining ring-forming atoms, and non-limiting examples thereof include a tetrahydrofuranlyl group and a tetrahydrothiophenyl group. As used herein, a C_1 - C_{10} heterocycloalkylene group refers to a divalent group having the same structure as the C_1 - C_{10} heterocycloalkyl group.

As used herein, a C_3 - C_{10} cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms as ring-forming atoms and at least one carbon-carbon double bond in the ring thereof and does not have aromaticity, and non-limiting examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. As used herein, a C_3 - C_{10} cycloalkenylene group refers to a divalent group having the same structure as the C_3 - C_{10} cycloalkenyl group.

As used herein, a C_1 - C_{10} heterocycloalkenyl group refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms as the remaining ring-forming atoms, and at least one double bond in its ring. Non-limiting examples of the C_1 - C_{10} heterocycloalkenyl group include a 2,3-hydrofuranlyl group and a 2,3-hydrothiophenyl group. As used herein, a C_1 - C_{10} heterocycloalkenylene group refers to a divalent group having the same structure as the C_1 - C_{10} heterocycloalkenyl group.

As used herein, a C_6 - C_{60} aryl group refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C_6 - C_{60} arylene group as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C_6 - C_{60} aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a

pyrenyl group, and a chrysenyl group. When the C_6 - C_{60} aryl group and/or the C_6 - C_{60} arylene group include two or more rings, the rings may be fused to each other.

As used herein, a C_1 - C_{60} heteroaryl group refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, and 1 to 60 carbon atoms as the remaining ring-forming atoms. As used herein, a C_1 - C_{60} heteroarylene group refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, and 1 to 60 carbon atoms as the remaining ring-forming atoms. Non-limiting examples of the C_1 - C_{60} heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C_1 - C_{60} heteroaryl group and/or the C_1 - C_{60} heteroarylene group include two or more rings, the rings may be fused to each other.

As used herein, a C_6 - C_{60} aryloxy group refers to a group represented by $-OA_{102}$ (where A_{102} is the C_6 - C_{60} aryl group), and a C_6 - C_{60} arylthio group refers to a group represented by $-SA_{103}$ (where A_{103} is the C_6 - C_{60} aryl group).

As used herein, a monovalent non-aromatic condensed polycyclic group refers to a monovalent non-aromatic condensed polycyclic group that has two or more rings condensed to each other, only carbon atoms (for example, the number of carbon atoms may be in a range of 8 to 60) as ring-forming atoms, and no overall aromaticity. Non-limiting example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. As used herein, a divalent non-aromatic condensed polycyclic group refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

As used herein, a monovalent non-aromatic condensed heteropolycyclic group refers to a monovalent group that has two or more rings condensed to each other, has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, and carbon atoms as the remaining ring-forming atoms (for example, the number of carbon atoms may be in a range of 1 to 60), and has no overall aromaticity. Non-limiting example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. As used herein, a divalent non-aromatic condensed heteropolycyclic group refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

As used herein, at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10} cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, substituted a divalent non-aromatic condensed polycyclic group, substituted a divalent non-aromatic condensed heteropolycyclic group, substituted C_1 - C_{60} alkyl group, substituted C_2 - C_{60} alkenyl group, substituted C_2 - C_{60} alkynyl group, substituted C_1 - C_{60} alkoxy group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_6 - C_{60} aryloxy group, substituted C_6 - C_{60} arylthio group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed

polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁₁)(Q₁₂)(Q₁₃);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₂₁)(Q₂₂)(Q₂₃); and

—Si(Q₃₁)(Q₃₂)(Q₃₃),


where Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

As used herein, “Ph” refers to a phenyl group, “Me” refers to a methyl group, “Et” refers to an ethyl group, and “ter-Bu” or “But” refers to a tert-butyl group.

Hereinafter, an organic light-emitting device according to one or more embodiments of the present invention will be described with reference to Synthesis Examples and Examples. The expression “B was used instead of A” when describing Synthesis Examples means that a molar equivalent of A was identical to a molar equivalent of B.


EXAMPLE

Synthesis Example 1: Synthesis of Compound 1



77

-continued



Compound 1

Synthesis of Intermediate 1-1

(2-(4-methylphenyl)-4-amino pyridine)

25 g (183.89 mmol) of 4-methylphenyl boronic acid, 19.70 g (153.24 mmol) of 2-chloro-4-aminopyridine, 80 mL of a 2M K_2CO_3 aqueous solution, and 350 mL of toluene were added to a 1000 mL 3-neck round bottom flask that was first dried using a torch. The reaction mixture was degassed for 30 minutes and heated to a temperature of 60° C. Then, 8.87 g (3 mol %) of $Pd(PPh_3)_4$ was added thereto, and the resulting mixture was stirred at 90° C. under nitrogen airflow for 15 hours. The obtained reaction mixture was cooled to room temperature and washed with an excessive amount of water. Then, an organic layer was extracted therefrom using 2M hydrochloric acid and ethyl acetate, and moisture was removed therefrom with anhydrous $MgSO_4$. The resultant thus obtained was filtered using a low-pressure filtering device and separated through column chromatography using dichloromethane, as a solvent, and thus Intermediate 1-1 (2-(4-methylphenyl)-4-aminopyridine) (yield: 76%) was obtained.

1H -NMR (300 MHz, $CDCl_3$, ppm): δ 8.32-8.30 (d, 1H), 7.84-7.81 (d, 2H), 7.25 (s, 1H), 6.95-6.94 (d, 2H), 6.350-6.47 (m, 1H), 4.19 (s, 2H), 2.41 (s, 3H)

Synthesis of Intermediate 1-2

(2-(4-methylphenyl)-4-bromopyridine)

21.53 g (116.89 mmol) of Intermediate 1-1, 450 mL of HBr, 400 mL of distilled water, and (0.44 g, 3 mol %) of CuBr were added to a 1000 mL 3-neck round bottom flask that was first dried using a torch. The reaction mixture was stirred at 60° C. under nitrogen airflow for 30 minutes. Then, 31.71 g (459.72 mmol) of 5N $NaNO_2$ was added thereto, and the resulting mixture was stirred at 60° C. under nitrogen airflow for 1 hour. The obtained reaction mixture was cooled to room temperature and titrated to pH 10 using 50% NaOH. Then, the resultant was extracted therefrom using water and dichloromethane, and moisture was removed therefrom with anhydrous $MgSO_4$. The resultant thus obtained was filtered using a low-pressure filtering device and separated through column chromatography using n-hexane/dichloromethane (at a v/v ratio of 1:1), as a solvent, and thus Intermediate 1-2 (2-(4-methylphenyl)-4-bromopyridine) (yield: 46%) was obtained.

1H -NMR (300 MHz, $CDCl_3$, ppm): δ 8.53-8.49 (d, 1H), 7.90-7.89 (d, 2H), 7.87 (s, 1H), 7.40-7.39 (m, 1H), 7.32-7.29 (d, 2H), 2.43 (s, 3H)

78

Synthesis of Intermediate 1-3

(2-(4-methylphenyl)-4-cyclohexylpyridine)

8.38 g (33.77 mmol) of Intermediate 1-2 and 200 mL of THF were added to a 50 mL 3-neck round bottom flask that was first dried using a torch. The reaction mixture was degassed for 30 minutes and stirred at 130° C. under nitrogen airflow for 1 hour. After cooling the resulting reaction mixture to a temperature of -25° C. using liquid nitrogen, 0.18 g (1 mol %) of $Ni(dppp)_2Cl_2$ was injected thereto, and the mixture was stirred for 30 minutes. Then, 20.26 mL (50.66 mmol) of cyclohexylmagnesium bromide was injected thereto, and the obtained mixture was stirred for 4 hours and then heated to room temperature. The resultant was extracted therefrom using 2M hydrochloric acid and ether, and moisture was removed therefrom with anhydrous $MgSO_4$. The resultant thus obtained was filtered using a low-pressure filtering device and separated through column chromatography using n-hexane/ethyl acetate (at a v/v ratio of 20:1), as a solvent, and thus Intermediate 1-3 (2-(4-methylphenyl)-4-cyclohexylpyridine) (yield: 58%) was obtained.

1H -NMR (300 MHz, $CDCl_3$, ppm): δ 8.58-8.56 (d, 1H), 7.90-7.88 (d, 2H), 7.55 (s, 1H), 7.30-7.28 (d, 2H), 7.08-7.06 (m, 1H), 2.61-2.52 (m, 1), 2.42 (s, 3H), 1.95-1.77 (m, 5H), 1.55-1.27 (m, 5H)

Synthesis of Compound 1

3.5 eq. (5 g, 19.89 mmol) of Intermediate 1-3, 1 eq. of iridium(III) acetylacetonate ($Ir(acac)_3$), and ethylene glycol were added to a dried 3-neck flask. The reaction mixture was degassed for 30 minutes and stirred at 200° C. under nitrogen airflow for 36 hours. Then, the resulting reaction mixture was cooled to room temperature, the resultant was extracted therefrom using distilled water and ethyl acetate, and moisture was removed therefrom with anhydrous $MgSO_4$. The resultant thus obtained was filtered using a low-pressure filtering device and separated through column chromatography using n-hexane/ethyl acetate (at a v/v ratio of 6:1), as a solvent, and thus, Compound 1 (yield: 21%) was obtained.

1H -NMR (300 MHz, $CDCl_3$, ppm): δ 7.89 (s, 1H), 7.66-7.64 (d, 1H), 7.19-7.17 (d, 1H), 6.97-6.94 (m, 1H), 6.60-6.57 (d, 1H), 6.51 (s, 1H), 2.58-2.49 (m, 1), 2.43 (s, 3H), 1.95-1.78 (m, 5H), 1.55-1.28 (m, 5H)

Synthesis Example 2: Synthesis of Compound 17

Synthesis of

2-(4-cyclohexylphenyl)-4-methylpyridine

1.02 g (41.81 mmol) of Mg and 50 mL of diethyl ether were added to a 100 mL 3-neck flask under nitrogen airflow, 10 g (41.81 mmol) of 1-bromo-4-cyclohexylbenzene was added to the flask, and the mixture was stirred for 3 hours to prepare a Grignard reagent. Also, 6.25 g (36.36 mmol) of 2-bromo-4-methylpyridine and 0.19 g (0.36 mmol) of $Ni(dppp)Cl_2$ were added to 50 mL of diethyl ether in a 250 mL 3-neck flask, and the resulting mixture was stirred. Then, the Grignard reagent was slowly and dropwisely added thereto to allow the solution to react overnight. Water was added to the resultant thus obtained to complete the reaction. Then, an organic layer was extracted therefrom using methylene chloride, and moisture was removed therefrom with anhydrous $MgSO_4$. Next, a solvent was removed from the

resultant, and the resultant was purified by column chromatography to obtain 3.47 g of 2-(4-cyclohexylphenyl)-4-methylpyridine (yield: 38%).

¹H-NMR (300 MHz, CDCl₃, δ/ppm): 8.54 (d, 1H), 7.92 (d, 2H), 7.54 (s, 1H), 7.33 (d, 2H), 7.05 (d, 1H), 2.58 (m, 1H), 2.42 (s, 3H), 1.86 (m, 5H), 1.41 (m, 5H)

Synthesis of Compound 17

1 g (3.98 mmol) of 2-(4-cyclohexylphenyl)-4-methylpyridine and 0.59 g (1.21 mmol) of iridium acetylacetonate were added to a 50 ml 3-neck flask, and 10 ml of ethylene glycol was added to the flask. The resultant thus obtained was degassed, stirred at 180° C. for 24 hours, and cooled to room temperature. Water was added thereto, and the resulting mixture was stirred, filtered using a filter, washed with EtOH, and purified by column chromatography to obtain 0.45 g of Compound 17 (yield: 40%).

¹H-NMR (300 MHz, CD₂Cl₂, δ/ppm): 7.69 (s, 3H), 7.56 (d, 3H), 7.45 (d, 3H), 6.75 (m, 9H), 2.43 (s, 9H), 2.23 (s, 3H), 1.73 (m, 15H), 1.33 (m, 15H)

Evaluation Example 1

Evaluation of Light-Emitting Characteristics of Compound 1 and Compound 17

Light-emitting characteristics of each of Compounds 1 and 17 were evaluated by analyzing a UV absorption spectrum and a PL spectrum of Compounds 1 and 17. First, Compound 1 was diluted in CH₂Cl₂ at a concentration of 10⁻⁵ M to obtain a UV absorption spectrum of Compound 1 by using a Shimadzu UV-350 Spectrometer. This process was then repeated for Compound 17 and Ir(ppy)₃. In addition, Compound 1 was diluted in CH₂Cl₂ at a concentration of 10⁻⁵ M to obtain a PL spectrum of Compound 1 by using an ISS PC1 Spectrofluorometer with a xenon lamp. This process was then repeated for Compound 17 and Ir(ppy)₃. The results are shown in Table 1, and the UV absorption spectrum and the PL spectrum of Compound 1 and Ir(ppy)₃ are shown in FIG. 2.

TABLE 1

	Peak position of UV absorption spectrum (nm)	Maximum emission wavelength in PL spectrum (nm)	PL color coordinate
Compound 1	289, 377	466	(0.217, 0.611)
Compound 17	247, 288, 380	508	(0.245, 0.634)
Ir(ppy) ₃	244, 283, 380	513	(0.266, 0.633)

Compound 1






TABLE 1-continued

	Peak position of UV absorption spectrum (nm)	Maximum emission wavelength in PL spectrum (nm)	PL color coordinate
--	--	---	---------------------

Compound 17



Ir(ppy)₃



Referring to Table 1 and FIG. 2, emission peaks of Compound 1 and Compound 17 have maximum emission wavelengths (λ_{max}) that are smaller than that of an emission peak of Ir(ppy)₃, and accordingly, Compound 1 and Compound 17 can emit green light with high color purity.

Example 1

An indium tin oxide (ITO) glass substrate (available from Corning) having an ITO layer deposited thereon at a thickness of 15 Ω/cm² (1200 Å) was cut to a size of 50 mm×50 mm×0.7 mm, sonicated in isopropyl alcohol and pure water for 5 minutes each, and then cleaned with UV and ozone for 30 minutes. The obtained ITO glass substrate was then mounted on a vacuum depositor.

4,4'-Bis[N-phenyl-N-(9-phenylcarbazol-3-yl)amino]-1,1'-biphenyl (NPB) was deposited on the ITO glass substrate to form a hole injection layer having a thickness of 400 Å, TCTA was deposited on the hole injection layer to form a hole transport layer having a thickness of 100 Å, and then CBP (a host) and Compound 1 (a dopant) were co-deposited at a weight ratio of 95:5 on the hole transport layer to form an emission layer having a thickness of 300 Å. Bphen was deposited on the emission layer to form an electron transport layer having a thickness of 500 Å, LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was deposited on the electrode injection layer to form a cathode having a thickness of 1100 Å, thereby completing the manufacture of an organic light-emitting device.

Example 2 and Comparative Example 1

Organic light-emitting devices were manufactured in the same (or substantially the same) manner as in Example 1,

81

except that compounds shown in Table 2 were respectively used instead of Compound 1 as a dopant.


Evaluation Example 2

Driving voltages, current densities, light-emitting efficiencies, and color coordinates of the organic light-emitting devices prepared in Examples 1 and 2 and Comparative Example 1 were evaluated by using a Keithley SMU 236 and a luminance meter PR650, and the results are shown in Table 2.


TABLE 2

	Dopant	Driving voltage (V)	Current density (mA/cm ²)	Light-emitting efficiency (cd/A)	Color coordinate
Example 1	Compound 1	4.7	9.3	96.7	(0.229, 0.714)
Example 2	Compound 17	3.8	10.2	87.9	(0.238, 0.707)
Comparative Example 1	Compound A	5.3	15.8	57.2	(0.262, 0.697)

Compound 1




Compound 17



82

TABLE 2-continued

	Dopant	Driving voltage (V)	Current density (mA/cm ²)	Light-emitting efficiency (cd/A)	Color coordinate
5	Compound A				
10					
15					
20					



Referring to Table 2, driving voltages, current densities, light-emitting efficiencies, and color purities of the organic light-emitting devices prepared in Examples 1 and 2 were significantly better as compared to those of the organic light-emitting device prepared in Comparative Example 1.

As described above, an organic light-emitting device including an organometallic compound according to one or more embodiments of the present invention may have low driving voltage, high efficiency, and excellent color purity.


It should be understood that the exemplary embodiments described therein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment should typically be considered as available for other similar features or aspects in other exemplary embodiments.

While one or more exemplary embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims and equivalents thereof.

What is claimed is:

1. An organometallic compound represented by Formula 1:

Formula 1



wherein, in Formula 1,

R₁ and R₂ are each independently selected from: a C₁-C₁₀ alkyl group and a C₅-C₁₀ cycloalkyl group; and


83

- a C₅-C₁₀ cycloalkyl group substituted with at least one C₁-C₁₀ alkyl group, and at least one of R₁ and R₂ is selected from:
- a C₅-C₁₀ cycloalkyl group; and
 - a C₅-C₁₀ cycloalkyl group substituted with at least one C₁-C₁₀ alkyl group.
2. The organometallic compound of claim 1, wherein R₁ and R₂ are each independently selected from:
- a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group; and
 - a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group, and
- at least one of R₁ and R₂ is selected from:
- a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group; and
 - a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group.
3. The organometallic compound of claim 1, wherein R₁ and R₂ are each independently selected from:
- a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group; and
 - a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group, each substituted with at least one selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, and a tert-octyl group.


84

- selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group.
4. The organometallic compound of claim 1, wherein R₁ and R₂ are each independently selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group, and
- at least one of R₁ and R₂ is selected from a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cylcooctyl group, an adamantanyl group, and a norbornanyl group.
5. The organometallic compound of claim 1, wherein R₁ is a C₁-C₁₀ alkyl group, and R₂ is selected from:
- a C₅-C₁₀ cycloalkyl group; and
 - a C₅-C₁₀ cycloalkyl group substituted with at least one C₁-C₁₀ alkyl group.
6. The organometallic compound of claim 1, wherein R₁ is selected from:
- a C₅-C₁₀ cycloalkyl group; and
 - a C₅-C₁₀ cycloalkyl group substituted with at least one C₁-C₁₀ alkyl group, and
- R₂ is a C₁-C₁₀ alkyl group.
7. The organometallic compound of claim 1, wherein R₁ is selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group, and R₂ is selected from groups represented by Formulae 2-1 to 2-6:


Formula 2-1




Formula 2-2



Formula 2-3





Formula 2-4









85

-continued



8. The organometallic compound of claim 1, wherein R_1 is selected from groups represented by Formulae 2-1 to 2-6, and R_2 is selected from a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, and a tert-butyl group:



86

9. The organometallic compound of claim 1 having an emission peak with a maximum emission wavelength in a range of about 460 nm to about 510 nm.

10. The organometallic compound of claim 1, wherein the organometallic compound is one of Compounds 1 to 32:

Formula 2-5

Formula 2-6

Formula 2-1




Formula 2-2

Formula 2-3

Formula 2-4

Formula 2-5


Formula 2-6



87

-continued

4



5

10


15

20

88


-continued

7



5 25

8




30

35


40

45



6

9




50

55

60


65



89

-continued

10



5

10


15

20

90


-continued

13



11 25

14




30

35

40

45

12





50

55

60


65

15



91

-continued



16

5


10

15

20

92

-continued



19

25


17

30

35

40

45



20



18

50

55

60


65



21

93


-continued



22

94

-continued



25

5


10

15

20

23

25




30

35

40

24

45




50

55


60

65

26






27



95

-continued



96

-continued

5

10

15

20

25

29

30

35

40

45



30

50

55

60

65



11. An organic light-emitting device comprising:

a first electrode;

a second electrode facing the first electrode; and

an organic layer between the first electrode and the second electrode,

wherein the organic layer comprises an emission layer and at least one organometallic compound of claim 1.

12. The organic light-emitting device of claim 11, wherein the first electrode is an anode,

the second electrode is a cathode, and

the organic layer comprises:


a hole transport region between the first electrode and the emission layer, the hole transport region comprising at least one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer and

an electron transport region between the emission layer and the second electrode, the electron transport region comprising at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.


13. The organic light-emitting device of claim 11, wherein the organometallic compound is in the emission layer.

14. The organic light-emitting device of claim 13, wherein a concentration of the organometallic compound is in a range of about 1 wt % to about 30 wt % based on 100 wt % of the emission layer.

15. The organic light-emitting device of claim 13, wherein the organometallic compound in the emission layer functions as a phosphorescent dopant, and the emission layer further comprises a compound represented by Formula 50 or Formula 51:



Formula 50



Formula 51

wherein, in Formulae 50 and 51,

A₁ is CR₁₁ or N, A₂ is CR₁₂ or N, A₃ is CR₁₃ or N, A₄ is CR₁₄ or N, A₅ is CR₁₅ or N, A₆ is CR₁₆ or N, A₇ is CR₁₇ or N, A₈ is CR₁₈ or N, A₉ is CR₁₉ or N, A₁₀ is CR₂₀ or N, A₁₁ is CR₂₁ or N, A₁₂ is CR₂₂ or N, A₁₃ is CR₂₃ or N, A₁₄ is CR₂₄ or N, A₁₅ is CR₂₅ or N, A₁₆ is CR₂₆ or N, A₁₇ is CR₂₇ or N, A₁₈ is CR₂₈ or N, A₁₉ is CR₂₉ or N, A₂₀ is CR₃₀ or N, A₂₁ is CR₃₁ or N, A₂₂ is CR₃₂ or N, A₂₃ is CR₃₃ or N, and A₂₄ is CR₃₄ or N,

rings B₁ and B₂ are each independently selected from a benzene, a pyridine, a pyrimidine, a pyrazine, a naphthalene, a quinoline, an isoquinoline, a quinoxaline, a quinazoline, a cinnoline, a fluorene, a carbazole, a dibenzofuran, and a dibenzothiophene,

X is —C(R₄₀)(R₄₁)—, —N(R₄₂)—, —S—, —O—, —Si(R₄₃)(R₄₄)—, P(R₄₅)—, —P(=O)(R₄₆)—, or —B(R₄₇)—,

Ar₁ is selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a

substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

R₁₁ to R₃₆ and R₄₀ to R₄₇ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁)(Q₂), —Si(Q₃)(Q₄)(Q₅), and B(Q₆)(Q₇), where at least two of R₁₁ to R₂₉ are optionally linked to each other to form a saturated or unsaturated ring,

e and f1 are each independently an integer selected from 0 to 2,

f2 and f3 are each independently an integer selected from 0 to 7,

at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted a divalent non-aromatic condensed polycyclic group, substituted a divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group; a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a

C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and B(Q₂₆)(Q₂₇); and

—N(Q₃₁)(Q₃₂), —Si(Q₃₃)(Q₃₄)(Q₃₅), and B(Q₃₆)(Q₃₇), wherein Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

16. The organic light-emitting device of claim **15**, wherein at least one of A₁₅ to A₁₉ in Formula 50 is N, and at least one of A₂₀ to A₂₄ in Formula 51 is N, rings B₁ and B₂ in Formula 51 are each independently selected from a benzene, a fluorene, a dibenzofuran, and a dibenzothiophene,

in Formulae 50 and 51, Ar₁ is selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a

phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylenylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylenylene group, an oxadiazolylenylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a thiadiazolylenylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylenylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylenylene group, an oxadiazolylenylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a thiadiazolylenylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group.

group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group,

R₁₁ to R₃₆ and R₄₀ to R₄₇ are each independently selected from:

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group,

an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and


a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophe-

103

nyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$,

wherein Q_{33} to Q_{35} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spirofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.

17. The organic light-emitting device of claim 13, wherein the organometallic compound in the emission layer functions as a phosphorescent dopant, and the emission layer further comprises at least one compound represented below:



5

10

15

20

25

30

35

40

45

50

55


60

65


104

-continued


80




81



82




83



105

-continued

84



5


10

15

20

25

85



30

35

40


45

86 50

55


60

65

**106**


-continued

87




25

88






45

89







107

-continued


**108**

-continued



109

-continued



97

5

10

15

20

25


98

30

35

40

45




99

55


60

65




110

-continued




100

101






102



111

-continued




112

-continued

103

106



104

20

107


25

30

105

35

40



18. The organic light-emitting device of claim 13, wherein
the organic light-emitting device emits green phosphores-
cent light.

* * * * *

专利名称(译)	有机金属化合物和包括其的有机发光器件		
公开(公告)号	US9991454	公开(公告)日	2018-06-05
申请号	US14/967202	申请日	2015-12-11
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD. 产学合作基础庆尚大学		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM HEEYEON KWON SOONKI KIM MIKYUNG KIM YUNHI SEO JIHYUN JEONG HYEIN		
发明人	KIM, HEEYEON KWON, SOONKI KIM, MIKYUNG KIM, YUNHI SEO, JIHYUN JEONG, HYEIN		
IPC分类号	C09K11/00 C07D413/00 H01L51/00 C07F15/00 C09K11/06 C09K11/02 C07D413/14 H01L51/50		
CPC分类号	H01L51/0085 C07D413/00 C07D413/14 C07F15/0033 C09K11/06 C09K11/025 H01L51/5016 C09K2211/1007 C09K2211/1029 C09K2211/185		
优先权	1020140181615 2014-12-16 KR		
其他公开文献	US20160172607A1		
外部链接	Espacenet USPTO		

摘要(译)

有机发光装置包括第一电极;面向第一电极的第二电极;第一电极和第二电极之间的有机层, 其中有机层包括发光层和至少一种式1的有机金属化合物。 包含式1的有机金属化合物的有机发光装置可具有低驱动电压, 高效率和优异的色纯度。

10

190
150
110