



US 20150364695A1


(19) **United States**(12) **Patent Application Publication**
Hwang et al.(10) **Pub. No.: US 2015/0364695 A1**(43) **Pub. Date: Dec. 17, 2015**(54) **CONDENSED CYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**(52) **U.S. CL.**CPC **H01L 51/0071** (2013.01); **C07D 519/00**
(2013.01); **H01L 51/5056** (2013.01)(71) Applicants: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-City (KR); **PUSAN NATIONAL
UNIVERSITY
INDUSTRY-UNIVERSITY
COOPERATION FOUNDATION**,
Busan (KR)

(57)

ABSTRACT

An organic light-emitting device includes a first electrode, a second electrode, and an organic layer between the first electrode and the second electrode and including at least one condensed cyclic compound represented by Formula 1:


Formula 1


(72) Inventors: **Jin-Soo Hwang**, Yongin-City (KR);
Myeong-Suk Kim, Yongin-City (KR);
Sung-Wook Kim, Yongin-City (KR);
Sam-Il Kho, Yongin-City (KR);
Hong-Suk Seo, Busan (KR)(21) Appl. No.: **14/596,574**(22) Filed: **Jan. 14, 2015**(30) **Foreign Application Priority Data**

Jun. 16, 2014 (KR) 10-2014-0072969

Publication Classification(51) **Int. Cl.****H01L 51/00** (2006.01)**C07D 519/00** (2006.01)

The organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have low driving voltage, high efficiency, high brightness, and long lifespan.

10




CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2014-0072969, filed on Jun. 16, 2014, in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

[0002] 1. Field

[0003] One or more aspects of embodiments of the present invention relate to a condensed cyclic compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art

[0005] Organic light emitting devices are self-emission devices that have wide viewing angles, high contrast ratios, and short response times, and have excellent brightness, driving voltage, and response speed characteristics, as well as the ability to produce full-color images.

[0006] The organic light-emitting device may include a first electrode positioned on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, sequentially positioned on the first electrode. Holes from the first electrode may pass through the hole transport region toward the emission layer, and electrons from the second electrode may pass through the electron transport region toward the emission layer. Carriers (i.e. holes and electrons), can recombine in the emission layer to produce excitons. When these excitons drop from an excited state to a ground state, light is generated.


[0007] Conventional arylamine hole carrier materials for a hole transport region have good transport efficiency, but may have short lifespan.

SUMMARY

[0008] One or more aspects of embodiments of the present invention are directed to a novel condensed cyclic compound and an organic light-emitting device including the same. One or more aspects of embodiments of the present invention provide an organic light-emitting device with a condensed cyclic compound that provides both improved hole injection and transport capacity, and long lifespan to the organic light-emitting device.

[0009] In one embodiment, a condensed cyclic compound is represented by Formula 1:

Formula 1



[0010] In Formula 1,

[0011] X is an oxygen (O) atom or a sulfur (S) atom;

[0012] R₁ to R₁₀ are each independently selected from a hydrogen, a deuterium, a halogen atom, a cyano group, a nitro

group, a hydroxyl group, a carboxyl acid, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₁-C₃₀ heteroaryl group (e.g. a substituted or unsubstituted C₂-C₃₀ heteroaryl group), a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group,

[0013] a plurality of R₁ and a plurality of R₂ are each independent (i.e. each R₁ of the plurality of R₁ may be the same as or different from another R₁, and each R₂ of the plurality of R₂ may be the same as or different from another R₂),

[0014] one or more of the plurality of R₁ and the plurality of R₂ are linked to each other to form a condensed ring;

[0015] at least one substituent of the substituted C₁-C₁₀ alkyl group, substituted C₂-C₁₀ alkenyl group, substituted C₂-C₁₀ alkynyl group, substituted C₁-C₁₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₃-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ heterocycloalkenyl group, substituted C₆-C₃₀ aryl group, substituted C₁-C₃₀ heteroaryl group (e.g. substituted C₂-C₃₀ heteroaryl group), substituted C₆-C₃₀ aryloxy group, and substituted C₆-C₃₀ arylthio group is selected from

[0016] a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl, and a C₁-C₁₀ alkoxy group;

[0017] a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

[0018] a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, and a monovalent C₂-C₃₀ non-aromatic condensed polycyclic group;

[0019] a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic

group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, C₃-C₁₀ a cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

[0020] —Si(Q₃₁)(Q₃₂)(Q₃₃) and —B(Q₃₄)(Q₃₅), and

[0021] Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₅ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group.

[0022] According to one or more embodiments of the present invention, an organic light-emitting device includes a first electrode, a second electrode facing the first electrode, and an organic layer between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes at least one condensed cyclic compound described above.


BRIEF DESCRIPTION OF THE DRAWINGS

[0023] These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawing, which is a schematic view of an organic light-emitting device according to an embodiment of the present invention.

DETAILED DESCRIPTION

[0024] Reference will now be made in more detail to embodiments, examples of which are illustrated in the accompanying drawing, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the drawing, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list. Further, the use of “may” when describing embodiments of the present invention refers to “one or more embodiments of the present invention.”

[0025] A condensed cyclic compound according to an embodiment of the present invention is represented by Formula 1:



[0026] In Formula 1,

[0027] X is an oxygen (O) atom or a sulfur (S) atom;

[0028] R₁ to R₁₀ are each independently selected from a hydrogen, a deuterium, a halogen atom, a cyano group, a nitro group, a hydroxyl group, a carboxyl acid, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₁-C₃₀ heteroaryl group (e.g. a substituted or unsubstituted C₂-C₃₀ heteroaryl group), a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, and a substituted or unsubstituted monovalent C₆-C₃₀ non-aromatic condensed polycyclic group.

[0029] a plurality of R₁ (R_{1s}) and a plurality of R₂ (R_{2s}) are each independent (i.e. each R₁ of the plurality of R₁ may be the same as or different from another R₁, and each R₂ of the plurality of R₂ may be the same as or different from another R₂),

[0030] one or more of the plurality of R₁ and the plurality of R₂ are linked to each other to form a condensed ring;

[0031] at least one substituent of the substituted C₁-C₁₀ alkyl group, substituted C₂-C₁₀ alkenyl group, substituted C₂-C₁₀ alkynyl group, substituted C₁-C₁₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₃-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ heterocycloalkenyl group, substituted C₆-C₃₀ aryl group, substituted C₁-C₃₀ heteroaryl group (e.g. substituted C₂-C₃₀ heteroaryl group), substituted C₆-C₃₀ aryloxy group, substituted C₆-C₃₀ arylthio group, and substituted monovalent C₆-C₃₀ non-aromatic condensed polycyclic group is selected from

[0032] a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl, and a C₁-C₁₀ alkoxy group;

[0033] a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid

or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

[0034] a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, and a monovalent C₂-C₃₀ non-aromatic condensed polycyclic group;

[0035] a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, C₃-C₁₀ a cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

[0036] —Si(Q₃₁)(Q₃₂)(Q₃₃) and —B(Q₃₄)(Q₃₅), and

[0037] Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₅ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group.

[0038] In one embodiment, the plurality of R₁ are each independently selected from a hydrogen and a C₁-C₁₀ alkyl group.

[0039] In another embodiment, at least one of the plurality of R₁ is selected from a hydrogen and a C₁-C₁₀ alkyl group, and two or more of the plurality of R₁ (different from the at least one of the plurality of R₁) are linked to each other to form a substituted or unsubstituted naphthylene group or anthrylene group that is fused together with an 'a' benzene ring, and

[0040] at least one substituent of the substituted naphthylene group and/or the substituted anthrylene group may be selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, and a C₆-C₃₀ aryl group.

[0041] In one embodiment, the plurality of R₂ are each independently selected from a hydrogen and a C₁-C₁₀ alkyl group.

[0042] In another embodiment, at least one of the plurality of R₂ is selected from a hydrogen and a C₁-C₁₀ alkyl group, and two or more of the plurality of R₂ (different from the at least one of the plurality of R₂) are linked to each other to form

a substituted or unsubstituted naphthylene group or anthrylene group that is fused together with a 'b' benzene ring, and

[0043] at least one substituent of the substituted naphthylene group and/or the substituted anthrylene group may be selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, and a C₆-C₃₀ aryl group.

[0044] In one embodiment, at least one of the plurality of R₁ and R₂ is selected from a hydrogen and a C₁-C₁₀ alkyl group, and at least another one R₁ of the plurality of R₁ and at least another one R₂ of the plurality of R₂ are linked to each other to form a substituted or unsubstituted C₁₃-C₃₀ condensed ring that is fused together with the 'a' and 'b' benzene rings,

[0045] where at least one substituent of the substituted C₁₃-C₃₀ condensed ring may be selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, and a C₆-C₃₀ aryl group.


[0046] In one embodiment, R₃ to R₁₀ may be each independently selected from a hydrogen, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, a decyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a biphenyl group, a heptalenyl group, a phenalenyl group, a fluorenyl group, a phenanthrenyl group, an anthryl group, a fluoranthenyl group, a pyrenyl group, a benzofluorenyl group, a naphthacenyl group, a chrysenyl group, a triphenylenyl group, a terphenyl group, a perylenyl group, a picenyl group, a hexacenyl group, a spiro fluorenyl group, a pyrrolyl group, a furyl group, a pyrazolyl group, an imidazolyl group, an oxazolyl group, an isoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a pyranyl group, a thiophenyl group, a thiazolyl group, an isothiazolyl group, a thiopyranyl group, an indolyl group, an isoindolyl group, an indolizinyll group, a benzofuryl group, an isobenzofuryl group, an indazolyl group, a benzimidazolyl group, a benzoxazolyl group, a benzisoxazolyl group, an imidazopyridyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a phthalazinyl group, a quinazolinyl group, a quinoxalinyl group, a naphthyridinyl group, a cinnolyl group, a benzothiophenyl group, a benzothiazolyl group, a carbazolyl group, a benzocarbazolyl group, a pyridoindolyl group, a dibenzofuryl group, a phenanthridinyl group, a benzoquinolyl group, a phenazinyl group, a dibenzosilolyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzacridinyl group; and

[0047] a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, and a decyl group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, and an amino group; and


[0048] a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a biphenyl group, a heptalenyl group, a phenalenyl group, a fluorenyl group, a phenanthrenyl

group, an anthryl group, a fluoranthenyl group, a pyrenyl group, a benzofluorenyl group, a naphthacenyl group, a chrysenyl group, a triphenylenyl group, a terphenyl group, a perylenyl group, a picenyl group, a hexacenyl group, a spiro fluorenyl group, a pyrrolyl group, a furyl group, a pyrazolyl group, an imidazolyl group, an oxazolyl group, an isoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a pyranyl group, a thiophenyl group, a thiazolyl group, an isothiazolyl group, a thiopyranyl group, an indolyl group, an isoindolyl group, an indoliziny group, a benzofuryl group, an isobenzofuryl group, an indazolyl group, a benzimidazolyl group, bensoxazolyl group, an benisoxazolyl group, an imidazopyridyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a phthalazinyl group, a quinazolinyl group, a quinoxaliny group, a naphthyridinyl group, a cinnoliny group, a benzothiophenyl group, a benzothiazolyl group, a carbazolyl group, a benzocarbazolyl group, a pyridoindolyl group, a dibenzofuryl group, a phenanthridinyl group, benzoquinolyl group, a phenazinyl group, a dibenzosilolyl group, a dibenzothiophenyl group and a benzocarbazolyl group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₄-C₃₀ heteroaryl group, a C₅-C₃₀ aryloxy group, a C₅-C₃₀ arylthio group, and —Si(Q₃₁)(Q₃₂)(Q₃₃) (where Q₃₁ to Q₃₃ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, and a C₆-C₂₀ aryl group).


[0049] In one embodiment, an A part represented by a dotted line box in Formula 1 may be selected from Formulae 2A to 2AA:




2A



2B




2C




2D


-continued




2E




2F




2G




2H



2I




2J




2K







-continued



-continued



[0050] In one embodiment, B and C parts represented by dotted line boxes in Formula 1 may be each independently selected from Formulae 3A to 3F:



[0051] According to one or more embodiments of the present invention, the condensed cyclic compound represented by Formula 1 may be represented by one of Formula 1-1 and Formula 1-2:

3A

Formula 1-1



3B

3C

3D

3E

3F



[0052] In Formula 1-1 and Formula 1-2, X is an oxygen atom or a sulfur atom, and R_1 to R_{10} are as described herein.

[0053] In one embodiment, the plurality of R_1 are each independently selected from a hydrogen and a C_1 - C_{10} alkyl group.

[0054] In another embodiment, at least one of the plurality of R_1 is selected from a hydrogen and a C_1 - C_{10} alkyl group, and two or more of the plurality of R_1 (different from the at least one of the plurality of R_1) are interlinked with each other to form a substituted or unsubstituted naphthylene group or anthrylene group that is fused together with an 'a' benzene ring, and

[0055] at least one substituent of the substituted naphthylene group and/or the substituted anthrylene group may be selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{10} alkyl group, and a C_6 - C_{30} aryl group.

[0056] In one embodiment, the plurality of R_2 are each independently selected from a hydrogen and a C_1 - C_{10} alkyl group,


[0057] In another embodiment, at least one of the plurality of R_2 is selected from a hydrogen and a C_1 - C_{10} alkyl group, and two or more of the plurality of R_2 (different from the at least one of the plurality of R_2) are linked to each other to form a substituted or unsubstituted naphthylene group or anthrylene group that is fused together with a 'b' benzene ring, and

[0058] at least one substituent of the substituted naphthyl-ene group and/or the substituted anthrylene group may be selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{10} alkyl group, and a C_6 - C_{30} aryl group.


[0059] In one embodiment, at least one of the plurality of R_1 and R_2 is selected from a hydrogen and a C_1 - C_{10} alkyl group, and at least another one R_1 of the plurality of R_1 and at least another one R_2 of the plurality of R_2 are linked to each other to form a substituted or unsubstituted C_{13} - C_{30} condensed ring that is fused with the 'a' and 'b' benzene rings,

[0060] where at least one substituent of the substituted C_{13} - C_{30} condensed ring may be selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{10} alkyl group, and a C_6 - C_{30} aryl group.


[0061] In one embodiment, an A1 part represented by a dotted line box in Formula 1-1 and Formula 1-2 may be selected from Formulae 2A to 2AA:




2A




2B




2C



2D




2E




2F


-continued




2G




2H




2I




2J



2K




2L



2M


-continued



-continued


2N

2U




2O

2V




2P

2W




2Q

2X




2R

2Y




2S

2Z




2T

-continued



2AA


-continued




3F

[0062] In one embodiment, B1 and C1 parts represented by dotted line boxes in Formula 1-1 and Formula 1-2 may be each independently selected from Formulae 3A to 3F:


[0063] The condensed cyclic compound of Formula 1 may be represented by one of Compounds 101 to 141 below:




3A




3B




3C




3D




3E




101



102




103




104

-continued


111




112




113




114



115




116




-continued


117




118




119




120



121




122




-continued


123




124




125




126



127




128




-continued


129




130




131




132




133




-continued




134




135




136



137




138




139

-continued



140



141

[0064] The condensed cyclic compound of Formula 1 may include a carbazole derivative group that further includes a sulfur atom and/or an oxygen atom in the condensed ring and that may improve the hole injection and transport capacity, thereby improving the device performance. In other words, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have low driving voltage, high efficiency, high brightness, and long lifespan.

[0065] The condensed cyclic compound represented by Formula 1 may be synthesized by any suitable organic synthetic method. A synthesis method of the condensed cyclic compound should become apparent to one of ordinary skill in the art in view of the following examples.

[0066] In one embodiment, the condensed cyclic compound of Formula 1 may be positioned between a pair of electrodes of an organic light-emitting device. For example, the condensed cyclic compound may be included a hole transport region (e.g., a hole transport layer). In one embodiment of the present invention, an organic light-emitting device includes a first electrode, a second electrode facing the first electrode, and an organic layer between the first electrode and the second electrode and including at least one condensed cyclic compound represented by Formula 1.

[0067] The organic layer may further include a hole transport region between the first electrode and the emission layer, and an electron transport region between the emission layer and the second electrode. The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer. The hole transport region may include at least one selected from an electron blocking layer, a hole transport layer, and a hole injection layer.

[0068] The expression “an organic layer includes at least one condensed cyclic compound represented by Formula 1” as used herein may refer to an organic layer including one condensed cyclic compound represented by Formula 1 or an

organic layer including two or more different condensed cyclic compounds represented by Formula 1.”

[0069] In one embodiment, the organic layer may include only one kind of the condensed cyclic compound of Formula 1. The compound may be included in the emission layer, the electron transport layer, and/or the hole transport layer of the organic light-emitting device. In another embodiment, the organic layer may include two different condensed cyclic compounds of Formula 1. The two different condensed cyclic compounds may both be included in the same layer (for example, the two different condensed cyclic compounds may both be included in the emission layer) or in different layers (for example, one of the two different condensed cyclic compounds may be included in the hole transport layer, and the other one may be included in the electron transport layer.)

[0070] The emission layer, the hole transport region, and/or the electron transport region may include the condensed cyclic compound represented by Formula 1.

[0071] For example, the electron transport region may include the electron transport layer, and the electron transport layer may include the condensed cyclic compound represented by Formula 1.

[0072] The term “organic layer” as used herein refers to a single layer and/or a plurality of layers between the first electrode and the second electrode of an organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0073] The drawing is a schematic view of an organic light-emitting device 10 according to an embodiment of the present invention. The organic light-emitting device 10 includes a substrate 11, a first electrode 13, an organic layer 15, and a second electrode 17.

[0074] Hereinafter, the structure of an organic light-emitting device according to an embodiment of the present invention and a method of manufacturing an organic light-emitting device according to an embodiment of the present invention will be described in connection with the drawing.

[0075] The substrate 11 may be a glass substrate or a transparent plastic substrate, each with good mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water repellency.

[0076] The first electrode 13 may be formed by depositing or sputtering a material for forming the first electrode on the substrate. When the first electrode 13 is an anode, the material for the first electrode 13 may be selected from materials with a high work function, in order for the holes to be easily injected. The first electrode 13 may be a reflective electrode, a transmissive electrode, or a semi-transmissive electrode. A material for the first electrode 13 may be a transparent and highly conductive material, and non-limiting examples of such material include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), and zinc oxide (ZnO). When the first electrode 13 is a semi-transmissive electrode or a reflective electrode, the material for forming the first electrode 13 may include at least one of magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag).

[0077] The first electrode 13 may have a single-layer structure, or a multi-layer structure including two or more layers. For example, the first electrode 13 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 13 is not limited thereto.

[0078] In one embodiment, the organic layer 15 is positioned on the first electrode 13. The organic layer 15 may include an emission layer.

[0079] The organic layer 15 may further include a hole transport region between the first electrode 13 and the emission layer, and an electron transport region disposed between the emission layer and the second electrode 17.

[0080] The hole transport region may include at least one selected from a hole injection layer (HIL), a hole transport layer (HTL), a buffer layer, and an electron blocking layer (EBL), and the electron transport region may include at least one selected from a hole blocking layer (HBL), an electron transport layer (ETL), and an electron injection layer (EIL), but the layers which may be included in the hole transport region or in the electron transport region are not limited thereto.

[0081] The hole transport region may have a single-layered structure formed of a single material, a single-layered structure formed of a plurality of different materials, or a multi-layered structure including a plurality of layers formed of a plurality of different materials.

[0082] For example, the hole transport region may have a single-layered structure formed of a plurality of different materials, or a structure of hole injection layer/hole transport layer, a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole injection layer/buffer layer, a structure of hole injection layer/buffer layer/hole transport layer, a structure of hole transport layer/buffer layer, or a structure of hole injection layer/hole transport layer/electron blocking layer, the layers of each structure being sequentially stacked on the first electrode 13 in the stated order, but the structure of the hole transport region is not limited thereto.

[0083] When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode 13 by various methods, such as, for example, vacuum deposition, spin coating casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, or laser-induced thermal imaging.


[0084] When the hole injection layer is formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of about 100 to about 500° C., a vacuum degree of about 10⁻⁸ to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Å/sec, depending on the compound for forming the hole injection layer, and the structure of the hole injection layer to be formed.

[0085] When the hole injection layer is formed by spin coating, the spin coating may be performed at a coating rate of about 2,000 rpm to about 5,000 rpm, and at a temperature of about 80° C. to 200° C., depending on the compound for forming the hole injection layer, and the structure of the hole injection layer to be formed.


[0086] When the hole transport region includes a hole transport layer, the hole transport layer may be formed on the first electrode 13 or on the hole injection layer by various methods, such as, for example, vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When the hole transport layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the hole transport layer may be similar to the deposition and coating conditions for the hole injection layer.

[0087] The hole transport region may include at least one selected from the condensed cyclic compound represented by Formula 1, m-MTDATA, TDATA, 2-TNATA, NPB, β-NPB,


TPD, spiro-TPD, spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




m-MTDATA





TDATA



2-TNATA




NPB

 β -NPB


methylated-NPB

-continued




spiro-NPB


-continued




TAPC




TPD




TCTA




HMTPD



PEDOT/PSS



spiro-TPD



[0088] In Formulae 201 and 202,

[0089] L₂₀₁ to L₂₀₅ may be each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀

arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group (e.g. a substituted or unsubstituted C_2 - C_{60} heteroarylene group), and a substituted or unsubstituted divalent C_6 - C_{60} non-aromatic condensed polycyclic group;

[0090] xa1 to xa4 may be each independently selected from 0, 1, 2, and 3;

[0091] xa5 may be selected from 1, 2, 3, 4, and 5; and

[0092] R₂₀₁ to R₂₀₄ may be each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₂-C₆₀ heteroaryl group, and a substituted or unsubstituted monovalent C₆-C₃₀ non-aromatic condensed polycyclic group.

[0093] In one embodiment, L_{201} to L_{205} in Formulae 201 and 202 may be each independently selected from

[0094] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorene group, a dibenzofluorene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysenylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylenylene group, a quinazolinylene group, a carbazolylenylene group, and a triazinylenylene group; and

[0095] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysenylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylenylene group, a quinazolinylene group, a carbazolylenylene group, and a triazinylene group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0096] xa1 to xa4 may be each independently 0, 1, or 2;


[0097] xa5 may be 1, 2, or 3;

[0098] R₂₀₁ to R₂₀₄ may be each independently selected from


[0099] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0100] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an azulenyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, but embodiments of the present invention are not limited thereto.


[0101] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A:



[0102] For example, the compound represented by Formula 201 may be represented by Formula 201A-1, but is not limited thereto:



[0103] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A, but is not limited thereto:



[0104] L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} in Formulae 201A, 201A-1, and 202A may be as described above, R_{211} may be described as R_{203} , and R_{213} to R_{216} may be each independently selected from a hydrogen, a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_2 - C_{60} heteroaryl group, and a C_6 - C_{60} non-aromatic condensed polycyclic group.

[0105] In one embodiment, in Formulae 201A, 201A-1, and 202A,

[0106] L_{201} to L_{203} may be each independently selected from a phenylene group, naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysenylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylene group, a carbazolylenylene group and a triazinylene group; and

[0107] a phenylene group, naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysenylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylene group, a carbazolylenylene group and a triazinylene group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0108] $xa1$ to $xa3$ may be each independently 0 or 1;



[0109] R_{203} , R_{211} , and R_{212} may be each independently selected from

[0125] The compound represented by Formula 201, and the compound represented by Formula 202 may each include compounds HT1 to HT20 illustrated below, but are not limited thereto.


-continued

HT3


HT1



HT2




HT4




-continued

HT5




-continued


HT7



HT6




HT8




-continued

HT9





-continued

HT11




HT12


HT10




HT13




-continued




HT15




HT16




HT17




-continued



HT19




HT20



[0126] The thickness of the hole transport region may be from about 100 Å to about 10,000 Å, for example, from about 100 Å to about 1,000 Å. When the hole transport region includes both the hole injection layer and the hole transport layer, the thickness of the hole injection layer may be from about 100 Å to about 10,000 Å (e.g. 9,950 Å), for example, from about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be from about 50 Å to about 2,000 Å, for example, from about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within any of these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0127] The hole transport region may further include a charge generation material to improve electric conductivity, in addition to the materials described above. The charge generation material may be dispersed in the hole transport region homogeneously or heterogeneously.

[0128] The charge generation material may be, for example, a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but is not limited thereto. Non-limiting examples of the p-dopant include a quinone derivative such as tetracyanoquinodimethane (TCNQ) and tetrafluorotetracyanoquinodimethane (F4-TCNQ); a metal oxide such as a tungsten oxide and a molybdenum oxide; and 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HATCN):



[0129] The hole transport region may further include at least one selected from a buffer layer and an electron blocking layer, in addition to the hole injection layer and hole transport layer. Since the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, light-emission efficiency of the resulting organic light-emitting device may be improved. Materials that are included in the hole transport region may be utilized as a material for the buffer layer. In one embodiment, the electron blocking layer prevents (or reduces) the injection of electrons from the electron transport region.


[0130] An emission layer may be formed on the first electrode 13 or on the hole transport region by various methods, such as, for example, vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When the emission layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the emission layer may be similar to the deposition and coating conditions for the hole injection layer.


[0131] When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, to correspond to individual sub pixels, respectively. In some embodiments of the present invention, the emission layer may emit white light and may have a stacked structure in which the red emission layer, the green emission layer, and the blue emission layer are stacked upon one another, or a structure in which a red-light emission

material, a green-light emission material, and a blue-light emission material are mixed with each other in a single layer.


[0132] The emission layer may include a host and a dopant.

[0133] The host may include at least one selected from TPBi, TBADN, ADN, CBP, CDBP, and TCP:





[0134] According to another embodiment of the present invention, the host may include a compound represented by Formula 301.



Formula 301

[0135] Ar_{301} in Formula 301 may be selected from

[0136] naphthalene, heptalene, fluorene, spiro-fluorene, benzofluorene, dibenzofluorene, phenalene, phenanthrene, anthracene, fluoranthene, triphenylene, pyrene, chrysene, naphthacene, picene, perylene, pentaphene, and indenoanthracene;

[0137] naphthalene, heptalene, fluorene, spiro-fluorene, benzofluorene, dibenzofluorene, phenalene, phenanthrene, anthracene, fluoranthene, triphenylene, pyrene, chrysene, naphthacene, picene, perylene, pentaphene, and indenoanthracene, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_3\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_3\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_2\text{-C}_{60}$ heteroaryl group, a monovalent $\text{C}_2\text{-C}_{60}$ non-aromatic condensed polycyclic group, and $-\text{Si}(\text{Q}_{301})(\text{Q}_{302})$ (Q_{301} to Q_{303} are each independently selected from a hydrogen, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, and a $\text{C}_2\text{-C}_{60}$ heteroaryl group);

[0138] L_{301} may be described as L_{201} ;

[0139] R_{301} may be selected from

[0140] a $\text{C}_1\text{-C}_{20}$ alkyl group and a $\text{C}_1\text{-C}_{20}$ alkoxy group;

[0141] a $\text{C}_1\text{-C}_{20}$ alkyl group and a $\text{C}_1\text{-C}_{20}$ alkoxy group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro

group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0142] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0143] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group and a triazinyl group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0144] $\text{xb}1$ may be selected from 0, 1, 2, and 3;

[0145] $\text{xb}2$ may be selected from 1, 2, 3, and 4.

[0146] In one embodiment, in Formula 301,

[0147] L_{301} may be selected from

[0148] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, and a chrysenylene group; and

[0149] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, and a chrysenylene group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazine group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

[0150] R_{301} may be selected from


[0151] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group;

[0152] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

[0153] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

[0154] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one of a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, but R_{301} is not limited thereto.

[0155] In one embodiment, the host may include a compound represented by Formula 301A:




$[(L_{301})_{x1}-R_{301}]_{x2}$.

Formula 301A


[0156] Substituents of Formula 301A may be as described above and herein.

[0157] The compound represented by Formula 301 may include at least one of Compounds H1 to H42, but is not limited thereto:




H1


-continued




H2




H3




H4



H5




H6




H7

-continued




H8


-continued




H13




H9




H14




H10




H15




H11



H16




H12




H17

-continued




-continued




-continued


H28




H29




H30



H31




H32




-continued


H33




H34



H35




-continued




H36


-continued




H39




H37



H40




H38



H41


-continued

H42




-continued


H45




H46



H47




H48




[0158] According to another embodiment of the present invention, the host may include at least one of Compounds H43 to H49, but is not limited thereto:

H43




H44





-continued

H49




[0159] As a dopant, any suitable dopant may be utilized and may include at least one of a fluorescent dopant and a phosphorescent dopant. The phosphorescent dopant may be an organic metallic complex including one or a combination of at least two of Ir, Pt, Os, Re, Ti, Zr, and Hf, but is not limited thereto.


[0160] Non-limiting examples of a blue dopant include bis[3,5-difluoro-2-(2-pyridyl)phenyl](picolinato)iridium (III) (F_2Irpic), $(F_2ppy)_2Ir(tmd)$, $Ir(dfppz)_3$, 4,4'-bis(2,2'-diphenylethen-1-yl)biphenyl (DPVBi), 4,4'-bis[4-(diphenylamino)styryl]biphenyl (DPAVBi), and 2,5,8,11-tetra-tert-butyl perylene (TPBe), which are illustrated below:



DPAVBi




DPABi




TPBe


[0161] In one embodiment, a blue dopant includes at least one of the compounds illustrated below, but is not limited thereto:






-continued






[0162] Non-limiting examples of a red dopant include the compounds shown below including Pt(II) octaethylporphine (PtOEP), tris(2-phenylisoquinoline)iridium ($\text{Ir}(\text{piq})_3$), bis(2-(2'-benzothienyl)-pyridinato-N,C3')iridium(acetylacetonate) ($\text{Btp}_2\text{Ir}(\text{acac})$), 4-(dicyanomethylene)-2-methyl-6-[p-(dimethylamino)styryl]-4H-pyran (DCM), and 4-(dicyanomethylene)-2-tert-butyl-6-(1,1,7,7-tetramethyljulolidyl-9-enyl)-4H-pyran (DCJTb):














[0163] Non-limiting examples of a green dopant include tris(2-phenylpyridine) iridium ($\text{Ir}(\text{ppy})_3$), bis(2-phenylpyridine)(acetylacetonato)iridium(III) ($\text{Ir}(\text{ppy})_2(\text{acac})$), tris(2-(4-tolyl)phenylpyridine)iridium ($\text{Ir}(\text{mppy})_3$), and 10-(2-benzothiazolyl)-1,1,7,7-tetramethyl-2,3,6,7-tetrahydro-1H,5H,11H-[1]benzopyrano[6,7,8-ij]-quinolizin-11-one (C545T):















[0164] In one embodiment, the dopant included in the emission layer may be a Pt-complex and may be selected from Compounds D1 to D50, but is not limited thereto:








-continued



-continued




-continued




-continued

D20




D25

D21




D26

D22




D27

D28




D23



D29


D24




D30

-continued


D31




D32




D33




D34



D35




D36




-continued


D37




D38




D39








D40



D41




-continued




-continued

D42




D47

D43




D48

D44



D49


D45







D50

[0165] In one embodiment, the dopant included in the emission layer may be selected from Os-complexes illustrated below, but is not limited thereto:

D46



Os(fppz)₂(PPh₂Me)₂Os(bppz)₂(PPh₃)₂Os(fptz)₂(PPh₂Me)₂Os(hptz)₂(PPh₂Me)₂

[0166] An amount of the dopant in the emission layer may be about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but is not limited thereto.

[0167] A thickness of the emission layer may be about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within any of these ranges, good (or desired) light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0168] In one embodiment, an electron transport region may be positioned on the emission layer.

[0169] The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer (ETL), and an electron injection layer, but is not limited thereto.


[0170] For example, the electron transport region may only include an electron transport layer, or may have a structure of electron transport layer/electron injection layer, or a structure of hole blocking layer/electron transport layer/electron injection layer, wherein the layers of each structure are sequentially stacked on the emission layer in the stated order, but the structure of the electron transport region is not limited thereto.

[0171] According to one embodiment of the present invention, the organic layer 15 of the organic light-emitting device may include an electron transport region between the emission layer and the second electrode 17.


[0172] The electron transport region may include a hole blocking layer. When the emission layer includes a phosphorescent dopant, the hole blocking layer may be formed to prevent (or reduce) the diffusion of excitons or holes into an electron transport layer.

[0173] When the electron transport region includes a hole blocking layer, the hole blocking layer may be formed on the emission layer by various methods, such as, for example, vacuum deposition, spin coating casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When the hole blocking layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the hole blocking layer may be similar to the deposition and coating conditions for the hole injection layer.

[0174] The hole blocking layer may include, for example, at least one of BCP and Bphen, but is not limited thereto:



BCP




Bphen

[0175] A thickness of the hole blocking layer may be about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within any of these ranges, the hole blocking layer may have improved hole blocking ability without a substantial increase in driving voltage.


[0176] The electron transport region may include an electron transport layer. The electron transport layer may be formed on the emission layer or on the hole blocking layer by various methods, such as, for example, vacuum deposition,

spin coating casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When the electron transport layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the electron transport layer may be similar to the deposition and coating conditions for the hole injection layer.

[0177] The electron transport layer may further include at least one selected from the condensed cyclic compound represented by Formula 1, BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ, some of which are illustrated below:



[0178] According to another embodiment of the present invention, the electron transport layer may further include at least one compound represented by Formula 601:



Formula 601

[0179] In Formula 601,

[0180] Ar₆₀₁ may be described as Ar₃₀₁;

[0181] L₆₀₁ may be described as L₂₀₁; and

[0182] in some embodiments, L₆₀₁ may be selected from

[0183] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and


[0184] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a ben-

zofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group;

[0185] xe1 may be selected from 0, 1, 2, and 3;

[0186] xe2 may be selected from 1, 2, 3, and 4.

[0187] In some embodiments of the present invention, the electron transport layer may further include at least one of compounds represented by Formula 602:



Formula 602

[0188] In Formula 602,

[0189] X_{611} is N or $C-(L_{611})_{xe611}-R_{611}$, X_{612} is N or $C-(L_{612})_{xe612}-R_{612}$, X_{613} is N or $C-(L_{613})_{xe613}-R_{613}$, and at least one of X_{611} to X_{613} is N;


[0190] L_{611} to L_{616} may be each independently described as L_{201} ;

[0191] R_{611} to R_{616} may be each independently selected from

[0192] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0193] xe611 to xe616 may be each independently selected from 0, 1, 2, and 3.


[0194] The compound represented by Formula 601 and the compound represented by Formula 602 may each include at least one of Compounds ET1 to ET15 illustrated below:




ET1

-continued


ET2



ET3




ET4




-continued

ET5




-continued


ET8




ET6



ET9




ET7




-continued

ET10




-continued

ET13




ET14





ET15

ET11




ET12



[0195] A thickness of the electron transport layer may be about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within any of these ranges, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.

[0196] The electron transport layer may further include, in addition to the materials described above, a metal-containing material.

[0197] The metal-containing material may include a Li complex. The Li complex may include, for example, lithium quinolate (LiQ) or lithium [2-(2-hydroxyphenyl)benzothiazole] (LiBTz):



[0198] The electron transport region may include an electron injection layer that allows electrons to be easily provided (or injected) from the second electrode 17.

[0199] The electron injection layer may be formed on the electron transport layer by various methods, such as, for example, vacuum deposition, spin coating casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When the electron injection layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the electron injection layer may be similar to the deposition and coating conditions for the hole injection layer.

[0200] The electron injection layer may include, for example, at least one selected from LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

[0201] A thickness of the electron injection layer may be about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within any of these ranges, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0202] In one embodiment, the second electrode 17 is positioned on the organic layer 15 having the structure according to embodiments of the present invention. The second electrode 17 may be a cathode (which is an electron injection electrode), and a material for forming the second electrode 17 may be a material having a low work function, for example, a metal, an alloy, an electrically conductive compound, or a mixture thereof. Non-limiting examples of the material for forming the second electrode 17 include lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag). According to another embodiment of the present invention, the material for forming the second electrode 17 may be ITO or IZO. The second electrode 17 may be a reflective electrode or a transmissive electrode.

[0203] Although the organic light-emitting device has been described with reference to the drawing, embodiments of the present invention are not limited thereto. For example, in the organic light-emitting device shown in the drawing, the substrate 11 is positioned under the first electrode 13, but the substrate 11 can also be positioned above the second electrode 17.

[0204] An alkyl group as used herein refers to a linear or branched aliphatic hydrocarbon monovalent group, and non-limiting examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. An alkylene group as used herein refers to a divalent group having the same structure as the alkyl group.

[0205] An alkoxy group as used herein refers to a monovalent group represented by —OA₁₀₁ (where A₁₀₁ is a C₁–C₆₀ alkyl group), and non-limiting examples of the alkoxy group include a methoxy group, an ethoxy group, and an isopropoxy group.

[0206] An alkenyl group as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond at one or more positions along a carbon chain of the alkyl group. For example, the alkenyl group may include a terminal alkene and/or an internal alkene, and non-limiting examples thereof include an ethenyl group, a propenyl group, and a butenyl group. An alkenylene group as used herein refers to a divalent group having the same structure as the alkenyl group.

[0207] An alkynyl group as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond at one or more positions along a carbon chain of the alkyl group. For example, the alkynyl group may include a terminal alkyne and/or an internal alkyne, and non-limiting examples thereof include an ethynyl group, a propynyl group, and a butynyl group. An alkynylene group as used herein refers to a divalent group having the same structure as the alkynyl group.

[0208] A cycloalkyl group as used herein refers to a monovalent hydrocarbon monocyclic group, and non-limiting examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A cycloalkylene group as used herein refers to a divalent group having the same structure as the cycloalkyl group.

[0209] A heterocycloalkyl group as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, and carbon atoms as the remaining ring-forming atoms. Non-limiting examples of the heterocycloalkyl group include a tetrahydrofuranyl group and a tetrahydrothiophenyl group. A heterocycloalkylene group as used herein refers to a divalent group having the same structure as the heterocycloalkyl group.

[0210] A cycloalkenyl group as used herein refers to a monovalent monocyclic group that has at least one carbon-carbon double bond in the ring, but does not have aromaticity, and non-limiting examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A cycloalkenylene group as used herein refers to a divalent group having the same structure as the cycloalkenyl group.

[0211] A heterocycloalkenyl group as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom (and carbon atoms as the remaining ring-forming atoms), and at least one double bond in the ring. Non-limiting examples of the heterocycloalkenyl group include a 2,3-hydrofuranyl group and a 2,3-hydrothiophenyl group. A heterocycloalkenylene group as used herein refers to a divalent group having the same structure as the heterocycloalkenyl group.

[0212] An aryl group as used herein refers to a monovalent group that has a carbocyclic aromatic system, and an arylene group as used herein refers to a divalent group that has a carbocyclic aromatic system. Non-limiting examples of the aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the aryl group and/or the arylene group have at least two rings, the rings may be respectively fused to each other.

[0213] A heteroaryl group as used herein refers to a monovalent group that has at least one heteroatom selected

from N, O, P, and S as a ring-forming atom (and carbon atoms as the remaining ring-forming atoms) and a carbocyclic aromatic system. A heteroarylene group as used herein refers to a divalent group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom (and carbon atoms as the remaining ring-forming atoms) and a carbocyclic aromatic system. Non-limiting examples of the heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the heteroaryl group and/or the heteroarylene group include two or more rings, the rings may be respectively fused to each other.

[0214] An aryloxy group as used herein refers to a monovalent group represented by —OA_{102} (where A_{102} is the aryl group), and an arylthio group as used herein refers to a monovalent group represented by —SA_{103} (where A_{103} is the aryl group.)

[0215] A monovalent non-aromatic condensed polycyclic group as used herein refers to a monovalent group that has two or more rings condensed to each other, and the entire molecular structure does not have aromaticity. The monovalent non-aromatic condensed polycyclic group may include only carbon atoms as ring-forming atoms, or at least one heteroatom selected from N, O, P, and S as a ring-forming atom (and carbon atoms as the remaining ring-forming atoms). Non-limiting examples of the monovalent non-aromatic condensed polycyclic group include a heptalenyl group and a triquinacenyl group. Herein, a divalent non-aromatic condensed polycyclic group refers to a divalent group that has the same structure as the monovalent non-aromatic condensed polycyclic group.

[0216] $\text{C}_m\text{—C}_n$ ($m < n$) as used herein refers to a number of carbon atoms in a given group. For example, a $\text{C}_1\text{—C}_{10}$ alkyl group refers to an alkyl group that has between 1 and 10 carbon atoms, and a $\text{C}_6\text{—C}_{30}$ aryl group refers to an aryl group that has between 6 and 30 carbon atoms.




[0217] Hereinafter, an organic light-emitting device according to an embodiment of the present invention will be described in more detail with reference to Synthesis Examples and Examples. The expression “B was included instead of A” in describing Synthesis Examples means that a molar equivalent of A was identical to a molar equivalent of B.

SYNTHESIS EXAMPLE

Synthesis Example 1

Synthesis of Compound 101

[0218]




[0219] 3 g (13.7 mmol) of 4-iodo-phenylamine was dissolved in 30 ml of DMF/ H_2O to synthesize 1.89 g (75%) of biphenyl-4,4'-diamine (Intermediate A) through Buchwald-Hartwig amination.


[0220] 2.96 g (17.8 mmol) of [2,2']bithiophenyl was subjected to bromination to prepare 3,3',5,5'-tetrabromo-[2,2']bithiophenyl, and then 3.45 g (13.3 mmol, 80%) of 3,3'-dibromo-[2,2']bithiophenyl (Intermediate B) was synthesized via a debromination reaction using zinc. Afterward, the synthesized Intermediate A and Intermediate B were added to 30 ml of toluene, and the resulting solution was used (utilized) to perform Buchwald-Hartwig amination using (utilizing) $\text{Pd}_2(\text{dba})_3$, CHCl_3 , dppf(1',1'-bis(diphenyl-diphosphino)ferrocene), and NaOt-Bu to synthesize Compound 101 (2.08 g, 40%).

Synthesis Example 2

Synthesis of Compound 107

[0221]






[0222] 2.5 g (8 mmol) 4,4'-dibromo biphenyl was used (utilized) to perform a cyclization reaction to synthesize 2.08 g (80%) of 4,4'-dibromo carbazole. The 4,4'-dibromo carbazole and iodinated phenyl were dissolved in 40 ml of toluene to synthesize Intermediate C through a Buchwald reaction.

[0223] 2.96 g (17.8 mmol) of [2,2']bithiophenyl was used (utilized) to prepare 3,5,3',5'-tetrabromo-[2,2']bithiophenyl via bromination, and then 2.16 g (55%) of 3-bromo-[2,2']bithiophenyl was synthesized through a debromination reaction using zinc. Then, the 3-bromo-[2,2']bithiophenyl was used (utilized) to perform a nucleophilic substitution reaction (SN2 reaction) and a cyclization reaction to synthesize Intermediate D. The Intermediate C and Intermediate D were then used (utilized) to perform Buchwald-Hartwig cross-coupling to synthesize 2.99 g (83%) of Compound 107.


Synthesis Example 3

Synthesis of Compound 109

[0224]



-continued





[0225] 2.5 g (14.9 mmol) of carbazole was used (utilized) to perform an NBS bromination to synthesize 2,5-dibromocarbazole. Then, the 2,5-dibromocarbazole and iodinated phenyl were used (utilized) to synthesize 3.72 g (9.28 mmol) of Intermediate E through a Buchwald reaction.

[0226] Afterward, the Intermediate E and Intermediate D were used (utilized) to perform Buchwald-Hartwig cross-coupling to synthesize 3.65 g (66%) of Compound 109.

Synthesis Example 4

Synthesis of Compound 121

[0227]



[0228] 2.5 g (14.9 mmol) of naphthalene acetic acid was used (utilized) to synthesize 2.3 g of the Intermediate F (1 equivalent weight) and 2.4 g of the Intermediate D (2.2 equivalent weight) through the synthesis pathway represented by the reaction scheme shown above, and then 2.52 g (72%) of Compound 121 was synthesized by performing Buchwald-Hartwig cross-coupling.

[0229] The ^1H NMR and MS/FAB results of the synthesized compounds are shown in Table 1.

[0230] Methods of synthesizing compounds other than the compounds shown in Table 1 should be apparent to those of ordinary skill in the art by referring to the synthesis path and source materials described above.

TABLE 1

Com- pound	^1H NMR (CDCl_3 , 300 MHz)	MS/FAB	
		Measured value	Calculated value
101	6.96(4H), 7.2(4H), 7.3(4H), 7.5(4H)	508.02	508.70
107	6.96(4H), 7.0(2H), 7.2(4H), 7.3(5H), 7.4(2H), 7.6(2H)	597.05	597.79
109	6.96(4H), 7.1(2H), 7.2(4H), 7.3(5H), 7.4(2H), 7.6(2H)	597.05	597.79
121	1.93(6H), 6.96(4H), 7.2(4H), 7.7(2H), 7.8(2H), 7.9(2H)	572.05	572.79

EXAMPLE

Example 1

[0231] An ITO glass substrate (a product of Corning Co., Ltd) having an ITO layer having a thickness of 1200 Å and a sheet resistance of $15\Omega/\square$ was cut to a size of 50 mm×50 mm×0.7 mm, and then, sonicated with isopropyl alcohol and pure water, each for 5 minutes, and cleaned by exposure to ultraviolet rays for 30 minutes, and then to ozone, and the resulting ITO glass substrate was mounted on a vacuum deposition apparatus.

[0232] 2-TNATA was deposited on the ITO anode to form a hole injection layer having a thickness of 600 Å, and then, Compound 101 was deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å. On the hole transport layer, an emission layer having a thickness of 200 Å was formed by using (utilizing) 95 wt % ADN and 5% F_2Irpic as a blue dopant.

[0233] Thereafter, Alq_3 was deposited on the emission layer to form an electron transport layer having a thickness of 300 Å, and LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was deposited on the electron injection layer to form a cathode having a thickness of 3000 Å, thereby manufacturing an organic light-emitting device.

Example 2

[0234] An organic light-emitting device was manufactured as in Example 1, except that in forming a hole transport layer, Compound 107 was included instead of Compound 1.

Example 3

[0235] An organic light-emitting device was manufactured as in Example 1, except that in forming a hole transport layer, Compound 109 was used instead of Compound 1.

Example 4

[0236] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming a hole transport layer, Compound 121 was included instead of Compound 1.

Comparative Example 1

[0237] An organic light-emitting device was manufactured as in Example 1, except that in forming a hole transport layer,

NPB was included instead of Compound 101, and in forming an electron transport layer, BAQ was included instead of Alq₃.

Comparative Example 2

[0238] An organic light-emitting device was manufactured as in Example 1, except that in forming a hole transport layer, NPB was included instead of Compound 101, and in forming an electron transport layer, TAZ was included instead of Alq₃.

Evaluation Example

[0239] The driving voltage and light-emitting efficiency of each of the organic light-emitting devices of Examples 1 to 4 and Comparative Examples 1 to 2 were measured, and the results are shown in Table 2.

TABLE 2

	Hole transport layer	Electron transport layer	Driving voltage (V)	Brightness (cd/m ²)	Light-emitting efficiency (cd/A)	Emission color
Example 1	Compound 101	Alq ₃	3.9	494	4.84	Blue
Example 2	Compound 107	Alq ₃	4.0	467	5.37	Blue
Example 3	Compound 109	Alq ₃	3.7	477	4.97	Blue
Example 4	Compound 121	Alq ₃	4.6	389	4.11	Blue
Comparative Example 1	NPB	BAQ	4.9	205	2.35	Blue
Comparative Example 2	NPB	TAZ	4.4	302	4.01	Blue

[0240] As can be seen from the results in Table 1, the driving voltage, brightness, current efficiency, and half-life span of the organic light-emitting devices of Example 1 to Example 4 are better than the driving voltage, brightness, current efficiency, and half-life span of the organic light-emitting devices of Comparative Examples 1 and 2.

[0241] The organic light-emitting device including the condensed cyclic compound according to embodiments of the present invention may have a low driving voltage, high efficiency, high brightness, and long lifespan.


[0242] It should be understood that the exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0243] While one or more embodiments of the present invention have been described with reference to the drawing, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims and equivalents thereof.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:

Formula 1



wherein

X is an oxygen (O) atom or a sulfur (S) atom;

R₁ to R₁₀ are each independently selected from a hydrogen, a deuterium, a halogen atom, a cyano group, a nitro group, a hydroxyl group, a carboxylic acid, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₃₀ aryl group, a substituted or unsubstituted C₁-C₃₀ heteroaryl group, a substituted or unsubstituted C₆-C₃₀ aryloxy group, a substituted or unsubstituted C₆-C₃₀ arylthio group, and a substituted or unsubstituted monovalent C₆-C₃₀ non-aromatic condensed polycyclic group,

each R₁ in a plurality of R₁ and each R₂ in a plurality of R₂ are independent of one another,

at least one of the plurality of R₁ and the plurality of R₂ is linked to an adjacent R₁ and/or R₂ to form a condensed ring;

at least one substituent of the substituted C₁-C₁₀ alkyl group, substituted C₂-C₁₀ alkenyl group, substituted C₂-C₁₀ alkynyl group, substituted C₁-C₁₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₃-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ heterocycloalkenyl group, substituted C₆-C₃₀ aryl group, substituted C₁-C₃₀ heteroaryl group, substituted C₆-C₃₀ aryloxy group, substituted C₆-C₃₀ arylthio group, and substituted monovalent C₆-C₃₀ non-aromatic condensed polycyclic group is selected from

a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl, and a C₁-C₁₀ alkoxy group;

a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, and a C₁-C₁₀ alkoxy group, each substi-

tuted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, —N(Q₁₁)(Q₁₂), —Si(Q₁₃)(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, and a C₆-C₃₀ arylthio group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, a C₆-C₃₀ aryloxy group, a C₆-C₃₀ arylthio group, a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group, —N(Q₂₁)(Q₂₂), —Si(Q₂₃)(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

—Si(Q₃₁)(Q₃₂)(Q₃₃) and —B(Q₃₄)(Q₃₅),

wherein Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₅ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₂-C₃₀ heteroaryl group, and a monovalent C₆-C₃₀ non-aromatic condensed polycyclic group.

2. The condensed cyclic compound of claim 1,

wherein the plurality of R₁ are each independently selected from a hydrogen and a C₁-C₁₀ alkyl group,

or at least one R₁ of the plurality of R₁ is selected from a hydrogen and a C₁-C₁₀ alkyl group, and two or more R₁ of the plurality of R₁ different from the at least one R₁ of the plurality of R₁ are linked to each other to form a substituted or unsubstituted naphthylene group or a substituted or unsubstituted anthrylene group with an 'a' benzene ring, and

wherein at least one substituent of the substituted naphthylene group or the substituted anthrylene group is selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, and a C₆-C₃₀ aryl group.

3. The condensed cyclic compound of claim 1,

wherein the plurality of R₂ are each independently selected from a hydrogen and a C₁-C₁₀ alkyl group,

or at least one R₂ of the plurality of R₂ is selected from a hydrogen and a C₁-C₁₀ alkyl group, and two or more R₂ of the plurality of R₂ different from the at least one R₂ of the plurality of R₂ are linked to each other to form a substituted or unsubstituted naphthylene group or a substituted or unsubstituted anthrylene group with a 'b' benzene ring, and

wherein at least one substituent of the substituted naphthylene group or the substituted anthrylene group is selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, and a C₆-C₃₀ aryl group.

4. The condensed cyclic compound of claim 1,

wherein at least one of the plurality of R₁ and the plurality of R₂ is selected from a hydrogen and a C₁-C₁₀ alkyl group,

and at least another one R₁ of the plurality of R₁ and at least another one R₂ of the plurality of R₂ are linked to each other to form a substituted or unsubstituted C₁₃-C₃₀ condensed ring with the 'a' and 'b' benzene rings, and

wherein at least one substituent of the substituted C₁₃-C₃₀ condensed ring is selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, and a C₆-C₃₀ aryl group.

5. The condensed cyclic compound of claim 1,

wherein R₃ to R₁₀ are each independently selected from a hydrogen, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, a decyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a biphenyl group, a heptalenyl group, a phenalenyl group, a fluorenyl group, a phenanthrenyl group, an anthryl group, a fluoranthrenyl group, a pyrenyl group, a benzofluorenyl group, a naphthacenyl group, a chrysenyl group, a triphenylenyl group, a terphenyl group, a perylenyl group, a picenyl group, a hexacenyl group, a spiro fluorenyl group, a pyrrolyl group, a furyl group, a pyrazolyl group, an imidazolyl group, an oxazolyl group, an isoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a pyranlyl group, a thiophenyl group, a thiazolyl group, an isothiazolyl group, a thiopyranlyl group, an indolyl group, an isoindolyl group, an indolizynyl group, a benzofuryl group, an isobenzofuryl group, an indazolyl group, an benzimidazolyl group, a benzoxazolyl group, a benzisoxazolyl group, an imidazopyridyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a phthalazinyl group, a quinazolinyl group, a quinoxalinyl group, a naphthyridinyl group, a cinnolinyl group, a benzothiophenyl group, a benzothiazolyl group, a carbazolyl group, a benzocarbazolyl group, a pyridoindolyl group, a dibenzofuryl group, a phenanthridinyl group, a benzoquinolyl group, a phenazinyl group, a diben-

zosilolyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzacridinyl group; and


a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, and a decyl group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, and an amino group; and

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, an indacenyl group, an acenaphthyl group, a biphenyl group, a heptalenyl group, a phenalenyl group, a fluorenyl group, a phenanthrenyl group, an anthryl group, a fluoranthenyl group, a pyrenyl group, a benzofluorenyl group, a naphthacenyl group, a chrysenyl group, a triphenylenyl group, a terphenyl group, a perylenyl group, a picenyl group, a hexacenyl group, a spiro fluorenyl group, a pyrrolyl group, a furyl group, a pyrazolyl group, an imidazolyl group, an oxazolyl group, an isoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a pyranyl group, a thiophenyl group, a thiazolyl group, an isothiazolyl group, a thiopyranyl group, an indolyl group, an isoindolyl group, an indoliziny group, a benzofuryl group, an isobenzofuryl group, an indazolyl group, a benzimidazolyl group, a bensoxazolyl group, a benzisoxazolyl group, an imidazopyridyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a phthalazinyl group, a quinazolinyl group, a quinoxalinyl group, a naphthyridinyl group, a cinnolinyl group, a benzothiophenyl group, a benzothiazolyl group, a carbazolyl group, a benzocarbazolyl group, a pyridoindolyl group, a dibenzofuryl group, a phenanthridinyl group, a benzoquinolyl group, a phenazinyl group, a dibenzosilolyl group, a dibenzothiophenyl group and a benzocarbazole group, each substituted with at least one selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₁₀ alkyl group, a C₂-C₁₀ alkenyl group, a C₂-C₁₀ alkynyl group, a C₁-C₁₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₃₀ aryl group, a C₄-C₃₀ heteroaryl group, a C₅-C₃₀ aryloxy group, a C₅-C₃₀ arylthio group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),

wherein Q₃₁ to Q₃₃ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, and a C₆-C₂₀ aryl group.


6. The condensed cyclic compound of claim 1,

wherein an A part represented by a dotted line box in Formula 1 is selected from Formulae 2A to 2AA:




2A


-continued




2B




2C




2D




2E



2F




2G




2H

-continued




-continued

2I




2Q

2J




2R

2K




2S

2L




2T

2M




2U

2N



2V





2O



2W



2P

-continued




7. The condensed cyclic compound of claim 1,

wherein B and C parts represented by dotted line boxes in Formula 1 are each independently selected from Formulae 3A to 3F:




-continued

2X




3C

2Y




3D

2Z



3E

2AA



3F


8. The condensed cyclic compound of claim 1,

wherein the condensed cyclic compound is represented by any one of Formula 1-1 and Formula 1-2:

3A


Formula 1-1

3B



-continued

Formula 1-2



9. The condensed cyclic compound of claim 8, wherein the plurality of R_1 are each independently selected from a hydrogen and a C_1 - C_{10} alkyl group, or at least one R_1 of the plurality of R_1 is selected from a hydrogen and a C_1 - C_{10} alkyl group, and two or more R_1 of the plurality of R_1 different from the at least one R_1 of the plurality of R_1 are linked to each other to form a substituted or unsubstituted naphthylene group or a substituted or unsubstituted anthrylene group with an 'a' benzene ring, and

wherein at least one substituent of the substituted naphthylene group or the substituted anthrylene group is selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{10} alkyl group, and a C_6 - C_{30} aryl group.

10. The condensed cyclic compound of claim 8, wherein the plurality of R_2 are each independently selected from a hydrogen and a C_1 - C_{10} alkyl group, or at least one R_2 of the plurality of R_2 is selected from a hydrogen and a C_1 - C_{10} alkyl group, and two or more R_2 of the plurality of R_2 different from the at least one R_2 of the plurality of R_2 are linked to each other to form a substituted or unsubstituted naphthylene group or a substituted or unsubstituted anthrylene group with a 'b' benzene ring, and

wherein at least one substituent of the substituted naphthylene group or the substituted anthrylene group is selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{10} alkyl group, and a C_6 - C_{30} aryl group.

11. The condensed cyclic compound of claim 8, wherein at least one of the plurality of R_1 and the plurality of R_2 is selected from a hydrogen and a C_1 - C_{10} alkyl group,


and at least another one R_1 of the plurality of R_1 , and at least another one R_2 the plurality of R_2 are linked to each other to form a substituted or unsubstituted C_{13} - C_{30} condensed ring with the 'a' and 'b' benzene rings, and

wherein at least one substituent of the substituted C_{13} - C_{30} condensed ring is selected from a deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an


amino group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{10} alkyl group, and a C_6 - C_{30} aryl group.

12. The condensed cyclic compound of claim 8,


wherein an A1 part represented by dotted line boxes in Formula 1-1 and Formula 1-2 is selected from Formulae 2A to 2AA:




2A




2B




2C




2D



2E










2F




2G

-continued




-continued

2H




2O

2I




2P

2J




2Q

2K




2R

2L




2S

2M




2T

2N




2U

-continued




2V

3A




2W

3B




2X

3C




2Y

3D









2Z

3E









2AA

3F








13. The condensed cyclic compound of claim 8, wherein B1 and C1 parts represented by dotted line boxes in Formula 1-1 and Formula 1-2 are each independently selected from Formulae 3A to 3F:

14. The condensed cyclic compound of claim 1,
wherein the condensed cyclic compound is selected from
one of Compounds 101 to 141:




-continued

108




-continued


112




113




114




115



116




117




-continued


118




119




120




121



122




123




-continued


124




125




126




127



128




129




-continued


130




131




132




133




134




-continued



135




136




137

-continued




140




141


15. The condensed cyclic compound of claim 1,
wherein the condensed cyclic compound is selected from
Compounds 101, 107, 109, and 121:




138



101




139



107

-continued



16. An organic light-emitting device, the organic light-emitting device comprising:

- a first electrode;
- a second electrode; and
- an organic layer between the first electrode and the second electrode and comprising an emission layer and at least one condensed cyclic compound of claim 1.

17. The organic light-emitting device of claim 16, wherein the organic layer further comprises:

- a hole transport region between the first electrode and the emission layer; and
- an electron transport region between the emission layer and the second electrode.

18. The organic light-emitting device of claim 17, wherein the hole transport region comprises at least one selected from an electron blocking layer, a hole transport layer, and a hole injection layer.

19. The organic light-emitting device of claim 17, wherein the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

20. The organic light-emitting device of claim 17, wherein the hole transport region comprises the condensed cyclic compound.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US20150364695A1	公开(公告)日	2015-12-17
申请号	US14/596574	申请日	2015-01-14
[标]申请(专利权)人(译)	三星显示有限公司 釜山NAT UNIV UNIV IND合作FOUND		
申请(专利权)人(译)	三星DISPLAY CO. , LTD. 釜山大学产学合作基金会		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD. 釜山大学产学合作基金会		
[标]发明人	HWANG JIN SOO KIM MYEONG SUK KIM SUNG WOOK KHO SAM IL SEO HONG SUK		
发明人	HWANG, JIN-SOO KIM, MYEONG-SUK KIM, SUNG-WOOK KHO, SAM-IL SEO, HONG-SUK		
IPC分类号	H01L51/00 C07D519/00		
CPC分类号	H01L51/0071 H01L51/5056 C07D519/00 H01L51/0052 H01L51/0059		
优先权	1020140072969 2014-06-16 KR		
其他公开文献	US9705090		
外部链接	Espacenet USPTO		

摘要(译)

有机发光装置包括第一电极，第二电极，以及在第一电极和第二电极之间并且包含至少一种由式1表示的稠环化合物的有机层：包含由式1表示的稠环化合物的有机发光装置可以具有低驱动电压，高效率，高亮度和长寿命。

