



US009385345B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 9,385,345 B2**
(45) **Date of Patent:** **Jul. 5, 2016**

(54) **ORGANIC LIGHT EMITTING DISPLAY
DEVICE AND METHOD OF FABRICATING
THE SAME**

(71) Applicant: **LG Display Co., Ltd.**, Seoul (KR)

(72) Inventors: **Heui-Dong Lee**, Paju-si (KR);
Kwan-Soo Kim, Paju-si (KR);
Dae-Gwon Song, Goyang-si (KR);
Jin-Ho Park, Paju-si (KR); **Sung-Ji**
Yoon, Paju-si (KR); **Dong-Hyeok Lim**,
Incheon (KR)

(73) Assignee: **LG DISPLAY CO., LTD.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/134,119**

(22) Filed: **Dec. 19, 2013**

(65) **Prior Publication Data**

US 2014/0183493 A1 Jul. 3, 2014

(30) **Foreign Application Priority Data**

Dec. 28, 2012 (KR) 10-2012-0157157

(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/56 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 51/56** (2013.01); **H01L 51/506**
(2013.01); **H01L 51/5064** (2013.01); **H01L**
27/3211 (2013.01)

(58) **Field of Classification Search**
CPC H01L 51/5052; H01L 51/506; H01L
51/5064; H01L 51/5068; H01L 27/3211
USPC 257/40
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2005/0173700 A1 * 8/2005 Liao H01L 27/3211
257/40

2008/0116793 A1 5/2008 Lee et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 102024844 A 4/2011
CN 102569676 7/2012

(Continued)

OTHER PUBLICATIONS

Office Action for Taiwanese Patent Application No. TW 102146428,
Oct. 1, 2015, 13 Pages.

(Continued)

Primary Examiner — John C Ingham


Assistant Examiner — Frederick B Hargrove

(74) *Attorney, Agent, or Firm* — Fenwick & West LLP

(57) **ABSTRACT**

Disclosed herein are an organic light emitting display device includes first to third sub-pixels realizing different colors, wherein each of the first to third sub-pixels includes first and second electrodes disposed on a substrate so as to face each other, an emission layer formed between the first and second electrodes, a multi-layered hole transporting layer formed between the first electrode and the emission layer to be in contact with the first electrode and the emission layer, and an electron transporting layer formed between the second electrode and the emission layer, wherein multi-layered hole transporting layer of at least one of the first to third sub-pixels includes an at least two-layered first hole transporting layer formed of a hole host and a p-type dopant having a doping concentration of 1 to 10% and a second hole transporting layer formed of the hole host.

19 Claims, 18 Drawing Sheets



(51) **Int. Cl.** 2013/0043498 A1* 2/2013 Pyo et al. 257/89
H01L 51/50 (2006.01)
H01L 27/32 (2006.01)

FOREIGN PATENT DOCUMENTS

(56) **References Cited**

U.S. PATENT DOCUMENTS

2009/0072720 A1* 3/2009 Lee et al. 313/504
 2010/0133994 A1 6/2010 Song et al.
 2011/0037056 A1* 2/2011 Dubois et al. 257/40
 2011/0297977 A1* 12/2011 Kajimoto 257/89
 2012/0164772 A1* 6/2012 Lee 438/34
 2012/0235178 A1 9/2012 Mori

TW I264459 10/2006
 TW 200824497 A 6/2008
 TW I372578 A 9/2012

OTHER PUBLICATIONS

Office Action for Chinese Patent Application No. CN 201310727093.
 3, Feb. 1, 2016, 16 Pages.

* cited by examiner

FIG.1




FIG.2




FIG.3A




FIG.3B




FIG.4




FIG. 5




FIG.6A




FIG.6B




FIG. 7A




FIG. 7B




FIG.8




FIG. 9




FIG.10




FIG.11A




FIG.11B




FIG.12A




FIG.12B




FIG.13A




FIG.13B




FIG.13C




FIG.13D




FIG.13E





FIG.13F



ORGANIC LIGHT EMITTING DISPLAY DEVICE AND METHOD OF FABRICATING THE SAME

This application claims the benefit of Korean Patent Application No. 10-2012-0157157, filed on Dec. 28, 2012, which is hereby incorporated by reference in its entirety.

BACKGROUND

1. Technical Field

The present disclosure relates to an organic light emitting display device with reduced power consumption and improved efficiency and lifespan and a method of fabricating the same.

2. Discussion of the Related Art

In line with recent information era, display field, which visually displays electrical information signals, has rapidly developed. To meet such development, various flat panel display devices with excellent performance, such as ultra-thin in thickness, lightweight, and low power consumption, have been developed.

Examples of flat panel display devices include, without being limited to, a liquid crystal display (LCD) device, a plasma display panel (PDP) device, a field emission display (FED) device, and an organic light emitting device (OLED).

In particular, OLEDs, which are self-emissive devices, have faster response time, higher luminous efficiency, higher luminance and wider viewing angles than other flat panel display devices.

An organic light emitting display device includes a sub-pixel having an anode and a cathode opposite to each other in a state in which an emission layer is disposed between the anode and the cathode. Holes injected from the anode and electrons injected from the cathode are re-coupled with each other in the emission layer to form excitons, which are hole-electron pairs. When the excitons return to a ground state, the excitons generate energy, by which light is emitted.

In an conventional organic light emitting display device, trap energy is increased due to a gap at an interface between an anode and a hole injection layer. The increase of the trap energy raises a hole injection barrier. For this reason, it is not possible to stably supply holes to an emission layer. As a result, power consumption of the device is increased and efficiency and lifespan of the device are reduced.

SUMMARY

Accordingly, the present disclosure is directed to an organic light emitting display device and a method of fabricating the same that substantially obviate one or more problems due to limitations and disadvantages of the related art.

An object of the present disclosure is to provide an organic light emitting display device with reduced power consumption and improved efficiency and lifespan and a method of fabricating the same.

Additional advantages, objects, and features of the disclosure will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following or may be learned from practice of the disclosure. The objectives and other advantages of the disclosure may be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these objects and other advantages and in accordance with the purpose of the disclosure, as embodied and

broadly described herein, an organic light emitting display device includes first to third sub-pixels realizing different colors, wherein each of the first to third sub-pixels includes first and second electrodes on a substrate to face each other, an emission layer formed between the first and second electrodes, a multi-layered hole transporting layer formed between the first electrode and the emission layer to be in contact with the first electrode and the emission layer, and an electron transporting layer formed between the second electrode and the emission layer, and the multi-layered hole transporting layer of at least one of the first to third sub-pixels includes an at least two-layered first hole transporting layer formed of a hole host and a p-type dopant having a doping concentration of 1 to 10% and a second hole transporting layer formed of the hole host.

The first sub-pixel may be a red sub-pixel realizing red through a red emission layer, the second sub-pixel may be a green sub-pixel realizing green through a green emission layer, and the third sub-pixel may be a blue sub-pixel realizing blue through a blue emission layer, the hole transporting layer of each of the red and green sub-pixels may include a common hole transporting layer formed by sequentially stacking the first and second hole transporting layers and an optical adjustment layer formed between the common hole transporting layer and the first electrode, and the hole transporting layer of the blue sub-pixel may include a common hole transporting layer formed by sequentially stacking the first and second hole transporting layers.

The red, green, and blue sub-pixels may in common include blue emission layers, the blue emission layer of the red sub-pixel may be formed between the red emission layer and the electron transporting layer, and the blue emission layer of the green sub-pixel may be formed between the green emission layer and the electron transporting layer.

The optical adjustment layer may include first and second optical adjustment layers sequentially formed between the first electrode and the common hole transporting layer, the first optical adjustment layer may be formed of a hole host and a p-type dopant identical to or different from that of the first hole transporting layer, and the second optical adjustment layer may be formed of a hole host identical to or different from that of the second hole transporting layer.

The optical adjustment layer may include a first optical adjustment layer formed between the first electrode and the common hole transporting layer and the first optical adjustment layer may be formed of a hole host and a p-type dopant identical to or different from that of the first hole transporting layer.

The first optical adjustment layer of the red sub-pixel may have a larger thickness than the first optical adjustment layer of the green sub-pixel.

The p-type dopant may be formed of F4-TCNQ, 1,4-TCAQ, 6,3-TCPQ, TCAQ, TCNTHPQ, or TCNPQ and the hole host may be formed of NPB, PPD, TPAC, BFA-1T, or TBDB.

The p-type dopant may have a lowest unoccupied molecular orbital (LUMO) level less than that of the hole host.

The optical adjustment layer and the first hole transporting layer including the p-type dopant may occupy 10 to 25% the multi-layered hole transporting layer.

In another aspect of the present disclosure, a method of fabricating an organic light emitting display device including first to third sub-pixels realizing different colors includes forming first electrodes of the first to third sub-pixels on a substrate, forming multi-layered hole transporting layers on the first electrodes, forming emission layers on the hole transporting layers, forming electron transporting layers on the

emission layers, and forming second electrodes on the electron transporting layers, wherein the multi-layered hole transporting layer of at least one of the first to third sub-pixels includes an at least two-layered first hole transporting layer formed of a hole host and a p-type dopant having a doping concentration of 1 to 10% and a second hole transporting layer formed of the hole host.

The first sub-pixel may be a red sub-pixel realizing red through a red emission layer, the second sub-pixel may be a green sub-pixel realizing green through a green emission layer, and the third sub-pixel may be a blue sub-pixel realizing blue through a blue emission layer, the step of forming the hole transporting layers of the red, green, and blue sub-pixels may include forming optical adjustment layers on the first electrodes of the red and green sub-pixels and forming common hole transporting layers each comprising the first and second hole transporting layers at the red, green, and blue sub-pixels, and at least one of optical adjustment layers, first hole transporting layers, and second hole transporting layers may be formed by scanning or deposition using a shutter.

It is to be understood that both the foregoing general description and the following detailed description of are exemplary and explanatory and are intended to provide further explanation of the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the present disclosure and are incorporated in and constitute a part of this application, illustrate embodiment(s) and together with the description serve to explain the principle of the present disclosure. In the drawings:

FIG. 1 is a sectional view showing an organic light emitting display device according to a first embodiment;

FIG. 2 is a view illustrating a relationship between a hole host and a p-type dopant shown in FIG. 1;

FIGS. 3A and 3B are views illustrating voltage and lifespan characteristics of the organic light emitting display device shown in FIG. 1 and a comparative example;

FIG. 4 is a view showing an apparatus for forming a hole transporting layer shown in FIG. 1;

FIG. 5 is a sectional view showing an organic light emitting display device according to a second embodiment;

FIGS. 6A and 6B are views illustrating voltage and lifespan characteristics of a red sub-pixel of the organic light emitting display device shown in FIG. 5 and a red sub-pixel of a comparative example;

FIGS. 7A and 7B are views illustrating voltage and lifespan characteristics of a green sub-pixel of the organic light emitting display device shown in FIG. 5 and a green sub-pixel of the comparative example;

FIG. 8 is a sectional view showing an organic light emitting display device according to a third embodiment;

FIG. 9 is a sectional view showing an organic light emitting display device according to a fourth embodiment;

FIG. 10 is a sectional view showing another form of the organic light emitting display device according to the fourth embodiment;

FIGS. 11A and 11B are views illustrating voltage and lifespan characteristics of a red sub-pixel of the organic light emitting display device shown in FIG. 9 and a red sub-pixel of a comparative example;

FIGS. 12A and 12B are views illustrating voltage and lifespan characteristics of a green sub-pixel of the organic light emitting display device shown in FIG. 9 and a green sub-pixel of the comparative example; and

FIGS. 13A to 13F are sectional views illustrating a method of forming a hole transporting layer of the organic light emitting display device shown in FIG. 5.

DETAILED DESCRIPTION

Reference will now be made in detail to the embodiments, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

FIG. 1 is a sectional view showing an organic light emitting display device according to the present disclosure.

The organic light emitting display device shown in FIG. 1 includes a first electrode 102, a multi-layered hole transporting layer 114, an emission layer 110, an electron transporting layer 116, a second electrode 104, and a capping layer 120.

Any one of the first and second electrodes 102 and 104 is formed of a semi-transparent electrode and the other of the first and second electrodes 102 and 104 is formed of a reflective electrode. In a case in which the first electrode 102 is a semi-transparent electrode and the second electrode 104 is a reflective electrode, the organic light emitting display device is configured to have a rear light emitting structure in which light is emitted downward. In a case in which the second electrode 104 is a semi-transparent electrode and the first electrode 102 is a reflective electrode, the organic light emitting display device is configured to have a front light emitting structure in which light is emitted upward. In the present disclosure, the first electrode 102, as an anode, formed of a reflective electrode and the second electrode 104, as a cathode, formed of a semi-transparent electrode will be described by way of example.

The first electrode 102 is configured to have a multi-layered structure including a metal layer formed of aluminum (Al) or an aluminum alloy, such as AlNd, and a transparent layer formed of indium tin oxide (ITO) or indium zinc oxide (IZO). The first electrode 102 functions as a reflective electrode.

The second electrode 104 is configured to have a single-layered structure or a multi-layered structure. Each layer constituting the second electrode 104 may be formed of a metal, an inorganic substance, a mixture of metals, a mixture of a metal and an inorganic substance, or a mixture thereof. In a case in which each layer is formed of a mixture of a metal and an inorganic substance, a volume ratio of the metal to the inorganic substance is 10:1 to 1:10. In a case in which each layer is formed of a mixture of metals, a ratio of one to the other of the metals is 10:1 to 1:10. The second electrode 104 is formed of a metal, such as Ag, Mg, Yb, Li, or Ca. The second electrode 104 is formed of an inorganic substance, LiO₂, CaO, LiF, or MgF₂. The second electrode 104 assists movement of electrons such that a large amount of electrons are supplied to the emission layer 110.

The capping layer 120 is formed of a material exhibiting a higher refractive index than an external air layer. Light transmitted through the capping layer 120 is reflected from an interface between the capping layer 120 and the external air layer and exits out through the capping layer 120 while repeatedly reflected and transmitted between the first electrode 102 and the capping layer 120. As a result, the amount of light lost due to total reflection from the interface between the capping layer 120 and the external air layer is reduced and the amount of light transmitted is increased, thereby improving light emission efficiency.

5

In the emission layer **110**, holes supplied through the hole transporting layer **114** and electrons supplied through the electron transporting layer **116** are re-coupled to generate light.

The electron transporting layer **116** supplies electrons from the second electrode **104** to the emission layer **110**.


The hole transporting layer **114** includes first hole transporting layers **114a** doped with a p-type dopant and second hole transporting layers **114b** not doped with a p-type dopant, which are alternately formed. The first hole transporting layers **114a** doped with the p-type dopant are formed to have a two-layered structure between the first electrode **102** and the emission layer **110**. FIG. 1, the first and second hole transporting layers **114a** and **114b** being alternately formed twice is described by way of example. However, embodiments of the present disclosure are not limited thereto.

Each first hole transporting layer **114a** is formed by doping a hole host with a p-type dopant at a doping concentration of 1 to 10%. If the doping concentration of the p-type dopant is less than 1%, it is not possible to obtain device characteristics. If the doping concentration of the p-type dopant is greater than 10%, the amount of holes exceeds that of electrons. As a result, excitons are formed at an interface between the electron transporting layer **116** and the emission layer **110**, not in the emission layer **110**, whereby efficiency is lowered and lifespan is shortened. At this time, the hole host has a highest occupied molecular orbital (HOMO) level of 5.0 eV or more. The p-type dopant has a lowest unoccupied molecular orbital (LUMO) level less than that of the hole host. The first hole transporting layers **114a** occupy 10 to 25% the entirety of the hole transporting layer **114**. If the first hole transporting layers **114a** occupy less than 10% the entirety of the hole transporting layer **114**, it is not possible to obtain an effect superior to that of a comparative example. If the first hole transporting layers **114a** occupy greater than 25% the entirety of the hole transporting layer **114**, the amount of holes exceeds that of electrons. As a result, excitons are formed at the interface between the electron transporting layer **116** and the emission layer **110**, not in the emission layer **110**, whereby efficiency is lowered and lifespan is shortened.

Each second hole transporting layer **114b** is formed of a hole host having the same material as each first hole transporting layer **114a**. Consequently, each second hole transporting layer **114b** has a HOMO level of 5.0 eV or more. The second hole transporting layers **114b** occupy 75 to 90% the entirety of the hole transporting layer **114**.

The host used in the first and second hole transporting layers **114a** and **114b** is formed of a material, such as NPB, PPD, TPAC, BFA-1T, or TBDB, as represented by Chemical formula 1.


[Chemical formula 1]




NPB

6


-continued




BFA-1T



PPD




TPAC



TBDB

The p-type dopant is formed of a material, such as [F4-TCNQ], [1,4-TCAQ], [6,3-TCPQ], [TCAQ], [TCNHPQ], or [TCNPQ], as represented by Chemical formula 2.



The p-type dopant doped in each first hole transporting layer **114a** may fill gaps of the hole host having a laminated structure to improve stability of the interface between the first electrode **102** and the hole transporting layer **114** and to lower a hole injection barrier. Consequently, Joule heating at the interface between the first electrode **102** and the hole transporting layer **114** may be reduced. As a result, the holes may be stably supplied to the emission layer **110**, thereby improving efficiency and lifespan characteristics.

Specifically, as shown in FIG. 3A, it can be seen that an example in which first hole transporting layers **114a** and second hole transporting layers **114b** each doped with 3% of

a p-type dopant are formed between a first electrode **102** and an emission layer **110** and another example in which first hole transporting layers **114a** and second hole transporting layers **114b** each doped with 5% of a p-type dopant are formed between a first electrode **102** and an emission layer **110** have lower driving voltage to generate the same current density than a comparative example in which a hole injection layer and a hole transporting layer are formed between a first electrode and an emission layer.

TABLE 1

	Efficiency (cd/A)				T95 lifespan (hrs)			
	R	G	B	W	R	G	B	W
Example	35.6	49.3	3.85	24.4	160	800	320	510
Comparative example	34.1	50.0	3.3	23.8	110	400	420	220

As shown in Table 1, it can be seen that the example has an efficiency characteristic equal to that of the comparative example. In addition, as shown in Table 1 and FIG. 3B, it can be seen that the example has a lifespan characteristic 100% greater than that of the comparative example. In Table 1, T95 means time until the lifespan of a white organic light emitting device reaches about 95%.

The hole transporting layer **114** is formed on the first electrode **102** using a deposition apparatus shown in FIG. 4 (S22). The deposition apparatus shown in FIG. 4 includes a guide rail **158**, a body **156** to perform reciprocating scan motion along the guide rail **158**, and first and second deposition sources **152** and **154** provided in the body **156**. The first deposition source **152** supplies a hole host to a substrate **101** and the second deposition source **154** supplies a p-type dopant to the substrate **101**. At this time, supply speeds of the hole host and the p-type dopant may be changed to adjust a mixture ratio of the hole host to the p-type dopant. As the hole host from the first deposition source **152** and the p-type dopant from the second deposition source **154** are supplied to the substrate **101** as described above, a first hole transporting layer **114a** constituted by the p-type dopant and the hole host is formed on the substrate. Subsequently, a second hole transporting layer **114b** constituted by a hole host is formed on the first hole transporting layer **114a**. Meanwhile, in a case in which the body **156** having the first and second deposition sources **152** and **154** performs reciprocating scan motion in one direction and in the opposite direction, first and second hole transporting layers **114a** and **114b** are alternately formed as shown in FIG. 1. The number of the first and second hole transporting layers **114a** and **114b** may be adjusted according to the number of times of reciprocating scan motion.

FIG. 5 is a sectional view showing an organic light emitting display device according to a second embodiment of the present disclosure.

The organic light emitting display device shown in FIG. 5 is identical in construction to that shown in FIG. 1 except that red, green, and blue sub-pixels have different distances between a first electrode **102** and an emission layer **110** and, therefore, a detailed description of the same components will be omitted.

The distance between the first electrode **102** and the emission layer **110** of the blue (B) sub-pixel is the smallest. The distance between the first electrode **102** and the emission layer **110** the red (R) sub-pixel is the largest. The distance between the first electrode **102** and the emission layer **110** the green (G) sub-pixel is intermediate. The respective sub-pixels

constructively interfere with exit light, thereby optimizing vertical efficiency at each sub-pixel.

To this end, the red (R), green (G), and blue (B) sub-pixels each include a common hole transporting layer **114**. The red (R) and green (G) sub-pixels each include an optical adjustment layer **112** formed between the common hole transporting layer **114** and the first electrode **102**. In this case, the optical adjustment layer **112** of the red (R) sub-pixel has a larger thickness than the optical adjustment layer **112** of the green (G) sub-pixel.

The optical adjustment layer **112** includes first and second optical adjustment layers **112a** and **112b**. The common hole transporting layer **114** includes first and second hole transporting layers **114a** and **114b**.

The first optical adjustment layer **112a** and the first hole transporting layer **114a** are formed by doping a hole host with a p-type dopant at a doping concentration of 1 to 10%. At this time, the hole host has a HOMO level of 5.0 eV or more. The p-type dopant has a LUMO level less than the HOMO level of the hole host.

The second optical adjustment layer **112b** and the second hole transporting layer **114b** are formed of a hole host having the same material as or different materials from the first optical adjustment layer **112a** and the first hole transporting layer **114a**. Consequently, the second optical adjustment layer **112b** and the second hole transporting layer **114b** each have a HOMO level of 5.0 eV or more. The second optical adjustment layer **112b** and the second hole transporting layer **114b** occupy 75% to 90% the entirety of the hole transporting layer **114**.

The host used in the first and second optical adjustment layers **112a** and **112b** and the first and second hole transporting layers **114a** and **114b** is formed of a material, such as NPB, PPD, TPAC, BFA-1T, or TBDB, as represented by Chemical formula 1. The same host or different hosts may be used in the first and second optical adjustment layers **112a** and **112b** and the host used in the first and second hole transporting layers **114a** and **114b**.

The p-type dopant is formed of a material, such as [F4-TCNQ], [1,4-TCAQ], [6,3-TCPQ], [TCAQ], [TCNTHPQ], or [TCNPQ], as represented by Chemical formula 2. The same p-type dopant or different p-type dopants may be used in the first optical adjustment layer **112a** and the first hole transporting layer **114a**. The p-type dopant used in the first optical adjustment layer **112a** and the first hole transporting layer **114a** may have the same doping concentration or different concentrations. In a case in which the doping concentration of the p-type dopant in the first optical adjustment layer **112a** of the red sub-pixel having the largest thickness is higher than that of the p-type dopant in the first optical adjustment layer **112a** of the green sub-pixel, driving voltage of the red (R) sub-pixel may be lowered, thereby reducing power consumption.

Specifically, Table 2 illustrates electro-optic characteristics of red sub-pixels of a comparative example and examples.

TABLE 2

Structure	Volt	cd/A	lm/W	CIE _x	CIE _y
Comparative example	4.8	54.1	35.6	0.665	0.332
Example (3%)	4.4	52.8	37.6	0.664	0.334
Example (5%)	4.3	54.6	39.9	0.662	0.331
Example (7%)	4.2	54.1	40.4	0.662	0.335

In Table 2, the comparative example and the examples are devices having the following stacked structures.

Comparative example: a hole transporting layer (100 Å) doped with a 3% p-type dopant/hole transporting layer (1900 Å)/red emission layer/electron transporting layer/second electrode/capping layer

Example (3%): a first optical adjustment layer (100 Å) doped with a 3% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/red emission layer/electron transporting layer/second electrode/capping layer

Example (5%): a first optical adjustment layer (100 Å) doped with a 5% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/red emission layer/electron transporting layer/second electrode/capping layer

Example (7%): a first optical adjustment layer (100 Å) doped with a 7% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/red emission layer/electron transporting layer/second electrode/capping layer

As shown in Table 2 and FIG. 6A, it can be seen that the example in which the first optical adjustment layer **112a** of the red sub-pixel is doped with the 7% p-type dopant has maximally 0.6V lower driving voltage to generate the same current density than the comparative example. In addition, as shown in FIG. 6B, it can be seen that lifespan of the example is somewhat increased.

Table 3 illustrates electro-optic characteristics of green sub-pixels of a comparative example and examples.

TABLE 3

Structure	Volt	cd/A	lm/W	CIE _x	CIE _y
Comparative example	4.8	54.1	35.6	0.665	0.332
Example (3%)	4.4	52.8	37.6	0.664	0.334
Example (5%)	4.3	54.6	39.9	0.662	0.331
Example (7%)	4.2	54.1	40.4	0.662	0.335

In Table 3, the comparative example and the examples are devices having the following stacked structures.

Comparative example: a hole transporting layer (100 Å) doped with a 3% p-type dopant/hole transporting layer (1900 Å)/green emission layer/electron transporting layer/second electrode/capping layer

Example (3%): a first optical adjustment layer (100 Å) doped with a 3% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/green emission layer/electron transporting layer/second electrode/capping layer

Example (5%): a first optical adjustment layer (100 Å) doped with a 5% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/green emission layer/electron transporting layer/second electrode/capping layer

Example (7%): a first optical adjustment layer (100 Å) doped with a 7% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/green emission layer/electron transporting layer/second electrode/capping layer

As shown in Table 3 and FIG. 7A, it can be seen that the example in which the first optical adjustment layer **112a** of

the green sub-pixel is doped with the 5% p-type dopant and the example in which the first optical adjustment layer **112a** of the green sub-pixel is doped with the 7% p-type dopant have maximally 0.3V lower driving voltage to generate the same current density than the comparative example. In addition, as shown in FIG. 7B, it can be seen that lifespan of each example is increased.

FIG. 8 is a sectional view showing an organic light emitting display device according to a third embodiment of the present disclosure. The organic light emitting display device shown in FIG. 8 is identical in construction to that shown in FIG. 5 except that optical adjustment layers **112** of red and green sub-pixels each include only a first optical adjustment layer and, therefore, a detailed description of the same components will be omitted.

A red (R) sub-pixel includes an optical adjustment layer **112** formed between a common hole transporting layer **114** and a first electrode **102**. A green (G) sub-pixel includes an optical adjustment layer **112**, having a smaller thickness than the optical adjustment layer **112** of the red R sub-pixel, formed between a common hole transporting layer **114** and a first electrode **102**.

The optical adjustment layer **112** of each of the red and green sub-pixels includes only a first optical adjustment layer. The common hole transporting layer **114** is formed by sequentially stacking first and second hole transporting layers **114a** and **114b**.

The optical adjustment layer **112** and the first hole transporting layer **114a** are formed by doping a hole host with a p-type dopant at a doping concentration of 1 to 10%. At this time, the hole host has a HOMO level of 5.0 eV or more. The p-type dopant has a LUMO level less than the HOMO level of the hole host.

The second hole transporting layer **114b** is formed of a hole host having the same material as the first hole transporting layer **114a**. Consequently, the second hole transporting layer **114b** has a HOMO level of 5.0 eV or more.

The host used in the optical adjustment layer **112** and the first and second hole transporting layers **114a** and **114b** is formed of a material, such as NPB, PPD, TPAC, BFA-1T, or TBDB, as represented by Chemical formula 1. The same host or different hosts may be used in the optical adjustment layer **112** and the first and second hole transporting layers **114a** and **114b**.

The p-type dopant is formed of a material, such as [F4-TCNQ], [1,4-TCAQ], [6,3-TCPQ], [TCAQ], [TCNTHPQ], or [TCNPQ], as represented by Chemical formula 2. The same p-type dopant or different p-type dopants may be used in the optical adjustment layer **112** and the first hole transporting layer **114a**. The p-type dopant used in the optical adjustment layer **112** and the first hole transporting layer **114a** may have the same doping concentration or different concentrations. In a case in which the doping concentration of the p-type dopant in the optical adjustment layer **112** of the red sub-pixel, which is thick, is higher than that of the p-type dopant in the optical adjustment layer **112** of the green (G) sub-pixel, driving voltage of the red sub-pixel may be lowered, thereby reducing power consumption.

FIGS. 9 and 10 are sectional views showing an organic light emitting display device according to a fourth embodiment of the present disclosure. The organic light emitting display device shown in FIGS. 9 and 10 are identical in construction to those shown in FIGS. 5 and 8 except that red, green, and blue sub-pixels in common have blue emission layers having the same thickness and, therefore, a detailed description of the same components will be omitted.

The red (R) sub-pixel shown in FIGS. 9 and 10 includes a red emission layer **110a** and a blue emission layer **110b** sequentially stacked on a second hole transporting layer **114b** of a common hole transporting layer **114**. In this case, short-wavelength blue light generated from the blue emission layer **110b** is absorbed by long-wavelength red light generated from the red emission layer **110a**. Consequently, the red sub-pixel embodies red (R) without being mixed with blue light.

The green (G) sub-pixel shown in FIGS. 9 and 10 includes a green (G) emission layer **110a** and a blue emission layer **110b** sequentially stacked on a second hole transporting layer **114b** of a common hole transporting layer **114**. In this case, short-wavelength blue light generated from the blue emission layer **110b** is absorbed by long-wavelength green light generated from the green (G) emission layer **110a**. Consequently, the green sub-pixel embodies green (G) without being mixed with blue light.

At this time, the red emission layer **110a** of the red (R) sub-pixel is formed such that the thickness of the red emission layer **110a** of the red (R) sub-pixel is greater than that of the green emission layer **110a** of the green (G) sub-pixel. Consequently, the total thickness of the red (R) sub-pixel is the largest, the total thickness of the green (G) sub-pixel is intermediate, and the total thickness of the blue (B) sub-pixel is the smallest. In the organic light emitting display device according to the fourth embodiment of the present disclosure, therefore, the total thicknesses of the red (R), green (G), and blue (B) sub-pixels are adjusted using the optical adjustment layer **112**, the red (R) emission layer **110a**, and the green (G) emission layer **110a** to constructively interfere with exit light, thereby optimizing vertical efficiency at each sub-pixel.

Table 4 illustrates electro-optic characteristics of red sub-pixels of a comparative example and an example according to the fourth embodiment of the present disclosure.

TABLE 4

Structure	Volt	cd/A	Im/W	CIE _x	CIE _y
Comparative example	4.9	55.1	35.7	0.662	0.335
Example (7%)	4.4	55.8	39.6	0.660	0.338

In Table 4, the comparative example and the example are devices having the following stacked structures.

Comparative example: a hole transporting layer (100 Å) doped with a 3% p-type dopant/hole transporting layer (1900 Å)/red emission layer/blue emission layer/electron transporting layer/second electrode/capping layer
 Example (7%): a first optical adjustment layer (100 Å) doped with a 7% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/red emission layer/blue emission layer/electron transporting layer/second electrode/capping layer

As shown in Table 4 and FIG. 11A, it can be seen that the example in which the first optical adjustment layer **112a** of the optical adjustment layer **112** of the red sub-pixel is doped with the 7% p-type dopant has maximally 0.5V lower driving voltage to generate the same current density than the comparative example. In addition, as shown in FIG. 11B, it can be seen that lifespan of the example is somewhat increased.

Table 5 illustrates electro-optic characteristics of green sub-pixels of a comparative example and an example.

TABLE 5

Structure	Volt	cd/A	Im/W	CIE _x	CIE _y
Comparative example	5.1	53.6	33.0	0.268	0.705
Example (5%)	4.6	54.9	37.6	0.271	0.703

In Table 5, the comparative example and the example are devices having the following stacked structures.

Comparative example: a hole transporting layer (100 Å) doped with a 3% p-type dopant/hole transporting layer (1900 Å)/green emission layer/blue emission layer/electron transporting layer/second electrode/capping layer

Example (5%): a first optical adjustment layer (100 Å) doped with a 5% p-type dopant/second optical adjustment layer (700 Å)/first hole transporting layer (100 Å) doped with a 3% p-type dopant/second hole transporting layer (1100 Å)/green emission layer/blue emission layer/electron transporting layer/second electrode/capping layer

As shown in Table 5 and FIG. 12A, it can be seen that the example in which the first optical adjustment layer 112a of the optical adjustment layer 112 of the green sub-pixel is doped with the 5% p-type dopant has maximally 0.5V lower driving voltage to generate the same current density than the comparative example. In addition, as shown in FIG. 12B, it can be seen that lifespan of the example is equal to that of the comparative example.

FIGS. 13A to 13F are sectional views illustrating a method of fabricating an organic light emitting display device according to the present disclosure. Hereinafter, a method of fabricating the organic light emitting display device shown in FIG. 5 will be described by way of example.

First, a metal layer and a transparent layer are sequentially deposited on a substrate 101 and the metal layer and the transparent layer are patterned by photolithography and etching to form a first electrode 102. The first electrode 102 is formed to have a multi-layered structure including a metal layer formed of aluminum (Al) or an aluminum alloy, such as AlNd, and a transparent layer formed of indium tin oxide (ITO) or indium zinc oxide (IZO).

Subsequently, an optical adjustment layer 112 and a common hole transporting layer 114 are sequentially formed on the substrate 101, on which the first electrode 102 is formed.

Specifically, as shown in FIG. 13A, a first evaporation source 132a containing a p-type dopant D and a second evaporation source 132b containing a hole host H are provided in a vacuum chamber 138. In addition, shutters 122a and 122b are formed at the first and second evaporation sources 132a and 132b, respectively.

The substrate 101, on which the first electrode 102 is formed, is located in the vacuum chamber 138. Subsequently, the shutters 122a and 122b of the first and second evaporation sources 132a and 132b are opened. The p-type dopant D and the hole host H evaporated from the first and second evaporation sources 132a and 132b are deposited on the substrate 101 through an opening of a shadow mask 128 to form a first optical adjustment layer 112a of an optical adjustment layer 112 of a red (R) sub-pixel.

Subsequently, as shown in FIG. 13B, the shutter 122a of the first evaporation source 132a is closed and the shutter 122b of the second evaporation source 132b is opened. The hole host H evaporated from the second evaporation source 132b is deposited on the first optical adjustment layer 112a of the red (R) sub-pixel through the opening of the shadow mask 128 to form a second optical adjustment layer 112b.

Subsequently, as shown in FIG. 13C, the shutters 122a and 122b of the first and second evaporation sources 132a and 132b are opened. The p-type dopant D and the hole host H evaporated from the first and second evaporation sources 132a and 132b are deposited on the substrate 101 through the opening of the shadow mask 128 to form a first optical adjustment layer 112a of a green (G) sub-pixel. At this time, doping concentration of the p-type dopant doped in the first optical adjustment layer 112a of the green (G) sub-pixel is lower than that of the p-type dopant doped in the first optical adjustment layer 112a of the red (R) sub-pixel.

Subsequently, as shown in FIG. 13D, the shutter 122a of the first evaporation source 132a is closed and the shutter 122b of the second evaporation source 132b is opened. The hole host H evaporated from the second evaporation source 132b is deposited on the first optical adjustment layer 112a of the green (G) sub-pixel through the opening of the shadow mask 128 to form a second optical adjustment layer 112b of the green (G) sub-pixel.

At this time, the second optical adjustment layer 112b of the green (G) sub-pixel is formed such that the thickness of the second optical adjustment layer 112b of the green (G) sub-pixel is less than that of the second optical adjustment layer 112b of the optical adjustment layer 112 of the red (R) sub-pixel.

Subsequently, as shown in FIG. 13E, the shutters 122a and 122b of the first and second evaporation sources 132a and 132b are opened. The p-type dopant D and the hole host H evaporated from the first and second evaporation sources 132a and 132b are deposited on the substrate 101 through the opening of the shadow mask 128 to form first hole transporting layers 114a of common hole transporting layers 114 of the red (R) sub-pixel, the green (G) sub-pixel, and a blue (B) sub-pixel.

Subsequently, as shown in FIG. 13F, the shutter 122a of the first evaporation source 132a is closed and the shutter 122b of the second evaporation source 132b is opened. The hole host H evaporated from the second evaporation source 132b is deposited on the first hole transporting layers 114a of the common hole transporting layers 114 through the opening of the shadow mask 128 to form second hole transporting layers 114b of the common hole transporting layers 114 of the red (R), green (G), and blue (B) sub-pixels. In FIGS. 13A to 13F, the hole host and the p-type dopant deposited on the optical adjustment layers 112 and the common hole transporting layers 114 are formed of the same material and, therefore, the first and second evaporation sources 132a and 132b are provided. In a case in which the hole host and the p-type dopant are formed of different materials, however, additional evaporation sources are needed.

Subsequently, red (R), green (G), and blue (B) emission layers 110 are sequentially formed on the substrate 101, on which the optical adjustment layers 112 and the common hole transporting layers 114 are formed. Electron transporting layers 116 are formed on the substrate 101, on which the red (R), green (G), and blue (B) emission layers 110 are formed. Second electrodes 104 and capping layers 120 are sequentially formed on the substrate 101, on which the electron transporting layers 116 are formed. Each second electrode 104 is formed of a metal, an inorganic substance, a mixture of metals, a mixture of a metal and an inorganic substance, or a mixture thereof. Each second electrode 104 is formed as a semi-transparent electrode.

As is apparent from the above description, the organic light emitting display device according to the present disclosure is configured such that at least two layers of the multi-layered hole transporting layer are formed as hole transporting layers

15

doped with the p-type dopant. In the organic light emitting display device according to the present disclosure, therefore, power consumption is reduced and lifespan and efficiency characteristics are improved.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present disclosure without departing from the spirit or scope of the disclosure. Thus, it is intended that the present disclosure covers the modifications and variations of the embodiments provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An organic light emitting display device comprising a first sub-pixel, a second sub-pixel, and a third sub-pixel for emitting different colored light, each of the sub-pixels comprising:

an anode and a cathode on a substrate configured to face each other;

an emission layer between the anode and the cathode;

a multi-layered hole transporting layer between, and in contact with, the anode and the emission layer; and

an electron transporting layer between the cathode and the emission layer,

wherein the multi-layered hole transporting layer of at least one of the first sub-pixel, the second sub-pixel and the third sub-pixel comprises:

a first hole transporting layer, wherein the first hole transporting layer is of at least two materials, the at least two materials including a hole host and a p-type dopant having a doping concentration of 1 vol. % to 10 vol. %; and

a second hole transporting layer formed of the hole host, wherein the second hole transporting layer is over the first hole transporting layer and is farther from the anode than the first hole transporting layer is from the anode, and has a doping concentration less than the doping concentration of the first hole transporting layer, and

wherein the first hole transporting layer comprising the p-type dopant occupies 10 vol. % to 25 vol. % in the multi-layered hole transporting layer.

2. The organic light emitting display device according to claim 1, wherein:

the first sub-pixel is a red sub-pixel configured to emit red light through a red emission layer;

the second sub-pixel is a green sub-pixel configured to emit green light through a green emission layer; and

the third sub-pixel is a blue sub-pixel configured to emit blue light through a blue emission layer,

wherein the multi-layered hole transporting layer of each of the red and green sub-pixels comprises:

a common hole transporting layer formed by sequentially stacking the first hole transporting layer and the second hole transporting layer; and

an optical adjustment layer between the common hole transporting layer and the anode, and

wherein the multi-layered hole transporting layer of the blue sub-pixel comprises a common hole transporting layer formed by sequentially stacking the first hole transporting layer and the second hole transporting layer.

3. The organic light emitting display device according to claim 2, wherein:

the red, green, and blue sub-pixels in common comprise blue emission layers;

16

the blue emission layer of the red sub-pixel is between the red emission layer and the electron transporting layer; and

the blue emission layer of the green sub-pixel is between the green emission layer and the electron transporting layer.

4. The organic light emitting display device according to claim 2, wherein:

the optical adjustment layer comprises a first optical adjustment layer and a second optical adjustment layer between the anode and the common hole transporting layer, wherein:

the first optical adjustment layer is formed of a hole host and a p-type dopant identical to or different from that of the first hole transporting layer; and

the second optical adjustment layer is formed of a hole host identical to or different from that of the second hole transporting layer, and is farther from the anode than the first optical adjustment layer is from the anode.

5. The organic light emitting display device according to claim 4, wherein the first optical adjustment layer of the red sub-pixel has a larger thickness than the first optical adjustment layer of the green sub-pixel.

6. The organic light emitting display device according to claim 4, wherein the first optical adjustment layer and the first hole transporting layer comprising the p-type dopant occupy 10 vol. % to 25 vol. % in the multi-layered hole transporting layer.

7. The organic light emitting display device according to claim 2, wherein:

the optical adjustment layer comprises a first optical adjustment layer between the anode and the common hole transporting layer; and

the first optical adjustment layer is formed of a hole host and a p-type dopant identical to or different from that of the first hole transporting layer.

8. The organic light emitting display device according to claim 7, wherein the first optical adjustment layer of the red sub-pixel has a larger thickness than the first optical adjustment layer of the green sub-pixel.

9. The organic light emitting display device according to claim 7, wherein the first optical adjustment layer and the first hole transporting layer comprising the p-type dopant occupy 10 vol. % to 25 vol. % in the multi-layered hole transporting layer.

10. The organic light emitting display device according to claim 1, wherein:

the p-type dopant is formed of a compound selected from the group consisting of F4-TCNQ, 1,4-TCAQ, 6,3-TCPQ, TCAQ, TCNTHPQ, and TCNPQ; and

the hole host is formed of a compound selected from the group consisting of NPB, PPD, TPAC, BFA-1T, and TBDB.

11. The organic light emitting display device according to claim 10, wherein the p-type dopant has a lowest unoccupied molecular orbital (LUMO) level less than that of the hole host.

12. A method of fabricating an organic light emitting display device comprising a first sub-pixel, a second sub-pixel, and a third sub-pixel for emitting colored light, the method comprising:

forming anodes of the first sub-pixel, the second sub-pixel, and the third sub-pixel on a substrate;

forming multi-layered hole transporting layers on the anodes;

forming emission layers on the hole transporting layers;

17

forming electron transporting layers on the emission layers; and

forming cathodes on the electron transporting layers, wherein the multi-layered hole transporting layer of at least one of the first sub-pixel, the second sub-pixel, and the third sub-pixel comprises:

a first hole transporting layer, wherein the first hole transporting layer is of at least two materials, the at least two materials including a hole host and a p-type dopant having a doping concentration of 1 vol. % to 10 vol. %; and

a second hole transporting layer formed of the hole host, wherein the second hole transporting layer is over the first hole transporting layer and farther from the anode than the first hole transporting layer is from the anode, and has a doping concentration less than the doping concentration of the first hole transporting layer, and wherein the first hole transporting layer comprising the p-type dopant occupies 10 vol. % to 25 vol. % in the multi-layered hole transporting layer.

13. The method according to claim 12, wherein:

the first sub-pixel is a red sub-pixel configured to emit red light through a red emission layer;

the second sub-pixel is a green sub-pixel configured to emit green light through a green emission layer; and

the third sub-pixel is a blue sub-pixel configured to emit blue light through a blue emission layer;

wherein forming the multi-layered hole transporting layers of the red sub-pixel, the green sub-pixel, and blue sub-pixel comprises:

forming optical adjustment layers on the anodes of the red sub-pixel and the green sub-pixel; and

forming common hole transporting layers each comprising the first and second hole transporting layers on the optical adjustment layers of the red and green sub-pixels and on the anode of the blue sub-pixel; and

at least one of the optical adjustment layers, first hole transporting layers, and second hole transporting layers is formed by scanning or deposition using a shutter.

14. The method according to claim 13, wherein

forming each optical adjustment layer comprises sequentially forming a first optical adjustment layer and a second optical adjustment layer between the anode and the common hole transporting layer, wherein:

the first optical adjustment layer is formed of a hole host and a p-type dopant identical to or different from that of the first hole transporting layer; and

the second optical adjustment layer is formed of a hole host identical to or different from that of the second hole transporting layer, and is farther from the anode than the first optical adjustment layer is from the anode.

18

15. The method according to claim 14, wherein the first optical adjustment layer of a red sub-pixel has a larger thickness than the first optical adjustment layer of a green sub-pixel.

16. The method according to claim 13, wherein:

forming each optical adjustment layer comprises forming a first optical adjustment layer between the anode and the common hole transporting layer; and

the first optical adjustment layer is formed of a hole host and a p-type dopant identical to or different from that of the first hole transporting layer.

17. The method according to claim 16, wherein the first optical adjustment layer of the red sub-pixel has a larger thickness than the first optical adjustment layer of the green sub-pixel.

18. The method according to claim 12, wherein:

the p-type dopant is formed of a compound selected from the group consisting of F4-TCNQ, 1,4-TCAQ, 6,3-TCPQ, TCAQ, TCNTHPQ, and TCNPQ; and

the hole host is formed of a compound selected from the group consisting of NPB, PPD, TPAC, BFA-1T, and TBDB.

19. An organic light emitting display device comprising a first sub-pixel, a second sub-pixel, and a third sub-pixel for emitting different colored light, each of the sub-pixels comprising:

an anode and a cathode on a substrate configured to face each other;

an emission layer formed between the anode and the cathode;

a multi-layered hole transporting layer formed between, and in contact with, the anode and the emission layer; and

an electron transporting layer formed between the cathode and the emission layer,

wherein the multi-layered hole transporting layer of at least one of the first sub-pixel, the second sub-pixel and the third sub-pixel comprises:

a first hole transporting layer, wherein the first hole transporting layer is of at least two materials, the two materials including a hole host and a p-type dopant having a doping concentration of 1 vol. % to 10 vol. %; and

a second hole transporting layer formed of the hole host, wherein the second hole transporting layer is over the first hole transporting layer and farther from the anode than the first hole transporting layer is from the anode, and has a doping concentration of 0 vol. %, and

wherein the first hole transporting layer comprising the p-type dopant occupies 10 vol. % to 25 vol. % in the multi-layered hole transporting layer.

* * * *

专利名称(译)	有机发光显示装置及其制造方法		
公开(公告)号	US9385345	公开(公告)日	2016-07-05
申请号	US14/134119	申请日	2013-12-19
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	LEE HEUI DONG KIM KWAN SOO SONG DAE GWON PARK JIN HO YOON SUNG JI LIM DONG HYEOK		
发明人	LEE, HEUI-DONG KIM, KWAN-SOO SONG, DAE-GWON PARK, JIN-HO YOON, SUNG-JI LIM, DONG-HYEOK		
IPC分类号	H01L51/00 H01L51/56 H01L51/50 H01L27/32		
CPC分类号	H01L51/56 H01L51/506 H01L51/5064 H01L27/3211 H01L2251/558		
优先权	1020120157157 2012-12-28 KR		
其他公开文献	US20140183493A1		
外部链接	Espacenet USPTO		

摘要(译)

本发明公开了一种有机发光显示装置，包括实现不同颜色的第一至第三子像素，其中第一至第三子像素中的每一个包括设置在基板上以彼此面对的第一和第二电极，形成发光层在第一和第二电极之间，形成在第一电极和发光层之间以与第一电极和发光层接触的多层空穴传输层，以及形成在第二电极和发光层之间的电子传输层其中，第一至第三子像素中的至少一个的多层空穴传输层包括由空穴主体和掺杂浓度为1至10的p型掺杂剂形成的至少两层的第一空穴传输层%和由空穴主体形成的第二空穴传输层。

