



US010522778B2

(12) **United States Patent**
Bloom et al.

(10) **Patent No.:** **US 10,522,778 B2**
(45) **Date of Patent:** **Dec. 31, 2019**

(54) **ORGANIC LIGHT-EMITTING DIODE INCLUDING AN ELECTRONIC TRANSPORT LAYER COMPRISING A THREE COMPONENT BLEND OF A MATRIX COMPOUND AND TWO LITHIUM COMPOUNDS**

(71) Applicant: **Novaled GmbH**, Dresden (DE)

(72) Inventors: **Francisco Bloom**, Eindhoven (NL);
Thomas Rosenow, Dresden (DE);
Tobias Canzler, Dresden (DE); **Bodo Wallikewitz**, Dresden (DE)

(73) Assignee: **Novaled GmbH**, Dresden (DE)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 288 days.

(21) Appl. No.: **15/516,067**

(22) PCT Filed: **Sep. 30, 2015**

(86) PCT No.: **PCT/EP2015/072630**

§ 371 (c)(1),

(2) Date: **Mar. 31, 2017**

(87) PCT Pub. No.: **WO2016/050882**

PCT Pub. Date: **Apr. 7, 2016**

(65) **Prior Publication Data**

US 2017/0301876 A1 Oct. 19, 2017

(30) **Foreign Application Priority Data**

Oct. 1, 2014 (EP) 14187326

(51) **Int. Cl.**

H01L 51/50 (2006.01)

H01L 51/00 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/5072** (2013.01); **H01L 51/0077** (2013.01); **H01L 51/508** (2013.01); **H01L 51/5056** (2013.01); **H01L 51/5076** (2013.01); **H01L 51/0072** (2013.01)

(58) **Field of Classification Search**

None

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2009/0142618 A1	6/2009	Begley et al.	
2011/0215308 A1*	9/2011	Im	H01L 51/006 257/40
2013/0228753 A1	9/2013	Moon et al.	
2014/0014927 A1	1/2014	Kim et al.	

FOREIGN PATENT DOCUMENTS

WO	2013/079676 A1	6/2013
WO	2013/079678 A1	6/2013

OTHER PUBLICATIONS

PCT International Search Report and Written Opinion for PCT Application No. PCT/EP2015/072630 dated Jan. 12, 2016 (11 pages).

* cited by examiner


Primary Examiner — Gregory D Clark

(74) *Attorney, Agent, or Firm* — Eversheds Sutherland (US) LLP

(57) **ABSTRACT**

The present invention relates to an organic light-emitting diode (100) comprising an emission layer (150) and at least one electron transport layer (161), wherein the at least one electron transport layer (161) comprises at least one matrix compound and at least two lithium compounds.

25 Claims, 3 Drawing Sheets






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8

1

**ORGANIC LIGHT-EMITTING DIODE
INCLUDING AN ELECTRONIC TRANSPORT
LAYER COMPRISING A THREE
COMPONENT BLEND OF A MATRIX
COMPOUND AND TWO LITHIUM
COMPOUNDS**

CROSS REFERENCE TO RELATED
APPLICATIONS

This application is a U.S. national stage application of PCT/EP2015/072630, filed Sep. 30, 2015, which claims priority to European Application No. 14187326.5, filed Oct. 1, 2014. The contents of these applications are hereby incorporated by reference.

DESCRIPTION

The present invention relates to an organic light-emitting diode containing an electron transport layer comprising a three-component blend of a matrix compound and two lithium compounds, and a method of manufacturing the same.

DESCRIPTION OF THE RELATED

Organic light-emitting diodes (OLEDs), which are self-emitting devices, have a wide viewing angle, excellent contrast, quick response, high brightness, excellent driving voltage characteristics, and color reproduction. A typical OLED includes an anode, a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and a cathode, which are sequentially stacked on a substrate. In this regard, the HTL, the EML, and the ETL are thin films formed from organic compounds.

When a voltage is applied to the anode and the cathode, holes injected from the anode move to the EML, via the HTL, and electrons injected from the cathode move to the EML, via the ETL. The holes and electrons recombine in the EML to generate excitons. When the excitons drop from an excited state to a ground state, light is emitted. The injection and flow of holes and electrons should be balanced, so that an OLED having the above-described structure has excellent efficiency and/or a long lifetime.

SUMMARY

It is one object to provide organic light-emitting diode having an increased external quantum efficiency (EQE), especially for blue emitting OLEDs but also, for example, for red, green or white emitting OLEDs, and/or an increased lifetime, in particular for top and/or bottom emission organic light-emitting diodes (OLED).

According to one aspect, there is provided an organic light-emitting diode (OLED) comprising an emission layer and at least one electron transport layer, wherein the at least one electron transport layer comprises at least one matrix compound and at least two lithium compounds.

According to one aspect, there is provided an organic light-emitting diode (OLED) comprising an emission layer and one electron transport layer, wherein the electron transport layer comprises one matrix compound and two lithium compounds.

According to various aspects of the present invention the organic light-emitting diode (OLED) may contain more than one electron transport layer, for example two or three

2

electron transport layers. More than one electron transport layer is referred to as electron transport layer stack in the specification and claims.

According to various aspects the organic light-emitting diode (OLED) may comprises one or two electron transport layers.

According to various aspects the lithium compound can be a lithium organic complex. According to various aspects of the present invention an electron transport layer stack may contain at least one electron transport layer comprising at least one matrix compound and at least two lithium compounds.

According to various aspects the at least two lithium compounds can be lithium organic complexes.

According to various aspects of the present invention an electron transport layer stack may contain two electron transport layer, wherein two electron transport layers or preferably one electron transport layer, comprising one matrix compound and two lithium compounds.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and the second electron transport layer comprising one matrix compound only.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and the second electron transport layer comprising one matrix compound and one lithium compound.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and the second ETL comprising a matrix compound and an elemental metal, wherein the elemental metal is selected from a group comprising alkali, alkaline earth and/or rare earth metals.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and the second electron transport layer does not comprise a matrix compound and at least two lithium compounds.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and a second electron transport layer comprising a matrix compound and at least two lithium compounds.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and a second electron transport layer comprising a matrix compound and at least two lithium compounds, wherein the matrix compound of the first electron transport layer is same or different from the second electron transport layer.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and a second electron transport layer comprising a matrix compound and at least two lithium compounds, wherein at least one lithium

compound, preferably two lithium compounds, of the first electron transport layer is same or different from the second electron transport layer.

According to various aspects of the OLED the electron transport layer stack of two electron transport layers may contain a first electron transport layer comprising a matrix compound and at least two lithium compounds and a second electron transport layer comprising a matrix compound and at least two lithium compounds, wherein at least the matrix compound and at least one lithium compound, preferably two lithium compounds, of the first electron transport layer is same or different from the second electron transport layer.

According to various aspects of the OLED the electron transport layer stack may be formed of three or more electron transport layers, containing at least one electron transport layer comprising a matrix compound and at least two lithium compounds.

According to various aspects the OLED comprises at least one electron transport layer or at least one layer of an electron transport layer stack comprising:

at least one matrix compound and at least two lithium compounds selected from the group comprising lithium organic complexes; and/or

at least one matrix compound and at least two lithium compounds, wherein at least a first lithium compound is selected from the group comprising lithium organic complexes and at least a second lithium compound is selected from the group comprising lithium halides.

According to various aspects of the OLED the electron transport layer stack may be formed of three or more electron transport layers, containing at least two electron transport layers comprising a matrix compound and at least two lithium compounds, wherein the matrix compound and/or at least one lithium compound or two lithium compounds of each electron transport layer containing the three component blend are same or different.

In the context of the present specification "triple mix" means a combination of a matrix compound and two lithium compounds.

According to various aspects of the OLED the electron transport layer and/or electron transport layer stack is free of elemental metal.

According to various aspects of the OLED the electron transport layer stack may contain at least one electron transport layer that is free of a lithium compound selected from the group lithium halide and/or lithium organic complex.

According to various aspects of the OLED the electron transport layer stack may contain at least one electron transport layer that is free of a metal salt and/or a metal organic complex.

In the context that the electron transport layer or layers are free of a metal salt, lithium halide and/or a metal organic complex, the term "free of" means that the so called "free off" electron transport layer or layers may comprise of about 5 wt.-% or less of a metal salt, lithium halide and/or a lithium organic complex, preferably about 0.5 wt.-% or less, and more preferably about 0.05 wt.-% or less, and even more preferably about 0.005 wt.-% or less of metal salt, lithium halide and/or lithium organic complex and most preferred no metal salt, lithium halide and/or a lithium organic complex.

According to various aspects, there is provided an organic light-emitting diode, whereby the organic light-emitting diode does not contain a charge generation layer (CGL).

According to various aspects the matrix compound can be selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphepine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo[c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl)diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline. According to various aspects the lithium halide is selected from the group comprising LiF, LiCl, LiBr or LiI, and preferable LiF.

According to various aspects, wherein for an OLED comprising one electron transport layer only the OLED may contain at least one electron injection layer.

According to various aspects, wherein for an electron transport layer stack of at least two electron transport layers the first electron transport layer is arranged closest to an emission layer and the second electron transport layer is arranged closest to a cathode.

According to various aspects, wherein for an electron transport layer stack of three electron transport layers the first electron transport layer is arranged closest to an emission layer, the second electron layer is sandwiched between the first and the third electron transport layer and the third electron transport layer is arranged closest to a cathode.

The organic light-emitting diode can be a bottom emission OLED or a top emission OLED.

For the following defined terms, these definitions shall be applied, unless a different definition is given in the claims or elsewhere in this specification.

The external quantum efficiency, also named EQE, is measured in percent (%).

The lifetime, also named LT, between starting brightness and 97% of the original brightness is measured in hours (h).

The voltage, also named V, is measured in Volt (V) at 10 milliAmpere per square centimeter (mA/cm²) in bottom emission devices and at 15 mA/cm² for top emission devices.

The color space is described by coordinates CIE-x and CIE-y (International Commission on Illumination 1931). For blue emission the CIE-y is of particular importance. A smaller CIE-y denotes a deeper blue color.

The highest occupied molecular orbital, also named HOMO, and lowest unoccupied molecular orbital, also named LUMO, are measured in electron volt (eV).

The term "OLED" and "organic light-emitting diode" is simultaneously used and having the same meaning.

The term "lithium borate" as used in the specification includes a lithium organic borate complex.

The term "lithium compound" as used in the specification includes a lithium organic complex.

5

The term “lithium phenolate” as used in the specification includes a lithium phosphoryl aryl complex.

As used herein, . . . weight percent“, . . . wt.-%“, . . . percent by weight“, . . . % by weight“, and variations thereof refer to a composition, component, substance or agent as the weight of that component, substance or agent of the respective electron transport layer divided by the total weight of the respective electron transport layer thereof and multiplied by 100. It is understood that the total weight percent amount of all components, substances and agents of the respective electron transport layer are selected such that it does not exceed 100 wt.-%.

All numeric values are herein assumed to be modified by the term “about“, whether or not explicitly indicated. As used herein, the term “about” refers to variation in the numerical quantity that can occur. Whether or not modified by the term “about“, the claims include equivalents to the quantities.

It should be noted that, as used in this specification and the appended claims, the singular forms “a“, “an“, and “the” include plural referents unless the content clearly dictates otherwise.

The term “free of“, “does not contain“, “does not comprise” does not exclude impurities. Impurities have no technical effect with respect to the object achieved by the present invention.

The term “alkyl” refers to straight-chain or branched alkyl groups. The term “1 to 20 carbon atoms” as used herein refers to straight-chain or branched alkyl groups having 1 to 20 carbon atoms. The alkyl groups can be selected from the group comprising methyl, ethyl and the isomers of propyl, butyl or pentyl, such as isopropyl, isobutyl, tert.-butyl, sec.-butyl and/or isopentyl. The term “aryl” refers to aromatic groups for example phenyl or naphthyl.

Herein, when a first element is referred to as being formed or disposed “on” a second element, the first element can be disposed directly on the second element or one or more other elements may be disposed there between. When a first element is referred to as being formed or disposed “directly on” a second element, no other elements are disposed there between.

According to various embodiments of the OLED the electron transport layer and/or electron transport layer stack may comprise as a lithium compound a lithium organic complex only.

According to various embodiments of the OLED the electron transport layer and/or electron transport layer stack may comprise at least two lithium compounds, preferably two lithium compounds, selected from the group comprising a lithium quinolate, a lithium borate, a lithium phenolate, preferably the lithium phenolate is a lithium phosphoryl aryl complex, a lithium pyridinolate or a lithium Schiff base and lithium fluorid, preferably a lithium 2-(diphenylphosphoryl)-phenolate, lithium tetra(1H-pyrazol-1-yl)borate, a lithium quinolate of formula (III), a lithium 2-(pyridin-2-yl)phenolate and LiF, and more preferred selected from the group comprising a lithium 2-(diphenylphosphoryl)-phenolate, lithium tetra(1H-pyrazol-1-yl)borate, a lithium quinolate of formula (III), a lithium 2-(pyridin-2-yl)phenolate.

According to various embodiments of the organic light-emitting diode at least one electron transport layer or at least two electron transport layers comprising:

about ≤ 90 wt.-% to about ≥ 30 wt.-%, preferably about ≤ 80 wt.-% to about ≥ 35 wt.-% and also preferred about ≤ 70 wt.-% to about ≥ 45 wt.-% and also preferred about ≤ 65 wt.-% to about ≥ 50 wt.-% of at least one matrix compound, preferably an anthracene based compound or a

6

heteroaryl substituted anthracene based compound, a phosphine oxide based compound, a substituted phenanthroline compound; and

about ≥ 10 wt.-% to about ≤ 70 wt.-%, preferably about ≥ 20 wt.-% to about ≤ 65 wt.-% and also preferred about ≥ 30 wt.-% to about ≤ 55 wt.-% and also preferred about ≥ 35 wt.-% to about ≤ 50 wt.-% of at least two lithium compounds, preferably two lithium organic complexes or a lithium organic complex and a lithium halide, wherein the lithium halide is preferably a lithium fluoride; wherein the weight percent is based on the total weight of the corresponding electron transport layer.

According to various embodiments of the organic light-emitting diode at least one electron transport layer or at least two electron transport layers comprising:

about ≤ 90 wt.-% to about ≥ 30 wt.-%, preferably about ≤ 80 wt.-% to about ≥ 35 wt.-% and also preferred about ≤ 70 wt.-% to about ≥ 45 wt.-% and also preferred about ≤ 65 wt.-% to about ≥ 50 wt.-% of at least one matrix compound, preferably a phosphine oxide based compound, and more preferred a (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenyl-phosphine oxide; and

about ≥ 10 wt.-% to about ≤ 70 wt.-%, preferably about ≥ 20 wt.-% to about ≤ 65 wt.-% and also preferred about ≥ 30 wt.-% to about ≤ 55 wt.-% and also preferred about ≥ 35 wt.-% to about ≤ 50 wt.-% of at least two lithium compounds, preferably two lithium organic complexes, more preferred of two lithium organic complexes selected from the group comprising a lithium quinolate, a lithium borate, a lithium phenolate, preferably the lithium phenolate is a lithium phosphoryl aryl complex, a lithium pyridinolate or a lithium Schiff base, and most preferred of two lithium organic complexes selected from the group comprising a lithium 2-(diphenylphosphoryl)-phenolate, lithium tetra(1H-pyrazol-1-yl)borate, a lithium quinolate of formula (III) and lithium 2-(pyridin-2-yl)phenolate; wherein the weight percent is based on the total weight of the corresponding electron transport layer.


Lithium Organic Complex

According to various aspects at least one electron transport layer or at least two electron transport layers comprising at least two lithium compounds of lithium organic complexes, selected from the group comprising:

a lithium quinolate, a lithium borate, a lithium phenolate, preferably the lithium phenolate is a lithium phosphoryl aryl complex, a lithium pyridinolate or a lithium Schiff base; or

at least one lithium borate or at least one pyridinolate, and in addition a lithium organic complex selected from the group comprising a lithium quinolate, a lithium borate, a lithium phenolate, preferably the lithium phenolate is a lithium phosphoryl aryl complex, a lithium pyridinolate or a lithium Schiff base; preferably



the lithium quinolate has the formula I, II or III:



(I)

7

-continued



wherein

A_1 to A_6 are same or independently selected from CH, CR, N, O;




R is same or independently selected from hydrogen, halogen, alkyl or aryl or heteroaryl with 1 to 20 carbon atoms; and more preferred A_1 to A_6 are CH;

preferably the lithium borate is a lithium tetra(1H-pyrazol-1-yl)borate;

preferably the lithium phenolate is a lithium 2-(pyridin-2-yl)phenolate, a lithium 2-(diphenylphosphoryl)phenolate, a lithium imidazol phenolates, or a lithium 2-(pyridin-2-yl)phenolate and more preferred a lithium 2-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenolate;


preferably the a lithium pyridinolate is a lithium 2-(diphenylphosphoryl)pyridin-3-olate,

preferably the lithium Schiff base has the structure 100, 101, 102 or 103:



8


-continued



Quinolates that can be suitable used are disclosed in WO 2013079217 A1 and incorporated by reference.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the organic ligand of the lithium organic complex can be a borate based organic ligand.

Preferably, the lithium compound can be a lithium organic borate complex, also referred as lithium borate, which is a compound of formula IV:



Formula IV

wherein each of A^1 , A^2 , A^3 and/or A^4 is independently selected from the group comprising substituted or unsubstituted C_6 - C_{20} aryl and substituted or unsubstituted C_2 - C_{20} heteroaryl, wherein A^1 , A^2 , A^3 and/or A^4 of Formula IV are not a phenolate group.

According to one embodiment wherein the substituted or unsubstituted aryl is a C_6 - C_{18} , preferably C_6 - C_{10} .


According to one embodiment wherein the substituted or unsubstituted heteroaryl is a C_3 - C_{18} , preferably C_3 - C_{10} , and more preferred a C_3 - C_6 heteroaryl.

Preferably the lithium organic borate complex is a lithium tetra(1H-pyrazol-1-yl)borate.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the organic ligand of the lithium organic complex can be a phenolate ligand.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the organic ligand of the lithium organic complex can be a phosphoryl phenolate ligand.

According to one embodiment the lithium compound can be a lithium organic complex which can be a phosphoryl aryl compound of formula V:



Formula V

wherein D^1 is a C_6 - C_{20} arylene and each of D^2 to D^3 is independently selected from a C_6 - C_{20} aryl, wherein the aryl arylene may be unsubstituted or substituted.


According to one embodiment the lithium organic complex can be a phosphoryl aryl compound of formula V, wherein D^1 , D^2 and D^3 are independently selected from C_1 - C_{30} -alkyl, C_3 - C_{30} -cycloalkyl, C_2 - C_{30} -heteroalkyl, C_6 - C_{30} -aryl, C_2 - C_{30} -heteroaryl, C_1 - C_{30} -alkoxy, C_3 - C_{30} -cycloalkyloxy, C_6 - C_{30} -aryloxy.

9

Preferably the lithium organic complex is a lithium 2-(di-phenylphosphoryl)phenolate.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the organic ligand of the lithium organic complex can be a phosphoryl aryl ligand, namely a phosphoryl heteroarylolate ligand.

According to another embodiment, the lithium organic phosphoryl complex of formula V can be a lithium organic phosphoryl heteroaryl complex:



Formula V

wherein

D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring; and

each of D² and D³ is independently selected from a C₆-C₃₀ aryl and C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring and wherein either

- i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring, and/or
- ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring.

In a further preferred embodiment, D¹, D² and/or D³ are independently selected from

C₁-C₁₂-alkyl, C₃-C₈-cycloalkyl, C₂-C₁₂-heteroalkyl, C₆-C₁₈-aryl, C₂-C₁₈-heteroaryl, C₁-C₁₂-alkoxy, C₃-C₈-cycloalkyloxy, C₆-C₁₈-aryloxy.

Further, phenolate ligands may be selected from the group comprising pyridinolate, preferably 2-(diphenylphosphoryl)pyridin-3-olate. Pyridine phenolate ligands that can be suitable used are disclosed in JP 2008195623 and incorporated by reference.

In addition, phenolate ligands can be selected from the group comprising imidazol phenolates, preferably 2-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenolate. Imidazol phenolate ligands that can be suitable used are disclosed in JP 2001291593 and incorporated by reference.

Also, phenolate ligands can be selected from the group comprising oxazol phenolates, preferably 2-(benzo[d]oxazol-2-yl)phenolate. Oxazol phenolate ligands that can be suitable used are disclosed in US 20030165711 and incorporated by reference.

According to one embodiment of the OLED, wherein at least one electron transport layer comprises:


at least one lithium compound selected from the group comprising a lithium organic borate complex or a lithium phosphoryl aryl complex; and/or

at least two lithium compounds selected from the group comprising a lithium organic borate complex and/or a lithium phosphoryl aryl complex.

According to another embodiment of the OLED, wherein at least one electron transport layer comprises at least one lithium compound of a lithium organic complex of:


10

a lithium organic borate complex of Formula IV:



(IV)

wherein each of A¹, A², A³ and/or A⁴ is independently selected from H, substituted or unsubstituted C₆-C₂₀ aryl and substituted or unsubstituted C₂-C₂₀ heteroaryl, preferably at least one A¹, A², A³ and/or A⁴ is a phenolate, and more preferred the lithium organic borate complex is a lithium tetra(1H-pyrazol-1-yl)borate; and/or a lithium phosphoryl aryl complex of Formula V:



(V)

wherein D¹ is a unsubstituted or substituted C₆-C₂₀ arylene and each of D² to D³ is independently selected from a unsubstituted or substituted C₆-C₂₀ aryl, and more preferred the lithium phosphoryl aryl complex is a lithium 2-(diphenylphosphoryl)phenolate; and/or wherein D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring; and each of D² and D³ is independently selected from a C₆-C₃₀ aryl and C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring and wherein either


- i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring, and/or
- ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring.

According to a further preferred embodiment of a lithium phosphoryl aryl complex of Formula V, D¹ is C₆-C₁₂ arylene or C₂-C₁₂ heteroarylene.

According to a further preferred embodiment of a lithium phosphoryl aryl complex of Formula V, each of D² and D³ are independently selected from a C₆-C₁₀ aryl or C₂-C₁₂ heteroaryl; or preferably each of D² and D³ are independently selected from phenyl and pyridyl.

Preferably the lithium organic complex is a lithium 2-(diphenylphosphoryl)pyridin-3-olate.




According to various embodiments of the organic light-emitting diode (OLED) of the present invention the organic ligand of the lithium organic complex can be selected from a borate ligand and a phosphoryl aryl ligand and a heteroaryl ligand. Preferably, the organic ligand of the lithium organic complex is selected from a borate ligand and a phosphoryl aryl ligand. Further, Lithium Schiff base organic complexes can be used. Lithium Schiff base organic complexes that can be suitable used having the structure 100, 101, 102 or 103:



100

11

-continued



Suitable organic ligands to form a lithium organic complex that can be used for the first electron transport layer and/or the second electron transport layer are disclosed, and incorporated by reference, for example in US 2014/0048792 and Kathirgamanathan, Poopathy; Arkley, Vincent; Surendrakumar, Sivagnanasundram; Chan, Yun F.; Ravichandran, Seenivasagam; Ganeshamurugan, Subramaniam; Kumara-verl, Muttulingam; Antipan-Lara, Juan; Paramaswara, Gnanamolly; Reddy, Vanga R., Digest of Technical Papers—Society for Information Display International Symposium (2010), 41(Bk. 1), 465-468.

According to another embodiment of the OLED, wherein at least one electron transport layer comprises:

at least one lithium organic complex selected from a lithium borate complex or a lithium phosphoryl aryl complex, preferably a lithium organic borate complex of Formula IV or a lithium phosphoryl aryl complex of Formula V; and

at least one lithium organic complex selected from a lithium quinolate, a lithium pyridinolate or a lithium Schiff base, preferably a lithium quinolate having the formula I, II or III and more preferred having the formula III.

According to another embodiment of the OLED, wherein at least one electron transport layer comprises:


at least one lithium organic complex selected from a lithium borate complex or a lithium phosphoryl aryl complex, preferably a lithium organic borate complex of Formula IV or a lithium phosphoryl aryl complex of Formula V; and

at least one lithium compound that is a lithium halide selected from the group comprising LiF, LiCl, LiBr or LiI, and preferably LiF.


12

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises:

at least one lithium organic complex that is selected from:
a lithium organic borate complex of Formula IV:



wherein each of A¹, A², A³ and A⁴ is independently selected from substituted or unsubstituted C₆-C₂₀ aryl and substituted or unsubstituted C₂-C₂₀ heteroaryl, wherein A¹, A², A³ and/or A⁴ of Formula (IV) are not a phenolate group; and more preferred the lithium organic borate complex is a lithium tetra(1H-pyrazol-1-yl)borate; and/or
a lithium phosphoryl aryl complex of Formula V:



wherein

D¹ is a substituted or unsubstituted C₆-C₂₀ arylene and each of D² to D³ is independently selected from a substituted or unsubstituted C₆-C₂₀ aryl, preferably at least one D¹, D² and/or D³ is a phenolate, and more preferred the lithium phosphoryl aryl complex is a lithium 2-(diphenylphosphoryl)phenolate; and/or

wherein

D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring; and

each of D² and D³ is independently selected from a C₆-C₃₀ aryl and C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring and wherein either

i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring, and/or

ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4'-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-

13


yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl) 5 diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7, 9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl- 4-yl)-4,7-diphenyl-1,10-phenanthroline. 10

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises:


at least one lithium compound of a lithium organic complex that is selected from:

a lithium organic borate complex of Formula IV:



wherein each of A¹, A², A³ and A⁴ is independently selected from substituted or unsubstituted C₆-C₂₀ aryl and substituted or unsubstituted C₂-C₂₀ heteroaryl, wherein A¹, A², A³ and/or A⁴ of Formula (IV) are not a phenolate group; and more preferred the lithium organic borate complex is a lithium tetra(1H-pyrazol-1-yl)borate; and/or 30

a lithium phosphoryl aryl complex of Formula V:



wherein

D¹ is a unsubstituted or substituted C₆-C₂₀ arylene and each of D² to D³ is independently selected from a unsubstituted or substituted C₆-C₂₀ aryl, preferably at least one D¹, D² and/or D³ is a phenolate, and more preferred the lithium phosphoryl aryl complex is a lithium 2-(diphenylphosphoryl)phenolate; and/or 45

wherein

D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring; and 55

each of D² and D³ is independently selected from a C₆-C₃₀ aryl and C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring and wherein either 60

i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring, and/or

ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring; and 65

14


wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine.


According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises:

at least one lithium compound can be lithium organic complex that is selected from:

a lithium organic borate complex of Formula IV:



wherein each of A¹, A², A³ and A⁴ is independently selected from substituted or unsubstituted C₆-C₂₀ aryl and substituted or unsubstituted C₂-C₂₀ heteroaryl, wherein A¹, A², A³ and/or A⁴ of Formula (IV) are not a phenolate group; and more preferred the lithium organic borate complex is a lithium tetra(1H-pyrazol-1-yl)borate; and/or a lithium phosphoryl aryl complex of Formula V:



wherein

D¹ is a unsubstituted or substituted C₆-C₂₀ arylene and each of D² to D³ is independently selected from a unsubstituted or substituted C₆-C₂₀ aryl, preferably at least one D¹, D² and/or D³ is a phenolate, and more preferred the lithium phosphoryl aryl complex is a lithium 2-(diphenylphosphoryl)phenolate; and/or

wherein

D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring; and

each of D² and D³ is independently selected from a C₆-C₃₀ aryl and C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring and wherein either

i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring, and/or

ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]


15

phosphepine-3-oxide, bis(4-(anthracen-9-yl)phenyl) (phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl) diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises:


at least one lithium compound of a lithium organic complex that is selected from:

a lithium organic borate complex of Formula IV:



wherein each of A¹, A², A³ and A⁴ is independently selected from substituted or unsubstituted C₆-C₂₀ aryl and substituted or unsubstituted C₂-C₂₀ heteroaryl, wherein A¹, A², A³ and/or A⁴ of Formula (IV) are not a phenolate group; and more preferred the lithium organic borate complex is a lithium tetra(1H-pyrazol-1-yl)borate; and/or

a lithium phosphoryl aryl complex of Formula V:



wherein

D¹ is a unsubstituted or substituted C₆-C₂₀ arylene and each of D² to D³ is independently selected from a unsubstituted or substituted C₆-C₂₀ aryl, preferably at least one D¹, D² and/or D³ is a phenolate, and more preferred the lithium phosphoryl aryl complex is a lithium 2-(diphenylphosphoryl)phenolate; and/or

wherein

D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring; and

each of D² and D³ is independently selected from a C₆-C₃₀ aryl and C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring and wherein either

i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S and N in an aromatic ring, and/or

ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S and N in an aromatic ring; and

16

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium organic borate complex or a lithium phosphoryl aryl complex; and wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-(1,1'-biphenyl)-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N₄,N₄"-di(naphthalen-1-yl)-N₄,N₄"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphepine-3-oxide, bis(4-(anthracen-9-yl)phenyl) (phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl) diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least two lithium organic complexes that are selected from the group comprising a lithium organic borate complex and a lithium phosphoryl aryl complex; and wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-(1,1'-biphenyl)-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N₄,N₄"-di(naphthalen-1-yl)-N₄,N₄"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphepine-3-oxide, bis(4-(anthracen-9-yl)phenyl) (phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl) diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium organic borate complex or a lithium phosphoryl aryl complex; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di (naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least two lithium organic complexes that are selected from the group comprising a lithium organic borate complex and a lithium phosphoryl aryl complex; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di (naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium organic borate complex or a lithium phosphoryl aryl complex; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl) diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least two lithium organic complexes that are selected from the group comprising a lithium organic borate complex and a lithium phosphoryl aryl complex; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-

yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl)

diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium organic borate complex or a lithium phosphoryl aryl complex; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least two lithium organic complexes that are selected from the group comprising a lithium organic borate complex and a lithium phosphoryl aryl complex; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium tetra(1H-pyrazol-1-yl)borate, a lithium 2-(diphenyl-phosphoryl)phenolate, and/or a lithium 2-(diphenyl-phosphoryl)pyridin-3-olate; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di (naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo [c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl)

diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium 8-hydroxyquinolate, lithium tetra(1H-

19

pyrazol-1-yl)borate, lithium 2-(diphenyl-phosphoryl)phenolate, lithium 2-(pyridin-2-yl)phenolate, lithium 2-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenolate, lithium 2-(benzo[d]oxazol-2-yl)phenolate, lithium 2-(diphenyl-phosphoryl)pyridin-3-olate; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphepine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo[c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl)diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED comprising at least one or two electron transport layers, wherein at least one electron transport layer comprises at least one lithium organic complex that is selected from the group comprising a lithium tetra(1H-pyrazol-1-yl)borate, a lithium

20

2-(diphenyl-phosphoryl)phenolate, and/or a lithium 2-(diphenyl-phosphoryl)pyridin-3-olate; and

wherein the matrix compound of at least one or two electron transport layers is selected from the group comprising:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphepine-3-oxide, bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo[c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl)diphenylphosphine oxide and/or phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide; or

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

According to another embodiment of the OLED, at least one electron transport layer may comprises a third lithium compound, wherein the third lithium compound can be a lithium quinolate or a lithium phenolate, preferably the lithium phenolate is a lithium phosphoryl aryl complex.

Suitable lithium organic complexes that can be most preferably used for the electron transport layer are mentioned in Table 1 below.

TABLE 1








Lithium organic complex that can be suitable used		
Compound Name	Structure	Reference
LiQ lithium 8-hydroxyquinolate		WO 2013079217 A1
Li-1 lithium tetra(1H-pyrazol-1-yl)borate		WO 2013079676 A1

TABLE 1-continued

Lithium organic complex that can be suitable used		
Compound	Name	Structure
Li-2	lithium 2-(diphenyl-phosphoryl)phenolate	
Li-3	lithium 2-(pyridin-2-yl)phenolate	
Li-4	lithium 2-(1-phenyl-1H-benzo[d]imidazol-2-yl)phenolate	
Li-5	lithium 2-(benzo[d]oxazol-2-yl)phenolate	
Li-6	lithium 2-(diphenyl-phosphoryl)pyridin-3-olate	

Matrix compounds

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the electron transport layer or the electron transport layers of an electron transport layer stack, may comprises at least one matrix compound each.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention comprising an electron transport layer stack of at least two electron transport layers or at least three electron transport layers, wherein each electron transport layer comprises at least one matrix compound, whereby the matrix compound of the electron transport layers are selected same or different.

According to various embodiments of the organic light-emitting diode (OLED) the at least two electron transport layers (161/162) or the at least three electron transport layers (161/162/163) of an electron transport layer stack comprise at least one matrix compound, whereby the matrix com-

pound of the electron transport layers are selected same or different, and wherein the matrix compound is selected from:

an anthracene based compound or a heteroaryl substituted anthracene based compound, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole, 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole and/or N4,N4''-di(naphthalen-1-yl)-N4,N4''-diphenyl-[1,1':4',1''-terphenyl]-4,4''-diamine;

a phosphine oxide based compound, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, phenyl bis(3-(pyren-1-yl)phenyl)phosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphine-3-oxide, phenyldi(pyren-1-yl)phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-

23

biphenyl]-3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo[c,h]acridin-7-yl)-[1,1'-biphenyl]-4-yl) diphenylphosphine oxide and/or bis(4-(anthracen-9yl) phenyl)(phenyl)phosphine oxide; or

24

a substituted phenanthroline compound, preferably 2,4,7,9-tetraphenyl-1,10-phenanthroline or 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline.

Suitable matrix compounds that can be most preferably used for the electron transport layer are mentioned in Table 2 below.

TABLE 2




Chemical structures of matrix compounds that can be suitable used			
Compound	Name	Structure	Reference
MX 1	2-(4-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole		U.S. Pat. No. 6,878,469 B2
MX 2	(3-(dibenzo[c,h]acridin-7-yl)phenyl) diphenylphosphine oxide		EP 2395571B1, WO2013079217A1
MX 3	Phenylbis(3-(pyren-1-yl)phenyl)phosphine		EP13187905.8

TABLE 2-continued









Chemical structures of matrix compounds that can be suitable used		
Compound Name	Structure	Reference
MX 4 3-Phenyl-3H-benzo[b]dinaphtho[2,1-d:1',2'-f]phosphine-3-oxide		EP13199361.0
MX 5 Phenyldi(pyren-1-yl)phosphine oxide		JP4876333
MX 6 2,4,7,9-tetraphenyl-1,10-phenanthroline		EP1786050
MX 8 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthroline		EP1786050

TABLE 2-continued

Chemical structures of matrix compounds that can be suitable used			
Compound	Name	Structure	Reference
MX 9	bis(4-(anthracen-9-yl)phenyl)(phenyl)phosphine oxide		EP13187905
MX 10	(3-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)diphenylphosphine oxide		WO2015052284A1
MX 11	4,7-diphenyl-2,9-di-p-tolyl-1,10-phenanthroline		EP1786050
MX 12	9-(4-(naphthalen-1-yl)phenyl)-10-phenylanthracene		US2015060785

According to various embodiments of the organic light-emitting diode (OLED) the thicknesses of an OLED with one electron transport layer or the thicknesses of at least a first electron transport layer (161) of an electron transport layer stack and/or the thicknesses of at least a second electron transport layer (162) of an electron transport layer stack, are the same or each independently, in the range of about ≥ 0.5 nm to about ≤ 95 nm, preferably of about ≥ 3 nm to about ≤ 80 nm, further preferred of about ≥ 5 nm to about ≤ 60 nm, also preferred of about ≥ 6 nm to about ≤ 40 nm, in addition preferred about ≥ 8 nm to about ≤ 20 nm and more preferred of about > 10 nm to about ≤ 18 nm.

According to various embodiments of the organic light-emitting diode (OLED) the thicknesses of the electron transport layer stack can be in the range of about ≥ 25 nm to about ≤ 100 nm, preferably of about ≥ 30 nm to about ≤ 80 nm, further preferred of about ≥ 35 nm to about ≤ 60 nm, and more preferred of about ≥ 36 nm to about ≤ 40 nm.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the electron transport layer stack has 2 to 4 electron transport layers and more preferred 2 to 3 electron transport layers.

According to various embodiments of the organic light-emitting diode (OLED) of the present invention the second electron transport layer can be arranged directly on the first electron transport layer and an optional third electron transport layer can be arranged directly on the second electron transport layer, so that the second electron transport layer is sandwiched between the first and third electron transport layers.

According to another aspect, there is provided an organic light-emitting diode comprising: a substrate; a first anode electrode arranged on the substrate; a second cathode electrode arranged on the first anode electrode; and one electron transport layer arranged between the first anode electrode and the second cathode electrode, comprising or consisting of at least two electron transport layers or at least three electron transport layers.

According to another aspect, there is provided an organic light-emitting diode comprising: a substrate; a first anode electrode arranged on the substrate; a second cathode electrode arranged on the first anode electrode; and an electron transport layer stack arranged between the first anode electrode and the second cathode electrode, comprising or consisting of at least two electron transport layers or at least three electron transport layers.

According to various embodiments, the organic light-emitting diode (OLED) may further include at least one layer selected from the group consisting of a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, arranged between the first anode electrode and the electron transport layer.

According to another aspect, there is provided an organic light-emitting diode comprising in addition: at least one layer selected from the group consisting of a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, arranged between the first anode electrode and the electron transport layer stack.

According to various aspects, there is provided an organic light-emitting diode further comprising an electron injection layer arranged between the electron transport layer and the second cathode electrode.

According to another aspect, there is provided an organic light-emitting diode comprising one electron transport layer and at least one electron injection layer; or a transport layer stack having two to four electron transport layers, preferably three electron transport layers and most preferred two elec-

tron transport layers, whereby at least one electron transport layer comprises a matrix compound and at least two lithium compounds.

According to another aspect the organic light-emitting diode comprising a transport layer stack can be free of an electron injection layer.

According to various embodiments of the OLED of the present invention, the OLED may not comprise an electron injection layer.

According to various embodiments of the OLED of the present invention, the OLED may not comprise a charge generation layer.

According to various embodiments of the OLED of the present invention, the OLED may not comprise an electron injection layer and a charge generation layer.

According to another aspect, there is provided a method of manufacturing an organic light-emitting diode (OLED), the method using:

deposition via at least three deposition sources; or deposition via vacuum thermal evaporation; or deposition via solution processing, preferably the processing is selected from spin-coating, printing, casting and/or slot-die coating.

According to various aspects, there is provided a method using:

a first deposition source to release the matrix compound, and
a second deposition source to release a first lithium compound of lithium halide or lithium organic complex, preferably a first lithium organic complex, and
a third deposition source to release a second lithium compound of lithium halide or lithium organic complex, preferably a second lithium organic complex; and

the method comprising the steps of forming the electron transport layer; whereby the electron transport layer is formed by releasing the matrix compound from at least one deposition source and a first lithium halide or lithium organic complex from a different deposition source and a second lithium halide or lithium organic complex, preferably lithium organic complex, from a different deposition source.

According to various aspects, there is provided a method using:

a first or a first and a fourth deposition source to release the matrix compound, and
a second deposition source to release a first lithium compound of lithium halide or lithium organic complex, preferably a first lithium organic complex, and
a third deposition source to release a second lithium compound of lithium halide or lithium organic complex, preferably a second lithium organic complex; and

the method comprising the steps of forming the electron transport layer or the electron transport layer stack; whereby a first electron transport layer is formed by releasing the matrix compound from at least one deposition source (first deposition source) and a first lithium halide or lithium organic complex, from a different deposition source (second deposition source) and a second lithium halide or lithium organic complex, preferably lithium organic complex, from a different deposition source (third deposition source);

optional onto the first electron transport layer a second electron transport layer is formed by releasing the matrix compound from at least one deposition source and optional the first and second lithium compound from different deposition source;

31

optional onto the second electron transport layer a third electron transport layer is formed by releasing the matrix compound from at least one deposition source and optional the first and second lithium compound from different deposition source;

preferably the second electron transport layer or the second and third electron transport layer can be free of a first and second lithium compound.

According to various aspects, the method may further include forming on the first anode electrode an emission layer and at least one layer selected from the group consisting of forming a hole injection layer, forming a hole transport layer, or forming a hole blocking layer, between the first anode electrode and the electron transport layer or electron transport layer stack.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed,

on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

on the electron transport layer or the electron transport layer stack a second cathode electrode is formed,

optional a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, are formed between the at least first anode electrode and the electron transport layer or electron transport layer stack,

optional an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the one electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed,

on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

on the electron transport layer or the electron transport layer stack a second cathode electrode is formed,

optional a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, are formed between the at least first anode electrode and the electron transport layer or electron transport layer stack,

optional an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the one electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed,

on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

on the electron transport layer or the electron transport layer stack a second cathode electrode is formed,

optional a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, are formed between the at least first anode electrode and the electron transport layer or electron transport layer stack,

optional an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the one electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed,

on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

on the electron transport layer or the electron transport layer stack a second cathode electrode is formed,

optional a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, are formed between the at least first anode electrode and the electron transport layer or electron transport layer stack,

optional an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the one electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed,

on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

on the electron transport layer or the electron transport layer stack a second cathode electrode is formed,

optional a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, are formed between the at least first anode electrode and the electron transport layer or electron transport layer stack,

optional an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein an electron injection layer is formed between the one electron transport layer or electron transport layer stack, and the at least second cathode electrode.

According to various aspects, the method may further include the steps for forming an organic light-emitting diode (OLED), wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed,

on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

32

However, according to various embodiments of the OLED of the present invention, the OLED may not comprise an electron injection layer and/or a charge generation layer.

Additional aspects and/or advantages of the invention will be set fourth in part in the description which follows and, in part, will be obvious from the description, or may be learned by practice of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects and advantages of the present invention will become apparent and more readily appreciated from the following description of the exemplary embodiments, taken in conjunction with the accompanying drawings, of which:

FIG. 1 is a schematic sectional view of an organic light-emitting diode (OLED), according to an exemplary embodiment of the present invention with an emission layer, one electron transport layer and an electron injection layer;

FIG. 2 is a schematic sectional view of an organic light-emitting diode (OLED), according to an exemplary embodiment of the present invention with an emission layer and two electron transport layers;

FIG. 3 is a schematic sectional view of an OLED, according to an exemplary embodiment of the present invention with an emission layer and three electron transport layers;

FIG. 4 is a schematic sectional view of an organic light-emitting diode (OLED), according to an exemplary embodiment of the present invention with an emission layer and one electron transport layer;

FIG. 5 is a schematic sectional view of an organic light-emitting diode (OLED), according to an exemplary embodiment of the present invention with an emission layer and two electron transport layers;

FIG. 6 is a schematic sectional view of an OLED, according to an exemplary embodiment of the present invention with an emission layer and three electron transport layers,

FIG. 7 is a schematic sectional view of an OLED, according to an exemplary embodiment of the present invention with an emission layer and two electron transport layers and having no electron injection layer (EIL).

FIG. 8 is a schematic sectional view of an OLED, according to an exemplary embodiment of the present invention with three electron transport layers and having no electron injection layer (EIL).

DETAILED DESCRIPTION

Reference will now be made in detail to the exemplary aspects, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to the like elements throughout. The exemplary embodiments are described below, in order to explain the aspects, by referring to the figures.

Herein, when a first element is referred to as being formed or disposed "on" a second element, the first element can be disposed directly on the second element, or one or more other elements may be disposed there between. When a first element is referred to as being formed or disposed "directly on" a second element, no other elements are disposed there between.

FIG. 1 is a schematic sectional view of an organic light-emitting diode 100, according to an exemplary embodiment of the present invention. The OLED 100 includes an emission layer 150, an electron transport layer

(ETL) **161** and an electron injection layer **180**, whereby the electron transport layer **161** is disposed directly on the emission layer **150** and the electron injection layer **180** is disposed directly on the electron transport layer **161**.

FIG. 2 is a schematic sectional view of an organic light-emitting diode **100**, according to an exemplary embodiment of the present invention. The OLED **100** includes an emission layer **150** and an electron transport layer stack (ETL) **160** comprising a first electron transport layer **161** and a second electron transport layer **162**, whereby the second electron transport layer **162** is disposed directly on the first electron transport layer **161**.

FIG. 3 is a schematic sectional view of an organic light-emitting diode **100**, according to an exemplary embodiment of the present invention. The OLED **100** includes an emission layer **150** and an electron transport layer stack (ETL) **160** comprising a first electron transport layer **161**, a second electron transport layer **162**, and a third electron transport layer **163**, whereby the second electron transport layer **162** is disposed directly on the first electron transport layer **161** and the third electron transport layer **163** is disposed directly on the first electron transport layer **162**.

FIG. 4 is a schematic sectional view of an organic light-emitting diode **100**, according to an exemplary embodiment of the present invention. The OLED **100** includes a substrate **110**, a first electrode **120**, a hole injection layer (HIL) **130**, a hole transport layer (HTL) **140**, an emission layer (EML) **150**, one electron transport layer (ETL) **161**, an electron injection layer (EIL) **180**, and a second electrode **190**. The electron transport layer (ETL) **161** includes a matrix compound and two lithium organic complexes. The electron transport layer (ETL) **161** is formed directly on the EML **150**.

FIG. 5 is a schematic sectional view of an organic light-emitting diode **100**, according to an exemplary embodiment of the present invention. The OLED **100** includes a substrate **110**, a first electrode **120**, a hole injection layer (HIL) **130**, a hole transport layer (HTL) **140**, an emission layer (EML) **150**, an electron transport layer (ETL) **160**, an electron injection layer (EIL) **180**, and a second electrode **190**. The electron transport layer (ETL) **160** includes a first electron transport layer **161** including a matrix compound, a lithium halide and a lithium organic complex and a second electron transport layer **162** including a matrix compound but is free of a lithium halide and a lithium organic complex. The second electron transport layer **162** is directly formed on the first electron transport layer **161**. The first layer **161** may be formed directly on the EML **150**.

FIG. 6 is a schematic sectional view of an organic light-emitting diode **100**, according to an exemplary embodiment of the present invention. The OLED **100** includes a substrate **110**, a first electrode **120**, a hole injection layer (HIL) **130**, a hole transport layer (HTL) **140**, an emission layer (EML) **150**, an electron transport layer (ETL) **160**, an electron injection layer (EIL) **180**, and a second electrode **190**. The electron transport layer (ETL) **160** includes a first electron transport layer **161** and a third electron transport layer **163** including a matrix compound and two different lithium organic complexes; and the second electron transport layer **162** includes a matrix compound which is free of a lithium halide and lithium organic complex. The second electron transport layer **162** is directly formed on the first electron transport layer **161** and the third electron layer **163** is directly formed on the second electron layer **162**. The first layer **161** may be formed directly on the emission layer (EML) **150**.

The substrate **110** may be any substrate that is commonly used in manufacturing of organic light-emitting diodes. If light is emitted through the substrate, the substrate **110** may be a transparent material, for example a glass substrate or a transparent plastic substrate, having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and waterproofness. If light is emitted through the top surface, the substrate **110** may be a transparent or non-transparent material, for example a glass substrate, a plastic substrate, a metal substrate or a silicon substrate.

The first anode electrode **120** may be formed by depositing or sputtering a compound that is used to form the first anode electrode **120**. The compound used to form the first anode electrode **120** may be a high work-function compound, so as to facilitate hole injection. If a p-doped HIL is used, the anode material may also be selected from a low work function material (i.e. Aluminum). The first anode electrode **120** may be a transparent or reflective electrode. Transparent conductive compounds, such as indium tin oxide (ITO), indium zinc oxide (IZO), tin-dioxide (SnO₂), and zinc oxide (ZnO), may be used to form the first anode electrode **120**. The first anode electrode **120** may also be formed using magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), silver (Ag), gold (Au), or the like.

The HIL **130** may be formed on the first anode electrode **120** by vacuum deposition, spin coating, printing, casting, slot-die coating, Langmuir-Blodgett (LB) deposition, or the like. When the HIL **130** is formed using vacuum deposition, the deposition conditions may vary according to the compound that is used to form the HIL **130**, and the desired structure and thermal properties of the HIL **130**. In general, however, conditions for vacuum deposition may include a deposition temperature of 100° C. to 500° C., a pressure of 10⁻⁸ to 10⁻³ Torr (1 Torr equals 133.322 Pa), and a deposition rate of 0.1 to 10 nm/sec.

When the HIL **130** is formed using spin coating, printing, coating conditions may vary according to a compound that is used to form the HIL **130**, and the desired structure and thermal properties of the HIL **130**. For example, the coating conditions may include a coating speed of about 2000 rpm to about 5000 rpm, and a thermal treatment temperature of about 80° C. to about 200° C. Thermal treatment removes a solvent after the coating is performed.

The HIL **130** may be formed of any compound that is commonly used to form an HIL. Examples of compounds that may be used to form the HIL **130** include a phthalocyanine compound, such as copper phthalocyanine (CuPc), 4,4',4"-tris (3-methylphenylphenylamino) triphenylamine (m-MTDATA), TDATA, 2T-NATA, polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), and polyaniline/poly(4-styrenesulfonate) (PANI/PSS).

The HIL **130** may be a pure layer of p-dopant or may be selected from a hole-transporting matrix compound doped with a p-dopant. Typical examples of known redox doped hole transport materials are: copper phthalocyanine (CuPc), which HOMO level is approximately -5.2 eV, doped with tetrafluoro-tetracyanoquinonodimethane (F4TCNQ), which LUMO level is about -5.2 eV; zinc phthalocyanine (ZnPc) (HOMO = -5.2 eV) doped with F4TCNQ; α -NPD (N,N'-Bis(naphthalen-1-yl)-N,N'-bis(phenyl)-benzidine) doped with F4TCNQ. α -NPD doped with 2,2'-(perfluoronaphthalene-2,

35



6-diylidene) dimalononitrile (PD1). α -NPD doped with 2,2',2''-(cyclopropane-1,2,3-triylidene)tris(2-(p-cyanotetrafluorophenyl)acetonitrile) (PD2). Dopant concentrations can be selected from 1 to 20 wt.-%, more preferably from 3 wt.-% to 10 wt.-%.

36

carbazolyl)triphenylamine (TCTA). Among these compounds, TCTA can transport holes and inhibit excitons from being diffused into the EML.

Compounds that can be preferably used are mentioned in Table 3.

TABLE 3

IUPAC name	Structure	Reference
N4,N4''-di(naphthalen-1-yl)-N4,N4''-diphenyl-[1,1':4',1''-terphenyl]-4,4''-diamine		DE102012101652 A1
2,2',2''-(cyclopropane-1,2,3-triylidene)tris(2-(p-cyanotetrafluorophenyl)acetonitrile)		EP 1988587 A1, EP 2180029 A1

The thickness of the HIL **130** may be in the range of about 1 nm to about 100 nm, and for example, about 1 nm to about 25 nm. When the thickness of the HIL **130** is within this range, the HIL **130** may have excellent hole injecting characteristics, without a substantial increase in driving voltage.

The hole transport layer (HTL) **140** may be formed on the HIL **130** by vacuum deposition, spin coating, slot-die coating, printing, casting, Langmuir-Blodgett (LB) deposition, or the like. When the HTL **140** is formed by vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL **130**. However, the conditions for the vacuum or solution deposition may vary, according to the compound that is used to form the HTL **140**.

The HTL **140** may be formed of any compound that is commonly used to form a HTL. Compound that can be suitably used is disclosed for example in Yasuhiko Shirota and Hiroshi Kageyama, Chem. Rev. 2007, 107, 953-1010 and incorporated by reference. Examples of the compound that may be used to form the HTL **140** are: a carbazole derivative, such as N-phenylcarbazole or polyvinylcarbazole; an amine derivative having an aromatic condensation ring, such as N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (TPD), or N,N'-di(naphthalene-1-yl)-N,N'-diphenyl benzydine (α -NPD); and a triphenylamine-based compound, such as 4,4',4''-tris(N-





The thickness of the HTL **140** may be in the range of about 5 nm to about 250 nm, preferably, about 10 nm to about 200 nm, further about 20 nm to about 190 nm, further about 40 nm to about 180 nm, further about 60 nm to about 170 nm, further about 80 nm to about 160 nm, further about 100 nm to about 160 nm, further about 120 nm to about 140 nm. A preferred thickness of the HTL **140** may be 170 nm to 200 nm.

When the thickness of the HTL **140** is within this range, the HTL **140** may have excellent hole transporting characteristics, without a substantial increase in driving voltage.

The EML **150** may be formed on the HTL **140** by vacuum deposition, spin coating, slot-die coating, printing, casting, LB, or the like. When the EML **150** is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL **130**. However, the conditions for deposition and coating may vary, according to the compound that is used to form the EML **150**.

The emission layer (EML) **150** may be formed of a combination of a host and a dopant. Example of the host are Alq3, 4,4'-N,N'-dicarbazole-biphenyl (CBP), poly(n-vinylcarbazole) (PVK), 9,10-di(naphthalene-2-yl)anthracene (ADN), TCTA, 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di-2-naphthylanthracene (TBADN), distyrylarylene (DSA), Bis(2-(2-hydroxyphenyl)benzothiazolate)zinc (Zn(BTZ) 2), E3 below, ADN and referred to as Formula 1, Compound 1 below, and Compound 2 below.



37





The dopant may be a phosphorescent or fluorescent emitter. Phosphorescent emitters are preferred due to their higher efficiency

Examples of a red dopant are PtOEP, Ir(piq) 3, and Btp 2Ir(acac) but are not limited thereto. These compounds are phosphorescent emitters, however, fluorescent red dopants could also be used.

38




Examples of a phosphorescent green dopant are Ir(ppy) 3 (ppy=phenylpyridine), Ir(ppy) 2(acac), Ir(mpyp) 3 are shown below. Compound 3 is an example of a fluorescent green emitter and the structure is shown below.




39

-continued

Compound 3




Examples of a phosphorescent blue dopant are F_2Irpic , $(F_2ppy)_2Ir(tmd)$ and $Ir(dfppz)$ 3, ter-fluorene, the structures are shown below. 4,4'-bis(4-diphenyl amino)styryl)biphenyl (DPAVBi), 2,5,8,11-tetra-tert-butyl perylene (TBPe), and Compound 4 below are examples of fluorescent blue dopants.



40

-continued

Compound 4



The amount of the dopant may be in the range of about 0.01 to about 50 parts by weight, based on 100 parts by weight of the host. The EML **150** may have a thickness of about 10 nm to about 100 nm, for example, about 20 nm to about 60 nm. When the thickness of the EML **150** is within this range, the EML **150** may have excellent light emission, without a substantial increase in driving voltage.

When the EML **150** comprises a phosphorescent dopant, a hole blocking layer (HBL) (not shown) may be formed on the EML **150**, by using vacuum deposition, spin coating, slot-die coating, printing, casting, LB deposition, or the like, in order to prevent the diffusion of triplet excitons or holes into the ETL **160**. When the HBL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL **130**. However, the conditions for deposition and coating may vary, according to the compound that is used to form the HBL. Any compound that is commonly used to form a HBL may be used. Examples of compounds for forming the HBL include an oxadiazole derivative, a triazole derivative, and a phenanthroline derivative.

The HBL may have a thickness of about 5 nm to about 100 nm, for example, about 10 nm to about 30 nm. When the thickness of the HBL is within this range, the HBL may have excellent hole-blocking properties, without a substantial increase in driving voltage.

The ETL **160** may be formed on the EML **150** or on the HBL if the HBL is formed.

The ETL **160** has a stacked structure, preferably of two ETL-layers (**161/162**), so that injection and transport of electrons may be balanced and holes may be efficiently blocked. In a conventional OLED, since the amounts of electrons and holes vary with time, after driving is initiated, the number of excitons generated in an emission area may be reduced. As a result, a carrier balance may not be maintained, so as to reduce the lifetime of the OLED.

However, in the ETL **160**, the first layer **161** and the second layer **162** may have similar or identical energy levels. In general the matrix compound for the first electron layer (**161**) and second electron layer (**162**) can be identical or different.

Matrix compound for the first electron layer (**161**) and second electron layer (**162**) that can be suitably used are selected from the group comprising anthracene compounds, preferably 2-(4-(9,10-di(naphthalen-2-yl)anthracen-2-yl)phenyl)-1-phenyl-1H-benzo[d]imidazole and 1-(4-(10-([1,1'-biphenyl]-4-yl)anthracen-9-yl)phenyl)-2-ethyl-1H-benzo[d]imidazole.

Anthracene compounds that can be used as matrix compounds are disclosed in U.S. Pat. No. 6,878,469 B and incorporated by reference.

Other matrix compounds that can be used are diphenylphosphine oxide, preferably (3-(dibenzo[c,h]acridin-7-yl)phenyl)diphenylphosphine oxide, phenylbis(3-(pyren-1-yl)

41


phenyl)phosphine oxide, 3-phenyl-3H-benzo[b]dinaphtho
[2,1-d:1',2'-f]phosphine-3-oxide, bis(4-(anthracen-9-yl)
phenyl)(phenyl)phosphine oxide, phenyldi(pyren-1-yl)
phosphine oxide, (3-(9,10-di(naphthalen-2-yl)anthracen-2-
yl)phenyl)diphenylphosphine oxide, phenyldi(pyren-1-yl)
phosphine oxide, diphenyl(5-(pyren-1-yl)pyridin-2-yl)
phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-biphenyl]-
3-yl)phosphine oxide, diphenyl(4'-(pyren-1-yl)-[1,1'-
biphenyl]-3-yl)phosphine oxide, (3'-(dibenzo[c,h]acridin-7-
yl)-[1,1'-biphenyl]-4-yl)diphenylphosphine oxide and/or
phenyldi(pyren-1-yl)phosphine oxide.

Diphenylphosphine oxide compounds that can be used as
matrix compounds are disclosed in EP 2395571 A1,
WO2013079217 A1, EP 13187905, EP13199361 and
JP2002063989 A1, incorporated by reference.


Other suitable matrix compounds that can be used are
phenanthroline compounds, preferably selected from the
group comprising 2,4,7,9-tetraphenyl-1,10-phenanthroline
and 2,9-di(biphenyl-4-yl)-4,7-diphenyl-1,10-phenanthro-
line. Phenanthroline compounds that can be used as matrix
compounds are disclosed in EP 1786050 A1 and incorpo-
rated by reference.

The matrix compound of the first electron layer (**161**)
and/or second electron transport layer (**162**) may be a
compound that efficiently transports electrons, such as an
anthracene-based compound, diphenylphosphine oxide
based compound, or a phenanthroline based compound,
preferably a matrix compound mentioned in Table 2. For
example, the matrix compound of the first electron layer
and/or second electron transport layer may be selected from
the group consisting of ADN and referred to as Formula 1,
a compound represented by Formula 2, and a compound
represented by Formula 3 below:

Formula 1 (ADN)




Formula 2



42

-continued

Formula 3



In Formulae 2 and 3, R_1 to R_6 are each independently a
hydrogen atom, a halogen atom, a hydroxy group, a cyano
group, a substituted or unsubstituted C_1 - C_{30} alkyl group, a
substituted or unsubstituted C_1 - C_{30} alkoxy group, a substi-
tuted or unsubstituted C_1 - C_{30} acyl group, a substituted or
unsubstituted C_2 - C_{30} alkenyl group, a substituted or unsub-
stituted C_2 - C_{30} alkynyl group, a substituted or unsubstituted
 C_6 - C_{30} aryl group, or a substituted or unsubstituted C_3 - C_{30}
heteroaryl group. At least two adjacent R_1 to R_6 groups are
optionally bonded to each other, to form a saturated or
unsaturated ring. L_1 is a bond, a substituted or unsubstituted
 C_1 - C_{30} alkylene group, a substituted or unsubstituted C_6 - C_{30}
arylene group, or a substituted or unsubstituted C_3 - C_{30}
heteroarylene group. Q_1 through Q_9 are each independently
a hydrogen atom, a substituted or unsubstituted C_6 - C_{30} aryl
group, or a substituted or unsubstituted C_3 - C_{30} hetero aryl
group, and "a" is an integer from 1 to 10.

For example, R_1 to R_6 may be each independently
selected from the group consisting of a hydrogen atom, a
halogen atom, a hydroxy group, a cyano group, a methyl
group, an ethyl group, a propyl group, a butyl group, a
methoxy group, an ethoxy group, a propoxy group, a butoxy
group, a phenyl group, a naphthyl group, an anthryl group,
a pyridinyl group, and a pyrazinyl group.



In particular, in Formula 2 and/or 3, R_1 to R_4 may each be
a hydrogen atom, R_5 may be selected from the group
consisting of a halogen atom, a hydroxy group, a cyano
group, a methyl group, an ethyl group, a propyl group, a
butyl group, a methoxy group, an ethoxy group, a propoxy
group, a butoxy group, a phenyl group, a naphthyl group, an
anthryl group, a pyridinyl group, and a pyrazinyl group. In
addition, in Formula 3, R_1 to R_6 may each be a hydrogen
atom.

For example, in Formula 2 and/or 3, Q_1 to Q_9 are each
independently a hydrogen atom, a phenyl group, a naphthyl
group, an anthryl group, a pyridinyl group, and a pyrazinyl
group. In particular, in Formulae 2 and/or 3, Q_1 , Q_3 - Q_6 , Q_8
and Q_9 are hydrogen atoms, and Q_2 and Q_7 may be each
independently selected from the group consisting of a phen-
yl group, a naphthyl group, an anthryl group, a pyridinyl
group, and a pyrazinyl group.

For example, L_1 , in Formula 2 and/or 3, may be selected
from the group consisting of a phenylene group, a naphth-
ylene group, an anthrylene group, a pyridinylene group, and
a pyrazinylene group. In particular, L_1 may be a phenylene
group or a pyridinylene group. For example, "a" may be 1,
2, or 3.

43

The matrix compound may be further selected from Compound 6 or 7 below:



The first electron transport layer **161** comprises a lithium halide or a lithium organic complex; and the second electron transport layer **162** comprises an elemental metal selected from the group comprising lithium, magnesium, and/or ytterbium.

According to another aspect the first electron transport layer **161** comprises an elemental metal selected from the group comprising lithium, magnesium and/or ytterbium; and the second electron transport layer **162** comprises a lithium halide or a lithium organic complex.

According to another aspect the first electron transport layer **161** comprises a lithium halide or a lithium organic complex; and the second electron transport layer **162** comprises an elemental metal selected from the group comprising lithium, magnesium and/or ytterbium; and the third electron transport layer **163** comprises a lithium halide or a lithium organic complex that is the same or differs from the lithium halide or lithium organic complex of the first electron transport layer **161**.

Suitable organic ligands to form a lithium organic complex that can be used for the first electron transport layer or the second electron transport layer are disclosed, and incor-

44

porated by reference, for example in WO 2013079676 A1, WO 2013079678 A1 and EP 2724388 and Kathirgamanathan, Poopathy; Arkley, Vincent; Surendrakumar, Sivaganasundram; Chan, Yun F.; Ravichandran, Seenivasagam; Ganeshamurugan, Subramaniam; Kumaravel, Muttulingam; Antipan-Lara, Juan; Paramaswara, Gnanamolly; Reddy, Vanga R., Digest of Technical Papers—Society for Information Display International Symposium (2010), 41(Bk. 1), 465-468.

The ETL layer stack thickness can be adjusted such that the light out coupling is maximized. Further ETL layer stack thickness can be adjusted for the desired color tuning, for example to achieve a deeper shade of blue, i.e. smaller CIE-y.

The thicknesses of the first electron transport layer **161**, second electron transport layer **162** and/or third electron transport layer **163** may be the same or each independently in the range of about ≥ 0.5 nm to about ≤ 95 nm, preferably of about ≥ 3 nm to about ≤ 80 nm, further preferred of about ≥ 5 nm to about ≤ 60 nm, also preferred of about ≥ 6 nm to about ≤ 40 nm, in addition preferred about ≥ 8 nm to about ≤ 20 nm and more preferred of about ≥ 10 nm to about ≤ 18 nm.

When the thicknesses of the first electron transport layer **161**, second electron transport layer **162** and/or third electron transport layer **163** within this range, preferably of about ≥ 10 nm to about ≤ 18 nm, the electron transport layer stack **160** may effectively inject and transport electrons, without a substantial increase in driving voltage.

For blue emitting OLEDs, the thickness of the ETL layer stack is 10 to 50 nm, preferably 30 to 40 nm. For red and green emitting OLEDs, the thickness of ETLs is 20 to 100 nm, preferably 20 to 100 nm and more preferably 30 to 80 nm. The thickness is selected so as to maximize efficiency of light emission.

The amount of the total lithium organic complexes in at least one electron transport layer (**161**) that is free of a metal salt may be in the range of about ≥ 10 wt.-% to about ≤ 70 wt.-%, preferably about ≥ 20 wt.-% to about ≤ 65 wt.-% and also preferred about ≥ 30 wt.-% to about ≤ 55 wt.-% and also preferred about ≥ 35 wt.-% to about ≤ 50 wt.-%, by weight of the first electron transport layer **161**.

The amount of the lithium halide and lithium organic complex in the first electron transport layer **161** may be in the range of about ≥ 10 wt.-% to about ≤ 70 wt.-%, preferably about ≥ 20 wt.-% to about ≤ 65 wt.-% and also preferred about ≥ 30 wt.-% to about ≤ 55 wt.-% and also preferred about ≥ 35 wt.-% to about ≤ 50 wt.-%, by weight of the first electron transport layer **161**.

The ETL **160** may be formed on the EML **150** by vacuum deposition, spin coating, slot-die coating, printing, casting, or the like. When the ETL **160** is formed by vacuum deposition or spin coating, the deposition and coating conditions may be similar to those for formation of the HIL **130**. However, the deposition and coating conditions may vary, according to a compound that is used to form the ETL **160**.

Using vacuum deposition, the first electron transport layer **161** of the ETL **160** may be formed using a first deposition source to deposit a matrix compound, and a second deposition source to deposit a lithium halide or first lithium organic complex and a third deposition source to deposit a second lithium organic complex. The first deposition source, second deposition source and third deposition source are positioned relative to one another, such that a mixed deposition region of the first electron transport layer **161** is formed directly on the EML **150**.

The second electron transport layer **162** of the ETL **160** may be formed using a first or a third deposition source, for example if the matrix compound is different to the ETL **161**.

In case the second electron transport layer **162** of the ETL **160** may comprise a different matrix compound than ETL **1** a fourth deposition source is used to deposit the matrix compound. In case a lithium halide and a lithium organic complex or two different lithium organic complexes are deposit for forming the ETL **2** additional deposition sources are used. If compounds used to form the first ETL **1** and second ETL **2** are identical, than the same deposition sources can be used.

The deposition sources are positioned relative to one another, such that a mixed deposition region of the second electron transport layer **162** is formed directly on the first electron transport layer **161**.

The stacking process is more simply and quickly performed, as compared to prior methods. In particular, since a plurality of ETL layers may be almost simultaneously deposited in a single chamber, the chamber may not be required to be exhausted after the formation of each layer.

The EIL **180**, which facilitates injection of electrons from the cathode, may be formed on the ETL **160**, preferably directly on the second electron transport layer **162**. Examples of materials for forming the EIL **180** include LiF, NaCl, CsF, Li₂O, BaO, Ca, Ba, Yb, Mg which are known in the art. Deposition and coating conditions for forming the EIL **180** are similar to those for formation of the HIL **130**, although the deposition and coating conditions may vary, according to a material that is used to form the EIL **180**.

The thickness of the EIL **180** may be in the range of about 0.1 nm to 10 nm, for example, in the range of 0.5 nm to 9 nm. When the thickness of the EIL **180** is within this range, the EIL **180** may have satisfactory electron-injecting properties, without a substantial increase in driving voltage.

The second cathode electrode **190** is formed on the EIL **180** if present. The second cathode electrode **190** may be a cathode, which is an electron-injecting electrode. The second electrode **190** may be formed of a metal, an alloy, an electrically conductive compound, or a mixture thereof. The second electrode **190** may have a low work function. For example, the second electrode **190** may be formed of lithium (Li), magnesium (Mg), aluminum (Al), aluminum (Al)-lithium (Li), calcium (Ca), barium (Ba), ytterbium (Yb), magnesium (Mg)-indium (In), magnesium (Mg)-silver (Ag), or the like. In addition, the second electrode **190** may be formed of a transparent conductive material, such as ITO or IZO.

The thickness of the cathode electrode **190** may be in the range of about 5 nm to 1000 nm, for example, in the range of 10 nm to 100 nm. When the cathode electrode **190** is in the range of 5 nm to 50 nm, the electrode will transparent even if a metal or metal alloy is used.

Since the layers of the ETL **160** have similar or identical energy levels, the injection and transport of the electrons may be controlled, and the holes may be efficiently blocked. Thus, the OLED **100** may have long lifetime.

FIG. 7 and FIG. 8 is a schematic sectional view of an OLED **200**, according to another exemplary embodiment of the present invention. The OLED **200** of FIGS. 7 and 8 has no electron injection layer (EIL) **180**.

Referring to FIGS. 7 and 8 the OLED **200** includes a substrate **110**, a first electrode **120**, a HIL **130**, a HTL **140**, an EML **150**, an ETL **160**, and a second electrode **190**. The ETL stack **160** of FIG. 7 includes a first ETL layer **161** and

a second ETL layer **162**. The ETL stack **160** of FIG. 8 includes a first ETL layer **161**, a second ETL layer **162** and a third ETL layer **163**.

The electron transport layer stack **160** of FIG. 7 comprises at least two electron transport layers **161** and **162**, wherein a first electron transport layer **161** and a second electron transport layer **162** comprises at least one matrix compound and in addition,

the first electron transport layer comprises two lithium organic complexes, and

the second electron transport layer comprises two lithium organic complexes; wherein the first electron transport layer is arranged closest to an anode and the second electron transport layer is arranged closest to a cathode.

The electron transport layer stack **160** of FIG. 8 comprises at least three electron transport layers **161**, **162** and **163**, wherein a first electron transport layer **161**, a second electron transport layer **162** and a third electron transport layer **163** comprises at least one matrix compound and in addition,

the first electron transport layer **161** comprises a lithium halide and lithium organic complex,

the third electron transport layer **163** comprises two lithium organic complexes, and

the second electron transport layer **162** is free of lithium halide and lithium organic complex; wherein the first electron transport layer **161** is arranged closest to an anode and the third electron transport layer **163** is arranged closest to a cathode.

The layers of the ETL **161** and **162** or of the ETL **161** and **163** have similar or identical energy level. The OLED **200** have an improved lifetime (LT). The substrate **110**, the first electrode **120**, the hole injection layer **130**, the hole transport layer **140**, the emission layer **150**, and the electron transport layer **161** and **162** of the OLED **200** of FIG. 7 and FIG. 8 are similar to corresponding elements described with reference to FIGS. 5 and 6, respectively. Even though the structure of the OLED **200** and the method of manufacturing the OLED **200** are described with reference to FIGS. 5 and 6, other methods known in the art can be used. For example, the ETL stack **160** may include three or more ETL layers but two ETL layers of ETL **161** and **162** may be preferred and one ETL layer only can be most preferred.

In the description above the method of manufacture an OLED of the present invention is started with a substrate **110** onto which a first anode electrode **120** is formed, on the first anode electrode **120** an emission layer **150** is formed. An electron transport layer **161** or electron transport layer stack **160** is formed on the emission layer **150**, wherein in case of an electron transport layer stack **160** the first electron transport layer **161** is formed on the emission layer **150** and the second electron transport layer **162** is formed directly on the first electron transport layer **161**, on the electron transport layer stack **160**, in this case on the second electron transport layer **162**, a cathode electrode **190** is formed, optional a hole injection layer **130**, and a hole transport layer **140**, are formed between the first anode electrode **120** and the electron transport layer stack **160**, an optional hole blocking layer is formed between the emission layer and the ETL layer stack, and optionally an electron injection layer **180** is formed between the electron transport layer **160** and the second cathode electrode **190**.

However, the OLED of the present invention can be manufactured also the other way around, starting with the second cathode electrode **190** onto which optionally an electron injection layer **180** is formed. On the second cathode electrode **190** or on the electron injection layer **180**, if present, the electron transport layer **161** or electron

transport layer stack (160) is formed, whereby directly on the second electron transport layer 162 the first electron transport layer 161 is formed, and so on.

In case of a three layer electron transport layer stack 160, the second electron layer 162 is formed on the first electron layer 161 and the third electron layer 163 is formed on the second electron layer 162. Then a cathode electrode 190 is formed, optional a hole injection layer 130, and a hole transport layer 140, are formed between the first anode electrode 120 and the electron transport layer stack 160, an optional hole blocking layer is formed between the emission layer and the ETL layer stack, and optionally an electron injection layer 180 is formed between the electron transport layer 160 and the second cathode electrode 190.

While not shown in FIGS. 5 to 8, a sealing layer may further be formed on the second electrodes 190, in order to seal the OLEDs 100, 200. In addition, various other modifications may be applied thereto.

Hereinafter, one or more exemplary aspects will be described in detail with, reference to the following examples. However, these examples are not intended to limit the purpose and scope of the one or more exemplary aspects.

EXAMPLES

General procedure

For bottom emission devices, a 15Ω/cm² glass substrate (available from Corning Co.) with 100 nm ITO was cut to a size of 50 mm×50 mm×0.7 mm, ultrasonically cleaned with isopropyl alcohol for 5 minutes and then with pure water for 5 minutes, and cleaned again with UV ozone for 30 minutes, to prepare a first electrode.

For top emission devices, the anode electrode was formed from 100 nm silver on glass which was prepared by the same methods as described above.

Then, 92 wt.-% of N4, N4"-di(naphthalen-1-yl)-N4, N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine and 8 wt.-% of 2,2',2"-(cyclopropane-1,2,3-triylidene)tris(2-(p-cyanotetrafluorophenyl)acetonitrile) was vacuum deposited on the ITO electrode, to form a HIL having a thickness of 10 nm. Then N4, N4"-di(naphthalen-1-yl)-N4, N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine was vacuum deposited on the HIL, to form a HTL having a thickness of 130 nm in top emission devices and 120 nm in bottom emission devices. 97 wt.-% of ABH113 (Sun Fine Chemicals) as a host and 3 wt.-% of NUBD370 (Sun Fine Chemicals) as a dopant were deposited on the HTL, to form a blue-emitting EML with a thickness of 20 nm.

Then the ETL-layer stack is formed by depositing the first electron transport layer (ETL 1) including a matrix compound according to Example 1 to Example 11 and comparative example 1 by depositing the matrix compound from a first deposition source and the lithium organic complex, lithium halide of from a second and third deposition source directly on the EML or the two lithium organic complexes from a second and third deposition source.

Then optional the second electron transport layer (ETL2) including a matrix compound is formed by depositing the matrix compound from a first deposition source or if the matrix material is different to the matrix material of the first electron transport layer (ETL1), from a different deposition source.

For the comparative example 1 only one electron transport layer ETL1 is formed. The wt.-% of the lithium organic complex for the ETL1 can be taken from Table 4 and 5, whereby the wt.-% amount of the matrix compound is added to 100 wt.-%, respectively. That means, that the matrix compound of ETL1 are added in a wt.-% amount such that the given wt.-% of the two lithium organic complexes for the ETL1 and the matrix compound of the ETL1 are in total 100 wt.-%, based on the weight of the ETL1. Further, the thickness d (in nm) of the ETL1 can be taken from Table 4 and 5. The cathode was evaporated at ultra-high vacuum of 10⁻⁷ bar. Therefore, a thermal single co-evaporation of one or several metals was performed with a rate of 0, 1 to 10 nm/s (0.01 to 1 Å/s) in order to generate a homogeneous cathode with a thickness of 5 to 1000 nm. For top emission devices, the cathode electrode was formed from 13 nm magnesium (90 vol.-%) and silver (10 vol.-%) alloy, followed by 60 nm N4,N4"-di(naphthalen-1-yl)-N4,N4"-diphenyl-[1,1':4',1"-terphenyl]-4,4"-diamine. For bottom emission devices, the cathode electrode was formed from 100 nm aluminum.

The OLED stack is protected from ambient conditions by encapsulation of the device with a glass slide. Thereby, a cavity is formed, which includes a getter material for further protection.

To assess the performance of the inventive examples compared to the prior art, the current efficiency is measured under ambient conditions (20° C.). Current voltage measurements are performed using a Keithley 2400 sourcemeter, and recorded in V. At 15 mA/cm², a calibrated spectrometer CAS140 from Instrument Systems is used for measurement of CIE coordinates and brightness in Candela. Lifetime LT of the device is measured at ambient conditions (20° C.) and 15 mA/cm², using a Keithley 2400 sourcemeter, and recorded in hours. The brightness of the device is measured using a calibrated photo diode. The lifetime LT is defined as the time till the brightness of the device is reduced to 97% of its initial value.

In bottom emission devices, the emission is predominately Lambertian and quantified in percent external quantum efficiency (EQE). To determine the efficiency EQE in % the light output of the device is measured using a calibrated photodiode at 10 mA/cm².

In top emission devices, the emission is forward directed, non-Lambertian and also highly dependent on the micro-cavity. Therefore, the efficiency EQE will be higher compared to bottom emission devices. To determine the efficiency EQE in % the light output of the device is measured using a calibrated photodiode at 10 mA/cm².

Technical Effect of the Invention

Top Emission Devices

a) Lifetime and efficiency improvement with one electron transport layer (ETL1)

In Table 4 results are shown for top emission devices with one electron transport layer (ETL1) containing one matrix compound and two lithium organic complexes AD1 and AD2. An external quantum efficiency (EQE) and lifetime improvement is observed compared to the emission device with one lithium organic complex only—Table 4.

TABLE 4

External quantum efficiency (EQE) and lifetime of top emission OLEDs with a single triple mixed ETL							
	ETL1 (ETM:AD1:AD2)	d (ETL)/ nm	wt %* ¹ ETM:AD1:AD2	V at 15 mA/cm ² /V	EQE* ² /%	CIE-y	LT/h
Comp.	MX-2:LiQ	36	50:50:00	4.63	9.6	0.047	140
Example 1	MX-2:Li-2:Li-1	36	65:25:10	4.30	13.2	0.050	25
Example 2	MX-2:LiQ:Li-1	36	65:25:10	4.32	12.6	0.049	39
Example 3	MX-2:Li-3:Li-2	36	50:25:25	4.89	10.2	0.050	140
Example 4	MX-3:LiQ:Li-1	37	65:25:10	4.16	12.5	0.069	21
Example 5	MX-11:LiQ:Li-1	36	65:25:10	5.02	10.5	0.066	32
Example 6	MX-11:Li-2:Li-1	36	65:25:10	5.26	11.3	0.067	22

*¹= the wt.-% of the matrix compound (ETM) and the wt.-% of the lithium organic complexes (AD1 and AD2) are in total 100 wt.-% based on weight of the ETL1

*²= detecting the light output efficiency with a calibrated photo diode

In the Table 4 above device data for a single ETL device with one lithium organic complex compared to a device with a single ETL containing two lithium organic complexes is shown. As can be seen, the efficiency are improved for devices having a single ETL containing two lithium organic complexes compared to a device having a single ETL with just one lithium organic complex (Comparative example 1).

In Example 2 and 4, and 5 and 6, respectively, the effect of a second lithium organic complex, lithium borate (Li-1), is compared to comparative example 1, containing just one lithium organic complex, lithium quinolate LiQ. The efficiency is increased compared to comparative example 1, thereby demonstrating an advantageous effect of a second lithium organic complex, in particular of lithium borate.

(MX-11). In both cases, an efficiency improvement is observed compared to the comparative example 1. However, the efficiency improvement is more pronounced for the phosphine oxide matrix compound.

The lifetime and efficiency is also improved when comparing the single ETL device of Example 3 with the comparative example 1.

Bottom Emission Devices

a) Lifetime and efficiency improvement with one electron transport layer (ETL1)

In Table 5 results are shown for bottom emission devices with one electron transport layer (ETL1) containing one matrix compound and two lithium organic complexes AD1 and AD2.

TABLE 5

External quantum efficiency (EQE) and lifetime of bottom emission OLEDs with a single triple mixed ETL							
	ETL1 (ETM:AD1:AD2)	d (ETL)/ nm	wt %* ¹ ETM:AD1:AD2	V at 15 mA/cm ² /V	EQE* ² /%	CIE-y	LT/h
Example 7	MX-2:LiQ:Li-3	37	65:25:10	4.8	5.6	0.098	200
Example 8	MX-12:LiQ:Li-1	36	65:25:10	7.6	6.3	0.096	7
Example 9	MX-2:LiQ:Li-1	36	65:25:10	4.4	8	0.097	45
Example 10	MX-12:Li-2:Li-1	36	65:25:10	6.8	7.8	0.093	6
Example 11	MX-2:Li-2:Li-1	36	65:25:10	4.4	8.6	0.095	27

*¹= the wt.-% of the matrix compound (ETM) and the wt.-% of the lithium organic complexes (AD1 and AD2) are in total 100 wt.-% based on weight of the ETL1

*²= detecting the light output efficiency with a calibrated photo diode

In Example 1 and 6, the effect of a second lithium compound which is not LiQ is compared to Example 2 and 5 containing LiQ and lithium borate Li-1. In Example 1 and 6, lithium phosphoryl aryl complex (Li-2), is used instead of LiQ. As can be seen in Table 4, the efficiency is improved even further, from 12.6 to 13.2% EQE for phosphine oxide matrix, and from 10.5 to 11.3% EQE for phenanthroline matrix. These results clearly show a technical benefit of selecting the first and second lithium compound from lithium borate and lithium phosphoryl aryl complex, respectively.

An increase in efficiency can be obtained for matrix compounds with various LUMO levels and functional groups. In Example 2 and 4, phosphine oxide matrix compounds with a LUMO level ranging from -2.64 eV (MX-2) to -2.36 eV (MX-3) are compared. As can be seen in Table 4, the efficiency improvement is independent of the LUMO level of the phosphine oxide matrix.

In Example 1 and 6, two different materials classes of matrix compounds are compared, a phosphine oxide matrix compound (MX-2) and a phenanthroline matrix compound

In the Table 5 above a device data is shown for a single ETL device with two lithium organic complexes, AD1 and AD2.

In Example 7, phosphine oxide matrix compound (MX-2) is doped with a first lithium organic complex (LiQ) and a second lithium organic complex (Li-3). The structures of LiQ and Li-3 are shown in Table 1. Both lithium organic complexes are lithium phenolates whereby the phenolate ring is substituted further. As can be seen in Table 5, the efficiency is 5.6% EQE and the lifetime is 200 hours.

In Example 8, an anthracene matrix compound (MX-12) is doped with a first lithium organic complex containing a nitrogen heterocyclic ligand bearing a hydroxyl group and a second lithium organic complex which does not contain a heterocyclic ligand bearing a hydroxyl group. In Example 8, the first lithium organic complex is LiQ and the second lithium organic complex is lithium borate Li-1. The efficiency is 6.3% EQE and the lifetime is 7 hours.

In Example 9, a phosphine oxide matrix compound (MX-2) is doped with a first lithium organic complex containing a nitrogen heterocyclic ligand bearing a hydroxyl group and

51

a second lithium organic complex which does not contain a heterocyclic ligand bearing a hydroxyl group. In Example 9, the first lithium organic complex is LiQ and the second lithium organic complex is borate Li-1. The efficiency is 8% EQE and the lifetime is 45 hours. Efficiency and lifetime are significantly improved compared to Example 8, thereby demonstrating the beneficial effect of a phosphine oxide matrix compound compared to an anthracene matrix compound.

In Example 10 and 11, two lithium organic complexes are used which do not containing a nitrogen heterocyclic ligand bearing a hydroxyl group. The first lithium organic complex is lithium phosphoryl aryl complex Li-2 and the second lithium organic complex is borate Li-1. Two matrix compounds are compared, an anthracene matrix compound (MX-12) in Example 10, and a phosphine oxide matrix compound (MX-2) in Example 11, respectively. In both examples, the efficiency EQE is 7.8 and 8.6% EQE. The efficiency is significantly improved over Examples 8 and 9, and thereby it is shown that there is an additive beneficial effect of using lithium organic complexes which do not contain a nitrogen heterocyclic ligand bearing a hydroxyl group. The beneficial effect of two lithium organic complexes, in particular of two lithium organic complexes which are based on borate and/or phosphoryl aryl ligand is apparent even for different matrix compound classes, for example anthracene matrix compound and phosphine oxide matrix compounds. The lifetime in Examples 10 is 6 hours while the lifetime in Example 11 is 27 hours.

In summary, a significant improvement in external quantum efficiency EQE is achieved for matrix compounds doped with at least on lithium organic complex selected from a lithium borate complex or a lithium phosphoryl aryl complex. Additionally, a significant increase in lifetime is observed for matrix compounds comprising a phosphine oxide compared to anthracene-based matrix compounds.

The OLED according to the invention comprising a single ETL, a double ETL as well as the triple ETL could also be employed for other emission colors, for example green, red, and white-light emitting devices.

Another aspect is directed to an organic light-emitting diode (OLED) comprising more than one emission layer (EML) 150, for example two, three or four emission layers may be present. An organic light-emitting diode (OLED) comprising more than one emission layer is also described as a tandem OLED or stacked OLED.

Another aspect is directed to a device comprising at least one organic light-emitting diode (OLED). A device comprising organic light-emitting diodes is for example a display or a lighting panel.

From the foregoing detailed description and examples, it will be evident that modifications and variations can be made to the compositions and methods of the invention without departing from the spirit and scope of the invention. Therefore, it is intended that all modifications and/or combinations of embodiments made to the invention without departing from the spirit and scope of the invention come within the scope of the appended claims.

The invention claimed is:


1. An organic light-emitting diode (OLED) comprising an emission layer and at least one electron transport layer, wherein the at least one electron transport layer comprises at least one matrix compound and at least two lithium compounds, and wherein

at least one lithium compound is a lithium organic complex, which is selected from a lithium borate complex or a lithium phosphoryl aryl complex, and

52


at least one lithium compound is a lithium halide selected from LiF, LiCl, LiBr, or LiI.

2. The OLED according to claim 1, wherein: the lithium borate complex is of Formula IV:



wherein each of A¹, A², A³, and A⁴ is independently selected from substituted or unsubstituted C₆-C₂₀ aryl or substituted or unsubstituted C₂-C₂₀ heteroaryl, wherein A¹, A², A³, and/or A⁴ of Formula (IV) are not a phenolate group; and/or

the lithium phosphoryl aryl complex is of Formula V:



wherein

D¹ is a unsubstituted or substituted C₆-C₂₀ arylene and each of D² to D³ is independently selected from a unsubstituted or substituted C₆-C₂₀ aryl; and/or

wherein

D¹ is a C₆-C₃₀ arylene or C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S, or N in an aromatic ring; and

each of D² and D³ is independently selected from a C₆-C₃₀ aryl or C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S, or N in an aromatic ring and wherein either

- i) D¹ is C₂-C₃₀ heteroarylene comprising at least one atom selected from O, S, or N in an aromatic ring, and/or
- ii) at least one of D² and D³ is a C₂-C₃₀ heteroaryl comprising at least one atom selected from O, S, or N in an aromatic ring.

3. The OLED according to claim 2, wherein the lithium phosphoryl aryl complex is a lithium 2-(diphenylphosphoryl) phenolate.

4. The OLED according to claim 2, wherein the lithium borate complex is a lithium tetra(1H-pyrazol-1-yl)borate.

5. The OLED according to claim 1, wherein the matrix compound is selected from:

- an anthracene based compound or a heteroaryl substituted anthracene based compound;
- a phosphine oxide based compound; or
- a substituted phenanthroline compound.

6. The OLED according to claim 1, wherein the at least one electron transport layer or at least two electron transport layers comprise:

- about <90 wt.-% to about >30 wt.-% of the at least one matrix compound; and
 - about >10 wt.-% to about <70 wt.-% of the at least two lithium compounds;
- wherein the weight percent is based on the total weight of the corresponding electron transport layer.

7. The OLED according to claim 1, wherein the at least one electron transport layer comprises a third lithium compound selected from a lithium quinolate or a lithium phenolate.

53

8. The OLED according to claim 1, wherein the at least one electron transport layer or at least two electron transport layers comprise:

about <80 wt.-% to about >35 wt.-% of the at least one matrix compound; and

about >20 wt.-% to about <65 wt.-% of the at least two lithium compounds;

wherein the weight percent is based on the total weight of the corresponding electron transport layer.

9. The OLED according to claim 1, wherein the OLED comprises one electron transport layer and at least one electron injection layer; or a transport layer stack having two to four electron transport layers, whereby at least one electron transport layer comprises the at least one matrix compound and the at least two lithium compounds.

10. The OLED according to claim 1, wherein an at least second electron transport layer is arranged directly on the at least first electron transport layer and/or an at least third electron transport layer is arranged directly on the at least second electron transport layer so that the second electron transport layer is sandwiched between the first electron transport layer and the third electron transport layer.

11. The OLED according to claim 1 comprising: a substrate; a first anode electrode that is arranged on the substrate; a second cathode electrode that is arranged on the at least first anode electrode; and the at least one electron transport layer or an electron transport layer stack comprising the at least one electron transport layer, that is arranged between the at least first anode electrode and the at least second cathode electrode.

12. The OLED according to claim 11, further comprising an electron injection layer arranged between the electron transport layer stack and the at least second cathode electrode.

13. The OLED according to claim 1, further comprising at least one layer selected from the group consisting of a hole injection layer, a hole transport layer and a hole blocking layer, arranged between the at least first anode electrode and the electron transport layer stack.

14. The OLED according to claim 1, wherein the lithium borate complex is a lithium tetra(1H-pyrazol-1-yl)borate.

15. A method of manufacturing an organic light-emitting diode according to claim 1, the method using:

at least three deposition sources; and/or deposition via vacuum thermal evaporation; and/or deposition via solution processing.

16. A method of manufacturing an organic light-emitting diode according to claim 15, the method using:

a first or a first and a fourth deposition source to release the matrix compound, and

a second deposition source to release a first lithium compound of lithium halide or lithium organic complex, and

a third deposition source to release a second lithium compound of lithium halide or lithium organic complex; and the method comprising the steps of forming the electron transport layer or the electron transport layer stack; whereby

a first electron transport layer is formed by releasing the matrix compound from at least one deposition source and a first lithium halide or lithium organic complex, from a different deposition source and a second lithium halide or lithium organic complex, from a different deposition source;

optional onto the first electron transport layer a second electron transport layer is formed by releasing the matrix compound from at least one deposition source

54

and optional the first and second lithium compound from different deposition source;

optional onto the second electron transport layer a third electron transport layer is formed by releasing the matrix compound from at least one deposition source and optional the first and second lithium compound from different deposition source.

17. The method of claim 15, comprising the steps, wherein

on a substrate a first anode electrode is formed,

on the first anode electrode an emission layer is formed, on the emission layer at least a first electron transport layer is formed, optional a second electron transport layer is formed directly on the first electron transport layer or optional in case of a third electron transport layer, the third electron transport layer is formed directly on the second electron transport layer,

on the electron transport layer or the electron transport layer stack a second cathode electrode is formed, optional a hole injection layer, a hole transport layer, an emission layer, and a hole blocking layer, are formed between the at least first anode electrode and the electron transport layer or electron transport layer stack,



optional an electron injection layer is formed between the electron transport layer or electron transport layer stack, and the at least second cathode electrode.

18. A device comprising at least one organic light-emitting diode of claim 1.

19. An organic light-emitting diode (OLED) comprising an emission layer and at least one electron transport layer, wherein the at least one electron transport layer comprises at least one matrix compound and at least two lithium compounds,


wherein (i) at least one of the at least two lithium compounds is a lithium organic complex, which is selected from a lithium phenolate, a lithium pyridinolate, or a lithium Schiff base, or (ii) one of the at least two lithium compounds is a lithium borate or a lithium pyridinolate, and one of the at least two lithium compounds is a lithium quinolate, a lithium borate, a lithium phenolate, a lithium pyridinolate or a lithium Schiff base; and

wherein (a) the lithium phenolate is a lithium 2-(1-phenyl-1H-benzo imidazol-2-yl)phenolate, (b) the lithium pyridinolate is a lithium 2-(diphenylphosphoryl)pyridin-3-olate, and/or (c) the lithium Schiff base has the structure 100, 101, 102 or 103—






55

-continued



20. The OLED according to claim 19, wherein the lithium quinolate has the formula I, II or III:



wherein

A 1 to A 6 are same or independently selected from CH, CR, N, or O;

56

R is same or independently selected from hydrogen, halogen, alkyl or aryl or heteroaryl with 1 to 20 carbon atoms.


21. The OLED according to claim 20, wherein A 1 to A 6 are CH.

22. The OLED according to claim 19, wherein the lithium phenolate is a lithium 2-(pyridin-2-yl)phenolate, a lithium 2-(diphenylphosphoryl)phenolate, a lithium imidazol phenolate, or a lithium 2-(pyridin-2-yl)phenolate.

23. The OLED according to claim 19, wherein the OLED comprises the lithium 2-(diphenylphosphoryl)pyridin-3-olate.


24. The OLED according to claim 19, wherein the OLED comprises the lithium Schiff base having the structure 100, 101, 102 or 103:

(I)



25

(II)




30

35

40

(III)

45



50

25. The OLED according to claim 19, wherein the OLED comprises the lithium 2-(1-phenyl-1H-benzimidazol-2-yl)phenolate.

* * * * *

专利名称(译)	有机发光二极管，包括电子传输层，该电子传输层包含基质化合物和两种锂化合物的三组分共混物		
公开(公告)号	US10522778	公开(公告)日	2019-12-31
申请号	US15/516067	申请日	2015-09-30
[标]申请(专利权)人(译)	诺瓦莱德公开股份有限公司		
申请(专利权)人(译)	Novaled公司GMBH		
当前申请(专利权)人(译)	Novaled公司GMBH		
[标]发明人	BLOOM FRANCISCO ROSENOW THOMAS CANZLER TOBIAS WALLIKIEWITZ BODO		
发明人	BLOOM, FRANCISCO ROSENOW, THOMAS CANZLER, TOBIAS WALLIKIEWITZ, BODO		
IPC分类号	H01L51/50 H01L51/00		
CPC分类号	H01L51/5056 H01L51/508 H01L51/5072 H01L51/0077 H01L51/5076 H01L51/0072		
审查员(译)	CLARK , GREGORYð		
优先权	2014187326 2014-10-01 EP		
其他公开文献	US20170301876A1		
外部链接	Espacenet		

摘要(译)

本发明涉及一种有机发光二极管100，其包括发射层150和至少一个电子传输层161，其中至少一个电子传输层161) 包括至少一种基质化合物和至少两种锂化合物。

