



US 20120097929A1

(19) **United States**(12) **Patent Application Publication**
Kim et al.(10) **Pub. No.: US 2012/0097929 A1**(43) **Pub. Date: Apr. 26, 2012**(54) **HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**(52) **U.S. Cl. 257/40; 544/180; 548/305.1; 548/416; 544/294; 548/145; 546/256; 544/281; 257/E51.018**(75) **Inventors:** **Young-Kook Kim**, Yongin-City (KR); **Seok-Hwan Hwang**, Yongin-City (KR); **Yoon-Hyun Kwak**, Yongin-City (KR); **Sun-Young Lee**, Yongin-City (KR); **Hye-Jin Jung**, Yongin-City (KR); **Jin-O Lim**, Yongin-City (KR); **Jong-Hyuk Lee**, Yongin-City (KR)(57) **ABSTRACT**

A heterocyclic compound represented by Formula 1 below and an organic light-emitting device including the heterocyclic compound:

(73) **Assignee:** **Samsung Mobile Display CO., LTD.**, Yongin-City (KR)

Formula 1

(21) **Appl. No.:** **13/210,599**(22) **Filed:** **Aug. 16, 2011**(30) **Foreign Application Priority Data**

Oct. 25, 2010 (KR) 10-2010-0104186



Publication Classification(51) **Int. Cl.**
H01L 51/54 (2006.01)
C07D 403/10 (2006.01)
C07D 487/04 (2006.01)
C07D 239/26 (2006.01)
C07D 413/10 (2006.01)
C07D 251/24 (2006.01)
C07D 209/82 (2006.01)wherein R₁ to R₁₂ are defined as in the specification.

FIG. 1



HETEROCYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME


CROSS-REFERENCE TO RELATED PATENT APPLICATION

[0001] This application claims the benefit of Korean Patent Application No. 10-2010-0104186, filed on Oct. 25, 2010, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a heterocyclic compound represented by Formula 1 and an organic light-emitting device including the heterocyclic compound.



Formula 1

[0004] 2. Description of the Related Art

[0005] Light-emitting devices are self-emission type display devices and have a wide viewing angle, a high contrast ratio, and a short response time. Due to these characteristics, light-emitting devices are drawing more attention. Such light-emitting devices can be roughly classified into inorganic light-emitting devices that include emission layers containing inorganic compounds, and organic light-emitting devices that include emission layers containing organic compounds. Specifically, organic light-emitting devices have higher luminance, lower driving voltages, and shorter response times than inorganic light-emitting devices; and can render multi-colored displays. Thus, much research into such organic light-emitting devices has been conducted. Typically, an organic light-emitting device has a stack structure including an anode, a cathode and an organic emission layer interposed therebetween. However, a hole injection layer and/or a hole transport layer may be further stacked between the anode and the organic emission layer, and/or an electron transport layer may be further stacked between the organic emission layer and the cathode. In other words, an organic light-emitting device may have a stack structure of anode/hole transport layer/organic emission layer/cathode or a stack structure of anode/hole transport layer/organic emission layer/electron transport layer/cathode.

[0006] Anthracene derivatives are widely known as materials for organic light-emission layer materials. Alq3, 2,2',2''-

(1,3,5-phenylene)tris-(1-phenyl)-1H-benzimidazol (TPBI), 2-biphenyl-4-yl-5-(4-tert-butyl-phenyl)-[1,3,4]oxadiazole (PBD), perfluorinated chemical (PF-6P), and 2,5-bis(6'-(2',2''-bipyridyl))-1,1-dimethyl-3,4-diphenylsilyl (Py-PySPyPy) are known as electron transport materials. However, these materials are not yet satisfactory to meet requirements for organic light-emitting devices in terms of efficiency and lifespan, thereby improvement in this regard still being necessary.

SUMMARY OF THE INVENTION


[0007] The present invention provides a heterocyclic compound having good electrical characteristics, charge transporting capabilities, light-emission capabilities, and a high glass-transition temperature that is high enough to prevent crystallization.

[0008] The present invention provides an organic light-emitting device including the heterocyclic compound.

[0009] The present invention provides a flat panel display device including the organic light-emitting device.


[0010] The present invention provides an organic light-emitting device including at least one layer containing the heterocyclic compound, wherein the at least one layer is formed using a wet process.

[0011] According to an aspect of the present invention, there is provided a heterocyclic compound represented by Formula 1 below:



Formula 1

[0012] wherein, in Formula 1, R₁ to R₁₂ are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₅-C₆₀ aryloxy group, a substituted or unsubstituted C₅-C₆₀ arylthio group, a substituted or unsubstituted C₅-C₆₀ aryl group, a substituted amino group with a C₅-C₆₀ aryl group or a C₂-C₆₀ heterocyclic group, a substituted or unsubstituted C₂-C₆₀ heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, and a carboxyl group, wherein R₆ and R₇ may be respectively linked to binding sites indicated by ** and *, respectively, in Formula 2 below:




Formula 2

[0013] wherein, in Formula 2, R_{13} and R_{14} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsub-


stituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_5 - C_{60} aryloxy group, a substituted or unsubstituted C_5 - C_{60} arylthio group, a substituted or unsubstituted C_5 - C_{60} aryl group, a substituted amino group with a C_5 - C_{60} aryl or C_2 - C_{60} heterocyclic group, a substituted or unsubstituted C_2 - C_{60} heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group; and

[0014] two adjacent substituents among R_1 to R_{14} are optionally linked to each other to form a ring.


[0015] The heterocyclic compound of Formula 1 may be one of the compounds below:




7



8



13





29

-continued



37

64



65



68



-continued



69

79





86

94





99

107




-continued
109

116



119



[0016] According to another aspect of the present invention, there is provided an organic light-emitting device including: a first electrode; a second electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer includes the heterocyclic compound represented by Formula 1 above.

[0017] The organic layer may include an emission layer including the heterocyclic compound of Formula 1 above as a host for a fluorescence or phosphorescence device.

[0018] The organic layer may include an emission layer including the heterocyclic compound of Formula 1 above as a dopant for a fluorescence device.

[0019] The organic layer may include an electron injection layer or an electron transport layer.

[0020] The organic layer may include a single layer having both an electron injection function and an electron transport function.

[0021] In some embodiments the organic layer may include an emission layer, an electron injection layer, or an electron transport layer. The emission layer, the electron injection layer, or the electron transport layer may include the heterocyclic compound of Formula 1 above. The emission layer may include an anthracene compound, an arylamine compound, or a styryl compound.

[0022] In some other embodiments the organic layer may include an emission layer, an electron injection layer, or an electron transport layer. The emission layer, the electron injection layer, or the electron transport layer may include the heterocyclic compound of Formula 1 above. The emission

layer may include red, green, blue, and white emission layers one of which includes a phosphorescent compound.

[0023] According to another aspect of the present invention, there is provided an organic light-emitting device including: a first electrode; a second electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer includes at least one layer comprising the heterocyclic compound of Formula 1 above, the at least one layer being formed using a wet process.

[0024] According to another aspect of the present invention, there is provided a flat panel display device including the organic light-emitting device described above, wherein the first electrode of the organic light-emitting device is electrically connected to a source electrode or a drain electrode of a thin-film transistor.

BRIEF DESCRIPTION OF THE DRAWING

[0025] The above and other features and advantages of the present invention will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawing in which:

[0026] FIG. 1 is a diagram of the structure of an organic light-emitting device according to an embodiment of the present invention.


DETAILED DESCRIPTION OF THE INVENTION

[0027] Organic light-emitting devices manufactured using anthracene derivatives, for example, a compound of phenylanthracene dimer or trimer, as organic emission layer mate-

rials are widely known. However, such organic light-emitting devices [text missing or illegible when filed]


[0028] The present invention will now be described more fully with reference to the accompanying drawings, in which exemplary embodiments of the invention are shown.

[0029] An aspect of the present invention includes a heterocyclic compound represented by Formula 1 below:



Formula 1

[0030] where R_1 to R_{12} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_5 - C_{60} aryloxy group, a substituted or unsubstituted C_5 - C_{60} arylthio group, a substituted or unsubstituted C_5 - C_{60} aryl group, a substituted amino group with a C_5 - C_{60} aryl group or a C_2 - C_{60} heterocyclic group, a substituted or unsubstituted C_2 - C_{60} heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group, wherein R_6 and R_7 may be linked to each other to form a group represented by Formula 2 in which ** and * indicates binding sites corresponding to the binding sites of R_6 and R_7 of Formula 1:



Formula 2

[0031] wherein R_{13} to R_{14} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_5 - C_{60} aryloxy group, a substituted or unsubstituted C_5 - C_{60} arylthio group, a substituted or unsubstituted C_5 - C_{60} aryl group, a substituted amino group


with a C_5 - C_{60} aryl group or a C_2 - C_{60} heterocyclic group, a substituted or unsubstituted C_2 - C_{60} heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group; and

[0032] two adjacent substituents among R_1 to R_{14} may be linked to each other to form a ring.

[0033] In some embodiments the heterocyclic compound of Formula 1 may be used as a light-emitting material, an electron-transporting material or an electron-injecting material. The heterocyclic compound of Formula 1, having a heterocyclic group in the molecules thereof, has a high glass transition temperature (Tg) or a high melting point due to the inclusion of the heterocyclic group. Thus, the heterocyclic compound has high heat resistance against Joule's heat generated in an organic layer, between organic layers, or between an organic layer and a metal electrode when light emission occurs, and has high durability in high-temperature environments.

[0034] An organic light-emitting device manufactured using the heterocyclic compound of Formula 1 has high durability when stored or operated. In addition, due to the inclusion of a substituent such as an aryl group or heterocyclic group, molecular layers formed as thin films may be maintained in good condition, thereby improving the characteristics of the organic light-emitting device.

[0035] When R_6 and R_7 in Formula 1 may be linked to each other to form the group represented by Formula 2, the heterocyclic compound represented by Formula 1 is a compound represented by Formula 1a:




Formula 1a


[0036] wherein R_1 - R_{14} in Formula 1a are the same as those described above.

[0037] Substituents in Formulae 1 and 2 will now be described in detail.

[0038] In some embodiments R_1 to R_{14} in Formulae 1 and 2 may be each independently a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a C_1 - C_{20} alkyl group, or groups represented by Formulae 2a to 2l below:



-continued




[0039] In Formula 2a to 2l above, Q₁ and Q₂ are each independently a linking group selected from among —C(R₁₅)(R₁₆)—, —N(R₁₅)—, —S—, and —O—; Y₁, Y₂, Y₃, Y₄, Y₅ and Y₆ are each independently a linking group selected from among —N=, —C(R₁₇)=, —S—, and —O—;

[0040] Z₁, Z₂, Ar₁₂, Ar₁₃, R₁₅, R₁₆, and R₁₇ are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₅-C₂₀ aryl group, a substituted or unsubstituted C₂-C₂₀ heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;


[0041] Ar₁₁ is a substituted or unsubstituted C₁-C₂₀ alkylene group, a substituted or unsubstituted C₅-C₂₀ arylene group, or a substituted or unsubstituted C₂-C₂₀ divalent heterocyclic group; and

[0042] p is an integer from 1 to 12; q is an integer from 1 to 12; r is an integer from 0 to 5; and * indicates a binding site.


[0043] In some embodiments R₁ to R₁₄ in Formulae 1 and 2 above may be each independently a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, or groups represented by Formulae 3a to 3h below:




-continued




formula 3d




formula 3e



formula 3f



formula 3g



formula 3h

[0044] In Formulae 3a to 3h above, Z_1 , Ar_{12} , and Ar_{13} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted aryl group, or a substituted or unsubstituted C_2 - C_{20} heterocyclic group; and

[0045] r is an integer from 0 to 2; p is an integer from 1 to 5; and * indicates a binding site.


[0046] According to an embodiment of the present embodiment, in Formula 1, R_2 to R_5 and R_7 to R_{11} may be each independently a hydrogen atom or a deuterium atom.

[0047] In some embodiments, R_2 to R_5 and R_7 to R_{11} in Formula 1 are each independently a hydrogen atom or a deuterium atom; and R_1 , R_6 and R_{12} are each independently a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_5 - C_{60} aryloxy group, a substituted or unsubstituted C_5 - C_{60} arylthio group, a substituted or unsubstituted C_5 - C_{60} aryl group, a substituted amino group with a C_5 - C_{60} aryl group or a C_2 - C_{60} heterocyclic group, a substituted or unsubstituted C_2 - C_{60} heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group.


[0048] In some embodiments, R_2 to R_5 , and R_7 to R_{11} in Formula 1 are each independently a hydrogen atom or a deuterium atom; and R_1 , R_6 and R_{12} are each independently a

halogen atom, a cyano group, a substituted or unsubstituted C_1 - C_{20} alkyl group, or groups represented by Formulae 2a to 2l below.


[0049] In some embodiments, R_2 to R_5 , and R_6 to R_{11} in Formula 1 are each independently a hydrogen atom or a deuterium atom; and R_1 , R_{12} , R_{13} , and R_{14} are each independently a halogen atom, a cyano group, a substituted or unsubstituted C_1 - C_{20} alkyl group, or groups represented by Formulae 2a to 2l below:




formula 2a




formula 2b




formula 2c




formula 2d




formula 2e



formula 2f




formula 2g




formula 2h


-continued




formula 2i



formula 2j



formula 2k



formula 2l

[0050] In Formulae 2a to 2l, Q_1 and Q_2 are each independently a linking group selected from among $-C(R_{15})-$ (R_{16}), $-N(R_{15})-$, $-S-$, and $-O-$;


[0051] $Y_1, Y_2, Y_3, Y_4, Y_5,$ and Y_6 are each independently a linking group selected from among $-N=$, $-C(R_{17})=$, $-S-$, and $-O-$;

[0052] $Z_1, Z_2, Ar_{12}, Ar_{13}, R_{15}, R_{16},$ and R_{17} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1-C_{20} alkyl group, a substituted or unsubstituted C_5-C_{20} aryl group, a substituted or unsubstituted C_2-C_{20} heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group;

[0053] Ar_{11} is a substituted or unsubstituted C_1-C_{20} alkylene group, a substituted or unsubstituted C_5-C_{20} arylene group, or a substituted or unsubstituted C_2-C_{20} divalent heterocyclic group; and


[0054] p is an integer from 1 to 12; q is an integer from 1 to 12; r is an integer from 0 to 5; and $*$ indicates a binding site.

[0055] In some embodiments, in Formulae 1 and 2 above, R_1, R_2, R_3, R_4, R_5 and R_{12} may be respectively identical with $R_{14}, R_8, R_9, R_{10}, R_{11},$ and R_{13} ; and R_1 to R_5 and R_8 to R_{14} may be each independently a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, or groups represented by Formulae 3a to 3h below:




formula 3a


-continued




formula 3b




formula 3c




formula 3d




formula 3e



formula 3f



formula 3g




formula 3h

[0056] In Formulae 3a to 3h above, $Z_1, Ar_{12},$ and Ar_{13} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted aryl group, or a substituted or unsubstituted C_2-C_{20} heterocyclic group; and


[0057] r is an integer from 0 to 2; p is an integer from 1 to 5; and $*$ indicates a binding site.

[0058] In some embodiments, in Formulae 1 and 2 above, $R_1, R_2, R_3, R_4, R_5,$ and R_{12} may be respectively identical with $R_{14}, R_8, R_9, R_{10}, R_{11},$ and R_{13} ; R_2 to R_5 and R_8 to R_{11} are each respectively a hydrogen atom or a deuterium atom; and $R_1,$


R_{12} , R_{13} and R_{14} are each independently a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, or groups represented by Formulae 3a to 3h below:




formula 3a




formula 3b




formula 3c



formula 3d




1




2


-continued




formula 3e



formula 3f



formula 3g



formula 3h

[0059] In Formulae 3a to 3h above, Z_1 , Ar_{12} , and Ar_{13} are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted aryl group, or a substituted or unsubstituted C_2 - C_{20} heterocyclic group; and



[0060] r is an integer from 0 to 2; p is an integer from 1 to 5; and $*$ indicates a binding site.

[0061] Examples of the heterocyclic compound of Formula 1 include, but are not limited to, Compounds 1 to 125 represented below. However, the heterocyclic compounds represented by Formula 1 are not limited thereto.

-continued



3

4





5

6



7



8



-continued



9

10




11

12




-continued


13




14




15



16






-continued



17

18



19



20



-continued



21


22



23

24






-continued



25

26



27



28



-continued



29

30











31


32



-continued




-continued





41

42





43

44





45

46




47

48




-continued


49




50




51




52









53



54




-continued




-continued


61




62




63




64



65





66



-continued



67

68







69

70





-continued



-continued



75

76



77



78



-continued



79

80




81

82




-continued





83

84





85

86



87



88



-continued



89

90





91

92





93

94



95



96




-continued

97


98




99











100



101





-continued



-continued



110

111





112

113



114



115



-continued



116

117



118



119



-continued



120

121





122

123



-continued
124

125



[0062] Hereinafter, substituents described with reference to Formulae 1 and 2 will now be described in detail. In this regard, the numbers of carbons in substituents are presented only for illustrative purposes and do not limit the characteristics of the substituents

[0063] As used herein, the term “substituted A” in the term “substituted or unsubstituted A (wherein A is an arbitrary substituent)” refers to a group A whose at least one hydrogen atom is substituted with a deuterium atom, a halogen atom, a hydroxy group, a cyano group, an amidino group, a hydrazinyl group, a carboxylic acid group or a salt derivative thereof, a sulfonic acid group or a salt derivative thereof, a phosphoric acid group or a salt derivative thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₃-C₆₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₂-C₆₀ heterocyclic group, —N(Q₁₀₁)(Q₁₀₂), or —Si(Q₁₀₃)(Q₁₀₄)(Q₁₀₅).

[0064] In particular, Q₁₀₁ to Q₁₀₅ may be each independently a hydrogen atom, a halogen atom, a hydroxy group, a cyano group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₃-C₆₀ cycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₃-C₆₀ aryloxy group, or a substituted or unsubstituted C₂-C₆₀ heterocyclic group. In this regard, the “substituted A” may include at least one substitute, wherein at least two substituents may be the same or different from each other.

[0065] In some embodiments, the “substituted A” may refer to a group A in which at least one hydrogen atom is substituted with a deuterium atom, a halogen atom, a hydroxy group, a cyano group, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₆-C₂₀ aryl group, a substituted or unsubstituted C₂-C₂₀ heterocyclic group, —N(Q₁)(Q₂), or —Si(Q₃)(Q₄)(Q₅), wherein Q₁ to Q₅ may be each independently a hydrogen atom, a halogen atom, a hydroxy group, a cyano group, a substituted or unsubstituted C₁-C₁₀ alkyl group, a substituted or unsubstituted C₁-C₁₀ alkoxy group, a substituted or unsubstituted C₆-C₂₀ aryl group, or a substituted or unsubstituted C₂-C₂₀ heterocyclic group.

[0066] In some embodiments, the “substituted A” may refer to a group A in which at least one hydrogen atoms is substituted with a deuterium atom, a halogen atom, a

[0067] As used herein, the term “unsubstituted C₁-C₆₀ alkyl group” may have a linear or branched group. Examples of the C₁-C₆₀ alkyl group include, but are not limited to, methyl, ethyl, propyl, isobutyl, sec-butyl, pentyl, iso-amyl, hexyl, and the like. Substituents of the substituted C₁-C₆₀ alkyl group are the same as those described above in conjunction with the “substituted A”.

[0068] As used herein, the unsubstituted C₂-C₆₀ alkenyl group indicates a hydrocarbon chain having at least one carbon-carbon double bond in the center or at a terminal of the unsubstituted C₂-C₆₀ alkyl group. Non-limiting examples of the unsubstituted C₂-C₆₀ alkenyl group include ethenyl, propenyl, butenyl, pentenyl, hexenyl, heptenyl, octenyl, propadienyl, isoprenyl, and allyl. Substituents of the substituted C₂-C₆₀ alkenyl group are the same as those described above in conjunction with the “substituted A”.

[0069] As used herein, the unsubstituted C₂-C₆₀ alkynyl group indicates a hydrocarbon chain having at least one carbon-carbon triple bond in the center or at a terminal of the

unsubstituted C_2-C_{60} alkyl group. An example of the unsubstituted C_2-C_{60} alkynyl group is acetylenyl. Substituents of the substituted C_2-C_{60} alkynyl group are the same as those described above in conjunction with the "substituted A".

[0070] As used herein, the unsubstituted C_1-C_{60} alkoxy group refers to a group having a structure of $-OY$ wherein Y is an unsubstituted C_1-C_{60} alkyl group as described above. Examples of the unsubstituted C_1-C_{60} alkoxy group include a methoxy group, an ethoxy group, a propoxy group, an isopropoxy group, a butoxy group, and a pentoxy group. Substituents of the substituted C_1-C_{60} alkoxy group are the same as those described above in conjunction with the "substituted A".

[0071] As used herein, the unsubstituted C_3-C_{60} cycloalkyl group indicates a cyclic saturated hydrocarbon group. Examples of the unsubstituted C_3-C_{60} cycloalkyl group include cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, and cyclooctyl. Substituents of the substituted C_1-C_{60} cycloalkyl group are the same as those described above in conjunction with the "substituted A".

[0072] As used herein, the unsubstituted C_3-C_{60} cycloalkenyl group indicates a nonaromatic, cyclic unsaturated hydrocarbon group with at least one carbon-carbon double bond. Examples of the unsubstituted C_3-C_{60} cycloalkenyl group include cyclopropenyl, cyclobutenyl, cyclopentenyl, cyclohexenyl, cycloheptenyl, 1,3-cyclohexadienyl, 1,4-cyclohexadienyl, 2,4-cycloheptadienyl, and 1,5-cyclooctadienyl. Substituents of the substituted C_3-C_{60} cycloalkenyl group are the same as those described above in conjunction with the "substituted A".

[0073] As used herein, the unsubstituted C_5-C_{60} aryl group indicates a monovalent group including a C_6-C_{60} carbocyclic aromatic system, which may be monocyclic or polycyclic. In a polycyclic group, at least two rings may be fused to each other. Examples of the unsubstituted C_5-C_{60} aryl group include phenyl, pentalenyl, indenyl, naphthyl, azulenyl, heptalenyl, indacenyl, acenaphthyl, fluorenyl, spiro-fluorenyl, phenalenyl, phenanthrenyl, anthryl, fluoranthenyl, triphenylenyl, pyrenyl, chrysenyl, naphthacenyl, picenyl, perylenyl, pentaphenyl, and hexacenyl. Substituents of the substituted C_5-C_{60} aryl group are the same as those described above in conjunction with the "substituted A".

[0074] As used herein, the unsubstituted C_5-C_{60} aryloxy group refers to a group having a structure of $-OY$, wherein Y is an unsubstituted C_5-C_{60} aryl group as described above. An example of the unsubstituted C_5-C_{60} aryloxy group is a phenoxy group. Substituents of the substituted C_5-C_{60} aryloxy group are the same as those described above in conjunction with the "substituted A".

[0075] As used herein, the unsubstituted C_5-C_{60} arylthio group refers to a group having a structure of $-SY$, wherein Y is an unsubstituted C_5-C_{60} aryl group as described above. Examples of the unsubstituted C_5-C_{60} arylthio group include a benzenethio group and a naphthylthio group. Substituents of the substituted C_5-C_{60} arylthio group are the same as those described above in conjunction with the "substituted A".

[0076] As used herein, the unsubstituted C_6-C_{60} arylene group indicates a divalent group including a C_6-C_{60} carbocyclic aromatic system, which may be monocyclic or polycyclic. Examples of the unsubstituted C_6-C_{60} arylene group may be understood from those of the unsubstituted C_6-C_{60} aryl group. Substituents of the substituted C_6-C_{60} arylene group are the same as those described above in conjunction with the "substituted A".

[0077] As used herein, the unsubstituted C_2-C_{60} heterocyclic group indicates a monocyclic or polycyclic group including at least one ring member with at least one heteroatom

selected from among N, O, P, and S. In a polycyclic group, at least two rings may be fused to each other. Examples of the unsubstituted C_2-C_{60} heterocyclic group include pyrrolyl, imidazolyl, pyrazolyl, pyridinyl, pyrazinyl, pyrimidinyl, pyridazinyl, isoindolyl, indolyl, indazolyl, purinyl, quinolinyl, benzoquinolinyl, phthalazinyl, naphthyridinyl, quinoxalinyl, quinazolinyl, cinnolinyl, carbazolyl, phenanthridinyl, acridinyl, phenanthrolinyl, phenazinyl, benzooxazolyl, benzimidazolyl, furanyl, benzofuranyl, thiophenyl, benzothiophenyl, thiazolyl, isothiazolyl, benzothiazolyl, isoxazolyl, oxazolyl, triazolyl, tetrazole, oxadiazolyl, triazinyl, and benzooxazolyl. Substituents of the substituted C_2-C_{60} heterocyclic group are the same as those described above in conjunction with the "substituted A".

[0078] As used herein, the unsubstituted C_2-C_{20} divalent heterocyclic group indicates a divalent monocyclic or polycyclic group including at least one ring with at least one heteroatom selected from among N, O, P, and S. Examples of the unsubstituted C_2-C_{20} divalent heterocyclic group may be understood from those of the unsubstituted C_2-C_{60} heterocyclic group described above. Substituents of the substituted C_2-C_{20} divalent heterocyclic group may be understood from those described above in conjunction with the "substituted A".

[0079] The heterocyclic compound of Formula 1 may be synthesized by using organic synthesis. A synthesis method of the heterocyclic compound of Formula 1 may be understood by those of ordinary skill in the art from the examples that will be described below.

[0080] The heterocyclic compound of Formula 1 may be used in an organic light-emitting device. According to another aspect of the present invention, an organic light-emitting device includes a first electrode, a second electrode disposed opposite to the first electrode, and an organic layer between the first electrode and the second electrode, wherein the first layer includes the heterocyclic compound of Formula 1 described above.

[0081] When the organic layer, including the heterocyclic compound of Formula 1, is an emission layer, the heterocyclic compound of Formula 1 may be used as a host or dopant for a fluorescence or phosphorescence device.

[0082] The organic layer may be an electron injection layer or an electron transport layer. The organic layer may be a single layer having both electron injection and electron transport functions.

[0083] In some embodiments the organic layer of the organic light-emitting device may include an emission layer, an electron injection layer, or an electron transport layer, wherein the emission layer, the electron injection layer, or the electron transport layer may include the heterocyclic compound of Formula 1 above, and the emission layer may include a known anthracene, arylamine or styryl compound.

[0084] In some embodiments the organic layer of the organic light-emitting device may include an emission layer, an electron injection layer, or an electron transport layer, wherein the emission layer, the electron injection layer, or the electron transport layer may include the heterocyclic compound of Formula 1 above, and a red, green, blue or white emission layer in the emission layer may include a known phosphorescent compound.

[0085] The first electrode may be an anode, and the second electrode may be a cathode, but the reverse is also possible.

[0086] In some embodiments, the organic light-emitting device may have a first electrode/hole injection layer/emission layer/second electrode structure, a first electrode/hole injection layer/hole transport layer/emission layer/electron transport layer/second electrode structure, or a first electrode/

hole injection layer/hole transport layer/emission layer/electron transport layer/electron injection layer/second electrode structure. In some other embodiments, the organic light-emitting device may have a first electrode/single layer having both hole injection and hole transport capabilities/emission layer/electron transport layer/second electrode structure, or a first electrode/single layer having both hole injection and hole transport capabilities/emission layer/electron transport layer/electron injection layer/second electrode structure. Alternatively, the organic light-emitting device may have a first electrode/hole transport layer/emission layer/single layer having both electron injection and electron transport capabilities/second electrode structure, a first electrode/hole injection layer/emission layer/single layer having both electron injection and electron transport capabilities/second electrode structure, or a first electrode/hole injection layer/hole transport layer/emission layer/single layer having both electron injection and electron transport capabilities/second electrode structure.

[0087] According to some embodiments of the present invention, the organic light-emitting device may be either a top-emission organic light-emitting device or a bottom-emission organic light-emitting device.

[0088] Hereinafter, a method of manufacturing an organic light-emitting device according to an embodiment of the present invention will be described with reference to FIG. 1. FIG. 1 illustrates the structure of an organic light-emitting device according to an embodiment of the present invention. Referring to FIG. 1, the organic light-emitting device according to the present embodiment includes a substrate (not shown), a first electrode (anode), a hole injection layer (HIL), a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), an electron injection layer (EIL), and a second electrode (cathode).

[0089] The substrate may be any substrate that is used in conventional organic light emitting devices. In some embodiments the substrate may be a glass substrate or a transparent plastic substrate with strong mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0090] The first electrode may be formed by depositing or sputtering a first electrode-forming material on the substrate. When the first electrode constitutes an anode, a material having a high work function may be used as the first electrode-forming material to facilitate hole injection. The first electrode may be a reflective electrode or a transmission electrode. Suitable first electrode-forming materials include transparent and conductive materials such as ITO, IZO, SnO₂, and ZnO. The first electrode may be formed as a reflective electrode using magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or the like. The first electrode may include two different materials. The first electrode may have any of various structures, and in some embodiments, may have a double-layer structure including two different materials.

[0091] An organic layer(s) is formed on the first electrode. The term "organic layer" used herein indicates any layer interposed between the first electrode and the second electrode. The organic layer may not be formed of pure organic materials, and may also include a metal complex.

[0092] The organic layer may include a first layer including the heterocyclic compound of Formula 1. The organic layer


may further include at least one of a HIL, a HTL, an EML, a hole blocking layer (HBL), an ETL and an EIL. The first layer may include an emission layer.

[0093] Next, the HIL may be formed on the first electrode by using any of a variety of methods, and in some embodiments, by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, or the like.

[0094] When the HIL is formed using vacuum deposition, vacuum deposition conditions may vary according to the compound that is used to form the HIL, and the desired structure and thermal properties of the HIL to be formed. For example, vacuum deposition may be performed at a temperature of about 100° C. to about 500° C., a pressure of about 10⁻⁸ torr to about 10⁻³ torr, and a deposition rate of about 0.01 to about 100 Å/sec. However, the deposition conditions are not limited thereto.


[0095] When the HIL is formed using spin coating, the coating conditions may vary according to the compound that is used to form the HIL, and the desired structure and thermal properties of the HIL to be formed. For example, the coating rate may be in the range of about 2000 rpm to about 5000 rpm, and a temperature at which heat treatment is performed to remove a solvent after coating may be in the range of about 80° C. to about 200° C. However, the coating conditions are not limited thereto.

[0096] The HIL may be formed of any hole-injecting material that is known in the art. Non-limiting examples of suitable hole-injecting materials include a phthalocyanine compound such as copperphthalocyanine, 4,4',4"-tris (3-methylphenylphenylamino) triphenylamine (m-MTDATA; see the formula below), TDATA (see the formula below), 2-TNATA (see formula below), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), and polyaniline/poly(4-styrenesulfonate) (PANI/PSS).



m-MTDATA


-continued




TDATA

tions for deposition and coating may be similar to those for the formation of the HIL, though the conditions for the deposition and coating may vary according to the material that is used to form the HTL.


[0099] Any known hole-transporting material, for example, TPD (see the formula below), or NPB (see the formula below), may be used to form the HTL.



TPD



NPB



2-TNATA


[0097] The thickness of the HIL may be from about 100 Å to about 10000 Å, and in some embodiments, may be from about 100 Å to about 1000 Å. When the thickness of the HIL is within these ranges, the HIL may have good hole injecting ability without a substantial increase in driving voltage.

[0098] Next, the HTL may be formed on the HIL using various methods, for example, vacuum deposition, spin coating, casting, LB deposition, or the like. When the HTL is formed using vacuum deposition or spin coating, the condi-



[0100] The thickness of the HTL may be from about 50 Å to about 1000 Å, and in some embodiments, may be from about 100 Å to about 800 Å. When the thickness of the HTL is within these ranges, the HTL may have good hole transporting ability without a substantial increase in driving voltage.

[0101] Then, the EML may be formed on the HTL by using vacuum deposition, spin coating, casting, LB deposition, or the like. When the EML is formed using vacuum deposition or spin coating, the deposition and coating conditions may be similar to those for the formation of the HIL, though the conditions for deposition and coating may vary according to the material that is used to form the EML.



[0102] The EML may include the heterocyclic compound represented by Formula 1 above as a host or a dopant. In some embodiments the EML may further include a known host or dopant, in addition to the heterocyclic compound of Formula 1 above. Non-limiting examples of suitable hosts include 4,4'-N,N'-dicarbazole-biphenyl (CPB), ADN (see the formula below), TPBI (see the formula below), TBADN (see the formula below), and E3 (see the formula below).




[0103] Non-limiting examples of suitable red dopants include PtOEP (see the formula below), Ir(piq)₃ (see the formula below), and Btp₂Ir(acac) (see the formula below).






[0104] Non-limiting examples of suitable green dopants include Ir(ppy)₃ (ppy=phenylpyridine, see the formula below), Ir(ppy)₂(acac) (see the formula below), and Ir(m-ppy)₃ (see the formula below).






[0105] Non-limiting examples of suitable blue dopants include F_2Irpic (see the formula below), $(\text{F}_2\text{ppy})_2\text{Ir(tmd)}$ (see the formula below), Ir(dfppz)_3 (see the formula below), DPVBi (see the formula below), 4,4'-bis(4-diphenylaminostyryl)biphenyl (DPAVBi, see the formula below), and 2,5,8,11-tetra-tert-butyl perylene (TBPe, see the formula below).



-continued





[0106] If the emission layer includes both a host and a dopant, the amount of the dopant may be from about 0.01 to about 15 parts by weight based on 100 parts by weight of the host. However, the amount of the dopant is not limited to this range.

[0107] The thickness of the EML may be from about 100 Å to about 1000 Å, and in some embodiments, may be from about 200 Å to about 600 Å. When the thickness of the EML is within these ranges, the EML may have good light emitting ability without a substantial increase in driving voltage.

[0108] When the EML further includes a phosphorescent dopant, a HBL may be formed between the HTL and the EML by using vacuum deposition, spin coating, casting, LB deposition, or the like, to prevent diffusion of triplet excitons or holes into an ETL. When the HBL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL, though the conditions for deposition and coating may vary according to the material that is used to form the HBL. Any known hole-blocking material may be used. Non-limiting examples of hole-blocking materials include an oxadiazole derivative, a triazole derivative, and a phenanthroline derivative.

[0109] The thickness of the HBL may be from about 50 Å to about 1000 Å, and in some embodiments, may be from about 100 Å to about 300 Å. When the thickness of the HBL is within these ranges, the HBL may have a good hole blocking ability without a substantial increase in driving voltage.

[0110] Then, an ETL may be formed on the HBL or EML by vacuum deposition, spin coating, casting, or the like. When the ETL is formed using vacuum deposition or spin coating, the deposition or coating conditions may be similar to those applied to form the HIL, though the deposition or coating conditions may vary according to the material that is used to form the ETL. Electron-transporting materials for the ETL should be able to stably transport electrons injected from an electron injecting electrode (cathode). An example of electron-transporting materials is the heterocyclic compound of Formula 1 above. In some other embodiments any known electron-transporting material may be used. Non-limiting examples of suitable electron-transporting materials for the ETL include a quinoline derivative, such as tris(8-quinolinolate)aluminum (Alq3), TAZ (see the formula below), BAlq (see the formula below), and beryllium bis(benzoquinolinolate) (Bebq₂).



[0111] The thickness of the ETL may be from about 100□ to about 1,000□, and in some embodiments, may be from about 150□ to about 500□. When the thickness of the ETL is within these ranges, the ETL may have satisfactory electron transporting ability without a substantial increase in driving voltage.

[0112] Then, an EIL, which facilitates injection of electrons from the cathode, may be formed on the ETL. Any suitable electron-injecting material may be used to form the EIL.

[0113] Examples of electron-injecting materials for the EIL include LiF, NaCl, CsF, Li₂O, and BaO, which are known in the art. The deposition and coating conditions for forming the EIL may be similar to those for the formation of the HIL, though the deposition and coating conditions may vary according to the material that is used to form the EIL.

[0114] The thickness of the EIL may be from about 1 Å to about 100 Å, and in some embodiments, may be from about 3 Å to about 90 Å. When the thickness of the EIL is within these ranges, the EIL may have satisfactory electron injection ability without a substantial increase in driving voltage.

[0115] Finally, the second electrode, which may be a transmission electrode, is disposed on the organic layer. The second electrode may be a cathode, which is an electron injection electrode. A material for forming the second electrode may be a metal, an alloy, an electro-conductive compound, which have a low work function, or a mixture thereof. In this regard, the second electrode may be formed of lithium (Li), magnesium (Mg), aluminum (Al), aluminum (Al)-lithium (Li), calcium (Ca), magnesium (Mg)-indium (In), magnesium (Mg)-silver (Ag), or the like, and may be formed as a thin film type transmission electrode. In some embodiments, to manufacture a top-emission light-emitting device, the transmission electrode may be formed of indium tin oxide (ITO) or indium zinc oxide (IZO).

[0116] According to embodiments of the present invention, the organic light-emitting device may be included in various types of flat panel display devices, such as in a passive matrix organic light-emitting display device, in an active matrix organic light-emitting display device, or in a double-screen flat display device. In particular, when the organic light-emitting device is included in an active matrix organic light-emitting display device including a thin-film transistor, the first electrode on the substrate may function as a pixel electrode, electrically connected to a source electrode or a drain electrode of the thin-film transistor.

[0117] According to embodiments of the present invention, the organic light-emitting device may include a plurality of organic layers, wherein at least one of the organic layers may be formed of the heterocyclic compound of Formula 1 by using a deposition method or a wet method of coating a solution of the heterocyclic compound of Formula 1.






[0118] Hereinafter, the present invention will be described in detail with reference to the following synthesis examples and other examples. However, these examples are for illustrative purposes only and are not intended to limit the scope of the present invention.


EXAMPLES

Synthesis Example 1

Synthesis of Compound 7

[0119]





Synthesis of Intermediate I-1

[0120] 3.07 g (10.0 mmol) of 6-bromochrysene, 2.54 g (10.0 mmol) of bis(pinacolato)diborane, 0.36 g (0.5 mmol) of [1,1'-bis(diphenylphosphino)ferrocene]dichloro palladium (II) (hereinafter, PdCl₂(dppf)₂), and 2.94 g (30.0 mmol) of KOAc were dissolved in 40 mL of dimethylsulfoxide (DMSO) to obtain a solution, which was then stirred at about 80° C. for about 6 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 50 mL of water and 50 mL of diethylether. The organic phase was collected, and was dried using magnesium sulfate to

evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 3.01 g of Intermediate I-1 (Yield: 85%) This compound was identified using liquid chromatography-mass spectroscopy (LC-MS). C₂₄H₂₃BO₂: M+354.2

Synthesis of Intermediate I-2

[0121] 7.08 g (20.0 mmol) of Intermediate I-1, 4.04 g (20.0 mmol) of 2-bromonitrobenzene, 1.15 g (1.0 mmol) of tetrakis triphenylphosphine palladium (Pd(PPh₃)₄), and 8.29 g (60.0 mmol) of K₂CO₃ were dissolved in 60 mL of a mixed tetrahydrofuran (THF) and H₂O (2:1) solution to obtain a solution, which was then stirred at about 70° C. for about 5 hours. The reaction solution was cooled to room temperature, and 40 mL of water was added thereto, followed by extraction three times with 50 mL of ethylether. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 6.22 g of Intermediate I-2 (Yield: 89%) This compound was identified using LC-MS. C₂₄H₁₅NO₂: M+349.1

Synthesis of Intermediate I-3

[0122] 3.49 g (10.0 mmol) of Intermediate I-2 and 5.77 g (22 mmol) of triphenylphosphine (PPh₃) were dissolved in 30 mL of 1,2-dichlorobenzene to obtain a solution, which was then stirred at about 170° C. for about 12 hours. The reaction solution was cooled to room temperature, and the solvent was removed therefrom under vacuum conditions, followed by extraction three times with 50 mL of water and 50 mL of dichloromethane. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.35 g of Intermediate I-3 (Yield: 74%) This compound was identified using LC-MS. C₂₄H₁₅N: M+317.1

Synthesis of Intermediate I-4

[0123] 4.76 g (15.0 mmol) of Intermediate I-3 was dissolved in 100 mL of dichloromethane to obtain a solution, and 1.75 mL (15.0 mmol) of bromine (Br₂) was slowly dropwise added to the solution at about 0° C. to obtain a reaction solution. The reaction solution was stirred at about 0° C. for about 3 hours. 60 mL of water and 30 mL of a 20% aqueous thiosodium sulfate solution were added to the reaction solution, followed by extraction three times with 80 mL of dichloromethane. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified by silica gel column chromatography, followed by recrystallization with a dichloromethane/hexane solution to obtain 3.80 g of Intermediate I-4 (Yield 64%). This compound was identified using LC-MS. C₂₄H₁₄BrN: M+395.0

Synthesis of Intermediate I-5

[0124] 3.96 g (10.0 mmol) of Intermediate I-4, 3.06 g (15.0 mmol) of iodobenzene, 0.19 g (1.0 mmol) of CuI, 0.05 g (0.2 mmol) of 18-Crown-6, and 4.15 g (30.0 mmol) of K₂CO₃ were dissolved in 30 mL of 1,3-dimethyl-3,4,5,6-tetrahydro-2(1H)-pyrimidinone (DMPU) to obtain a solution, which was then stirred at about 170° C. for about 12 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 50 mL of water and 50 mL of dichloromethane. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The resi-

due was separated and purified using silica gel column chromatography to obtain 4.29 g of Intermediate I-5 (Yield: 91%) This compound was identified using LC-MS. $C_{30}H_{16}BrN$: M+471.1

Synthesis of Intermediate I-6

[0125] 4.72 g (10.0 mmol) of Intermediate I-5, 2.54 g (10.0 mmol) of bis(pinacolato)diborane, 0.36 g (0.5 mmol) of [1,1'-bis(diphenylphosphino)ferrocene]dichloro palladium (II) (hereinafter, $PdCl_2(dppf)_2$), and 2.94 g (30.0 mmol) of KOAc were dissolved in 40 mL of DMSO to obtain a solution, which was then stirred at about 80° C. for about 6 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 50 mL of water and 50 mL of diethyl-ether. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 4.10 g of Intermediate I-6 (Yield: 79%) This compound was identified using LC-MS. $C_{36}H_{30}BNO_2$: M+519.2

Synthesis of Compound 7

[0126] 2.59 g (5.0 mmol) of Intermediate I-6, 1.34 g (5.0 mmol) of 2-chloro-4,6-diphenyl[1,3,5]-triazine, 0.29 g (0.25 mmol) of $Pd(PPh_3)_4$, and 2.07 g (15.0 mmol) of K_2CO_3 were dissolved in 30 mL of a mixed solution THF/ H_2O (2:1) to obtain a solution, which was then stirred at about 70° C. for about 5 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 50 mL of water and 50 mL of diethylether. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.24 g of Compound 7 (Yield: 72%) This compound was identified using LC-MS and nuclear magnetic resonance (NMR). $C_{45}H_{28}N_4$: M+624.2




[0127] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.31 (s, 1H), 9.01-8.98 (m, 1H), 8.83 (d, 1H), 8.67-8.63 (m, 4H), 8.52 (d, 1H), 8.43-8.40 (m, 1H), 8.20 (d, 1H), 7.71-7.61 (m, 3H), 7.51-7.25 (m, 13H), 6.84-6.79 (m, 2H)

Synthesis Example 2

Synthesis of Compound 8

[0128]

I-4 \longrightarrow



Synthesis of Intermediate I-7

[0129] 5.29 g of Intermediate I-7 was synthesized from Intermediate I-4 and 2-bromo-9,9-dimethylfluorene in the same manner as in the synthesis of Intermediate I-5 (Yield: 90%). This compound was identified using LC-MS. $C_{39}H_{26}BrN$: M+587.1

Synthesis of Intermediate I-8

[0130] 4.64 g of Intermediate I-8 was synthesized from Intermediate I-7 in the same manner as in the synthesis of Intermediate I-6 (Yield: 73%). This compound was identified using LC-MS. $C_{45}H_{38}BNO_2$: M+635.3

Synthesis of Compound 8

[0131] 2.78 g of Compound 8 was synthesized from Intermediate I-8 in the same manner as in the synthesis of Compound 7 (Yield: 75%). This compound was identified using LC-MS and NMR. $C_{54}H_{36}N_4$: M+740.3



[0132] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.30 (s, 1H), 9.01-8.98 (m, 1H), 8.83 (dd, 1H), 8.67-8.63 (m, 4H), 8.52 (d, 1H), 8.43-8.40 (m, 1H), 8.20 (dd, 1H), 7.82-7.80 (m, 1H),

7.69-7.58 (m, 4H), 7.52 (m, 1H), 7.46-7.21 (m, 9H), 6.95 (dt, 1H), 6.85-6.77 (m, 2H), 6.67-6.66 (m, 1H), 6.38 (dd, 1H), 1.84 (s, 6H)

Synthesis Example 3

Synthesis of Compound 13

[0133]



13


[0134] 3.58 g of Compound 13 was synthesized from Intermediate I-8 and Intermediate I-9, synthesized using a known method, in the same manner as in the synthesis of Compound 8 (Yield: 92%). This compound was identified using LC-MS and NMR. $C_{58}H_{39}N_3$: M^+ 777.3

[0135] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.00 (d, 1H), 8.83 (d, 1H), 8.70 (s, 1H), 8.52 (d, 1H), 8.20 (dd, 1H), 8.17-8.13 (m, 2H), 7.81 (d, 1H), 7.73-7.59 (m, 4H), 7.53-7.36 (m, 8H), 7.35-7.12 (m, 8H), 6.95 (dt, 1H), 6.85-6.76 (m, 2H), 6.67-6.65 (m, 1H), 6.39-6.35 (m, 1H), 1.83 (s, 6H)

Synthesis Example 4

Synthesis of Compound 29

[0136]




[0137] 2.94 g of Compound 29 was synthesized from Intermediate I-6 and Intermediate I-10, synthesized using a known method, in the same manner as in the synthesis of Compound 13 (Yield: 83%). This compound was identified using


[0138] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.99 (d, 1H), 8.89 (s, 1H), 8.73 (d, 1H), 8.42 (dd, 1H), 8.18 (dd, 1H), 7.83-7.66 (m, 3H), 7.62-7.52 (m, 5H), 7.46-7.32 (m, 5H), 6.96-6.89 (m, 2H), 6.74-6.58 (m, 8H)

Synthesis Example 5

Synthesis of Compound 37

[0139]





Synthesis of Intermediate I-11

[0140] 2.68 g (10 mmol) of 2-chloro-4,6-diphenyl-[1,3,5]-triazine, 3.00 g (15.0 mmol) of 4-bromophenyl-1-boronic acid, 0.58 g (0.5 mmol) of Pd(PPh₃)₄, and 4.14 g (30.0 mmol) of K₂CO₃ were dissolved in 60 mL of a mixed solution THF/H₂O (2:1) to obtain a solution, which was then stirred at about 70° C. for about 5 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 60 mL of water and 60 mL of diethylether. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.56 g of Intermediate I-11 (Yield: 66%) This compound was identified using LC-MS. C₂₁H₁₄BrN₃; M+387.0

Synthesis of Compound 37


[0141] 1.59 g (5 mmol) of Intermediate I-3, 2.14 g (1.5 mmol) of Intermediate I-11, 0.08 g (0.5 mmol) of CuI, 0.025 g (0.1 mmol) of 18-Crown-6, and 2.07 g (30.0 mmol) of K₂CO₃ were dissolved in 30 mL of 1,3-dimethyl-3,4,5,6-tetrahydro-2(1H)-pyrimidinone (DMPU) to obtain a solution, which was then stirred at about 170° C. for about 12 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 50 mL of water and 50 mL of dichloromethane. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.72 g of Compound 37 (Yield: 81%) This compound was identified using LC-MS and NMR. C₄₅H₂₈N₄; M+624.2

[0142] ¹H NMR (CDCl₃, 400 MHz) δ (ppm) 9.08 (d, 1H), 8.81 (d, 1H), 8.70-8.63 (m, 7H), 8.56 (dd, 1H), 8.25 (m, 1H),


8.05 (d, 1H), 7.82 (m, 1H), 7.68 (dt, 1H), 7.63 (dt, 1H), 7.52-7.25 (m, 9H), 6.89-6.79 (m, 4H)

Synthesis Example 6 Synthesis of Compound 64

[0143]



-continued



Synthesis of Intermediate I-12

[0144] 2.66 g of Intermediate I-12 was synthesized from Intermediate I-1 and 2,4-dibromo-1-nitrobenzene in the same manner as in the synthesis of Intermediate I-2 (Yield: 62%). This compound was identified using LC-MS. $C_{24}H_{14}BrNO_2$: $M+427.0$

Synthesis of Intermediate I-13

[0145] 3.25 g of Intermediate I-13 was synthesized from Intermediate I-12 in the same manner as in the synthesis of Intermediate I-3 (Yield: 82%). This compound was identified using LC-MS. $C_{24}H_{14}BrN$: $M+395.0$

Synthesis of Intermediate I-14

[0146] 4.20 g of Intermediate I-14 was synthesized from Intermediate I-13 in the same manner as in the synthesis of Intermediate I-5 (Yield: 89%). This compound was identified using LC-MS. $C_{30}H_{18}BrN$: $M+471.1$

Synthesis of Intermediate I-15

[0147] 3.95 g of Intermediate I-15 was synthesized from Intermediate I-14 in the same manner as in the synthesis of Intermediate I-6 (Yield: 76%). This compound was identified using LC-MS. $C_{36}H_{30}BNO_2$: $M+519.2$

Synthesis of Compound 64

[0148] 2.75 g of Compound 64 was synthesized from Intermediate I-9 and Intermediate I-15 in the same manner as in the synthesis of Compound 29 (Yield: 83%). This compound was identified using LC-MS and NMR. $C_{49}H_{31}N_3$: $M+661.3$

[0149] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.06 (d, 1H), 8.78 (d, 1H), 8.63 (d, 1H), 8.49 (d, 1H), 8.19-8.16 (m, 2H),

8.03 (d, 1H), 7.91 (d, 1H), 7.82 (dd, 1H), 7.75-7.59 (m, 3H), 7.51-7.23 (m, 16H), 7.17-7.11 (m, 1H), 7.00-6.97 (m, 1H), 6.88 (dt, 1H)

Synthesis Example 7


Synthesis of Compound 65

[0150] 2.25 g of Compound 65 was synthesized from Intermediate I-15 and 2-chloro-4,6-diphenyl[1,3,5]-triazine in the same manner as in the synthesis of Compound 64 (Yield: 72%). This compound was identified using LC-MS and NMR. $C_{45}H_{28}N_4$: $M+624.2$

[0151] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.03 (d, 1H), 8.82-8.76 (m, 2H), 8.68-8.53 (m, 6H), 8.48 (d, 1H), 8.46-8.43 (m, 1H), 8.07 (d, 1H), 7.85-7.82 (m, 1H), 7.78 (dt, 1H), 7.64-7.60 (m, 1H), 7.49-7.31 (m, 12H), 6.96 (dt, 1H)

Synthesis Example 8

Synthesis of Compound 68

[0152]

[0153] 2.15 g of Compound 68 was synthesized from Intermediate I-15 and Intermediate I-17 (2-chloro-4,6-diphenylpyrimidine) in the same manner as in the synthesis of Compound 64 (Yield: 69%). This compound was identified using LC-MS and NMR. $C_{46}H_{29}N_3$: $M+623.2$


[0154] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.96 (d, 1H), 8.78 (d, 1H), 8.59 (dt, 2H), 8.49-8.43 (m, 2H), 8.32-8.30 (m,

1H), 8.10 (d, 1H), 7.99-7.92 (m, 6H), 7.82 (dd, 1H), 7.76 (s, 1H), 7.68-7.60 (m, 2H), 7.54-7.46 (m, 5H), 7.39-7.30 (m, 5H), 6.87 (dt, 1H)


Synthesis Example 9

Synthesis of Compound 69

[0155]



-continued



Synthesis of Intermediate I-16

[0156] 6.14 g (20.0 mmol) of bromochrysene. 2.68 g (22.0 mmol) of 1-phenylboronic acid, 1.15 g (1.0 mmol) of $\text{Pd}(\text{PPh}_3)_4$, and 4.29 g (60.0 mmol) of K_2CO_3 were dissolved in 100 mL of a mixed THF/ H_2O (2:1) solution to obtain a solution, which was then stirred at about 70° C. for about 5 hours. The reaction solution was cooled to room temperature, followed by extraction three times with 100 mL of water and 100 mL of diethylether. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 5.66 g of Intermediate I-16 (Yield: 93%). This compound was identified using LC-MS. $\text{C}_{24}\text{H}_{16}$: M+304.1

Synthesis of Intermediate I-17

[0157] 2.34 g of Intermediate I-17 was synthesized from Intermediate I-16 and Br_2 in the same manner as in the synthesis of Intermediate I-4 (Yield: 61%). This compound was identified using LC-MS. $\text{C}_{24}\text{H}_{15}\text{Br}$: M+382.0

Synthesis of Intermediate I-18

[0158] 3.23 g of Intermediate I-12 was synthesized from Intermediate I-17 and 2,4-dibromo-1-nitrobenzene in the same manner as in the synthesis of Intermediate I-12 (Yield: 64%). This compound was identified using LC-MS. $\text{C}_{30}\text{H}_{18}\text{BrNO}_2$: M+503.1

Synthesis of Intermediate I-19

[0159] 4.06 g of Intermediate I-19 was synthesized from Intermediate I-18 in the same manner as in the synthesis of

Intermediate I-13 (Yield: 86%). This compound was identified using LC-MS. $\text{C}_{30}\text{H}_{18}\text{BrN}$: M+471.1

Synthesis of Intermediate I-20

[0160] 4.88 g of Intermediate I-20 was synthesized from Intermediate I-19 in the same manner as in the synthesis of Intermediate I-14 (Yield: 89%). This compound was identified using LC-MS. $\text{C}_{36}\text{H}_{22}\text{BrN}$: M+547.1

Synthesis of Intermediate I-21

[0161] 4.70 g of Intermediate I-21 was synthesized from Intermediate I-20 in the same manner as in the synthesis of Intermediate I-15 (Yield: 79%). This compound was identified using LC-MS. $\text{C}_{42}\text{H}_{34}\text{BrNO}_2$: M+595.3


Synthesis of Compound 69




[0162] 2.33 g of Compound 69 was synthesized from Intermediate I-21 and 2-bromo-5-phenyl[1,3,4]-oxadiazole in the same manner as in the synthesis of Compound 64 (Yield: 76%). This compound was identified using LC-MS and NMR. $\text{C}_{44}\text{H}_{27}\text{N}_3\text{O}$: M+613.2

[0163] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.99 (d, 1H), 8.75 (s, 1H), 8.70 (d, 1H), 8.47 (d, 1H), 8.31-8.26 (m, 2H), 8.22 (s, 1H), 8.15-8.09 (m, 2H), 7.72-7.62 (m, 4H), 7.56-7.42 (m, 10H), 7.38-7.31 (m, 3H), 6.84 (dt, 1H)

Synthesis Example 10

Synthesis of Compound 79

[0164]



Synthesis of Intermediate I-22

[0165] 5.74 g of Intermediate I-22 was synthesized from Intermediate I-1 and 1,4-dibromo-2-nitrobenzene in the same manner as in the synthesis of Intermediate I-18 (Yield: 67%). This compound was identified using LC-MS. $C_{24}H_{14}BrNO_2$: M+427.0

Synthesis of Intermediate I-23

[0166] 3.53 g of Intermediate I-23 was synthesized from Intermediate I-22 in the same manner as in the synthesis of Intermediate I-19 (Yield: 89%). This compound was identified using LC-MS. $C_{24}H_{14}BrN$: M+395.0

Synthesis of Intermediate I-24

[0167] 4.29 g of Intermediate I-24 was synthesized from Intermediate I-23 in the same manner as in the synthesis of Intermediate I-20 (Yield: 91%). This compound was identified using LC-MS. $C_{30}H_{18}BrN$: M+471.1

Synthesis of Intermediate I-25

[0168] 3.95 g of Intermediate I-25 was synthesized from Intermediate I-24 in the same manner as in the synthesis of Intermediate I-21 (Yield: 76%). This compound was identified using LC-MS. $C_{36}H_{30}BNO_2$: M+519.2

Synthesis of Compound 79


[0169] 2.25 g of Compound 79 was synthesized from Intermediate I-25 and 2-chloro-4,6-diphenyl-[1,3,5]-triazine in the same manner as in the synthesis of Compound 69 (Yield: 72%). This compound was identified using LC-MS and NMR. $C_{45}H_{28}N_4$: M+624.2


[0170] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 9.06 (d, 1H), 8.84 (d, 1H), 8.65 (d, 5H), 8.56 (d, 1H), 8.35-8.33 (m, 2H), 8.23 (d, 1H), 8.01 (d, 1H), 7.85 (dd, 1H), 7.66 (dt, 1H), 7.59 (dt, 1H), 7.48-7.27 (m, 12H), 6.83 (dt, 1H)

Synthesis Example 11

Synthesis of Compound 86

[0171]





Synthesis of Intermediate I-26

[0172] 3.86 g (10.0 mmol) of 6,12-dibromochrysene was dissolved in 30 mL of THF and then 8 mL of *n*-butyllithium (*n*-BuLi, 2.5M in hexane) was slowly added thereto at a temperature of -78°C . to obtain a solution, which was then stirred at the same temperature for about 1 hour. Then, 2.78 mL (25 mmol) of $\text{B}(\text{OMe})_3$ was slowly added thereto. The temperature was slowly raised to room temperature, followed by further stirring for about 3 hours. After the reaction was completed, 20 mL of a 10% HCl aqueous solution was added,

followed by extraction three times with 30 mL of EtOAc and 40 mL of water. The organic phase was collected and was dried using magnesium sulfate to evaporate the solvent. The residue was recrystallized using diethylether to obtain 2.67 g of Intermediate I-26 (Yield: 79%) This compound was identified using LC-MS. $\text{C}_{18}\text{H}_{14}\text{B}_4\text{O}_4$; $\text{M}+338.1$

Synthesis of Intermediate I-27

[0173] 3.86 g of Intermediate I-27 was synthesized from Intermediate I-26 and 2-bromonitrobenzene in the same manner as in the synthesis of Intermediate I-2 (Yield: 82%). This compound was identified using LC-MS. $\text{C}_{30}\text{H}_{18}\text{N}_2\text{O}_4$; $\text{M}+470.1$

Synthesis of Intermediate I-28

[0174] 2.97 g of Intermediate I-28 was synthesized from Intermediate I-27 in the same manner as in the synthesis of Intermediate I-3 (Yield: 73%). This compound was identified using LC-MS. $\text{C}_{30}\text{H}_{16}\text{N}_2$; $\text{M}+406.1$

Synthesis of Compound 86

[0175] 2.43 g of Compound 86 was synthesized from Intermediate I-28 in the same manner as in the synthesis of Intermediate I-5 (Yield: 87%). This compound was identified using LC-MS and NMR. $\text{C}_{42}\text{H}_{26}\text{N}_2$; $\text{M}+558.2$

[0176] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.66-8.60 (m, 2H), 8.22 (dd, 2H), 8.01-7.97 (m, 2H), 7.63-7.40 (m, 8H), 7.38-7.23 (m, 6H), 7.03-6.83 (m, 5H), 6.82-6.78 (m, 1H)

Synthesis Example 12

Synthesis of Compound 94

[0177] 3.19 g of Compound 94 was synthesized from Intermediate I-28 and 9-bromophenanthrene in the same manner as in the synthesis of Compound 86 (Yield: 84%). This compound was identified using LC-MS and NMR. $\text{C}_{58}\text{H}_{34}\text{N}_2$; $\text{M}+758.3$

[0178] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.67-8.60 (m, 4H), 8.47 (d, 2H), 8.36-8.33 (m, 2H), 8.19 (dd, 2H), 8.07 (s, 2H), 8.01-7.97 (m, 2H), 7.68-7.55 (m, 6H), 7.48 (dt, 2H), 7.41 (dt, 2H), 7.35-7.22 (m, 4H), 6.95-6.82 (m, 4H), 6.80-6.76 (m, 2H)

Synthesis Example 13

Synthesis of Compound 99

[0179] 3.32 g of Compound 99 was synthesized from Intermediate I-28 and 2-bromo-9,9-dimethylfluorene in the same manner as in the synthesis of Compound 86 (Yield: 84%). This compound was identified using LC-MS and NMR. $\text{C}_{60}\text{H}_{42}\text{N}_2$; $\text{M}+790.3$

[0180] ^1H NMR (CDCl_3 , 400 MHz) δ (ppm) 8.66-8.61 (m, 2H), 8.22-8.18 (m, 2H), 8.03-7.99 (m, 2H), 7.83-7.78 (m, 2H), 7.60 (d, 2H), 7.54 (dd, 2H), 7.37-7.19 (m, 6H), 6.99-6.83 (m, 6H), 6.78 (dd, 2H), 6.68 (dd, 2H), 6.38 (dd, 2H), 1.82 (s, 12H)

Synthesis Example 14

Synthesis of Compound 107

[0181] 3.35 g of Compound 107 was synthesized from Intermediate I-28 and 4-bromotriphenylamine in the same

manner as in the synthesis of Compound 86 (Yield: 75%). This compound was identified using LC-MS and NMR. $C_{66}H_{44}N_4$: M+892.4

[0182] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.58 (dd, 2H), 8.18 (dd, 2H), 7.96 (dd, 2H), 7.80-7.76 (m, 4H), 7.42-7.28 (m, 12H), 6.98-7.82 (m, 6H), 6.68 (dt, 4H), 6.43 (d, 4H), 6.22 (dd, 8H)

Synthesis Example 15

Synthesis of Compound 109

[0183] 3.30 g of Compound 109 was synthesized from Intermediate I-28 and 4-bromophenyl-2-fluorophenyl-*o*-tolylamine in the same manner as in the synthesis of Compound 86 (Yield: 69%). This compound was identified using LC-MS and NMR. $C_{68}H_{46}F_2N_4$: M+956.4

[0184] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.62 (dd, 2H), 8.24 (dd, 2H), 7.99 (dd, 2H), 7.78 (d, 4H), 7.38-6.90 (m, 20H), 6.86 (d, 2H), 6.68 (dd, 2H), 6.32 (d, 4H), 6.21 (dt, 2H), 2.01 (s, 6H)

Synthesis Example 16

Synthesis of Compound 116


[0185] 2.91 g of Compound 116 was synthesized from Intermediate I-28 and 4-bromophenyl-4-pyridinyl-*o*-tolylamine in the same manner as in the synthesis of Compound 86 (Yield: 63%). This compound was identified using LC-MS and NMR. $C_{66}H_{46}N_6$: M+922.4


[0186] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.62 (dd, 2H), 8.23 (dd, 2H), 8.15-8.11 (m, 4H), 7.99 (dd, 2H), 7.81-7.74 (m, 4H), 7.42-7.22 (m, 6H), 7.17 (dt, 2H), 7.03-6.86 (m, 6H), 6.82 (dd, 2H), 6.72 (dd, 4H), 6.62 (d, 2H), 6.41-6.30 (m, 4H), 2.00 (6H)

Synthesis Example 17

Synthesis of Compound 119

[0187]





Synthesis of Intermediate I-29

[0188] 4.02 g of Intermediate I-29 was synthesized from Intermediate I-26 and 2,4-dibromo-1-nitrobenzene in the same manner as in the synthesis of Intermediate I-27 (Yield: 64%). This compound was identified using LC-MS. $C_{30}H_{16}Br_2N_2O_4$: M+625.9

Synthesis of Intermediate I-30

[0189] 4.34 g of Intermediate I-30 was synthesized from Intermediate I-29 in the same manner as in the synthesis of Intermediate I-28 (Yield: 77%). This compound was identified using LC-MS. $C_{30}H_{16}Br_2N_2$: M+562.0

Synthesis of Intermediate I-31

[0190] 6.09 g of Intermediate I-31 was synthesized from Intermediate I-30 in the same manner as in the synthesis of Compound 86 (Yield: 85%). This compound was identified using LC-MS. $C_{42}H_{24}Br_2N_2$: M+714.0

Synthesis of Compound 119

[0191] 3.58 g (5.0 mmol) of Intermediate I-31, 1.31 g (5.5 mmol) of 9,9-dimethylfluorene-2-boronic acid, 0.29 g (0.25 mmol) of $Pd(PPh_3)_4$, and 2.07 g (15.0 mmol) of K_2CO_3 were dissolved in 30 mL of a mixed solution THF/ H_2O (2:1) to obtain a solution, which was then stirred at about 70° C. for about 5 hours. The reaction solution was cooled to room temperature, and 30 mL of water was added thereto, followed by extraction three times with 30 mL of ethylether. The organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 3.44 g of Compound 119 (Yield: 73%) This compound was identified using LC-MS and NMR. $C_{72}H_{50}N_2$: M+942.4


[0192] 1H NMR ($CDCl_3$, 400 MHz) δ (ppm) 8.98 (dd, 2H), 8.58 (dd, 2H), 7.89 (d, 2H), 7.78 (dd, 2H), 7.65 (dd, 2H), 7.54-7.42 (m, 10H), 7.38-7.30 (m, 2H), 7.22 (dt, 2H), 7.05-6.84 (m, 14H), 1.85 (s, 12H)

Example 1

[0193] To manufacture an anode, a coming $15\Omega/cm^2$ (1200 \AA) ITO glass substrate was cut to a size of $50 \text{ mm} \times 50 \text{ mm} \times 0.7 \text{ mm}$ and then sonicated in isopropyl alcohol and pure water each for five minutes, and then cleaned by irradiation of

ultraviolet rays for 30 minutes and exposure to ozone. The resulting glass substrate was loaded into a vacuum deposition device.

[0194] Then, 2-TNATA, which is a HIL material, was vacuum-deposited on the glass substrate to form a HIL having a thickness of about 600 \AA . Then, 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB), which is a hole transporting compound, was vacuum-deposited on the HIL to form a HTL having a thickness of about 300 \AA .



[0195] Then, a green fluorescent host Alq3 and a green fluorescent dopant C545T were deposited at the same time in a weight ratio of 98:2, on the HTL, to form an EML with a thickness of 300 Å.

[0196] Then, Compound 7 was deposited on the EML to form an ETL having a thickness of 300 Å, and then LiF, which is a halogenated alkali metal, was deposited on the ETL to form an EIL having a thickness of 10 Å. Then, Al was vacuum-deposited on the EIL to form a cathode having a thickness of 3000 Å, thereby forming an LiF/Al electrode and completing the manufacture of an organic light-emitting device.

[0197] The organic light-emitting device had a driving voltage of 5.65V at a current density of 50 mA/cm², a high luminosity of 8,350 cd/m², color coordinates of (0.313, 0.644), and a luminescent efficiency of 16.7 cd/A.

Example 2

[0198] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 8 was used, instead of Compound 7, to form the ETL.

[0199] The organic light-emitting device had a driving voltage of 5.60V at a current density of 50 mA/cm², a high luminosity of 8,460 cd/m², color coordinates of (0.311, 0.643), and a luminescent efficiency of 16.92 cd/A.

Example 3

[0200] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 13 was used, instead of Compound 7, to form the ETL.

[0201] The organic light-emitting device had a driving voltage of 5.73V at a current density of 50 mA/cm², a high luminosity of 8,967 cd/m², color coordinates of (0.311, 0.641), and a luminescent efficiency of 17.93 cd/A.

Example 4

[0202] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 37 was used, instead of Compound 7, to form the ETL.

[0203] The organic light-emitting device had a driving voltage of 5.42V at a current density of 50 mA/cm², a high luminosity of 8,684 cd/m², color coordinates of (0.310, 0.644), and a luminescent efficiency of 17.37 cd/A.

Example 5

[0204] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 64 was used, instead of Compound 7, to form the ETL.

[0205] The organic light-emitting device had a driving voltage of 5.81V at a current density of 50 mA/cm², a high luminosity of 8,692 cd/m², color coordinates of (0.311, 0.643), and a luminescent efficiency of 17.38 cd/A.

Example 6

[0206] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 65 was used, instead of Compound 7, to form the ETL.

[0207] The organic light-emitting device had a driving voltage of 5.65V at a current density of 50 mA/cm², a high

luminosity of 8,262 cd/m², color coordinates of (0.311, 0.643), and a luminescent efficiency of 16.52 cd/A.

Example 7

[0208] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 68 was used, instead of Compound 7, to form the ETL.

[0209] The organic light-emitting device had a driving voltage of 5.62V at a current density of 50 mA/cm², a high luminosity of 8,354 cd/m², color coordinates of (0.311, 0.643), and a luminescent efficiency of 16.71 cd/A.

Example 8

[0210] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 69 was used, instead of Compound 7, to form the ETL.

[0211] The organic light-emitting device had a driving voltage of 6.12V at a current density of 50 mA/cm², a high luminosity of 7,684 cd/m², color coordinates of (0.311, 0.643), and a luminescent efficiency of 15.37 cd/A.

Example 9

[0212] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Compound 79 was used, instead of Compound 7, to form the ETL.

[0213] The organic light-emitting device had a driving voltage of 5.67V at a current density of 50 mA/cm², a high luminosity of 7,958 cd/m², color coordinates of (0.311, 0.643), and a luminescent efficiency of 15.92 cd/A.

Example 10

[0214] To manufacture an anode, a coming 15Ω/cm² (1200 Å) ITO glass substrate was cut to a size of 50 mm×50 mm×0.7 mm and then sonicated in isopropyl alcohol and pure water each for five minutes, and then cleaned by irradiation of ultraviolet rays for 30 minutes and exposure to ozone. The resulting glass substrate was loaded into a vacuum deposition device.

[0215] Then, 2-TNATA, which is a HIL material, was vacuum-deposited on the glass substrate to form a HIL having a thickness of about 600 Å. Then, 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB), which is a hole transporting compound, was vacuum-deposited on the HIL to form a HTL having a thickness of about 300 Å.

[0216] A blue fluorescent host 9,10-di-naphthalene-2-yl-anthracene (ADN) and Compound 29, which is a blue fluorescent dopant, were deposited at the same time on the HTL in a weight ratio of 98:2 to form an EML having a thickness of 300 Å.


[0217] Then, Alq3 was deposited on the EML to form an ETL having a thickness of 300 Å, and then LiF, which is a halogenated alkali metal, was deposited on the ETL to form an EIL having a thickness of 10 Å. Then, Al was vacuum-deposited on the EIL to form a cathode having a thickness of 3000 Å, thereby forming an LiF/Al electrode and completing the manufacture of an organic light-emitting device.

[0218] The organic light-emitting device had a driving voltage of 6.24V at a current density of 50mA/cm², a luminosity of 2,890 cd/m², and a luminescent efficiency of 5.78 cd/A, and emitted blue light.

Comparative Example 1

[0219] An organic light-emitting device was manufactured in the same manner as in Example 1, except that Alq₃ was used, instead of Compound 7, to form the ETL.


[0220] The organic light-emitting device had a driving voltage of 7.45V at a current density of 50 mA/cm², a high luminosity of 6,102 cd/m², color coordinates of (0.309, 0.642), which are almost the same as those of the organic light-emitting device of Example 1, and a luminescent efficiency of 12.2 cd/A.



Comparative Example 2

[0221] An organic light-emitting device was manufactured in the same manner as in Example 10, except that a blue fluorescent dopant 1,4-bis-(2,2-diphenylvinyl)biphenyl (DPVBi) was used, instead of Compound 29, to form the EML.

[0222] The organic light-emitting device had a driving voltage of 7.85V at a current density of 50 mA/cm², a luminosity of 1,560 cd/m², and a luminescent efficiency of 3.12 cd/A, and emitted blue light.



DPVBi

[0223] The organic light-emitting devices including the heterocyclic compounds of Formula 1 as ETL or EML materials had a driving voltage that was lower by 1V or greater than devices manufactured using Alq₃, and thus had higher efficiency and good I-V-L characteristics. In particular, lifetime characteristics were markedly improved in the organic light-emitting devices of Examples 1 through 9, as compared to the organic light-emitting device of Comparative Example 1. The organic light-emitting device of Example 10 manufactured by using Compound 29 as a blue fluorescent dopant for the EML had a driving voltage that was lower by 1.5V or greater as compared to the organic light-emitting device manufactured using DPVBi, and thus had higher efficiency and good I-V-L characteristics. In addition, the organic light-emitting device of Example 10 had lifetime characteristics markedly improved from the organic light-emitting device including DPVBi.

[0224] The characteristics of the organic light-emitting devices of Examples 1-10 and Comparative Examples 1 and 2 are tabled in Table 1 below.




TABLE 1

	EML or ETL material	Driving voltage (V)	Current density (mA/cm ²)	Luminosity (cd/m ²)	Luminescent efficiency (cd/A)	Color of light	Half-life span (hr @100 mA/cm ²)
Example 1	Compound 7	5.65	50	8350	16.7	Green	490 hr
Example 2	Compound 8	5.60	50	8460	16.92	Green	510 hr
Example 3	Compound 13	5.73	50	8967	17.93	Green	562 hr
Example 4	Compound 37	5.42	50	8684	17.37	Green	486 hr
Example 5	Compound 64	5.81	50	8692	17.38	Green	557 hr
Example 6	Compound 65	5.65	50	8262	16.52	Green	506 hr
Example 7	Compound 68	5.62	50	8354	16.71	Green	523 hr
Example 8	Compound 69	6.12	50	7684	15.37	Green	370 hr
Example 9	Compound 79	5.67	50	7958	15.92	Green	397 hr
Example 10	Compound 29	6.24	50	2890	5.78	Blue	212 hr
Comparative Example 1	Alq ₃	7.45	50	6102	12.2	Green	237 hr
Comparative Example 2	DPVBi	7.85	50	1560	3.12	Blue	113 hr

Example 11

[0225] To manufacture an anode, a coming $15\Omega/\text{cm}^2$ (1200 Å) ITO glass substrate was cut to a size of $50\text{ mm}\times 50\text{ mm}\times 0.7\text{ mm}$ and then sonicated in isopropyl alcohol and pure water each for five minutes, and then cleaned by irradiation of ultraviolet rays for 30 minutes and exposure to ozone. The resulting glass substrate was loaded into a vacuum deposition device.

[0226] Then, 2-TNATA, which is a HIL material, was vacuum-deposited on the glass substrate to form a HIL having a thickness of about 600 Å. Then, 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB), which is a hole transporting compound, was vacuum-deposited on the HIL to form a HTL having a thickness of about 300 Å.



[0227] A blue fluorescent host 9,10-di-naphthalene-2-yl-anthracene (ADN) and Compound 86, which is a blue fluorescent dopant, were deposited at the same time on the HTL in a weight ratio of 98:2 to form an EML having a thickness of 300 Å.

[0228] Then, Alq3 was deposited on the EML to form an ETL having a thickness of 300 Å, and then LiF, which is a halogenated alkali metal, was deposited on the ETL to form an EIL having a thickness of 10 Å. Then, Al was vacuum-deposited on the EIL to form a cathode having a thickness of 3000 Å, thereby forming an LiF/Al electrode and completing the manufacture of an organic light-emitting device.

[0229] The organic light-emitting device had a driving voltage of 6.72V at a current density of 50 mA/cm², a luminosity of 2183 cd/m², and a luminescent efficiency of 4.37 cd/A, and emitted blue light.

Example 12

[0230] An organic light-emitting device was manufactured in the same manner as in Example 11, except that Compound 94 was used, instead of Compound 86, to form the EML.

[0231] The organic light-emitting device had a driving voltage of 6.47V at a current density of 50 mA/cm², a luminosity of 2254 cd/m², and a luminescent efficiency of 4.51 cd/A, and emitted blue light.

Example 13

[0232] An organic light-emitting device was manufactured in the same manner as in Example 11, except that Compound 99 was used, instead of Compound 86, to form the EML.

[0233] The organic light-emitting device had a driving voltage of 6.59V at a current density of 50 mA/cm², a luminosity of 2405 cd/m², and a luminescent efficiency of 4.81 cd/A, and emitted blue light.

Example 14

[0234] An organic light-emitting device was manufactured in the same manner as in Example 11, except that Compound 107 was used, instead of Compound 86, to form the EML.

[0235] The organic light-emitting device had a driving voltage of 6.31V at a current density of 50 mA/cm², a luminosity of 2590 cd/m², and a luminescent efficiency of 5.18 cd/A, and emitted blue light.

Example 15

[0236] An organic light-emitting device was manufactured in the same manner as in Example 11, except that Compound 109 was used, instead of Compound 86, to form the EML.

[0237] The organic light-emitting device had a driving voltage of 6.26V at a current density of 50 mA/cm², a luminosity of 2870 cd/m², and a luminescent efficiency of 5.74 cd/A, and emitted blue light.

Example 16

[0238] An organic light-emitting device was manufactured in the same manner as in Example 11, except that Compound 116 was used, instead of Compound 86, to form the EML.

[0239] The organic light-emitting device had a driving voltage of 6.15V at a current density of 50 mA/cm², a luminosity of 2623 cd/m², and a luminescent efficiency of 5.25 cd/A, and emitted blue light.

Example 17

[0240] An organic light-emitting device was manufactured in the same manner as in Example 11, except that Compound 119 was used, instead of Compound 86, to form the EML.

[0241] The organic light-emitting device had a driving voltage of 6.66V at a current density of 50 mA/cm², a luminosity of 2324 cd/m², and a luminescent efficiency of 4.64 cd/A, and emitted blue light.

[0242] The organic light-emitting devices including Compounds 86-119, the heterocyclic compounds of Formula 1, as EML materials had a driving voltage that was lower by 1V or greater than devices manufactured using DPVBi, and thus had higher efficiency and good I-V-L characteristics. In particular, lifetime characteristics were markedly improved in the organic light-emitting devices of Examples 11-17, as compared to the organic light-emitting device of Comparative Example 2. The characteristics of the organic light-emitting devices of Examples 11-17 and Comparative Example 2 are tabled in Table 2 below.


materials that are suitable for any color fluorescent or phosphorescent devices, such as red, green, blue, and white fluorescent or phosphorescent devices, and may be used as light emitting materials for green, blue, or white fluorescent devices. Therefore, organic light-emitting devices having high efficiency, low driving voltages, high luminance, and long lifetime may be manufactured using the heterocyclic compounds.

[0244] While the present invention has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims.

What is claimed is:

1. A heterocyclic compound represented by Formula 1 below:

Formula 1



wherein, in Formula 1, R₁ to R₁₂ are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkyne group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₅-C₆₀ ary-


TABLE 2

EML material	Driving voltage (V)	Current density (mA/cm ²)	Luminosity (cd/m ²)	Luminescent efficiency (cd/A)	Color of light	Half-life span (hr @100 mA/cm ²)	
Example 11	Compound 86	6.72	50	2,183	4.37	Blue	209 hr
Example 12	Compound 94	6.47	50	2,254	4.51	Blue	218 hr
Example 13	Compound 99	6.59	50	2,405	4.81	Blue	225 hr
Example 14	Compound 107	6.31	50	2,590	5.18	Blue	235 hr
Example 15	Compound 109	6.26	50	2,870	5.74	Blue	210 hr
Example 16	Compound 116	6.15	50	2,623	5.25	Blue	196 hr
Example 17	Compound 119	6.66	50	2,324	4.64	Blue	260 hr
Comparative Example 2	DPVBi	7.85	50	1,560	3.12	Blue	113 hr

[0243] The heterocyclic compounds of Formula 1 according to embodiments of the present invention have good light emitting characteristics and charge transporting capability, and thus, may be used as electron injecting or transporting

loxy group, a substituted or unsubstituted C₅-C₆₀ arylthio group, a substituted or unsubstituted C₅-C₆₀ aryl group, a substituted amino group with a C₅-C₆₀ aryl group or a C₂-C₆₀ heterocyclic group, a substituted or

unsubstituted C₂-C₆₀ heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, and a carboxyl group, wherein R₆ and R₇ are optionally linked to each other to form a group represented by Formula 2 in which ** and * indicates binding sites corresponding to the binding sites corresponding to the binding sites of R₆ and R₇ of Formula 1:




Formula 2


wherein, in Formula 2, R₁₃ and R₁₄ are each independently a hydrogen atom, a deuterium atom, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₅-C₆₀ aryloxy group, a substituted or unsubstituted C₅-C₆₀ arylthio group, a substituted or unsubstituted C₅-C₆₀ aryl group, a substituted amino group with a C₅-C₆₀ aryl or C₂-C₆₀ heterocyclic group, a substituted or unsubstituted C₂-C₆₀ heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, or a carboxyl group; and

two adjacent substituents among R₁ to R₁₄ are optionally linked to each other to form a ring.


2. The heterocyclic compound of claim 1, wherein R₁ to R₁₄ in Formulae 1 and 2 are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a C₁-C₂₀ alkyl group, and groups represented by Formulae 2a to 2l below:




formula 2a



formula 2b




formula 2c




formula 2d

-continued


formula 2e




formula 2f




formula 2g




formula 2h




formula 2i




formula 2j



formula 2k



formula 2l



wherein, in Formulae 2a to 2l, Q₁ and Q₂ are each independently a linking group selected from the group consisting of —C(R₁₅)(R₁₆)—, —N(R₁₅)—, —S—, and —O—;

Y₁, Y₂, Y₃, Y₄, Y₅, and Y₆ are each independently a linking group selected from the group consisting of —N—, —C(R₁₇)—, —S—, and —O—;

Z₁, Z₂, Ar₁₂, Ar₁₃, R₁₅, R₁₆, and R₁₇ are each independently selected from the group consisting of a hydrogen

atom, a deuterium atom, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₅-C₂₀ aryl group, a substituted or unsubstituted C₂-C₂₀ heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, and a carboxyl group;

Ar₁₁ is selected from the group consisting of a substituted or unsubstituted C₁-C₂₀ alkylene group, a substituted or unsubstituted C₅-C₂₀ arylene group, and a substituted or unsubstituted C₂-C₂₀ divalent heterocyclic group;


p is an integer from 1 to 12;

q is an integer from 1 to 12;


r is an integer from 0 to 5; and

* indicates a binding site.


3. The heterocyclic compound of claim 1, wherein R₁ to R₁₄ in Formulae 1 and 2 are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, and groups represented by Formulae 3a to 3h below:




formula 3a




formula 3b




formula 3c



formula 3d




formula 3e




formula 3f

-continued



formula 3g



formula 3h

wherein, in Formulae 3a to 3h, Z₁, Ar₁₂, and Ar₁₃ are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a substituted or unsubstituted aryl group, and a substituted or unsubstituted C₂-C₂₀ heterocyclic group;

r is an integer from 0 to 2;

p is an integer from 1 to 5; and


* indicates a binding site.

4. The heterocyclic compound of claim 1, wherein, in Formula 1, R₂ to R₅ and R₇ to R₁₁ are each independently a hydrogen atom or a deuterium atom.

5. The heterocyclic compound of claim 1, wherein R₂ to R₅ and R₇ to R₁₁ in Formula 1 are each independently a hydrogen atom or a deuterium atom; and R₁, R₆ and R₁₂ are each independently selected from the group consisting of a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₅-C₆₀ aryloxy group, a substituted or unsubstituted C₅-C₆₀ arylthio group, a substituted or unsubstituted C₅-C₆₀ aryl group, a substituted amino group with a C₅-C₆₀ aryl group or a C₂-C₆₀ heterocyclic group, a substituted or unsubstituted C₂-C₆₀ heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, and a carboxyl group;


6. The heterocyclic compound of claim 1, wherein, in Formula 1, R₂ to R₅, and R₇ to R₁₁ are each independently a hydrogen atom or a deuterium atom; and R₁, R₆ and R₁₂ are each independently selected from the group consisting of a halogen atom, a cyano group, a C₁-C₂₀ alkyl group, and groups represented by Formulae 2a to 2l below; or

wherein, in Formulae 1 and 2, R₂ to R₅ and R₈ to R₁₁ are each independently a hydrogen atom or a deuterium atom; and R₁, R₁₂, R₁₃, and R₁₄ are each independently selected from the group consisting of a halogen atom, a cyano group, a C₁-C₂₀ alkyl group, and groups represented by Formulae 2a to 2l below:




formula 2a


-continued



formula 2b




formula 2c




formula 2d


formula 2e




formula 2f




formula 2g




formula 2h




formula 2i




formula 2j



-continued



formula 2k



formula 2l

wherein, in Formulae 2a to 2l, Q_1 and Q_2 are each independently a linking group selected from the group consisting of $-C(R_{15})(R_{16})-$, $-N(R_{15})-$, $-S-$, and $-O-$;

Y_1 , Y_2 , Y_3 , Y_4 , Y_5 , and Y_6 are each independently a linking group selected from the group consisting of $-N=$, $-C(R_{17})=$, $-S-$, and $-O-$;

Z_1 , Z_2 , Ar_{12} , Ar_{13} , R_{15} , R_{16} , and R_{17} are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_5 - C_{20} aryl group, a substituted or unsubstituted C_2 - C_{20} heterocyclic group, a halogen atom, a cyano group, a nitro group, a hydroxyl group, and a carboxyl group;

Ar_{11} is selected from the group consisting of a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_5 - C_{20} arylene group, and a substituted or unsubstituted C_2 - C_{20} divalent heterocyclic group;

p is an integer from 1 to 12;

q is an integer from 1 to 12;


r is an integer from 0 to 5; and

* indicates a binding site.

7. The heterocyclic compound of claim 1, wherein R_6 and R_7 are linked to each other to form the group represented by Formula 2.


8. The heterocyclic compound of claim 7, wherein, in Formulae 1 and 2, R_1 , R_2 , R_3 , R_4 , R_5 and R_{12} are respectively identical with R_{14} , R_8 , R_9 , R_{10} , R_{11} and R_{13} ;

R_1 to R_5 and R_8 to R_{14} are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, and groups represented by Formulae 3a to 3h below:




formula 3a


-continued




formula 3b




formula 3c




formula 3d




formula 3e



formula 3f



formula 3g



formula 3h

wherein, in Formulae 3a to 3h, Z_1 , Ar_{12} , and Ar_{13} are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a substituted or unsubstituted aryl group, and a substituted or unsubstituted C_2 - C_{20} heterocyclic group;

r is an integer from 0 to 2;


p is an integer from 1 to 5; and

* indicates a binding site.


9. The heterocyclic compound of claim 7, wherein, in Formulae 1 and 2, R_1 , R_2 , R_3 , R_4 , R_5 and R_{12} are respectively identical with R_{14} , R_8 , R_9 , R_{10} , R_{11} and R_{13} ;

R_2 to R_5 and R_8 to R_{11} are each independently a hydrogen atom or a deuterium atom; and


R_1 , R_{12} , R_{13} and R_{14} are each independently selected from the group consisting of a hydrogen atom, a deuterium atom, a halogen atom, a cyano group, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, and groups represented by Formulae 3a to 3h below:




formula 3a




formula 3b




formula 3c




formula 3d



formula 3e




formula 3f



formula 3g

-continued



formula 3h

wherein, in Formulae 3a to 3h, Z_1 , Ar_{12} , and Ar_{13} are each independently selected from the group consisting of a


hydrogen atom, a deuterium atom, a substituted or unsubstituted aryl group, and a substituted or unsubstituted C_2 - C_{20} heterocyclic group;

r is an integer from 0 to 2;


p is an integer from 1 to 5; and

* indicates a binding site.


10. The heterocyclic compound of claim 1, wherein the heterocyclic compound of Formula 1 is one of the compounds below:




7



8




13




29

-continued


37




64



65





68



-continued



69

79





86

94





99

107




-continued
109

116



119



11. An organic light-emitting device comprising:
a first electrode;
a second electrode; and
an organic layer between the first electrode and the second electrode, the organic layer comprising the heterocyclic compound of claim 1.

12. The organic light-emitting device of claim 11, wherein the organic layer comprises an emission layer comprising the heterocyclic compound of Formula 1 as a host for a fluorescence or phosphorescence device.

13. The organic light-emitting device of claim 11, wherein the organic layer comprises an emission layer comprising the heterocyclic compound of Formula 1 as a dopant for a fluorescence device.

14. The organic light-emitting device of claim 11, wherein the organic layer comprises an electron injection layer or an electron transport layer.

15. The organic light-emitting device of claim 11, wherein the organic layer comprises a single layer having both an electron injection function and an electron transport function.

16. The organic light-emitting device of claim 11, wherein the organic layer comprises at least one layer of an emission layer, an electron injection layer and an electron transport layer;

at least one of said at least one layer of the emission layer, the electron injection layer and the electron transport layer comprises the heterocyclic compound of Formula 1; and

the emission layer comprises an anthracene compound, an arylamine compound, or a styryl compound.

17. The organic light-emitting device of claim 11, wherein: the organic layer comprises at least one layer of an emission layer, an electron injection layer and an electron transport layer;

at least one of said at least one layer of the emission layer, the electron injection layer and the electron transport layer comprises the heterocyclic compound of Formula 1; and

the emission layer comprises red, green, blue, and white emission layers one of which comprises a phosphorescent compound.

18. The organic light-emitting device of claim 11, wherein R_6 and R_7 are linked to each other to form the group represented by Formula 2.

19. An organic light-emitting device comprising:

a first electrode;


a second electrode; and

an organic layer between the first electrode and the second electrode,

wherein the organic layer comprises at least one layer comprising the heterocyclic compound of Formula 1 in claim 1, the at least one layer being formed using a wet process.


20. A flat panel display device comprising the organic light-emitting device of claim 11, wherein the first electrode of the organic light-emitting device is electrically connected to a source electrode or a drain electrode of a thin-film transistor.

21. The organic light-emitting device of claim 11, wherein the heterocyclic compound of Formula 1 is one of the compounds below:





1

2





3

4



5



6



-continued



7

8





9

10



11



12



-continued



13

14



15



16



-continued



17

18



19



20



-continued



21


22



23

24






-continued



25

26





27

28





-continued
29

30





31

32




33

34




-continued






35

36





37

38




39

40




41

42




-continued


43




44




45




46



47




48




-continued


49




50




51




52









53



54




-continued




-continued


61




62




63




64



65




66




-continued


67




68







69




70



-continued






-continued



75

76



77



78



-continued



79



80



81


82




-continued
83

84


22. The organic light-emitting device of claim 11, wherein the heterocyclic compound of Formula 1 is one of the compounds below:




85



86



87





88

-continued



89

90





91

92





93

94



95



96




-continued

97


98




99











100



101





-continued



-continued



110

111





112

113



114



115



-continued



116

117



118



119



-continued



120

121




122

123




-continued
124

125



* * * * *



专利名称(译)	杂环化合物和包括其的有机发光装置		
公开(公告)号	US20120097929A1	公开(公告)日	2012-04-26
申请号	US13/210599	申请日	2011-08-16
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星移动显示器有限公司.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM YOUNG KOOK HWANG SEOK HWAN KWAK YOON HYUN LEE SUN YOUNG JUNG HYE JIN LIM JIN O LEE JONG HYUK		
发明人	KIM, YOUNG-KOOK HWANG, SEOK-HWAN KWAK, YOON-HYUN LEE, SUN-YOUNG JUNG, HYE-JIN LIM, JIN-O LEE, JONG-HYUK		
IPC分类号	H01L51/54 C07D403/10 C07D487/04 C07D239/26 C07D413/10 C07D251/24 C07D209/82		
CPC分类号	C07D209/80 H01L51/5092 C07D401/10 C07D401/12 C07D401/14 C07D403/04 C07D403/10 C07D403/14 C07D405/04 C07D409/04 C07D409/14 C07D413/04 C07D413/10 C07D417/10 C07D471/04 C07D487/04 H01L51/0054 H01L51/0059 H01L51/0069 H01L51/0072 H01L51/5012 H01L51/0073 H01L51/0068 H01L51/0061 H01L51/0058 H01L51/0052 H01L51/5076 C07D401/04		
优先权	1020100104186 2010-10-25 KR		
其他公开文献	US8815417		
外部链接	Espacenet USPTO		

摘要(译)

由下式1表示的杂环化合物和包含该杂环化合物的有机发光装置：其中R1至R12如说明书中所定义。

