





US 20160164007A1

(19) **United States**(12) **Patent Application Publication**
LIN et al.(10) **Pub. No.: US 2016/0164007 A1**(43) **Pub. Date: Jun. 9, 2016**(54) **ORGANIC METAL COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
EMPLOYING THE SAME**(71) Applicant: **INDUSTRIAL TECHNOLOGY
RESEARCH INSTITUTE**, Hsinchu
(TW)(72) Inventors: **Jin-Sheng LIN**, Taipei City (TW);
Cheng-An WU, New Taipei City (TW);
Pang-Chi HUANG, Taoyuan City (TW);
Meng-Hao CHANG, New Taipei City
(TW); **Han-Cheng YEH**, Taipei City
(TW); **Chun-Neng KU**, Tainan City
(TW)(73) Assignee: **INDUSTRIAL TECHNOLOGY
RESEARCH INSTITUTE**, Hsinchu
(TW)(21) Appl. No.: **14/837,844**(22) Filed: **Aug. 27, 2015**(30) **Foreign Application Priority Data**

Dec. 3, 2014 (TW) 103141945

Publication Classification(51) **Int. Cl.**
H01L 51/00 (2006.01)
C09K 11/06 (2006.01)
C09K 11/02 (2006.01)
C07F 15/00 (2006.01)(52) **U.S. CL.**
CPC **H01L 51/0085** (2013.01); **C07F 15/0033**
(2013.01); **C09K 11/06** (2013.01); **C09K**
11/025 (2013.01); **H01L 51/0061** (2013.01);
C09K 2211/1007 (2013.01); **C09K 2211/1029**
(2013.01); **C09K 2211/1092** (2013.01); **C09K**
2211/185 (2013.01); **H01L 51/0072** (2013.01);
H01L 51/5016 (2013.01)(57) **ABSTRACT**Organic metal compounds, and organic light-emitting
devices employing the same, are provided. The organic metal
compound has a chemical structure represented by formula
(I):

Formula (I)

wherein each R¹ can be independently hydrogen, C₁₋₁₂ alkyl
group, C₅₋₁₀ cycloalkyl group, C₃₋₁₂ heteroaryl group, or
C₆₋₁₂ aryl group; R² can be independently hydrogen, halogen,
C₁₋₁₂ alkyl group, C₅₋₁₀ cycloalkyl group, C₃₋₁₂ heteroaryl
group, or C₆₋₁₂ aryl group.10




FIG. 1




FIG. 2

ORGANIC METAL COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE EMPLOYING THE SAME

CROSS REFERENCE TO RELATED APPLICATION

[0001] The application is based on, and claims priority from, Taiwan Application Serial Number 103141945, filed on Dec. 3, 2014, the disclosure of which is hereby incorporated by reference herein in its entirety.

TECHNICAL FIELD

[0002] The disclosure relates to an organic metal compound and an organic light-emitting device employing the same.

BACKGROUND


[0003] An organic light-emitting diode (OLED) is a light-emitting diode employing an organic electroluminescent layer as an active layer. OLED display devices have high luminescent efficiency and long operating lifespans. In comparison with liquid-crystal displays, due to the characteristic of spontaneous emission, a device employing an organic light-emitting diode is free of a back-light source.

[0004] Generally, an organic light-emitting device is composed of a light-emission layer sandwiched between a pair of electrodes. When an electric field is applied to the electrodes, the cathode injects electrons into the light-emission layer and the anode injects holes into the light-emission layer. When the electrons recombine with the holes in the light-emission layer, excitons are formed. Recombination of the electron and hole results in light emission.

[0005] Depending on the spin states of the hole and electron, the exciton, which results from the recombination of the hole and electron, can have either a triplet or singlet spin state. Luminescence from a singlet exciton results in fluorescence whereas luminescence from a triplet exciton results in phosphorescence. The emissive efficiency of phosphorescence is three times that of fluorescence. Therefore, it is crucial to develop highly efficient phosphorescent material, in order to increase the emissive efficiency of an OLED.

SUMMARY

[0006] According to an embodiment of the disclosure, the disclosure provides an organic metal compound having a structure of Formula (I):



Formula (I)

[0007] wherein, R¹ is independently hydrogen, C₁₋₁₂ alkyl group, C₅₋₁₀ cycloalkyl group, C₃₋₁₂ heteroaryl group, or

C₆₋₁₂ aryl group; R² is independently hydrogen, halogen, C₁₋₁₂ alkyl group, C₅₋₁₀ cycloalkyl group, C₃₋₁₂ heteroaryl group, or C₆₋₁₂ aryl group.

[0008] According to another embodiment of the disclosure, the disclosure provides an organic light-emitting device. The device includes a pair of electrodes and an organic light-emitting element, disposed between the electrodes, wherein the organic light-emitting element includes the aforementioned organic metal compound.

[0009] A detailed description is given in the following embodiments with reference to the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] The disclosure can be more fully understood by reading the subsequent detailed description and examples with references made to the accompanying drawings, wherein:

[0011] FIG. 1 is a Single-Crystal X-ray diffraction pattern of the organic metal compound obtained in Example 1.

[0012] FIG. 2 shows a cross section of an organic light-emitting device disclosed by an embodiment of the disclosure.


DETAILED DESCRIPTION

[0013] The following description is of the best-contemplated mode of carrying out the disclosure. This description is made for the purpose of illustrating the general principles of the disclosure and should not be taken in a limiting sense. The scope of the disclosure is best determined by reference to the appended claims.


[0014] Organic Metal Compound

[0015] The disclosure provides an organic metal compound and an organic light-emitting device employing the same. The organic metal compound can be a tris-facial six-coordinate iridium compound including specific thienopyridine-based ligand, such as thieno[3,2-c]pyridine-based derivative ligand. Since the thermal stability can be enhanced by means of the bondings between iridium and ligands, the organic metal compound of the disclosure can have a thermal degradation temperature (T_d) that is higher than about 400° C. Therefore, the organic metal compound having Formula (I) of the disclosure is suitable for being purified by a sublimation process (the organic metal compound having Formula (I) of the disclosure has a sublimation yield that is higher than about 80%). In addition, due to the specific chemical structure, the organic metal compound of the disclosure can have a suitable highest occupied molecular orbital (HOMO) and lowest unoccupied molecular orbital (LUMO) energy gap (between about 6.0 eV and 3.0 eV), thereby facilitating the electrons recombining with the holes to form excitons, and resulting in luminescence. Therefore, the organic metal compound having Formula (I) of the disclosure can serve as phosphorescence light-emitting material for enhancing the luminous efficiency of the organic light-emitting device employing the same.

[0016] According to an embodiment of the disclosure, the disclosure provides an organic metal compound having a structure of Formula (I):



Formula (I)




Formula (II)

[0017] wherein, R^1 is independently hydrogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group; R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.

[0018] The organic metal compounds of the disclosure can serve as a green or yellow phosphorescent dopant material (having a maximum luminous intensity peak of between about 520 nm to 570 nm), and can be applied to an organic light-emitting device for enhancing the luminous efficiency.

[0019] According to an embodiment of the disclosure, each R^1 is independently hydrogen, methyl, ethyl, propyl, isopropyl, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclohexyl group, cyclopentyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl.

[0020] In Formula (I), the structure






and R^2 are independent. According to an embodiment of the disclosure, each R^2 can be independently hydrogen, fluorine, methyl, ethyl, propyl, isopropyl, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclohexyl group, cyclopentyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl.

[0021] According to some embodiments of the disclosure, at least one of R^1 and R^2 of the organic metal compound having the structure of Formula (I) is not hydrogen. According to some embodiments of the disclosure, at least one of R^2 of the organic metal compound having the structure of Formula (I) is not hydrogen. According to some embodiments of the disclosure, R^1 of the organic metal compound having the structure of Formula (I) is not hydrogen and at least one of R^2 of the organic metal compound having the structure of Formula (I) is not hydrogen.


[0022] According to some embodiments of the disclosure, the organic metal compound can have a structure of Formula (II):

[0023] wherein, R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group. The organic metal compound having a structure of Formula (II) can be






[0024] According to some embodiments of the disclosure, the organic metal compound can have a structure of Formula (III):




Formula (III)

[0025] wherein, R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group. The organic metal compound having a structure of Formula (III) can be





[0026] According to some embodiments of the disclosure, the organic metal compound can have a structure of (IV):









Formula (IV)

[0027] wherein, R^1 is independently hydrogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group. The organic metal compound having a structure of Formula (IV) can be



Formula (V)

[0029] wherein, R^1 is independently hydrogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group. The organic metal compound having a structure of Formula (V) can be




[0028] According to some embodiments of the disclosure, the organic metal compound can have a structure of Formula (V):

[0030] According to some embodiments of the disclosure, the organic metal compound can have a structure of Formula (VI):


Example 1

Preparation of Organic Metal Compound (I)

[0033]




[0031] wherein, R¹ is independently hydrogen, C₁₋₁₂ alkyl group, C₅₋₁₀ cycloalkyl group, C₃₋₁₂ heteroaryl group, or C₆₋₁₂ aryl group. The organic metal compound having a structure of Formula (VI) can be



[0032] The following examples are intended to illustrate the disclosure more fully without limiting the scope, since numerous modifications and variations will be apparent to those skilled in this art.



[0034] Organic Metal Compound (I)

[0035] 9.0 g of 2-(2-aminoethyl)thiophene (70.9 mmol) and 40 mL of water were added into a reaction bottle. Next, 11 mL of benzoyl chloride and 45 mL of sodium hydroxide aqueous solution (20 wt %) were added into the reaction bottle at 0° C., and a white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (1) with a yield of 95%. The synthesis pathway of the above reaction was as follows:




[0036] The physical measurement of the compound (1) is listed below: ¹H NMR (200 MHz, CDCl₃, 294 K): δ 8.81 (d, 2H), 7.47~7.30 (m, 4H), 7.11 (d, 1H), 7.91 (t, 1H), 6.80 (d, 1H), 3.66 (q, 2H), 3.10 (t, 2H).

[0037] 11.6 g of Compound (1) (50 mmol) and 50 mL of toluene were added into a reaction bottle and the reaction bottle was cooled to 0° C. Next, 11.5 g of phosphoryl chloride (POCl₃, 75 mmol) was slowly added into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate (EA) and water as the extraction solvent. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (2) with a yield of 75%. The synthesis pathway of the above reaction was as follows:





[0038] The physical measurement of the compound (2) is listed below: ^1H NMR (200 MHz, CDCl_3 , 294 K): δ 7.50 (d, 2H), 7.30-7.22 (m, 3H), 6.91 (d, 1H), 6.84 (d, 1H), 3.78 (t, 2H), 2.76 (t, 2H).

[0039] 10.6 g of Compound (2) (50 mmol), 10 g of palladium 10% on carbon (Pd/C catalyst), and 50 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate (EA) and water as the extraction solvent, and an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (3) with a yield of 95%. The synthesis pathway of the above reaction was as follows:






[0040] The physical measurement of the compound (3) is listed below: ^1H NMR (200 MHz, CDCl_3 , 294 K): δ 8.53 (d, 1H), 7.81 (d, 2H), 7.77 (d, 1H), 7.60~7.40 (m, 5H).

[0041] Next, 28 mg of Compound (3) (4.4 mmol), and 598 mg of IrCl_3 (2 mmol), 15 mL of 2-methoxyethanol, and 5 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (4) with a yield of 72%. The synthesis pathway of the above reaction was as follows:




[0042] Next, 1.3 g of Compound (4) (1 mmol), acetyl acetone, 300 mg, 3 mmol), 212 mg of sodium carbonate (Na_2CO_3 , 2 mmol), and 2-methoxyethanol (20 mL) were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (5) with a yield of 72%. The synthesis pathway of the above reaction was as follows:





[0043] The physical measurement of the compound (5) is listed below: ^1H NMR (200 MHz, CDCl_3 , 294 K): δ 8.52 (d, 2H), 8.13 (d, 2H), 7.87 (d, 2H), 7.68 (d, 2H), 7.59 (d, 2H), 6.99 (t, 2H), 6.69 (t, 2H), 6.29 (d, 2H), 5.33 (s, 1H), 1.82 (s, 6H).

[0044] 711 mg of Compound (5) (1 mmol), 422 mg of Compound (3) (2 mmol), and 10 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (I). The synthesis pathway of the above reaction was as follows:



[0045] The physical measurement of the organic metal compound (I) is listed below: ^1H NMR (200 MHz, CDCl_3 ,

294 K): δ 8.35 (d, 3H), 8.22 (d, 3H), 7.51 (d, 3H), 7.34 (m, 6H), 6.90 (m, 9H). Elemental analysis: $\text{C}_{39}\text{H}_{24}\text{IrN}_3\text{S}_3$; N, 5.11; C, 56.91; H, 2.94. Found: N, 5.09; C, 56.88; H, 2.97.

[0046] Organic metal compound (I) was analyzed by X-ray diffraction spectroscopy, and the result was shown in FIG. 1.

[0047] As the result of NMR and X-ray diffraction spectroscopy, Organic metal compound (I) of Example 1 has a facial arrangement.

Comparative Example 1

[0048] Compound (3) (6.6 mmol), IrCl_3 (2 mmol), and glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 12 hours, the reaction bottle was cooled to room temperature, and a black precipitate was obtained. After analyzing the black precipitate, iridium organic compound was not obtained since the iridium intermediate was apt to be decomposed.

Comparative Example 2


[0049] Compound (4) (0.5 mmol), Compound (3) (1 mmol), 138 mg of potassium carbonate (K_2CO_3 , 1 mmol), and 10 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and a black precipitate was obtained. After analyzing the black precipitate, iridium organic compound was not obtained since the iridium intermediate was apt to be decomposed.

Example 2

Preparation of Organic Metal Compound (II)


[0050]

Organic metal compound (II)




[0051] 76.3 g of 2-(2-aminoethyl)thiophene (600 mmol) and 1 L of water were added into a reaction bottle. Next, 91 mL of 4-tert-butylbenzoyl chloride (500 mmol) and sodium hydroxide aqueous solution (20 wt %, 150 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and

washed with water and hexane, obtaining compound (6) with a yield of 99%. The synthesis pathway of the above reaction was as follows:




[0052] 50 g of compound (6) (174 mmol) and 170 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 17 mL of phosphoryl chloride (POCl₃, 174 mmol). After the addition was complete, the reaction bottle was heated to reflux. After reacting for 12 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (7) with a yield of 72%. The synthesis pathway of the above reaction was as follows:




[0053] 46 g of Compound (7) (174 mmol), 50 g of Pd/C catalyst (palladium 10% on carbon), and 170 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux for 48 hours. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times

using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (8) with a yield of 90%. The synthesis pathway of the above reaction was as follows:






[0054] Next, Compound (8) (18.7 g, 70 mmol), 10.4 g of IrCl₃ (35 mmol), 262 mL of 2-methoxyethanol, and 88 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (9) with a yield of 90%. The synthesis pathway of the above reaction was as follows:



[0055] Next, 26.6 g of Compound (9) (17.5 mmol), 7 g of acetyl acetone (70 mmol), 7.4 g of sodium carbonate (Na₂CO₃, 70 mmol), and 175 mL of 2-methoxyethanol were



added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (10) with a yield of 64%. The synthesis pathway of the above reaction was as follows:




Example 3

Preparation of Organic Metal Compound (III)

[0057]




Organic metal compound (III)




[0056] 18.3 g of Compound (10) (22.2 mmol), 11.9 g of Compound (8) (44.5 mmol), and 220 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (II). The synthesis pathway of the above reaction was as follows:


[0058] 30.0 g of 2-(2-(2-aminoethyl)thiophene) (235.8 mmol), and 500 mL of water were added into a reaction bottle. Next, 40.1 g of 4-methyl-benzoyl chloride (259.4 mmol) and sodium hydroxide aqueous solution (20 wt %, 200 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (11) with a yield of 89%. The synthesis pathway of the above reaction was as follows:




[0059] 5.0 g of Compound (11) (23.0 mmol) and 100 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 10.5 g of phosphoryl chloride (POCl_3 , 69.1 mmol) were added slowly into a reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (12) with a yield of 50%. The synthesis pathway of the above reaction was as follows:





[0060] 5.0 g of Compound (12) (22.0 mmol), 5 g of Pd/C catalyst (palladium 10% on carbon), and 30 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux for 24 hours. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (13) with a yield of 83%. The synthesis pathway of the above reaction was as follows:



[0061] Next, compound (13) (1 g, 4.4 mmol), and 630 mg of IrCl_3 (2.1 mmol), 30 mL of 2-methoxyethanol, and 10 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (14) with a yield of 73%. The synthesis pathway of the above reaction was as follows:




[0062] Next, 1.04 g of Compound (14) (0.77 mmol), 230 mg of acetyl acetone (2.3 mmol), sodium carbonate (Na_2CO_3 , 250 mg, 2.3 mmol), and 30 mL of 2-methoxyethanol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (15) with a yield of 74%. The synthesis pathway of the above reaction was as follows:





Example 4

Preparation of Organic Metal Compound (IV)


[0064]




Organic metal compound (IV)



[0063] 3.0 g of Compound (15) (4.05 mmol), 1.82 g of Compound (13) (8.1 mmol), and 15 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (III). The synthesis pathway of the above reaction was as follows:




[0065] 30.0 g of 2-(2-aminoethyl)thiophene (235.8 mmol), and 400 mL of water were added into a reaction bottle. Next, 40.9 g of 4-fluorine-benzoyl chloride (259.4 mmol) and sodium hydroxide aqueous solution (20 wt %, 200 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (16) with a yield of 93%. The synthesis pathway of the above reaction was as follows:




[0066] 5.0 g of Compound (16) (20.1 mmol) and 100 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 9.2 g of phosphoryl chloride

(POCl_3 , 60.21 mmol) was added slowly into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40°C ., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (17) with a yield of 55%. The synthesis pathway of the above reaction was as follows:




[0067] 5.0 g of Compound (17) (21.6 mmol), 5 g of Pd/C catalyst (palladium 10% on carbon), and 30 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (18) with a yield of 85%. The synthesis pathway of the above reaction was as follows:




[0068] Next, 1.69 g of Compound (18) (7.4 mmol), and 1000 mg of IrCl_3 (3.35 mmol), 30 mL of 2-methoxyethanol, and 10 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120°C . After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining


Compound (19) with a yield of 70%. The synthesis pathway of the above reaction was as follows:



[0069] Next, 3.0 g of Compound (19) (2.2 mmol), 880 mg of acetyl acetone (8.8 mmol), 930 mg of sodium carbonate (Na_2CO_3 , 8.8 mmol), and 20 mL of 2-methoxyethanol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120°C . After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (20) with a yield of 75%. The synthesis pathway of the above reaction was as follows:




-continued




Compound (20)


[0070] 1000 mg of Compound (20) (1.33 mmol), 610 mg of Compound (18) (2.7 mmol), and 20 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (IV). The synthesis pathway of the above reaction was as follows:



Compound (20)



Compound (18)




Organic metal compound (IV)

Example 5



Preparation of Organic Metal Compound (V)

[0071]







Organic metal compound (V)

[0072] 30.0 g of 2-(2-aminoethyl)thiophene (235.8 mmol), and 500 mL of water were added into a reaction bottle. Next, 45.6 g of 2,4-difluorine-benzoyl chloride (259.4 mmol) and sodium hydroxide aqueous solution (20 wt %, 200 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (21) with a yield of 90%. The synthesis pathway of the above reaction was as follows:




Compound (21)

[0073] 5.0 g of compound (21) (18.7 mmol) and 100 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 8.5 g of phosphoryl chloride (POCl₃, 56.2 mmol) was added slowly into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (22) with a yield of 53%. The synthesis pathway of the above reaction was as follows:




[0074] 5.0 g of Compound (22) (20.1 mmol), 5.0 g of Pd/C catalyst (palladium 10% on carbon), and 30 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (23) with a yield of 85%. The synthesis pathway of the above reaction was as follows:




[0075] Next, compound (23) (1000 mg, 4.0 mmol), and IrCl₃ (548 mg, 1.84 mmol), 2-methoxyethanol, 30 mL), and 10 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (24) with a yield of 78%. The synthesis pathway of the above reaction was as follows:



[0076] Next, Compound (24) (1.04 g, 0.72 mmol), 289 mg of acetyl acetone (2.9 mmol), 306 mg of sodium carbonate (Na₂CO₃, 2.9 mmol), and 30 mL of 2-methoxyethanol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (25) with a yield of 70%. The synthesis pathway of the above reaction was as follows:



-continued




[0077] 782 mg of Compound (25) (0.99 mmol), 492 mg of Compound (23) (1.99 mmol), and 15 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 96 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (V). The synthesis pathway of the above reaction was as follows:




Example 6

Preparation of Organic Metal Compound (VI)

[0078]




[0079] 9.0 g of 2-(2-aminoethyl)-5-benzyl-thiophene, 44.3 mmol, and 40 mL of water were added into a reaction bottle. Next, benzoyl chloride (6.2 g, 44.3 mmol) and sodium hydroxide aqueous solution (20 wt %, 45 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (26) with a yield of 91%. The synthesis pathway of the above reaction was as follows:




[0080] 15.4 g of Compound (26) (50 mmol) and 50 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 11.5 g of phosphoryl chloride (POCl₃, 75 mmol) was slowly added into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtain-

ing Compound (27) with a yield of 71%. The synthesis pathway of the above reaction was as follows:




[0081] 14.5 g of Compound (27) (50 mmol), 10 g of Pd/C catalyst (palladium 10% on carbon), and 50 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (28) with a yield of 94%. The synthesis pathway of the above reaction was as follows:


[0082] Next, 600 mg of Compound (28) (2.09 mmol), and 282 mg of IrCl_3 (0.95 mmol), 30 mL of 2-methoxyethanol, and 10 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120°C . After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (29) with a yield of 65%. The synthesis pathway of the above reaction was as follows:



[0083] Next, 595 mg of compound (29) (0.37 mmol), 148 mg of acetyl acetone (1.47 mmol), sodium carbonate 157 mg of (Na_2CO_3 , 1.48 mmol), and 2-methoxyethanol, 30 mL) were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120°C . After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining compound (30) with a yield of 65%. The synthesis pathway of the above reaction was as follows:




[0084] 373 mg of Compound (30) (0.43 mmol), 248 mg of Compound (28) (0.86 mmol), and 15 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200°C . After reacting for 72 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (VI). The synthesis pathway of the above reaction was as follows:



Example 7


Preparation of Organic Metal Compound (VII)

[0085]




Organic metal compound (VII)

[0086] 10.0 g of 2-(2-aminoethyl)thiophene (78.7 mmol) and 100 mL of water were added into a reaction bottle. Next, 17 g of 4-benzyl-benzoyl chloride (78.7 mmol) and sodium hydroxide aqueous solution (20 wt %, 50 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (31) with a yield of 82%. The synthesis pathway of the above reaction was as follows:




[0087] 5.0 g of compound (31) (16.3 mmol) and 100 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 7.4 g of phosphoryl chloride (POCl_3 , 48.8 mmol) was added slowly into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate

was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (32) with a yield of 55%. The synthesis pathway of the above reaction was as follows:








[0088] 5.0 g of Compound (32) (17.3 mmol), 5.0 g of Pd/C catalyst (palladium 10% on carbon), and 30 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux for 24 hours. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (33) with a yield of 80%. The synthesis pathway of the above reaction was as follows:




[0089] Next, 5.0 g of compound (33) (17.4 mmol), and 2360 mg of IrCl_3 (7.9 mmol), 50 mL of 2-methoxyethanol, and 17 mL of water were added into a reaction bottle. Next,

after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (34) with a yield of 65%. The synthesis pathway of the above reaction was as follows:




[0090] Next, 3.0 g of Compound (34) (1.87 mmol), 750 mg of acetyl acetone (7.5 mmol), 790 mg of sodium carbonate (Na_2CO_3 , 7.5 mmol), and 30 mL of 2-methoxyethanol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (35) with a yield of 68%. The synthesis pathway of the above reaction was as follows:


[0091] 1000 mg of Compound (35) (1.16 mmol), 660 mg of Compound (33) (2.3 mmol), and 25 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 72 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (VII). The synthesis pathway of the above reaction was as follows:



Compound (35)



Compound (33)




Organic metal compound (VII)

Example 8




Preparation of Organic Metal Compound (VIII)

[0092]




Organic metal compound (VIII)

[0093] 9.0 g of 2-(2-aminoethyl)-5-methyl-thiophene (63.7 mmol) and 40 mL of water were added into a reaction bottle. Next, 8.9 g of benzoyl chloride (63.7 mmol) and sodium hydroxide aqueous solution (20 wt %, 45 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (36) with a yield of 90%. The synthesis pathway of the above reaction was as follows:




Compound (36)

[0094] 5.0 g of Compound (36) (20.4 mmol) and 30 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 4.7 g of phosphoryl chloride (POCl_3 , 30.6 mmol) was added slowly into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (37) with a yield of 70%. The synthesis pathway of the above reaction was as follows:




Compound (36)

-continued




Compound (37)



Compound (39)


[0095] 11.4 g of Compound (37) (50 mmol), 10 g of Pd/C catalyst (palladium 10% on carbon), and 50 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux for 12 hours. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (38) with a yield of 92%. The synthesis pathway of the above reaction was as follows:



Compound (37)


Compound (38)

[0096] Next, 991 mg of Compound (38) (4.4 mmol), and 598 mg of IrCl_3 (2 mmol), 15 mL of 2-methoxyethanol, and 5 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (39) with a yield of 69%. The synthesis pathway of the above reaction was as follows:





Compound (38)

[0097] Next, 1.3 g of Compound (39) (1 mmol), 300 mg of acetyl acetone (3 mmol), 212 mg of sodium carbonate (Na_2CO_3 , 2 mmol), and 20 mL of 2-methoxyethanol were added into a reaction bottle. Next, After removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (40) with a yield of 75%. The synthesis pathway of the above reaction was as follows:




Compound (39)



Compound (40)

[0098] 3000 mg Compound (40) (4.05 mmol), compound (38) (1820 mg, 8.1 mmol), and 15 mL of glycerol were added into a reaction bottle. Next, After removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtain-


ing Organic metal compound (VIII). The synthesis pathway of the above reaction was as follows:




Example 9

Preparation of Organic Metal Compound (IX)


[0099]



[0100] 9.0 g of 2-(2-aminoethyl)-5-methyl-thiophene (63.7 mmol) and 40 mL of water were added into a reaction bottle. Next, 12.5 g of 4-tert-butylbenzoyl chloride (63.7 mmol) and sodium hydroxide aqueous solution (20 wt %, 45 mL) were added into the reaction bottle at 0° C. A white powder product was separated out during the reaction. Next, after reacting for 12 hours, the mixture was filtrated and the filter cake was collected. Next, the filter cake was ground to fine powders and washed with water and hexane, obtaining Compound (41) with a yield of 85%. The synthesis pathway of the above reaction was as follows:




[0101] 15.1 g of Compound (41) (50 mmol) and 50 mL of toluene were added into a reaction bottle, and the reaction bottle was cooled to 0° C. Next, 11.5 g of phosphoryl chloride (POCl_3 , 75 mmol) was slowly added into the reaction bottle. After the addition was complete, the reaction bottle was heated to reflux. After reacting for 2 hours, the reaction bottle was cooled to 40° C., and sodium hydrogen carbonate was added into the reaction bottle to neutralize the mixture. Next, the result was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining compound (42) with a yield of 74%. The synthesis pathway of the above reaction was as follows:




[0102] 14.2 g of Compound (42) (50 mmol), 10 g of Pd/C catalyst (palladium 10% on carbon), and 50 mL of toluene were added into a reaction bottle. Next, the reaction bottle was heated to reflux. Next, after removing Pd/C catalyst by filtration, the filtrate was extracted three times using ethyl acetate and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography,

obtaining Compound (43) with a yield of 91%. The synthesis pathway of the above reaction was as follows:





[0103] Next, 1238 mg of Compound (43) (4.4 mmol), and 598 mg of IrCl_3 (2 mmol), 2-methoxyethanol, 15 mL, and 5 mL of water were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dried under vacuum, obtaining Compound (44) with a yield of 76%. The synthesis pathway of the above reaction was as follows:




[0104] Next, 1.57 g of Compound (44) (1 mmol), 300 mg acetyl acetone (3 mmol), 212 mg of sodium carbonate (Na_2CO_3 , 2 mmol), and 2-methoxyethanol, 20 mL) were added into a reaction bottle. Next, after removing moisture

and purging nitrogen gas several times, the reaction bottle was heated to 120° C. After reacting for 12 hours and cooling down to room temperature, the result was filtrated. The filter cake was collected and washed with water and hexane, and then dissolved in dichloromethane. Next, the solution was extracted three times using dichloromethane and water. Next, an organic phase was separated and concentrated, and then purified by column chromatography, obtaining Compound (45) with a yield of 71%. The synthesis pathway of the above reaction was as follows:



[0105] 852 mg of Compound (45) (1 mmol), 562 mg of Compound (43) (2 mmol), and 5 mL of glycerol were added into a reaction bottle. Next, after removing moisture and purging nitrogen gas several times, the reaction bottle was heated to 200° C. After reacting for 48 hours, the reaction bottle was cooled to room temperature, and water was added into the reaction bottle to produce precipitate. Finally, the precipitate was collected and washed with ethyl acetate and water, and then purified by column chromatography, obtaining Organic metal compound (IX). The synthesis pathway of the above reaction was as follows:



[0106] Next, thermal degradation temperature (T_d) of Organic metal compounds (I)-(V) was measured by thermogravimetric analyzer (TGA), and the result is shown in Table 1. Next, Organic metal compounds (I)-(V) were dissolved into CH₂Cl₂ individually obtaining solutions with a concentration of 10⁻⁵ M. Next, the photoluminescence (PL) spectra and the maximum luminous intensity peak (Emission λ_{max}) of the solutions were measured, and the results are shown in Table 1.

TABLE 1

	thermal degradation temperature (T_d , ° C.)	maximum luminous intensity peak (Emission λ_{max} , nm)
Organic metal compound (I)	421	560
Organic metal compound (II)	444	556
Organic metal compound (III)	413	552

TABLE 1-continued

	thermal degradation temperature (T_d , ° C.)	maximum luminous intensity peak (Emission λ_{max} , nm)
Organic metal compound (IV)	435	528
Organic metal compound (V)	403	534

[0107] As shown in Table 1, the organic metal compound of the disclosure can have a thermal degradation temperature (T_d) that is higher than 400° C. Therefore, the organic metal compound is suitable for being purified by a sublimation process. In addition, Organic metal compound (I) (with 4-phenylthieno[3,2-c]pyridine ligand) has a maximum luminous intensity peak of 560 nm, and can serve as a yellow phosphorescent material. Furthermore, the organic metal compounds with a modified 4-phenylthieno[3,2-c]pyridine ligand, which the hydrogen bonded in the phenyl group thereof is replaced with an electron withdrawing group (such as fluorine), can exhibit a blue-shifted emission in comparison with Organic metal compound (I). For example, Organic metal compounds (IV) and (V) have a maximum luminous intensity peak of 528 nm and 534 nm respectively, and can serve as green phosphorescent materials.

[0108] Organic Light-Emitting Device

[0109] FIG. 2 shows an embodiment of an organic light-emitting device 10. The organic light-emitting device 10 includes a substrate 12, a bottom electrode 14, an organic light-emitting element 16, and a top electrode 18, as shown in FIG. 2. The organic light-emitting device 10 can be a top-emission, bottom-emission, or dual-emission devices. The substrate 12 can be a glass, plastic, or semiconductor substrate. Suitable materials for the bottom electrode 14 and top electrode 18 can be Ca, Ag, Mg, Al, Li, In, Au, Ni, W, Pt, Cu, indium tin oxide (ITO), indium zinc oxide (IZO), aluminum zinc oxide (AZO), or zinc oxide (ZnO), formed by sputtering, electron beam evaporation, thermal evaporation, or chemical vapor deposition. Furthermore, at least one of the bottom and top electrodes 14 and 18 is transparent.

[0110] The organic light-emitting element 16 at least includes an emission layer, and can further include a hole injection layer, a hole transport layer, an electron transport layer, and an electron injection layer. In an embodiment of the disclosure, at least one layer of the organic light-emitting element 16 includes the aforementioned organometallic compound.

[0111] According to another embodiment of the disclosure, the organic light-emitting device can be a phosphorescent organic light-emitting device, and the emission layer of the organic light-emitting element can include a host material and a dopant, wherein the dopant can include the aforementioned organic compounds. The dose of the dopant is not limited and can optionally be modified by a person of ordinary skill in the field.

[0112] In order to clearly disclose the organic light-emitting devices of the disclosure, the following examples (having an emitting layer employing the organic metal compounds of the disclosure formed by deposition (dry process) or coating (wet process)) are intended to illustrate the disclosure more fully without limiting their scope, since numerous modifications and variations will be apparent to those skilled in this art.

Example 10

Organic Light-Emitting Device (I)

[0113] A glass substrate with an indium tin oxide (ITO) film with a thickness of 150 nm was provided and then washed with a cleaning agent, acetone, and isopropanol with ultrasonic agitation. After drying with nitrogen flow, the ITO film was subjected to a UV/ozone treatment for 30 min.

[0114] Next, PEDOT(poly(3,4)-ethylenedioxythiophen):PSS(e-polystyrenesulfonate) was coated on the ITO film by a blade and spin coating process (with a rotation rate of 4000 rpm) and baked at 100° C. for 40 min to form a PEDOT:PSS film serving as a hole injection layer (with a thickness of 50 nm). Next, TAPC (1,1-bis[4-[N,N'-di(p-tolyl)amino]phenyl]cyclobexane, with a thickness of 40 nm), TCTA (4,4',4'-tri(N-carbazolyl)triphenylamine) doped with Organic metal compound (I) (the weight ratio between TCTA and Organic metal compound (I) was 100:6, with a thickness of 10 nm), TmPyPB (1,3,5-tri(p-pyrid-3-yl-phenyl)benzene, with a thickness of 42 nm), LiF (with a thickness of 0.5 nm), and Al (with a thickness of 120 nm), were subsequently formed on the PEDOT:PSS film at 10⁻⁶ torr, obtaining the organic light-emitting device (I) after encapsulation. The materials and layers formed therefrom are described in the following: ITO/PEDOT/TAPC/TCTA:Organic metal compound (I) (6%)/TmPyPB/LiF/Al

[0115] Next, the optical properties of the light-emitting device (I) were measured by a spectra colorimeter PR650 (purchased from Photo Research Inc.) and a luminance meter LS110 (purchased from Konica Minolta). The results are shown in Table 2.

Example 11

Organic Light-Emitting Device (II)

[0116] Example 11 was performed in the same manner as in Example 10 except that Organic metal compound (II) was substituted for Organic metal compound (I), obtaining the organic light-emitting device (II). The materials and layers formed therefrom are described in the following: ITO/PEDOT/TAPC/TCTA:Organic metal compound (II) (6%)/TmPyPB/LiF/Al

[0117] Next, the optical properties of the light-emitting device (II) were measured by a spectra colorimeter PR650 (purchased from Photo Research Inc.) and a luminance meter LS110 (purchased from Konica Minolta). The results are shown in Table 2.

Example 12

Organic Light-Emitting Device (III)

[0118] Example 12 was performed in the same manner as in Example 11 except that Cs₂CO₃ was substituted for LiF, obtaining the organic light-emitting device (III). The materials and layers formed therefrom are described in the following: ITO/PEDOT/TAPC/TCTA:organic metal compound (II) (6%)/TmPyPB/Cs₂CO₃/Al

[0119] Next, the optical properties of the light-emitting device (III) were measured by a spectra colorimeter PR650 (purchased from Photo Research Inc.) and a luminance meter LS110 (purchased from Konica Minolta). The results are shown in Table 2.

Example 13

Organic Light-Emitting Device (IV)

[0120] Example 13 was performed in the same manner as in Example 10 except that Organic metal compound (III) was substituted for Organic metal compound (I), obtaining the organic light-emitting device (IV). The materials and layers formed therefrom are described in the following: ITO/PEDOT/TAPC/TCTA:Organic metal compound (III) (6%)/TmPyPB/LiF/Al

[0121] Next, the optical properties of the light-emitting device (IV) were measured by a spectra colorimeter PR650 (purchased from Photo Research Inc.) and a luminance meter LS110 (purchased from Konica Minolta). The results are shown in Table 2.

Example 14

Organic Light-Emitting Device (V)

[0122] Example 14 was performed in the same manner as in Example 10 except that Organic metal compound (IV) was substituted for Organic metal compound (I), obtaining the organic light-emitting device (V). The materials and layers formed therefrom are described in the following: ITO/PEDOT/TAPC/TCTA:Organic metal compound (IV) (6%)/TmPyPB/LiF/Al

[0123] Next, the optical properties of the light-emitting device (V) were measured by a spectra colorimeter PR650 (purchased from Photo Research Inc.) and a luminance meter LS110 (purchased from Konica Minolta). The results are shown in Table 2.

TABLE 2

	current efficiency (Cd/A)	power efficiency (lm/W)	maximum luminous intensity peak (nm)	C.I.E coordinate
organic light-emitting device (I)	38.4	24.1	557	(0.48, 0.51)
organic light-emitting device (II)	74.6	46.9	556	(0.48, 0.51)
organic light-emitting device (III)	73.6	66.0	560	(0.49, 0.51)
organic light-emitting device (IV)	67.6	38.6	556	(0.48, 0.52)
organic light-emitting device (V)	48.8	30.7	528	(0.38, 0.59)

[0124] As shown in Table 2, the organic light-emitting devices (I)-(V) of the disclosure have a power efficiency that is equal to or greater than 24.1 lm/W (measured at a brightness of 1000 Cd/m²). When Organic metal compounds (I)-(III) serve as a phosphorescence dopant material of the light-emitting layer, the obtained organic light-emitting devices are yellow organic light-emitting devices. In addition, when Organic metal compound (IV) serves as a phosphorescence dopant material of the light-emitting layer, the obtained organic light-emitting device is a green organic light-emitting device due to the blue-shifted emission resulting from the fluorine-modified 4-phenylthieno[3,2-c]pyridine ligand.

[0125] Moreover, since Cs_2CO_3 was substituted for LiF, the power efficiency of the organic light-emitting device (III) is about 1.41 times higher than that of the organic light-emitting device (II).

Example 15

Organic Light-Emitting Device (VI)

[0126] A glass substrate with an indium tin oxide (ITO) film with a thickness of 150 nm was provided and then washed with a cleaning agent, acetone, and isopropanol with ultrasonic agitation. After drying with nitrogen flow, the ITO film was subjected to a UV/ozone treatment for 30 min.

[0127] PEDOT(poly(3,4)-ethylenedioxythiophen):PSS (e-polystyrenesulfonate) was coated on the ITO film by a blade and spin coating process (with a rotation rate of 4000 rpm) and baked at 100° C. for 40 min to form a PEDOT:PSS film serving as a hole injection layer (with a thickness of 50 nm). Next, a composition was used for forming a light-emitting layer coated on the PEDOT:PSS film by a blade coating process and baked at 100° C. for 40 min to form the light-emitting layer (with a thickness of 30 nm). The composition used for forming a light-emitting layer includes TCTA (4, 4',4'-tri(N-carbazolyl)triphenylamine) and Organic metal compound (II), wherein the weight ratio of TCTA and Organic metal compound (II) was 93:7, dissolved in chlorobenzene. Next, TmPyPB (1,3,5-tri(p-pyrid-3-yl-phenyl) benzene was coated on the light-emitting layer by a spin coating process to form a TmPyPB film (with a thickness of 50 nm). Next, LiF (with a thickness of 1 nm), and Al (with a thickness of 120 nm) were subsequently formed on the TmPyPB film at 10^{-6} torr, obtaining the organic light-emitting device (VI) after encapsulation. The materials and layers formed therefrom are described in the following: ITO/PEDOT/TCTA: Organic metal compound (II) (7%)/TmPyPB/LiF/Al.


[0128] Next, the optical properties of the light-emitting device (VI) were measured by a spectra colorimeter PR650 (purchased from Photo Research Inc.) and a luminance meter LS110 (purchased from Konica Minolta).

[0129] During the formation of the light-emitting device (VI) via a wet process, it shows that Organic metal compound (II) exhibits high solubility when the solvent has a solid content that is greater than 4 wt %. Therefore, the organic metal compound of the disclosure can be uniformly mixed with the host material (TCTA). Furthermore, the organic light-emitting device (VI) fabricated via the wet process has a power efficiency of 13.5 lm/W (measured at a brightness of 1000 Cd/m²).

[0130] While the disclosure has been described by way of example and in terms of the preferred embodiments, it should be understood that the disclosure is not limited to the disclosed embodiments. On the contrary, it is intended to cover various modifications and similar arrangements (as would be apparent to those skilled in the art). Therefore, the scope of the appended claims should be accorded the broadest interpretation so as to encompass all such modifications and similar arrangements.

What is claimed is:

1. An organic metal compound, having a structure of Formula (I):




Formula (I)

wherein, R^1 is independently hydrogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group; R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.

2. The organic metal compound as claimed in claim 1, wherein R^1 is independently hydrogen, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.

3. The organic metal compound as claimed in claim 1, wherein R^2 is independently hydrogen, fluorine, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.

4. The organic metal compound as claimed in claim 1, wherein the organic metal compound has a structure of Formula (II):








Formula (II)


wherein, R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.

5. The organic metal compound as claimed in claim 4, wherein R^2 is independently hydrogen, fluorine, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.

6. The organic metal compound as claimed in claim 4, wherein the organic metal compound is




-continued



7. The organic metal compound as claimed in claim 1, wherein the organic metal compound has a structure of Formula (III):


Formula (III)




wherein, R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.

8. The organic metal compound as claimed in claim 7, wherein R^2 is independently hydrogen, fluorine, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.

9. The organic metal compound as claimed in claim 7, wherein the organic metal compound is









wherein, R^1 is independently hydrogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.



11. The organic metal compound as claimed in claim 10, wherein R^1 is independently hydrogen, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.



12. The organic metal compound as claimed in claim 10, wherein the organic metal compound is




10. The organic metal compound as claimed in claim 1, wherein the organic metal compound has a structure of Formula (IV):

Formula (IV)






13. The organic metal compound as claimed in claim 1, wherein the organic metal compound has a structure of Formula (V):



Formula (V)




16. The organic metal compound as claimed in claim 1, wherein the organic metal compound has a structure of Formula (VI):


wherein, R^2 is independently hydrogen, halogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.

14. The organic metal compound as claimed in claim 13, wherein R^2 is independently hydrogen, fluorine, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.

15. The organic metal compound as claimed in claim 13, wherein the organic metal compound is





Formula (VI)



wherein, R^1 is independently hydrogen, C_{1-12} alkyl group, C_{5-10} cycloalkyl group, C_{3-12} heteroaryl group, or C_{6-12} aryl group.

17. The organic metal compound as claimed in claim 16, wherein R^1 is independently hydrogen, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, isobutyl group, sec-butyl group, tert-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group, octyl group, decyl group, dodecyl group, phenyl group, biphenyl group, or naphthyl group.

18. The organic metal compound as claimed in claim 16, wherein the organic metal compound is



19. An organic light-emitting device, comprising:

a pair of electrodes; and

an organic light-emitting element, disposed between the electrodes, wherein the organic light-emitting element comprises the organic metal compound as claimed in claim 1.

20. The organic light-emitting device as claimed in claim 19, wherein the organic light-emitting element comprises a light-emitting layer, wherein the light-emitting layer comprises a host material and the organic metal compound as claimed in claim 1.

* * * * *

专利名称(译)	有机金属化合物和使用其的有机发光装置		
公开(公告)号	US20160164007A1	公开(公告)日	2016-06-09
申请号	US14/837844	申请日	2015-08-27
[标]申请(专利权)人(译)	财团法人工业技术研究院		
申请(专利权)人(译)	工业技术研究院		
当前申请(专利权)人(译)	工业技术研究院		
[标]发明人	LIN JIN SHENG WU CHENG AN HUANG PANG CHI CHANG MENG HAO YEH HAN CHENG KU CHUN NENG		
发明人	LIN, JIN-SHENG WU, CHENG-AN HUANG, PANG-CHI CHANG, MENG-HAO YEH, HAN-CHENG KU, CHUN-NENG		
IPC分类号	H01L51/00 C09K11/06 C09K11/02 C07F15/00		
CPC分类号	H01L51/0085 C07F15/0033 C09K11/06 C09K11/025 H01L51/0061 H01L51/5016 C09K2211/1029 C09K2211/1092 C09K2211/185 H01L51/0072 C09K2211/1007 C09K2211/1037		
优先权	103141945 2014-12-03 TW		
其他公开文献	US10164199		
外部链接	Espacenet USPTO		

摘要(译)

提供有机金属化合物和使用其的有机发光装置。有机金属化合物具有由式 (I) 表示的化学结构：其中每个R 1可以独立地为氢，C 1-12 烷基，C 5-10 环烷基，C 3- 12 杂芳基，或C 6-12 芳基; R 2 可以独立地为氢，卤素，C 1-12 烷基，C 5-10 环烷基，C 3- 12 杂芳基，或C 6-12 芳基。

