



US 20190027692A1

(19) **United States**

(12) **Patent Application Publication**
Kim

(10) **Pub. No.: US 2019/0027692 A1**
(43) **Pub. Date: Jan. 24, 2019**

(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

H01L 51/50 (2006.01)
C07C 15/28 (2006.01)

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si (KR)

(52) **U.S. Cl.**
CPC *H01L 51/0052* (2013.01); *C09K 11/06* (2013.01); *H01L 51/0072* (2013.01); *C09K 2211/1029* (2013.01); *C07C 15/28* (2013.01); *C09K 2211/1011* (2013.01); *H01L 51/5016* (2013.01)

(72) Inventor: **Seulong Kim**, Yongin-si (KR)

(21) Appl. No.: **15/859,200**

(22) Filed: **Dec. 29, 2017**

(57) **ABSTRACT**

(30) **Foreign Application Priority Data**

Jul. 21, 2017 (KR) 10-2017-0092732

A condensed cyclic compound is represented by Formula 1. An organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode, the organic layer including an emission layer and at least one of the condensed cyclic compound.

Publication Classification

(51) **Int. Cl.**
H01L 51/00 (2006.01)
C09K 11/06 (2006.01)

10

190
150
110

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210

**CONDENSED CYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DEVICE
INCLUDING THE SAME**

**CROSS-REFERENCE TO RELATED
APPLICATION**

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2017-0092732, filed on Jul. 21, 2017, in the Korean Intellectual Property Office, the entire content of which is incorporated herein by reference.

BACKGROUND

1. Field

[0002] One or more embodiments relate to a condensed cyclic compound and an organic light-emitting device including the same.

2. Description of the Related Art

[0003] Organic light-emitting devices are self-emission devices that have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of brightness, driving voltage, and response speed, compared to devices in the art.


[0004] An example of such organic light-emitting devices may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transit (e.g., transition or relax) from an excited state to a ground state, thereby generating light.

SUMMARY

[0005] Aspects of embodiments of the present disclosure provide an organic light-emitting device having a low driving voltage, high efficiency, and a long lifespan.


[0006] Additional aspects of embodiments will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0007] An aspect of an embodiment of the present disclosure provides a condensed cyclic compound represented by Formula 1 below:



Formula 1

-continued



Formula 2

[0008] In Formulae 1 and 2,

[0009] X₁₂ may be N or C(R₁₂), X₁₃ may be N or C(R₁₃), X₁₄ may be N or C(R₁₄), X₁₅ may be N or C(R₁₅), X₁₆ may be N or C(R₁₆), X₁₇ may be N or C(R₁₇), X₁₈ may be N or C(R₁₈), and X₁₉ may be N or C(R₁₉),

[0010] R₁ to R₄ and R₁₁ to R₁₉ may each independently be selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂), provided that R₁₁ to R₁₉ are not the group represented by Formula 2,

[0011] R₁₁ is not hydrogen,

[0012] at least one selected from R₃ and R₄ is the group represented by Formula 2,

[0013] a₁ and a₂ may each independently be an integer from 0 to 4,

[0014] when a₁ is two or more, two or more R₁(s) may be identical to or different from each other, and when a₂ is two or more, two or more R₂(s) may be identical to or different from each other,

[0015] at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the

substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, the substituted monovalent non-aromatic condensed heteropolycyclic group, and the substituted pyridine group may be selected from:

[0016] deuterium, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0017] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

[0018] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

[0019] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —B(Q₂₁)(Q₂₂), —N(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and


[0020] —Si(Q₃₁)(Q₃₂)(Q₃₃), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂);

[0021] Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a


monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group

[0022] * indicates a binding site to a neighboring atom.

[0023] Another aspect of an embodiment of the present disclosure provides a condensed cyclic compound represented by Formula 1 and satisfying conditions of Equations 1 and 2:



Formula 1



Formula 2

$$2E_{T1} < E_{T2}$$

Equation 1

$$2E_{T1} > E_{S1}$$

Equation 2

[0024] X₁₂ to X₁₉, R₁ to R₄, R₁₁ to R₁₉, a₁, and a₂ in Formulae 1 and 2 are the same as described herein,

[0025] in Equations 1 and 2,

[0026] E_{T1} is an energy level of a first triplet excited state of the compound represented by Formula 1,

[0027] E_{T2} is an energy level of a first triplet excited state of a compound represented by Formula 2, and E_{S1} is an energy level of a lowest singlet excited state of the compound represented by Formula 1, and

[0028] E_{T1}, E_{T2}, and E_{S1} are evaluated by using a Density Functional Theory (DFT) method of a Gaussian program structurally optimized at a level of B3LYP/6-31G*(d,p).

[0029] Another aspect of an embodiment provides an organic light-emitting device including: a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode, wherein the organic layer includes an emission layer and at least one of the condensed cyclic compound.

BRIEF DESCRIPTION OF THE DRAWINGS

[0030] These and/or other aspects or embodiments will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings in which:

[0031] FIG. 1 is a schematic view of an organic light-emitting device according to an embodiment;

[0032] FIG. 2 is a schematic view of an organic light-emitting device according to an embodiment;


[0033] FIG. 3 is a schematic view of an organic light-emitting device according to an embodiment; and

[0034] FIG. 4 is a schematic view of an organic light-emitting device according to an embodiment.


DETAILED DESCRIPTION

[0035] Reference will now be made in more detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by referring to the figures, to explain aspects of embodiments. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0036] A condensed cyclic compound according to an embodiment is represented by Formula 1 below:



Formula 1



Formula 2

[0037] In Formula 2, X_{12} may be N or C(R_{12}), X_{13} may be N or C(R_{13}), X_{14} may be N or C(R_{14}), X_{15} may be N or C(R_{15}), X_{16} may be N or C(R_{16}), X_{17} may be N or C(R_{17}), X_{18} may be N or C(R_{18}), and X_{19} may be N or C(R_{19}).

[0038] For example, X_{12} may be C(R_{12}), X_{13} may be C(R_{13}), X_{14} may be C(R_{14}), X_{15} may be C(R_{15}), X_{16} may be C(R_{16}), X_{17} may be C(R_{17}), X_{18} may be C(R_{18}), and X_{19} may be C(R_{19}), but embodiments of the present disclosure are not limited thereto.

[0039] In Formulae 1 and 2, R_1 to R_4 and R_{11} to R_{19} may each independently be selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a

hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted mono-valent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), and —P(=O)(Q_1)(Q_2), provided that R_{11} to R_{19} are not a group represented by Formula 2,

[0040] R_{11} is not hydrogen, and

[0041] at least one selected from R_3 and R_4 is a group represented by Formula 2.

[0042] In one embodiment, R_1 to R_4 and R_{11} to R_{19} may each independently be selected from:

[0043] a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0044] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinoxalinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuran group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuran group, a benzonaphthofuran group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

[0045] a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a

pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a benzonaphthofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a benzonaphthofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); and —Si(Q₁)(Q₂)(Q₃), B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂), and

[0046] Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a biphenyl group, a terphenyl group, a naphthyl group, and a dibenzofuranyl group.

[0047] For example, R₁ and R₂ may each be hydrogen, but embodiments of the present disclosure are not limited thereto.

[0048] For example, R₃ and R₄ may be identical to each other and may each be a group represented by Formula 2, but embodiments of the present disclosure are not limited thereto.

[0049] For example, R₁₁ may be selected from a C₁-C₁₀ alkyl group, a C₆-C₂₀ aryl group, a C₁-C₂₀ heteroaryl group, and —Si(Q₁)(Q₂)(Q₃), and

[0050] Q₁ to Q₃ may each independently be selected from a C₁-C₁₀ alkyl group, a phenyl group, a biphenyl group, and a terphenyl group, but embodiments of the present disclosure are not limited thereto.

[0051] In one embodiment, in Formula 2, i) X₁₄ may be C(R₁₄), X₁₅ may be C(R₁₅), and X₁₆ may be C(R₁₆), and

[0052] ii) at least one selected from R₁₁ and R₁₄ to R₁₆ may be a C₁-C₁₀ alkyl group.

[0053] In one embodiment, R₃ and R₄ may each be a group represented by Formula 2,

[0054] X₁₂ may be C(R₁₂), X₁₃ may be C(R₁₃), X₁₄ may be C(R₁₄), X₁₅ may be C(R₁₅), X₁₆ may be C(R₁₆), X₁₇ may be C(R₁₇), X₁₈ may be C(R₁₈), and X₁₉ may be C(R₁₉), and



[0055] i) R₁₁ may be a C₁-C₁₀ alkyl group, and R₁₂ to R₁₉ may each be hydrogen;

[0056] ii) R₁₁ may be a C₁-C₁₀ alkyl group, R₁₄ or R₁₅ may be a C₁-C₁₀ alkyl group, and R₁₂, R₁₃, and R₁₆ to R₁₉ may each be hydrogen; or

[0057] iii) R₁₁ and R₁₆ may each be a C₁-C₁₀ alkyl group, and R₁₂ to R₁₅ and R₁₇ to R₁₉ may each be hydrogen.

[0058] a1 and a2 in Formula 1 respectively indicate the number of R₁(s) and the number of R₂(s). a1 and a2 may each independently be an integer from 0 to 4, wherein, when a1 is two or more, two or more R₁(s) may be identical to or different from each other, and when a2 is two or more, two or more R₂(s) may be identical to or different from each other.

[0059] In one embodiment, the compound represented by Formula 1 may be selected from Compounds 1 to 3:




1

2

-continued

3



[0060] In some embodiments, the compound represented by Formula 1 satisfies conditions of Equations 1 and 2:

$$2E_{T1} < E_{T2} \quad \text{Equation 1}$$

$$2E_{T1} > E_{S1} \quad \text{Equation 2}$$

[0061] In Equations 1 and 2,

[0062] E_{T1} is an energy level of a first triplet excited state of the compound represented by Formula 1,


[0063] E_{T2} is an energy level of a first triplet excited state of the compound represented by Formula 2, and E_{S1} is an energy level of a lowest singlet excited state of the compound represented by Formula 1, and

[0064] E_{T1} , E_{T2} , and E_{S1} are evaluated (e.g., calculated or computed) by using a density functional theory (DFT) method of Gaussian program (e.g., Gaussian 16, available from Gaussian, Inc. of Wallingford, Conn.) structurally optimized at a level of B3LYP/6-31G*(d,p) (e.g., using the B3LYP hybrid functional and the 6-31G*(d,p) basis set).


[0065] Since the condensed cyclic compound represented by Formula 1 satisfies the conditions of Equations 1 and 2, triplet energy of the condensed cyclic compound is effectively up-converted into a singlet state through interaction with an adjacent triplet. Therefore, the emission layer including the condensed cyclic compound may emit high-efficiency delayed fluorescence.

[0066] Also, the compound represented by Formula 1 has a singlet conversion efficiency of about 40% to about 62.5%, and the singlet conversion efficiency is evaluated by using a transient EL apparatus.

[0067] In one embodiment, a dihedral angle between a plane P1 including a moiety represented by



and a plane P2 including a moiety represented by



in Formula 2 may be about 60° or more, and * and *¹ each indicate a binding site to a neighboring atom. For example, the dihedral angle between the planes P1 and P2 may be in a range of about 60° to about 82°.

[0068] Since the dihedral angle between the planes P1 and P2 is about 60° or more, a conjugate structure between a ligand and a core is cut off to maintain high triplet energy of the ligand. Accordingly, the ligand may have more than twice the triplet energy of the core. Consequently, excellent delayed fluorescence characteristics may be exhibited.


[0069] For example, since the condensed cyclic compound represented by Formula 1 excludes hydrogen from R_{11} in Formula 2, the dihedral angle of 60° or more may be exhibited between the planes P1 and P2 by the principle of forming a large angle between ligands by introducing a substituent (for example, a methyl group) having greater steric hindrance than that of hydrogen to cause steric hindrance between the ligands. If R_{11} in Formula 2 is hydrogen, the dihedral angle between the planes P1 and P2 becomes less than 60° or less, and thus, it is difficult to exhibit excellent delayed fluorescence characteristics implemented in embodiments of the present disclosure.

[0070] Furthermore, the condensed cyclic compound does not include substituents other than hydrogen at positions other than 9- and 10-positions of an anthracene core. When a substituent other than hydrogen, e.g., an aromatic compound, is substituted at anthracene, a singlet energy (S1) thereof may be reduced. Thus, in order to prevent such reduction (or to reduce a likelihood or amount of such a reduction), only hydrogen may be substituted at positions other than 9- and 10-positions of an anthracene core, the positions being involved in emission. Accordingly, the singlet energy (S1) may be maintained, which may enable the anthracene core to serve as a receptor emitting a deep blue light.


[0071] A synthesis method of the condensed cyclic compound represented by Formula 1 may be readily apparent to those of ordinary skill in the art when referring to the Examples provided below.

[0072] Another aspect of an embodiment provides a condensed cyclic compound represented by Formula 1 and satisfy conditions of Equations 1 and 2:

Formula 1



-continued



Formula 2

$$2E_{T1} < E_{T2}$$

Equation 1

$$2E_{T1} > E_{S1}$$

Equation 2

[0073] X_{12} to X_{19} , R_1 to R_4 , R_{11} to R_{19} , a_1 , and a_2 in Formulae 1 and 2 are the same as described herein,

[0074] in Equations 1 and 2,

[0075] E_{T1} is an energy level of a first triplet excited state of the compound represented by Formula 1,

[0076] E_{T2} is an energy level of a second triplet excited state of a compound represented by Formula 1, and E_{S1} is an energy level of a lowest singlet excited state of the compound represented by Formula 1, and

[0077] E_{T1} , E_{T2} , and E_{S1} are evaluated by using a DFT method of Gaussian program structurally optimized at a level of B3LYP/6-31G*(d,p) (e.g., calculated using a density functional theory method using a B3LYP hybrid functional and a 6-31G*(d,p) basis set).


[0078] When the triplet energy of the structure represented by Formula 2 (e.g., the ligand) is more than twice the triplet energy of the structure represented by Formula 1 (e.g., the core) an organic light-emitting device using the condensed cyclic compound as an acceptor may exhibit excellent delayed fluorescence characteristics.

[0079] Another aspect of an embodiment provides an organic light-emitting device including: a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes at least one of the condensed cyclic compound described herein.

[0080] In one embodiment, the emission layer may include the compound represented by Formula 1, and the emission layer may emit blue light having an upper (e.g., a maximum) emission wavelength of about 420 nm to about 470 nm.

[0081] For example, the emission layer may further include a fluorescent luminescent material, an amount of the compound represented by Formula 1 may be larger than an amount of the fluorescent luminescent material, and the compound represented by Formula 1 in the emission layer may act as a host.

[0082] For example, the fluorescent luminescent material may include an arylamine compound or a styrylamine compound, or include a compound represented by Formula 501:



Formula 501

[0083] In Formula 501,

[0084] Ar_{501} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0085] L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0086] xd_1 to xd_3 may each independently be an integer from 0 to 3,

[0087] R_{501} and R_{502} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

[0088] xd_4 may be an integer from 1 to 6.

[0089] In one embodiment, the first electrode may be an anode, the second electrode may be a cathode, the organic layer may include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode, the hole transport region may include a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and the electron transport region may include a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or any combination thereof.

[0090] For example, the hole transport region may include at least one selected from hole injection layer, the hole transport layer, the buffer layer, and the electron blocking layer, and the electron transport region may include at least one selected from the hole blocking layer, the electron transport layer, and the electron injection layer.

[0091] For example, the hole transport region may include a p-dopant, and the p-dopant may have a lowest unoccupied molecular orbital (LUMO) energy level of about -3.5 eV or less. For example, the p-dopant may include a cyano group-containing compound.

[0092] The statement “(an organic layer) includes at least one condensed cyclic compound,” as used herein, may include a case in which “(an organic layer) includes identical compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different condensed cyclic compounds.”

[0093] The term “organic layer,” as used herein, refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0094] [Description of FIG. 1]

[0095] FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

[0096] Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing the organic light-emitting device 10 will be described in connection with FIG. 1.

[0097] [First Electrode 110]

[0098] In FIG. 1, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0099] The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for a first electrode may be selected from materials with a high work function to facilitate hole injection.

[0100] The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming a first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and any combinations thereof, but embodiments of the present disclosure are not limited thereto. In one or more embodiments, when the first electrode 110 is a semi-transmissive electrode or a reflectable electrode, a material for forming a first electrode may be selected from magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), and any combinations thereof, but embodiments of the present disclosure are not limited thereto.

[0101] The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 110 is not limited thereto.

[0102] [Organic Layer 150]

[0103] The organic layer 150 is disposed on the first electrode 110. The organic layer 150 may include an emission layer.

[0104] The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer, and an electron transport region between the emission layer and the second electrode 190.

[0105] [Hole Transport Region in Organic Layer 150]


[0106] The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0107] The hole transport region may include at least one layer selected from a hole injection layer, a hole transport layer, an emission auxiliary layer, and an electron blocking layer.


[0108] For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure

having a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode 110 in this stated order, but the structure of the hole transport region is not limited thereto.

[0109] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




-continued




2-TNATA


-continued




Spiro-TPD




Spiro-NPB




NPB




methylated NPB




β -NPB




TAPC




TPD



HMTPD



Formula 201



Formula 202

[0110] In Formulae 201 and 202,

[0111] L_{201} to L_{204} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

[0112] L_{205} may be selected from $*\text{---O---}^*$, $*\text{---S---}^*$, $*\text{---N}(\text{Q}_{201})\text{---}^*$, a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_2 - C_{20} alkenylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

[0113] xa1 to xa4 may each independently be an integer from 0 to 3,

[0114] xa5 may be an integer from 1 to 10, and

[0115] R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0116] For example, in Formula 202, R_{201} and R_{202} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.

[0117] In one embodiment, in Formulae 201 and 202,

[0118] L_{201} to L_{205} may each independently be selected from:

[0119] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene

group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

[0120] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylenylene group, a pentacenylenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, ---F , ---Cl , ---Br , ---I , a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with ---F , a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzofuranyl group, a benzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, $\text{---Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $\text{---N}(\text{Q}_{31})(\text{Q}_{32})$, and

[0121] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0122] In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

[0123] In one or more embodiments, xa5 may be 1, 2, 3, or 4.

[0124] In one or more embodiments, R_{201} to R_{204} and Q_{201} may each independently be selected from:

[0125] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenylyl group, a picenyl group, a perylenyl group, a pentaphenylyl group, a hexacenylyl group, a pentacenylyl group, a rubicenylyl group, a coronenylyl group, an ovalenylyl group, a thiophenylyl group, a furanylyl group, a carbazolyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenylyl group, a dibenzofuranylyl group, a dibenzothiophenylyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

[0126] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenylyl group, a picenyl group, a perylenyl group, a pentaphenylyl group, a hexacenylyl group, a pentacenylyl group, a rubicenylyl group, a coronenylyl group, an ovalenylyl group, a thiophenylyl group, a furanylyl group, a carbazolyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenylyl group, a dibenzofuranylyl group, a dibenzothiophenylyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenylyl group, a picenyl group, a perylenyl group, a pentaphenylyl group, a hexacenylyl group, a pentacenylyl group, a rubicenylyl group, a coronenylyl group, an ovalenylyl group, a thiophenylyl group, a furanylyl group, a carbazolyl group, an indolylyl group, an isoindolylyl group, a benzofuranylyl group, a benzothiophenylyl group, a dibenzofuranylyl group, a dibenzothiophenylyl group, a benzocarbazolyl group, a dibenzocarbazolyl group,

a dibenzosilolyl group, a pyridinyl group, —Si(Q_{31})(Q_{32})(Q_{33}), and —N(Q_{31})(Q_{32}), and

[0127] Q_{31} to Q_{33} are the same as described herein.

[0128] In one or more embodiments, at least one selected from R_{201} to R_{203} in Formula 201 may each independently be selected from:

[0129] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0130] a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0131] but embodiments of the present disclosure are not limited thereto.

[0132] In one or more embodiments, in Formula 202, i) R_{201} and R_{202} may be linked via a single bond, and/or ii) R_{203} and R_{204} may be linked via a single bond.

[0133] In one or more embodiments, at least one selected from R_{201} to R_{204} in Formula 202 may be selected from:


[0134] a carbazolyl group; and

[0135] a carbazolyl group, substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,


[0136] but embodiments of the present disclosure are not limited thereto.

[0137] The compound represented by Formula 201 may be represented by Formula 201A:


Formula 201A




[0138] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A(1) below, but embodiments of the present disclosure are not limited thereto:




[0139] In one embodiment, the compound represented by Formula 201 may be represented by Formula 201A-1 below, but embodiments of the present disclosure are not limited thereto:



[0140] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A:



[0141] In one embodiment, the compound represented by Formula 202 may be represented by Formula 202A-1:



[0142] In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,


[0143] L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ are the same as described elsewhere herein,

[0144] R₂₁₁ and R₂₁₂ may be understood by referring to the description provided herein in connection with R₂₀₃.


[0145] R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0146] The hole transport region may include at least one compound selected from Compounds HT1 to HT39, but embodiments of the present disclosure are not limited thereto:


HT1




HT2



HT3





HT4





-continued
HT5

HT6



HT7



HT8



-continued



HT9

HT10



HT11



HT12



-continued



HT13

HT14





HT15

HT16



HT17


HT18



-continued


HT19

HT20




HT21

HT22





-continued

HT23





HT24

HT25



HT26


HT27



-continued


HT28

HT29




HT30

HT31




HT32

HT33




-continued


HT34




HT35




HT36




HT37



HT38



HT39



[0147] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one selected from a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, suitable or satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0148] The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described herein.

[0149] [P-Dopant]

[0150] The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0151] The charge-generation material may be, for example, a p-dopant.

[0152] In one embodiment, the p-dopant may have a lowest unoccupied molecular orbital (LUMO) energy level of about -3.5 eV or less.

[0153] The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments of the present disclosure are not limited thereto.

[0154] For example, the p-dopant may include at least one selected from:



[0155] a quinone derivative, such as tetracyanoquinodimethane (TCNQ) or 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

[0156] a metal oxide, such as tungsten oxide or molybdenum oxide;


[0157] HAT-CN (1,4,5,8,9,12-hexaazatriphenylenehexacarbonitrile); and

[0158] a compound represented by Formula 221 below;

[0159] but embodiments of the present disclosure are not limited thereto:



Formula 221



[0160] In Formula 221,

[0161] R_{221} to R_{223} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, provided that at least one selected from R_{221} to R_{223} has at least one substituent selected from a cyano group, -F, -Cl, -Br, -I, a C_1 - C_{20} alkyl group substituted with -F, a C_1 - C_{20} alkyl group substituted with -Cl, a C_1 - C_{20} alkyl group substituted with -Br, and a C_1 - C_{20} alkyl group substituted with -I.

[0162] [Emission Layer in Organic Layer 150]

[0163] When the organic light-emitting device 10 is a full-color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or are separated from each other. In one or more embodiments, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

[0164] The emission layer may include a host and a dopant. The dopant may include at least one selected from a phosphorescent dopant and a fluorescent dopant.

[0165] In the emission layer, an amount of the dopant may be in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

[0166] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0167] [Host in Emission Layer]

[0168] The host may include a compound represented by Formula 1.

[0169] In one or more embodiments, the host may further include a compound represented by Formula 301 below.



[0170] In Formula 301,

[0171] Ar_{301} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

[0172] $\text{xb}11$ may be 1, 2, or 3,

[0173] L_{301} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

[0174] $\text{xb}1$ may be an integer from 0 to 5,

[0175] R_{301} may be selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ alkyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{60}$ alkenyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{60}$ alkynyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ alkoxy group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{301})(\text{Q}_{302})(\text{Q}_{303})$, $-\text{N}(\text{Q}_{301})$

(Q_{302}) , $-\text{B}(\text{Q}_{301})(\text{Q}_{302})$, $-\text{C}(=\text{O})(\text{Q}_{301})$, $-\text{S}(=\text{O})_2(\text{Q}_{301})$, and $-\text{P}(=\text{O})(\text{Q}_{301})(\text{Q}_{302})$,

[0176] $\text{xb}21$ may be an integer from 1 to 5, and

[0177] Q_{301} to Q_{303} may each independently be selected from a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.


[0178] In one embodiment, Ar_{301} in Formula 301 may be selected from:

[0179] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothioephene group; and


[0180] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothioephene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and

[0181] Q_{31} to Q_{33} may each independently be selected from $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto. In Formula 301, when $\text{xb}11$ is two or more, two or more of $\text{Ar}_{301}(\text{s})$ may be linked via a single bond.

[0182] In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



Formula 301-1



Formula 301-2

[0183] In Formulae 301-1 and 301-2,

[0184] A_{301} to A_{304} may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group, a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

[0185] X_{301} may be O, S, or N- $[(L_{304})_{xb4}-R_{304}]$,

[0186] R_{311} to R_{314} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

[0187] $xb22$ and $xb23$ may each independently be 0, 1, or 2,

[0188] L_{301} , $xb1$, R_{301} , and Q_{31} to Q_{33} are the same as described elsewhere herein,

[0189] L_{302} to L_{304} may each independently be the same as described in connection with L_{301} ,

[0190] $xb2$ to $xb4$ may each independently be the same as described in connection with $xb1$, and

[0191] R_{302} to R_{304} may each independently be the same as described in connection with R_{301} .

[0192] For example, in Formulae 301, 301-1, and 301-2, L_{301} to L_{304} may each independently be selected from:

[0193] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a benzimidazolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazininylenylene group, a quinolininylenylene group, an isoquinolininylenylene group, a benzoquinolininylenylene group, a phthalazininylenylene group, a naphthyridinylenylene group, a quinoxalininylenylene group, a quinazolininylenylene group, a cinnolininylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazininylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group; and

[0194] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a benzimidazolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazininylenylene group, a quinolininylenylene group, an isoquinolininylenylene group, a benzoquinolininylenylene group, a phthalazininylenylene group, a naphthyridinylenylene group, a quinoxalininylenylene group, a quinazolininylenylene group, a cinnolininylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazininylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

[0195] Q_{31} and Q_{33} may be the same as described elsewhere herein.

[0196] In one embodiment, in Formulae 301, 301-1, and 301-2, R_{301} to R_{304} may each independently be selected from:

[0197] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


[0198] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexaceny group, a pentaceny group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a diben-

zocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), and


[0199] Q₃₁ and Q₃₃ may be the same as described elsewhere herein.

[0200] In one or more embodiments, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.


[0201] The host may include at least one selected from 9,10-di-(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55, but embodiments of the present disclosure are not limited thereto:



H1




H2




H3


-continued




H4




H5




H6



H7




H8




H9


-continued




H10




H11



H12




H13




H14

-continued


H15




H16




H17



H18




H19




-continued


H20




H21




H22



H23




-continued




H24

-continued




H27


H25




H28




H26



H29




-continued




H30


-continued




H35




H31




H36




H32




H37



H33




H34




H38


-continued



H39




H40




H41


-continued



H42




H43




H44

-continued




H45


-continued




H50




H51




H46




H52




H47




H53



H48




H54



H49


-continued




H55

[0202] [Phosphorescent Dopant included in Emission Layer in Organic Layer 150]

[0203] The phosphorescent dopant may include an organometallic complex represented by Formula 401 below:



Formula 401



Formula 402

[0204] In Formulae 401 and 402,

[0205] M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

[0206] L_{401} may be selected from ligands represented by Formula 402, and $xc1$ may be 1, 2, or 3, wherein, when $xc1$ is two or more, two or more $L_{401}(s)$ may be identical to or different from each other,

[0207] L_{402} may be an organic ligand, and $xc2$ may be an integer from 0 to 4, wherein, when $xc2$ is two or more, two or more $L_{402}(s)$ may be identical to or different from each other,

[0208] X_{401} to X_{404} may each independently be nitrogen or carbon,

[0209] X_{401} and X_{403} may be linked via a single bond or a double bond, and X_{402} and X_{404} may be linked via a single bond or a double bond,

[0210] A_{401} and A_{402} may each independently be selected from a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

[0211] X_{405} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{411})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{411})=*$, or $*=C(Q_{411})-*$, wherein Q_{411} and Q_{412} may each independently be hydro-

gen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

[0212] X_{406} may be a single bond, O, or S,

[0213] R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_{401})(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$, wherein Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

[0214] $xc11$ and $xc12$ may each independently be an integer from 0 to 10, and

[0215] $*$ and $*'$ in Formula 402 each indicate a binding site to M in Formula 401.

[0216] In one embodiment, in Formula 402, A_{401} and A_{402} may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

[0217] In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) X_{401} and X_{402} may each be nitrogen concurrently (e.g., at the same time).

[0218] In one or more embodiments, R_{401} and R_{402} in Formula 401 may each independently be selected from:

[0219] hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0220] a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

[0221] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0222] a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0223] —Si(Q₄₀₁)(Q₄₀₂)(Q₄₀₃), —N(Q₄₀₁)(Q₄₀₂), —B(Q₄₀₁)(Q₄₀₂), —C(=O)(Q₄₀₁), —S(=O)₂(Q₄₀₁), and —P(=O)(Q₄₀₁)(Q₄₀₂), and


[0224] Q₄₀₁ to Q₄₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but are not limited thereto.

[0225] In one or more embodiments, when xc1 in Formula 401 is two or more, two A₄₀₁(s) in two or more L₄₀₁(s) may optionally be linked via X₄₀₇, which is a linking group, or two A₄₀₂(s) in two or more L₄₀₁(s) may optionally be linked via X₄₀₈, which is a linking group (see Compounds PD1 to PD4 and PD7). X₄₀₇ and X₄₀₈ may each independently be a single bond, *—O—*, *—C(=O)—*, *—N(Q₄₁₃)—*, *—C(Q₄₁₃)(Q₄₁₄)—*, or *—C(Q₄₁₃)=C(Q₄₁₄)—* (wherein Q₄₁₃ and Q₄₁₄ may each independently be hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group), but embodiments of the present disclosure are not limited thereto.


[0226] L₄₀₂ in Formula 401 may be a monovalent, divalent, or trivalent organic ligand. For example, L₄₀₂ may be selected from halogen, diketone (for example, acetylacetonate), carboxylic acid (for example, picolinate), —C(=O), isonitrile, —CN, and phosphorus (for example, phosphine, or phosphite), but embodiments of the present disclosure are not limited thereto.

[0227] In one or more embodiments, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25, but embodiments of the present disclosure are not limited thereto:


PD1




PD2




PD3









PD4



PD5




-continued




-continued

PD6




PD12

PD7



PD13


PD8



PD14


PD9

PD10








PD15

PD11




PD16

-continued




-continued

PD17




PD18


PD19



PD20



PD21



PD22

PD23


PD24

PD25

[0228] [Fluorescent Dopant in Emission Layer]

[0229] The fluorescent dopant may include an arylamine compound or a styrylamine compound.

[0230] The fluorescent dopant may include a compound represented by Formula 501 below:



Formula 501

[0231] In Formula 501,

[0232] Ar_{501} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

[0233] L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0234] $xd1$ to $xd3$ may each independently be an integer of 0 to 3,

[0235] R_{501} and R_{502} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

[0236] $xd4$ may be an integer of 1 to 6.

[0237] In one embodiment, Ar_{501} in Formula 501 may be selected from:

[0238] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

[0239] a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl

group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0240] In one or more embodiments, L_{501} to L_{503} in Formula 501 may each independently be selected from:

[0241] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

[0242] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

[0243] In one or more embodiments, R_{501} and R_{502} in Formula 501 may each independently be selected from:




[0244] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

[0245] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃), and

[0246] Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


[0247] In one or more embodiments, xd4 in Formula 501 may be 2, but embodiments of the present disclosure are not limited thereto.

[0248] For example, the fluorescent dopant may be selected from Compounds FD1 to FD22:




-continued

FD5




-continued


FD8




FD6




FD9




FD7




FD10




-continued




-continued




FD12




FD17




FD13



FD18





FD14




FD19

FD15




-continued

FD20




FD21




-continued


FD22




[0249] In one or more embodiments, the fluorescent dopant may be selected from the following compounds, but embodiments of the present disclosure are not limited thereto:



DPVBi



DPAVBi



[0250] [Electron Transport Region in Organic Layer 150]

[0251] The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0252] The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer, but embodiments of the present disclosure are not limited thereto.

[0253] For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from an emission layer. However, embodiments of the structure of the electron transport region are not limited thereto.

[0254] The electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region) may include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.

[0255] The " π electron-depleted nitrogen-containing ring" indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

[0256] For example, the " π electron-depleted nitrogen-containing ring" may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed with each other (e.g., combined together), or iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, is condensed with (e.g., combined together with) at least one C_5 - C_{60} carbocyclic group.

[0257] Examples of the π electron-depleted nitrogen-containing ring include an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a

pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, but are not limited thereto.

[0258] For example, the electron transport region may include a compound represented by Formula 601:



[0259] In Formula 601,

[0260] Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

[0261] $\text{xe}11$ may be 1, 2, or 3,

[0262] L_{601} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

[0263] $\text{xe}1$ may be an integer from 0 to 5,

[0264] R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{601})(\text{Q}_{602})(\text{Q}_{603})$, $-\text{C}(=\text{O})(\text{Q}_{601})$, $-\text{S}(=\text{O})_2(\text{Q}_{601})$, and $-\text{P}(=\text{O})(\text{Q}_{601})(\text{Q}_{602})$.

[0265] Q_{601} to Q_{603} may each independently be a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

[0266] $\text{xe}21$ may be an integer from 1 to 5.

[0267] In one embodiment, at least one of $\text{Ar}_{601}(\text{s})$ in the number of $\text{xe}11$ and $\text{R}_{601}(\text{s})$ in the number of $\text{xe}21$ may include the π electron-depleted nitrogen-containing ring.

[0268] In one embodiment, ring Ar_{601} in Formula 601 may be selected from:

[0269] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a

pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

[0270] a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazole group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$ and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and


[0271] Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0272] When $\text{xe}11$ in Formula 601 is two or more, two or more $\text{Ar}_{601}(\text{s})$ may be linked via a single bond.

[0273] In one or more embodiments, Ar_{601} in Formula 601 may be an anthracene group.

[0274] In one or more embodiments, a compound represented by Formula 601 may be represented by Formula 601-1:

Formula 601-1



[0275] In Formula 601-1,

[0276] X_{614} may be N or C(R_{614}), X_{615} may be N or C(R_{615}), X_{616} may be N or C(R_{616}), and at least one selected from X_{614} to X_{616} may be N,

[0277] L_{611} to L_{613} may each independently be the same as described in connection with L_{601} ,

[0278] $xe611$ to $xe613$ may each independently be the same as described in connection with $xe1$,

[0279] R_{611} to R_{613} may each independently be the same as described in connection with R_{601} ,

[0280] R_{614} to R_{616} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0281] In one embodiment, L_{601} and L_{611} to L_{613} in Formulae 601 and 601-1 may each independently be selected from:

[0282] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylylene group, a pyrenylylene group, a chrysenylylene group, a perylynylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazololylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazololylylene group, an isoxazololylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a pyridazinylylene group, a triazinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinnolinylylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a phenazinylylene group, a benzimidazololylylene group, an isobenzothiazolylylene group, a benzoxazololylylene group, an isobenzoxazololylylene group, a triazololylylene group, a tetrazolylylene group, an imidazopyridinylylene group, an imidazopyrimidinylylene group, and an azacarbazolylylene group; and

[0283] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylylene group, a pyrenylylene group, a chrysenylylene group, a perylynylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a thiophenylylene group, a furanylylene group, a carbazolylylene group, an indolylylene group, an isoindolylylene group, a benzofuranylylene group, a benzothiophenylylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a dibenzosilolylylene group, a pyridinylylene group, an imidazololylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazololylylene group, an isoxazololylylene group, a thiadiazolylylene group, an oxadiazolylylene group, a pyrazinylylene group, a pyrimidinylylene group, a

pyridazinylylene group, a triazinylylene group, a quinolinylylene group, an isoquinolinylylene group, a benzoquinolinylylene group, a phthalazinylylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylylene group, a cinnolinylylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a phenazinylylene group, a benzimidazololylylene group, an isobenzothiazolylylene group, a benzoxazololylylene group, an isobenzoxazololylylene group, a triazololylylene group, a tetrazolylylene group, an imidazopyridinylylene group, an imidazopyrimidinylylene group, and an azacarbazolylylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenylyl group, a triphenylylyl group, a pyrenyl group, a chrysenyl group, a perylynyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinylyl group, an isoquinolinylyl group, a benzoquinolinylyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylyl group, a quinazolinylyl group, a cinnolinylyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinylyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group,

[0284] but embodiments of the present disclosure are not limited thereto.

[0285] In one or more embodiments, $xe1$ and $xe611$ to $xe613$ in Formulae 601 and 601-1 may each independently be 0, 1, or 2.

[0286] In one or more embodiments, in Formulae 601 and 601-1, R_{601} and R_{611} to R_{613} may each independently be selected from:

[0287] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenylyl group, a triphenylylyl group, a pyrenyl group, a chrysenyl group, a perylynyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinylyl group, an isoquinolinylyl group, a benzoquinolinylyl

group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

[0288] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylyl group, a pentacenylyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzox-


azolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and

[0289] —S(=O)₂(Q₆₀₁) and —P(=O)(Q₆₀₁)(Q₆₀₂), and


[0290] Q₆₀₁ and Q₆₀₂ may be the same as described elsewhere herein.

[0291] The electron transport region may include at least one compound selected from Compounds ET1 to ET36, but embodiments of the present disclosure are not limited thereto:


ET1



ET2




-continued




ET3


-continued




ET6




ET4



ET7




ET5




ET8

-continued




ET9

-continued





ET11

ET12




ET10

ET13




-continued




ET14


-continued




ET17




ET15



ET18




ET16




ET19

-continued




ET20

-continued




ET23

ET24





ET21




ET22

ET25




-continued




ET32

-continued




ET35

ET33






ET36



[0292] In one or more embodiments, the electron transport region may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BALq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ:

ET34

Alq₃



[0293] Thicknesses of the buffer layer, the hole blocking layer, and the electron control layer may each be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.


[0294] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the foregoing range, the electron transport layer may have suitable or satisfactory electron transport characteristics without a substantial increase in driving voltage.

[0295] The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described herein, a metal-containing material.

[0296] The metal-containing material may include at least one selected from alkali metal complex and alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a

hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenyloxazole, a hydroxy phenylthiazole, a hydroxy diphenyloxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

[0297] For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2:



[0298] The electron transport region may include an electron injection layer that facilitates injection of electrons from the second electrode 190. The electron injection layer may directly contact the second electrode 190.

[0299] The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

[0300] The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof.

[0301] The alkali metal may be selected from Li, a Na, K, Rb, and Cs. In one embodiment, the alkali metal may be Li, a Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs, but embodiments of the present disclosure are not limited thereto.

[0302] The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

[0303] The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

[0304] The alkali metal compound, the alkaline earth-metal compound, and the rare earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare earth metal.

[0305] The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, or KI. In one embodiment, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI, but embodiments of the present disclosure are not limited thereto.

[0306] The alkaline earth-metal compound may be selected from alkaline earth-metal oxides, such as BaO, SrO, CaO, $Ba_xSr_{1-x}O$ ($0 < x < 1$), or $Ba_xCa_{1-x}O$ ($0 < x < 1$). In one embodiment, the alkaline earth-metal compound may be selected from BaO, SrO, and CaO, but embodiments of the present disclosure are not limited thereto.

[0307] The rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one embodiment, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments of the present disclosure are not limited thereto.

[0308] The alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include an ion of alkali metal, alkaline earth-metal, and rare earth metal as described herein, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare earth metal complex may be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenyloxazole, hydroxy phenylthiazole, hydroxy diphenyloxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

[0309] The electron injection layer may include (or consist of) an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof, as described herein. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

[0310] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the foregoing range, the electron injection layer may have suitable or satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0311] [Second Electrode 190]

[0312] The second electrode 190 may be disposed on the organic layer 150 having such a structure. The second electrode 190 may be a cathode which is an electron injection electrode, and in this regard, a material for forming the second electrode 190 may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function.

[0313] The second electrode 190 may include at least one selected from lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al-Li), calcium (Ca), magnesium-indium (Mg-In), magnesium-silver (Mg-Ag), ITO, and IZO, but embodiments of the present disclosure

are not limited thereto. The second electrode 190 may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

[0314] The second electrode 190 may have a single-layered structure, or a multi-layered structure including two or more layers.

[0315] [Description of FIGS. 2 to 4]

[0316] An organic light-emitting device 20 of FIG. 2 includes a first capping layer 210, a first electrode 110, an organic layer 150, and a second electrode 190 which are sequentially stacked in this stated order, an organic light-emitting device 30 of FIG. 3 includes a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220 which are sequentially stacked in this stated order, and an organic light-emitting device 40 of FIG. 4 includes a first capping layer 210, a first electrode 110, an organic layer 150, a second electrode 190, and a second capping layer 220.

[0317] Regarding FIGS. 2 to 4, the first electrode 110, the organic layer 150, and the second electrode 190 may be understood by referring to the description presented in connection with FIG. 1.

[0318] In the organic layer 150 of each of the organic light-emitting devices 20 and 40, light generated in an emission layer may pass through the first electrode 110, which is a semi-transmissive electrode or a transmissive electrode, and the first capping layer 210 toward the outside, and in the organic layer 150 of each of the organic light-emitting devices 30 and 40, light generated in an emission layer may pass through the second electrode 190, which is a semi-transmissive electrode or a transmissive electrode, and the second capping layer 220 toward the outside.

[0319] The first capping layer 210 and the second capping layer 220 may increase external luminescent efficiency according to the principle of constructive interference.





[0320] The first capping layer 210 and the second capping layer 220 may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

[0321] At least one selected from the first capping layer 210 and the second capping layer 220 may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, a naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be optionally substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include an amine-based compound.

[0322] In one embodiment, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include the compound represented by Formula 201 or the compound represented by Formula 202.


[0323] In one or more embodiments, at least one selected from the first capping layer 210 and the second capping layer 220 may each independently include a compound selected

from Compounds HT28 to HT33 and Compounds CP1 to CP5, but embodiments of the present disclosure are not limited thereto:



-continued

CP5



[0324] Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with FIGS. 1 to 4. However, embodiments of the present disclosure are not limited thereto.

[0325] Layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region may be formed in a certain region by using one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

[0326] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by vacuum deposition, the vacuum deposition may be performed at a deposition temperature of about 100° C. to about 500° C., at a vacuum degree of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition speed of about 0.01 Å/sec to about 100 Å/sec by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0327] When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to about 200° C. by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[0328] [General Definitions of some of the Substituents]

[0329] The term “C₁-C₆₀ alkyl group,” as used herein, refers to a linear or branched aliphatic saturated hydrocarbon monovalent group having 1 to 60 carbon atoms, and examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₆₀ alkyl group.

[0330] The term “C₂-C₆₀ alkenyl group,” as used herein, refers to a hydrocarbon group having at least one carbon-carbon double bond in a main chain (e.g., at the middle) or at an end (e.g., a terminus) of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group,” as used herein refers, to a divalent group having substantially the same structure as the C₂-C₆₀ alkenyl group, except that the C₂-C₆₀ alkenylene group is divalent instead of monovalent.

[0331] The term “C₂-C₆₀ alkynyl group,” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in a main chain (e.g., at the middle) or at an end (e.g., at a terminus) of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group,” as used herein refers, to a divalent group having substantially the same structure as the C₂-C₆₀ alkynyl group, except that the C₂-C₆₀ alkynylene group is divalent instead of monovalent.

[0332] The term “C₁-C₆₀ alkoxy group,” as used herein, refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

[0333] The term “C₃-C₁₀ cycloalkyl group,” as used herein, refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkyl group, except that the C₃-C₁₀ cycloalkylene group is divalent instead of monovalent.

[0334] The term “C₁-C₁₀ heterocycloalkyl group,” as used herein, refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuran group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkyl group, except that the C₁-C₁₀ heterocycloalkylene group is divalent instead of monovalent.

[0335] The term “C₃-C₁₀ cycloalkenyl group,” as used herein, refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity (e.g., the ring is not aromatic), and examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₃-C₁₀ cycloalkenyl group, except that the C₃-C₁₀ cycloalkenylene group is divalent instead of monovalent.

[0336] The term “C₁-C₁₀ heterocycloalkenyl group,” as used herein, refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuran group, and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group,” as used herein, refers to a divalent group having substantially the same structure as the C₁-C₁₀ heterocycloalkenyl group, except that the C₁-C₁₀ heterocycloalkenylene group is divalent instead of monovalent.

[0337] The term “C₆-C₆₀ aryl group,” as used herein, refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and the term “C₆-C₆₀ arylene group,” used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms.

Non-limiting examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other (e.g., combined together).

[0338] The term “C₁-C₆₀ heteroaryl group,” as used herein, refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group,” as used herein, refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be condensed with each other (e.g., combined together).

[0339] The term “C₆-C₆₀ aryloxy group,” as used herein, refers to —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

[0340] The term “monovalent non-aromatic condensed polycyclic group,” as used herein, refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other (e.g., combined together), only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure (e.g., the entire molecule is not aromatic). A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group,” as used herein, refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed polycyclic group, except that the divalent non-aromatic condensed polycyclic group is divalent instead of monovalent.

[0341] The term “monovalent non-aromatic condensed heteropolycyclic group,” as used herein, refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure (e.g., the entire molecule is not aromatic). An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group,” as used herein, refers to a divalent group having substantially the same structure as the monovalent non-aromatic condensed heteropolycyclic group, except that the divalent non-aromatic condensed heteropolycyclic group is divalent instead of monovalent.

[0342] The term “C₅-C₆₀ carbocyclic group,” as used herein, refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring, such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents

connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

[0343] The term “C₁-C₆₀ heterocyclic group,” as used herein, refers to a group having substantially the same structure as the C₁-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

[0344] At least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

[0345] deuterium (-D), —F, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0346] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

[0347] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0348] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a

cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

[0349] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); and

[0350] Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

[0351] The term “Ph,” as used herein, refers to a phenyl group, the term “Me,” as used herein, refers to a methyl group, the term “Et,” as used herein, refers to an ethyl group, the term “ter-Bu” or “Bu’,” as used herein, refers to a tert-butyl group, and the term “OMe,” as used herein, refers to a methoxy group.

[0352] The term “biphenyl group,” as used herein, refers to “a phenyl group substituted with a phenyl group.” In other words, the “biphenyl group” includes a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

[0353] The term “terphenyl group,” as used herein, refers to “a phenyl group substituted with a biphenyl group.” In other words, the “terphenyl group” includes a phenyl group having, as a substituent, a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group.


[0354] * and *, as used herein, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula.

[0355] Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in more detail with reference to Synthesis Examples and Examples. The wording “B was used instead of A” used in describing Synthesis Examples refers to that an identical (e.g., substantially identical) molar equivalent of B was used in place of A.


Synthesis Example 1

Synthesis of Compound 1

[0356]



-continued




1

[0357] 3 g (0.0089 mol) of 9,10-dibromoanthracene and 5.24 g (0.0178 mol) of 4,4,5,5-tetramethyl-2-(2'-methyl-[1,1'-biphenyl]-3-yl)-1,3,2-dioxaborolane were added to a 100-ml 3-neck flask, 3 ml of 2N Na₂CO₃ and a mixed solution of toluene and EtOH were added thereto, and oxygen was removed therefrom while stirring the resultant mixture. Then, nitrogen substitution was performed thereon, 0.5 g of Pd(pph₃)₄ acting as a catalyst was added thereto, and the mixture was refluxed at a temperature of 110° C. for 8 hours. The reaction was terminated by using water, an extraction process was performed on the reaction product three times by using methylene chloride (MC), and a solvent was removed therefrom. Column chromatography was performed on the result obtained therefrom by using a solvent of ethyl acetate (EA): hexane (Hex) (1:5) to obtain 3.64 g (80%) of Compound 1. H-NMR data of Compound 1 was as follows:


[0358] H-NMR(CDCl₃): 8.21(4H, d), 7.90 (2H, s), 7.72-7.68 (4H, m), 7.60-7.55 (4H, t), 7.40-7.30(10H, m), 2.32 (6H, s).

Synthesis Example 2

Synthesis of Compound 2

[0359]

-continued




2


[0360] 3 g (0.0089 mol) of 9,10-dibromoanthracene and 5.49 g (0.0178 mol) of 2-(2,2'-dimethyl-[1,1'-biphenyl]-3-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane were added to a 100-ml 3-neck flask, 3 ml of 2N Na₂CO₃ and a mixed solution of toluene and EtOH were added thereto, and oxygen was removed therefrom while stirring the resultant mixture. Then, nitrogen substitution was performed thereon, 0.5 g of Pd(pph₃)₄ acting as a catalyst was added thereto, and the mixture was refluxed at a temperature of 110° C. for 8 hours. The reaction was terminated by using water, an extraction process was performed on the reaction product three times by using MC, and a solvent was removed therefrom. Column chromatography was performed on the result obtained therefrom by using a solvent of EA:Hex (1:5) to obtain 3.6 g (75%) of Compound 2. H-NMR data of Compound 2 was as follows:

[0361] H-NMR(CDCl₃): 8.21(4H, d), 7.80 (4H, d), 7.70 (2H, d), 7.58 (2H, t), 7.40-7.30(10H, m), 2.30 (6H, s), 2.18 (6H, s).

Synthesis Example 3

Synthesis of Compound 3

[0362]



[0363] 3 g (0.0089 mol) of 9,10-dibromoanthracene and 5.49 g (0.0178 mol) of 2-(2,6'-dimethyl-[1,1'-biphenyl]-3-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborolane were added to a 100-ml 3-neck flask, 3 ml of 2N Na₂CO₃ and a mixed solution of toluene and EtOH were added thereto, and oxygen was removed therefrom while stirring the resultant mixture. Then, nitrogen substitution was performed thereon, 0.5 g of Pd(pph₃)₄ acting as a catalyst was added thereto, and the mixture was refluxed at a temperature of 110° C. for 8 hours. The reaction was terminated by using water, an extraction process was performed on the reaction product three times by using MC, and a solvent was removed therefrom. Column chromatography was performed on the result obtained therefrom by using a solvent of EA:Hex (1:5) to obtain 4.1 g (85%) of Compound 3. H-NMR data of Compound 3 was as follows:

[0364] H-NMR(CDCl₃): 8.21(4H, d), 7.93 (2H, s), 7.73 (2H, t), 7.61-7.50 (6H, m), 7.35 (4H, m), 7.21 (4H, m), 2.57 (12H, s).

Evaluation Example 1





[0365] Electrical and optical characteristics of Compounds 1 to 3 synthesized according to Synthesis Examples 1 to 3, mNPA, and Compounds A to C were evaluated by using a CV and UV band gap measurement method. Results thereof are shown in Table 1 below, which shows the energy level of the highest occupied molecular orbital (HOMO) in electron volts (eV), the energy level of the lowest unoccupied molecular orbital (LUMO) in eV, an energy level (T1) of a first triplet excited state of the compound in eV, and an energy level (T2) of a second triplet excited state of the compound in eV.

TABLE 1

	HOMO (eV)	LUMO (eV)	T1(eV)	T2(eV)
Compound 1	-6.02	-2.48	1.65	3.30
Compound 2	-5.93	-2.52	1.65	3.43
Compound 3	-5.95	-2.55	1.65	3.32
mNPA	-6.0	-2.6	1.71	2.62

TABLE 1-continued

	HOMO (eV)	LUMO (eV)	T1(eV)	T2(eV)
Compound A	-5.58	-2.51	1.67	3.30
Compound B	-6.01	-2.50	1.65	3.28
Compound C	-6.11	-2.48	1.68	3.20



Example 1

[0366] As a substrate and an ITO anode, 15 Ω/cm² (120 nm) ITO glass substrate (a product of Corning Co., Ltd) was cut to a size of 50 mm×50 mm×0.5 mm, sonicated with acetone, isopropyl alcohol, and deionized water each for 5 minutes, and cleaned by exposure to ultraviolet rays and ozone for 10 minutes. Then, the resultant ITO glass substrate was provided to a vacuum deposition apparatus.

[0367] HATCN was vacuum-deposited on the ITO anode to form a hole injection layer having a thickness of 100 Å, and TAPC was deposited on the hole injection layer to a thickness of 500 Å to form a hole transport layer having a thickness of 10 nm.

[0368] TCTA was deposited on the hole transport layer to form an auxiliary layer having a thickness of 50 Å.

[0369] Then, Compound 1 and a fluorescent dopant D1 ((4,4'-bis(9-ethyl-3-carbazovinylene)-1,1'-biphenyl) (BCz-VBi)) were co-deposited on the auxiliary layer (weight ratio=90:10) to form an emission layer having a thickness of 300 Å. Then, TPBI and LiQ were mixed on the emission layer to form an electron transport layer having a thickness of 360 Å (50:50), LiQ was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Mg and Ag were co-deposited on the electron injection layer (weight ratio=800:10) to form a cathode having a thickness of 130 Å, thereby completing the manufacture of an organic light-emitting device.

Example 2

[0370] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 2 was used instead of Compound 1.

Example 3


[0371] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound 3 was used instead of Compound 1.

Comparative Example 1

[0372] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that mNPA was used instead of Compound 1.

Comparative Example 2

[0373] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound A was used instead of Compound 1.




A

Comparative Example 3

[0374] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound B was used instead of Compound 1.


B



Comparative Example 4

[0375] An organic light-emitting device was manufactured in substantially the same manner as in Example 1, except that Compound C was used instead of Compound 1.

C



Evaluation Example 2

[0376] The driving voltage, current density, luminance, power, and color purity of the organic light-emitting devices manufactured according to Examples 1 to 3 and Comparative Examples 1 to 4 were evaluated by using a Keithley SMU 236 and a PR650 Spectroscan Source Measurement Unit (manufactured by PhotoResearch Inc.). Evaluation results thereof are shown in Table 2.

TABLE 2

	Color	Driving voltage (V)	Luminance (Cd/m ²)	Efficiency (cd/A)	Lifespan (T90)	Delayed fluorescence component
Example 1	blue	4.21	1000	11.2	45	47%
Example 2	blue	4.11	1000	13.3	85	58%
Example 3	blue	4.20	1000	12.5	35	50%
Comparative Example 1	blue	4.28	1000	8.5	5	23%
Comparative Example 2	blue	4.35	1000	10.5	30	40%
Comparative Example 3	blue	4.25	1000	11.2	30	40%
Comparative Example 4	blue	4.42	1000	9.1	48	30%

[0377] Referring to Table 2, it is confirmed that the organic light-emitting devices of Examples 1 to 3 have a low driving voltage, high efficiency, a long lifespan, and a large amount of delayed fluorescence component, as compared with those of the organic light-emitting devices of Comparative Examples 1 to 4.

[0378] An organic light-emitting device including at least one of the condensed cyclic compound may have a low driving voltage, high efficiency, a long lifespan, and a large amount of a delayed fluorescence component.

[0379] It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

[0380] It will be understood that, although the terms “first,” “second,” “third,” etc., may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section described below could be termed a second element, component, region, layer or section, without departing from the spirit and scope of the present disclosure.

[0381] Spatially relative terms, such as “beneath,” “below,” “lower,” “under,” “above,” “upper,” and the like, may be used herein for ease of explanation to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or in operation, in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” or “under” other elements or features would then be oriented “above” the other elements or features. Thus, the example terms “below” and “under” can encompass both an orientation of above and below. The device may be otherwise oriented (e.g., rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein should be interpreted accordingly.

[0382] It will be understood that when an element or layer is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it can be directly on, connected to, or coupled to the other element or layer, or one or more intervening elements or layers may be present. In addition, it will also be understood that when an element or layer is referred to as being “between” two elements or layers, it can be the only element or layer between the two elements or layers, or one or more intervening elements or layers may also be present.

[0383] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the present disclosure. As used herein, the singular forms “a” and “an” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises,” “comprising,” “includes,” and “including,” when used in this specification, specify the presence of the stated features, integers, acts, operations, elements, and/or components, but do not preclude the presence or addition of

one or more other features, integers, acts, operations, elements, components, and/or groups thereof.


[0384] As used herein, the terms “substantially,” “about,” and similar terms are used as terms of approximation and not as terms of degree, and are intended to account for the inherent deviations in measured or calculated values that would be recognized by those of ordinary skill in the art. Further, the use of “may” when describing embodiments of the present disclosure refers to “one or more embodiments of the present disclosure.” As used herein, the terms “use,” “using,” and “used” may be considered synonymous with the terms “utilize,” “utilizing,” and “utilized,” respectively. Also, the term “exemplary” is intended to refer to an example or illustration.

[0385] Also, any numerical range recited herein is intended to include all sub-ranges of the same numerical precision subsumed within the recited range. For example, a range of “1.0 to 10.0” is intended to include all subranges between (and including) the recited minimum value of 1.0 and the recited maximum value of 10.0, that is, having a minimum value equal to or greater than 1.0 and a maximum value equal to or less than 10.0, such as, for example, 2.4 to 7.6. Any maximum numerical limitation recited herein is intended to include all lower numerical limitations subsumed therein, and any minimum numerical limitation recited in this specification is intended to include all higher numerical limitations subsumed therein. Accordingly, Applicant reserves the right to amend this specification, including the claims, to expressly recite any sub-range subsumed within the ranges expressly recited herein.


[0386] While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure as defined by the following claims, and equivalents thereof.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



Formula 1



Formula 2

wherein, in Formulae 1 and 2,

X_{12} is N or C(R_{12}), X_{13} is N or C(R_{13}), X_{14} is N or C(R_{14}), X_{15} is N or C(R_{15}), X_{16} is N or C(R_{16}), X_{17} is N or C(R_{17}), X_{18} is N or C(R_{18}), and X_{19} is N or C(R_{19}).

R_1 to R_4 and R_{11} to R_{19} are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), and —P(=O)(Q_1)(Q_2), provided that R_{11} to R_{19} are not the group represented by Formula 2,

R_{11} is not hydrogen,

at least one selected from R_3 and R_4 is the group represented by Formula 2,

a_1 and a_2 are each independently an integer from 0 to 4, when a_1 is two or more, two or more R_1 (s) are identical to or different from each other, and when a_2 is two or more, two or more R_2 (s) are identical to or different from each other,

at least one substituent of the substituted C_3 - C_{10} cycloalkylene group, the substituted C_1 - C_{10} heterocycloalkylene group, the substituted C_3 - C_{10} cycloalkenylene group, the substituted C_1 - C_{10} heterocycloalkenylene group, the substituted C_6 - C_{60} arylene group, the substituted C_1 - C_{60} heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, the substituted monovalent non-aromatic condensed heteropolycyclic group, and the substituted pyridine group is selected from:

deuterium, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

a group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12});

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q_{21})(Q_{22})(Q_{23}), —B(Q_{21})(Q_{22}), —N(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22}); and

—Si(Q_{31})(Q_{32})(Q_{33}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* indicates a binding site to a neighboring atom.

2. The condensed cyclic compound of claim 1, wherein: X_{12} is $C(R_{12})$, X_{13} is $C(R_{13})$, X_{14} is $C(R_{14})$, X_{15} is $C(R_{15})$, X_{16} is $C(R_{16})$, X_{17} is $C(R_{17})$, X_{18} is $C(R_{18})$, and X_{19} is $C(R_{19})$.

3. The condensed cyclic compound of claim 1, wherein: R_1 to R_4 and R_{11} to R_{19} are each independently selected from:

a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a spiro-fluorene-benzofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a benzonaphthofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, and an imidazopyrimidinyl group;

a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a benzonaphthofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a

dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a benzonaphthofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyrimidinyl group, an imidazopyrimidinyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}); and

—Si(Q_1)(Q_2)(Q_3), B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O)₂(Q_1), and —P(=O)(Q_1)(Q_2), and

Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a biphenyl group, a terphenyl group, a naphthyl group, and a dibenzofuranyl group.

4. The condensed cyclic compound of claim 1, wherein: R_1 and R_2 are each hydrogen.

5. The condensed cyclic compound of claim 1, wherein: R_3 and R_4 are identical to each other and are each a group represented by Formula 2.

6. The condensed cyclic compound of claim 1, wherein: R_{11} is selected from a C_1 - C_{10} alkyl group, a C_6 - C_{20} aryl group, a C_1 - C_{20} heteroaryl group, and —Si(Q_1)(Q_2)(Q_3), and

Q_1 to Q_3 are each independently selected from a C_1 - C_{10} alkyl group, a phenyl group, a biphenyl group, and a terphenyl group.

7. The condensed cyclic compound of claim 1, wherein:

i) X_{14} is $C(R_{14})$, X_{15} is $C(R_{15})$, and X_{16} is $C(R_{16})$, and
ii) at least one selected from R_{11} and R_{14} to R_{16} is a C_1 - C_{10} alkyl group.

8. The condensed cyclic compound of claim 1, wherein: R_3 and R_4 are each a group represented by Formula 2,




X_{12} is $C(R_{12})$, X_{13} is $C(R_{13})$, X_{14} is $C(R_{14})$, X_{15} is $C(R_{15})$, X_{16} is $C(R_{16})$, X_{17} is $C(R_{17})$, X_{18} is $C(R_{18})$, and X_{19} is $C(R_{19})$, and

i) R_{11} is a C_1 - C_{10} alkyl group, and R_{12} to R_{19} are each hydrogen;

ii) R_{11} is a C_1 - C_{10} alkyl group, R_{14} or R_{15} is a C_1 - C_{10} alkyl group, and R_{12} , R_{13} , and R_{16} to R_{19} are each hydrogen; or


iii) R_{11} and R_{16} are each a C_1 - C_{10} alkyl group, and R_{12} to R_{15} and R_{17} to R_{19} are each hydrogen.

9. The condensed cyclic compound of claim 1, wherein: the compound represented by Formula 1 is selected from Compounds 1 to 3:




10. The condensed cyclic compound of claim 1, wherein: the compound represented by Formula 1 has a singlet conversion efficiency of about 40% to about 62.5%, and the singlet conversion efficiency is evaluated by using a transient electroluminescent (EL) apparatus.

11. The condensed cyclic compound of claim 1, wherein: a dihedral angle between a plane P1 comprising a moiety represented by




and a plane P2 comprising a moiety represented by




in Formula 2 is about 60° or more, and * and *¹ each indicate a binding site to a neighboring atom.

12. A condensed cyclic compound represented by Formula 1 and satisfying conditions of Equations 1 and 2:

Formula 1



Formula 2



Equation 1

$$2E_{T1} < E_{T2}$$

Equation 2

$$2E_{T1} > E_{S1},$$

wherein, in Formulae 1 and 2,

X₁₂ is N or C(R₁₂), X₁₃ is N or C(R₁₃), X₁₄ is N or C(R₁₄), X₁₅ is N or C(R₁₅), X₁₆ is N or C(R₁₆), X₁₇ is N or C(R₁₇), X₁₈ is N or C(R₁₈), and X₁₉ is N or C(R₁₉),

R₁ to R₄ and R₁₁ to R₁₉ are each independently selected from a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a

cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂), provided that R₁₁ to R₁₉ are not the group represented by Formula 2,

R₁₁ is not hydrogen,

at least one selected from R₃ and R₄ is the group represented by Formula 2,

a1 and a2 are each independently an integer from 0 to 4, when a1 is two or more, two or more R₁(s) are identical to or different from each other, and when a2 is two or more, two or more R₂(s) are identical to or different from each other,

at least one substituent of the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, the substituted monovalent non-aromatic condensed heteropolycyclic group, and the substituted pyridine group is selected from:

deuterium, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ het-

erocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —B(Q₂₁)(Q₂₂), —N(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and —Si(Q₃₁)(Q₃₂)(Q₃₃), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* indicates a binding site to a neighboring atom, and

wherein, in Equations 1 and 2,

E_{T1} is an energy level of a first triplet excited state of the compound represented by Formula 1,

E_{T2} is an energy level of a second triplet excited state of the compound represented by Formula 1, and E_{S1} is an energy level of a lowest singlet excited state of the compound represented by Formula 1, and

E_{T1} , E_{T2} , and E_{S1} are calculated using a density functional theory (DFT) method using a B3LYP hybrid functional and a 6-31G*(d,p) basis set.

13. An organic light-emitting device comprising:

a first electrode;

a second electrode facing the first electrode; and

an organic layer disposed between the first electrode and the second electrode,

wherein the organic layer comprises an emission layer and at least one of the condensed cyclic compound of claim 1.

14. The organic light-emitting device of claim 13, wherein:

the emission layer comprises a compound represented by Formula 1, and

the emission layer emits blue light having a maximum emission wavelength of about 420 nm to about 470 nm.

15. The organic light-emitting device of claim 14, wherein:


the emission layer further comprises a fluorescent luminescent material,

an amount of the compound represented by Formula 1 is larger than an amount of the fluorescent luminescent material, and

the compound represented by Formula 1 in the emission layer acts as a host.

16. The organic light-emitting device of claim 15, wherein:

the fluorescent luminescent material comprises an arylamine compound, a styrylamine compound, or a compound represented by Formula 501:



Formula 501

wherein, in Formula 501,

Ar_{501} is a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

L_{501} to L_{503} are each independently selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic con-

densed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

x_{d1} to x_{d3} are each independently an integer from 0 to 3,

R_{501} and R_{502} are each independently selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

x_{d4} is an integer from 1 to 6.

17. The organic light-emitting device of claim 13, wherein:

the first electrode is an anode,

the second electrode is a cathode,

the organic layer further comprises a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,

the hole transport region comprises a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and

the electron transport region comprises a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or any combination thereof.

18. The organic light-emitting device of claim 17, wherein:

the hole transport region comprises at least one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and the electron transport region comprises at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

19. The organic light-emitting device of claim 17, wherein:

the hole transport region comprises a p-dopant, and

the p-dopant has a lowest unoccupied molecular orbital (LUMO) energy level of about -3.5 eV or less.

20. The organic light-emitting device of claim 19, wherein:

the p-dopant comprises a cyano group-containing compound.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光器件		
公开(公告)号	US20190027692A1	公开(公告)日	2019-01-24
申请号	US15/859200	申请日	2017-12-29
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KIM SEULONG		
发明人	KIM, SEULONG		
IPC分类号	H01L51/00 C09K11/06 H01L51/50 C07C15/28		
CPC分类号	H01L51/0052 C09K11/06 H01L51/0072 H01L51/5016 C07C15/28 C09K2211/1011 C09K2211/1029 C07C2603/24 H01L51/5012		
优先权	1020170092732 2017-07-21 KR		
外部链接	Espacenet USPTO		

摘要(译)

式1表示稠合环状化合物。有机发光装置包括：第一电极;面向第一电极的第二电极;和设置在第一电极和第二电极之间的有机层，有机层包括发光层和至少一种缩合环状化合物。

10

190
150
110