



US009331308B2

(12) **United States Patent**
Choi et al.

(10) **Patent No.:** **US 9,331,308 B2**
(45) **Date of Patent:** **May 3, 2016**

(54) **ORGANIC LIGHT EMITTING DISPLAY
APPARATUS AND METHOD OF
MANUFACTURING THE SAME**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin,
Gyeonggi-Do (KR)

(72) Inventors: **Jun-Ho Choi**, Yongin (KR);
Kwan-Hyun Cho, Yongin (KR);
Jin-Koo Chung, Yongin (KR)

(73) Assignee: **Samsung Display Co., Ltd.** (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/066,519**

(22) Filed: **Oct. 29, 2013**

(65) **Prior Publication Data**

US 2014/0353611 A1 Dec. 4, 2014

(30) **Foreign Application Priority Data**

May 29, 2013 (KR) 10-2013-0061251

(51) **Int. Cl.**
H01L 51/52 (2006.01)
H01L 51/56 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/5262** (2013.01); **H01L 51/5228**
(2013.01); **H01L 51/5234** (2013.01); **H01L**
51/5203 (2013.01); **H01L 2251/5315** (2013.01)

(58) **Field of Classification Search**
CPC H01L 27/3276; H01L 27/3279; H01L
51/5203; H01L 51/5262; H01L 51/56; H01L
51/5228; H01L 51/5234; H01L 2251/5315
USPC 438/29; 257/40
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,026,658	B2	4/2006	Park et al.	
7,173,373	B2	2/2007	Yamada et al.	
7,597,602	B2	10/2009	Yamada et al.	
7,772,760	B2 *	8/2010	Yoo et al.	313/504
8,872,206	B2 *	10/2014	Chung et al.	257/98
8,895,972	B2 *	11/2014	Chung et al.	257/40
8,994,010	B2 *	3/2015	Choi et al.	257/40
2005/0062408	A1 *	3/2005	Yoo et al.	313/504
2010/0102713	A1	4/2010	Seo et al.	
2010/0140649	A1 *	6/2010	Kim et al.	257/98
2010/0171106	A1 *	7/2010	Jung et al.	257/40
2012/0104422	A1 *	5/2012	Lee et al.	257/88

(Continued)

FOREIGN PATENT DOCUMENTS

EP	2 530 717	A3 *	12/2012		H01L 27/32
JP	2012-253015	*	12/2012		H05B 33/10

(Continued)


Primary Examiner — Mary Wilczewski

(74) *Attorney, Agent, or Firm* — Innovation Counsel LLP

(57) **ABSTRACT**

An organic light emitting display apparatus and a method of manufacturing the same are provided. The apparatus includes a substrate, a first electrode formed on the substrate, an intermediate layer formed on the first electrode. The intermediate layer includes an organic emission layer. A second electrode is formed on the intermediate layer, and a capping layer is formed on the second electrode in a first region. The capping layer includes a first edge portion and at least two layers. A third electrode is formed on the second electrode in a second region. The second region is not overlapped with the first region, and the third electrode includes a second edge portion having a side portion facing a side portion of the first edge portion of the capping layer. Electric properties and image quality may be improved.

15 Claims, 21 Drawing Sheets



(56)

References Cited

FOREIGN PATENT DOCUMENTS

U.S. PATENT DOCUMENTS

2012/0138918	A1	6/2012	Naraoka et al.		KR	100528911	A	11/2005
2012/0313099	A1 *	12/2012	Chung et al.	257/59	KR	1020100036008	A	4/2010
2013/0161656	A1 *	6/2013	Choi et al.	257/88	KR	1020100047457	A	5/2010
2013/0328022	A1 *	12/2013	Choi et al.	257/40	KR	1020100081773	A	7/2010
2014/0145152	A1 *	5/2014	Chung et al.	257/40	KR	1020100128794	A	12/2010
2014/0145156	A1 *	5/2014	Choi et al.	257/40	KR	101086580	A	11/2011
2014/0353611	A1 *	12/2014	Choi et al.	257/40	KR	1020120080536	A	7/2012

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG. 31




FIG. 32




FIG. 33




FIG. 34





FIG. 35



ORGANIC LIGHT EMITTING DISPLAY APPARATUS AND METHOD OF MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED PATENT APPLICATION

This application claims the benefit of Korean Patent Application No. 10-2013-0061251, filed on May 29, 2013, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field of the Invention

The present invention relates to an organic light emitting display apparatus and a method of manufacturing the same, and more particularly, to an organic light emitting display apparatus having improved electric properties and image quality.

2. Description of the Related Art

Portable and thin film type flat panel apparatus are increasingly used as display apparatuses. Among flat panel display apparatuses, an organic light emitting display apparatus is a self-emitting display apparatus having a wide viewing angle, good contrast and rapid response time, and has been attracting attention as a next generation display apparatus.

The organic light emitting display apparatus includes an intermediate layer, a first electrode and a second electrode. The intermediate layer includes an organic light emitting layer. When a voltage is applied to the first electrode and the second electrode, visible lights may be generated from the organic light emitting layer.

In this case, contamination and damage may be generated due to a sealing part disposed on the second electrode or impurities.

Due to the above-described factors, the improvement of the image quality and electric properties of the organic light emitting display apparatus may be limited.

SUMMARY OF THE INVENTION

An organic light emitting display apparatus of which electric properties and image quality may be easily improved, and a method of manufacturing the organic light emitting display apparatus are provided.

According to an aspect, there is provided an organic light emitting display apparatus including a substrate, a first electrode formed on the substrate, an intermediate layer formed on the first electrode. The intermediate layer includes an organic emission layer. A second electrode is formed on the intermediate layer and a capping layer is formed on the second electrode in a first region. The capping layer includes a first edge portion and at least two layers. A third electrode is formed on the second electrode in a second region. The second region is not overlapped with the first region, and the third electrode includes a second edge portion having a side portion facing another side portion of the first edge portion of the capping layer.

The third electrode may include a plurality of layers stacked in sequence.

The third electrode may include a lower electrode layer and an upper electrode layer stacked in sequence, and the capping layer may include a first capping layer and a second capping layer stacked in sequence.

The third electrode may include a single layer, and the capping layer may include a first capping layer and a second capping layer stacked in sequence.

The third electrode may include a lower electrode layer and an upper electrode layer stacked in sequence, and the capping layer may include a first capping layer, a second capping layer, a third capping layer and a fourth capping layer stacked in sequence.

A thickness of the third electrode may be greater than the thickness of the second electrode.

The adhesiveness between the third electrode and the capping layer may be smaller than the adhesiveness between the third electrode and the second electrode.

The capping layer may include 8-quinolinolato lithium, N,N-diphenyl-N,N-bis(9-phenyl-9H-carbazol-3-yl)biphenyl-4,4'-diamine), N(diphenyl-4-yl)9,9-dimethyl-N-(4(9-phenyl-9H-carbazol-3-yl)phenyl)-9H-fluorene-2-amine), or 2-(4-(9,10-di(naphthalene-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo-[D]imidazole.

The third electrode may include Mg.

The apparatus may include a light-transmitting area for transmitting an external light and a pixel area adjacent to the light-transmitting area and emitting light. The light-transmitting area and the pixel area may be positioned in the first region, and the first electrode may be overlapped with the pixel area.

The apparatus may further include a thin film transistor including an active layer, a gate electrode, a source electrode and a drain electrode, the thin film transistor making an electric connection with the first electrode, and the first electrode may be disposed so as to shield the thin film transistor.

The capping layer may be light-transmitting. All of edge portions of the capping layer and an edge portion of the third electrode may make be in contact with one another.

An area of the capping layer may be greater than an area emitting light in one pixel.

According to another aspect, there is provided a method of manufacturing an organic light emitting display apparatus including forming a first electrode on a substrate, forming an intermediate layer including an organic emission layer on the first electrode, forming a second electrode on the intermediate layer, and forming a capping layer on the second electrode in a first region. The capping layer has a first edge portion and at least two layers. A third electrode is formed on the second electrode in a second region. The second region is not overlapped with the first region, and the third electrode includes a second edge portion having a side portion facing a side portion of the first edge portion of the capping layer.

The third electrode and the capping layer may be formed through conducting a deposition process.

The adhesiveness between a metal for forming the third electrode and the capping layer may be smaller than the adhesiveness between the metal for forming the third electrode and the second electrode.

The capping layer may be formed by using a mask including a slit part of corresponding pattern of the capping layer.

The third electrode may be formed by using an open mask including an opening over the capping layer.

The third electrode may be formed by performing a deposition process without using a mask.

The forming of the capping layer may include forming a first layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part of corresponding pattern of the capping layer, and forming a remaining layer of the capping layer by using an open mask including an opening over the capping layer.

The forming of the capping layer may include forming a first layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part of corresponding pattern of the capping layer, and forming a remaining layer of the capping layer without using a mask.

The forming of the third electrode may be conducted after forming at least one layer of the capping layer.

The forming of the third electrode and the capping layer may include forming a first layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part of corresponding pattern of the capping layer, and forming the third electrode and a remaining layer of the capping layer by using an open mask in a co-deposition process, the open mask including an opening over the first layer of the capping layer.

The third electrode may include a plurality of electrode layers stacked in sequence.

The forming of the third electrode and the capping layer may include forming a lowermost layer making a contact with the second electrode among the plurality of the layers of the capping layer by using a mask including a slit part of corresponding pattern of the capping layer, and forming a lowermost electrode layer making a contact with the second electrode among the plurality of the electrode layers of the third electrode by using an open mask including an opening over the lowermost layer of the capping layer.

The method may include forming a remaining layer excluding the lowermost layer among the plurality of the layers of the capping layer by using a mask having a slit part of corresponding pattern of the capping layer, and forming a remaining layer excluding the lowermost electrode layer among the plurality of the electrode layers of the third electrode by using an open mask.

The method may include forming the remaining layer excluding the lowermost layer among the plurality of the layers of the capping layer by using the open mask, and forming the remaining layer excluding the lowermost electrode layer among the plurality of the electrode layers of the third electrode by using the open mask.

The forming of the third electrode and the capping layer may include alternately disposing a plurality of first deposition sources including a material for forming the capping layer and a plurality of second deposition sources including a material for forming the third electrode, and moving the substrate including the second electrode so as to correspond the substrate to the plurality of the first deposition sources and the plurality of the second deposition sources one by one.

The forming of the third electrode and the capping layer may include forming a layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part of corresponding pattern of the capping layer, and forming at least one layer of the third electrode and at least one layer of the remaining layer of the capping layer at the same time by using an open mask by means of a co-deposition process, the open mask including an opening over the capping layer.

According to the organic light emitting display apparatus and the method of manufacturing the organic light emitting display apparatus according to the present disclosure, electric properties and image quality may be easily improved.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features and advantages will become more apparent by describing example embodiments with reference to the attached drawings in which:

FIG. 1 is a schematic cross-sectional view of an organic light emitting display apparatus according to an example embodiment;

FIG. 2 is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment;

FIG. 3 is an enlarged view of X in FIG. 1;

FIG. 4 is an enlarged view of Y1 and Y2 in FIG. 3;

FIGS. 5 to 10 illustrate a method of manufacturing the organic light emitting display apparatus in FIG. 1 in sequence;

FIGS. 11 to 13 illustrate various embodiments of the shapes of a capping layer of the organic light emitting display apparatus in FIG. 1;

FIGS. 14 to 17 illustrate another example embodiment of a method of manufacturing the organic light emitting display apparatus in FIG. 1;

FIG. 18 illustrates another example embodiment of a method of manufacturing the organic light emitting display apparatus in FIG. 1;

FIG. 19 is a cross-sectional view of an organic light emitting display apparatus according to another example embodiment;

FIG. 20 is an enlarged view of Y1 and Y2 in FIG. 19;

FIGS. 21 & 22 illustrate a method of manufacturing the organic light emitting display apparatus in FIG. 19;

FIG. 23 is a cross-sectional view of an organic light emitting display apparatus according to another example embodiment;

FIG. 24 is an enlarged view of Y1 and Y2 in FIG. 23;

FIGS. 25 to 28 illustrate a method of manufacturing the organic light emitting display apparatus in FIG. 23 in sequence;

FIGS. 29 to 32 illustrate another method of manufacturing the organic light emitting display apparatus in FIG. 23 in sequence;

FIG. 33 is a plan view illustrating an organic light emitting display apparatus according to another example embodiment;

FIG. 34 is a cross-sectional view illustrating one pixel of the organic light emitting display apparatus in FIG. 33; and

FIG. 35 is a plan view illustrating an organic light emitting display apparatus according to another example embodiment.

DETAILED DESCRIPTION OF THE INVENTION

Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, example embodiments are merely described below, by referring to the figures, to explain aspects of the present description.

As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items.

Hereinafter, the constitution and operation will be explained in detail with reference to example embodiments illustrated in attached drawings.

FIG. 1 is a schematic cross-sectional view of an organic light emitting display apparatus according to an example embodiment.

Referring to FIG. 1, an organic light emitting display apparatus according to an embodiment includes an organic light emitting part 110 formed on a substrate 101 and an encapsulation substrate 191 for sealing the organic light emitting part 110.

The encapsulation substrate **191** may be formed to include a light-transmitting material, so that visible light generated at the organic light emitting part **110** may penetrate the encapsulation substrate **191**, and the encapsulation substrate **191** may prevent the penetration of external gas and humidity into the organic light emitting part **110**.

The substrate **101** and the encapsulation substrate **191** may be combined by a sealing material **150**, and a space **25** between the substrate **101** and the encapsulation substrate **191** may be sealed. In the space **25**, a moisture absorbent material or a filler may be disposed.

FIG. **2** is a schematic cross-sectional view of an organic light emitting display apparatus according to another example embodiment.

In the organic light emitting display apparatus **100'** in FIG. **2**, a encapsulation layer **192** of a thin film may be formed on an organic light emitting part **110'** instead of forming the encapsulation substrate **191** in FIG. **1**, so as to protect the organic light emitting part **110'** from external air. The encapsulation layer **192** may be obtained by alternately forming a layer including an inorganic material, such as, for example, silicon oxide or silicon nitride, and a layer including an organic material, such as, for example, epoxy and polyimide, without limitation. Any sealing structure on a light-transmitting thin film may be applicable.

FIG. **3** is an enlarged view of a region X outlined in FIG. **1**, and FIG. **4** is an enlarged view of regions Y1 and Y2 outlined in FIG. **3**. More particularly, FIG. **3** illustrates one pixel of the organic light emitting part **110** illustrated in FIG. **1**. Alternatively, FIG. **3** may illustrate one pixel of the organic light emitting part **110'** illustrated in FIG. **2**.

Referring to FIG. **3**, a buffer layer **102** is formed on a substrate **101**, and a thin film transistor TR is formed on the buffer layer **102**. The thin film transistor TR includes an active layer **103**, a gate electrode **105**, a source electrode **107** and a drain electrode **108**.

Even though only one thin film transistor TR is illustrated in FIG. **3**, the pixel may constitute a pixel circuit by further including at least one other thin film transistor and a capacitor.

The active layer **103** is formed on the buffer layer **102**.

The buffer layer **102** may prevent the penetration of impurity elements and may function to planarize the surface thereof. The buffer layer **102** may be formed by using various materials that may perform the above-mentioned functions. For example, the buffer layer **102** may be formed by using an inorganic material such as silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, titanium oxide, titanium nitride, etc., or an organic material such as polyimide, polyester, acryl, etc., or may be formed as a stacked structure thereof. The buffer layer **102** may be omitted.

The active layer **103** may be formed of amorphous silicon, polycrystalline silicon or organic semiconductor material, but is not necessarily limited thereto. The active layer **103** may be formed by using an oxide semiconductor. For example, the active layer **103** may be a G-I-Z-O layer $[(\text{In}_2\text{O}_3)_a(\text{Ga}_2\text{O}_3)_b(\text{ZnO})_c \text{ layer}]$ (in which a, b and c are real numbers satisfying $a \geq 0$, $b \geq 0$ and $c \geq 0$, respectively).

A gate insulating layer **104** covering the active layer **103** is formed on the buffer layer **102**, and a gate electrode **105** is formed on the gate insulating layer **104**.

An interlayer insulating layer **106** is formed on the gate insulating layer **104** to cover the gate electrode **105**, and a source electrode **107** and a drain electrode **108** are formed on the interlayer insulating layer **106** and make respective contact with the active layer **103** through contact holes.

The structure of the above-described thin film transistor TR is not necessarily limited thereto, and various types of the structures of the thin film transistor may be applicable. For example, the thin film transistor TR illustrated in FIG. **3** may have a top gate structure. Alternatively, a thin film transistor TR of a gate bottom gate structure may be used. Alternatively, other applicable structures of all of the thin film transistors may be applied.

A pixel circuit (not illustrated) including a capacitor along with the thin film transistor TR may be formed.

A passivation layer **109** covering the pixel circuit including the thin film transistor TR is formed. The passivation layer **109** may be an insulating layer having a planarized upper surface of a single layer or a plurality of layers. The passivation layer **109** may be formed by using an inorganic material and/or an organic material.

On the passivation layer **109**, an organic light emitting device EL is formed so as to make an electric connection with the thin film transistor TR. The organic light emitting device EL includes a first electrode **121**, a second electrode **122** and an intermediate layer **120**.

Particularly, the first electrode **121** is formed so as to make an electric connection with the drain electrode **108**.

On the passivation layer **109**, a pixel defining layer **119** covering the edge portion of the first electrode **121** is formed. The pixel defining layer **119** includes an opening portion **119a** positioned to correspond to the center portion of the first electrode **121**.

On the first electrode **121** exposed through the opening portion **119a**, the intermediate layer **120** including an organic emission layer is formed and the second electrode **122** covering the intermediate layer **120** is formed.

The intermediate layer may include a low molecular weight organic layer or a high molecular weight organic layer. When the low molecular weight organic layer is used, a hole injection layer (HIL), a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), an electron injection layer (EIL), etc. may be used as a single layer structure or as a stacked complex structure. The low molecular weight organic layer may be formed by means of a vacuum deposition method.

The HIL may be formed by using, for example, a phthalocyanine compound such as copper phthalocyanine, etc. or a starburst type amine such as tris(4-carbazoyl-9-ylphenyl)amine (TCTA), 4,4',4''-tris(N-3-methylphenyl-N-phenylamino)triphenylamine (m-MTDATA), 1,3,5-tris[4-(2-methylphenylphenylamino)phenyl]benzene (m-MTDAPB), etc.

The HTL may be formed by using, for example, N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1-biphenyl]-4,4'-diamine (TDP), N,N'-di(naphthalene-1-yl)-N,N'-diphenylbenzidine (α -NPD), etc.

The EIL may be formed by using, for example, a material such as LiF, NaCl, CsF, Li_2O , BaO, 8-hydroxy-quinolinato lithium (LiQ), etc.

The ETL may be formed by using, for example, tris(8-hydroxy)aluminum (Alq3).

The EML may include a host material and a dopant material. The EML may include an emission layer emitting various colors of visible light. In addition, the disposition of the EML may be diversely defined and may be disposed so as to produce different colors according to the pixels. However, the present disclosure may not be limited to the above-described embodiments. Color filters of different colors may be disposed according to the desired colors of the pixels after stacking a plurality of emission layers so as to accomplish white light with respect to the whole pixels according to a white light emitting method.

The first electrode **121** may function as an anode electrode, and the second electrode **122** may function as a cathode electrode. Alternatively, the polarities of the first electrode **121** and the second electrode **122** may be interchanged.

When the first electrode **121** functions as the anode electrode, the first electrode **121** may include a material having a high work function such as, for example, ITO, IZO, ZnO, In₂O₃, etc. and may additionally include a reflection layer formed by using, for example, Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Yb, Ca, etc.

When the second electrode **122** functions as a cathode electrode, the second electrode **122** may be formed by using a metal such as, for example, Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, Li, Ca, etc. In addition, the second electrode **122** may include, for example, ITO, IZO, ZnO, In₂O₃, etc. for the light transmission. In addition, the second electrode **122** may be formed as a thin film by using, for example, Al, Ag and/or Mg. The second electrode **122** is formed so that a common voltage may be applied to all of the pixels, and is thus formed as a common electrode which is not patterned to correspond to the pattern of the pixels. Alternatively, the second electrode **122** as the common electrode may be patterned in a mesh shape obtained by removing portions of the common electrode except for those overlapping the light emitting regions.

When the second electrode **122** is formed as the common electrode, a voltage drop may be generated at the second electrode **122**. Particularly, when the apparatus in FIG. 3 is a top emitting type apparatus in which a user may view an image from the upper portion in FIG. 3, the sheet resistance of the second electrode **122** may be increased because the second electrode **122** includes a light-transmitting metal oxide or a metal thin film. In this case, the generated voltage drop may be even larger.

In order to solve the above-described defects, a third electrode **130** making an electric connection with the second electrode **122** may be further formed in the present disclosure.

In addition, the upper surface of the second electrode **122** may be damaged due to the encapsulation substrate **191** illustrated in FIG. 1. The upper surface of the second electrode **122** may also be easily damaged during the formation of the encapsulation layer **192** in FIG. 2. In order to solve the above-described defects, a capping layer **140** is formed on the second electrode **122**.

The capping layer **140** is formed on the second electrode **122** in a first region **R1** and has a first edge portion **140a**.

The third electrode **130** is formed on the second electrode **122** in a second region **R2** and has a second edge portion **130a**. The third electrode **130** is disposed adjacent to the capping layer **140** while maintaining a horizontal state.

The area of a first region **R1** is larger than an area generating light emission in at least one pixel, and corresponds to a region covering the region generating the light emission in one pixel. The capping layer **140** is formed on the whole first region **R1**, and the edge portion of the first region **R1** is the first edge portion **140a** of the capping layer **140**. The second region **R2** corresponds to a region excluding the first region **R1** from the second electrode **122**. The third electrode **130** is formed on the whole second region **R2**, and the edge portion of the second region **R2** is the second edge portion **130a** of the third electrode **130**. The second region **R2** is a region excluding the area generating the light emission.

The side portion of the first edge portion **140a** of the capping layer **140** and the side portion of the second edge portion **130a** of the third electrode **130** are in contact with each other.

The third electrode may be formed to have a thickness greater than that of the second electrode **122** so as to decrease the sheet resistance of the second electrode **122**.

Because the capping layer **140** may cover the region generating the light emission in the pixel, the capping layer **140** may be formed so as to transmit light. The capping layer **140** may be formed as a thin film layer having a thickness smaller than the third electrode **130**, however, the thickness of the capping layer **140** is not limited thereto.

In an example embodiment, the material of the third electrode **130** and the capping layer **140** may be selected so that adhesiveness between the third electrode **130** and the capping layer **140** may be smaller than that between the third electrode **130** and the second electrode **122**.

The capping layer may be formed by using, for example, a material including 8-quinolinolato lithium (Liq), N,N-diphenyl-N,N-bis(9-phenyl-9H-carbazol-3-yl)biphenyl-4,4'-diamine, N(diphenyl-4-yl)9,9-dimethyl-N-(4(9-phenyl-9H-carbazol-3-yl)phenyl)-9H-fluorene-2-amine, or 2-(4-(9,10-di(naphthalene-2-yl)anthracene-2-yl)phenyl)-1-phenyl-1H-benzo-[D]imidazole.

The third electrode **130** may be formed by using, for example, Mg.

Mg used for forming the third electrode **130** is similar to the material used for forming second electrode **122**, that is, both are formed by using metals, and the adhesiveness between the third and second electrodes **130** and **120** is good. However, the adhesiveness between Mg and the material of the above-described capping layer **140** is not good. Thus, the third electrode **130** may be simply patterned by using the adhesiveness properties between the third electrode **130** and the capping layer **140**.

As described above, the third electrode **130** is patterned so as to be formed only in the second region **R2**. However, after forming the intermediate layer **120** of the organic light emitting device EL, the third electrode **130** may be patterned without having to use a wet process such as a photolithography process, which is widely used as a patterning method of a common metal layer. When humidity and/or oxygen penetrate into the intermediate layer **120** while conducting the wet process, the lifetime of the organic light emitting device EL may be rapidly decreased.

Thus, the patterning of the third electrode **130** is very difficult in a practical process.

According to the present disclosure, the third electrode **130** may be patterned by using the adhesive properties between the third electrode **130** and the capping layer **140**. Particular methods will be described below.

The third electrode **130** and the capping layer **140** may each include multiple layers, respectively.

Referring to FIG. 4, the third electrode **130** includes a lower electrode layer **131** and an upper electrode layer **132**.

In addition, the capping layer **140** includes a first capping layer **141** and a second capping layer **142**. The first capping layer **141** and the second capping layer **142** include the above-described materials of the capping layer **140** and may be formed by using the same material or different materials.

In order to secure the target thickness of the capping layer **140**, the deposition process is conducted more than once; it is conducted as two separate deposition processes. First, the first capping layer **141** is formed and the lower electrode layer **131** is formed. Then, the second capping layer **142** is formed and the upper electrode layer **132** is formed. In this case, the patterning of the third electrode **130** and the capping layer **140** may be easily conducted, and control of each process to form the minute pattern of the third electrode **130** and the capping layer **140** may be possible. In addition, the third electrode **130** may be easily prevented from being formed in the first region **R1**, and thus the transmittance of the organic light emitting display apparatus **100** may be improved.

In this example embodiment, the capping layer **140** is formed by conducting the deposition process twice, and the third electrode **130** is formed by conducting the deposition process twice. However, the deposition process may not be limited thereto, and may be separately conducted three or more times.

FIGS. **5** to **10** illustrate a method of manufacturing the organic light emitting display apparatus illustrated in FIG. **1** in sequence.

First, referring to FIG. **5**, elements up to the second electrode **122** are formed on the substrate **101**.

Then, referring to FIG. **6**, a deposition process is conducted with respect to the substrate **101** on which the elements up to the second electrode **122** are formed. That is, a mask **170** is disposed so as to face the substrate **101**, and the deposition process is conducted by using a first deposition source **S1**. The first deposition source **S1** includes at least one material from among the above-described various materials for forming the capping layer **140**.

The mask **170** includes a shielding part **171** and a slit part **172**. The slit part **172** has a specific pattern corresponding to a region for forming the capping layer **140**, that is, to the first region **R1**.

The deposition process by using the first deposition source **S1** is conducted to form the first capping layer **141** of the capping layer **140** on the second electrode **122** in the first region **R1**, as illustrated in FIG. **7**.

Then, referring to FIG. **8**, the deposition process is conducted with respect to the substrate **101** including the elements formed up to the first capping layer **141**. That is, an open mask **180** is disposed so as to face the substrate **101**, and the deposition process is conducted using a second deposition source **S2**. The second deposition source **S2** includes the above-described material for forming the third electrode **130**, that is, Mg. The open mask **180** includes a shield part **181** and an opening part **182**. The shield part **181** has a similar shape as a square window frame, and the opening part **182** forms the center of the shield part **181**. The open mask **180** includes the opening part **182** having no specific pattern. That is, different from the above-described mask **170**, the open mask **180** is formed to pass the deposition material onto the whole surface of the substrate **101**, including over the capping layer deposited in the pattern, except for those portions of the surface of the substrate that are blocked by the borders of the shield part **181**.

Meanwhile, even though the open mask **180** is provided in this example embodiment, the open mask **180** may be omitted when using the second deposition source **S2** during the deposition process.

Through conducting the deposition process through the second deposition source **S2**, the lower electrode layer **131** of the third electrode **130** is formed on the second electrode **122** in the second region **R2**.

In this case, because the material for forming the third electrode **130** included in the second deposition source **S2** has poor adhesiveness with the first capping layer **141**, a layer of second deposition source **S2** material may not be formed on the first capping layer **141**, but a layer may be formed only on the exposed portions of second electrode **122**, the second electrode **122** having relatively good adhesiveness with the second deposition source **S2** material.

Thus, the lower electrode layer **131** may be naturally patterned without using a separate mask or without conducting a patterning process. Particularly, the whole of the third electrode **130** may be formed by conducting the deposition process more than once. That is, the whole of the third electrode **130** may be formed by first forming the lower electrode layer

131 to a specific thickness corresponding to half of the desired thickness of the third electrode **130**. In this case, the minute patterning of the lower electrode layer **131** may be possible.

Then, referring to FIG. **9**, the deposition process is conducted with respect to the substrate **101** including elements formed up to the lower electrode layer **131**. That is, the mask **170** is disposed so as to face the substrate **101** as illustrated in FIG. **6**, and the deposition process is conducted using the first deposition source **S1** to form the second capping layer **142** on the first capping layer **141** in the first region **R1**, to complete the capping layer **140**. Because the mask **170** is the same as that described above, detailed description thereof will be omitted. In addition, because the masks **270** and **370** in this example embodiment are the same as the mask **170**, detailed description thereof will also be omitted.

Referring to FIG. **10**, the deposition process is conducted with respect to the substrate **101** including the elements formed up to the second capping layer **142**. That is, as illustrated in FIG. **8**, the open mask **180** is disposed so as to face the substrate **101**, and the deposition process is conducted using the second deposition source **S2** to form the upper electrode layer **132** on the lower electrode layer **131** in the second region **R2** to complete the third electrode **130**. As described above, the upper electrode layer **132** may be formed by conducting the deposition process using the second deposition source **S2** without using the open mask **180**.

Because the open mask **180** is the same as described above, detailed description thereof will be omitted. In addition, because the open masks **280** and **380** in a following example embodiment are the same as the open mask **180**, detailed description thereof will also be omitted.

In this example embodiment, the first capping layer **141** and the second capping layer **142** are formed by using the mask **170** two separate times to complete the capping layer **140**. Through the processes, the capping layer **140** may be easily formed into a target pattern having a target thickness. Particularly, the minute pattern of the capping layer **140** may be controlled so that it corresponds to only the first region **R1** may be possible.

In addition, the lower electrode layer **131** and the upper electrode layer **132** are formed by using the open mask **180** two separate times to complete the third electrode **130**. Particularly, after forming the first capping layer **141**, the lower electrode layer **131** is formed in the second region **R2** to a desired shape by using the first capping layer **141**. In addition, after forming the second capping layer **142**, the upper electrode layer **132** is formed in the second region **R2** to a desired shape by using the second capping layer **142**. Through the method, the minute patterning of the third electrode **130** in the second region **R2** without using a mask having a specific pattern may be easily accomplished.

FIGS. **11** to **13** illustrate various example embodiments of the shapes of a capping layer of the organic light emitting display apparatus in FIG. **1**.

As illustrated in FIG. **11**, one capping layer **140** may be provided per one pixel **P** as an island shape. In FIG. **11**, the capping layer **140** has an area covering the whole area of one pixel **P**. However, the capping layer **140** may have an area covering only the light emitting region of pixel **P** as described above, without limitation. In this case, the third electrode **130** may form a lattice pattern between each of the pixels **P**.

As illustrated in FIG. **12** as another example embodiment, one capping layer **140** may be provided for a plurality of the pixels **P** as an island shape. In this case, the third electrode **130** may form a lattice pattern between the pluralities of the pixels **P**.

As illustrated in FIG. 13 as another example embodiment, the capping layer 140 may be provided for a plurality of the pixels P arranged in a row in a stripe shape. In this case, the third electrode 130 may form a stripe pattern between each row of the pixels P.

FIGS. 14 to 17 illustrate another example embodiment of a method of manufacturing the organic light emitting display apparatus in FIG. 1.

Referring to FIG. 14, a deposition process is conducted with respect to a substrate 101 including the elements formed up to a second electrode 122. A mask 170 includes a shield part 171 and a slit part 172. The slit part 172 has a specific pattern corresponding to a region for forming a capping layer 140, that is, a first region R1.

Through conducting the deposition process using a first deposition source S1, a first capping layer 141 of the capping layer 140 is formed on the second electrode 122 in the first region R1.

Then, referring to FIG. 15, the deposition process is conducted with respect to the substrate 101 including the elements formed up to the first capping layer 141. That is, an open mask 180 is disposed so as to face the substrate 101, and the deposition process is conducted using a second deposition source S2. Through conducting the deposition process using the second deposition source S2, a lower electrode layer 131 of the third electrode 130 is formed on the second electrode in a second region R2.

Then, referring to FIG. 16, the deposition process is conducted with respect to the substrate 101 including the elements formed up to the lower electrode layer 131. Particularly, the open mask 180 is disposed so as to face the substrate 101, and the deposition process is conducted by using the first deposition source S1 to form a second capping layer 142 on the first capping layer 141 in the first region R1 to complete the capping layer 140. In this case, the material for forming the second capping layer 142 included in the first deposition source S1 has good adhesive properties with respect to the first capping layer 141 and has poor adhesive properties with respect to the lower electrode layer 131. Thus, a layer of the first deposition source S1 material may not be formed on the lower electrode layer 131, but a layer of the first deposition source material S1 may be formed on the first capping layer 141 having relatively good adhesiveness.

Then, referring to FIG. 17, the deposition process is conducted with respect to the substrate 101 including the elements formed up to the second capping layer 142. That is, the open mask 180 is disposed so as to face the substrate 101, and the deposition process using the second deposition source S2 is conducted to form an upper electrode layer 132 on the lower electrode layer 131 in the second region R2 to complete the third electrode 130.

FIG. 18 illustrates another example embodiment of a method of manufacturing the organic light emitting display apparatus illustrated in FIG. 1.

Referring to FIG. 18, the deposition process is continuously conducted while moving a substrate 101 that includes elements formed up to second electrode 122 along a direction indicated by the arrow A (x-axis direction). That is, a deposition process is conducted with respect to the substrate 101 using a first deposition source S1. A mask 170 is disposed over the substrate 101 to form a first capping layer in a first region R1.

Then, the deposition process is conducted using a second deposition source S2, the first deposition source S1, the second deposition source S2, the first deposition source S1 and the second deposition source S2 one by one. Particularly, an open mask 180 is disposed over the substrate 101 to conduct

the deposition process. Alternatively, the deposition process may be conducted excluding the open mask 180.

Through conducting the above-described processes, a third electrode 130 obtained by stacking three layers and a capping layer 140 obtained by integrating three layers may be easily formed.

FIG. 19 is a cross-sectional view of an organic light emitting display apparatus according to another example embodiment. FIG. 20 is an enlarged view of the regions Y1 and Y2 shown in FIG. 19. For the convenience of explanation, different portions from the above-described example embodiment will be explained in priority.

Referring to FIGS. 19 and 20, a buffer layer 202 is formed on a substrate 201, and a thin film transistor TR is formed on the buffer layer 202. The thin film transistor TR includes an active layer 203, a gate electrode 205, a source electrode 207 and a drain electrode 208.

The active layer 203 is formed on the buffer layer 202, a gate insulating layer 204 covering the active layer 203 is formed, and a gate electrode 205 is formed on the gate insulating layer 204. An interlayer insulating layer 206 covering the gate electrode 205 is formed on the gate insulating layer 204. On the interlayer insulating layer 206, a source electrode 207 and a drain electrode 208 are formed and respectively make contact with the active layer 203 through contact holes. A passivation layer 209 covering a pixel circuit including the thin film transistor TR is formed. On the passivation layer 209, an organic light emitting device EL making an electric connection with the thin film transistor TR is formed. The organic light emitting device EL includes a first electrode 221, a second electrode 222 and an intermediate layer 220. Particularly, the first electrode 221 is formed so as to make an electric connection with the drain electrode 208. On the passivation layer 209, a pixel defining layer 219 including an opening portion 219a is formed.

On the first electrode 221, an intermediate layer 220 including an organic light emission layer is formed, and the second electrode 222 covering the intermediate layer 220 is formed.

A third electrode 230 making an electric connection with the second electrode 222 is formed, and a capping layer 240 is formed on the second electrode 222.

The capping layer 240 is formed on the second electrode 222 in the first region R1, and has a first edge portion 240a.

The third electrode 230 is formed on the second electrode 222 in the second region R2, and has a second edge portion 230a. The third electrode 230 is disposed adjacent to the capping layer 240 while maintaining a horizontal state.

The side portion of the first edge portion 240a of the capping layer 240 and the side portion of the second edge portion 230a of the third electrode 230 may contact each other.

The third electrode 230 may be formed to have a thickness greater than the second electrode 222 so as to decrease the sheet resistance of the second electrode 222.

Because the capping layer 240 may cover the region of emitting light in the pixel, the capping layer 240 may be formed so as to transmit light. The capping layer 240 may be formed as a thin film layer having a thickness smaller than the third electrode 230, however, the thickness of the capping layer 240 is not limited thereto.

As illustrated in an example embodiment, the materials of the third electrode 230 and the capping layer 240 may be selected so that the adhesiveness between the third electrode 230 and the capping layer 240 is smaller than the adhesiveness between the third electrode 230 and the second electrode 222.

The capping layer **240** includes multiple layers in this example embodiment.

Referring to FIG. **20**, the capping layer **240** includes a first capping layer **241** and a second capping layer **242**. The first capping layer **241** and the second capping layer **242** may include the above-described materials of the capping layer **240**, and may be formed by using the same material or different materials.

In order to achieve the target thickness of the capping layer **240**, the deposition process may be conducted more than one time. Particularly, the deposition process is conducted two separate times. That is, after forming the first capping layer **241**, the third electrode **230** and the second capping layer **242** are formed at the same time, as described below. Through the above-described processes, the third electrode **230** and the capping layer **240** may be easily patterned and controlled, and the minute pattern of each layer may be possible. In addition, the formation of the third electrode **230** in the first region **R1** may be easily prevented to improve the transmittance of the organic light emitting display apparatus **200**.

FIGS. **21** and **22** illustrate a method of manufacturing the organic light emitting display apparatus illustrated in FIG. **19**.

First, referring to FIG. **21**, a deposition process is conducted with respect to the substrate **201**. Even though not illustrated, elements up to the second electrode **222** are formed on the substrate **201**.

A mask **270** is disposed so as to face the substrate **201**, and the deposition process is conducted using the first deposition source **S1**. The mask **270** includes a shielding part **271** and a slit part **272**. The slit part **272** includes a specific pattern corresponding to a region for forming the capping layer **240**, that is, the first region **R1**.

Through conducting the deposition process by using the first deposition source **S1**, the first capping layer **241** of the capping layer **240** is formed on the second electrode **222** in the first region **R1**.

Then, referring to FIG. **22**, the deposition process is conducted with respect to the substrate **201** including the elements formed up to the first capping layer **241**. That is, an open mask **280** is disposed so as to face the substrate **201**, and a co-deposition process using the first deposition source **S1** and the second deposition source **S2** is conducted. Alternatively, the use of the open mask **280** may be omitted.

Through conducting the co-deposition process by using the first deposition source **S1** and the second deposition source **S2**, the third electrode **230** is formed on the second electrode **222** in the second region **R2**, and the second capping layer **242** is formed on the first capping layer **241** in the first region **R1**.

In this case, because the adhesiveness of the material for forming the third electrode **230** included in the second deposition source **S2** with the first capping layer **241** is not good, a layer may not be formed on the first capping layer **241**. However, a layer may be formed on the second electrode **222** having relatively good adhesiveness. Similarly, the material for forming the second capping layer **242** included in the first deposition source **S1** may be formed on the first capping layer **241** having relatively good adhesiveness.

Thus, the third electrode **230** and the second capping layer **242** may be naturally patterned without using a separate mask or without conducting a separate patterning process.

In this example embodiment, after forming the first capping layer **241** using the mask **270**, the second capping layer **242** is formed using the open mask **280** to complete the capping layer **240**. Through conducting the above-described processes, the capping layer **240** may be easily formed as a pattern having a target thickness. Particularly, the minute

pattern of the capping layer **240** corresponding to only the first region **R1** may be possible.

In addition, the third electrode **230** is formed while depositing the second capping layer **242** using the open mask **280**. Through conducting the processes, the minute patterning of the third electrode **230** in the second region **R2** without using a mask having a specific pattern may be easily accomplished.

FIG. **23** is a cross-sectional view of an organic light emitting display apparatus according to another example embodiment. FIG. **24** is an enlarged view of regions **Y1** and **Y2** shown in FIG. **23**. For the convenience of the explanation, different portions from the above-described example embodiment will be explained in priority.

Referring to FIGS. **23** and **24**, a buffer layer **302** is formed on a substrate **301**, and a thin film transistor **TR** is formed on the buffer layer **302**. The thin film transistor **TR** includes an active layer **303**, a gate electrode **305**, a source electrode **307** and a drain electrode **308**.

On the buffer layer **302**, the active layer **303** is formed, a gate insulating layer **304** covering the active layer **303** is formed, and the gate electrode **305** is formed on the gate insulating layer **304**. An interlayer insulating layer **306** covering the gate electrode **305** is formed on the gate insulating layer **304**, and the source electrode **307** and the drain electrode **308** are formed on the interlayer insulating layer **306** to respectively make contact with the active layer **303** through contact holes. A passivation layer **309** covering a pixel circuit including the thin film transistor **TR** is formed. On the passivation layer **309**, an organic light emitting device **EL** making an electric connection with the thin film transistor **TR** is formed. The organic light emitting device **EL** includes a first electrode **321**, a second electrode **322** and an intermediate layer **320**. Particularly, the first electrode **321** is formed so as to make an electric connection with the drain electrode **308**. On the passivation layer **309**, a pixel defining layer **319** including an opening portion **319a** is formed.

On the first electrode **321**, the intermediate layer **320** including the organic light emission layer is formed, and the second electrode **322** covering the intermediate layer **320** is formed.

A third electrode **330** is formed so as to make an electric connection with the second electrode, and a capping layer **340** is formed on the second electrode **322**.

The capping layer **340** is formed on the second electrode **322** in the first region **R1** and has a first edge portion **340a**.

The third electrode **330** is formed on the second electrode **322** in the second region **R2** and has a second edge portion **330a**. The third electrode **330** is disposed adjacent to the capping layer **340** while maintaining a horizontal state.

The side portion of the first edge portion **340a** of the capping layer **340** and the side portion of the second edge portion **330a** of the third electrode **330** contact each other.

The third electrode **330** may be formed to have a thickness greater than the second electrode **322** so as to decrease the sheet resistance of the second electrode **322**.

Because the capping layer **340** may cover a region emitting light in the pixel, the capping layer may be formed so as to transmit the light. The capping layer **340** may be formed as a thin film layer having a thickness smaller than the third electrode **330**, however, the thickness of the capping layer **340** is not limited thereto.

In an example embodiment, the materials for forming the third electrode **330** and the capping layer **340** may be selected so that the adhesiveness between the third electrode **330** and the capping layer **340** is smaller than the adhesiveness between the third electrode **330** and the second electrode **322**.

The capping layer 340 and the third electrode 330 each include multiple layers.

Referring to FIG. 24, the third electrode 330 includes a lower electrode layer 331 and an upper electrode layer 332. In addition, the capping layer 340 includes a first capping layer 341, a second capping layer 342, a third capping layer 343 and a fourth capping layer 344. The first capping layer 341 to the fourth capping layer 344 may be formed by using the same material or different materials.

In order to achieve the target thickness of the capping layer 340, the deposition process may be conducted more than one time. The deposition process is conducted multiple times, particularly, four times. In addition, in order to achieve the target thickness of the third electrode 330, the deposition process may be conducted two times.

That is, after forming the first capping layer 341, the lower electrode layer 331 and the second capping layer 342 are formed at the same time. After forming the third capping layer 343, the upper electrode layer 332 and the fourth capping layer 344 are formed at the same time. Particular explanation will be described herein below.

Through conducting the above-described processes, the patterning of the third electrode 330 and the capping layer 340 may be easily conducted and controlled, and the minute pattern for each layer may be possible. In addition, the formation of the third electrode 330 in the first region R1 may be easily prevented, and the transmittance of the organic light emitting display apparatus 300 may be improved.

FIGS. 25 to 28 illustrate a method of manufacturing the organic light emitting display apparatus illustrated in FIG. 23 in sequence.

Referring to FIG. 25, a deposition process is conducted with respect to the substrate 301. Even though not illustrated, the elements up to second electrode 322 are formed on the substrate 301.

A mask 370 is disposed so as to face the substrate 301, and the deposition process is conducted by using a first deposition source S1. The mask includes a shielding part 371 and a slit part 372. The slit part 372 has a specific pattern corresponding to a region for forming the capping layer 340, that is, the first region R1.

Through conducting the deposition process by using the first deposition source S1, the first capping layer 341 of the capping layer 340 is formed on the second electrode 322 in the first region R1.

Referring to FIG. 26, the deposition process is conducted with respect to the substrate 301 including the elements formed up to the first capping layer 341. That is, an open mask 380 is disposed so as to face the substrate 301, and a co-deposition process using the first deposition source S1 and the second deposition source S2 is conducted. Alternatively the use of the open mask 380 may be omitted.

Through conducting the co-deposition process by using the first deposition source S1 and the second deposition source S2, the lower electrode layer 331 is formed on the second electrode 322 in the second region R2, and the second capping layer 342 is formed on the first capping layer 341 in the first region R1.

In this case, the material for forming the lower electrode layer 331 of the third electrode 330 included in the second deposition source S2 has poor adhesiveness with the first capping layer 341. Thus, a layer of deposition source S2 material may not be formed on the first capping layer 341, but a layer of deposition source S2 material may be formed on the second electrode 322 having relatively good adhesiveness. Similarly, the material for forming the second capping layer

342 included in the first deposition source S1 may be formed on the first capping layer 341 having relatively good adhesiveness.

Then, referring to FIG. 27, the deposition process is conducted with respect to the substrate 301 including the elements formed up to the lower electrode layer 331 and the second capping layer 342.

After disposing the mask 370 so as to face the substrate 301, the deposition process is conducted by using the first deposition source S1. The deposition process through the first deposition source S1 is conducted to form the third capping layer 343 on the second capping layer 342 in the first region R1.

Then, referring to FIG. 28, the deposition process is conducted with respect to the substrate 301 including the elements formed up to the third capping layer 343. That is, the open mask 380 is disposed so as to face the substrate 301, and the co-deposition process using the first deposition source S1 and the second deposition source S2 is conducted. Alternatively, the use of the open mask 380 may be omitted.

Through conducting the co-deposition process using the first deposition source S1 and the second deposition source S2, the upper electrode layer 332 is formed on the lower electrode layer 331 in the second region R2, and the fourth capping layer 344 is formed on the third capping layer 343 in the first region R1.

In this case, the material for forming the upper electrode layer 332 of the third electrode 330 included in the second deposition source S2 has poor adhesiveness with the third capping layer 343. Thus, a layer of the second deposition source S2 material may not be formed on the third capping layer 343, but a layer of the second source S2 material may be formed on the lower electrode layer 331 having relatively good adhesiveness. Similarly, the material for forming the fourth capping layer 344 included in the first deposition source S1 may form a layer on the third capping layer 343 having relatively good adhesiveness.

In this example embodiment, after forming the first capping layer 341 using the mask 370, the second capping layer 342 and the lower electrode layer 331 are formed using the open mask 380 at the same time. In addition, after forming the third capping layer 343 using the mask 370, the fourth capping layer 344 and the upper electrode layer 332 are formed using the open mask 380 at the same time.

Through conducting the above-described processes, the capping layer 340 having a pattern with a target thickness may be easily formed. Particularly, the minute pattern of the capping layer 340 may be controlled so as to correspond to only the first region R1 may be possible.

In addition, while depositing the second capping layer 342 and the fourth capping layer 344 using the open mask 380, the lower electrode layer 331 and the upper electrode layer 332 of the third electrode 330 may be formed at the same time. Thus, the minute patterning of the third electrode 330 in the second region R2 without using a specific pattern mask may be easily conducted.

FIGS. 29 to 32 illustrate another method of manufacturing the organic light emitting display apparatus illustrated in FIG. 23 in sequence.

First, referring to FIG. 29, a deposition process is conducted with respect to the substrate 301. Even though not illustrated, the elements up to second electrode 322 are formed on the substrate 301.

A mask 370 is disposed so as to face the substrate 301, and the deposition process is conducted using the first deposition source S1. The mask 370 includes the shielding part 371 and

the slit part **372**. The slit part **372** has a specific pattern corresponding to a region for forming the capping layer **340**, that is, the first region **R1**.

Through conducting the deposition process by using the first deposition source **S1**, the first capping layer **341** of the capping layer **340** is formed on the second electrode **322** in the first region **R1**.

Referring to FIG. **30**, the deposition process is conducted with respect to the substrate **301** including the elements formed up to the first capping layer **341**. That is, the open mask **380** is disposed so as to face the substrate **301**, and the co-deposition process is conducted using the first deposition source **S1** and the second deposition source **S2**. Alternatively, the use of the open mask **380** may be omitted.

Through conducting the co-deposition process using the first deposition source **S1** and the second deposition source **S2**, the lower electrode layer **331** is formed on the second electrode **322** in the second region **R2**, and the second capping layer **342** is formed on the first capping layer **341** in the first region **R1**.

In this case, the material for forming the lower electrode layer **331** of the third electrode **330** included in the second deposition source **S2** has poor adhesiveness with the first capping layer **341**. Thus, a layer of the second deposition source **S2** material may not be formed on the first capping layer **341**, but a layer of the second deposition source **S2** material may be formed on the second electrode **322** having relatively good adhesiveness. Similarly, the material for forming the second capping layer **342** included in the first deposition source **S1** may form a layer on the first capping layer **341** having relatively good adhesiveness.

Then, referring to FIG. **31**, the deposition process is conducted with respect to the substrate **301** including the elements formed up to the lower electrode layer **331** and the second capping layer **342**.

After disposing the mask **380** so as to face the substrate **301**, the deposition process is conducted by using the first deposition source **S1**. Through conducting the deposition process by using the first deposition source **S1**, the third capping layer **343** is formed on the second capping layer **342** in the first region **R1**. In this case, the material for forming the third capping layer included in the first deposition source **S1** has good adhesiveness with the second capping layer **342** but has poor adhesiveness with the lower electrode layer **331**. Thus, a layer of the first deposition source **S1** material may not be formed on the lower electrode layer **331**, but a layer of the first deposition source **S1** material may be formed on the second capping layer **342** having relatively good adhesiveness.

Referring to FIG. **32**, the deposition process is conducted with respect to the substrate **301** including the elements formed up to the third capping layer **343**. That is, the open mask **380** is disposed so as to face the substrate **301**, and the co-deposition process using the first deposition source **S1** and the second deposition source **S2** is conducted. Alternatively, the use of the open mask **380** may be omitted.

Through conducting the co-deposition process by using the first deposition source **S1** and the second deposition source **S2**, the upper electrode layer **332** is formed on the lower electrode layer **331** in the second region **R2**, and the fourth capping layer **344** is formed on the third capping layer **343** in the first region **R1**.

In this case, the material for forming the upper electrode layer **332** of the third electrode **330** included in the second deposition source **S2** has poor adhesiveness with the third capping layer. Thus, a layer of the second deposition source **S2** material may not be formed on the third capping layer **343**,

but a layer of the second deposition source **S2** material may be formed on the lower electrode layer **331** having relatively good adhesiveness. Similarly, the material for forming the fourth capping layer **344** included in the first deposition source **S1** may form a layer on the third capping layer **343** having relatively good adhesiveness.

In this example embodiment, after forming the first capping layer **341** using the mask **370**, the second capping layer **342** and the lower electrode layer **331** are formed using the open mask **380** at the same time. Then, after forming the third capping layer **343** using the open mask **380**, the fourth capping layer **344** and the upper electrode layer **332** are formed using the open mask **380** at the same time.

Through conducting the above-described processes, the capping layer **340** having a target pattern to a target thickness may be easily formed. Particularly, the minute pattern of the capping layer **340** may be controlled so as to correspond only to the first region **R1** may be possible.

In addition, while depositing the second capping layer **342** and the fourth capping layer **344** using the open mask **380**, the lower electrode layer **331** and the upper electrode layer **332** of the third electrode **330** may be formed at the same time. Thus, the minute patterning of the third electrode **330** in the second region **R2** without using a mask having a specific pattern may be easily accomplished.

FIG. **33** is a plan view illustrating an organic light emitting display apparatus according to another example embodiment, and FIG. **34** is a cross-sectional view illustrating one pixel of the organic light emitting display apparatus in FIG. **33**.

The organic light emitting display apparatus **400** includes a light-transmitting area **TA** formed to transmit an external light, and a plurality of pixel areas **PA** separated from each on either side of the light-transmitting area **TA**.

As illustrated in FIG. **33**, a pixel circuit part **PC** is positioned in each of the pixel areas **PA**, and a plurality of conductive lines such as a scan line **S**, a data line **D** and a power source line **V** are electrically connected to the pixel circuit part **PC**. Even though not illustrated, various conductive lines apart from the scan line **S**, the data line **D** and the power source line **V** may be provided according to the constitution of the pixel circuit part **PC**.

In addition, the pixel circuit part **PC** includes a first thin film transistor **T1** connected to the scan line **S** and the data line **D**, a second thin film transistor **T2** connected to the first thin film transistor **T1** and the power source line **V**, and a capacitor **Cst** connected to the first thin film transistor **T1** and the second thin film transistor **T2**. In this case, the first thin film transistor **T1** may be a switching transistor, and the second thin film transistor **T2** may be a driving transistor. The second thin film transistor **T2** is electrically connected to the first electrode **421**. The number of the above-described thin film transistors and the capacitor is not limited to that of the illustrated example embodiment, and two or more thin film transistors and one or more capacitors may be combined according to the pixel circuit part **PC**.

Referring to FIG. **33**, the scan line **S** and the first electrode **421** are disposed overlapping each other. However, example embodiments are not limited thereto. At least one of the plurality of the conductive lines including the scan line **S**, the data line **D** and the power source line **V** may be disposed overlapping the first electrode **421**. Alternatively, all of the plurality of the conductive lines including the scan line **S**, the data line **D** and the power source line **V** may be disposed overlapping the first electrode **421**, or may be disposed adjacent to the first electrode **421** according to the design requirements.

In this example embodiment, distortion due to the scattering of the external light due to the patterns of the devices in the pixel circuit part PC may be prevented.

The pixel area PA and the light-transmitting area TA are formed so that the ratio of the area of the light-transmitting area TA to the total area of the pixel area PA and the light-transmitting area TA is in the range of from about 5% to about 90%.

When the ratio of the area of the light-transmitting area TA to the total area of the pixel area PA and the light-transmitting area TA is less than about 5%, it may be difficult for a user to observe an object or an image positioned at the opposite side of the organic light emitting display apparatus 400. That is, the transparency of the organic light emitting display apparatus 400 is poor. However, when the intensity of an external light is high, even if the ratio of the area of the light-transmitting area TA to the total area of the pixel area PA and the light-transmitting area TA is about 5%, a user may be able to visually recognize an object or an image positioned at the opposite side of the organic light emitting display apparatus 400. Thus, the user may recognize the organic light emitting display apparatus 400 as a light-transmitting display apparatus.

When the ratio of the area of the light-transmitting area TA to the total area of the pixel area PA and the light-transmitting area TA exceeds about 90%, it may be difficult to generate a stable image through the light emitting in the pixel area PA. That is, as the area of the pixel area PA decreases, the luminance of the light emitted from the intermediate layer 420 is to be increased to generate a stable image. When the luminance of the light emitted from the organic light emitting device is increased as described above, the lifetime of the organic light emitting device may be rapidly decreased.

The ratio of the area of the light-transmitting area TA to the total area of the pixel area PA and the light-transmitting area TA may be in the range of from about 20% to about 70%.

When the ratio of the area of the light-transmitting area TA to the total area of the pixel area PA and the light-transmitting area TA is less than about 20%, the area of the pixel area PA is excessively large when compared with the light-transmitting area TA. Thus, a user may perceive the limit in observing the image at the opposite position through the light-transmitting area TA. When the ratio exceeds about 70%, the design of the pixel circuit part PC to be disposed in the pixel area PA may be limited.

In the pixel area PA, the first electrode 421, which is electrically connected to the pixel circuit part PC, may be provided. The pixel circuit part PC may be overlapped by the first electrode 421 so as to be shielded by the first electrode 421. In addition, at least one of the conductive lines including the above-described scan line S, the data line D and the power source line V may be disposed so as to cross the first electrode 421. Alternatively, because these conductive lines have a smaller inhibition ratio on the transmittance when compared with the pixel circuit part PC, all of the conductive lines may be disposed adjacent to the first electrode 421 according to design constraints.

As described above, when the first electrode 421 includes a reflection layer manufactured by using a conductive metal for reflecting light, the first electrode 421 may shield the pixel circuit part PC, and the distortion of the external image due to the pixel circuit part PC in the pixel area PA may be prevented.

As illustrated in FIG. 34, the pixel area PA and the light-transmitting area TA are positioned in the first region R1.

In this case, because the capping layer 440 is positioned in the first region R1, all of the pixel area PA and the light-transmitting area TA may be covered. In addition, the third

electrode 430 is provided in the second region R2 which is at the outer region of the first region R1.

In this example embodiment, because the capping layer 440 uses light-transmitting organic materials as described above, the light transmittance in the light-transmitting area TA may not be affected. The structure, the material, the manufacturing method, etc. of the capping layer 440 and the third electrode 430 are the same as those described in the above-described embodiments.

Even though not illustrated in the drawings, the light transmittance in the light-transmitting area TA may be increased by forming a light-transmitting window by excluding at least a portion of the second electrode 430 in the light-transmitting area TA. In this case, the light-transmitting window may be further formed on at least one layer among the pixel defining layer 419, the passivation layer 409, the interlayer insulating layer 406, the gate insulating layer 404 and the buffer layer 402, let alone the second electrode 430 by removing a portion of the second electrode 430.

FIG. 35 is a plan view illustrating an organic light emitting display apparatus according to another example embodiment. Particularly, FIG. 35 illustrates three plan views corresponding to three sub-pixels of an organic light emitting display apparatus 500.

Referring to FIG. 35, one light-transmitting area TA corresponding to first electrodes 521a, 521b and 521c of the three sub-pixels is formed. The first data line D1 to third data line D3 are electrically connected with the first electrodes 521a, 521b and 521c of the three sub-pixels, respectively. In addition, a first power source line V1 makes an electric connection with the first electrode 521a and the second first electrode 521b, and a second power source line V2 makes an electric connection with the third first electrode 521c.

In this structure, one large light-transmitting area TA may be provided with respect to a plurality of the sub-pixels. Thus, the transmittance of the total display may be increased even higher, and the image distortion due to the scattering of light may be decreased still more.

Even though not illustrated, a light-transmitting window may be further formed on at least one layer of a second electrode, a pixel defining layer, a passivation layer, an insulating interlayer, a gate insulating layer and a buffer layer in the light-transmitting area TA.

In addition, in this example embodiment, the light-transmitting area TA and the pixel area PA are disposed in the first region (not illustrated), and a capping layer (not illustrated) is disposed in the first region (not illustrated) to cover the light-transmitting area TA and the pixel area PA. In addition, a third electrode (not illustrated) may be formed in the second region which is the outer region of the first region (not illustrated).

While the present disclosure has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present disclosure, including the following claims.

What is claimed is:

1. A method of manufacturing an organic light emitting display apparatus comprising:
 - forming a first electrode on a substrate;
 - forming an intermediate layer including an organic emission layer on the first electrode;
 - forming a second electrode on the intermediate layer;
 - forming a capping layer on the second electrode in a first region, the capping layer having a first edge portion and at least two layers; and

21

forming a third electrode on the second electrode in a second region, the second region being not overlapped with the first region, the third electrode including a second edge portion having a side portion facing a side portion of the first edge portion of the capping layer, and wherein the third electrode comprises a plurality of electrode layers stacked in sequence.

2. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the third electrode and the capping layer are formed through a deposition process.

3. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein an adhesiveness between a metal for forming the third electrode and the capping layer is smaller than an adhesiveness between the metal for forming the third electrode and the second electrode.

4. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming the capping layer includes using a mask having a slit part that corresponds to a pattern of the capping layer.

5. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming the third electrode includes using an open mask including an opening over the capping layer.

6. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming the third electrode includes performing a deposition process without using a mask.

7. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the capping layer comprises:

forming a first layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part that corresponds to a pattern of the capping layer; and

forming a remaining layer of the capping layer by using an open mask including an opening over the capping layer.

8. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the capping layer comprises:

forming a first layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part that corresponds to a pattern of the capping layer; and

forming a remaining layer of the capping layer without using a mask.

9. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the third electrode is conducted after forming at least one layer of the capping layer.

10. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the third electrode and the capping layer comprises:

forming a first layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part that corresponds to a pattern of the capping layer; and

forming the third electrode and a remaining layer of the capping layer by using an open mask in a co-deposition

22

process, the open mask including an opening over the first layer of the capping layer.

11. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the third electrode and the capping layer comprises:

forming a lowermost layer in contact with the second electrode among the plurality of the layers of the capping layer by using a mask having a slit part that corresponds to a pattern of the capping layer; and

forming a lowermost electrode layer in contact with the second electrode among the plurality of the electrode layers of the third electrode by using an open mask including an opening over the lowermost layer of the capping layer.

12. The method of manufacturing an organic light emitting display apparatus of claim 11, comprising:

forming a remaining layer excluding the lowermost layer among the plurality of the layers of the capping layer by using a mask having a slit part that corresponds to the pattern of the capping layer; and

forming a remaining electrode layer excluding the lowermost electrode layer among the plurality of the electrode layers of the third electrode by using an open mask.

13. The method of manufacturing an organic light emitting display apparatus of claim 11, comprising:

forming the remaining layer excluding the lowermost layer among the plurality of the layers of the capping layer by using the open mask; and

forming the remaining electrode layer excluding the lowermost electrode layer among the plurality of the electrode layers of the third electrode by using the open mask.

14. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the third electrode and the capping layer comprises:

alternately disposing a plurality of first deposition sources including a material for forming the capping layer and a plurality of second deposition sources including a material for forming the third electrode; and

moving the substrate including the second electrode so as to position the substrate corresponding to the plurality of the first deposition sources and the plurality of the second deposition sources one by one.

15. The method of manufacturing an organic light emitting display apparatus of claim 1, wherein the forming of the third electrode and the capping layer comprises:

forming a layer disposed on the second electrode among at least two layers of the capping layer by using a mask having a slit part that corresponds to a pattern of the capping layer; and

forming at least one electrode layer of the third electrode and at least one layer of a remaining layer of the capping layer at the same time by using an open mask in a co-deposition process, the open mask including an opening over the capping layer.

* * * * *

专利名称(译)	有机发光显示装置及其制造方法		
公开(公告)号	US9331308	公开(公告)日	2016-05-03
申请号	US14/066519	申请日	2013-10-29
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	CHOI JUN HO CHO KWAN HYUN CHUNG JIN KOO		
发明人	CHOI, JUN-HO CHO, KWAN-HYUN CHUNG, JIN-KOO		
IPC分类号	H01L51/52 H01L51/56		
CPC分类号	H01L51/5262 H01L51/5228 H01L51/5234 H01L51/5203 H01L2251/5315 H01L27/326 H01L27/3248 H01L27/3258 H01L27/3272 H01L51/0052 H01L51/0061 H01L51/0072 H01L51/0077 H01L51/5256		
优先权	1020130061251 2013-05-29 KR		
其他公开文献	US20140353611A1		
外部链接	Espacenet USPTO		

摘要(译)

提供一种有机发光显示装置及其制造方法。该装置包括基板，形成在基板上的第一电极，形成在第一电极上的中间层。中间层包括有机发光层。在中间层上形成第二电极，并且在第一区域中的第二电极上形成覆盖层。覆盖层包括第一边缘部分和至少两个层。在第二区域中的第二电极上形成第三电极。第二区域不与第一区域重叠，第三电极包括第二边缘部分，该第二边缘部分具有面向覆盖层的第一边缘部分的侧部的侧部。可以改善电特性和图像质量。

