



US010580999B2

(12) United States Patent
Ito et al.**(10) Patent No.: US 10,580,999 B2****(45) Date of Patent: Mar. 3, 2020****(54) CONDENSED CYCLIC COMPOUND AND AN ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME****(71) Applicant: SAMSUNG DISPLAY CO., LTD.,**
Yongin-si, Gyeonggi-Do (KR)**(72) Inventors: Naoyuki Ito,** Yongin-si (KR); **Seulong Kim,** Yongin-si (KR); **Yoonsun Kim,** Yongin-si (KR); **Dongwoo Shin,** Yongin-si (KR); **Jungsub Lee,** Yongin-si (KR); **Jino Lim,** Yongin-si (KR)**(73) Assignee: SAMSUNG DISPLAY CO., LTD.,**
Yongin-si, Gyeonggi-do (KR)**(*) Notice:** Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 54 days.**(21) Appl. No.: 15/399,155****(22) Filed: Jan. 5, 2017****(65) Prior Publication Data**

US 2017/0194571 A1 Jul. 6, 2017

(30) Foreign Application Priority DataJan. 5, 2016 (KR) 10-2016-0001115
Jan. 5, 2016 (KR) 10-2016-0001122
Jan. 20, 2016 (KR) 10-2016-0006995
Jan. 20, 2016 (KR) 10-2016-0006996**(51) Int. Cl.****H01L 51/54** (2006.01)
C09K 11/06 (2006.01)
H01L 51/00 (2006.01)
C07D 307/77 (2006.01)
C09K 11/02 (2006.01)
C07D 333/50 (2006.01)
C07D 307/91 (2006.01)
C07D 493/04 (2006.01)
C07D 495/04 (2006.01)
C07D 405/10 (2006.01)

(Continued)

(52) U.S. Cl.CPC **H01L 51/0073** (2013.01); **C07D 307/77** (2013.01); **C07D 307/91** (2013.01); **C07D 333/50** (2013.01); **C07D 405/10** (2013.01); **C07D 493/04** (2013.01); **C07D 495/04** (2013.01); **C09K 11/025** (2013.01); **C09K 11/06** (2013.01); **H01L 51/006** (2013.01); **H01L 51/0052** (2013.01); **H01L 51/0058** (2013.01); **H01L 51/0074** (2013.01); **H01L 51/5265** (2013.01); **C09K 2211/1007** (2013.01); **C09K 2211/1011** (2013.01); **C09K 2211/1014** (2013.01); **H01L 51/0054** (2013.01); **H01L 51/5012** (2013.01); **H01L 51/5016** (2013.01); **H01L 51/5056** (2013.01); **H01L 51/5072** (2013.01); **H01L 51/5206** (2013.01); **H01L 51/5221** (2013.01)**(58) Field of Classification Search**

CPC .. C07D 307/77; C07D 307/91; C07D 333/50; C07D 405/00; C07D 405/10; C07D 493/00; C07D 493/04; C07D 495/00; C07D 495/02; C07D 495/04; C09K 11/025; C09K 11/06; C09K 2211/00; C09K 2211/10; C09K 2211/1011; C09K 2211/1014; C09K 2211/1007; H01L 51/0032; H01L 51/005; H01L 51/0052; H01L 51/0054; H01L 51/0058; H01L 51/006; H01L 51/0072; H01L 51/0073; H01L 51/0074; H01L 51/50; H01L 51/5012; H01L 51/5016; H01L 51/5056; H01L 51/5072

USPC 428/690, 691, 917, 411.4, 336; 427/58, 427/66; 313/500-512; 257/40, 88-104, 257/E51.001-E51.052; 252/301.16-301.35

See application file for complete search history.

(56) References Cited

U.S. PATENT DOCUMENTS

7,839,074 B2 11/2010 Ikeda et al.
8,241,763 B2 8/2012 Buesing et al.
2006/0043858 A1 3/2006 Ikeda et al.
(Continued)

FOREIGN PATENT DOCUMENTS

KR 10-2008-0049770 6/2008
KR 10-2008-0109000 12/2008
(Continued)

OTHER PUBLICATIONS

Machine translation of KR2013-0075982 (Year: 2013).*

(Continued)


Primary Examiner — Andrew K Bohaty

(74) Attorney, Agent, or Firm — F. Chau & Associates, LLC

(57) ABSTRACT

A condensed cyclic compound represented by Formula 1 and an organic light-emitting device including the same.

[Formula 1]



(51) **Int. Cl.**
H01L 51/52 (2006.01)
H01L 51/50 (2006.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2008/0193797 A1 8/2008 Heil et al.
 2009/0261717 A1 10/2009 Buesing et al.
 2010/0032658 A1 2/2010 Lee et al.
 2011/0156016 A1 6/2011 Kawamura et al.
 2012/0138914 A1* 6/2012 Kawamura C07D 307/79
 257/40
 2013/0069523 A1 3/2013 Matsuura et al.
 2014/0332793 A1 11/2014 Park et al.
 2015/0372237 A1 12/2015 Kawamura et al.

FOREIGN PATENT DOCUMENTS

KR 10-2009-0065201 6/2009
 KR 10-2010-0007780 1/2010
 KR 10-2011-0043625 4/2011
 KR 10-2011-0047278 5/2011

KR 10-2012-0003692 1/2012
 KR 10-2012-0038402 4/2012
 KR 10-2013-0075982 7/2013
 KR 20130075982 A * 7/2013
 KR 10-2014-0049186 4/2014
 KR 10-2015-0128583 11/2015
 WO 2010137285 12/2010
 WO 2014061963 4/2014

OTHER PUBLICATIONS

Office Action for U.S. Appl. No. 15/399,255 dated Apr. 18, 2018 in related application.

Notice of Allowance issued in corresponding U.S. Appl. No. 15/399,255 dated Sep. 18, 2019.

Office Action issued in corresponding U.S. Appl. No. 15/399,414 dated May 2, 2019.

Office Action issued in corresponding U.S. Appl. No. 15/399,414 dated Sep. 26, 2019.

Office Action issued in corresponding U.S. Appl. No. 16/399,349 dated Sep. 25, 2019.

* cited by examiner

FIG. 1

10

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3

30

220
190
150
110

FIG. 4

40

220
190
150
110
210

1

CONDENSED CYCLIC COMPOUND AND AN ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of Korean Patent Application Nos.: 10-2016-0006996, filed on Jan. 20, 2016; 10-2016-0001122, filed on Jan. 5, 2016; 10-2016-0001115, filed on Jan. 5, 2016; 10-2016-0006995, filed on Jan. 20, 2016 in the Korean Intellectual Property Office. The above-referenced disclosures are incorporated by reference herein.

TECHNICAL FIELD

Exemplary embodiments of the present invention relate to a condensed cyclic compound, and more particularly to an organic light-emitting device including the same.

DISCUSSION OF RELATED ART


Organic light-emitting devices may be self-emission devices. Organic light-emitting devices may produce full-color images. Organic light-emitting devices may have relatively wide viewing angles, relatively high contrast ratios, and relatively short response times, and increased brightness, driving voltage, and response speed characteristics.

Organic light-emitting devices may include a first electrode disposed on a substrate. Organic light-emitting devices may include a hole transport region, an emission layer, an electron transport region, and a second electrode sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region. Electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, may recombine in the emission layer to produce excitons. The excitons may transition from an excited state to a ground state, thus generating light.

SUMMARY

One or more exemplary embodiments of the present invention may include a condensed cyclic compound and an organic light-emitting device including the same.

According to an exemplary embodiment of the present invention, a condensed cyclic compound is represented by Formula 1:




<Formula 1>

2

-continued

<Formula 1-1>



In Formulae 1 and 1-1,

A₁ is selected from groups represented by Formula 1-1, n₁ is an integer selected from 1 to 5,

X₁ is selected from oxygen (O) and sulfur (S),

ring B₁ and ring B₂ are each independently selected from a C₇-C₆₀ aromatic ring and a C₁-C₆₀ heteroaromatic ring,

L₁ and L₂ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₁ is an integer selected from 1 to 3,

a₂ is an integer selected from 0 to 3,

Ar₁ is selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

b₁ is an integer selected from 1 to 5,

* indicates a binding site to a neighboring atom,

R₁ to R₈, R₁₁, and R₁₂ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂),

c₁₁ is an integer selected from 0 to 7,

c₁₂ is an integer selected from 0 to 8,

at least one substituent selected from the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic

condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{11})(Q_{12})(O_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12}),

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22}), and

—Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}), and

Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10}

cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a terphenyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a C_6 - C_{60} aryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

According to an exemplary embodiment of the present invention, an organic light-emitting device includes a first electrode; a second electrode facing the first electrode; and an organic layer disposed between the first electrode and the second electrode. The organic layer includes an emission layer. The organic layer includes at least one of the condensed cyclic compounds represented by Formula 1.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features of the present invention will become more apparent by describing in detail exemplary embodiments thereof, with reference to the accompanying drawings, in which:

FIG. 1 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention;


FIG. 2 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention;

FIG. 3 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention; and

FIG. 4 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

A condensed cyclic compound according to an exemplary embodiment of the present invention may be represented by Formula 1:



5

In Formula 1, A_1 may be selected from groups represented by Formula 1-1.

n_1 in Formula 1 may be an integer selected from 1 to 5. n_1 may indicate the number of $A_1(s)$. When n_1 is 2 or greater, at least $A_1(s)$ may be the same as or different from each other. According to an exemplary embodiment of the present invention, n_1 may be 1 or 2. According to an exemplary embodiment of the present invention, n_1 may be 1. However, exemplary embodiments of the present invention are not limited thereto.


In Formula 1-1, ring B_1 and ring B_2 may each independently be a C_7 - C_{60} aromatic ring or a C_1 - C_{60} heteroaromatic ring.

According to an exemplary embodiment of the present invention, ring B_1 and ring B_2 in Formula 1-1 may each independently be selected from a naphthalene group, a heptalene group, a phenalene group, a phenanthrene group, an anthracene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, a quinoline group, an isoquinoline group, a quinoxaline group, a quinazoline group, a cinnoline group, a naphthyridine group, an acridine group, and a phenanthroline group.


According to an exemplary embodiment of the present invention, ring B_1 and ring B_2 may each independently be selected from a naphthalene group and a phenanthrene group.

In Formula 1-1, X_1 may be selected from oxygen (O) and sulfur (S).


In Formula 1, A_1 may be selected from groups represented by Formulae 1-1(1) to 1-1(20):



Formula 1-1(1)




Formula 1-1(2)




Formula 1-1(3)

6


-continued




Formula 1-1(4)




Formula 1-1(5)




Formula 1-1(6)




Formula 1-1(7)



Formula 1-1(8)



Formula 1-1(9)




Formula 1-1(10)


7

-continued


Formula 1-1(11)




Formula 1-1(12)




Formula 1-1(13)



Formula 1-1(14)




Formula 1-1(15)




8

-continued


Formula 1-1(16)




Formula 1-1(17)




Formula 1-1(18)



Formula 1-1(19)



Formula 1-1(20)



In Formulae 1-1(1) to 1-1(20), X_1 , R_{11} , R_{12} , c_{11} , c_{12} , and
 * may each independently be the same as defined herein,
 R_{11a} and R_{11b} may each independently be the same as
 defined herein with respect to R_{11} ,

R_{12a} and R_{12b} may each independently be the same as defined herein with respect to R_{12} ,

ca11 may be an integer selected from 0 to 3, and

ca12, cb11, and cb12 may each independently be an integer selected from 0 to 4.

In Formula 1, L_1 and L_2 may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

For example, L_1 and L_2 in Formula 1 may each independently be selected from:


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothioiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothioiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothioiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothioiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

indinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothioiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothioiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylenylene group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothioiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothioiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}).

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.










According to an exemplary embodiment of the present invention, L_1 and L_2 may each independently be selected from groups represented by Formulae 3-1 to 3-41:



Formula 3-1

11

-continued




12

-continued


Formula 3-2

5




Formula 3-3

10




Formula 3-4

15




20




Formula 3-5

25




Formula 3-6

30




35




Formula 3-7

40




Formula 3-8

45




50



55


Formula 3-9

60



Formula 3-10

65



Formula 3-11

Formula 3-12

Formula 3-13

Formula 3-14

Formula 3-15

Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19










Formula 3-20

Formula 3-21

Formula 3-22

13

-continued




14

-continued

Formula 3-23

5




Formula 3-24

10


Formula 3-25

20



Formula 3-26

25




Formula 3-27

30

Formula 3-28


35



40

Formula 3-29

45




Formula 3-30

55

Formula 3-31

60



65

Formula 3-32

Formula 3-33

Formula 3-34





Formula 3-35

Formula 3-36

Formula 3-37

15

-continued



In Formulae 3-1 to 3-41,

Y_1 may be O, S, C(Z_3)(Z_4), N(Z_5), or Si(Z_6)(Z_7),

Z_1 to Z_7 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a triazinyl group, a benzimidazolyl group, a phenanthrolinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, an alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

16

d_2 may be an integer selected from 1 and 2,

d_3 may be an integer selected from 1 to 3,

d_4 may be an integer selected from 1 to 4,

5 d_5 may be an integer selected from 1 to 5,

d_6 may be an integer selected from 1 to 6,

d_8 may be an integer selected from 1 to 8, and

10 * and *' may each independently indicate a binding site to a neighboring atom.


Formula 3-39

According to an exemplary embodiment of the present invention, L_1 and L_2 may each independently be selected from groups represented by Formulae 4-1 to 4-35:

15

Formula 4-1


20



Formula 3-40


Formula 4-2

25



Formula 4-3


30



Formula 3-41


Formula 4-4

35




Formula 4-5

40




45

Formula 4-6




Formula 4-7

50



Formula 4-8

55










60

65

17


-continued

**18**

-continued


Formula 4-9

5




Formula 4-10

10




Formula 4-11

20




Formula 4-12

25




Formula 4-13

35




Formula 4-14

40




Formula 4-15


60



55



65



Formula 4-16

Formula 4-17

Formula 4-18

Formula 4-19

Formula 4-20

Formula 4-21









Formula 4-22

Formula 4-23

Formula 4-24

19


-continued




20

-continued

Formula 4-25




Formula 4-26



Formula 4-27

Formula 4-28



Formula 4-29

Formula 4-30

Formula 4-31

Formula 4-32

Formula 4-33

Formula 4-34

Formula 4-35

In Formulae 4-1 to 4-35, * and *' may each independently indicate a binding site to a neighboring atom.

In Formula 1, a₁ may be an integer selected from 1 to 3, and a₂ may be an integer selected from 0 to 3. a₁ may indicate the number of L₁(s). When a₁ is 2 or greater, at least two L₁(s) may be the same as or different from each other. a₂ may be the same as a₁ and the structures of Formulae 1 and 2.

According to an exemplary embodiment of the present invention, in Formula 1, a₁ may be an integer selected from 1 and 2. According to an exemplary embodiment of the present invention, a₁ may be 1. According to an exemplary embodiment of the present invention, in Formula 1, a₂ may be an integer selected from 0 and 1; however, exemplary embodiments of the present invention are not limited thereto.

In Formula 1, Ar₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

For example, Ar₁ in Formula 1 may be selected from: a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an

azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and


a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a

fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃).


Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

According to an exemplary embodiment of the present invention, Ar₁ may be selected from groups represented by Formulae 5-1 to 5-79:


Formula 5-1




Formula 5-2




Formula 5-3



Formula 5-4










Formula 5-5




23

-continued


**24**

-continued


Formula 5-6




Formula 5-7




Formula 5-8




Formula 5-9




Formula 5-10



Formula 5-11



Formula 5-12



Formula 5-13

Formula 5-14

Formula 5-15

Formula 5-16










Formula 5-17

Formula 5-18

Formula 5-19

25


-continued

**26**


-continued

Formula 5-20


5




Formula 5-21 10




15




Formula 5-22 20



25




Formula 5-23 30




35


Formula 5-24 40




Formula 5-25 45



Formula 5-26 50



Formula 5-27 55



60

Formula 5-28 65

Formula 5-29

Formula 5-30

Formula 5-31

Formula 5-32

Formula 5-33

Formula 5-34

Formula 5-35










Formula 5-36

Formula 5-37

Formula 5-38

29

-continued




30

-continued


Formula 5-62

5



Formula 5-63


10



15


Formula 5-64

20




Formula 5-65

25



Formula 5-66


30



35


Formula 5-67

40



Formula 5-68


45



50

Formula 5-69

55



Formula 5-70

60

In Formulae 5-1 to 5-79,

Y_{31} and Y_{32} may each independently be O, S, C(Z_{33}) (Z_{34}), N(Z_{35}), or Si(Z_{36})(Z_{37}),

Z_{31} to Z_{37} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a

Formula 5-71

Formula 5-72

Formula 5-73

Formula 5-74

Formula 5-75

Formula 5-76

Formula 5-77

Formula 5-78

Formula 5-79

31

terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzimidazolyl group, a phenanthrolinyl group, a triazinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

e_2 may be an integer selected from 1 and 2,

e_3 may be an integer selected from 1 to 3,

e_4 may be an integer selected from 1 to 4,


e_5 may be an integer selected from 1 to 5,

e_6 may be an integer selected from 1 to 6,


e_8 may be an integer selected from 1 to 8, and

$*$ may indicate a binding site to a neighboring atom.


According to an exemplary embodiment of the present invention, Ar_1 may be selected from groups represented by Formulae 6-1 to 6-44:




Formula 6-1 25




Formula 6-2 30




Formula 6-3 35




Formula 6-4 40




Formula 6-5 45




Formula 6-6 50



Formula 6-7 55




Formula 6-8 60




32

-continued


Formula 6-9




Formula 6-10




Formula 6-11




Formula 6-12




Formula 6-13



Formula 6-14











Formula 6-15



Formula 6-16

33


-continued

**34**

-continued


Formula 6-17

5




Formula 6-18

10



Formula 6-19


15



20


Formula 6-20

25



Formula 6-21


30



35


Formula 6-22

40




Formula 6-23

45



Formula 6-24


50



55

Formula 6-25

60



65

Formula 6-26

Formula 6-27

Formula 6-28

Formula 6-29

Formula 6-30

Formula 6-31

Formula 6-32









Formula 6-33

Formula 6-34

Formula 6-35

35

-continued




36

-continued

Formula 6-44

Formula 6-36



Formula 6-37

In Formulae 6-1 to 6-44, * may indicate a binding site to a neighboring atom.

In Formula 1, b1 may be an integer selected from 1 to 5. b1 may indicate the number of Ar₁(s). When b1 is 2 or greater, at least two Ar₁(s) may be the same as or different from each other. According to an exemplary embodiment of the present invention, b1 may be 1 or 2. According to an exemplary embodiment of the present invention, b1 may be 1. However, exemplary embodiments of the present invention are not limited thereto.

Formula 6-38

Formula 6-39

Formula 6-40

Formula 6-41

Formula 6-42

Formula 6-43

In Formulae 1 and 2, R₁ to R₈, R₁₁, and R₁₂ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂).

According to an exemplary embodiment of the present invention, R₁ to R₈, R₁₁, and R₁₂ in Formulae 1 and 2 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₁-C₂₀ alkoxy group, a substituted or unsubstituted C₆-C₂₀ aryl group, a substituted or unsubstituted C₁-C₂₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁)(Q₂)(Q₃).

According to an exemplary embodiment of the present invention, R₁ to R₈, R₁₁, and R₁₂ in Formulae 1 and 2 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F,

—Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, and a hydrazono group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinoli-

nyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃), and

—Si(Q₁)(Q₂)(Q₃).

Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

According to an exemplary embodiment of the present invention, R₁ to R₈, R₁₁, and R₁₂ in Formula 1 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, and a C₁-C₁₀ alkoxy group;

a C₁-C₁₀ alkyl group and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, and a hydrazono group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group; and


a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group.

In Formula 1-1, c11 may be an integer selected from 0 to 7, and c12 may be an integer selected from 0 to 8. c11 may indicate the number of R₁₁(s). When c11 is 2 or greater, at least two R₁₁(s) may be the same as or different from each other. C12 may be the same as c11 and the structures of Formula 1.


According to an exemplary embodiment of the present invention, c11 and c12 in Formula 1-1 may each independently be an integer selected from 1 and 2. According to an exemplary embodiment of the present invention, c11 and c12 in Formula 1-1 may each independently be 1. However, exemplary embodiments of the present invention are not limited thereto.

According to an exemplary embodiment of the present invention, the condensed cyclic compound represented by Formula 1 may be represented by at least one of Formulae 1A to 1T:

<Formula 1A>




<Formula 1B>




-continued


<Formula 1C>




<Formula 1D>



<Formula 1E>



<Formula 1F>




41


42

-continued


<Formula 1G>




<Formula 1H>



<Formula 1I>



<Formula 1J>




43


44

-continued


<Formula 1K>




<Formula 1L>




<Formula 1M>



<Formula 1N>




<Formula 1O>




-continued


<Formula 1P>




<Formula 1Q>



<Formula 1R>



<Formula 1S>




47

48

-continued

<Formula 1T>



In Formulae 1A to 1T, X_1 , L_1 , L_2 , a_1 , a_2 , Ar_1 , b_1 , R_1 to R_8 , R_{11} , R_{12} , c_{11} , and c_{12} may each independently be the same as defined herein,

R_{11a} and R_{11b} may each independently be the same as described herein with respect to R_{11} ,

R_{12a} and R_{12b} may each independently be the same as described herein with respect to R_{12} ,


ca_{11} may be an integer selected from 0 to 3, and

ca_{12} , cb_{11} , and cb_{12} may each independently be an integer selected from 0 to 4.

According to an exemplary embodiment of the present invention, the condensed cyclic compound represented by Formula 1 may be represented by at least one of Formulae 1A(1) to 1T(1):



-continued

<Formula 1C(1)>





<Formula 1A(1)>

<Formula 1D(1)>



<Formula 1B(1)>


<Formula 1E(1)>



49

-continued

<Formula 1F(1)>




5

10

<Formula 1G(1)>

15




20

25

<Formula 1H(1)>

30




35

40

<Formula 1I(1)>


45



50

<Formula 1J(1)>

55




60

65


50

-continued


<Formula 1K(1)>




<Formula 1L(1)>




<Formula 1M(1)>



<Formula 1N(1)>




<Formula 1O(1)>



51

-continued

<Formula 1P(1)>



5


10

15

52

-continued

<Formula 1S(1)>




20

25

30


<Formula 1Q(1)>



35

40

<Formula 1R(1)>



In Formulae 1A(1) to 1T(1), X_1 , L_1 , and Ar_1 may each independently be the same as described herein.



For example, in Formulae 1A(1) to 1T(1),

X_1 may be selected from oxygen (O) and sulfur (S),


L_1 and L_2 may each independently be selected from groups represented by Formulae 4-1 to 4-35, and

Ar_1 may be selected from groups represented by Formulae 6-1 to 6-44.

The condensed cyclic compound represented by Formula 1 may be at least one selected from the compounds below:









-continued



55

-continued






56



57

-continued






58



59

-continued





60



61

-continued







62



63

-continued


64



65

-continued







66



67

-continued






68



69

70






-continued



71

-continued






72



73

-continued







74









75







-continued

76










-continued



81

-continued






82



83

-continued






84










85

-continued







86









-continued









-continued








-continued









-continued









-continued



-continued









-continued









101

-continued

102









-continued



105

-continued







106



107

-continued


108



109

-continued







110



111

-continued







112



113

-continued


114



115

116






-continued



117

-continued






118



119

120


-continued



121

-continued






122



123

-continued






124



125

-continued






126



127

128





-continued



129

130






-continued



131

-continued






132



133

-continued






134



135

136






-continued



137

-continued







138



139

-continued






140



141

142






-continued



143

-continued







144



145






-continued

146



147





148



149

150






-continued



151

152






-continued



153

-continued






154



155

-continued






156



157

-continued






158



159

160






-continued



161

162







-continued



163

164







-continued



165

-continued







166



167

-continued






168



169

-continued






170



171






-continued

172



173

-continued









174






175

-continued

176









-continued



179

-continued






180



181

-continued






182



183

-continued






184



185

-continued


186



187

-continued







188









189

-continued

190






193

194







-continued









195

-continued







196



-continued









-continued



201

-continued


202



203

-continued







204



205

-continued







206



207

-continued







208



209

-continued






210








211

-continued

212










215

-continued

216










219

-continued






220



221

-continued






222



223

224






-continued



225

-continued






226



227






-continued

228



229





230



231






-continued

232



233






234



235

-continued






236



237

238


-continued



239

240

-continued




In Formula 1, ring B₁ and ring B₂ may each independently be selected from a C₇-C₆₀ aromatic ring and a C₁-C₆₀ heteroaromatic ring. Accordingly, the size of the entire molecular structure of the condensed cyclic compound represented by Formula 1 may increase to thereby easily disperse electrons of heteroatoms, for example, oxygen (O) or sulfur (S), and stabilize the entire molecular structure of the condensed cyclic compound represented by Formula 1. Therefore, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have a relatively high efficiency and a relatively long lifespan.

In Formula 1, L₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group. a₁ may indicate the number of L₁(s) might not be 0. Thus, a group represented by $*(L_1)_{a1}-(A_1)_{n1}$ in Formula 1 may include L₁. Accordingly, electrons on the core of the anthracene group may be localized and may stabilize the entire molecular structure of the condensed cyclic compound represented by Formula 1. The entire molecular structure of the condensed cyclic compound represented by Formula 1 is a three-dimensional structure, which may be easily subjected to non-crystallization, thereby increasing film characteristics upon deposition. Therefore, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have a relatively high efficiency and a relatively long lifespan.

As illustrated in Formula 1A', the condensed cyclic compound represented by Formula 1 may be combined with a group represented by Formula 1-1 on a particular position. Accordingly, the condensed cyclic compound represented by Formula 1 may be configured to serve as a host in an emission layer. Therefore, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have a relatively high efficiency and a relatively long lifespan.

<Formula 1A'>



The condensed cyclic compound represented by Formula 1 may be synthesized by known suitable organic synthesis methods. A synthesis method of the condensed cyclic compound represented by Formula 1 may be recognizable by one of ordinary skill in the art in view of the following Examples.

According to an exemplary embodiment of the present invention, an organic light-emitting device may include a first electrode, a second electrode facing the first electrode, and an organic layer disposed between the first electrode and the second electrode. The organic layer may include an emission layer. The organic layer may include at least one condensed cyclic compound represented by Formula 1 as described herein.

The expression that “(an organic layer) includes at least one condensed cyclic compound” as used herein may refer to a case in which “(an organic layer) includes identical condensed cyclic compound represented by Formula 1” and a case in which “(an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1”.

For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may be in an emission layer of the organic light-emitting device. According to an exemplary embodiment of the present invention, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. According to an exemplary embodiment of the present invention, Compound 1 and Compound 2 may both be in an identical layer. For example, Compound 1 and Compound 2 may both be in an emission layer. Alternatively, Compound 1 and Compound 2 may be in different layers. For example, Compound 1 may be in a hole transport layer and Compound 2 may be in an emission layer.

According to an exemplary embodiment of the present invention, the first electrode of the organic light-emitting device may be an anode. The second electrode of the organic light-emitting device may be a cathode.

According to an exemplary embodiment of the present invention, the organic layer may include a hole transport region and an electron transport region. The hole transport region may be disposed between the first electrode and the emission layer. The hole transport region may include at least one of a hole injection layer, a hole transport layer, a buffer layer, or an electron blocking layer. The electron transport region may be disposed between the emission layer and the second electrode. The electron transport region may include at least one of a hole blocking layer, an electron transport layer, or an electron injection layer. At least one of the hole transport region or the emission layer may include at least one of the condensed cyclic compound represented by Formula 1. For example, the emission layer of the organic light-emitting device may include at least one of the condensed cyclic compounds represented by Formula 1. The condensed cyclic compound represented by Formula 1 included in the emission layer may be configured to serve as a host. The emission layer may include a dopant. The dopant may be a phosphorescent dopant or a fluorescent dopant. For example, the dopant may be a fluorescent dopant.

The term "organic layer" used herein may refer to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the "organic layer" is not limited to an organic material.

FIG. 1 is a schematic cross-sectional schematic diagram of an organic light-emitting device according to an exemplary embodiment of the present invention. An organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

A structure of an organic light-emitting device according to an exemplary embodiment of the present invention and a method of manufacturing an organic light-emitting device according to an exemplary embodiment of the present invention will be described in more detail below with reference to FIG. 1.

Referring to FIG. 1, a substrate may be disposed below the first electrode 110. Alternatively, the substrate may be disposed above the second electrode 190. The substrate may include a glass substrate or a plastic substrate. The glass substrate and the plastic substrate may each have a relatively high mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water-resistance.

The first electrode 110 may be formed by, for example, depositing or sputtering a material included in the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material included in the first electrode 110 may include materials with a relatively high work function, which may facilitate hole injection.

The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material included in the first electrode 110 may include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), or any combination thereof; however, exemplary embodiments of the present invention are not limited thereto. When the first electrode 110 is a semi-transmissive electrode or a reflective electrode, a material included in the first electrode 110 may include magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or any combination thereof; however, exemplary embodiments of the present invention are not limited thereto.

The first electrode 110 may have a single-layered structure. Alternatively, the first electrode 110 may have a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO; however, the structure of the first electrode 110 is not limited thereto.

The organic layer 150 may be disposed on the first electrode 110. The organic layer 150 may include an emission layer.


The organic layer 150 may include a hole transport region and an electron transport region. The hole transport region may be disposed between the first electrode 110 and the emission layer. The electron transport region may be disposed between the emission layer and the second electrode 190.

The hole transport region may have a single-layered structure including a single material. The hole transport region may have a single-layered structure including a plurality of different materials. The hole transport region may have a multi-layered structure having a plurality of layers including a plurality of different materials.

The hole transport region may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).

For example, the hole transport region may have a single-layered structure. The single layered structure may include a single layer including a plurality of different materials. Alternatively, the hole transport region may have a multi-layered structure. The multi-layered structure may include a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure. For each structure, the layers may be sequentially stacked on the first electrode 110; however, the structure of the hole transport region is not limited thereto.


The hole transport region may further include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTDP, triphenylamine(4,4',4''-tris(N-carbazolyl)triphenylamine) (TCTA), polyaniline/dodecyl benzene sulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), polyaniline/poly(4-styrenesulfonate) (Pani/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




m-MTDATA

243


-continued




TDATA




2-TNATA




NPB

 β -NPB**244**


-continued




TPD




Spiro-TPD



Spiro-NPB




methylated NPB




TAPC

245


-continued



HMTPD



<Formula 201>



<Formula 202>

In Formulae 201 and 202:

L₂₀₁ to L₂₀₄ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

L₂₀₅ may be selected from *-O-*, *-S-*, *-N (Q₂₀₁)-*, a substituted or unsubstituted C₁-C₂₀ alkylene group, a substituted or unsubstituted C₂-C₂₀ alkenylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

xa1 to xa4 may each independently be an integer selected from 0 to 3.

xa5 may be an integer selected from 1 to 10.

R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group,

246

a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

For example, in Formula 202, R₂₀₁ and R₂₀₂ may be connected to each other via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R₂₀₃ and R₂₀₄ may be connected to each other via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group. However, exemplary embodiments of the present invention are not limited thereto.

According to an exemplary embodiment of the present invention, in Formulae 201 and 202,

L₂₀₁ to L₂₀₅ may each independently be selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a phenanthracenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a heptacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a benzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a benzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl

group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$.

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

According to an exemplary embodiment of the present invention, in Formulae 201 and 202, xa1 to xa4 may each independently be an integer selected from 0, 1, and 2.

According to an exemplary embodiment of the present invention, in Formula 202, xa5 may be an integer selected from 1, 2, 3, and 4.

According to an exemplary embodiment of the present invention, in Formulae 201 and 202, R_{201} to R_{204} and Q_{201} may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, and a pyridinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an

amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-\text{F}$, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})$, and $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$.

Q_{31} to Q_{33} may be the same as described above.

According to an exemplary embodiment of the present invention, in Formula 201, at least one of R_{201} to R_{203} may each independently be selected from:

a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, or a dibenzothiophenyl group; and

a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-\text{F}$, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; however, exemplary embodiments of the present invention are not limited thereto.

According to an exemplary embodiment of the present invention, in Formula 202, R_{201} and R_{202} may be linked via a single bond, and/or R_{203} and R_{204} may be linked via a single bond.

According to an exemplary embodiment of the present invention, in Formula 202, at least one of R_{201} to R_{204} may be selected from:


a carbazoyl group; and

a carbazoyl group substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-\text{F}$, a naphthyl group, a


249

fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; however, exemplary embodiments of the present invention are not limited thereto.


The compound represented by Formula 201 may be represented by Formula 201A:



The compound represented by Formula 201 may be represented by Formula 201A(1); however, exemplary embodiments of the present invention are not limited thereto:




The compound represented by Formula 201 may be represented by Formula 201A-1; however, exemplary embodiments of the present invention are not limited thereto:



According to an exemplary embodiment of the present invention, the compound represented by Formula 202 may be represented by Formula 202A:


250

<Formula 202A>



According to an exemplary embodiment of the present invention, the compound represented by Formula 202 may be represented by Formula 202A-1:

<Formula 202A-1>



In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, L_{201} to L_{203} , $xa1$ to $xa3$, $xa5$, and R_{202} to R_{204} may each independently be the same as described above.

In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, R_{211} and R_{212} may be the same as R_{203} .

In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, R_{213} to R_{217} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C_1 - C_{10} alkyl group, a phenyl group substituted with $-F$, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.



The hole transport region may include at least one compound selected from Compounds HT1 to HT39; however, exemplary embodiments of the present invention are not limited thereto:

251

252



HT1

HT2




HT3

HT4




253

-continued
HT5



254

HT6




HT7

HT8




255


-continued
HT9

256


HT10




HT11



HT12




257


-continued
HT13

258


HT14




HT15




HT16



HT17



HT18





259

260



-continued
HT19

HT20




HT21

HT22




HT23




261

-continued
HT24




262


HT25




HT26




HT27



HT28




HT29



263


-continued

HT30




264


HT31




HT32




HT33



HT34



HT35




265


266

-continued
HT36



HT37



HT38



HT39



A thickness of the hole transport region may be in a range of from about 100 Å to about 10,000 Å, for example, from about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of from about 100 Å to about 9,000 Å, for example, from about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of from about 50 Å to about 2,000 Å, for example, from about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within any of these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The emission auxiliary layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer. Thus, the light-emission efficiency of a formed organic light-emitting device may be increased. The electron blocking layer may decrease or prevent injection of electrons from the electron transport region. The emission auxiliary layer and the electron blocking layer may include materials as described herein.

The hole transport region may include a charge-generation material, which may increase conductive properties of

the hole transport region. The charge-generation material may be substantially homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant.

According to an exemplary embodiment of the present invention, a lowest unoccupied molecular orbital (LUMO) of the p-dopant may be -3.5 eV or less.

The p-dopant may be one of a quinone derivative, a metal oxide, or a compound containing a cyano group; however, exemplary embodiments of the present invention are not limited thereto.

For example, p-dopant may include at least one selected from:


a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) and 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ);

a metal oxide, such as a tungsten oxide or a molybdenum oxide;


a compound containing a cyano group, such as 1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); or

a compound represented by Formula 221; however, exemplary embodiments of the present invention are not limited thereto:


267



<HAT-CN>



<F4-TCNQ>



<Formula 221>

In Formula 221:

R₂₂₁ to R₂₂₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, wherein at least one selected from R₂₂₁ to R₂₂₃ may include a substituent selected from a cyano group, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group substituted with —F, a C₁-C₂₀ alkyl group substituted with —Cl, a C₁-C₂₀ alkyl group substituted with —Br, and a C₁-C₂₀ alkyl group substituted with —I.

When the organic light-emitting device **10** is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and/or a blue emission layer, according to a sub-pixel. According to an exemplary embodiment of the present invention, the emission layer may have a stacked structure. The stacked structure may include two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer. The two or more layers may be in direct contact with each other. Alternatively, the two or more layers may be separated from each other. According to an exemplary embodiment of the present invention, the emission layer may include two or more materials. The two or more materials may include a red-light emission material, a green-light emission material, or a blue-light emission material. The two or more materials may be mixed with each other in a single layer. The two or more materials mixed with each other in the single layer may emit white light.

268


The emission layer may include a host and a dopant. The dopant may include at least one of a phosphorescent dopant or a fluorescent dopant.

An amount of the above dopant in the emission layer may be in a range of from about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host; however, exemplary embodiments of the present invention are not limited thereto.


A thickness of the emission layer may be in a range of from about 100 Å to about 1,000 Å, for example, from about 200 Å to about 600 Å. When the thickness of the emission layer is within any of these ranges, increased light-emission characteristics may be obtained without a substantial increase in driving voltage.

The host may include the condensed cyclic compound represented by Formula 1.

The phosphorescent dopant may include an organometallic complex represented by Formula 401:



<Formula 401>



<Formula 402>

In Formulae 401 and 402, M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm).

L₄₀₁ may be selected from an organic ligand represented by Formula 402, and xc1 may be an integer selected from 1, 2, and 3. When xc1 is 2 or greater, at least two L₄₀₁(s) may be the same as or different from each other.

In Formulae 401 and 402, L₄₀₂ may be an organic ligand, and xc2 may be an integer selected from 0 to 4. When xc2 is 2 or greater, at least two or L₄₀₂(s) may be the same as or different from each other.

In Formulae 401 and 402, X₄₀₁ to X₄₀₄ may each independently be selected from nitrogen (N) and carbon (C).

In Formulae 401 and 402, X₄₀₁ and X₄₀₃ may be linked via a single bond or a double bond, and X₄₀₂ and X₄₀₄ may be linked via a single bond or a double bond.

In Formulae 401 and 402, A₄₀₁ and A₄₀₂ may each independently be selected from a C₅-C₆₀ carbocyclic group and a C₁-C₆₀ heterocyclic group.

In Formulae 401 and 402, X₄₀₅ may be a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q₄₁₁)—*, *—C(Q₄₁₁)(Q₄₁₂)—*, *—C(Q₄₁₁)=C(Q₄₁₂)—*, *—C(Q₄₁₁)=*, or *—C(Q₄₁₁)=*. Q₄₁₁ and Q₄₁₂ may each independently be selected from hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In Formulae 401 and 402, X₄₀₆ may be selected from a single bond, oxygen (O), and sulfur (S).

In Formulae 401 and 402, R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group —Si(Q_{401})(Q_{402})(Q_{403}), —N(Q_{401})(Q_{402}), —B(Q_{401})(Q_{402}), —C(=O)(Q_{401}), —S(=O)₂(Q_{401}), and —P(=O)(Q_{401})(Q_{402}).

Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, or a C_1 - C_{20} heteroaryl group.

In Formulae 401 and 402, xc11 and xc12 may each independently be an integer selected from 0 to 10.

in Formula 402, * and *' may each indicate a binding site to M of Formula 401.

According to an exemplary embodiment of the present invention, in Formula 402, A_{401} and A_{402} may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinoxaline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

According to an exemplary embodiment of the present invention, in Formula 402, X_{401} may be N and X_{402} may be carbon (C). Alternatively, X_{401} and X_{402} may each be nitrogen (N).

According to an exemplary embodiment of the present invention, in Formula 402, R_{401} and R_{402} may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group; and —Si(Q_{401})(Q_{402})(Q_{403}), —N(Q_{401})(Q_{402}), —B(Q_{401})(Q_{402}), —C(=O)(Q_{401}), —S(=O)₂(Q_{401}), and —P(=O)(Q_{401})(Q_{402}).

Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group; however, exemplary embodiments of the present invention are not limited thereto.






According to an exemplary embodiment of the present invention, in Formula 401, when xc1 is 2 or greater, two $A_{401}(s)$ in at least two $L_{401}(s)$ may be linked to each other via X_{407} , which is a linking group. Alternatively, two $A_{402}(s)$ in at least two $L_{401}(s)$ may be linked to each other via X_{408} , which is a linking group (see, e.g., Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be selected from a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q_{413})—*, *—C(Q_{413})(Q_{414})—*, and *—C(Q_{413})=C(Q_{414})—*, in which Q_{413} and Q_{414} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group; however, exemplary embodiments of the present invention are not limited thereto.

In Formula 401, L_{402} may be selected from a monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from a halogen ligand, a diketone ligand (e.g., acetylacetonate), a carboxylic acid ligand (e.g., picolinate), —C(=O), an isonitrile ligand, —CN, and a phosphorus ligand (e.g., phosphine and phosphite); however, exemplary embodiments of the present invention are not limited thereto.







According to an exemplary embodiment of the present invention, the phosphorescent dopant may be, for example,

271

selected from Compounds PD1 to PD25; however, exemplary embodiments of the present invention are not limited thereto:

**272**

-continued



PD6

PD7

PD8






PD9

PD10

PD11

273

-continued

**274**

-continued

PD12

5

10

15

PD13

20

25

PD14

30

35

PD15

40

45






50

PD16

55

60

65



PD17

PD18





PD19

PD20

PD21

275

-continued




According to an exemplary embodiment of the present invention, the fluorescent dopant may include an arylamine compound or a stylamine compound.

The fluorescent dopant may include a compound represented by Formula 501:

276

PD22

<Formula 501>



In Formula 501, Ar_{501} may be selected from a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group and a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group.

In Formula 501, L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

In Formula 501, $xd1$ to $xd3$ may each independently be an integer selected from 0 to 3.

In Formula 501, R_{501} and R_{502} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

In Formula 501, $xd4$ may be an integer selected from 1 to 6.

According to an exemplary embodiment of the present invention, in Formula 501, Ar_{501} may be selected from:

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

According to an exemplary embodiment of the present invention, in Formula 501, L_{501} to L_{503} may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene

277

group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

According to an exemplary embodiment of the present invention, in Formula 501, R₅₀₁ and R₅₀₂ may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least

278


one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a pyridinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃)

Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


According to an exemplary embodiment of the present invention, in Formula 501, xd4 may be 2; however, exemplary embodiments of the present invention are not limited thereto.

As an example, the fluorescent dopant may be selected from Compounds FD1 to FD22:

FD1






FD2



279

-continued



280

-continued

FD3


FD6

5

10

15

20



FD4

FD7


25

30

35

40

45



FD5


FD8

50

55

60


65



281

-continued

FD9



5

10

15

20

FD10

25

30

35

FD11

40

45


50

FD12

55

60


65




282

-continued


FD13




FD14



FD15






FD16



283

-continued

**284**

-continued

FD17

FD20

5

10

FD18

15

FD19

30

FD21

20




25

FD22


35

40

45



According to an exemplary embodiment of the present invention, the fluorescent dopant may be selected from the compounds illustrated below; however, exemplary embodiments of the present invention are not limited thereto:




DPVBi


285

286


-continued




DPAVBi




TBPe




DCJTb



DCM



Coumarin 6



C545T

The electron transport region may have a single-layered structure including a single material. The electron transport region may have a single-layered structure including a plurality of different materials. The electron transport region may have a multi-layered structure having a plurality of layers each including a plurality of different materials.

The electron transport region may include at least one layer selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer; however, exemplary embodiments of the present invention are not limited thereto.

For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron trans-

port layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure. For each structure, the layers may be sequentially stacked on an emission layer; however, exemplary embodiments of the structure of the electron transport region are not limited thereto.

The electron transport region, for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region, may include a metal-free compound including at least one π electron-depleted nitrogen-containing ring.

The π electron-depleted nitrogen-containing ring may indicate a C_1 - C_{60} heterocyclic group including at least one $*-N=*$ moiety as a ring-forming moiety.

For example, the π electron-depleted nitrogen-containing ring may be a 5-membered to 7 membered heteromonocyclic group having at least one $*-N=*$ moiety. The π electron-depleted nitrogen-containing ring may be a heteropolycyclic group in which two or more 5-membered to 7 membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed with each other. The π electron-depleted nitrogen-containing ring may be a heteropolycyclic group in which at least one 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety is condensed with at least one C_5 - C_{60} carbocyclic group.

Examples of the π electron-depleted nitrogen-containing ring may include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, phenanthroline, phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazol, an imidazopyridine, an imidazopyrimidine, or an azacarbazole; however, exemplary embodiments of the present invention are not limited thereto.

For example, the electron transport region may include a compound represented by Formula 601:



In Formula 601, Ar_{601} may be selected from a substituted or unsubstituted C_5 - C_{60} carbocyclic group and a substituted or unsubstituted C_1 - C_{60} heterocyclic group.

In Formula 601, $xe11$ may be an integer selected from 1, 2, and 3.

In Formula 601, L_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

In Formula 601, $xe1$ may be an integer selected from 0 to 5.

In Formula 601, R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(Q_{601})(Q_{602})(Q_{603})$, $-\text{C}(=\text{O})(Q_{601})$, $-\text{S}(=\text{O})_2(Q_{601})$, and $-\text{P}(=\text{O})(Q_{601})(Q_{602})$.

Q_{601} to Q_{603} may each independently be a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In Formula 601, $xe21$ may be an integer selected from 1 to 5.

According to an exemplary embodiment of the present invention, at least one selected from $xe11$, $Ar_{601}(s)$ and/or at least one selected from $xe21$, $R_{601}(s)$ may include the π electron-depleted nitrogen-containing ring.

According to an exemplary embodiment of the present invention, in Formula 601, ring Ar_{601} may be selected from:

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group; and

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an isobenzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, $-\text{Si}(Q_{31})(Q_{32})(Q_{33})$, $-\text{S}(=\text{O})_2(Q_{31})$, and $-\text{P}(=\text{O})(Q_{31})(Q_{32})$.


Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In Formula 601, when $xe11$ is 2 or greater, at least $Ar_{601}(s)$ may be linked via a single bond.

According to an exemplary embodiment of the present invention, in Formula 601, Ar_{601} may be an anthracene group.

According to an exemplary embodiment of the present invention, the compound represented by Formula 601 may be represented by Formula 601-1:

<Formula 601-1>



In Formula 601-1, X_{614} may be nitrogen (N) or $C(R_{614})$, X_{615} may be nitrogen (N) or $C(R_{615})$, X_{616} may be nitrogen (N) or $C(R_{616})$, and at least one of X_{614} to X_{616} may be nitrogen (N).

In Formula 601-1, L_{611} to L_{613} may each independently be the same as L_{601} .

In Formula 601-1, $xe611$ to $xe613$ may each independently be the same as $xe1$.

In Formula 601-1, R_{611} to R_{613} may each independently be the same as R_{601} .

In Formula 601-1, L_{614} to R_{616} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

According to an exemplary embodiment of the present invention, in Formulae 601 and 601-1, L_{601} and L_{611} to L_{613} may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazininylenylene group, an isoquinolininylenylene group, a benzoquinolininylenylene group, a phthalazininylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolininylenylene group, a cinnolininylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofura-

nylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazininylenylene group, a quinolininylenylene group, an isoquinolininylenylene group, a benzoquinolininylenylene group, a phthalazininylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolininylenylene group, a cinnolininylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, each substituted with at least one selected from deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, a thiophenyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazoyl group; however, exemplary embodiments of the present invention are not limited thereto.

According to an exemplary embodiment of the present invention, in Formulae 601 and 601-1, $xe1$ and $xe611$ to $xe613$ may each independently be an integer selected from 0, 1, and 2.

According to an exemplary embodiment of the present invention, in Formulae 601 and 601-1, R_{601} and R_{611} to R_{613} may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a

291

pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


—S(=O)₂(Q₆₀₁) and —P(=O)(Q₆₀₁)(Q₆₀₂).

Q₆₀₁ and Q₆₀₂ may be the same as described above.


The electron transport region may include at least one compound selected from Compounds ET1 to ET36; however, exemplary embodiments of the present invention are not limited thereto:

292


ET1



ET2




ET3



293

-continued

ET4



5

10


15

20

294

-continued

ET7




25

30


35

40


ET8




ET5



ET9



ET6




55

60

65

295

-continued



ET10

5

10

15

20

25



ET11

30

35

40

45



ET12

50


55

60


65

296


-continued



ET13






ET14



ET15

297

-continued



298

-continued


ET16

5

10

15

20



ET19


ET17

25

30

35

40



ET20


ET18 45

50

55

60

65




ET21

299

-continued

ET22



5


10

15

20

25

ET23




30

35

40

45

ET24



55

60

65

300

-continued

ET25

5

10

15

20

25

ET26

30

35

40

45




50

ET27


55

60

65



301
-continued



ET28


5

10

15

20

ET29



25


30

35

40

45

ET30




50

55

60

65


302
-continued



ET31




ET32

ET33



303


-continued





According to an exemplary embodiment of the present invention, the electron transport region may include at least one compound selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ.

304


ET34



ET35



ET36



A thicknesses of the buffer layer, the hole blocking layer, and the electron control layer may each independently be in a range of from about 20 Å to about 1,000 Å, for example, from about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within any of these ranges, the electron blocking layer may have relatively high electron blocking characteristics and/or electron control characteristics, without a substantial increase in driving voltage.

A thickness of the electron transport layer may be in a range of from about 100 Å to about 1,000 Å, for example,


305

from about 150 Å to about 500 Å. When the thickness of the electron transport layer is within any of these ranges, satisfactory electron transport characteristics may be obtained without a substantial increase in driving voltage.


The electron transport region, for example, an electron transport layer in the electron transport region, may include a material including metal.

The material including metal may include at least one selected from an alkali metal complex and an alkaline earth metal complex. The alkali metal complex may include a metal ion selected from a lithium (Li) ion, a sodium (Na) ion, a potassium (K) ion, a rubidium (Rb), or a cesium (Cs) ion. The alkaline earth metal complex may include a metal ion selected from a beryllium (Be) ion, a magnesium (Mg) ion, a calcium (Ca) ion, a strontium (Sr) ion, and a barium (Ba) ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth metal complex may be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyl oxazole, a hydroxyphenyl thiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenylthiadiazol, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene; however, exemplary embodiments of the present invention are not limited thereto.

For example, the material including metal may include a lithium (Li) complex. The lithium (Li) complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) and/or ET-D2:



ET-D1



ET-D2

The electron transport region may include an electron injection layer. The electron injection layer may be configured to facilitate injection of electrons from the second electrode 190. The electron injection layer may be in direct contact with the second electrode 190.

The electron injection layer may have a single-layered structure including a single material. The electron injection layer may have a single-layered structure including a plurality of different materials. The electron injection layer may have a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth metal compound, a rare earth

306

metal compound, an alkali metal complex, an alkaline earth metal complex, a rare earth metal complex, or any combination thereof.

The alkali metal may be selected from Li, Na, K, Rb, and Cs. According to an exemplary embodiment of the present invention, the alkali metal may be Li, Na, or Cs. According to an exemplary embodiment of the present invention, the alkali metal may be Li or Cs; however, exemplary embodiments of the present invention are not limited thereto.

The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

The rare earth metal may be selected from scandium (Sc), yttrium (Y), cerium (Ce), ytterbium (Yb), gadolinium (Gd), and terbium (Tb).

The alkali metal compound, the alkaline earth metal compound, and the rare earth metal compound may be respectively selected from oxides and halides (e.g., fluorides, chlorides, bromides, and/or iodides) of the alkali metal, the alkaline earth metal, or the rare earth metal.

The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , and K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, and KI. According to an exemplary embodiment of the present invention, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI; however, exemplary embodiments of the present invention are not limited thereto.

The alkaline earth metal compound may be selected from alkaline earth metal compounds, such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), and $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$). According to an exemplary embodiment of the present invention, the alkaline earth metal compound may be selected from BaO, SrO, and CaO; however, exemplary embodiments of the present invention are not limited thereto.

The rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . According to an exemplary embodiment of the present invention, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 ; however, exemplary embodiments of the present invention are not limited thereto.

The alkali metal complex, the alkaline earth metal complex, and the rare earth metal complex may each include an alkali metal ion, an alkaline earth metal ion, or a rare earth metal ion as described above. A ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth metal complex, or the rare earth metal complex may be selected from a hydroxyquinoline, a hydroxyisoquinoline, a hydroxybenzoquinoline, a hydroxyacridine, a hydroxyphenanthridine, a hydroxyphenyl oxazole, a hydroxyphenyl thiazole, a hydroxydiphenyl oxadiazole, a hydroxydiphenylthiadiazol, a hydroxyphenyl pyridine, a hydroxyphenyl benzimidazole, a hydroxyphenyl benzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene; however, exemplary embodiments of the present invention are not limited thereto.

The electron injection layer may include the alkali metal, the alkaline earth metal, the rare earth metal, the alkali metal compound, the alkaline earth metal compound, the rare earth metal compound, the alkali metal complex, the alkaline earth metal complex, the rare earth metal complex, or any combination thereof. According to an exemplary embodiment of the present invention, the electron injection layer may include an organic material. When the electron injection layer includes the organic material, the alkali metal, the alkaline earth metal, the rare earth metal, the alkali metal compound, the alkaline earth metal compound, the rare earth

307

metal compound, the alkali metal complex, the alkaline earth metal complex, the rare earth metal complex, or any combination thereof may be substantially homogeneously or non-homogeneously dispersed in a matrix including the organic material.

A thickness of the electron injection layer may be in a range of from about 1 Å to about 100 Å, for example, from about 3 Å to about 90 Å. When the thickness of the electron injection layer is any of these ranges, satisfactory electron injection characteristics may be obtained without a substantial increase in driving voltage.

The second electrode **190** may be disposed on the organic layer **150**. The organic layer **150** may have a structure as described above. The second electrode **190** may be a cathode. The cathode may be an electron injection electrode. Thus, the second electrode **190** may include a metal, an alloy, an electrically conductive compound, or any combination thereof, which may have a relatively low work function.

The second electrode **190** may include at least one of magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), indium tin oxide (ITO), or indium zinc oxide (IZO); however, exemplary embodiments of the present invention are not limited thereto. The second electrode **190** may be a semi-transmissive electrode or a transmissive electrode.

The second electrode **190** may have a single-layered structure. Alternatively, the second electrode **190** may have a multi-layered structure including two or more layers.

FIG. 2 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. Referring to FIG. 2, an organic light-emitting device **20** may include a first capping layer **210**, the first electrode **110**, the organic layer **150**, and the second electrode **190**. The first capping layer **210**, the first electrode **110**, the organic layer **150**, and the second electrode **190** may be sequentially stacked.

FIG. 3 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. Referring to FIG. 3, an organic light-emitting device **30** may include the first electrode **110**, the organic layer **150**, the second electrode **190**, and a second capping layer **220**. The first electrode **110**, the organic layer **150**, the second electrode **190**, and the second capping layer **220** may be sequentially stacked.

FIG. 4 is a schematic cross-sectional diagram illustrating an organic light-emitting device according to an exemplary embodiment of the present invention. Referring to FIG. 4, an organic light-emitting device **40** may include the first capping layer **210**, the first electrode **110**, the organic layer **150**, the second electrode **190**, and the second capping layer **220**. The first capping layer **210**, the first electrode **110**, the organic layer **150**, the second electrode **190**, and the second capping layer **220** may be sequentially stacked.

In the organic layer **150** of each of the organic light-emitting devices **20** and **40**, light generated in the emission layer may pass through the first electrode **110** and the first capping layer **210** toward the outside. The first electrode **110** may be a semi-transmissive electrode or a transmissive electrode. In the organic layer **150** of each of the organic

308

light-emitting devices **30** and **40**, light generated in the emission layer may pass through the second electrode **190** and the second capping layer **220** toward the outside. The second electrode **190** may be a semi-transmissive or a transmissive electrode.

The first capping layer **210** and the second capping layer **220** may increase external luminescent efficiency according to the principle of constructive interference.


The first capping layer **210** and the second capping layer **220** may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

At least one of the first capping layer **210** and the second capping layer **220** may include at least one material selected from a carbocyclic compound, a heterocyclic compound, an amine-based compound, a porphine derivative, a phthalocyanine derivative, a naphthalocyanine derivative, an alkaline metal complex, and an alkaline earth-based complex. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be substituted with a substituent at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I.

According to an exemplary embodiment of the present invention, at least one of the first capping layer **210** and the second capping layer **220** may include an amine-based compound.


According to an exemplary embodiment of the present invention, at least one of the first capping layer **210** and the second capping layer **220** may include the compound represented by Formula 201 or the compound represented by Formula 202.

According to an exemplary embodiment of the present invention, at least one of the first capping layer **210** and the second capping layer **220** may include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5; however, exemplary embodiments of the present invention are not limited thereto:



309

-continued



The organic light-emitting device according to an exemplary embodiment of the present invention has been described with reference to FIGS. 1 to 4. However, exemplary embodiments of the present invention are not limited thereto.

Layers included in the hole transport region, the emission layer, and the electron transport region may be formed by, for example, vacuum deposition, spin coating, casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, or laser induced thermal imaging (LITI).

When the respective layers of the hole transport region, the emission layer, and the electron transport region are formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of from about 100° C. to about 500° C., at a vacuum degree of from about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate of from about 0.01 Å/sec to about 100 Å/sec, depending on the compound to be included in each layer, and the intended structure of each layer.

When the layers included in the hole transport region, the emission layer, and the layers included in electron transport

310

region are formed by spin coating, for example, the spin coating may be performed at a coating speed of from about 2,000 rpm to about 5,000 rpm, and at a temperature of from about 80° C. to 200° C., depending on the compound to be included in each layer, and the structure of the layer to be formed.

The term “C₁-C₆₀ alkyl group” as used herein refers to a linear or branched monovalent aliphatic saturated hydrocarbon group having 1 to 60 carbon atoms, and non-limiting examples thereof may include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, or a hexyl group. The term “C₁-C₆₀ alkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond at one or more positions along the hydrocarbon chain of the C₂-C₆₀ alkyl group (e.g., in the middle and/or at either terminus of the C₂-C₆₀ alkyl group), and non-limiting examples thereof may include an ethenyl group, a propenyl group, or a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond at one or more positions along the hydrocarbon chain of the C₂-C₆₀ alkyl group (e.g., in the middle and/or at either terminus of the C₂-C₆₀ alkyl group), and non-limiting examples thereof may include an ethynyl group or a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁, in which A₁₀₁ is the C₁-C₆₀ alkyl group, and non-limiting examples thereof may include a methoxy group, an ethoxy group, or an isopropoxy group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and non-limiting examples thereof may include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, or a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

The term “C₁-C₁₀ heterocycloalkyl group” as used herein refers to a monovalent saturated monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and non-limiting examples thereof may include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuran group, or a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

The term “C₃-C₁₀ cycloalkenyl group” as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof, and does not have aromaticity. Non-limiting examples of the C₃-C₁₀ cycloalkenyl group may include a cyclopentenyl group, a cyclohexenyl group, or a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a

ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Non-limiting examples thereof may include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranyl group, or a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. The term “C₆-C₆₀ arylene group” as used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group may include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, or a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the respective rings may be chemically bonded to each other.

The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having an aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having an aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group may include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the respective rings may be chemically bonded to each other.

The term “C₆-C₆₀ aryloxy group” as used herein refers to a monovalent group represented by —OA₁₀₂, in which A₁₀₂ is the C₆-C₆₀ aryl group. The term “C₆-C₆₀ arylthio group” as used herein refers to a monovalent group represented by —SA₁₀₃, in which A₁₀₃ is the C₆-C₆₀ aryl group.

The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group, for example, having 8 to 60 carbon atoms. The monovalent group has two or more rings condensed with each other. Additionally, only carbon atoms are used as ring-forming atoms. The entire molecular structure has non-aromaticity. A non-limiting example of the monovalent non-aromatic condensed polycyclic group may include a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group, for example, having 1 to 60 carbon atoms. The monovalent group has two or more rings condensed with each other. The monovalent group has at least one heteroatom selected from N, O, Si, P, and S. Additionally, atoms other than carbon atoms are used as ring-forming atoms. The entire molecular structure has non-aromaticity. A non-limiting example of the monovalent non-aromatic condensed heteropolycyclic group may include a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic hetero-condensed polycyclic group.

The term “C₅-C₆₀ carbocyclic group” as used herein refers to a monocyclic or polycyclic group having only carbon atoms as ring-forming atoms (e.g., 5 to 60 carbon

atoms). The C₅-C₆₀ cyclic group may be a carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring same as a benzene, a monovalent group such as a phenyl group, or a divalent group such as a phenylene group. According to an exemplary embodiment of the present invention, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent quadrant group.

The term “C₁-C₆₀ heterocyclic group” as used herein refers to a group having the same structure as the C₅-C₆₀ carbocyclic group, but including at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms (e.g., 1 to 60 carbon atoms), as ring-forming atoms.

At least one substituent selected from the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —B(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano

313

group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂).

Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

The term “Ph” as used herein refers to a phenyl group; the term “Me” as used herein refers to a methyl group; the term “Et” as used herein refers to an ethyl group; the term “ter-Bu” or “Bu” as used herein refers to a tert-butyl group; and the term “OMe” as used herein refers to a methoxy group.

The term “biphenyl group” as used herein refers to “a phenyl group substituted with a phenyl group.” As an example, a biphenyl group is a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

The term “terphenyl group” as used herein may refer to “a phenyl group substituted with a biphenyl group.” As an example, a terphenyl group is a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

The symbols * and * as used herein, unless defined otherwise, refer to a binding site to a neighboring atom in a corresponding formula.

A compound according to one or more exemplary embodiments of the present invention and an organic light-emitting device according one or more exemplary embodiments of the present invention will be described in more detail below with reference to Synthesis Examples and Examples. The wording “B was used instead of A” as used in describing Synthesis Examples refers to an example in which a molar equivalent of B was used in place of A.

EXAMPLES

Synthesis Examples


Synthesis Example 1

Synthesis of Intermediate A

Intermediate A was synthesized according to Reaction Scheme 1-1:

314

<Reaction Scheme 1-1>



(1) Synthesis of Intermediate A-1

In an argon gas atmosphere, 19.2 g of (2-methoxynaphthalen-1-yl) boronic acid, 35.1 g of 4-bromo-2-fluoro-1-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2 M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO₄, and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 32.3 g (yield: 84.6%) of 4-bromo-2-fluoro-2'-methoxy-1,1'-binaphthalene (Intermediate A-1).

(2) Synthesis of Intermediate A-2

32.3 g of Intermediate A-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0° C. 27.5 g of 1M boron tribromide (BBr₃) was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of −78° C., and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was trans-

315

ferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 30.9 g (yield: 99.5%) of 4-bromo-2-fluoro-2'-methoxy-1,1'-binaphthalene (Intermediate A-2).


(3) Synthesis of Intermediate A

30.9 g of Intermediate A-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 20.0 g (yield: 68.3%) of Intermediate A.

Synthesis Example 2


Synthesis of Intermediate B

Intermediate B was synthesized according to Reaction Scheme 1-2:



316

-continued



(1) Synthesis of Intermediate B-1

In an argon gas atmosphere, 19.2 g of (1-methoxynaphthalen-2-yl) boronic acid, 35.1 g of 4-bromo-2-fluoro-1-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 32.5 g (yield: 85.3%) of 4-bromo-2-fluoro-1'-methoxy-1,2'-binaphthalene (Intermediate B-1).

(2) Synthesis of Intermediate B-2

32.5 g of Intermediate B-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C , and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 31.2 g (yield: 99.5%) of 4-bromo-2-fluoro-(1,2'-binaphthalen)-1'-ol (Intermediate B-2).

(3) Synthesis of Intermediate B


31.2 g of Intermediate B-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 18.9 g (yield: 64.3%) of Intermediate B.

Synthesis Example 3

Synthesis of Intermediate C

Intermediate C was synthesized according to Reaction Scheme 3:

317



(1) Synthesis of Intermediate C-1

In an argon gas atmosphere, 20.7 g of (2-[methylthio]naphthalen-1-yl) boronic acid, 35.1 g of 4-bromo-2-fluoro-1-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 33.6 g (yield: 84.5%) of 4'-bromo-2'-fluoro-[1,1'-binaphthalen]-2-yl(methyl)sulfane (Intermediate C-1).

(2) Synthesis of Intermediate C-2

33.6 g of Intermediate C-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C ., and the excited state thereof was inactivated with

318

methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 32.2 g (yield: 99.3%) of 4'-bromo-2'-fluoro-(1,1'-binaphthalene)-2-thiol (Intermediate C-2).


(3) Synthesis of Intermediate C

32.2 g of Intermediate C-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 19.7 g (yield: 64.6%) of Intermediate C.

Synthesis Example 4


Synthesis of Intermediate D

Intermediate D was synthesized according to Reaction Scheme 4:



319

-continued



(1) Synthesis of Intermediate D-1

In an argon gas atmosphere, 23.9 g of (10-methoxyphenanthren-9-yl) boronic acid, 35.1 g of 4-bromo-2-fluoro-1-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 36.4 g (molecular weight: 431.30 g/mol, yield: 84.5%) of 9-(4-bromo-2-fluoronaphthalen-1-yl)-10-methoxyphenanthrene (Intermediate D-1).

(2) Synthesis of Intermediate D-2

36.4 g of Intermediate D-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C ., and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 35.0 g (yield: 99.4%) of 10-(4-bromo-2-fluoronaphthalen-1-yl) phenanthren-9-ol (Intermediate D-2).

(3) Synthesis of Intermediate D

35.0 g of Intermediate D-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 21.6 g (yield: 64.8%) of Intermediate D.


Synthesis Example 5

Synthesis of Intermediate E

Intermediate E was synthesized according to Reaction Scheme 5:

320

<Reaction Scheme 5>



(1) Synthesis of Intermediate E-1

In an argon gas atmosphere, 19.2 g of (3-methoxynaphthalen-2-yl) boronic acid, 35.1 g of 4-bromo-1-fluoro-2-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2M sodium carbonate solution added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 32.4 g (yield: 85.1%) of 4-bromo-1-fluoro-3'-methoxy-2,2'-binaphthalene (Intermediate E-1).

(2) Synthesis of Intermediate E-2

32.4 g of Intermediate E-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C ., and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried,

321

thus preparing 31.1 g (yield: 99.5%) of 4'-bromo-1'-fluoro-(2,2'-binaphthalen)-3-ol (Intermediate E-2).


(3) Synthesis of Intermediate E

31.1 g of Intermediate E-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200° C. After the completion of the reaction, the reaction solution was cooled to room temperature, 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using $MgSO_4$, and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 19.9 g (yield: 67.6%) of Intermediate E.

Synthesis Example 6

Synthesis of Intermediate F

Intermediate F was synthesized according to Reaction Scheme 6:



322

(1) Synthesis of Intermediate F-1

In an argon gas atmosphere, 17.3 g of (2,3-dimethoxyphenyl) boronic acid, 17.5 g of 1-bromo-2-fluorobenzene, 2.34 g of tetrakis(triphenylphosphine) palladium (0), 300 mL of 1,2-dimethoxyethane, and 150 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using $MgSO_4$, and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 18.9 g (yield: 85.8%) of 2'-fluoro-2,3-dimethoxy-1,1'-biphenyl (Intermediate F-1).

(2) Synthesis of Intermediate F-2

In an argon gas atmosphere, 18.9 g of Intermediate F-1 and 500 mL of anhydrous THF were added to a flask, and 55 mL of a hexane solution containing 1.6 M n-butyllithium was added thereto. The reaction solution was stirred for about 4 hours at room temperature, followed by being cooled to a temperature of -78° C. Then, 30 mL of THF containing 28.1 g of trimethyl borate was added thereto drop by drop. A temperature at which the reaction occurs was raised up to room temperature while stirring was performed for about 8 hours. 200 mL of a 10% HCl solution was added to the reaction solution, followed by being stirred for about 2 hours. After removal of a water solution from the resulting reaction through an extraction process using ether, an organic layer collected therefrom was then washed using sodium thiosulfate and dried using $MgSO_4$. The product was concentrated, and the resulting residue was washed using hexane, thus preparing 14.3 g (yield: 63.9%) of (2'-fluoro-2,3-dimethoxy-[1,1'-biphenyl]-4-yl) boronic acid (Intermediate F-2).


(3) Synthesis of Intermediate F

31.1 g of Intermediate F-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200° C. After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using $MgSO_4$, and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 19.4 g (yield: 65.9%) of Intermediate F.


Synthesis Example 7

Synthesis of Intermediate G

Intermediate G was synthesized according to Reaction Scheme 7:



323



(1) Synthesis of Intermediate G-1

In an argon gas atmosphere, 19.2 g of (1-methoxynaphthalen-2-yl) boronic acid, 35.1 g of 4-bromo-1-fluoro-2-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 32.5 g (yield: 85.3%) of 4-bromo-1-fluoro-1'-methoxy-2,2'-binaphthalene (Intermediate G-1).

(2) Synthesis of Intermediate G-2

32.5 g of Intermediate G-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C ., and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 31.2 g (yield: 99.5%) of 4'-bromo-1'-fluoro-(2,2'-binaphthalen)-1-ol (Intermediate G-2).

(3) Synthesis of Intermediate G

31.2 g of Intermediate G-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column

324


using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 19.3 g (yield: 65.4%) of Intermediate G.

Synthesis Example 8

Synthesis of Intermediate H

Intermediate H was synthesized according to Reaction Scheme 8:

<Reaction Scheme 8>



(1) Synthesis of Intermediate H-1

In an argon gas atmosphere, 20.7 g of (1-(methylthio)naphthalen-2-yl) boronic acid, 35.1 g of 1-bromo-2-fluoro-3-iodonaphthalene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, and 90 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thereby completing the preparation of 33.6 g (yield: 84.6%) of 4'-bromo-3'-fluoro-[2,2'-binaphthalen]-1-yl(methyl) sulfane (Intermediate H-1).

(2) Synthesis of Intermediate H-2

33.6 g of Intermediate H-1 250 mL of and dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added

325

thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C ., and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 32.3 g (yield: 99.5%) of 4'-bromo-3'-fluoro-(2,2'-binaphthalene)-1-thiol (Intermediate H-2).


(3) Synthesis of Intermediate H

32.3 g of Intermediate H-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 19.6 g (yield: 64.1%) of Intermediate H.


Synthesis Example 9

Synthesis of Intermediate I

Intermediate I was synthesized according to Reaction Scheme 9:



326



(1) Synthesis of Intermediate I-1

In an argon gas atmosphere, 19.2 g of (3-methoxynaphthalen-2-yl) boronic acid, 40.1 g of 3-bromo-10-fluoro-9-iodophenanthrene, 1.28 g of tetrakis(triphenylphosphine) palladium (0), 180 mL of toluene, 90 mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 36.3 g (yield: 84.2%) of 3-bromo-10-fluoro-9-(3-methoxynaphthalen-2-yl)phenanthrene (Intermediate I-1).

(2) Synthesis of Intermediate I-2

36.3 g of Intermediate I-1 and 250 mL of dichloromethane (dehydrated) were added to a flask, followed by being cooled to a temperature of 0°C . 27.5 g of BBr_3 was added thereto, and the mixed solution was stirred for about 24 hours at room temperature. After the completion of the reaction, the reaction solution was cooled to a temperature of -78°C ., and the excited state thereof was inactivated with methanol and a sufficient amount of water in a sequential manner. The resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using dichloromethane. The extracted solution was then dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated, and the resulting sample was vacuum-dried, thus preparing 35.0 g (yield: 99.5%) of 3-(3-bromo-10-fluorophenanthren-9-yl)naphthalen-2-ol (Intermediate I-2).

(3) Synthesis of Intermediate I

35.0 g of Intermediate I-2, 300 mL of N-methyl-2-pyrrolidinone (dehydrated), and 24.5 g of K_2CO_3 were added to a flask, followed by being stirred for about 2 hours at a temperature of 200°C . After the completion of the reaction, the reaction solution was cooled to room temperature, and 2 l of toluene was added thereto. The reaction solution was transferred into a separatory funnel, followed by being washed using water. Then, the resulting solution was dried using MgSO_4 , and passed through a short column using silica gel to remove impurities. The product was concentrated and subjected to recrystallization using a mixed solvent including toluene and methanol, thus preparing 21.2 g (yield: 63.8%) of Intermediate I.

Synthesis Example 10


Synthesis of Compound H1

Compound H1 was synthesized according to Reaction Scheme 10:

327

328

<Reaction Scheme 10>



(1) Synthesis of Intermediate H1-1

34.7 g of Intermediate A and 500 mL of tetrahydrofuran (dehydrated) were added to a flask, and the mixed solution was cooled to a temperature of -78°C . 66 mL of n-BuLi (1.6 M in hexane) was added thereto, and a temperature at which the reaction occurs was increased to 0°C . while stirring was performed on the reaction solution for about 2 hours. Then, 327.5 g of $\text{B}(\text{OMe})_3$ was added thereto, and the resulting solution was stirred for about 10 minutes at a temperature of -78°C . and for about 5 hours at room temperature in a sequential manner. After the completion of the reaction, 200 mL of 1N HCl aq. was added thereto, followed by being stirred for about 1 hour at room temperature. Afterwards, the resulting solution was transferred into a separatory funnel, and an extraction process was performed thereon using ethyl acetate. The extracted solution was then dried using MgSO_4 , and the product was concentrated and washed using n-hexane, thus preparing 19.9 g (yield: 63.5%) of Intermediate H1-1.

(2) Synthesis of Intermediate H1-2

In an argon gas atmosphere, 19.9 g of Intermediate H1-1, 19.8 g of 1-bromo-4-iodobenzene, 1.52 g of tetrakis(triphenylphosphine) palladium (0), 200 mL of toluene, and 100

mL of a 2M sodium carbonate solution were added to a flask. The mixed solution was heated for about 8 hours while being stirred under reflux. After the reaction solution was cooled to room temperature, an extraction process using toluene was performed thereon to remove a water layer. An organic layer collected therefrom was then washed using sodium thiosulfate, dried using MgSO_4 , and concentrated. The resulting residue was purified by silica gel column chromatography, thus preparing 21.8 g (yield: 72.5%) of Intermediate H1-2.


(3) Synthesis of Compound H1

In an argon gas atmosphere, 21.8 g of Intermediate H1-2, 16.4 g of (10-(naphthalen-2-yl)anthracen-9-yl)boronic acid, 0.232 g of tetrakis(triphenylphosphine) palladium (0), 40 mL of 1,2-dimethoxyethane, and 20 mL of a 2 M sodium carbonate solution were added to a flask. The mixed solution was stirred under reflux for about 8 hours. After the reaction solution was cooled to room temperature, a precipitated solid was filtered. Then, the solid was washed using a mixture including water and methanol, and subjected to recrystallization using toluene, thus preparing 19.2 g (yield: 64.1%) of Compound H1. The obtained compound was identified using MS/FAB.

calcd: 646.23, found: 646.79.

Synthesis of Compound H2

Compound H2 was synthesized according to Reaction 5
Scheme 11:



(1) Synthesis of Intermediate H2-1

20.0 g (yield: 64.0%) of Intermediate H2-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate B was used instead of Intermediate A.

(2) Synthesis of Intermediate H2-2

22.2 g (yield: 73.1%) of Intermediate H2-2 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate H2-1 was used instead of Intermediate H1-1.


(3) Synthesis of Compound H2

19.3 g (yield: 63.9%) of Compound H2 was obtained in substantially the same manner as in preparing Compound H1 according to Synthesis Example 10, except that Intermediate H2-2 was used instead of Intermediate H1-2. The obtained compound was identified using MS/FAB.

calcd: 646.23, found: 646.79.

Synthesis of Compound H3

Compound H3 was synthesized according to Reaction 5
Scheme 12:



(1) Synthesis of Intermediate H3-1

20.9 g (yield: 63.6%) of Intermediate H3-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate C was used instead of Intermediate A.

(2) Synthesis of Intermediate H3-2

22.3 g (yield: 72.2%) of Intermediate H3-2 was obtained in substantially the same manner as in preparing Intermediate H1-2 according to Synthesis Example 10, except that Intermediate H3-1 was used instead of Intermediate H1-1.


(3) Synthesis of Compound H3

18.0 g (yield: 64.0%) of Compound H3 was obtained in substantially the same manner as in preparing Compound H1 according to Synthesis Example 10, except that Intermediate H3-2 and (10-phenylanthracen-9-yl) boronic acid were used instead of Intermediate H1-2 and 10-(naphthalen-2-yl) anthracen-9-yl boronic acid, respectively. The

obtained compound was identified using MS/FAB.

calcd: 612.79, found: 612.19.

Compound H4 was synthesized according to Reaction Scheme 13:



(1) Synthesis of Intermediate H4-1

23.0 g (yield: 63.6%) of Intermediate H4-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate D was used instead of Intermediate A.

(2) Synthesis of Intermediate H4-2

24.0 g (yield: 72.4%) of Intermediate H4-2 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate H4-1 was used instead of Intermediate H1-1.


(3) Synthesis of Compound H4

20.2 g (yield: 62.8%) of Compound H4 was obtained in substantially the same manner as in preparing Compound H1 according to Synthesis Example 10, except that Intermediate H4-2 and (10-(naphthalen-1-yl) anthracen-9-yl) boronic acid were used instead of Intermediate H1-2 and 10-(naphthalen-2-yl) anthracen-9-yl) boronic acid, respectively. The obtained compound was identified using MS/FAB.

calcd: 696.85, found: 696.25.

Synthesis of Compound H5

Compound H5 was synthesized according to Reaction ⁵
Scheme 14:



(1) Synthesis of Intermediate H5-1

19.9 g (yield: 63.6%) of Intermediate H5-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate E was used instead of Intermediate A.

(2) Synthesis of Intermediate H5-2

23.2 g (yield: 70.2%) of Intermediate H5-2 was obtained in substantially the same manner as in preparing Intermediate H1-2 according to Synthesis Example 10, except that Intermediate H5-1 was used instead of Intermediate H1-1.


(3) Synthesis of Compound H5

19.4 g (yield: 62.5%) of Compound H5 was obtained in substantially the same manner as in preparing Intermediate H1 according to Synthesis Example 10, except that Intermediate H5-2 and (10-(naphthalen-1-yl)anthracen-9-yl) boronic acid were used instead of Intermediate H1-2 and (10-(naphthalen-2-yl)anthracen-9-yl) boronic acid, respectively. The obtained compound was identified using MS/FAB.

calcd: 696.85, found: 696.25.

Synthesis of Compound H6

Compound H6 was synthesized according to Reaction ⁵
Scheme 15:



(1) Synthesis of Intermediate H6-1

20.0 g (yield: 64.0%) of Intermediate H6-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate F was used instead of Intermediate A.

(2) Synthesis of Intermediate H6-2


21.9 g (yield: 72.7%) of Intermediate H6-2 was obtained in substantially the same manner as in preparing Intermediate H1-2 according to Synthesis Example 10, except that Intermediate H6-1 was used instead of Intermediate H1-1.

(3) Synthesis of Compound H6

21.0 g (yield: 63.2%) of Compound H6 was obtained in substantially the same manner as in preparing Compound H1 according to Synthesis Example 10, except that Intermediate H6-2 and (10-(9,9-dimethyl-9H-fluoren-3-yl)anthracen-9-yl) boronic acid were used instead of Intermediate H1-2 and 10-(naphthalen-2-yl)anthracen-9-yl boronic acid, respectively. The obtained compound was identified using MS/FAB.

calcd: 712.89, found: 712.28.

Compound H7 was synthesized according to Reaction Scheme 16:



(1) Synthesis of Intermediate H7-1

19.9 g (yield: 63.6%) of Intermediate H7-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate G was used instead of Intermediate A.

(2) Synthesis of Intermediate H7-2

23.8 g (yield: 71.8%) of Intermediate H7-2 was obtained in substantially the same manner as in preparing Intermediate H1-2 according to Synthesis Example 10, except that Intermediate H7-1 was used instead of Intermediate H1-1.

(3) Synthesis of Compound H7

18.7 g (yield: 63.3%) of Compound H7 was obtained in substantially the same manner as in preparing Intermediate Compound H1 according to Synthesis Example 10, except that Intermediate H7-2 and (10-phenylanthracen-9-yl)boronic acid were used instead of Intermediate H1-2 and (10-(naphthalen-2-yl)anthracen-9-yl)boronic acid, respectively. The obtained compound was identified using MS/FAB.

calcd: 646.79, found: 646.23.


341

Synthesis Example 17

342

Synthesis of Compound H8

Compound H8 was synthesized according to Reaction ⁵
Scheme 17:



55

(1) Synthesis of Intermediate H8-1

20.2 g (yield: 61.5%) of Intermediate H8-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate H was used instead of Intermediate A.

(2) Synthesis of Intermediate H8-2


21.4 g (yield: 71.4%) of Intermediate H8-2 was obtained in substantially the same manner as in preparing Intermediate H1-2 according to Synthesis Example 10, except that Intermediate H8-1 was used instead of Intermediate H1-1.

(3) Synthesis of Compound H8

20.4 g (yield: 62.8%) of Compound H8 was obtained in substantially the same manner as in preparing Intermediate Compound H1 according to Synthesis Example 10, except that Intermediate H8-2 and (10-(4-phenylnaphthalen-1-yl)anthracen-9-yl) boronic acid were used instead of Intermediate H1-2 and (10-(naphthalen-2-yl)anthracen-9-yl) boronic acid, respectively. The obtained compound was identified using MS/FAB.

calcd: 738.95, found: 738.24.

Compound H9 was synthesized according to Reaction Scheme 18:



(1) Synthesis of Intermediate H9-1

23.0 g (yield: 63.6%) of Intermediate H9-1 was obtained in substantially the same manner as in preparing Intermediate H1-1 according to Synthesis Example 10, except that Intermediate I was used instead of Intermediate A.

(2) Synthesis of Intermediate H9-2

24.0 g (yield: 72.6%) of Intermediate H9-2 was obtained in substantially the same manner as in preparing Intermediate H1-2 according to Synthesis Example 10, except that Intermediate H9-1 was used instead of Intermediate H1-1.

(3) Synthesis of Compound H9

21.0 g (yield: 61.7%) of Compound H9 was obtained in substantially the same manner as in preparing Intermediate Compound H1 according to Synthesis Example 10, except that Intermediate H9-2 and (10-(dibenzofuran-2-yl)anthracen-9-yl)boronic acid were used instead of Intermediate H1-2 and (10-(naphthalen-2-yl)anthracen-9-yl)boronic acid, respectively. The obtained compound was identified using MS/FAB.

calcd: 736.87, found: 736.24.

Example 1


As a substrate and an anode, an ITO glass substrate having a thickness of 15 Ω/cm^2 (1,200 Å) was cut to a size of 50 mm×50 mm×0.7 mm, sonicated by using isopropyl alcohol and pure water for about 5 minutes each, and cleaned by the exposure to ultraviolet rays for about 30 minutes, and then ozone, and the resulting ITO glass substrate was mounted on a vacuum deposition apparatus.

Compound HT28 was vacuum deposited on the ITO glass substrate to form a hole injection layer having a thickness of about 500 Å, and then, Compound HT3 was vacuum deposited on the hole injection layer to form a hole transport layer having a thickness of about 450 Å.

Then, Compound H1 (as a host) and FD1 (as a dopant) were co-deposited on the hole transport layer at a weight ratio of 95:5 to form an emission layer having a thickness of about 300 Å.


345

Compound ET1 was deposited on the emission layer to form an electron transport layer having a thickness of about 250 Å. LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of about 50 Å. Al was vacuum deposited on the electron injection layer to form a cathode having a thickness of about 1,500 Å. Thus, an organic light-emitting device was formed.



HT28

HT3



25

30

35

40

45

50

55

60

65

70

75

80

85

90

95

100

105

110

115

120

125

130

135

140

145

150

155

160

165

170

175

180

185

190

195

200

205

210

215

220

225

230

235

240


245

250

346

-continued

ET1



Examples 2 to 9 and a Comparatives Example 1 to 5

Organic light-emitting devices were each manufactured in substantially the same manner as in Example 1, except that compounds listed in Table 1 were used as hosts in forming the emission layer, instead of Compound H1.

Evaluation Example 1

Efficiency (cd/A) of each of the organic light-emitting devices of Examples 1 to 9 and a Comparative Examples 1 to 5 was measured by using a Kethley SMU 236 at current density of 10 mA/cm², and results thereof are shown in Table 1.

Half lifespan (T₈₀) of each of the organic light-emitting devices of Examples 1 to 9 and a Comparative Examples 1 to 5 were measured by using a PR650 luminance measuring unit at current density of 50 mA/cm², and results thereof are shown in Table 1. The half lifespan (T₈₀) is the time taken after being driven for the organic light-emitting device to reach about 80% of the initial luminance (100%).


TABLE 1

	Host	Efficiency (cd/A)	Half lifespan (T ₈₀ , hr)
Example 1	Compound H1	5.0	100
Example 2	Compound H2	5.1	90
Example 3	Compound H3	4.9	90
Example 4	Compound H4	5.0	110
Example 5	Compound H5	4.9	120
Example 6	Compound H6	5.1	100
Example 7	Compound H7	5.1	110
Example 8	Compound H8	4.9	100
Example 9	Compound H9	5.1	110
Comparative Example 1	Compound A	4.5	50
Comparative Example 2	Compound B	4.7	80
Comparative Example 3	Compound C	4.8	90


347

TABLE 1-continued


	Host	Efficiency (cd/A)	Half lifespan (T ₈₀ , hr)
Comparative Example 4	Compound D	4.7	70
Comparative Example 5	Compound E	4.6	60




H1




H2




H3



H4



H5




H6

348


TABLE 1-continued

	Host	Efficiency (cd/A)	Half lifespan (T ₈₀ , hr)
--	------	----------------------	---


5




15



25




35



40


Compound A



45

50

Compound B



55



60

Compound C

65

349

TABLE 1-continued

Host	Efficiency (cd/A)	Half lifespan (T ₈₀ , hr)	
			5
			10
			15
			20
			25
			30
			35
			40
			45
			50
			55
			60
			65

Referring to Table 1, the organic light-emitting devices of Examples 1 to 9 had relatively high efficiency and half lifespan, compared to those of the organic light-emitting devices of Comparative Examples 1 to 5.

As described above, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have a relatively high efficiency and a relatively long lifespan.

It should be understood that one or more exemplary embodiments of the present invention described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment of the present invention should typically be considered as available for other similar features or aspects in other exemplary embodiments of the present invention.


While one or more exemplary embodiments of the present invention have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention.

What is claimed is:


1. A condensed cyclic compound represented by Formula 1:

350

<Formula 1>



<Formula 1-1>



wherein, in Formulae 1 and 1-1,

A₁ is selected from groups represented by Formula 1-1, n₁ is an integer selected from 1 to 5,

X₁ is selected from oxygen (O) and sulfur (S),

ring B₁ is a naphthalene group and ring B₂ is a phenanthrene group; or

ring B₁ is a phenanthrene group and ring B₂ is a naphthalene group,

L₁ and L₂ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₁ is an integer selected from 1 to 3,

a₂ is an integer selected from 0 to 3,

Ar₁ is selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

b₁ is an integer selected from 1 to 5,

* indicates a binding site to a neighboring atom,

R₁ to R₈, R₁₁, and R₁₂ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a

substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, $-\text{B}(\text{Q}_1)(\text{Q}_2)$, $-\text{C}(=\text{O})(\text{Q}_1)$, $-\text{S}(=\text{O})_2(\text{Q}_1)$, and $-\text{P}(=\text{O})(\text{Q}_1)(\text{Q}_2)$,

c11 is an integer selected from 0 to 7,

c12 is an integer selected from 0 to 8,

at least one substituent selected from the substituted C_3 - C_{10} cycloalkylene group, the substituted C_1 - C_{10} heterocycloalkylene group, the substituted C_3 - C_{10} cycloalkenylene group, the substituted C_1 - C_{10} heterocycloalkylene group, the substituted C_6 - C_{60} arylene group, the substituted C_1 - C_{60} heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$, $-\text{N}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{B}(\text{Q}_{11})(\text{Q}_{12})$, $-\text{C}(=\text{O})(\text{Q}_{11})$, $-\text{S}(=\text{O})_2(\text{Q}_{11})$, and $-\text{P}(=\text{O})(\text{Q}_{11})(\text{Q}_{12})$;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;


a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic con-

densed heteropolycyclic group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, $-\text{N}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{B}(\text{Q}_{21})(\text{Q}_{22})$, $-\text{C}(=\text{O})(\text{Q}_{21})$, $-\text{S}(=\text{O})_2(\text{Q}_{21})$, and $-\text{P}(=\text{O})(\text{Q}_{21})(\text{Q}_{22})$, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$, and


Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_6 - C_{60} aryl group, a terphenyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a C_6 - C_{60} aryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

2. The condensed cyclic compound of claim 1, wherein A_1 is selected from groups represented by Formulae 1-1(10) to 1-1(18):

Formula 1-1(10)




Formula 1-1(11)




353


-continued




Formula 1-1(12)




Formula 1-1(13)



Formula 1-1(14)




Formula 1-1(15)




Formula 1-1(16)

354

-continued



Formula 1-1(17)



Formula 1-1(18)

wherein, in Formulae 1-1(10) to 1-1(18), X_1 , R_{11} , R_{12} , c_{11} , c_{12} , and $*$ are each independently the same as in claim 1,

R_{11a} and R_{11b} are each independently the same as R_{11} in claim 1,

R_{12a} and R_{12b} are each independently the same as R_{12} in claim 1,

ca_{11} is an integer selected from 0 to 3, and ca_{12} , cb_{11} , and cb_{12} are each independently an integer selected from 0 to 4.

3. The condensed cyclic compound of claim 1, wherein L_1 and L_2 are each independently selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthaceenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzox-

355

azolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphe-
 60 nyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl

356


group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and

Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


4. The condensed cyclic compound of claim 1, wherein L_1 and L_2 are each independently selected from groups represented by Formulae 3-1 to 3-41:




Formula 3-1




Formula 3-2




Formula 3-3



Formula 3-4













Formula 3-5



Formula 3-6

357

-continued




358

-continued


Formula 3-7

5




Formula 3-8

10




15



20


Formula 3-9

25




Formula 3-10

30




Formula 3-11

35




Formula 3-12

40



Formula 3-13


45



50


Formula 3-14

55




Formula 3-15

60



Formula 3-16

65



Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21

Formula 3-22

Formula 3-23

Formula 3-24









Formula 3-25

Formula 3-26

Formula 3-27

359

-continued




360

-continued

Formula 3-28

5



Formula 3-29 10

15

Formula 3-30

20

25

Formula 3-31

30

Formula 3-32

35

40

Formula 3-33

45

Formula 3-34





50

55

Formula 3-35

60

65



Formula 3-36

Formula 3-37


Formula 3-38

Formula 3-39

Formula 3-40

361

-continued



wherein, in Formulae 3-1 to 3-41,

Y_1 is selected from O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, and $Si(Z_6)(Z_7)$,

Z_1 to Z_7 are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, a dibenzothiophenyl group, a triazinyl group, a benzimidazolyl group, a phenanthrolinyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$.

Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

d_2 is an integer selected from 1 and 2,

d_3 is an integer selected from 1 to 3,

d_4 is an integer selected from 1 to 4,




d_5 is an integer selected from 1 to 5,

d_6 is an integer selected from 1 to 6,

d_8 is an integer selected from 1 to 8, and

* and *' each independently indicate a binding site to a neighboring atom.

5. The condensed cyclic compound of claim 1, wherein L_1 and L_2 are each independently selected from groups represented by Formulae 4-1 to 4-35:



Formula 3-41

5

10

15

20

25

30

35

40

45

50

Formula 4-1

Formula 4-2

Formula 4-3










55

60

65

362

-continued



Formula 4-4

Formula 4-5

Formula 4-6

Formula 4-7

Formula 4-8

Formula 4-9









Formula 4-10

Formula 4-11

Formula 4-12

363

-continued




364

-continued


Formula 4-13

5




Formula 4-14

10




15



20


Formula 4-15

25



Formula 4-16


30



35


Formula 4-17

40



Formula 4-18


45



50


Formula 4-19

55



Formula 4-20

60



65

Formula 4-21

Formula 4-22

Formula 4-23

Formula 4-24

Formula 4-25

Formula 4-26







Formula 4-27

Formula 4-28

Formula 4-29

365

-continued



wherein, in Formulae 4-1 to 4-35, * and *' each independently indicate a binding site to a neighboring atom.

6. The condensed cyclic compound of claim 1, wherein a1 is 1, and a2 is an integer selected from 0 and 1.

7. The condensed cyclic compound of claim 1, wherein Ar₁ is selected from:

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group,

366

an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and


a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzothiazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pental-

367


enyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and

Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


8. The condensed cyclic compound of claim 1, wherein Ar_1 is selected from groups represented by Formulae 5-1 to 5-79:




Formula 5-1



Formula 5-2



Formula 5-3




Formula 5-4


368

-continued


Formula 5-5




Formula 5-6




Formula 5-7




Formula 5-8




Formula 5-9



Formula 5-10











Formula 5-11



369

-continued




370

-continued


Formula 5-12

5




Formula 5-13

10




Formula 5-14

15




Formula 5-15

25




Formula 5-16

30




Formula 5-17

40




Formula 5-18

50




Formula 5-19

60



65



Formula 5-20

Formula 5-21

Formula 5-22

Formula 5-23

Formula 5-24

Formula 5-25

Formula 5-26












Formula 5-27

Formula 5-28

Formula 5-29

371

-continued




372

-continued


Formula 5-30

5




Formula 5-31

10




Formula 5-32

15




Formula 5-33

20




Formula 5-34

25




Formula 5-35

30




Formula 5-36

35




Formula 5-37

40




Formula 5-38

45




Formula 5-39

50




Formula 5-40



55



60



65



Formula 5-41

Formula 5-42

Formula 5-43

Formula 5-44

Formula 5-45

Formula 5-46

Formula 5-47

Formula 5-48

Formula 5-49

Formula 5-50

Formula 5-51















Formula 5-52

Formula 5-53

Formula 5-54

373

-continued




374

-continued


Formula 5-55

5




Formula 5-56

10




Formula 5-57

15




Formula 5-58

20




Formula 5-59

25




Formula 5-60

30




Formula 5-61

35




Formula 5-62

40




Formula 5-63

45




Formula 5-64

50




Formula 5-65

60



Formula 5-66

65



Formula 5-67

Formula 5-68

Formula 5-69

Formula 5-70

Formula 5-71

Formula 5-72

Formula 5-73

Formula 5-74



Formula 5-75

Formula 5-76

Formula 5-77

375

-continued



wherein, in Formulae 5-1 to 5-79,

Y_{31} and Y_{32} are each independently selected from O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, and $Si(Z_{36})(Z_{37})$,

Z_{31} to Z_{37} are each independently selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzimidazolyl group, a phenanthrolyl group, a triazinyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$,

Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

e_2 is an integer selected from 1 and 2,

e_3 is an integer selected from 1 to 3,

e_4 is an integer selected from 1 to 4,





e_5 is an integer selected from 1 to 5,

e_6 is an integer selected from 1 to 6,

e_8 is an integer selected from 1 to 8, and

* indicates a binding site to a neighboring atom.

9. The condensed cyclic compound of claim 1, wherein Ar_1 is selected from groups represented by Formulae 6-1 to 6-44:



Formula 5-78

5

Formula 5-79

10

15

20

25

30

35

40

45

Formula 6-1

50

Formula 6-2

55

Formula 6-3











60

Formula 6-4

65

376

-continued



Formula 6-5

Formula 6-6

Formula 6-7

Formula 6-8

Formula 6-9

Formula 6-10

Formula 6-11









Formula 6-12

Formula 6-13

Formula 6-14

377


-continued

**378**

-continued

Formula 6-15


5



10


Formula 6-16

15




Formula 6-17

25




Formula 6-18

35




Formula 6-19

40




Formula 6-20

45



Formula 6-21



55



50

Formula 6-22

65



Formula 6-23

Formula 6-24

Formula 6-25

Formula 6-26

Formula 6-27

Formula 6-28











Formula 6-29

Formula 6-30

Formula 6-31

379


-continued




380

-continued


Formula 6-32



Formula 6-33



Formula 6-34



Formula 6-35

Formula 6-36

25 wherein, in Formulae 6-1 to 6-44, * indicates a binding site to a neighboring atom.

Formula 6-37

10. The condensed cyclic compound of claim 1, wherein R_1 to R_8 , R_{11} , and R_{12} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_6 - C_{20} aryl group, a substituted or unsubstituted C_1 - C_{20} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_1)(Q_2)(Q_3).

Formula 6-38

11. The condensed cyclic compound of claim 1, wherein R_1 to R_8 , R_{11} , and R_{12} are each independently selected from: hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

Formula 6-39

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, and a hydrazono group;

Formula 6-40

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

381

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an

382

isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃); and —Si(Q₁)(Q₂)(Q₃), and

Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

12. The condensed cyclic compound of claim 1, wherein R₁ to R₈, R₁₁, and R₁₂ are each independently selected from: hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, and a C₁-C₁₀ alkoxy group;


a C₁-C₁₀ alkyl group and a C₁-C₁₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, and a hydrazono group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group; and

a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group deuterium, each substituted with at least one selected from —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group.


13. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one selected from Formulae 1J to 1R:

<Formula 1J>



<Formula 1K>

<Formula 1L>




383


384

-continued


<Formula 1M>




<Formula 1N>



<Formula 1O>



<Formula 1P>




385


386

-continued

<Formula 1Q>



<Formula 1R>



wherein, in Formulae 1J to 1R, X₁, L₁, L₂, a1, a2, Ar₁, b1, R₁ to R₈, R₁₁, R₁₂, c11, and c12 are each independently the same as in claim 1,

R_{11a} and R_{11b} are each independently the same as R₁₁ in claim 1, 40

R_{12a} and R_{12b} are each independently the same as R₁₂ in claim 1,


ca11 is an integer selected from 0 to 3, and 45

ca12, cb11, and cb12 are each independently an integer selected from 0 to 4.



14. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one selected from Formulae 1J(1) to 1R(1): 50

-continued

<Formula 1K(1)>




<Formula 1L(1)>



387

-continued


<Formula 1M(1)>



5

10

<Formula 1N(1)>




15

20

25

<Formula 1O(1)>




30

35

40


<Formula 1P(1)>



45

50

<Formula 1Q(1)>




60

65

388

-continued

<Formula 1R(1)>




wherein, in Formulae 1J(1) to 1R(1), X_1 , L_1 , and Ar_1 are each independently the same as in claim 1.

15. The condensed cyclic compound of claim 14, wherein X_1 is selected from O and S,


L_1 and L_2 are each independently selected from groups represented by Formulae 4-1 to 4-35, and

Ar_1 is selected from groups represented by Formulae 6-1 to 6-44:


Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4




Formula 4-5



Formula 4-6











Formula 4-7



389


-continued

**390**

-continued


Formula 4-8

5




Formula 4-9

10




Formula 4-10

20




Formula 4-11

30




Formula 4-12

40




Formula 4-13

45




Formula 4-14

50




55



Formula 4-15

60



65

Formula 4-16

Formula 4-17

Formula 4-18

Formula 4-19









Formula 4-20

Formula 4-21

Formula 4-22


Formula 4-23

Formula 4-24

391
-continued**392**
-continued

Formula 4-25

5




10

Formula 4-26

15

Formula 4-27

20




Formula 4-28

25

30

Formula 4-29



35



40

Formula 4-30


45



50



Formula 4-31

55




Formula 4-32

60



65



Formula 4-33

Formula 4-34

Formula 4-35

Formula 6-1

Formula 6-2

Formula 6-3










Formula 6-4

Formula 6-5

Formula 6-6

393

-continued



394


-continued

Formula 6-7


5

Formula 6-8


10




Formula 6-9 15




Formula 6-10 20



Formula 6-11 25




Formula 6-12 30




Formula 6-13 35

40




Formula 6-14 45

50




Formula 6-15 55

60



65



Formula 6-16

Formula 6-17

Formula 6-18

Formula 6-19

Formula 6-20

Formula 6-21











Formula 6-22

Formula 6-23

Formula 6-24

395


-continued

**396**

-continued


Formula 6-25

5




Formula 6-26

10



Formula 6-27

15




Formula 6-28

20


Formula 6-29

30




Formula 6-30

35




Formula 6-31

40




Formula 6-32

50




Formula 6-33

55



Formula 6-34

60



65

Formula 6-35

Formula 6-36

Formula 6-37

Formula 6-38

Formula 6-39

Formula 6-40


Formula 6-41

Formula 6-42

Formula 6-43

397

-continued



wherein, in Formulae 4-1 to 4-35 and 6-1 to 6-44, * and *' each independently indicate a binding site to a neighboring atom.

16. An organic light-emitting device comprising:
a first electrode;
a second electrode facing the first electrode; and
an organic layer disposed between the first electrode and the second electrode, the organic layer comprising an emission layer,

Formula 6-44

5

10

15

398

wherein the organic layer comprises at least one condensed cyclic compound represented by Formula 1 of claim 1.

17. The organic light-emitting device of claim 16, wherein the first electrode is an anode,

the second electrode is a cathode, and

the organic layer comprises a hole transport region disposed between the first electrode and the emission layer and an electron transport region disposed between the emission layer and the second electrode.

18. The organic light-emitting device of claim 16, wherein the emission layer comprises at least one condensed cyclic compound represented by Formula 1 of claim 1.

19. The organic light-emitting device of claim 16, wherein the emission layer further comprises a fluorescent dopant.

* * * * *

专利名称(译)	耦合环状化合物和包括该耦合环状化合物的有机发光装置		
公开(公告)号	US10580999	公开(公告)日	2020-03-03
申请号	US15/399155	申请日	2017-01-05
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	ITO NAOYUKI KIM SEULONG KIM YOUNSUN SHIN DONGWOO LEE JUNG SUB LIM JINO		
发明人	ITO, NAOYUKI KIM, SEULONG KIM, YOUNSUN SHIN, DONGWOO LEE, JUNG SUB LIM, JINO		
IPC分类号	H01L51/54 C07D307/77 C09K11/02 H01L51/00 C09K11/06 C07D333/50 C07D307/91 C07D493/04 C07D495/04 C07D405/10 H01L51/52 H01L51/50		
CPC分类号	C09K11/06 H01L51/0074 H01L51/0052 C07D493/04 C09K11/025 H01L51/006 C07D333/50 C07D405/10 H01L51/0073 H01L51/0058 H01L51/5265 C07D307/91 C07D307/77 C07D495/04 C09K2211/1014 H01L51/5056 H01L51/5072 C09K2211/1011 H01L51/0054 H01L51/5012 C09K2211/1007 H01L51/5206 H01L51/5221 H01L51/5016 C09K2211/1088 H01L51/0061 H01L51/0072		
优先权	1020160001115 2016-01-05 KR 1020160001122 2016-01-05 KR 1020160006995 2016-01-20 KR 1020160006996 2016-01-20 KR		
其他公开文献	US20170194571A1		
外部链接	Espacenet		

摘要(译)

由式1表示的耦合环状化合物和包括该耦合环状化合物的有机发光装置。

[Formula 1]

