



US010633585B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 10,633,585 B2**

(45) **Date of Patent:** **Apr. 28, 2020**

(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(58) **Field of Classification Search**

None

See application file for complete search history.

(71) Applicants: **Samsung Display Co., Ltd.**, Yongin-si, Gyeonggi-do (KR); **Research & Business Foundation SONGKYUNKWAN UNIVERSITY**, Suwon-si, Gyeonggi-do (KR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,748,010 B2 6/2014 Heil et al.
 9,221,820 B2 12/2015 Park et al.
 2015/0372237 A1 12/2015 Kawamura et al.

FOREIGN PATENT DOCUMENTS

JP 2007-123863 A 5/2007
 KR 10-2009-0011488 * 2/2009 C09K 11/06

(Continued)

Primary Examiner — Gregory D Clark

(74) *Attorney, Agent, or Firm* — Innovation Counsel LLP

(72) Inventors: **Sung-Wook Kim**, Yongin-si (KR); **Myeong-Suk Kim**, Yongin-si (KR); **Hwan-Hee Cho**, Yongin-si (KR); **Seung-Soo Yoon**, Suwon-si (KR)

(73) Assignees: **SAMSUNG DISPLAY CO., LTD.** (KR); **RESEARCH & BUSINESS FOUNDATION SONGKYUNKWAN UNIVERSITY** (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 129 days.

(21) Appl. No.: **15/590,527**

(22) Filed: **May 9, 2017**

(65) **Prior Publication Data**

US 2017/0321118 A1 Nov. 9, 2017

(30) **Foreign Application Priority Data**

May 9, 2016 (KR) 10-2016-0056605

(51) **Int. Cl.**

H01L 51/50 (2006.01)

C09K 11/06 (2006.01)

(Continued)


(52) **U.S. Cl.**

CPC **C09K 11/06** (2013.01); **C07C 13/72** (2013.01); **C07D 521/00** (2013.01);

(Continued)

(57) **ABSTRACT**

A condensed cyclic compound and an organic light-emitting device including the same are provided. The condensed cyclic compound may have a structure shown below:



wherein details about the possible constituents are provided in detail in the disclosure.

20 Claims, 4 Drawing Sheets

10

190

150

110

- (51) **Int. Cl.** *2211/1022* (2013.01); *C09K 2211/1029*
C07D 521/00 (2006.01) (2013.01); *C09K 2211/1037* (2013.01); *C09K*
H05B 33/14 (2006.01) *2211/1059* (2013.01); *C09K 2211/1088*
H01L 51/00 (2006.01) (2013.01); *C09K 2211/185* (2013.01); *H01L*
C07C 13/72 (2006.01) *51/5012* (2013.01)
- (52) **U.S. Cl.**
CPC *H01L 51/006* (2013.01); *H01L 51/0052* (56) **References Cited**
(2013.01); *H01L 51/0054* (2013.01); *H01L*
51/0057 (2013.01); *H01L 51/0058* (2013.01);
H01L 51/0067 (2013.01); *H01L 51/0072*
(2013.01); *H01L 51/0073* (2013.01); *H05B*
33/14 (2013.01); *C07C 2603/24* (2017.05);
C07C 2603/42 (2017.05); *C07C 2603/50*
(2017.05); *C07C 2603/94* (2017.05); *C09K*
2211/1007 (2013.01); *C09K 2211/1011*
(2013.01); *C09K 2211/1014* (2013.01); *C09K*
- FOREIGN PATENT DOCUMENTS
- | | | |
|----|-------------------|---------|
| KR | 10-2012-0038402 A | 4/2012 |
| KR | 10-2012-0043623 A | 5/2012 |
| KR | 10-2013-0052663 A | 5/2013 |
| KR | 10-2013-0122602 A | 11/2013 |
| KR | 10-2014-0100911 A | 8/2014 |
- * cited by examiner

FIG. 1**10**

190
150
110

FIG. 2

20

190
150
110
210

FIG. 3**30**

220
190
150
110

FIG. 4

40

220
190
150
110
210

CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application claims the benefit of Korean Patent Application No. 10-2016-0056605 filed on May 9, 2016 in the Korean Intellectual Property Office, the disclosure of which is incorporated herein in its entirety by reference.

BACKGROUND

1. Field

One or more embodiments relate to a condensed cyclic compound and an organic light-emitting device including the same.

2. Description of the Related Art

Organic light-emitting devices are self-emission devices that produce full-color images, and also have wide viewing angles, high contrast ratios, short response times, as well as excellent brightness, driving voltage, and response speed characteristics.

An example of such organic light-emitting devices may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transition from an excited state to a ground state, thereby generating light.


SUMMARY

One or more embodiments include a novel condensed cyclic compound and an organic light-emitting device including the same.

Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

According to one or more embodiments, a condensed cyclic compound is represented by Formula 1:

<Formula 1>



In Formula 1,

ring A₁ may be selected from a benzene, a naphthalene, a pyridine, a pyrimidine, a pyrazine, a quinoline, an isoquinoline, a quinoxaline, a quinazoline, and a cinnoline,

L₁ may be a substituted or unsubstituted condensed polycyclic group having three or more carbocyclic groups condensed with one another,

a₁ may be an integer from 1 to 5, wherein when a₁ is two or more, two or more L₁(s) may be identical to or different from each other,

L₂ and L₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₂ and a₃ may each independently be an integer from 0 to 5, wherein when a₂ is two or more, two or more L₂(s) may be identical to or different from each other, and when a₃ is two or more, two or more L₃(s) may be identical to or different from each other,

R₁ to R₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂),

b₁ to b₃, b₆, and b₇ may each independently be an integer from 0 to 4,

b₄ and b₅ may each independently be an integer from 0 to 6,

c₁ may be an integer from 1 to 4, c₂ may be an integer from 0 to 4, and c₃ may be an integer from 0 to 6, and

at least one substituent of the substituted condensed polycyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ ary-

loxy group, the substituted C_6-C_{60} arylthio group, the substituted C_1-C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group;

a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, and a C_1-C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12});

a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryloxy group, a C_6-C_{60} arylthio group, a C_1-C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22}); and

—Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1-C_{60} alkyl group, a C_2-C_{60} alkenyl group, a C_2-C_{60} alkynyl group, a C_1-C_{60} alkoxy group, a C_3-C_{10} cycloalkyl group, a C_1-C_{10} heterocycloalkyl group, a C_3-C_{10} cycloalkenyl group, a C_1-C_{10} heterocycloalkenyl group, a C_6-C_{60} aryl group, a C_6-C_{60} aryl group substituted with a C_1-C_{60} alkyl group, a C_6-C_{60} aryl group substituted with a C_6-C_{60} aryl group, a terphenyl group, a C_1-C_{60} heteroaryl group, a C_1-C_{60} heteroaryl group substituted with a C_1-C_{60} alkyl group, a C_1-C_{60} heteroaryl group substituted with a C_6-C_{60} aryl group, a monovalent non-aromatic con-

densed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

According to one or more embodiments, an organic light-emitting device includes: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer may include at least one condensed cyclic compound described above.

BRIEF DESCRIPTION OF THE DRAWINGS

These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawings in which:

FIG. 1 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment;

FIG. 2 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment;


FIG. 3 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment; and

FIG. 4 is a schematic cross-sectional view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

A condensed cyclic compound according to an embodiment may be represented by Formula 1:

<Formula 1>



Ring A₁ in Formula 1 may be fused with a neighboring 5-membered ring, while sharing carbon therewith. Ring A₁ in Formula 1 may each independently be selected from a benzene, a naphthalene, a pyridine, a pyrimidine, a pyrazine, a quinoline, an isoquinoline, a quinoxaline, a quinazoline, and a cinnoline.

For example, ring A₁ in Formula 1 may each independently be selected from a benzene, a naphthalene, a pyridine, a quinoline, and an isoquinoline.

In one or more embodiments, ring A₁ in Formula 1 may be a benzene or a pyridine, but embodiments of the present disclosure are not limited thereto.

L₁ in Formula 1 may be a substituted or unsubstituted condensed polycyclic group having three or more carbocyclic groups condensed with one another. L₁ may include carbon as a ring-forming atom and may not include heteroatom (for example, N, O, S, P, or the like). Thus, for example, since a naphthylene group is a condensed polycyclic group having two carbocyclic groups condensed with each other, the naphthylene group is not included in L₁, and since a

pyridinylene group includes N as a ring-forming atom, the pyridinylene group is not included in L_1 .

In one or more embodiments, L_1 in Formula 1 may be selected from:

an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzo-fluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, and an ovalenylene group; and

an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzo-fluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, and an ovalenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolynyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, L_1 in Formula 1 may be selected from:

a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triph-

enylenylene group, a pyrenylene group, a chrysenylene group, and a perylenylene group; and

a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, and a perylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolynyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranlyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranlyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

wherein Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

a_1 in Formula 1 may be an integer from 1 to 5, wherein when a_1 is two or more, two or more L_1 (s) may be identical to or different from each other. That is, " L_1 " is essentially present in a group represented by $*-[L_1]_{a_1}-(R_1)_{b_1}$ in Formula 1.

In one or more embodiments, a_1 in Formula 1 may be 1 or 2, or may be 1, but embodiments of the present disclosure are not limited thereto.

L_2 and L_3 in Formula 1 may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

For example, L_2 and L_3 may each independently be selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a hep-


talenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylenylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylenylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an oxadiazolylenylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a thiadiazolylenylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylenylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylenylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylenylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an oxadiazolylenylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a thiadiazolylenylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy


group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),

wherein Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


In one or more embodiments, L₁ may be selected from groups represented by Formulae 3-8, 3-9, 3-25, and 3-35 to 3-41, and L₂ and L₃ may each independently be selected from groups represented by Formulae 3-1 to 3-41:




Formula 3-1



Formula 3-2











Formula 3-3



Formula 3-4

11

-continued



12


-continued

Formula 3-27

5


Formula 3-28

10



Formula 3-29

20




Formula 3-30

25

Formula 3-31

30




Formula 3-32

40

Formula 3-33


50



55

Formula 3-34

60



65

Formula 3-35



Formula 3-36

Formula 3-37

Formula 3-38

Formula 3-39

-continued



In Formulae 3-1 to 3-41,

Y_1 may be O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$,

Z_1 to Z_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a triazinyl group, a benzimidazolyl group, a phenanthrolinyl group, and $-Si(Q_{31})(Q_{32})(Q_{33})$.

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

d_2 may be 1 or 2,

d_3 may be an integer from 1 to 3,

d_4 may be an integer from 1 to 4,

d_5 may be an integer from 1 to 5,

d_6 may be an integer from 1 to 6,


d_8 may be an integer from 1 to 8, and

$*$ and † each indicate a binding site to a neighboring atom.


In one or more embodiments, L_1 may be selected from groups represented by Formulae 4-11, 4-13, 4-27, and 4-29 to 4-35, and L_2 and L_3 may each independently be selected from groups represented by Formulae 4-1 to 4-35, but embodiments of the present disclosure are not limited thereto:

Formula 3-40

5




10




Formula 3-41


15




20




25



30




35




40


45



55



60



Formula 4-1

Formula 4-2

Formula 4-3

Formula 4-4

Formula 4-5

Formula 4-6

Formula 4-7









Formula 4-8

Formula 4-9

Formula 4-10

15


-continued

**16**

-continued

Formula 4-11


5



10


Formula 4-12

15



Formula 4-13


20




25

Formula 4-14

30




35




Formula 4-15

40



Formula 4-16


45



50


Formula 4-17

55



Formula 4-18

60



65

Formula 4-19

Formula 4-20

Formula 4-21

Formula 4-22

Formula 4-23

Formula 4-24








Formula 4-25

Formula 4-26

Formula 4-27

17

-continued




18

-continued

Formula 4-35

Formula 4-28



Formula 4-29

10

15 * and * in Formulae 4-1 to 4-35 each indicate a binding site to a neighboring atom.

Formula 4-30

20

a2 and a3 in Formula 1 may each independently be an integer from 0 to 5, wherein when a2 is two or more, two or more L₂(s) may be identical to or different from each other, and when a3 is two or more, two or more L₃(s) may be identical to or different from each other.

In one or more embodiments, a2 and a3 in Formula 1 may each independently be 0, 1, or 2, or may each independently be 0 or 1, but embodiments of the present disclosure are not limited thereto

Formula 4-31

30

R₁ to R₇ in Formula 1 may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂).

Formula 4-33

45

For example, R₁ to R₇ in Formula 1 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

Formula 4-34

55

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, and a hydrazono group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a

coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group,

a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a phthalazinyl group, a naphthyridinyl group, a quinoxaliny group, a quinazoliny group, a cinnoliny group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃); and

—Si(Q₁)(Q₂)(Q₃).

wherein Q₁ to Q₃ and Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, R₁ to R₇ in Formula 1 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinoliny group, an isoquinoliny group, a benzoquinoliny group, a quinoxaliny group, a quinazoliny group, a carbazolyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl


21

group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzofuranyl group, a benzothio-phenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophe-nyl group, an imidazopyridinyl group, an imidazopyrimidi-nyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$; and


$-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$,

wherein Q_1 to Q_5 and Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


In one or more embodiments, R_1 to R_7 in Formula 1 may each independently be selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydra-zono group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, groups represented by Formulae 5-1 to 5-75, and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, wherein Q_1 to Q_3 may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group:




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5



Formula 5-6




Formula 5-7




Formula 5-8

22


-continued




Formula 5-9




Formula 5-10




Formula 5-11




Formula 5-12




Formula 5-13




Formula 5-14




Formula 5-15



Formula 5-16




Formula 5-17



Formula 5-18


23

-continued




24

-continued



25



In Formulae 5-1 to 5-75,

Y_{31} may be O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, or $Si(Z_{36})(Z_{37})$,

Z_{31} to Z_{37} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a triazyl group, a benzimidazolyl group, a phenanthrolinyl group, a triazinyl group, — $N(Q_{31})(Q_{32})$, and — $Si(Q_{31})(Q_{32})(Q_{33})$,

Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

$e3$ may be an integer from 1 to 3,

$e4$ may be an integer from 1 to 4,

$e5$ may be an integer from 1 to 5,

$e6$ may be an integer from 1 to 6,

$e7$ may be an integer from 1 to 7,


26

$e8$ may be an integer from 1 to 8,

$e9$ may be an integer from 1 to 9, and


* indicates a binding site to a neighboring atom.

In one or more embodiments, R_1 to R_7 in Formula 1 each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, groups represented by Formulae 6-1 to 6-158, and — $Si(Q_1)(Q_2)(Q_3)$, wherein Q_1 to Q_3 may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto:




27


-continued




Formula 6-22




Formula 6-23




Formula 6-24




Formula 6-25




Formula 6-26




Formula 6-27




Formula 6-28




Formula 6-29




Formula 6-30




Formula 6-31




Formula 6-32




Formula 6-33




Formula 6-34




Formula 6-35




Formula 6-36




Formula 6-37




Formula 6-38




Formula 6-39



Formula 6-40




Formula 6-41




Formula 6-42

28


-continued




Formula 6-43




Formula 6-44




Formula 6-45




Formula 6-46




Formula 6-47




Formula 6-48




Formula 6-49




Formula 6-50




Formula 6-51




Formula 6-52




Formula 6-53




Formula 6-54




Formula 6-55



Formula 6-56




Formula 6-57




Formula 6-58

29


-continued




Formula 6-59




Formula 6-60




Formula 6-61




Formula 6-62




Formula 6-63




Formula 6-64




Formula 6-65




Formula 6-66




Formula 6-67




Formula 6-68




Formula 6-69




Formula 6-70




Formula 6-71



Formula 6-72




Formula 6-73




Formula 6-74

30


-continued




Formula 6-75




Formula 6-76




Formula 6-77




Formula 6-78




Formula 6-79




Formula 6-80




Formula 6-81




Formula 6-82




Formula 6-83




Formula 6-84




Formula 6-85



Formula 6-86




Formula 6-87



Formula 6-88


31

-continued




Formula 6-89

Formula 6-90




Formula 6-91

Formula 6-92




Formula 6-93

Formula 6-94



Formula 6-95

Formula 6-96




Formula 6-97

Formula 6-98


32

-continued




Formula 6-99

Formula 6-100




Formula 6-101

Formula 6-102




Formula 6-103

Formula 6-104



Formula 6-105

Formula 6-106




Formula 6-107

Formula 6-108


33

-continued




Formula 6-109

Formula 6-110




Formula 6-111

Formula 6-112




Formula 6-113

Formula 6-114




Formula 6-115

Formula 6-116



Formula 6-117


Formula 6-118



Formula 6-119

Formula 6-120

Formula 6-121




Formula 6-122

Formula 6-123


34

-continued




Formula 6-124

Formula 6-125




Formula 6-126

Formula 6-127



Formula 6-128


Formula 6-129



Formula 6-130


Formula 6-131

Formula 6-132




Formula 6-133

Formula 6-134



Formula 6-135

Formula 6-136




Formula 6-137


Formula 6-138

35


-continued




Formula 6-139




Formula 6-140




Formula 6-141




Formula 6-142




Formula 6-143




Formula 6-144




Formula 6-145




Formula 6-146




Formula 6-147




Formula 6-148




Formula 6-149




Formula 6-150




Formula 6-151




Formula 6-152



Formula 6-153




Formula 6-154




Formula 6-155

36


-continued



Formula 6-156



Formula 6-157



Formula 6-158

* in Formulae 6-1 to 6-158 indicates a binding site to a neighboring atom.

In one or more embodiments, in Formula 1,

R₂ to R₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, and —Si(Q₃)(Q₄)(Q₅), and

R₁ may be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group (for example, groups represented by Formulae 5-1 to 5-75, or groups represented by Formulae 6-1 to 6-158).

In one or more embodiments, in Formula 1,

R₂ to R₇ may be hydrogen, and

R₁ may be selected from groups represented by Formulae 5-1 to 5-75 (for example, groups represented by Formulae 6-1 to 6-158), but embodiments of the present disclosure are not limited thereto.

In Formula 1, b₁ to b₃, b₆, and b₇ may each independently be an integer from 0 to 4, and b₄ and b₅ may each independently be an integer from 0 to 6.

For example, b₁ in Formula 1 may be 1 or 2, or may be 1, but embodiments of the present invention are not limited thereto.

In one or more embodiments, b₂ to b₇ in Formula 1 may each independently be 0, 1, or 2, or may each independently be 0 or 1, but embodiments of the present disclosure are not limited thereto.

c₁ in Formula 1 may be an integer from 1 to 4. That is, a group represented by *-(L₁)_{a1}-(R₁)_{b1}] in Formula 1 is essentially present. In one or more embodiments, c₂ may be an integer from 0 to 4 and c₃ may be an integer from 0 to 6.


For example, c₁ in Formula 1 may be 1 or 2, or may be 1, but embodiments of the present disclosure are not limited thereto. In one or more embodiments, c₂ and c₃ in Formula

37


1 may each independently be 0 or 1, or may each be 0, but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, the condensed cyclic compound may be represented by one of Formulae 1A to 1D:


Formula 1A




Formula 1B



Formula 1C



Formula 1D



38

In Formulae 1A to 1D,

L_1 to L_3 , a_1 to a_3 , R_1 to R_7 , b_1 to b_7 , and c_1 to c_3 are the same as described above,


X_{11} may be N or C(R_{11}), X_{12} may be N or C(R_{12}), X_{13} may be N or C(R_{13}), X_{14} may be N or C(R_{14}), X_{15} may be N or C(R_{15}), and X_{16} may be N or C(R_{16}), and

R_{11} to R_{16} are the same as described in connection with R_5 .


In one or more embodiments, none, one, or two of X_{11} to X_{16} in Formulae 1A to 1D may be N. In one or more embodiments, none or one of X_{11} to X_{16} in Formulae 1A to 1D may be N.

In one or more embodiments, the condensed cyclic compound may be represented by one of Formulae 1A-1 to 1A-4:


Formula 1A-1



Formula 1A-2




Formula 1A-3



39

-continued

Formula 1A-4



5


10

15

40

-continued

Formula 2B



5

10

15

Formula 2C

In Formulae 1A-1 to 1A-4,

L_1 to L_3 , $a1$ to $a3$, R_1 to R_7 , $b1$ to $b7$, and $c1$ to $c3$ are the same as described above, and

$ba3$ may be an integer from 0 to 3 and $ba4$ may be an integer from 0 to 4.

In one or more embodiments, in Formulae 1A-1 to 1A-4,

L_1 may be selected from groups represented by Formulae 3-8, 3-9, 3-25, and 3-35 to 3-41 (for example, groups represented by Formulae 4-11, 4-13, 4-27, and 4-29 to 4-35),

$a1$ may be 1 or 2,

L_2 and L_3 may each independently be selected from groups represented by Formulae 3-1 to 3-41 (for example, groups represented by Formulae 4-1 to 4-35),

$a2$ and $a3$ may each independently be 0 or 1,

R_1 may be selected from groups represented by Formulae 5-1 to 5-75 (for example, groups represented by Formulae 6-1 to 6-158),

$b1$ may be 1 or 2,

R_2 to R_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, and $-Si(Q_3)(Q_4)(Q_5)$,

Q_3 to Q_5 may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,


$b2$ to $b7$ may each independently be 0, 1, or 2,

$c1$ may be 1 or 2, and $c2$ and $c3$ may each independently be 0 or 1, and

$ba3$ and $ba4$ may each independently be 0 or 1.

In one or more embodiments, the condensed cyclic compound may be represented by one of Formulae 2A to 2D:

Formula 2A



In Formulae 2A to 2D, ring A_1 , L_1 , $a1$, R_1 , R_4 to R_7 , $b1$, $b4$ to $b7$, and $c1$ are the same as described above.

In one or more embodiments, in Formulae 2A to 2D, ring A_1 may be selected from a benzene, a naphthalene, a pyridine, a quinoline, and an isoquinoline,

L_1 may be selected from groups represented by Formulae 3-8, 3-9, 3-25, and 3-35 to 3-41 (for example, groups represented by Formulae 4-11, 4-13, 4-27, and 4-29 to 4-35),

$a1$ may be 1 or 2,

R_1 may be selected from groups represented by Formulae 5-1 to 5-75 (for example, groups represented by Formulae 6-1 to 6-158),

$b1$ may be 1 or 2,

R_4 to R_7 may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, and $-Si(Q_3)(Q_4)(Q_5)$,




Q_3 to Q_5 may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

$b4$ to $b7$ may each independently be 0, 1, or 2, and

$c1$ may be 1 or 2.




41

In one or more embodiments, the condensed cyclic compound may be represented by one of Formulae 2B-1 to 2B-3 and 2C-1 to 2C-3:

**42**

-continued

Formula 2C-1



In Formulae 2B-1 to 2B-3 and 2C-1 to 2C-3, ring A₁, R₁, R₄ to R₇, Z₁, Z₂, b₄ to b₇, d₄, and d₅ are the same as described above.

For example, ring A₁ may be a benzene or a pyridine,

R₁ may be selected from groups represented by Formulae 5-1 to 5-75,


R₄ to R₇, Z₁, and Z₂ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl

43


group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, and a naphthyl group, and

b4 to b7, d4, and d5 may each independently be 0, 1, or 2.


In one or more embodiments, the condensed cyclic compound may be represented by one of Formulae 1-1 to 1-24, but embodiments of the present disclosure:




Formula 1-1



Formula 1-2



Formula 1-3




Formula 1-4

44

-continued


Formula 1-5



10

15

Formula 1-6




20

25

30

Formula 1-7




35

40

45

50

Formula 1-8



55


60

65

45

-continued

Formula 1-9




5

10

15

Formula 1-10




20

25

30

Formula 1-11




35

40

45

50

Formula 1-12



55


60

65


46

-continued


Formula 1-13

R₁


Formula 1-14

R₁

Formula 1-15

R₁


Formula 1-16

R₁

47

-continued

Formula 1-17



5

10


15

20

48

-continued

Formula 1-20



25


30

35


40

45

Formula 1-18



Formula 1-21



45


50

55


60

65

Formula 1-19




Formula 1-22



49

-continued

Formula 1-23



5

10

15

20

25

30

35

40

45

50

1

55


60

65

In Formulae 1-1 to 1-24,


R₁ may be selected from groups represented by Formulae 6-1 to 6-158.

For example, the condensed cyclic compound represented by Formula 1 may be one of Compounds 1 to 54, but embodiments of the present disclosure are not limited thereto.


**50**

-continued


2




3



4




5




51

-continued


**52**

-continued




53

-continued




54

-continued




55

-continued


**56**

-continued




57

-continued



58


-continued



59

-continued

44



5

10

15

20

45

25

30

46


40

45

50

47


60




60

-continued


48




49




50



41




52




61

-continued



The condensed cyclic compound represented by Formula 1 may have a condensed cyclic core represented by Formula 1':



Accordingly, since the condensed cyclic compound has an energy level capable of increasing capabilities to inject and transport holes and electrons toward an emission layer, the efficiency of an organic light-emitting device may be increased. Also, when a condensed heteropolycyclic group is included in a molecular structure, an injected amount of holes and electrons may further increase, thereby further improving the efficiency of the organic light-emitting device may be further increased.

Also, since the molecular structure of the condensed cyclic compound has a high resistance to electrons, a degradation of the molecular structure due to the electrons in the organic light-emitting device may be reduced, thereby increasing the lifespan of the organic light-emitting device.

L_1 in the condensed cyclic compound represented by Formula 1 has "three or more carbocyclic groups" con-

62

densed with one another and may be a substituted or unsubstituted condensed polycyclic group that does not include a heteroatom as a ring-forming atom, and a_1 indicating the number of $L_1(s)$ and the number of $L_2(s)$ is not zero. That is, " L_1 " is essentially present in the group represented by $*-[(L_1)_{a_1}-(R_1)_{b_1}]$ in Formula 1. Also, c_1 in Formula 1 is one or more. That is, the group represented by $*-[(L_1)_{a_1}-(R_1)_{b_1}]$ in Formula 1 is essentially present. The condensed cyclic compound represented by Formula 1 is adjustable to have an appropriate energy level between a host and a dopant, exciton energy generated in the host may be efficiently transferred, thereby improving the efficiency of the organic light-emitting device.

A synthesis method for the condensed cyclic compound represented by Formula 1 would be apparent to one of skilled in the art by referring to the following examples.

At least one condensed cyclic compound represented by Formula 1 may be used between a pair of electrodes constituting an organic light-emitting device. For example, the condensed cyclic compound may be included in at least one layer selected from a hole transport region and an emission layer. In one or more embodiments, the condensed cyclic compound represented by Formula 1 may be used as a material for forming a capping layer positioned outside the pair of electrodes of the organic light-emitting device.

Accordingly, provided is an organic light-emitting device including: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer includes at least one condensed cyclic compound represented by Formula 1.

The expression "(an organic layer) includes at least one condensed cyclic compound" used herein may include a case in which "(an organic layer) includes identical compounds represented by Formula 1" and a case in which "(an organic layer) includes two or more different condensed cyclic compounds represented by Formula 1."

For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may exist in an emission layer of the organic light-emitting device. In one or more embodiments, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may exist in an identical layer (for example, Compound 1 and Compound 2 may all exist in an emission layer), or different layers (for example, Compound 1 may exist in an emission layer and Compound 2 may exist in a hole transport layer).

According to one or more embodiments, the first electrode of the organic light-emitting device may be an anode,

the second electrode of the organic light-emitting device may be a cathode,

the organic layer of the organic light-emitting device may further include a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,

the hole transport region may include a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and

the electron transport region may include a hole blocking layer, a buffer layer, an electron transport layer, an electron injection layer, or any combination thereof.

In one or more embodiments, the emission layer may include the condensed cyclic compound represented by Formula 1. The condensed cyclic compound represented by Formula 1 may act as a host, and the emission layer may

further include, in addition to the condensed cyclic compound represented by Formula 1, another host. In one or more embodiments, the emission layer of the organic light-emitting device may include a host and a dopant, the host may include the condensed cyclic compound represented by Formula 1, and the dopant may include a fluorescent dopant. However, embodiments of the present disclosure are not limited thereto.

The organic light-emitting device may further include at least one selected from a first capping layer disposed in a pathway along which light generated in an emission layer proceeds toward the outside through the first electrode and a second capping layer disposed in a pathway along which light generated in an emission layer proceeds toward the outside through the second electrode, and the at least one selected from the first capping layer and the second capping layer may include at least one of the condensed cyclic compounds.

For example, the organic light-emitting device may have i) a stack structure including a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order, ii) a stack structure including a first capping layer, a first electrode, an organic layer, and a second electrode which are sequentially stacked in this stated order, or iii) a stack structure including a first capping layer, a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order, and at least one selected from the first capping layer and the second capping layer may include the condensed cyclic compound.

The term "organic layer" used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the "organic layer" is not limited to an organic material.

[Description of FIG. 1]

FIG. 1 is a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 includes a first electrode 110, an organic layer 150, and a second electrode 190.

Hereinafter, the structure of the organic light-emitting device 10 according to an embodiment and a method of manufacturing the organic light-emitting device 10 will be described in connection with FIG. 1.

[First Electrode 110]

In FIG. 1, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for a first electrode may be selected from materials with a high work function to facilitate hole injection.

The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming a first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and any combinations thereof, but

embodiments of the present disclosure are not limited thereto. In one or more embodiments, when the first electrode 110 is a semi-transmissive electrode or a reflectable electrode, a material for forming a first electrode may be selected from magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), and any combinations thereof, but embodiments of the present disclosure are not limited thereto.

The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 110 is not limited thereto.

[Organic Layer 150]

The organic layer 150 is disposed on the first electrode 110. The organic layer 150 may include an emission layer.

The organic layer 150 may further include a hole transport region between the first electrode 110 and the emission layer, and an electron transport region between the emission layer and the second electrode 190.

[Hole Transport Region in Organic Layer 150]


The hole transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The hole transport region may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).

For example, the hole transport region may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode 110 in this stated order, but the structure of the hole transport region is not limited thereto.


The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPD), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:

65




66

-continued




67


-continued




methylated NPB




TAPC



HMTPD



<Formula 201>



<Formula 202>

In Formulae 201 and 202,

L_{201} to L_{204} are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

L_{205} may be selected from $^*\text{—O—}^*$, $^*\text{—S—}^*$, $^*\text{—N—}^*$ (Q_{201})- * , a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_2 - C_{20} alkenylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

68

cloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic,

xa1 to xa4 may each independently be an integer from 0 to 3,

xa5 may be an integer from 1 to 10,

R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

In one or more embodiments, in Formula 202, R_{201} and R_{202} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.

In one or more embodiments, regarding Formulae 201 and 202,

L_{201} to L_{205} may each independently be selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, and a pyridinylene group;

a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, and

a pyridinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂), and

Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group and a naphthyl group.

In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

In one or more embodiments, xa5 may be 1, 2, 3, or 4.

In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently may be selected from a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, and a pyridinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an

amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂); and

Q₃₁ to Q₃₃ are the same as described above.

In one or more embodiments, at least one from R₂₀₁ to R₂₀₃ in Formula 201 may each independently be selected from:

a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, in Formula 202, i) R₂₀₁ and R₂₀₂ may be linked via a single bond, and/or ii) R₂₀₃ and R₂₀₄ may be linked via a single bond.

In one or more embodiments, at least one from R₂₀₁ to R₂₀₄ in Formula 202 may be selected from:

a carbazoyl group; and

a carbazoyl group that is substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazoyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;


but embodiments of the present disclosure are not limited thereto.

The compound represented by Formula 201 may be represented by Formula 201A:

71


72

<Formula 201A>




In one or more embodiments, the compound represented by Formula 201 may be represented by Formula 201A(1) below, but embodiments of the present disclosure are not limited thereto:

<Formula 201A(1)>




In one or more embodiments, the compound represented by Formula 201 may be represented by Formula 201A-1 below, but embodiments of the present disclosure are not limited thereto:

<Formula 201A-1>




In one or more embodiments, the compound represented by Formula 202 may be represented by Formula 202A:

<Formula 202A>



In one or more embodiments, the compound represented by Formula 202 may be represented by Formula 202A-1:

<Formula 202A-1>



In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1, L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ are the same as described above,


R₂₁₁ and R₂₁₂ may be understood by referring to the description provided herein in connection with R₂₀₃.

R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

The hole transport region may include at least one compound selected from Compounds HT1 to HT39, but embodiments of the present disclosure are not limited thereto:


73

HT1




74


HT2



HT3




HT4



75


-continued

HT5





76

HT6



HT7


HT8



77


-continued

HT9




78


HT10



HT11



HT12





79

80

-continued



HT13

HT14





HT15

HT16



HT17

HT18





81

82



-continued
HT19

HT20




HT21


HT22



HT23




83


-continued
HT24

84


HT25




HT26




HT27




HT28



HT29




85


-continued
HT30

86


HT31




HT32




HT33



HT34



HT35




87


88

-continued
HT36



HT37



HT38



HT39



A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region includes at least one of a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, for example, about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, for example about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described above.

[p-Dopant]

The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-gener-

tion material may be homogeneously or non-homogeneously dispersed in the hole transport region.

The charge-generation material may be, for example, a p-dopant.

In one or more embodiments, a lowest unoccupied molecular orbital (LUMO) of the p-dopant may be -3.5 eV or less.

The p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound, but embodiments of the present disclosure are not limited thereto.

For example, the p-dopant may include at least one selected from:




a quinone derivative, such as tetracyanoquinodimethane (TCNQ) and 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

a metal oxide, such as tungsten oxide or molybdenum oxide;

1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and

a compound represented by Formula 221 below:

but embodiments of the present disclosure are not limited thereto:



<Formula 221>

In Formula 221,

R_{221} to R_{223} may each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, wherein at least one from R_{221} to R_{223} may have at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, a C_1 - C_{20} alkyl group substituted with —F, a C_1 - C_{20} alkyl group substituted with —Cl, a C_1 - C_{20} alkyl group substituted with —Br, and a C_1 - C_{20} alkyl group substituted with —I.

[Emission Layer in Organic Layer 150]

When the organic light-emitting device **10** is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or are separated from each other. In one or more embodiments, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

The emission layer may include a host and a dopant. The dopant may include at least one selected from a phosphorescent dopant and a fluorescent dopant.

An amount of the dopant in the emission layer may be, in general, in a range of about 0.01 parts to about 15 parts by weight based on 100 parts by weight of the host, but embodiments of the present disclosure are not limited thereto.

A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer is within these ranges, excellent luminescent characteristics may be obtained without a substantial increase in driving voltage.

[Host in Emission Layer]

The host may include the condensed cyclic compound represented by Formula 1.

In one or more embodiments, the host may further include, in addition to the condensed cyclic compound, a compound represented by Formula 301.



In Formula 301,

Ar_{301} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

$xb11$ may be 1, 2, or 3,

L_{301} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

$xb1$ may be an integer selected from 0 to 5,

R_{301} may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{301})(Q_{302})(Q_{303}), —N(Q_{301})(Q_{302}), —B(Q_{301})(Q_{302}), —C(=O)(Q_{301}), S(=O)₂(Q_{301}), and —P(=O)(Q_{301})(Q_{302}).

$xb21$ may be an integer selected from 1 to 5,

Q_{301} to Q_{303} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, Ar_{301} in Formula 301 may be selected from:

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene


group, a chrysene group, naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group;

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothiophene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}), and


Q_{31} to Q_{33} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments of the present disclosure are not limited thereto

When xb11 in Formula 301 is two or more, two or more Ar301(s) may be linked via a single bond.

In one or more embodiments, the compound represented by Formula 301 may be represented by Formula 301-1 or 301-2:



<Formula 301-1>



<Formula 301-2>

In Formulae 301-1 and 301-2,

A_{301} to A_{304} may each independently be selected from a benzene group, a naphthalene group, a phenanthrene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a pyridine group, a pyrimidine group, an indene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, an indole group, a carbazole group, a benzocarbazole group, a dibenzocarbazole group, a furan group, a benzofuran group, a dibenzofuran group, a naphthofuran group, a benzonaphthofuran group, a dinaphthofuran group, a thiophene group, a benzothiophene group, a dibenzothiophene group, a naphthothiophene group, a benzonaphthothiophene group, and a dinaphthothiophene group,

X_{301} may be O, S, or N-[(L_{304})xb4-R₃₀₄],

R_{311} to R_{314} may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl

group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

xb22 and xb23 may each independently be 0, 1, or 2,

L_{301} , xb1, R_{301} , and Q_{31} to Q_{33} may be the same as described above,

L_{302} to L_{304} may each independently be the same as described in connection with L_{31} ,

Xb2 to xb4 may each independently be the same as described in connection with xb1, and

R_{302} to R_{304} may each independently be the same as described in connection with R_{301} .

For example, L_{301} to L_{304} in Formulae 301, 301-1, and 301-2 may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarba-

zolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazininylenylene group, a quinolininylenylene group, an isoquinolininylenylene group, a benzoquinolininylenylene group, a phthalazininylenylene group, a naphthyridinylenylene group, a quinoxalininylenylene group, a quinazolininylenylene group, a cinnolininylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazininylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidininylenylene group, and an azacarbazolylenylene group;

a phenylene group, a naphthylene group, a fluorenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quiazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalynyl group, a quiazolynyl group, a cinnolynyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an aza carbazoyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}); and Q_{31} to Q_{33} are the same as described above.

In one or more embodiments, R₃₀₁ to R₃₀₄ in Formulae 301, 301-1, and 301-2 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group,

a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinno-





95

linyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an aza carbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, $-\text{N}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{B}(\text{Q}_{31})(\text{Q}_{32})$, $-\text{C}(=\text{O})(\text{Q}_{31})$, $-\text{S}(=\text{O})_2(\text{Q}_{31})$, and $-\text{P}(=\text{O})(\text{Q}_{31})(\text{Q}_{32})$; and

Q_{31} to Q_{33} may be the same as described above.







In one or more embodiments, the host may include an alkaline-earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.

The host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolylbenzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55, but embodiments of the present disclosure are not limited thereto:




96

-continued




97

-continued




H11

5




H12

10




H13

15



H14

20



H15

25

30

35

40

45

50


55

60


65

98


-continued




H16




H17



H18



H19




H20

99

-continued

H21



5

10

15

H22

20

25

30

H23

35

40

45




H24

50

55



60

65

**100**




-continued

H25



H26

101
-continued



102
-continued

H27

H30

5

10

15

20

H28

25

30

35

40

45






H29

50

55





60

65






103

-continued





**104**

-continued



105

-continued

**106**

-continued

H42

H46

5

10

15

H43

20

H47

25

30

H48

35

H44

40

H49

45

H50

H45







50

55

H51





60

65



107

-continued



[Phosphorescent Dopant Included in Emission Layer in Organic Layer 150]

The phosphorescent dopant may include an organometallic complex represented by Formula 401 below:

H52

H53

H54

H55

H56

H57

H58

H59

H60

H61

H62

H63

H64

H65

H66

H67

H68

H69

H70

H71

H72

H73

H74

H75

H76

H77

H78

H79


H80

H81

108

<Formula 401>

<Formula 402>

M (L₄₀₁)_{xc1}(L₄₀₂)_{xc2}

In Formulae 401 and 402,

M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

L₄₀₁ may be selected from ligands represented by Formula 402, and xc1 may be 1, 2, or 3, wherein, when xc1 is two or more, two or more L₄₀₁(s) may be identical to or different from each other,

L₄₀₂ may be an organic ligand, and xc2 may be an integer selected from 0 to 4, wherein, when xc2 is two or more, two or more L₄₀₂(s) may be identical to or different from each other,

X₄₀₁ to X₄₀₄ may each independently be nitrogen or carbon,

X₄₀₁ and X₄₀₃ may be linked via a single bond or a double bond, X₄₀₂ and X₄₀₄ may be linked via a single bond or a double bond,

A₄₀₁ and A₄₀₂ may each independently be a C₅-C₆₀ carbocyclic group or a C₁-C₆₀ heterocyclic group,

X₄₀₅ may be a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q₄₁₁)—*, *—C(Q₄₁₁)(Q₄₁₂)—*, *—C(Q₄₁₁)=C(Q₄₁₂)—*, *—C(Q₄₁₁)=*, or *—C=*, wherein Q₄₁₁ and Q₄₁₂ may be hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

X₄₀₆ may be a single bond, O, or S,

R₄₀₁ and R₄₀₂ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₂₀ alkyl group, a substituted or unsubstituted C₁-C₂₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group —Si(Q₄₀₁)(Q₄₀₂)(Q₄₀₃), —N(Q₄₀₁)(Q₄₀₂), —B(Q₄₀₁)(Q₄₀₂), —C(=O)(Q₄₀₁), —S(=O)₂(Q₄₀₁), and —P(=O)(Q₄₀₁)(Q₄₀₂), wherein Q₄₀₁ to Q₄₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a C₆-C₂₀ aryl group, and a C₁-C₂₀ heteroaryl group,

109

xc11 and xc12 may each independently be an integer from 0 to 10, and

* and *¹ in Formula 402 may each indicate a binding site to M in Formula 401.

In one or more embodiments, A₄₀₁ and A₄₀₂ in Formula 402 may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

In one or more embodiments, in Formula 402, i) X₄₀₁ may be nitrogen, and X₄₀₂ may be carbon, or ii) X₄₀₁ and X₄₀₂ may each be nitrogen at the same time.

In one or more embodiments, R₄₀₁ and R₄₀₂ in Formula 402 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and —Si(Q₄₀₁)(Q₄₀₂)(Q₄₀₃), —N(Q₄₀₁)(Q₄₀₂), —B(Q₄₀₁)(Q₄₀₂), —C(=O)(Q₄₀₁), —S(=O)₂(Q₄₀₁), and —P(=O)(Q₄₀₁)(Q₄₀₂),

110


wherein Q₄₀₁ to Q₄₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group, but are not limited thereto.

In one or more embodiments, when xc1 in Formula 401 is two or more, two A₄₀₁(s) in two or more L₄₀₁(s) may optionally be linked to each other via X₄₀₇, which is a linking group, or two A₄₀₂(s) in two or more L₄₀₁(s) may optionally be linked to each other via X₄₀₈, which is a linking group (see Compounds PD1 to PD4 and PD7). X₄₀₇ and X₄₀₈ may each independently be a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q₄₁₃)*, *—C(Q₄₁₃)(Q₄₁₄)*, or *—C(Q₄₁₃)=C(Q₄₁₄)* (wherein Q₄₁₃ and Q₄₁₄ may each independently be hydrogen, deuterium, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group), but are not limited thereto.


L₄₀₂ in Formula 401 may be a monovalent, divalent, or trivalent organic ligand. For example, L₄₀₂ may be selected from halogen, diketone (for example, acetylacetonate), carboxylic acid (for example, picolinate), —C(=O), isonitrile, —CN, and phosphorus (for example, phosphine, or phosphite), but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25, but embodiments of the present disclosure are not limited thereto:


PD1



PD2









PD3



111

-continued

**112**

-continued

PD4

5

10

PD5

20

25

PD6

30

35

PD7

40

45

PD8






50

55

PD9

60

65



PD10

PD11






PD12

PD13

PD14


113

-continued


**114**

-continued


PD15




PD16




PD17



PD18



PD19



PD20


PD21

PD22


PD23

115

-continued



PD24




PD25

[Fluorescent Dopant in Emission Layer]

The fluorescent dopant may include an arylamine compound or a styrylamine compound.

The fluorescent dopant may include a compound represented by Formula 501:



<Formula 501>

In Formula 501,

Ar_{501} may be a substituted or unsubstituted $\text{C}_5\text{-C}_{60}$ carbocyclic group or a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heterocyclic group,

L_{501} to L_{503} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

xd1 to xd3 may each independently be an integer of 0 to 3;

R_{501} and R_{502} may each independently be selected from a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substi-

116

tuted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group,

xd4 may be an integer of 1 to 6.

In one or more embodiments, Ar_{501} in Formula 501 may be selected from:

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, L_{501} to L_{503} in Formula 501 may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group,

117

a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

In one or more embodiments, R_{501} and R_{501} in Formula 502 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group;


a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a pyridinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}); and

Q_{31} to Q_{33} may be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


In one or more embodiments, $xd4$ in Formula 501 may be 2, but embodiments of the present disclosure are not limited thereto.

For example, the fluorescent dopant may be selected from Compounds FD1 to FD22:


118



FD1




FD2



FD3

119

-continued



FD4

5

10

15

20

25

FD5

30

35

40

45


FD6

50

55


60

65




120

-continued




FD7






FD8







FD9



121
-continued




122
-continued



123


-continued

FD19


**124**

-continued

FD21




FD20




FD22


In one or more embodiments, the fluorescent dopant may be selected from the following compounds, but embodiments of the present disclosure are not limited thereto.



DPVBi



DPAVB



[Electron Transport Region in Organic Layer 150]

The electron transport region may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron transport region may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer, but embodiments of the present disclosure are not limited thereto.

For example, the electron transport region may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from an emission layer. However, embodiments of the structure of the electron transport region are not limited thereto.

The electron transport region (for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer in the electron transport region) may include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.

The “ π electron-depleted nitrogen-containing ring” indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

For example, the “ π electron-depleted nitrogen-containing ring” may be i) a 5-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed with each other, or iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each

having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

Examples of the π electron-depleted nitrogen-containing ring include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinazoline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazol, an imidazopyridine, an imidazopyrimidine, and an azacarbazole, but are not limited thereto.

For example, the electron transport region may include a compound represented by Formula 601:



In Formula 601,

Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

$xe11$ may be 1, 2, or 3,

L_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

$xe1$ may be an integer selected from 0 to 5,

R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted

tuted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₆₀₁)(Q₆₀₂)(Q₆₀₃), —C(=O)(Q₆₀₁), —S(=O)₂(Q₆₀₁), and —P(=O)(Q₆₀₁)(Q₆₀₂)

Q₆₀₁ to Q₆₀₃ may each independently be a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and

xe21 may be an integer selected from 1 to 5.

In one or more embodiments, at least one selected from Ar₆₀₁(S) in the number of xe11 and R₆₀₁(s) in the number of xe21 may include the π electron-depleted nitrogen-containing ring.

In one or more embodiments, ring Ar₆₀₁ in Formula 601 may be selected from:

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, phenanthroline group, phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an aza carbazole group;

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, phenanthroline group, phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an aza carbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); and


Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

When xe11 in Formula 601 is two or more, two or more Ar₆₀₁(s) may be linked via a single bond.

In one or more embodiments, Ar₆₀₁ in Formula 601 may be an anthracene group.

In one or more embodiments, a compound represented by Formula 601 may be represented by Formula 601-1:

<Formula 601-1>



In Formula 601-1,

X₆₁₄ may be N or C(R₆₁₄), X₆₁₅ may be N or C(R₆₁₅), X₆₁₆ may be N or C(R₆₁₆), and at least one selected from X₆₁₄ to X₆₁₆ may be N.

L₆₁₁ to L₆₁₃ may each independently be the same as described in connection with L₆₀₁,

xe611 to xe613 may each independently be the same as described in connection with xe1,

R₆₁₁ to R₆₁₃ may each independently be the same as described in connection with R₆₀₁, and

R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, L₆₀₁ and L₆₁₁ to L₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazininylenylene group, a quinolininylenylene group, an isoquinolininylenylene group, a benzoquinolininylenylene group, a phthalazininylenylene group, a naphthyridinylenylene group, a quinoxalininylenylene group, a quinazolininylenylene group, a cinnolininylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazininylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a benzoquinolinylenylene group, a phthalazinylenylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a cinnolinylenylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylenylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a triazolylenylene group, a tetrazolylenylene group, an imidazopyridinylenylene group, an imidazopyrimidinylenylene group, and an azacarbazolylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

but embodiments of the present disclosure are not limited thereto.

In one or more embodiments, xe1 and xe611 to xe613 in Formulae 601 and 601-1 may each independently be 0, 1, or 2.

In one or more embodiments, R₆₀₁ and R₆₁₁ to R₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenan-

threnyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenylenylene group, a pentacenylenylene group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzo-

131


quinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

$-\text{S}(=\text{O})_2(\text{Q}_{601})$ and $-\text{P}(=\text{O})(\text{Q}_{601})(\text{Q}_{602})$; and

Q_{601} and Q_{602} are the same as described above.

The electron transport region may include at least one compound selected from Compounds ET1 to ET36, but embodiments of the present disclosure are not limited thereto:

ET1



20


25

30

35

40

ET2



45

50

55


60

65


132

-continued


ET3




ET4




ET5




133
-continued



134
-continued



135
-continued



ET11


5

10

15

20

136
-continued



ET14



ET12

25

30

35

40



ET15

ET13



45

50

55




60

65



ET16

137
-continued



138
-continued

ET17

ET20

5

10

15

20

25

ET18

ET21

30

35

40

45




ET19 50

ET22

55

60


65



139

-continued

ET23



5


10

15

20

25

ET24



30


35

40

45

ET25

50




65

140


-continued

ET26




25

ET27



45

ET28



55


60

65

141

-continued

ET29



5

10


15

20

142

-continued

ET32



25


ET30

30

35

40

45



ET33


ET31

50


55

60

65





ET34




143

-continued





In one or more embodiments, the electron transport region may include at least one compound selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, Balq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ:



144


-continued

ET35



TAZ

ET36



NTAZ

A thickness of the buffer layer, the hole blocking layer, or the electron control layer may be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.

A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, for example, about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.


The electron transport region (for example, the electron transport layer in the electron transport region) may further include, in addition to the materials described above, a metal-containing material.

The metal-containing material may include at least one selected from an alkali metal complex and an alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenylan oxazole, a hydroxy phenylthiazole, a hydroxy diphenylan oxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phenylpyridine, a hydroxy phenylbenzimidazole, a


145

hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

For example, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



ET-D1



ET-D2

The electron transport region may include an electron injection layer that facilitates injection of electrons from the second electrode **190**. The electron injection layer may directly contact the second electrode **190**.

The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron injection layer may include an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare-earth metal complex, or any combinations thereof.

The alkali metal may be selected from Li, Na, K, Rb, and Cs. In one or more embodiments, the alkali metal may be Li, Na, or Cs. In one or more embodiments, the alkali metal may be Li or Cs, but embodiments of the present disclosure are not limited thereto.

The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

The rare-earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

The alkali metal compound, the alkaline earth-metal compound, and the rare-earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare-earth metal.

The alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF , NaF , CsF , KF , LiI , NaI , CsI , or KI . In one or more embodiments, the alkali metal compound may be selected from LiF , Li_2O , NaF , LiI , NaI , CsI , and KI , but embodiments of the present disclosure are not limited thereto.

The alkaline earth-metal compound may be selected from alkaline earth-metal compounds, such as BaO , SrO , CaO ,

146

$\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$). In one or more embodiments, the alkaline earth-metal compound may be selected from BaO , SrO , and CaO , but embodiments of the present disclosure are not limited thereto.

The rare-earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In one or more embodiments, the rare-earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 , but embodiments of the present disclosure are not limited thereto.

The alkali metal complex, the alkaline earth-metal complex, and the rare-earth metal complex may include an ion of an alkali metal, an alkaline earth-metal, and a rare-earth metal as described above, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare-earth metal complex may be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenyl oxazole, hydroxy phenylthiazole, hydroxy diphenyl oxadiazole, hydroxy diphenylthiadiazol, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene, but embodiments of the present disclosure are not limited thereto.

The electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare-earth metal complex, or any combinations thereof, as described above. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare-earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare-earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare-earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[Second Electrode **190**]

The second electrode **190** may be disposed on the organic layer **150** having such a structure. The second electrode **190** may be a cathode which is an electron injection electrode, and in this regard, a material for forming the second electrode **190** may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function.

The second electrode **190** may include at least one selected from lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO, but embodiments of the present disclosure are not limited thereto. The second electrode **190** may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

The second electrode **190** may have a single-layered structure, or a multi-layered structure including two or more layers.

147

[Description of FIGS. 2 to 4]

An organic light-emitting device **20** of FIG. 2 includes a first capping layer **210**, a first electrode **110**, an organic layer **150**, and a second electrode **190** which are sequentially stacked in this stated order, an organic light-emitting device **30** of FIG. 3 includes a first electrode **110**, an organic layer **150**, a second electrode **190**, and a second capping layer **220** which are sequentially stacked in this stated order, and an organic light-emitting device **40** of FIG. 4 includes a first capping layer **210**, a first electrode **110**, an organic layer **150**, a second electrode **190**, and a second capping layer **220**.

Regarding FIGS. 2 to 4, the first electrode **110**, the organic layer **150**, and the second electrode **190** may be understood by referring to the description presented in connection with FIG. 1.

In the organic layer **150** of each of the organic light-emitting devices **20** and **40**, light generated in an emission layer may pass through the first electrode **110**, which is a semi-transmissive electrode or a transmissive electrode, and the first capping layer **210** toward the outside, and in the organic layer **150** of each of the organic light-emitting devices **30** and **40**, light generated in an emission layer may pass through the second electrode **190**, which is a semi-transmissive electrode or a transmissive electrode, and the second capping layer **220** toward the outside.

The first capping layer **210** and the second capping layer **220** may increase external luminescent efficiency according to the principle of constructive interference.


The first capping layer **210** and the second capping layer **220** may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

At least one selected from the first capping layer **210** and the second capping layer **220** may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be optionally substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one or more embodiments, at least one selected from the first capping layer **210** and the second capping layer **220** may each independently include an amine-based compound.


In one or more embodiments, at least one selected from the first capping layer **210** and the second capping layer **220** may each independently include the compound represented by Formula 201 or the compound represented by Formula 202.

In one or more embodiments, at least one selected from the first capping layer **210** and the second capping layer **220** may each independently include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5, but embodiments of the present disclosure are not limited thereto.

148



-continued



Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with FIGS. 1-4. However, embodiments of the present disclosure are not limited thereto.

Layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region may be formed in a certain region by using one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of about 100° C. to about 500° C., at a vacuum degree of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate of about 0.01 Å/sec to about 100 Å/sec by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

When layers constituting the hole transport region, an emission layer, and layers constituting the electron transport region are formed by spin coating, the spin coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to 200° C. by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[General Definition of Substituents]

The term “C₁-C₆₀ alkyl group” used herein refers to a linear or branched aliphatic saturated hydrocarbon monovalent group having 1 to 60 carbon atoms, and examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

The term C₁-C₁₀ heterocycloalkyl group used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuranlyl group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

The term C₃-C₁₀ cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity, and examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuranlyl group and a 2,3-dihydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be condensed with each other.

The term “C₆-C₆₀ aryloxy group” as used herein refers to —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other, only carbon atoms as ring-forming atoms, and no aromaticity in the entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group,” used herein, refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in the entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazoyl group. The term “divalent non-aromatic condensed heteropolycyclic group,” used herein, refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

The term “C₅-C₆₀ carbocyclic group” as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₅ carbocyclic group may be a ring, such as a benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

The term “C₁-C₆₀ heterocyclic group” as used herein refers to a group having the same structure as the C₁-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

At least one substituent of the substituted C₅-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

deuterium (-D), —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino

group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); and

Q₁₁ to Q₁₃, Q₂₁ to Q₂₃ and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

The term “Ph” as used herein represents a phenyl group, the term “Me” as used herein represents a methyl group, the term “Et” as used herein represents an ethyl group, the term “ter-Bu” or “Bu^t,” as used herein, represents a tert-butyl group, and the term “OMe” as used herein represents a methoxy group.

The term “biphenyl group” used herein refers to a “phenyl group substituted with a phenyl group. The “biphenyl group” is a “substituted phenyl group” having a “C₆-C₆₀ aryl group” as a substituent.

153


The term “terphenyl group” used herein refers to a “phenyl group substituted with a biphenyl group. The “terphenyl group” is a “substituted phenyl group” having, as a substituent, a “C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group.”

* and *¹ used herein, unless defined otherwise, each refer to a binding site to a neighboring atom in a corresponding formula.

Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in detail with reference to Synthesis Examples and Examples. The expression “B was used instead of A” used in describing Synthesis Examples means that an identical number of molar equivalents of A was used in place of molar equivalents of B.

EXAMPLE

Synthesis Example 1: Synthesis of Compound 1



0.58 g (1 eq, 1.30 mmol) of 2'-bromospiro[benzo[de]anthracene-7,9'-fluorene], 0.43 g (1.1 eq, 1.43 mmol) of a (10-phenylanthracen-9-yl)boronic acid, and 0.06 g (0.04 eq, 0.052 mmol) of tetrakis(triphenylphosphine)palladium (0) were added to a flask and vacuum-dried, and then, the flask was filled with nitrogen gas. 13 ml of toluene was added to the flask and the compounds were dissolved therein. Then, 6.5 ml of ethanol and 6.5 ml (10 eq, 13.0 mmol) of a 2.0 M sodium carbonate aqueous solution were added thereto and the resultant mixture was refluxed and stirred at a tempera-


154

ture of 80° C. for 3 hours. After the reaction was completed, washing thereof was performed by using distilled water, and an organic layer was extracted by using ethyl acetate. Then, the organic layer was dried by using magnesium sulfate and filtered through celite. Then, column chromatography was performed thereon to obtain 0.640 g (yield=80%) of Compound 1 (2'-(10-phenylanthracen-9-yl)spiro[benzo[de]anthracene-7,9'-fluorene]).

¹H NMR: 8.41 (1H), 8.01 (1H), 7.91 (7H), 7.77 (1H), 7.65 (3H), 7.58 (1H), 7.51 (5H), 7.41 (7H), 7.27 (4H), 7.00 (1H)

APCI-MS (m/z): 618[M⁺]

Synthesis Example 2: Synthesis of Compound 2



0.58 g (1 eq, 1.30 mmol) of 7'-bromospiro[benzo[de]anthracene-7,5'-indeno[1,2-c]pyridine], 0.43 g (1.1 eq, 1.43 mmol) of a (10-phenylanthracen-9-yl)boronic acid, and 0.06 g (0.04 eq, 0.052 mmol) of tetrakis(triphenylphosphine)palladium (0) were added to a flask and vacuum-dried, and then, the flask was filled with nitrogen gas. 13 ml of toluene was added to the flask and the compounds were dissolved therein. Then, 6.5 ml of ethanol and 6.5 ml (10 eq, 13.0 mmol) of a 2.0 M sodium carbonate aqueous solution were added thereto and the resultant mixture was refluxed and stirred at a temperature of 80° C. for 3 hours. After the reaction was completed, washing thereof was performed by using distilled water and an organic layer was extracted by using ethyl acetate. Then, the organic layer was dried by using magnesium sulfate and filtered through celite. Then,


155

column chromatography was performed thereon to obtain 0.640 g (yield=80%) of Compound 2 (7'-(10-phenylanthracen-9-yl)spiro[benzo[de]anthracene-7,5'-indeno[1,2-c]pyridine]).

¹H NMR: 9.24 (1H), 8.41 (1H), 8.01 (2H), 7.91 (6H), 7.85 (1H), 7.73 (2H), 7.58 (1H), 7.51 (4H), 7.42 (6H), 7.32 (3H), 7.03 (2H)

APCI-MS (m/z): 619[M⁺]

Synthesis Example 3: Synthesis of Compound 9




0.58 g (1 eq, 1.30 mmol) of 3'-bromospiro[benzo[de]anthracene-7,9'-fluorene], 0.43 g (1.1 eq, 1.43 mmol) of a (10-phenylanthracen-9-yl)boronic acid, and 0.06 g (0.04 eq, 0.052 mmol) of tetrakis(triphenylphosphine)palladium (0) were added to a flask and vacuum-dried, and then, the flask was filled with nitrogen gas. 13 ml of toluene was added to the flask and the compounds were dissolved therein. Then, 6.5 ml of ethanol and 6.5 ml (10 eq, 13.0 mmol) of a 2.0 M sodium carbonate aqueous solution were added thereto and the resultant mixture was refluxed and stirred at a temperature of 80° C. for 3 hours. After the reaction was completed, washing thereof was performed by using distilled water and an organic layer was extracted by using ethyl acetate. Then, the organic layer was dried by using magnesium sulfate and filtered through celite. Then, column chromatography was performed thereon to obtain 0.640 g (yield=80%) of Compound 9 (3'-(10-phenylanthracen-9-yl)spiro[benzo[de]anthracene-7,9'-fluorene]).

¹H NMR: 8.41 (1H), 8.06 (1H), 8.01 (1H), 7.91 (6H), 7.67 (1H), 7.58 (3H), 7.51 (5H), 7.41 (7H), 7.27 (3H), 7.00 (1H)

APCI-MS (m/z): 618[M⁺]

156

Synthesis Example 4: Synthesis of Compound 50



0.58 g (1 eq, 1.30 mmol) of 7'-bromospiro[benzo[de]anthracene-7,5'-indeno[1,2-c]pyridine], 0.55 g (1.1 eq, 1.43 mmol) of a (10-(dibenzo[b,d]furan-2-yl)anthracen-9-yl)boronic acid, and 0.06 g (0.04 eq, 0.052 mmol) of tetrakis(triphenylphosphine)palladium (0) were added to a flask and vacuum-dried, and then, the flask was filled with nitrogen gas. 13 ml of toluene was added to the flask and the compounds were dissolved therein. Then, 6.5 ml of ethanol and 6.5 ml (10 eq, 13.0 mmol) of a 2.0 M sodium carbonate aqueous solution were added thereto and the resultant mixture was refluxed and stirred at a temperature of 80° for 3 hours. After the reaction was completed, washing thereof was performed by using distilled water and an organic layer was extracted by using ethyl acetate. Then, the organic layer was dried by using magnesium sulfate and filtered through celite. Then, column chromatography was performed thereon to obtain 0.737 g (yield=80%) of Compound 50 (7'-(10-(dibenzo[b,d]furan-2-yl)anthracen-9-yl)spiro[benzo[de]anthracene-7,5'-indeno[1,2-c]pyridine]).

¹H NMR: 9.24 (1H), 8.41 (1H), 8.01 (2H), 7.91 (8H), 7.70 (6H), 7.38 (6H), 7.30 (4H), 7.06 (2H)

APCI-MS (m/z): 709[M⁺]

Example 1

An anode was prepared by cutting an ITO glass substrate (manufactured by Corning), on which an ITO layer was

157

deposited to a thickness of $15 \Omega/\text{cm}^2$ ($1,200 \text{ \AA}$), to a size of $50 \text{ mm} \times 50 \text{ mm} \times 0.7 \text{ mm}$, ultrasonically cleaning the ITO glass substrate by using isopropyl alcohol and pure water each for 5 minutes, and then, exposing the ITO glass substrate to UV irradiation and ozone for 30 minutes to clean the ITO glass substrate. The ITO glass substrate was loaded into a vacuum deposition apparatus.

2-TNATA was vacuum-deposited on the anode to form a hole injection layer having a thickness of $600 \text{ \AA}$, and 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB) was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of $300 \text{ \AA}$.

Compound 1 (host) and DPAVB (dopant) were co-deposited on the hole transport layer at a weight ratio of 95:5 to form an emission layer having a thickness of 20 nm .

Compound ET1 was deposited on the emission layer to form an electron transport layer having a thickness of $300 \text{ \AA}$, LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of $10 \text{ \AA}$, and Al was vacuum-deposited on the electron injection layer to form a cathode having a thickness of $3,000 \text{ \AA}$, thereby completing the manufacture of an organic light-emitting device.

Examples 2 to 4 and Comparative Examples 1 to 4


Organic light-emitting devices of Examples 2 to 4 and Comparative Examples 1 to 4 were manufactured in the same manner as in Example 1, except that Compounds shown in Table 1 were each used instead of Compound 1 as a host in forming an emission layer.

Evaluation Example 1

The driving voltage, current density, luminance, and efficiency of the organic light-emitting devices manufactured according to Examples 1 to 4 and Comparative Examples 1 to 4 were evaluated by using a Keithley SMU 236 and a luminance meter PR650, and results thereof are shown in Table 1.

TABLE 1

	Host	Driving voltage (V)	Current density (mA/cm^2)	Luminance (cd/m^2)	Efficiency (cd/A)
Example 1	Compound 1	3.6	10	550	5.50
Example 2	Compound 2	3.5	10	522	5.22
Example 3	Compound 9	3.6	10	476	4.76
Example 4	Compound 50	3.2	10	491	4.91
Comparative Example 1	Compound A	4.5	10	311	3.11
Comparative Example 2	Compound B	4.3	10	367	3.67
Comparative Example 3	Compound C	4.2	10	416	4.16
Comparative Example 4	<Compound D>	4.3	10	380	3.80




1


158

TABLE 1-continued


	Host	Driving voltage (V)	Current density (mA/cm^2)	Luminance (cd/m^2)	Efficiency (cd/A)
5					
10					
15					
20					
25					
30					
35					
40					
45					
50					
55					
60					
65					




2




9




50



Compound A




Compound B



Compound C

TABLE 1-continued

Host	Driving voltage (V)	Current density (mA/cm ²)	Luminance (cd/m ²)	Efficiency (cd/A)
				
compound D				

Referring to Table 1, it was confirmed that the organic light-emitting devices of Examples 1 to 4 had excellent driving voltage, luminance, and efficiency, compared to those of the organic light-emitting devices of Comparative Example 1 to 4.


According to one or more embodiments, an organic light-emitting device including the condensed cyclic compound may have a low driving voltage, high efficiency, and a high luminance.

It should be understood that embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

While one or more embodiments have been described with reference to the figures, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope as defined by the following claims.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



wherein, in Formula 1,

ring A₁ is selected from a pyridine, a pyrimidine, a pyrazine, a quinoline, an isoquinoline, a quinoxaline, a quinazoline, and a cinnoline,

L₁ is a substituted or unsubstituted condensed polycyclic group having three or more carbocyclic groups condensed with one another,

a₁ is an integer from 1 to 5, wherein when a₁ is two or more, two or more L₁(s) are identical to or different from each other,

L₂ and L₃ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

a₂ and a₃ are each independently an integer from 0 to 5, wherein when a₂ is two or more, two or more L₂(s) are identical to or different from each other, and when a₃ is two or more, two or more L₃(s) are identical to or different from each other,

R₁ to R₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), and —P(=O)(Q₁)(Q₂),

b₁ to b₃, b₆, and b₇ are each independently an integer from 0 to 4,

b₄ and b₅ are each independently an integer from 0 to 6, c₁ is an integer from 1 to 4, c₂ is an integer from 0 to 4, and c₃ is an integer from 0 to 6, and

at least one substituent of the substituted condensed polycyclic group, the substituted C₃-C₁₀ cycloalkylene group, the substituted C₁-C₁₀ heterocycloalkylene group, the substituted C₃-C₁₀ cycloalkenylene group, the substituted C₁-C₁₀ heterocycloalkenylene group, the substituted C₆-C₆₀ arylene group, the substituted C₁-C₆₀ heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic condensed heteropolycyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

161

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12});

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22}); and

—Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),

wherein Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group, a C_1 - C_{60} heteroaryl group substituted with a C_1 - C_{10} alkyl group, a C_1 - C_{60} heteroaryl group substituted with a C_6 - C_{60} aryl group, a monovalent

162

non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

2. The condensed cyclic compound of claim 1, wherein ring A_1 is selected from pyridine, a quinoline, and an isoquinoline.

3. The condensed cyclic compound of claim 1, wherein L_1 is selected from:

an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzo-fluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, and an ovalenylene group; and

an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzo-fluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a rubicenylene group, a coronenylene group, and an ovalenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzo-

carbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,

wherein Q_{31} to Q_3 are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

4. The condensed cyclic compound of claim 1, wherein L_1 is selected from:


a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, and a perylenylene group; and

a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, and a perylenylene group, each substituted with at least one selected from deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$,


wherein Q_{31} to Q_3 are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

5. The condensed cyclic compound of claim 1, wherein L_1 is selected from groups represented by Formulae 3-8, 3-9, 3-25, and 3-35 to 3-41, and L_2 and L_3 are each independently selected from groups represented by Formulae 3-1 to 3-41:


Formula 3-1




Formula 3-2




Formula 3-3




Formula 3-4




Formula 3-5




Formula 3-6




Formula 3-7



Formula 3-8















Formula 3-9



165

-continued




166

-continued


Formula 3-10

5




Formula 3-11

10




Formula 3-12

15



Formula 3-13

20




Formula 3-14

25


Formula 3-15

30




Formula 3-16

35



Formula 3-17

40




Formula 3-18

45

Formula 3-19

50




Formula 3-20

55

Formula 3-21

60



65

Formula 3-22

Formula 3-23

Formula 3-24

Formula 3-25

Formula 3-26

Formula 3-27








Formula 3-28

Formula 3-29

Formula 3-30

167


-continued




168

-continued


Formula 3-31



Formula 3-32




Formula 3-33



Formula 3-34

Formula 3-35



Formula 3-36

Formula 3-37

Formula 3-38

Formula 3-39

Formula 3-40

Formula 3-41

wherein, in Formulae 3-1 to 3-41,

Y_1 is O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$,

Z_1 to Z_7 are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, a dibenzothiophenyl group, a triazinyl group, a benzimidazolyl group, a phenanthrolinyl group, and —Si(Q_{33})(Q_{32})(Q_{33}),

169

Q₃₁ to Q₃₃ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

d2 is 1 or 2,

d3 is an integer from 1 to 3,

d4 is an integer from 1 to 4,


d5 is an integer from 1 to 5,

d6 is an integer from 1 to 6,


d8 is an integer from 1 to 8, and

* and *' each indicate a binding site to a neighboring atom.


6. The condensed cyclic compound of claim 1, wherein L₁ is selected from groups represented by Formulae 4-11, 4-13, 4-27, and 4-29 to 4-35, and L₂ and L₃ are each independently selected from groups represented by Formulae 4-1 to 4-35:




Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4




Formula 4-5



Formula 4-6



Formula 4-7




Formula 4-8


170

-continued


Formula 4-9




Formula 4-10




Formula 4-11




Formula 4-12




Formula 4-13




Formula 4-14



Formula 4-15












Formula 4-16



171

-continued




172

-continued


Formula 4-17

5



Formula 4-18


10



15


Formula 4-19

20



Formula 4-20


25



30


Formula 4-21

35



Formula 4-22

40




Formula 4-23

45

Formula 4-24


50



55

Formula 4-25

60



65

Formula 4-26

Formula 4-27

Formula 4-28

Formula 4-29

Formula 4-30


Formula 4-31

Formula 4-32


Formula 4-33

173

-continued



Formula 4-34



Formula 4-35

wherein * and *' in Formulae 4-1 to 4-35 each indicate a binding site to a neighboring atom.

7. The condensed cyclic compound of claim 1, wherein a1 is 1, and

a2 and a3 are each independently 0 or 1.

8. The condensed cyclic compound of claim 1, wherein R₁ to R₇ are each independently selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, and a hydrazono group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group,

174

a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;


a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl

175


group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenaziny group, a benzimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$; and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$,

wherein Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


9. The condensed cyclic compound of claim 1, wherein R_1 to R_7 are each independently selected from hydrogen, deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, groups represented by Formulae 5-1 to 5-75, and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, wherein Q_1 to Q_3 are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group:




Formula 5-1




Formula 5-2




Formula 5-3



Formula 5-4



Formula 5-5




Formula 5-6


176

-continued


Formula 5-7




Formula 5-8




Formula 5-9




Formula 5-10




Formula 5-11



Formula 5-12











Formula 5-13



177

-continued




178

-continued


Formula 5-14

5




Formula 5-15

10




Formula 5-16

15




Formula 5-17

20




Formula 5-17

25




Formula 5-18

30




Formula 5-18

35




Formula 5-19

40




Formula 5-19

45




Formula 5-20

50




Formula 5-20

55



Formula 5-21

60



Formula 5-21

65

Formula 5-22

Formula 5-23

Formula 5-24

Formula 5-25

Formula 5-26

Formula 5-27

Formula 5-28

Formula 5-29














Formula 5-30

Formula 5-31

Formula 5-32

179

-continued




180

-continued


Formula 5-33

5




Formula 5-34

10




Formula 5-35

15




Formula 5-36

20




Formula 5-37

25




Formula 5-38

30




Formula 5-39

35




Formula 5-40

40




Formula 5-41

45




Formula 5-42

50




Formula 5-43

55




Formula 5-44

60



Formula 5-45

65



Formula 5-46

Formula 5-47

Formula 5-48

Formula 5-49

Formula 5-50

Formula 5-51

Formula 5-52

Formula 5-53

Formula 5-54

Formula 5-55











Formula 5-56

Formula 5-57

Formula 5-58

181

-continued




182

-continued


Formula 5-59

5




Formula 5-60

10




Formula 5-61

15




Formula 5-62

20




Formula 5-63

25




Formula 5-64

30




Formula 5-65

35




Formula 5-66

40




Formula 5-67

45



Formula 5-68

50



55

wherein, in Formulae 5-1 to 5-75,

Y₃₁ is O, S, C(Z₃₃)(Z₃₄), N(Z₃₅), or Si(Z₃₆)(Z₃₇),

Z₃₁ to Z₃₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuran group, a dibenzothiophenyl group, a benzimidazolyl group, a phenanthrolinyl group, a triazinyl group, —N(Q₃₁)(Q₃₂), and —Si(Q₃₁)(Q₃₂)(Q₃₃),

Q₃₁ to Q₃₃ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group,

e₃ is an integer from 1 to 3,e₄ is an integer from 1 to 4,e₅ is an integer from 1 to 5,

183

e6 is an integer from 1 to 6,

e7 is an integer from 1 to 7,

e8 is an integer from 1 to 8,


e9 is an integer from 1 to 9, and

* indicates a binding site to a neighboring atom.


10. The condensed cyclic compound of claim 1, wherein R₁ is selected from groups represented by Formulae 6-1 to 6-158, and

R₂ to R₇ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, and —Si(Q₁)(Q₂)(Q₃),


wherein Q₁ to Q₃ are each independently selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group:




Formula 6-1 25




Formula 6-2 30




Formula 6-3 35




Formula 6-4 40




Formula 6-5 45




Formula 6-6 50



Formula 6-7 55



Formula 6-8 60




Formula 6-9 65


184

-continued


Formula 6-10




Formula 6-11




Formula 6-12




Formula 6-13




Formula 6-14




Formula 6-15




Formula 6-16




Formula 6-17



Formula 6-18










Formula 6-19



185

-continued



Formula 6-20

5

10

Formula 6-21

15

20

Formula 6-22

25

30

Formula 6-23

35

40

Formula 6-24

45

50

Formula 6-25

55

Formula 6-26


60

65


186

-continued


Formula 6-27




Formula 6-28




Formula 6-29




Formula 6-30



Formula 6-31









Formula 6-32



187


-continued

**188**

-continued

Formula 6-33


5



10

Formula 6-34


15



20

Formula 6-35


25




30

Formula 6-36

35




40




45

Formula 6-37

50




55



Formula 6-38

60



65

Formula 6-39

Formula 6-40

Formula 6-41

Formula 6-42

Formula 6-43










Formula 6-44

Formula 6-45

Formula 6-46

189


-continued

**190**

-continued


Formula 6-47

5



Formula 6-48


10



15


Formula 6-49

20



Formula 6-50


25



30


Formula 6-51

35



Formula 6-52


40



45


Formula 6-53

50




Formula 6-54

55



Formula 6-55

60



65

Formula 6-56

Formula 6-57

Formula 6-58

Formula 6-59

Formula 6-60

Formula 6-61










Formula 6-62

Formula 6-63

Formula 6-64

191


-continued

**192**

-continued


Formula 6-65

5



Formula 6-66


10



15


Formula 6-67

20




Formula 6-68

25



Formula 6-69


30



35


Formula 6-70

40



Formula 6-71


45



50


Formula 6-72

55



Formula 6-73

60



65

Formula 6-74

Formula 6-75

Formula 6-76

Formula 6-77

Formula 6-78

Formula 6-79







Formula 6-80

Formula 6-81

Formula 6-82

193


-continued

**194**

-continued

Formula 6-83

5



Formula 6-84

10

15

Formula 6-85

20

25

Formula 6-86

30

35

Formula 6-87

40

45





50

Formula 6-88

55

60

65



Formula 6-89

Formula 6-90






Formula 6-91

Formula 6-92

Formula 6-93

195


-continued

**196**

-continued

Formula 6-94


5



10

Formula 6-95

15




20

25

Formula 6-96


30



35

Formula 6-97

40




45

50

Formula 6-98

55



60

65

Formula 6-99

Formula 6-100








Formula-101

Formula 6-102

Formula 6-103

197


-continued

**198**

-continued

Formula 6-104


5



10

Formula 6-105


15



20

Formula 6-106


25



30


Formula 6-107

35




Formula 6-108

45



Formula 6-109


50



55

Formula 6-110

60



65

Formula 6-111

Formula 6-112

Formula 6-113

Formula 6-114











Formula 6-115

Formula 6-116

Formula 6-117

199

-continued

**200**

-continued

Formula 6-118

5

Formula 6-119

10

Formula 6-120

15

Formula 6-121

20

Formula 6-122

25

Formula 6-123

30

Formula 6-124

40

Formula 6-125

45








Formula 6-126

55

Formula 6-127

60

65



Formula 6-128

Formula 6-129

Formula 6-130

Formula 6-131










Formula 6-132

Formula 6-133

Formula 6-134

201


-continued

**202**

-continued


Formula 6-135

5




Formula 6-136

10



Formula 6-137


15



20


Formula 6-138

25



Formula 6-139


30



35


Formula 6-140

40



Formula 6-141


45



50


Formula 6-142

55




Formula 6-143

60



65



Formula 6-144

Formula 6-145

Formula 6-146

Formula 6-147

Formula 6-148

Formula 6-149

Formula 6-150






Formula 6-151

Formula 6-152

Formula 6-153

203


-continued



wherein * in Formulae 6-1 to 6-158 indicates a binding site to a neighboring atom.

11. The condensed cyclic compound of claim 1, wherein c1 is 1 and c2 and c3 are each 0.

12. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1A to 1 D:



Formula 6-154

5

Formula 6-155

10

Formula 6-156

15

Formula 6-157

25

Formula 6-158


35

40

204


-continued

Formula 1B



Formula 1C


20



30

Formula 1D

40



Formula 1A

55

wherein, in Formulae 1A to 1D,

L₁ to L₃, a1 to a3, R₁ to R₇, b1 to b7, and c1 to c3 are the same as described in claim 1,

X₁₁ is N or C(R₁₁), X₁₂ is N or C(R₁₂), X₁₃ is N or C(R₁₃), X₁₄ is N or C(R₁₄), X₁₅ is N or C(R₁₅), and X₁₆ is N or C(R₁₆), and


R₁₁ to R₁₆ are the same as described in connection with R₅ in claim 1; at least one of X₁₁ to X₁₄ is N in Formula 1A; at least one of X₁₁ to X₁₆ is N in Formula 1B to Formula 1 D.

65


13. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1A-2 to 1 A-4:

205


Formula 1A-2



Formula 1A-3




Formula 1A-4



wherein, in Formulae 1A-2 to 1A-4,
 L_1 to L_3 , a_1 to a_3 , R_1 to R_7 , b_1 to b_7 , and c_1 to c_3 are the
 same as described in claim 1, and
 ba_3 is an integer from 0 to 3 and ba_4 is an integer from
 0 to 4.

14. The condensed cyclic compound of claim 1, wherein
 the condensed cyclic compound is represented by one of
 Formulae 2A to 2D:


Formula 2A




206

-continued


Formula 2B



Formula 2C




Formula 2D



wherein, in Formulae 2A to 2D,
 ring A_1 , L_1 , a_1 , R_1 , R_4 to R_7 , b_1 , b_4 to b_7 , and c_1 are the
 same as described in claim 1.


15. The condensed cyclic compound of claim 1, wherein
 the condensed cyclic compound is represented by one of
 Formulae 2B-1 to 2B-3 and 2C-1 to 2C-3:

Formula 2B-1



207
-continued

Formula 2B-2



5


10

15

20


208
-continued

Formula 2C-2



Formula 2C-3

Formula 2B-3




25

30

35

40

Formula 2C-1



45

50

55

60

65

wherein, in Formulae 2B-1 to 2B-3 and 2C-1 to 2C-3,
ring A₁, R₁, R₄ to R₇, and b₄ to b₇ are the same as
described in claim 1, and

Z₁ and Z₂ are each independently selected from hydrogen,
deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a
cyano group, a nitro group, an amidino group, a
hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl
group, a C₁-C₂₀ alkoxy group, a phenyl group, a
biphenyl group, a terphenyl group, a naphthyl group, a
fluorenyl group, a spiro-bifluorenyl group, a benzo fluo-
renyl group, a dibenzofluorenyl group, a phenanthrenyl
group, an anthracenyl group, a pyrenyl group, a chry-
senyl group, a pyridinyl group, a pyrazinyl group, a
pyrimidinyl group, a pyridazinyl group, a quinolinyl
group, an isoquinolinyl group, a quinoxalinyl group, a
quinazolinyl group, a carbazolyl group, a dibenzofura-
nyl group, a dibenzothiophenyl group, a triazinyl
group, a benzimidazolyl group, a phenanthrolinyl
group, and —Si(Q₃₁)(Q₃₂)(Q₃₃),





Q₃₁ to Q₃₃ are each independently selected from a C₁-C₁₀
alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a
biphenyl group, a terphenyl group, and a naphthyl
group,

d₄ is an integer from 1 to 4,

d₅ is an integer from 1 to 5.


209

16. The condensed cyclic compound of claim 1, wherein the condensed cyclic compound is represented by one of Formulae 1-2 to 1-4, 1-6 to 1-8, 1-10 to 1-12, 1-14 to 1-16, 1-18 to 1-20, and 1-22 to 1-24:


**210**

-continued


Formula 1-7




Formula 1-8



Formula 1-10




Formula 1-11




65

211
-continued


Formula 1-12




Formula 1-14



Formula 1-15




Formula 1-16




212
-continued


Formula 1-18



Formula 1-19




Formula 1-20



213

-continued

Formula 1-22




5

10

15

Formula 1-23




20

25

30

Formula 1-24





40

45

50

wherein, in Formulae 1-1 to 1-24,

R₁ is selected from groups represented by Formulae 6-1 to 6-158:

Formula 6-1

Formula 6-2


60

65


214

-continued


Formula 6-3




Formula 6-4




Formula 6-5




Formula 6-6




Formula 6-7




Formula 6-8




Formula 6-9




Formula 6-10




Formula 6-11




Formula 6-12



Formula 6-13










Formula 6-14



215


-continued

**216**

-continued


Formula 6-15

5




Formula 6-16

10




Formula 6-17

15




Formula 6-18

25




Formula 6-19

35



Formula 6-20

45



Formula 6-21

60

65

Formula 6-22

Formula 6-23

Formula 6-24







Formula 6-25

Formula 6-26

Formula 6-27

217

-continued


**218**

-continued

Formula 6-34

Formula 6-28

5



10

Formula 6-29

wherein * in Formulae 6-1 to 6-158 indicates a binding site to a neighboring atom.

15


17. A condensed cyclic compound represented by one of Compounds 2, 4 6-8, 10, 12 and 14 to 54:

20

Formula 6-30

25

30



Formula 6-31


35

40

Formula 6-32

45

50




55

Formula 6-33


60

65




219

-continued




220

-continued




221

-continued

**222**


-continued



223

-continued

23




5

10

15


24



20

25

25




35

40

45

26 50



55


60

65


224

-continued

27



28




25

35

40


45

26 50




29

30




225

-continued




**226**

-continued








227

-continued

**228**





-continued



229


-continued

50

**230**

-continued

54

**18.** An organic light-emitting device comprising:

a first electrode;

a second electrode facing the first electrode; and

an organic layer between the first electrode and the second electrode, the organic layer comprising an emission layer,

wherein the organic layer comprises at least one condensed cyclic compound of claim 1.

19. The organic light-emitting device of claim 18, wherein the first electrode is an anode,

the second electrode is a cathode, and

the organic layer further comprises i) a hole transport region that is disposed between the first electrode and the emission layer and comprises at least one of a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and ii) an electron transport region that is disposed between the emission layer and the second electrode and comprises at least one of a hole blocking layer, an electron transport layer, and an electron injection layer.

20. The organic light-emitting device of claim 18, wherein the emission layer comprises the condensed cyclic compound.

* * * * *

专利名称(译)	耦合环状化合物和包括该耦合环状化合物的有机发光装置		
公开(公告)号	US10633585	公开(公告)日	2020-04-28
申请号	US15/590527	申请日	2017-05-09
[标]申请(专利权)人(译)	三星显示有限公司 成均馆大学校产学协力团		
申请(专利权)人(译)	三星DISPLAY CO. , LTD. 研究与业务基础韩国成均馆大学		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD. 研究与业务基础韩国成均馆大学		
[标]发明人	KIM SUNG WOOK KIM MYEONG SUK CHO HWAN HEE YOON SEUNG SOO		
发明人	KIM, SUNG-WOOK KIM, MYEONG-SUK CHO, HWAN-HEE YOON, SEUNG-SOO		
IPC分类号	H01L51/50 C07C13/72 H01L51/00 H05B33/14 C07D521/00 C09K11/06		
CPC分类号	H01L51/0067 H01L51/0057 C07D521/00 H01L51/0052 H01L51/0073 H01L51/0072 H05B33/14 H01L51/006 C09K11/06 H01L51/0054 C07C13/72 H01L51/0058 C09K2211/1059 C07C2603/94 C07C2603/50 C09K2211/1088 C09K2211/1037 H01L51/5012 C09K2211/1014 C09K2211/1011 C09K2211/1007 C07C2603/24 C09K2211/1022 C09K2211/185 C07C2603/42 C09K2211/1029		
审查员(译)	CLARK , GREGORYð		
优先权	1020160056605 2016-05-09 KR		
其他公开文献	US20170321118A1		
外部链接	Espacenet		

摘要(译)

提供了耦合的环状化合物和包括该耦合的环状化合物的有机发光装置。
耦合的环状化合物可具有如下所示的结构： 其中在本公开中详细提供了关于可能的成分的细节。

10

190
150
110