



US010693083B2

(12) **United States Patent**
Jeong et al.

(10) **Patent No.: US 10,693,083 B2**
(45) **Date of Patent: Jun. 23, 2020**

(54) **CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME**

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si, Gyeonggi-do (KR)

(72) Inventors: **Eunjae Jeong**, Yongin-si (KR); **Junha Park**, Yongin-si (KR); **Munki Sim**, Yongin-si (KR); **Hyoyoung Lee**, Yongin-si (KR); **Youngkook Kim**, Yongin-si (KR); **Seokhwan Hwang**, Yongin-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 318 days.

(21) Appl. No.: **15/628,688**

(22) Filed: **Jun. 21, 2017**

(65) **Prior Publication Data**

US 2018/0166635 A1 Jun. 14, 2018

(30) **Foreign Application Priority Data**

Dec. 9, 2016 (KR) 10-2016-0168009

(51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/50 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 51/0072** (2013.01); **C07D 221/18** (2013.01); **C07D 471/04** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC .. C07D 221/18; C07D 471/04; C07D 471/06; C09K 11/06; C09K 2211/1018;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,281,489 A * 1/1994 Mori C09K 11/06
313/498

5,645,948 A 7/1997 Shi et al.
(Continued)

FOREIGN PATENT DOCUMENTS

EP 2 147 962 A1 1/2010
JP 10-017860 A 1/1998
(Continued)

OTHER PUBLICATIONS

Evoniuk et al., Journal of the American Chemical Society, (2017), vol. 139, pp. 16210-16221. (Year: 2017).*

(Continued)


Primary Examiner — Dawn L Garrett

(74) *Attorney, Agent, or Firm* — Lewis Roca Rothgerber Christie LLP

(57) **ABSTRACT**


A condensed cyclic compound and an organic light-emitting device including the same, the condensed cyclic compound being represented by Formula 1:

<Formula 1>



18 Claims, 1 Drawing Sheet

20



- (51) **Int. Cl.**
C07D 471/04 (2006.01)
C09K 11/06 (2006.01)
C07D 221/18 (2006.01)
C07D 471/06 (2006.01)
- (52) **U.S. Cl.**
 CPC *C07D 471/06* (2013.01); *C09K 11/06* (2013.01); *H01L 51/0014* (2013.01); *H01L 51/0052* (2013.01); *H01L 51/0054* (2013.01); *H01L 51/0067* (2013.01); *H01L 51/50* (2013.01); *H01L 51/508* (2013.01); *H01L 51/5068* (2013.01); *C09K 2211/1018* (2013.01); *H01L 51/5004* (2013.01); *H01L 51/5072* (2013.01); *H01L 2251/552* (2013.01)
- (58) **Field of Classification Search**
 CPC H01L 2251/552; H01L 51/0014; H01L 51/0052; H01L 51/0054; H01L 51/0067; H01L 51/0072; H01L 51/50; H01L 51/5004; H01L 51/5068; H01L 51/5072; H01L 51/508
 See application file for complete search history.
- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- | | | |
|------------------|---------|---------------------------------|
| 6,465,115 B2 | 10/2002 | Shi et al. |
| 6,596,415 B2 | 7/2003 | Shi et al. |
| 6,878,469 B2 | 4/2005 | Yoon et al. |
| 8,153,279 B2 | 4/2012 | Eum et al. |
| 9,269,909 B2 | 2/2016 | Dogra et al. |
| 2007/0050927 A1* | 3/2007 | Cole A61K 8/4926
8/636 |
- 2010/0033083 A1* 2/2010 Eum C09K 11/06 313/504
 2015/0108458 A1* 4/2015 Shibata H01L 51/5088 257/40
 2016/0233434 A1 8/2016 Jeong et al.
 2017/0048346 A1 2/2017 Ravidran et al.
- FOREIGN PATENT DOCUMENTS
- | | | |
|----|-------------------|--------|
| JP | 11-087067 A | 3/1999 |
| KR | 10-0691543 B1 | 3/2007 |
| KR | 10-2010-0000121 A | 1/2010 |
| KR | 10-2014-0040686 A | 4/2014 |
| KR | 10-2016-0041019 A | 4/2016 |
| KR | 10-2016-0046703 A | 4/2016 |
| KR | 10-2016-0096782 A | 8/2016 |
| WO | WO 2017/028734 A1 | 2/2017 |
- OTHER PUBLICATIONS
- Tour, et al., "Imine-Bridged Planar Poly (p-phenylene) Derivatives for Maximization of Extended π -Conjugation. The Common Intermediate Approach," JACS, 1994, 116, 11723-11736.
 Klemm, et al., "Synthesis of 5, I 2-Diazabenz [a,h] anthracene (1)," Journal of Heterocyclic Chemistry vol. 8 (1971) p. 763-768.
 EESR by the EPO on Nov. 10, 2017 in the examination of corresponding European Application No. 17186962.1.
 Applied Physics Letters, 51, 1987, pp. 913-915.
 Applied Physics Letters, 57, 1990, pp. 531-533.
 Advanced Materials, 1998, 10, No. 14, pp. 1136-1141.
 Applied Physics Letters, 77, 2000, pp. 1575-1577.
 J. American Chemical Society, 2000, 122 (8), pp. 1832-1833.
 Chemistry Letters, 98, 2001, pp. 98-99.
- * cited by examiner

FIG. 1





FIG. 2



1

CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

Korean Patent Application No. 10-2016-0168009, filed on Dec. 9, 2016, in the Korean Intellectual Property Office, and entitled: "Condensed Cyclic Compound and Organic Light-Emitting Device Including the Same," is incorporated by reference herein in its entirety.

BACKGROUND

1. Field

Embodiments relate to a condensed cyclic compound for an organic light-emitting device and an organic light-emitting device including the same.


2. Description of the Related Art

Organic light-emitting devices are self-emission devices that have wide viewing angles, high contrast ratios, short response times, and excellent characteristics in terms of brightness, driving voltage, and response speed, compared to devices in the art.

An example of such organic light-emitting devices may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, recombine in the emission layer to produce excitons. These excitons transit from an excited state to a ground state, thereby generating light.

SUMMARY


The embodiments may be realized by providing a condensed cyclic compound represented by Formula 1:



wherein, in Formula 1, R₁ to R₁₂ are each independently a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, or a

2

substituted or unsubstituted C₁-C₆₀ alkoxy group, provided that at least one of R₁ to R₁₂ is not hydrogen,



<Formula 2>

wherein, in Formula 2, L₁ is a substituted or unsubstituted C₃-C₆₀ carbocyclic group, a substituted or unsubstituted C₁-C₆₀ heterocyclic group, *—Si(Q₁)(Q₂)-*, *—N(Q₁)-*, *—B(Q₁)-*, *—C(=O)-*, *—S(=O)₂-*, or *—P(=O)(Q₁)-*, a₁ is an integer of 0 to 4, wherein, when a₁ is zero, *(L₁)_{a1}-* is a single bond, and when a₁ is 2, 3, or 4, the 2, 3, or 4 L₁(s) are identical to or different from each other, Ar₁ is a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₁)(Q₂), —B(Q₁)(Q₂), —C(=O)(Q₁), —S(=O)₂(Q₁), or —P(=O)(Q₁)(Q₂), b₁ is an integer of 1 to 4, wherein, when b₁ is 2, 3, or 4, the 2, 3, or 4 Ar₁(s) are identical to or different from each other, at least one substituent of the substituted C₃-C₆₀ carbocyclic group, the substituted C₁-C₆₀ heterocyclic group, the substituted C₁-C₆₀ alkyl group, the substituted C₂-C₆₀ alkenyl group, the substituted C₂-C₆₀ alkynyl group, the substituted C₁-C₆₀ alkoxy group, the substituted C₃-C₁₀ cycloalkyl group, the substituted C₁-C₁₀ heterocycloalkyl group, the substituted C₃-C₁₀ cycloalkenyl group, the substituted C₁-C₁₀ heterocycloalkenyl group, the substituted C₆-C₆₀ aryl group, the substituted C₆-C₆₀ aryloxy group, the substituted C₆-C₆₀ arylthio group, the substituted C₁-C₆₀ heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group; a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₁)(Q₁₂), —B(Q₁₁)(Q₁₂), —C(=O)(Q₁₁), —S(=O)₂(Q₁₁), and —P(=O)(Q₁₁)(Q₁₂); a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group; a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aro-

matic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₁)(Q₂₂), —B(Q₂₁)(Q₂₂), —C(=O)(Q₂₁), —S(=O)₂(Q₂₁), and —P(=O)(Q₂₁)(Q₂₂); and —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂), Q₁ to Q₃, Q₁₁ to Q₁₃, Q₂₁ to Q₂₃, and Q₃₁ to Q₃₃ are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and * and *' each indicate a binding site to a neighboring atom.

The embodiments may be realized by providing an organic light-emitting device including a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, the organic layer comprising an emission layer, wherein the organic layer includes the condensed cyclic compound according to an embodiment.

BRIEF DESCRIPTION OF THE DRAWINGS

Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawings in which:

FIG. 1 illustrates a schematic view of an organic light-emitting device according to an embodiment; and

FIG. 2 illustrates a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION


Example embodiments will now be described more fully hereinafter with reference to the accompanying drawings; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. It will also be understood that when a layer or element is referred to as being “on” another layer or element, it can be directly on the other layer or element, or intervening layers may also be present. In addition, it will also be understood that when a layer is referred to as being “between” two layers, it can

be the only layer between the two layers, or one or more intervening layers may also be present. As used herein, the term “or” is not an exclusive term, e.g., A or B includes A, B, or A and B. Like reference numerals refer to like elements throughout.

A condensed cyclic compound according to an embodiment is represented by Formula 1:

<Formula 1>



R₁ to R₁₂ may each independently be, e.g., a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, or a substituted or unsubstituted C₁-C₆₀ alkoxy group. In an implementation, at least one of R₁ to R₁₂ is not hydrogen. In an implementation, at least one of R₁ to R₁₂ in Formula 1 may be a group represented by Formula 2.

*-(L₁)_{a1}-(Ar₁)_{b1}.

<Formula 2>

In Formulae 1 and 2,

L₁ may be selected from or include, e.g., a substituted or unsubstituted C₃-C₆₀ carbocyclic group, a substituted or unsubstituted C₁-C₆₀ heterocyclic group, *—Si(Q₁)(Q₂)-*', *—N(Q₁)-*', *—B(Q₁)-*', *—C(=O)-*', *—S(=O)₂-*', and *—P(=O)(Q₁)-*.

In an implementation, L₁ may be selected from:

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-bifluorene group, a spiro-benzofluorene-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pyrrole group, a thiophene group, a furan group, a silole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a triazine group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a dibenzosilole group, a carbazole group, a quinoline group, an isoquinoline group, a benzocarbazole group, a dibenzocarbazole group, a benzimidazole group, an imidazopyridine group, and an imidazopyrimidine group;

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-bifluorene group, a spiro-benzofluorene-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene

5

group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pyrrole group, a thiophene group, a furan group, a silole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a triazine group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a dibenzosilole group, a carbazole group, a quinoline group, an isoquinoline group, a benzocarbazole group, a dibenzocarbazole group, a benzimidazole group, an imidazopyridine group, and an imidazopyrimidine group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), and —B(Q₃₁)(Q₃₂); 35 and

—S(=O)₂— and *—P(=O)(Q₁)-*,

Q₁ and Q₃₁ to Q₃₃ may each independently be selected from, e.g., a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, and a pyridinyl group, and 40

* and *' each indicate a binding site to a neighboring atom.


In an implementation, L₁ may be selected from:

a benzene group, a naphthalene group, an anthracene group, a fluorene group, a spiro-bifluorene group, a pyridine group, a pyrimidine group, a triazine group, a carbazole group, a quinoline group, and an isoquinoline group; 45

a benzene group, a naphthalene group, an anthracene group, a fluorene group, a spiro-bifluorene group, a pyridine group, a pyrimidine group, a triazine group, a carbazole group, a quinoline group, and an isoquinoline group, each substituted with at least one selected from a cyano group, a C₁-C₂₀ alkyl group, a phenyl group, a biphenyl group, a pyridinyl group, and a fluorenyl group; and 50

—S(=O)₂— and *—P(=O)(Q₁)-*.

In an implementation, L₁ may be, e.g., a group represented by one of Formulae 3-1 to 3-31, 3-31', 3-32', and 3-32 to 3-35. 55




Formula 3-1


6

-continued


Formula 3-2




Formula 3-3




Formula 3-4




Formula 3-5




Formula 3-6




Formula 3-7




Formula 3-8



Formula 3-9















Formula 3-10



7

-continued




8

-continued


Formula 3-11

5




Formula 3-12

10



Formula 3-13

15




Formula 3-14

20

Formula 3-15

25




Formula 3-16

30


Formula 3-17

35



Formula 3-18

40




Formula 3-19

45

Formula 3-20

50




55

Formula 3-21

60

Formula 3-22

65



Formula 3-23

Formula 3-24

Formula 3-25

Formula 3-26








Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30

-continued



In Formulae 3-1 to 3-31, 3-31', 3-32', and 3-32 to 3-35, Y_1 may be, e.g., O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$.

Z_1 to Z_7 may each independently be selected from, e.g., deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrim-

Formula 3-31

idinyl group, a pyridazinyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, and —Si(Q_{31})(Q_{32})(Q_{33}),

Formula 3-32

d_2 may be an integer of 0 to 2,
 d_3 may be an integer of 0 to 3,
 d_4 may be an integer of 0 to 4,
 d_5 may be an integer of 0 to 5,
 d_6 may be an integer of 0 to 6,
 d_8 may be an integer of 0 to 8, and

Formula 3-31'

*, *', and *'' each indicate a binding site to a neighboring atom. For example, when a variable is 0, e.g., when d_2 is 0, hydrogen atoms are present in place of Z_{31} .

Formula 3-32'

a_1 in Formulae 1 and 2 may be an integer of 0 to 4, wherein, when a_1 is 0, *-(L_1) $_{a_1}$ -*' may be a single bond, and when a_1 is 2, 3, or 4, the 2, 3, or 4 L_1 (s) may be identical to or different from each other.

Formula 3-33

Ar_1 in Formula 2 may be selected from or include, e.g., a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_1)(Q_2)(Q_3), —N(Q_1)(Q_2), —B(Q_1)(Q_2), —C(=O)(Q_1), —S(=O) $_2$ (Q_1), and —P(=O)(Q_1)(Q_2).

Formula 3-34

In an implementation, Ar_1 may be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a thiophenyl group, a furanyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzonaphthofuranyl group, a dinaphthofuranyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a benzonaphthosilolyl group, a dinaphthosilolyl group, a benzimidazolyl group, and an imidazopyridinyl group;

Formula 3-35

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a

hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a thiophenyl group, a furanyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzonaphthofuranyl group, a dinaphthofuranyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a benzonaphthosilolyl group, a dinaphthosilolyl group, a benzimidazolyl group, and an imidazopyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a thiophenyl group, a furanyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, —N(Q₃₁)(Q₃₂), and —Si(Q₃₁)(Q₃₂)(Q₃₃); and —S(=O)(Q₁)(Q₂), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), —P(=O)₂(Q₁), —P(=S)(Q₁)(Q₂), and —P(=S)₂(Q₁).


In an implementation, Ar₁ may be selected from:

a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, and a carbazolyl group;


a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a phenanthrenyl group, an anthracenyl group, a triphenylenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, and a carbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a carbazolyl group, —N(Q₃₁)(Q₃₂), and —Si(Q₃₁)(Q₃₂)(Q₃₃); and

—S(=O)(Q₁)(Q₂), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), —P(=O)₂(Q₁), —P(=S)(Q₁)(Q₂), and —P(=S)₂(Q₁).


In an implementation, Ar₁ may be a group represented by one of Formulae 5-1 to 5-49, —S(=O)(Q₁)(Q₂), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂), —P(=O)₂(Q₁), —P(=S)(Q₁)(Q₂), or —P(=S)₂(Q₁).




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5




Formula 5-6



Formula 5-7











Formula 5-8



Formula 5-9

13


-continued




14

-continued


Formula 5-10




Formula 5-11




Formula 5-12





Formula 5-13




Formula 5-14




Formula 5-15



Formula 5-16



Formula 5-17



Formula 5-18

Formula 5-19

Formula 5-20

Formula 5-21

Formula 5-22












Formula 5-23

Formula 5-24

Formula 5-25

15

-continued




16


-continued

Formula 5-26

5




10




Formula 5-27

15




20




Formula 5-28

25




Formula 5-29

30




Formula 5-30

35



Formula 5-31


40



Formula 5-32


Formula 5-33

50




Formula 5-34

55



Formula 5-35

60



Formula 5-36

65

Formula 5-37

Formula 5-38

Formula 5-39

Formula 5-40

Formula 5-41

Formula 5-42

Formula 5-43



Formula 5-44

Formula 5-45

Formula 5-46

Formula 5-47

-continued



In Formulae 5-1 to 5-49,

Y_{31} may be, e.g., O, S, $C(Z_{33})(Z_{34})$, $N(Z_{35})$, or $Si(Z_{36})(Z_{37})$,

Z_{31} to Z_{37} may each independently be selected from, e.g., deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, a pyridinyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, and — $Si(Q_{31})(Q_{32})(Q_{33})$,

Q_1 , Q_2 , and Q_{31} to Q_{33} may each independently be selected from, e.g., a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, and a pyridinyl group,

e_2 may be an integer of 0 to 2,

e_3 may be an integer of 0 to 3,

e_4 may be an integer of 0 to 4,

e_5 may be an integer of 0 to 5,

e_6 may be an integer of 0 to 6,

e_7 may be an integer of 0 to 7,

e_9 may be an integer of 0 to 9, and


* indicates a binding site to a neighboring atom.

In an implementation, Ar_1 may be, e.g., a group represented by one of Formulae 5-1 to 5-4, 5-7, 5-13, 5-14, 5-20 to 5-23, 5-30, 5-31, 5-34, 5-41, and 5-48, — $S(=O)_2(Q_1)$, or — $P(=O)(Q_1)(Q_2)$.


In an implementation, Ar_1 may be, e.g., a group represented by one of Formulae 6-1 to 6-110, group represented by one of Formulae 10-1 to 10-11, — $S(=O)_2(Q_1)$, or — $P(=O)(Q_1)(Q_2)$.

Formula 5-48

5




10











Formula 5-49

15



20



Formula 6-1

Formula 6-2

Formula 6-3

Formula 6-4

Formula 6-5

Formula 6-6

Formula 6-7

Formula 6-8










Formula 6-9

Formula 6-10

Formula 6-11

19

-continued




20

-continued


Formula 6-12

5




Formula 6-13

10




Formula 6-14

15




Formula 6-15

20




Formula 6-16

25




Formula 6-17

30




Formula 6-18

35




Formula 6-19

40



Formula 6-20

45



50

Formula 6-21

Formula 6-22

Formula 6-23

Formula 6-24

Formula 6-25









Formula 6-26

Formula 6-27

Formula 6-28

21


-continued

**22**

-continued

Formula 6-29

5




Formula 6-30

10

Formula 6-31


15



20


Formula 6-32

25



Formula 6-33


30



35


Formula 6-34

40



Formula 6-35


50




55

Formula 6-36

60



65



Formula 6-37

Formula 6-38

Formula 6-39

Formula 6-40

Formula 6-41










Formula 6-42

Formula 6-43

Formula 6-44

23


-continued

**24**

-continued


Formula 6-45

5




Formula 6-46

10




Formula 6-47

20




Formula 6-48

25




Formula 6-49

30




Formula 6-50

40




Formula 6-51

45



Formula 6-52

55



Formula 6-53

60

65

Formula 6-54

Formul 6-55

Formula 6-56

Formula 6-57

Formula 6-58








Formula 6-59

Formula 6-60

Formula 6-61

25

-continued




26

-continued


Formula 6-62

5




Formula 6-63

10




Formula 6-64

20




Formula 6-65

30



Formula 6-66

40




Formula 6-67

50

55

Formula 6-68

60



65

Formula 6-69

Formula 6-70

Formula 6-71







Formula 6-72

Formula 6-73

Formula 6-74

27


-continued

**28**

-continued

Formula 6-75


5



10

Formula 6-76


15



20

Formula 6-77


25



30

Formula 6-78

35




40

45

Formula 6-79

50



55

Formula 6-80

60

65

Formula 6-81

Formula 6-82









Formula 6-83

Formula 6-84

Formula 6-85

29


-continued



30


-continued

Formula 6-86




10

Formula 6-87




20

Formula 6-88




Formula 6-89




35

Formula 6-90




Formula 6-91




50

Formula 6-92



Formula 6-93



65

Formula 6-94

Formula 6-95

Formula 6-96

Formula 6-97









Formula 6-98

Formula 6-99

Formula 6-100

31

-continued




32

-continued

Formula 6-101


5



Formula 6-102


10

15




Formula 6-103

20




25



Formula 6-104


30



Formula 6-105

35


40



Formula 6-106


45

50



Formula 6-107

55



Formula 6-108

60

65

Formula 6-109

Formula 6-110

Formula 10-1

Formula 10-2

Formula 10-3

Formula 10-4





Formula 10-5

Formula 10-6

Formula 10-7

33

-continued



In Formulae 6-1 to 6-110 and 10-1 to 10-11, Ph indicates a phenyl group and * indicates a binding site to a neighboring atom.

In an implementation, Ar_1 may be, e.g., a group represented by one of Formulae 6-1 to 6-3, 6-22, 6-23, 6-36, 6-44, 6-56, 6-64, 6-76, 6-84, 6-96, 6-103 to 6-105, and 6-107 to 6-110 or a group represented by one of Formulae 10-1 to 10-3, 10-6, and 10-8 to 10-11.

In an implementation, in Formula 1, at least one of R_1 , R_5 , R_7 , and R_{11} may be a group represented by Formula 2.

In an implementation, at least one of R_2 and R_8 may be a substituted or unsubstituted C_1 - C_{60} alkyl group.

In an implementation, R_3 , R_4 , R_6 , R_9 , R_{10} , and R_{12} may each be hydrogen.

In an implementation, in Formula 1, i) R_1 , R_5 , and R_7 may each be a group represented by Formula 2, R_2 and R_8 may each be a substituted or unsubstituted C_1 - C_{60} alkyl group, and R_3 , R_4 , R_6 , R_9 , R_{10} , R_{11} , and R_{12} may each be hydrogen.

In an implementation R_1 , R_5 , R_7 , and R_{11} may each be a group represented by Formula 2, R_2 and R_8 may each be a substituted or unsubstituted C_1 - C_{60} alkyl group, and R_3 , R_4 , R_6 , R_9 , R_{10} , and R_{12} may each be hydrogen.

In an implementation R_1 and R_7 may each be a group represented by Formula 2, R_2 and R_8 may each be a substituted or unsubstituted C_1 - C_{60} alkyl group, and R_3 , R_4 , R_5 , R_6 , R_9 , R_{10} , R_{11} , and R_{12} may each be hydrogen.

In an implementation, the condensed cyclic compound represented by Formula 1 may be one of the following Compounds 1 to 138.

34

Formula 10-8

5

10

Formula 10-9

15

Formula 10-10

20

25

Formula 10-11

30

35

40






45

50

55





60

65







35

-continued





**36**

-continued








37

-continued






**38**

-continued







39





-continued

**40**

-continued








-continued



-continued

35






39

5

10

15

40




20

25

30


41 35



40

45


50
42



55


60

65




43


44



45




46



45

-continued




47

5

10

15

48




20

25

30

49




35

40

45

50



50


55

60


65

46


-continued




51



52







53







54

47

-continued





**48**

-continued







49

-continued





**50**

-continued






51

-continued


**52**

-continued



53

-continued




78

5

10

15

20


25
79

40

45

50


80



65

54

-continued




81

25

79

82



30


35

40

45

50

80



55

60


65

83

55

-continued

84



5

10

15

20

25


85

30

35

40

45




86 50

55


60

65

**56**


-continued

87




25

88




45

89



57

-continued



90

5


10

15

20

58

-continued



93


25

30

35

40

45




94

50


55

60

65




92



95

59

-continued



60

-continued

96

5

10

15

20

25

30

35

40

97


45

50



55

60

65




98



99

61

-continued



62

-continued

100

102

5

10

15


20

25

30

35

40



45

103



101

50

55


60

65



63

-continued



64

-continued

104

106

5

10

15


20

25

30

35

40



105

107



45

50

55


60

65



65

-continued



66

-continued

108

110

5

10

15

20

25

30

35

40

109




45

50

55

60




65



111

67



-continued

**68**


-continued

112

115




113



50


114



65

69

-continued




5

10

15

120




20

25

30

121 35




40

45

50

122




55

60


65

70


-continued




123



124







125







126

71

-continued


**72**

-continued




73


-continued




135



136



137



138

The condensed cyclic compound may have a structure of Formula 1 (including a group represented by Formula 2). For example, one or more substituents other than hydrogen

74

may be included in the condensed cyclic compound, electron mobility may increase with an increase in a conjugation length, and heat resistance characteristics may be improved with an increase in a molecular weight.

5 In an implementation, the condensed cyclic compound may include two heteroatoms in a core and may have a planar structure, and it may be expected that an intermolecular interaction will increase such that electron injection and transport characteristics are improved.

10 A synthesis method for the condensed cyclic compound represented by Formula 1 may be apparent to those of ordinary skill in the art by referring to the following examples.

At least one condensed cyclic compound represented by Formula 1 may be used or included between a pair of electrodes constituting an organic light-emitting device. For example, the condensed cyclic compound may be included in at least one layer in a hole transport region, an electron transport region, or an emission layer. In an implementation, the condensed cyclic compound of Formula 1 may be used as a material for a capping layer located outside a pair of electrodes of an organic light-emitting device.

According to another aspect of embodiments, an organic light-emitting device may include: a first electrode, a second electrode, and an organic layer between the first electrode and the second electrode, the organic layer including an emission layer and at least one heterocyclic compound represented by Formula 1 described above.

The expression “(an organic layer) includes at least one condensed cyclic compound” used herein may include a case in which “(an organic layer) includes identical compounds represented by Formula 1” and a case in which “(an organic layer) includes two or more different condensed cyclic compounds.”

35 In an implementation, the first electrode is an anode, and the second electrode is a cathode, and the organic layer further a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode, and the hole transport region includes a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or any combination thereof, and the electron transport region includes a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or any combination thereof.

In an implementation, the electron transport region may include at least one condensed cyclic compound described above.

The emission layer may include a host, and the host of the emission layer may include at least one selected from an anthracene-based compound, a pyrene-based compound, and a spiro-bifluorene-based compound.

The emission layer may include a dopant, and the dopant of the emission layer may include at least one selected from a styryl-based compound and an amine-based compound.

In an implementation, the emission layer of the organic light-emitting device may be a first emission layer for emitting first color light.

In an implementation, the organic light-emitting device may include i) at least one second emission layer for emitting second color light or ii) at least one second emission layer for emitting second color light and at least one third emission layer for emitting third color light, between the first electrode and the second electrode.

In an implementation, a maximum emission wavelength of the second emission layer for emitting first color light, a maximum emission wavelength of the second emission layer

for emitting second color light, and a maximum emission wavelength of the third emission layer for emitting third color light are identical to or different from each other.

In an implementation, the first color light and the second color light are emitted in the form of mixed light, or the first color light, the second color light, and the third color light are emitted in the form of mixed light.

In an implementation, the organic light-emitting device may further include at least one selected from a first capping layer disposed in a pathway along which light generated in an emission layer proceeds toward the outside through the first electrode and a second capping layer disposed in a pathway along which light generated in an emission layer proceeds toward the outside through the second electrode, and the at least one selected from the first capping layer and the second capping layer may include at least one condensed cyclic compound represented by Formula 1.

In an implementation, the organic light-emitting device may have i) a stack structure including a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order, ii) a stack structure including a first capping layer, a first electrode, an organic layer, and a second electrode which are sequentially stacked in this stated order, or iii) a stack structure including a first capping layer, a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order, and at least one selected from the first capping layer and the second capping layer may include the condensed cyclic compound.

The term “organic layer” used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[Description of FIGS. 1 and 2]

FIG. 1 illustrates a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

FIG. 2 illustrates a schematic view of an organic light-emitting device 20 according to an embodiment. The organic light-emitting device 20 may include the first electrode 110, the organic layer 150 including a hole transport region 150a, an emission layer 150b, and an electron transport region 150c, and a second electrode 190.

Hereinafter, the structure of each of the organic light-emitting devices 10 and 20 according to embodiments and a method of manufacturing the same will be described in connection with FIGS. 1 and 2.

[First Electrode 110]

Referring to FIGS. 1 to 2, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a plastic substrate, each having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for a first electrode may be selected from materials with a high work function to facilitate hole injection.

The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. When the first electrode 110 is a transmissive electrode, a material for forming a first electrode may be selected from indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO₂), zinc oxide (ZnO), and any combinations thereof. In an implementation, when the first electrode 110 is a semi-transmissive electrode or a reflectable electrode, a material for forming a first electrode may be selected from magnesium (Mg), silver (Ag), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), and any combinations thereof.

The first electrode 110 may have a single-layered structure, or a multi-layered structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO.

[Organic Layer 150]

The organic layer 150 is disposed on the first electrode 110. The organic layer 150 may include the emission layer 150b.

The organic layer 150 may further include the hole transport region 150a between the first electrode 110 and the emission layer 150b, and the electron transport region 150c between the emission layer 150b and the second electrode 190.

[Hole Transport Region 150a in Organic Layer 150]


The hole transport region 150a may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The hole transport region 150a may include at least one layer selected from a hole injection layer (HIL), a hole transport layer (HTL), an emission auxiliary layer, and an electron blocking layer (EBL).


For example, the hole transport region 150a may have a single-layered structure including a single layer including a plurality of different materials, or a multi-layered structure having a hole injection layer/hole transport layer structure, a hole injection layer/hole transport layer/emission auxiliary layer structure, a hole injection layer/emission auxiliary layer structure, a hole transport layer/emission auxiliary layer structure, or a hole injection layer/hole transport layer/electron blocking layer structure, wherein for each structure, constituting layers are sequentially stacked from the first electrode 110 in this stated order.

The hole transport region 150a may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB (NPB), β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated-NPB, TAPC, HMTDP, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), polyaniline/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:


77



m-MTDATA




TDATA





2-TNATA

78


-continued




NPB

 β -NPB


TPD



Spiro-TPD




Spiro-NPB




methylated NPB

79


-continued




TAPC



HMTDP



<Formula 201>



<Formula 202>

In Formulae 201 and 202,

L_{201} to L_{204} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

L_{205} may be selected from $^*\text{—O—}^*$, $^*\text{—S—}^*$, $^*\text{—N—}^*$, $^*\text{—Q}_{201}\text{—}^*$, a substituted or unsubstituted C_1 - C_{20} alkylene group, a substituted or unsubstituted C_2 - C_{20} alkenylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

80

cloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

xa1 to xa4 may each independently be an integer from 0 to 3,

xa5 may be an integer from 1 to 10,

R_{201} to R_{204} and Q_{201} may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

For example, in Formula 202, R_{201} and R_{202} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group, and R_{203} and R_{204} may optionally be linked via a single bond, a dimethyl-methylene group, or a diphenyl-methylene group.

In one or more embodiments, in Formulae 201 and 202,

L_{201} to L_{205} may each independently be selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylene group, a dibenzofuranylenylene group, a dibenzothiophenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylene group, and a pyridinylenylene group;

a phenylene group, a pentalenylene group, an indenylene group, a naphthalenylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylenylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a thiophenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group,

group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, and a pyridinylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂); and

Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, xa1 to xa4 may each independently be 0, 1, or 2.

In one or more embodiments, xa5 may be 1, 2, 3, or 4.

In one or more embodiments, R₂₀₁ to R₂₀₄ and Q₂₀₁ may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a

picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —N(Q₃₁)(Q₃₂); and

Q₃₁ to Q₃₃ may be the same as described above.

In one or more embodiments, at least one selected from R₂₀₁ to R₂₀₃ in Formula 201 may each independently be selected from:

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a benzothiophenyl group; and

a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a benzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a benzothiophenyl group.

In one or more embodiments, in Formula 202, i) R₂₀₁ and R₂₀₂ may be linked via a single bond, and/or ii) R₂₀₃ and R₂₀₄ may be linked via a single bond.

In one or more embodiments, at least one selected from R₂₀₁ to R₂₀₄ in Formula 202 may be selected from:

a carbazolyl group; and


a carbazolyl group, substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino

83

group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.


The compound represented by Formula 201 may be represented by Formula 201A:

<Formula 201A>




In an implementation, the compound represented by Formula 201 may be represented by Formula 201A(1) below:

<Formula 201A(1)>



In an implementation, the compound represented by Formula 201 may be represented by Formula 201A-1:


<Formula 201A-1>



84


In an implementation, the compound represented by Formula 202 may be represented by Formula 202A:

<Formula 202A>



In an implementation, the compound represented by Formula 202 may be represented by Formula 202A-1:

<Formula 202A-1>



In Formulae 201A, 201A(1), 201A-1, 202A, and 202A-1,

L₂₀₁ to L₂₀₃, xa1 to xa3, xa5, and R₂₀₂ to R₂₀₄ are the same as described above,


R₂₁₁ and R₂₁₂ may be understood by referring to the description provided herein in connection with R₂₀₃.

R₂₁₃ to R₂₁₇ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a phenyl group substituted with a C₁-C₁₀ alkyl group, a phenyl group substituted with —F, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group.

In an implementation, the hole transport region 150a may include at least one compound selected from Compounds HT1 to HT39:


85

HT1




86


HT2



HT3




HT4




87

-continued
HT5




88


HT6



HT7




HT8




89

-continued
HT9




90


HT10




HT11



HT12




91

-continued
HT13



92

HT14





HT15

HT16



HT17

HT18





93

94

-continued



HT19

HT20



HT21

HT22




95

96



-continued

HT23





HT24

HT25



HT26

HT27





97

98

-continued



HT28

HT29





HT30

HT31





HT32

HT33



HT34

HT35





99

100



-continued
HT36

HT37



HT38

HT39



A thickness of the hole transport region **150a** may be in a range of about 100 Å to about 10,000 Å, for example, about 100 Å to about 1,000 Å. When the hole transport region **150a** includes at least one selected from a hole injection layer and a hole transport layer, the thickness of the hole injection layer may be in a range of about 100 Å to about 9,000 Å, and for example, about 100 Å to about 1,000 Å, and the thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, and for example, about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region **150a**, the hole injection layer and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

The emission auxiliary layer may increase light-emission efficiency by compensating for an optical resonance distance according to the wavelength of light emitted by an emission layer, and the electron blocking layer may block the flow of electrons from an electron transport region. The emission auxiliary layer and the electron blocking layer may include the materials as described above.

[p-Dopant]

The hole transport region **150a** may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region **150a**.

The charge-generation material may be, for example, a p-dopant.

In one or more embodiments, a lowest unoccupied molecular orbital (LUMO) energy level of the p-dopant may be -3.5 eV or less.

In an implementation, the p-dopant may include at least one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound.

For example, the p-dopant may include at least one selected from:


- a quinone derivative, such as tetracyanoquinodimethane (TCNQ) and 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4-TCNQ);

- a metal oxide, such as tungsten oxide or molybdenum oxide;

101

1,4,5,8,9,11-hexaazatriphenylene-hexacarbonitrile (HAT-CN); and

a compound represented by Formula 221 below:



In Formula 221,

R₂₂₁ to R₂₂₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, provided that at least one selected from R₂₂₁ to R₂₂₃ has at least one substituent selected from a cyano group, —F, —Cl, —Br, —I, a C₁-C₂₀ alkyl group substituted with —F, a C₁-C₂₀ alkyl group substituted with —Cl, a C₁-C₂₀ alkyl group substituted with —Br, and a C₁-C₂₀ alkyl group substituted with —I.

[Emission Layer 150b in Organic Layer 150]

When the organic light-emitting device 10 is a full-color organic light-emitting device, the emission layer 150b may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub-pixel. In one or more embodiments, the emission layer 150b may have a stacked structure of two or more layers selected from a red emission layer, a green emission layer, and a blue emission layer, in which the two or more layers contact each other or are separated from each other. In an implementation, the emission layer may include two or more materials selected from a red light-emitting material, a green light-emitting material, and a blue light-emitting material, in which the two or more materials are mixed with each other in a single layer to emit white light.

The emission layer 150b may include a host and a dopant. The dopant may include at least one selected from a phosphorescent dopant and a fluorescent dopant.


An amount of the dopant in the emission layer 150b may be, in general, in a range of about 0.01 parts by weight to about 15 parts by weight based on 100 parts by weight of the host.

102

A thickness of the emission layer 150b may be in a range of about 100 Å to about 1,000 Å, for example, about 200 Å to about 600 Å. When the thickness of the emission layer 150b is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[Host in Emission Layer 150b]

In an implementation, the host may further include a compound represented by Formula 301:



In Formula 301,

Ar₃₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group,

xb11 may be 1, 2, or 3,

L₃₀₁ is selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

xb1 may be an integer from 0 to 5,

R₃₀₁ may be selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₃₀₁)(Q₃₀₂)(Q₃₀₃), —N(Q₃₀₁)(Q₃₀₂), —B(Q₃₀₁)(Q₃₀₂), —C(=O)(Q₃₀₁), —S(=O)₂(Q₃₀₁), and —P(=O)(Q₃₀₁)(Q₃₀₂),

xb21 may be an integer from 1 to 5, and

Q₃₀₁ to Q₃₀₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, Ar₃₀₁ in Formula 301 may be selected from:

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, and a dibenzothio-phenene group;

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoan-


103

thracene group, a dibenzofuran group, and a dibenzothio-
 phene group, each substituted with at least one selected from
 deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano
 group, a nitro group, an amidino group, a hydrazino group,
 a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy
 group, a phenyl group, a biphenyl group, a terphenyl group,
 a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂),
 —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂(Q₃₁), and
 —P(=O)(Q₃₁)(Q₃₂); and


Q₃₁ to Q₃₃ may each independently be selected from a
 C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group,
 a biphenyl group, a terphenyl group, and a naphthyl group.

When xb11 in Formula 301 is two or more, two or more
 of Ar₃₀₁(s) may be linked via a single bond.

In an implementation, the compound represented by For-
 mula 301 may be represented by Formula 301-1 or 301-2:



<Formula 301-1>



<Formula 301-2>

In Formulae 301-1 and 301-2,

A₃₀₁ to A₃₀₄ may each independently be selected from a
 benzene group, a naphthalene group, a phenanthrene group,
 a fluoranthene group, a triphenylene group, a pyrene group,
 a chrysene group, a pyridine group, a pyrimidine group, an
 indene group, a fluorene group, a spiro-bifluorene group, a
 benzofluorene group, a dibenzofluorene group, an indole
 group, a carbazole group, a benzocarbazole group, a diben-
 zocarbazole group, a furan group, a benzofuran group, a
 dibenzofuran group, a naphthofuran group, a benzonaphtho-
 furan group, a dinaphthofuran group, a thiophene group, a
 benzothiophene group, a dibenzothiophene group, a naph-
 thothiophene group, a benzonaphthothiophene group, and a
 dinaphthothiophene group,

X₃₀₁ may be O, S, or N—[(L₃₀₄)_{xb4}—R₃₀₄],

R₃₁₁ to R₃₁₄ may each independently be selected from
 hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl
 group, a cyano group, a nitro group, an amidino group, a
 hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group,
 a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a
 terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃),
 —N(Q₃₁)(Q₃₂), —B(Q₃₁)(Q₃₂), —C(=O)(Q₃₁), —S(=O)₂
 (Q₃₁), and —P(=O)(Q₃₁)(Q₃₂),

xb22 and xb23 may each independently be 0, 1, or 2,

L₃₀₁, xb1, R₃₀₁, and Q₃₁ to Q₃₃ may be the same as
 described above,

L₃₀₂ to L₃₀₄ may each independently be the same as
 described in connection with L₃₀₁,

104

xb2 to xb4 may each independently be the same as
 described in connection with xb1,

R₃₀₂ to R₃₀₄ may each independently be the same as
 described in connection with R₃₀₁.

For example, L₃₀₁ to L₃₀₄ in Formulae 301, 301-1, and
 301-2 may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene
 group, a spiro-bifluorenylene group, a benzofluorenylene
 group, a dibenzofluorenylene group, a phenanthrenylene
 group, an anthracenylene group, a fluoranthenylene group, a
 triphenylenylene group, a pyrenylene group, a chrysenedylene
 group, a perylenylene group, a pentaphenylenylene group, a
 hexacenylenylene group, a pentacenylenylene group, a thiophe-
 nylenylene group, a furanylenylene group, a carbazolylenylene group, an
 indolylenylene group, an isoindolylenylene group, a benzofura-
 nylenylene group, a benzothiophenylenylene group, a dibenzofura-

nylenylene group, a dibenzothiophenylenylene group, a benzocarpa-
 zolylenylene group, a dibenzocarbazolylenylene group, a
 dibenzosilolylenylene group, a pyridinylenylene group, an imida-
 zolylenylene group, a pyrazolylenylene group, a thiazolylenylene group,
 an isothiazolylenylene group, an oxazolylenylene group, an isox-
 azolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene
 group, a pyrazinylenylene group, a pyrimidinylenylene group, a
 pyridazinylenylene group, a triazinylenylene group, a quinolinylenylene
 group, an isoquinolinylenylene group, a benzoquinolinylenylene group,
 a phthalazinylenylene group, a naphthyridinylenylene group,
 a quinoxalinylenylene group, a quinazolinylenylene group, a cinnol-
 inylenylene group, a phenanthridinylenylene group, an acridinylenylene
 group, a phenanthrolinylenylene group, a phenazinylenylene group,
 a benzimidazolylenylene group, an isobenzothiazolylenylene group,
 a benzoxazolylenylene group, an isobenzoxazolylenylene group, a
 triazolylenylene group, a tetrazolylenylene group, an imidazopyridi-
 nylenylene group, an imidazopyrimidinylenylene group, and an
 azacarbazolylenylene group;

a phenylene group, a naphthylene group, a fluorenylene
 group, a spiro-bifluorenylene group, a benzofluorenylene
 group, a dibenzofluorenylene group, a phenanthrenylene
 group, an anthracenylene group, a fluoranthenylene group, a
 triphenylenylene group, a pyrenylene group, a chrysenedylene
 group, a perylenylene group, a pentaphenylenylene group, a
 hexacenylenylene group, a pentacenylenylene group, a thiophe-
 nylenylene group, a furanylenylene group, a carbazolylenylene group, an
 indolylenylene group, an isoindolylenylene group, a benzofura-
 nylenylene group, a benzothiophenylenylene group, a dibenzofura-
 nylenylene group, a dibenzothiophenylenylene group, a benzocarpa-

zolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalynyl group, a quinazolynyl group, a cinnolynyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}); and

Q_{31} and Q_{33} may be the same as described above.

In an implementation, R_{301} to R_{304} in Formulae 301, 301-1, and 301-2 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl

group, a naphthyridinyl group, a quinoxalynyl group, a quinazolynyl group, a cinnolynyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group; and


a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalynyl group, a quinazolynyl group, a cinnolynyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolynyl group, an isoquinolynyl group, a benzoquinolynyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalynyl group, a quinazolynyl group, a cinnolynyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, an azacarbazolyl group, —Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}); and

Q_{31} and Q_{33} may be the same as described above.


107

In an implementation, the host may include an alkaline earth metal complex. For example, the host may be selected from a Be complex (for example, Compound H55), a Mg complex, and a Zn complex.


In an implementation, the host may include at least one selected from 9,10-di(2-naphthyl)anthracene (ADN), 2-methyl-9,10-bis(naphthalen-2-yl)anthracene (MADN), 9,10-di-(2-naphthyl)-2-t-butyl-anthracene (TBADN), 4,4'-bis(N-carbazolyl)-1,1'-biphenyl (CBP), 1,3-di-9-carbazolyl-benzene (mCP), 1,3,5-tri(carbazol-9-yl)benzene (TCP), and Compounds H1 to H55:




H1 15




H2 25



H3 35



H4 45




H5 55

108

-continued


H6



5


10

H7




20

H8




30

H9




40

H10



50


H11



60

65

109
-continued




H12

5

10

H13


15



20

25


H14



30

35


H15




40

45


50




110
-continued




H17




H18



H19



H20



H21


H16

55

60

65

111
-continued



H22

5

10

15

20

H23

25

30

35

40

45



H24

50


55

60


65




112
-continued



H25







H26



H27

113


-continued

**114**

-continued


H28

H32




H33

H29




H34




H35

H30




H36

H31




115
-continued




H37


116
-continued




H40




H38



H41







H39



H42

117

-continued

**118**

-continued

H43

H47

5

10

15

20

H44

H48

25

30

H45

H50

35

40

45

H46

50







H51

55

H52




60

65





119

-continued



[Phosphorescent Dopant Included in Emission Layer 150b in Organic Layer 150]

The phosphorescent dopant may include an organometallic complex represented by Formula 401:



120

In Formulae 401 and 402,

H53 M may be selected from iridium (Ir), platinum (Pt), palladium (Pd), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), rhodium (Rh), and thulium (Tm),

5 L_{401} may be selected from ligands represented by Formula 402, and $xc1$ may be 1, 2, or 3, wherein, when $xc1$ is two or more, two or more $L_{401}(s)$ may be identical to or different from each other,

10 L_{402} may be an organic ligand, and $xc2$ may be an integer from 0 to 4, wherein, when $xc2$ is two or more, two or more $L_{402}(s)$ may be identical to or different from each other,

H54 X_{401} to X_{404} may each independently be nitrogen or carbon,

15 X_{401} and X_{403} may be linked via a single bond or a double bond, and X_{402} and X_{404} may be linked via a single bond or a double bond,

A_{401} and A_{402} may each independently be selected from a C_5 - C_{60} carbocyclic group or a C_1 - C_{60} heterocyclic group,

20 X_{405} may be a single bond, $*-O-*$, $*-S-*$, $*-C(=O)-*$, $*-N(Q_{411})-*$, $*-C(Q_{411})(Q_{412})-*$, $*-C(Q_{411})=C(Q_{412})-*$, $*-C(Q_{411})=*$, or $*=C=*$, Q_{411} and Q_{412} may be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group,

25 X_{406} may be a single bond, O, or S,

H55 R_{401} and R_{402} may each independently be selected from hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{20} alkyl group, a substituted or unsubstituted C_1 - C_{20} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q)(Q_{402})(Q_{403})$, $-N(Q_{401})(Q_{402})$, $-B(Q_{401})(Q_{402})$, $-C(=O)(Q_{401})$, $-S(=O)_2(Q_{401})$, and $-P(=O)(Q_{401})(Q_{402})$, and Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a C_6 - C_{20} aryl group, and a C_1 - C_{20} heteroaryl group,

30 $xc11$ and $xc12$ may each independently be an integer from 0 to 10, and

<Formula 401>

<Formula 402>

* and *' in Formula 402 each indicate a binding site to May be in Formula 401.

In one or more embodiments, A_{401} and A_{402} in Formula 402 may each independently be selected from a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, an indene group, a pyrrole group, a thiophene group, a furan group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a quinoxaline group, a quinazoline group, a carbazole group, a benzimidazole group, a benzofuran group, a benzothiophene group, an isobenzothiophene group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, a dibenzofuran group, and a dibenzothiophene group.

121

In one or more embodiments, in Formula 402, i) X_{401} may be nitrogen, and X_{402} may be carbon, or ii) X_{401} and X_{402} may each be nitrogen at the same time.

In one or more embodiments, R_{402} and R_{402} in Formula 401 may each independently be selected from:

hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a phenyl group, a naphthyl group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, and a norbornenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, an adamantanyl group, a norbornanyl group, a norbornenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

—Si(Q_{401})(Q_{402})(Q_{403}), —N(Q_{401})(Q_{402}), —B(Q_{401})(Q_{402}), —C(=O)(Q_{401}), —S(=O)₂(Q_{401}), and —P(=O)(Q_{401})(Q_{402}); and

Q_{401} to Q_{403} may each independently be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, and a naphthyl group.

In one or more embodiments, when xc1 in Formula 401 is two or more, two A_{401} (s) in two or more L_{401} (s) may optionally be linked via X_{407} , which is a linking group, or two A_{402} (s) in two or more L_{401} (s) may optionally be linked via X_{408} , which is a linking group (see Compounds PD1 to PD4 and PD7). X_{407} and X_{408} may each independently be a single bond, *—O—*, *—S—*, *—C(=O)—*, *—N(Q_{413})*, *—C(Q_{413})(Q_{414})*, or *—C(Q_{413})=C(Q_{414})* (wherein Q_{413} and Q_{414} may each independently be hydrogen, deuterium, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group).


L_{402} in Formula 401 may be a monovalent, divalent, or trivalent organic ligand. For example, L_{402} may be selected from halogen, diketone (for example, acetylacetonate), car-

122


boxylic acid (for example, picolinate), —C(=O), isonitrile, —CN, and phosphorus containing material (for example, phosphine, or phosphite).

In an implementation, the phosphorescent dopant may be selected from, for example, Compounds PD1 to PD25:


PD1




PD2



PD3









PD4



123

-continued

**124**

-continued

PD5

5

10

PD6

15

20

PD7

25

30

PD8

35

40

PD9

45

50

PD10

55

60

65






PD11

PD12

PD13






PD14

PD15



125

-continued

**126**

-continued

PD16

5

10

PD17

15

20

PD18

25

30

PD19

35

40

45





50

PD20

55

60

65



PD21


PD22

PD23

PD24

127

-continued




PD25

[Fluorescent Dopant in Emission Layer 150b]

The fluorescent dopant may include an arylamine compound or a styrylamine compound.

The fluorescent dopant may include a compound represented by Formula 501:



<Formula 501>

In Formula 501,

Ar₅₀₁ may be a substituted or unsubstituted C₅-C₆₀ carbocyclic group or a substituted or unsubstituted C₁-C₆₀ heterocyclic group.

L₅₀₁ to L₅₀₃ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.

xd1 to xd3 may each independently be an integer from 0 to 3;

R₅₀₁ and R₅₀₂ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and

xd4 may be an integer from 1 to 6.

In one or more embodiments, Ar₅₀₁ in Formula 501 may be selected from:

a naphthalene group, a heptalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene

128

group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group; and

- a naphthalene group, a heptalene group, a fluorene group,
- 5 a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, and an indenophenanthrene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, L₅₀₁ to L₅₀₃ in Formula 501 may each independently be selected from:

- a phenylene group, a naphthylene group, a fluorenylene group,
- 20 a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group; and

- a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a thiophenylenylene group, a furanylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a dibenzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, and a pyridinylenylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazoyl group, an indoyl group, an isoindoyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazoyl group, a dibenzocarbazoyl group, a dibenzosiloyl group, and a pyridinyl group.

In one or more embodiments, R₅₀₁ and R₅₀₂ in Formula 501 may each independently be selected from:

- a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group,
- 65 a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group,

129


a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, and a pyridinyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, and —Si(Q_{31})(Q_{32})(Q_{33}); and

Q_{31} to Q_{33} may be selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In an implementation, xd4 in Formula 501 may be 2.

In an implementation, the fluorescent dopant may be selected from Compounds FD1 to FD22:



FD1

50

55


60

65


130

-continued


FD2



FD3



131
-continued



FD4

5

10

15

20

25

FD5

30

35

40

45

FD6


50

55

60


65

132
-continued




FD7

FD8








FD9







133

-continued


**134**

-continued




135

-continued




FD19




FD20

136

-continued




FD21




FD22


In an implementation, the fluorescent dopant may be selected from the following compounds.



DPVBi




DPAVB



TBP

137

138



[Electron Transport Region **150c** in Organic Layer **150**]

The electron transport region **150c** may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron transport region **150c** may include at least one selected from a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, and an electron injection layer.

In an implementation, the electron transport region **150c** may have an electron transport layer/electron injection layer structure, a hole blocking layer/electron transport layer/electron injection layer structure, an electron control layer/electron transport layer/electron injection layer structure, or a buffer layer/electron transport layer/electron injection layer structure, wherein for each structure, constituting layers are sequentially stacked from the emission layer **150b**.

In an implementation, the electron transport region **150c** may include the condensed cyclic compound represented by Formula 1.

In an implementation, the electron transport region **150c** (for example, a buffer layer, a hole blocking layer, an electron control layer, or an electron transport layer **150c** in the electron transport region) may include a metal-free compound containing at least one π electron-depleted nitrogen-containing ring.


The “ π electron-depleted nitrogen-containing ring” indicates a C_1 - C_{60} heterocyclic group having at least one $*-N=*$ moiety as a ring-forming moiety.

For example, the “ π electron-depleted nitrogen-containing ring” may be i) a 60-membered to 7-membered heteromonocyclic group having at least one $*-N=*$ moiety, ii) a heteropolycyclic group in which two or more 5-membered to 7-membered heteromonocyclic groups each having at least one $*-N=*$ moiety are condensed with each other, or

iii) a heteropolycyclic group in which at least one of 5-membered to 7-membered heteromonocyclic groups, each having at least one $*-N=*$ moiety, is condensed with at least one C_5 - C_{60} carbocyclic group.

Examples of the π electron-depleted nitrogen-containing ring include an imidazole, a pyrazole, a thiazole, an isothiazole, an oxazole, an isoxazole, a pyridine, a pyrazine, a pyrimidine, a pyridazine, an indazole, a purine, a quinoline, an isoquinoline, a benzoquinoline, a phthalazine, a naphthyridine, a quinoxaline, a quinoxaline, a cinnoline, a phenanthridine, an acridine, a phenanthroline, a phenazine, a benzimidazole, an isobenzothiazole, a benzoxazole, an isobenzoxazole, a triazole, a tetrazole, an oxadiazole, a triazine, thiadiazol, an imidazopyridine, an imidazopyrimidine, and an azacarbazole.

For example, the electron transport region **150c** may include a compound represented by Formula 601:



<Formula 601>

In Formula 601,

Ar_{601} may be a substituted or unsubstituted C_5 - C_{60} carbocyclic group or a substituted or unsubstituted C_1 - C_{60} heterocyclic group,

$xe11$ may be 1, 2, or 3,

L_{601} is selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

$xe1$ may be an integer from 0 to 5,

R_{601} may be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubsti-

tuted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₆₀₁)(Q₆₀₂)(Q₆₀₃), —C(=O)(Q₆₀₁), —S(=O)₂(Q₆₀₁), and —P(=O)(Q₆₀₁)(Q₆₀₂),

Q₆₀₁ to Q₆₀₃ may each independently be a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, or a naphthyl group, and xe21 may be an integer from 1 to 5.

In an implementation, at least one of Ar₆₀₁(s) in the number of xe11 and R₆₀₁(s) in the number of xe21 may include the n electron-depleted nitrogen-containing ring.

In an implementation, ring Ar₆₀₁ in Formula 601 may be selected from:

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, a phenanthroline group, a phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group;

a benzene group, a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a dibenzofuran group, a dibenzothiophene group, a carbazole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, an indazole group, a purine group, a quinoline group, an isoquinoline group, a benzoquinoline group, a phthalazine group, a naphthyridine group, a quinoxaline group, a quinazoline group, a cinnoline group, a phenanthridine group, an acridine group, phenanthroline group, phenazine group, a benzimidazole group, an iso-benzothiazole group, a benzoxazole group, an isobenzoxazole group, a triazole group, a tetrazole group, an oxadiazole group, a triazine group, thiadiazol group, an imidazopyridine group, an imidazopyrimidine group, and an azacarbazole group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a

phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —S(=O)₂(Q₃₁), and —P(=O)(Q₃₁)(Q₃₂); and


Q₃₁ to Q₃₃ may each independently be selected from a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

When xe11 in Formula 601 is two or more, two or more Ar₆₀₁(s) may be linked via a single bond.

In an implementation, Ar₆₀₁ in Formula 601 may be an anthracene group.

In an implementation, the compound represented by Formula 601 may be represented by Formula 601-1:

<Formula 601-1>



In Formula 601-1,

X₆₁₄ may be N or C(R₆₁₄), X₆₁₅ may be N or C(R₆₁₅), X₆₁₆ may be N or C(R₆₁₆), and at least one selected from X₆₁₄ to X₆₁₆ may be N,

L₆₁₁ to L₆₁₃ may each independently be the same as described in connection with L₆₀₁,

xe611 to xe613 may each independently be the same as described in connection with xe1,

R₆₁₁ to R₆₁₃ may each independently be the same as described in connection with R₆₀₁,

R₆₁₄ to R₆₁₆ may each independently be selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

In one or more embodiments, L₆₀₁ and L₆₁₁ to L₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylenylene group, a thiophenylenylene group, a furanylenylene group, a carbazolylenylene group, an indolylenylene group, an isoindolylenylene group, a benzofuranylenylene group, a benzothiophenylenylene group, a benzofuranylenylene group, a dibenzothiophenylenylene group, a benzocarbazolylenylene group, a dibenzocarbazolylenylene group, a dibenzosilolylenylene group, a pyridinylenylene group, an imidazolylenylene group, a pyrazolylenylene group, a thiazolylenylene group, an isothiazolylenylene group, an oxazolylenylene group, an isoxazolylenylene group, a thiadiazolylenylene group, an oxadiazolylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a triazinylenylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylenylene group, an acridinylenylene group, a phenanthrolinylenylene group, a phenazinylene group, a benzimidazolylenylene group, an isobenzothiazolylenylene group, a benzoxazolylenylene group, an isobenzoxazolylenylene group, a

triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-bifluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylenylene group, a pentacenylene group, a thiophenylene group, a furanylene group, a carbazolylene group, an indolylene group, an isoindolylene group, a benzofuranylene group, a benzothiophenylene group, a dibenzofuranylene group, a dibenzocarbazolylene group, a dibenzocarbazolylene group, a dibenzosilolylene group, a pyridinylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a thiadiazolylene group, an oxadiazolylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a triazinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzimidazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an imidazopyridinylene group, an imidazopyrimidinylene group, and an azacarbazolylene group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group.

In one or more embodiments, x₁ and x₆₁₁ to x₆₁₃ in Formulae 601 and 601-1 may each independently be 0, 1, or 2.

In one or more embodiments, R₆₀₁ and R₆₁₁ to R₆₁₃ in Formulae 601 and 601-1 may each independently be selected from:

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group,

a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a pyridinyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a thiadiazolyl group, an oxadiazolyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group.



143

group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzimidazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and an azacarbazolyl group;

$-S(=O)_2(Q_{601})$ and $-P(=O)(Q_{601})(Q_{602})$; and

Q_{601} and Q_{602} may be the same as described above.

In an implementation, the electron transport region **150c** may include at least one compound selected from Compounds ET1 to ET36:






5
10
15
20
25
30
35
40
45
50
55
60
65

144

-continued


ET3



145

-continued

ET6




5

10

15

20

ET7




25

30

35

40

ET8



50

55


60

65


146

-continued

ET9




ET10




147
-continued

ET11




148
-continued

ET14




ET12

25




ET15




ET13

50






ET16



149

-continued

**150**

-continued

ET17

5

10

15

20

25

ET18

30

35

40

45

ET19




50

55

60

65

ET20




ET21

ET22

151
-continued

ET23



5


10

15


20

152
-continued

ET26



ET24 25




30

35


40

45

ET27



ET25 50




55

60


65

ET28



153

-continued



ET29

5


10

15

20

154

-continued



ET32

25

ET30


30

35

40

45

ET33



ET31



50

55

60



65

ET34




155

-continued






In an implementation, the electron transport region **150c** may include at least one selected from 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), Alq₃, BAlq, 3-(biphenyl-4-yl)-5-(4-tert-butylphenyl)-4-phenyl-4H-1,2,4-triazole (TAZ), and NTAZ.

Alq₃**156**

-continued

ET35



NTAZ

Thicknesses of the buffer layer, the hole blocking layer, and the electron control layer may each be in a range of about 20 Å to about 1,000 Å, for example, about 30 Å to about 300 Å. When the thicknesses of the buffer layer, the hole blocking layer, and the electron control layer are within these ranges, the electron blocking layer may have excellent electron blocking characteristics or electron control characteristics without a substantial increase in driving voltage.

A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, e.g., about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.


The electron transport region **150c** (for example, the electron transport layer in the electron transport region **150c**) may further include, in addition to the materials described above, a metal-containing material.

The metal-containing material may include at least one selected from alkali metal complex and alkaline earth-metal complex. The alkali metal complex may include a metal ion selected from a Li ion, a Na ion, a K ion, a Rb ion, and a Cs ion, and the alkaline earth-metal complex may include a metal ion selected from a Be ion, a Mg ion, a Ca ion, a Sr ion, and a Ba ion. A ligand coordinated with the metal ion of the alkali metal complex or the alkaline earth-metal complex may be selected from a hydroxy quinoline, a hydroxy isoquinoline, a hydroxy benzoquinoline, a hydroxy acridine, a hydroxy phenanthridine, a hydroxy phenylan oxazole, a hydroxy phenylthiazole, a hydroxy diphenylan oxadiazole, a hydroxy diphenylthiadiazol, a hydroxy phe-


157

nylpyridine, a hydroxy phenylbenzimidazole, a hydroxy phenylbenzothiazole, a bipyridine, a phenanthroline, and a cyclopentadiene.

In an implementation, the metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



ET-D1



ET-D2

The electron transport region **150c** may include an electron injection layer that facilitates injection of electrons from the second electrode **190**. The electron injection layer may directly contact the second electrode **190**.

The electron injection layer may have i) a single-layered structure including a single layer including a single material, ii) a single-layered structure including a single layer including a plurality of different materials, or iii) a multi-layered structure having a plurality of layers including a plurality of different materials.

The electron injection layer may include an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof.

The alkali metal may be selected from Li, Na, K, Rb, and Cs. In an implementation, the alkali metal may be Li, Na, or Cs. In an implementation, the alkali metal may be Li or Cs.

The alkaline earth metal may be selected from Mg, Ca, Sr, and Ba.

The rare earth metal may be selected from Sc, Y, Ce, Tb, Yb, and Gd.

The alkali metal compound, the alkaline earth-metal compound, and the rare earth metal compound may be selected from oxides and halides (for example, fluorides, chlorides, bromides, or iodides) of the alkali metal, the alkaline earth-metal, and the rare earth metal.

In an implementation, the alkali metal compound may be selected from alkali metal oxides, such as Li_2O , Cs_2O , or K_2O , and alkali metal halides, such as LiF, NaF, CsF, KF, LiI, NaI, CsI, or KI. In an implementation, the alkali metal compound may be selected from LiF, Li_2O , NaF, LiI, NaI, CsI, and KI.

In an implementation, the alkaline earth-metal compound may be selected from alkaline earth-metal oxides, such as BaO, SrO, CaO, $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$), or $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$).

158

In an implementation, the alkaline earth-metal compound may be selected from BaO, SrO, and CaO.

In an implementation, the rare earth metal compound may be selected from YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 , and TbF_3 . In an implementation, the rare earth metal compound may be selected from YbF_3 , ScF_3 , TbF_3 , YbI_3 , ScI_3 , and TbI_3 .

In an implementation, the alkali metal complex, the alkaline earth-metal complex, and the rare earth metal complex may include an ion of alkali metal, alkaline earth-metal, and rare earth metal as described above, and a ligand coordinated with a metal ion of the alkali metal complex, the alkaline earth-metal complex, or the rare earth metal complex may be selected from hydroxy quinoline, hydroxy isoquinoline, hydroxy benzoquinoline, hydroxy acridine, hydroxy phenanthridine, hydroxy phenyl oxazole, hydroxy phenylthiazole, hydroxy diphenyl oxadiazole, hydroxy diphenylthiadiazole, hydroxy phenylpyridine, hydroxy phenylbenzimidazole, hydroxy phenylbenzothiazole, bipyridine, phenanthroline, and cyclopentadiene.

The electron injection layer may consist of an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof, as described above. In one or more embodiments, the electron injection layer may further include an organic material. When the electron injection layer further includes an organic material, an alkali metal, an alkaline earth metal, a rare earth metal, an alkali metal compound, an alkaline earth-metal compound, a rare earth metal compound, an alkali metal complex, an alkaline earth-metal complex, a rare earth metal complex, or any combinations thereof may be homogeneously or non-homogeneously dispersed in a matrix including the organic material.

A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, for example, about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[Second Electrode **190**]

The second electrode **190** may be disposed on the organic layer **150** having such a structure. The second electrode **190** may be a cathode which is an electron injection electrode, and in this regard, a material for forming the second electrode **190** may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function.

In an implementation, the second electrode **190** may include at least one selected from lithium (Li), silver (Ag), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), ITO, and IZO. The second electrode **190** may be a transmissive electrode, a semi-transmissive electrode, or a reflective electrode.

The second electrode **190** may have a single-layered structure, or a multi-layered structure including two or more layers.

Hereinbefore, the organic light-emitting device according to an embodiment has been described in connection with FIGS. 1 and 2.

[Capping Layer]

In an implementation, the organic light-emitting device may include a first capping layer, a first electrode, an organic

159

layer, and a second electrode which are sequentially stacked in this stated order. In one or more embodiments, the organic light-emitting device may include a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order. In one or more embodiments, the organic light-emitting device may include a first capping layer, a first electrode, an organic layer, a second electrode, and a second capping layer which are sequentially stacked in this stated order.

Light generated in an emission layer of an organic layer of the organic light-emitting device may be extracted toward the outside through a first electrode, which may be a semi-transmissible electrode or a transmissible electrode, and a first capping layer, or may be extracted toward the outside through a second electrode, which may be a semi-transmissible electrode or a transmissible electrode, and a second capping layer.


The first capping layer and the second capping layer may increase external luminescent efficiency according to the principle of constructive interference.

The first capping layer and the second capping layer may each independently be an organic capping layer including an organic material, an inorganic capping layer including an inorganic material, or a composite capping layer including an organic material and an inorganic material.

At least one selected from the first capping layer and the second capping layer may each independently include at least one material selected from carbocyclic compounds, heterocyclic compounds, amine-based compounds, porphyrine derivatives, phthalocyanine derivatives, a naphthalocyanine derivatives, alkali metal complexes, and alkaline earth-based complexes. The carbocyclic compound, the heterocyclic compound, and the amine-based compound may be optionally substituted with a substituent containing at least one element selected from O, N, S, Se, Si, F, Cl, Br, and I. In one or more embodiments, at least one selected from the first capping layer and the second capping layer may each independently include an amine-based compound.


In one or more embodiments, at least one selected from the first capping layer and the second capping layer may each independently include the compound represented by Formula 201 or the compound represented by Formula 202.

In an implementation, at least one selected from the first capping layer and the second capping layer may each independently include a compound selected from Compounds HT28 to HT33 and Compounds CP1 to CP5.



160

-continued



Layers constituting the hole transport region **150a**, the emission layer **150b**, and layers constituting the electron transport region **150c** may be formed in a certain region by using one or more suitable methods selected from vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, ink-jet printing, laser-printing, and laser-induced thermal imaging.

When layers constituting the hole transport region **150a**, the emission layer **150b**, and layers constituting the electron transport region **150c** are formed by vacuum deposition, for example, the vacuum deposition may be performed at a deposition temperature of about 100° C. to about 500° C., at a vacuum degree of about 10⁻⁸ torr to about 10⁻³ torr, and at a deposition rate of about 0.01 Å/sec to about 100 Å/sec by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

When layers constituting the hole transport region **150a**, the emission layer **150b**, and layers constituting the electron transport region **150c** are formed by spin coating, the spin

coating may be performed at a coating speed of about 2,000 rpm to about 5,000 rpm and at a heat treatment temperature of about 80° C. to about 200° C. by taking into account a material to be included in a layer to be formed, and the structure of a layer to be formed.

[General Definition of Substituents]

The term “C₁-C₆₀ alkyl group” used herein refers to a linear or branched aliphatic saturated hydrocarbon monovalent group having 1 to 60 carbon atoms, and examples thereof include a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The term “C₁-C₆₀ alkylene group” used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

The term “C₂-C₆₀ alkenyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon double bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethenyl group, a propenyl group, and a butenyl group. The term “C₂-C₆₀ alkenylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

The term “C₂-C₆₀ alkynyl group” as used herein refers to a hydrocarbon group having at least one carbon-carbon triple bond in the middle or at the terminus of the C₂-C₆₀ alkyl group, and examples thereof include an ethynyl group, and a propynyl group. The term “C₂-C₆₀ alkynylene group” as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

The term “C₁-C₆₀ alkoxy group” as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and examples thereof include a methoxy group, an ethoxy group, and an isopropoxy group.

The term “C₃-C₁₀ cycloalkyl group” as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms, and examples thereof include a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. The term “C₃-C₁₀ cycloalkylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

The term C₁-C₁₀ heterocycloalkyl group used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and examples thereof include a 1,2,3,4-oxatriazolidinyl group, a tetrahydrofuran group, and a tetrahydrothiophenyl group. The term “C₁-C₁₀ heterocycloalkylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkyl group.

The term C₃-C₁₀ cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one carbon-carbon double bond in the ring thereof and no aromaticity, and examples thereof include a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. The term “C₃-C₁₀ cycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

The term “C₁-C₁₀ heterocycloalkenyl group” as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one carbon-carbon double bond in its ring. Non-limiting examples of the C₁-C₁₀ heterocycloalkenyl group include a 4,5-dihydro-1,2,3,4-oxatriazolyl group, a 2,3-dihydrofuran group, and a 2,3-dihydrothiophenyl group. The term

“C₁-C₁₀ heterocycloalkenylene group” as used herein refers to a divalent group having the same structure as the C₁-C₁₀ heterocycloalkenyl group.

The term “C₆-C₆₀ aryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Non-limiting examples of the C₆-C₆₀ aryl group include a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

The term “C₁-C₆₀ heteroaryl group” as used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. The term “C₁-C₆₀ heteroarylene group” as used herein refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, Si, P, and S as a ring-forming atom, in addition to 1 to 60 carbon atoms. Non-limiting examples of the C₁-C₆₀ heteroaryl group include a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₁-C₆₀ heteroaryl group and the C₁-C₆₀ heteroarylene group each include two or more rings, the rings may be condensed with each other.

The term “C₆-C₆₀ aryloxy group” as used herein refers to —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a C₆-C₆₀ arylthio group used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

The term “monovalent non-aromatic condensed polycyclic group” as used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) having two or more rings condensed with each other, only carbon atoms as ring-forming atoms, and no aromaticity in its entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. The term “divalent non-aromatic condensed polycyclic group,” used herein, refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

The term “monovalent non-aromatic condensed heteropolycyclic group” as used herein refers to a monovalent group (for example, having 1 to 60 carbon atoms) having two or more rings condensed to each other, at least one heteroatom selected from N, O, Si, P, and S, other than carbon atoms, as a ring-forming atom, and no aromaticity in its entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. The term “divalent non-aromatic condensed heteropolycyclic group” as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

The term “C₅-C₆₀ carbocyclic group” as used herein refers to a monocyclic or polycyclic group having 5 to 60 carbon atoms in which a ring-forming atom is a carbon atom only. The C₅-C₆₀ carbocyclic group may be an aromatic carbocyclic group or a non-aromatic carbocyclic group. The C₅-C₆₀ carbocyclic group may be a ring, such as benzene, a monovalent group, such as a phenyl group, or a divalent group, such as a phenylene group. In one or more embodiments, depending on the number of substituents connected to the C₅-C₆₀ carbocyclic group, the C₅-C₆₀ carbocyclic group may be a trivalent group or a quadrivalent group.

The term "C₁-C₆₀ heterocyclic group" as used herein refers to a group having the same structure as the C₁-C₆₀ carbocyclic group, except that as a ring-forming atom, at least one heteroatom selected from N, O, Si, P, and S is used in addition to carbon (the number of carbon atoms may be in a range of 1 to 60).

At least one substituent of the substituted C₅-C₆₀ carbocyclic group, substituted C₁-C₆₀ heterocyclic group, substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted divalent non-aromatic condensed polycyclic group, substituted divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from:

deuterium (-D), -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, -Si(Q₁₁)(Q₁₂)(Q₁₃), -N(Q₁₁)(Q₁₂), -B(Q₁₁)(Q₁₂), -C(=O)(Q₁₁), -S(=O)₂(Q₁₁), and -P(=O)(Q₁₁)(Q₁₂); a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group,

-Si(Q₂₁)(Q₂₂)(Q₂₃), -N(Q₂₁)(Q₂₂), -B(Q₂₁)(Q₂₂), -C(=O)(Q₂₁), -S(=O)₂(Q₂₁), and -P(=O)(Q₂₁)(Q₂₂); -Si(Q₃₁)(Q₃₂)(Q₃₃), -N(Q₃₁)(Q₃₂), -B(Q₃₁)(Q₃₂), -C(=O)(Q₃₁), -S(=O)₂(Q₃₁), and -P(=O)(Q₃₁)(Q₃₂); and

Q₁₁ to Q₁₃, Q₂₁ to Q₂₃ and Q₃₁ to Q₃₃ may each independently be selected from hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

The term "Ph" used herein refers to a phenyl group, the term "Me" used herein refers to a methyl group, the term "Et" used herein refers to an ethyl group, the term "ter-Bu" or "But" used herein refers to a tert-butyl group, and the term "OMe" used herein refers to a methoxy group.

The term "biphenyl group" as used herein refers to "a phenyl group substituted with a phenyl group." In other words, the "biphenyl group" is a substituted phenyl group having a C₆-C₆₀ aryl group as a substituent.

The term "terphenyl group" as used herein refers to "a phenyl group substituted with a biphenyl group." In other words, the "terphenyl group" is a phenyl group having, as a substituent, a C₆-C₆₀ aryl group substituted with a C₆-C₆₀ aryl group.


*, **, and *** used herein, unless defined otherwise, each refer to a binding site to a neighboring atom, e.g., in a corresponding formula.

Hereinafter, a compound according to embodiments and an organic light-emitting device according to embodiments will be described in detail with reference to Synthesis Examples and Examples. The wording "B was used instead of A" used in describing Synthesis Examples refers to that an identical molar equivalent of B was used in place of A.

The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.


EXAMPLE

Synthesis Example 1: Synthesis of Compound 4




165

-continued

**166**

-continued



Synthesis of Intermediate 4-1

2.64 g (10 mmol) of 1,4-dibromo-2,5-dimethylbenzene was dissolved in 30 mL of tetrahydrofuran (THF), and 8 mL of n-butyllithium (2.5 M in hexane) was added thereto at a temperature of -78°C . After 1 hour, 4.08 mL (20 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane was added thereto at the same temperature. The resultant mixture was stirred at ambient temperature for 5 hours. Then, water was added to the resultant mixture, and washing thereof was performed three times using 30 mL of diethyl ether. A washed diethyl ether layer was dried using MgSO_4 and then dried under reduced pressure. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 2.69 g (yield: 75%) of Intermediate 4-1 as a white solid. The obtained compound was identified by LC-MS. $\text{C}_{20}\text{H}_{32}\text{B}_2\text{O}_4$; M^+ 328.1.

Synthesis of Intermediate 4-2

5.37 g (15.0 mmol) of Intermediate 4-1, 2.02 g (10.0 mmol) of 1-bromo-2-nitrobenzene, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$, 0.16 g (0.5 mmol) of tetrabutylammonium bromide (TBAB), and 3.18 g (30.0 mmol) of Na_2CO_3 were dissolved in 60 mL of a mixed solvent of toluene/ethanol/

167

H₂O (volume ratio 3/3/1) and stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature, and an extraction process was performed thereon three times using 60 mL of water and 60 mL of diethyl ether. Then, an organic layer obtained therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 2.82 g (yield: 80%) of Intermediate 4-2. The obtained compound was identified by LC-MS. C₂₀H₂₄BNO₄: M⁺ 353.1.

Synthesis of Intermediate 4-3

3.53 g (10.0 mmol) of Intermediate 4-2, 5.62 g (20.0 mmol) of 1,4-dibromo-2-nitrobenzene, 0.58 g (0.5 mmol) of Pd(PPh₃)₄, 0.16 g (0.5 mmol) of TBAB, and 3.18 g (30.0 mmol) of Na₂CO₃ were dissolved in 60 mL of a mixed solvent of toluene/ethanol/H₂O (volume ratio 3/3/1) and stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature, and an extraction process was performed thereon three times using 60 mL of water and 60 mL of diethyl ether. Then, an organic layer obtained therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 2.99 g (yield: 70%) of Intermediate 4-3. The obtained compound was identified by LC-MS. C₂₀H₁₅BrN₂O₄: M⁺ 426.0.

Synthesis of Intermediate 4-4

4.27 g (10.0 mmol) of Intermediate 4-3, 4.75 g (40 mmol) of tin, and 10 mL (100 mmol, conc. 36.5%) of HCl were dissolved in 60 mL of ethanol and stirred at a temperature of 100° C. for 8 hours. The reaction solution was cooled to ambient temperature and filtered under reduced pressure to obtain a filtrate. 3 g of sodium hydroxide was dissolved in 10 mL of water and added to the filtrate, and an extraction process was performed thereon three times using 60 mL of water and 60 mL of dichloromethane. An organic layer obtained therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 3.30 g (yield: 90%) of Intermediate 4-4. The obtained compound was identified by LC-MS. C₂₀H₁₉BrN₂: M⁺ 366.0.

Synthesis of Intermediate 4-5

3.67 g (10.0 mmol) of Intermediate 4-4 and 13.9 mL (100 mmol) of triethylamine were dissolved in 60 mL of THF, and 3.49 mL (30 mmol) of benzoyl chloride was added thereto at a temperature of 0° C. The resultant mixture was stirred at ambient temperature for 5 hours. Then, water was added to the resultant mixture, and washing thereof was performed three times using 30 mL of diethyl ether. A washed diethyl ether layer was dried using MgSO₄ and then dried under reduced pressure. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.32 g (yield: 75%) of Intermediate 4-5 as a white solid. The obtained compound was identified by LC-MS. C₃₄H₂₇BrN₂O₂: M⁺ 574.1.

168

Synthesis of Intermediate 4-6


5.76 g (10 mmol) of Intermediate 4-5 and 14.2 g (50 mmol) of phosphorus pentoxide were dissolved in 10 mL of POCl₃ and stirred at a temperature of 105° C. for 48 hours. The reaction solution was cooled to ambient temperature and quenched using NaOH. Then, an extraction process was performed thereon three times using 60 mL of water and 60 mL of dichloromethane. An organic layer obtained therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 3.23 g (yield: 60%) of Intermediate 4-6. The obtained compound was identified by LC-MS. C₃₄H₂₃BrN₂: M⁺ 538.1.


Synthesis of Compound 4

5.39 g (10 mmol) of Intermediate 4-6, 3.04 g (10 mmol) of 4,4,5,5-tetramethyl-2-(phenanthren-9-yl)-1,3,2-dioxaborolane, 0.58 g (0.5 mmol) of Pd(PPh₃)₄ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K₂CO₃ were dissolved in 60 mL of a mixed solvent of THF/H₂O (volume ratio of 2/1) and stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer obtained therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.14 g (yield: 65%) of Compound 4. The obtained Compound was identified by MS/FAB and ¹H NMR. C₄₈H₃₂N₂: M⁺ cal.: 636.26, found: 636.16.

¹H NMR (400 MHz, CDCl₃) δ (ppm) 8.93 (d, 1H), 8.64 (d, 1H), 8.55 (d, 1H), 8.42 (d, 1H), 8.23 (s, 1H), 8.07-7.77 (m, 10H), 7.69-7.50 (m, 10H), 7.13 (t, 1H), 2.99 (s, 3H), 2.97 (s, 3H).

Synthesis Example 2: Synthesis of Compound 9







5.39 g (10 mmol) of Intermediate 4-6, 1.23 g (10 mmol) of pyridin-3-ylboronic acid, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80°C . for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 2.95 g (yield: 55%) of Compound 9. The obtained compound was identified by MS/FAB and ^{11}NMR . $\text{C}_{39}\text{H}_{27}\text{N}_3$; M^+ cal.: 537.22, found: 537.12.

$^1\text{H NMR}$ (400 MHz, CDCl_3) δ (ppm) 9.07 (s, 1H), 8.93 (d, 1H), 8.66-8.60 (m, 2H), 8.17-7.85 (m, 9H), 7.67-7.52 (m, 8H), 2.99 (s, 3H), 2.97 (s, 3H).

Synthesis Example 3: Synthesis of Compound 18



Synthesis of Intermediate 18-1

5.39 g (10 mmol) of Intermediate 4-6 was dissolved in 30 mL of THF, and 4 mL of n-butyllithium (2.5 M in hexane) was added thereto at a temperature of -78°C . After 1 hour, 2.04 mL (10 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane was added thereto at the same temperature. The resultant mixture was stirred at ambient temperature for 5 hours. Then, water was added to the resultant mixture, and washing thereof was performed three times using 30 mL of diethyl ether. A layer of the diethyl ether used for the washing was dried using MgSO_4 and then dried under reduced pressure. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.11 g (yield: 70%) of Intermediate 18-1. The obtained compound was identified by LC-MS. $\text{C}_{40}\text{H}_{35}\text{BN}_2\text{O}_2$; M^+ 586.2.

Synthesis of Compound 18


5.86 g (10 mmol) of Intermediate 18-1, 4.22 g (10 mmol) of 7-bromo-9,9-diphenyl-9H-fluorene-2-carbonitrile, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solution of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80°C . for 16 hours. The

171

reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 5.21 g (yield: 65%) of Compound 18. The obtained compound was identified by MS/FAB and ^1H NMR. $\text{C}_{60}\text{H}_{39}\text{N}_3$; M^+ cal.: 801.31, found: 801.21.

^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.93 (d, 1H), 8.43 (d, 1H), 8.19 (s, 1H), 8.06 (d, 1H), 7.99-7.83 (m, 7H), 7.74-7.55 (m, 10H), 7.39-7.28 (m, 6H), 7.15-7.06 (m, 6H), 2.99 (s, 3H), 2.97 (s, 3H).

Synthesis Example 4: Synthesis of Compound 43



Synthesis of Intermediate 43-1

1.47 g (10 mmol) of 4-cyanophenylboronic acid, 3.56 g (15 mmol) of 2,6-dibromopyridine, 0.58 g (0.5 mmol) of

172


$\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80°C . for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 1.81 g (yield: 70%) of Intermediate 43-1. The obtained compound was identified by LC-MS. $\text{C}_{12}\text{H}_7\text{BrN}_2$; M^+ 257.9.

Synthesis of Compound 43

2.59 g (10 mmol) of Intermediate 43-1, 5.86 g (10 mmol) of Intermediate 18-1, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80°C . for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue was separated and purified by silica gel column chromatography to obtain 4.15 g (yield: 65%) of Compound 43. The obtained compound was identified by MS/FAB and ^1H NMR. $\text{C}_{46}\text{H}_{30}\text{N}_4$; M^+ cal.: 638.25, found: 638.15.


^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.93 (d, 1H), 8.84 (d, 1H), 8.64 (s, 1H), 8.44 (d, 1H), 8.33 (d, 2H), 8.06 (d, 1H), 7.99-7.85 (m, 6H), 7.77-7.60 (m, 11H), 2.99 (s, 3H), 2.97 (s, 3H).

Synthesis Example 5: Synthesis of Compound 45



173

-continued



Synthesis of Intermediate 45-1

5.39 g (10 mmol) of Intermediate 4-6 was dissolved in 30 mL of THF, and 4 mL of n-butyl lithium (2.5 M in hexane) was added thereto at a temperature of -78°C . After 1 hour, 1.98 mL (11 mmol) of chlorodiphenylphosphine was added thereto at the same temperature. The resultant mixture was stirred at ambient temperature for 5 hours. Then, water was added to the resultant mixture, and washing thereof was performed three times using 30 mL of diethyl ether. A layer of the diethyl ether used for the washing was dried using MgSO_4 and then dried under reduced pressure. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.52 g (yield: 70%) of Intermediate 45-1. The obtained compound was identified by LC-MS. $\text{C}_{46}\text{H}_{33}\text{N}_2\text{P}$: M^+ 644.2.


Synthesis of Compound 45

6.45 g (10 mmol) of Intermediate 45-1 was dissolved in 50 mL of dichloromethane, and 2 mL of hydrogen peroxide (aqueous solution, 50 wt %) was added thereto. Then, the mixed solution was stirred at ambient temperature for 2 hours. Then, 50 mL of water was added to the mixed solution, and an extraction process was performed thereon three times using 50 mL of dichloromethane. An organic layer collected therefrom was dried by using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 6.28 g (yield: 95%) of Compound 45. The obtained compound was identified by MS/FAB and ^1H NMR. $\text{C}_{46}\text{H}_{33}\text{N}_2\text{OP}$: M^+ cal.: 660.23, found: 660.13.

174


^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.93 (d, 1H), 8.55-8.48 (m, 2H), 8.07-7.60 (m, 18H), 7.52-7.39 (m, 6H), 2.99 (s, 3H), 2.97 (s, 3H).

Synthesis Example 6: Synthesis of Compound 46



175

-continued



46

Synthesis of Intermediate 46-1

5.86 g (10 mmol) of Intermediate 18-1, 4.25 g (15 mmol) of 1-bromo-4-iodobenzene, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80°C . for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using ethyl ether. An organic layer collected therefrom was dried by using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.62 g (yield: 75%) of Compound 46-1. The obtained compound was identified by LC-MS. $\text{C}_{40}\text{H}_{27}\text{BrN}_2$; M^+ 614.1.

Synthesis of Intermediate 46-2

6.16 g (10 mmol) of Intermediate 46-1 was dissolved in 30 mL of THF, and 4 mL of n-butyl lithium (2.5 M in hexane) was added thereto at a temperature of -78°C . After 1 hour, 1.98 mL (11 mmol) of chlorodiphenylphosphine was added thereto at the same temperature. The resultant mixture was stirred at ambient temperature for 5 hours. Then, water was added to the resultant mixture, and washing thereof was performed three times using 30 mL of diethyl ether. A layer of the diethyl ether used for the washing was dried using MgSO_4 and then dried under reduced pressure. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 5.05 g (yield: 70%) of Intermediate 46-2. The obtained compound was identified by LC-MS. $\text{C}_{52}\text{H}_{37}\text{N}_2\text{P}$; M^+ 720.2.

Synthesis of Compound 46


7.21 g (10 mmol) of Intermediate 46-2 was dissolved in 50 mL of dichloromethane and 2 mL of hydrogen peroxide (aqueous solution, 50 wt %). Then, the resultant mixture was stirred at ambient temperature for 2 hours. Then, 50 mL of water was added to the resultant mixture, and an extraction process was performed thereon three times using 50 mL of dichloromethane. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 7.00 g (yield: 95%) of Compound 46. The obtained

176



compound was identified by MS/FAB and ^1H NMR. $\text{C}_{52}\text{H}_{37}\text{N}_2\text{OP}$; M^+ cal.: 736.26, found: 736.16.

^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.93 (d, 1H), 8.57 (d, 1H), 8.06 (d, 1H), 8.00-7.60 (m, 22H), 7.52-7.39 (m, 6H), 2.99 (s, 3H), 2.97 (s, 3H).


Synthesis Example 7: Synthesis of Compound 51



18-1




51-1



51-2

177

-continued



51

Synthesis of Intermediate 51-1

5.86 g (10 mmol) of Intermediate 18-1, 4.25 g (15 mmol) of 1-bromo-5-iodobenzene, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.62 g (yield: 75%) of Compound 51-1. The obtained compound was identified by LC-MS. $\text{C}_{40}\text{H}_{27}\text{BrN}_2$; M^+ 614.1.

Synthesis of Intermediate 51-2

6.16 g (10 mmol) of Intermediate 51-1 was dissolved in 30 mL of THF, and 4 mL of n-butyl lithium (2.5 M in hexane) was added thereto at a temperature of -78° C. After 1 hour, 2.04 mL (10 mmol) of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborolane was added thereto at the same temperature. The resultant mixture was stirred at ambient temperature for 5 hours. Then, water was added to the resultant mixture, and washing thereof was performed three times using 30 mL of diethyl ether. A layer of the diethyl ether used for the washing was dried using MgSO_4 and then dried under reduced pressure. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.64 g (yield: 70%) of Intermediate 51-2. The obtained compound was identified by LC-MS. $\text{C}_{46}\text{H}_{39}\text{BN}_2\text{O}_2$; M^+ 662.3.


178

Synthesis of Compound 51

6.63 g (10 mmol) of Intermediate 51-2, 2.68 g (10 mmol) of 2-chloro-4,6-diphenyl-1,3,5-triazine, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature. Then, 40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. A product obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.79 g (yield: 65%) of Compound 51. The obtained compound was identified by MS/FAB and ^1H NMR. $\text{C}_{52}\text{H}_{37}\text{N}_2\text{O}$; M^+ cal.: 736.26, found: 736.16.

^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.93 (d, 1H), 8.79 (d, 4H), 8.73-8.70 (m, 2H), 8.58 (d, 1H), 8.20 (s, 1H), 8.06 (d, 1H), 7.99-7.85 (m, 7H), 7.67-7.59 (m, 12H), 7.42-7.38 (m, 2H), 2.99 (s, 3H), 2.97 (s, 3H).


Synthesis Example 8: Synthesis of Compound 56



18-1

179

-continued



56

180

40 mL of water was added to the reaction solution, and an extraction process was performed thereon three times using 50 mL of ethyl ether. An organic layer collected therefrom was dried using magnesium sulfate, and a solvent was evaporated therefrom. The residue obtained therefrom was separated and purified by silica gel column chromatography to obtain 4.49 g (yield: 65%) of Compound 51. The obtained compound was identified by MS/FAB and ^1H NMR. $\text{C}_{50}\text{H}_{34}\text{N}_4$: M^+ cal.: 690.28, found: 690.18.


^1H NMR (400 MHz, CDCl_3) δ (ppm) 8.94-8.92 (m, 3H), 8.67 (d, 2H), 8.44 (d, 1H), 8.20 (s, 1H), 8.07-7.84 (m, 12H), 7.67-7.60 (m, 7H), 7.50-7.46 (m, 2H), 2.99 (s, 3H), 2.97 (s, 3H).

Synthesis methods of compounds other than Compounds synthesized according to Synthesis Examples 1 to 8 may be recognized by referring to the synthesis mechanisms and source materials described above.


Example 1

5.86 g (10 mmol) of Intermediate 18-1, 3.11 g (10 mmol) of 3,3'-(5-bromo-1,3-phenylene)dipyridine, 0.58 g (0.5 mmol) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenylphosphine)palladium), and 4.14 g (30 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solvent of THF/ H_2O (volume ratio of 2/1) and stirred at a temperature of 80° C. for 16 hours. The reaction solution was cooled to ambient temperature. Then,

As an anode, a Corning 15 Ω/cm^2 (1,200 Å) ITO glass substrate was cut to a size of 50 mm×50 mm×0.7 mm, then sonicated with isopropyl alcohol and pure water each for 5 minutes, and then cleaned by irradiation with ultraviolet rays and exposure to ozone for 30 minutes, and the resultant glass substrate was provided to a vacuum deposition apparatus.



2-TNATA




ADN

NPB

181

182

-continued



DPAVBi

2-TNATA was vacuum-deposited on the ITO glass substrate to form a hole injection layer having a thickness of 600 Å, and 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB) was vacuum-deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å. 9,10-di-naphthalene-2-yl-anthracene (ADN) a blue fluorescent host, and 4,4'-bis[2-(4-(N,N-diphenylamino)phenyl)vinyl]biphenyl (DPAVBi), a blue fluorescent dopant, were co-deposited on the hole transport layer at a weight ratio of 98:2 to form an emission layer having a thickness of 300 Å.

Then, Compound 4 was deposited on the emission layer to form an electron transport layer having a thickness of 300 Å, LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was vacuum-deposited on the electron transport layer to form a LiF/Al electrode (cathode electrode) having a thickness of 3,000 Å, thereby completing the manufacture of an organic light-emitting device.

The organic light-emitting device showed a driving voltage of 5.05 V, a light emission luminance of 3,020 cd/m², a light emission efficiency of 5.76 cd/A, and a half lifespan (hr @100 mA/cm²) of 273 hours at a current density of 50 mA/cm².

Example 2

An organic light-emitting device of Example 2 was manufactured in the same manner as in Example 1, except that Compound 9 was used instead of Compound 4 in forming the electron transport layer.

Example 3

An organic light-emitting device of Example 3 was manufactured in the same manner as in Example 1, except that Compound 18 was used instead of Compound 4 in forming the electron transport layer.

Example 4

An organic light-emitting device of Example 4 was manufactured in the same manner as in Example 1, except that Compound 43 was used instead of Compound 4 in forming the electron transport layer.

Example 5

An organic light-emitting device of Example 5 was manufactured in the same manner as in Example 1, except that Compound 45 was used instead of Compound 4 in forming the electron transport layer.

Example 6

An organic light-emitting device of Example 6 was manufactured in the same manner as in Example 1, except that Compound 46 was used instead of Compound 4 in forming the electron transport layer.

Example 7


An organic light-emitting device of Example 7 was manufactured in the same manner as in Example 1, except that Compound 51 was used instead of Compound 4 in forming the electron transport layer.

Example 8

An organic light-emitting device of Example 8 was manufactured in the same manner as in Example 1, except that Compound 56 was used instead of Compound 4 in forming the electron transport layer.

Comparative Example 1

An organic light-emitting device of Comparative Example 1 was manufactured in the same manner as in Example 1, except that Alq₃ was used instead of Compound 4 in forming the electron transport layer.



The organic light-emitting device of Comparative Example 1 showed a driving voltage of 7.35 V, a light emission luminance of 2,065 cd/m², a light emission efficiency of 4.13 cd/A, and a half lifespan (hr @100 mA/cm²) of 145 hours at a current density of 50 mA/cm².

183

Comparative Example 2

An organic light-emitting device of Comparative Example 2 was manufactured in the same manner as in Example 1, except that Compound A was used instead of Compound 4 in forming the electron transport layer.


184

The driving voltage, luminance, efficiency (cd/A), and half lifespan of the organic light-emitting devices manufactured according to Examples 1 to 8 and Comparative Examples 1 to 3 were measured at a current density of 50 mA/cm². Results thereof are shown in Table 1.

TABLE 1

	Material	Driving voltage (V)	Current density (mA/cm ²)	Luminance (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @ 100 mA/cm ²)
Example 1	Compound 4	5.80	50	3,050	6.10	Blue	322 hr
Example 2	Compound 9	5.72	50	3,075	6.15	Blue	365 hr
Example 3	Compound 18	5.69	50	3,190	6.38	Blue	335 hr
Example 4	Compound 43	5.65	50	3,175	6.35	Blue	350 hr
Example 5	Compound 45	5.52	50	3,265	6.53	Blue	290 hr
Example 6	Compound 46	5.68	50	3,225	6.45	Blue	300 hr
Example 7	Compound 51	5.56	50	3,310	6.62	Blue	280 hr
Example 8	Compound 56	5.65	50	3,330	6.66	Blue	340 hr
Comparative Example 1	Alq ₃	7.35	50	2,065	4.13	Blue	145 hr
Comparative Example 2	Compound A	6.38	50	2,790	5.58	Blue	250 hr
Comparative Example 3	Compound B	6.53	50	2,825	5.65	Blue	230 hr


<Compound A>



Comparative Example 3

An organic light-emitting device of Comparative Example 3 was manufactured in the same manner as in Example 1, except that Compound B was used instead of Compound 4 in forming the electron transport layer.

<Compound B>




Referring to Table 1, it may be seen that when the Compounds of Examples 1 to 8 were used as electron transport materials, there was a reduction in driving voltage by 1 V or more and excellent I-V-L characteristics having remarkably improved efficiency were shown, as compared to when Alq₃ was used. For example, excellent lifespan improvement effects were shown.

Also, as compared with Comparative Examples 2 and 3 that respectively used Compounds A and B as electron transport materials, driving voltage was reduced and both luminance and lifespan were improved.


For example, when Compounds according to one or more embodiments are used as the electron transport material of the organic light-emitting device, the organic light-emitting device exhibited excellent effects in terms of driving voltage, luminance, efficiency, and lifespan.

185

-continued

**186**

-continued




50 According to one or more embodiments, an organic
45 light-emitting device may have a low driving voltage, high efficiency, and a long lifespan.


55 Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art
60 that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:

1. A condensed cyclic compound represented by Formula 1:



wherein, in Formula 1, R_1 to R_{12} are each independently a group represented by Formula 2, hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group, provided that at least one of R_1 , R_5 , R_7 , and R_{11} is a group represented by Formula 2, and at least two selected from R_1 , R_5 , R_7 , and R_{11} are not hydrogen,



wherein, in Formula 2,

L_1 is a substituted or unsubstituted C_3 - C_{60} carbocyclic group, a substituted or unsubstituted C_1 - C_{60} heterocyclic group, $^*Si(Q_1)(Q_2)^*$, $^*N(Q_1)^*$, $^*B(Q_1)^*$, $^*C(=O)^*$, $^*S(=O)_2^*$, or $^*P(=O)(Q_1)^*$,

a_1 is an integer of 0 to 4, wherein, when a_1 is zero, $^*(L_1)_{a1}^*$ is a single bond, and when a_1 is 2, 3, or 4, the 2, 3, or 4 L_1 (s) are identical to or different from each other,

Ar_1 is a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $^*Si(Q_1)(Q_2)(Q_3)^*$, $^*N(Q_1)(Q_2)^*$, $^*B(Q_1)(Q_2)^*$, $^*C(=O)(Q_1)^*$, $^*S(=O)_2(Q_1)^*$, or $^*P(=O)(Q_1)(Q_2)^*$,

b_1 is an integer of 1 to 4, wherein, when b_1 is 2, 3, or 4, the 2, 3, or 4 Ar_1 (s) are identical to or different from each other,

at least one substituent of the substituted C_3 - C_{60} carbocyclic group, the substituted C_1 - C_{60} heterocyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the

substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $^*Si(Q_{11})(Q_{12})(Q_{13})^*$, $^*N(Q_{11})(Q_{12})^*$, $^*B(Q_{11})(Q_{12})^*$, $^*C(=O)(Q_{11})^*$, $^*S(=O)_2(Q_{11})^*$, and $^*P(=O)(Q_{11})(Q_{12})^*$;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;

a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, $^*Si(Q_{21})(Q_{22})(Q_{23})^*$, $^*N(Q_{21})(Q_{22})^*$, $^*B(Q_{21})(Q_{22})^*$, $^*C(=O)(Q_{21})^*$, $^*S(=O)_2(Q_{21})^*$, and $^*P(=O)(Q_{21})(Q_{22})^*$; and

$^*Si(Q_{31})(Q_{32})(Q_{33})^*$, $^*N(Q_{31})(Q_{32})^*$, $^*B(Q_{31})(Q_{32})^*$, $^*C(=O)(Q_{31})^*$, $^*S(=O)_2(Q_{31})^*$, and $^*P(=O)(Q_{31})(Q_{32})^*$;

Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group.

189

heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryl group substituted with a C₁-C₆₀ alkyl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and

* and *' each indicate a binding site to a neighboring atom.

2. The condensed cyclic compound as claimed in claim 1, wherein:

a1 is an integer of 1 to 4,

L₁ is:

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-bifluorene group, a spiro-benzofluorene-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pyrrole group, a thiophene group, a furan group, a silole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a triazine group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a dibenzosilole group, a carbazole group, a quinoline group, an isoquinoline group, a benzocarbazole group, a dibenzocarbazole group, a benzimidazole group, an imidazopyridine group, or an imidazopyrimidine group;

a benzene group, a pentalene group, an indene group, a naphthalene group, an azulene group, a heptalene group, an indacene group, an acenaphthalene group, a fluorene group, a spiro-bifluorene group, a spiro-benzofluorene-fluorene group, a benzofluorene group, a dibenzofluorene group, a phenalene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pyrrole group, a thiophene group, a furan group, a silole group, an imidazole group, a pyrazole group, a thiazole group, an isothiazole group, an oxazole group, an isoxazole group, a pyridine group, a pyrazine group, a pyrimidine group, a pyridazine group, a triazine group, a benzofuran group, a benzothiophene group, a benzosilole group, a dibenzofuran group, a dibenzothiophene group, a dibenzosilole group, a carbazole group, a quinoline group, an isoquinoline group, a benzocarbazole group, a dibenzocarbazole group, a benzimidazole group, an imidazopyridine group, or an imidazopyrimidine group, each substituted with deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a

190

picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₁)(Q₃₂), or —B(Q₃₁)(Q₃₂); or

—S(=O)₂— and *—P(=O)(Q₁)*,

Q₁ and Q₃₁ to Q₃₃ are each independently a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, or a pyridinyl group, and

* and *' each indicate a binding site to a neighboring atom.

3. The condensed cyclic compound as claimed in claim 1, wherein:

a1 is an integer of 1 to 4,

L₁ is:

a benzene group, a naphthalene group, an anthracene group, a fluorene group, a spiro-bifluorene group, a pyridine group, a pyrimidine group, a triazine group, a carbazole group, a quinoline group, or an isoquinoline group;

a benzene group, a naphthalene group, an anthracene group, a fluorene group, a spiro-bifluorene group, a pyridine group, a pyrimidine group, a triazine group, a carbazole group, a quinoline group, or an isoquinoline group, each substituted with a cyano group, a C₁-C₂₀ alkyl group, a phenyl group, a biphenyl group, a pyridinyl group, or a fluorenyl group; or

—S(=O)₂— or *—P(=O)(Q₁)*,


Q₁ is a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, or a pyridinyl group, and

* and *' each indicate a binding site to a neighboring atom.


4. The condensed cyclic compound as claimed in claim 1, wherein:

a1 is an integer of 1 to 4, and


L₁ is a group represented by one of Formulae 3-1 to 3-31, 3-31', and 3-32 to 3-35:



Formula 3-1












Formula 3-2



Formula 3-3

191

-continued




192

-continued


Formula 3-4

5




Formula 3-5

10




Formula 3-6

15




Formula 3-7

20




Formula 3-8

25




Formula 3-9


30




35



40




45



50


Formula 3-10

55




Formula 3-11

60



Formula 3-12

65



Formula 3-13

Formula 3-14

Formula 3-15

Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21









Formula 3-22

Formula 3-23

Formula 3-24

193


-continued



194


-continued

Formula 3-25




Formula 3-26

10




Formula 3-27

15




Formula 3-28

20




Formula 3-29

25




Formula 3-30

30




Formula 3-31

35



Formula 3-32

40



wherein, in Formulae 3-1 to 3-31, 3-31', 3-32', 3-32 to 3-35,

Y_1 is O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$,

Z_1 to Z_7 are each independently deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, or $-Si(Q_{31})(Q_{32})(Q_{33})$,

Q_{31} to Q_{33} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, or a pyridinyl group,

d_2 is an integer of 0 to 2,

d_3 is an integer of 0 to 3,

195

d4 is an integer of 0 to 4,
 d5 is an integer of 0 to 5,
 d6 is an integer of 0 to 6,
 d8 is an integer of 0 to 8, and
 *, **, and *** each indicate a binding site to a neighboring 5
 atom.

5. The condensed cyclic compound as claimed in claim 1,
 wherein:

Ar¹ is:

a phenyl group, a biphenyl group, a terphenyl group, a 10
 pentalenyl group, an indenyl group, a naphthyl group,
 an azulenyl group, a heptalenyl group, an indacenyl
 group, an acenaphthyl group, a fluorenyl group, a
 spiro-bifluorenyl group, a benzofluorenyl group, a
 dibenzofluorenyl group, a phenalenyl group, a phenan- 15
 threnyl group, an anthracenyl group, a fluoranthenyl
 group, a triphenylenyl group, a pyrenyl group, a chry-
 senyl group, a naphthacenyl group, a picenyl group, a
 perylenyl group, a pentaphenyl group, a hexacenyl
 group, a pentacenyl group, a rubicenyl group, a cor- 20
 onenyl group, an ovalenyl group, a pyridinyl group, a
 pyrazinyl group, a pyrimidinyl group, a pyridazinyl
 group, a triazinyl group, a thiophenyl group, a furanyl
 group, a quinolinyl group, an isoquinolinyl group, a
 carbazolyl group, a benzofuranyl group, a benzothio- 25
 phenyl group, a dibenzofuranyl group, a dibenzothio-
 phenyl group, a benzonaphthofuranyl group, a dinaph-
 thofuranyl group, a benzocarbazolyl group, a
 dibenzocarbazolyl group, a dibenzosilolyl group, a
 benzonaphthosilolyl group, a dinaphthosilolyl group, a 30
 benzimidazolyl group, or an imidazopyridinyl group;

a phenyl group, a biphenyl group, a terphenyl group, a
 pentalenyl group, an indenyl group, a naphthyl group,
 an azulenyl group, a heptalenyl group, an indacenyl 35
 group, an acenaphthyl group, a fluorenyl group, a
 spiro-bifluorenyl group, a benzofluorenyl group, a
 dibenzofluorenyl group, a phenalenyl group, a phenan-
 threnyl group, an anthracenyl group, a fluoranthenyl
 group, a triphenylenyl group, a pyrenyl group, a chry- 40
 senyl group, a naphthacenyl group, a picenyl group, a
 perylenyl group, a pentaphenyl group, a hexacenyl
 group, a pentacenyl group, a rubicenyl group, a cor-
 onenyl group, an ovalenyl group, a pyridinyl group, a
 pyrazinyl group, a pyrimidinyl group, a pyridazinyl 45
 group, a triazinyl group, a thiophenyl group, a furanyl
 group, a quinolinyl group, an isoquinolinyl group, a
 carbazolyl group, a benzofuranyl group, a benzothio-
 phenyl group, a dibenzofuranyl group, a dibenzothio-
 phenyl group, a benzonaphthofuranyl group, a dinaph- 50
 thofuranyl group, a benzocarbazolyl group, a
 dibenzocarbazolyl group, a dibenzosilolyl group, a
 benzonaphthosilolyl group, a dinaphthosilolyl group,
 a benzimidazolyl group, or an imidazopyridinyl group,
 each substituted with deuterium, —F, —Cl, —Br, —I, 55
 a hydroxyl group, a cyano group, a nitro group, an
 amidino group, a hydrazino group, a hydrazono group,
 a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclo-
 pentyl group, a cyclohexyl group, a cycloheptyl group,
 a cyclopentenyl group, a cyclohexenyl group, a phenyl 60
 group, a biphenyl group, a terphenyl group, a pental-
 enyl group, an indenyl group, a naphthyl group, an
 azulenyl group, a heptalenyl group, an indacenyl group,
 an acenaphthyl group, a fluorenyl group, a spiro-bif-
 luorenyl group, a benzofluorenyl group, a dibenzofluo- 65
 renyl group, a phenalenyl group, a phenanthrenyl
 group, an anthracenyl group, a fluoranthenyl group, a
 triphenylenyl group, a pyrenyl group, a chrysenyl

196

group, a naphthacenyl group, a picenyl group, a peryle-
 nyl group, a pentaphenyl group, a hexacenyl group, a
 pentacenyl group, a rubicenyl group, a coronenyl
 group, an ovalenyl group, a pyridinyl group, a pyrazi-
 nyl group, a pyrimidinyl group, a pyridazinyl group, a
 triazinyl group, a thiophenyl group, a furanyl group, a
 quinolinyl group, an isoquinolinyl group, a carbazolyl
 group, a benzofuranyl group, a benzothiophenyl group,
 a dibenzofuranyl group, a dibenzothiophenyl group, a
 benzocarbazolyl group, a dibenzocarbazolyl group, a
 dibenzosilolyl group, —N(Q₃₁)(Q₃₂), or —Si(Q₃₁)
 (Q₃₂)(Q₃₃); or
 —S(=O)(Q₁)(Q₂), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂),
 —P(=O)₂(Q₁), —P(=S)(Q₁)(Q₂), or —P(=S)₂(Q₁);
 and

Q₁, Q₂, and Q₃₁ to Q₃₃ are each independently a C₁-C₂₀
 alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a
 biphenyl group, a terphenyl group, a naphthyl group, or
 a pyridinyl group.

6. The condensed cyclic compound as claimed in claim 5,
 wherein:

Ar¹ is:


a phenyl group, a biphenyl group, a naphthyl group, a
 fluorenyl group, a spiro-bifluorenyl group, a phenan-
 threnyl group, an anthracenyl group, a triphenylenyl
 group, a pyridinyl group, a pyrimidinyl group, a triazi-
 nyl group, a quinolinyl group, an isoquinolinyl group,
 or a carbazolyl group;

a phenyl group, a biphenyl group, a naphthyl group, a
 fluorenyl group, a spiro-bifluorenyl group, a phenan-
 threnyl group, an anthracenyl group, a triphenylenyl
 group, a pyridinyl group, a pyrimidinyl group, a triazi-
 nyl group, a quinolinyl group, an isoquinolinyl group,
 or a carbazolyl group, each substituted with deuterium,
 —F, —Cl, —Br, —I, a hydroxyl group, a cyano group,
 a nitro group, an amidino group, a hydrazino group, a
 hydrazono group, a C₁-C₂₀ alkyl group, a C₁-C₂₀
 alkoxy group, a phenyl group, a biphenyl group, a
 naphthyl group, a fluorenyl group, a phenanthrenyl
 group, an anthracenyl group, a pyridinyl group, a
 pyrimidinyl group, a triazinyl group, a quinolinyl
 group, an isoquinolinyl group, a carbazolyl group,
 —N(Q₃₁)(Q₃₂), or —Si(Q₃₁)(Q₃₂)(Q₃₃); or
 —S(=O)(Q₁)(Q₂), —S(=O)₂(Q₁), —P(=O)(Q₁)(Q₂),
 —P(=O)₂(Q₁), —P(=S)(Q₁)(Q₂), or —P(=S)₂(Q₁);
 and


Q₁, Q₂, and Q₃₁ to Q₃₃ are each independently a C₁-C₂₀
 alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a
 biphenyl group, a terphenyl group, a naphthyl group, or
 a pyridinyl group.

7. The condensed cyclic compound as claimed in claim 1,
 wherein Ar¹ is a group represented by one of Formulae 5-1
 to 5-49, —S(=O)(Q₁)(Q₂), —S(=O)₂(Q₁), —P(=O)(Q₁)
 (Q₂), —P(=O)₂(Q₁), —P(=S)(Q₁)(Q₂), or —P(=S)₂(Q₁):

Formula 5-1











Formula 5-2



197

-continued




198

-continued

Formula 5-3

5




Formula 5-4

10


Formula 5-5

15




Formula 5-6

25




Formula 5-7

30




Formula 5-8

40




Formula 5-9

50




Formula 5-10

60



65



Formula 5-11

Formula 5-12

Formula 5-13

Formula 5-14









Formula 5-15

Formula 5-16

Formula 5-17


Formula 5-18

199
-continued





200
-continued


Formula 5-19




Formula 5-20




Formula 5-21




Formula 5-22






Formula 5-23





Formula 5-24



Formula 5-25



Formula 5-26



Formula 5-27

Formula 5-28

Formula 5-29

Formula 5-30

Formula 5-31

Formula 5-32

Formula 5-33

Formula 5-34

Formula 5-35











Formula 5-36

Formula 5-37

Formula 5-38

201

-continued



202

-continued

Formula 5-49

Formula 5-39

5

Formula 5-40

10

Formula 5-41

15

Formula 5-42

20

Formula 5-43

25

Formula 5-44

30

Formula 5-45

40

Formula 5-46

45

Formula 5-47

50

Formula 5-48

60

wherein, in Formulae 5-1 to 5-49,

Y_{31} is O, S, C(Z_{33})(Z_{34}), N(Z_{35}), or Si(Z_{36})(Z_{37}),

Z_{31} to Z_{37} are each independently deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, a silolyl group, a pyridinyl group, an indolyl group, an isoindolyl group, a benzofuranyl group, a benzothiophenyl group, a benzosilolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a dibenzosilolyl group, a carbazolyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, or —Si(Q_{31})(Q_{32})(Q_{33}),

Q_1 , Q_2 , and Q_{31} to Q_{33} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, or a pyridinyl group,

e_2 is an integer of 0 to 2,

e_3 is an integer of 0 to 3,

e_4 is an integer of 0 to 4,

e_5 is an integer of 0 to 5,

e_6 is an integer of 0 to 6,

e_7 is an integer of 0 to 7,












e_9 is an integer of 0 to 9, and

* indicates a binding site to a neighboring atom.

8. The condensed cyclic compound as claimed in claim 7, wherein Ar^1 is a group represented by one of Formulae 5-1 to 5-4, 5-7, 5-13, 5-14, 5-20 to 5-23, 5-30, 5-31, 5-34, 5-41, and 5-48, —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2), in which Q_1 and Q_2 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, or a pyridinyl group.

9. The condensed cyclic compound as claimed in claim 1, wherein Ar^1 is a group represented by one of Formulae 6-1 to 6-110, a group represented by one of Formulae 10-1 to 10-11, —S(=O)₂(Q_1), or —P(=O)(Q_1)(Q_2), in which Q_1 and Q_2 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, or a pyridinyl group:

203




204

-continued


Formula 6-1

5




Formula 6-2

10




Formula 6-3

15



Formula 6-4

20




Formula 6-5

25


Formula 6-6

30



Formula 6-7


35



Formula 6-8


40

45



Formula 6-9

50




Formula 6-10

55

Formula 6-11

60

65



Formula 6-12

Formula 6-13

Formula 6-14

Formula 6-15

Formula 6-16

Formula 6-17









Formula 6-18

Formula 6-19

Formula 6-20

205


-continued

**206**

-continued


Formula 6-21

5




Formula 6-22

10




Formula 6-23

15




Formula 6-24

25




Formula 6-25

35




40



Formula 6-26


45



50

Formula 6-27

55



Formula 6-28

60

65

Formula 6-29

Formula 6-30

Formula 6-31

Formula 6-32

Formula 6-33









Formula 6-34

Formula 6-35

Formula 6-36

207


-continued

**208**

-continued

Formula 6-37


5



10


Formula 6-38

15




Formula 6-39

25




Formula 6-40

30




Formula 6-41

35



Formula 6-42


40



45

Formula 6-43


50




55

Formula 6-44

60



65



Formula 6-45

Formula 6-46

Formula 6-47

Formula 6-48

Formula 6-49

Formula 6-50









Formula 6-51

Formula 6-52

Formula 6-53

209


-continued

**210**

-continued


Formula 6-54

5




Formula 6-55

10




Formula 6-56

15




Formula 6-57

20




Formula 6-58

25




Formula 6-59

30



Formula 6-60

35



Formula 6-61

40

Formula 6-62

Formula 6-63

Formula 6-64

Formula 6-65







Formula 6-66

Formula 6-67

Formula 6-68

211


-continued

**212**

-continued

Formula 6-69


5



10

Formula 6-70


15



20

Formula 6-71


25



30

Formula 6-72

35




40

45

Formula 6-73


50



55

Formula 6-74

60



65

Formula 6-75

Formula 6-76

Formula 6-77






Formula 6-78

Formula 6-79

Formula 6-80

213


-continued

**214**

-continued

Formula 6-81


5



10

Formula 6-82


15



20

Formula 6-83

25




30

35

Formula 6-84

40




45

50


Formula 6-85

55



60

65



Formula 6-86

Formula 6-87

Formula 6-88

Formula 6-89

Formula 6-90








Formula 6-91

Formula 6-92

Formula 6-93

215


-continued

**216**

-continued


Formula 6-94

5




Formula 6-95

10




Formula 6-96

15




Formula 6-97

20




Formula 6-98

25



Formula 6-99


30



35

Formula 6-100

40



45

Formula 6-101

Formula 6-102

Formula 6-103

Formula 6-104










Formula 6-105

Formula 6-106

Formula 6-107

217

-continued




218

-continued

Formula 6-108

5



Formula 6-109

10

Formula 6-110

15

20

25

Formula 10-1

30

Formula 10-2

35

Formula 10-3

40

Formula 10-4

45

Formula 10-5

50

Formula 10-6

55

60

65

Formula 10-7

Formula 10-8

Formula 10-9

Formula 10-10

Formula 10-11

wherein, in Formulae 6-1 to 6-110 and 10-1 to 10-11, Ph indicates a phenyl group and * indicates a binding site to a neighboring atom.

10. The condensed cyclic compound as claimed in claim 1, wherein at least one of R_2 and R_8 is a substituted or unsubstituted C_1 - C_{60} alkyl group.

11. The condensed cyclic compound as claimed in claim 1, wherein R_3 , R_4 , R_6 , R_9 , R_{10} , and R_{12} are each hydrogen.

12. The condensed cyclic compound as claimed in claim 1, wherein:




i) R_1 , R_5 , and R_7 are each a group represented by Formula 2, R_2 and R_8 are each a substituted or unsubstituted C_1 - C_{60} alkyl group, and R_3 , R_4 , R_6 , R_9 , R_{10} , R_{11} , and R_{12} are each hydrogen;

ii) R_1 , R_5 , R_7 , and R_{11} are each a group represented by Formula 2, R_2 and R_8 are each a substituted or unsubstituted C_1 - C_{60} alkyl group, and R_3 , R_4 , R_6 , R_9 , R_{10} , and R_{12} are each hydrogen; or

iii) R_1 and R_7 are each a group represented by Formula 2, R_2 and R_8 are each a substituted or unsubstituted C_1 - C_{60} alkyl group, and R_3 , R_4 , R_5 , R_6 , R_9 , R_{10} , R_{11} , and R_{12} are each hydrogen.


219

13. The condensed cyclic compound as claimed in claim 1, wherein the condensed cyclic compound is one of Compounds 1 to 138:


**220**

-continued


4




5



6







7



221

-continued

**222**

-continued

8

12

5

10

15

9

13

20

25

30

10

35

14

40

45

50





11

55

15


60

65










223

-continued


**224**

-continued




225

-continued





**226**

-continued



227

-continued

**228**

-continued

32

36

5

10

15

33

20

25

30

34

35

40

45





50

35

55

60


65




229

-continued


40




41



42



43




230

-continued


44

5



45


20



42

46


40



50

47

55




65

231

-continued


48



5

10

49




20

25

30

50




35

40

45

51



55


60

65


232

-continued


52




53



54







55







233

-continued





**234**

-continued







235

-continued





**236**

-continued






237

-continued


**238**

-continued



239

-continued



79

5

10

15

20

25

80

30

35

40

45



81

50


55

60


65

**240**


-continued



82




83








84

241

-continued




**242**

-continued






243

-continued


**244**

-continued



245

-continued



246

-continued

97

99

5

10

15

20

25

30

35

40

98

100




45

50

55


60

65



247

-continued



248

-continued

101

103

5

10

15

20

25

30

35

40

102

45




104

50

55


60

65



249

-continued

**250**

-continued

105

5

10

15

20

25

30

35

40

106

45




50

55

60

65



107



108

251

-continued

**252**

-continued

109

111

5

10

15

20

25

30

35

40

45

110

50



112

55

60





65

113







253

-continued


**254**

-continued



255


-continued



5

10

15



20

25


30

35

40

45

124 50




55

60


65

256


-continued




125



126



127




128


257

-continued


129




130



131



132




65


258

-continued


133




134



135





136



259

-continued



14. An organic light-emitting device, comprising:
a first electrode;

a second electrode facing the first electrode; and

an organic layer between the first electrode and the second electrode, the organic layer comprising an emission layer,

wherein the organic layer includes the condensed cyclic compound as claimed in claim 1.

15. The organic light-emitting device as claimed in claim 14, wherein:

the first electrode is an anode,

the second electrode is a cathode,

the organic layer includes a hole transport region between the first electrode and the emission layer and an electron transport region between the emission layer and the second electrode,

the hole transport region includes a hole injection layer, a hole transport layer, an emission auxiliary layer, an electron blocking layer, or a combination thereof, and the electron transport region includes a buffer layer, a hole blocking layer, an electron control layer, an electron transport layer, an electron injection layer, or a combination thereof.

16. An organic light-emitting device, comprising:
a first electrode;

a second electrode facing the first electrode; and

an organic layer between the first electrode and the second electrode, the organic layer comprising:

an emission layer,


a hole transport region between the first electrode and the emission layer, and

an electron transport region between the emission layer and the second electrode,

260

wherein the electron transport region includes a condensed cyclic compound represented by Formula 1:

<Formula 1>



wherein, in Formula 1, R_1 to R_{12} are each independently a group represented by Formula 2, hydrogen, deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, a hydrazino group, a hydrazono group, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group, provided that at least two selected from R_1 , R_5 , R_7 , and R_{11} are not hydrogen,

$$*-(L_1)_{a1}-(Ar_1)_{b1},$$

<Formula 2>

wherein, in Formula 2,

L_1 is a substituted or unsubstituted C_3 - C_{60} carbocyclic group, a substituted or unsubstituted C_1 - C_{60} heterocyclic group, $*-Si(Q_1)(Q_2)-*$, $*-N(Q_1)-*$, $*-B(Q_1)-*$, $*-C(=O)-*$, $*-S(=O)_2-*$, or $*-P(=O)(Q_1)-*$,

a_1 is an integer of 0 to 4, wherein, when a_1 is zero, $*-(L_1)_{a1}-*$ is a single bond, and when a_1 is 2, 3, or 4, the 2, 3, or 4 L_1 (s) are identical to or different from each other,

Ar_1 is a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-Si(Q_1)(Q_2)(Q_3)$, $-N(Q_1)(Q_2)$, $-B(Q_1)(Q_2)$, $-C(=O)(Q_1)$, $-S(=O)_2(Q_1)$, or $-P(=O)(Q_1)(Q_2)$,

b_1 is an integer of 1 to 4, wherein, when b_1 is 2, 3, or 4, the 2, 3, or 4 Ar_1 (s) are identical to or different from each other,

at least one substituent of the substituted C_3 - C_{60} carbocyclic group, the substituted C_1 - C_{60} heterocyclic group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_1 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_1 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_6 - C_{60} aryloxy group, the substituted C_6 - C_{60} arylthio group, the substituted C_1 - C_{60} heteroaryl group, the substituted monovalent non-aro-

261

matic condensed polycyclic group, and the substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

- deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;
- a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q_{11})(Q_{12})(Q_{13}), —N(Q_{11})(Q_{12}), —B(Q_{11})(Q_{12}), —C(=O)(Q_{11}), —S(=O)₂(Q_{11}), and —P(=O)(Q_{11})(Q_{12});
- a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group;
- a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60}

262

- alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, a terphenyl group, —Si(Q_{21})(Q_{22})(Q_{23}), —N(Q_{21})(Q_{22}), —B(Q_{21})(Q_{22}), —C(=O)(Q_{21}), —S(=O)₂(Q_{21}), and —P(=O)(Q_{21})(Q_{22}); and
- Si(Q_{31})(Q_{32})(Q_{33}), —N(Q_{31})(Q_{32}), —B(Q_{31})(Q_{32}), —C(=O)(Q_{31}), —S(=O)₂(Q_{31}), and —P(=O)(Q_{31})(Q_{32}),
- Q_1 to Q_3 , Q_{11} to Q_{13} , Q_{21} to Q_{23} , and Q_{31} to Q_{33} are each independently selected from hydrogen, deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amidino group, a hydrazino group, a hydrazono group, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryl group substituted with a C_1 - C_{60} alkyl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, a biphenyl group, and a terphenyl group, and
- * and *' each indicate a binding site to a neighboring atom.
17. The organic light-emitting device as claimed in claim 15, wherein:
- the electron transport region includes the electron transport layer, and
- the electron transport layer includes the condensed cyclic compound.
18. The organic light-emitting device as claimed in claim 15, wherein:
- the hole transport region includes a p-dopant, and
- a lowest unoccupied molecular orbital (LUMO) energy level of the p-dopant is –3.5 eV or less.

* * * * *

专利名称(译)	稠合环状化合物和包括该稠合环状化合物的有机发光装置		
公开(公告)号	US10693083	公开(公告)日	2020-06-23
申请号	US15/628688	申请日	2017-06-21
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	JEONG EUNJAE PARK JUNHA SIM MUNKI LEE HYOYOUNG KIM YOUNGKOOK HWANG SEOKHWAN		
发明人	JEONG, EUNJAE PARK, JUNHA SIM, MUNKI LEE, HYOYOUNG KIM, YOUNGKOOK HWANG, SEOKHWAN		
IPC分类号	H01L51/00 H01L51/50 C07D471/04 C07D221/18 C09K11/06 C07D471/06		
CPC分类号	H01L51/5068 C07D471/06 H01L51/0067 C09K11/06 H01L51/0052 C07D471/04 H01L51/50 C07D221/18 H01L51/0072 H01L51/0014 H01L51/0054 H01L51/508 H01L51/5072 H01L51/5004 H01L2251/552 C09K2211/1018 C07F9/6561 C09K2211/1007 C09K2211/1011 C09K2211/1029 C09K2211/1044 C09K2211/1059 H01L51/0056 H01L51/0058 H01L51/0094		
优先权	1020160168009 2016-12-09 KR		
其他公开文献	US20180166635A1		
外部链接	Espacenet		

摘要(译)

稠合环状化合物和包括该稠合环状化合物的有机发光装置，该稠合环状化合物由式1表示：

