



US 20140239269A1

(19) **United States**

(12) **Patent Application Publication**
Jeong et al.

(10) **Pub. No.: US 2014/0239269 A1**

(43) **Pub. Date: Aug. 28, 2014**

(54) **PYRENE-BASED COMPOUND AND
ORGANIC LIGHT-EMITTING DIODE
COMPRISING THE SAME**

(30) **Foreign Application Priority Data**

Feb. 25, 2013 (KR) 10-2013-0020013

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin City
(KR)

Publication Classification

(72) Inventors: **Eun-Jae Jeong**, Yongin-City (KR);
Seok-Hwan Hwang, Yongin-City (KR);
Young-Kook Kim, Yongin-City (KR);
Hye-Jin Jung, Yongin-City (KR);
Jun-Ha Park, Yongin-City (KR);
Eun-Young Lee, Yongin-City (KR);
Jin-O Lim, Yongin-City (KR);
Sang-Hyun Han, Yongin-City (KR);
Soo-Yon Kim, Yongin-City (KR);
Jong-Hyuk Lee, Yongin-City (KR)

(51) **Int. Cl.**
H01L 51/00 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 51/0054** (2013.01); **H01L 51/0072**
(2013.01); **H01L 51/0067** (2013.01); **H01L**
51/0071 (2013.01); **H01L 51/007** (2013.01);
H01L 51/0069 (2013.01); **H01L 51/0074**
(2013.01); **H01L 51/0073** (2013.01)
USPC **257/40**; 548/310.7; 548/269.4; 548/224;
548/145; 548/136; 544/281; 546/121;
548/343.5; 548/160; 544/353; 546/173

(21) Appl. No.: **13/959,551**

(57) **ABSTRACT**

(22) Filed: **Aug. 5, 2013**

A pyrene-based compound, and an organic light-emitting diode including the pyrene-based compound are provided.





FIG. 1



**PYRENE-BASED COMPOUND AND
ORGANIC LIGHT-EMITTING DIODE
COMPRISING THE SAME**

INCORPORATION BY REFERENCE TO ANY
PRIORITY APPLICATIONS

[0001] Any and all applications for which a foreign or domestic priority claim is identified in the Application Data Sheet as filed with the present application are hereby incorporated by reference under 37 C.F.R. §1.57.

[0002] This application claims the benefit of Korean Patent Application No. 10-2013-0020013, filed on Feb. 25, 2013, in the Korean Intellectual Property Office, the disclosure of which is incorporated herein by reference.

BACKGROUND

[0003] 1. Field

[0004] One or more embodiments relate to a compound for organic light-emitting diodes, and an organic light-emitting diode.

[0005] 2. Description of the Related Technology

[0006] Organic light-emitting diodes (OLEDs), which are self-emitting diodes, have advantages such as wide viewing angles, excellent contrast, quick response, high brightness, excellent driving voltage characteristics, and can provide multicolored images.

[0007] A typical OLED has a structure including a substrate, and an anode, a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and a cathode which are sequentially stacked on the substrate. In this regard, the HTL, the EML, and the ETL are organic thin films comprising organic compounds.

[0008] An operating principle of an OLED having the above-described structure is as follows.

[0009] When a voltage is applied between the anode and the cathode, holes injected from the anode move to the EML via the HTL, and electrons injected from the cathode move to the EML via the ETL. The holes and electrons recombine in the EML to generate excitons. When the excitons drop from an excited state to a ground state, light is emitted.


SUMMARY

[0010] One or more embodiments include a pyrene-based compound having a novel structure, and an organic light-emitting diode including the pyrene-based compound.

[0011] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented embodiments.

[0012] According to one or more embodiments, there is provided a pyrene-based compound represented by Formula 1 below:

Formula 1



[0013] wherein, in Formula 1,

[0014] L_1 and L_2 are each independently selected from a substituted or unsubstituted C_3-C_{10} cycloalkylene group, a substituted or unsubstituted C_2-C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3-C_{10} cycloalkenylene group, a substituted or unsubstituted C_2-C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6-C_{60} arylene group, and a substituted or unsubstituted C_2-C_{60} heteroarylene group;

[0015] R_1 is selected from a substituted or unsubstituted N-containing 5-membered cyclic group, and a substituted or unsubstituted N-containing 5-membered cyclic group fused with a 6-membered ring;

[0016] R_2 is selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{10} cycloalkyl group, a substituted or unsubstituted C_2-C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3-C_{10} cycloalkenyl group, a substituted or unsubstituted C_2-C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthiol group, a substituted or unsubstituted C_2-C_{60} heteroaryl group, $-N(Q_1)(Q_2)$, and $-Si(Q_3)(Q_4)(Q_5)$ (where Q_1 to Q_5 are each independently a C_1-C_{60} alkyl group, a C_1-C_{60} alkoxy group, a C_6-C_{60} aryl group, or a C_2-C_{60} heteroaryl group);

[0017] a_1 and b_1 are each independently an integer from 1 to 5; and

[0018] a_2 and b_2 are each independently an integer from 0 to 5.

[0019] According to one or more embodiments, an organic light-emitting diode includes: a first electrode; a second electrode disposed opposite to the first electrode; and an organic layer disposed between the first electrode and the second electrode and including an emission layer, wherein the organic layer includes a hole transport region between the first electrode and the emission layer, and an electron transport region between the emission layer and the second electrode, and the organic layer includes at least one of the pyrene-based compounds of Formula 1 defined above.

BRIEF DESCRIPTION OF THE DRAWINGS

[0020] These and/or other aspects will become apparent and more readily appreciated from the following description of the embodiments, taken in conjunction with the accompanying drawing in which:

[0021] FIG. 1 is a schematic view of a structure of an organic light-emitting diode according to an embodiment.


DETAILED DESCRIPTION

[0022] Reference will now be made in detail to embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to the like elements throughout. In this regard, the present embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the embodiments are merely described below, by refer-

ring to the figures, to explain aspects of the present description. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0023] According to an embodiment, there is provided a pyrene-based compound represented by Formula 1 below:

Formula 1



[0024] In Formula 1, L_1 and L_2 may each independently be selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, and a substituted or unsubstituted C_2 - C_{60} heteroarylene group.

[0025] In some embodiments, L_1 and L_2 may each independently be selected from

[0026] i) a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthrylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pyrrolylene group, an imidazolylene group, a pyrazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylene group, a benzoimidazolylene group, a furanylene group, a benzofuranylene group, a thiophenylene group, a benzothiophenylene group, a thiazolylene group, an isothiazolylene group, a benzothiazolylene group, an isoxazolylene group, an oxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a benzooxazolylene group, a dibenzopuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, and a dibenzosilolylene group; and

[0027] ii) a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthrylene group, a fluoranthrenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene

group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pyrrolylene group, an imidazolylene group, a pyrazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylene group, a benzoimidazolylene group, a furanylene group, a benzofuranylene group, a thiophenylene group, a benzothiophenylene group, a thiazolylene group, an isothiazolylene group, a benzothiazolylene group, an isoxazolylene group, an oxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a benzooxazolylene group, a dibenzopuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, and a dibenzosilolylene group, each substituted with at least one selected from

[0028] a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,


[0029] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0030] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, and


[0031] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

[0032] In some embodiments, L_1 and L_2 may each independently be one of the groups represented by Formulae 2-1 to 2-27 below:

Formula 2-1



-continued



Formula 2-2

Formula 2-3

Formula 2-4

Formula 2-5

Formula 2-6


Formula 2-7

Formula 2-8

Formula 2-9

Formula 2-10

-continued



Formula 2-11

Formula 2-12

Formula 2-13

Formula 2-14

Formula 2-15

Formula 2-16

Formula 2-17


Formula 2-18

Formula 2-19


Formula 2-20

Formula 2-21


-continued




Formula 2-22




Formula 2-23




Formula 2-24



Formula 2-25




Formula 2-26



Formula 2-27

[0033] In Formulae 2-1 to 2-27,**[0034]** Y_1 may be O, S, $C(Z_3)(Z_4)$, or $N(Z_5)$;**[0035]** Z_1 to Z_5 may each independently be selected from**[0036]** a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,**[0037]** a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,**[0038]** a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,**[0039]** a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or asalt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and **[0040]** $-Si(Q_{13})(Q_{14})(Q_{15})$ (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, or a C_2 - C_{20} heteroaryl group);**[0041]** d_1 may be an integer from 1 to 4;**[0042]** d_2 may be an integer from 1 to 3;**[0043]** d_3 may be an integer from 1 to 6;**[0044]** d_4 may be an integer from 1 to 8;**[0045]** d_5 may be 1 or 2;**[0046]** * indicates a binding site of pyrene in Formula 1 or a binding site of adjacent L_1 ; and**[0047]** *' indicates a binding site of adjacent L_1 in Formula 1 or a binding site of R_1 .**[0048]** In some embodiments, in Formulae 2-1 to 2-27, Z_1 to Z_5 may each independently be selected from**[0049]** a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,**[0050]** a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,**[0051]** a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,**[0052]** a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and**[0053]** $-Si(Q_{13})(Q_{14})(Q_{15})$ (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).

[0054] In some other embodiments, L_1 and L_2 in Formula 1 above may each independently be one of the groups represented by Formulae 3-1 to 3-20:



Formula 3-1

Formula 3-2

Formula 3-3

Formula 3-4

Formula 3-5


Formula 3-6

Formula 3-7

Formula 3-8

Formula 3-9

-continued



Formula 3-10

Formula 3-11

Formula 3-12

Formula 3-13

Formula 3-14


Formula 3-15

Formula 3-16

Formula 3-17


Formula 3-18

-continued



Formula 3-19

Formula 3-20




[0055] In Formulae 3-1 to 3-20, * may be a binding site of pyrene in Formula 1 or a binding site of adjacent L_1 ; and *' may be a binding site of adjacent L_1 in Formula 1 or a binding site of R_1 .


[0056] In Formula 1, a_1 indicates the number of L_1 s, and a_2 indicates the number of L_2 s. For example, a_1 may be an integer from 1 to 5, and a_2 may be an integer from 0 to 5. Since a_1 is nonzero, L_1 is always present in Formula 1. For example, a_1 may be 1 or 2, and a_2 may be 0, 1, or 2. When a_2 is 0, R_2 may be directly bound to the 7th carbon of the pyrene core in Formula 1. When a_1 is 2 or greater, the two or more L_1 s may be identical to or differ from each other. When a_2 is 2 or greater, the two or more L_2 s may be identical to or differ from each other.

[0057] In Formula 1, R_1 may be selected from a substituted or unsubstituted N-containing 5-membered cyclic group, and a substituted or unsubstituted N-containing 5-membered cyclic group fused with a 6-membered ring.


[0058] For example, R_1 may be one of the groups represented by Formulae 4-1 to 4-10:



Formula 4-1




Formula 4-2




Formula 4-3


-continued




Formula 4-4




Formula 4-5




Formula 4-6




Formula 4-7



Formula 4-8



Formula 4-9



Formula 4-10

- [0059]** In Formulae 4-1 to 4-10,
[0060] Y_{11} may be O, S, N(Z_{11}), or C(Z_{12})(Z_{13});
[0061] Y_{21} may be N or C(Z_{21});
[0062] Y_{22} may be N or C(Z_{22});
[0063] Y_{23} may be N or C(Z_{23});
[0064] Y_{24} may be N or C(Z_{24});
[0065] Y_{25} may be N or C(Z_{25});
[0066] Y_{26} may be N or C(Z_{26});
[0067] Z_{11} to Z_{13} , and Z_{21} to Z_{27} may each independently be selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

[0068] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0069] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

[0070] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazoyl group, a phenylcarbazoyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0071] —Si(Q13)(Q14)(Q15) (where Q13 to Q15 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, or a C_2 - C_{20} heteroaryl group); and

[0072] * may be a binding site of L_1 in Formula 1.

[0073] In some embodiments, Z_{11} to Z_{13} , and Z_{21} to Z_{27} in Formulae 4-1 to 4-10 may each independently be selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

[0074] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0075] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazoyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,

[0076] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazoyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazoyl group, a phenylcarbazoyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0077] —Si(Q13)(Q14)(Q15) (where Q13 to Q15 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazoyl group, a phenylcarbazoyl group, a pyridinyl

group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).

[0078] In some embodiments, R_1 in Formula 1 may be selected from

[0079] i) a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a triazolyl group, an oxazolyl group, an isoxazolyl group, an oxadiazolyl group, an oxatriazolyl group, a triazolyl group, an isothiazolyl group, a thiazolyl group, a thiatriazolyl group, a benzoimidazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzooxazolyl group, and a benzothiazolyl group; and

[0080] ii) a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a triazolyl group, an oxazolyl group, an isoxazolyl group, an oxadiazolyl group, an oxatriazolyl group, a triazolyl group, an isothiazolyl group, a thiazolyl group, a thiatriazolyl group, a benzoimidazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzooxazolyl group, and a benzothiazolyl group, each substituted with at least one selected from

[0081] a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

[0082] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0083] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

[0084] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazoyl group, a phenylcarbazoyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0085] —Si(Q13)(Q14)(Q15) (where Q13 to Q15 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group or a C_2 - C_{20} heteroaryl group).

[0086] In some other embodiments, R_1 in Formula 1 may be selected from

[0087] i) a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a triazolyl group, an oxazolyl group, an isoxazolyl group, an oxadiazolyl group, an oxatriazolyl group, a triazolyl group, an isothiazolyl group, a thiazolyl group, a thiatriazolyl group, a benzoimidazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzooxazolyl group, and a benzothiazolyl group; and

[0088] ii) a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a triazolyl group, an oxazolyl group, an isoxazolyl group, an oxadiazolyl group, an oxatriazolyl group, a triazolyl group, an isothiazolyl group, a thiazolyl group, a thiatriazolyl group, a benzoimidazolyl group, an imidazopy-

rimidinyl group, an imidazopyridinyl group, a benzooxazolyl group, and a benzothiazolyl group, each substituted with at least one selected from

[0089] a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group,

[0090] a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0091] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,


[0092] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0093] —Si(Q₁₃)(Q₁₄)(Q₁₅) (where Q₁₃ to Q₁₅ are each independently a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group). However, the present embodiments are not limited thereto


[0094] For example, R₁ in Formula 1 may be one of the groups represented by Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1):

-continued


Formula 4-1(3)




Formula 4-2(1)




Formula 4-4(1)




Formula 4-4(2)




Formula 4-4(3)




Formula 4-6(1)




Formula 4-6(2)



Formula 4-1(1)




Formula 4-1(2)



-continued

Formula 4-8(1)



[0095] The above-detailed descriptions of Z_{11} and Z_{21} , and Z_{21} to Z_{26} may be referred to here as those of Z_{11} and Z_{21} , and Z_{21} to Z_{26} in Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1).

[0096] For example, Z_{11} and Z_{21} to Z_{26} may each independently be selected from

[0097] a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group.

[0098] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0099] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,

[0100] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0101] $-\text{Si}(\text{Q}_{13})(\text{Q}_{14})(\text{Q}_{15})$ (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).

[0102] In Formula 1, R_2 may be selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric

acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthiol group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, $-\text{N}(\text{Q}_1)(\text{Q}_2)$, and $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$ (where Q_1 to Q_5 are each independently a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a C_6 - C_{60} aryl group, or a C_2 - C_{60} heteroaryl group).

[0103] In some embodiments, R_2 in Formula 1 may be selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

[0104] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0105] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

[0106] a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0107] $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$ (where Q_3 to Q_5 are each independently a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a C_6 - C_{60} aryl group, or a C_2 - C_{60} heteroaryl group). However, the present embodiments are not limited thereto.

[0108] In some embodiments, R_2 in Formula 1 may be selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

[0109] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0110] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a

triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a dibenzopuranyl group, and a dibenzothiophenyl group,

[0111] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a dibenzopuranyl group, and a dibenzothiophenyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0112] $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$ (where Q_3 to Q_5 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).

[0113] In Formula 1, b1 indicates the number of R_1 s, and b2 indicates the number of R_2 s. For example, b1 may be an integer from 1 to 5, and b2 may be an integer from 0 to 5. Since b1 is nonzero, R_1 is always present in Formula 1. For example, b1 may be 1 or 2, and b2 may be 0, 1, or 2. When b1 is 2 or greater, the two or more R_1 s may be identical to or differ from each other. When b2 is 2 or greater, the two or more R_2 s may be identical to or differ from each other.


[0114] In some other embodiments, R_2 in Formula 1 may be selected from

[0115] a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,


[0116] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substitute with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0117] groups represented by Formulae 5-1 to 5-22 below, and


[0118] $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$ (where Q_3 to Q_5 are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5




Formula 5-6




Formula 5-7



Formula 5-8




Formula 5-9



Formula 5-10

-continued



Formula 5-11

Formula 5-12

Formula 5-13

Formula 5-14

Formula 5-15


Formula 5-16

Formula 5-17

Formula 5-18

Formula 5-19

-continued



Formula 5-20

Formula 5-21

Formula 5-22

[0119] For example, in Formula 1, a₁ may be 1, b₁ may be 1, a₂ may be 0, and b₂ may be 1, but the present embodiments are not limited thereto.

[0120] In some other embodiments, in Formula 1 above,

[0121] i) L₁ may be one of the groups represented by Formulae 2-1 to 2-27 (for example, one of the groups represented by Formulae 3-1 to 3-20 above);

[0122] ii) a₁ may be 1 or 2;

[0123] iii) R₁ may be one of the groups represented by Formulae 4-1 to 4-10 above (for example, one of the groups represented by Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1));

[0124] iv) b₁ may be 1;

[0125] v) a₂ may be 0 or 1;

[0126] vi) R₂ may be selected from

[0127] a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group,

[0128] a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0129] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a dibenzopuranyl group, and a dibenzothiophenyl group,

[0130] a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a dibenzopuranyl group, and a dibenzothiophenyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluore-

nyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

[0131] —Si(Q₃)(Q₄)(Q₅) (where Q₃ to Q₅ are each independently a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group) (for example, R₂ may be selected from the groups represented by Formulae 5-1 to 5-22), and


[0132] vii) b₂ may be 1.

[0133] In some embodiments, in Formula 1, L₁ and L₂ in Formula 1 may each independently be one of the groups represented by Formulae 2-1 to 2-27 (for example, one of the














groups represented by Formulae 3-1 to 3-20); R₁ and R₂ may each independently be one of the groups represented by Formulae 4-1 to 4-10 (for example, one of the groups represented by Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1)); and a₁, a₂, b₁, and b₂ may each independently be 1 or 2.

[0134] In some other embodiments, in Formula 1, L₁ may be identical to L₂, R₁ may be identical to R₂, a₁ may be identical to a₂, and b₁ may be identical to b₂. In this regards, L₁ and L₂ may be one of the groups represented by Formulae 2-1 to 2-27 (for example, one of the groups represented by Formulae 3-1 to 3-20 above); R₁ and R₂ may be one of the groups represented by Formulae 4-1 to 4-10 (for example, one of the groups represented by Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1)); and a₁, a₂, b₁, and b₂ may be 1.

[0135] In some embodiments, the pyrene-based compound of Formula 1 may be one of Compounds 1 to 60 below, but is not limited thereto:




-continued




-continued

22




23


24



25




26




27

28




29




-continued


30




31




32




33




34




35




36




37




38




39













40




41




-continued




-continued




52




53



54




55




56

-continued


57




58



59



60



[0136] At least one of the substituted C_3 - C_{10} cycloalkylene group, the substituted C_2 - C_{10} heterocycloalkylene group, the substituted C_3 - C_{10} cycloalkenylene group, the substituted C_2 - C_{10} heterocycloalkenylene group, the substituted C_6 - C_{60} arylene group, the substituted C_2 - C_{60} heteroarylene group, the substituted C_3 - C_{10} cycloalkyl group, the substituted C_2 - C_{10} heterocycloalkyl group, the substituted C_3 - C_{10} cycloalkenyl group, the substituted C_2 - C_{10} heterocycloalkenyl group, the substituted C_6 - C_{60} aryl group, the substituted C_2 - C_{60} heteroaryl group, the substituted C_1 - C_{60} alkyl group, the substituted C_2 - C_{60} alkenyl group, the substituted C_2 - C_{60} alkynyl group, the substituted C_1 - C_{60} alkoxy group, the substituted C_6 - C_{60} aryloxy group, and the substituted C_6 - C_{60} arylthio group may be selected from

[0137] a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group,

[0138] a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

[0139] a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, and a C_2 - C_{60} heteroaryl group,

[0140] a C_3 - C_{10} cycloalkyl group, a C_3 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_3 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, and a C_2 - C_{60} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof,

thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and [0141] —Si(Q₁₃)(Q₁₄)(Q₁₅) (where Q₁₃ to Q₁₅ are each independently a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₆-C₆₀ aryl group, or a C₂-C₆₀ heteroaryl group), but the present embodiments are not limited thereto.

[0142] In Formula 1, R₁ is connected to the 2nd carbon of the pyrene core via the linker L₁.

[0143] As used herein, “R₁” may be a N-containing 5-membered cyclic group or a N-containing 5-membered cyclic group fused with a 6-membered ring, so that an organic light-emitting diode including the pyrene-based compound of Formula 1 may have a lower driving voltage.

[0144] In the pyrene-based compound of Formula 1, at least one linker L₁ is necessarily bound between R₁ and the 2nd carbon of the pyrene core. Since the electron-rich pyrene core is separated from the electron-deficient R₁ by the linker L₁, the pyrene-based compound of Formula 1 may have a large gap between the highest occupied molecular orbital (HOMO) and the lowest unoccupied molecular orbital, which consequently may increase a molecular dipole moment. The pyrene-based compound of Formula 1 is apt to be oriented into layers, and thus an organic light-emitting diode including the pyrene-based compound of Formula 1 may have a lower driving voltage and improved lifetime.

[0145] Since R₁ in Formula 1 is bound to the “2nd carbon of the pyrene core” via the linker L₁, an organic light-emitting diode including the pyrene-based compound of Formula 1 may have improved lifetime.

[0146] Therefore, an organic light-emitting diode including the pyrene-based compound of Formula 1 above may have a low driving voltage, a high efficiency, a high luminance, and a long lifetime.

[0147] The pyrene-based compound of Formula 1 may be synthesized by using organic synthesis. A synthesis method of the pyrene-based compound of Formula 1 may be understood by those of ordinary skill in the art from the examples that will be described below.

[0148] The pyrene-based compound of Formula 1 above may be used between a pair of electrodes of an organic light-emitting diode. For example, the pyrene-based compound of Formula 1 may be present in an emission layer and/or an electron transport region between the emission layer and a cathode (for example, a hole blocking layer, an electron injection layer, an electron transport layer, or the like).

[0149] According to another embodiment, an organic light-emitting diode includes a first electrode, a second electrode disposed opposite to the first electrode, and an organic layer disposed between the first electrode and the second electrode, wherein the organic layer includes at least one of the pyrene-based compounds of Formula 1 described above. The organic layer may include a hole transport region between the first electrode and an emission layer, and an electron transport region between the emission layer and the second electrode. The pyrene-based compound of Formula 1 may be present in either the electron transport region or the emission layer, or in both the electron transport region and the emission layer. When the pyrene-based compound of Formula 1 is in both the electron transport region and the emission layer, the pyrene-

based compounds in the electron transport region and the emission layer may be identical to or differ from each other.

[0150] As used herein, “(for example, the organic layer) including at least one pyrene-based compound means that “(the organic layer) including one of the pyrene-based compounds of Formula 1 above, or at least two different pyrene-based compounds of Formula 1 above”.

[0151] In some embodiments, the organic layer may include only Compound 1 above as the pyrene-based compound. In this regard, the Compound 1 may be present in the electron transport layer of the organic light-emitting diode. In some embodiments, the organic layer may include Compounds 1 and 2 as the pyrene-based compound. In this regard, Compounds 1 and 10 may be present in the same layer (for example, in the electron transport layer) or may be present in different layers (for example, in the electron transport layer and the emission layer, respectively).

[0152] A hole transport region in the organic layer may include at least one of a hole injection layer, a hole transport layer, and a functional layer having both hole injection and hole transport capabilities (hereinafter, a H-functional layer), a buffer layer, and an electron blocking layer. The electron transport region in the organic layer may include at least one of a hole blocking layer, and electron transport layer, and an electron injection layer.

[0153] The term “organic layer” as used herein refers to a single layer and/or a plurality of layers disposed between the first and second electrodes of the organic light-emitting diode.

[0154] FIG. 1 is a schematic sectional view of an organic light-emitting diode 10 according to an embodiment. Hereinafter, a structure of an organic light-emitting diode according to an embodiment and a method of manufacturing the same will now be described with reference to FIG. 1.

[0155] The substrate 11 may be any substrate that is used in existing organic light-emitting diodes. In some embodiments the substrate 11 may be a glass substrate or a transparent plastic substrate with strong mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water resistance.

[0156] The first electrode 13 may be formed by depositing or sputtering a first electrode-forming material on the substrate 11. When the first electrode 13 constitutes an anode, a material having a high work function may be used as the first electrode-forming material to facilitate hole injection. The first electrode 13 may be a reflective electrode or a transmission electrode. Transparent and conductive materials such as ITO, IZO, SnO₂, and ZnO may be used to form the first electrode 13. The first electrode 13 may be formed as a reflective electrode using magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag), or the like.

[0157] The first electrode 13 may have a single-layer structure or a multi-layer structure including at least two layers. For example, the first electrode 13 may have a three-layered structure of ITO/Ag/ITO, but is not limited thereto.

[0158] The organic layer 15 may be disposed on the first electrode 13.

[0159] The organic layer 15 may include a hole transport region including a hole injection layer (HIL) and a hole transport layer (HTL) that are sequentially stacked upon one another; an emission layer (EML); and an electron transport


region including an electron transport layer (ETL) and an electron injection layer (EIL) that are sequentially stacked upon one another.

[0160] The HIL may be formed on the first electrode 13 by any of a variety of methods, including vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, and the like.


[0161] When the HIL is formed using vacuum deposition, vacuum deposition conditions may vary depending on the compound that is used to form the HIL, and the desired structure and thermal properties of the HIL to be formed. For example, vacuum deposition may be performed at a temperature of about 100° C. to about 500° C., a pressure of about 10^{-8} torr to about 10^{-3} torr, and a deposition rate of about 0.01 to about 100 Å/sec. However, the deposition conditions are not limited thereto.

[0162] When the HIL is formed using spin coating, the coating conditions may vary according to the compound that is used to form the HIL, and the desired structure and thermal properties of the HIL to be formed. For example, the coating rate may be in the range of about 2000 rpm to about 5000 rpm, and a temperature at which heat treatment is performed to remove a solvent after coating may be in the range of about 80° C. to about 200° C. However, the coating conditions are not limited thereto.


[0163] Non-limiting examples of known hole injecting materials that may be used to form the HIL are N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine (DNTPD), a phthalocyanine compound such as copper phthalocyanine, 4,4',4"-tris(3-methylphenylphenylamino) triphenylamine (m-MTDATA), N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB), TDATA, 2-TNATA, polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), and polyaniline/poly(4-styrenesulfonate) (PANI/PSS).



-continued



TDATA




2-TNATA

[0164] The thickness of the HIL may be about 100 Å to about 10000 Å, and in some embodiments, may be from about 100 Å to about 1000 Å. When the thickness of the HIL is within these ranges, the HIL may have good hole injecting ability without a substantial increase in driving voltage.

[0165] Then, a HTL may be formed on the HIL by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, or the like. When the HTL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL, though the conditions for the deposition and coating may vary according to the material that is used to form the HTL.

[0166] Non-limiting examples of suitable HTL materials are carbazole derivatives, such as N-phenylcarbazole or polyvinylcarbazole, N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1-biphenyl]-4,4'-diamine (TPD), 4,4',4"-tris(N-carba-

zoyl)triphenylamine (TCTA), and N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB).




TPD

[0167] The thickness of the HTL may be from about 50 Å to about 2000 Å, and in some embodiments, may be from about 100 Å to about 1500 Å. When the thickness of the HTL is within these ranges, the HTL may have good hole transporting ability without a substantial increase in driving voltage.

[0168] In some embodiments, the organic light-emitting diode 10 may include the H-functional layer, instead of the HIL and the HTL. The H-functional layer may contain at least one material from each group of the hole injection layer materials and hole transport layer materials. The thickness of the H-functional layer may be from about 100 Å to about 10,000 Å, and in some embodiments, may be from about 100 Å to about 1,000 Å. When the thickness of the H-functional layer is within these ranges, the H-functional layer may have good hole injection and transport capabilities without a substantial increase in driving voltage.


[0169] In some embodiments, at least one of the HIL, HTL, and H-functional layer may include at least one of a compound of Formula 300 below and a compound of Formula 301 below:



Formula 300

-continued

<Formula 301>



[0170] In Formula 300, Ar₁₀₁ and Ar₁₀₂ may be each independently a substituted or unsubstituted C₆-C₆₀ arylene group.

[0171] For example, Ar₁₀₁ and Ar₁₀₂ in Formula 300 may each independently be one selected from a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthrylene group, a fluoranthylene group, a triphenylenylene group, a pyrenylene group, a chrysénylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, and a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthrylene group, a fluoranthylene group, a triphenylenylene group, a pyrenylene group, a chrysénylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, and a C₂-C₆₀ heteroaryl group.

[0172] In Formula 300, xa and xb may be each independently an integer from 0 to 5, for example, may be 0, 1, or 2. For example, xa may be 1, and xb may be 0, but embodiments are not limited thereto.


[0173] In Formulae 300 and 301 above, R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉, and R₁₂₁ to R₁₂₄ may be each independently selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, and a substituted or unsubstituted C₆-C₆₀ arylthio group.

[0174] For example, R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉, and R₁₂₁ to R₁₂₄ may be each independently one selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an

amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, or the like), and a C_1 - C_{10} alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, or the like), a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, and a pyrenyl group, and a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, and a pyrenyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, and a C_1 - C_{10} alkoxy group, but embodiments are not limited thereto.

[0175] In some embodiments, R_{109} in Formula 300 may be one selected from a phenyl group, a naphthyl group, an anthryl group, a biphenyl group, and a pyridinyl group; and a phenyl group, a naphthyl group, an anthryl group, a biphenyl group, and a pyridinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{20} alkyl group, and a substituted or unsubstituted C_1 - C_{20} alkoxy group.


[0176] For example, the compound of Formula 300 may be a compound represented by Formula 300A below:




Formula 300A

[0177] In Formula 300A, R_{101} , R_{111} , R_{112} , and R_{109} may be as defined above.


[0178] In some non-limiting embodiments, at least one of the HIL, HTL, and H-functional layer may include at least one of compounds represented by Formulae 301 to 320 below:




301



302









303



304

-continued

-continued





-continued

-continued



311

313



312


314




-continued

-continued

315





317




318

316




-continued

319




320




[0179] The hole transport region may further include a charge-generating material for improving conductivity of layers, in addition to a hole injection material and/or a hole transport material as those described above.

[0180] The charge-generating material may be, for example, a p-dopant. The p-dopant may be one of quinine derivatives, metal oxides, and compounds with a cyano group, but are not limited thereto. Non-limiting examples of the p-dopant are quinone derivatives such as tetracyanoquinodimethane (TCNQ), 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4-TCNQ), and the like; metal oxides such as tungsten oxide, molybdenum oxide, and the like; and cyano-containing compounds such as Compound 200 below.

Compound 200



<F4-TCNQ>



[0181] When the hole transport region further includes such a charge-generating material as described above, the charge-generating material may be homogeneously dispersed or inhomogeneously distributed in the hole transport region.

[0182] The hole transport region may further include a buffer layer between the HTL and the EML (or between the H-functional layer and the EML).


[0183] The buffer layer may compensate for an optical resonance distance of light according to a wavelength of the light emitted from the EML, and thus may increase efficiency. The buffer layer may include any hole injecting material or hole transporting material that are widely known. In some other embodiments, the buffer layer may include the material as one of the materials in the HTL (or the H-functional layer) underlying the buffer layer.

[0184] Then, the EML may be formed on the hole transport region by using vacuum deposition, spin coating, casting, LB deposition, or the like. When the EML is formed using vacuum deposition or spin coating, the deposition and coating conditions may be similar to those for the formation of the HTL, though the conditions for deposition and coating may vary depending on the material that is used to form the EML.


[0185] The EML may include a host, and a dopant.

[0186] Non-limiting example of the host are Alq3, 4,4'-N,N'-dicarbazole-biphenyl (CBP), poly(n-vinylcarbazole) (PVK), 9,10-di(naphthalene-2-yl)anthracene (DNA), TCTA, 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di-2-naphthylanthracene (TBADN), E3, distyrylarylene (DSA), dmCBP (see a formula below), and Compounds 501 to 509 below.


-continued




TPBI




CBP




dmCBP




TBADN




E3




PVK




ADN



501




502




503


-continued



504




505




506


-continued



507




508



509

[0187] In some embodiments, an anthracene-based compound represented by Formula 400 below may be used as the host.

Formula 400



[0188] In Formula 400, Ar_{111} and Ar_{112} are each independently a substituted or unsubstituted C_6 - C_{60} arylene group;

Ar₁₁₃ to Ar₁₁₆ are each independently a substituted or unsubstituted C₁-C₁₀ alkyl group, or a substituted or unsubstituted C₆-C₆₀ aryl group; and g, h, I, and j are each independently an integer from 0 to 4.

[0189] In some embodiments, Ar₁₁₁ and Ar₁₁₂ in Formula 400 may be each independently a phenylene group, a naphthylene group, a phenanthrenylene group, or a pyrenylene group; or a phenylene group, a naphthylene group, a phenanthrenylene group, a fluorenyl group, or a pyrenylene group that are substituted with at least one of a phenyl group, a naphthyl group, and an anthryl group, but are not limited thereto.


[0190] In Formula 400 above, g, h, I, and j may be each independently 0, 1, or 2.

[0191] In some embodiments, Ar₁₁₃ to Ar₁₁₆ in Formula 400 may each independently be one selected from

[0192] a C₁-C₁₀ alkyl group substituted with at least one of a phenyl group, a naphthyl group, and an anthryl group,


[0193] a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, a phenanthrenyl group, and a fluorenyl group,

[0194] a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, a phenanthrenyl group, and a fluorenyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, a phenanthrenyl group, and a fluorenyl group, and




but embodiments are not limited thereto.


[0195] For example, the anthracene-based compound of Formula 400 may be one of the compounds represented by the following formulae:




-continued




-continued




-continued






-continued





-continued




-continued




-continued





[0196] In some embodiments, an anthracene-based compound represented by Formula 401 below may be used as the host.

Formula 401







[0197] The detailed descriptions of Ar_{122} to Ar_{125} in Formula 401 may be the same as those described above in conjunction with Ar_{113} in Formula 400.

[0198] Ar_{126} and Ar_{127} in Formula 401 above may be each independently a C_1 - C_{10} alkyl group, for example, a methyl group, an ethyl group, or a propyl group.

[0199] In Formula 401, k and l may be each independently an integer from 0 to 4, for example, 0, 1, or 2.

[0200] For example, the anthracene compound of Formula 401 above may be one of the compounds represented by the following formulae, but is not limited thereto:



[0201] When the organic light-emitting diode is a full color organic light-emitting diode, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. In some embodiments, the EML 23 may include a red emission layer, a green emission layer, and/or a blue emission layer that are stacked upon one another to emit white light, but is not limited thereto.


[0202] The pyrene-based compound of Formula 1 may be used as a dopant of the EML. The pyrene-based compound of Formula 1 may also serve as a fluorescent dopant emitting


light based on fluorescence mechanism. In some embodiments, the pyrene-based compound of Formula 1 may serve as a fluorescent dopant emitting blue light, green light, or bluish green light, but not limited thereto.

[0203] Examples of the dopant which can be used with the pyrene-based compound of Formula 1 are as follows.


[0204] At least one of the red EML, the green EML, and the blue EML may include a dopant below (ppy=phenylpyridine).





[0205] Non-limiting examples of the blue dopant are compounds represented by the following formulae.








[0206] Non-limiting examples of a red dopant are compounds represented by the following formulae. For example, the red dopant may be DCM or DCJTb, which will be described later.













[0207] Non-limiting examples of a green dopant are compounds represented by the following formulae. For example, the green dopant may be C545T represented below.



[0208] Non-limiting examples of the dopant for the EML are complexes represented by the following formulae.




-continued




D3

-continued




D9

D4




D10

D5




D11

D6



D12


D7




D13

D8


-continued




D14




D15



D16




D17




D18


-continued




D19




D20



D21









D22




D23

-continued




-continued

D24




D30

D25



D31


D26



D32


D33

D27




D34

D28




D35

D29




-continued




D36


D37




D38




D39




D40




-continued




D41




D42



D43




D44




D45


-continued




D46




D47








D48



D49



D50

Os(fppz)₂(CO)₂Os(fppz)₂(PPh₂Me)₂Os(bppz)₂(PPh₃)₂Os(fptz)₂(PPh₂Me)₂Os(hptz)₂(PPhMe₂)₂

[0209] Non-limiting examples of the dopant for the EML are Os complexes represented by the following formulae.

[0210] When the EML includes both a host and a dopant, the amount of the dopant may be from about 0.01 to about 15

parts by weight based on 100 parts by weight of the host. However, the amount of the dopant is not limited to this range.


[0211] The thickness of the EML may be about 100 Å to about 1000 Å, and in some embodiments, may be from about 200 Å to about 600 Å. When the thickness of the EML is within these ranges, the EML may have good light emitting ability without a substantial increase in driving voltage.

[0212] Then, an ETL may be formed on the EML by vacuum deposition, spin coating, casting, or the like. When the ETL is formed using vacuum deposition or spin coating, the deposition and coating conditions may be similar to those for the formation of the HIL, though the deposition and coating conditions may vary depending on the compound that is used to form the ETL. A material for the ETL may be, for example, the pyrene-based compound of Formula 1 described above.

[0213] The thickness of the ETL may be from about 100 Å to about 1,000 Å, and in some embodiments, may be from about 150 Å to about 500 Å. When the thickness of the ETL is within these ranges, the ETL may have satisfactory electron transporting ability without a substantial increase in driving voltage.

[0214] In some embodiments the ETL may further include a metal-containing material, in addition to the above-described pyrene-based compound of Formula 1.

[0215] The metal-containing material may include a lithium (Li) complex. Non-limiting examples of the Li complex are lithium quinolate (LiQ) and Compound 203 below:



Compound 203

[0216] Then, an EIL, which facilitates injection of electrons from the cathode, may be formed on the ETL. Any suitable electron-injecting material may be used to form the EIL.

[0217] Non-limiting examples of materials for forming the EIL include LiF, NaCl, CsF, Li₂O, and BaO. The deposition and coating conditions for forming the EIL 18 may be similar to those for the formation of the HIL, though the deposition and coating conditions may vary according to the material that is used to form the EIL 18.


[0218] The thickness of the EIL may be from about 1 Å to about 100 Å, and in some embodiments, may be from about 3 Å to about 90 Å. When the thickness of the EIL is within these ranges, the EIL may have satisfactory electron injection ability without a substantial increase in driving voltage.

[0219] The second electrode 17 is disposed on the organic layer 15. The second electrode 17 may be a cathode that is an electron injection electrode. A material for forming the second electrode 17 may be a metal, an alloy, an electro-conductive compound, which have a low work function, or a mixture thereof. In this regard, the second electrode 9 may comprise lithium (Li), magnesium (Mg), aluminum (Al), aluminum

(Al)-lithium (Li), calcium (Ca), magnesium (Mg)-indium (In), magnesium (Mg)-silver (Ag), or the like, and may be formed as a thin film type transmission electrode. In some embodiments, to manufacture a top-emission light-emitting diode, the transmission electrode may comprise indium tin oxide (ITO) or indium zinc oxide (IZO).

[0220] Although the organic light-emitting diode of FIG. 1 is described above, the present embodiments are not limited thereto.

[0221] When a phosphorescent dopant is used in the EML, a HBL may be formed between the HTL and the EML or between the H-functional layer and the EML by using vacuum deposition, spin coating, casting, Langmuir-Blodgett (LB) deposition, or the like, in order to prevent diffusion of triplet excitons or holes into the ETL. When the HBL is formed using vacuum deposition or spin coating, the conditions for deposition and coating may be similar to those for the formation of the HIL, although the conditions for deposition and coating may vary according to the material that is used to form the HBL. Any known hole-blocking material may be used. Non-limiting examples of hole-blocking materials are oxadiazole derivatives, triazole derivatives, and phenanthroline derivatives. For example, bathocuproine (BCP) represented by the following formula may be used as a material for forming the HBL.



[0222] BCP

[0223] The thickness of the HBL may be from about 20 Å to about 1000 Å, and in some embodiments, may be from about 30 Å to about 300 Å. When the thickness of the HBL is within these ranges, the HBL may have improved hole blocking ability without a substantial increase in driving voltage.

[0224] As used herein, the unsubstituted C₁-C₆₀ alkyl group (or a C₁-C₆₀ alkyl group) may be a linear or branched C₁-C₆₀ alkyl group, including a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. The substituted C₁-C₆₀ alkyl group may include at least one substituent selected from a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group; a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof; a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₃-C₁₀ heterocycloalk-

enyl group, a C₆-C₆₀aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, and a C₂-C₆₀ heteroaryl group; a C₃-C₁₀cycloalkyl group, a C₃-C₁₀heterocycloalkyl group, a C₃-C₁₀cycloalkenyl group, a C₃-C₁₀heterocycloalkenyl group, a C₆-C₆₀aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, and a C₂-C₆₀ heteroaryl group that are substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group; and —N(Q₁₁)(Q₁₂) and —Si(Q₁₁)(Q₁₂)(Q₁₃) (where Q₁₁ and Q₁₂ may be each independently a C₆-C₆₀aryl group, or a C₂-C₆₀heteroaryl group, and Q₁₃ to Q₁₅ may be each independently a C₁-C₆₀alkyl group, a C₁-C₆₀alkoxy group, a C₆-C₆₀aryl group, or a C₂-C₆₀heteroaryl group), but is not limited thereto.

[0225] As used herein, the unsubstituted C₁-C₆₀alkoxy group (or a C₁-C₆₀alkoxy group) is represented by —OA (where A indicates a C₁-C₆₀alkyl group as described above), and may be, for example, a methoxy group, an ethoxy group, or an isopropoxy group. At least one hydrogen atoms of these alkyl groups may be substituted with those substituents described above in conjunction with the substituted C₁-C₆₀alkyl group.

[0226] As used herein, the unsubstituted C₂-C₆₀ alkenyl group (or a C₂-C₆₀ alkenyl group) means as a C₂-C₆₀ alkyl group as described above with at least one carbon double bond in the middle or terminal thereof. Examples of the alkenyl group are an ethenyl group, a propenyl group, a butenyl group, and the like. At least one hydrogen atom in the unsubstituted C₂-C₆₀ alkenyl group may be substituted with those substituents described above in conjunction with the substituted C₁-C₆₀alkyl group.

[0227] The unsubstituted C₂-C₆₀ alkynyl group is a C₂-C₆₀ alkyl group having at least one carbon-carbon triple bond in the center or at a terminal thereof. Examples of the unsubstituted C₂-C₆₀ alkynyl group are an ethynyl group, a propynyl group, and the like. At least one hydrogen atom in the alkynyl group may be substituted with those substituents described above in conjunction with the substituted C₁-C₆₀alkyl group.

[0228] The unsubstituted C₆-C₆₀ aryl group is monovalent carbocyclic aromatic system having 6 to 60 carbon atoms including at least one aromatic ring. The unsubstituted C₆-C₆₀ arylene group is a divalent group having a divalent carbocyclic aromatic system having 6 to 60 carbon atoms including at least one aromatic ring. When the aryl group and the arylene group have at least two rings, they may be fused to each other via a single bond. At least one hydrogen atom in the aryl group and the arylene group may be substituted with those substituents described above in conjunction with the C₁-C₆₀alkyl group.

[0229] Examples of the substituted or unsubstituted C₆-C₆₀ aryl group are a phenyl group, a C₁-C₁₀alkylphenyl group (e.g., an ethylphenyl group), a C₁-C₁₀alkylbiphenyl group (e.g., an ethylbiphenyl group), a halophenyl group (e.g., an o-, m- or p-fluorophenyl group and a dichlorophenyl group), a

dicyanophenyl group, a trifluoromethoxyphenyl group, an o-, m- or p-tolyl group, an o-, m- or p-cumenyl group, a mesityl group, a phenoxyphenyl group, a (α,α-dimethylbenzene) phenyl group, a (N,N'-dimethyl)aminophenyl group, a (N,N'-diphenyl)aminophenyl group, a pentalenyl group, an indenyl group, a naphthyl group, a halonaphthyl group (e.g., a fluoronaphthyl group), a C₁-C₁₀alkylnaphthyl group (e.g., a methylnaphthyl group), a C₁-C₁₀alkoxynaphthyl group (e.g., a methoxynaphthyl group), an anthracenyl group, an azulenyl group, a heptalenyl group, an acenaphthyl group, a phenalenyl group, a fluorenyl group, an anthraquinolinyl group, a methylanthryl group, a phenanthryl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, an ethyl-chrysenyl group, a picenyl group, a perylenyl group, a chloroperlylenyl group, a pentaphenyl group, a pentacenyl group, a tetraphenylenyl group, a hexaphenyl group, hexacenyl group, a rubicenyl group, a coronenyl group, a trinaphthylenyl group, a heptaphenyl group, a heptacenyl group, a pyranthrenyl group, and an ovalenyl group. Examples of the substituted C₆-C₆₀ aryl group may be inferred based on those of the unsubstituted C₆-C₆₀ aryl group and the substituted C₁-C₃₀alkyl group described above. Examples of the substituted or unsubstituted C₆-C₆₀ arylene group may be inferred based on those examples of the substituted or unsubstituted C₆-C₆₀ aryl group described above.

[0230] The unsubstituted C₂-C₆₀ heteroaryl group is a monovalent group having at least one aromatic ring having at least one of the heteroatoms selected from the group consisting of N, O, P, and S. The unsubstituted C₂-C₆₀ heteroarylene group is a divalent group having at least one aromatic ring having at least one of the heteroatoms selected from the group consisting of N, O, P, and S. In this regard, when the heteroaryl group and the heteroarylene group have at least two rings, they may be fused to each other via a single bond. At least one hydrogen atom in the heteroaryl group and the heteroarylene group may be substituted with those substituents described with reference to the C₁-C₆₀alkyl group.

[0231] Examples of the unsubstituted C₂-C₆₀ heteroaryl group are a pyrazolyl group, an imidazolyl group, an oxazolyl group, a thiazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridinyl group, a pyridazinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, an indolyl group, a quinolinyl group, an isoquinolinyl group, a benzoimidazolyl group, an imidazopyridinyl group and an imidazopyrimidinyl group. Examples of the substituted or unsubstituted C₂-C₆₀ heteroarylene group may be inferred based on those examples of the substituted or unsubstituted C₂-C₆₀ arylene group described above.

[0232] The substituted or unsubstituted C₆-C₆₀ aryloxy group indicates —OA₂ (where A₂ is a substituted or unsubstituted C₆-C₆₀ aryl group described above). The substituted or unsubstituted C₅-C₆₀ arylthiol group indicates —SA₃ (where A₃ is a substituted or unsubstituted C₆-C₆₀ aryl group described above).

[0233] Hereinafter, the present embodiments will be described in detail with reference to the following synthesis examples and other examples. However, these examples are for illustrative purposes only and are not intended to limit the scope of the present embodiments.


EXAMPLES

Synthesis Example 1

Synthesis of Compound 2

[0234] Compound 2 was synthesized according to Reaction Scheme 1 below:

Reaction Scheme 1



Ⓜ indicates text missing or illegible when filed

Synthesis of Intermediate I-2(1)

[0235] 4.04 g (20.0 mmol) of pyrene, 5.59 g (22.0 mmol) of bis(pinacolato)diborane, 0.66 g (1.0 mmol) of 1,5-cyclooctadiene(methoxy)iridium(I) dimer($[\text{Ir}(\text{OMe})\text{COD}]_2$), and 0.54 g (2.0 mmol) of 4,4'-di-tert-butyl-2,2'-bipyridine (dtbpy) were mixed with 80 mL of cyclohexane to obtain a mixture, which was then stirred at about 80 °C for about 24 hours. The resulting mixture was cooled down to room temperature, followed by evaporation to remove the solvent. The residue was separated and purified by silica gel column chromatography to obtain 4.26 g of Intermediate I-1 (Yield: 65%). This compound was identified using liquid chromatography-mass spectroscopy (LC-MS).

[0236] $\text{C}_{22}\text{H}_{21}\text{BO}_2$ M+329.1

Synthesis of Intermediate I-2(2)

[0237] 3.28 g (10.0 mmol) of Intermediate I-2, 1.85 g (10.0 mmol) of 4-bromobenzaldehyde, 0.58 g (0.5 mmol) of tetrakis(triphenylphosphine)palladium ($\text{Pd}(\text{PPh}_3)_4$), and 4.14 g (30.0 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solution of tetrahydrofuran (THF) and H_2O (2:1 by volume), and then stirred at about 80 °C for about 5 hours. The reaction solution was cooled down to room temperature, followed by three times of extraction with 60 mL of water and 60 mL of diethyl ether. An organic layer was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.14 g of Intermediate I-2(2) (Yield: 70%). This compound was identified using LC-MS.

[0238] $\text{C}_{23}\text{H}_{14}\text{O}$ M+307.1

Synthesis of Compound 2

[0239] 2.14 g (7.0 mmol) of Intermediate I-2(2) and 1.29 g (7 mmol) of N-phenyl-1,2-diaminobenzene were mixed with 50 mL of toluene and 10 mL of acetic acid, and then heated while stirring for about 24 hours. The reaction solution was cooled down to room temperature, followed by adding distilled water to obtain a precipitate, which was then filtered. An organic layer was collected and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.47 g of Compound 2 (Yield: 75%). This compound was identified using mass spectroscopy/fast atom bombardment (MS/FAB) and proton nuclear magnetic resonance (^1H NMR).

[0240] $\text{C}_{35}\text{H}_{22}\text{N}_2$ cal. 470.18 found 471.18


[0241] ^1H NMR (400 MHz, CDCl_3) δ =8.30 (s, 2H), 8.23 (d, 2H), 8.09-8.01 (m, 3H), 7.84-7.71 (m, 7H), 7.66 (d, 1H), 7.58-7.55 (m, 2H), 7.45-7.35 (m, 3H), 7.32-7.20 (m, 2H)


Synthesis Example 2

Synthesis of Compound 6

[0242] Compound 2 was synthesized according to Reaction Scheme 2 below:

Reaction Scheme 2





Synthesis of Intermediate I-6(1)

[0243] 3.56 g (20.0 mmol) of Intermediate I-2, 3.70 g (20.0 mmol) of 4-bromobenzoic acid methylester, 1.16 g (1 mmol) of tetrakis(triphenylphosphine)palladium ($\text{Pd}(\text{PPh}_3)_4$), and 8.28 g (60.0 mmol) of K_2CO_3 were dissolved in 150 mL of a mixed solution of THF and H_2O (2:1 by volume), and then stirred at about 80 °C for about 5 hours. The reaction solution was cooled down to room temperature, followed by three times of extraction with 60 mL of water and 100 mL of diethyl ether. An organic phase was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 5.04 g of Intermediate I-6(1) (Yield: 75%). This compound was identified using LC-MS.

[0244] $\text{C}_{24}\text{H}_{16}\text{O}_2$ M+337.1

Synthesis of Intermediate i-6(2)

[0245] 5.04 g (15 mmol) of Intermediate I-6(1) was dissolved in 3 mL (60 mmol) of hydrazine monohydrate were dissolved in 100 mL of methanol, and then stirred at room temperature for about 2 hours and further at about 80 °C. for about 20 hours. The reaction solution was cooled down to room temperature to precipitate a white solid, which was then filtered, washed with methanol, and dried to obtain 4.54 g of Intermediate I-6(2) (Yield: 90%). This compound was identified using LC-MS.

[0246] $\text{C}_{23}\text{H}_{16}\text{N}_2\text{O}$ M+337.1

Synthesis of Intermediate I-6(3)

[0247] After 4.54 g (13.5 mmol) of Intermediate I-6(3) and 4.6 mL (26.4 g) of diisopropylethylamine were dissolved in 50 mL of xylene, 2.4 mL (20.25 mmol) of benzoyl chloride was dropwise added thereto at about 0 °C. After 20 minutes the solution was reacted at about 140 °C, followed by cooling to room temperature to precipitate a white solid, which was then filtered, washed, and then dried to obtain 4.3 g of Intermediate I-6(3) (Yield: 73%). This compound was identified using LC-MS.

[0248] $\text{C}_{30}\text{H}_{20}\text{N}_2\text{O}_2$ M+441.1

Synthesis of Compound 6

[0249] After 3.96 g (9 mmol) of Intermediate I-6(3), 4.70 g (54 mmol) of aniline were dispersed in 1,2-dichlorobenzene, 0.84 mL (9 mmol) of POCl_3 was slowly dropwise added thereto. The reaction solution was stirred at about 180 °C for about 4 hours for reaction, followed by cooling to room temperature to precipitate a white solid, which was then filtered. The resulting solid was dispersed in a 2M NaOH solution, and then heated at about 70 °C while stirring, followed by filtering to obtain a solid, which was then washed with water and dried to obtain 3.05 g of Compound 6 (Yield: 68%). This compound was identified using MS/FAB and ^1H NMR.


[0250] $\text{C}_{36}\text{H}_{23}\text{N}_3$ cal. 497.19 found 498.29

[0251] ^1H NMR (400 MHz, CDCl_3) δ =8.30 (s, 2H), 8.23 (d, 2H), 8.09-8.01 (m, 5H), 7.90 (d, 2H), 7.82 (d, 2H), 7.69-7.65 (m, 2H), 7.58-7.50 (m, 3H), 7.42-7.39 (m, 2H), 7.37-7.28 (m, 3H)

Synthesis Example 3

Synthesis of Compound 8

[0252] Compound 8 was synthesized according to Reaction Scheme 3 below:



[0253] 3.06 g (10.0 mmol) of Intermediate I-2(2) and 1.31 g (12 mmol) of 2-aminophenol were dissolved in 80 mL of acetic acid, and then stirred at room temperature for about 30 minutes. 5.32 g (12 mmol) of lead(IV) acetate was added into

the mixture, and stirred at 50° C. for 1 hour. The resulting reaction product was added with water, followed by extraction with ethyl acetate and evaporation under reduced pressure to remove the solvent. The residue was purified by column separation, and dried to obtain 1.97 g of Compound 8 as white solid (Yield: 50%). This compound was identified using MS/FAB and ¹H NMR.



[0254] C₂₉H₁₇NO cal. 395.13 found 396.23

[0255] ¹H NMR (400 MHz, CDCl₃) δ=8.32-8.29 (m, 4H), 8.22 (d, 2H), 8.13-8.01 (m, 5H), 7.82 (d, 2H), 7.72 (d, 1H), 7.43 (d, 2H), 7.30-7.23 (m, 1H)

Synthesis Example 4

Synthesis of Compound 12

[0256] Intermediate I-12(5) was synthesized according to Reaction Scheme 4 below:



I-12(5)

Ⓢ indicates text missing or illegible when filed

Synthesis of Intermediate I-12(1)

[0257] 4.04 g (20 mmol) of pyrene was dissolved in 50 mL of methyl chloroform (MC) to obtain a reaction solution, which was then added with 100 mg (0.2 mmol) of 10% palladium. The reaction solution was stirred in a hydrogen atmosphere for about 12 hours, and then filtered through Celite to obtain palladium precipitate, followed by drying in a vacuum to remove the solvent and obtain 3.50 g of Intermediate I-12(1) (Yield: 85%). This compound was identified using LC-MS.

[0258] C₁₆H₁₄ M+207.1

Synthesis of Intermediate I-12(2)

[0259] 3.56 g (20 mmol) of N-bromosuccinimide (NBS) was completely dissolved in 50 mL of dimethylformamide (DMF) to obtain a solution, which was then added with 2.06 g (10 mmol) of Intermediate I-12(1) and stirred at room temperature for about 24 hours. The reaction solution was extracted twice with 50 mL of water and 50 mL of dichloromethane. An organic layer was collected and dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.51 g of Intermediate I-12(2) (Yield: 69%). This compound was identified using LC-MS.

[0260] C₁₆H₁₂Br₂ M+362.9

Synthesis of Intermediate I-12(3)

[0261] 3.64 g (10 mmol) of Intermediate I-12(2) was dissolved in 50 mL of MC to obtain a reaction solution, which was then added with 2.50 g (11 mmol) of 2,3-dichloro-5,6-dicyano-p-quinone. The reaction solution was stirred for about 12 hours, and then filtered through Celite to obtain palladium precipitate, followed by drying in a vacuum to remove the solvent and obtain 2.74 g of Intermediate I-12(3) (Yield: 76%). This compound was identified using LC-MS.

[0262] C₁₆H₈Br₂ M+358.9

Synthesis of Intermediate I-12(4)

[0263] 3.64 g (10 mmol) of intermediate I-12(3) and 6.25 mL (10 mmol) of n-BuLi (1.60M hexane solution) were reacted with THF at about -78 °C for 3 hours. The reaction solution was added at about -78 °C with 2.04 g (12 mmol) of 2-isopropylboronic acid pinacol ester, and then stirred at room temperature for about 12 hours, followed by adding 5 mL of a 1N HCl aqueous solution into the reaction solution. After an organic layer was separated from the reaction solution, the remaining aqueous layer was extracted twice with 100 mL of dichloromethane to obtain the organic layer. The organic layer was dried using magnesium sulfate to evaporate

the solvent. The residue was separated and purified using silica gel column chromatography to obtain 3.20 g of Intermediate I-12(4) (Yield: 78%). This compound was identified using LC-MS.

[0264] $C_{22}H_{20}BBrO_2$ M+407.0

Synthesis of Intermediate I-12(5)

[0265] 4.11 g (10 mmol) of Intermediate I-12(4), 2.58 g (15 mmol) of 2-naphthyl boronic acid (Compound A-12), 0.29 g (0.25 mmol) of tetrakis(triphenylphosphine)palladium (Pd(PPh₃)₄), and 0.62 g (4.48 mmol) of K₂CO₃ were dissolved in 60 mL of a mixed solution of THF and H₂O (2:1 by volume), and then stirred at about 70 °C for about 5 hours. The reaction solution was cooled down to room temperature, and 40 mL of water was added thereto, followed by three times of extraction with 50 mL of ethylether. An organic layer was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 3.39 g of Intermediate I-12(5) (Yield: 74%). This compound was identified using LC-MS.

[0266] $C_{32}H_{27}BO_2$ M+455.2

Synthesis of Compound 12

[0267] Compound 12 was synthesized in the same manner as in Synthesis Example 1, except that Intermediate I-12(5) instead of Intermediate I-2(1) was used. This compound was identified using MS/FAB and ¹H NMR.

[0268] $C_{45}H_{28}N_2$ cal. 596.23 found 597.23


[0269] ¹H NMR (400 MHz, CDCl₃) δ=8.37 (s, 2H), 8.31 (s, 2H), 8.24 (s, 1H), 8.02-7.92 (m, 7H), 7.86 (d, 1H), 7.80-7.72 (m, 5H), 7.66 (d, 1H), 7.62-7.49 (m, 4H), 7.44-7.36 (m, 3H), 7.32-7.21 (m, 2H)

Synthesis Example 5


Synthesis of Compound 16

Synthesis of Intermediate I-16

[0270]



I-16



[0271] Intermediate I-16 was synthesized in the same manner as in the synthesis of Intermediate I-12(5) in Synthesis Example 4, except that Compound A-16 instead of Compound A-12 was used. This compound was identified using LC-MS.

[0272] $C_{32}H_{33}BO_2$ M+461.2

Synthesis of Compound 16

[0273] Compound 16 was synthesized in the same manner as in Synthesis Example 2, except that Intermediate I-16 instead of Intermediate I-2(1) was used. This compound was identified using MS/FAB and ¹H NMR.

[0274] $C_{46}H_{35}N_3$ cal. 629.28 found 629.28


[0275] ¹H NMR (400 MHz, CDCl₃) δ=8.31 (s, 2H), 8.24 (s, 2H), 8.07 (d, 2H), 7.94 (d, 4H), 7.89 (d, 2H), 7.70-7.65 (m, 2H), 7.62-7.51 (m, 5H), 7.42-7.40 (m, 2H), 7.37-7.28 (m, 5H), 1.39 (s, 9H)

Synthesis Example 6


Synthesis of Compound 18

Synthesis of Intermediate I-18

[0276]



I-18



[0277] Intermediate I-18 was synthesized in the same manner as in the synthesis of Intermediate I-12(5) in Synthesis Example 4, except that Compound A-18 instead of Compound A-12 was used. This compound was identified using LC-MS.

[0278] $C_{29}H_{24}BNO_2$ M+430.2

Synthesis of Compound 18

[0279] Compound 18 was synthesized in the same manner as in Synthesis Example 3, except that Intermediate I-18 instead of Intermediate I-2(1) was used. This compound was identified using MS/FAB and ¹H NMR.


[0280] $C_{36}H_{20}N_2O$ cal. 496.16 found 497.16

[0281] ¹H NMR (400 MHz, CDCl₃) δ=8.32-8.29 (m, 6H), 8.12 (d, 2H), 7.94 (s, 4H), 7.77 (d, 2H), 7.71 (d, 1H), 7.65 (d, 2H), 7.43 (d, 2H), 7.29-7.23 (m, 1H)

Synthesis Example 7

Synthesis of Compound 22

[0282]



[0283] Compound 22 was synthesized in the same manner as in Synthesis Example 4, except that Compound A-22 instead of Compound A-12 in the synthesis of Intermediate I-12(5) was used. This compound was identified using MS/FAB and ^1H NMR.


[0284] $\text{C}_{50}\text{H}_{34}\text{N}_2$ cal. 662.27 found 663.29

[0285] ^1H NMR (400 MHz, CDCl_3) δ =8.31 (s, 2H), 8.14 (s, 2H), 8.00-7.92 (m, 5H), 7.81-7.71 (m, 8H), 7.66 (d, 1H), 7.58-7.53 (m, 2H), 7.44-7.28 (m, 5H), 7.25-7.21 (m, 1H), 7.15-7.09 (m, 2H), 1.57 (s, 6H)

Synthesis Example 8

Synthesis of Compound 26

[0286]



A-26

[0287] Compound 26 was synthesized in the same manner as in Synthesis Example 5, except that Compound A-26 instead of Compound A-16 in the synthesis of Intermediate I-16 was used. This compound was identified using MS/FAB and ^1H NMR.


[0288] $\text{C}_{48}\text{H}_{29}\text{N}_3\text{S}$ cal. 679.21 found 680.23

[0289] ^1H NMR (400 MHz, CDCl_3) δ =8.57-8.55 (m, 1H), 8.31 (s, 2H), 8.22 (s, 2H), 8.11-8.05 (m, 3H), 8.00-7.88 (m, 8H), 7.79 (d, 1H), 7.70-7.63 (m, 2H), 7.58-7.50 (m, 4H), 7.46-7.28 (m, 6H)

Synthesis Example 9

Synthesis of Compound 28

[0290]



A-28

[0291] Compound 28 was synthesized in the same manner as in Synthesis Example 6, except that Compound A-28 instead of Compound A-18 in the synthesis of Intermediate I-18 was used. This compound was identified using MS/FAB and ^1H NMR.


[0292] $\text{C}_{41}\text{H}_{23}\text{NOS}$ cal. 577.15 found 578.25

[0293] ^1H NMR (400 MHz, CDCl_3) δ =8.32-8.29 (m, 6H), 8.17-8.10 (m, 4H), 7.98-7.84 (m, 6H), 7.72 (d, 1H), 7.57-7.53 (m, 1H), 7.45-7.37 (m, 4H), 7.29-7.23 (m, 1H)

Synthesis Example 10

Synthesis of Compound 32

[0294]



A-32

[0295] Compound 32 was synthesized in the same manner as in Synthesis Example 4, except that Compound A-32 instead of Compound A-12 in the synthesis of Intermediate I-12(5) was used. This compound was identified using MS/FAB and ^1H NMR.


[0296] $\text{C}_{44}\text{H}_{27}\text{N}_3$ cal. 597.22. found 598.32

[0297] ^1H NMR (400 MHz, CDCl_3) δ =8.99 (m, 1H), 8.39-8.06 (m, 15H), 7.84-7.59 (m, 4H), 7.41-7.22 (m, 7H)


Synthesis Example 11

Synthesis of Compound 5

[0298]



I-2(1)



A-5

[0299] 3.28 g (10.0 mmol) of Intermediate I-2(1), 3.01 g (10.0 mmol) of Compound A-5, 0.58 g (0.5 mmol) of tetrakis(triphenylphosphine)palladium ($\text{Pd}(\text{PPh}_4)_4$), and 4.14 g (30.0 mmol) of K_2CO_3 were dissolved in 60 mL of a mixed solution of THF and H_2O (2:1 by volume), and then stirred at about 80 $^\circ\text{C}$ for about 5 hours. The reaction solution was cooled down to room temperature, followed by three times of extraction with 60 mL of water and 60 mL of diethyl ether. An organic layer was collected, and was dried using magnesium sulfate to evaporate the solvent. The residue was separated and purified using silica gel column chromatography to obtain 2.95 g of Compound 5 (Yield: 70%). This compound was identified using MS/FAB and ^1H NMR.



[0300] $\text{C}_{30}\text{H}_{18}\text{N}_2\text{O}$ cal. 422.14. found 423.15

[0301] ^1H NMR (400 MHz, CDCl_3) δ =8.29 (s, d, m, 4H), 8.09-8.00 (m, 5H), 7.82 (d, 2H), 7.60-7.52 (m, 3H)

Synthesis Example 12

Synthesis of Compound 13

[0302]



Synthesis of Intermediate I-13

[0303] Intermediate I-13 was synthesized in the same manner as in the synthesis of Intermediate I-12(4) in Synthesis Example 4, except that Compound A-13(1) instead of Compound A-12 was used. This compound was identified using LC-MS.

[0304] $C_{32}H_{33}BO_2$ M+461.2

Synthesis of Compound 13

[0305] Compound 13 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Intermediate I-13 and Compound A-13(2) instead of Intermediate I-2(1) and Compound A-5, respectively, were used. This compound was identified using MS/FAB and 1H NMR.


[0306] $C_{43}H_{37}SiN_3O$ cal. 619.24. found 620.24

[0307] 1H NMR (400 MHz, $CDCl_3$) δ =9.07 (s, 1H), 8.60 (d, 1H), 8.31 (s, 2H), 8.15 (s, 2H), 7.96 (s, 4H), 7.94 (s, 4H), 7.85 (d, 2H), 7.67 (d, 2H), 7.56 (d, 2H), 7.45-7.37 (m, 3H), 7.18-7.15 (m, 1H), 0.35 (s, 9H)

Synthesis Example 13

Synthesis of Compound 19

[0308]



Synthesis of Intermediate I-19(5)

[0309] Intermediate I-19(5) was synthesized in the same manner as in the synthesis of Intermediate I-12(5) in Synthesis Example 4, except that 2-pyridine boronic acid instead of Compound A-12 was used.

Synthesis of Intermediate I-19(6)

[0310] Intermediate I-19(6) was synthesized in the same manner as in the synthesis of Intermediate I-2(2) in Synthesis Example 1, except that Intermediate I-19(5) instead of Intermediate I-2(1) was used.

Synthesis of Compound 19

[0311] Compound 19 was synthesized in the same manner as in the synthesis of Compound 8 in Synthesis Example 3, except that Intermediate I-19(6) and 2-aminothiophenol instead of Intermediate I-2(2) and 2-aminophenol, respectively, were used. This compound was identified using MS/FAB and 1H NMR.


[0312] $C_{33}H_{21}SN_2$ cal. 488.13. found 489.15

[0313] 1H NMR (400 MHz, $CDCl_3$) δ =8.67 (dd, 1H), 8.51 (s, 2H), 8.31 (s, 2H), 8.28-8.25 (m, 2H), 8.18 (d, 2H), 8.04-7.99 (m, 3H), 7.89-7.82 (m, 4H), 7.77-7.73 (m, 1H), 7.47-7.27 (m, 3H)

Synthesis Example 14


Synthesis of Compound 31

[0314]



-continued

A-31



[0315] Compound 31 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Intermediate I-31 and Compound A-31 instead of Intermediate I-2(1) and Compound A-5, respectively, were used. This compound was identified using MS/FAB and ^1H NMR.

[0316] $\text{C}_{34}\text{H}_{27}\text{N}_3$ cal. 597.22. found 598.32


[0317] ^1H NMR (400 MHz, CDCl_3) δ =8.61 (s, 2H), 8.28 (s, 2H), 8.25-8.19 (m, 4H), 8.08-7.99 (m, 5H), 7.86-7.63 (m, 7H), 7.41-7.20 (m, 7H)

Synthesis Example 15


Synthesis of Compound 34

[0318]

I-34



A-34



[0319] Compound 34 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Intermediate I-34 and Compound A-34 instead of Intermediate I-2(1) and Compound A-5, respectively, were used. This compound was identified using MS/FAB and ^1H NMR.

[0320] $\text{C}_{43}\text{H}_{30}\text{N}_2$ cal. 574.24. found 575.34


[0321] ^1H NMR (400 MHz, CDCl_3) δ =8.72 (s, 1H), 8.29 (s, 2H), 7.98-7.69 (m, 4H), 7.89-7.82 (m, 4H), 7.77-7.72 (m, 2H), 7.66 (d, 1H), 7.48-7.34 (m, 9H), 6.90 (t, 1H), 2.29 (s, 3H), 2.19 (s, 3H)

Synthesis Example 16

Synthesis of Compound 43

[0322]

A-43



[0323] Compound 43 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Compound A-43 instead of Intermediate A-5 was used. This compound was identified using MS/FAB and ^1H NMR.

[0324] $\text{C}_{46}\text{H}_{28}\text{N}_4$ cal. 636.23. found 637.25


[0325] ^1H NMR (400 MHz, CDCl_3) δ =9.07 (s, 1H), 8.60 (d, 1H), 8.34 (s, 2H), 8.24-8.20 (m, 4H), 8.09-8.01 (m, 3H), 7.87-7.83 (m, 4H), 7.77-7.71 (m, 2H), 7.51-7.18 (m, 10H), 6.97 (t, 1H)

Synthesis Example 17

Synthesis of Compound 44

[0326]

A-44




[0327] Compound 44 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Compound A-44 instead of Compound A-5 was used. This compound was identified using MS/FAB and ^1H NMR.

[0328] $\text{C}_{46}\text{H}_{28}\text{N}_4$ cal. 584.23. found 585.34

[0329] ^1H NMR (400 MHz, CDCl_3) δ =8.23-8.21 (m, 4H), 8.09-8.1 (m, 3H), 7.93 (d, 1H), 7.87-7.82 (m, 3H), 7.69 (d, 1H), 7.56 (d, 1H), 7.34-7.27 (m, 4H), 7.22 (m, 2H), 7.15-7.06 (m, 9H)

Synthesis Example 18
Synthesis of Compound 47

[0330]





[0331] Compound 47 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Compound A-47 instead of Compound A-5 was used. This compound was identified using MS/FAB and ^1H NMR.

[0332] $\text{C}_{36}\text{H}_{20}\text{SON}_2$ cal. 528.13, found 529.25

[0333] ^1H NMR (400 MHz, CDCl_3) δ =8.41 (s, 2H), 8.23-8.20 (m, 5H), 8.13-8.01 (m, 6H), 7.96 (d, 1H), 7.87 (s, 1H), 7.84 (s, 1H), 7.73 (m, 1H), 7.58-7.53 (m, 2H), 7.46-7.41 (m, 1H)

Synthesis Example 19
Synthesis of Compound 53

[0334]



2-TNATA

NPB

[0335] Compound 53 was synthesized in the same manner as in the synthesis of Compound 5 in Synthesis Example 11, except that Intermediate I-57 instead of Intermediate I-2(1), and 2 equivalents of Compound A-5 were used. This compound was identified using MS/FAB and ^1H NMR.

[0336] $\text{C}_{44}\text{H}_{24}\text{O}_2\text{N}_4$ cal. 642.21, found 643.21

[0337] ^1H NMR (400 MHz, CDCl_3) δ =8.31 (s, 4H), 8.18-8.12 (m, 8H), 8.04-8.00 (m, 4H), 7.94 (s, 4H), 7.60-7.52 (m, 6)

Example 1



[0338] To manufacture an anode, a corning 15 Ω/cm^2 (1200 $\square$) ITO glass substrate was cut to a size of 50 mm $\times$ 50 mm $\times$ 0.7 mm and then sonicated in isopropyl alcohol and pure water each for five minutes, and then cleaned by irradiation of ultraviolet rays for 30 minutes and exposure to ozone. The resulting glass substrate was loaded into a vacuum deposition device.

[0339] 2-TNATA was deposited on the ITO layer (anode) to form an HIL having a thickness of about 600 $\square$, and then NPB was deposited on the HIL to form a HTL having a thickness of about 300 $\square$.

[0340] 9,10-di-naphthalene-2-yl-anthracene (ADN, host) and DPAVB (dopant) were co-deposited on the HTL in a weight ratio of about 98:2 to form an EML having a thickness of about 300 $\square$.

[0341] Then, Compound 2 was deposited on the EML to form an ETL having a thickness of about 300 $\square$, and then LiF was deposited on the ETL to form an EIL having a thickness of about 10 $\square$. Then, Al was deposited on the EIL to form a second electrode (cathode) having a thickness of about 3000 $\square$, thereby completing the manufacture of an organic light-emitting diode.

-continued



Example 2

[0342] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 8 instead of Compound 2 was used to form the ETL.

Example 3

[0343] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 12 instead of Compound 2 was used to form the ETL.

Example 4

[0344] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 16 instead of Compound 2 was used to form the ETL.

Example 5

[0345] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 18 instead of Compound 2 was used to form the ETL.

Example 6

[0346] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 19 instead of Compound 2 was used to form the ETL.

Example 7

[0347] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 31 instead of Compound 2 was used to form the ETL.

Example 8

[0348] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 43 instead of Compound 2 was used to form the ETL.

Example 9

[0349] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 44 instead of Compound 2 was used to form the ETL.


Example 10

[0350] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound 53 instead of Compound 2 was used to form the ETL.

Comparative Example 1

[0351] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound A instead of Compound 2 was used to form the ETL.


Compound A



Comparative Example 2

[0352] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound B instead of Compound 2 was used to form the ETL.


Compound B



Comparative Example 3

[0353] An organic light-emitting diode was manufactured in the same manner as in Example 1, except that Compound C instead of Compound 2 was used to form the ETL.

Compound C



[0354] Driving voltages, current densities, luminances, emission colors, efficiencies, and half-life spans (@50 mA/cm²) of the organic light-emitting diodes of Examples 1 to 10 and Comparative Examples 1 to 3 were evaluated using a PR650 (Spectroscan) Source Measurement Unit (available from Photo Research, Inc.). The results are shown in Table 1 below.

TABLE 1

	ETL material	Dopant	Driving voltage (V)	Current density (mA/cm ²)	Luminance (cd/m ²)	Efficiency (cd/A)	Emission color	Half-lifespan (hr)
Example 1	Compound 2	DPAVBi	5.43	50	3,075	6.15	Blue	320
Example 2	Compound 8	DPAVBi	5.21	50	3,025	6.05	Blue	330
Example 3	Compound 12	DPAVBi	6.05	50	3,380	6.76	Blue	290
Example 4	Compound 16	DPAVBi	5.95	50	3,105	6.21	Blue	370
Example 5	Compound 18	DPAVBi	6.12	50	3,450	6.90	Blue	280
Example 6	Compound 19	DPAVBi	5.20	50	2,880	5.76	Blue	260
Example 7	Compound 31	DPAVBi	5.54	50	2,940	5.88	Blue	310
Example 8	Compound 43	DPAVBi	5.33	50	2,950	5.90	Blue	260
Example 9	Compound 44	DPAVBi	5.90	50	3,160	6.32	Blue	305
Example 10	Compound 53	DPAVBi	5.30	50	3,225	6.45	Blue	280
Comparative Example 1	Compound A	DPAVBi	7.35	50	2,065	4.12	Blue	145 h

TABLE 1-continued

	ETL material	Dopant	Driving voltage (V)	Current density (mA/cm ²)	Luminance (cd/m ²)	Efficiency (cd/A)	Emission color	Half-lifespan (hr)
Comparative Example 2	Compound B	DPAVBi	6.95	50	2,575	5.15	Blue	130 h
Comparative Example 3	Compound C	DPAVBi	6.83	50	2,660	5.32	Blue	143 h


[0355] Referring to Table 1, the organic light-emitting diodes of Examples 1 to 10 were found to have lower driving voltages, higher luminances, higher efficiencies, higher color purities, and better lifetime characteristics as compared to the organic light-emitting diodes of Comparative Examples 1 to 3.

[0356] As described above, according to the one or more of the above embodiments, an organic light-emitting diode including any of the pyrene-based compounds of Formula 1 may have a low driving voltage, a high luminance, a high efficiency, and a long lifetime.

[0357] It should be understood that the example embodiments described therein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each embodiment should typically be considered as available for other similar features or aspects in other embodiments.

What is claimed is:

1. A pyrene-based compound represented by Formula 1 below:



wherein, in Formula 1,

L_1 and L_2 are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, and a substituted or unsubstituted C_2 - C_{60} heteroarylene group;

R_1 is selected from a substituted or unsubstituted N-containing 5-membered cyclic group, and a substituted or unsubstituted N-containing 5-membered cyclic group fused with a 6-membered ring;

R_2 is selected from a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted

C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_2 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthiol group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, $-N(Q_1)(Q_2)$, and $-Si(Q_3)(Q_4)(Q_5)$ (where Q_1 to Q_5 are each independently a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a C_6 - C_{60} aryl group, or a C_2 - C_{60} heteroaryl group);

a_1 and b_1 are each independently an integer from 1 to 5; and

a_2 and b_2 are each independently an integer from 0 to 5.

2. The pyrene-based compound of claim 1, wherein L_1 and L_2 are each independently selected from

a phenylene group, a pentalenyne group, an indenylene group, a naphthylene group, an azulenyne group, a heptalenyne group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a phenalenyne group, a phenanthrenylene group, an anthrylene group, a fluoranthenyne group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenyne group, a hexacenylene group, a pyrrolylene group, an imidazolylene group, a pyrazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzooxazolylene group, a benzimidazolylene group, a furanylene group, a benzofuranylene group, a thiophenyne group, a benzothiophenyne group, a thiazolylene group, an isothiazolylene group, a benzothiazolylene group, an isoxazolylene group, an oxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a benzooxazolylene group, a dibenzopuranylene group, a dibenzothiophenyne group, a benzocarbazolylene group, and a dibenzosilolylene group; each optionally substituted with at least one selected from


a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,


a C₆-C₂₀ aryl group and a C₂-C₂₀ heteroaryl group, and

a C₆-C₂₀ aryl group and a C₂-C₂₀ heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinoxalinyl group, and an isoquinolinyl group.


3. The pyrene-based compound of claim 1, wherein L₁ and L₂ are each independently one of the groups represented by Formulae 2-1 to 2-27 below:




Formula 2-1




Formula 2-2



Formula 2-3




Formula 2-4




Formula 2-5


-continued




Formula 2-6




Formula 2-7




Formula 2-8




Formula 2-9




Formula 2-10




Formula 2-11




Formula 2-12



Formula 2-13




Formula 2-14




Formula 2-15


-continued




Formula 2-16




Formula 2-17




Formula 2-18




Formula 2-19




Formula 2-20




Formula 2-21




Formula 2-22



Formula 2-23




Formula 2-24




Formula 2-25

-continued

Formula 2-26



Formula 2-27



wherein, in Formulae 2-1 to 2-27,

Y_1 is O, S, $C(Z_3)(Z_4)$, or $N(Z_5)$;

Z_1 to Z_5 are each independently selected from

a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

— $Si(Q_{13})(Q_{14})(Q_{15})$ (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, or a C_2 - C_{20} heteroaryl group);

d_1 is an integer from 1 to 4;

d_2 is an integer from 1 to 3;

d_3 is an integer from 1 to 6;

d_4 is an integer from 1 to 8;

d_5 is 1 or 2;

* indicates a binding site of pyrene in Formula 1 or a binding site of adjacent L_1 ; and

*' indicates a binding site of adjacent L_1 in Formula 1 or a binding site of R_1 .

4. The pyrene-based compound of claim 3, wherein Z_1 to Z_5 are each independently selected from

a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,


a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,

a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and


—Si(Q_{13})(Q_{14})(Q_{15}) (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).

5. The pyrene-based compound of claim 1, wherein L_1 and L_2 are each independently one of the groups represented by Formulae 3-1 to 3-20 below:


-continued




Formula 3-3




Formula 3-4




Formula 3-5




Formula 3-6




Formula 3-7




Formula 3-8




Formula 3-9




Formula 3-10



Formula 3-11




Formula 3-1




Formula 3-2


-continued




Formula 3-12




Formula 3-13




Formula 3-14




Formula 3-15




Formula 3-16



Formula 3-17




Formula 3-18



Formula 3-19

-continued


Formula 3-20




wherein, in Formulae 3-1 to 3-20, * indicate a binding site of pyrene in Formula 1 or a binding site of adjacent L_1 ; and

*' indicates a binding site of adjacent L_1 in Formula 1 or a binding site of R_1 .


6. The pyrene-based compound of claim 1, wherein R_1 is one of the groups represented by Formulae 4-1 to 4-10:




Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4



Formula 4-5




Formula 4-6




Formula 4-7


-continued



Formula 4-8



Formula 4-9



Formula 4-10

wherein, in Formulae 4-1 to 4-10,

Y_u is O, S, N(Z_{11}), or C(Z_{12})(Z_{13});

Y_{21} is N or C(Z_{21});

Y_{22} is N or C(Z_{22});

Y_{23} is N or C(Z_{23});

Y_{24} is N or C(Z_{24});

Y_{25} is N or C(Z_{25});

Y_{26} is N or C(Z_{26});

Z_{11} to Z_{13} , and Z_{21} to Z_{27} are each independently selected from

a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

—Si(Q_{13})(Q_{14})(Q_{15}) (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, or a C_2 - C_{20} heteroaryl group); and

* indicates a binding site of L_1 in Formula 1.

7. The pyrene-based compound of claim 6, wherein Z_{11} to Z_{13} , and Z_{21} to Z_{27} are each independently selected from

a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,

a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

—Si(Q_{13})(Q_{14})(Q_{15}), wherein Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group.

8. The pyrene-based compound of claim 1, wherein R_1 is selected from

a pyrrolyl group, an imidazolyl group, a pyrazolyl group, a triazolyl group, an oxazolyl group, an isoxazolyl group, an oxadiazolyl group, an oxatriazolyl group, a triazolyl group, an isothiazolyl group, a thiazolyl group, a thia-triazolyl group, a benzoimidazolyl group, an imidazopyrimidinyl group, an imidazopyridinyl group, a benzooxazolyl group, and a benzothiazolyl group, each optionally substituted with at least one selected from

a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt

thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,


a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,


a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and

— $Si(Q_{13})(Q_{14})(Q_{15})$, wherein Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group.


9. The pyrene-based compound of claim 1, wherein R_1 is one of the groups represented by Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1):



Formula 4-1(1)




Formula 4-1(2)




Formula 4-1(3)

-continued


Formula 4-2(1)




Formula 4-4(1)




Formula 4-4(2)




Formula 4-4(3)



Formula 4-6(1)



Formula 4-6(2)




Formula 4-8(1)

wherein, in Formulae 4-1(1), 4-1(2), 4-1(3), 4-2(1), 4-4(1), 4-4(2), 4-4(3), 4-6(1), 4-6(2), and 4-8(1), Z_{11} and Z_{21} , and Z_{21} to Z_{26} are each independently selected from


a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or

- a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group,
- a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,
- a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group,
- a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and
- Si(Q₁₃)(Q₁₄)(Q₁₅) (where Q₁₃ to Q₁₅ are each independently a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group).
- 10.** The pyrene-based compound of claim 1, wherein R₂ is selected from
- a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group,
- a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,
- a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a dibenzopuranyl group, and a dibenzothiophenyl group,
- a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a dibenzopuranyl group, and a dibenzothiophenyl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group, and
- Si(Q₃)(Q₄)(Q₅), wherein Q₃ to Q₅ are each independently a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group.
- 11.** The pyrene-based compound of claim 1, wherein R₂ is selected from
- a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group,
- a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,
- groups represented by Formulae 5-1 to 5-22 below, and
- Si(Q₃)(Q₄)(Q₅), wherein Q₃ to Q₅ are each independently a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, or an isoquinolinyl group.











Formula 5-1



Formula 5-2



-continued



Formula 5-3

Formula 5-4

Formula 5-5

Formula 5-6

Formula 5-7

Formula 5-8










Formula 5-9

Formula 5-10

Formula 5-11

Formula 5-12

-continued



Formula 5-13

Formula 5-14

Formula 5-15

Formula 5-16

Formula 5-17


Formula 5-18

Formula 5-19

Formula 5-20

Formula 5-21

-continued




Formula 5-22

12. The pyrene-based compound of claim 1, wherein $L_1=L_2$, $R_1=R_2$, $a1=a2$, and $b1=b2$.


13. The pyrene-based compound of claim 1, wherein L_1 and L_2 are each independently one of the groups represented by Formulae 2-1 to 2-27 below;

R_1 and R_2 are each independently one of the groups represented by Formulae 4-1 to 4-10; and


$a1$, $a2$, $b1$, and $b2$ are each independently 1 or 2:




Formula 2-1




Formula 2-2




Formula 2-3



Formula 2-4




Formula 2-5




Formula 2-6


-continued




Formula 2-7




Formula 2-8




Formula 2-9




Formula 2-10




Formula 2-11




Formula 2-12




Formula 2-13



Formula 2-14













Formula 2-15



Formula 2-16

-continued



Formula 2-17

Formula 2-18

Formula 2-19

Formula 2-20

Formula 2-21

Formula 2-22


Formula 2-23

Formula 2-24

Formula 2-25

Formula 2-26

-continued



Formula 2-27

wherein, in Formulae 2-1 to 2-27,

Y_1 is O, S, $C(Z_3)(Z_4)$, or $N(Z_5)$;

Z_1 to Z_5 are each independently selected from

a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_{20} alkoxy group;

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substitute with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinoxalyl group, and an isoquinolinyl group, and

— $Si(Q_{13})(Q_{14})(Q_{15})$ (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, or a C_2 - C_{20} heteroaryl group);

$d1$ is an integer from 1 to 4;

$d2$ is an integer from 1 to 3;


$d3$ is an integer from 1 to 6;

$d4$ is an integer from 1 to 8;

$d5$ is 1 or 2;


* indicate a binding site of pyrene in Formula 1 or a binding site of adjacent L_1 ;

*' indicates a binding site of adjacent L_1 in Formula 1 or a binding site of R_1 ,




Formula 4-1


-continued




Formula 4-2




Formula 4-3




Formula 4-4




Formula 4-5




Formula 4-6



Formula 4-7




Formula 4-8



Formula 4-9

-continued

Formula 4-10



wherein, in Formulae 4-1 to 4-10,

Y_{11} is O, S, N(Z_{11}), or C(Z_{12})(Z_{13});

Y_{21} is N or C(Z_{21});

Y_{22} is N or C(Z_{22});

Y_{23} is N or C(Z_{23});

Y_{24} is N or C(Z_{24});

Y_{25} is N or C(Z_{25});

Y_{26} is N or C(Z_{26});

Z_{11} to Z_{13} , and Z_{21} to Z_{27} are each independently selected from

a hydrogen atom, a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group,

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof,













a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group,

a C_6 - C_{20} aryl group and a C_2 - C_{20} heteroaryl group, each substituted with at least one of a deuterium atom, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine, a hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a phenyl group, a naphthyl group, an anthryl group, a fluorenyl group, a dimethylfluorenyl group, a diphenylfluorenyl group, a carbazolyl group, a phenylcarbazolyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinoxalinyl group, and an isoquinolinyl group, and

—Si(Q_{13})(Q_{14})(Q_{15}) (where Q_{13} to Q_{15} are each independently a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a C_6 - C_{20} aryl group, or a C_2 - C_{20} heteroaryl group); and

* indicates a binding site of L_1 in Formula 1.



14. The pyrene-based compound of claim 1, wherein the pyrene-based compound is one of Compounds 1 to 60 below:




-continued

13


14



15





16





17

18




19


20



21




22




-continued

23


24



25




26




27

28




29




30

31




-continued


32




33




34




35




36




37




38




39




40



41





42



-continued



43

44





45

46





47

48





49

50




51


52




53




-continued




54




55




56



57




58



59

-continued

60



15. An organic light-emitting diode comprising: a first electrode; a second electrode disposed opposite to the first electrode; and an organic layer disposed between the first electrode and the second electrode and comprising an emission layer, wherein the organic layer comprises a hole transport region between the first electrode and the emission layer, and an electron transport region between the emission layer and the second electrode, and the organic layer comprises at least one of the pyrene-based compounds of Formula 1 of claim 1.

16. The organic light-emitting diode of claim **15**, wherein the hole transport region comprises at least one of a hole injection layer, a hole transport layer, a functional layer having both hole injection and hole transport capabilities, a buffer layer, and an electron blocking layer; wherein the electron transport region comprises at least one of a hole blocking

layer, an electron transport layer, and an electron injection layer; and the pyrene-based compound is in the electron transport region.

17. The organic light-emitting diode of claim **16**, wherein the electron transport region comprises an electron transport layer, and the pyrene-based compound is in the electron transport layer.

18. The organic light-emitting diode of claim **17**, wherein the electron transport layer further comprises a metal-containing material.

19. The organic light-emitting diode of claim **15**, wherein the pyrene-based compound is in the emission layer.

20. The organic light-emitting diode of claim **15**, wherein the hole transport region comprises a charge-generating material.

* * * * *

专利名称(译)	基于芘的化合物和包含其的有机发光二极管		
公开(公告)号	US20140239269A1	公开(公告)日	2014-08-28
申请号	US13/959551	申请日	2013-08-05
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	JEONG EUN JAE HWANG SEOK HWAN KIM YOUNG KOOK JUNG HYE JIN PARK JUN HA LEE EUN YOUNG LIM JIN O HAN SANG HYUN KIM SOO YON LEE JONG HYUK		
发明人	JEONG, EUN-JAE HWANG, SEOK-HWAN KIM, YOUNG-KOOK JUNG, HYE-JIN PARK, JUN-HA LEE, EUN-YOUNG LIM, JIN-O HAN, SANG-HYUN KIM, SOO-YON LEE, JONG-HYUK		
IPC分类号	H01L51/00		
CPC分类号	H01L51/0054 H01L51/0067 H01L51/0069 H01L51/0074 H01L51/0071 H01L51/0072 H01L51/0073 H01L51/007 C09K11/06 H01L51/5072 C07D235/18 H01L51/0059 H01L51/0062 H01L51/5056		
优先权	1020130020013 2013-02-25 KR		
其他公开文献	US10193072		
外部链接	Espacenet USPTO		

摘要(译)

提供芘系化合物和包含芘系化合物的有机发光二极管。

