



US 20150069347A1

(19) **United States**(12) **Patent Application Publication**  
**KIM et al.**(10) **Pub. No.: US 2015/0069347 A1**(43) **Pub. Date: Mar. 12, 2015**(54) **CONDENSED CYCLIC COMPOUND AND  
ORGANIC LIGHT-EMITTING DEVICE  
INCLUDING THE SAME**(71) Applicant: **SAMSUNG DISPLAY CO., LTD.,**  
Yongin-City (KR)(72) Inventors: **Kwang-Hyun KIM**, Yongin-City (KR);  
**Seok-Hwan HWANG**, Yongin-City  
(KR); **Young-Kook KIM**, Yongin-City  
(KR); **Jun-Ha PARK**, Yongin-City  
(KR); **Hye-Jin JUNG**, Yongin-City  
(KR); **Eun-Young LEE**, Yongin-City  
(KR); **Jong-Woo KIM**, Yongin-City  
(KR); **Jin-O LIM**, Yongin-City (KR);  
**Sang-Hyun HAN**, Yongin-City (KR);  
**Eun-Jae JEONG**, Yongin-City (KR);  
**Soo-Yon KIM**, Yongin-City (KR)(73) Assignee: **SAMSUNG DISPLAY CO., LTD.,**  
Yongin-City (KR)(21) Appl. No.: **14/294,376**(22) Filed: **Jun. 3, 2014**(30) **Foreign Application Priority Data**

Sep. 6, 2013 (KR) ..... 10-2013-0107509

**Publication Classification**(51) **Int. Cl.**  
**H01L 51/00** (2006.01)  
**H01L 51/50** (2006.01)  
(52) **U.S. Cl.**  
CPC ..... **H01L 51/0054** (2013.01); **H01L 51/0072**  
(2013.01); **H01L 51/0067** (2013.01); **H01L**  
**51/0058** (2013.01); **H01L 51/0073** (2013.01);  
**H01L 51/0074** (2013.01); **H01L 51/50**  
(2013.01); **H01L 2251/53** (2013.01)  
USPC ..... **257/40**; 548/444; 546/276.7; 546/256;  
546/173; 544/242; 544/180; 549/460(57) **ABSTRACT**

A condensed cyclic compound and an organic light-emitting device including the same, the condensed cyclic compound being represented by Formula 1:

&lt;Formula 1&gt;




FIG. 1

10

|     |
|-----|
| 190 |
| 150 |
| 110 |

# CONDENSED CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

## CROSS-REFERENCE TO RELATED APPLICATION

[0001] Korean Patent Application No. 10-2013-0107509, filed on Sep. 6, 2013, in the Korean Intellectual Property Office, and entitled: "Condensed Cyclic Compound and Organic Light-Emitting Device Including The Same," is incorporated by reference herein in its entirety.

## BACKGROUND

[0002] 1. Field

[0003] Embodiments relate to a condensed cyclic compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art

[0005] Organic light emitting devices are self-emission devices that have wide viewing angles, a high contrast ratio, short response times, and excellent brighter, driving voltage, and response speed characteristics, and produce full-color images.


[0006] An organic light-emitting device may include a first electrode on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which may be sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, e.g., holes and electrons, may be recombined in the emission layer to produce excitons. These excitons may change from an excited state to a ground state, thereby generating light.

## SUMMARY

[0007] Embodiments are directed to a condensed cyclic compound and an organic light-emitting device including the same.

[0008] One or more embodiments related to a condensed cyclic compound and an organic light-emitting device including the same.


[0009] An embodiment provides a condensed cyclic compound represented by Formula 1:



<Formula 1>

-continued

<Formula 2>



[0010] wherein Formulae 1 and 2,

[0011]  $X_1$  is  $N(R_{21})$ , O, or S;

[0012]  $L_1$  is selected from a substituted or unsubstituted  $C_3$ - $C_{10}$  cycloalkylene group, a substituted or unsubstituted  $C_2$ - $C_{10}$  heterocycloalkylene group, a substituted or unsubstituted  $C_3$ - $C_{10}$  cycloalkenylene group, a substituted or unsubstituted  $C_2$ - $C_{10}$  heterocycloalkenylene group, a substituted or unsubstituted  $C_6$ - $C_{60}$  arylene group, a substituted or unsubstituted  $C_2$ - $C_{60}$  heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic hetero-condensed polycyclic group;

[0013]  $a_1$  is selected from 0, 1, 2, and 3;

[0014]  $R_1$  to  $R_{12}$  are each independently selected from a group represented by Formula 2, a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a substituted or unsubstituted  $C_1$ - $C_{60}$  alkyl group, a substituted or unsubstituted  $C_2$ - $C_{60}$  alkenyl group, a substituted or unsubstituted  $C_2$ - $C_{60}$  alkynyl group, a substituted or unsubstituted  $C_1$ - $C_{60}$  alkoxy group, a substituted or unsubstituted  $C_3$ - $C_{10}$  cycloalkyl group, a substituted or unsubstituted  $C_2$ - $C_{10}$  heterocycloalkyl group, a substituted or unsubstituted  $C_3$ - $C_{10}$  cycloalkenyl group, a substituted or unsubstituted  $C_2$ - $C_{10}$  heterocycloalkenyl group, a substituted or unsubstituted  $C_6$ - $C_{60}$  aryl group, a substituted or unsubstituted  $C_6$ - $C_{60}$  aryloxy group, a substituted or unsubstituted  $C_6$ - $C_{60}$  arylthio group, a substituted or unsubstituted  $C_2$ - $C_{60}$  heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic hetero-condensed polycyclic group (here, the group of Formula 2 is excluded or different from "the substituted monovalent non-aromatic hetero-condensed polycyclic group"),  $-N(Q_1)(Q_2)$ ,  $-Si(Q_3)(Q_4)(Q_5)$ , and  $-B(Q_6)(Q_7)$ ;

[0015] at least one of  $R_1$  to  $R_{12}$  is represented by Formula 2 above;

[0016]  $b_1$  and  $b_2$  are each independently selected from 0, 1, 2, and 3;

[0017] at least one substituent of the substituent of the substituted  $C_3$ - $C_{10}$  cycloalkylene group, the substituted  $C_2$ - $C_{10}$  heterocycloalkylene group, the substituted  $C_3$ - $C_{10}$  cycloalkenylene group, the substituted  $C_2$ - $C_{10}$  heterocycloalkenylene group, the substituted  $C_6$ - $C_{60}$  arylene group, the substituted  $C_2$ - $C_{60}$  heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic hetero-condensed polycyclic group, the substituted  $C_1$ - $C_{60}$  alkyl group, the substituted  $C_2$ - $C_{60}$  alkenyl group, the substituted  $C_2$ - $C_{60}$  alkynyl group, the substituted  $C_1$ - $C_{60}$  alkoxy group, the substituted  $C_3$ - $C_{10}$  cycloalkyl group, the substituted  $C_2$ - $C_{10}$  heterocycloalkyl

group, the substituted  $C_3$ - $C_{10}$  cycloalkenyl group, the substituted  $C_2$ - $C_{10}$  heterocycloalkenyl group, the substituted  $C_6$ - $C_{60}$  aryl group, the substituted  $C_6$ - $C_{60}$  aryloxy group, the substituted  $C_6$ - $C_{60}$  arylthio group, the substituted  $C_2$ - $C_{60}$  heteroaryl group, the substituted monovalent non-aromatic condensed polycyclic group, and the substituted monovalent non-aromatic hetero-condensed polycyclic group may be selected from

[0018] a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{60}$  alkyl group, a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, and a  $C_1$ - $C_{60}$  alkoxy;

[0019] a  $C_1$ - $C_{60}$  alkyl group, a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, and a  $C_1$ - $C_{60}$  alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group,  $-N(Q_{11})$  ( $Q_{12}$ ),  $-Si(Q_{13})(Q_{14})(Q_{15})$ , and  $-B(Q_{16})(Q_{17})$ ;

[0020] a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic hetero-condensed polycyclic group;

[0021] a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic hetero-condensed polycyclic group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{60}$  alkyl group, a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, and a  $C_1$ - $C_{60}$  alkoxy group, a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group,  $-N(Q_{21})$  ( $Q_{22}$ ),  $-Si(Q_{23})(Q_{24})(Q_{25})$ , and  $-B(Q_{26})(Q_{27})$ ; and

[0022]  $-N(Q_{31})(Q_{32})$ ,  $-Si(Q_{33})(Q_{34})(Q_{35})$ , and  $-B(Q_{36})(Q_{37})$ ; and

[0023]  $R_{21}$ ,  $R_{31}$ ,  $R_{32}$ ,  $Q_1$  to  $Q_7$ ,  $Q_{11}$  to  $Q_{17}$ ,  $Q_{21}$  to  $Q_{27}$ , and  $Q_{31}$  to  $Q_{37}$  may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric

acid and a salt thereof, a  $C_1$ - $C_{60}$  alkyl group, a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, and a  $C_1$ - $C_{60}$  alkoxy group, a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group.

[0024] Another embodiment provides an organic light-emitting device including: a first electrode; a second electrode facing the first electrode; and an organic layer that is disposed between the first and second electrodes and includes an emission layer, wherein the organic layer includes at least one condensed cyclic compound described above.

## BRIEF DESCRIPTION OF THE DRAWING

[0025] Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawing in which:

[0026] FIG. 1 illustrates a schematic view of a structure of an organic light-emitting device according to an embodiment.

## DETAILED DESCRIPTION


[0027] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawing; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

[0028] In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. Like reference numerals refer to like elements throughout.


[0029] Expressions such as "at least one of," when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0030] A condensed cyclic compound according to an embodiment may be represented by Formula 1 below. At least one of  $R_1$  to  $R_{12}$  in Formula 1 may be a group represented by Formula 2 below.

<Formula 1>



<Formula 2>



**[0031]** In Formulae 1 and 2,  $X_1$  may be  $N(R_{21})$ , O, or S.  $R_{21}$  may be understood by referring to a detailed description thereof provided below. \* may represent a binding site, e.g., to Formula 1.


**[0032]** According to an embodiment, each  $L_1$  in Formula 2 may be independently selected from:

**[0033]** a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isooxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzooxazolylene group, an isobenzooxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and


**[0034]** a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isooxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a ben-

zothiophenylene group, an isobenzothiazolylene group, a benzooxazolylene group, an isobenzooxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentanyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, but is not limited thereto.

**[0035]** According to another embodiment, each  $L_1$  in Formula 2 may be independently represented by one of Formulae 3-1 to 3-32 below, in which \* and \*' represent binding sites.











Formula 3-1



Formula 3-2

-continued



Formula 3-3

Formula 3-4

Formula 3-5

Formula 3-6











Formula 3-7

Formula 3-8

Formula 3-9

Formula 3-10

-continued



Formula 3-11

Formula 3-12

Formula 3-13

Formula 3-14

Formula 3-15

Formula 3-16










Formula 3-17

Formula 3-18

Formula 3-19


Formula 3-20

-continued




-continued

Formula 3-21




Formula 3-22

Formula 3-23



Formula 3-24



Formula 3-25

Formula 3-26

Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30

Formula 3-31

Formula 3-32

[0036] In Formulae 3-1 to 3-32,

[0037]  $Y_1$  may be O, S, C( $Z_3$ )( $Z_4$ ), N( $Z_5$ ), or Si( $Z_6$ )( $Z_7$ );

[0038]  $Z_1$  to  $Z_7$  may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazoyl group, and a triazinyl group;

[0039]  $d_1$  may be selected from an integer of 1 to 4;

[0040]  $d_2$  may be selected from an integer of 1 to 3;

[0041]  $d_3$  may be selected from an integer of 1 to 6;


[0042]  $d_4$  may be selected from an integer of 1 to 8;

[0043]  $d_5$  may be selected from 1 or 2; and










[0044]  $d_6$  may be selected from an integer of 1 to 5.

[0045] According to another embodiment, each  $L_1$  in Formula 2 may be independently represented by one of Formulae 4-1 to 4-23 below, in which \* and \*' represent binding sites.

Formula 4-1



-continued



Formula 4-2

Formula 4-3

Formula 4-4

Formula 4-5

Formula 4-6








Formula 4-7

Formula 4-8

Formula 4-9

Formula 4-10

-continued



Formula 4-11

Formula 4-12

Formula 4-13


Formula 4-14

Formula 4-15


Formula 4-16

Formula 4-17


-continued




Formula 4-18




Formula 4-19




Formula 4-20



Formula 4-21



Formula 4-22



Formula 4-23

**[0046]**  $a_1$  in Formula 1 may be selected from 0, 1, 2, and 3. For example,  $a_1$  in Formula 1 may be 0 or 1. When  $a_1$  in Formula 1 is 0,  $-(L_1)_{a_1}-$  is a single bond. When  $a_1$  is 2 or more, a plurality of  $L_1$ s may be identical to or different from each other.

**[0047]** According to another embodiment,  $X_1$  may be  $N(R_{21})$ , and  $R_{21}$  may be selected from:

**[0048]** a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an

isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinoxalinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazolpyridinyl group, and an imidazopyrimidinyl group; and

**[0049]** a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinoxalinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazolpyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentanylyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoox-

azolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolyl group, an isoquinolyl group, a benzoquinolyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, but is not limited thereto.

**[0050]** According to another embodiment,  $X_1$  may be  $N(R_{21})$ , and  $R_{21}$  may be selected from:

**[0051]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

**[0052]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

**[0053]** According to another embodiment,  $R_1$  to  $R_6$  in Formulae 1 and 2 may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

**[0054]** In an implementation,  $R_1$  to  $R_{12}$  in Formula 1 may each be each independently selected from:

**[0055]** a group represented by Formula 2, a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolyl group, an isoquinolyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, and  $Si(Q_3)(Q_4)(Q_5)$  (in which,  $Q_3$  to  $Q_5$  are each independently selected from a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, and a naphthyl group); and at least one of  $R_1$  to  $R_{12}$  may be a group represented by Formula 2.


**[0056]** According to another embodiment,  $R_{12}$  in Formula 1 may be a group represented by Formula 2, but is not limited thereto.

**[0057]** In an implementation, regarding Formulae 1 and 2,


**[0058]**  $R_{21}$  may be selected from Formulae 5-1 to 5-35 below, in which \* represents a binding site;

**[0059]**  $R_1$  to  $R_{12}$  may be each independently selected from a group represented by Formula 2, a hydrogen, deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, and a group represented by Formulae 5-1 to 5-35 below, in which at least one of  $R_1$  to  $R_{12}$  may be represented by Formula 2.


**[0060]**  $R_{31}$  and  $R_{32}$  may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, and a group represented by Formula 5-1 to 5-35 below, but are not limited thereto.



Formula 5-1










Formula 5-2



Formula 5-3

-continued



Formula 5-4

Formula 5-5

Formula 5-6









Formula 5-7

Formula 5-8

Formula 5-9

Formula 5-10

-continued



Formula 5-11

Formula 5-12

Formula 5-13

Formula 5-14











Formula 5-15

Formula 5-16

Formula 5-17

Formula 5-18

-continued



Formula 5-19

Formula 5-20

Formula 5-21

Formula 5-22

Formula 5-23

Formula 5-24






Formula 5-25

Formula 5-26

Formula 5-27

Formula 5-28

-continued



Formula 5-29


Formula 5-30

Formula 5-31

Formula 5-32

Formula 5-33


-continued




Formula 5-34

-continued

&lt;Formula 1-2&gt;




Formula 5-35




**[0061]** In an implementation,  $b_1$  in Formulae 1 and 2 may be selected from 0, 1, 2, and 3. For example,  $b_1$  may be 0, 1, or 2. when  $b_1$  is 2 or more, a plurality of  $R_{31}$ s may be identical to or different from each other.  $b_2$  may be understood by referring to the description provided in connection with  $b_1$ . For example,  $b_2$  may be defined the same as  $b_1$ .

**[0062]** In an implementation, the condensed cyclic compound represented by Formula 1 may be represented by one of Formulae 1-1 to 1-12 below.


&lt;Formula 1-3&gt;




&lt;Formula 1-1&gt;



&lt;Formula 1-4&gt;




-continued




<Formula 1-5>

-continued




<Formula 1-8>


<Formula 1-6>




<Formula 1-9>



<Formula 1-7>




<Formula 1-10>




-continued


&lt;Formula 1-11&gt;




1



&lt;Formula 1-12&gt;



2




**[0063]**  $X_1$ ,  $L_1$ ,  $a_1$ ,  $R_6$ ,  $R_{31}$ ,  $R_{32}$ , and  $b_1$  and  $b_2$  in Formulae 1-1 to 1-12 may be understood by referring to the corresponding description provided herein. For example,  $X_1$ ,  $L_1$ ,  $a_1$ ,  $R_6$ ,  $R_{31}$ ,  $R_{32}$ , and  $b_1$  and  $b_2$  in Formulae 1-1 to 1-12 may be the same as those defined with respect to Formula 1.

**[0064]** In an implementation, the condensed cyclic compound may be represented by one of Formulae 1-1 to 1-12,  $L_1$  in Formulae 1-1 to 1-12 may be represented by one of Formulae 4-1 to 4-23 above;  $a_1$  may be 0 or 1;  $x_1$  may be  $N(R_{21})$ , O, or S;  $R_{21}$  may be selected from Formulae 5-1 to 5-35 above;  $R_6$ ,  $R_{31}$ , and  $R_{32}$  may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, and Formulae 5-1 to 5-35 above; and  $b_1$  and  $b_2$  may be each independently 0, 1, or 2, but they are not limited thereto.


**[0065]** In an implementation, the condensed cyclic compound represented by Formula 1 may be represented by one of Formulae 1-1, 1-5, 1-6, and 1-9.

**[0066]** In an implementation, the condensed cyclic compound represented by Formula 1 may be one of Compounds 1 to 116 below, but is not limited thereto.




3




-continued



-continued




-continued




8

-continued




10

9




11




16

-continued




12

-continued




14


13



15




-continued




16

-continued




18


17



19




-continued




20

-continued




22


21



23




-continued




24

-continued




26


25



27




-continued




28


-continued



30




29




31

-continued




32


-continued



34




33




35

36




-continued




37

-continued




39


38



40




-continued




41


-continued



43




42




44

-continued




45


-continued



47




46



48


-continued



49



-continued

51




50

52




-continued




53


-continued



55




54



56


27

-continued




57

-continued




59


58



60




-continued




61

-continued




63


62



64




-continued




65


-continued



67






66



68


-continued




-continued

69

72




70



73


71

-continued




74



-continued



75



76




77

78


79

-continued




80

-continued




82


81



83




-continued




84

-continued




86


85



87




-continued




88

-continued





90

91




89

92




-continued




93

-continued




96

94




95

97




-continued




98

-continued




100




101




99





102






-continued





-continued




-continued



-continued




-continued




113


-continued



115




114



116

**[0067]** Formula 1 may include a group represented by Formula 2. The group represented by Formula 2 may include, e.g., a “carbazole-based ring” that is substituted with “CN (cyano)” (see Formula 2' below).



[0068] Formula 2 may include a “carbazole-based ring” substituted with CN, and  $X_1$ , which may be a heteroatom of the “carbazole-based ring,” may help offset electron withdrawing effects of CN. Accordingly, the compound represented by Formula 1 may have excellent thermal stability. thus, an organic light-emitting device including a compound represented by Formula 1 may have a long lifespan.

[0069] Also, Formula 2 may include a “carbazole-based ring” substituted with CN, and an intramolecular bonding force may be enhanced. Thus, an organic light-emitting device including a compound represented by Formula 1 may have a long lifespan.

[0070] Accordingly, an organic light-emitting device including the condensed cyclic compound represented by Formula 1 may have a low driving voltage, high efficiency, high brightness, and long lifespan.

[0071] The condensed cyclic compound represented by Formula 1 may be synthesized by a suitable organic synthesis method. A synthesis method of the condensed cyclic compound may be obvious to one of ordinary skill in the art in view of the following embodiments or examples.

[0072] The condensed cyclic compound of Formula 1 may be used or included between a pair of electrodes of an organic light-emitting device. In an implementation, the condensed cyclic compound may be included in an electron transport region, e.g., an electron transport layer. Accordingly, an organic light-emitting device according to an embodiment may include a first electrode; a second electrode facing the first electrode; and an organic layer between the first and second electrodes. The organic layer may include an emission layer. The organic layer may include at least one of the condensed cyclic compounds described above, e.g., the compound represented by Formula 1.

[0073] The expression “(an organic layer) includes at least one condensed cyclic compound” used herein includes a case in which “(an organic layer) includes one condensed cyclic compound of Formula 1 and a case in which (an organic layer) includes two or more different condensed cyclic compounds of Formula 1”.

[0074] For example, the organic layer may include, as the condensed cyclic compound, only Compound 1. In this regard, Compound 1 may exist in an electron transport layer of the organic light-emitting device. In another embodiment of the present invention, the organic layer may include, as the condensed cyclic compound, Compound 1 and Compound 2. In this regard, Compound 1, and Compound 2 may exist in an identical layer (for example, Compound 1 and Compound 2 may both exist in an electron transport layer), or different layers (for example, Compound 1 may exist in an emission layer and Compound 2 may exist in an electron transport layer).

[0075] The organic layer may include, e.g., i) a hole transport region between the first electrode and the emission layer. The hole transport region may include at least one of a hole injection layer, a hole transport layer, a buffer layer, or an electron blocking layer. The organic layer may include, e.g., ii) an electron transport region between the emission layer and the second electrode. The electron transport region may include at least one of a hole blocking layer, an electron transport layer, or an electron injection layer. The electron transport region may include the condensed cyclic compound represented by Formula 1. For example, the electron transport region may include the electron transport layer, and the electron transport layer may include the condensed cyclic compound represented by Formula 1.

[0076] The expression “organic layer” used herein refers to a single layer and/or a plurality of layers disposed between the first and second electrodes of an organic light-emitting device. A material of the “organic layer” is not limited to an organic material.

[0077] FIG. 1 illustrates a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

[0078] Hereinafter a structure of the organic light-emitting device 10 and a method of manufacturing the organic light-emitting device 10, according to an embodiment, will be described with reference to FIG. 1.

[0079] In an implementation, a substrate may be additionally disposed or provided under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or a transparent plastic substrate, each with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water repellancy.

[0080] The first electrode 110 may be formed by depositing or sputtering a material for forming the first electrode 110 on the substrate. When the first electrode 110 is an anode, the material for the first electrode 110 may be selected from materials with a high work function facilitate hole injection. The first electrode 110 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode. The material for the first electrode 110 may be a transparent and highly conductive material, and examples of such a material may include indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide ( $\text{SnO}_2$ ), and zinc oxide (ZnO). When the first electrode 110 is a semi-transmissive electrode or a reflective electrode, a material for forming the first electrode 110 may include at least one of magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), and magnesium-silver (Mg—Ag).

[0081] The first electrode 110 may have a single-layer structure, or a multi-layer structure including two or more layers. For example, the first electrode 110 may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode 120 is not limited thereto.

[0082] The organic layer 150 may be disposed on the first electrode 110. The organic layer 150 may include an emission layer.

[0083] The organic layer **150** may further include a hole transport region between the first electrode **110** and the emission layer, and/or an electron transport region between the emission layer and the second electrode **190**.

[0084] The hole transport region may include at least one selected from a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer. The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer. However, the hole transport region and the electron transport region are not limited thereto.

[0085] The hole transport region may have a single-layered structure formed of a single material, a single-layered structure formed of different materials, or a multi-layered structure having a plurality of layers formed of different materials.

[0086] For example, the hole transport region may have a single-layered structure formed of different materials, or a structure of hole injection layer/hole transport layer, a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole injection layer/buffer layer, a structure of hole transport layer/buffer layer, or a structure of hole injection layer/hole transport layer/electron blocking layer, wherein layers of each structure are sequentially stacked from the first electrode **110** in this stated order, but are not limited thereto.


[0087] When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode **110** by using various methods, such as vacuum deposition, spin coating, casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, or laser-induced thermal imaging (LITI).

[0088] When a hole injection layer is formed by vacuum deposition, the vacuum deposition may be performed, for example, at a deposition temperature of about 100 to about 500° C. at a vacuum degree of about  $10^{-8}$  to about  $10^{-3}$  torr, and at a deposition rate of about 0.01 to about 100 Å/sec in consideration of a compound for a hole injection layer to be deposited, and the structure of a hole injection layer to be formed.


[0089] When a hole injection layer is formed by spin coating, the spin coating may be performed, for example, at a coating rate of about 2,000 rpm to about 50,000 rpm, and at a temperature of about 80° C. to 200° C. in consideration of a compound for a hole injection layer to be deposited, and the structure of a hole injection layer to be formed.

[0090] When the hole transport region includes a hole transport layer, the hole transport layer may be formed on the first electrode **110** or the hole injection layer by using various methods, such as vacuum deposition, spin coating, casting, an LB method, ink-jet printing, laser-printing, or LITI. when the hole transport layer is formed by vacuum deposition and spin coating, deposition and coating conditions for the hole transport layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0091] The hole transport region may include at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB,  $\beta$ -NPB, TPD, Spiro-TBD, Spiro-NPB,  $\alpha$ -NPB, TAPC, HMTPD, 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201 below, and a compound represented by Formula 202 below.




m-MTDATA




TDATA



-continued



2-TNATA




NPB


 $\beta$ -NPB

TPD



-continued




Spiro-TPD




Spiro-NPB

 $\alpha$ -NPB

TAPC



HMTPD



[0092] In Formulae 201 and 202,

[0093]  $L_{201}$  to  $L_{205}$  may be understood by referring to the description provided herein in connection with  $L_1$ ;

[0094]  $xa1$  to  $xa4$  may be each independently selected from 0, 1, 2, and 3;

[0095]  $xa5$  may be selected from 1, 2, 3, 4, and 5; and

[0096]  $R_{201}$  to  $R_{204}$  may be understood by referring to the description provided herein in connection with  $R_{21}$ .

[0097] In an implementation, in Formulae 201 and 201,

[0098]  $L_{201}$  to  $L_{205}$  may be each independently selected from;

[0099] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysénylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a carbazolylenylene group, and a triazinylenylene group; and

[0100] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysénylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylenylene group, a carbazolylenylene group, and a triazinylenylene group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinalinyl group, a quinazolinalinyl group, a carbazolyl group, and a triazinyl group;

[0101]  $xa1$  to  $xa4$  may be each independently 0, 1, or 2;

[0102]  $xa5$  may be 1, 2, or 3; and


[0103]  $R_{201}$  to  $R_{204}$  may be each independently selected from:

[0104] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a


quinolinyl group, an isoquinolinyl group, a quinoxalinalinyl group, a quinazolinalinyl group, a carbazolyl group, and a triazinyl group; and

[0105] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinalinyl group, a quinazolinalinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, and a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, an azulenylyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysényl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinalinyl group, a quinazolinalinyl group, a carbazolyl group, and a triazinyl group, but are not limited thereto.


[0106] The compound represented by Formula 201 may be represented by Formula 201A below.



[0107] For example, the compound represented by Formula 201 may be represented by Formula 201A-1 below, but is not limited thereto.



[0108] For example, the compound represented by Formula 202 may be represented by Formula 202A below, but is not limited thereto.



**[0109]**  $L_{201}$  to  $L_{203}$ ,  $xa1$  to  $xa3$ ,  $xa5$ , and  $R_{202}$  to  $R_{204}$  in Formulae 201A, 201A-1, and 202A are already described above,  $R_{211}$  may be understood by referring to the description provided in connection with  $R_{203}$ , and  $R_{213}$  to  $R_{216}$  may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{60}$  alkyl group, and a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, a  $C_1$ - $C_{60}$  alkoxy group, a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group and a monovalent non-aromatic condensed heterocyclic group.

**[0110]** In an implementation, in Formulae 201A, 201A-1, and 202A,

**[0111]**  $L_{201}$  to  $L_{203}$  may be each independently selected from:

**[0112]** a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a carbazolylenylene group, and a triazinylene group; and

**[0113]** a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylenylene group, an isoquinolinylenylene group, a quinoxalinylenylene group, a quinazolinylene group, a carbazolylenylene group, and a triazinylene group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

**[0114]**  $xa1$  to  $xa3$  may be each independently 0 or 1;

**[0115]**  $R_{203}$ ,  $R_{211}$ , and  $R_{212}$  may be each independently selected from:

**[0116]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

**[0117]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, and a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

**[0118]**  $R_{213}$  and  $R_{214}$  may be each independently selected from:

**[0119]** a  $C_1$ - $C_{20}$  alkyl group and a  $C_1$ - $C_{20}$  alkoxy group;

**[0120]** a  $C_1$ - $C_{20}$  alkyl group and a  $C_1$ - $C_{20}$  alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

**[0121]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

**[0122]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a

nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, and a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0123]  $R_{215}$  and  $R_{216}$  may be each independently selected from:

[0124] a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, and a  $C_1$ - $C_{20}$  alkoxy;

[0125] a  $C_1$ - $C_{20}$  alkyl group and a  $C_1$ - $C_{20}$  alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0126] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, and a triazinyl group;


[0127] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0128]  $x_5$  may be 1 or 2.


[0129]  $R_{213}$  and  $R_{214}$  in Formulae 201A and 201A-1 may bind to each other to form a saturated or unsaturated ring.

[0130] The compound represented by Formula 201 and the compound represented by Formula 201 may include compounds HT1 to HT20 illustrated below, but are not limited thereto.

HT1




HT2




-continued

HT3




-continued


HT5



HT4




HT6




-continued

HT7





-continued

HT9




HT10

HT8




-continued


HT11



HT12




HT13




-continued


HT14




HT15






HT16



HT17



-continued




② indicates text missing or illegible when filed

[0131] A thickness of the hole transport region may be about 100 Å to about 10,000 Å, e.g., about 100 Å to about 1,000 Å. When the hole transport region includes a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be about 100 Å to about 10,000 Å, e.g., about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be about 50 Å to about 2,000 Å, e.g., about 100 Å to about 1,500 Å. When the thickness of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.


[0132] The hole transport region may further include, in addition to these materials, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0133] The charge-generation material may be, e.g., a p-dopant. The p-dopant may include, e.g., one of a quinone derivative, a metal oxide, and a cyano group-containing compound, but is not limited thereto. For example, non-limiting examples of the p-dopant may include a quinone derivative, such as tetracyanoquinonedimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonedimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide; and compound HT-D1 illustrated below, but are not limited thereto.

&lt;Compound HT-D1&gt;



&lt;F4-TCNQ&gt;








[0134] The hole transport region may further include, in addition to the hole injection layer and the hole transport layer, at least one of a buffer layer and an electron blocking layer. The buffer layer may help compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, and thus, a light-emission efficiency of a formed organic light-emitting device may be improved. For use as a material of the buffer layer, materials of the hole transport region may be used. The electron blocking layer may help prevent injection of electrons from the electron transport region.

[0135] An emission layer may be formed on the first electrode 110 or the hole transport region by using various methods, e.g., vacuum deposition, spin coating, casting, an LB method, ink-jet printing, laser-printing, or LITI. When the emission layer is formed by vacuum deposition and spin coating, deposition and coating conditions for the emission layer may be determined by referring to the deposition and coating conditions for the hole injection layer.


[0136] When the organic light-emitting device 10 is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer, according to a sub-pixel. In some embodiments, the emission layer may have a stacked structure of a red emission layer, a green emission layer, and a blue emission layer, or may include a red-light emission material, a green-light emission material, and a blue-light emission material, which are mixed with each other in a single layer, to emit white light.

[0137] The emission layer may include a host and a dopant.

[0138] The host may include at least one selected from TPBi, TBADN, ADN (also referred to as “DNA”), CBP, CDBP, and TCP.



-continued



[0139] According to another embodiment, the host may include a compound represented by Formula 301 below.

[0140] <Formula 301>

[0141]  $\text{Ar}_{301} - [(\text{L}_{301})_{x b1} - \text{R}_{301}]_{x b2}$

[0142] In Formula 301,

[0143]  $\text{Ar}_{301}$  may be selected from:

[0144] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene;

[0145] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $\text{C}_1$ - $\text{C}_{60}$  alkyl group, a  $\text{C}_2$ - $\text{C}_{60}$  alkenyl group, a  $\text{C}_2$ - $\text{C}_{60}$  alkynyl group, a  $\text{C}_1$ - $\text{C}_{60}$  alkoxy group, a  $\text{C}_3$ - $\text{C}_{10}$  cycloalkyl group, a  $\text{C}_2$ - $\text{C}_{10}$  heterocycloalkyl group, a  $\text{C}_3$ - $\text{C}_{10}$ -cycloalkenyl group, a  $\text{C}_2$ - $\text{C}_{10}$  heterocycloalkenyl group, a  $\text{C}_6$ - $\text{C}_{60}$  aryl group, a  $\text{C}_6$ - $\text{C}_{60}$  aryloxy group, a  $\text{C}_6$ - $\text{C}_{60}$  arylthio group, a  $\text{C}_2$ - $\text{C}_{60}$  heteroaryl group, a monovalent non-aromatic hetero-condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group and  $-\text{Si}(\text{Q}_{301})(\text{Q}_{302})(\text{Q}_{303})$  (wherein  $\text{Q}_{301}$  to  $\text{Q}_{303}$  are each independently selected from a hydrogen, a  $\text{C}_1$ - $\text{C}_{60}$  alkyl group, a  $\text{C}_2$ - $\text{C}_{60}$  alkenyl group, a  $\text{C}_6$ - $\text{C}_{60}$  aryl group, and a  $\text{C}_2$ - $\text{C}_{60}$  heteroaryl group);

[0146]  $\text{L}_{301}$  may be understood by referring to the description provided in connection with  $\text{L}_{201}$ :

[0147]  $\text{R}_{301}$  may be selected from:

[0148] a  $\text{C}_1$ - $\text{C}_{20}$  alkyl group and a  $\text{C}_1$ - $\text{C}_{20}$  alkoxy group;

[0149] a  $\text{C}_1$ - $\text{C}_{20}$  alkyl group and a  $\text{C}_1$ - $\text{C}_{20}$  alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group,

a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0150] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0151] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0152]  $x_{b1}$  may be selected from 0, 1, 2, and 3; and

[0153]  $x_{b2}$  may be selected from 1, 2, 3, and 4.

[0154] In this regard, in Formula 301,

[0155]  $L_{301}$  may be selected from:

[0156] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, and a chrysenylene group; and

[0157] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, and a chrysenylene group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid, and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

[0158]  $R_{301}$  may be selected from:

[0159] a  $C_1$ - $C_{20}$  alkyl group and a  $C_1$ - $C_{20}$  alkoxy group;

[0160] a  $C_1$ - $C_{20}$  alkyl group and a  $C_1$ - $C_{20}$  alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group,


an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

[0161] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

[0162] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, but they are not limited thereto.

[0163] For example, the host may include a compound represented by Formula 301A below.


<Formula 301A>




[0164] Substituents of Formula 301A may be the same as those that are already described above.

[0165] The compound represented by Formula 301 may include at least one of Compounds H1 to H42 below. However, the compound represented by 301A is not limited thereto.


H1




-continued




H2




H3




H4



H5




H6




H7


-continued




H8




H9



H10




H11




H12

-continued


H13




H14




H15



H16




H17




-continued


H18




H19




H20



H21




H22




-continued


H23




H24




H25



H26




H27




-continued


H28




H29




H30



H31




H32




-continued

H33




-continued


H36




H34



H37




H35




-continued

H38




-continued


H41



H39




H42




(?) indicates text missing or illegible when filed

**[0166]** According to another embodiment, the host may include at least one of Compounds H43 to H40 below. However, the host is not limited thereto.


H40



H43




-continued




H44


-continued




H47




H45



H48




H46



H49

[0167] The dopant may include at least one selected from a fluorescent dopant and a phosphorescent dopant.

[0168] The phosphorescent dopant may include an organo-metallic complex represented by Formula 401 below.



&lt;Formula 401&gt;

[0169] In Formula 401,

[0170] M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm);

[0171]  $X_{401}$  to  $X_{404}$  may be each independently nitrogen or carbon;

[0172]  $A_{401}$  and  $A_{402}$  rings may be each independently selected from a substituted or unsubstituted benzene, a substituted or unsubstituted naphthalene, a substituted or unsubstituted fluorene, a substituted or unsubstituted spiro-fluorene, a substituted or unsubstituted indene, a substituted or unsubstituted pyrrole, a substituted or unsubstituted thiophene, a substituted or unsubstituted furan, a substituted or unsubstituted imidazole, a substituted or unsubstituted pyrazole, a substituted or unsubstituted thiazole, a substituted or unsubstituted isothiazole, a substituted or unsubstituted oxazole, a substituted or unsubstituted isoxazole, a substituted or unsubstituted pyridine, a substituted or unsubstituted pyrazine, a substituted or unsubstituted pyrimidine, a substituted or unsubstituted pyridazine, a substituted or unsubstituted quinoline, a substituted or unsubstituted isoquinoline, a substituted or unsubstituted benzoquinoline, a substituted or unsubstituted quinoxaline, a substituted or unsubstituted quinazoline, a substituted or unsubstituted carbazole, a substituted or unsubstituted benzimidazole, a substituted or unsubstituted benzofuran, a substituted or unsubstituted benzothiophene, a substituted or unsubstituted isobenzothiophene, a substituted or unsubstituted benzoxazole, a substituted or unsubstituted isobenzoxazole, a substituted or unsubstituted triazole, a substituted or unsubstituted oxadiazole, a substituted or unsubstituted triazine, a substituted or unsubstituted dibenzofuran, and a substituted or unsubstituted dibenzothiophene; and

[0173] a substituent of at least one selected from the substituted benzene, substituted naphthalene, substituted fluorene, substituted spiro-fluorene, substituted indene, substituted pyrrole, substituted thiophene, substituted furan, substituted imidazole, substituted pyrazole, substituted thiazole, substituted isothiazole, substituted oxazole, substituted isoxazole, substituted pyridine, substituted pyrazine, substituted pyrimidine, substituted pyridazine, substituted quinoline, substituted isoquinoline, substituted benzoquinoline, substituted quinoxaline, substituted quinazoline, substituted carbazole, substituted benzimidazole, substituted benzofuran, substituted benzothiophene, substituted isobenzothiophene, substituted benzoxazole, substituted isobenzoxazole, substituted triazole, substituted oxadiazole, substituted triazine, substituted dibenzofuran, and substituted dibenzothiophene may be selected from:

[0174] a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino

group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{60}$  alkyl group, a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, and a  $C_1$ - $C_{60}$  alkoxy group;

[0175] a  $C_1$ - $C_{60}$  alkyl group, a  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, and a  $C_1$ - $C_{60}$  alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed cyclic group, a monovalent non-aromatic condensed heteropolycyclic group —N( $Q_{401}$ )( $Q_{402}$ ), —Si( $Q_{403}$ )( $Q_{404}$ )( $Q_{405}$ ), and —B( $Q_{406}$ )( $Q_{407}$ );

[0176] a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group and a monovalent non-aromatic condensed heteropolycyclic group;

[0177] a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$  cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{60}$  alkyl group,  $C_2$ - $C_{60}$  alkenyl group, a  $C_2$ - $C_{60}$  alkynyl group, a  $C_1$ - $C_{60}$  alkoxy group, a  $C_3$ - $C_{10}$  cycloalkyl group, a  $C_2$ - $C_{10}$  heterocycloalkyl group, a  $C_3$ - $C_{10}$ -cycloalkenyl group, a  $C_2$ - $C_{10}$  heterocycloalkenyl group, a  $C_6$ - $C_{60}$  aryl group, a  $C_6$ - $C_{60}$  aryloxy group, a  $C_6$ - $C_{60}$  arylthio group, a  $C_2$ - $C_{60}$  heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group, —N( $Q_{411}$ )( $Q_{412}$ ), —Si( $Q_{413}$ )( $Q_{414}$ )( $Q_{415}$ ), and —B( $Q_{416}$ )( $Q_{417}$ ); and

[0178] —N( $Q_{421}$ )( $Q_{422}$ ), —Si( $Q_{423}$ )( $Q_{424}$ )( $Q_{425}$ ), and —B( $Q_{426}$ )( $Q_{427}$ ); and

[0179] Let  $L_{401}$  may be an organic ligand;

[0180]  $xc1$  may be 1, 2, or 3; and


[0181]  $xc2$  may be 0, 1, 2, or 3.

[0182]  $L_{401}$  may be a monovalent, divalent, or trivalent organic ligand. For example,  $L_{401}$  may be selected from a halogen ligand (for example, Cl or F), a diketone ligand (for example, acetylacetonate, 1,3-diphenyl-1,3-propanedionate, 2,2,6,6-tetramethyl-3,5-heptanedionate, or hexafluoroacetonate), a carboxylic acid ligand (for example, picolinate, dimethyl-3-pyrazolecarboxylate, or benzoate), a carbon monoxide ligand, an isonitrile ligand, a cyano ligand, and a phosphorous ligand (for example, phosphine or phosphite), but is not limited thereto.

**[0183]** When  $A_{401}$  in Formula 401 has two or more substituents, the substituents of  $A_{401}$  may bind to each other to form a saturated or unsaturated ring.

**[0184]** When  $A_{402}$  in Formula 401 has two or more substituents, the substituents of  $A_{402}$  may bind to each other to form a saturated or unsaturated ring.

**[0185]** When xc1 in Formula 401 is two or more, a plurality of ligands




(?) indicates text missing or illegible when filed


in Formula 401 may be identical to or different from each other. When xc1 in Formula 401 is two or more,  $A_{401}$  and  $A_{402}$  may be respectively directly connected to  $A_{401}$  and  $A_{402}$  of other neighboring ligands, or  $A_{401}$  and  $A_{402}$  may be respectively connected to  $A_{401}$  and  $A_{402}$  of other neighboring ligands with a linker (for example, a  $C_1$ - $C_5$  alkylene, or  $-N(R')$ — (wherein  $R'$  may be a  $C_1$ - $C_{10}$  alkyl group or a  $C_6$ - $C_{20}$  aryl group) or  $-C(=O)-$ ) therebetween.

**[0186]** The phosphorescent dopant may include at least one of Compounds PD1 to PD74 below, but is not limited thereto.


-continued




PD3




PD4




PD5




PD6



PD1




PD2




PD7

-continued




PD8

-continued




PD13

PD9




PD14





PD15

PD10





PD16

PD11








PD17

PD12




-continued




-continued

PD18




PD23

PD19




PD24

PD20




PD25

PD21








PD26

PD22




PD27

-continued




-continued

PD28




PD33

PD29




PD34

PD30




PD35

PD31




PD36

PD32




PD37

-continued




PD38

-continued




PD39


PD43




PD40




PD44




PD41




PD45




PD42




PD46




PD47




-continued




PD48




PD49




PD50



PD51




PD52




PD53


-continued




PD54




PD55



PD56








PD57



PD58

-continued



-continued






PD59

PD60

PD61

PD62

PD63



PD64





PD65

PD66

PD67


PD68

-continued




-continued

PD69



PD73


PD70



PD74

PD71


**[0187]** In an implementation, the phosphorescent dopant may include PtOEP below.




PD72

PtOEP


**[0188]** The fluorescent dopant may include at least one selected from DPAVB<sub>i</sub>, BDAVB<sub>i</sub>, TBPe, DCM, DCJT<sub>B</sub>, Coumarin 6, and C545T below.

DPVB<sub>i</sub>

-continued




DPAVBi



TBPe

DCM

DCJTB




Coumarin 6

C545T

Ⓢ indicates text missing or illegible when filed

[0189] In an implementation, the fluorescent dopant may include a compound represented by Formula 501 below.



&lt;Formula 501&gt;

[0190] In Formula 501,

[0191] Ar<sub>501</sub> may be selected from:

[0192] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene;

[0193] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phe-

nalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>60</sub> alkyl group, C<sub>2</sub>-C<sub>60</sub> alkenyl group, a C<sub>2</sub>-C<sub>60</sub> alkynyl group, a C<sub>1</sub>-C<sub>60</sub> alkoxy group, a C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a C<sub>3</sub>-C<sub>10</sub>-cycloalkenyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, a C<sub>6</sub>-C<sub>60</sub> aryloxy group, a C<sub>6</sub>-C<sub>60</sub> arylthio group, a C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic heterocondensed polycyclic group and —Si(Q<sub>501</sub>)(Q<sub>502</sub>)(Q<sub>503</sub>) (wherein Q<sub>501</sub> to Q<sub>503</sub> are each independently selected from a hydrogen, a C<sub>1</sub>-C<sub>60</sub> alkyl group, a C<sub>2</sub>-C<sub>60</sub> alkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, and a C<sub>2</sub>-C<sub>60</sub> heteroaryl group);

[0194]  $L_{501}$  to  $L_{503}$  may be understood by referring to the description provided in connection with  $L_{201}$ ;

[0195]  $R_{501}$  and  $R_{502}$  may be each independently selected from:

[0196] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, a dibenzofuran-yl group, and a dibenzothiophenyl group; and

[0197] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, a dibenzofuran-yl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, a dibenzofuran-yl group, and a dibenzothiophenyl group; and


[0198]  $xd1$  to  $xd3$  may be each independently selected from 0, 1, 2, and 3; and

[0199]  $xb4$  may be selected from 1, 2, 3, and 4.


[0200] The fluorescent host may include at least one of Compounds FD1 to FD8 below.

-continued


FD2




FD3



FD4




FD1




-continued


FD5




FD6



FD7



FD8



[0201] An amount of the dopant in the emission layer may be, e.g., about 0.01 to about 15 parts by weight, based on 100 parts by weight of the host, but is not limited thereto.

[0202] A thickness of the emission layer may be about 100 Å to about 1,000 Å, e.g., about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0203] Then, an electron transport region may be disposed on the emission layer.

[0204] The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer, but is not limited thereto.


[0205] For example, the electron transport region may have a structure of electron transport layer/electron injection layer or a structure of hole blocking layer/electron transport layer/electron injection layer, wherein layers of each structure are sequentially stacked from the emission layer in the stated order, but is not limited thereto.

[0206] According to an embodiment, the organic layer 150 of the organic light-emitting device may include an electron transport region between the emission layer and the second electrode 190, wherein the electron transport region includes the condensed cyclic compound represented by Formula 1.


[0207] The electron transport region may include a hole blocking layer. When the emission layer includes a phosphorescent dopant, the hole blocking layer may help prevent diffusion of triplet excitons or holes into an electron transport layer.

[0208] When the electron transport region includes a hole blocking layer, the hole blocking layer may be formed on the emission layer by using various methods, such as vacuum deposition, spin coating casting, an LB method, ink-jet printing, laser-printing, or LITL. When the hole blocking layer is formed by vacuum deposition and spin coating, deposition and coating conditions for the hole blocking layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0209] The hole blocking layer may include, e.g., at least one of BCP and Bphen below, but is not limited thereto.



BCP






Bphen

[0210] A thickness of the hole blocking layer may be about 20 Å to about 1,000 Å, e.g., about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have excellent hole blocking characteristics without a substantial increase in driving voltage.

[0211] The electron transport region may include an electron transport layer. The electron transport layer may be formed on the emission layer or the hole blocking layer by using various methods, such as vacuum deposition, spin coating casting, an LB method, ink-jet printing, laser-printing, or LITI. When an electron transport layer is formed by vacuum deposition and spin coating, deposition and coating conditions for the electron transport layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0212] According to an embodiment, the organic layer 150 of the organic light-emitting device may include an electron transport region between the emission layer and the second electrode 190. The electron transport region may include an electron transport layer, and the electron transport layer may include the condensed cyclic compound represented by Formula 1.

[0213] The electron transport layer may further include, in addition to the condensed cyclic compound represented by Formula 1, at least one selected from BCP, Bphen, and Alq<sub>3</sub>, Balq, TAZ, and NTAZ below.




Ⓢ indicates text missing or illegible when filed


[0214] A thickness of the electron transport layer may be about 100 Å to about 1,000 Å, e.g., about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transportation characteristics without a substantial increase in driving voltage.

[0215] The electron transport layer may further include a metal-containing material in addition to the materials described above.

[0216] The metal-containing material may include a Li complex. The Li complex may include, e.g., Compound ET-D1 (lithium quinolate, LiQ) or ET-D2 below.



ET-D1



ET-D2

[0217] The electron transport region may include an electron injection layer that facilitates electron injection from the second electrode 190.

[0218] The electron injection layer may be formed on the electron transport layer by using various methods, such as vacuum deposition, spin coating casting, an LB method, ink-jet printing, laser-printing, or LITI. When an electron injection

tion layer is formed by vacuum deposition and spin coating, deposition and coating conditions for the electron injection layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0219] The electron injection layer may include at least one selected from, LiF, NaCl, CsF, Li<sub>2</sub>O, BaO, and LiQ.

[0220] A thickness of the electron injection layer may be about 1 Å to about 100 Å, e.g., about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron transportation characteristics without a substantial increase in driving voltage.

[0221] The second electrode 190 may be on the organic layer 150 having such a structure. The second electrode 190 may be a cathode that is an electron injection electrode, and in this regard, a material for forming the second electrode 190 may be a material having a low work function, and such a material may be a metal, an alloy, an electrically conductive compound, or a mixture thereof. Detailed examples of the second electrode 190 may include lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag). According to another embodiment of the present invention, the material for forming the second electrode 190 may be ITO or IZO. The second electrode 190 may be a reflection electrode, a semi-transmissive electrode, or a transmissive electrode.

[0222] Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1, but is not limited thereto.

[0223] A C<sub>1</sub>-C<sub>60</sub> alkyl group used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and detailed examples thereof are a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C<sub>1</sub>-C<sub>60</sub> alkylene group used herein refers to a divalent group having the same structure as the C<sub>1</sub>-C<sub>60</sub> alkyl group.

[0224] A C<sub>1</sub>-C<sub>60</sub> alkoxy group used herein refers to a monovalent group represented by —OA<sub>101</sub> (wherein A<sub>101</sub> is the C<sub>1</sub>-C<sub>60</sub> alkyl), and detailed examples thereof are a methoxy group, an ethoxy group, and an isopropoxy group.

[0225] A C<sub>2</sub>-C<sub>60</sub> alkenyl group used herein refers to a hydrocarbon group formed by substituting at least one carbon double bond in the middle or terminal of the C<sub>2</sub>-C<sub>60</sub> alkyl group, and detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C<sub>2</sub>-C<sub>60</sub> alkenylene group used herein refers to a divalent group having the same structure as the C<sub>2</sub>-C<sub>60</sub> alkenyl group.

[0226] A C<sub>2</sub>-C<sub>60</sub> alkynyl group used herein refers to a hydrocarbon group formed by substituting at least one carbon triple bond in the middle or terminal of the C<sub>2</sub>-C<sub>60</sub> alkyl group, and detailed examples thereof are an ethynyl group and a propynyl group. A C<sub>2</sub>-C<sub>60</sub> alkynylene group used herein refers to a divalent group having the same structure as the C<sub>2</sub>-C<sub>60</sub> alkynyl group.

[0227] A C<sub>3</sub>-C<sub>10</sub> cycloalkyl group used herein refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms, and detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C<sub>3</sub>-C<sub>10</sub> cycloalkylene group used herein refers to a divalent group having the same structure as the C<sub>3</sub>-C<sub>10</sub> cycloalkyl group.

[0228] A C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group used herein refers to a monovalent monocyclic group having at least one heteroatom selected from N, O, P, and S as a ring-forming atom and 2 to 10 carbon atoms, and detailed examples thereof are a tetrahydrofuranyl group and a tetrahydrothiophenyl group. A C<sub>2</sub>-C<sub>10</sub> heterocycloalkylene group used herein refers to a divalent group having the same structure as the C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group.

[0229] A C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and does not have aromaticity, and detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C<sub>3</sub>-C<sub>10</sub> cycloalkenylene group used herein refers to a divalent group having the same structure as the C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group.

[0230] A C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, 2 to 10 carbon atoms, and at least one double bond in its ring. Detailed examples of the C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group are a 2,3-hydrofuranyl group and a 2,3-hydrothiophenyl group. A C<sub>2</sub>-C<sub>10</sub> heterocycloalkenylene group used herein refers to a divalent group having the same structure as the C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group.

[0231] A C<sub>6</sub>-C<sub>60</sub> aryl group used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C<sub>6</sub>-C<sub>60</sub> arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C<sub>6</sub>-C<sub>60</sub> aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C<sub>6</sub>-C<sub>60</sub> aryl group and the C<sub>6</sub>-C<sub>60</sub> arylene group each include two or more rings, the rings may be fused to each other.

[0232] A C<sub>2</sub>-C<sub>60</sub> heteroaryl group used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, and 2 to 60 carbon atoms. A C<sub>2</sub>-C<sub>60</sub> heteroarylene group used herein refers to a divalent group having a carbocyclic aromatic system that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, and 2 to 60 carbon atoms. Detailed examples of the C<sub>2</sub>-C<sub>60</sub> heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C<sub>2</sub>-C<sub>60</sub> heteroaryl group and the C<sub>2</sub>-C<sub>60</sub> heteroarylene group each include two or more rings, the rings may be fused to each other.

[0233] C<sub>6</sub>-C<sub>60</sub> aryloxy group used herein indicates —OA<sub>102</sub> (wherein A<sub>102</sub> is the C<sub>6</sub>-C<sub>60</sub> aryl group), and a C<sub>6</sub>-C<sub>60</sub> arylthio group used herein indicates —SA<sub>103</sub> (wherein A<sub>103</sub> is the C<sub>6</sub>-C<sub>60</sub> aryl group).

[0234] A monovalent non-aromatic condensed polycyclic group (for example, having 8 to 60 carbons) used herein refers to a monovalent group that has two or more rings condensed to each other, only carbon atoms as a ring-forming atom, and non-aromaticity in the entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. A divalent non-aromatic condensed polycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0235] A monovalent non-aromatic condensed heteropolycyclic group (for example, having 2 to 60 carbons) used herein refers to a monovalent group that has two or more rings condensed to each other, has a heteroatom selected from N, O, P, and S, other than carbon atoms, as a ring forming atom, and has non-aromaticity in the entire molecular structure. A detailed example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0236] The term “Ph” used herein refers to a phenyl group, the term “Me” used herein refers to a methyl group, the term “Et” used herein refers to an ethyl group, and the term “tert-Bu” or “But” used herein may refer to a tert-butyl group.

[0237] Hereinafter, an organic light-emitting device according to an embodiment of the present invention will be described in detail with reference to Synthesis Examples and Examples. The wording “B” was used instead of “A” used in describing Synthesis Examples means that a molar equivalent of A was identical to a molar equivalent of B.








[0238] The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.


#### EXAMPLE

##### Synthesis Example 1

##### Synthesis of Compound 2

[0239]



**[0240]** 1) Synthesis of Intermediate A-1

**[0241]** 6.69 g (40 mmol) of 9H-carbazole, 6.28 g (40 mmol) of bromobenzene, 1.52 g (24 mmol) of copper powder, and 8.29 g (60 mmol) of  $K_2CO_3$  were dissolved in 100 mL of o-dichlorobenzene, and then, the resultant solution was stirred at a temperature of 180° C. for 24 hours. The reaction solution was cooled to room (e.g., ambient) temperature, 60 mL of water was added thereto, and the result was extracted three times by using 50 mL of ethyl acetate. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporation of a solvent therefrom were separation-purified by using silica gel column chromatography to obtain 7.10 g of Intermediate A-1 (yield: 73%). The obtained compound was identified by LC-MS.  $C_{18}H_{13}N$ : M+243.1.

**[0242]** 2) Synthesis of Intermediate A-2

**[0243]** 7.10 g (29.2 mmol) of Intermediate A-1 was completely dissolved in 100 mL of  $CH_2Cl_2$  (methylene chloride), 5.20 g (29.2 mmol) of N-bromosuccinimide was added thereto, and the resultant solution was stirred at room temperature for 12 hours. 80 mL of water was added to the reaction solution, and then an extraction was performed thereon three times by using 60 mL of methylene chloride. An organic layer obtained therefrom was dried by using magnesium sulfate, a solvent was evaporated therefrom, and then, the resultant

solution was re-crystallized by using methanol to obtain 7.70 g (yield 82%) of Intermediate A-2. The obtained compound was identified by LC-MS.  $C_{18}H_{12}BrN$ : M+321.0.

**[0244]** 3) Synthesis of Intermediate A-3

**[0245]** 7.70 g (23.9 mmol) of Intermediate A-2 and 3.21 g (35.9 mmol) of CuCN were dissolved in 100 mL of DMF, and then, the resultant solution was stirred at a temperature of 150° C. for 24 hours. The reaction solution was cooled at room temperature, 80 mL of ammonia water and 80 mL of water were added thereto, and the result was extracted three times by using 60 mL of methylene chloride. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporation of a solvent therefrom were separation-purified by using silica gel column chromatography to obtain 5.82 g (yield: 91%) of Intermediate A-3. The obtained compound was identified by LC-MS.  $C_{19}H_{12}N_2$ : M+268.1.

**[0246]** 4) Synthesis of Intermediate A-4

**[0247]** 5.82 g (21.7 mmol) of Intermediate A-3 was completely dissolved in 100 mL of  $CH_2Cl_2$ , 3.86 g (21.7 mmol) of N-bromosuccinimide was added thereto, and the resultant solution was stirred at room temperature for 8 hours. 80 mL of water was added to the reaction solution, and then an extraction was performed thereon three times by using 60 mL of methylene chloride. An organic layer was dried by using magnesium sulfate, a solvent was evaporated therefrom, and then, the resultant solution was re-crystallized by using methanol to obtain 7.22 g (yield 96%) of Intermediate A-4. The obtained compound was identified by LC-MS.  $C_{19}H_{11}BrN_2$ : M+346.0.

**[0248]** 5) Synthesis of Intermediate A-5

**[0249]** 7.22 g (20.8 mmol) of Intermediate A-4, 5.81 g (22.9 mmol) of bis-(pinacolato)diboron, 6.12 g (62.4 mmol) of KOAc, and 0.50 g (0.62 mmol) of palladium(diphenylphosphinoferrocene)chloride were dissolved in 100 mL of DMSO in a 250 mL flask, and then, the resultant solution was refluxed at a temperature of 80° C. for 12 hours. The reaction solution was cooled to room temperature, 60 mL of distilled water was added thereto, and the result was extracted three times by using 60 mL of methylene chloride. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were washed with ethanol and dried to obtain 6.70 g (yield: 82%) of Intermediate A-5. The obtained compound was identified by LC-MS,  $C_{25}H_{23}BN_2O_2$ : M+394.2

**[0250]** 6) Synthesis of Intermediate A-6

**[0251]** 7.72 g (20 mmol) of 6,12-dibromochrysene, 1.83 g (15 mmol) of phenylboronic acid, 0.35 g (0.30 mmol) of  $Pd(PPh_3)_4$ , and 8.29 g (60 mmol) of  $K_2CO_3$  were dissolved in 80 mL of THF/ $H_2O$  mixture (volume ratio of 2/1), and then, the resultant solution was stirred at a temperature of 70° C. for 5 hours. The reaction solution was cooled to room temperature, 60 mL of water was added thereto, and the result was extracted three times by using 60 mL of ethyl ether. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were separation-purified by using silica gel column chromatography to obtain 5.35 g (yield: 70%) of Intermediate A-6. The obtained compound was identified by LC-MS.  $C_{22}H_{13}Br$ : M+356.0.

**[0252]** 7) Synthesis of Compound 2

**[0253]** 3.0 g (7.8 mmol) of Intermediate A-6, 3.15 g (8.0 mmol) of Intermediate A-5, 0.46 g (0.4 mmol) of  $\text{Pd}(\text{PPh}_3)_4$ , and 3.32 g (24 mmol) of  $\text{K}_2\text{CO}_3$  were dissolved in 80 mL of THF/ $\text{H}_2\text{O}$  mixture (volume ratio of 2/1), and then, the resultant mixture was stirred at a temperature of 80° C. for 12 hours. The reaction solution was cooled to room temperature, and then an extraction was performed thereon three times by using 50 mL of water and 50 mL of ethyl acetate. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were separation-purified by using silica gel column chromatography to obtain 3.20 g (yield: 72%) of Compound 2. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

**[0254]**  $\text{C}_{43}\text{H}_{26}\text{N}_2$  cal. 570.7, found 570.7.

**[0255]**  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.40 (s, 1H), 8.03 (s, 1H), 7.98 (m, 2H), 7.80 (d, 2H), 7.61 (m, 2H), 7.52 (d, 1H), 7.47 (d, 1H), 7.34-7.25 (m, 5H), 7.21-7.12 (m, 7H), 7.08-6.94 (m, 4H).

## Synthesis Example 2

## Synthesis of Compound 5

**[0256]** 3.58 g (yield: 74%) of Compound 5 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that 2-bromonaphthalene was used instead of bromobenzene in the synthesis of Compound 2. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

**[0257]**  $\text{C}_{47}\text{H}_{28}\text{N}_2$  cal. 620.8, found 620.8.

**[0258]**  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.32 (s, 1H), 7.94-7.92 (m, 3H), 7.72-7.70 (d, 2H), 7.59 (s, 1H), 7.45-7.37 (m, 7H), 7.26-7.12 (m, 10H), 7.03-6.94 (m, 4H).

## Synthesis Example 3

## Synthesis of Compound 10


**[0259]** 3.90 g (yield: 69%) of Compound 10 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that 2-bromo-4,6-diphenylpyrimidine was used instead of bromobenzene in the synthesis of Compound 2. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

**[0260]**  $\text{C}_{53}\text{H}_{32}\text{N}_4$  cal. 724.8, found 724.8.

**[0261]**  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.49 (s, 1H), 8.07 (2, 1H), 8.00 (d, 1H), 7.97 (d, 1H), 7.77 (d, 1H), 7.70-7.67 (m, 6H), 7.46 (s, 1H), 7.43 (d, 1H), 7.37 (d, 1H), 7.33 (t, 1H), 7.25-7.08 (m, 12H), 6.99-6.90 (m, 5H).

## Synthesis Example 4

## Synthesis of Compound 13

**[0262]**

**[0263]** 1) Synthesis of Intermediate A-7

**[0264]** 7.67 g (20 mmol) of Intermediate A-6, 3.01 g (15 mmol) of 4-bromophenylboronic acid, 0.35 g (0.30 mmol) of  $\text{Pd}(\text{PPh}_3)_4$ , and 8.29 g (60 mmol) of  $\text{K}_2\text{CO}_3$  were dissolved in 100 mL of THF/ $\text{H}_2\text{O}$  mixture (volume ratio of 2/1), and then, the resultant solution was stirred at a temperature of 70°C. for 5 hours. The reaction solution was cooled to room temperature, 80 mL of water was added thereto, and the result was extracted three times by using 80 mL of ethyl ether. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were separation0purified by using silica gel column chromatography to obtain 6.25 g (yield: 68%) of Intermediate A-7. The obtained compound was identified by LC-MS.  $\text{C}_{30}\text{H}_{16}\text{Br}$ :  $\text{M}+459.4$ .

**[0265]** 2) Synthesis of Compound 13

**[0266]** 3.48 g (yield: 69%) of Compound 13 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate A-7 was used instead of Intermediate A-5. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

**[0267]**  $\text{C}_{49}\text{H}_{30}\text{N}_2$  cal. 647.8, found 646.8.

**[0268]**  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.13 (s, 1H), 8.06 (s, 1H), 8.01 (d, 2H), 7.81 (d, 1H) 7.73 (d, 1H), 7.62-7.55 (m, 4H), 7.47-7.28 (m, 9H), 7.22-7.13 (m, 7H), 7.07 7.02 (m, 2H), 6.96 (t, 2H).

## Synthesis Example 5

## Synthesis of Compound 17

**[0269]** 3.61 g (yield: 64%) of Compound 17 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that 2-bromo-6-phenylpyrimidine was used instead of bromobenzene in the synthesis of Compound 2. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.



**[0270]**  $\text{C}_{54}\text{H}_{33}\text{N}_3$  cal. 723.9, found 723.9.

**[0271]**  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.42 (s, 1H), 8.31 (s, 1H), 8.07 (d, 1H), 8.02 (d, 1H) 7.77-7.66 (m, 5H), 7.55-7.52 (m, 2H), 7.44-7.27 (m, 11H), 7.21-7.11 (m, 7H), 7.06-6.93 (m, 4H).

## Synthesis Example 6

## Synthesis of Compound 36

**[0272]**



Ⓢ indicates text missing or illegible when filed

**[0273]** 1) Synthesis of Intermediate A-8

**[0274]** 8.78 g (yield: 73%) of Intermediate A-8 was obtained in the same manner as used to synthesize Intermediate A-1 in Synthesis Example 1, except that 2,7-dibromo-9H-carbazole was used instead of 9H-carbazole. The obtained compound was identified by LC-MS.  $\text{C}_{18}\text{H}_{11}\text{Br}_2\text{N}$ :  $\text{M}+398.9$ .

**[0275]** 2) Synthesis of Intermediate A-9

**[0276]** 3.57 g (yield: 47%) of Intermediate A-9 was obtained in the same manner as used to synthesize Intermediate A-3 in Synthesis Example 1, except that Intermediate A-8 was used instead of Intermediate A-2. The obtained compound was identified by LC-MS.  $\text{C}_{19}\text{H}_{11}\text{Br}_2\text{N}$ :  $\text{M}+346.0$

**[0277]** 3) Synthesis of Intermediate A-10

**[0278]** 3.57 g (10.3 mmol) of Intermediate A-9, 2.87 g (11.3 mmol) of bis(pinacolato) diboron, 3.03 g (30.9 mmol) of KOAc, and 0.25 g (0.31 mmol) of palladium(diphenylphosphinoferrocene)chloride were dissolved in 70 mL of DMSO in a 250 mL flask, and then, the resultant solution was refluxed at a temperature of 80°C. for 12 hours. The reaction solution was cooled to room temperature, 40 mL of distilled water was added thereto, and the result was extracted three times by using 40 mL of methylene chloride. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were washed with ethanol and dried to obtain 3.14 g (yield: 82%) of Intermediate A-10. The obtained compound was identified by LC-MS.  $\text{C}_{25}\text{H}_{23}\text{BN}_2\text{O}_2$ :  $\text{M}+394.2$ .

**[0279]** 4) Synthesis of Compound 36

**[0280]** 2.98 g (yield: 67%) of Compound 36 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate A-10 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

**[0281]**  $\text{C}_{43}\text{H}_{26}\text{N}_2$  cal. 570.7, found 570.7.

**[0282]**  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.18 (s, 1H), 7.94 (d, 1H), 7.86 (dd, 2H), 7.61 (d, 1H) 7.46-7.40 (m, 5H), 7.19-6.96 (m, 12H), 6.91-6.76 (m, 4H).

## Synthesis Example 7

## Synthesis of Compound 41

## [0283] 1) Synthesis of Intermediate C-1

[0284] Intermediate C-1 was obtained in the same manner as used to synthesize Intermediate A-6 in Synthesis Example 1, except that 6-bromo-2,4-bipyridine was used instead of bromophenyl.

## [0285] 2) Synthesis of Compound 41

[0286] 3.09 g (yield: 61%) of Compound 41 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-10 and C-1 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

[0287]  $\text{C}_{47}\text{H}_{28}\text{N}_4$  cal. 648.8, found 648.8.

[0288]  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.31 (s, 1H), 8.22 (s, 1H), 7.91 (d, 1H), 7.83 (m, 2H), 7.57 (m, 2H), 7.47 (d, 1H), 7.42-7.38 (m, 5H), 7.33-7.27 (m, 2H), 7.22-7.06 (m, 9H), 6.94-6.85 (m, 4H).

## Synthesis Example 8

## Synthesis of Compound 67

## [0289] 1) Synthesis of Intermediate C-2

[0290] Intermediate C-2 was obtained in the same manner as used to synthesize Intermediate A-7 in Synthesis Example 4, except that 6-bromonaphthalenylboronic acid was used instead of 4-bromophenylboronic acid.

## [0291] 2) Synthesis of Compound 67

[0292] 3.97 g (yield: 73%) of Compound 67 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-10 and C-2 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.



[0293]  $\text{C}_{53}\text{H}_{32}\text{N}_2$  cal. 696.9, found 696.9.

[0294]  $^1\text{H}$  NMR (400 MHz,  $\text{CDCl}_3$ )  $\delta$  8.25 (s, 1H), 7.89 (d, 1H), 7.83 (t, 2H), 7.60 (dd, 1H), 7.43-7.31 (m, 7H), 7.24-6.97 (m, 14H), 6.90-6.86 (m, 2H), 6.81-6.78 (m, 2H), 6.70-6.67 (m, 2H).

## Synthesis Example 9

## Synthesis of Compound 71

## [0295]



**[0296]** 1) Synthesis of Intermediate A-11

**[0297]** 9.75 g (30 mmol) of 2,6-dibromo-9H-carbazole, 4.71 g (30 mmol) of bromobenzene, 1.14 g (18 mmol) of copper powder, and 6.22 g (45 mmol) of  $K_2CO_3$  were dissolved in 100 mL of o-dichlorobenzene, and then, the resultant solution was stirred at a temperature of 180° C. for 24 hours. The reaction solution was cooled to room temperature, 60 mL of water was added thereto and the result was extracted three times by using 50 mL of ethyl acetate. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporation of a solvent therefrom were separation-purified by using silica gel column chromatography to obtain 9.16 g of Intermediate A-11 (yield: 76%). The obtained compound was identified by LC-MS.  $C_{18}H_{11}Br_2N$ : M+401.1.

**[0298]** 2) Synthesis of Intermediate A-12

**[0299]** 9.16 g (22.8 mmol) of Intermediate A-11 and 2.69 g (30 mmol) of CuCN were dissolved in 100 mL of DMF, and the resultant was stirred at a temperature of 150° C., for 24 hours. The reaction solution was cooled to room temperature, 80 mL of ammonia water and 80 mL of water were added to the reaction solution, and then an extraction was performed thereon three times by using 60 mL of methylene chloride. An organic layer obtained therefrom was dried by using magnesium sulfate, a solvent was evaporated therefrom, and then, the resultant solution was re-crystallized by using methanol to obtain 4.91 g (yield 62%) of Intermediate A-12. The obtained compound was identified by LC-MS.  $C_{19}H_{11}BrN_2$ : M+347.2.

**[0300]** 3) Synthesis of Intermediate A-13

**[0301]** 4.91 g (14.1 mmol) of Intermediate A-12, 3.81 g (15 mmol) of bis(pinacolato) diboron, 4.15 g (42.3 mmol) of KOAc, and 0.34 g (0.42 mmol) of palladium(diphenylphosphinoferrocene)chloride were dissolved in 100 mL of DMSO in a 250 mL flask, and then, the resultant solution was refluxed at a temperature of 80° C. for 12 hours. The reaction solution was cooled to room temperature, 60 mL of distilled water was added thereto, and the result was extracted three times by using 60 mL of methylene chloride. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were washed with ethanol and dried to obtain 4.78 g (yield: 86%) of Intermediate A-13. The obtained compound was identified by LC-MS.  $C_{25}H_{23}BN_2O_2$ : M+394.2.

**[0302]** 4) Synthesis of Intermediate A-14

**[0303]** 6.24 g (yield: 72%) of Intermediate A-14 was obtained in the same manner as used to synthesize Intermediate A-6 in Synthesis Example 1, except that naphthylboronic acid was used instead of phenylboronic acid. The obtained compound was identified by LC-MS.  $C_{28}H_{17}Br$ : M+433.4

**[0304]** 5) Synthesis of Compound 71

**[0305]** 3.15 g (8 mmol) of Intermediate A-13, 3.68 g (8.5 mmol) of Intermediate A-14, 0.46 g (0.4 mmol) of  $Pd(PPh_3)_4$ , and 3.32 g (24 mmol) of  $K_2CO_3$  were dissolved in 80 mL of THF/ $H_2O$  mixture (volume ratio of 2/1), and then, the resultant solution was stirred at room temperature of 80° C. for 12 hours. The reaction solution was cooled to room temperature, and then an extraction was performed thereon three times by using 50 mL of water and 50 mL of ethyl acetate. An organic layer obtained therefrom was dried by using magnesium sulfate, and then residues obtained by evaporating a solvent therefrom were separation-purified by using silica gel column


chromatography to obtain 3.68 g (yield: 74%) of Compound 71. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

**[0306]**  $C_{47}H_{28}N_2$  cal. 620.8, found 620.8

**[0307]**  $^1H$  NMR (400 MHz,  $CDCl_3$ )  $\delta$  8.12 (s, 2H), 7.84 (d, 1H), 7.82 (d, 1H), 7.62 (s, 1H), 7.58 (d, 1H), 7.41 (d, 1H), 7.31 (d, 1H), 7.73-7.60 (m, 7H), 7.10-7.03 (m, 5H), 7.00 (d, 1H), 6.96-6.83 (m, 6H), 6.79 (t, 1H).

## Synthesis Example 10

## Synthesis of Compound 79

**[0308]****[0309]** 1) Synthesis of Intermediate A-15

**[0310]** 3.14 g (yield: 46%) of Intermediate A-15 was obtained in the same manner as used to synthesize Intermediate A-3 in Synthesis Example 1, except that 2,8-dibromodibenzofuran was used instead of Intermediate A-2. The obtained compound was identified by LC-MS.  $C_{13}H_6BrNO$ : M+272.1.

**[0311]** 2) Synthesis of Intermediate I-16

**[0312]** 2.98 g (yield: 81%) of Intermediate A-16 was obtained in the same manner as used to synthesize Intermediate A-5 in Synthesis Example 1, except that Intermediate A-15 was used instead of Intermediate A-4. The obtained compound was identified by LC-MS.  $C_{19}H_{18}BNO$ : M+319.2.

**[0313]** 3) Synthesis of Intermediate C-3

**[0314]** Intermediate C-3 was obtained in the same manner as used to synthesize Intermediate A-6 in Synthesis Example 1, except that 2-bromonaphthalene was used instead of bromophenyl.

**[0315]** 4) Synthesis of Compound 79

**[0316]** 3.58 g (yield: 73%) of Compound 79 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates C-3 and A-16 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1H$  NMR.



**[0317]**  $C_{47}H_{28}N_2$  cal. 545.6, found 545.6

**[0318]**  $^1H$  NMR (400 MHz,  $CDCl_3$ )  $\delta$  8.11 (s, 1H), 7.98 (m, 3H), 7.88 (d, 1H), 7.84 (d, 1H), 7.64 (s, 1H), 7.50-7.38 (m, 9H), 7.31-7.20 (m, 5H), 7.25 (t, 2H).

## Synthesis Example 11

## Synthesis of Compound 100

[0319]



[0320] 1) Synthesis of Intermediate A-17

[0321] 2.89 g (yield: 71%) of Intermediate A-17 was obtained in the same manner as used to synthesize Intermediate A-7 in Synthesis Example 4, except that 4,6-diphenylpyrimidinylboronic acid was used instead of 4-bromophenylboronic acid. The obtained compound was identified by LC-MS.  $C_{40}H_{25}BrN_2$ :  $M+613.6$ .

[0322] 2) Synthesis of Intermediate A-18

[0323] 2.91 g (yield: 79%) of Intermediate A-18 was obtained in the same manner as used to synthesize Intermediates A-15 and A-16 in Synthesis Example 10 in this stated order, except that 4,6-dibromodibenzofuran was used instead of 2,8-dibromodibenzofuran in the synthesis of Intermediate A-15. The obtained compound was identified by LC-MS.  $C_{19}H_{18}BNO_3$ :  $M+319.2$ .

[0324] 3) Synthesis of Compound 100

[0325] 3.95 g (yield: 68%) of Compound 100 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-18 and A-17 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1H$  NMR.


[0326]  $C_{53}H_{31}N_3O$  cal. 725.9, found 725.9.


[0327]  $^1H$  NMR (400 MHz,  $CDCl_3$ )  $\delta$  8.36 (s, 1H), 8.23 (s, 1H), 7.89 (d, 1H), 7.69-7.57 (m, 7H), 7.45 (dd, 1H), 7.37 (s, 1H), 7.3 (d, 1H), 7.26-7.21 (m, 5H), 7.16-6.99 (m, 10H), 6.89 (m, 2H), 6.81 (t, 1H).

## Synthesis Example 12

## Synthesis of Compound 109

[0328]



**[0329]** 1) Synthesis of Intermediate A-19

**[0330]** 3.27 g (yield: 53%) of Intermediate A-19 was obtained in the same manner as used to synthesize Intermediate A-15 in Synthesis Example 10, except that 2,8-dibromodibenzothiophene was used instead of 2,8-dibromodibenzofuran. The obtained compound was identified by LC-MS.  $C_{16}H_6BrNS$ :  $M+286.9$ .

**[0331]** 2) Synthesis of Intermediate A-20

**[0332]** 2.79 g (yield: 73%) of Intermediate A-20 was obtained in the same manner as used to synthesize Intermediate A-16 in Synthesis Example 10, except that Intermediate A-19 was used instead of Intermediate A-15. The obtained compound was identified by LC-MS.  $C_{19}H_{18}BNO_2S$ :  $M+335.1$ .

**[0333]** 3) Synthesis of Intermediate C-4

**[0334]** Intermediate C-4 was obtained in the same manner as used to synthesize Intermediate A-6 in Synthesis Example 1, except that 4,6-diphenyl-1,3,5-triazinylboronic acid was used instead of phenylboronic acid.

**[0335]** 4) Synthesis of Compound 109

**[0336]** 3.83 g (yield: 69%) of Compound 109 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-20 and C-4 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

**[0337]**  $C_{39}H_{21}NS$  cal. 666.8, found 666.8.

**[0338]**  $^1H$  NMR (400 MHz,  $CDCl_3$ )  $\delta$  8.37 (s, 1H), 8.34 (s, 1H), 8.05 (d, 1H), 7.92-7.89 (m, 5H), 7.82-7.79 (m, 2H), 7.65 (d, 1H), 7.47 (d, 1H), 7.39 (d, 1H), 7.36 (dd, 1H), 7.32-7.27 (m, 2H), 7.17-7.10 (m, 7H), 6.99-6.97 (m, 2H), 6.88 (t, 1H).

## Synthesis Example 13

## Synthesis of Compound 4

**[0339]** 2.87 g (yield: 69%) of Compound 4 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate A-14 was used

instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 14

## Synthesis of Compound 8

**[0340]** 3.48 g (yield: 71%) of Compound 8 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate C-5 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 15

## Synthesis of Compound 12

**[0341]** 3.16 g (yield: 73%) of Compound 12 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate C-6 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 16

## Synthesis of Compound 15

**[0342]** 3.67 g (yield: 74%) of Compound 15 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate C-7 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 17

## Synthesis of Compound 19

**[0343]** 2.96 g (yield: 73%) of Compound 19 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate C-8 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 18

## Synthesis of Compound 27

**[0344]** 3.17 g (yield: 68%) of Compound 27 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate C-9 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 19

## Synthesis of Compound 34

**[0345]** 3.34 g (yield: 76%) of Compound 34 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediate C-10 was used instead of Intermediate A-6. The obtained compound was identified by MS/FAB and  $^1H$  NMR.

## Synthesis Example 20

## Synthesis of Compound 40

**[0346]** 3.07 g (yield: 68%) of Compound 40 was obtained in the same manner as used to synthesize Compound 2 in

Synthesis Example 1, except that Intermediates A-10 and C-11 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 21

##### Synthesis of Compound 45

**[0347]** 3.43 g (yield: 74%) of Compound 45 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-10 and A-21 were used instead of Intermediate A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 22

##### Synthesis of Compound 58

**[0348]** 2.98 g (yield: 69%) of Compound 58 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-10 and C-12 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 23

##### Synthesis of Compound 68

**[0349]** 3.16 g (yield: 69%) of Compound 68 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-10 and C-10 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 24

##### Synthesis of Compound 73

**[0350]** 3.04 g (yield: 69%) of Compound 73 was obtained in the same manner as used to synthesize Compound 2 in

Synthesis Example 1, except that Intermediates A-13 and A-7 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 25

##### Synthesis of Compound 75

**[0351]** 3.44 g (yield: 69%) of Compound 75 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-16 and C-13 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 26

##### Synthesis of Compound 94

**[0352]** 2.76 g (yield: 69%) of Compound 94 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-18 and A-14 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

#### Synthesis Example 27

##### Synthesis of Compound 102

**[0353]** 3.31 g (yield: 69%) of Compound 102 was obtained in the same manner as used to synthesize Compound 2 in Synthesis Example 1, except that Intermediates A-20 and A-6 were used instead of Intermediates A-5 and A-6, respectively. The obtained compound was identified by MS/FAB and  $^1\text{H}$  NMR.

**[0354]**  $^1\text{H}$  NMR and MS/FAB results of synthesized compounds are shown in Table 1, below.

**[0355]** Synthesis methods for other compounds (e.g., than the compounds shown in Table 1) may be performed by referring to synthetic paths and source materials of Synthesis Examples 1 to 27.

TABLE 1

| Compound | $^1\text{H}$ NMR ( $\text{CDCl}_3$ , 400 MHz)                                                                                                                                                                                  | MS/FAB |        |
|----------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|--------|
|          |                                                                                                                                                                                                                                | found  | calc.  |
| 4        | $\delta$ = 8.36 (s, 1H), 8.24 (s, 1H), 7.95-7.92 (m, 2H), 7.73-7.70 (m, 2H), 7.46 (d, 1H), 7.40 (dd, 2H), 7.29-7.19 (m, 7H), 7.16-7.11 (m, 5H), 7.08 (d, 1H), 7.01-6.89 (m, 1H), 7.05 (t, 1H)                                  | 620.76 | 620.71 |
| 8        | $\delta$ = 8.30 (s, 1H), 8.17 (d, 1H), 8.01 (s, 1H), 7.91 (dd, 2H), 7.74 (d, 1H), 7.70 (d, 2H), 7.62 (d, 1H), 7.56 (d, 1H), 7.49-7.46 (m, 2H), 7.44 (d, 1H), 7.38 (d, 1H), 7.32 (d, 1H), 7.29-7.08 (m, 12H), 7.01-6.86 (m, 4H) | 697.84 | 697.69 |
| 12       | $\delta$ = 8.05-7.98 (m, 3H), 7.82 (s, 1H), 7.75-7.70 (m, 2H), 7.61-7.55 (m, 4H), 7.48 (d, 1H), 7.39-7.29 (m, 8H), 7.23-7.19 (m, 4H), 7.10-7.03 (m, 2H), 7.15 (t, 1H)                                                          | 570.69 | 570.73 |
| 15       | $\delta$ = 8.11 (s, 1H), 7.96 (s, 1H), 7.84 (t, 2H), 7.65 (s, 1H), 7.59 (s, 1H), 7.47-7.44 (m, 2H), 7.37-7.20 (m, 12H), 7.16-7.12 (m, 5H), 7.10 (d, 1H), 7.04-6.93 (m, 5H), 6.87 (t, 1H)                                       | 696.85 | 696.78 |
| 19       | $\delta$ = 8.16 (dd, 1H), 8.00 (s, 2H), 7.89 (d, 2H), 7.74 (dd, 1H), 7.69 (d, 1H), 7.62-7.60 (m, 2H), 7.56 (dd, 1H), 7.49-7.46 (m, 4H), 7.37-7.08 (m, 17H), 7.02-6.96 (m, 2H), 6.91 (t, 2H)                                    | 773.94 | 773.85 |
| 27       | $\delta$ = 8.19 (d, 1H), 8.01 (d, 1H), 7.97 (s, 1H), 7.90-7.84 (m, 3H), 7.70 (s, 1H), 7.55-7.41 (m, 7H), 7.28-7.23 (m, 4H), 7.16-7.08 (m, 7H), 7.04-6.99 (m, 3H), 6.95 (t, 1H)                                                 | 647.78 | 647.74 |

TABLE 1-continued

| Compound | 1H NMR (CDCl <sub>3</sub> , 400 MHz)                                                                                                                                                              | MS/FAB |        |
|----------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|--------|
|          |                                                                                                                                                                                                   | found  | calc.  |
| 34       | $\delta$ = 8.21 (s, 1H), 8.13 (s, 1H), 7.83 (d, 2H), 7.62 (s, 2H), 7.44-7.35 (m, 4H), 7.27-7.12 (m, 15H), 7.09 (d, 1H), 7.03-6.99 (m, 3H), 6.94 (t, 2H), 7.05-6.93 (m, 3H)                        | 746.91 | 746.83 |
| 40       | $\delta$ = 8.42 (s, 1H), 8.32 (s, 1H), 7.96 (s, 1H), 7.61-7.51 (m, 5H), 7.45-7.41 (m, 3H), 7.30-6.83 (m, 18H)                                                                                     | 647.78 | 647.66 |
| 45       | $\delta$ = 8.32 (s, 1H), 8.28 (s, 1H), 8.01 (d, 1H), 7.88-7.85 (m, 4H), 7.79 (d, 1H), 7.61 (d, 1H), 7.50 (d, 1H), 7.36-7.33 (m, 3H), 7.24 (m, 1H), 7.14-7.03 (m, 12H), 6.97-6.84 (m, 5H)          | 725.86 | 725.67 |
| 58       | $\delta$ = 8.05-7.99 (m, 4H), 7.61-7.54 (m, 6H), 7.45 (dd, 1H), 7.40 (dd, 1H), 7.35-6.92 (m, 18H)                                                                                                 | 646.79 | 646.84 |
| 68       | $\delta$ = 8.28 (s, 1H), 8.20 (s, 1H), 7.89 (d, 2H), 7.68 (d, 1H), 7.52-7.42 (m, 6H), 7.36 (dd, 1H), 7.31-7.16 (m, 13H), 7.14 (dd, 1H), 7.08-7.05 (m, 3H), 6.99 (t, 2H), 6.91-6.84 (m, 3H)        | 746.91 | 746.79 |
| 73       | $\delta$ = 8.27 (s, 1H), 8.19 (m, 1H), 8.14 (d, 2H), 7.92 (d, 1H), 7.72-7.70 (m, 2H), 7.63-7.58 (m, 3H), 7.53-7.48 (m, 4H), 7.44-7.37 (m, 4H), 7.32-7.20 (m, 7H), 7.14-7.08 (m, 3H), 7.02 (t, 2H) | 646.79 | 646.68 |
| 75       | $\delta$ = 8.17 (s, 1H), 8.02 (d, 1H), 7.97 (s, 1H), 7.92 (s, 1H), 7.70 (d, 2H), 7.58-7.53 (m, 2H), 7.45-7.24 (m, 8H), 7.18 (t, 1H)                                                               | 419.48 | 419.41 |
| 94       | $\delta$ = 8.29 (s, 1H), 8.15 (s, 1H), 7.83 (dd, 2H), 7.51 (dd, 1H), 7.46 (dd, 1H), 7.39-7.33 (m, 3H), 7.27-7.04 (m, 10H), 6.98-6.89 (m, 3H), 6.83 (t, 1H)                                        | 545.64 | 545.52 |
| 102      | $\delta$ = 8.20 (d, 1H), 8.14 (s, 1H), 8.05-7.99 (m, 4H), 7.67 (d, 1H), 7.60-7.51 (m, 5H), 7.33-7.28 (m, 4H), 7.17-7.09 (m, 3H), 6.99 (t, 1H), 6.94 (t, 1H)                                       | 511.64 | 511.58 |

## Example 1

[0356] An ITO glass substrate (a product of Corning Co., Ltd) including an 15  $\Omega/\text{cm}^2$  ITO layer (1,200 Å thickness) was cut to a size of 50 mm×50 mm×0.7 mm, sonicated by using isopropyl alcohol and pure water each for 5 minutes, and cleaned by the exposure to ultraviolet rays for 30 minutes and then to ozone. Then, the ITO glass substrate was mounted on a vacuum deposition apparatus.

[0357] 2-TNATA was deposited on the ITO layer acting as an anode to form a hole injection layer having a thickness of 600 Å, NPB was deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å, and then, ADN (host) and DPAVB<sub>i</sub> (dopant) were co-deposited at a weight ratio of 98:2 on the hole transport layer to form an emission layer having a thickness of 300 Å.

[0358] Thereafter, Compound 2 was deposited on the emission layer to form an electron transport layer having a thickness of 300 Å, LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was deposited on the electron injection layer to form a cathode having a thickness of 3,000 Å, thereby completing the manufacture of an organic light-emitting device.

## Example 2

[0359] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 5 was used instead of Compound 2.

## Example 3

[0360] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 10 was used instead of Compound 2.

## Example 4

[0361] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 13 was used instead of Compound 2.

## Example 5

[0362] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 17 was used instead of Compound 2.

## Example 6

[0363] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 36 was used instead of Compound 2.

## Example 7

[0364] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 41 was used instead of Compound 2.

## Example 8

[0365] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 67 was used instead of Compound 2.

## Example 9

[0366] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 71 was used instead of Compound 2.

## Example 10

[0367] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 79 was used instead of Compound 2.

## Example 11


[0368] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 100 was used instead of Compound 2.

## Example 12

[0369] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound 109 was used instead of Compound 2.

## Comparative Example 1


[0370] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Alq<sub>3</sub> was used instead of Compound 2.



## Comparative Example 2

[0371] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound A was used instead of Compound 2.


&lt;Compound A&gt;



## Comparative Example 3

[0372] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming an electron transport layer, Compound B was used instead of Compound 2.

&lt;Compound B&gt;



## Evaluation Wxample 1

[0373] The driving voltage, current density, brightness, efficiency, and half-lifespan of the organic light-emitting devices manufactured according to Examples 1 to 12, and Comparative Examples 1 to 3 were measured by using a Kethley SMU 236 and a brightness photometer PR650, and

results thereof are shown to Table 2, below. The half-lifespan is a period of time that is taken until the brightness of the organic light-emitting device reduces down to 50% of the initial brightness.

TABLE 2

|                       | Electron transport layer | Driving voltage (V) | Current Density (mA/cm <sup>2</sup> ) | Brightness (cd/m <sup>2</sup> ) | Efficiency (cd/A) | Emission color | Half lifespan (hr @ 100 mA/cm <sup>2</sup> ) |
|-----------------------|--------------------------|---------------------|---------------------------------------|---------------------------------|-------------------|----------------|----------------------------------------------|
| Example 1             | Compound 2               | 5.27                | 50                                    | 3285                            | 6.57              | Blue           | 524                                          |
| Example 2             | Compound 5               | 5.46                | 50                                    | 3165                            | 6.33              | Blue           | 489                                          |
| Example 3             | Compound 10              | 5.13                | 50                                    | 3390                            | 6.78              | Blue           | 427                                          |
| Example 4             | Compound 13              | 5.36                | 50                                    | 3310                            | 6.62              | Blue           | 463                                          |
| Example 5             | Compound 17              | 5.05                | 50                                    | 3505                            | 7.01              | Blue           | 308                                          |
| Example 6             | Compound 36              | 5.30                | 50                                    | 3405                            | 6.81              | Blue           | 467                                          |
| Example 7             | Compound 41              | 4.95                | 50                                    | 3560                            | 7.12              | Blue           | 280                                          |
| Example 8             | Compound 67              | 5.47                | 50                                    | 3435                            | 6.87              | Blue           | 454                                          |
| Example 9             | Compound 71              | 5.43                | 50                                    | 3490                            | 6.98              | Blue           | 479                                          |
| Example 10            | Compound 79              | 5.39                | 50                                    | 3140                            | 6.28              | Blue           | 435                                          |
| Example 11            | Compound 100             | 5.34                | 50                                    | 3410                            | 6.82              | Blue           | 336                                          |
| Example 12            | Compound 109             | 5.12                | 50                                    | 3465                            | 6.93              | Blue           | 348                                          |
| Comparative Example 1 | Alq <sub>3</sub>         | 7.28                | 50                                    | 2160                            | 4.32              | Blue           | 145                                          |
| Comparative Example 2 | Compound A               | 5.45                | 50                                    | 2680                            | 5.36              | Blue           | 449                                          |
| Comparative Example 3 | Compound B               | 5.96                | 50                                    | 2990                            | 5.98              | Blue           | 328                                          |


[0374] From Table 1, it may be seen that the driving voltage, current density, brightness, efficiency, and half-lifespan of the organic light-emitting devices manufactured according to Examples 1 to 12 were higher than the driving voltage, current density, brightness, efficiency, and half-lifespan of the organic light-emitting devices manufactured according to Comparative Examples 1 to 3, e.g., Comparative Examples 1 and 3.

[0375] As described above, an organic light -emitting device including a condensed cyclic compound according to an embodiment may have a low driving voltage, high efficiency, high brightness, and long lifespan.

[0376] Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:


1. A condensed cyclic compound represented by Formula 1:



<Formula 1>

wherein, in Formula 1, R<sub>1</sub> to R<sub>12</sub> are each independently selected from a group represented by Formula 2, below, a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a substituted or unsubstituted C<sub>1</sub>-C<sub>60</sub> alkyl group, a substituted or unsubstituted C<sub>2</sub>-C<sub>60</sub> alkenyl group, a substituted or unsubstituted C<sub>2</sub>-C<sub>60</sub> alkynyl group, a substituted or unsubstituted C<sub>1</sub>-C<sub>60</sub> alkoxy group, a sub-

stituted or unsubstituted C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a substituted or unsubstituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a substituted or unsubstituted C<sub>3</sub>-C<sub>10</sub>-C<sub>10</sub> cycloalkenyl group, a substituted or unsubstituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a substituted or unsubstituted C<sub>6</sub>-C<sub>60</sub> aryl group, a substituted or unsubstituted C<sub>6</sub>-C<sub>60</sub> aryloxy group, a substituted or unsubstituted C<sub>6</sub>-C<sub>60</sub> arylthio group, a substituted or unsubstituted C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic hetero-condensed polycyclic group, the group represented by Formula 2 being different from the substituted monovalent non-aromatic hetero-condensed polycyclic group, —N(Q<sub>1</sub>)(Q<sub>2</sub>), —Si(Q<sub>3</sub>)(Q<sub>4</sub>)(Q<sub>5</sub>), and —B(Q<sub>6</sub>)(Q<sub>7</sub>), provided that at least one of R<sub>1</sub> to R<sub>12</sub> is a group represented by Formula 2, in which \* represents a binding site;



wherein in Formulae 1 and 2,

X<sub>1</sub> is N(R<sub>21</sub>), O, or S;

each L<sub>1</sub> is independently selected from a substituted or unsubstituted C<sub>3</sub>-C<sub>10</sub> cycloalkylene group, a substituted or unsubstituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkylene group, a substituted or unsubstituted C<sub>3</sub>-C<sub>10</sub> cycloalkenylene group, a substituted or unsubstituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkenylene group, a substituted or unsubstituted C<sub>6</sub>-C<sub>60</sub> arylene group, a substituted or unsubstituted C<sub>2</sub>-C<sub>60</sub> heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic hetero-condensed polycyclic group;

a<sub>1</sub> is selected from 0, 1, 2, and 3;

b<sub>1</sub> and b<sub>2</sub> are each independently selected from 0, 1, 2, and 3;

at least one substituent of the substituted C<sub>3</sub>-C<sub>10</sub> cycloalkylene group, the substituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkylene group, the substituted C<sub>3</sub>-C<sub>10</sub> cycloalkenylene group, the substituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkenylene group, the substituted C<sub>6</sub>-C<sub>60</sub> arylene group, the substituted C<sub>2</sub>-C<sub>60</sub> heteroarylene group, the substituted divalent non-aromatic condensed polycyclic group, the substituted divalent non-aromatic hetero-condensed polycyclic group, the substituted C<sub>6</sub>-C<sub>60</sub> alkyl group, the substituted C<sub>2</sub>-C<sub>60</sub> alkenyl group, the substituted C<sub>2</sub>-C<sub>60</sub> alkynyl group, the substituted C<sub>2</sub>-C<sub>60</sub> alkoxy group, the substituted C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, the substituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, the substituted C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group, the substituted C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, the substituted C<sub>6</sub>-C<sub>60</sub> aryl group, the substituted C<sub>6</sub>-C<sub>60</sub> aryloxy group, the substituted C<sub>6</sub>-C<sub>60</sub> arylthio group, the substituted C<sub>2</sub>-C<sub>60</sub> heteroaryl group, the substituted monovalent non-aromatic con-

densed polycyclic group, and the substituted monovalent non-aromatic hetero-condensed polycyclic group is selected from:

- a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>60</sub> alkyl group, a C<sub>2</sub>-C<sub>60</sub> alkenyl group, a C<sub>2</sub>-C<sub>60</sub> alkynyl group, and a C<sub>1</sub>-C<sub>60</sub> alkoxy;
- a C<sub>1</sub>-C<sub>60</sub> alkyl group, a C<sub>2</sub>-C<sub>60</sub> alkenyl group, a C<sub>2</sub>-C<sub>60</sub> alkynyl group, and a C<sub>1</sub>-C<sub>60</sub> alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, a C<sub>6</sub>-C<sub>60</sub> aryloxy group, a C<sub>6</sub>-C<sub>60</sub> arylthio group, a C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group, —N(Q<sub>11</sub>)(Q<sub>12</sub>), —Si(Q<sub>13</sub>)(Q<sub>14</sub>)(Q<sub>15</sub>), and —B(Q<sub>16</sub>)(Q<sub>17</sub>);
- a C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, a C<sub>6</sub>-C<sub>60</sub> aryloxy group, a C<sub>6</sub>-C<sub>60</sub> arylthio group, a C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic hetero-condensed polycyclic group;
- a C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, a C<sub>6</sub>-C<sub>60</sub> aryloxy group, a C<sub>6</sub>-C<sub>60</sub> arylthio group, a C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic hetero-condensed polycyclic group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>60</sub> alkyl group, a C<sub>2</sub>-C<sub>60</sub> alkenyl group, a C<sub>2</sub>-C<sub>60</sub> alkynyl group, a C<sub>1</sub>-C<sub>60</sub> alkoxy group, a C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a C<sub>3</sub>-C<sub>10</sub>-C<sub>10</sub> cycloalkenyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, a C<sub>6</sub>-C<sub>60</sub> aryloxy group, a C<sub>6</sub>-C<sub>60</sub> arylthio group, a C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group —N(Q<sub>21</sub>)(Q<sub>22</sub>), —Si(Q<sub>23</sub>)(Q<sub>24</sub>)(Q<sub>25</sub>); and —N(Q<sub>31</sub>)(Q<sub>32</sub>), —Si(Q<sub>33</sub>)(Q<sub>34</sub>)(Q<sub>35</sub>), and —B(Q<sub>36</sub>)(Q<sub>37</sub>); and

R<sub>21</sub>, R<sub>31</sub>, R<sub>32</sub>, Q<sub>1</sub> to Q<sub>7</sub>, Q<sub>11</sub> to Q<sub>17</sub>, Q<sub>21</sub> to Q<sub>27</sub>, and Q<sub>31</sub> to Q<sub>37</sub> may be each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>60</sub> alkyl group, a C<sub>2</sub>-C<sub>60</sub> alkenyl group, a C<sub>2</sub>-C<sub>60</sub> alkynyl

group, and a C<sub>1</sub>-C<sub>60</sub> alkoxy group, a C<sub>3</sub>-C<sub>10</sub> cycloalkyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkyl group, a C<sub>3</sub>-C<sub>10</sub> cycloalkenyl group, a C<sub>2</sub>-C<sub>10</sub> heterocycloalkenyl group, a C<sub>6</sub>-C<sub>60</sub> aryl group, a C<sub>2</sub>-C<sub>60</sub> heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic hetero-condensed polycyclic group.


2. The condensed cyclic compound as claimed in claim 1, wherein each L<sub>1</sub> is independently selected from:

a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isooxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzooxazolylene group, an isobenzooxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group;


and  
a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isooxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a purinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene

group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylene group, an isobenzothiazolylene group, a benzooxazolylene group, an isobenzooxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylene group, a benzocarbazolylene group, a dibenzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>20</sub> alkyl group, a C<sub>1</sub>-C<sub>20</sub> alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentanylyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazolpyridinyl group, and an imidazopyrimidinyl group.

3. The condensed cyclic compound as claimed in claim 1, wherein each L<sub>1</sub> is independently a group represented by one of Formulae 3-1 to 3-32, below:




Formula 3-1



Formula 3-2

-continued



Formula 3-3

Formula 3-4

Formula 3-5

Formula 3-6

Formula 3-7


Formula 3-8

Formula 3-9

Formula 3-10

Formula 3-11

-continued



Formula 3-12

Formula 3-13

Formula 3-14

Formula 3-15

Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19










Formula 3-20

Formula 3-21

Formula 3-22

Formula 3-23

-continued



(?) indicates text missing or illegible when filed

Formula 3-24

wherein in Formulae 3-1 to 3-32,

 $Y_1$  is O, X,  $C(Z_3)(Z_4)$ ,  $N(Z_5)$ , or  $Si(Z_6)(Z_7)$ ;

Formula 3-25

$Z_1$  to  $Z_7$  are each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group,

Formula 3-26

Formula 3-27


Formula 3-28

 $d_1$  is selected from an integer of 1 to 4; $d_2$  is selected from an integer of 1 to 3; $d_3$  is selected from an integer of 1 to 6; $d_4$  is selected from an integer of 1 to 8; $d_5$  is selected from 1 to 2; $d_6$  is selected from an integer of 1 to 5, and $*$  and  $*1$  represent binding sites.

Formula 3-29


4. The condensed cyclic compound as claimed in claim 1, wherein each  $L_1$  is independently a group represented by one of Formulae 4-1 to 4-23 below, in which  $*$  and  $*1$  represent binding sites:

Formula 3-30




Formula 4-1

Formula 3-31




Formula 4-2


Formula 3-32




Formula 4-3




Formula 4-4










Formula 4-5



Formula 4-6



-continued



Formula 4-7

Formula 4-8

Formula 4-9









Formula 4-10

Formula 4-11

Formula 4-12

Formula 4-13

-continued



Formula 4-14

Formula 4-15

Formula 4-16

Formula 4-17


Formula 4-18

Formula 4-19


Formula 4-20

Formula 4-21

-continued



Formula 4-22



Formula 4-23

5. The condensed cyclic compound as claimed in claim 1, wherein a1 in Formula 2 is 0 or 1.

6. The condensed cyclic compound as claimed in claim 1, wherein in Formula 2,

$X_1$  is  $N(R_{21})$ ; and

$R_{21}$  is selected from:

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a benzocarbazolyl group, a thiadiazolyl group, an imidazolpyridinyl group, and an imidazopyrimidinyl group; and

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group,

a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a benzocarbazolyl group, a thiadiazolyl group, an imidazolpyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentanylyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluorantenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isooxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzooxazolyl group, an isobenzooxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a benzocarbazolyl group, a thiadiazolyl group, an imidazolpyridinyl group, and an imidazopyrimidinyl group.

7. The condensed cyclic compound as claimed in claim 1, wherein

$X_1$  is  $N(R_{21})$ ; and

$R_{21}$  is selected from:

a phenyl group, a naphthyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a carbazolyl group, and a triazinyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

8. The condensed cyclic compound as claimed in claim 1, wherein:

$R_1$  to  $R_{12}$  are each independently selected from:

a group represented by Formula 2, a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, and  $Si(Q_3)(Q_4)(Q_5)$ , in which  $Q_3$  to  $Q_5$  are each independently selected from a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, and a naphthyl group; and

at least one of  $R_1$  to  $R_{12}$  is a group represented by Formula 2.

9. The condensed cyclic compound as claimed in claim 1, wherein, in Formula 1,  $R_{12}$  is a group represented by Formula 2.

10. The condensed cyclic compound as claimed in claim 1, wherein, in Formulae 1 and 2:


$X_1$  is  $N(R_{21})$ ; and

$R_{21}$  is selected from Formulae 5-1 to 5-35 below, in which \* represents a binding site;


$R_1$  to  $R_{12}$  are each independently selected from a group represented by Formula 2, a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, and a group represented by one of Formu-

lae 5-1 to 5-35 below, wherein at least one of  $R_1$  to  $R_{12}$  is a group represented by Formula 2; and


$R_{31}$  and  $R_{32}$  are each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, and a group represented by one of Formulae 5-1 to 5-35 below:




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4



Formula 5-5









Formula 5-6



Formula 5-7

-continued



Formula 5-8

Formula 5-9











Formula 5-10

Formula 5-11

Formula 5-12

Formula 5-13

-continued



Formula 5-14

Formula 5-15

Formula 5-16

Formula 5-17

Formula 5-18

Formula 5-19









Formula 5-20

Formula 5-21

Formula 5-22

Formula 5-23

-continued



Formula 5-24

Formula 5-25

Formula 5-26

Formula 5-27





Formula 5-28

Formula 5-29

Formula 5-30

Formula 5-31

-continued



Formula 5-32

Formula 5-33


Formula 5-34

Formula 5-35


11. The condensed cyclic compound as claimed in claim 1, wherein the condensed polycyclic compound represented by Formula 1 is represented by any one of Formulae 1-1 to 1-12 below:

-continued

&lt;Formula 1-1&gt;





&lt;Formula 1-4&gt;





&lt;Formula 1-5&gt;

&lt;Formula 1-2&gt;




&lt;Formula 1-6&gt;

&lt;Formula 1-3&gt;




-continued




&lt;Formula 1-7&gt;

-continued




&lt;Formula 1-10&gt;

&lt;Formula 1-11&gt;





&lt;Formula 1-8&gt;

&lt;Formula 1-12&gt;













&lt;Formula 1-9&gt;



wherein,  $X_1$ ,  $L_1$ ,  $a_1$ ,  $R_6$ ,  $R_{31}$ ,  $R_{32}$ , and  $b_1$  and  $b_2$  in Formulae 1-1 to 1-12 are the same as those defined with respect to Formula 1.

**12.** The condensed cyclic compound as claimed in claim 11, wherein the Formulae 1-1 to 1-12,  $a_1$  is 0 or 1, and  $L_1$  is a group represented by Formula 4-1 to 4-23 below, in which \* and \*' represent binding sites:

-continued



Formula 4-1

Formula 4-2

Formula 4-3

Formula 4-4

Formula 4-5








Formula 4-6

Formula 4-7

Formula 4-8

Formula 4-9

Formula 4-10



Formula 4-11

Formula 4-12

Formula 4-13


Formula 4-14

Formula 4-15


Formula 4-16

Formula 4-17


-continued




Formula 4-18




Formula 4-19




Formula 4-20



Formula 4-21



Formula 4-22




Formula 4-23

13. The condensed cyclic compound as claimed in claim 11, wherein, in Formulae 1-1 to 1-12:


$X_1$  is  $N(R_{21})$ ;

$R_{21}$  is a group selected from Formulae 5-1 to 5-35, below, in which \* represents a binding site; and


$R_6$ ,  $R_{31}$ , and  $R_{32}$  are each independently selected from a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, and Formulae 5-1 to 5-35 below:




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5



Formula 5-6










Formula 5-7



Formula 5-8

-continued



Formula 5-9

Formula 5-10

Formula 5-11












Formula 5-12

Formula 5-13

Formula 5-14

Formula 5-15

-continued



Formula 5-16

Formula 5-17

Formula 5-18

Formula 5-19

Formula 5-20

Formula 5-21

Formula 5-22







Formula 5-23

Formula 5-24

Formula 5-25

Formula 5-26

-continued



Formula 5-27

Formula 5-28




Formula 5-29

Formula 5-30

Formula 5-31


Formula 5-32

-continued



**14.** The condensed cyclic compound as claimed in claim **11**, wherein the condensed polycyclic compound represented by Formula 1 is represented by any one of Formulae 1-1, 1-5, 1-6, and 1-9.


**15.** The condensed cyclic compound as claimed in claim **1**, wherein the condensed polycyclic compound represented by Formula 1 is one of Compounds 1 to 116 below:



Formula 5-33

Formula 5-34


Formula 5-35



2

3

4




5

6


7

-continued




7

-continued




9


8



10




-continued




11


-continued



13




12




14

-continued




15

-continued




17


16



18




-continued




19


-continued



21




20




22

-continued




23

-continued




25


24



26




-continued




27

-continued




28


29



30




-continued




31


-continued



33






32





34


-continued



-continued




-continued




40


-continued



42




41




43

-continued




44


-continued



46




45




47

-continued




48


-continued



50




49




51

-continued





-continued

54




55






-continued



-continued



60

62




61

63




-continued




64


-continued



66




65




67

-continued




68

-continued




71

69




70

72




-continued




73

-continued




75


74




76



77




-continued



78


-continued



79


81

80




82

-continued




83

-continued




86

84




85




87

-continued




88

-continued




90


89




91



92




-continued




93


-continued




94




95



96





97






98


-continued



-continued




-continued




104

-continued




105



107



106




108



109


123

-continued




110

-continued




112


111



113




-continued



114

-continued



116

**16.** An organic light-emitting device: comprising:

a first electrode;

a second electrode facing the first electrode; and

an organic layer that between the first and second electrodes, wherein:

the organic layer includes an emission layer, and

the organic layer includes at least one condensed polycyclic compound as claimed in claim 1.

115

**17.** The organic light-emitting device as claimed in claim 16, wherein the organic layer further includes:


a hole transport region between the first electrode and the emission layer, the hole transport region including at least one of a hole injection layer, a hole transport layer, a buffer layer, or an electron blocking layer, and


an electron transport region between the emission layer and the second electrode, the electron transport region including at least one of a hole blocking layer, an electron transport layer, or an electron injection layer.

**18.** The organic light-emitting device as claimed in claim 17, wherein the electron transport region includes the at least one condensed polycyclic compound.

**19.** The organic light-emitting device as claimed in claim 18, wherein the electron transport region includes the electron transport layer, the electron transport layer including the at least one condensed polycyclic compound.

**20.** The organic light-emitting device as claimed in claim 17, wherein the hole transport region includes at least one of a compound represented by Formulae 201A and 202A below:





wherein in Formulae 201A and 202A,

$L_{201}$  to  $L_{203}$  are each independently selected from:

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, a chrysenylene group, a pyridinylenylene group, a pyrazinylenylene group, a pyrimidinylenylene group, a pyridazinylenylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylenylene group, a quinazolinylene group, a carbazolylenylene group, and a triazinylene group; and

a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylene group, a pyrenylene group, a chrysenylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, a quinolinylene group, an isoquinolinylene group, a quinoxalinylene group, a quinazolinylene group, a carbazolylene group, and a triazinylene group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a  $C_1$ - $C_{20}$  alkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

xa1 to xa3 are each independently 0 or 1;

$R_{203}$ ,  $R_{211}$ , and  $R_{212}$  are each independently selected from:

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl

group, a quinoxaliny group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>20</sub> alkyl group, a C<sub>1</sub>-C<sub>20</sub> alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

$R_{213}$  and  $R_{214}$  are each independently selected from:

a C<sub>1</sub>-C<sub>20</sub> alkyl group and a C<sub>1</sub>-C<sub>20</sub> alkoxy group;

a C<sub>1</sub>-C<sub>20</sub> alkyl group and a C<sub>1</sub>-C<sub>20</sub> alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazoyl group, and a triazinyl group;

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>20</sub> alkyl group, a C<sub>1</sub>-C<sub>20</sub> alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridi-

nyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

R<sub>215</sub> and R<sub>216</sub> are each independently selected from:

a hydrogen, a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>20</sub> alkyl group, and a C<sub>1</sub>-C<sub>20</sub> alkoxy group;

a C<sub>1</sub>-C<sub>20</sub> alkyl group and a C<sub>1</sub>-C<sub>20</sub> alkoxy group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

nyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, -F, -Cl, -Br, -I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid and a salt thereof, a sulfonic acid and a salt thereof, a phosphoric acid and a salt thereof, a C<sub>1</sub>-C<sub>20</sub> alkyl group, a C<sub>1</sub>-C<sub>20</sub> alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

xa5 is 1 or 2.

\* \* \* \* \*

|                |                                                                                                                                                                                              |         |            |
|----------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | 缩合环状化合物和包括其的有机发光器件                                                                                                                                                                           |         |            |
| 公开(公告)号        | <a href="#">US20150069347A1</a>                                                                                                                                                              | 公开(公告)日 | 2015-03-12 |
| 申请号            | US14/294376                                                                                                                                                                                  | 申请日     | 2014-06-03 |
| [标]申请(专利权)人(译) | 三星显示有限公司                                                                                                                                                                                     |         |            |
| 申请(专利权)人(译)    | 三星DISPLAY CO. , LTD.                                                                                                                                                                         |         |            |
| 当前申请(专利权)人(译)  | 三星DISPLAY CO. , LTD.                                                                                                                                                                         |         |            |
| [标]发明人         | KIM KWANG HYUN<br>HWANG SEOK HWAN<br>KIM YOUNG KOOK<br>PARK JUN HA<br>JUNG HYE JIN<br>LEE EUN YOUNG<br>KIM JONG WOO<br>LIM JIN O<br>HAN SANG HYUN<br>JEONG EUN JAE<br>KIM SOO YON            |         |            |
| 发明人            | KIM, KWANG-HYUN<br>HWANG, SEOK-HWAN<br>KIM, YOUNG-KOOK<br>PARK, JUN-HA<br>JUNG, HYE-JIN<br>LEE, EUN-YOUNG<br>KIM, JONG-WOO<br>LIM, JIN-O<br>HAN, SANG-HYUN<br>JEONG, EUN-JAE<br>KIM, SOO-YON |         |            |
| IPC分类号         | H01L51/00 H01L51/50                                                                                                                                                                          |         |            |
| CPC分类号         | H01L51/0054 H01L51/0072 H01L51/0067 H01L2251/53 H01L51/0073 H01L51/0074 H01L51/50<br>H01L51/0058 H01L51/5072                                                                                 |         |            |
| 优先权            | 1020130107509 2013-09-06 KR                                                                                                                                                                  |         |            |
| 其他公开文献         | US9825231                                                                                                                                                                                    |         |            |
| 外部链接           | <a href="#">Espacenet</a> <a href="#">USPTO</a>                                                                                                                                              |         |            |

#### 摘要(译)

缩合环状化合物和包含其的有机发光装置，该稠合环状化合物由式1表示：

