



US 20160099411A1

(19) **United States**(12) **Patent Application Publication**
Kim et al.(10) **Pub. No.: US 2016/0099411 A1**(43) **Pub. Date: Apr. 7, 2016**(54) **CONDENSED-CYCLIC COMPOUND AND
ORGANIC LIGHT-EMITTING DIODE
INCLUDING THE SAME****C09K 11/02** (2006.01)**C07F 7/08** (2006.01)**C07C 211/61** (2006.01)**C09K 11/06** (2006.01)(71) Applicants: **SFC Co., Ltd.**, Cheongwon-gun (KR);
Samsung Display Co., Ltd.,
Yongin-City (KR)(52) **U.S. Cl.**CPC **H01L 51/006** (2013.01); **H01L 51/0077**
(2013.01); **C07C 211/61** (2013.01); **C09K**
11/06 (2013.01); **C09K 11/025** (2013.01);
H01L 51/0094 (2013.01); **H01L 51/0061**
(2013.01); **H01L 51/0058** (2013.01); **C07F**
7/0818 (2013.01); **C07D 213/74** (2013.01);
H01L 51/5076 (2013.01)(72) Inventors: **Myeong-Suk Kim**, Yongin-City (KR);
Jong-Tae Je, Cheongwon-gun (KR);
Se-Jin Lee, Cheongwon-gun (KR);
Seok-Bae Park, Cheongwon-gun (KR);
Se-Jin Yu, Cheongwon-gun (KR);
Jea-Geon Lim, Cheongwon-gun (KR);
Byoung-Ki Choi, Yongin-City (KR);
Tae-Kyung Kim, Yongin-City (KR);
Jeoung-In Yi, Yongin-City (KR)

(57)

ABSTRACTA condensed-cyclic compound represented by Formula 1
below, and an organic light-emitting diode including the con-
densed-cyclic compound.(21) Appl. No.: **14/969,767**(22) Filed: **Dec. 15, 2015**

Formula 1

Related U.S. Application Data(63) Continuation-in-part of application No. 13/352,150,
filed on Jan. 17, 2012, now Pat. No. 9,238,623.(30) **Foreign Application Priority Data**

Jan. 17, 2011 (KR) 10-2011-0004523

Oct. 13, 2011 (KR) 10-2011-0104825



Publication Classification(51) **Int. Cl.****H01L 51/00** (2006.01)**C07D 213/74** (2006.01)wherein R₁ through R₆, Ar₅ and Ar₆, and X₁ through X₁₀ are
defined as in the specification.

FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5



CONDENSED-CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DIODE INCLUDING THE SAME

Formula 1

CLAIM OF PRIORITY

[0001] This application is a continuation in part under 35 U.S.C. §120 of U.S. application Ser. No. 13/352,150, filed on Jan. 17, 2012 which is herein incorporated by reference. This application also makes reference to, incorporates the same herein, and claims all benefits accruing under 35 U.S.C. §119 from applications for CONDENSED-CYCLIC COMPOUND AND ORGANIC LIGHT-EMITTING DIODE INCLUDING THE SAME earlier filed in the Korean Intellectual Property Office on 17 Jan. 2011 and 13 Oct. 2011 and there duly assigned Serial Nos. 10-2011-0004523 and 10-2011-0104825, respectively.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a condensed-cyclic compound represented by Formula 1 and an organic light-emitting diode including the same.

[0004] 2. Description of the Related Art

[0005] Organic light-emitting diodes (OLEDs), which are self-emitting devices, have advantages such as a wide viewing angle, excellent contrast, quick response, high brightness, and excellent driving voltage. The OLEDs can provide multicolored images.

[0006] A general OLED has a structure including a substrate, an anode, a hole transport layer (HTL), an emission layer (EML), an electron transport layer (ETL), and a cathode which are sequentially stacked on the substrate. In this regard, the HTL, the EML, and the ETL are organic layers formed of organic compounds.

[0007] An operating principle of an OLED having the above-described structure is as follows.


[0008] When a voltage is applied between the anode and the cathode, holes injected from the anode move to the EML via the HTL, and electrons injected from the cathode move to the EML via the ETL. The holes and electrons recombine in the EML to generate excitons. When the excitons drop from an excited state to a ground state, light is emitted.

SUMMARY OF THE INVENTION

[0009] The present invention provides a condensed-cyclic compound having a novel structure.

[0010] The present invention also provides an organic light-emitting diode including the above condensed-cyclic compound.

[0011] According to an aspect of the present invention, there is provided a condensed-cyclic compound represented by Formula 1 below:



[0012] wherein R_1 may be represented by $-(Ar_1)_{a1}-$ ($R_{11})_{b1}$, R_2 may be represented by $-(Ar_2)_{a2}-$ ($R_{12})_{b2}$, R_3 may be represented by $-(Ar_3)_{a3}-$ ($R_{13})_{b3}$, and R_4 may be represented by $-(Ar_4)_{a4}-$ ($R_{14})_{b4}$; Ar_1 through Ar_4 may be each independently a substituted or unsubstituted C_6-C_{60} aromatic linking group or a substituted or unsubstituted C_2-C_{60} heteroaromatic linking group; Ar_5 and Ar_6 may be each independently a substituted or unsubstituted C_6-C_{60} arylene group or a substituted or unsubstituted C_2-C_{60} heteroarylene group; R_5 , R_6 , and R_{11} through R_{14} may be each independently non-covalent electron pairs, hydrogen, deuterium, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{60} cycloalkyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_2-C_{60} heteroaryl group, or a substituted or unsubstituted C_2-C_{60} condensed-cyclic group; a_1 through a_4 may be each independently an integer of 0 to 3; b_1 through b_4 may be each independently an integer of 1 to 5; c and d may be each independently an integer of 0 to 3; X_1 through X_{10} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{60} cycloalkyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_2-C_{60} heteroaryl group, $-(Si(R_{21})(R_{22})(R_{23}))$, or $-(N(R_{24})(R_{25}))$; and R_{21} through R_{25} may be each independently hydrogen, deuterium, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{60} cycloalkyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, or a substituted or unsubstituted C_2-C_{60} heteroaryl group.

[0013] In some embodiments of the present invention, R_{11} through R_{14} in Formula 1 may be each independently hydrogen, deuterium, a substituted or unsubstituted C_1-C_{10} alkyl


group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted pentalenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted azulenyl group, a substituted or unsubstituted heptalenyl group, a substituted or unsubstituted indacenyl group, a substituted or unsubstituted acenaphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted phenalenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted anthryl group, a substituted or unsubstituted fluoranthenyl group, a substituted or unsubstituted triphenylenyl group, a substituted or unsubstituted pyrenyl group, a substituted or unsubstituted chrysenyl group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted picenyl group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted pentaphenyl group, a substituted or unsubstituted hexacenyl group, a substituted or unsubstituted cyclopentyl group, a substituted or unsubstituted cyclohexyl group, a substituted or unsubstituted cycloheptyl group, a substituted or unsubstituted dihydronaphthyl group, a substituted or unsubstituted tetrahydronaphthyl group, or a substituted or unsubstituted dihydro-indenyl group.

[0014] In some embodiments of the present invention, Ar₁ through Ar₄ in Formula 1 may be each independently a substituted or unsubstituted benzene linking group, a substituted or unsubstituted pentalene linking group, a substituted or unsubstituted indene linking group, a substituted or unsubstituted naphthalene linking group, a substituted or unsubstituted azulene linking group, a substituted or unsubstituted heptalene linking group, a substituted or unsubstituted indacene linking group, a substituted or unsubstituted acenaphthylene linking group, a substituted or unsubstituted fluorene linking group, a substituted or unsubstituted phenalene linking group, a substituted or unsubstituted phenanthrene linking group, a substituted or unsubstituted anthracene linking group, a substituted or unsubstituted fluoranthene linking group, a substituted or unsubstituted triphenylene linking group, a substituted or unsubstituted pyrene linking group, a substituted or unsubstituted crycene linking group, a substituted or unsubstituted naphthacene linking group, a substituted or unsubstituted pycene linking group, a substituted or unsubstituted perylene linking group, a substituted or unsubstituted pentacene linking group, or a substituted or unsubstituted hexacene linking group.


[0015] In some embodiments of the present invention, a₁ through a₄ in Formula 1 may be each independently 0, 1, or 2, and b₁ through b₄ may be each independently 1 or 2.

[0016] In some embodiments of the present invention, R₁₁ through R₁₄ in Formula 1 may be each independently one of hydrogen; deuterium; a C₁-C₁₀ alkyl group; a phenyl group; a naphthyl group; a phenanthrenyl group; a fluorenyl group; a pyrenyl group; a cyclopentyl group; a cyclohexyl group; a tetrahydronaphthyl group; a dihydro-indenyl group; and a phenyl group, a naphthyl group, a phenanthrenyl group, a fluorenyl group, a pyrenyl group, a cyclopentyl group, a cyclohexyl group, a tetrahydronaphthyl group, and a dihydro-indenyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, and —Si(Q₁)(Q₂)(Q₃); Q₁


through Q₃ may be each independently a C₁-C₁₀ alkyl group or a C₆-C₁₄ aryl group; Ar₁ through Ar₄ may be each independently represented by one of Formulae 3A through 3G below.




Formula 3A




Formula 3B




Formula 3C




Formula 3D



Formula 3E



Formula 3F




Formula 3G

[0017] Wherein Z_{11} through Z_{14} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group; s may be an integer of 1 to 6; and t may be an integer of 1 to 3.

[0018] In some embodiments of the present invention, R_5 and R_6 in Formula 1 may be each independently hydrogen, deuterium, a substituted or unsubstituted C_1 - C_{10} alkyl group, or a substituted or unsubstituted C_6 - C_{20} aryl group.

[0019] In some embodiments of the present invention, R_5 and R_6 in Formula 1 may be each independently one of hydrogen; deuterium; a C_1 - C_{10} alkyl group; a phenyl group; a naphthyl group; and a phenyl group and a naphthyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group.

[0020] In some embodiments of the present invention, R_5 and R_6 in Formula 1 may be linked to each other via a single bond, a linking group represented by Formula 4A below, or a linking group represented by Formula 4B below.



Formula 4A




Formula 4B


[0021] Wherein X_{21} through X_{23} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, or a substituted or unsubstituted C_2 - C_{60} heteroaryl group.

[0022] In some embodiments of the present invention, the condensed-cyclic compound of Formula 1 may include one of the compounds represented by Formulae 1A through 1D below:


Formula 1A



Formula 1B




Formula 1C



-continued

Formula 1D




[0023] wherein R_1 through R_4 , Ar_5 , Ar_6 , c , d , X_1 through X_{10} , and X_{21} through X_{23} are the same as defined above.

[0024] Z_{21} and Z_{22} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group; u may be an integer of 1 to 4; and v may be an integer of 1 to 6.


[0025] In some embodiments of the present invention, at least one of a combination of R_1 and R_2 and a combination of R_3 and R_4 in Formula 1 may be linked to each other.

[0026] In some embodiments of the present invention, at least one of $-N(R_1)(R_2)$ and $-N(R_3)(R_4)$ in Formula 1 may be represented by one of Formulae 5A through 5F below.

Formula 5A




Formula 5B




-continued


Formula 5C




Formula 5D



Formula 5E




Formula 5F




[0027] Wherein Z_{31} through Z_{42} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group, or a substituted or unsubstituted C_6 - C_{60} aryl group; and w and x may be each independently an integer of 1 to 8.

[0028] In some embodiments of the present invention, the condensed-cyclic compound may be one of Compounds 1, 3, 9, 10, 11, 12, 14, 17, 22, 26, 28, 29, 54, 64, and 68:


Compound 1




Compound 3




Compound 9




Compound 10



Compound 11




Compound 12




-continued


Compound 14




Compound 17




Compound 22




Compound 26




Compound 28




-continued
Compound 29


Compound 54



Compound 64



Compound 68



[0029] According to another aspect of the present invention, there is provided an organic light-emitting diode including a first electrode; a second electrode facing the first electrode; and an organic layer interposed between the first electrode and the second electrode, wherein the organic layer includes at least one of the condensed-cyclic compounds of Formula 1.


[0030] In some embodiments of the present invention, the organic layer may include at least one of a hole injection layer, a hole transport layer, a functional layer having hole injection and hole transport abilities, an emission layer, an electron transport layer, and an electron injection layer.

[0031] In some embodiments of the present invention, the emission layer may include the condensed-cyclic compound.

[0032] In some embodiments of the present invention, the emission layer may include a host and the condensed-cyclic compound in the emission layer acts as a dopant.

[0033] In some embodiments of the present invention, the host may include an anthracene-based compound represented by Formula 60 below.

Formula 60



[0034] Wherein Ar_{11} and Ar_{12} may be each independently a substituted or unsubstituted C_6-C_{60} arylene group; Ar_{13} and Ar_{14} may be each independently a substituted or unsubstituted C_1-C_{10} alkyl group or a substituted or unsubstituted C_6-C_{60} aryl group; and e and f may be each independently an integer of 0 to 5.

[0035] In some embodiments of the present invention, the electron transport layer may include an electron transport organic compound and a metal-containing material.

[0036] In some embodiments of the present invention, the metal-containing material may be a lithium complex.

[0037] In some embodiments of the present invention, the organic layer may include at least one of a hole injection layer, a hole transport layer, and a functional layer having hole injection and hole transport abilities, and at least one of the hole injection layer, the hole transport layer, and the functional layer having hole injection and hole transport abilities comprises a charge-generating material.

BRIEF DESCRIPTION OF THE DRAWINGS

[0038] A more complete appreciation of the present invention, and many of the attendant advantages thereof, will be readily apparent as the present invention becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings in which like reference symbols indicate the same or similar components, wherein:

[0039] FIG. 1 is a schematic structure of an organic light-emitting diode (OLED) according to an embodiment of the present invention;

[0040] FIG. 2 is a graph showing lifetime characteristics of OLEDs manufactured according to Examples 1 through 4 and Comparative Example 1 according to an embodiment of the present invention;

[0041] FIG. 3 is a graph showing lifetime characteristics of OLEDs manufactured according to Examples 5 through 8 and Comparative Example 2 according to an embodiment of the present invention;

[0042] FIG. 4 is a graph showing changes in current density versus voltage characteristics of OLEDs of Examples 5 through 8 and Comparative Example 2 according to an embodiment of the present invention; and

[0043] FIG. 5 is a graph showing changes in current density versus voltage characteristics of OLEDs of Examples 1 through 4 and Comparative Example 1 according to an embodiment of the present invention.


DETAILED DESCRIPTION OF THE INVENTION

[0044] Hereinafter, the present invention will be described more fully with reference to the accompanying drawings, in which exemplary embodiments of the present invention are shown.

[0045] As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0046] According to an embodiment of the present invention, there is provided a condensed-cyclic compound represented by Formula 1 below:

Formula 1



[0047] Wherein R_1 may be represented by $-(Ar_1)_{a1}-(R_{11})_{b1}$, R_2 may be represented by $-(Ar_2)_{a2}-(R_{12})_{b2}$, R_3 may be represented by $-(Ar_3)_{a3}-(R_{13})_{b3}$, and R_4 may be represented by $-(Ar_4)_{a4}-(R_{14})_{b4}$; R_5 and R_6 may be each independently non-covalent electron pairs, hydrogen, deuterium, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, or a substituted or unsubstituted C_2 - C_{60} condensed-cyclic group.


[0048] In Formula 1, R_{11} through R_{14} may be each independently non-covalent electron pairs, hydrogen, deuterium, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, or a substituted or unsubstituted C_2 - C_{60} condensed-cyclic group.

[0049] For example, R_{11} through R_{14} may be each independently hydrogen, deuterium, a substituted or unsubstituted C_1 - C_{10} alkyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted pentalenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted azulenyl group, a substituted or unsubstituted heptalenyl group, a substituted or unsubstituted indacenyl group, a substituted or unsubstituted acenaphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted phenalenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted anthryl group, a substituted or unsubstituted fluoranthenyl group, a substituted or unsubstituted triphenylenyl group, a substituted or unsubstituted pyrenyl group, a substituted or unsubstituted chrysenyl group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted picenyl group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted pentaphenyl group, a substituted or unsubstituted hexacenyl group, a substituted or unsubstituted cyclopentyl group, a substituted or unsubstituted cyclohexyl group, a substituted or unsubstituted cycloheptyl group, a


substituted or unsubstituted dihydronaphthyl group, a substituted or unsubstituted tetrahydronaphthyl group, or a substituted or unsubstituted dihydro-indenyl group, but are not limited thereto.

[0050] R_{11} through R_{14} may be each independently one of hydrogen; deuterium; a C_1 - C_{10} alkyl group; a phenyl group; a naphthyl group; a phenanthrenyl group; a fluorenyl group; a pyrenyl group; a cyclopentyl group; a cyclohexyl group; a tetrahydronaphthyl group; a dihydro-indenyl group; and a phenyl group, a naphthyl group, a phenanthrenyl group, a fluorenyl group, a pyrenyl group, a cyclopentyl group, a cyclohexyl group, a tetrahydronaphthyl group, and a dihydro-indenyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$; Q_1 through Q_3 are each independently a C_1 - C_{10} alkyl group or a C_6 - C_{14} aryl group.


[0051] For example, R_{11} through R_{14} may be each independently hydrogen, deuterium, or a group represented by one of Formulae 2A through 2K below, but are not limited thereto:




Formula 2A




Formula 2B



Formula 2C




Formula 2D




Formula 2E


-continued




Formula 2F




Formula 2G




Formula 2H



Formula 2I



Formula 2J



Formula 2K

[0052] In Formulae 2A through 2K, Z_1 through Z_4 may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group (e.g., a C_1 - C_{10} alkyl group), a C_2 - C_{60} alkenyl group (e.g., a C_2 - C_{10} alkenyl group), a C_2 - C_{60} alkynyl group (e.g., a C_2 - C_{10} alkynyl group), a C_1 - C_{60} alkoxy group (e.g., a C_1 - C_{10} alkoxy group), or $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$; p is an integer of 1 to 11; and q is an integer of 1 to 4. In this regard, Q_1 through Q_3 may be each independently a C_1 - C_{10} alkyl group or a C_6 - C_{14} aryl group.


[0053] For example, in Formulae 2A through 2K, Z_1 through Z_4 may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, or $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$ where Q_1 through Q_3 may be each independently a C_1 - C_{10} alkyl group (e.g., a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, and the like).

[0054] In Formulae 2A through 2K, * denotes a binding site with "N" of Formula 1 when each of a_1 through a_4 is 0 and denotes a binding site with each of Ar_1 through Ar_4 when each of a_1 through a_4 is not 0.


[0055] In Formula 1, Ar₁ through Ar₄ may be each independently a substituted or unsubstituted C₆-C₆₀ aromatic linking group or a substituted or unsubstituted C₂-C₆₀ heteroaromatic linking group. Ar₁ through Ar₄ may be each independently a divalent linking group (refer to Formula 3A below), a trivalent linking group (refer to Formula 3C below), a tetravalent linking group, or a pentavalent group according to the number of each of R₁₁ groups to R₁₄ groups that are respectively linked to Ar₁ through Ar₄, and this may be easily understood with reference to Compounds 1 through 78 below, which are condensed-cyclic compounds.

[0056] In Formula 1, Ar₁ through Ar₄ may be each independently a substituted or unsubstituted benzene linking group, a substituted or unsubstituted pentalene linking group, a substituted or unsubstituted indene linking group, a substituted or unsubstituted naphthalene linking group, a substituted or unsubstituted azulene linking group, a substituted or unsubstituted heptalene linking group, a substituted or unsubstituted indacene linking group, a substituted or unsubstituted acenaphthylene linking group, a substituted or unsubstituted fluorene linking group, a substituted or unsubstituted phenalene linking group, a substituted or unsubstituted phenanthrene linking group, a substituted or unsubstituted anthracene linking group, a substituted or unsubstituted fluoranthene linking group, a substituted or unsubstituted triphenylene linking group, a substituted or unsubstituted pyrene linking group, a substituted or unsubstituted crycene linking group, a substituted or unsubstituted naphthacene linking group, a substituted or unsubstituted pycene linking group, a substituted or unsubstituted perylene linking group, a substituted or unsubstituted pentacene linking group, or a substituted or unsubstituted hexacene linking group.


[0057] For example, Ar₁ through Ar₄ may be each independently represented by one of Formulae 3A through 3G below:




Formula 3A




Formula 3B



Formula 3C




Formula 3D




Formula 3E

-continued



Formula 3F



Formula 3G

[0058] In Formulae 3A through 3G, Z₁₁ through Z₁₄ may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group (e.g., a C₁-C₁₀ alkyl group), a C₂-C₆₀ alkenyl group (e.g., a C₂-C₁₀ alkenyl group), a C₂-C₆₀ alkynyl group (e.g., a C₂-C₁₀ alkynyl group), or a C₁-C₆₀ alkoxy group (e.g., a C₁-C₁₀ alkoxy group); s is an integer of 1 to 6; and t is an integer of 1 to 3.

[0059] For example, in Formulae 3A through 3G, Z₁₁ through Z₁₄ may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, or a pentoxy group, but are not limited thereto.

[0060] In Formulae 3A through 3G, * denotes a binding site with “N” of Formula 1 and *' denotes a binding site with each of R₁₁ through R₁₄.

[0061] In Formula 1, a₁ through a₄ may be each independently an integer of 0 to 3 and b₁ through b₄ may be each independently an integer of 1 to 5. For example, a₁ through a₄ may be each independently an integer of 0, 1, or 2 and b₁ through b₄ may be each independently an integer of 1 or 2, but they are not limited thereto. If a₁ is 2 or more, two or more Ar₁ groups may be identical to or different from each other. If a₂ is 2 or more, two or more Ar₂ groups may be identical to or different from each other. If a₃ is 2 or more, two or more Ar₃ groups may be identical to or different from each other. If a₄ is 2 or more, two or more Ar₄ groups may be identical to or different from each other. If b₁ is 2 or more, two or more R₁₁ groups may be identical to or different from each other. If b₂ is 2 or more, two or more R₁₂ groups may be identical to or different from each other. If b₃ is 2 or more, two or more R₁₃ groups may be identical to or different from each other. If b₄ is 2 or more, two or more R₁₄ groups may be identical to or different from each other.

[0062] With reference to the description above, in Formula 1, R₁ through R₄ may be selected. For example, R₁ through R₄ may be each independently selected such that R₁₁ through R₁₄ are each independently one selected from hydrogen; deu-

terium; a C₁-C₁₀ alkyl group; a phenyl group; a naphthyl group; a phenanthrenyl group; a fluorenyl group; a pyrenyl group; a cyclopentyl group; a cyclohexyl group; a tetrahydronaphthyl group; a dihydro-indenyl group; and a phenyl group, a naphthyl group, a phenanthrenyl group, a fluorenyl group, a pyrenyl group, a cyclopentyl group, a cyclohexyl group, a tetrahydronaphthyl group, and a dihydro-indenyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, and —Si(Q₁)(Q₂)(Q₃) where Q₁ through Q₃ are each independently a C₁-C₁₀ alkyl group or a C₆-C₁₄ aryl group; and Ar₁ through Ar₄ are each independently represented by one of Formulae 3A through 3G.

[0063] Alternatively, R₁ through R₄ may be each independently selected such that R₁₁ through R₁₄ are each independently hydrogen or deuterium, or represented by one of Formulae 2A through 2K, and Ar₁ through Ar₄ are each independently represented by one of Formulae 3A through 3G, but are not limited thereto.

[0064] In Formula 1, R₁ through R₄ may be identical to or different from each other.

[0065] In Formula 1, Ar₅ and Ar₆ may be each independently a substituted or unsubstituted C₆-C₆₀ arylene group, or a substituted or unsubstituted C₂-C₆₀ heteroarylene group.


[0066] For example, Ar₅ and Ar₆ may be each independently a substituted or unsubstituted phenylene group, a substituted or unsubstituted pentalenylene group, a substituted or unsubstituted indenylene group, a substituted or unsubstituted naphthylene group, a substituted or unsubstituted azulenylenylene group, a substituted or unsubstituted heptalenylene group, a substituted or unsubstituted indacenylene group, a substituted or unsubstituted acenaphthylene group, a substituted or unsubstituted fluorenylene group, a substituted or unsubstituted phenalenylene group, a substituted or unsubstituted phenanthrenylene group, a substituted or unsubstituted anthrylene group, a substituted or unsubstituted fluoranthenylenylene group, a substituted or unsubstituted triphenylenylene group, a substituted or unsubstituted pyrenylene group, a substituted or unsubstituted chrysenylene group, a substituted or unsubstituted naphthacenylene group, a substituted or unsubstituted pycenylene group, a substituted or unsubstituted perylenylene group, a substituted or unsubstituted pentacenylene group, or a substituted or unsubstituted hexacenylene group.

[0067] For example, R₅ and R₆ are each independently hydrogen, deuterium, a substituted or unsubstituted C₁-C₁₀ alkyl group, or a substituted or unsubstituted C₆-C₂₀ aryl group.

[0068] For example, R₅ and R₆ may be each independently one of hydrogen; deuterium; a C₁-C₁₀ alkyl group; a phenyl group; a naphthyl group; and a phenyl group and a naphthyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group (e.g., methyl, ethyl, propyl, butyl, pentyl, and the like), a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group (e.g., methoxy, ethoxy, propoxy, butoxy, pentoxy, and the like), but are not limited thereto.

[0069] In Formula 1, c and d may be each independently an integer of 0 to 3. For example, c and d may be each independently an integer of 0 or 1, but are not limited thereto.

[0070] In Formula 1, R₅ and R₆ may be linked to each other via a single bond, a linking group represented by Formula 4A below, or a linking group represented by Formula 4B below:



Formula 4A



Formula 4B


[0071] Wherein X₂₁ through X₂₃ may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₆₀ cycloalkyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, or a substituted or unsubstituted C₂-C₆₀ heteroaryl group.

[0072] For example, in Formulae 4A and 4B, X₂₁ through X₂₃ may be each independently one of hydrogen; deuterium; a halogen atom; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; hydrazine; hydrazone; a carboxyl group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid or a salt thereof; a C₁-C₁₀ alkyl group; a phenyl group; a naphthyl group; and a phenyl group and a naphthyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group (e.g., methyl, ethyl, propyl, butyl, pentyl, and the like), a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group (e.g., methoxy, ethoxy, propoxy, butoxy, pentoxy, and the like), but are not limited thereto.


[0073] When R₅ and R₆ of Formula 1 are linked to each other via a single bond, a linking group of Formula 4A, or a linking group of Formula 4B as described above, the condensed-cyclic compound may be represented by one of Formulae 1A through 1D (in Formula 1, each of R₅ and R₆ is independently a substituted or unsubstituted phenyl group):

-continued


Formula 1A




Formula 1D



Formula 1B



Formula 1C




[0074] Wherein R_1 through R_4 , Ar_5 , Ar_6 , c , d , X_1 through X_{10} , and X_{21} through X_{23} are the same as defined above; Z_{21} and Z_{22} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group; u may be an integer of 1 to 4; and v may be an integer of 1 to 6.


[0075] For example, in Formulae 1A through 1D, Z_{21} and Z_{22} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, or a pentoxy group, but are not limited thereto.

[0076] In Formula 1, at least one of a combination of R_1 and R_2 and a combination of R_3 and R_4 may be linked to each other. For example, in Formula 1, at least one of $-N(R_1)(R_2)$ and $-N(R_3)(R_4)$ may be represented by one of Formulae 5A through 5F below, but are not limited thereto:


Formula 5A




-continued




Formula 5B




Formula 5C



Formula 5D



Formula 5E




Formula 5F

[0077] Wherein Z_{31} through Z_{42} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group,


or a substituted or unsubstituted C_6 - C_{60} aryl group; and w and x may be each independently an integer of 1 to 8.

[0078] For example, in Formulae 5A through 5F, Z_{31} through Z_{42} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, or an anthryl group, but are not limited thereto.


[0079] For example, in Formula 1, at least one of $—N(R_1)$ (R_2) and $—N(R_3)(R_4)$ may be represented by one of Formulae 6A through 6F below, but are not limited thereto:




Formula 6A



Formula 6B




Formula 6C




Formula 6D

-continued



Formula 6E



Formula 6F

[0080] In Formulae 6A through 6F, a detailed description of Z_{31} , Z_{32} , Z_{33} , Z_{34} , Z_{35} , and Z_{42} is already provided above. For example, Z_{31} , Z_{32} , Z_{33} , Z_{34} , and Z_{35} may be each independently hydrogen or a substituted or unsubstituted C_1 - C_{10} alkyl group, and Z_{42} may be a phenyl group, a naphthyl group, or an anthryl group.


[0081] In Formula 1, X_1 through X_{10} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted

C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_2 - C_{60} heteroaryl group, $-\text{Si}(\text{R}_{21})(\text{R}_{22})(\text{R}_{23})$, or $-\text{N}(\text{R}_{24})(\text{R}_{25})$; and where R_{21} through R_{25} may be each independently hydrogen, deuterium, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{60} cycloalkyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, or a substituted or unsubstituted C_2 - C_{60} heteroaryl group.


[0082] For example, in Formula 1, X_1 through X_{10} may be each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{10} alkyl group, a substituted or unsubstituted C_1 - C_{10} alkoxy group, or a substituted or unsubstituted C_6 - C_{14} aryl group. At least two adjacent substituents of X_1 through X_{10} may be linked to each other to form a saturated or unsaturated ring.

[0083] The condensed-cyclic compound may be one of Compounds 1 through 78 below, but is not limited thereto; wherein TMS is trimethyl silyl:


Compound 1




Compound 2



Compound 3




Compound 4




-continued


Compound 5




Compound 6




Compound 7




Compound 8




Compound 9




Compound 10



Compound 11




Compound 12




-continued


Compound 13



Compound 14




Compound 15




-continued


Compound 16




Compound 17




Compound 18



Compound 19




Compound 20




-continued


Compound 21




Compound 22




Compound 23




Compound 24



Compound 25




Compound 26




-continued


Compound 27




Compound 28




Compound 29




Compound 30




Compound 31




Compound 32



Compound 33




Compound 34




-continued


Compound 35




Compound 36




Compound 37




Compound 38




Compound 39



Compound 40




Compound 41




-continued


Compound 42




Compound 43




Compound 44




Compound 45




Compound 46




Compound 47



Compound 48




Compound 49




-continued


Compound 50




Compound 51




Compound 52



Compound 53




Compound 54




-continued


Compound 55




Compound 56




Compound 57




Compound 58




Compound 59




Compound 60




Compound 61




Compound 62




-continued
Compound 63




Compound 64




Compound 65



Compound 66




Compound 67




-continued


Compound 68




Compound 69



Compound 70




Compound 71




-continued


Compound 72




Compound 73




Compound 74




Compound 75




Compound 76



Compound 77




Compound 78




[0084] In some embodiments of the present invention, the condensed-cyclic compound may be one of Compounds 1A through 3A and 5A to 30A below, but is not limited thereto; wherein TMS is trimethyl silyl:


<Compound 1A>




<Compound 2A>




<Compound 3A>



<Compound 5A>




<Compound 6A>




-continued


<Compound 7A>




<Compound 8A>




<Compound 9A>




<Compound 10A>




<Compound 11A>



<Compound 12A>




<Compound 13A>




-continued

<Compound 14A>




<Compound 15A>




<Compound 16A>

<Compound 17A>




-continued


<Compound 18A>




<Compound 19A>




<Compound 20A>




<Compound 21A>



<Compound 22A>




<Compound 23A>




-continued


<Compound 24A>




<Compound 25A>




<Compound 26A>




<Compound 27A>




<Compound 28A>



<Compound 29A>



<Compound 30A>



[0085] Examples of the unsubstituted C_1 - C_{60} alkyl group (or C_1 - C_{60} alkyl group) include methyl, ethyl, propyl, isobutyl, sec-butyl, pentyl, iso-amyl, hexyl, and the like. The substituted C_1 - C_{60} alkyl group may be a group in which at least one hydrogen of the unsubstituted C_1 - C_{60} alkyl group is substituted with deuterium; a halogen atom; a hydroxyl group; a cyano group; a nitro group; an amino group; an amidino group; hydrazine; hydrazone; a carboxyl group or a salt thereof; a sulfonic acid group or a salt thereof; a phosphoric acid or a salt thereof; a C_1 - C_{60} alkyl group; a C_2 - C_{60} alkenyl group; a C_2 - C_{60} alkynyl group; a C_1 - C_{60} alkoxy group; a C_3 - C_{60} cycloalkyl group; a C_6 - C_{60} aryl group; a C_6 - C_{60} aryloxy group; a C_6 - C_{60} arylthio group; a C_2 - C_{60} heteroaryl group; a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{60} cycloalkyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, or a C_2 - C_{60} heteroaryl group that is substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group; $-\text{N}(\text{Q}_1)(\text{Q}_2)$; or $-\text{Si}(\text{Q}_3)(\text{Q}_4)(\text{Q}_5)$ (Q_1 through Q_5 maybe be each independently a C_3 - C_{60} cycloalkyl group; a C_6 - C_{60} aryl group; a C_6 - C_{60} aryloxy group; a C_6 - C_{60} arylthio group; a C_2 - C_{60} heteroaryl group); and a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, a C_3 - C_{60} cycloalkyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, or a C_2 - C_{60} heteroaryl group that is substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group.

[0086] The unsubstituted C_1 - C_{60} alkoxy group (or C_1 - C_{60} alkoxy group) has a formula of $-\text{OA}$ (in this regard, A is the unsubstituted C_1 - C_{60} alkyl group as described above) and examples thereof include methoxy, ethoxy, isopropoxy, and the like. At least one hydrogen atom of the unsubstituted C_1 - C_{60} alkoxy group may be substituted with the same substituent as in the substituted C_1 - C_{60} alkyl group described above.

[0087] The unsubstituted C_2 - C_{60} alkenyl group (or C_2 - C_{60} alkenyl group) is interpreted to contain at least one carbon-carbon double bond in the center or at a terminal of the unsubstituted C_2 - C_{60} alkyl group. Examples of the unsubstituted C_2 - C_{60} alkenyl group include ethenyl, propenyl, butenyl, and the like. At least one hydrogen atom of the unsubstituted C_2 - C_{60} alkenyl group may be substituted with the substituents described with reference to the substituted C_1 - C_{60} alkyl group described above.

[0088] The unsubstituted C_2 - C_{60} alkynyl group (or C_2 - C_{60} alkynyl group) is interpreted to contain at least one carbon-carbon triple bond in the center or at a terminal of the C_2 - C_{60} alkyl group defined above. Examples of the unsubstituted C_2 - C_{60} alkynyl group include ethynyl, propynyl, and the like. At least one hydrogen atom of the unsubstituted C_2 - C_{60} alkynyl group may be substituted with the substituents described with reference to the substituted C_1 - C_{60} alkyl group described above.

[0089] The unsubstituted C_6 - C_{60} aryl group indicates a monovalent group having an aromatic carbocyclic system that has 5 to 60 carbon atoms and at least one aromatic ring and the unsubstituted C_6 - C_{60} arylene group indicates a divalent group having an aromatic carbocyclic system that has 5 to 60 carbon atoms and at least one aromatic ring. If the C_6 - C_{60} aryl group and the C_6 - C_{60} arylene group each independently have two or more aromatic rings, the rings may be fused with each other. At least one hydrogen atom of each of the unsubstituted C_6 - C_{60} aryl group and the unsubstituted C_6 - C_{60} arylene group may be substituted with the substituents described with reference to the substituted C_1 - C_{60} alkyl group described above.

[0090] Examples of the unsubstituted C_6 - C_{60} aryl group include, but are not limited to, a phenyl group, a C_1 - C_{10} alkylphenyl group (e.g., an ethylphenyl group), a C_1 - C_{10} alkylbiphenyl group (e.g., an ethylbiphenyl group), a halophenyl group (e.g., an o-, m- and p-fluorophenyl group, and a dichlorophenyl group), a dicyanophenyl group, a trifluoromethoxyphenyl group, an o-, m-, and p-tolyl group, an o-, m- and p-cumenyl group, a mesityl group, a phenoxyphenyl group, an (α,α -dimethylbenzene)phenyl group, a (N,N'-dimethyl)aminophenyl group, a (N,N'-diphenyl)aminophenyl group, a pentalenyl group, an indenyl group, a naphthyl group, a halonaphthyl group (e.g., a fluoronaphthyl group), a C_1 - C_{10} alkyl naphthyl group (e.g., a methyl naphthyl group), a C_1 - C_{10} alkoxynaphthyl group (e.g., a methoxynaphthyl group), an anthracenyl group, an azulenyl group, a heptalenyl group, an acenaphthylenyl group, a phenalenyl group, a fluorenyl group, an anthraquinolyl group, a methylanthryl group, a phenanthryl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, an ethyl-chrysenyl group, a picenyl group, a perylenyl group, a chloroperlylenyl group, a pentaphenyl group, a pentacenyl group, a tetraphenylenyl group, a hexaphenyl group, a hexacenyl group, a rubicenyl group, a coroneryl group, a trinaphthylenyl group, a heptaphenyl group, a heptacenyl, a pyranthrenyl group, and an ovalenyl group.

[0091] Examples of the substituted C_6 - C_{60} aryl group may be easily understood with reference to the examples of the unsubstituted C_6 - C_{60} aryl group described above and the substituents of the substituted C_1 - C_{60} alkyl group described above.

[0092] Examples of the substituted or unsubstituted C_6 - C_{60} arylene group may be easily understood with reference to the substituted or unsubstituted C_6 - C_{60} aryl group described above.

[0093] The unsubstituted C_2 - C_{60} heteroaryl group indicates a monovalent group having at least one aromatic ring system including carbon rings and at least one hetero atom selected from the group consisting of N, O, P, and S, and the unsubstituted C_2 - C_{60} heteroarylene group indicates a divalent group having at least one aromatic ring system including carbon rings and at least one hetero atom selected from the group consisting of N, O, P, and S. In this regard, if the C_2 - C_{60} heteroaryl group and the C_2 - C_{60} heteroarylene group each independently have two or more aromatic rings, the rings may be fused with each other. At least one hydrogen atom of each of the unsubstituted C_2 - C_{60} heteroaryl group and the unsubstituted C_2 - C_{60} heteroarylene group may be substituted with the substituents described with reference to the substituted C_1 - C_{60} alkyl group described above.

[0094] Examples of the unsubstituted C_2 - C_{60} heteroaryl group include, but are not limited to, a pyrazolyl group, an

imidazolyl group, an oxazolyl group, a thiazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a pyridinyl group, a pyridazinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, an indolyl group, a quinolyl group, an isoquinolyl group, a benzoimidazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group. Examples of the substituted or unsubstituted C_2 - C_{60} heteroarylene group may be easily understood with reference to the examples of the substituted or unsubstituted C_2 - C_{60} heteroarylene group described above.


[0095] The substituted or unsubstituted C_6 - C_{60} aryloxy group has a formula of $-OA_2$ wherein A_2 is the substituted or unsubstituted C_6 - C_{60} aryl group as described above, and the substituted or unsubstituted C_6 - C_{60} arylthio group has a formula of $-SA_3$ wherein A_3 is the substituted or unsubstituted C_6 - C_{60} aryl group described above.

[0096] The condensed-cyclic compound of Formula 1 may be synthesized using a well-known organic synthesis method. The synthesis method of the condensed-cyclic compound of Formula 1 may be easily understood by one of ordinary skill in the art with reference to Examples, which will be described later.

[0097] The condensed-cyclic compound of Formula 1 may have excellent thermal resistance and luminous properties. In particular, A-site carbon and B-site carbon of Formula 1 are linked respectively to $-N(R_1)(R_2)$ and $-N(R_3)(R_4)$, optionally, via Ar_5 and Ar_6 , respectively.

[0098] In general, when conjugation lengths of backbone in condensed rings become longer, the band gap becomes smaller and thus the emission wavelength moves to longer wavelengths. On the other hand, the condensed-cyclic compound of Formula 1 has a structure in which the C-site carbon is broken conjugation of condensed rings between the A-site carbon and the B-site carbon as shown in Formula 1 below. Each of the C-site carbon, A-site carbon and B-site carbon is linked to an amine group and thus may form a wider band gap as compared to the conjugated structure. Thus, the condensed-cyclic compound of Formula 1 may be usefully used as a blue light-emitting material due to the wide band gap effected by an appropriate conjugation state.

Formula 1



[0099] When an organic light-emitting diode (OLED) including the condensed-cyclic compound of Formula 1 between a pair of electrodes (anode and cathode) is operated, the OLED may exhibit excellent driving voltage, efficiency, brightness and life-time characteristics since the condensed-cyclic compound of Formula 1 has high heat resistance to Joule's heat generated between organic layers positioned between the pair of electrodes or between one of the organic layers and one of the electrodes.

[0100] The condensed-cyclic compound of Formula 1 may be used between a pair of electrodes of an OLED. For example, the condensed-cyclic compound of Formula 1 may be used as a light-emitting material, but is not limited thereto.

[0101] According to another embodiment of the present invention, there is provided an OLED including a first electrode, a second electrode facing the first electrode, and an organic layer interposed between the first electrode and the second electrode, wherein the organic layer includes at least one of the condensed-cyclic compound of Formula 1 described above.

[0102] The organic layer may include at least one of the condensed-cyclic compound of Formula 1. For example, an OLED manufactured according to Example 1, which will be described later, includes only Compound 1 (acting as a blue dopant) as the condensed-cyclic compound of Formula 1. Alternatively, an emission layer of the OLED may include Compounds 1 and 3 (acting as a blue dopant) as the condensed-cyclic compound of Formula 1. That is, various modifications are possible in this embodiment. As used herein, the expression "the organic layer may include at least one of the condensed-cyclic compound of Formula 1" may be easily understood by one of ordinary skill in the art with reference to the above description.

[0103] The organic layer may include at least one of a hole injection layer (HIL), a hole transport layer (HTL), a functional layer having hole injection and hole transport abilities, an electron blocking layer (EBL), an emission layer (EML), a hole blocking layer (HBL), an electron transport layer (ETL), an electron injection layer (EIL), and a functional layer having electron transport and electron injection abilities.

[0104] For example, the organic layer may have, but is not limited to, a HIL/HTL/EML/ETL/EIL structure or a functional layer having hole injection and hole transport abilities/EML/ETL/EIL structure.

[0105] The term "organic layer" used herein refers to a single layer or multiple layers interposed between the first electrode and the second electrode and may include a metal complex in addition to an organic material.

[0106] For example, the organic layer may include an EML including the condensed-cyclic compound of Formula 1. In other words, the condensed-cyclic compound of Formula 1 may be used as a light-emitting material. In this regard, the EML may further include a host and the condensed-cyclic compound of Formula 1 included in the EML may serve as a dopant.

[0107] The EML may be a red, green or blue EML. For example, the EML may be a blue EML. In this regard, the condensed-cyclic compound of Formula 1 is used as a blue dopant, whereby an OLED including the condensed-cyclic compound of Formula 1 may have high efficiency, brightness and color purity and long lifetime.

[0108] FIG. 1 is a schematic cross-sectional view of an OLED according to an embodiment of the present invention. Hereinafter, a structure and manufacturing method of an

OLED will be described in more detail with reference to FIG. 1. The OLED includes a substrate 10, a first electrode 20, a HIL 30, a HTL 40, an EML 50, an ETL 60, an EIL 70, and a second electrode 80 that are sequentially formed.

[0109] First, the substrate 10 may be a substrate used in a general OLED, and may be a glass substrate or a transparent plastic substrate having excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and waterproofness.

[0110] The first electrode 20 may be formed by applying a first electrode material on the substrate 10 by deposition or sputtering. When the first electrode 20 is an anode, the first electrode material may be selected from materials having a high work function so as to facilitate hole injection. The first electrode 20 may be a reflective electrode or a transparent electrode. Examples of the first electrode material may include indium-tin oxide (ITO), indium-zinc-oxide (IZO), tin oxide (SnO_2), and zinc oxide (ZnO). Also, when magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) is used as the first electrode material, the first electrode 20 may be formed as a reflective electrode.

[0111] The first electrode 20 may be formed as a single layer or have a multi-layered structure having at least two layers.



[0112] An organic layer including the HIL 30, HTL 40, the EML 50, the ETL 60, and the EIL 70 is formed on the first electrode 20 sequentially.


[0113] The HIL 30 may be formed on the first electrode 20 by using various methods such as vacuum deposition, spin coating, casting, or LB deposition.

[0114] When the HIL 30 is formed by vacuum deposition, the deposition conditions may vary according to a compound used as a material for forming the HIL 30, a structure of a desired HIL, and thermal characteristics. For example, the deposition conditions may be, but are not limited to, a deposition temperature of about 100°C . to about 500°C ., a degree of vacuum of about 10^{-8} torr to about 10^{-3} torr, and a deposition speed of about $0.01\text{ \AA/sec}$ to about $100\text{ \AA/sec}$.

[0115] When the HIL 30 is formed by spin coating, the coating conditions may vary according to a compound used as a material for forming the HIL 30, a structure of a desired HIL, and thermal characteristics. For example, the coating conditions may be, but are not limited to, a coating speed of about 2,000 rpm to about 5,000 rpm and a heat treatment temperature for removing a solvent after coating of about 80°C . to about 200°C .

[0116] The material for forming the HIL 30 may be a known hole injection material. Examples of the known hole injection material include, but are not limited to, N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine (DNTPD), a phthalocyanine compound such as copper phthalocyanine, 4,4',4''-tris(3-methylphenyl)phenylamino)triphenylamine (m-MTDATA), 4,4' 4''-tris(N,N-diphenylamino)triphenylamine (TDATA), 4,4',4''-tris[N, -(2-naphthyl)-N-phenylamino]-triphenylamine (2T-NATA), polyaniline/dodecylbenzenesulfonic acid (PANI/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (PANI/CSA), and polyaniline/poly(4-styrenesulfonate) (PANI/PSS).






[0117] The thickness of the HIL 30 may be in the range of about 100 Å to about 10,000 Å. In some embodiments, the thickness of the HIL 30 may be in the range of about 100 Å to about 1,000 Å. When the thickness of the HIL 30 is within these range, satisfactory hole injection properties may be obtained without a substantial increase in driving voltage.

[0118] Next, the HTL 40 may be formed on the HIL 30 by using various methods such as vacuum deposition, spin coating, casting, or LB deposition. When the HTL 40 is formed by vacuum deposition or spin coating, the deposition and coating conditions may vary according to used compounds. However, in general, the deposition and coating conditions may be almost the same as the conditions for forming the HIL 30.

[0119] A material for forming the HTL 40 may be a known hole transporting material. Examples of the known hole transporting material include, but are not limited to, carbazole derivatives such as N-phenylcarbazole and polyvinylcarbazole, N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (TPD), 4,4',4''-tris(N-carbazolyl)triphenylamine (TCTA), and N,N'-di-1-naphthyl-N,N'-diphenyl-1,1'-biphenyl-4,4'-diamine (NPD).




[0120] The thickness of the HTL 40 may be in the range of about 50 Å to about 2,000 Å. In some embodiments, the thickness of the HTL 40 may be in the range of about 100 Å to about 1,500 Å. When the thickness of the HTL 40 is within these ranges, satisfactory hole transport properties may be obtained without a substantial increase in driving voltage.

[0121] In addition, the functional layer having hole injection and hole transport abilities may be formed instead of the HIL and the HTL. A material for forming the functional layer having hole injection and hole transport abilities may be selected from known materials.

[0122] At least one of the HIL, the HTL, and the functional layer having hole injection and hole transport abilities may further include a charge-generating material so as to increase the conductivity of the layers, in addition to the known hole injection material, the known hole transport material and/or the material for forming the functional layer having hole injection and hole transport abilities.

[0123] The charge-generating material may be, for example, a p-dopant. Examples of the p-dopant may include, but are not limited to, quinone derivatives such as tetracyanoquinodimethane (TCNQ) and 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinodimethane (F4TCNQ); metal oxides such as tungsten oxide and a molybdenum oxide; and cyano-containing compounds such as Compound 200 below and the like.




[0124] When the HIL, the HTL or the functional layer having hole injection and hole transport abilities further include the charge-generating material, the charge-generating material may be homogeneously or inhomogeneously dispersed in these layers.


[0125] The EML 50 may be formed on the HTL 40 (or the functional layer having hole injection and hole transport abilities, optionally) by vacuum deposition, spin coating, casting, or LB deposition. When the EML 50 is formed by vacuum deposition or spin coating, the deposition and coating conditions may vary according to used compounds. However, in general, the conditions may be almost the same as the conditions for forming the HIL 30.

[0126] A material for forming the EML 50 may be at least one of the condensed-cyclic compound of Formula 1 and a known light-emitting material (host and/or dopant). For example, the EML 50 may include a known host and the condensed-cyclic compound of Formula 1 as a dopant. In this regard, the condensed-cyclic compound of Formula 1 may act as a blue dopant.

[0127] Examples of the known host may include, but are not limited to, Tris(8-hydroxyquinolino)aluminum (Alq3), 4,4'-N,N'-dicarbazole-biphenyl (CBP), poly(n-vinylcarbazole) (PVK), 9,10-di(naphthalene-2-yl)anthracene (ADN), TCTA, 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di(naphth-2-yl)anthracene (TBADN), E3, and distyrylarylene (DSA).



[0128] Alternatively, the host may be an anthracene-based compound represented by Formula 60 below:



Formula 60

[0129] In Formula 60, Ar₁₁ and Ar₁₂ may be each independently a substituted or unsubstituted C₆-C₆₀ arylene group; Ar₁₃ and Ar₁₄ may be each independently a substituted or

unsubstituted C₁-C₁₀ alkyl group or a substituted or unsubstituted C₆-C₆₀ aryl group; and e and f may be each independently an integer of 0 to 5.

[0130] For example, in Formula 60, Ar₁₁ and Ar₁₂ may be each independently a phenylene group; or a phenylene group that is substituted with at least one of a phenyl group, a naphthyl group, and an anthryl group, but are not limited thereto.


[0131] In Formula 60, e and f may be each independently 0, 1, or 2.

[0132] In Formula 60, Ar₁₃ and Ar₁₄ may be each independently a C₁-C₁₀ alkyl group that is substituted with at least one of a phenyl group, a naphthyl group, and an anthryl group; a phenyl group; a naphthyl group; an anthryl group; a pyrenyl group; a phenanthrenyl group; and a phenyl group, a naphthyl group, an anthryl group, a pyrenyl group, and a phenanthrenyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group,


an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, but are not limited thereto.

[0133] For example, in Formula 60, Ar_{11} and Ar_{12} may be each independently a phenylene group; or a phenylene group that is substituted with at least one of a phenyl group, a naphthyl group, and an anthryl group; e and f may be each independently 0, 1, or 2; and Ar_{13} and Ar_{14} may be each independently one selected from a C_1 - C_{10} alkyl group that is substituted with at least one of a phenyl group, a naphthyl group, and an anthryl group; a phenyl group; a naphthyl group; an anthryl group; a pyrenyl group; and a phenanthrenyl group, but are not limited thereto.


[0134] For example, the anthracene-based compound of Formula 60 may be one of Compounds BH01 through BH39 below, but is not limited thereto:




BH01




BH02



BH03




BH04




BH05

-continued




BH06

-continued




BH09


BH07




BH10




BH08



BH11




-continued




BH12

-continued




BH15


BH13



BH14




BH16




BH17

-continued




BH18

-continued




BH20


BH19



BH21




-continued




BH22

-continued




BH25


BH23




BH24




BH26



BH27




-continued




BH28

-continued




BH30


BH29



BH31




-continued




BH32

-continued




BH35

B H33





BH36




BH37


BH34



-continued




BH38





BH39

[0135] Meanwhile, to manufacture a full-color OLED, a red EML and a green EML may be further patterned.




[0136] In this regard, examples of known red dopants include, but are not limited to, PtOEP, Ir(piq)₃, and Btp₂Ir(acac).





-continued



[0137] Examples of known green dopants include, but are not limited to, Ir(ppy)₃ (ppy=phenylpyridine), Ir(ppy)₂(acac), Ir(mppy)₃, and C545T.






Compound 201



[0138] The amount of the dopants in the EML 50 may be generally in the range of about 0.01 to about 15 parts by weight based on 100 parts by weight of the host, but is not limited thereto.

[0139] The thickness of the EML 50 may be in the range of about 100 Å to about 1,000 Å. In some embodiments, the thickness of the HIL 30 may be in the range of about 200 Å to about 600 Å. When the thickness of the EML 50 is within these ranges, excellent luminescent properties may be obtained without a substantial increase in driving voltage. Next, the ETL 60 is formed on the EML 50 by using various methods such as vacuum deposition, spin coating, or casting. When the ETL 60 is formed by vacuum deposition or spin coating, the deposition and coating conditions may vary according to used compounds. However, in general, the deposition and coating conditions may be almost the same as the conditions for forming the HIL 30.

[0140] A material for forming the ETL 60 may be a known electron transporting material to stably transport electrons injected from a cathode. Examples of the known electron transporting materials may include, but are not limited to, a quinoline derivative such as tris(8-quinolinolate)aluminum (Alq_3), TAZ, Balq, beryllium bis(benzoquinolin-10-olate) (Bebq_2), AND, Compound 201 below, and Compound 202 below.



Compound 202




TAZ

[0141] The thickness of the ETL 60 may be in the range of about 100 Å to about 1,000 Å. In some embodiment, the thickness of the ETL may be in the range of about 150 Å to about 500 Å. When the thickness of the ETL 60 is within these ranges, satisfactory electron transport properties may be obtained without a substantial increase in driving voltage.

[0142] In addition, the ETL 60 may include a known electron transporting organic compound and a metal-containing material.

[0143] The metal-containing material may include a Li-complex. Examples of the Li-complex may include lithium quinolate (LiQ) and Compound 203 below:



Compound 203

[0144] Also, the EIL 70, which facilitates electron injection from a cathode, may be formed on the ETL 60, and a material for forming the EIL 70 is not particularly limited.

[0145] The material for forming the EIL 70 may include a well-known material for forming an EIL, such as LiF, NaCl, CsF, Li₂O, or BaO. The deposition conditions of the EIL may vary according to a used compound. However, in general, the conditions may be almost the same as the conditions for forming the HIL 30.

[0146] The thickness of the EIL 70 may be in the range of about 1 Å to about 100 Å. In some embodiment, the thickness of the ETL may be in the range of about 3 Å to about 90 Å. When the thickness of the EIL 70 is within these ranges, satisfactory electron injection properties may be obtained without a substantial increase in driving voltage.

[0147] The second electrode 80 is formed on the EIL 70. The second electrode 80 may be a cathode, which is an electron injection electrode. Here, a metal for forming the second electrode 80 may include a metal having low work function, such as metal, an alloy, an electric conducting compound, or a mixture thereof. In particular, the second electrode 80 may be formed as a thin film by using lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag), thus being transparent. In order to obtain a top-emission type OLED, the second electrode 80 may be formed as a transparent electrode by using ITO or IZO.

[0148] The OLED may be used in a display device and a monochrome or white light illumination device. The display device and the illumination device may further include at least one thin film transistor (TFT), and a first electrode of the OLED may contact one of a source electrode and a drain electrode that are included in the TFT.

[0149] An OLED according to an embodiment of the present invention will now be described in more detail with reference to the following Examples. These Examples are for illustrative purposes only and are not intended to limit the scope of the invention.

EXAMPLES


Synthesis Example 1

Synthesis of Compound 1

Synthesis Example 1-(1)

Synthesis of Intermediate 1-a

[0150] Intermediate 1-a was synthesized according to Reaction Scheme 1 below:





[0151] 50 g (194 mmol) of 9-bromo phenanthrene was added to a round-bottom flask containing 500 ml of tetrahydrofuran, and a temperature of the round-bottom flask was then adjusted to be -78°C . in a nitrogen atmosphere. After 30 minutes, 146 ml (233 mmol) of normal butyl lithium was slowly dropped to the mixture, 28.3 g (274 mmol) of trimethylborate was slowly dropped thereto after 1 hour, and the temperature was raised to room temperature. The resultant mixture was stirred for about 12 hours at room temperature and 2N (normal) aqueous hydrochloric acid solution was dropped to the reaction solution until the solution becomes an acid solution, and the resultant solution was then extracted. The organic layer was separated and evaporated under reduced pressure. The residue was recrystallized with normal hexane and the resulting product was filtered and dried. As a result, 35 g of white solid Intermediate 1-a (yield: 81%) was obtained.

Synthesis Example 1-(2)

Synthesis of Intermediate 1-b

[0152] Intermediate 1-b was synthesized according to Reaction Scheme 2 below:






[0153] To a round-bottom flask was added 24 g (112 mmol) of methyl 2-bromobenzoate, 34.7 g (0.156 mmol) of Intermediate 1-a, 2.6 g (2 mmol) of tetrakis(triphenylphosphine) palladium $\{Pd(PPh_3)_4\}$, 30.9 g (223 mmol) of potassium carbonate, 50 ml of water, 125 ml of toluene, and 125 ml of tetrahydrofuran and the resultant mixture was then refluxed for 12 hours. After the reaction was terminated, the reactant was subjected to a layer separation process to obtain an organic layer. The obtained organic layer was concentrated under reduced pressure, purified by column and then dried. As a result, 25 g of white solid Intermediate 1-b (yield: 72%) was obtained.

Synthesis Example 1-(3)

Synthesis of Intermediate 1-c

[0154] Intermediate 1-c was synthesized according to Reaction Scheme 3 below:

[Reaction Scheme 3](#)



[0155] 25 g (80 mmol) of Intermediate 1-b was added to a round-bottom flask containing 250 ml of tetrahydrofuran, and a temperature of the round-bottom flask was then reduced to -78°C . in a nitrogen atmosphere. After 30 minutes, 150 ml (240 mmol) of 1.6M phenyl lithium was slowly dropped to the mixture and the temperature was raised to room temperature after 1 hour. The resultant mixture was stirred at room temperature for about 2 hours and an aqueous ammonium chloride solution was added thereto. Thereafter, the resulting solution was extracted to obtain an organic layer and the obtained organic layer was then evaporated under reduced


pressure. The residue was recrystallized with normal hexane and the resulting product was filtered and dried. As a result, 29 g of white solid Intermediate 1-c (yield: 83%) was obtained.

Synthesis Example 1-(4)

Synthesis of Intermediate 1-d

[0156] Intermediate 1-d was synthesized according to Reaction Scheme 4 below:

[Reaction Scheme 4](#)




[0157] 29 g (66 mmol) of Intermediate 1-c was added to a round-bottom flask containing 290 ml of acetic acid. Subsequently, a temperature of the round-bottom flask was raised to 80°C . and 1 to 2 droplets of an aqueous hydrochloric acid solution was added thereto, and the resultant solution was refluxed for about 2 hours and the temperature was adjusted to room temperature. The solid produced therefrom was filtered and dried. As a result, 27 g of white solid Intermediate 1-d (yield: 93%) was obtained.


Synthesis Example 1-(5)

Synthesis of Intermediate 1-e

[0158] Intermediate 1-e was synthesized according to Reaction Scheme 5 below:

[Reaction Scheme 5](#)






[0159] 27 g (65 mmol) of Intermediate 1-d was added to a round-bottom flask containing 216 ml of chloroform and the mixture was stirred. Subsequently, 28.9 g (181 mmol) of bromine was diluted with 54 ml of chloroform, the diluted mixture was slowly dropped to the stirred mixture, and the resultant mixture was stirred at room temperature for 48 hours. Thereafter, solid produced therefrom was filtered and dried. As a result, 27 g of white solid Intermediate 1-e (yield: 93%) was obtained.

Synthesis Example 1-(6)

Synthesis of Compound 1

[0160] Compound 1 was synthesized according to Reaction Scheme 7 below:



[0161] To a round-bottom flask were added 10 g (17 mmol) of Intermediate 1-e, 7.6 g (45 mmol) of diphenyl amine, 0.2 g (0.7 mmol) of palladium acetate $\{Pd(OAc)_2\}$, 6.7 g (69 mmol) of sodium tertiary butoxide, 0.14 g (0.7 mmol) of tri-tertiary butylphosphine, and 100 ml of toluene and the mixture was maintained at a reaction temperature of 100° C. for 2 hours to induce a reaction therebetween. After the reaction was terminated, the reaction solution was filtered, the filtrate was concentrated, and the resulting filtrate was purified by column chromatography. Thereafter, the resulting product was recrystallized with toluene and methanol and solid produced therefrom was filtered and dried. As a result, 5.7 g of Compound 1 was obtained as a pale yellow solid (yield: 40%).

[0162] The produced compound was identified using NMR.

[0163] MS: m/z 752 $[M]^+$

[0164] 1H NMR ($CDCl_3$) δ 8.89 (d, 1H), 8.47 (d, 1H), 8.40 (s, 1H), 8.24 (d, 1H), 7.73 (t, 1H), 7.63 (m, 2H), 7.27 (m, 23H), 7.01 (m, 10H)


Synthesis Example 2

Synthesis of Compound 3

Synthesis Example 2-(1)

Synthesis of Intermediate 2-a

[0165] Intermediate 2-a was synthesized according to Reaction Scheme 8 below:



[0166] To a round-bottom flask were added 16.3 g (96 mmol) of 4-amino biphenyl, 15.8 g (101 mmol) of bromobenzene, 0.32 g (1.4 mmol) of palladium acetate, 0.9 g (1.4 mmol) of 2,2-bis(diphenylphosphino)-1,1'-binaphthyl, 18.5 g (193 mmol) of sodium tertiary butoxide, and 160 ml of toluene and the mixture was refluxed for 24 hours. After the temperature was adjusted to be room temperature, the mixture was filtered, the filtrate was concentrated, and the resulting filtrate was purified by column chromatography. Thereafter, the resulting product was recrystallized with dichloromethane and methanol and solid produced therefrom was filtered and dried. As a result, 15 g of white solid Intermediate 2-a was obtained (yield: 60%).

Synthesis Example 2-(2)

Synthesis of Compound 3

[0167] 3.7 g of Compound 3 was obtained as a pale yellow solid (yield: 31%) in the same manner as in Synthesis Example 1-(6), except that Intermediate 2-a was used instead of diphenyl amine.

[0168] The produced compound was identified using NMR.

[0169] MS: m/z 904 [M]⁺

[0170] ¹H NMR (CDCl₃) δ 8.90 (d, 1H), 8.51 (m, 2H), 8.27 (d, 1H), 7.75 (t, 2H), 7.61 (m, 6H), 7.48 (m, 9H), 7.36 (m, 9H), 7.23 (m, 11H), 7.12 (m, 7H)

Synthesis Example 3

Synthesis of Compound 9

[0171] 4.7 g of Compound 9 was obtained as a pale yellow solid (yield: 39%) in the same manner as in Synthesis Example 2, except that, in Synthesis Example 2-(1), 4-tertiary-butylaniline was used instead of 4-amino biphenyl and 1-bromo-4-tertiary-butylbenzene was used instead of bromobenzene.

[0172] The produced compound was identified using NMR.

[0173] MS: m/z 977 [M]⁺

[0174] ¹H NMR (CDCl₃) δ 8.89 (s, 1H), 8.49 (d, 1H), 8.23 (s, 1H), 7.68 (m, 3H), 7.31 (m, 21H), 7.05 (m, 9H), 1.38 (s, 18H), 1.37 (s, 18H)

Synthesis Example 4

Synthesis of Compound 10

[0175] 2.7 g of Compound 10 was obtained as a pale yellow solid (yield: 24%) in the same manner as in Synthesis Example 2, except that, in Synthesis Example 2-(1), 4-tertiary-butylaniline was used instead of 4-amino biphenyl and bromobenzene-d₅ was used instead of bromobenzene.

[0176] The produced compound was identified using NMR.

[0177] MS: m/z 875 [M]⁺

[0178] ¹H NMR (CDCl₃) δ 8.91 (d, 1H), 8.45 (m, 2H), 8.26 (d, 1H), 7.67 (m, 3H), 7.30 (m, 15H), 7.07 (m, 6H)

Synthesis Example 5

Synthesis of Compound 11

[0179] 6.4 g of Compound 11 was obtained as a pale yellow solid (yield: 67%) in the same manner as in Synthesis Example 2, except that, in Synthesis Example 2-(1), 4-tertiary-butylaniline was used instead of 4-amino biphenyl and 1-bromo-4-(trimethylsilyl)benzene was used instead of bromobenzene.

[0180] The produced compound was identified using NMR.

[0181] MS: m/z 1009 [M]⁺

[0182] ¹H NMR (CDCl₃) δ 8.88 (d, 1H), 8.51 (d, 1H), 8.43 (s, 1H), 8.24 (d, 1H), 7.73 (t, 1H), 7.64 (m, 2H), 7.21 (m, 29H), 1.36 (s, 9H), 1.35 (s, 9H), 0.30 (s, 9H), 0.29 (s, 9H)

Synthesis Example 6

Synthesis of Compound 12

[0183] 5.1 g of Compound 12 was obtained as a pale yellow solid (yield: 49%) in the same manner as in Synthesis Example 2, except that 1-bromo-4-tertiary-butylbenzene was used instead of bromobenzene in Synthesis Example 2-(1).

[0184] The produced compound was identified using NMR.

[0185] MS: m/z 1017 [M]⁺

[0186] ¹H NMR (CDCl₃) δ 8.93 (s, 1H), 8.50 (m, 2H), 8.29 (d, 1H), 7.40 (m, 42H), 1.41 (s, 9H), 1.40 (s, 9H)

Synthesis Example 7

Synthesis of Compound 28

[0187] 3.3 g of Compound 28 was obtained as a pale yellow solid (yield: 38%) in the same manner as in Synthesis Example 1, except that methyl magnesium bromide was used instead of phenyl lithium in Synthesis Example 1-(3).

[0188] The produced compound was identified using NMR.

[0189] MS: m/z 628 [M]⁺

[0190] ¹H NMR (CDCl₃) δ 8.84 (s, 1H), 8.53 (m, 2H), 8.26 (s, 2H), 7.42 (m, 25H), 1.75 (s, 6H)

Synthesis Example 8

Synthesis of Compound 29

[0191] 3.3 g of Compound 29 was obtained as a pale yellow solid (yield: 38%) in the same manner as in Synthesis Example 1, except that methyl magnesium bromide was used instead of phenyl lithium in Synthesis Example 1-(3) and Intermediate 2-a was used instead of diphenyl amine in Synthesis Example 1-(6).

[0192] The produced compound was identified using NMR.

[0193] MS: m/z 780 [M]⁺

[0194] ¹H NMR (CDCl₃) δ 8.85 (s, 1H), 8.55 (m, 2H), 8.28 (s, 2H), 7.47 (m, 33H), 1.76 (s, 6H)


Synthesis Example 9

Synthesis of Compound 14


Synthesis Example 9-(1)

Synthesis of Intermediate 9-a

[0195] Intermediate 9-a was synthesized according to Reaction Scheme 9 below:



-continued




[0196] To a 1 L round-bottom flask were added 30 g (111.56 mmol) of 2,4-dibromo-6-fluoroaniline, 31.2 g (245.44 mmol) of phenylboronic acid-d₅, 61.9 g (446.27 mmol) of potassium carbonate, 2.6 g (2.20 mmol) of tetrakis(triphenylphosphine)palladium, 120 ml of water, 300 ml of toluene, and 300 ml of tetrahydrofuran and the mixture was maintained at a reaction temperature of 80° C. for 24 hours to induce a reaction therebetween. After the reaction was terminated, the reaction product was subjected to a layer separation process to remove a water layer and separate an organic layer therefrom, and the obtained organic layer was concentrated under reduced pressure. The resulting product was purified by column chromatography by using hexane and dichloromethane and solid produced therefrom was dried. As a result, 24.2 g of white solid Intermediate 9-a was obtained (yield: 79.4%).

Synthesis Example 9-(2)


Synthesis of Intermediate 9-b

[0197] Intermediate 9-b was synthesized according to Reaction Scheme 10 below:

Reaction Scheme 10



-continued



[0198] To a round-bottom flask were added 15 g (55 mmol) of Intermediate 9-a, 8.9 g (55 mmol) of bromobenzene-d₅, 0.25 g (1.1 mmol) of palladium acetate, 0.68 g (1.1 mmol) of 2,2-bis(diphenylphosphino)-1,1'-binaphthyl, 10.6 g (110 mmol) of sodium tertiary butoxide, and 150 ml of toluene and the mixture was refluxed for 24 hours. The resultant mixture was filtered, the filtrate was concentrated, and the resulting filtrate was purified by column chromatography. Thereafter, the resulting product was recrystallized with dichloromethane and methanol and solid produced therefrom was filtered and dried. As a result, 14 g of white solid Intermediate 9-b was obtained (yield: 72%).

Synthesis Example 9-(3)

Synthesis of Compound 14

[0199] 3.1 g of Compound 14 was obtained as a pale yellow solid (yield: 24%) in the same manner as in Synthesis Example 1, except that Intermediate 9-b was used instead of diphenyl amine in Synthesis Example 1-(6).

[0200] The produced compound was identified using NMR.

[0201] MS: m/z 1123 [M]⁺

[0202] ¹H NMR (CDCl₃) δ 8.81 (s, 1H), 8.35 (d, 1H), 8.05 (s, 2H), 7.71 (t, 2H), 7.34 (m, 16H), 6.84 (d, 2H)

Synthesis Example 10

Synthesis of Compound 17

[0203] 4.3 g of Compound 17 was obtained as a pale yellow solid (yield: 42%) in the same manner as in Synthesis Example 2, except that 4-cyanoaniline was used instead of 4-amino biphenyl in Synthesis Example 2-(1).

[0204] The produced compound was identified using NMR.

[0205] MS: m/z 803 [M]⁺

[0206] ¹H NMR (CDCl₃) δ 8.90 (d, 1H), 8.51 (m, 2H), 8.33 (d, 1H), 7.74 (m, 3H), 7.25 (m, 29H), 6.93 (d, 2H)


Synthesis Example 11

Synthesis of Compound 22

Synthesis Example 11-(1)

Synthesis of Intermediate 11-a

[0207] Intermediate 11-a was synthesized according to Reaction Scheme 11 below:




[0208] To a reactor were added 50 g (197 mmol) of 1,3-dibromo-5-fluorobenzene, 28.8 g (167 mmol) of 1-naphthyl boronic acid, 4.6 g (3.9 mmol) of tetrakis(triphenylphosphine)palladium, 54.4 g (394 mmol) of potassium carbonate, 450 ml of toluene, and 150 ml of water and the mixture was refluxed. After the reaction was terminated, the resultant mixture was extracted to separate an organic layer. Thereafter, the organic layer was evaporated under reduced pressure and purified by column chromatography. As a result, 25 g of Intermediate 11-a was obtained in a transparent liquid state (yield: 42%).


Synthesis Example 11-(2)

Synthesis of Intermediate 11-b

[0209] Intermediate 11-b was synthesized according to Reaction Scheme 12 below:



-continued



[0210] Intermediate 11-b was synthesized in the same manner as in Synthesis Example 2-(1), except that 4-tert-butylaniline was used instead of 4-amino biphenyl and Intermediate 11-a was used instead of bromobenzene.

Synthesis Example 11-(3)

Synthesis of Compound 22

[0211] 1.6 g of Compound 22 was obtained as a pale yellow solid (yield: 21%) in the same manner as in Synthesis Example 1, except that Intermediate 11-b was used instead of diphenyl amine in Synthesis Example 1-(6).

[0212] The produced compound was identified using NMR.

[0213] MS: m/z 1153 $[M]^+$

[0214] $^1\text{H NMR}$ (CDCl_3) δ 8.88 (d, 1H), 8.56 (m, 2H), 8.28 (d, 1H), 7.88 (m, 6H), 7.71 (m, 3H), 7.30 (m, 30H), 6.86 (m, 5H), 1.35 (s, 9H), 1.34 (s, 9H)

Synthesis Example 12

Synthesis of Compound 26

[0215] 2.7 g of Compound 26 was obtained as a pale yellow solid (yield: 36%) in the same manner as in Synthesis Example 1, except that 9,9-dimethyl-N-phenyl-9H-fluorene-2-amine was used instead of diphenyl amine in Synthesis Example 1-(6).

[0216] The produced compound was identified using NMR.

[0217] MS: m/z 985 $[M]^+$

[0218] $^1\text{H NMR}$ (CDCl_3) δ 8.89 (s, 1H), 8.37 (m, 3H), 7.64 (m, 7H), 7.24 (m, 33H), 1.42 (s, 6H), 1.36 (s, 6H)

Synthesis Example 13

Synthesis of Compound 54

[0219] 3.3 g of Compound 54 was obtained as a pale yellow solid (yield: 37%) in the same manner as in Synthesis Example 2, except that 2-bromo-9,9-dimethyl-9H-fluorene was used instead of bromobenzene in Synthesis Example 2-(1).

[0220] The produced compound was identified using NMR.

[0221] MS: m/z 1013 $[M]^+$

[0222] $^1\text{H NMR}$ (CDCl_3) δ 8.86 (s, 1H), 8.50 (d, 1H), 8.30 (s, 2H), 7.53 (m, 39H), 1.76 (s, 6H), 1.49 (s, 12H)


Synthesis Example 14

Synthesis of Compound 64

Synthesis Example 14-(1)

Synthesis of Intermediate 14-a

[0223] Intermediate 14-a was synthesized according to Reaction Scheme 13 below:




[0224] To a reactor were added 500 ml of acetic acid and 120 g (1.39 mol) of 3-methyl-2-butanone and the temperature was raised to 60° C. Subsequently, 150 g (1.39 mol) of phenylhydrazine was slowly added to the mixture and the resultant mixture was refluxed. After the reaction was terminated, 500 ml of water was added to the mixture and the mixture was neutralized with sodium hydroxide. The resultant mixture was extracted several times with ethyl acetate and the obtained organic layer was evaporated under reduced pressure and the residue was purified by column chromatography. As a result, 156 g of Intermediate 14-a was obtained (yield: 71%).

Synthesis Example 14-(2)

Synthesis of Intermediate 14-b

[0225] Intermediate 14-b was synthesized according to Reaction Scheme 14 below:



[0226] 100 g (0.628 mol) of Intermediate 14-a and 500 ml of acetic acid were added to a reactor. Subsequently, 118 g (1.88 mol) of sodium cyanoborohydride was slowly added to the mixture so as not to incur severe heat generation. The resultant mixture was stirred for 5 hours, 300 ml of water was added thereto, and the mixed solution was made basic with sodium hydroxide. Thereafter, ethyl acetate was added to the resultant solution, the solution was extracted several times to separate an organic layer, and the obtained organic layer was concentrated. The resulting product was then purified by column chromatography. As a result, 55 g of Intermediate 14-b was obtained (yield: 54%).

Synthesis Example 14-(3)

Synthesis of Compound 64

[0227] 1.8 g of Compound 64 was obtained as a pale yellow solid (yield: 34%) in the same manner as in Synthesis Example 1, except that Intermediate 14-b was used instead of diphenyl amine in Synthesis Example 1-(6).

[0228] The produced compound was identified using NMR.

[0229] MS: m/z 737 $[M]^+$

[0230] ^1H NMR (CDCl_3) δ 8.90 (s, 1H), 8.76 (d, 1H), 8.57 (s, 1H), 8.43 (d, 1H), 7.78 (m, 3H), 7.16 (m, 21H), 4.01 (s, 1H), 3.83 (s, 1H), 1.37 (s, 3H), 1.35 (s, 3H), 1.26 (m, 6H), 1.14 (m, 6H)


Synthesis Example 15

Synthesis of Compound 68

Synthesis Example 15-(1)

Synthesis of Intermediate 15-a

[0231] Intermediate 15-a was synthesized according to Reaction Scheme 15 below:



[0232] To a 500 ml round-bottom flask were added 50 g (0.462 mol) of phenylhydrazine and 170 ml of acetic acid and a temperature of the flask was raised to 60° C. Subsequently, 51.9 g (0.462 mol) of 2-methylcyclohexanone was added to the heated round-bottom flask. After the addition of the compound was terminated, the mixture was refluxed for 8 hours. After the reaction was terminated, 100 ml of water was added to the mixture and the resultant mixture was made basic with sodium hydroxide.


[0233] The resulting solution was extracted with water and ethyl acetate to separate an organic layer. The obtained organic layer was subjected to anhydrous treatment with magnesium sulfate and concentrated under reduced pressure. Thereafter, the resulting product was purified by column chromatography by using hexane and ethyl acetate as a developing solvent. As a result, 72 g of Intermediate 15-a was obtained (yield: 84%).

Synthesis Example 15-(2)

Synthesis of Intermediate 15-b

[0234] Intermediate 15-b was synthesized according to Reaction Scheme 16 below:

Reaction Scheme 16



[0235] 57 g (0.308 mol) of Intermediate 15-a obtained according to Reaction Scheme 15 was dissolved in 570 ml of toluene in a 2 L round-bottom flask with a nitrogen atmosphere, and the temperature was then reduced to -10°C . Subsequently, 300 ml (0.474 mol) of 1.6M methyllithium was slowly added to the solution and maintained at -10°C for 3 hours to induce a reaction therebetween. After the reaction was terminated, water was slowly added to the reaction solution until the solution had no reactivity.


[0236] The resulting solution was extracted with water and ethyl acetate to separate an organic layer. The obtained organic layer was subjected to anhydrous treatment with magnesium sulfate and concentrated under reduced pressure. Thereafter, the resulting product was purified by column chromatograph by using hexane and ethyl acetate as a developing solvent. As a result, 47 g of Intermediate 15-b was obtained (yield: 76%).

Synthesis Example 15-(3)

Synthesis of Intermediate 15-c

[0237] Intermediate 15-b was synthesized according to Reaction Scheme 17 below:

Reaction Scheme 17



[0238] To a 1 L round-bottom flask were added 40 g (0.199 mol) of Intermediate 15-b obtained according to Reaction Scheme 16, 48.6 g (0.238 mol) of iodobenzene, 0.89 g (0.004 mol) of tris(dibenzylideneacetone)dipalladium(0), 2.47 g (0.004 mol) of 2,2-bis(diphenylphosphino)-1,1'-binaphthyl, 38.19 g (0.397 mol) of sodium tertiarybutoxide, and 400 ml of toluene and the mixture was refluxed for 8 hours. After the reaction was terminated, the resulting mixture was filtered with celite, and the filtrate was concentrated under reduced


pressure. The resulting product was purified by column chromatography using hexane as a developing solvent. As a result, 44 g of Intermediate 15-c was obtained (yield: 79%).

Synthesis Example 15-(4)

Synthesis of Intermediate 15-d

[0239] Intermediate 15-d was synthesized according to Reaction Scheme 18 below:

Reaction Scheme 18



[0240] Intermediate 15-c Intermediate 15-d

[0241] To a 500 ml round-bottom flask were added 44 g (0.158 mol) of Intermediate 15-c obtained according to Reaction Scheme 17 and 130 ml of dimethylformamide and the temperature was reduced to 0°C . Subsequently, 25.2 g (0.142 mol) of N-bromosuccinimide was dissolved in 200 ml of dimethylformamide and the solution was slowly added to the mixture. After the addition of the solution was terminated, the temperature was raised to room temperature and the resulting solution was stirred for 2 hours.


[0242] After the reaction was terminated, the resultant solution was extracted with water and dichloromethane to separate an organic layer. The obtained organic layer was subjected to anhydrous treatment with magnesium sulfate and concentrated under reduced pressure. Thereafter, the resulting product was crystallized with hexane and crystal produced therefrom was filtered. As a result, 45 g of Intermediate 15-d was obtained (yield: 80%).

Synthesis Example 15-(5)


Synthesis of Intermediate 15-e

[0243] Intermediate 15-e was synthesized according to Reaction Scheme 19 below:

Reaction Scheme 19



-continued



Intermediate 15-e

[0244] To a 1 L round-bottom flask were added 40 g (0.112 mol) of Intermediate 15-d obtained according to Reaction Scheme 18, 34 g (0.134 mol) of bis(pinacolato)diboron, 2.73 g (0.003 mol) of palladium(II) chloride-1,1'-bis(diphenylphosphino)ferrocene, 32.9 g (0.335 mol) of potassium acetate, and 480 ml of toluene and the mixture was refluxed for 8 hours. After the reaction was terminated, the resultant mixture was filtered with celite and the filtrate was concentrated under reduced pressure. Thereafter, the resulting product was purified by column chromatography by using hexane and ethyl acetate as a developing solvent. As a result, 26 g of Intermediate 15-e was obtained (yield: 58%).

Synthesis Example 15-(6)

Synthesis of Compound 68

[0245] To a round-bottom flask were added 5.0 g (9 mmol) of Intermediate 15-e, 8.4 g (2.1 mmol) of Intermediate 1-e, 0.4 g (0.3 mmol) of tetrakis(triphenylphosphine)palladium, 3.6 g (26 mmol) of potassium carbonate, 25 ml of 1,4-dioxane, 25 ml of toluene, and 10 ml of water, and the mixture was refluxed. After the reaction was terminated, water and hexane were added to the resultant mixture. Crystals produced therefrom were filtered. The crystals were recrystallized to obtain 5.3 g of Compound 68 (yield: 57%).

[0246] The produced compound was identified using NMR.

[0247] MS: m/z 969 $[M]^+$

[0248] ^1H NMR (CDCl_3) δ 9.07 (d, 1H), 8.95 (m, 2H), 8.48 (d, 1H), 7.75 (m, 6H), 7.37 (m, 24H), 6.62 (s, 2H), 2.00 (m, 2H), 1.60 (m, 14H), 1.30 (s, 3H), 1.28 (s, 3H), 1.18 (s, 3H), 1.15 (s, 3H)

Example 1

[0249] ITO glass was patterned to have an emission area of 2 mm $\times$ 2 mm and then washed. The ITO glass was placed in a vacuum chamber, CuPc was deposited on the ITO glass at a base pressure of 1×10^{-7} torr to form a HIL having a thickness of 800 Å, and α -NPD was deposited on the HIL to form a HTL having a thickness of 300 Å. Compound BH01 and Compound 1 (3 wt %) were co-deposited on the HTL to form an EML having a thickness of 250 Å and Alq₃ was deposited on the EML to form an ETL having a thickness of 350 Å. Thereafter, a LiF EIL having a thickness of 5 Å was formed on the ETL and an Al electrode having a thickness of 500 Å was formed on the EIL, thereby completing the manufacturing of an OLED.


Examples 2 Through 8

[0250] OLEDs were manufactured in the same manner as in Example 1, except that Compounds 3, 9, 10, 11, 12, 28, and 29 were respectively used instead of Compound 1.

Comparative Example 1

[0251] An OLED was manufactured in the same manner as in Example 1, except that Compound A below was used instead of Compound 1.


Compound A



Comparative Example 2

[0252] An OLED was manufactured in the same manner as in Example 1, except that Compound B below was used instead of Compound 1.

Compound B



Evaluation Example 1

[0253] Driving voltage, current, luminance (measured at 0.4 mA), color coordinate, and lifetime (T80) of each of the

OLEDs manufactured according to Examples 1 through 8 and Comparative Examples 1 and 2 were measured using PR650 Spectroscan Source Measurement Unit (manufactured by PhotoResearch), and the measurement results are shown in Table 1 below. In addition, lifetime data of the OLEDs are illustrated in FIGS. 2 and 3 and current density data of the OLEDs are illustrated in FIGS. 4 and 5. T80 indicates the time at which the luminance of each of the OLEDs is decreased to 80% of the initial luminance and it was measured at 3,000 nit.

TABLE 1

	dopant	Vol. (V)	Current density (mA/cm ²)	External quantum efficiency	Luminance (cd/m ²)	CIE _x	CIE _y	T80 (hr)
Example 1	1	4.0	10	5.61	471	0.145	0.096	187
Example 2	3	3.6	10	6.83	690	0.142	0.123	379
Example 3	9	3.8	10	6.09	695	0.141	0.148	257
Example 4	10	3.8	10	6.33	624	0.143	0.120	207
Example 5	11	4.0	10	6.71	677	0.142	0.125	180
Example 6	12	3.8	10	6.16	693	0.141	0.145	211
Example 7	28	3.8	10	5.43	480	0.145	0.103	150
Example 8	29	3.9	10	6.46	663	0.141	0.127	194
Comparative Example 1	A	4.3	10	5.06	534	0.133	0.137	45
Comparative Example 2	B	4.3	10	4.59	504	0.134	0.144	35

[0254] From the results as shown in Table 1 and FIGS. 2 through 5, it is confirmed that each of the OLEDs of Examples 1 through 8 has excellent driving voltage and external quantum efficiency, higher luminance, higher color purity, and longer lifetime, as compared to the OLEDs of Comparative Examples 1 and 2.

[0255] As described above, the condensed-cyclic compound of Formula 1 may have high thermal resistance and excellent luminous properties, and thus an OLED including the condensed-cyclic compound of Formula 1 may have excellent driving voltage, high efficiency, high luminance, excellent external quantum efficiency, and long lifetime.


Synthesis Example 21

Synthesis of Compound 2A


Synthesis Example 21-(1)

Synthesis of [Intermediate 2A-a]

[0256]



-continued




[Intermediate 2A-a]


[0257] 1-bromo-2-iodobenzene (31.7 g, 112 mmol), 9-phenanthrylboronic acid (34.6 g, 156 mmol), tetrakis(triphenylphosphine)palladium (2.6 g, 2 mmol), potassium carbonate (30.9 g, 223 mmol), 50 mL of water, 125 mL of toluene, and 125 mL of tetrahydrofuran were loaded into a round-bottom flask, and then, the mixture was refluxed for 12 hours. Once an organic layer was concentrated under reduced pressure, the resultant was subjected to column chromatography to obtain 26.9 g (yield of 72%) of [Intermediate 2A-a].

Synthesis Example 21-(2)

Synthesis of [Intermediate 2A-b]

[0258]






[0259] [Intermediate 2A-a] (4.1 g, 12.2 mmol) was added to 50 mL of tetrahydrofuran, and then, at a temperature of -78°C ., n-butyllithium (5.8 mL, 14.6 mmol) was added dropwise thereto. The resultant was stirred for about 1 hour. Then, at the same temperature, 9-fluorenone (1.9 g, 10.8 mmol) dissolved in 10 mL of tetrahydrofuran was slowly added dropwise thereto and the resultant was stirred for 2 hours, and then, stirred for 12 hours at room temperature. After extraction using ethyl acetate, the resultant was recrystallized by using diethylether to obtain 4.2 g (yield of 79%) of [Intermediate 2A-b].

Synthesis Example 21-(3)

Synthesis of [Intermediate 2A-c]

[0260]





[0261] [Intermediate 2A-b] (28.8 g, 66.3 mmol) was added to 300 mL of an acetic acid, and then, the temperature was raised to 80°C . and one or two drops of an HCl aqueous solution were added thereto, followed by two hours of refluxing. The temperature was dropped to room temperature, and the resultant was filtered to obtain 25.4 g (yield of 92%) of [Intermediate 2A-c].

Synthesis Example 21-(4)

Synthesis of [Intermediate 2A-d]

[0262]




[0263] [Intermediate 2A-c] (22.9 g, 0.055 mol) was added to 250 mL of dimethylformamide, and the resultant was stirred at a temperature of 0°C . n-bromosuccinimide (21.5 g, 0.121 mol) dissolved in 70 mL of dimethylformamide was added dropwise thereto, and the resultant was stirred for 12 hours. The reaction product was filtered by using distilled water and washed with hexane. Then, the resultant was dissolved in dichloromethane and heated, and then, subjected to an active charcoal treatment with acid white clay. Then, the resultant was washed with dichloromethane and re-crystallized by using hexane, thereby obtaining 23.7 g (yield of 75%) of [Intermediate 2A-d].

Synthesis Example 21-(5)

Synthesis of [Intermediate 2A-e]

[0264]





[0265] (4-chlorophenyl)trimethylsilane (18.5 g, 0.1 mol), 4-amino-tert-butylbenzene (14.9 g, 0.1 mol), palladium acetate (0.08 g, 0.32 mmol), 2,2'-bis(diphenylphosphino)-1,1'-binaphthyl (0.26 g, 0.42 mmol), and sodium tertiarybutoxide (15.2 g, 0.16 mol) were added to 150 mL of toluene, and the mixture was refluxed for 12 hours. The resultant was cooled to room temperature, and then, washed by using methanol and re-crystallized by using dichloromethane and methanol, thereby obtaining 22.3 g (yield of 75%) of [Intermediate 2A-e].

Synthesis Example 21-(6)

Synthesis of [Compound 2A]

[0266]



[0267] [Intermediate 2A-d] (5.5 g, 9.5 mmol), [Intermediate 1-e] (7.4 g, 24.8 mmol), and palladium acetate (0.15 g, 0.67 mmol) were added to 80 mL of toluene, and the mixture was stirred at a temperature of 60° C. Tritertiarybutylphosphine (0.42 g, 1.9 mmol) and potassium tertiarybutoxide (4.2 g, 38.1 mmol) were slowly added dropwise thereto, and then, reacted at a temperature of 100° C. for 2 hours. The reaction product was subjected to an extraction process using dichloromethane, followed by column chromatography, thereby obtaining 4.1 g (yield of 43%) of [Compound 2A].

[0268] MS (MALDI-TOF): m/z 1006.51 $[M]^+$


Synthesis Example 22


Synthesis of Compound 6A

Synthesis Example 22-(1)

Synthesis of Intermediate 6A-a

[0269]





[0270] 4-amino biphenyl (16.3 g, 96 mmol), bromobenzene (15.8 g, 101 mmol), palladium acetate (0.32 g, 1.4 mmol), 2,2-bis(diphenylphosphino)-1,1'-binaphthyl (0.9 g, 1.4 mmol), sodium tertiary butoxide (18.5 g, 193 mmol), and 160 ml of toluene were added to a round-bottom flask, and then, the mixture was refluxed for 24 hours. The temperature was adjusted to be room temperature, and then, the resultant was filtered and the obtained filtrate was concentrated and purified by column chromatography. Thereafter, the resultant was re-crystallized by using dichloromethane and methanol, and filtered and dried, thereby producing 15 g (yield of 60%) of [Intermediate 6A-a], which was in the form of white solid.

Synthesis Example 22-(2)

Synthesis of [Compound 6A]

[0271] [Compound 6A] (yield of 45%) was obtained in the same manner as in Synthesis Example 21-(6), except that [Intermediate 6A-a] was used instead of [Intermediate 2A-e].

[0272] MS (MALDI-TOF): m/z 902.37 [M]⁺

Synthesis Example 23

Synthesis of Compound 8A

[0273] [Compound 8A] (yield of 47%) was obtained in the same manner as in Synthesis Example 21-(5), except that pentadeuterated iodobenzene was used instead of (4-chlorophenyl)trimethylsilane.

[0274] MS (MALDI-TOF): m/z 872.49 [M]⁺

Synthesis Example 24

Synthesis of Compound 18A

[0275] [Compound 18A] (yield of 44%) was obtained in the same manner as in Synthesis Example 21, except that, in Synthesis Example 21-(5), 1-cyano-4-chlorobenzene was used instead of (4-chlorophenyl)trimethylsilane, and 2-methyl-5-aminopyridine was used instead of 4-amino-tertiary-butylbenzene.

[0276] MS (MALDI-TOF): m/z 830.32 [M]⁺

Example 21

[0277] ITO glass was patterned such that an emission area thereof was a size of 2 mm×2 mm, and then, washed. The ITO glass was mounted on a vacuum chamber, and then, a base pressure was adjusted to be 1×10^{-7} torr. Then, CuPc was deposited on the ITO glass to form a hole injection layer having a thickness of 800 Å, and α -NPD was deposited on the hole injection layer to form a hole transport layer having a thickness of 300 Å. Compound BH1 and Compound 2A (3 wt. %) were co-deposited on the hole transport layer to form an emission layer having a thickness of 250 Å, and then, Alq₃ was deposited on the emission layer to form an electron transport layer having a thickness of 350 Å. Subsequently, LiF electron injection layer having a thickness of 5 Å and Al electrode having a thickness of 500 Å were sequentially formed thereon, thereby completing the manufacture of an organic light-emitting diode.

Examples 22 to 24

[0278] Organic light-emitting diodes were manufactured in the same manner as in Example 21, except that Compounds 6A, 8A, and 18A were used instead of Compound 2A.

Evaluation Example 2

[0279] Driving voltage, current, luminance (measured at 0.4 mA), color coordinate, and lifetime (T80) of the organic light-emitting diodes manufactured according to Examples 21 to 24 and Comparative Examples 1 and 2 were measured by using PR650 Spectroscan Source Measurement Unit. (a product of PhotoResearch Company), and results thereof are shown in Table 2. T80 indicates a period of time that has elapsed when luminance reduces to 80% of the initial luminance, and herein, was measured at 3,000 nit.

TABLE 2


	Dopant	Voltage (V)	Current density (mA/cm ²)	External quantum efficiency	Luminance (cd/m ²)	External		T80 (hr)
						CIE _x	CIE _y	
Example 21	2A	3.6	10	7.67	645	0.142	0.112	412
Example 22	6A	3.6	10	7.12	674	0.142	0.120	397
Example 23	8A	3.7	10	6.99	661	0.141	0.118	378
Example 24	18A	3.7	10	6.56	624	0.141	0.121	325
Comparative Example 1	A	4.3	10	5.06	534	0.133	0.137	45
Comparative Example 2	B	4.3	10	4.59	504	0.134	0.144	35

[0280] From the results as shown in Table 2, it is confirmed that each of the OLEDs of Examples 21 through 24 has excellent driving voltage and external quantum efficiency, higher luminance, higher color purity, and longer lifetime, as compared to the OLEDs of Comparative Examples 1 and 2.

[0281] While the present invention has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims.

What is claimed is:

1. A condensed-cyclic compound represented by Formula 1A below:



wherein R_1 is represented by $-(Ar_1)_{a1}-(R_{11})_{b1}$, R_2 is represented by $-(Ar_2)_{a2}-(R_{12})_{b2}$, R_3 is represented by $-(Ar_3)_{a3}-(R_{13})_{b3}$, and R_4 is represented by $-(Ar_4)_{a4}-(R_{14})_{b4}$;

Ar_1 through Ar_4 are each independently a substituted or unsubstituted C_6-C_{60} aromatic linking group or a substituted or unsubstituted C_2-C_{60} heteroaromatic linking group;

Ar_5 and Ar_6 are each independently a substituted or unsubstituted C_6-C_{60} arylene group or a substituted or unsubstituted C_2-C_{60} heterarylene group;

R_{11} through R_{14} are each independently non-covalent electron pairs, hydrogen, deuterium, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{60} cycloalkyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_2-C_{60} heteroaryl group, or a substituted or unsubstituted C_2-C_{60} condensed-cyclic group;

$a1$ through $a4$ are each independently an integer of 0 to 3; $b1$ through $b4$ are each independently an integer of 1 to 5; c and d are each independently an integer of 0 to 3;

X_1 through X_{10} are each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a

sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{60} cycloalkyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, a substituted or unsubstituted C_2-C_{60} heteroaryl group, $-\text{Si}(R_{21})(R_{22})(R_{23})$, or $-\text{N}(R_{24})(R_{25})$;

R_{21} through R_{25} are each independently hydrogen, deuterium, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, a substituted or unsubstituted C_1-C_{60} alkoxy group, a substituted or unsubstituted C_3-C_{60} cycloalkyl group, a substituted or unsubstituted C_6-C_{60} aryl group, a substituted or unsubstituted C_6-C_{60} aryloxy group, a substituted or unsubstituted C_6-C_{60} arylthio group, or a substituted or unsubstituted C_2-C_{60} heteroaryl group;

Z_{21} and Z_{22} are each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1-C_{60} alkyl group, a substituted or unsubstituted C_2-C_{60} alkenyl group, a substituted or unsubstituted C_2-C_{60} alkynyl group, or a substituted or unsubstituted C_1-C_{60} alkoxy group;

u is an integer of 1 to 4; and

v is an integer of 1 to 6.

2. The condensed-cyclic compound of claim 1, wherein R_{11} through R_{14} are each independently hydrogen, deuterium, a substituted or unsubstituted C_1-C_{10} alkyl group, a substituted or unsubstituted phenyl group, a substituted or unsubstituted pentalenyl group, a substituted or unsubstituted indenyl group, a substituted or unsubstituted naphthyl group, a substituted or unsubstituted azuleny group, a substituted or unsubstituted heptalenyl group, a substituted or unsubstituted indacenyl group, a substituted or unsubstituted acenaphthyl group, a substituted or unsubstituted fluorenyl group, a substituted or unsubstituted phenalenyl group, a substituted or unsubstituted phenanthrenyl group, a substituted or unsubstituted anthryl group, a substituted or unsubstituted fluorantheny group, a substituted or unsubstituted triphenylenyl group, a substituted or unsubstituted pyrenyl group, a substituted or unsubstituted chrysenyl group, a substituted or unsubstituted naphthacenyl group, a substituted or unsubstituted picenyl group, a substituted or unsubstituted perylenyl group, a substituted or unsubstituted pentaphenyl group, a substituted or unsubstituted hexacenyl group, a substituted or unsubstituted cyclopentyl group, a substituted or unsubstituted cyclohexyl group, a substituted or unsubstituted cycloheptyl group, a substituted or unsubstituted dihydronaphthyl group, a substituted or unsubstituted tetrahydronaphthyl group, or a substituted or unsubstituted dihydro-indenyl group.

3. The condensed-cyclic compound of claim 1, wherein Ar_1 through Ar_4 are each independently a substituted or unsubstituted benzene linking group, a substituted or unsubstituted pentalene linking group, a substituted or unsubstituted indene linking group, a substituted or unsubstituted naphthalene linking group, a substituted or unsubstituted azu-


lene linking group, a substituted or unsubstituted heptalene linking group, a substituted or unsubstituted indacene linking group, a substituted or unsubstituted acenaphthylene linking group, a substituted or unsubstituted fluorene linking group, a substituted or unsubstituted phenalene linking group, a substituted or unsubstituted phenanthrene linking group, a substituted or unsubstituted anthracene linking group, a substituted or unsubstituted fluoranthene linking group, a substituted or unsubstituted triphenylene linking group, a substituted or unsubstituted pyrene linking group, a substituted or unsubstituted crycene linking group, a substituted or unsubstituted naphthacene linking group, a substituted or unsubstituted pycene linking group, a substituted or unsubstituted perylene linking group, a substituted or unsubstituted pentacene linking group, or a substituted or unsubstituted hexacene linking group.

4. The condensed-cyclic compound of claim 1, wherein a_1 through a_4 are each independently 0, 1, or 2, and b_1 through b_4 are each independently 1 or 2.


5. The condensed-cyclic compound of claim 1, wherein R_{11} through R_{14} are each independently one of hydrogen; deuterium; a C_1 - C_{10} alkyl group; a phenyl group; a naphthyl group; a phenanthrenyl group; a fluorenyl group; a pyrenyl group; a cyclopentyl group; a cyclohexyl group; a tetrahydronaphthyl group; a dihydro-indenyl group; and a phenyl group, a naphthyl group, a phenanthrenyl group, a fluorenyl group, a pyrenyl group, a cyclopentyl group, a cyclohexyl group, a tetrahydronaphthyl group, and a dihydro-indenyl group that are substituted with at least one of deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, and $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$;

Q_1 through Q_3 are each independently a C_1 - C_{10} alkyl group or a C_6 - C_{14} aryl group;


Ar_1 through Ar_4 are each independently represented by one of Formulae 3A through 3G below:



Formula 3A




Formula 3B




Formula 3C


-continued




Formula 3D



Formula 3E



Formula 3F



Formula 3G


wherein Z_{11} through Z_{14} are each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, or a C_1 - C_{60} alkoxy group;

s is an integer of 1 to 6; and

t is an integer of 1 to 3.


6. The condensed-cyclic compound of claim 1, wherein at least one of a combination of R_1 and R_2 and a combination of R_3 and R_4 in Formula 1 is linked to each other.

7. The condensed-cyclic compound of claim 1, wherein at least one of $-\text{N}(\text{R}_1)(\text{R}_2)$ and $-\text{N}(\text{R}_3)(\text{R}_4)$ in Formula 1 is represented by one of Formulae 5A through 5F:




Formula 5A

-continued




Formula 5B


-continued




Formula 5E



Formula 5C



Formula 5F




Formula 5D

wherein Z_{31} through Z_{42} are each independently hydrogen, deuterium, a halogen atom, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, hydrazine, hydrazone, a carboxyl group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, or a substituted or unsubstituted C_1 - C_{60} alkoxy group, or a substituted or unsubstituted C_6 - C_{60} aryl group; and


w and x are each independently an integer of 1 to 8.

8. The condensed-cyclic compound of claim 1, wherein the condensed-cyclic compound is one of Compounds 1A to 3A, 74 and 5A to 30A:

<Compound 1A>




<Compound 2A>




-continued


<Compound 3A>




<Compound 74>




<Compound 5A>




<Compound 6A>



<Compound 7A>




<Compound 8A>




-continued


<Compound 9A>




<Compound 10A>




<Compound 11A>



<Compound 12A>




<Compound 13A>




-continued

<Compound 14A>




<Compound 15A>




<Compound 16A>

<Compound 17A>




-continued


<Compound 18A>




<Compound 19A>




<Compound 20A>




<Compound 21A>



<Compound 22A>




<Compound 23A>




-continued


<Compound 24A>




<Compound 25A>




<Compound 26A>




<Compound 27A>




<Compound 28A>



<Compound 29A>



<Compound 30A>



9. An organic light-emitting diode comprising:

a first electrode;

a second electrode facing the first electrode; and

an organic layer interposed between the first electrode and the second electrode; wherein the organic layer comprises at least one of the condensed-cyclic compound according to claim 1.


10. The organic light-emitting diode of claim 9, wherein the organic layer comprises a hole injection layer, a hole transport layer, a functional layer having hole injection and hole transport abilities, an emission layer, an electron transport layer, an electron injection layer, or any combination thereof.

11. The organic light-emitting diode of claim 10, wherein the emission layer comprises the condensed-cyclic compound.

12. The organic light-emitting diode of claim 11, wherein the emission layer further comprises a host and the condensed-cyclic compound in the emission layer acts as a dopant.

13. The organic light-emitting diode of claim 12, wherein the host comprises an anthracene-based compound represented by Formula 60 below:

Formula 60



wherein Ar_{11} and Ar_{12} are each independently a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylene group;

Ar_{13} and Ar_{14} are each independently a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ alkyl group or a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group; and

e and f are each independently an integer of 0 to 5.

14. The organic light-emitting diode of claim 10, wherein the electron transport layer comprises an electron transport organic compound and a metal-containing material.

15. The organic light-emitting diode of claim 14, wherein the metal-containing material is a lithium complex.

16. The organic light-emitting diode of claim 10, wherein the organic layer comprises a hole injection layer, a hole transport layer, a functional layer having hole injection and hole transport abilities, or any combination thereof, and at least one of the hole injection layer, the hole transport layer, and the functional layer having hole injection and hole transport abilities comprises a charge-generating material.

* * * * *

专利名称(译)	缩合环状化合物和包括其的有机发光二极管		
公开(公告)号	US20160099411A1	公开(公告)日	2016-04-07
申请号	US14/969767	申请日	2015-12-15
[标]申请(专利权)人(译)	SFC股份有限公司 三星显示有限公司		
申请(专利权)人(译)	SFC CO. , LTD. 三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD. SFC CO. , LTD.		
[标]发明人	KIM MYEONG SUK JE JONG TAE LEE SE JIN PARK SEOK BAE YU SE JIN LIM JEA GEON CHOI BYOUNG KI KIM TAE KYUNG YI JEOUNG IN		
发明人	KIM, MYEONG-SUK JE, JONG-TAE LEE, SE-JIN PARK, SEOK-BAE YU, SE-JIN LIM, JEA-GEON CHOI, BYOUNG-KI KIM, TAE-KYUNG YI, JEOUNG-IN		
IPC分类号	H01L51/00 C07D213/74 C09K11/02 C07F7/08 C07C211/61 C09K11/06		
CPC分类号	H01L51/006 C09K2211/1022 C07C211/61 C09K11/06 C09K11/025 H01L51/0094 H01L51/0061 H01L51/0058 C07F7/0818 C07D213/74 H01L51/5076 H01L51/5012 H01L51/0055 C07C2103/52 C09K2211/1007 C09K2211/1011 C09K2211/1014 H01L51/0056 H01L51/0067 C07C2103/97 C09K2211/1029 H01L51/0077 C07B59/001 C07C255/58 C07C2601/14 C07C2602/08 C07C2602/10 C07C2603/52 C07C2603/97 C07D209/86 C07D403/10 C07D487/14 C07F7/081 H01L51/0052 H01L51/ /0085 H01L51/0087		
优先权	1020110104825 2011-10-13 KR 1020110004523 2011-01-17 KR		
其他公开文献	US9653689		
外部链接	Espacenet USPTO		

摘要(译)

由下式1表示的稠环化合物，和包含该稠环化合物的有机发光二极管。其中R 1 到R 6 ，Ar 5 和Ar 6 ，X 1 通过X 10 在规范中定义。

