




US 20160190467A1

(19) **United States**(12) **Patent Application Publication**
JANG et al.(10) **Pub. No.: US 2016/0190467 A1**(43) **Pub. Date: Jun. 30, 2016**(54) **AMINE-BASED COMPOUND AND ORGANIC
LIGHT-EMITTING DEVICE INCLUDING THE
SAME**(52) **U.S. CL.**
CPC *H01L 51/0061* (2013.01); *H01L 51/006*
(2013.01); *C07D 405/10* (2013.01); *H01L*
51/506 (2013.01)(71) Applicant: **SAMSUNG DISPLAY CO., LTD.,**
Yongin-si (KR)(72) Inventors: **Hyungseok JANG**, Yongin-si (KR);
Youngkook KIM, Yongin-si (KR);
Jongwoo KIM, Yongin-si (KR); **Jino**
LIM, Yongin-si (KR); **Seokhwan**
HWANG, Yongin-si (KR)(57) **ABSTRACT**An amine-based compound and an organic light-emitting
device, the amine-based compound being represented by For-
mula 1 below:

<Formula 1>

(21) Appl. No.: **14/963,281**(22) Filed: **Dec. 9, 2015**(30) **Foreign Application Priority Data**


Dec. 30, 2014 (KR) 10-2014-0194320

Publication Classification(51) **Int. Cl.**
H01L 51/00 (2006.01)
C07D 405/10 (2006.01)

10

190150110

FIG. 1



AMINE-BASED COMPOUND AND ORGANIC LIGHT-EMITTING DEVICE INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

[0001] Korean Patent Application No. 10-2014-0194320, filed on Dec. 30, 2014, in the Korean Intellectual Property Office, and entitled: "Amine-Based Compound and Organic Light-Emitting Device Including the Same," is incorporated by reference herein in its entirety.

BACKGROUND

[0002] 1. Field

[0003] Embodiments relate to an amine-based compound and an organic light-emitting device including the same.

[0004] 2. Description of the Related Art


[0005] Organic light-emitting devices are self-emission devices that have wide viewing angles, high contrast ratios, short response times, and excellent brightness, driving voltage, and response speed characteristics, and produce full-color images.

[0006] The organic light-emitting device may include a first electrode disposed on a substrate, and a hole transport region, an emission layer, an electron transport region, and a second electrode, which are sequentially disposed on the first electrode. Holes provided from the first electrode may move toward the emission layer through the hole transport region, and electrons provided from the second electrode may move toward the emission layer through the electron transport region. Carriers, such as holes and electrons, are recombined in the emission layer to produce excitons. These excitons change from an excited state to a ground state, thereby generating light.

SUMMARY

[0007] Embodiments are directed to an amine-based compound and an organic light-emitting device including the same.

[0008] An aspect provides an amine-based compound represented by Formula 1 below:



[0009] wherein in Formula 1,

[0010] A may be a substituted or unsubstituted C₆-C₂₀ aromatic ring;

[0011] X₁ may be selected from N-(L₂)_{a2}-(Ar₂), an oxygen atom (O), and a sulfur atom (S);

[0012] L₁ to L₇ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

[0013] a₁ to a₇ may each independently be an integer selected from 0 to 3;

[0014] Ar₁ to Ar₄ may each independently be selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;

[0015] R₁ to R₄ may each independently be selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), and —B(Q₄)(Q₅);

[0016] b₁ and b₃ may each independently be an integer selected from 0 to 4, b₂ and b₄ are each independently an integer selected from 0 to 3;

[0017] at least one substituent of the substituted C₆-C₂₀ aromatic ring, substituted C₃-C₁₀ cycloalkylene group, substituted C₁-C₁₀ heterocycloalkylene group, substituted C₃-C₁₀ cycloalkenylene group, substituted C₁-C₁₀ heterocycloalkenylene group, substituted C₆-C₆₀ arylene group, substituted C₁-C₆₀ heteroarylene group, substituted a divalent non-aromatic condensed polycyclic group, substituted a divalent non-aromatic condensed heteropolycyclic group, substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic con-

densified polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

[0018] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0019] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), and —B(Q₁₄)(Q₁₅);

[0020] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0021] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —B(Q₃₄)(Q₃₅), each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), and —B(Q₂₄)(Q₂₅); and

[0022] Q₁ to Q₅, Q₁₁ to Q₁₅, Q₂₁ to Q₂₅ and Q₃₁ to Q₃₅ may each independently be a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic con-

densified polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

[0023] Another aspect provides an organic light-emitting device that includes: a first electrode; a second electrode facing the first electrode; and an organic layer that is disposed between the first electrode and the second electrode and includes an emission layer, wherein the organic layer includes at least one of the amine-based compound described above.

BRIEF DESCRIPTION OF THE DRAWING

[0024] Features will be apparent to those of skill in the art by describing in detail exemplary embodiments with reference to the attached drawing in which:


[0025] FIG. 1 illustrates a schematic view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0026] Example embodiments will now be described more fully hereinafter with reference to the accompanying drawing; however, they may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey exemplary implementations to those skilled in the art.

[0027] In the drawing figures, the dimensions of layers and regions may be exaggerated for clarity of illustration. Like reference numerals refer to like elements throughout.

[0028] An amine-containing (e.g., tertiary amine-containing) or amine-based compound according to an embodiment may be represented by Formula 1 below.




[0029] A in Formula 1 may be or may include, e.g., a substituted or unsubstituted C₆-C₂₀ aromatic ring.


[0030] In an implementation, A in Formula 1 may be selected from or include, e.g., a substituted or unsubstituted a benzene group, a substituted or unsubstituted a naphthalene group, a substituted or unsubstituted an anthracene group, a substituted or unsubstituted a pyrene group, a substituted or unsubstituted a phenanthrene group, a substituted or unsubstituted a chrysene group, and a substituted or unsubstituted triphenylene group.

[0031] In an implementation, A may be a group represented by one of the following Formulae 2-1 to 2-19.


-continued




Formula 2-1




Formula 2-2




Formula 2-3




Formula 2-4




Formula 2-5




Formula 2-6




Formula 2-7




Formula 2-8




Formula 2-9



Formula 2-10








Formula 2-11



Formula 2-12

-continued



Formula 2-13



Formula 2-14

Formula 2-15

Formula 2-16

Formula 2-17

-continued



Formula 2-18

Formula 2-19

[0032] In Formulae 2-1 to 2-19,

[0033] Z_{21} and Z_{22} may each independently be selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0034] f_1 may be 1 or 2, f_2 may be an integer selected from 1 to 3, f_3 may be an integer selected from 1 to 4, f_4 may be an integer selected from 1 to 5, and f_5 may be an integer selected from 1 to 7;

[0035] $*$ and $*$ indicate binding sites to neighboring atoms, and $**$ indicates a binding site to L_5 in $-(L_5)_{a5}$ - or to N. L_5 and a_5 will be described in detail below.

[0036] In an implementation, A may be selected from:

[0037] a benzene; and

[0038] a benzene substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl

group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

[0039] X_1 in Formula 1 may be selected from, e.g., N-(L_2)_{a2}-(Ar₂), O (oxygen atom) and S (sulfur atom). For example, X_1 may be O or S.

[0040] In an implementation, X_1 may be O.

[0041] L_1 to L_7 may each independently be selected from or include, e.g., a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group.


[0042] In an implementation, L_1 to L_7 in Formula 1 may each independently be selected from a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a furinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiothiazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiothiazolylene group, a benzocarbazolylene group, a benzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group; and

[0043] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a furinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiothiazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiothiazolylene group, a benzocarbazolylene group, a benzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group.


enylene group, a pyrenylene group, a chrysenylene group, a naphthacenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a furinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiothiazolylene group, an isobenzothiazolylene group, a benzoxazolylene group, an isobenzoxazolylene group, a triazolylene group, a tetrazolylene group, an oxadiazolylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiothiazolylene group, a benzocarbazolylene group, a benzocarbazolylene group, a thiadiazolylene group, an imidazopyridinylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a pherylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiothiazolyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiothiazolyl group, a benzocarbazolyl group, a benzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.

[0044] In an implementation, L_1 to L_7 in Formula 1 may each independently be a group represented by one of Formulae 3-1 to 3-33 below.


-continued




Formula 3-1




Formula 3-2




Formula 3-3




Formula 3-4




Formula 3-5




Formula 3-6




Formula 3-7




Formula 3-8




Formula 3-9




Formula 3-10




Formula 3-11




Formula 3-12




Formula 3-13




Formula 3-14




Formula 3-15




Formula 3-16




Formula 3-17



Formula 3-18













Formula 3-19



Formula 3-20

-continued



Formula 3-21

Formula 3-22

Formula 3-23

Formula 3-24

Formula 3-25

Formula 3-26




Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30

-continued



Formula 3-31

Formula 3-32

Formula 3-33

[0045] In Formulae 3-1 to 3-33,

[0046] Y_1 may be O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$;

[0047] Z_1 to Z_7 may each independently be selected from a hydrogen, a deuterium, —F, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazoyl group, and a triazinyl group,












[0048] d_1 may be an integer selected from 1, 2, 3, and 4, d_2 may be an integer selected from 1, 2, and 3, d_3 may be an integer selected from 1, 2, 3, 4, 5, and 6, d_4 may be an integer selected from 1, 2, 3, 4, 5, 6, 7, and 8, d_5 may be 1 or 2, and d_6 may be an integer selected from 1, 2, 3, 4, and 5, and * and *' indicate binding sites to neighboring atoms.

[0049] a_1 , a_2 , a_3 , a_4 , a_5 , a_6 , and a_7 in Formula 1 respectively indicate numbers of L_1 , L_2 , L_3 , L_4 , L_5 , L_6 , and L_7 , and may each independently be an integer selected from 0 to 3.

[0050] For example, a_1 , a_2 , a_5 , a_6 , and a_7 may each independently be 0, 1, 2, or 3, and a_3 and a_4 may each independently be 0 or 1.

[0051] When a_1 , a_2 , a_3 , a_4 , a_5 , a_6 , or a_7 are 2 or more, 2 or more L_1 , L_2 , L_3 , L_4 , L_5 , L_6 , or L_7 may be identical or different.

[0052] $*(L_1)_{a1}*$, $*(L_2)_{a2}*$, $*(L_3)_{a3}*$, $*(L_6)_{a6}*$, and $*(L_7)_{a7}*$ in Formula 1 may each independently be a single bond or may be a group represented by one of the following Formulae 4-1 to 4-27.



Formula 4-1

Formula 4-2

Formula 4-3

Formula 4-4

Formula 4-5

Formula 4-6

Formula 4-7











Formula 4-8

Formula 4-9

Formula 4-10

Formula 4-11

-continued



Formula 4-12

Formula 4-13

Formula 4-14

Formula 4-15

Formula 4-16

Formula 4-17


Formula 4-18

Formula 4-19


Formula 4-20

Formula 4-21


-continued




Formula 4-22




Formula 4-23




Formula 4-24



Formula 4-25



Formula 4-26



Formula 4-27

[0053] * and *' in Formulae 4-1 to 4-27 indicate binding sites to neighboring atoms.

[0054] Ar₁ to Ar₄ in Formula 1 may each independently be selected from or include, e.g., a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0055] In an implementation, Ar₁ to Ar₄ in Formula 1 may each independently be selected from

[0056] a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a

pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinoxalinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzofuranyl group, a thiadiazolyl group, an imidazopyridinyl group, or an imidazopyrimidinyl group; and

[0057] a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinoxalinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzofuranyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an iso-

quinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{B}(\text{Q}_{34})(\text{Q}_{35})$

[0058] Q_{31} to Q_{35} may each independently be selected from a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.

[0059] In an implementation, Ar_1 to Ar_4 in Formula 1 may each independently be selected from


[0060] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and

[0061] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{B}(\text{Q}_{34})(\text{Q}_{35})$


[0062] Q_{31} to Q_{35} may each independently be selected from a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a

carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.


[0063] In an implementation, Ar_1 to Ar_4 in Formula 1 may each independently be a group represented by one of Formulae 5-1 to 5-16 below.




Formula 5-1




Formula 5-2




Formula 5-3




Formula 5-4




Formula 5-5




Formula 5-6



Formula 5-7




Formula 5-8




Formula 5-9


-continued




Formula 5-10




Formula 5-11




Formula 5-12




Formula 5-13



Formula 5-14




Formula 5-15




Formula 5-16

[0064] In Formulae 5-1 to 5-16,**[0065]** Y_{31} may be $C(Z_{33})(Z_{34})$ or $N(Z_{35})$;**[0066]** Z_{31} to Z_{35} may each independently be selected from**[0067]** a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;**[0068]** a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;**[0069]** a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl


group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group;

[0070] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, and a naphthyl group; and**[0071]** $-Si(Q_{31})(Q_{32})(Q_{33})$.**[0072]** Q_{31} to Q_{33} may each independently be selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.**[0073]** e_1 may be an integer of 1 to 5; e_2 may be an integer of 1 to 7; e_3 may be an integer of 1 to 3; e_4 may be an integer of 1 to 4; e_5 may be 1 or 2; and * indicates a binding site to a neighboring atom.**[0074]** In an implementation, Ar_1 to Ar_4 in Formula 1 may each independently be a group represented by one of Formulae 6-1 to 6-24 below.


Formula 6-1



Formula 6-2












Formula 6-3




Formula 6-4

-continued




-continued


Formula 6-5




Formula 6-6




Formula 6-7




Formula 6-8




Formula 6-9




Formula 6-10




Formula 6-11



Formula 6-12



Formula 6-13



Formula 6-14

Formula 6-15

Formula 6-16

Formula 6-17


Formula 6-18

Formula 6-19


Formula 6-20

Formula 6-21


-continued



Formula 6-22



Formula 6-23



Formula 6-24

[0075] wherein * in Formulae 6-1 to 6-24 indicates a binding site to a neighboring atom.

[0076] In an implementation, Ar₁ to Ar₄ in Formula 1 may each independently be selected from

[0077] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

[0078] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃).

[0079] Q₃₁ to Q₃₃ may each independently be selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group.

[0080] R₁ to R₄ in Formula 1 may each independently be selected from or include, e.g., a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt

thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), and —B(Q₄)(Q₅). Q₁ to Q₅ may be the same as described below.

[0081] In an implementation, R₁ to R₄ in Formula 1 may each independently be selected from

[0082] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

[0083] a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a pyridinyl group, and a pyrimidinyl group;

[0084] a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

[0085] a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isoben-

zothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —Si(Q_{31})(Q_{32})(Q_{33}) and —B(Q_{34})(Q_{35}); and

[0086] —Si(Q_1)(Q_2)(Q_3).

[0087] Q_1 to Q_3 and Q_{31} to Q_{33} may each independently be selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

[0088] In an implementation, R_1 to R_4 in Formula 1 may each independently be selected from

[0089] a hydrogen, —F, a cyano group, a nitro group, a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;

[0090] a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy

group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from —F, a cyano group, a nitro group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and —Si(Q_{33})(Q_{34})(Q_{35}); and

[0091] —Si(Q_1)(Q_2)(Q_3).


[0092] Q_1 to Q_3 and Q_{33} to Q_{35} may each independently be selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

[0093] b_1 , b_2 , b_3 , and b_4 in Formula 1 respectively indicate numbers of R_1 , R_2 , R_3 , and R_4 , and b_1 and b_3 may be each independently 1, 2, 3, or 4 and b_2 and b_4 may be each independently 1, 2, or 3. When b_1 , b_2 , b_3 , or b_4 is 2 or more, 2 or more R_1 , R_2 , R_3 or R_4 may be identical or different.


[0094] In an implementation, Q_1 to Q_5 , Q_{11} to Q_{15} , Q_{21} to Q_{25} and Q_{31} to Q_{35} may each independently be, e.g., a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

[0095] In an implementation, the amine-based compound represented by Formula 1 may be represented by one of the following Formulae 1A to 1F.

<Formula 1A>




<Formula 1B>




-continued

<Formula 1C>



-continued


<Formula 1F>




[0096] Descriptions of X_1 , A, L_1 to L_7 , a_1 to a_7 , Ar_1 to Ar_4 , R_1 to R_4 , and b_1 to b_4 in Formulae 1A to 1F may be the same as described above.

[0097] In an implementation, the amine-based compound represented by Formula 1 may be represented by one of the following Formulae 1A-1, 1A-2, 1B-1, 1B-2, 1C-1, 1C-2, 1D-1, 1D-2, 1E-1, 1E-2, 1F-1, and 1F-2.

<Formula 1D>





<Formula 1A-1>




<Formula 1A-2>

<Formula 1E>




-continued


<Formula 1C-2>



<Formula 1D-1>




<Formula 1D-2>




-continued

<Formula 1E-1>




-continued


<Formula 1 E-2>



<Formula 1 E-2>



<Formula 1 F-1>



[0098] In Formulae 1A-1, 1A-2, 1B-1, 1B-2, 1C-1, 1C-2, 1D-1, 1D-2, 1E-1, 1E-2, 1F-1, and 1F-2,

[0099] Z_{21} may be selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0100] f_2 may be an integer selected from 0 to 3;

[0101] X_1 may be O or S;

[0102] L_1 , L_5 , L_6 , and L_7 may each independently be selected from

[0103] a phenylene group, a naphthylene group, a pyridinylene group, a pyrimidinylene group, and a triazinylene group; and

[0104] a phenylene group, a naphthylene group, a pyridinylene group, a pyrimidinylene group, and a triazinylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spirofluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0105] a1 may be 0 or 1, and a5, a6, and a7 may each independently be an integer selected from 0 to 3;

[0106] Ar₁ to Ar₄ may each independently be selected from
[0107] a phenyl group, a naphthyl group, a fluorenyl group,
a spiro-fluorenyl group, a benzofluorenyl group, a dibenzof-

luorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and


[0108] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, —Si(Q_{31})(Q_{32})(Q_{33}), and —B(Q_{34})(Q_{35}),

[0109] Q_{31} to Q_{35} may each independently be selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

[0110] R_1 to R_4 may each independently be selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{20} alkyl group, and a substituted or unsubstituted C_1 - C_{20} alkoxy group;


[0111] b_1 and b_3 may each independently be an integer selected from 0 to 4, and b_2 and b_4 may each independently be an integer selected from 0 to 3.

[0112] In an implementation, the amine-based compound represented by Formula 1 may be one of the following Compounds 1 to 300.




1

-continued




2



3


-continued

4




-continued


6



5




7




-continued

8




-continued


10



9




11




-continued

12




-continued


14



13




15




-continued

16




-continued

18





19

17




20




-continued


21



22




23




-continued


24



25




26




-continued

27




-continued


29



28




30




-continued

31




-continued


33




34



32




35




-continued


36



37




38




-continued

39




40




-continued


41



42




43




-continued


44



45




46




-continued

47




-continued


50




48




51



49




52




-continued

53




-continued


56




54




57



55




58




-continued

59




-continued


62




60




63



61




64




-continued

65




-continued


68




69




70



66




67




-continued


71



72




73




-continued


74



75




76




-continued

77




-continued


79



78




80




-continued

81




-continued


84




85




86



82




83




-continued

87




-continued

90




91



88



89




92




-continued


93



94




95




-continued


96



97




-continued




98

-continued





101

99




100



102


-continued

103





-continued

105




106

104




107




-continued

108




-continued


110



109




111




-continued

112





-continued

114




115

113




116




-continued

117




-continued


120




118




121



119




122




-continued

123




-continued


126




124



127




125




-continued

128




-continued


130




131



129




132




-continued

133




-continued


135




136



134




137




-continued

138




-continued


141




139




142



140




143




-continued

144




-continued


146



145




147




-continued

148




-continued


150




151



149




152




-continued


153



154




155




-continued


156



157




158




-continued

159




-continued


161



160




162




-continued


163



164




165




-continued

166




167




-continued

168




-continued


170



169




171




-continued

172




-continued


174



173




175




-continued

176




-continued

178





179

177




180




-continued

181




-continued


183



182




184




-continued


185



186




187




-continued


188




189



190




-continued




191


-continued




194




192



195




193




196

-continued


197



198




199




-continued

200




201




-continued

202




-continued


204




205



206




203




-continued

207




-continued


209



208




210




-continued

211




-continued



213



214




215




-continued

216




-continued


218



217




219




-continued


220



221




222




-continued

223




224




-continued

225




-continued


228




226



229




227




-continued

230




-continued


232



231




233




-continued

234




-continued


236



235




237




-continued

238




-continued

240





241

239




242




-continued

243




-continued


245



244




246




-continued


247



248




249




-continued


250



251




252




-continued

253




-continued


255



264




256




-continued

257





-continued

260





261

258




262

259




-continued




263


-continued




266




264



267




265




268

-continued


269



270




271




-continued

272




273




-continued


274



275




276




-continued

277




278




-continued

279




-continued


281



280




282




-continued

283




-continued


285



284




286




-continued

287




-continued


289




290



291




288




-continued

292




-continued


294




293




295




-continued




-continued



297




299




-continued

300



[0113] In the amine-based compound represented by Formula 1, as shown in Formula 1A-1', below, either one substituted or unsubstituted dibenzofuran or one substituted or unsubstituted dibenzothiophene (when X_1 is O or S), and one substituted or unsubstituted carbazole may be bound to a core. Accordingly, due to an orbital principle, a planar structure may be easily formed, facilitating film formation in a deposition process and helping to provide high charge mobility efficiency of an organic light-emitting device.

[0114] Also, in the amine-based compound represented by Formula 1, as shown in Formula Formula 1A-1', a carbon atom a benzene ring of the carbazole may be directly bound to the core. Accordingly, due to the orbital principle, intermolecular hydrogen bonding and pi-pi stacking may easily occur. Thus, a planar structure may be easily formed, leading to an increase in efficiency and lifespan of an organic light-emitting device.



[0115] The amine-based compound represented by Formula 1 may be synthesized by using a suitable organic synthetic method. A synthesis method of the amine-based compound may be understood in view of the following embodiments.

[0116] The amine-based compound of Formula 1 may be used or included between a pair of electrodes of an organic light-emitting device. In an implementation, the amine-based compound may be included in a hole transport region, e.g., a hole transport layer. In an implementation, an organic light-emitting device may include, e.g., a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode and including an emission layer. The organic layer may include at least one of the amine-based compound described above.

[0117] The expression that “(an organic layer) includes at least one amine-based compound” used herein may include a case in which “(an organic layer) includes identical amine-based compounds represented by Formula 1 and a case in which (an organic layer) includes two or more different amine-based compounds represented by Formula 1.

[0118] For example, the organic layer may include, as the amine-based compound, only Compound 1. In this regard, Compound 1 may exist in a hole transport layer of the organic light-emitting device. In some embodiments, the organic layer may include, as the amine-based compound, Compound 1 and Compound 2. In this regard, Compound 1 and Compound 2 may exist in an identical layer (for example, Compound 1 and Compound 2 may all exist in a hole transport layer), or different layers (for example, Compound 1 may exist in an emission layer and Compound 2 may exist in a hole transport layer).

[0119] The organic layer may include, e.g. i) a hole transport region that is disposed between the first electrode (anode) and the emission layer and includes at least one of a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and/or ii) an electron transport region that is disposed between the emission layer and the second electrode (cathode) and includes at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer. The amine-based compound represented by Formula 1 may be included in the hole transport region. For example, the hole transport region may include a hole transport layer, and the hole transport layer may include the amine-based compound represented by Formula 1.

[0120] The term “organic layer” used herein refers to a single layer and/or a plurality of layers disposed between the first electrode and the second electrode of the organic light-emitting device. A material included in the “organic layer” is not limited to an organic material.

[0121] FIG. 1 illustrates a schematic view of an organic light-emitting device 10 according to an embodiment. The organic light-emitting device 10 may include a first electrode 110, an organic layer 150, and a second electrode 190.

[0122] Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device according to an embodiment will be described in connection with FIG. 1.

[0123] In FIG. 1, a substrate may be additionally disposed under the first electrode 110 or above the second electrode 190. The substrate may be a glass substrate or transparent plastic substrate, each with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water-resistance.

[0124] The first electrode **110** may be formed by depositing or sputtering a material for forming the first electrode on the substrate. When the first electrode **110** is an anode, the material for the first electrode **110** may be selected from materials with a high work function to make holes be easily injected. The first electrode **110** may be a reflective electrode or a transmissive electrode. The material for the first electrode **110** may be a transparent and highly conductive material, and examples of such a material are indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), and zinc oxide (ZnO). When the first electrode **110** is a semi-transmissive electrode or a reflective electrode, as a material for forming the first electrode, at least one of magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), magnesium-silver (Mg—Ag) may be used.

[0125] The first electrode **110** may have a single-layer structure, or a multi-layer structure including two or more layers. For example, the first electrode **110** may have a three-layered structure of ITO/Ag/ITO.

[0126] An organic layer **150** may be disposed on the first electrode **110**. The organic layer **150** may include an emission layer.

[0127] The organic layer **150** may further include a hole transport region between the first electrode and the emission layer, and/or an electron transport region between the emission layer and the second electrode.

[0128] The hole transport region may include the amine-based compound represented by Formula 1.

[0129] The hole transport region may include at least one selected from a hole injection layer (HIL), a hole transport layer (HTL), a buffer layer, and an electron blocking layer (EBL). The electron transport region may include at least one selected from a hole blocking layer (HBL), an electron transport layer (ETL), and an electron injection layer (EIL).

[0130] The hole transport region may have a single-layered structure formed of a single material, a single-layered structure formed of a plurality of different materials, or a multi-layered structure having a plurality of layers formed of a plurality of different materials.


[0131] For example, the hole transport region may have a single-layered structure formed of a plurality of different materials, or a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole injection layer/hole transport layer/buffer layer, a structure of hole transport layer/buffer layer, or a structure of hole injection layer/hole transport layer/electron blocking layer, wherein layers of each structure are sequentially stacked from the first electrode **110** in this stated order.




[0132] When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode **110** by using various methods, e.g., vacuum deposition, spin coating casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, or laser-induced thermal imaging.

[0133] When a hole injection layer is formed by vacuum deposition, e.g., the vacuum deposition may be performed at a temperature of a deposition temperature of about 100 to about 500° C., at a vacuum degree of about 10^{-8} to about 10^{-3} torr, and/or at a deposition rate of about 0.01 to about 100 Å/sec in consideration of a compound for a hole injection layer to be deposited, and the structure of a hole injection layer to be formed.

[0134] When a hole injection layer is formed by spin coating, the spin coating may be performed at a coating rate of about 2,000 rpm to about 5,000 rpm, and/or at a temperature of about 80° C. to 200° C. in consideration of a compound for a hole injection layer to be deposited, and the structure of a hole injection layer to be formed.

[0135] As a hole injection material, a suitable hole injection material may be used, and examples may include N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine (DNTPD), a phthalocyanine compound, such as a copper phthalocyanine, 4,4',4''-tris (3-methylphenylphenylamino) triphenylamine [m-MTDATA], N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB), TDATA, 2-TNATA, polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), and (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS).





[0136] A hole transport layer may be formed on the first electrode **110** or the hole injection layer by using various methods, e.g., vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging (LITI). When the hole transport layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the hole transport layer may be the same as the deposition and coating conditions for the hole injection layer.

[0137] A thickness of the hole transport region may be in a range of about 100 Å to about 10,000 Å, e.g., about 100 Å to about 1,000 Å. When the hole transport region includes both a hole injection layer and a hole transport layer, a thickness of the hole injection layer may be in a range of about 100 Å to about 10,000 Å, e.g., about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may be in a range of about 50 Å to about 2,000 Å, e.g., about 100 Å to about 1,500 Å. When the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transporting characteristics may be obtained without a substantial increase in driving voltage.

[0138] The hole transport region may further include, in addition to the amine-based compound represented by Formula 1, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or unhomogeneously dispersed in the hole transport region.

[0139] The charge-generation material may be, e.g., a p-dopant. The p-dopant may be one selected from a quinone derivative, a metal oxide, and a cyano group-containing compound. Examples of the p-dopant may include a quinone derivative, such as tetracyanoquinonodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ); a metal oxide, such as a tungsten oxide or a molybdenum oxide, and Compound HT-D1 illustrated below.







[0140] The hole transport region may further include, in addition to the hole injection layer and the hole transport layer, at least one of a buffer layer and an electron blocking layer. Since the buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, light-emission efficiency of a formed organic light-emitting device may be improved. For use as a material included in the buffer layer, materials that are included in the hole transport region may be used. The electron blocking layer prevents injection of electrons from the electron transport region.

[0141] An emission layer may be formed on the first electrode **110** or the hole transport region by using various methods, e.g., vacuum deposition, spin coating, casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When an emission layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the emission may be the same as those for the hole injection layer.


[0142] When the organic light-emitting device **10** is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, or a blue emission layer, according to a sub pixel. In an implementation, the emission layer may have a stacked structure of a red emission layer, a green emission layer, and a blue emission layer, or may include a red-light emission material, a green-light emission material, and a blue-light emission material, which are mixed with each other in a single layer, to emit white light.

[0143] The emission layer may include a host and a dopant.

[0144] The host may include at least one selected from TPBi, TBADN, ADN (also referred to as "DNA"), CBP, CDBP, and TCP:



[0145] In an implementation, the host may include a compound represented by Formula 301 below.



<Formula 301>

[0146] In Formula 301,

[0147] Ar_{301} may be selected from

[0148] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene; and

[0149] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, monovalent non-aromatic condensed heteropolycyclic group, and $-\text{Si}(\text{Q}_{301})(\text{Q}_{302})(\text{Q}_{303})$ (Q_{301} to Q_{303} may be each independently selected from a hydrogen, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_6 - C_{60} aryl group, and a C_1 - C_{60} heteroaryl group);

[0150] a description of L_{301} may be understood by referring to the description provided in connection with L_1 ;

[0151] R_{301} may be selected from

[0152] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group;

[0153] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a

pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

[0154] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0155] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

[0156] x_{b1} may be selected from 0, 1, 2, and 3;

[0157] x_{b2} may be selected from 1, 2, 3, and 4.

[0158] In Formula 301,

[0159] L_{301} may be selected from

[0160] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, and a chrysenylene group; and

[0161] a phenylene group, a naphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenanthrenylene group, an anthracenylenylene group, a pyrenylene group, and a chrysenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

[0162] R_{301} may be selected from

[0163] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group;

[0164] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a


sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

[0165] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

[0166] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group.

[0167] For example, the host may include a compound represented by Formula 301A below.


<Formula 301A>




[0168] Descriptions of substituents of Formula 301A may be understood by referring to the descriptions of similar groups provided herein.

[0169] The compound represented by Formula 301 may include at least one of Compounds H1 to H42.


H1




H2




-continued




H3




H4




H5



H6




H7




H8


-continued




H9




H10



H11




H12




H13

-continued


H14




H15




H16



H17




H18




-continued


H19




H20




H21



H22




H23




-continued

H24




-continued


H29




H25




H30



H26




H31




H32



H27



H33




H28




-continued

H34




-continued


H37




H35




H38




H36



H39




-continued




H40


[0170] In an implementation, the host may include at least one of Compounds H43 to H49 below.




H43




H41



H44







H42



H45

-continued




[0171] The dopant may include at least one selected from a fluorescent dopant and a phosphorescent dopant.

H46

[0172] The phosphorescent dopant may include an organo-metallic complex represented by Formula 401 below.

<Formula 401>



H47

[0173] In Formula 401,

[0174] M may be selected from iridium (Ir), platinum (Pt), osmium (Os), titanium (Ti), zirconium

[0175] (Zr), hafnium (Hf), europium (Eu), terbium (Tb), and thulium (Tm);

[0176] X₄₀₁ to X₄₀₄ may each independently be nitrogen or carbon;

[0177] rings A₄₀₁ and A₄₀₂ may each independently be selected from a substituted or unsubstituted benzene, a substituted or unsubstituted naphthalene, a substituted or unsubstituted fluorene, a substituted or unsubstituted spiro-fluorene, a substituted or unsubstituted indene, a substituted or unsubstituted pyrrole, a substituted or unsubstituted thiophene, a substituted or unsubstituted furan, a substituted or unsubstituted imidazole, a substituted or unsubstituted pyrazole, a substituted or unsubstituted thiazole, a substituted or unsubstituted isothiazole, a substituted or unsubstituted oxazole, a substituted or unsubstituted isoxazole, a substituted or unsubstituted pyridine, a substituted or unsubstituted pyrazine, a substituted or unsubstituted pyrimidine, a substituted or unsubstituted pyridazine, a substituted or unsubstituted quinoline, a substituted or unsubstituted isoquinoline, a substituted or unsubstituted benzoquinoline, a substituted or unsubstituted quinoxaline, a substituted or unsubstituted quinazoline, a substituted or unsubstituted carbazole, a substituted or unsubstituted benzimidazole, a substituted or unsubstituted benzofuran, a substituted or unsubstituted benzothiophene, a substituted or unsubstituted isobenzothiophene, a substituted or unsubstituted benzoxazole, a substituted or unsubstituted isobenzoxazole, a substituted or unsubstituted triazole, a substituted or unsubstituted oxadiazole, a substituted or unsubstituted triazine, a substituted or unsubstituted dibenzofuran, and a substituted or unsubstituted dibenzothiophene; and

H49

[0178] at least one substituent of the substituted benzene, substituted naphthalene, substituted fluorene, substituted spiro-fluorene, substituted indene, substituted pyrrole, substituted thiophene, substituted furan, substituted imidazole, substituted pyrazole, substituted thiazole, substituted isothiazole, substituted oxazole, substituted isoxazole, substituted pyridine, substituted pyrazine, substituted pyrimidine, substituted pyridazine, substituted quinoline, substituted isoquinoline, substituted benzoquinoline, substituted quinoxaline, substituted quinazoline, substituted carbazole, substituted benzimidazole, substituted benzofuran, substituted benzothiophene, substituted isobenzothiophene, substituted benzoxazole, substituted isobenzoxazole, substituted triazole, substituted oxadiazole, substituted triazine, substituted dibenzofuran, and substituted dibenzothiophene may be selected from

[0179] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0180] a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkenyl group, a C₁-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₄₀₁)(Q₄₀₂), —Si(Q₄₀₃)(Q₄₀₄)(Q₄₀₅), and —B(Q₄₀₆)(Q₄₀₇);

[0181] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0182] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —N(Q₄₁₁)(Q₄₁₂), —Si(Q₄₁₃)(Q₄₁₄)(Q₄₁₅) and —B(Q₄₁₆)(Q₄₁₇); and

[0183] —N(Q₄₂₁)(Q₄₂₂), —Si(Q₄₂₃)(Q₄₂₄)(Q₄₂₅), and —B(Q₄₂₆)(Q₄₂₇);

[0184] L₄₀₁ may be an organic ligand;

[0185] xc1 may be 1, 2, or 3; and

[0186] xc2 may be 0, 1, 2, or 3.

[0187] Q₄₀₁ to Q₄₀₇, Q₄₁₁ to Q₄₁₇, and Q₄₂₁ to Q₄₂₇ may be understood by referring to the descriptions of Q groups provided herein.


[0188] L₄₀₁ may be a monovalent, divalent, or trivalent organic ligand. For example, L₄₀₁ may be selected from a halogen ligand (for example, Cl or F), a diketone ligand (for example, acetylacetonate, 1,3-diphenyl-1,3-propanedionate, 2,2,6,6-tetramethyl-3,5-heptanedionate, or hexafluoroacetate), a carboxylic acid ligand (for example, picolinate, dimethyl-3-pyrazolecarboxylate, or benzoate), a carbon monoox-

ide ligand, an isonitrile ligand, a cyano ligand, and a phosphorous ligand (for example, phosphine, and phosphite).

[0189] When A₄₀₁ in Formula 401 has two or more substituents, the substituents of A₄₀₁ may bind to each other to form a saturated or unsaturated ring.

[0190] When A₄₀₁ in Formula 402 has two or more substituents, the substituents of A₄₀₂ may bind to each other to form a saturated or unsaturated ring.


[0191] When xc1 in Formula 401 is two or more, a plurality of ligands




in Formula 401 may be identical or different. When xc1 in Formula 401 is two or more, A₄₀₁ and A₄₀₂ may be respectively directly connected to A₄₀₁ and A₄₀₂ of other neighboring ligands with or without a linker (for example, a C₁-C₅ alkylene, or —N(R')— (wherein R' may be a C₁-C₁₀ alkyl group or a C₆-C₂₀ aryl group) or —C(=O)—) therebetween.

[0192] The phosphorescent dopant may include at least one of Compounds PD1 to PD74 below.


PD1








PD2



PD3




-continued




-continued

PD4




PD9

PD5




PD10

PD6




PD11

PD7








PD12

PD8




PD13

-continued




-continued

PD14




PD19

PD15




PD20

PD16




PD21

PD17



PD22


PD18



PD23


-continued

PD24




-continued


PD29




PD30




PD31




PD32




PD33




PD25




PD26




PD27




PD28




-continued




PD34




PD35



PD36




PD37




PD38


-continued




PD39




PD40



PD41









PD42




PD43

-continued




-continued

PD44




PD50

PD45




PD51

PD46




PD52

PD47




PD53

PD48




PD54

PD49




PD55

-continued




PD56


-continued




PD61




PD57




PD62




PD58




PD63




PD59



PD64








PD60




PD65

-continued




-continued

PD66




PD71

PD67




PD72

PD68



PD73


PD69



PD74


[0193] In some embodiments, the phosphorescent dopant may include PtOEP:

PD70





PtOEP


[0194] The fluorescent dopant may include at least one selected from DPAVB_i, BDAVB_i, TBPe, DCM, DCJT_B, Coumarin 6, and C545T.





DPVBi

DPAVB_i


TBPe



DCM


DCJT_B

Coumarin 6



C545T

[0195] In some embodiments, the fluorescent dopant may include a compound represented by Formula 501 below.



[0196] In Formula 501,

[0197] Ar_{501} may be selected from

[0198] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene;

[0199] a naphthalene, a heptalene, a fluorene, a spiro-fluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{501})(Q_{502})(Q_{503}) (Q_{501} to Q_{503} may be each independently selected from a hydrogen, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_6 - C_{60} aryl group, and a C_1 - C_{60} heteroaryl group);

[0200] Descriptions of L_{501} to L_{503} are the same as the descriptions provided herein in connection with L_{301} ;

[0201] R_{501} and R_{502} may each independently be selected from:

[0202] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, or a dibenzothiophenyl group; or

[0203] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl


group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, or a dibenzothiophenyl group;

[0204] x_{d1} to x_{d3} may each independently be selected from 0, 1, 2, and 3; and


[0205] x_{d4} may be selected from 1, 2, 3, and 4.

[0206] The fluorescent dopant may include at least one of Compounds FD1 to FD9.


FD1



FD2




-continued



FD3


-continued

FD5





FD6


FD4




FD7



-continued



FD9



[0207] An amount of the dopant in the emission layer may be, e.g., about 0.01 to about 15 parts by weight, based on 100 parts by weight of the host.

[0208] A thickness of the emission layer may be in a range of about 100 Å to about 1,000 Å, e.g., about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.

[0209] Then, an electron transport region may be disposed on the emission layer.

[0210] The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer (ETL), and an electron injection layer.


[0211] For example, the electron transport region may have a structure of electron transport layer/electron injection layer or a structure of hole blocking layer/electron transport layer/electron injection layer, wherein layers of each structure are sequentially stacked from the emission layer in the stated order.

[0212] According to an embodiment, the organic layer 150 of the organic light-emitting device may include an electron transport region disposed between the emission layer and the second electrode 190.


[0213] The electron transport region may include a hole blocking layer. The hole blocking layer may be formed, when the emission layer includes a phosphorescent dopant, to prevent diffusion of excitons or holes into an electron transport layer.

[0214] When the electron transport region includes a hole blocking layer, the hole blocking layer may be formed on the emission layer by using various methods, such as vacuum deposition, spin coating casting, a Langmuir-Blodgett (LB) method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When the hole blocking layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the hole blocking layer may be determined by referring to the deposition and coating conditions for the hole injection layer.

[0215] The hole blocking layer may include, for example, at least one of BCP and Bphen.



BCP




Bphen

[0216] A thickness of the hole blocking layer may be in a range of about 20 Å to about 1,000 Å, e.g., about 30 Å to about 300 Å. When the thickness of the hole blocking layer is within these ranges, the hole blocking layer may have excellent hole blocking characteristics without a substantial increase in driving voltage.

[0217] The electron transport region may include an electron transport layer. The electron transport layer may be formed on the emission layer or the hole blocking layer by using various methods, such as vacuum deposition, spin coating casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When an electron transport layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the electron transport layer may be the same as the deposition and coating conditions for the hole injection layer.

[0218] According to an embodiment, the organic layer 150 of the organic light-emitting device may include an electron transport region disposed between the emission layer and the second electrode 190. The electron transport region may include at least one selected from an electron transport layer and an electron injection layer.

[0219] The electron transport layer may further include at least one selected from BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ.



[0220] In an implementation, the electron transport layer may include at least one compound selected from a compound represented by Formula 601 and a compound represented by Formula 602 illustrated below.



[0221] In Formula 601,

[0222] Ar_{601} may be selected from

[0223] a naphthalene, a heptalene, a fluorene, a spirofluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene, a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene;

[0224] a naphthalene, a heptalene, a fluorene, a spirofluorene, a benzofluorene, a dibenzofluorene, a phenalene, a phenanthrene, an anthracene, a fluoranthene, a triphenylene,

a pyrene, a chrysene, a naphthacene, a picene, a perylene, a pentaphene, and an indenoanthracene, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{301})(Q_{302})(Q_{303}) (Q_{301} to Q_{303} may be each independently selected from a hydrogen, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, and a $\text{C}_2\text{-C}_{60}$ heteroaryl group);

[0225] descriptions of L_{601} may be understood by referring to the descriptions provided in connection with L_{301} ;

[0226] E_{601} may be selected from

[0227] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazoyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group; and


[0228] a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazoyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{20}$ alkyl group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a

cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzo-carbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

[0229] xe1 may be selected from 0, 1, 2, and 3; and

[0230] xe2 may be selected from 1, 2, 3, and 4.

<Formula 602>



[0231] In Formula 602,

[0232] X₆₁₁ may be N or C-(L₆₁₁)_{xe611}-R₆₁₁, X₆₁₂ may be N or C-(L₆₁₂)_{xe612}-R₆₁₂, X₆₁₃ may be N or C-(L₆₁₃)_{xe613}-R₆₁₃, and at least one selected from X₆₁₁ to X₆₁₃ may be N;

[0233] L₆₁₁ to L₆₁₆ may be understood by referring to the description provided herein in connection with L₃₀₁;

[0234] R₆₁₁ and R₆₁₆ may each independently be selected from

[0235] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and


[0236] a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzo-fluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group, each substituted with at least one selected from a

deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and


[0237] xe611 to xe616 may be each independently selected from 0, 1, 2, and 3.

[0238] The compound represented by Formula 601 and/or the compound represented by Formula 602 may each be selected from Compounds ET1 to ET15 illustrated below.

ET1




ET2




-continued

ET3




-continued


ET6



ET4





ET7




ET8

ET5




-continued




ET9

-continued




ET11

ET12




ET10

ET13




-continued

ET14



ET15




[0239] A thickness of the electron transport layer may be in a range of about 100 Å to about 1,000 Å, e.g., about 150 Å to about 500 Å. When the thickness of the electron transport layer is within the range described above, the electron transport layer may have satisfactory electron transport characteristics without a substantial increase in driving voltage.


[0240] In an implementation, the electron transport layer may further include, in addition to the materials described above, a metal-containing material.

[0241] The metal-containing material may include a Li complex. The Li complex may include, e.g., Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.

ET-D1



ET-D2



[0242] The electron transport region may include an electron injection layer that allows electrons to be easily provided from the second electrode 190.

[0243] The electron injection layer may be formed on the electron transport layer by using various methods, e.g., vacuum deposition, spin coating casting, a LB method, ink-jet printing, laser-printing, or laser-induced thermal imaging. When an electron injection layer is formed by vacuum deposition or spin coating, deposition and coating conditions for the electron injection layer may be the same as those for the hole injection layer.

[0244] The electron injection layer may include at least one selected from, LiF, NaCl, CsF, Li₂O, BaO, and LiQ.

[0245] A thickness of the electron injection layer may be in a range of about 1 Å to about 100 Å, e.g., about 3 Å to about 90 Å. When the thickness of the electron injection layer is within the range described above, the electron injection layer may have satisfactory electron injection characteristics without a substantial increase in driving voltage.

[0246] The second electrode 190 may be disposed on the organic layer 150 having such a structure. The second electrode 190 may be a cathode which is an electron injection electrode, and in this regard, a material for the second electrode 190 may be selected from metal, an alloy, an electrically conductive compound, and a mixture thereof, which have a relatively low work function. Examples of the material for the second electrode 190 may include lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag). In an implementation, the material for forming the second electrode 190 may be ITO or IZO. The second electrode 190 may be a reflective electrode, a semi-transmissive electrode, or a transmissive electrode.

[0247] Hereinbefore, the organic light-emitting device has been described with reference to FIG. 1.

[0248] A C₁-C₆₀ alkyl group used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms, and detailed examples thereof are a methyl group, an ethyl group, a propyl group, an isobutyl group, a sec-butyl group, a ter-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0249] A C₁-C₆₀ alkoxy group used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group), and detailed examples thereof are a methoxy group, an ethoxy group, and an isopropoxy group.

[0250] A C₂-C₆₀ alkenyl group used herein refers to a hydrocarbon group having at least one carbon double bond in the middle or at the terminal of the C₂-C₆₀ alkyl group, and detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0251] A C₂-C₆₀ alkynyl group used herein refers to a hydrocarbon group having one carbon triple bond in the middle or at the terminal of the C₂-C₆₀ alkyl group, and detailed examples thereof are an ethynyl group, and a propynyl group. A C₂-C₆₀ alkynylene group used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0252] A C₃-C₁₀ cycloalkyl group used herein refers to a monovalent hydrocarbon monocyclic group having 3 to 10 carbon atoms, and detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclooctyl group, a cyclononyl group, and a cyclodecyl group.

pyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C_3 - C_1 cycloalkylene group used herein refers to a divalent group having the same structure as the C_3 - C_{10} cycloalkyl group.

[0253] A C_1 - C_{10} heterocycloalkyl group used herein refers to a monovalent monocyclic group having at least one hetero atom selected from N, O, P, and S as a ring-forming atom and 1 to 10 carbon atoms, and detailed examples thereof are a tetrahydrofuranyl group, and a tetrahydrothiophenyl group. A C_1 - C_{10} heterocycloalkylene group used herein refers to a divalent group having the same structure as the C_1 - C_{10} heterocycloalkyl group.

[0254] A C_3 - C_{10} cycloalkenyl group used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof and does not have aromaticity, and detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C_3 - C_{10} cycloalkenylene group used herein refers to a divalent group having the same structure as the C_3 - C_{10} cycloalkenyl group.

[0255] A C_1 - C_{10} heterocycloalkenyl group used herein refers to a monovalent monocyclic group that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, 1 to 10 carbon atoms, and at least one double bond in its ring. Detailed examples of the C_1 - C_{10} heterocycloalkenyl group are a 2,3-hydrofuranyl group and a 2,3-hydrothiophenyl group. A C_1 - C_{10} heterocycloalkenylene group used herein refers to a divalent group having the same structure as the C_1 - C_{10} heterocycloalkenyl group.

[0256] A C_6 - C_{60} aryl group used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C_6 - C_{60} arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C_6 - C_{60} aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C_6 - C_{60} aryl group and the C_6 - C_{60} arylene group each include two or more rings, the rings may be fused to each other.

[0257] A C_1 - C_{60} heteroaryl group used herein refers to a monovalent group having a carbocyclic aromatic system that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. A C_1 - C_{60} heteroarylene group used herein refers to a divalent group having a carbocyclic aromatic system that has at least one hetero atom selected from N, O, P, and S as a ring-forming atom, and 1 to 60 carbon atoms. Examples of the C_1 - C_{60} heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C_1 - C_{60} heteroaryl group and the C_1 - C_{60} heteroarylene group each include two or more rings, the rings may be fused to each other.

[0258] A C_6 - C_{60} aryloxy group used herein indicates $-\text{OA}_{102}$ (wherein A_{102} is the C_6 - C_{60} aryl group), and a C_6 - C_{60} arylthio group indicates $-\text{SA}_{103}$ (wherein A_{103} is the C_6 - C_{60} aryl group).

[0259] A monovalent non-aromatic condensed polycyclic group used herein refers to a monovalent group (for example, having 8 to 60 carbon atoms) that has two or more rings condensed to each other, only carbon atoms as a ring forming atom, and non-aromaticity in the entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. A divalent non-aromatic condensed polycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0260] A monovalent non-aromatic condensed heteropolycyclic group used herein refers to a monovalent group (for example, having 2 to 60 carbon atoms) that has two or more rings condensed to each other, has a heteroatom selected from N, O, P, and S, other than carbon atoms, as a ring forming atom, and has non-aromaticity in the entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0261] at least one substituent of the substituted C_6 - C_{20} aromatic ring, substituted C_3 - C_{10} cycloalkylene group, substituted C_1 - C_{10} heterocycloalkylene group, substituted C_3 - C_{10} cycloalkenylene group, substituted C_1 - C_{10} heterocycloalkenylene group, substituted C_6 - C_{60} arylene group, substituted C_1 - C_{60} heteroarylene group, substituted a divalent non-aromatic condensed polycyclic group, substituted a divalent non-aromatic condensed heteropolycyclic group, substituted C_3 - C_{10} cycloalkyl group, substituted C_1 - C_{10} heterocycloalkyl group, substituted C_3 - C_{10} cycloalkenyl group, substituted C_1 - C_{10} heterocycloalkenyl group, substituted C_6 - C_{60} aryl group, substituted C_1 - C_{60} heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

[0262] a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group;

[0263] a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkenyl group, a C_1 - C_{60} alkynyl group, and a C_1 - C_{60} alkoxy group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{N}(\text{Q}_{11})$ (Q_{12}), $-\text{Si}(\text{Q}_{13})(\text{Q}_{14})(\text{Q}_{15})$, and $-\text{B}(\text{Q}_{16})(\text{Q}_{17})$;

[0264] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0265] a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group,

a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), and —B(Q₂₄)(Q₂₅); and

[0266] —Si(Q₃₁)(Q₃₂)(Q₃₃), and —B(Q₃₄)(Q₃₅);

[0267] Q₁₁ to Q₁₅, Q₂₁ to Q₂₅, and Q₃₁ to Q₃₅ may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0268] The term “Ph” used herein refers to a phenyl group, the term “Me” used herein refers to a methyl group, the term “Et” used herein refers to an ethyl group, and the term “ter-Bu” or “Bu” used herein refers to a tert-butyl group.

[0269] Hereinafter, an organic light-emitting device according to an embodiment will be described in detail with reference to Synthesis Examples and Examples. The wording “B was used instead of A” used in describing Synthesis Examples means that a molar equivalent of A was identical to a molar equivalent of B.


[0270] The following Examples and Comparative Examples are provided in order to highlight characteristics of one or more embodiments, but it will be understood that the Examples and Comparative Examples are not to be construed as limiting the scope of the embodiments, nor are the Comparative Examples to be construed as being outside the scope of the embodiments. Further, it will be understood that the embodiments are not limited to the particular details described in the Examples and Comparative Examples.

EXAMPLES


Synthesis Example 1

Synthesis of Compound 3

[0271]



-continued



[0272] Synthesis of Intermediate 1-1




[0273] 10 g of Starting Material 1 was diluted in 150 ml of THF, and then the temperature was decreased to -78°C . At -78°C , n-BuLi (2.5 M, 14.7 ml) was slowly added dropwise thereto. One hour after the addition, 3.8 g of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was slowly added thereto. Three minutes after the addition, the temperature was slowly raised to ambient temperature, and then, the result was stirred for 6 hours. The reaction was quenched by using a saturated ammonium chloride aqueous solution, and an organic layer was separated therefrom, and then, dried using an anhydrous magnesium sulfate and subjected to concentration under reduced pressure. The residual was separation-purified by silica gel column chromatography to obtain Intermediate 1-1 (9.9 g, yield: 78%).

[0274] Synthesis of Compound 3


[0275] Compound 3 (yield: 91%) was prepared in the same manner used to synthesize Intermediate 1-1, except that 3 g of Intermediate 1-1 was used instead of Starting Material 1 and 4.5 g of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 3.8 g of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

Synthesis Example 2
Synthesis of Compound 21

[0276]



-continued



21

[0277] Synthesis of Intermediate 2-1

[0278] 10 g of Starting Material 2 was diluted in 150 ml of THF, and then the temperature was decreased to -78°C . At -78°C , $n\text{-BuLi}$ (2.5 M, 14.7 ml) was slowly added dropwise thereto. One hour after the addition, 3 g of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborane was slowly added thereto. Three minutes after the addition, the temperature was slowly raised to ambient temperature, and then, the result was stirred for 6 hours. The reaction was quenched by using a saturated ammonium chloride aqueous solution, and an organic layer was separated therefrom, and then, dried using an anhydrous magnesium sulfate and subjected to concentration under reduced pressure. The residual was separation-purified by silica gel column chromatography to obtain Intermediate 2-1.

[0279] Synthesis of Intermediate 2-2

[0280] 9.9 g of Intermediate 2-1 and 4.8 g of 1,3,5-tribromo benzene were diluted in 120 ml of THF, and then, 1.5 g of $\text{Pd}(\text{PPh}_3)_4$ and 11 g of potassium carbonate were added thereto, and the result was stirred at a temperature of 60°C . 12 hours after the stirring, the temperature was decreased to ambient temperature, and then, an extraction process was

performed thereon three times by using ethyl acetate. A separated organic layer was dried by using anhydrous magnesium sulfate and distilled under reduced pressure, and the residual was separation-purified by silica gel column chromatography to obtain Intermediate 2-2.

[0281] Synthesis of Intermediate 2-3




[0282] Intermediate 2-3 was obtained in the same manner as used to synthesize Intermediate 1-1, except that 3 g of Intermediate 2-2 was used instead of Starting Material 2, and 3.8 g of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0283] Synthesis of Compound 21

[0284] Compound 21 (yield: 90.1%) was obtained in the same manner as used to synthesize Intermediate 1-1, except that 3 g of Intermediate 2-3 was used instead of Starting Material 2, and 4.5 g of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-isopropoxy-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

Synthesis Example 3
Synthesis of Compound 29

[0285]





29

[0286] Synthesis of Intermediate 3-1

[0287] Intermediate 3-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 3 was used instead of Starting Material 2.

[0288] Synthesis of Intermediate 3-2

[0289] Intermediate 3-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 3-1 was used instead of Intermediate 2-1.

[0290] Synthesis of Intermediate 3-3


[0291] Intermediate 3-3 was synthesized in the same manner as in synthesizing Intermediate 2-3, except that Intermediate 3-2 was used instead of Intermediate 2-2.

[0292] Synthesis of Compound 29



[0293] Compound 29 (yield: 90.2%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 3-3 was used instead of Intermediate 2-3.

Synthesis Example 4 Synthesis of Compound 40

[0294]



-continued



40

[0295] Synthesis of Intermediate 4-1

[0296] Intermediate 4-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 4 was used instead of Starting Material 2.

[0297] Synthesis of Intermediate 4-2

[0298] Intermediate 4-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 4-1 was used instead of Intermediate 2-1.

[0299] Synthesis of Intermediate 4-3


[0300] Intermediate 4-3 was synthesized in the same manner as in synthesizing Intermediate 2-3, except that Intermediate 4-2 was used instead of Intermediate 2-2.

[0301] Synthesis of Compound 40

[0302] Compound 40 (yield: 86.6%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 4-3 was used instead of Intermediate 2-3.

Synthesis Example 5
Synthesis of Compound 49

[0303]



[0304] Synthesis of Intermediate 5-1

[0305] Intermediate 5-1 was prepared in the same manner as used to synthesize Intermediate 1-1, except that Starting Material 5 was used instead of Starting Material 1, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5,-tetramethyl-1,3,2-diox-




aborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane.

[0306] Synthesis of Compound 49


[0307] Compound 49 (yield: 85.1%) was synthesized in the same manner as used to synthesize Compound 3, except that Intermediate 5-1 was used instead of Intermediate 1-1.

Synthesis Example 6
Synthesis of Compound 56

[0308]



-continued



56

[0309] Synthesis of Intermediate 6-1

[0310] Intermediate 6-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 6 was used instead of Starting Material 2.

[0311] Synthesis of Intermediate 6-2

[0312] Intermediate 6-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 6-1 was used instead of Intermediate 2-1.

[0313] Synthesis of Intermediate 6-3

[0314] Intermediate 6-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 6-2 was used instead of Intermediate 2-2, and

2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0315] Synthesis of Compound 56

[0316] Compound 56 (yield: 88.5%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 6-3 was used instead of Intermediate 2-3.


Synthesis Example 7

Synthesis of Compound 57



[0317]



-continued



7-3



57

[0318] Synthesis of Intermediate 7-1

[0319] Intermediate 7-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 7 was used instead of Starting Material 2.

[0320] Synthesis of Intermediate 7-2

[0321] Intermediate 7-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 7-1 was used instead of Intermediate 2-1.

[0322] Synthesis of Intermediate 7-3

[0323] Intermediate 7-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Interme-



diolate 7-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

[0324] Synthesis of Compound 57


[0325] Compound 57 (yield: 92.4%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 7-3 was used instead of Intermediate 2-3.

Synthesis Example 8
Synthesis of Compound 59


[0326]



8-2



8-3



59

[0327] Synthesis of Intermediate 8-1

[0328] Intermediate 8-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 8 was used instead of Starting Material 2.

[0329] Synthesis of Intermediate 8-2

[0330] Intermediate 8-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 8-1 was used instead of Intermediate 2-1.

[0331] Synthesis of Intermediate 8-3

[0332] Intermediate 8-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 8-2 was used instead of Intermediate 2-2, and

2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0333] Synthesis of Compound 59

[0334] Compound 59 (yield: 87.4%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 8-3 was used instead of Intermediate 2-3.


Synthesis Example 9

Synthesis of Compound 62



[0335]



-continued



9-3



62

[0336] Synthesis of Intermediate 9-1

[0337] Intermediate 9-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 9 was used instead of Starting Material 2.

[0338] Synthesis of Intermediate 9-2

[0339] Intermediate 9-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 9-1 was used instead of Intermediate 2-1, and 1,2,4-tribromobenzene was used instead of 1,3,5-tribromobenzene.

[0340] Synthesis of Intermediate 9-3




[0341] Intermediate 9-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 9-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0342] Synthesis of Compound 62

[0343] Compound 62 (yield: 88.6%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 9-3 was used instead of Intermediate 2-3.

Synthesis Example 10
Synthesis of Compound 63

[0344]





63

[0345] Synthesis of Intermediate 10-1

[0346] Intermediate 10-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 10 was used instead of Starting Material 2.

[0347] Synthesis of Intermediate 10-2

[0348] Intermediate 10-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 10-1 was used instead of Intermediate 2-1, and 1,2,4-tribromobenzene was used instead of 1,3,5-tribromobenzene.

[0349] Synthesis of Intermediate 10-3

[0350] Intermediate 10-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 10-2 was used instead of Intermediate 2-2, and

2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0351] Synthesis of Compound 63


[0352] Compound 63 (yield: 85.1%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 10-3 was used instead of Intermediate 2-3.

Synthesis Example 11

Synthesis of Compound 70

[0353]





[0354] Synthesis of Intermediate 11-1

[0355] Intermediate 11-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 11 was used instead of Starting Material 2.

[0356] Synthesis of Intermediate 11-2

[0357] Intermediate 11-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 11-1 was used instead of Intermediate 2-1.

[0358] Synthesis of Intermediate 11-3

[0359] Intermediate 11-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 11-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.




[0360] Synthesis of Compound 70


[0361] Compound 70 (yield: 90.2%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 11-3 was used instead of Intermediate 2-3.

Synthesis Example 12

Synthesis of Compound 74

[0362]





74

[0363] Synthesis of Intermediate 12-1

[0364] Intermediate 12-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 12 was used instead of Starting Material 2.

[0365] Synthesis of Intermediate 12-2

[0366] Intermediate 12-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 12-1 was used instead of Intermediate 2-1.

[0367] Synthesis of Intermediate 12-3

[0368] Intermediate 12-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 12-2 was used instead of Intermediate 2-2, and

2-(dibenzo[b,d]furan-4-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane.


[0369] Synthesis of Compound 74

[0370] Compound 74 (yield: 85.4%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 12-3 was used instead of Intermediate 2-3.

Synthesis Example 13


Synthesis of Compound 78

[0371]




12-2

-continued



12-3



74

[0372] Synthesis of Intermediate 13-1

[0373] Intermediate 13-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 13 was used instead of Starting Material 2.

[0374] Synthesis of Intermediate 13-2

[0375] Intermediate 13-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 13-1 was used instead of Intermediate 2-1.

[0376] Synthesis of Intermediate 13-3

[0377] Intermediate 13-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 13-2 was used instead of Intermediate 2-2, and

2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0378] Synthesis of Compound 78

[0379] Compound 78 (yield: 90.8%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 13-3 was used instead of Intermediate 2-3.

Synthesis Example 14


Synthesis of Compound 85

[0380]



14

14-1



[0381] Synthesis of Intermediate 14-1

[0382] Intermediate 14-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 14 was used instead of Starting Material 2.

[0383] Synthesis of Intermediate 14-2

[0384] Intermediate 14-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 14-1 was used instead of Intermediate 2-1.

[0385] Synthesis of Intermediate 14-3

[0386] Intermediate 14-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 14-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.




[0387] Synthesis of Compound 85

[0388] Compound 85 (yield: 86.1%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 14-3 was used instead of Intermediate 2-3.


Synthesis Example 15

Synthesis of Compound 89

[0389]



-continued



89

[0390] Synthesis of Intermediate 15-1

[0391] Intermediate 15-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 15 was used instead of Starting Material 2.

[0392] Synthesis of Intermediate 15-2

[0393] Intermediate 15-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 15-1 was used instead of Intermediate 2-1.

[0394] Synthesis of Intermediate 15-3

[0395] Intermediate 15-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 15-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5,-tetramethyl-1,3,2-diox-

aborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane.


[0396] Synthesis of Compound 89

[0397] Compound 89 (yield: 90.1%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 15-3 was used instead of Intermediate 2-3.

Synthesis Example 16

Synthesis of Compound 90


[0398]




16

16-1


-continued



16-2



16-3



[0399] Synthesis of Intermediate 16-1

[0400] Intermediate 16-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 16 was used instead of Starting Material 2.

[0401] Synthesis of Intermediate 16-2

[0402] Intermediate 16-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 16-1 was used instead of Intermediate 2-1.

[0403] Synthesis of Intermediate 16-3

[0404] Intermediate 16-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 16-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane.




[0405] Synthesis of Compound 90

[0406] Compound 90 (yield: 84.7%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 16-3 was used instead of Intermediate 2-3.

Synthesis Example 17

Synthesis of Compound 98

[0407]



[0408] Synthesis of Intermediate 17-1

[0409] Intermediate 17-1 was prepared in the same manner as used to synthesize Intermediate 1-1, except that Starting Material 17 was used instead of Starting Material 1, and 2-(dibenzo[b,d]furan-3-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0410] Synthesis of Compound 98

[0411] Compound 98 (yield: 87.2%) was synthesized in the same manner as used to synthesize Compound 3, except that Intermediate 17-1 was used instead of Intermediate 1-1.

Synthesis Example 18

Compound 102

[0412]



[0413] Synthesis of Intermediate 18-1

[0414] Intermediate 18-1 was prepared in the same manner as used to synthesize Intermediate 1-1, except that Starting Material 18 was used instead of Starting Material 1, and 2-(dibenzo[b,d]furan-3-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0415] Synthesis of Compound 102


[0416] Compound 102 (yield: 90.6%) was synthesized in the same manner as used to synthesize Compound 3, except that Intermediate 18-1 was used instead of Intermediate 1-1.

Synthesis Example 19

Synthesis of Compound 230

[0417]





[0418] Synthesis of Intermediate 19-1

[0419] Intermediate 19-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 19 was used instead of Starting Material 2.

[0420] Synthesis of Intermediate 19-2


[0421] Intermediate 19-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 19-1 was used instead of Intermediate 2-1, and 1,2,4-tribromobenzene was used instead of 1,3,5-tribromobenzene.

[0422] Synthesis of Intermediate 19-3

[0423] Intermediate 19-3 was synthesized in the same manner as in synthesizing Intermediate 2-3, except that Intermediate 19-2 was used instead of Intermediate 2-2.

[0424] Synthesis of Compound 230



[0425] Compound 230 (yield: 79%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 19-3 was used instead of Intermediate 2-3, and Compound X1 was used instead of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.




Synthesis Example 20

Synthesis of Compound 244

[0426]





[0427] Synthesis of Intermediate 20-1

[0428] Intermediate 20-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 20 was used instead of Starting Material 2.

[0429] Synthesis of Intermediate 20-2

[0430] Intermediate 20-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 20-1 was used instead of Intermediate 2-1, and 1,2,4-tribromobenzene was used instead of 1,3,5-tribromobenzene.

[0431] Synthesis of Intermediate 20-3

[0432] Intermediate 20-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Intermediate 20-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-3-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.


[0433] Synthesis of Compound 244


[0434] Compound 244 (yield: 81%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 20-3 was used instead of Intermediate 2-3, and Compound X1 was used instead of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

Synthesis Example 21

Synthesis of Compound 271

[0435]





[0436] Synthesis of Intermediate 21-1

[0437] Intermediate 20-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 21 was used instead of Starting Material 2.

[0438] Synthesis of Intermediate 21-2

[0439] Intermediate 21-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 21-1 was used instead of Intermediate 2-1, and 1,2,4-tribromobenzene was used instead of 1,3,5-tribromobenzene.

[0440] Synthesis of Intermediate 21-3

[0441] Intermediate 21-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Interme-


diate 21-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane.

[0442] Synthesis of Compound 271

[0443] Compound 271 (yield: 83%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 21-3 was used instead of Intermediate 2-3, and Compound X2 was used instead of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

Synthesis Example 22
Synthesis of Compound 289

[0444]



[0445] Synthesis of Intermediate 22-1

[0446] Intermediate 22-1 was prepared in the same manner as used to synthesize Intermediate 1-1, except that Starting Material 22 was used instead of Starting Material 1, and 2-(dibenzo[b,d]furan-4-yl)-4,4,5,5,-tetramethyl-1,3,2-diox-

aborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5,-tetramethyl-1,3,2-dioxaborane.

[0447] Synthesis of Compound 289


[0448] Compound 289 (yield: 87%) was synthesized in the same manner as used to synthesize Compound 3, except that


Intermediate 22-1 was used instead of Intermediate 1-1, and Compound X3 was used instead of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

Synthesis Example 23

Synthesis of Compound 299

[0449]





299

[0450] Synthesis of Intermediate 23-1

[0451] Intermediate 23-1 was synthesized in the same manner as used in synthesizing Intermediate 2-1, except that Starting Material 23 was used instead of Starting Material 2.

[0452] Synthesis of Intermediate 23-2

[0453] Intermediate 23-2 was synthesized in the same manner as in synthesizing Intermediate 2-2, except that Intermediate 23-1 was used instead of Intermediate 2-1, and 1,2,4-tribromobenzene was used instead of 1,3,5-tribromobenzene.

[0454] Synthesis of Intermediate 23-3

[0455] Intermediate 23-3 was prepared in the same manner as used to synthesize Intermediate 2-3, except that Interme-

diolate 23-2 was used instead of Intermediate 2-2, and 2-(dibenzo[b,d]furan-3-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane was used instead of 2-(dibenzo[b,d]furan-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

[0456] Synthesis of Compound 299

[0457] Compound 299 (yield: 71%) was synthesized in the same manner as used to synthesize Compound 21, except that Intermediate 23-3 was used instead of Intermediate 2-3, and Compound X4 was used instead of 2-(9-phenyl-9H-carbazole-2-yl)-4,4,5,5-tetramethyl-1,3,2-dioxaborane.

[0458] The compounds synthesized according to Synthesis Examples 1-23 were confirmed by ¹H NMR and MS/FAB. Results thereof are shown in Table 1 below.

TABLE 1

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		found	calc.
Compound 3	8.21 (d, 1H), 8.03 (s, 1H), 7.95 (t, 1H), 7.91 (d, 1H), 7.84 (d, 1H), 7.77 (d, 1H), 7.64 (d, 1H), 7.53 (m, 2H), 7.32 (m, 1H), 7.26 (m, 2H), 7.05 (m, 2H), 6.83 (t, 1H), 6.64 (m, 2H), 6.32 (m, 1H), 5.85 (m, 1H), 3.21 (t, 1H)	702.23	702.86
Compound 21	8.21 (d, 1H), 8.09 (s, 1H), 7.87 (t, 2H), 7.81 (m, 1H), 7.74 (m, 1H), 7.61 (m, 1H), 7.56 (m, 3H), 7.39 (m, 3H), 7.23 (m, 5H), 7.15 (m, 2H), 7.02 (t, 1H), 6.94 (t, 1H), 6.74 (m, 1H), 6.62 (m, 1H), 6.45 (m, 1H), 6.23 (m, 2H), 5.87 (m, 2H), 3.16 (m, 2H)	854.32	855.05
Compound 29	8.22 (d, 1H), 8.02 (s, 1H), 7.75 (t, 1H), 7.54 (m, 2H), 7.35 (m, 4H), 7.09 (m, 5H), 6.91 (t, 1H), 6.74 (m, 2H), 6.2 (m, 2H), 5.8 (m, 2H), 3.21 (m, 2H)	957.15	956.38
Compound 40	8.210 (d, 1H), 8.07 (s, 1H), 7.91 (t, 1H), 7.83 (m, 3H), 7.62 (m, 3H), 7.57 (t, 1H), 7.51 (m, 5H), 7.32 (m, 5H), 7.23 (m, 1H), 7.03 (m, 5H), 6.93 (m, 1H), 6.64 (m, 2H), 6.32 (d, 2H), 6.22 (d, 1H), 6.12 (m, 5H), 3.84 (s, 1H), 3.67 (d, 1H)	778.95	778.30
Compound 49	8.27 (d, 1H), 8.10 (s, 1H), 7.97 (t, 1H), 7.90 (d, 1H), 7.81 (d, 1H), 7.68 (m, 3H), 7.57 (d, 1H), 7.53 (t, 1H), 7.48 (m, 5H), 7.25 (m, 7H), 7.28 (d, 1H), 7.05 (m, 4H), 6.95 (d, 2H), 6.62 (m, 2H), 6.23 (m, 4H)	639.23	639.78
Compound 56	8.25 (d, 1H), 8.14 (s, 1H), 8.08 (t, 1H), 7.98 (t, 1H), 7.89 (d, 1H), 7.88 (s, 1H), 7.84 (m, 2H), 7.79 (t, 1H), 7.77 (d, 1H), 7.74 (t, 1H), 7.72 (d, 1H), 7.55 (m, 7H), 7.31 (m, 5H), 7.19 (d, 1H), 7.13 (d, 1H), 7.04 (m, 2H), 6.63 (t, 1H), 6.58 (m, 2H), 6.24 (m, 2H)	778.30	778.95
Compound 57	8.24 (d, 1H), 8.14 (s, 1H), 8.08 (t, 1H), 7.82 (m, 6H), 7.59 (d, 1H), 7.49 (m, 7H), 7.30 (m, 3H), 7.19 (d, 1H), 7.30 (m, 4H), 6.87 (m, 3H), 6.65 (t, 2H), 6.15 (m, 2H)	728.23	728.89

TABLE 1-continued

Compound	¹ H NMR (CDCl ₃ , 400 MHz)	MS/FAB	
		found	calc.
Compound 59	8.24 (d, 1H), 8.14 (s, 1H), 8.08 (t, 1H), 7.98 (t, 1H), 7.89 (d, 1H), 7.84 (t, 1H), 7.74 (m, 3H), 7.45 (m, 12H), 7.32 (m, 6H), 7.19 (d, 1H), 6.82 (m, 4H), 6.66 (m, 2H)	880.37	881.09
Compound 62	8.23 (d, 1H), 8.13 (s, 1H), 7.95 (t, 1H), 7.92 (d, 1H), 7.88 (d, 1H), 7.83 (t, 2H), 7.74 (d, 1H), 7.71 (s, 1H), 7.66 (m, 12H), 7.31 (m, 7H), 7.09 (m, 4H), 7.00 (s, 1H), 6.66 (t, 1H), 6.20 (m, 3H)	778.24	778.95
Compound 63	8.23 (d, 1H), 8.13 (s, 1H), 7.94 (t, 1H), 7.91 (d, 1H), 7.88 (d, 1H), 7.73 (t, 2H), 7.54 (d, 1H), 7.70 (s, 1H), 7.62 (m, 12H), 7.29 (m, 7H), 7.01 (m, 4H), 6.92 (s, 1H), 6.61 (t, 1H), 6.24 (m, 3H)	778.28	778.95
Compound 70	8.24 (d, 1H), 8.14 (s, 1H), 8.08 (s, 1H), 7.89 (d, 1H), 7.82 (m, 3H), 7.74 (m, 2H), 7.65 (m, 2H), 6.55 (m, 14H), 7.2 (m, 4H), 7.19 (d, 1H), 7.06 (t, 1H), 6.84 (m, 2H), 6.65 (s, 1H), 6.21 (m, 2H)	880.31	881.09
Compound 74	8.22 (d, 1H), 8.13 (s, 1H), 8.05 (s, 1H), 7.91 (d, 1H), 7.81 (m, 3H), 7.74 (d, 1H), 7.59 (m, 2H), 7.50 (m, 6H), 7.09 (m, 4H), 6.97 (s, 1H), 6.75 (d, 1H), 6.64 (t, 1H), 6.41 (d, 1H), 6.18 (m, 2H), 5.82 (m, 2H), 3.15 (d, 1H)	854.33	855.05
Compound 78	8.22 (d, 1H), 8.12 (s, 1H), 8.02 (s, 1H), 7.89 (d, 1H), 7.80 (m, 3H), 7.69 (d, 1H), 7.54 (m, 2H), 7.47 (m, 6H), 7.09 (m, 4H), 6.91 (s, 1H), 6.82 (d, 1H), 6.74 (t, 1H), 6.52 (d, 1H), 6.24 (m, 2H), 5.71 (m, 2H), 3.17 (d, 1H)	880.32	881.09
Compound 85	8.22 (d, 1H), 8.17 (s, 1H), 8.14 (s, 1H), 8.02 (d, 1H), 7.84 (m, 6H), 7.78 (d, 1H), 7.74 (d, 1H), 7.66 (t, 1H), 7.57 (d, 1H), 7.51 (m, 6H), 7.43 (d, 1H), 7.35 (t, 1H), 7.27 (m, 3H), 7.19 (d, 1H), 7.01 (m, 5H), 6.63 (m, 2H), 6.05 (m, 4H)	778.29	778.95
Compound 89	8.22 (d, 1H), 8.10 (s, 1H), 7.92 (s, 1H), 7.91 (d, 1H), 7.88 (m, 2H), 7.86 (d, 2H), 7.84 (d, 2H), 7.82 (m, 2H), 7.80 (d, 1H), 7.72 (m, 2H), 7.51 (m, 12H), 7.31 (m, 6H), 7.19 (d, 1H), 7.16 (d, 1H), 7.07 (m, 3H), 6.98 (d, 1H), 6.65 (t, 1H), 6.37 (d, 1H), 6.25 (m, 1H), 3.89 (s, 1H)	828.21	829.01
Compound 90	8.89 (d, 1H), 8.61 (s, 1H), 8.46 (s, 1H), 8.21 (m, 2H), 7.90 (m, 3H), 7.77 (m, 4H), 7.52 (m, 6H), 7.32 (m, 6H), 7.21 (d, 1H), 7.05 (m, 4H), 6.89 (m, 4H), 6.65 (m, 2H), 6.16 (m, 4H)	841.82	842.03
Compound 98	8.23 (d, 1H), 8.15 (s, 1H), 8.06 (s, 1H), 7.94 (d, 1H), 7.86 (d, 1H), 7.84 (s, 1H), 7.80 (s, 1H), 7.69 (m, 2H), 7.57 (d, 1H), 7.55 (t, 1H), 7.51 (m, 4H), 7.47 (m, 4H), 7.38 (m, 5H), 7.29 (m, 2H), 7.20 (m, 2H), 7.08 (m, 2H), 6.98 (s, 1H), 6.85 (m, 2H), 6.67 (t, 1H), 6.27 (d, 2H)	702.67	702.86
Compound 102	8.24 (d, 1H), 8.15 (s, 1H), 8.06 (s, 1H), 7.97 (d, 1H), 7.84 (d, 1H), 7.71 (s, 1H), 7.69 (m, 2H), 7.56 (m, 4H), 7.50 (m, 4H), 7.48 (m, 6H), 7.45 (m, 4H), 7.38 (m, 6H), 7.30 (m, 3H), 7.23 (t, 1H), 7.19 (m, 4H), 7.04 (t, 1H), 6.98 (s, 1H), 6.93 (s, 1H), 6.84 (s, 1H), 6.61 (m, 2H), 5.98 (d, 1H)	804.40	804.99
Compound 230	8.24 (d, 1H), 8.14 (s, 1H), 8.06 (s, 1H), 7.92 (d, 1H), 7.84 (s, 1H), 7.76 (s, 1H), 7.61 (m, 2H), 7.55 (d, 1H), 7.53 (t, 1H), 7.51 (m, 4H), 7.41 (m, 9H), 7.28 (m, 2H), 7.20 (m, 2H), 7.06 (m, 2H), 6.95 (s, 1H), 6.84 (m, 2H), 6.66 (t, 1H), 6.36 (d, 2H)	855.33	855.05
Compound 244	8.24 (d, 1H), 8.13 (s, 1H), 8.08 (t, 1H), 7.86 (t, 1H), 7.88 (d, 1H), 7.83 (t, 1H), 7.74 (m, 3H), 7.41 (m, 11H), 7.31 (m, 6H), 7.21 (d, 1H), 6.79 (m, 4H), 6.55 (m, 2H)	855.31	855.05
Compound 271	8.23 (d, 1H), 8.14 (s, 1H), 8.07 (s, 1H), 7.89 (d, 1H), 7.81 (m, 3H), 7.74 (m, 2H), 7.65 (m, 2H), 6.49 (m, 14H), 7.12 (m, 4H), 7.18 (d, 1H), 7.06 (t, 1H), 6.83 (m, 2H), 6.61 (s, 1H), 6.20 (m, 2H)	830.31	830.00
Compound 289	8.23 (d, 1H), 8.13 (s, 1H), 7.94 (t, 1H), 7.91 (d, 1H), 7.88 (d, 1H), 7.83 (t, 2H), 7.71 (d, 1H), 7.68 (s, 1H), 7.62 (m, 6H), 7.29 (m, 3H), 7.10 (m, 4H), 7.04 (s, 1H), 6.63 (t, 1H), 6.17 (m, 2H)	728.28	728.89
Compound 299	8.23 (d, 1H), 8.13 (s, 1H), 8.07 (s, 1H), 7.89 (d, 1H), 7.86 (m, 3H), 7.84 (m, 2H), 7.69 (m, 2H), 7.49 (m, 12H), 7.11 (m, 6H), 7.18 (d, 1H), 7.05 (t, 1H), 6.61 (s, 1H), 6.20 (m, 2H)	948.36	948.15

Example 1

[0459] An ITO glass substrate (a product of Corning Co., Ltd) having a sheet resistance of 15 Ω/cm² and thickness of 1,200 Å was cut to a size of 50 mm×50 mm×0.7 mm, and then, sonicated by using isopropyl alcohol and pure water each for 5 minutes, and cleaned by the exposure to ultraviolet rays for 30 minutes, and then ozone, and the ITO glass substrate was mounted on a vacuum deposition apparatus.


[0460] 2-TNATA was deposited on the ITO anode substrate to form an hole injection layer having a thickness of 600 Å, and then, Compound 3 was deposited on the hole injection

layer to form a hole transport layer having a thickness of 300 Å.


[0461] 9,10-di(naphthalen-2-yl)anthracene (ADN) (as a host) and N,N,N',N'-tetraphenyl-pyrene-1,6-diamine (TPD) (as a dopant) were co-deposited on the hole transport layer at a weight ratio of 98:2 to form an emission layer having a thickness of 300 Å.

[0462] Thereafter, Alq₃ was deposited on the emission layer to form an electron transport layer having a thickness of 300 Å, and LiF was deposited on the electron transport layer to form an electron injection layer having a thickness of 10 Å, and Al was deposited on the electron injection layer to form a


cathode having a thickness of 3,000 Å, thereby completing the manufacture of an organic light-emitting device.



2-TNATA



ADN



TPD

Example 2

[0463] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 21 was used instead of Compound 3.

Example 3

[0464] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 29 was used instead of Compound 3.

Example 4

[0465] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 40 was used instead of Compound 3.

Example 5

[0466] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 49 was used instead of Compound 3.

Example 6

[0467] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 56 was used instead of Compound 3.

Example 7

[0468] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 57 was used instead of Compound 3.

Example 8

[0469] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 59 was used instead of Compound 3.

Example 9

[0470] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 62 was used instead of Compound 3.

Example 10

[0471] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 63 was used instead of Compound 3.

Example 11

[0472] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 70 was used instead of Compound 3.

Example 12

[0473] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 74 was used instead of Compound 3.

Example 13

[0474] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 78 was used instead of Compound 3.

Example 14

[0475] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 85 was used instead of Compound 3.

Example 15

[0476] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 89 was used instead of Compound 3.

Example 16

[0477] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 90 was used instead of Compound 3.

Example 17

[0478] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 98 was used instead of Compound 3.

Example 18

[0479] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 102 was used instead of Compound 3.

Example 19

[0480] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 230 was used instead of Compound 3.

Example 20

[0481] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 244 was used instead of Compound 3.

Example 21

[0482] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 271 was used instead of Compound 3.

Example 22


[0483] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 289 was used instead of Compound 3.

Example 23

[0484] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, Compound 299 was used instead of Compound 3.

Comparative Example 1

[0485] An organic light-emitting device was manufactured in the same manner as in Example 1, except that in forming the hole transport layer, NPB was used instead of Compound 3.



NPB

Evaluation Example 1

[0486] The driving voltage, current density, brightness, efficiency, and half-lifespan of the organic light-emitting devices manufactured according to Examples 1 to 23 and Comparative Example 1 were measured by using Kethley SMU 236 and a brightness photometer PR650, and results thereof are shown in Table 2. The half-lifespan is a period of time that lapses until the brightness of the organic light-emitting device was 50% of initial brightness.

TABLE 2

	Hole transport layer Material	Driving voltage (V)	Current density (mA/cm ²)	Brightness (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @100 mA/cm ²)
Example 1	Compound 3	5.38	50	3580	6.16	Blue	345
Example 2	Compound 21	5.55	50	3895	6.17	Blue	328
Example 3	Compound 29	5.80	50	3342	6.26	Blue	312
Example 4	Compound 40	5.45	50	3568	6.19	Blue	320
Example 5	Compound 49	5.74	50	3680	6.42	Blue	345
Example 6	Compound 56	5.32	50	3670	6.22	Blue	325
Example 7	Compound 57	5.23	50	3220	6.44	Blue	335
Example 8	Compound 59	5.40	50	3450	6.50	Blue	340
Example 9	Compound 62	5.12	50	3330	6.56	Blue	355

TABLE 2-continued

	Hole transport layer Material	Driving voltage (V)	Current density (mA/cm ²)	Brightness (cd/m ²)	Efficiency (cd/A)	Emission color	Half lifespan (hr @100 mA/cm ²)
Example 10	Compound 63	5.20	50	3230	6.66	Blue	330
Example 11	Compound 70	5.21	50	3320	6.44	Blue	350
Example 12	Compound 74	5.15	50	3575	6.43	Blue	340
Example 13	Compound 78	5.51	50	3470	6.44	Blue	355
Example 14	Compound 85	5.23	50	3348	6.50	Blue	320
Example 15	Compound 89	5.43	50	3670	6.44	Blue	335
Example 16	Compound 90	5.51	50	3215	6.43	Blue	354
Example 17	Compound 98	5.60	50	3200	6.40	Blue	338
Example 18	Compound 102	5.15	50	3290	6.58	Blue	350
Example 19	Compound 230	5.80	50	3790	6.42	Blue	345
Example 20	Compound 244	5.57	50	3200	6.40	Blue	340
Example 21	Compound 271	5.61	50	3220	6.44	Blue	370
Example 22	Compound 289	5.70	50	3215	6.50	Blue	340
Example 23	Compound 299	5.55	50	3200	6.50	Blue	350
Comparative Example 1	NPB	7.01	50	2645	5.29	Blue	358


[0487] From Table 2, it may be that the organic light-emitting devices manufactured according to Examples 1 to 23 have higher driving voltage, higher brightness, higher efficiency, and longer half-lifespan than the organic light-emitting device manufactured according to Comparative Example 1.

[0488] An organic light-emitting device including the amine-based compound according to an embodiment may have a low driving voltage, high efficiency, high brightness, and long lifespan.

[0489] Example embodiments have been disclosed herein, and although specific terms are employed, they are used and are to be interpreted in a generic and descriptive sense only and not for purpose of limitation. In some instances, as would be apparent to one of ordinary skill in the art as of the filing of the present application, features, characteristics, and/or elements described in connection with a particular embodiment may be used singly or in combination with features, characteristics, and/or elements described in connection with other embodiments unless otherwise specifically indicated. Accordingly, it will be understood by those of skill in the art that various changes in form and details may be made without departing from the spirit and scope of the present invention as set forth in the following claims.

What is claimed is:

1. An amine-based compound represented by Formula 1 below:



wherein in Formula 1,

A is a substituted or unsubstituted C₆-C₂₀ aromatic ring;

X₁ is selected from N-(L₂)_{a2}-(Ar₂), an oxygen atom (O), and a sulfur atom (S);

L₁ to L₇ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group;

a1 to a7 are each independently an integer selected from 0 to 3;

Ar₁ to Ar₄ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group;

R₁ to R₄ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubsti-


- tuted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, and $-\text{B}(\text{Q}_4)(\text{Q}_5)$;
- b1 and b3 are each independently an integer selected from 0 to 4, b2 and b4 are each independently an integer selected from 0 to 3; and
- at least one substituent of the substituted $\text{C}_6\text{-C}_{20}$ aromatic ring, substituted $\text{C}_3\text{-C}_{10}$ cycloalkylene group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkylene group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkenylene group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenylene group, substituted $\text{C}_6\text{-C}_{60}$ arylene group, substituted $\text{C}_1\text{-C}_{60}$ heteroarylene group, substituted a divalent non-aromatic condensed polycyclic group, substituted a divalent non-aromatic condensed heteropolycyclic group, substituted $\text{C}_1\text{-C}_{60}$ alkyl group, substituted $\text{C}_2\text{-C}_{60}$ alkenyl group, substituted $\text{C}_2\text{-C}_{60}$ alkynyl group, substituted $\text{C}_1\text{-C}_{60}$ alkoxy group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, substituted $\text{C}_6\text{-C}_{60}$ aryl group, substituted $\text{C}_6\text{-C}_{60}$ aryloxy group, substituted $\text{C}_6\text{-C}_{60}$ arylthio group, substituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:
- a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, and a $\text{C}_1\text{-C}_{60}$ alkoxy group;
- a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, and a $\text{C}_1\text{-C}_{60}$ alkoxy group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{11})(\text{Q}_{12})(\text{Q}_{13})$, and $-\text{B}(\text{Q}_{14})(\text{Q}_{15})$;
- a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group; and
- a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and $-\text{B}(\text{Q}_{34})(\text{Q}_{35})$, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$

cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_{21})(\text{Q}_{22})(\text{Q}_{23})$, and $-\text{B}(\text{Q}_{24})(\text{Q}_{25})$;


wherein Q_1 to Q_5 , Q_{11} to Q_{15} , Q_{21} to Q_{25} and Q_{31} to Q_{35} are each independently a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, or a monovalent non-aromatic condensed heteropolycyclic group.

2. The amine-based compound as claimed in claim 1, wherein A is selected from a substituted or unsubstituted a benzene group, a substituted or unsubstituted a naphthalene group, a substituted or unsubstituted an anthracene group, a substituted or unsubstituted a pyrene group, a substituted or unsubstituted a phenanthrene group, a substituted or unsubstituted a chrysene group, and a substituted or unsubstituted triphenylene group.


3. The amine-based compound as claimed in claim 1, wherein A is a group represented by one of the following Formulae 2-1 to 2-19:




Formula 2-1



Formula 2-2








Formula 2-3




Formula 2-4


-continued




Formula 2-5




Formula 2-6




Formula 2-7



Formula 2-8



Formula 2-9



Formula 2-10


Formula 2-11

Formula 2-12


Formula 2-13

Formula 2-14


-continued




Formula 2-15



Formula 2-16




Formula 2-17



Formula 2-18

-continued

Formula 2-19



wherein, in Formulae 2-1 to 2-19,

Z_{21} and Z_{22} are each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

f_1 is 1 or 2, f_2 is an integer selected from 1 to 3, f_3 is an integer selected from 1 to 4, f_4 is an integer selected from 1 to 5, and f_5 is an integer selected from 1 to 7;

* and *' indicate binding sites to neighboring atoms, and *'' indicates a binding site to L_5 in $-(L_5)_{a5}$ or to N.

4. The amine-based compound as claimed in claim 1, wherein X_1 is O or S.

5. The amine-based compound as claimed in claim 1, wherein L_1 to L_7 are each independently selected from:


a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an indacenylene group, an acenaphthylene group, a fluorenylene group, a spiro-fluorenylene group, a benzofluorenylene group, a dibenzofluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, a pentaphenylene group, a hexacenylene group, a pentacenylene group, a rubicenylene group, a coronenylene group, an ovalenylene group, a pyrrolylene group, a thiophenylene group, a furanylene group, an imidazolylene group, a pyrazolylene group, a thiazolylene group, an isothiazolylene group, an oxazolylene group, an isoxazolylene group, a pyridinylene group, a pyrazinylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylene group, an indolylene group, an indazolylene group, a furinylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylene

group, a quinoxalinylene group, a quinazolinylene group, a cinnolinylene group, a carbazolylene group, a phenanthridinylene group, an acridinylene group, a phenanthrolinylene group, a phenazinylene group, a benzoimidazolylene group, a benzofuranylene group, a benzothiophenylylene group, an isobenzothiazolylylene group, a benzoxazolylylene group, an isobenzoxazolylylene group, a triazolylylene group, a tetrazolylylene group, an oxadiazolylylene group, a triazinylene group, a dibenzofuranylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a thiadiazolylylene group, an imidazopyridinylylene group, and an imidazopyrimidinylene group; and


a phenylene group, a pentalenylylene group, an indenylene group, a naphthylene group, an azulenylylene group, a heptalenylylene group, an indacenylene group, an acenaphthylene group, a fluorenylylene group, a spiro-fluorenylylene group, a benzofluorenylylene group, a dibenzofluorenylylene group, a phenalenylylene group, a phenanthrenylene group, an anthracenylylene group, a fluoranthenylylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylylene group, a picenylene group, a perylenylene group, a pentaphenylylene group, a hexacenylylene group, a pentacenylylene group, a rubicenylylene group, a coronenylylene group, an ovalenylylene group, a pyrrolylylene group, a thiophenylylene group, a furanylylene group, an imidazolylylene group, a pyrazolylylene group, a thiazolylylene group, an isothiazolylylene group, an oxazolylylene group, an isoxazolylylene group, a pyridinylylene group, a pyrazinylylene group, a pyrimidinylene group, a pyridazinylene group, an isoindolylylene group, an indolylylene group, an indazolylylene group, a furinylylene group, a quinolinylene group, an isoquinolinylene group, a benzoquinolinylene group, a phthalazinylene group, a naphthyridinylylene group, a quinoxalinylylene group, a quinazolinylene group, a cinnolinylylene group, a carbazolylylene group, a phenanthridinylylene group, an acridinylylene group, a phenanthrolinylylene group, a phenazinylylene group, a benzoimidazolylylene group, a benzofuranylylene group, a benzothiophenylylene group, an isobenzothiazolylylene group, a benzoxazolylylene group, an isobenzoxazolylylene group, a triazolylylene group, a tetrazolylylene group, an oxadiazolylylene group, a triazinylene group, a dibenzofuranylylene group, a dibenzothiophenylylene group, a benzocarbazolylylene group, a dibenzocarbazolylylene group, a thiadiazolylylene group, an imidazopyridinylylene group, and an imidazopyrimidinylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a pice-

nyl group, a pherylenyl group, a pentaphenyl group, a hexacenylylene group, a pentacenylylene group, a rubicenylylene group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinylylene group, a quinazolinyl group, a cinnolinylylene group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group.


6. The amine-based compound as claimed in claim 1, wherein L₁ to L₇ are each independently a group represented by one of the following Formulae 3-1 to 3-33 below:




Formula 3-1




Formula 3-2




Formula 3-3



Formula 3-4














Formula 3-5




Formula 3-6


-continued




-continued




Formula 3-28




Formula 3-29




Formula 3-30



Formula 3-31



Formula 3-32



Formula 3-33

wherein, in Formulae 3-1 to 3-33,

Y_1 is O, S, $C(Z_3)(Z_4)$, $N(Z_5)$, or $Si(Z_6)(Z_7)$;

Z_1 to Z_7 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzo-fluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

d_1 is an integer selected from 1, 2, 3, and 4, d_2 is an integer selected from 1, 2, and 3, d_3 is an integer selected from


1, 2, 3, 4, 5, and 6, d_4 is an integer selected from 1, 2, 3, 4, 5, 6, 7, and 8, d_5 is 1 or 2, and d_6 is an integer selected from 1, 2, 3, 4, and 5, and * and *' indicate binding sites to neighboring atoms.

7. The amine-based compound as claimed in claim 1, wherein:


a_1 , a_2 , a_5 , a_6 , and a_7 are each independently 0, 1, 2, or 3, and

a_3 and a_4 are each independently 0 or 1.


8. The amine-based compound as claimed in claim 1, wherein $*(L_1)_{a1}$ -, $*(L_2)_{a2}$ -, $*(L_3)_{a3}$ -, $*(L_4)_{a4}$ -, $*(L_5)_{a5}$ -, $*(L_6)_{a6}$ -, and $*(L_7)_{a7}$ - are each independently a single bond or a group represented by one of the following Formulae 4-1 to 4-27:




Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4




Formula 4-5




Formula 4-6



Formula 4-7




Formula 4-8




Formula 4-9


-continued




Formula 4-10




Formula 4-11




Formula 4-12




Formula 4-13




Formula 4-14




Formula 4-15



Formula 4-16




Formula 4-17




Formula 4-18


-continued




Formula 4-19




Formula 4-20




Formula 4-21




Formula 4-22




Formula 4-23




Formula 4-24



Formula 4-25



Formula 4-26



Formula 4-27

wherein * and *' indicate binding sites to neighboring atoms.

9. The amine-based compound as claimed in claim 1, wherein Ar₁ to Ar₄ are each independently selected from:

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chryse-


nyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a furinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzofuranyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenale-


nyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, —Si(Q₃₁)(Q₃₂)(Q₃₃), and —B(Q₃₄)(Q₃₅),

wherein Q₃₁ to Q₃₅ are each independently selected from a hydrogen, a deuterium, —F, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group.


10. The amine-based compound as claimed in claim 1, wherein Ar₁ to Ar₄ are each independently a group represented by one of the following Formulae 5-1 to 5-16:



Formula 5-1














Formula 5-2




Formula 5-3

-continued




-continued

Formula 5-4



Formula 5-5



Formula 5-6

wherein, in Formulae 5-1 to 5-16,

 Y_{31} is $C(Z_{33})(Z_{34})$ or $N(Z_{35})$; Z_{31} to Z_{35} are each independently selected from:

a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

Formula 5-7

Formula 5-8

Formula 5-9

Formula 5-10

Formula 5-11

Formula 5-12

Formula 5-13

Formula 5-14

Formula 5-15

Formula 5-16

a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, and a phosphoric acid or a salt thereof;

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and


a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, —Si(Q_{31})(Q_{32})(Q_{33}), and —B(Q_{34})(Q_{35}), each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, and a naphthyl group;

Q_{31} to Q_{35} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a


pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group; and

e1 is an integer of 1 to 5; e2 is an integer of 1 to 7; e3 is an integer of 1 to 3; e4 is an integer of 1 to 4; e5 is 1 or 2; and * indicates a binding site to a neighboring atom.


11. The amine-based compound as claimed in claim 1, wherein Ar₁ to Ar₄ are each independently a group represented by one of the following Formulae 6-1 to 6-24:




Formula 6-1




Formula 6-2




Formula 6-3




Formula 6-4




Formula 6-5




Formula 6-6




Formula 6-7



Formula 6-8




Formula 6-9




Formula 6-10

-continued


Formula 6-11




Formula 6-12




Formula 6-13




Formula 6-14




Formula 6-15




Formula 6-16




Formula 6-17




Formula 6-18




-continued




Formula 6-19




Formula 6-20




Formula 6-21



Formula 6-22



Formula 6-23



Formula 6-24

wherein, in Formulae 6-1 to 6-24, * indicates a binding site to a neighboring atom.

12. The amine-based compound as claimed in claim 1, wherein R_1 to R_4 are each independently selected from:

- a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;
- a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium,

—F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a phenyl group, a naphthyl group, a pyridinyl group, and a pyrimidinyl group;

- a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group;

- a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthrolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl

group, a carbazolyl group, a phenanthrolyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$; and

$-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$;

wherein Q_1 to Q_3 and Q_{31} to Q_{33} are each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

13. The amine-based compound as claimed in claim 1, wherein R_1 to R_4 are each independently selected from:

a hydrogen, $-\text{F}$, a cyano group, a nitro group, a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group;


a methyl group, an ethyl group, a propyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a sec-pentyl group, a tert-pentyl group, an n-hexyl group, an isohexyl group, a sec-hexyl group, a tert-hexyl group, an n-heptyl group, an isoheptyl group, a sec-heptyl group, a tert-heptyl group, an n-octyl group, an isooctyl group, a sec-octyl group, a tert-octyl group, an n-nonyl group, an isononyl group, a sec-nonyl group, a tert-nonyl group, an n-decanyl group, an isodecanyl group, a sec-decanyl group, a tert-decanyl group, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, and a triazinyl group, each substituted with at least one selected from $-\text{F}$, a cyano group, a nitro group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, and $-\text{Si}(\text{Q}_{33})(\text{Q}_{34})(\text{Q}_{35})$; and

$-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$;


wherein Q_1 to Q_3 and Q_{33} to Q_{35} are each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group.

14. The amine-based compound as claimed in claim 1, wherein the amine-based compound represented by Formula 1 is represented by one of the following Formulae 1A to 1F:


<Formula 1A>




<Formula 1B>



<Formula 1C>




<Formula 1D>




-continued

<Formula 1E>



<Formula 1F>




and

wherein, in Formulae 1A to 1f, X_1 , A, L_1 to L_7 , a1 to a7, Ar_1 to Ar_4 , R_1 to R_4 , and b1 to b4 are defined the same as X_1 , A, L_1 to L_7 , a1 to a7, Ar_1 to Ar_4 , R_1 to R_4 , and b1 to b4 of Formula 1.


15. The amine-based compound as claimed in claim 1, wherein the amine-based compound represented by Formula 1 is represented by one of the following Formulae 1A-1, 1A-2, 1B-1, 1B-2, 1C-1, 1C-2, 1D-1, 1D-2, 1E-1, 1E-2, 1F-1, and 1F-2,

<Formula 1A-1>




-continued


<Formula 1A-2>



<Formula 1B-1>




<Formula 1B-2>




-continued


<Formula 1C-1>



<Formula 1C-2>




<Formula 1D-1>




-continued


<Formula 1D-2>




<Formula 1E-1>



<Formula 1E-2>



-continued



wherein in Formulae 1A-1, 1A-2, 1B-1, 1B-2, 1C-1, 1C-2, 1D-1, 1D-2, 1E-1, 1E-2, 1F-1, and 1F-2,

Z_{21} is selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

f_2 is an integer selected from 0 to 3;

X_1 is O or S;

L_1 , L_5 , L_6 , and L_7 are each independently selected from: a phenylene group, a naphthylene group, a pyridinylene group, a pyrimidinylene group, and a triazinylene group; and

a phenylene group, a naphthylene group, a pyridinylene group, a pyrimidinylene group, and a triazinylene group, each substituted with at least one selected from a deute-

rium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, and a triazinyl group;

a_1 is 0 or 1,

a_5 , a_6 , and a_7 are each independently an integer selected from 0 to 3;

Ar_1 to Ar_4 are each independently selected from:

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group; and

a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, —Si(Q_{31})(Q_{32})(Q_{33}), and —B(Q_{34})(Q_{35}),

Q_{31} to Q_{35} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, a fluorenyl group, a spiro-fluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, and a chrysenyl group;

R_1 to R_4 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid or a salt thereof, a sulfonic acid or a salt thereof, a phosphoric acid or a salt thereof, a substituted or unsubstituted C_1 - C_{20} alkyl group, and a substituted or unsubstituted C_1 - C_{20} alkoxy group;

b_1 and b_3 are each independently an integer selected from 0 to 4, and



b_2 and b_4 are each independently an integer selected from 0 to 3.

16. The amine-based compound as claimed in claim 1, wherein the amine-based compound represented by Formula 1 is one of the following Compounds 1 to 300:

-continued



1

3




2

4




-continued

5




-continued


7



6




8




-continued

9




-continued


11



10




12




-continued

13




-continued


15



14




16




-continued

17




-continued


19




20



18




21




-continued


22



23




24




-continued

25




26




-continued

27




-continued


29



28




30




-continued

31




-continued


33




34



32




35




-continued


36



37




38




-continued

39




40




-continued


41



42




43




-continued


44




45




46




47




48




49




50



51




52




-continued

53




-continued


56




54




57



55




58




-continued

59




-continued


62




60




63



61




64




-continued

65




-continued


68




69




70



66




67




-continued


71



72




73




-continued


74



75




76




-continued

77




-continued


79



78




80




-continued

81




-continued


84




85




86



82




83




-continued


87



88




89




-continued


90



91




92




-continued


93



94




95




-continued


96



97




-continued




98

-continued





101

99




100



102


-continued

103




-continued


105



104




106




-continued

107




-continued


109



108




110




-continued

111




-continued

115




-continued


118




116




119



117




120




-continued

121




-continued

124





125


122



123




126




-continued

127




-continued

129





130

128




131




-continued


132



133




134




-continued


135



136




137




-continued

138




-continued


141




139




142



140




143




-continued

144




-continued


146



145




147




-continued

148




-continued

150





151

149




152




-continued

153




-continued


155



154




156




-continued

157




-continued


159



158




160




-continued

161




-continued


163



162




164




-continued

165




-continued


167



166




168




-continued

169




-continued


171



170




172




-continued

173




-continued


175



174




176




-continued

177




-continued


179



178




180




-continued

181




-continued


183



182




184




-continued

185




-continued


187




186



188




-continued




189


-continued




191



190




192




193


-continued




-continued




195



198




196



200


-continued

199




-continued


201



200




202




-continued

203




-continued


205



204



206





-continued

-continued



207

209




208

210




-continued

211




-continued


213



212




214




-continued

215




-continued


217



216




218




-continued


219



220




221




-continued

222




223




-continued

224




-continued

226





227

225




228




-continued

229




-continued


231



230




232




-continued

233




-continued


235



234




236




-continued

237





-continued

239




240

238




241




-continued


242



243




244




-continued

245




246




-continued


247



248




249




-continued


250



251




252




-continued

253




-continued


255



254




256




-continued

257





-continued

260





261

258




262


259




-continued





-continued



266




267




-continued


268



269




270




-continued

271




272




-continued

273




-continued


275



274




276




-continued

277




-continued


279



278




280




-continued

281




-continued


283



282




284




-continued

285




-continued


287




286



288




-continued




289

-continued




292


290



291




293




-continued

294




-continued


296



295




297




-continued

298




-continued

300



299



17. An organic light-emitting device, comprising:

a first electrode;
a second electrode facing the first electrode; and
an organic layer between the first electrode and the second electrode, the organic layer including an emission layer, wherein the organic layer includes at least one amine-based compound as claimed in claim 1.

18. The organic light-emitting device as claimed in claim 17, wherein

the first electrode is an anode,
the second electrode is a cathode, and
the organic layer includes:

a hole transport region between the first electrode and the emission layer, the hole transport region including at least one of a hole injection layer, a hole transport layer, a buffer layer, and an electron blocking layer, and

an electron transport region between the emission layer and the second electrode, the electron transport region including at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer.

19. The organic light-emitting device as claimed in claim 18, wherein the amine-based compound is included in the hole transport region.

20. The organic light-emitting device as claimed in claim 19, wherein the hole transport region further includes a charge-generating material.

* * * * *

专利名称(译)	胺类化合物和包括其的有机发光装置		
公开(公告)号	US20160190467A1	公开(公告)日	2016-06-30
申请号	US14/963281	申请日	2015-12-09
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	JANG HYUNGSEOK KIM YOUNGKOOK KIM JONGWOO LIM JINO HWANG SEOKHWAN		
发明人	JANG, HYUNGSEOK KIM, YOUNGKOOK KIM, JONGWOO LIM, JINO HWANG, SEOKHWAN		
IPC分类号	H01L51/00 C07D405/10		
CPC分类号	H01L51/0061 H01L51/006 C07D405/10 H01L51/0052 H01L51/0072 H01L51/0073 H01L51/506 C09K11/06 C07D261/00 C07D273/01 C07D273/02 C07D309/00 H01L51/0058 H01L51/0059 H01L51/5056		
优先权	1020140194320 2014-12-30 KR		
其他公开文献	US9957441		
外部链接	Espacenet USPTO		

摘要(译)

胺类化合物和有机发光装置，胺类化合物由下式1表示：

